

# AMERLOCK® 2

May 2013  
Revision of April 2013

<b>DESCRIPTION</b>	Fast Dry, Surface Tolerant, High Solids Epoxy Coating
<b>PRINCIPAL CHARACTERISTICS</b>	<ul style="list-style-type: none"> <li>– Fast dry</li> <li>– Low VOC</li> <li>– High performance general maintenance coating for new or old steel</li> <li>– Self priming over most existing coatings</li> <li>– Compatible with prepared damp surfaces</li> <li>– Compatible with adherent rust remaining on prepared surfaces</li> <li>– Dry temperature resistance up to 450°F on insulated or uninsulated surfaces when mixed with <i>Amercoat</i> 880 glass flake additive</li> <li>– Suitable for use in many industries including off-shore, water/wastewater, power, steel fabrication and public use facilities.</li> </ul>
<b>COLOR AND GLOSS*</b>	<p>Semi-gloss Standard primer colors, custom colors, and aluminum</p> <p><small>* Epoxy coatings will chalk and fade with exposure to sunlight. Light colors are prone to ambering to some extent. Note that product tinted to custom colors are not recommended for immersion service. Only use factory grind batches for immersion.</small></p>
<b>BASIC DATA</b>	
Volume solids	85% ± 3%
VOC	1.5 lbs/gal (180 g/L) EPA Method 24 (Use <i>Amerlock</i> 2 VOC when <100 g/L formulation is required) 1.4 lbs/gal (163 g/L) Directive 1999/13/EC, SED
Recommended Dry film thickness (per coat)	4 – 8 mils (100 – 200 microns)
Theoretical Spread Rate	@ 1 mils dft 1331 ft <sup>2</sup> /gal @ 5 mils dft 266 ft <sup>2</sup> /gal
Components	2
Dry Temperature Resistance*	Continuous — 250°F Intermittent — 350°F (<5% of the time, max 24 hours) <small>* Color will drift at elevated temperatures.</small>
Shelf Life	3 years from date of manufacture <small>* when stored in original sealed containers in dry conditions between 40-100°F</small>
<b>SURFACE PREPARATION</b>	<p>Coating performance is, in general, proportional to the degree of surface preparation. Abrasive blasting is usually the most effective and economical method. When this is impossible or impractical, <i>Amerlock</i> 2 can be applied over mechanically cleaned surfaces. All surfaces must be clean, dry and free of all contaminants, including salt deposits. Contact PPG for maximum allowable salt containment levels.</p>
Mild Steel	<ul style="list-style-type: none"> <li>– Remove all loose rust, dirt, grease or other contaminants by one of the following depending on the degree of cleanliness required: SSPC-SP2, 3, 6, 7 or 10 (ISO 8501-1 St-2, St-3, Sa 1, Sa 2.5). These minimum surface preparation standards apply to steel that has been previously abrasive blasted. The choice of surface preparation will depend on the system selected and end-use service conditions. For more severe service and immersion, clean to SSPC-SP10 (ISO8501-1 Sa 2.5). Blast to achieve an anchor profile of 1.0-5.0 mils (25-125 microns) as indicted by a Keane-Tator Surface profile Comparator or Testex Tape. Previously blasted steel may be ultra-high pressure water jetted to SSPC SP WJ-2(L) / NACE WJ-2(L). The wet surface can be dried by blowing with dry compressed air giving special attention to horizontal surfaces and recesses.</li> </ul>
Concrete	<ul style="list-style-type: none"> <li>– Prepare / clean surface in accordance with SSPC SP-13 guidelines. Abrade surface per ASTM D-4259 to remove all efflorescence and laitance, to expose sub-surface voids, and to provide a surface roughness equivalent of 60 grit sandpaper or coarser. Test for moisture by conducting a plastic sheet test in accordance with ASTM D4263. Fill voids as necessary with <i>Amercoat</i> 114A epoxy filler. For slabs on grade, test for moisture in accordance with ASTM F1869 (calcium chloride test). The maximum allowable moisture transmission is 3 lbs / 1,000 ft<sup>2</sup>/24 hours. Refer to Information Sheet 1496ACUS for further details regarding moisture measurements.</li> </ul>

## AMERLOCK 2

- Galvanized Steel
  - Remove oil or soap film with detergent or emulsion cleaner. Lightly abrasive blast with a fine abrasive in accordance with SSPC SP-16 guidelines to achieve a profile of 1.5-3.0 mils. When light abrasive blasting is not possible, galvanizing can be treated with a suitable zinc phosphate conversion coating. Galvanizing that has at least 12 months of exterior weathering and has a rough surface with white rust present may be over-coated after power washing and cleaning to remove white rust and other contaminants. The surface must have a measurable profile. A test patch is recommended to confirm adhesion. Not recommended over chromate sealed galvanizing without blasting to thoroughly remove chromates. Adhesion problems may occur.
- Non-Ferrous Metals and Stainless Steel
  - Abrasive blast in accordance with SSPC SP-16 guidelines to achieve a uniform and dense 1.5-4.0 mil anchor profile. Size and hardness of abrasive should be adjusted as necessary based on the hardness of the substrate. Aluminum may be treated with a surface treatment compliant with Mil-DTL-5541 or equivalent (non-immersion applications only).
- Aged coatings
  - All surfaces must be clean, dry, tightly bonded and free of all loose paint, corrosion products or chalky residue. Abrade surface, or clean with Prep 88. *Amerlock 2* is compatible over most types of properly applied and tightly adhering coatings, however, a test patch is recommended to confirm compatibility.
- Repair
  - Prepare damaged areas to original surface preparation specifications, feathering edges of intact coating. Thoroughly remove dust or abrasive residue before touch-up.

### ENVIRONMENTAL CONDITIONS

- Ambient temperatures\*
  - 20°F to 122°F (-6°C to 50°C)
  - \* *Amerlock 400 hardener can be used with the Amerlock 2/400 base component for applications that require a long pot life. The A component is the same for Amerlock 400 and Amerlock 2. The B components are interchangeable.*
- Material temperatures
  - 40°F to 90°F (5°C to 32°C)
- Relative humidity
  - 0 to 100%, surface must be free of visible moisture. For immersion service and for optimum performance, surface temperature must be at least 5°F above the dew point temperature.
- Surface temperature
  - 20°F to 122 °F (-6°C to 50°C)
  - \* *Amerlock 2 may be applied to surfaces as hot as 250°F (121°C) for non-immersion service. When applying Amerlock 2 to surfaces between 122°F and 250°F, Amerlock 2 must be thinned at 1/2 pint per gallon with only Amercoat 101 thinner. Multiple thin passes may be required to achieve film build and to avoid solvent blistering.*
- General air quality
  - Area should be sheltered from airborne particulates and pollutants. Avoid combustion gases or other sources of carbon dioxide that may promote amine blush. Ensure good ventilation during application and curing. Provide shelter to prevent wind from affecting spray patterns. Refer to Information Bulletin #1489 for further information on prevention, detection, and mitigation of amine blush.

### INSTRUCTIONS FOR USE

- Mixing ratio by volume
  - 1 part base to 1 part hardener
  - Pre-mix pigmented components with a pneumatic air mixer at moderate speeds to homogenize the container. Add hardener to base and agitate with a power mixer for 1-2 minutes until completely dispersed.

Pot life

	32°F	50°F	70°F	90°F
2	4 hours	2 hours	1 hour	0.5 hour
2AL	3 hours	1.5 hours	0.75 hour	0.5 hour

- Induction time
  - None required
- Airless spray
  - 45:1 pump or larger, 0.017-0.019 fluid tip
  - Can be sprayed with plural component application equipment.
- Air spray
  - Thin up to 20%, standard conventional equipment, 0.070" fluid orifice
- Brush & roll
  - Use a high quality natural bristle brush and / or solvent resistant, 3/8" nap roller. Ensure brush / roller is well loaded to avoid air entrainment. Multiple coats may be necessary to achieve adequate film build.
- Thinner
  - Amercoat 65 (xylene), Amercoat 101 (recommended for > 90°F), Amercoat T10, Amercoat 8 (to extend pot life 10-20%)*

# AMERLOCK 2

Cleaning solvent *Amercoat 12 Cleaner or Amercoat 65 thinner (xylene)*  
 Primers *Direct to substrate; Dimetcote series primers, Amercoat 68HS, Amercoat 68MCZ*  
 Topcoats *Amercoat 450 Series Polyurethanes, Amershield, PSX 700, PSX One, Amercoat 220 Series Acrylics, Pitthane Polyurethanes*  
 Safety precautions *For paint and recommended thinners see safety sheet 1430, 1431 and relevant material safety data sheets*  
*This is a solvent borne paint and care should be taken to avoid inhalation of spray mist or vapor as well as contact between the wet paint and exposed skin or eyes.*

## DRY/CURE TIMES

*Amerlock 2 @ 5 mils dft*

	32°F	50°F	70°F	90°F
Dry to touch	24 hours	8 hours	2 hours	1 hour
Dry through	38 hours	14 hours	5 hours	3 hours
Dry to recoat/topcoat	24 hours	12 hours	6 hours	3 hours
Max recoat, self	90 days	60 days	30 days	14 days
Max topcoat, urethanes, PSX	30 days	21 days	7 days	4 days
Cure to immersion <i>factory colors only</i>	21 days	7 days	4 days	3 days
Cure to immersion - potable water	Refer to: <a href="http://www.ppgamercoatus.ppgpmc.com/NSF/">www.ppgamercoatus.ppgpmc.com/NSF/</a> for specific application and curing requirements			

*Amerlock 2 Aluminum @ 5 mils dft*

	32°F	50°F	70°F	90°F
Dry to touch	30 hours	11 hours	3.5 hours	2 hours
Dry through	48 hours	17 hours	7 hours	3.5 hours
Dry to recoat	30 hours	12 hours	6 hours	3 hours
Max recoat, self	90 days	60 days	30 days	14 days
Max topcoat, urethanes, PSX	30 days	21 days	7 days	4 days
Cure to immersion	21 days	7 days	4 days	3 days

*\* Dry times are dependent on air and surface temperatures as well as film thickness, ventilation, and relative humidity. Maximum recoating time is highly dependent upon actual surface temperatures – not simply air temperatures. Surface temperatures should be monitored, especially with sun-exposed or otherwise heated surfaces. Higher surface temperatures shorten the maximum recoat window. An extended recoatable window may be allowable in some circumstances. Please contact your PPG PMC representative for more details.*

*Surface must be clean and dry. Any contamination must be identified and removed. A detergent wash with Prep 88 or equivalent is required prior to application of topcoats after 30 days of exposure. However, particular attention must be paid to surfaces exposed to sunlight where chalking may be present. In those situations, a further degree of cleaning may be required. PPG Technical Service can advise on suitable cleaning methods. If maximum recoat/topcoat time is exceeded, then roughen surface.*

## PRODUCT QUALIFICATIONS

- Compliant with USDA Incidental Food Contact Requirements
- NFPA Class A for Flame Spread and Smoke Development
- Qualified for ANSI/NSF Standard 61 (potable water) for tanks, pipes, valves, and fittings. For NSF application instructions, please visit our website at: [www.ppgamercoatus.ppgpmc.com/NSF/](http://www.ppgamercoatus.ppgpmc.com/NSF/)
- AWWA C210-98
- AWWA C550-98
- AWWA D102-06 ICS #1, #2, #3, #5
- LEED's compliant for Anti-corrosive Paint category
- Nuclear Service Level 2 (ANSI N 5.12, ANSI N 101.2)
- NORSOK M501 Rev. 5, System 7 Subsea surfaces

## AMERLOCK 2

### AVAILABILITY

Packaging	Available in 2-gallon and 5-gallon kits 2-gallon kits have 1 full gallon of base and 1 full gallon of hardener 5 gallon kits have 2.5 gallons of base and 2.5 gallons of hardener	
Inventory (made to order, etc..)	Global availability	
Product codes	AK2-1	Buff
	AK2-3	White
	AK2-9	Black
	AK2-23	Pearl Gray
	AK2-72	Oxide Red
	AK2-81	Safety Yellow
	AK2-T1	Deep Tint base*
	AK2-T2	Light Tint base*
	AK2-T3	Neutral Tint base*
	AK2-T4	Red Tint base*
	AK2-T5	High Hiding Yellow Tint base*
	AK2-B	Hardener component
	AK2-01A	Amerlock 2AL Aluminum Base
	AK2-01B	Amerlock 2AL Aluminum Hardener

\* Tintable using UCD V-Line colorants only.

Worldwide statement	While it is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.
---------------------	--

### WARRANTY STATEMENT

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product.

THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG.

Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

### LIMITATION OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT.

The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk.

PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product.

Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.