



CUTTING TOOLS





DRILLING

	PRODUCTS	DESCRIPTION	PAGE
	i-DREAM DRILLS CARBIDE INSERTS	- For Steels and Stainless Steel Alloys	41
	SOLID CARBIDE DREAM DRILLS - GENERAL (with/without Coolant Holes)	- With/without Coolant Holes - General Purpose HRc30 to HRc50	55
	SOLID CARBIDE DREAM DRILLS - HIGH FEED (with Coolant Holes)	- With Coolant Holes - 1.5 to 2 times faster feeding speed than 2 Flute drills	91
	SOLID CARBIDE DREAM DRILLS - FLAT BOTTOM (without Coolant Holes)	- Without Coolant Holes - In 180° Point Angle for Variety Drilling	103
	SOLID CARBIDE DREAM DRILLS - INOX (with Coolant Holes)	- With Coolant Holes - For Stainless Steels, Nickel Alloys and Titanium up to HRc35	111
	SOLID CARBIDE DREAM DRILLS - ALU (with Coolant Holes)	- With Coolant Holes - For Aluminum & Aluminum Alloys	133
	SOLID CARBIDE DREAM DRILLS - MQL TYPE (with Coolant Holes)	- With Coolant Holes - Minimum Quantity Lubrication - For Drilling Deep Holes 10D, 15D, 20D, 25D & 30D	143
	SOLID CARBIDE DREAM DRILLS - For HIGH HARDENED STEELS	- For High Hardened Steels, HRc50~HRc70	161
	STANDARD CARBIDE DRILLS	- General Purpose - 118° Point	169

DRILLING

	PRODUCTS	DESCRIPTION	PAGE
	HSS-PM MULTI-1 DRILLS	- Multi Purpose Drilling. Particularly for Stainless Steels, Titanium	177
	HPD DRILLS	- For Stainless Steels	185
	HSS GOLD-P DRILLS	- Gold-P Coating	195
	HSS STRAIGHT SHANK DRILLS	- General Purpose	215
	AIRCRAFT DRILLS	- 6 and 12 inch Length Drills	237
	SILVER & DEMING DRILLS	- 118° Split Point - 3 Flats Black and Gold	247
	HSS MORSE TAPER SHANK DRILLS	- General Purpose - Standard Length	253
	HSS (8% Cobalt) NC-SPOTTING DRILLS	- HSS(8% Cobalt) - Centering and Chamfering of Holes	259
	HSS COMBINATION DRILL & COUNTER SINK / CENTER DRILL	- Regular and Long Length	265

DRILLING

	PRODUCTS	DESCRIPTION	PAGE
	CARBIDE & HSS-PM SPADE DRILLS	- Carbide for Long Tool Life, and HSS-PM for General Machines and Large Diameters Higher Productivity than Other Drilling Tools	269
	TECHNICAL DATA		313

THREADING

	PRODUCTS	DESCRIPTION	PAGE
	SOLID CARBIDE THREAD MILLS	- For blind holes and through holes with one single tool - Higher cutting speed and feed than taps	355
	COMBO TAPS	- Multi Purpose tapping - YG-1's Patent - Super HSS & HSS-E for Prevention of Oversized Threads	363
	SPIRAL FLUTE TAPS	- Tapping Blind Holes - Super HSS, HSS-E, HSS-PM, HSS-V & HSS	389
	SPIRAL POINT TAPS	- Tapping Through Holes - Super HSS, HSS-E, HSS-PM, HSS-V & HSS	427
	STRAIGHT FLUTE TAPS	- Tapping Through & Blind Holes - Carbide, Super HSS & HSS	469
	FORMING TAPS	- Tapping by Forming Soft Materials (No Chips)	489
	SCREW THREAD INSERT TAPS	- Tapping STI Threads of Soft Materials (HSS-E)	499
	PIPE TAPS	- Tapping NPT, NPTF, NPS & NPSF threads	509
	TECHNICAL DATA		519




MILLING

	PRODUCTS	DESCRIPTION	
	CBN END MILLS	- Cubic Boron Nitride - For High Hardened Steels up to HRc70 - Mirror Finish	589
	i-Xmill, CARBIDE INSERT END MILLS	- For General Steels(~HRc50), Hardened Steels(up to HRc65) and Graphite	595
	i-Smart MODULAR TYPE END MILLS	- Exchangeable Modular Head for Semi-finishing and finishing - Pre-Hardened Steels up to HRc55	613
	X5070 NANO SOLID CARBIDE END MILLS	- For High Hardened Steels HRc45 to HRc70 - High Speed Machining - Dry Cutting	627
	4G MILLS SOLID CARBIDE END MILLS	- High Speed Cutting for Pre-Hardened Steels up to HRc55	661
	X-POWER SOLID CARBIDE END MILLS	- For Medium Steels and High Hardened Steels up to HRc70	847
	JET-POWER SOLID CARBIDE & HSS-PM END MILLS	- For Exotic Materials such as Stainless Steels, Nickel alloys and Titanium	935
	TitaNox-POWER SOLID CARBIDE END MILLS	- Silent Cutting for Stainless Steels up to HRc40 - Designed with Variable Leads - YG-1's Patent	957
	V7 PLUS A SOLID CARBIDE END MILLS	- Silent Cutting of Steels up to HRc40 Designed as Unequal Leads	977


MILLING

	PRODUCTS	DESCRIPTION	PAGE
	V7 MILL INOX SOLID CARBIDE END MILLS	- Silent Cutting for Stainless Steels up to HRc40 - Designed with Variable Leads - YG-1's Patent	1017
	ALU-POWER HPC SOLID CARBIDE END MILLS	- High Performance with High Feed, RPM and Chip Removal (Heavy Cutting) - For Aluminum, Non-Ferrous and Non-Metallic Materials	1035
	ALU-POWER SOLID CARBIDE & HSS-PM END MILLS	- For Aluminium Alloys with Silent Cutting - Mirror Surface	1047
	D-POWER GRAPHITE SOLID CARBIDE END MILLS	- Diamond Coated Carbide End Mills for Graphite	1091
	D-POWER CFRP SOLID CARBIDE END MILLS	- For Composite Materials including CFRP, GFRP	1107
	CARBIDE ROUTERS CFRP	- For Composite Materials including CFRP, GFRP	1113
	STANDARD SOLID CARBIDE END MILLS	- General Purpose	1119
	ONLY ONE COATED PM60 END MILLS	- Perfect solution to protect carbide chipping problems under vibrations	1171
	SINE-POWER HSS END MILLS	- High performance HSS Rougher for Titanium and Titanium Alloys	1187

MILLING

	PRODUCTS	DESCRIPTION	PAGE
	TANK-POWER HSS-PM END MILLS	- Next Generation of Powdered Metal End Mills - Higher Edge Strength & Feed Rates	1193
	COBALT & HSS END MILLS	- General Purpose, Non-coated, Any Coating Available	1211
	TECHNICAL DATA		1295

OTHER TOOLS

	PRODUCTS	DESCRIPTION	PAGE
	TOOL HOLDERS	- According to CAT + BT Standards	1305

CASE STUDY ♦ i-DREAM DRILL (Reference page : p.41 ~ p.54)

● i-DREAM DRILL - GENERAL

TOOL

HOLDER	ZB0302
INSERT	Y03B07


WORKPIECE - Structural Steels

ASTM	A36
DIN	St37-2
JIS	SS400

CONDITIONS

Cutting Speed	262 ft/min.
Feed	.0094 inch/rev.
Feedrate	16.59 inch/min.
RPM	1756 rev./min.
Drilling	1.89"
Coolant	Internal
Machine type	Vertical Machining Center

RESULT



YG-1 (Total Drilling 600 Holes)



Competitor A (Total Drilling 470 Holes)



● i-DREAM DRILL - INOX

TOOL

HOLDER	ZB0301
INSERT	YI3B01


WORKPIECE - Stainless Steels

AISI	304
DIN	X5CrNi189
JIS	SUS304


CONDITIONS

Cutting Speed	180 ft/min.
Feed	.0059 inch/rev.
Feedrate	7.402 inch/min.
RPM	1250 rev./min.
Drilling	1.97"
Coolant	Internal
Machine type	Vertical Machining Center


RESULT



YG-1 (Total Drilling 100 Holes)



Competitor A (Total Drilling 80 Holes)



● **FEATURES OF DREAM DRILLS-HIGH FEED**

Dream Drills-High Feed offers 1.5 to 2 times higher feeding speed compared to conventional 2-flute drills. The unique flute design and exceptional surface finish promises extraordinary chip evacuation.

YG-1 (Total Drilling 330 Holes)




Cutting Condition

Tools : DGR495100
 (Dream Drills High Feed)
Size : Ø10 x 10 x 61 x 103
Work Material : • AISI : 1045
 • JIS : S45C (HRc20)
 • DIN : C45
R.P.M : 3,200 rev./min.
Feed : .0197 inch/rev.
Drilling Depth : 1.97" (5xD)
Drilling Method : Blind Hole
Coolant : Wet Cut
Machine : Machining Center

COMPETITOR A (Total Drilling 330 Holes)





COMPETITOR B (Total Drilling 330 Holes)



● **SOLID CARBIDE DREAM DRILLS - Flat Bottom without Coolant Holes**

CUTTING CONDITION


- **Tool** : Dream Drills Flat Bottom
 - **Size** : Ø6.0 (.2362 inch)
 - **Work Material** : • AISI : 1045
 • JIS : S45C
 • DIN : C45
 • **Hardness** : HRc 20 (HB 228)
 - **Cutting Speed** : 75.4 m/min (244.4 ft/min.)
 - **RPM** : 4,000 rev/min
 - **Feed** : 0.1 mm/rev (.0039 in/rev.)
 - **Drilling Depth** : 12.0 mm (2XD)
 - **Coolant** : External Cooling Water Soluble (9% Emulsion)
Machine : Vertical Machining Center



▶ **YG-1**



▶ **COMPETITOR A**




Productivity (Carbon Steel)

Ø 10 5xD

1.6 times UP



CASE STUDY **DREAM DRILLS-INOX** (Reference page : p.111 ~ p.131)




— YG-1
— A Competitor A
— B Competitor B


CUTTING CONDITION

Tools : DREAM DRILLS-INOX
Size : Ø6 x Ø6 x 44 x 82
Work Material : • AISI : 304
 • JIS : SUS304
 • DIN : X5CrNi1810 (X4CrNi18-10)
R.P.M : 3,700 rev./min.
SFM : 229 ft/min.
Feed : .0028 inch/rev.
Drilling Depth : .94"
Coolant : Wet Cut

YG-1 (Total Drilling 400 Holes)



COMPETITOR A (Total Drilling 400 Holes)




COMPETITOR B (Total Drilling 400 Holes)



CASE STUDY **DREAM DRILLS-ALU** (Reference page : p.133 ~ p.141)

Surface Roughness of Work Piece




■ YG-1
■ COMPETITOR



CUTTING CONDITION

Tools : DREAM DRILLS-ALU
Size : Ø10
Work Material : • AISI : 6061
 • JIS : A6061
 • DIN : AlMgSiCu
R.P.M : 6,367 rev./min.
SFM : 656 ft/min.
Feed : .0157 ~ .0315 inch/rev.
Drilling Depth : 1.77"
Coolant : Wet cut

► YG-1 (Total Drilling 820 Holes)




► Competitor (Total Drilling 820 Holes)




● FEATURES OF DREAM DRILLS-MQL TYPE

- Flute Shape and Point Shape allowing better chip evacuation in deep hole drilling
- Excellent Coating and Surface Treatment for better performance and chip evacuation

● TEST RESULT AGAINST COMPETITOR'S DRILLS



YG-1 (After Drilling 1,000 Holes)




COMPETITOR A (After Drilling 546 Holes)



● FEATURES OF DREAM DRILLS F H HARDENED STEELS

- Low Helix Angle to maximize tools' rigidity.
- Special Point Thinning to improve chip evacuation.
- Excellent Coating and Surface Treatment for improved surface and better chip evacuation.


● TEST RESULT AGAINST COMPETITOR'S DRILLS



YG-1 (After Drilling 100 Holes)



COMPETITOR A (After Drilling 40 Holes)



● Comparison of edge wear - Test I




CUTTING CONDITION

- Work material : • AISI : 316
- JIS : SUS316
- DIN : X3CrNiMo17-13-3

- Drilling Depth : .94"
- Total Drilling(hole) : 300 Holes
- R.P.M : 600 rev./min.
- Feed : 4.3307 inch/min.

● Comparison of edge wear - Test II




CUTTING CONDITION


- Work material : • AISI : D2
- JIS : SKD11
- DIN : X155CrVMo12-1

- Drilling Depth : .94"
- Total Drilling(hole) : 200 Holes
- R.P.M : 600 rev./min.
- Feed : 4.3307 inch/min.

YG-1



COMPETITOR A



● COMBO - SPIRAL FLUTE

Cutting Condition

- Tools : Combo Spiral Flute Tap
- Size : M8×1.25
- Work Material : • AISI : 1045
- JIS : S45C(HRc35)
- DIN : C45
- Tapping Depth : .79"
- Coolant : Water Soluble Oil
- SFM (Tapping Speed) : 33 ft/min.

YG-1(Total Tapping 204 Holes)



COMPETITOR A (Total Tapping 159 Holes)



COMPETITOR B (Total Tapping 204 Holes)




● COMBO - SPIRAL POINT

Cutting Condition

- Tools : Combo Spiral Point Tap
- Size : M2×0.4
- Work Material : • AISI : 1045
- JIS : S45C(HRc35)
- DIN : C45
- Tapping Depth : .24"
- Coolant : Tapping Oil
- SFM (Tapping Speed) : 33 ft/min.

YG-1(Total Tapping 450 Holes)



COMPETITOR A (Total Tapping 318 Holes)


Tool was broken after tapping 318 holes

COMPETITOR B (Total Tapping 103 Holes)

Tool was broken after tapping 103 holes

● **TEST I (Total Milling Length : 787 ft)**

▶ **Surface Roughness of Work Piece**




CUTTING CONDITION (Ø1mm)


Tools : 2Flute, CBN Ball Nose End mill
Size : Ø1×Ø4×0.6×50
Work Material : • JIS : SKD11(HRc60)
 • DIN : X155CrV-Mo12-1
 • AISI : H13
Cutting Speed : 309 ft/min.
R.P.M : 30,000 rev./min.
Feed : 59.06 inch/min.
Milling Depth : .0004"
Coolant : Oil Mist
Machine : Machining Center

▶ **Maximum Wear (μm)**


YG-1 (19.611 μm)



COMPETITOR A (32.249 μm)




COMPETITOR B



● **TEST II (Total Milling Length : 2,460 ft)**

▶ **Surface Roughness of Work Piece**




CUTTING CONDITION (Ø2mm)

Tools : 2Flute, CBN Ball Nose End mill
Size : Ø2×Ø4×1.8×50
Work Material : • JIS : SKD11(HRc60)
 • DIN : X155CrV-Mo12-1
 • AISI : H13
Cutting Speed : 618 ft/min.
R.P.M : 30,000 rev./min.
Feed : 78.74 inch/min.
Milling Depth : .0004"
Coolant : Oil Mist
Machine : Machining Center

▶ **Maximum Wear (μm)**


YG-1 (57.630 μm)




COMPETITOR A (100.314 μm)




COMPETITOR B (71.471 μm)




COMPETITOR C (170.200 μm)



● **i-Xmill - BALL**




YG-1 i-Xmill (Total Milling Length 620 ft)



COMPETITOR A (Total Milling Length 620 ft)



COMPETITOR B (Total Milling Length 620 ft)



CUTTING CONDITION


Tools : i-Xmill Ball
Size : Ø16×R8.0
Work Material : JIS : SKD61 (HRc50),
 DIN : X40GrMoV51(1.2344)
 AISI : H13

Cutting Speed : 264 ft/min.
R.P.M : 1,600 rev./min.
Feed : 15.35 inch/min.
Feed per tooth : .0047 inch/tooth
Milling Method : Side Cutting


Milling Depth : Axial : .0315"
 Radial : .0630"

Coolant : Oil Mist
Overhang : YG-1, Competitor B : 1.89"
 Competitor A : 2.20"
Machine : Machining Center


● **i-Xmill - CORNER RADIUS**




YG-1 i-Xmill (Total Milling Length 1476 ft)



COMPETITOR A (Total Milling Length 1476 ft)



COMPETITOR B (Total Milling Length 1476 ft)



CUTTING CONDITION

Tools : i-Xmill Corner Radius
Size : Ø16 x R2.0
Work Material : KS : KP4M (Mold steels HRc35)
 DIN : 40CrMnNiMo8-6-4(1.2738)
 AISI : P20+Ni



Cutting Speed : 918 ft/min.
R.P.M : 5,570 rev./min.
Feed : 87.80 inch/min.
Feed per tooth : .0079 inch/tooth
Milling Method : Side Cutting

Milling Depth : Axial : .1181"
 Radial : .0079"

Coolant : Oil Mist
Overhang : 2.76"
Machine : Machining Center


● **TEST REPORT**

● **Carbide 6 Flute 45° Helix End Mill for Hardened Steel**



CUTTING CONDITION

Tools : 4Flute Corner Radius, Ø16, R1.0
Work Material : KP4M (HRc35 / AISI P20+Ni DIN 1.2738 Improved)
Cutting Speed : 511 ft/min.
R.P.M : 3,100 rev./min.
Feed : 11.02 inch/min.
Feed per Tooth : .0656 inch/tooth
Milling Method : Down & Side Cutting
Milling Depth : Axial : .4724"
 Radial : .0314"
Overhang/Coolant : 3.03"/Wet Cut
Machine : Machining Center LCV 650




CUTTING CONDITION


Tools : 6Flute, X5070 45° Helix
Size : Ø16×Ø16×40×110
Work Material : • AISI : H13
 • JIS : SKD61(HRc50)
 • DIN : X40CrMoV5-1(1.2344)
Cutting Speed : 317 ft/min.
R.P.M : 1,920 rev./min.
Feed : 35.91"
Milling Method : Down & Side Cutting
Milling Depth : Axial : .9449"
 Radial : .0378"
Coolant : Dry Cut
Overhang : 2.05"
Machine : Machining Center

▶ **Cutting Edges**


YG-1 (Total Milling Length : 196 ft)




COMPETITOR A (Total Milling Length : 196 ft)




COMPETITOR B (Total Milling Length : 196 ft)




YG-1 (Total Milling Length 328 ft)




COMPETITOR A (Total Milling Length 328 ft)




● **TEST REPORT (Ball)**



YG-1 (Total Cutting Length : 984 ft)




COMPETITOR A (Total Cutting Length : 984 ft)




CUTTING CONDITION

Tool : 2Flute, Carbide Ball End Mill
 Size : Ø6×6×12×90
 Work Material : KP4M (HRc35 / AISI P20+Ni DIN 1.2738 Improved)
 Cutting Speed : 426.7 ft/min.
 R.P.M : 6,900 rev./min.
 Feed : 32.68 inch/min.
 Feed per tooth : .0024 inch/tooth
 Milling Method : Profiling
 Milling Depth : Axial : .0079"
 Radial : .0472"
 Coolant : Oil Mist
 Overhang : 1.024"


● **TEST REPORT (Corner Radius)**



YG-1 (Total Cutting Length : 570 ft)




COMPETITOR A (Total Cutting Length : 570 ft)



CUTTING CONDITION

Tool : 4Flute, Carbide Corner Radius End Mill
 Size : Ø10(R0.5)×10×25×100
 Work Material : KP4M (HRc35 / AISI P20+Ni DIN 1.2738 Improved)
 Cutting Speed : 169 ft/min.
 R.P.M : 1,640 rev./min.
 Feed : 7.09 inch/min.
 Feed per tooth : .0011 inch/tooth
 Milling Method : Down & Side Cutting
 Milling Depth : Axial : .9842"
 Radial : .0197"
 Coolant : Oil Mist
 Overhang : 1.614"


● Test Report-1 ♦ Y-Coated Solid Carbide 4 Flutes with Double Core End Mills




CUTTING CONDITION

Size : Ø12(R1) x Ø12 x 26 x 80
 Work Material : DIN : TiAV6V4 (Titanium)
 Cutting Depth : .470" (Axial Depth)
 R.P.M : 1,591 rev./min.
 Feed : 10 inch/min.

Milling Method : Slotting
 Coolant : Wet Cut
 Overhang : 1.41"
 Machine : Machining Center




● Test Report-2 ♦ Y-Coated Solid Carbide 5 Flutes End Mills



CUTTING CONDITION

Size : Ø12 x Ø12 x 26 x 83
 Work Material : DIN : TiAV6V4 (Titanium)
 Cutting Depth : .470" (Axial Depth)
 R.P.M : 1,591 rev./min.
 Feed : 15.669 inch/min.

Milling Method : Down & Side Cutting
 Axial Depth : .710"
 Radial Depth : .141"
 Coolant : Wet Cut
 Machine : Machining Center





CASE STUDY ♦ V7 PLUS A END MILLS (Reference page : p.977 ~ p.1015)

● TEST I - 4 Flute vs Competitor

CUTTING CONDITION



Tools : 4 Flute, V7 PLUS A
 Wear(μm) : V7 PLUS A 83.518
 Competitor 203.381
 Milling Length(inch) : 160
 Size : Ø10 x Ø10 x 22 x 72
 Work Material : - AISI : 1045
 - JIS : S45C(HRc30)
 - DIN : C45
 Cutting Speed : 754 ft/min.
 R.P.M : 7,324 rev/min.
 Feed : 57.64 inch/min.
 Feed per tooth : .002 inch/tooth
 Milling Method : Down & Side Cutting
 Milling Depth : Axial : .394"
 Radial : .118"
 Coolant : Wet Cut
 Overhang : 1.339"
 Machine : Machining Center



● TEST II - 6 Flute vs Competitor


CUTTING CONDITION

Tools : 6 Flute, V7 PLUS A
 Wear(μm) : V7 PLUS A 70.855
 Competitor 76.498
 Milling Length(inch) : 1,181
 Size : Ø12(R1) x Ø2 x 26 x 83
 Work Material : - AISI : 1045
 - JIS : S45C(HRc30)
 - DIN : C45
 Cutting Speed : 914 ft/min.
 R.P.M : 7,392 rev/min.
 Feed : 295.08 inch/min.
 Feed per tooth : .007 inch/tooth
 Milling Method : Trochoidal Cutting
 Milling Depth : Axial : .945"
 Radial : .024"
 Coolant : Wet Cut
 Overhang : 1.417"
 Machine : Machining Center



CASE STUDY ♦ D-POWER CFRP END MILLS (Reference page : p.1107 ~ p.1112)


● TEST I - DUAL HELIX




CUTTING CONDITION

Tools : 4 Flute, D-Power Dual Helix
 Size : Ø6(R0.5)×Ø6×12×65
 Work Material : CFRP
 R.P.M : 7,960 rev./min.
 Feed : 45.87 inch/min.
 Cutting Depth : Axial : .24"
 Radial : .09"
 Coolant : Dry Cut
 Overhang : 1.14"
 Milling Method : Side Cutting
 Machine : Machining Center


YG-1
(Total Milling Length 262ft)



COMPETITOR
(Total Milling Length 262ft)




● TEST II - 4 FLUTE, FINISH




CUTTING CONDITION

Tools : 4 Flute, D-Power
 Size : Ø12×Ø12×36×100
 Work Material : CFRP
 R.P.M : 5,310 rev./min.
 Feed : 50.19 inch/min.
 Cutting Depth : Axial : .47"
 Radial : .05"
 Coolant : Dry Cut
 Overhang : 2.20"
 Milling Method : Down & Side Cutting
 Machine : Machining Center

YG-1
(Total Milling Length 459ft)



COMPETITOR
(Total Milling Length 459ft)



CASE STUDY ♦ **ONLY ONE COATED PM60 END MILLS** (Reference page : p.1171~ p.1186)

● **4 Flute Square End Mill, S45C**

CUTTING CONDITION

Tool : Only One Coated PM60/Coated Normal Carbide

Size : $\varnothing 10 \times \varnothing 10 \times 22 \times 72 / \varnothing 10 \times \varnothing 10 \times 22 \times 70$

Work Material : - AISI : 1045
 - JIS : S45C
 - KS : SM45C
 - DIN : C45

R.P.M : 2,750 rev/min.


Feed : 20.47 inch/min.

Milling Method : Down & Side Cutting

Milling Depth : Axial : 12"
 Radial : .04"

Coolant : Wet Cut

Machine : Machining Center



● **4 Flute Square End Mill, S45C**

CUTTING CONDITION

Tool : Only One Coated PM60/Coated Normal Carbide

Size : $\varnothing 10 \times \varnothing 10 \times 22 \times 72 / \varnothing 10 \times \varnothing 10 \times 22 \times 70$

Work Material : - AISI : 1045
 - JIS : S45C
 - KS : SM45C
 - DIN : C45

R.P.M : 2,750 rev/min.


Feed : 20.47 inch/min.

Milling Method : Down & Side Cutting

Milling Depth : Axial : .39"
 Radial : .04"

Coolant : Wet Cut

Machine : Machining Center



CASE STUDY ♦ **SINE-POWER END MILLS** (Reference page : p.1187 ~ p.1191)

● **HSS Co 8% 6 FLUTE END MILLS**


SINE-POWER

Material	HSS Co8%
Dimension	$\varnothing 2'' (R.125'') \times \varnothing 2'' \times 4'' \times 7-3/4''$
No. of Flute	6
Coating	Uncoated

CUTTING CONDITIONS

Milling Method	Slotting	Profiling
Material	Ti6Al4V (Titanium)	
Coolant	Wet Cut	
RPM	100 rev./min.	100 rev./min.
Feed	2 IPM	3.15 ~ 4.2 IPM
Axial Depth	1-1/2 inch	1-1/2 inch
Radial Depth	2 inch	0.1 ~ 0.2 inch
Feed/Tooth	.0018 inch/tooth	.0053 ~ .007 inch/tooth

The above cutting conditions achieved 5 hours of machining



SINE-POWER SPECIFIC GEOMETRY DESIGN HELPS OUR CUSTOMERS TO INCREASE THEIR PRODUCTIVITY BY 15% IN TITANIUM MACHINING.

DRILLING TOOLS



Global Cutting Tool Leader **YG-1**



i-DREAM DRILLS, CARBIDE INSERTS
SOLID CARBIDE DREAM DRILLS - GENERAL
(with & without Coolant Holes)
SOLID CARBIDE DREAM DRILLS - HIGH FEED
(with Coolant Holes)
SOLID CARBIDE DREAM DRILLS - FLAT BOTTOM
(without Coolant Holes)
SOLID CARBIDE DREAM DRILLS - INOX
(with Coolant Holes)
SOLID CARBIDE DREAM DRILLS - ALU
(with Coolant Holes)
SOLID CARBIDE DREAM DRILLS - MQL TYPE
(with Coolant Holes)
SOLID CARBIDE DREAM DRILLS FOR HIGH HARDENED STEELS
STANDARD CARBIDE DRILLS
HSS-PM MULTI-1 DRILLS
PREMIUM HSS HPD STRAIGHT SHANK DRILLS
HSS GOLD-P DRILLS
HSS STRAIGHT SHANK DRILLS
HSS AIRCRAFT DRILLS
HSS SILVER & DEMING DRILLS
HSS MORSE TAPER SHANK DRILLS
HSS (8% Cobalt) NC SPOTTING DRILLS
HSS COMBINATION DRILL & COUNTER SINK / CENTER DRILL
CARBIDE & HSS-PM SPADE DRILLS
TECHNICAL DATA

YG-1 YG-1 CO., LTD.

Contents

DRILLING TOOLS

Contents / DRILLING TOOLS

CARBIDE INSERT DRILLS

SOLID CARBIDE DRILLS

HSS DRILLS

CARBIDE & HSS-PM SPADE DRILLS

TECHNICAL DATA

i-DREAM DRILLS

For General Steels and Stainless Steels

i-DREAM
DRILLS

SOLID CARBIDE DREAM DRILLS - GENERAL (with & without Coolant Holes)

For General Purpose HRc30 to HRc50

DREAM
DRILLS
-GENERAL

SOLID CARBIDE DREAM DRILLS - HIGH FEED (with Coolant Holes)

For Carbon Steels, Alloy Steels and Cast Iron

DREAM
DRILLS
-HIGH FEED

SOLID CARBIDE DREAM DRILLS - FLAT BOTTOM (without Coolant Holes)

Just ONE Drill - 180 Degree Point Angle for Horizontal Surface and Sloped Surface

DREAM
DRILLS
-FLAT BOTTOM

SOLID CARBIDE DREAM DRILLS - INOX (with Coolant Holes)

For Tough Materials - Stainless Steels, Nickel Alloys and Titanium up to HRc35

DREAM
DRILLS
-INOX

SOLID CARBIDE DREAM DRILLS - ALU (with Coolant Holes)

For Aluminum and Aluminum Alloys

DREAM
DRILLS
-ALU

SOLID CARBIDE DREAM DRILLS - MQL TYPE (with Coolant Holes)

Minimum Quantity Lubrication Drilling Deep Holes (10×D ~ 30×D)

DREAM
DRILLS
-MQL TYPE

SOLID CARBIDE DREAM DRILLS for HIGH HARDENED STEELS

For High Hardened Steels HRc50 to HRc70

DREAM DRILLS
for HIGH
HARDENED
STEELS

STANDARD CARBIDE DRILLS

For General Purpose, 118° Point

STANDARD
CARBIDE
DRILLS

HSS-PM MULTI-1 DRILLS

For Multi Purpose Particularly for Stainless Steels and Titanium

MULTI-1
DRILLS

HPD DRILLS

For General Steels and Stainless Steels

HPD DRILLS

HSS GOLD-P DRILLS

Gold-P Coating

GOLD-P
DRILLS

HSS STRAIGHT SHANK DRILLS

For General Purpose

STRAIGHT
SHANK
DRILLS

AIRCRAFT DRILLS

6 and 12 inch Length Drills

AIRCRAFT
DRILLS

SILVER & DEMING DRILLS

118° Split Point, 3 Flat Black and Gold

SILVER &
DEMING
DRILLS

HSS MORSE TAPER SHANK DRILLS

For General Purpose, Standard Length

TAPER
SHANK
DRILLS

HSS (8% Cobalt) NC SPOTTING DRILLS

Centering and Chamfering of Holes

NC SPOTTING
DRILLS

HSS COMBINATION DRILLS & COUNTER SINK / CENTER DRILL

Regular and Long Lengths

COMBINATION
DRILLS
& COUNTERSINK

CARBIDE & HSS-PM SPADE DRILLS

Carbide for Long Tool Life, and HSS-PM for General Machines and Large Diameters
Higher Productivity than Other Drilling Tools

SPADE
DRILLS

TECHNICAL DATA





























TECHNICAL
DATA

◎ : Excellent ○ : Good

	ITEM	MODEL	DESCRIPTION	SIZE		PAGE
				MIN	MAX	
i-Dream Drills	Y03 *		Insert for General Purpose	.4724 (#A)	1.2500 (#J)	44~49
	Y13 *		Insert for Stainless Steels	.4724 (#A)	1.2500 (#J)	44~49
Spade Drills	S01~S08		HSS M4 Insert	.7031 (#1)	4.5000 (#8)	272~275
	S06~S08 (SM08)		Super Cobalt T15 Insert	.3740 (#Y)	4.5000 (#8)	276~282 292~295
	S11~S14		Primium cobalt M48 Insert	.3740 (#Y)	1.3780 (#2)	283~285
	S21~S23		Carbide C2, C5, C3 Insert	.3740 (#Y)	1.8750 (#3)	286~290
	S26~S28 (SM28)		Carbide C5 Insert (P40)	.3740 (#Y)	1.8750 (#3)	286~290 296~297
	S16~S18		Carbide C3 Insert (K10)	.3740 (#Y)	1.3780 (#2)	286~290
	SF05 SF15		Super Cobalt T15 Flat Bottom	.3750 (#Y)	1.3750 (#2)	298

Non-alloyed Steels, Free Machining Steels	P										M	K	N		
	Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron		Aluminum	Copper Alloys
	~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎		◎	◎		
○	○		○				○		○		◎			○	○
○	○	○	○		○		○	○			◎	◎	○	◎	◎
◎	◎	◎	◎	◎	○	○	◎	◎	○	○	○	○	◎	○	○
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	○	○	◎	○	○
○	○	○	○	○	◎	◎	○	○	○	○	◎	○	○	◎	◎
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	○	○	○	○	○
												◎	◎		
◎	◎	◎	◎	○	○	○	◎	◎	○	○	○	○	◎	○	○

◎ : Excellent ○ : Good

	ITEM	MODEL	INCH / METRIC	LENGTH	SIZE		PAGE
					MIN	MAX	
DREAM DRILLS-GENERAL	DH416 DH711		Inch	Short(3XD)	D1/8	D5/8	58
	DH418 DH712		Inch	Long(5XD)	D13/64	D1/2	60
	DH414		Inch	Stub(3XD)	D1/8	D5/8	61
	DH722		Inch	Long(5XD)	D13/64	D1/2	62
	DH406		Metric	Short(3XD)	D3.0	D20.0	63
	DH408		Metric	Long(5XD)	D1.0	D20.0	67
	DH421		Metric	Extra Long(8XD)	D3.0	D20.0	72
	DH404		Metric	Stub(3XD)	D3.0	D20.0	76
	DH423		Metric	Short(3XD)	D3.0	D20.0	78
	DH424		Metric	Long(5XD)	D1.0	D20.0	83
DREAM DRILLS-HIGH FEED	DGR493 DGR496		Inch	Short(3XD)	.1969	.7874	94
	DGR495 DGR497		Inch	Long(5XD)	.1969	.7874	98
DREAM DRILLS-FLAT BOTTOM	DPP447		Metric	Short(2×D)	D3.0	D20.0	106
DREAM DRILLS-INOX	DH463 DH714		Inch	Stub(3XD)	D1/8	D5/8	114
	DH464 DH715		Inch	Long(5XD)	D13/64	D1/2	116
	DH451		Metric	Short(3XD)	.1181	.7874	117
	DH452		Metric	Long(5XD)	.0394	.7874	122
	DH453		Metric	Extra Long(8XD)	.1181	.7874	127
DREAM DRILLS-ALU	DGE466 DGE718		Inch	Long(5XD)	D13/64	D1/2	136
	DGE433		Metric	Long(5XD)	.1181	.7874	137
DREAM DRILLS-MQL TYPE	DH510		Metric	Extra Long(10XD)	D3.0	D14.0	146
	DH515		Metric	Extra Long(15XD)	D3.0	D12.0	149
	DH520		Metric	Extra Long(20XD)	D3.0	D12.0	152
	DHM10		Metric	Extra Long(10XD)	D3.0	D14.0	155
	DHM15		Metric	Extra Long(15XD)	D3.0	D12.0	155
	DHM20		Metric	Extra Long(20XD)	D3.0	D12.0	156
	DHM25		Metric	Extra Long(25XD)	D3.0	D10.0	158
	DHM30		Metric	Extra Long(30XD)	D3.0	D8.0	129

P					H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~								
◎	◎	◎			○	○						
◎	◎	◎			○	○						
◎	◎	◎			○	○						
◎	◎	◎			○	○						
◎	◎	◎			○	○						
◎	◎	◎			○	○						
◎	◎	◎			○	○						
◎	◎	◎			○	○						
◎	◎	◎			○	○						
◎	◎	○				◎	○					
◎	◎	○				◎	○					
◎	◎	◎	○		○	◎	○	○				
◎	◎	○			◎		○				○	
◎	◎	○			◎		○				○	
◎	◎	○			◎		○				○	
							◎					
							◎					
◎	◎	○				○						
◎	◎	○				○						
◎	◎	○				○						
◎	◎	○				○						
◎	◎	○				○						
◎	◎	○				○						
◎	◎	○				○						

◎ : Excellent ○ : Good


	ITEM	MODEL	INCH / METRIC	LENGTH	SIZE		PAGE
					MIN	MAX	
STRAIGHT SHANK DRILLS	DN516		Inch	Screw Machine	A	Z	226
	DN515		Inch	Screw Machine	#47	#1	227
	DL517 DX517		Inch	Taper Length	D5/64	D1/2	228
	D4107		Metric	Screw Machine	D1.0	D31.0	229
AIRCRAFT DRILLS	DL601 DL604		Inch	Extension Length	D5/64	D1/2	240
	DL602 DL605		Inch	Extension Length	A	Z	241
	DL603 DL606		Inch	Extension Length	#43	#1	242
	D1631 D1634		Inch	Extension Length	D5/64	D1/2	243
	D1632 D1635		Inch	Extension Length	A	Z	244
	D1633 D1636		Inch	Extension Length	#43	#1	245
	SILVER & DEMING DRILLS	D1191		Inch	—	D1/2	D1-1/2
MORSE TAPER SHANK DRILLS	D1211		Inch	—	D1/2	D2-1/2	256
NC SPOTTING DRILLS	D2N90(90°)		Inch	—	D1/8	D1	262
	D2N90(120°)		Inch	—	D1/8	D1	262
COMBINATION DRILL & COUNTER SINK / CENTER DRILL	D1C90		Inch	—	D3/64	D7/32	268

P			H	M	K	N			S	
Carbon Steels ~HB225	Alloy Steels HB225~325	Prehardened Steels HRC30~45	Hardened Steels HRC45~55 HRC55~	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
◎	◎				○					
◎	◎				○					
◎	◎				○					
◎	◎				○	○				○
◎	○				○	○	○	○		
◎	○				○	○	○	○		
◎	◎	○			○	○	○	○		○
◎	◎	○			○	○	○	○		○
◎	◎				○	○	○	○		○
◎	◎	○			○	○	○			
◎	◎				○	○	○			
◎	◎				○	○	○	○		
◎	◎				○	○	○	○		○




Being the best through innovation

CARBIDE INSERT















Global Cutting Tool Leader **YG-1**



i - Dream Drills

- For Steels and Stainless Steel Alloys

ITEM	MODEL	DESCRIPTION	PAGE
Y03A / Y03B		<i>i-Dream Drills</i> General	44
YI3A / YI3B		<i>i-Dream Drills</i> INOX	44
Y03B / Y03C		<i>i-Dream Drills</i> General	45
YI3B / YI3C		<i>i-Dream Drills</i> INOX	45
Y03C / Y03D		<i>i-Dream Drills</i> General	46
YI3C / YI3D		<i>i-Dream Drills</i> INOX	46
Y03E / Y03F		<i>i-Dream Drills</i> General	47
YI3E / YI3F		<i>i-Dream Drills</i> INOX	47
Y03G / Y03H		<i>i-Dream Drills</i> General	48
YI3G / YI3H		<i>i-Dream Drills</i> INOX	48
Y03I / Y03J		<i>i-Dream Drills</i> General	49
YI3I / YI3J		<i>i-Dream Drills</i> INOX	49
RECOMMENDED CUTTING CONDITIONS			50

◎ : Excellent ○ : Good

Non-alloyed Steels, Free Machining Steels	P										M	K	N		
	Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron		Aluminum	Copper Alloys
	~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎		◎	◎		
○	○		○				○		○		◎			○	○
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎		◎	◎		
○	○		○				○		○		◎			○	○
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎		◎	◎		
○	○		○				○		○		◎			○	○
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎		◎	◎		
○	○		○				○		○		◎			○	○
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎		◎	◎		
○	○		○				○		○		◎			○	○

Comparison with Split Point Drill, Spade Drill & Dream Drill





Y03A / YI3A SERIES
Y03B / YI3B SERIES

i-DREAM DRILL INSERTS & HOLDERS

- Features of i-Dream Drill Inserts


- Secure and accurate seating resulting in accurate repeatability and concentricity.

i-Dream Drill General

- For most steel materials


i-Dream Drill INOX

- For tough, ductile materials and stainless steels
- Light, sharp cutting edge
- Minimize cutting forces
- Reduce built-up edge



- Features of i-Dream Drill Holders

- Special Alloy Steels that maintains its hardness and toughness under high temperatures with generous coolant holes for effective coolant flow.
- Innovative surface treatment that improves wear resistance and reduces corrosion.
- High Performance flute design allowing maximum chip evacuation and minimum interference.



cutting conditions : p.50~51

Series Range	Insert EDP No.		Insert O.D.		Length	Holder EDP No.	Diameter	Shank Dia.	Shank Length	Flange Dia.	Drilling Depth	Overall Length	Torx Screw No.									
	TiAIN	TiCN	h7																			
	General	INOX	dec.	inch / mm																		
A Ø12.00 to Ø13.99 3.6mm Thick	Y03A01	YI3A01	.4724	12.00	3D	ZA0301	.4528	3/4	2	1	1-27/64	4-29/64	TA1213									
	Y03A02	YI3A02	.4764	12.10	5D	ZA0501					2-23/64	5-13/32										
	Y03A03	YI3A03	.4803	12.20	7D	ZA0701					3-5/16	6-11/32										
	Y03A04	YI3A04	.4844	31/64	3D	ZA0302	.4724	3/4	2	1	1-15/32	4-1/2	TA1213									
	Y03A05	YI3A05	.4921	12.50							5D	ZA0502		2-29/64	5-31/64							
	Y03A06	YI3A06	.4961	12.60							7D	ZA0702		3-7/16	6-15/32							
	Y03A07	YI3A07	.5000	1/2	3D	ZA0303	.4921	3/4	2	1	1-17/32	4-37/64	TA1314									
	Y03A08	YI3A08	.5039	12.80							5D	ZA0503		2-9/16	5-19/32							
	Y03A09	YI3A09	.5079	12.90							7D	ZA0703		3-37/64	6-5/8							
	Y03A10	YI3A10	.5118	13.00	3D	ZA0304	.5118	3/4	2	1	1-19/32	4-39/64	TA1314									
	Y03A11	YI3A11	.5156	33/64							5D	ZA0504		2-21/32	5-43/64							
	Y03A12	YI3A12	.5197	13.20							7D	ZA0704		3-23/32	6-47/64							
	Y03A13	YI3A13	.5312	17/32	3D	ZB0301	.5315	3/4	2	1	1-21/32	4-23/32	TB1415									
	Y03A14	YI3A14	.5315	13.50							5D	ZB0501		2-3/4	5-13/16							
	Y03A15	YI3A15	.5354	13.60							7D	ZB0701		3-55/64	6-59/64							
	Y03A16	YI3A16	.5394	13.70	3D	ZB0301	.5315	3/4	2	1	1-21/32	4-23/32	TB1415									
	Y03A17	YI3A17	.5433	13.80							5D	ZB0501		2-3/4	5-13/16							
	Y03A18	YI3A18	.5469	35/64							7D	ZB0701		3-55/64	6-59/64							
B Ø14.00 to Ø15.99 4mm Thick	Y03B01	YI3B01	.5512	14.00	3D	ZB0301	.5315	3/4	2	1	1-21/32	4-23/32	TB1415									
	Y03B02	YI3B02	.5551	14.10							5D	ZB0501		2-3/4	5-13/16							
	Y03B03	YI3B03	.5591	14.20							7D	ZB0701		3-55/64	6-59/64							
	Y03B04	YI3B04	.5625	9/16							3D	ZC0301		.6102	3/4	2	1	1-57/64	4-61/64	TC1617		
	Y03B05	YI3B05	.5630	14.30														5D	ZC0501		3-5/32	6-7/32
	Y03B06	YI3B06	.5669	14.40														7D	ZC0701		4-13/32	7-15/32

◎ : Excellent ○ : Good

	P										M	K	N			
	Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
	~HRc24 (~HB250)	~HRc28 (~HB275)	~HRc28 (~HB275)	~HRc28 (~HB275)	~HRc28 (~HB275)	~HRc37 (~HB350)	~HRc37 (~HB350)	~HRc24 (~HB250)	~HRc24 (~HB250)	~HRc13 (~HB200)	~HRc13 (~HB200)	~HRc28 (~HB275)	~HRc19 (~HB220)	~HRc19 (~HB220)	~HRc8 (~HB180)	~HB110
Y03 *	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎
YI3 *	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○



Y03B / YI3B SERIES
Y03C / YI3C SERIES

i-DREAM DRILL INSERTS & HOLDERS

- Features of i-Dream Drill Inserts


- Secure and accurate seating resulting in accurate repeatability and concentricity.

i-Dream Drill General

- For most steel materials


i-Dream Drill INOX

- For tough, ductile materials and stainless steels
- Light, sharp cutting edge
- Minimize cutting forces
- Reduce built-up edge



- Features of i-Dream Drill Holders

- Special Alloy Steels that maintains its hardness and toughness under high temperatures with generous coolant holes for effective coolant flow.
- Innovative surface treatment that improves wear resistance and reduces corrosion.
- High Performance flute design allowing maximum chip evacuation and minimum interference.



cutting conditions : p.50~51

Series Range	Insert EDP No.		Insert O.D.		Length	Holder EDP No.	Diameter	Shank Dia.	Shank Length	Flange Dia.	Drilling Depth	Overall Length	Torx Screw No.									
	TiAIN	TiCN	h7																			
	General	INOX	dec.	inch / mm																		
B Ø14.00 to Ø15.99 4mm Thick	Y03B07	YI3B07	.5709	14.50	3D	ZB0302	.5512	3/4	2	1	1-23/32	4-51/64	TB1415									
	Y03B08	YI3B08	.5748	14.60	5D	ZB0502					2-55/64	5-15/16										
	Y03B09	YI3B09	.5781	37/64	7D	ZB0702					4	7-5/64										
	Y03B10	YI3B10	.5827	14.80	3D	ZB0303	.5709	3/4	2	1	1-49/64	4-7/8	TB1516									
	Y03B11	YI3B11	.5906	15.00							5D	ZB0503		2-61/64	6-3/64							
	Y03B12	YI3B12	.5938	19/32							7D	ZB0703		4-9/64	7-15/64							
	Y03B13	YI3B13	.5945	15.10	3D	ZB0304	.5906	3/4	2	1	1-53/64	4-29/32	TB1516									
	Y03B14	YI3B14	.5984	15.20							5D	ZB0504		3-3/64	6-1/8							
	Y03B15	YI3B15	.6024	15.30							7D	ZB0704		4-17/64	7-11/32							
	Y03B16	YI3B16	.6094	39/64	3D	ZB0304	.5906	3/4	2	1	1-53/64	4-29/32	TB1516									
	Y03B17	YI3B17	.6102	15.50							5D	ZB0504		3-3/64	6-1/8							
	Y03B18	YI3B18	.6142	15.60							7D	ZB0704		4-17/64	7-11/32							
Y03B19	YI3B19	.6181	15.70	3D	ZC0301	.6102	3/4	2	1	1-57/64	4-61/64	TC1617										
Y03B20	YI3B20	.6220	15.80							5D	ZC0501		3-5/32	6-7/32								
Y03B21	YI3B21	.6250	5/8							7D	ZC0701		4-13/32	7-15/32								
C Ø16.00 to Ø17.99 4.5mm Thick	Y03C01	YI3C01	.6299	16.00	3D	ZC0301	.6102	3/4	2	1	1-57/64	4-61/64	TC1617									
	Y03C02	YI3C02	.6335	16.09							5D	ZC0501		3-5/32	6-7/32							
	Y03C03	YI3C03	.6378	16.20							7D	ZC0701		4-13/32	7-15/32							
	Y03C04	YI3C04	.6406	41/64							3D	ZC0302		.6299	3/4	2	1	1-61/64	5-1/32	TC1617		
	Y03C05	YI3C05	.6417	16.30														5D	ZC0502		3-1/4	6-21/64
	Y03C06	YI3C06	.6496	16.50														7D	ZC0702		4-35/64	7-5/8
Y03C07	YI3C07	.6562	21/32	3D	ZC0302	.6299	3/4	2	1	1-61/64	5-1/32	TC1617										
Y03C08	YI3C08	.6614	16.80							5D	ZC0502		3-1/4	6-21/64								

◎ : Excellent ○ : Good

	P										M	K	N			
	Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
	~HRc24 (~HB250)	~HRc28 (~HB275)	~HRc28 (~HB275)	~HRc28 (~HB275)	~HRc28 (~HB275)	~HRc37 (~HB350)	~HRc37 (~HB350)	~HRc24 (~HB250)	~HRc24 (~HB250)	~HRc13 (~HB200)	~HRc13 (~HB200)	~HRc28 (~HB275)	~HRc19 (~HB220)	~HRc19 (~HB220)	~HRc8 (~HB180)	~HB110
Y03 *	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎
YI3 *	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○



Y03C / YI3C SERIES
Y03D / YI3D SERIES

i-DREAM DRILL INSERTS & HOLDERS

- Features of i-Dream Drill Inserts


- Secure and accurate seating resulting in accurate repeatability and concentricity.

i-Dream Drill General

- For most steel materials


i-Dream Drill INOX

- For tough, ductile materials and stainless steels
- Light, sharp cutting edge
- Minimize cutting forces
- Reduce built-up edge



- Features of i-Dream Drill Holders

- Special Alloy Steels that maintains its hardness and toughness under high temperatures with generous coolant holes for effective coolant flow.
- Innovative surface treatment that improves wear resistance and reduces corrosion.
- High Performance flute design allowing maximum chip evacuation and minimum interference.



cutting conditions : p.50~51

Series Range	Insert EDP No.		Insert O.D.		Length	Holder EDP No.	Diameter	Shank Dia.	Shank Length	Flange Dia.	Drilling Depth	Overall Length	Torx Screw No.
	TiAlN	TiCN	h7										
	General	INOX	dec.	inch / mm									
C Ø16.00 to Ø17.99 4.5mm Thick	Y03C09	YI3C09	.6693	17.00	3D	ZC0303	.6496	3/4	2	1	2-1/64	5-5/64	TC1718
	Y03C10	YI3C10	.6919	43/64	5D	ZC0503					3-11/32	6-13/32	
	Y03C11	YI3C11	.6875	11/16	7D	ZC0703					4-11/16	7-3/4	
	Y03C12	YI3C12	.6890	17.50	3D	ZC0304					2-1/16	5-5/32	
	Y03C13	YI3C13	.7008	17.80	5D	ZC0504					3-7/16	6-17/32	
	Y03C14	YI3C14	.7031	45/64	7D	ZC0704					4-53/64	7-29/32	
D Ø18.00 to Ø19.99 5mm Thick	Y03D01	YI3D01	.7087	18.00	3D	ZD0301	.6890	1	2-3/16	1-1/4	2-1/8	5-1/2	TD1819
	Y03D02	YI3D02	.7188	23/32	5D	ZD0501					3-35/64	6-59/64	
	Y03D03	YI3D03	.7283	18.50	3D	ZD0302					4-61/64	8-11/32	
	Y03D04	YI3D04	.7344	47/64	5D	ZD0502					2-3/16	5-35/64	
	Y03D05	YI3D05	.7402	18.80	7D	ZD0702					3-41/64	7	
	Y03D06	YI3D06	.7480	19.00	3D	ZD0303					5-3/32	8-29/64	
F Ø22.00 to Ø23.99 6mm Thick	Y03F01	YI3F01	.8661	22.00	3D	ZF0301	.8425	1	2-3/16	1-1/4	2-19/32	5-63/64	TF2223
	Y03F02	YI3F02	.8750	7/8	5D	ZF0501					4-21/64	7-23/32	
	Y03F03	YI3F03	.8858	22.50	3D	ZF0302					6-1/16	9-29/64	
	Y03F04	YI3F04	.8906	57/64	5D	ZF0502					2-21/32	6-1/32	
	Y03F05	YI3F05	.8937	22.70	7D	ZF0702					4-27/64	7-51/64	
	Y03F06	YI3F06	.9055	23.00	3D	ZF0303					6-13/64	9-9/16	
E Ø20.00 to Ø21.99 5.5mm Thick	Y03E01	YI3E01	.7874	20.00	3D	ZE0301	.7835	1	2-3/16	1-1/4	2-23/64	5-23/32	TE2021
	Y03E02	YI3E02	.7969	51/64	5D	ZE0501					3-15/16	7-9/32	
	Y03E03	YI3E03	.8071	20.50	3D	ZE0302					5-33/64	8-55/64	
	Y03E04	YI3E04	.8125	13/16	5D	ZE0502					2-27/64	5-51/64	
	Y03E05	YI3E05	.8150	20.70	7D	ZE0702					4-1/32	7-13/32	
	Y03E06	YI3E06	.8268	21.00	3D	ZE0303					5-21/32	9-1/64	
D Ø18.00 to Ø19.99 5mm Thick	Y03D07	YI3D07	.7500	3/4	3D	ZD0303	.7283	1	2-3/16	1-1/4	2-1/4	5-43/64	TD1920
	Y03D08	YI3D08	.7587	19.27	5D	ZD0503					3-47/64	7-5/32	
	Y03D09	YI3D09	.7656	49/64	7D	ZD0703					5-15/64	8-21/32	
	Y03D10	YI3D10	.7677	19.50	3D	ZD0304					2-19/64	5-45/64	
	Y03D11	YI3D11	.7795	19.80	5D	ZD0504					3-27/32	7-15/64	
	Y03D12	YI3D12	.7812	25/32	7D	ZD0704					5-3/8	8-25/32	

◎ : Excellent ○ : Good

	P										M	K	N			
	Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
	~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275)	~HRc28 (~HB275)	HRc28~ (~HB275)	~HRc37 (~HB350)	HRc37~ (~HB350)	~HRc24 (~HB250)	HRc24~ (~HB250)	~HRc13 (~HB200)	HRc13~ (~HB200)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220)	~HRc8 (~HB180)	~HB110
Y03 *	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎
YI3 *	○	○	○	○	○	○	○	○	○	○	○	◎	○	○	○	○



Y03E / YI3E SERIES
Y03F / YI3F SERIES

i-DREAM DRILL INSERTS & HOLDERS

- Features of i-Dream Drill Inserts


- Secure and accurate seating resulting in accurate repeatability and concentricity.

i-Dream Drill General

- For most steel materials


i-Dream Drill INOX

- For tough, ductile materials and stainless steels
- Light, sharp cutting edge
- Minimize cutting forces
- Reduce built-up edge



- Features of i-Dream Drill Holders

- Special Alloy Steels that maintains its hardness and toughness under high temperatures with generous coolant holes for effective coolant flow.
- Innovative surface treatment that improves wear resistance and reduces corrosion.
- High Performance flute design allowing maximum chip evacuation and minimum interference.



cutting conditions : p.50~51

Series Range	Insert EDP No.		Insert O.D.		Length	Holder EDP No.	Diameter	Shank Dia.	Shank Length	Flange Dia.	Drilling Depth	Overall Length	Torx Screw No.
	TiAlN	TiCN	h7										
	General	INOX	dec.	inch / mm									
E Ø20.00 to Ø21.99 5.5mm Thick	Y03E01	YI3E01	.7874	20.00	3D	ZE0301	.7835	1	2-3/16	1-1/4	2-23/64	5-23/32	TE2021
	Y03E02	YI3E02	.7969	51/64	5D	ZE0501					3-15/16	7-9/32	
	Y03E03	YI3E03	.8071	20.50	3D	ZE0302					5-33/64	8-55/64	
	Y03E04	YI3E04	.8125	13/16	5D	ZE0502					2-27/64	5-51/64	
	Y03E05	YI3E05	.8150	20.70	7D	ZE0702					4-1/32	7-13/32	
	Y03E06	YI3E06	.8268	21.00	3D	ZE0303					5-21/32	9-1/64	
	Y03E07	YI3E07	.8281	53/64	5D	ZE0503					2-31/64	5-7/8	
	Y03E08	YI3E08	.8438	27/32	7D	ZE0703					4-9/64	7-33/64	
	Y03E09	YI3E09	.8465	21.50	3D	ZE0304					5-25/32	9-11/64	
	Y03E10	YI3E10	.8543	21.70	5D	ZE0504					2-35/64	5-29/32	
	Y03E11	YI3E11	.8594	55/64	7D	ZE0704					4-15/64	7-19/32	
F Ø22.00 to Ø23.99 6mm Thick	Y03F01	YI3F01	.8661	22.00	3D	ZF0301	.8425	1	2-3/16	1-1/4	2-19/32	5-63/64	TF2223
	Y03F02	YI3F02	.8750	7/8	5D	ZF0501					4-21/64	7-23/32	
	Y03F03	YI3F03	.8858	22.50	3D	ZF0302					6-1/16	9-29/64	
	Y03F04	YI3F04	.8906	57/64	5D	ZF0502					2-21/32	6-1/32	
	Y03F05	YI3F05	.8937	22.70	7D	ZF0702					4-27/64	7-51/64	
	Y03F06	YI3F06	.9055	23.00	3D	ZF0303					6-13/64	9-9/16	
	Y03F07	YI3F07	.9062	29/32	5D	ZF0503					2-23/32	6-7/64	
	Y03F08	YI3F08	.9219	59/64	7D	ZF0703					4-17/32	7-29/32	
	Y03F09	YI3F09	.9252	23.50	3D	ZF0304					6-11/32	9-23/32	
	Y03F10	YI3F10	.9331	23.70	5D	ZF0504					2-25/32	6-3/16	
	Y03F11	YI3F11	.9375	15/16	7D	ZF0704					4-5/8	8-1/32	
D Ø18.00 to Ø19.99 5mm Thick	Y03D07	YI3D07	.7500	3/4	3D	ZD0303	.7283	1	2-3/16	1-1/4	2-1/4	5-43/64	TD1920
	Y03D08	YI3D08	.7587	19.27	5D	ZD0503					3-47/64	7-5/32	
	Y03D09	YI3D09	.7656	49/64	7D	ZD0703					5-15/64	8-21/32	
	Y03D10	YI3D10	.7677	19.50	3D	ZD0304					2-19/64	5-45/64	
	Y03D11	YI3D11	.7795	19.80	5D	ZD0504					3-27/32	7-15/64	
	Y03D12	YI3D12	.7812	25/32	7D	ZD0704					5-3/8	8-25/32	

◎ : Excellent ○ : Good

	P										M	K	N			
	Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
	~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275)	~HRc28 (~HB275)	HRc28~ (~HB275)	~HRc37 (~HB350)	HRc37~ (~HB350)	~HRc24 (~HB250)	HRc24~ (~HB250)	~HRc13 (~HB200)	HRc13~ (~HB200)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220)	~HRc8 (~HB180)	~HB110
Y03 *	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎
YI3 *	○	○	○	○	○	○	○	○	○	○	○	◎	○	○	○	○



Y03G / YI3G SERIES
Y03H / YI3H SERIES

i-DREAM DRILL INSERTS & HOLDERS

- Features of i-Dream Drill Inserts


- Secure and accurate seating resulting in accurate repeatability and concentricity.

i-Dream Drill General

- For most steel materials


i-Dream Drill INOX

- For tough, ductile materials and stainless steels
- Light, sharp cutting edge
- Minimize cutting forces
- Reduce built-up edge



- Features of i-Dream Drill Holders

- Special Alloy Steels that maintains its hardness and toughness under high temperatures with generous coolant holes for effective coolant flow.
- Innovative surface treatment that improves wear resistance and reduces corrosion.
- High Performance flute design allowing maximum chip evacuation and minimum interference.



cutting conditions : p.50~51

Series Range	Insert EDP No.		Insert O.D.		Length	Holder EDP No.	Diameter	Shank Dia.	Shank Length	Flange Dia.	Drilling Depth	Overall Length	Torx Screw No.			
	TiAIN	TiCN	h7													
	General	INOX	dec.	inch / mm												
G Ø24.00 to Ø25.99 6.5mm Thick	Y03G01	YI3G01	.9449	24.00	3D	ZG0301	.9213	1-1/4	2-3/8	1-15/32	2-53/64	6-1/2	TG2425			
	Y03G02	YI3G02	.9531	61/64	5D	ZG0501					4-23/32	8-25/64				
	Y03G03	YI3G03	.9646	24.50	7D	ZG0701					6-39/64	10-9/32				
	Y03G04	YI3G04	.9688	31/32	3D	ZG0302	.9409	1-1/4	2-3/8	1-15/32	2-57/64	6-17/32		TG2526		
	Y03G05	YI3G05	.9724	24.70	5D	ZG0502					4-53/64	8-15/32				
	Y03G06	YI3G06	.9843	63/64	7D	ZG0702					6-3/4	10-25/64				
	Y03G07	YI3G07	1.0000	1	3D	ZG0303	.9606	1-1/4	2-3/8	1-15/32	2-61/64	6-39/64			TG2627	
	Y03G08	YI3G08	1.0039	25.50	5D	ZG0503					4-59/64	8-37/64				
	Y03G09	YI3G09	1.0106	25.67	7D	ZG0703					6-57/64	10-35/64				
	Y03G10	YI3G10	1.0118	25.70	3D	ZG0304	.9803	1-1/4	2-3/8	1-15/32	3-1/64	6-47/64				TH2627
	Y03G11	YI3G11	1.0156	1-1/64	5D	ZG0504					5-1/64	8-47/64				
Y03H01	YI3H01	1.0236	26.00	7D	ZG0704	7-1/32					10-3/4					
H Ø26.00 to Ø27.99 7.1mm Thick	Y03H02	YI3H02	1.0312	1-1/32	3D	ZH0301	1.0000	1-1/4	2-3/8	1-15/32	3-5/64	6-3/4	TH2728			
	Y03H03	YI3H03	1.0433	26.50	5D	ZH0501					5-1/8	8-51/64				
	Y03H04	YI3H04	1.0469	1-3/64	7D	ZH0701					7-11/64	10-27/32				
	Y03H05	YI3H05	1.0625	1-1/16	3D	ZH0302	1.0197	1-1/4	2-3/8	1-15/32	3-1/8	6-51/64		TH2831		
	Y03H06	YI3H06	1.0630	27.00	5D	ZH0502					5-7/32	8-7/8				
	Y03H07	YI3H07	1.0827	27.50	7D	ZH0702					7-19/64	10-31/32				
	Y03H08	YI3H08	1.0938	1-3/32	3D	ZH0303	1.0394	1-1/4	2-3/8	1-15/32	3-3/16	6-7/8			TH2930	
	Y03J01	YI3J01	1.1811	30.00	5D	ZH0503					5-5/16	9				
Y03J02	YI3J02	1.1875	1-3/16	7D	ZH0703	7-7/16					11-1/8					
J Ø30.00 to Ø31.99 8mm Thick	Y03J03	YI3J03	1.0433	26.50	3D	ZH0304	1.0591	1-1/4	2-3/8	1-15/32	3-1/4	6-29/32	TJ2812			
	Y03J04	YI3J04	1.0469	1-3/64	5D	ZH0504					5-13/32	9-5/64				
	Y03J05	YI3J05	1.0625	1-1/16	7D	ZH0704					7-37/64	11-15/64				
	Y03J06	YI3J06	1.1929	1-1/4	3D	ZJ0301	1.1535	1-1/4	2-3/8	1-15/32	3-35/64	7-21/64		TJ3132		
	Y03J07	YI3J07	1.2402	31.50	5D	ZJ0501					5-29/32	9-45/64				
	Y03J08	YI3J08	1.2500	1-1/4	7D	ZJ0701					8-17/64	12-1/16				
	I Ø28.00 to Ø29.99 7.7mm Thick	Y03I01	YI3I01	1.1024	28.00	3D	ZI0301	1.0945	1-1/4	2-3/8	1-15/32	3-5/16			7	TI2829
		Y03I02	YI3I02	1.1094	1-7/64	5D	ZI0501					5-33/64			9-15/64	
Y03I03		YI3I03	1.1220	28.50	7D	ZI0701	7-23/32					11-7/16				
Y03I04		YI3I04	1.1250	1-1/8	3D	ZI0302	1.1142	1-1/4	2-3/8	1-15/32	3-23/64	7-1/16	TI2930			
Y03I05		YI3I05	1.1417	29.00	5D	ZI0502					5-39/64	9-5/16				
Y03I06		YI3I06	1.1562	1-5/32	7D	ZI0702					7-55/64	11-9/16				
Y03I07		YI3I07	1.1614	29.50	3D	ZI0303	1.1339	1-1/4	2-3/8	1-15/32	3-27/64	7-3/16		TJ3132		
Y03I08		YI3I08	1.1719	1-11/64	5D	ZI0503					5-45/64	9-15/32				
Y03J09	YI3J09	1.2008	30.50	7D	ZI0703	7-63/64					11-3/4					
K Ø32.00 to Ø33.99 8.5mm Thick	Y03K01	YI3K01	1.1811	30.00	3D	ZJ0304	1.1732	1-1/4	2-3/8	1-15/32	5-13/16	9-35/64			TJ3132	
	Y03K02	YI3K02	1.1875	1-3/16	5D	ZJ0504					5-13/16	9-35/64				
	Y03K03	YI3K03	1.2008	30.50	7D	ZJ0702					8-1/8	11-7/8				
	Y03K04	YI3K04	1.2031	1-13/64	3D	ZJ0303	1.1929	1-1/4	2-3/8	1-15/32	3-21/32	7-13/32	TJ3132			
	Y03K05	YI3K05	1.2188	1-7/32	5D	ZJ0503					6-7/64	9-55/64				
	Y03K06	YI3K06	1.2205	31.00	7D	ZJ0703					8-35/64	12-19/64				
	Y03K07	YI3K07	1.2402	31.50	3D	ZJ0304	1.2126	1-1/4	2-3/8	1-15/32	3-23/32	7-17/32		TJ3132		
	Y03K08	YI3K08	1.2500	1-1/4	5D	ZJ0504					6-13/64	10-1/64				
Y03K09	YI3K09	1.2500	1-1/4	7D	ZJ0704	8-11/16					12-31/64					

◎ : Excellent ○ : Good

Series	P										M	K	N			
	Non-alloy Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
	~HRc24 (~HB250)	~HRc28 (~HB275)	~HRc28 (~HB275)	~HRc28 (~HB275)	~HRc28 (~HB275)	~HRc37 (~HB350)	~HRc37 (~HB350)	~HRc24 (~HB250)	~HRc24 (~HB250)	~HRc13 (~HB200)	~HRc13 (~HB200)	~HRc28 (~HB275)	~HRc19 (~HB220)	~HRc19 (~HB220)	~HRc8 (~HB180)	~HB110
Y03 *	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎
YI3 *	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○



Y03I / YI3I SERIES
Y03J / YI3J SERIES

i-DREAM DRILL INSERTS & HOLDERS

- Features of i-Dream Drill Inserts


- Secure and accurate seating resulting in accurate repeatability and concentricity.

i-Dream Drill General

- For most steel materials


i-Dream Drill INOX

- For tough, ductile materials and stainless steels
- Light, sharp cutting edge
- Minimize cutting forces
- Reduce built-up edge



- Features of i-Dream Drill Holders

- Special Alloy Steels that maintains its hardness and toughness under high temperatures with generous coolant holes for effective coolant flow.
- Innovative surface treatment that improves wear resistance and reduces corrosion.
- High Performance flute design allowing maximum chip evacuation and minimum interference.



cutting conditions : p.50~51

Series Range	Insert EDP No.		Insert O.D.		Length	Holder EDP No.	Diameter	Shank Dia.	Shank Length	Flange Dia.	Drilling Depth	Overall Length	Torx Screw No.		
	TiAIN	TiCN	h7												
	General	INOX	dec.	inch / mm											
I Ø28.00 to Ø29.99 7.7mm Thick	Y03I01	YI3I01	1.1024	28.00	3D	ZI0301	1.0748	1-1/4	2-3/8	1-15/32	3-5/16	7	TI2829		
	Y03I02	YI3I02	1.1094	1-7/64	5D	ZI0501					5-33/64	9-15/64			
	Y03I03	YI3I03	1.1220	28.50	7D	ZI0701					7-23/32	11-7/16			
	Y03I04	YI3I04	1.1250	1-1/8	3D	ZI0302	1.0945	1-1/4	2-3/8	1-15/32	3-23/64	7-1/16		TI2930	
	Y03I05	YI3I05	1.1417	29.00	5D	ZI0502					5-39/64	9-5/16			
	Y03I06	YI3I06	1.1562	1-5/32	7D	ZI0702					7-55/64	11-9/16			
	Y03I07	YI3I07	1.1614	29.50	3D	ZI0303	1.1142	1-1/4	2-3/8	1-15/32	3-27/64	7-3/16			TJ2831
	Y03I08	YI3I08	1.1719	1-11/64	5D	ZI0503					5-45/64	9-15/32			
Y03J01	YI3J01	1.1811	30.00	7D	ZI0703	7-63/64					11-3/4				
J Ø30.00 to Ø31.99 8mm Thick	Y03J01	YI3J01	1.1811	30.00	3D	ZJ0301	1.1535	1-1/4	2-3/8	1-15/32	3-35/64	7-21/64	TJ2831		
	Y03J02	YI3J02	1.1875	1-3/16	5D	ZJ0501					5-29/32	9-45/64			
	Y03J03	YI3J03	1.2008	30.50	7D	ZJ0701					8-17/64	12-1/16			
	Y03J04	YI3J04	1.2031	1-13/64	3D	ZJ0302	1.1732	1-1/4	2-3/8	1-15/32	3-39/64	7-3/8		TJ3132	
	Y03J05	YI3J05	1.2188	1-7/32	5D	ZJ05									

INCH

ISO	Material	Tensile Strength MPa	Hardness		Cutting Speed Vc [SFM]	Feed [IPR]					
			HB	HRc		Ø31/64 ~Ø37/64	Ø19/32 ~Ø45/64	Ø23/32 ~Ø55/64	Ø7/8 ~Ø1-1/16	Ø1-3/32 ~Ø1-1/4	
P	Non-alloyed steels, Cast steels Free-machining steels	~500	100-150		312-394	.006~.011	.008~.014	.011~.016	.013~.020	.015~.022	
		500-850	150-250	~24	262-344	.006~.009	.008~.014	.011~.016	.013~.020	.015~.022	
	Low-alloyed steels, Cast steels (<5%) Carbon steels	~450	85-125		295-377	.006~.010	.008~.013	.010~.015	.012~.019	.013~.020	
		450-755	125-225	~19	230-295	.005~.008	.007~.011	.009~.013	.012~.018	.013~.019	
		755-900	225-265	19-27	197-262	.005~.008	.007~.011	.009~.013	.012~.018	.013~.019	
	Alloyed steels	8620, 4130, 4137, 4140, 6150 etc	~600	125-175	~7	262-328	.006~.009	.007~.011	.009~.013	.012~.018	.013~.020
			600-800	175-235	7-22	230-295	.005~.008	.007~.011	.009~.013	.012~.018	.013~.020
		800-950	235-280	22-29	197-262	.005~.008	.006~.010	.009~.013	.012~.018	.013~.020	
		950-1110	280-330	29-35	180-230	.004~.006	.005~.008	.008~.012	.010~.015	.011~.017	
		1110-1230	330-360	35-39	148-197	.003~.005	.005~.008	.008~.012	.010~.015	.011~.017	
		600-1020	225-300	19-32	148-197	.005~.008	.006~.010	.008~.012	.008~.012	.009~.014	
	High-alloyed steels	A355, 9840, 4340 etc	1020-1200	300-355	32-38	131-180	.004~.006	.004~.007	.008~.012	.008~.012	.009~.014
1200-1330			355-390	38-42	131-164	.003~.005	.004~.006	.007~.010	.007~.011	.009~.013	
Structural steels	A36, A516, A182 etc	100-150	246-312		246-312	.006~.009	.008~.014	.011~.017	.013~.019		
		500-850	150-250	~24	197-246	.005~.008	.008~.013	.009~.013	.010~.015	.011~.017	
Tool steels	H13, H21, A2, S1 etc	850-1200	250-355	24-38	164-213	.004~.006	.007~.011	.008~.012	.008~.013	.010~.015	
		500-705	150-210	~16	164-213	.004~.006	.005~.008	.007~.010	.008~.012	.009~.014	
M	Stainless steels	450-610	135-185	~9	145-197	.004~.006	.005~.007	.006~.008	.006~.011	.007~.011	
		610-930	185-275	9-28	89-145	.003~.005	.004~.006	.004~.006	.005~.008	.006~.009	
K	Grey cast iron	500-700	150-210	~16	328-410	.006~.010	.008~.015	.011~.017	.014~.020	.016~.022	
		700-850	210-250	16-24	246-312	.004~.008	.006~.011	.008~.012	.010~.014	.011~.016	
K	Cast iron nodular	540	165	4	312-394	.005~.009	.007~.012	.008~.013	.011~.016	.013~.017	
		850	250	24	246-312	.004~.008	.006~.010	.007~.011	.010~.014	.011~.016	
K	Malleable cast iron	450	125		328-410	.005~.009	.007~.012	.008~.013	.011~.016	.013~.017	
		780	230	21	246-312	.004~.007	.006~.010	.007~.011	.010~.014	.011~.016	
N	Aluminum alloys (Wrought)	not heat treatable	65		820-1083	.0118~.0157	.0138~.0177	.0157~.0197	.0177~.0217	.0197~.0236	
		hardened	150		656-820	.0118~.0157	.0138~.0177	.0157~.0197	.0177~.0217	.0197~.0236	
	Aluminum alloys (Cast)	≤12% Si, not heat treatable	75		656-820	.0098~.0138	.0118~.0157	.0138~.0177	.0157~.0197	.0177~.0217	
	≤12% Si, hardened	90		492-722	.0098~.0138	.0118~.0157	.0138~.0177	.0157~.0197	.0177~.0217		
N	Copper alloys	Free machining (Pb>1%)	110		377-476	.006~.011	.009~.014	.011~.014	.015~.018	.016~.019	
		Brass	90		476-607	.007~.011	.009~.015	.012~.015	.015~.018	.017~.019	
N	Non ferrous material	Electrolytic copper	100		312-394	.002~.004	.004~.005	.004~.005	.006~.007	.007~.009	
		Duroplastics Fiber plastics Hard rubber									

*Formulas:

$$SFM = \frac{RPM \cdot \pi \cdot (DIA.)}{12}$$

$$IPM = (RPM) \cdot (IPR)$$

$$RPM = \frac{(SFM) \cdot 12}{(\pi) \cdot (DIA.)}$$

RPM = revolution per minute (rev/min)
SFM = surface feet per minute (ft/min)
DIA. = diameter of drill (inch)
IPR = feed rate (inch/rev)
IPM = inch per minute penetration rate

- ▶ The recommendations for speeds, feeds and other parameters presented in this chart are nominal recommendations and should be considered only as good starting points.
- ▶ Speed and feed reductions (20% reduction in speed and 10% reduction in feed) are recommended.
- ▶ Recommend you to reduce the feed rate to 85%, 70% when you use 5xD, 7xD holders.
- ▶ For use of 7xD holder, we recommend to drill a centering pre-hole with equal to or larger than 140° point angle to min. 2/3 cutting diameter.
- ▶ The use of the centering pre-hole improves hole location, roundness and surface finish.

METRIC

ISO	Material	Tensile Strength [N/mm²]	Hardness		Cutting Speed Vc [M/min]	Feed [mm/rev]					
			HB	HRc		Ø12.00 ~Ø14.99	Ø15.00 ~Ø17.99	Ø18.00 ~Ø21.99	Ø22.00 ~Ø26.99	Ø27.00 ~Ø31.99	
P	Non-alloyed steels, Cast steels Free-machining steels	~500	100-150		95-120	0.16-0.28	0.21-0.35	0.27-0.40	0.34-0.52	0.37-0.55	
		500-850	150-250	~24	80-105	0.14-0.24	0.21-0.35	0.27-0.40	0.34-0.52	0.37-0.55	
	Low-alloyed steels, Cast steels (<5%) Carbon steels	~450	85-125		90-115	0.14-0.25	0.20-0.33	0.25-0.39	0.31-0.47	0.34-0.50	
		450-755	125-225	~19	70-90	0.12-0.20	0.17-0.28	0.22-0.32	0.30-0.46	0.33-0.49	
		755-900	225-265	19-27	60-80	0.12-0.20	0.17-0.28	0.22-0.32	0.30-0.46	0.33-0.49	
	Alloyed steels	45CrMo4, 42CrMo4, 16MnCr5, Ck75, 35CrMo4, 16MnCr5 etc	~600	125-175	~7	80-100	0.14-0.24	0.17-0.28	0.22-0.32	0.30-0.46	0.34-0.50
			600-800	175-235	7-22	70-90	0.12-0.20	0.17-0.28	0.22-0.32	0.30-0.46	0.34-0.50
		800-950	235-280	22-29	60-80	0.12-0.20	0.15-0.25	0.22-0.32	0.30-0.46	0.34-0.50	
		950-1110	280-330	29-35	55-70	0.10-0.16	0.13-0.21	0.21-0.30	0.25-0.38	0.29-0.43	
		1110-1230	330-360	35-39	45-60	0.08-0.12	0.13-0.21	0.21-0.30	0.25-0.38	0.29-0.43	
		600-1020	225-300	19-32	45-60	0.12-0.20	0.15-0.25	0.21-0.30	0.20-0.31	0.24-0.35	
	High-alloyed steels	36CrNiMo4, 41CrAlMo7 etc	1020-1200	300-355	32-38	40-55	0.10-0.16	0.11-0.18	0.21-0.30	0.20-0.31	0.24-0.35
1200-1330			355-390	38-42	40-50	0.08-0.12	0.09-0.14	0.18-0.26	0.19-0.29	0.23-0.34	
Structural steels	S333, S37-2, St44-2, St52, St60 etc	350-500	100-150		75-95	0.14-0.24	0.21-0.35	0.27-0.39	0.29-0.44	0.32-0.47	
		500-850	150-250	~24	60-75	0.12-0.20	0.20-0.33	0.22-0.32	0.25-0.38	0.29-0.43	
Tool steels	102Cr6, 105WCr6, C75W etc	850-1200	250-355	24-38	50-65	0.10-0.16	0.17-0.28	0.21-0.30	0.21-0.32	0.26-0.38	
		500-705	150-210	~16	50-65	0.10-0.16	0.13-0.21	0.18-0.26	0.20-0.31	0.24-0.35	
M	Stainless steels	450-610	135-185	~9	45-60	0.10-0.16	0.12-0.18	0.14-0.20	0.15-0.26	0.18-0.28	
		610-930	185-275	9-28	30-45	0.08-0.14	0.09-0.15	0.10-0.16	0.12-0.20	0.14-0.22	
K	Grey cast iron	500-700	150-210	~16	100-125	0.15-0.26	0.20-0.37	0.27-0.42	0.36-0.51	0.40-0.55	
		700-850	210-250	16-24	75-95	0.11-0.20	0.16-0.29	0.20-0.30	0.25-0.35	0.29-0.40	
K	Cast iron nodular	540	165	4	95-120	0.13-0.22	0.17-0.31	0.21-0.32	0.28-0.40	0.32-0.44	
		850	250	24	75-95	0.11-0.20	0.14-0.26	0.19-0.29	0.25-0.35	0.29-0.40	
K	Malleable cast iron	450	125		100-125	0.13-0.22	0.17-0.31	0.21-0.32	0.28-0.40	0.32-0.44	
		780	230	21	75-95	0.11-0.18	0.14-0.26	0.19-0.29	0.25-0.35	0.29-0.40	
N	Aluminum alloys (Wrought)	not heat treatable	65		250-330	0.30-0.40	0.35-0.45	0.40-0.50	0.45-0.55	0.50-0.60	
		hardened	150		200-250	0.30-0.40	0.35-0.45	0.40-0.50	0.45-0.55	0.50-0.60	
	Aluminum alloys (Cast)	≤12% Si, not heat treatable	75		200-50	0.25-0.35	0.30-0.40	0.35-0.45	0.40-0.50	0.45-0.55	
	≤12% Si, hardened	90		150-220	0.25-0.35	0.30-0.40	0.35-0.45	0.40-0.50	0.45-0.55		
N	Copper alloys	Free machining (Pb>1%)	110		115-145	0.16-0.28	0.23-0.36	0.29-0.36	0.37-0.45	0.41-0.48	
		Brass	90		145-185	0.17-0.29	0.24-0.37	0.30-0.38	0.38-0.46	0.42-0.49	
N	Non ferrous material	Electrolytic copper	100		95-120	0.06-0.09	0.09-0.13	0.11-0.13	0.15-0.18	0.19-0.22	
		Duroplastics Fiber plastics Hard rubber									

*Formulas :

$$M/min = \frac{(RPM) \cdot \pi \cdot (DIA.)}{1000}$$

$$mm/min = (RPM) \cdot (mm/rev)$$

$$RPM = \frac{(M/min) \cdot 1000}{(\pi) \cdot (DIA.)}$$

RPM = revolution per minute (rev/min)
M/min = surface meter per minute (M/min)
DIA. = diameter of drill (mm)
mm/rev = feed rate (mm/rev)

- ▶ The recommendations for speeds, feeds and other parameters presented in this chart are nominal recommendations and should be considered only as good starting points.
- ▶ Speed and feed reductions (20% reduction in speed and 10% reduction in feed) are recommended.
- ▶ Recommend you to reduce the feed rate to 85%, 70% when you use 5xD, 7xD holders.
- ▶ For use of 7xD holder, we recommend to drill a centering pre-hole with equal to or larger than 140° point angle to min. 2/3 cutting diameter.
- ▶ The use of the centering pre-hole improves hole location, roundness and surface finish.

Assembly of *i*-Dream Drills



Make sure to clean the insert and insert seat.



Slide the drill insert into the slot of the holder and press down the insert to touch the bottom of the slot.




After confirming the insert is pressed down to the bottom of the slot, tighten the screw using anti-seize compound.


WRENCH TYPE	PRODUCT No.	T-HANDLE No.	SERIES
 WING TYPE	TWWT08	—	A
			B
			C
 TORX BIT TYPE	TWBT15	TWH600	D
	TWBT20		E, F, G
	TWBT25		H, I, J

Use the wing type or T-type wrench.
 ▶ Need to use appropriate wrenches and screws as indicated.
 ▶ It's important to tighten up the screw properly.


CAUTION-NOT RECOMMENDABLE APPLICATION




Intersecting cross hole is bigger than the drill insert's Margin Length.



Material with slanting entrance and exit over 7 degree. (If drilling 7 degree or under slanting surface, reduce the feed about 30-50 %)



For drilling stacked plates, minimize the space between the plates. The space stacked plates can cause insert breakage or poor chip control.



The material needs to be fixtured securely before drilling.


- i-DREAM DRILLS
- DREAM DRILLS -GENERAL
- DREAM DRILLS -HIGH FEED
- DREAM DRILLS -FLAT BOTTOM
- DREAM DRILLS -INOX
- DREAM DRILLS -ALU
- DREAM DRILLS -MQL TYPE
- DREAM DRILLS for HIGH HARDENED STEELS
- STANDARD CARBIDE DRILLS
- MULTI-1 DRILLS
- HPD DRILLS
- GOLD-P DRILLS
- STRAIGHT SHANK DRILLS
- AIRCRAFT DRILLS
- SILVER & DEMING DRILLS
- TAPER SHANK DRILLS
- NC SPOTTING DRILLS
- COMBINATION DRILLS & COUNTERSINK
- SPADE DRILLS
- TECHNICAL DATA

- i-DREAM DRILLS
- DREAM DRILLS -GENERAL
- DREAM DRILLS -HIGH FEED
- DREAM DRILLS -FLAT BOTTOM
- DREAM DRILLS -INOX
- DREAM DRILLS -ALU
- DREAM DRILLS -MQL TYPE
- DREAM DRILLS for HIGH HARDENED STEELS
- STANDARD CARBIDE DRILLS
- MULTI-1 DRILLS
- HPD DRILLS
- GOLD-P DRILLS
- STRAIGHT SHANK DRILLS
- AIRCRAFT DRILLS
- SILVER & DEMING DRILLS
- TAPER SHANK DRILLS
- NC SPOTTING DRILLS
- COMBINATION DRILLS & COUNTERSINK
- SPADE DRILLS
- TECHNICAL DATA











RECOMMENDED CUTTING CONDITIONS

RECOMMENDED COOLANT PRESSURE AND FLOW RATE ON VERTICAL DRILLING



- Recommended emulsion mix is 6% - 8%.
- For Drilling in Stainless and High Strength steels, a mix of 10% is recommended.
- For horizontal drilling, 30% reduction on the coolant pressure and flow rate is possible.
- Dry drilling is possible for 1-2xD drilling. But not recommended.

TROUBLE SHOOTING

 <p>1) Heavy flank wear / Fast flank wear - Reduce cutting speed - Increase feed</p>	 <p>2) Chipping on cutting edge - Reduce feed - Check the rigidity of spindle and chuck - Rigid clamping of workpiece</p>
 <p>3) Build up on cutting edge - Increase cutting speed - Use a coated insert</p>	 <p>4) Chipping or break down on outer corner - Reduce feed - Rigid clamping of workpiece</p>
 <p>5) Wear of land margin - Rigid clamping of workpiece - Reduce cutting speed - Increase coolant flow</p>	 <p>6) Unsatisfactory positioning of the hole - Rigid clamping of workpiece - Reduce feed during entrance or exit</p>
 <p>7) Scratching on holder - Rigid clamping of workpiece - Reduce feed - Increase coolant flow</p>	 <p>8) Unsatisfactory surface finish - Rigid clamping of workpiece - Increase coolant flow and pressure</p>

CARBIDE



Being the best through innovation













DREAM DRILLS -GENERAL

WITH & WITHOUT COOLANT HOLES
- General Purpose HRc30 to HRc50 Alloys

SELECTION GUIDE

SOLID CARBIDE DREAM DRILLS-GENERAL

SOLID CARBIDE DREAM DRILLS-GENERAL (with & without Coolant Holes)
General Purpose HRc30 to HRc50 Alloys



ITEM	MODEL	DESCRIPTION		SIZE		PAGE
				MIN	MAX	
INCH						
3xD DH416 DH711		CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES	SHORT	D1/8	D5/8	58
5xD DH418 DH712		CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES	LONG	D13/64	D1/2	60
3xD DH414		CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES	STUB	D1/8	D5/8	61
5xD DH722		CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES	LONG	D13/64	D1/2	62
METRIC						
3xD DH406		CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES	SHORT	D3.0	D20.0	63
5xD DH408		CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES	LONG	D1.0	D20.0	67
8xD DH421		CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES	EXTRA LONG	D3.0	D20.0	72
3xD DH404		CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES	STUB	D3.0	D20.0	76
3xD DH423		CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES	SHORT	D3.0	D20.0	78
5xD DH424		CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES	LONG	D1.0	D20.0	83
RECOMMENDED CUTTING CONDITIONS						88

◎ : Excellent ○ : Good

P			H		M	K	N			S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							

◎	◎	◎			○	○					
◎	◎	◎			○	○					
◎	◎	◎			○	○					
◎	◎	◎			○	○					

◎	◎	◎			○	○					
◎	◎	◎			○	○					
◎	◎	◎			○	○					
◎	◎	◎			○	○					
◎	◎	◎			○	○					
◎	◎	◎			○	○					






DH416 SERIES
DH711 SERIES

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES *SHORT*

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation
- ▶ Tolerance : Dia. Tolerance $\varnothing D1$: See page 57
Shank Tolerance $\varnothing D2$: -.0001 -.0005



MG h6 140° 20 bar P.88 3 × D

EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length
	Fractional	Decimal					Fractional	Decimal			
TiAIN	D1		D2	L1	L2	TiAIN	D1		D2	L1	L2
DH711008	1/8	.1250	3/16	1.102	2.992	DH711217	Q	.3320	3/8	1.673	3.937
0081BTF	1/8	.1250	15/64	1.102	2.992	0221BTF	11/32	.3438	11/32	1.772	3.937
DH711011	11/64	.1719	3/16	1.417	3.386	DH711022	11/32	.3438	3/8	1.772	3.937
0111BTF	11/64	.1719	15/64	1.417	3.386	DH711023	23/64	.3594	3/8	1.87	4.174
DH711012	3/16	.1875	3/16	1.575	3.543	0231BTF	23/64	.3594	25/64	1.870	4.174
0121BTF	3/16	.1875	15/64	1.575	3.543	DH711221	U	.3680	3/8	1.87	4.174
0131BTF	13/64	.2031	15/64	1.082	3.228	2211BTF	U	.3680	25/64	1.870	4.174
DH711013	13/64	.2031	1/4	1.082	3.228	DH711024	3/8	.3750	3/8	1.969	4.174
0141BTF	7/32	.2188	15/64	1.181	3.228	0241BTF	3/8	.3750	25/64	1.969	4.174
DH711014	7/32	.2188	1/4	1.181	3.228	0251BTF	25/64	.3906	25/64	1.969	4.174
0151BTF	15/64	.2344	15/64	1.181	3.228	DH711025	25/64	.3906	7/16	1.969	4.174
DH711015	15/64	.2344	1/4	1.181	3.228	0261BTF	13/32	.4062	27/64	2.067	4.567
0161BTF	1/4	.2500	17/64	1.279	3.465	DH711026	13/32	.4062	7/16	2.067	4.567
2061BTF	F	.2570	17/64	1.279	3.465	0271BTF	27/64	.4219	27/64	2.165	4.567
DH711206	F	.2570	5/16	1.279	3.465	DH711027	27/64	.4219	7/16	2.165	4.567
0171BTF	17/64	.2656	17/64	1.378	3.465	DH711028	7/16	.4375	7/16	2.264	4.803
DH711017	17/64	.2656	5/16	1.378	3.465	0281BTF	7/16	.4375	15/32	2.264	4.803
2091BTF	I	.2720	.2720	1.378	3.465	0291BTF	29/64	.4531	15/32	2.264	4.803
DH711209	I	.2720	5/16	1.378	3.465	DH711029	29/64	.4531	1/2	2.264	4.803
0181BTF	9/32	.2812	5/16	1.476	3.701	0301BTF	15/32	.4688	15/32	2.362	4.803
0191BTF	19/64	.2969	5/16	1.476	3.701	DH711030	15/32	.4688	1/2	2.362	4.803
0201BTF	5/16	.3125	5/16	1.575	3.701	0311BTF	31/64	.4844	1/2	2.461	5.039
0211BTF	21/64	.3281	11/32	1.673	3.937	0321BTF	1/2	.5000	1/2	2.559	5.039
DH711021	21/64	.3281	3/8	1.673	3.937	0331BTF	33/64	.5156	35/64	2.657	5.276
2171BTF	Q	.3320	11/32	1.673	3.937	DH711033	33/64	.5156	9/16	2.657	5.276
						0341BTF	17/32	.5312	35/64	2.756	5.276

▶ Other shank types are available on your request. ▶ NEXT PAGE


P					H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~								
◎	◎	◎			○	○						



DH416 SERIES
DH711 SERIES

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES *SHORT*

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation
- ▶ Tolerance : Dia. Tolerance $\varnothing D1$: See page 57
Shank Tolerance $\varnothing D2$: -.0001 -.0005



MG h6 140° 20 bar P.88 3 × D

EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length
	Fractional	Decimal					Fractional	Decimal			
TiAIN	D1		D2	L1	L2	TiAIN	D1		D2	L1	L2
DH711034	17/32	.5312	9/16	2.756	5.276	0371BTF	37/64	.5781	37/64	2.953	5.512
0351BTF	35/64	.5469	35/64	2.756	5.276	DH711037	37/64	.5781	5/8	2.953	5.512
DH711035	35/64	.5469	9/16	2.756	5.276	0381BTF	19/32	.5937	5/8	3.051	5.709
DH711036	9/16	.5625	9/16	2.854	5.512	0391BTF	39/64	.6094	5/8	3.051	5.709
0361BTF	9/16	.5625	37/64	2.854	5.512	0401BTF	5/8	.6250	5/8	3.150	5.709

▶ Other shank types are available on your request.


P					H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~								
◎	◎	◎			○	○						



DH418 SERIES
DH712 SERIES

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES LONG

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation
- ▶ Tolerance : Dia. Tolerance ØD1 : See page 57
Shank Tolerance ØD2: -.0001 -.0005



MG h6 140° 20 bar P.88 5 × D

EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length
	Fractional	Decimal					Fractional	Decimal			
TiAlN	D1		D2	L1	L2	TiAlN	D1		D2	L1	L2
0131CTF	13/64	.2031	15/64	1-3/4	3-15/16	DH712022	11/32	.3438	3/8	2-27/32	5
DH712013	13/64	.2031	1/4	1-3/4	3-15/16	DH712023	23/64	.3594	3/8	3	5-23/64
0141CTF	7/32	.2188	15/64	1-57/64	3-15/16	0231CTF	23/64	.3594	25/64	3	5-23/64
DH712014	7/32	.2188	1/4	1-57/64	3-15/16	DH712221	U	.3680	3/8	3	5-23/64
0151CTF	15/64	.2344	15/64	1-57/64	3-15/16	2211CTF	U	.3680	25/64	3	5-23/64
DH712015	15/64	.2344	1/4	1-57/64	3-15/16	DH712024	3/8	.3750	3/8	3-5/32	5-23/64
DH712016	1/4	.2500	1/4	2-3/64	4-19/64	0241CTF	3/8	.3750	25/64	3-5/32	5-23/64
0161CTF	1/4	.2500	17/64	2-3/64	4-19/64	0251CTF	25/64	.3906	25/64	3-5/32	5-23/64
2061CTF	F	.2570	17/64	2-13/64	4-19/64	DH712025	25/64	.3906	7/16	3-5/32	5-23/64
DH712206	F	.2570	5/16	2-13/64	4-19/64	0261CTF	13/32	.4062	27/64	3-5/16	5-7/8
0171CTF	17/64	.2656	17/64	2-13/64	4-19/64	DH712026	13/32	.4062	7/16	3-5/16	5-7/8
DH712017	17/64	.2656	5/16	2-13/64	4-19/64	0271CTF	27/64	.4219	27/64	3-15/32	5-7/8
2091CTF	I	.2720	.2720	2-13/64	4-19/64	DH712027	27/64	.4219	7/16	3-15/32	5-7/8
DH712209	I	.2720	5/16	2-13/64	4-19/64	DH712028	7/16	.4375	7/16	3-5/8	6-7/32
0181CTF	9/32	.2812	5/16	2-23/64	4-41/64	0281CTF	7/16	.4375	15/32	3-5/8	6-7/32
0191CTF	19/64	.2969	5/16	2-33/64	4-41/64	0291CTF	29/64	.4531	15/32	3-25/32	6-7/32
0201CTF	5/16	.3125	5/16	2-33/64	4-41/64	DH712029	29/64	.4531	1/2	3-25/32	6-7/32
0211CTF	21/64	.3281	11/32	2-43/64	5	0301CTF	15/32	.4688	15/32	3-25/32	6-7/32
DH712021	21/64	.3281	3/8	2-43/64	5	DH712030	15/32	.4688	1/2	3-25/32	6-7/32
2171CTF	Q	.3320	11/32	2-43/64	5	0311CTF	31/64	.4844	1/2	3-15/16	6-37/64
DH712217	Q	.3320	3/8	2-43/64	5	0321CTF	1/2	.5000	1/2	4-3/32	6-37/64
0221CTF	11/32	.3438	11/32	2-27/32	5						

▶ Other shank types are available on your request.

© : Excellent ○ : Good


P			H		M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~							
◎	◎	◎			○	○					



DH414 SERIES

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES STUB

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation
- ▶ Tolerance : Dia. Tolerance ØD1 : See page 57
Shank Tolerance ØD2: -.0001 -.0005



MG h6 140° P.88 D1=D2 3 × D

EDP No.	Drill Diameter		Flute Length	Overall Length	EDP No.	Drill Diameter		Flute Length	Overall Length
	Fractional	Decimal				Fractional	Decimal		
TiAlN	D1 = D2		L1	L2	TiAlN	D1 = D2		L1	L2
0081ATF	1/8	.1250	45/64	1-59/64	0221ATF	11/32	.3438	2-3/16	3-7/8
0091ATF	9/64	.1406	25/32	2-3/64	0231ATF	23/64	.3594	2-9/32	4
0101ATF	5/32	.1562	7/8	2-3/16	2211ATF	U	.3680	2-9/32	4
0111ATF	11/64	.1719	15/16	2-9/32	0241ATF	3/8	.3750	2-3/8	4-1/8
0121ATF	3/16	.1875	1	2-7/16	0251ATF	25/64	.3906	2-3/8	4-1/8
0131ATF	13/64	.2031	1	2-7/16	0261ATF	13/32	.4062	2-5/8	4-13/32
0141ATF	7/32	.2188	1-1/8	2-5/8	0271ATF	27/64	.4219	2-11/16	4-1/2
0151ATF	15/64	.2344	1-1/8	2-5/8	0281ATF	7/16	.4375	2-13/16	4-5/8
0161ATF	1/4	.2500	1-5/8	3-3/16	0291ATF	29/64	.4531	2-7/8	4-3/4
2061ATF	F	.2570	1-11/16	3-17/64	0301ATF	15/32	.4688	2-7/8	4-3/4
0171ATF	17/64	.2656	1-11/16	3-17/64	0311ATF	31/64	.4844	3	5-5/16
2091ATF	I	.2720	1-11/16	3-17/64	0321ATF	1/2	.5000	3-1/16	5-3/8
0181ATF	9/32	.2812	1-3/4	3-7/16	0331ATF	33/64	.5156	3-11/32	5-11/16
0191ATF	19/64	.2969	1-7/8	3-9/16	0341ATF	17/32	.5312	3-11/32	5-11/16
0201ATF	5/16	.3125	1-7/8	3-9/16	0361ATF	9/16	.5625	3-1/2	5-15/16
0211ATF	21/64	.3281	2-1/16	3-3/4	0371ATF	37/64	.5781	3-37/64	6
2171ATF	Q	.3320	2-1/16	3-3/4	0401ATF	5/8	.6250	3-25/32	6-19/64


▶ Other shank types are available on your request.

© : Excellent ○ : Good

P			H		M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~							
◎	◎	◎			○	○					

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES LONG

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation
- ▶ Tolerance : Dia. Tolerance ØD1 : See page 57
Shank Tolerance ØD2: -.0001 -.0005



MG h6 140° P.88 5 × D

Unit : inch

EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length
	Fractional	Decimal					Fractional	Decimal			
TiAIN	D1		D2	L1	L2	TiAIN	D1		D2	L1	L2
DH722013	13/64	.2031	1/4	1-3/4	3-15/16	DH722022	11/32	.3438	3/8	2-27/32	5
DH722014	7/32	.2188	1/4	1-57/64	3-15/16	DH722023	23/64	.3594	3/8	3	5-23/64
DH722015	15/64	.2344	1/4	1-57/64	3-15/16	DH722221	U	.3680	3/8	3	5-23/64
DH722016	1/4	.2500	1/4	2-3/64	4-19/64	DH722024	3/8	.3750	3/8	3-5/32	5-23/64
DH722206	F	.2570	5/16	2-13/64	4-19/64	DH722025	25/64	.3906	7/16	3-5/32	5-23/64
DH722017	17/64	.2656	5/16	2-13/64	4-19/64	DH722026	13/32	.4062	7/16	3-5/16	5-7/8
DH722209	I	.2720	5/16	2-13/64	4-19/64	DH722027	27/64	.4219	7/16	3-15/32	5-7/8
DH722018	9/32	.2812	5/16	2-23/64	4-41/64	DH722028	7/16	.4375	7/16	3-5/8	6-7/32
DH722019	19/64	.2969	5/16	2-33/64	4-41/64	DH722029	29/64	.4531	1/2	3-25/32	6-7/32
DH722020	5/16	.3125	5/16	2-33/64	4-41/64	DH722030	15/32	.4688	1/2	3-25/32	6-7/32
DH722021	21/64	.3281	3/8	2-43/64	5	DH722031	31/64	.4844	1/2	3-15/16	6-37/64
DH722217	Q	.3320	3/8	2-43/64	5	DH722032	1/2	.5000	1/2	4-3/32	6-37/64


▶ Other shank types are available on your request.

◎ : Excellent ○ : Good

P			H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55 HRc55~							
◎	◎	◎		○	○					

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES SHORT

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537 MG h6 m7 140° 20 bar P.89 3 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH406030	3.0		.1181	6	20	62	DH406051	5.1		.2008	6	28	66
DH406031	3.1		.1220	6	20	62	DH406013F	5.159	13/64	.2031	6	28	66
DH406008F	3.175	1/8	.1250	6	20	62	DH406052	5.2		.2047	6	28	66
DH406032	3.2		.1260	6	20	62	DH406053	5.3		.2087	6	28	66
DH406033	3.3		.1299	6	20	62	DH406054	5.4		.2126	6	28	66
DH406034	3.4		.1339	6	20	62	DH406055	5.5		.2165	6	28	66
DH406035	3.5		.1378	6	20	62	DH406014F	5.556	7/32	.2188	6	28	66
DH406009F	3.572	9/64	.1406	6	20	62	DH406056	5.6		.2205	6	28	66
DH406036	3.6		.1417	6	20	62	DH406057	5.7		.2244	6	28	66
DH406037	3.7		.1457	6	20	62	DH406058	5.8		.2283	6	28	66
DH406038	3.8		.1496	6	24	66	DH406059	5.9		.2323	6	28	66
DH406039	3.9		.1535	6	24	66	DH406015F	5.953	15/64	.2344	6	28	66
DH406010F	3.969	5/32	.1563	6	24	66	DH406060	6.0		.2362	6	28	66
DH406040	4.0		.1575	6	24	66	DH406061	6.1		.2402	8	34	79
DH406041	4.1		.1614	6	24	66	DH406062	6.2		.2441	8	34	79
DH406042	4.2		.1654	6	24	66	DH406063	6.3		.2480	8	34	79
DH406043	4.3		.1693	6	24	66	DH406016F	6.350	1/4	.2500	8	34	79
DH406011F	4.366	11/64	.1719	6	24	66	DH406064	6.4		.2520	8	34	79
DH406044	4.4		.1732	6	24	66	DH406065	6.5		.2559	8	34	79
DH406045	4.5		.1772	6	24	66	DH406006L	6.528	F	.2570	8	34	79
DH406046	4.6		.1811	6	24	66	DH406066	6.6		.2598	8	34	79
DH406047	4.7		.1850	6	24	66	DH406067	6.7		.2638	8	34	79
DH406012F	4.763	3/16	.1875	6	24	66	DH406017F	6.747	17/64	.2656	8	34	79
DH406048	4.8		.1890	6	28	66	DH406068	6.8		.2677	8	34	79
DH406049	4.9		.1929	6	28	66	DH406069	6.9		.2717	8	34	79
DH406050	5.0		.1969	6	28	66	DH406009L	6.909	I	.2720	8	34	79

▶ Other shank types are available on your request.


▶ NEXT PAGE

◎ : Excellent ○ : Good

P			H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55 HRc55~							
◎	◎	◎		○	○					

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES SHORT

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537 MG h6 m7 140° 20 bar P.89 3 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH406070	7.0		.2756	8	34	79	DH406090	9.0		.3543	10	47	89
DH406071	7.1		.2795	8	41	79	DH406091	9.1		.3583	10	47	89
DH406018F	7.144	9/32	.2812	8	41	79	DH406023F	9.128	23/64	.3594	10	47	89
DH406072	7.2		.2835	8	41	79	DH406092	9.2		.3622	10	47	89
DH406073	7.3		.2874	8	41	79	DH406093	9.3		.3661	10	47	89
DH406074	7.4		.2913	8	41	79	DH406021L	9.347	U	.3680	10	47	89
DH406075	7.5		.2953	8	41	79	DH406094	9.4		.3701	10	47	89
DH406019F	7.541	19/64	.2969	8	41	79	DH406095	9.5		.3740	10	47	89
DH406076	7.6		.2992	8	41	79	DH406024F	9.525	3/8	.3750	10	47	89
DH406077	7.7		.3031	8	41	79	DH406096	9.6		.3780	10	47	89
DH406078	7.8		.3071	8	41	79	DH406097	9.7		.3819	10	47	89
DH406079	7.9		.3110	8	41	79	DH406098	9.8		.3858	10	47	89
DH406020F	7.938	5/16	.3125	8	41	79	DH406099	9.9		.3898	10	47	89
DH406080	8.0		.3150	8	41	79	DH406025F	9.922	25/64	.3906	10	47	89
DH406081	8.1		.3189	10	47	89	DH406100	10.0		.3937	10	47	89
DH406082	8.2		.3228	10	47	89	DH406101	10.1		.3976	12	55	102
DH406083	8.3		.3268	10	47	89	DH406102	10.2		.4016	12	55	102
DH406021F	8.334	21/64	.3281	10	47	89	DH406103	10.3		.4055	12	55	102
DH406084	8.4		.3307	10	47	89	DH406026F	10.319	13/32	.4062	12	55	102
DH406017L	8.433	Q	.3320	10	47	89	DH406104	10.4		.4094	12	55	102
DH406085	8.5		.3346	10	47	89	DH406105	10.5		.4134	12	55	102
DH406086	8.6		.3386	10	47	89	DH406106	10.6		.4173	12	55	102
DH406087	8.7		.3425	10	47	89	DH406107	10.7		.4212	12	55	102
DH406022F	8.731	11/32	.3438	10	47	89	DH406027F	10.716	27/64	.4219	12	55	102
DH406088	8.8		.3465	10	47	89	DH406108	10.8		.4252	12	55	102
DH406089	8.9		.3504	10	47	89	DH406109	10.9		.4291	12	55	102

▶ Other shank types are available on your request.


▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES SHORT

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537 MG h6 m7 140° 20 bar P.89 3 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH406110	11.0		.4330	12	55	102	DH406132	13.2		.5197	14	60	107
DH406111	11.1		.4370	12	55	102	DH406133	13.3		.5236	14	60	107
DH406028F	11.113	7/16	.4375	12	55	102	DH406134	13.4		.5276	14	60	107
DH406112	11.2		.4409	12	55	102	DH406135	13.5		.5314	14	60	107
DH406113	11.3		.4448	12	55	102	DH406136	13.6		.5354	14	60	107
DH406114	11.4		.4488	12	55	102	DH406137	13.7		.5394	14	60	107
DH406115	11.5		.4527	12	55	102	DH406138	13.8		.5433	14	60	107
DH406029F	11.509	29/64	.4531	12	55	102	DH406139	13.9		.5472	14	60	107
DH406116	11.6		.4566	12	55	102	DH406140	14.0		.5512	14	60	107
DH406117	11.7		.4606	12	55	102	DH406141	14.1		.5551	16	65	115
DH406118	11.8		.4645	12	55	102	DH406142	14.2		.5591	16	65	115
DH406119	11.9		.4685	12	55	102	DH406036F	14.288	9/16	.5625	16	65	115
DH406030F	11.906	15/32	.4688	12	55	102	DH406143	14.3		.5630	16	65	115
DH406120	12.0		.4724	12	55	102	DH406144	14.4		.5669	16	65	115
DH406121	12.1		.4764	14	60	107	DH406145	14.5		.5708	16	65	115
DH406122	12.2		.4803	14	60	107	DH406146	14.6		.5748	16	65	115
DH406123	12.3		.4843	14	60	107	DH406147	14.7		.5787	16	65	115
DH406031F	12.303	31/64	.4844	14	60	107	DH406148	14.8		.5827	16	65	115
DH406124	12.4		.4882	14	60	107	DH406149	14.9		.5866	16	65	115
DH406125	12.5		.4921	14	60	107	DH406150	15.0		.5905	16	65	115
DH406126	12.6		.4961	14	60	107	DH406151	15.1		.5945	16	65	115
DH406032F	12.7	1/2	.5000	14	60	107	DH406152	15.2		.5984	16	65	115
DH406128	12.8		.5039	14	60	107	DH406153	15.3		.6024	16	65	115
DH406129	12.9		.5079	14	60	107	DH406154	15.4		.6063	16	65	115
DH406130	13.0		.5118	14	60	107	DH406155	15.5		.6102	16	65	115
DH406131	13.1		.5157	14	60	107	DH406156	15.6		.6142	16	65	115

▶ Other shank types are available on your request.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					



DH406 SERIES

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES SHORT

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537 MG h6 m7 140° 20 bar P.89 3 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH406157	15.7		.6181	16	65	115	DH406179	17.9		.7047	18	73	123
DH406158	15.8		.6220	16	65	115	DH406180	18.0		.7087	18	73	123
DH406040F	15.875	5/8	.6250	16	65	115	DH406181	18.1		.7126	20	79	131
DH406159	15.9		.6260	16	65	115	DH406182	18.2		.7165	20	79	131
DH406160	16.0		.6299	16	65	115	DH406183	18.3		.7205	20	79	131
DH406161	16.1		.6339	18	73	123	DH406184	18.4		.7244	20	79	131
DH406162	16.2		.6378	18	73	123	DH406185	18.5		.7283	20	79	131
DH406163	16.3		.6417	18	73	123	DH406186	18.6		.7323	20	79	131
DH406164	16.4		.6457	18	73	123	DH406187	18.7		.7362	20	79	131
DH406165	16.5		.6495	18	73	123	DH406188	18.8		.7402	20	79	131
DH406166	16.6		.6535	18	73	123	DH406189	18.9		.7441	20	79	131
DH406167	16.7		.6575	18	73	123	DH406190	19.0		.7480	20	79	131
DH406168	16.8		.6614	18	73	123	DH406048F	19.050	3/4	.7500	20	79	131
DH406169	16.9		.6654	18	73	123	DH406191	19.1		.7520	20	79	131
DH406170	17.0		.6692	18	73	123	DH406192	19.2		.7559	20	79	131
DH406171	17.1		.6732	18	73	123	DH406193	19.3		.7598	20	79	131
DH406172	17.2		.6772	18	73	123	DH406194	19.4		.7638	20	79	131
DH406173	17.3		.6811	18	73	123	DH406195	19.5		.7676	20	79	131
DH406174	17.4		.6850	18	73	123	DH406196	19.6		.7717	20	79	131
DH406044F	17.463	11/16	.6875	18	73	123	DH406197	19.7		.7756	20	79	131
DH406175	17.5		.6889	18	73	123	DH406198	19.8		.7795	20	79	131
DH406176	17.6		.6929	18	73	123	DH406199	19.9		.7835	20	79	131
DH406177	17.7		.6968	18	73	123	DH406200	20.0		.7874	20	79	131
DH406178	17.8		.7008	18	73	123							

▶ Other shank types are available on your request.

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					



DH408 SERIES

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES LONG

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537 MG h6 m7 140° 20 bar P.89 5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH408010	1.0		.0394	3	8	55	DH408008F	3.175	1/8	.1250	6	28	66
DH408011	1.1		.0433	3	12	55	DH408032	3.2		.1260	6	28	66
DH408012	1.2		.0472	3	12	55	DH408033	3.3		.1299	6	28	66
DH408013	1.3		.0512	3	12	55	DH408034	3.4		.1339	6	28	66
DH408014	1.4		.0551	3	12	55	DH408035	3.5		.1378	6	28	66
DH408015	1.5		.0591	3	16	55	DH408009F	3.572	9/64	.1406	6	28	66
DH408004F	1.588	1/16	.0625	3	16	55	DH408036	3.6		.1417	6	28	66
DH408016	1.6		.0630	3	16	55	DH408037	3.7		.1457	6	28	66
DH408017	1.7		.0669	3	16	55	DH408038	3.8		.1496	6	36	74
DH408018	1.8		.0709	3	16	55	DH408039	3.9		.1535	6	36	74
DH408019	1.9		.0748	3	16	55	DH408010F	3.969	5/32	.1563	6	36	74
DH408005F	1.984	5/64	.0781	3	16	55	DH408040	4.0		.1575	6	36	74
DH408020	2.0		.0787	4	21	57	DH408041	4.1		.1614	6	36	74
DH408021	2.1		.0827	4	21	57	DH408042	4.2		.1654	6	36	74
DH408022	2.2		.0866	4	21	57	DH408043	4.3		.1693	6	36	74
DH408023	2.3		.0906	4	21	57	DH408011F	4.366	11/64	.1719	6	36	74
DH408006F	2.381	3/32	.0938	4	21	57	DH408044	4.4		.1732	6	36	74
DH408024	2.4		.0945	4	21	57	DH408045	4.5		.1772	6	36	74
DH408025	2.5		.0984	4	21	57	DH408046	4.6		.1811	6	36	74
DH408026	2.6		.1024	4	21	57	DH408047	4.7		.1850	6	36	74
DH408027	2.7		.1063	4	21	57	DH408012F	4.763	3/16	.1875	6	36	74
DH408007F	2.778	7/64	.1094	4	21	57	DH408048	4.8		.1890	6	44	82
DH408028	2.8		.1102	4	21	57	DH408049	4.9		.1929	6	44	82
DH408029	2.9		.1142	4	21	57	DH408050	5.0		.1969	6	44	82
DH408030	3.0		.1181	6	28	66	DH408051	5.1		.2008	6	44	82
DH408031	3.1		.1220	6	28	66	DH408013F	5.159	13/64	.2031	6	44	82

▶ Other shank types are available on your request.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					



DH408 SERIES

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES LONG

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537 MG h6 m7 140° 20 bar P.89 5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH408052	5.2		.2047	6	44	82	DH408018F	7.144	9/32	.2812	8	53	91
DH408053	5.3		.2087	6	44	82	DH408072	7.2		.2835	8	53	91
DH408054	5.4		.2126	6	44	82	DH408073	7.3		.2874	8	53	91
DH408055	5.5		.2165	6	44	82	DH408074	7.4		.2913	8	53	91
DH408014F	5.556	7/32	.2188	6	44	82	DH408075	7.5		.2953	8	53	91
DH408056	5.6		.2205	6	44	82	DH408019F	7.541	19/64	.2969	8	53	91
DH408057	5.7		.2244	6	44	82	DH408076	7.6		.2992	8	53	91
DH408058	5.8		.2283	6	44	82	DH408077	7.7		.3031	8	53	91
DH408059	5.9		.2323	6	44	82	DH408078	7.8		.3071	8	53	91
DH408015F	5.953	15/64	.2344	6	44	82	DH408079	7.9		.3110	8	53	91
DH408060	6.0		.2362	6	44	82	DH408020F	7.938	5/16	.3125	8	53	91
DH408061	6.1		.2402	8	53	91	DH408080	8.0		.3150	8	53	91
DH408062	6.2		.2441	8	53	91	DH408081	8.1		.3189	10	61	103
DH408063	6.3		.2480	8	53	91	DH408082	8.2		.3228	10	61	103
DH408016F	6.350	1/4	.2500	8	53	91	DH408083	8.3		.3268	10	61	103
DH408064	6.4		.2520	8	53	91	DH408021F	8.334	21/64	.3281	10	61	103
DH408065	6.5		.2559	8	53	91	DH408084	8.4		.3307	10	61	103
DH408006L	6.528	F	.2570	8	53	91	DH408017L	8.433	Q	.3320	10	61	103
DH408066	6.6		.2598	8	53	91	DH408085	8.5		.3346	10	61	103
DH408067	6.7		.2638	8	53	91	DH408086	8.6		.3386	10	61	103
DH408017F	6.747	17/64	.2656	8	53	91	DH408087	8.7		.3425	10	61	103
DH408068	6.8		.2677	8	53	91	DH408022F	8.731	11/32	.3438	10	61	103
DH408069	6.9		.2717	8	53	91	DH408088	8.8		.3465	10	61	103
DH408009L	6.909	I	.2720	8	53	91	DH408089	8.9		.3504	10	61	103
DH408070	7.0		.2756	8	53	91	DH408090	9.0		.3543	10	61	103
DH408071	7.1		.2795	8	53	91	DH408091	9.1		.3583	10	61	103

▶ Other shank types are available on your request.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					



DH408 SERIES

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES LONG

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537 MG h6 m7 140° 20 bar P.89 5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH408023F	9.128	23/64	.3594	10	61	103	DH408028F	11.113	7/16	.4375	12	71	118
DH408092	9.2		.3622	10	61	103	DH408112	11.2		.4409	12	71	118
DH408093	9.3		.3661	10	61	103	DH408113	11.3		.4448	12	71	118
DH408021L	9.347	U	.3680	10	61	103	DH408114	11.4		.4488	12	71	118
DH408094	9.4		.3701	10	61	103	DH408115	11.5		.4527	12	71	118
DH408095	9.5		.3740	10	61	103	DH408029F	11.509	29/64	.4531	12	71	118
DH408024F	9.525	3/8	.3750	10	61	103	DH408116	11.6		.4566	12	71	118
DH408096	9.6		.3780	10	61	103	DH408117	11.7		.4606	12	71	118
DH408097	9.7		.3819	10	61	103	DH408118	11.8		.4645	12	71	118
DH408098	9.8		.3858	10	61	103	DH408119	11.9		.4685	12	71	118
DH408099	9.9		.3898	10	61	103	DH408030F	11.906	15/32	.4688	12	71	118
DH408025F	9.922	25/64	.3906	10	61	103	DH408120	12.0		.4724	12	71	118
DH408100	10.0		.3937	10	61	103	DH408121	12.1		.4764	14	77	124
DH408101	10.1		.3976	12	71	118	DH408122	12.2		.4803	14	77	124
DH408102	10.2		.4016	12	71	118	DH408123	12.3		.4843	14	77	124
DH408103	10.3		.4055	12	71	118	DH408031F	12.303	31/64	.4844	14	77	124
DH408026F	10.319	13/32	.4062	12	71	118	DH408124	12.4		.4882	14	77	124
DH408104	10.4		.4094	12	71	118	DH408125	12.5		.4921	14	77	124
DH408105	10.5		.4134	12	71	118	DH408126	12.6		.4961	14	77	124
DH408106	10.6		.4173	12	71	118	DH408032F	12.7	1/2	.5000	14	77	124
DH408107	10.7		.4212	12	71	118	DH408128	12.8		.5039	14	77	124
DH408027F	10.716	27/64	.4219	12	71	118	DH408129	12.9		.5079	14	77	124
DH408108	10.8		.4252	12	71	118	DH408130	13.0		.5118	14	77	124
DH408109	10.9		.4291	12	71	118	DH408131	13.1		.5157	14	77	124
DH408110	11.0		.4330	12	71	118	DH408132	13.2		.5197	14	77	124
DH408111	11.1		.4370	12	71	118	DH408133	13.3		.5236	14	77	124

▶ Other shank types are available on your request.


▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES LONG

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537 MG h6 m7 140° 20 bar P.89 5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH408134	13.4		.5276	14	77	124	DH408040F	15.875	5/8	.6250	16	83	133
DH408135	13.5		.5314	14	77	124	DH408159	15.9		.6260	16	83	133
DH408136	13.6		.5354	14	77	124	DH408160	16.0		.6299	16	83	133
DH408137	13.7		.5394	14	77	124	DH408161	16.1		.6339	18	93	143
DH408138	13.8		.5433	14	77	124	DH408162	16.2		.6378	18	93	143
DH408139	13.9		.5472	14	77	124	DH408163	16.3		.6417	18	93	143
DH408140	14.0		.5512	14	77	124	DH408164	16.4		.6457	18	93	143
DH408141	14.1		.5551	16	83	133	DH408165	16.5		.6495	18	93	143
DH408142	14.2		.5591	16	83	133	DH408166	16.6		.6535	18	93	143
DH408036F	14.288	9/16	.5625	16	83	133	DH408167	16.7		.6575	18	93	143
DH408143	14.3		.5630	16	83	133	DH408168	16.8		.6614	18	93	143
DH408144	14.4		.5669	16	83	133	DH408169	16.9		.6654	18	93	143
DH408145	14.5		.5708	16	83	133	DH408170	17.0		.6692	18	93	143
DH408146	14.6		.5748	16	83	133	DH408171	17.1		.6732	18	93	143
DH408147	14.7		.5787	16	83	133	DH408172	17.2		.6772	18	93	143
DH408148	14.8		.5827	16	83	133	DH408173	17.3		.6811	18	93	143
DH408149	14.9		.5866	16	83	133	DH408174	17.4		.6850	18	93	143
DH408150	15.0		.5905	16	83	133	DH408175	17.5		.6889	18	93	143
DH408151	15.1		.5945	16	83	133	DH408176	17.6		.6929	18	93	143
DH408152	15.2		.5984	16	83	133	DH408177	17.7		.6968	18	93	143
DH408153	15.3		.6024	16	83	133	DH408178	17.8		.7008	18	93	143
DH408154	15.4		.6063	16	83	133	DH408179	17.9		.7047	18	93	143
DH408155	15.5		.6102	16	83	133	DH408180	18.0		.7087	18	93	143
DH408156	15.6		.6142	16	83	133	DH408181	18.1		.7126	20	101	153
DH408157	15.7		.6181	16	83	133	DH408182	18.2		.7165	20	101	151
DH408158	15.8		.6220	16	83	133	DH408183	18.3		.7205	20	101	151


▶ Other shank types are available on your request. ▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES LONG

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537 MG h6 m7 140° 20 bar P.89 5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH408184	18.4		.7244	20	101	153	DH408192	19.2		.7559	20	101	151
DH408185	18.5		.7283	20	101	153	DH408193	19.3		.7598	20	101	151
DH408186	18.6		.7323	20	101	151	DH408194	19.4		.7638	20	101	151
DH408187	18.7		.7362	20	101	153	DH408195	19.5		.7676	20	101	153
DH408188	18.8		.7402	20	101	153	DH408196	19.6		.7717	20	101	151
DH408189	18.9		.7441	20	101	153	DH408197	19.7		.7756	20	101	151
DH408190	19.0		.7480	20	101	153	DH408198	19.8		.7795	20	101	153
DH408048F	19.050	3/4	.7500	20	101	153	DH408199	19.9		.7835	20	101	151
DH408191	19.1		.7520	20	101	151	DH408200	20.0		.7874	20	101	153

▶ Other shank types are available on your request.

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					



DH421 SERIES

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES EXTRA LONG

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537 MG h6 m7 140° 20 bar P.89 8 x D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH421030	3.0		.1181	6	34	72	DH421049	4.9		.1929	6	57	95
DH421031	3.1		.1220	6	34	72	DH421050	5.0		.1969	6	57	95
DH421008F	3.175	1/8	.1250	6	34	72	DH421051	5.1		.2008	6	57	95
DH421032	3.2		.1260	6	34	72	DH421013F	5.159	13/64	.2031	6	57	95
DH421033	3.3		.1299	6	34	72	DH421052	5.2		.2047	6	57	95
DH421034	3.4		.1339	6	34	72	DH421053	5.3		.2087	6	57	95
DH421229G	3.450	#29	.1360	6	34	72	DH421054	5.4		.2126	6	57	95
DH421035	3.5		.1378	6	34	72	DH421055	5.5		.2165	6	57	95
DH421009F	3.572	9/64	.1406	6	34	72	DH421014F	5.556	7/32	.2188	6	57	95
DH421036	3.6		.1417	6	34	72	DH421056	5.6		.2205	6	57	95
DH421037	3.7		.1457	6	34	72	DH421057	5.7		.2244	6	57	95
DH421038	3.8		.1496	6	43	81	DH421058	5.8		.2283	6	57	95
DH421039	3.9		.1535	6	43	81	DH421059	5.9		.2323	6	57	95
DH421010F	3.969	5/32	.1563	6	43	81	DH421015F	5.953	15/64	.2344	6	57	95
DH421040	4.0		.1575	6	43	81	DH421060	6.0		.2362	6	57	95
DH421221G	4.040	#21	.1590	6	43	81	DH421061	6.1		.2402	8	76	114
DH421041	4.1		.1614	6	43	81	DH421062	6.2		.2441	8	76	114
DH421042	4.2		.1654	6	43	81	DH421063	6.3		.2480	8	76	114
DH421043	4.3		.1693	6	43	81	DH421016F	6.350	1/4	.2500	8	76	114
DH421011F	4.366	11/64	.1719	6	43	81	DH421064	6.4		.2520	8	76	114
DH421044	4.4		.1732	6	43	81	DH421065	6.5		.2559	8	76	114
DH421045	4.5		.1772	6	43	81	DH421106L	6.528	F	.2570	8	76	114
DH421046	4.6		.1811	6	43	81	DH421066	6.6		.2598	8	76	114
DH421047	4.7		.1850	6	43	81	DH421067	6.7		.2638	8	76	114
DH421012F	4.763	3/16	.1875	6	57	95	DH421017F	6.747	17/64	.2656	8	76	114
DH421048	4.8		.1890	6	57	95	DH421068	6.8		.2677	8	76	114

▶ Other shank types are available on your request. ▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~							
◎	◎	◎			○	○					



DH421 SERIES

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES EXTRA LONG

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537 MG h6 m7 140° 20 bar P.89 8 x D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH421069	6.9		.2717	8	76	114	DH421088	8.8		.3465	10	95	142
DH421009L	6.909	I	.2720	8	76	114	DH421089	8.9		.3504	10	95	142
DH421070	7.0		.2756	8	76	114	DH421090	9.0		.3543	10	95	142
DH421071	7.1		.2795	8	76	114	DH421091	9.1		.3583	10	95	142
DH421018F	7.144	9/32	.2813	8	76	114	DH421023F	9.128	23/64	.3594	10	95	142
DH421072	7.2		.2835	8	76	114	DH421092	9.2		.3622	10	95	142
DH421073	7.3		.2874	8	76	114	DH421093	9.3		.3661	10	95	142
DH421074	7.4		.2913	8	76	114	DH421121L	9.350	U	.3680	10	95	142
DH421075	7.5		.2953	8	76	114	DH421094	9.4		.3701	10	95	142
DH421019F	7.541	19/64	.2969	8	76	114	DH421095	9.5		.3740	10	95	142
DH421076	7.6		.2992	8	76	114	DH421024F	9.525	3/8	.3750	10	95	142
DH421077	7.7		.3031	8	76	114	DH421096	9.6		.3780	10	95	142
DH421078	7.8		.3071	8	76	114	DH421097	9.7		.3819	10	95	142
DH421079	7.9		.3110	8	76	114	DH421098	9.8		.3858	10	95	142
DH421020F	7.938	5/16	.3125	8	76	114	DH421099	9.9		.3898	10	95	142
DH421080	8.0		.3150	8	76	114	DH421025F	9.922	25/64	.3906	10	95	142
DH421081	8.1		.3189	10	95	142	DH421100	10.0		.3937	10	95	142
DH421082	8.2		.3228	10	95	142	DH421101	10.1		.3976	12	114	162
DH421083	8.3		.3268	10	95	142	DH421102	10.2		.4016	12	114	162
DH421021F	8.334	21/64	.3281	10	95	142	DH421103	10.3		.4055	12	114	162
DH421084	8.4		.3307	10	95	142	DH421026F	10.319	13/32	.4063	12	114	162
DH421117L	8.430	Q	.3320	10	95	142	DH421104	10.4		.4094	12	114	162
DH421085	8.5		.3346	10	95	142	DH421105	10.5		.4134	12	114	162
DH421086	8.6		.3386	10	95	142	DH421106	10.6		.4173	12	114	162
DH421087	8.7		.3425	10	95	142	DH421107	10.7		.4212	12	114	162
DH421022F	8.731	11/32	.3438	10	95	142	DH421027F	10.716	27/64	.4219	12	114	162

▶ Other shank types are available on your request. ▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~							
◎	◎	◎			○	○					



DH421 SERIES

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES EXTRA LONG

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537 MG h6 m7 140° 20 bar P.89 8 x D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
	TiAlN			D2	L1	L2		TiAlN			D2	L1	L2
DH421108	10.8		.4252	12	114	162	DH421130	13.0		.5118	14	133	178
DH421109	10.9		.4291	12	114	162	DH421033F	13.097	33/64	.5156	14	133	178
DH421110	11.0		.4330	12	114	162	DH421131	13.1		.5157	14	133	178
DH421111	11.1		.4370	12	114	162	DH421132	13.2		.5197	14	133	178
DH421028F	11.113	7/16	.4375	12	114	162	DH421133	13.3		.5236	14	133	178
DH421112	11.2		.4409	12	114	162	DH421134	13.4		.5276	14	133	178
DH421113	11.3		.4448	12	114	162	DH421135	13.5		.5314	14	133	178
DH421114	11.4		.4488	12	114	162	DH421136	13.6		.5354	14	133	178
DH421115	11.5		.4527	12	114	162	DH421137	13.7		.5394	14	133	178
DH421029F	11.509	29/64	.4531	12	114	162	DH421138	13.8		.5433	14	133	178
DH421116	11.6		.4566	12	114	162	DH421139	13.9		.5472	14	133	178
DH421117	11.7		.4606	12	114	162	DH421140	14.0		.5512	14	133	178
DH421118	11.8		.4645	12	114	162	DH421141	14.1		.5551	16	152	203
DH421119	11.9		.4685	12	114	162	DH421142	14.2		.5591	16	152	203
DH421030F	11.906	15/32	.4688	12	114	162	DH421036F	14.288	9/16	.5625	16	152	203
DH421120	12.0		.4724	12	114	162	DH421143	14.3		.5630	16	152	203
DH421121	12.1		.4764	14	133	178	DH421144	14.4		.5669	16	152	203
DH421122	12.2		.4803	14	133	178	DH421145	14.5		.5709	16	152	203
DH421123	12.3		.4843	14	133	178	DH421146	14.6		.5748	16	152	203
DH421031F	12.303	31/64	.4844	14	133	178	DH421147	14.7		.5787	16	152	203
DH421124	12.4		.4882	14	133	178	DH421148	14.8		.5827	16	152	203
DH421125	12.5		.4921	14	133	178	DH421149	14.9		.5866	16	152	203
DH421126	12.6		.4961	14	133	178	DH421150	15.0		.5905	16	152	203
DH421032F	12.7	1/2	.5000	14	133	178	DH421151	15.1		.5945	16	152	203
DH421128	12.8		.5039	14	133	178	DH421152	15.2		.5984	16	152	203
DH421129	12.9		.5079	14	133	178	DH421153	15.3		.6024	16	152	203

▶ Other shank types are available on your request.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					



DH421 SERIES

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES EXTRA LONG

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537 MG h6 m7 140° 20 bar P.89 8 x D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
	TiAlN			D2	L1	L2		TiAlN			D2	L1	L2
DH421154	15.4		.6063	16	152	203	DH421178	17.8		.7008	18	171	222
DH421155	15.5		.6102	16	152	203	DH421179	17.9		.7047	18	171	222
DH421156	15.6		.6142	16	152	203	DH421180	18.0		.7087	18	171	222
DH421157	15.7		.6181	16	152	203	DH421181	18.1		.7126	20	190	243
DH421158	15.8		.6220	16	152	203	DH421182	18.2		.7165	20	190	243
DH421040F	15.875	5/8	.6250	16	152	203	DH421183	18.3		.7205	20	190	243
DH421159	15.9		.6260	16	152	203	DH421184	18.4		.7244	20	190	243
DH421160	16.0		.6299	16	152	203	DH421185	18.5		.7283	20	190	243
DH421161	16.1		.6339	18	171	222	DH421186	18.6		.7323	20	190	243
DH421162	16.2		.6378	18	171	222	DH421187	18.7		.7362	20	190	243
DH421163	16.3		.6417	18	171	222	DH421188	18.8		.7402	20	190	243
DH421164	16.4		.6457	18	171	222	DH421189	18.9		.7441	20	190	243
DH421165	16.5		.6496	18	171	222	DH421190	19.0		.7480	20	190	243
DH421166	16.6		.6535	18	171	222	DH421048F	19.050	3/4	.7500	20	190	243
DH421167	16.7		.6575	18	171	222	DH421191	19.1		.7520	20	190	243
DH421168	16.8		.6614	18	171	222	DH421192	19.2		.7559	20	190	243
DH421169	16.9		.6654	18	171	222	DH421193	19.3		.7598	20	190	243
DH421170	17.0		.6693	18	171	222	DH421194	19.4		.7638	20	190	243
DH421171	17.1		.6732	18	171	222	DH421195	19.5		.7677	20	190	243
DH421172	17.2		.6772	18	171	222	DH421196	19.6		.7717	20	190	243
DH421173	17.3		.6811	18	171	222	DH421197	19.7		.7756	20	190	243
DH421174	17.4		.6850	18	171	222	DH421198	19.8		.7795	20	190	243
DH421175	17.5		.6890	18	171	222	DH421199	19.9		.7835	20	190	243
DH421176	17.6		.6929	18	171	222	DH421200	20.0		.7874	20	190	243
DH421177	17.7		.6968	18	171	222							

▶ Other shank types are available on your request.

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					



DH404 SERIES

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES STUB

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



D₁=D₂
3 × D

Unit : mm

EDP No.	Drill Diameter		Flute Length	Overall Length	EDP No.	Drill Diameter		Flute Length	Overall Length
	Metric	Inch				Metric	Inch		
TiAlN	D ₁ = D ₂		L ₁	L ₂	TiAlN	D ₁ = D ₂		L ₁	L ₂
DH404030	3.0	.1181	16	46	DH404056	5.6	.2205	28	66
DH404031	3.1	.1220	18	49	DH404057	5.7	.2244	28	66
DH404032	3.2	.1260	18	49	DH404058	5.8	.2283	28	66
DH404033	3.3	.1299	18	49	DH404059	5.9	.2323	28	66
DH404034	3.4	.1339	20	52	DH404060	6.0	.2362	28	66
DH404035	3.5	.1378	20	52	DH404061	6.1	.2402	31	70
DH404036	3.6	.1417	20	52	DH404062	6.2	.2441	31	70
DH404037	3.7	.1457	20	52	DH404063	6.3	.2480	31	70
DH404038	3.8	.1496	22	55	DH404064	6.4	.2520	31	70
DH404039	3.9	.1535	22	55	DH404065	6.5	.2559	31	70
DH404040	4.0	.1575	22	55	DH404066	6.6	.2598	31	70
DH404041	4.1	.1614	22	55	DH404067	6.7	.2638	31	70
DH404042	4.2	.1654	22	55	DH404068	6.8	.2677	34	74
DH404043	4.3	.1693	24	58	DH404069	6.9	.2717	34	74
DH404044	4.4	.1732	24	58	DH404070	7.0	.2756	34	74
DH404045	4.5	.1772	24	58	DH404071	7.1	.2795	34	74
DH404046	4.6	.1811	24	58	DH404072	7.2	.2835	34	74
DH404047	4.7	.1850	24	58	DH404073	7.3	.2874	34	74
DH404048	4.8	.1890	26	62	DH404074	7.4	.2913	34	74
DH404049	4.9	.1929	26	62	DH404075	7.5	.2953	34	74
DH404050	5.0	.1969	26	62	DH404076	7.6	.2992	37	79
DH404051	5.1	.2008	26	62	DH404077	7.7	.3031	37	79
DH404052	5.2	.2047	26	62	DH404078	7.8	.3071	37	79
DH404053	5.3	.2087	26	62	DH404079	7.9	.3110	37	79
DH404054	5.4	.2126	28	66	DH404080	8.0	.3150	37	79
DH404055	5.5	.2165	28	66	DH404081	8.1	.3189	37	79

▶ Other shank types are available on your request.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55								HRC55~
◎	◎	◎		○	○						



DH404 SERIES

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES STUB

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



D₁=D₂
3 × D

Unit : mm

EDP No.	Drill Diameter		Flute Length	Overall Length	EDP No.	Drill Diameter		Flute Length	Overall Length
	Metric	Inch				Metric	Inch		
TiAlN	D ₁ = D ₂		L ₁	L ₂	TiAlN	D ₁ = D ₂		L ₁	L ₂
DH404082	8.2	.3228	37	79	DH404105	10.5	.4134	43	89
DH404083	8.3	.3268	37	79	DH404110	11.0	.4331	47	95
DH404084	8.4	.3307	37	79	DH404115	11.5	.4528	47	95
DH404085	8.5	.3346	37	79	DH404120	12.0	.4724	51	102
DH404086	8.6	.3386	40	84	DH404130	13.0	.5118	51	102
DH404087	8.7	.3425	40	84	DH404135	13.5	.5314	54	107
DH404088	8.8	.3465	40	84	DH404140	14.0	.5512	54	107
DH404089	8.9	.3504	40	84	DH404145	14.5	.5708	56	111
DH404090	9.0	.3543	40	84	DH404150	15.0	.5905	56	111
DH404091	9.1	.3583	40	84	DH404155	15.5	.6102	58	115
DH404092	9.2	.3622	40	84	DH404160	16.0	.6299	58	115
DH404093	9.3	.3661	40	84	DH404165	16.5	.6495	60	119
DH404094	9.4	.3701	40	84	DH404170	17.0	.6692	60	119
DH404095	9.5	.3740	40	84	DH404175	17.5	.6889	62	123
DH404096	9.6	.3780	43	89	DH404180	18.0	.7087	62	123
DH404097	9.7	.3819	43	89	DH404185	18.5	.7283	64	127
DH404098	9.8	.3858	43	89	DH404190	19.0	.7480	64	127
DH404099	9.9	.3898	43	89	DH404195	19.5	.7676	66	131
DH404100	10.0	.3937	43	89	DH404200	20.0	.7874	66	131
DH404102	10.2	.4016	43	89					

▶ Other shank types are available on your request.

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55								HRC55~
◎	◎	◎		○	○						



DH423 SERIES

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES SHORT

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537
MG
h6
m7
140°
P.90
3 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH423030	3.0		.1181	6	20	62	DH423049	4.9		.1929	6	28	66
DH423031	3.1		.1220	6	20	62	DH423050	5.0		.1969	6	28	66
DH423008F	3.175	1/8	.1250	6	20	62	DH423051	5.1		.2008	6	28	66
DH423032	3.2		.1260	6	20	62	DH423013F	5.159	13/64	.2031	6	28	66
DH423033	3.3		.1299	6	20	62	DH423052	5.2		.2047	6	28	66
DH423034	3.4		.1339	6	20	62	DH423053	5.3		.2087	6	28	66
DH423035	3.5		.1378	6	20	62	DH423054	5.4		.2126	6	28	66
DH423009F	3.572	9/64	.1406	6	20	62	DH423055	5.5		.2165	6	28	66
DH423036	3.6		.1417	6	20	62	DH423014F	5.556	7/32	.2188	6	28	66
DH423037	3.7		.1457	6	20	62	DH423056	5.6		.2205	6	28	66
DH423038	3.8		.1496	6	24	66	DH423057	5.7		.2244	6	28	66
DH423039	3.9		.1535	6	24	66	DH423058	5.8		.2283	6	28	66
DH423010F	3.969	5/32	.1563	6	24	66	DH423059	5.9		.2323	6	28	66
DH423040	4.0		.1575	6	24	66	DH423015F	5.953	15/64	.2344	6	28	66
DH423041	4.1		.1614	6	24	66	DH423060	6.0		.2362	6	28	66
DH423042	4.2		.1654	6	24	66	DH423061	6.1		.2402	8	34	79
DH423043	4.3		.1693	6	24	66	DH423062	6.2		.2441	8	34	79
DH423011F	4.366	11/64	.1719	6	24	66	DH423063	6.3		.2480	8	34	79
DH423044	4.4		.1732	6	24	66	DH423016F	6.350	1/4	.2500	8	34	79
DH423045	4.5		.1772	6	24	66	DH423064	6.4		.2520	8	34	79
DH423046	4.6		.1811	6	24	66	DH423065	6.5		.2559	8	34	79
DH423047	4.7		.1850	6	24	66	DH423006L	6.528	F	.2570	8	34	79
DH423012F	4.763	3/16	.1875	6	24	66	DH423066	6.6		.2598	8	34	79
DH423048	4.8		.1890	6	28	66	DH423067	6.7		.2638	8	34	79

▶ Other shank types are available on your request.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					



DH423 SERIES

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES SHORT

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537
MG
h6
m7
140°
P.90
3 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH423017F	6.747	17/64	.2656	8	34	79	DH423085	8.5		.3346	10	47	89
DH423068	6.8		.2677	8	34	79	DH423086	8.6		.3386	10	47	89
DH423069	6.9		.2717	8	34	79	DH423087	8.7		.3425	10	47	89
DH423009L	6.909	I	.2720	8	34	79	DH423022F	8.731	11/32	.3438	10	47	89
DH423070	7.0		.2756	8	34	79	DH423088	8.8		.3465	10	47	89
DH423071	7.1		.2795	8	41	79	DH423089	8.9		.3504	10	47	89
DH423018F	7.144	9/32	.2812	8	41	79	DH423090	9.0		.3543	10	47	89
DH423072	7.2		.2835	8	41	79	DH423091	9.1		.3583	10	47	89
DH423073	7.3		.2874	8	41	79	DH423023F	9.128	23/64	.3594	10	47	89
DH423074	7.4		.2913	8	41	79	DH423092	9.2		.3622	10	47	89
DH423075	7.5		.2953	8	41	79	DH423093	9.3		.3661	10	47	89
DH423019F	7.541	19/64	.2969	8	41	79	DH423021L	9.347	U	.3680	10	47	89
DH423076	7.6		.2992	8	41	79	DH423094	9.4		.3701	10	47	89
DH423077	7.7		.3031	8	41	79	DH423095	9.5		.3740	10	47	89
DH423078	7.8		.3071	8	41	79	DH423024F	9.525	3/8	.3750	10	47	89
DH423079	7.9		.3110	8	41	79	DH423096	9.6		.3780	10	47	89
DH423020F	7.938	5/16	.3125	8	41	79	DH423097	9.7		.3819	10	47	89
DH423080	8.0		.3150	8	41	79	DH423098	9.8		.3858	10	47	89
DH423081	8.1		.3189	10	47	89	DH423099	9.9		.3898	10	47	89
DH423082	8.2		.3228	10	47	89	DH423025F	9.922	25/64	.3906	10	47	89
DH423083	8.3		.3268	10	47	89	DH423100	10.0		.3937	10	47	89
DH423021F	8.334	21/64	.3281	10	47	89	DH423101	10.1		.3976	12	55	102
DH423084	8.4		.3307	10	47	89	DH423102	10.2		.4016	12	55	102
DH423017L	8.433	Q	.3320	10	47	89	DH423103	10.3		.4055	12	55	102

▶ Other shank types are available on your request.


▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES SHORT

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



3 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH423026F	10.319	13/32	.4062	12	55	102	DH423123	12.3		.4843	14	60	107
DH423104	10.4		.4094	12	55	102	DH423031F	12.303	31/64	.4844	14	60	107
DH423105	10.5		.4134	12	55	102	DH423124	12.4		.4882	14	60	107
DH423106	10.6		.4173	12	55	102	DH423125	12.5		.4921	14	60	107
DH423107	10.7		.4213	12	55	102	DH423126	12.6		.4961	14	60	107
DH423027F	10.716	27/64	.4219	12	55	102	DH423032F	12.7	1/2	.5000	14	60	107
DH423108	10.8		.4252	12	55	102	DH423128	12.8		.5039	14	60	107
DH423109	10.9		.4291	12	55	102	DH423129	12.9		.5079	14	60	107
DH423110	11.0		.4331	12	55	102	DH423130	13.0		.5118	14	60	107
DH423111	11.1		.4370	12	55	102	DH423131	13.1		.5157	14	60	107
DH423028F	11.113	7/16	.4375	12	55	102	DH423132	13.2		.5197	14	60	107
DH423112	11.2		.4409	12	55	102	DH423133	13.3		.5236	14	60	107
DH423113	11.3		.4449	12	55	102	DH423134	13.4		.5276	14	60	107
DH423114	11.4		.4488	12	55	102	DH423135	13.5		.5315	14	60	107
DH423115	11.5		.4528	12	55	102	DH423136	13.6		.5354	14	60	107
DH423029F	11.509	29/64	.4531	12	55	102	DH423137	13.7		.5394	14	60	107
DH423116	11.6		.4567	12	55	102	DH423138	13.8		.5433	14	60	107
DH423117	11.7		.4606	12	55	102	DH423139	13.9		.5472	14	60	107
DH423118	11.8		.4646	12	55	102	DH423140	14.0		.5512	14	60	107
DH423119	11.9		.4685	12	55	102	DH423141	14.1		.5551	16	65	115
DH423030F	11.906	15/32	.4688	12	55	102	DH423142	14.2		.5591	16	65	115
DH423120	12.0		.4724	12	55	102	DH423036F	14.288	9/16	.5625	16	65	115
DH423121	12.1		.4764	14	60	107	DH423143	14.3		.5630	16	65	115
DH423122	12.2		.4803	14	60	107	DH423144	14.4		.5669	16	65	115

▶ Other shank types are available on your request.


▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES SHORT

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



3 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH423145	14.5		.5708	16	65	115	DH423168	16.8		.6614	18	73	123
DH423146	14.6		.5748	16	65	115	DH423169	16.9		.6654	18	73	123
DH423147	14.7		.5787	16	65	115	DH423170	17.0		.6692	18	73	123
DH423148	14.8		.5827	16	65	115	DH423171	17.1		.6732	18	73	123
DH423149	14.9		.5866	16	65	115	DH423172	17.2		.6772	18	73	123
DH423150	15.0		.5905	16	65	115	DH423173	17.3		.6811	18	73	123
DH423151	15.1		.5945	16	65	115	DH423174	17.4		.6850	18	73	123
DH423152	15.2		.5984	16	65	115	DH423044F	17.463	11/16	.6875	18	73	123
DH423153	15.3		.6024	16	65	115	DH423175	17.5		.6889	18	73	123
DH423154	15.4		.6063	16	65	115	DH423176	17.6		.6929	18	73	123
DH423155	15.5		.6102	16	65	115	DH423177	17.7		.6968	18	73	123
DH423156	15.6		.6142	16	65	115	DH423178	17.8		.7008	18	73	123
DH423157	15.7		.6181	16	65	115	DH423179	17.9		.7047	18	73	123
DH423158	15.8		.6220	16	65	115	DH423180	18.0		.7087	18	73	123
DH423040F	15.875	5/8	.6250	16	65	115	DH423181	18.1		.7126	20	79	131
DH423159	15.9		.6260	16	65	115	DH423182	18.2		.7165	20	79	131
DH423160	16.0		.6299	16	65	115	DH423183	18.3		.7205	20	79	131
DH423161	16.1		.6339	18	73	123	DH423184	18.4		.7244	20	79	131
DH423162	16.2		.6378	18	73	123	DH423185	18.5		.7283	20	79	131
DH423163	16.3		.6417	18	73	123	DH423186	18.6		.7323	20	79	131
DH423164	16.4		.6457	18	73	123	DH423187	18.7		.7362	20	79	131
DH423165	16.5		.6495	18	73	123	DH423188	18.8		.7402	20	79	131
DH423166	16.6		.6535	18	73	123	DH423189	18.9		.7441	20	79	131
DH423167	16.7		.6575	18	73	123	DH423190	19.0		.7480	20	79	131

▶ Other shank types are available on your request.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					



DH423 SERIES

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES *SHORT*

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537
MG
h6
m7
140°
P.90
3 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH423048F	19.050	3/4	.7500	20	79	131	DH423196	19.6		.7717	20	79	131
DH423191	19.1		.7520	20	79	131	DH423197	19.7		.7756	20	79	131
DH423192	19.2		.7559	20	79	131	DH423198	19.8		.7795	20	79	131
DH423193	19.3		.7598	20	79	131	DH423199	19.9		.7835	20	79	131
DH423194	19.4		.7638	20	79	131	DH423200	20.0		.7874	20	79	131
DH423195	19.5		.7676	20	79	131							

▶ Other shank types are available on your request.

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					



DH424 SERIES

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES *LONG*

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537
MG
h6
m7
140°
P.90
5 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH424010	1.0		.0394	3	8	55	DH424008F	3.175	1/8	.1250	6	28	66
DH424011	1.1		.0433	3	12	55	DH424032	3.2		.1260	6	28	66
DH424012	1.2		.0472	3	12	55	DH424033	3.3		.1299	6	28	66
DH424013	1.3		.0512	3	12	55	DH424034	3.4		.1339	6	28	66
DH424014	1.4		.0551	3	12	55	DH424035	3.5		.1378	6	28	66
DH424015	1.5		.0591	3	16	55	DH424009F	3.572	9/64	.1406	6	28	66
DH424004F	1.588	1/16	.0625	3	16	55	DH424036	3.6		.1417	6	28	66
DH424016	1.6		.0630	3	16	55	DH424037	3.7		.1457	6	28	66
DH424017	1.7		.0669	3	16	55	DH424038	3.8		.1496	6	36	74
DH424018	1.8		.0709	3	16	55	DH424039	3.9		.1535	6	36	74
DH424019	1.9		.0748	3	16	55	DH424010F	3.969	5/32	.1563	6	36	74
DH424005F	1.984	5/64	.0781	3	16	55	DH424040	4.0		.1575	6	36	74
DH424020	2.0		.0787	4	21	57	DH424041	4.1		.1614	6	36	74
DH424021	2.1		.0827	4	21	57	DH424042	4.2		.1654	6	36	74
DH424022	2.2		.0866	4	21	57	DH424043	4.3		.1693	6	36	74
DH424023	2.3		.0906	4	21	57	DH424011F	4.366	11/64	.1719	6	36	74
DH424006F	2.381	3/32	.0938	4	21	57	DH424044	4.4		.1732	6	36	74
DH424024	2.4		.0945	4	21	57	DH424045	4.5		.1772	6	36	74
DH424025	2.5		.0984	4	21	57	DH424046	4.6		.1811	6	36	74
DH424026	2.6		.1024	4	21	57	DH424047	4.7		.1850	6	36	74
DH424027	2.7		.1063	4	21	57	DH424012F	4.763	3/16	.1875	6	36	74
DH424007F	2.778	7/64	.1094	4	21	57	DH424048	4.8		.1890	6	44	82
DH424028	2.8		.1102	4	21	57	DH424049	4.9		.1929	6	44	82
DH424029	2.9		.1142	4	21	57	DH424050	5.0		.1969	6	44	82
DH424030	3.0		.1181	6	28	66	DH424051	5.1		.2008	6	44	82
DH424031	3.1		.1220	6	28	66	DH424013F	5.159	13/64	.2031	6	44	82

▶ Other shank types are available on your request.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎			○	○					



DH424 SERIES

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES LONG

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



5 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH424052	5.2		.2047	6	44	82	DH424018F	7.144	9/32	.2812	8	53	91
DH424053	5.3		.2087	6	44	82	DH424072	7.2		.2835	8	53	91
DH424054	5.4		.2126	6	44	82	DH424073	7.3		.2874	8	53	91
DH424055	5.5		.2165	6	44	82	DH424074	7.4		.2913	8	53	91
DH424014F	5.556	7/32	.2188	6	44	82	DH424075	7.5		.2953	8	53	91
DH424056	5.6		.2205	6	44	82	DH424019F	7.541	19/64	.2969	8	53	91
DH424057	5.7		.2244	6	44	82	DH424076	7.6		.2992	8	53	91
DH424058	5.8		.2283	6	44	82	DH424077	7.7		.3031	8	53	91
DH424059	5.9		.2323	6	44	82	DH424078	7.8		.3071	8	53	91
DH424015F	5.953	15/64	.2344	6	44	82	DH424079	7.9		.3110	8	53	91
DH424060	6.0		.2362	6	44	82	DH424020F	7.938	5/16	.3125	8	53	91
DH424061	6.1		.2402	8	53	91	DH424080	8.0		.3150	8	53	91
DH424062	6.2		.2441	8	53	91	DH424081	8.1		.3189	10	61	103
DH424063	6.3		.2480	8	53	91	DH424082	8.2		.3228	10	61	103
DH424016F	6.350	1/4	.2500	8	53	91	DH424083	8.3		.3268	10	61	103
DH424064	6.4		.2520	8	53	91	DH424021F	8.334	21/64	.3281	10	61	103
DH424065	6.5		.2559	8	53	91	DH424084	8.4		.3307	10	61	103
DH424006L	6.528	F	.2570	8	53	91	DH424017L	8.433	Q	.3320	10	61	103
DH424066	6.6		.2598	8	53	91	DH424085	8.5		.3346	10	61	103
DH424067	6.7		.2638	8	53	91	DH424086	8.6		.3386	10	61	103
DH424017F	6.747	17/64	.2656	8	53	91	DH424087	8.7		.3425	10	61	103
DH424068	6.8		.2677	8	53	91	DH424022F	8.731	11/32	.3438	10	61	103
DH424069	6.9		.2717	8	53	91	DH424088	8.8		.3465	10	61	103
DH424009L	6.909	I	.2720	8	53	91	DH424089	8.9		.3504	10	61	103
DH424070	7.0		.2756	8	53	91	DH424090	9.0		.3543	10	61	103
DH424071	7.1		.2795	8	53	91	DH424091	9.1		.3583	10	61	103

▶ Other shank types are available on your request.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~							
◎	◎	◎		○	○						



DH424 SERIES

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES LONG

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



5 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH424023F	9.128	23/64	.3594	10	61	103	DH424028F	11.113	7/16	.4375	12	71	118
DH424092	9.2		.3622	10	61	103	DH424112	11.2		.4409	12	71	118
DH424093	9.3		.3661	10	61	103	DH424113	11.3		.4449	12	71	118
DH424021L	9.347	U	.3680	10	61	103	DH424114	11.4		.4488	12	71	118
DH424094	9.4		.3701	10	61	103	DH424115	11.5		.4528	12	71	118
DH424095	9.5		.3740	10	61	103	DH424029F	11.509	29/64	.4531	12	71	118
DH424024F	9.525	3/8	.3750	10	61	103	DH424116	11.6		.4567	12	71	118
DH424096	9.6		.3780	10	61	103	DH424117	11.7		.4606	12	71	118
DH424097	9.7		.3819	10	61	103	DH424118	11.8		.4646	12	71	118
DH424098	9.8		.3858	10	61	103	DH424119	11.9		.4685	12	71	118
DH424099	9.9		.3898	10	61	103	DH424030F	11.906	15/32	.4688	12	71	118
DH424025F	9.922	25/64	.3906	10	61	103	DH424120	12.0		.4724	12	71	118
DH424100	10.0		.3937	10	61	103	DH424121	12.1		.4764	14	77	124
DH424101	10.1		.3976	12	71	118	DH424122	12.2		.4803	14	77	124
DH424102	10.2		.4016	12	71	118	DH424123	12.3		.4843	14	77	124
DH424103	10.3		.4055	12	71	118	DH424031F	12.303	31/64	.4844	14	77	124
DH424026F	10.319	13/32	.4062	12	71	118	DH424124	12.4		.4882	14	77	124
DH424104	10.4		.4094	12	71	118	DH424125	12.5		.4921	14	77	124
DH424105	10.5		.4134	12	71	118	DH424126	12.6		.4961	14	77	124
DH424106	10.6		.4173	12	71	118	DH424032F	12.7	1/2	.5000	14	77	124
DH424107	10.7		.4213	12	71	118	DH424128	12.8		.5039	14	77	124
DH424027F	10.716	27/64	.4219	12	71	118	DH424129	12.9		.5079	14	77	124
DH424108	10.8		.4252	12	71	118	DH424130	13.0		.5118	14	77	124
DH424109	10.9		.4291	12	71	118	DH424131	13.1		.5157	14	77	124
DH424110	11.0		.4331	12	71	118	DH424132	13.2		.5197	14	77	124
DH424111	11.1		.4370	12	71	118	DH424133	13.3		.5236	14	77	124

▶ Other shank types are available on your request.


▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~							
◎	◎	◎		○	○						

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES LONG

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537 MG h6 m7 140° P.90 5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH424134	13.4		.5276	14	77	124	DH424040F	15.875	5/8	.6250	16	83	133
DH424135	13.5		.5315	14	77	124	DH424159	15.9		.6260	16	83	133
DH424136	13.6		.5354	14	77	124	DH424160	16.0		.6299	16	83	133
DH424137	13.7		.5394	14	77	124	DH424161	16.1		.6339	18	93	143
DH424138	13.8		.5433	14	77	124	DH424162	16.2		.6378	18	93	143
DH424139	13.9		.5472	14	77	124	DH424163	16.3		.6417	18	93	143
DH424140	14.0		.5512	14	77	124	DH424164	16.4		.6457	18	93	143
DH424141	14.1		.5551	16	83	133	DH424165	16.5		.6495	18	93	143
DH424142	14.2		.5591	16	83	133	DH424166	16.6		.6535	18	93	143
DH424036F	14.288	9/16	.5625	16	83	133	DH424167	16.7		.6575	18	93	143
DH424143	14.3		.5630	16	83	133	DH424168	16.8		.6614	18	93	143
DH424144	14.4		.5669	16	83	133	DH424169	16.9		.6654	18	93	143
DH424145	14.5		.5708	16	83	133	DH424170	17.0		.6692	18	93	143
DH424146	14.6		.5748	16	83	133	DH424171	17.1		.6732	18	93	143
DH424147	14.7		.5787	16	83	133	DH424172	17.2		.6772	18	93	143
DH424148	14.8		.5827	16	83	133	DH424173	17.3		.6811	18	93	143
DH424149	14.9		.5866	16	83	133	DH424174	17.4		.6850	18	93	143
DH424150	15.0		.5905	16	83	133	DH424175	17.5		.6889	18	93	143
DH424151	15.1		.5945	16	83	133	DH424176	17.6		.6929	18	93	143
DH424152	15.2		.5984	16	83	133	DH424177	17.7		.6968	18	93	143
DH424153	15.3		.6024	16	83	133	DH424178	17.8		.7008	18	93	143
DH424154	15.4		.6063	16	83	133	DH424179	17.9		.7047	18	93	143
DH424155	15.5		.6102	16	83	133	DH424180	18.0		.7087	18	93	143
DH424156	15.6		.6142	16	83	133	DH424181	18.1		.7126	20	101	153
DH424157	15.7		.6181	16	83	133	DH424182	18.2		.7165	20	101	153
DH424158	15.8		.6220	16	83	133	DH424183	18.3		.7205	20	101	153

▶ Other shank types are available on your request.


▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55 HRc55~								
◎	◎	◎		○	○						

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES LONG

- ▶ Drilling for Steel, Cast Steel, Cast Iron, Malleable Cast Iron, Non-Ferrous, Abrasive Plastic
- ▶ Self centering and chip breaking by R-thinning
- ▶ Wave shape and negative land on the cutting edge for low thrust, stable torque and long tool life
- ▶ Optimized flute shape for strength of drilling and smooth chip evacuation



DIN 6537 MG h6 m7 140° P.90 5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAIN	D1			D2	L1	L2	TiAIN	D1			D2	L1	L2
DH424184	18.4		.7244	20	101	153	DH424192	19.2		.7559	20	101	153
DH424185	18.5		.7283	20	101	153	DH424193	19.3		.7598	20	101	153
DH424186	18.6		.7323	20	101	153	DH424194	19.4		.7638	20	101	153
DH424187	18.7		.7362	20	101	153	DH424195	19.5		.7676	20	101	153
DH424188	18.8		.7402	20	101	153	DH424196	19.6		.7717	20	101	153
DH424189	18.9		.7441	20	101	153	DH424197	19.7		.7756	20	101	153
DH424190	19.0		.7480	20	101	153	DH424198	19.8		.7795	20	101	153
DH424048F	19.005	3/4	.7500	20	101	153	DH424199	19.9		.7835	20	101	153
DH424191	19.1		.7520	20	101	153	DH424200	20.0		.7874	20	101	153

▶ Other shank types are available on your request.

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55 HRc55~								
◎	◎	◎		○	○						



RECOMMENDED CUTTING CONDITIONS

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES, TiAIN-COATED

DH416, DH418, DH711, DH712 SERIES

Table with columns for WORK MATERIAL, P (CARBON STEELS, ALLOY STEELS), and K (CAST IRON). Rows include STRENGTH, DRILLING SPEED(SFM), and DIAMETER (Fractional, Metric(mm)) with RPM and IPR values.

Recommend to reduce the feed rate as following
DH416/DH711(3xD) : Feed 100%
DH418/DH712(5xD) : Feed 85%
RPM = rev./min.
IPR = inch/rev.

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES, TiAIN-COATED

DH414, DH722 SERIES

Table with columns for WORK MATERIAL, P (CARBON STEELS, ALLOY STEELS), and K (CAST IRON). Rows include STRENGTH, DRILLING SPEED(SFM), and DIAMETER (Fractional, Metric(mm)) with RPM and IPR values.

Recommend to reduce the feed rate as following
DH414(3xD) : Feed 100%
DH722(5xD) : Feed 85%
RPM = rev./min.
IPR = inch/rev.



RECOMMENDED CUTTING CONDITIONS

CARBIDE, DREAM DRILLS - GENERAL with COOLANT HOLES, TiAIN-COATED

DH406, DH408, DH421 SERIES

Table with columns for WORK MATERIAL, P (NON-ALLOY STEELS, ALLOY STEELS), and K (SOFT GREY CAST IRON, HARD GREY CAST IRON). Rows include STRENGTH, DRILLING SPEED, and DIAMETER (Metric(mm), Decimal) with RPM, FEED, and IPR values.

Recommend to reduce the feed rate as following
DH406(3xD) : Feed 100%, DH408(5xD) : Feed 85%
DH421(8xD) : Feed 70%
RPM = rev./min.
FEED = mm/rev.
IPR = inch/rev.

i-DREAM DRILLS
DREAM DRILLS -GENERAL
DREAM DRILLS -HIGH FEED
DREAM DRILLS -FLAT BOTTOM
DREAM DRILLS -INOX
DREAM DRILLS -ALU
DREAM DRILLS -MQL TYPE
DREAM DRILLS for HIGH HARDENED STEELS
STANDARD CARBIDE DRILLS
MULTI-1 DRILLS
HPD DRILLS
GOLD-P DRILLS
STRAIGHT SHANK DRILLS
AIRCRAFT DRILLS
SILVER & DEMING DRILLS
TAPER SHANK DRILLS
NC SPOTTING DRILLS
COMBINATION DRILLS & COUNTERSINK
SPADE DRILLS
TECHNICAL DATA

i-DREAM DRILLS
DREAM DRILLS -GENERAL
DREAM DRILLS -HIGH FEED
DREAM DRILLS -FLAT BOTTOM
DREAM DRILLS -INOX
DREAM DRILLS -ALU
DREAM DRILLS -MQL TYPE
DREAM DRILLS for HIGH HARDENED STEELS
STANDARD CARBIDE DRILLS
MULTI-1 DRILLS
HPD DRILLS
GOLD-P DRILLS
STRAIGHT SHANK DRILLS
AIRCRAFT DRILLS
SILVER & DEMING DRILLS
TAPER SHANK DRILLS
NC SPOTTING DRILLS
COMBINATION DRILLS & COUNTERSINK
SPADE DRILLS
TECHNICAL DATA



RECOMMENDED CUTTING CONDITIONS

CARBIDE, DREAM DRILLS - GENERAL without COOLANT HOLES, TiAlN-COATED

DH404, DH423, DH424 SERIES

WORK MATERIAL		P						K											
		NON-ALLOY STEELS			ALLOY STEELS			SOFT GREY CAST IRON			HARD GREY CAST IRON								
STRENGTH		< HRc 20						> HRc 20											
DRILLING SPEED		130 ~ 400 ft/min						115 ~ 340 ft/min											
DIAMETER		RPM			FEED			IPR			RPM			FEED			IPR		
Metric(mm)	Decimal	RPM	FEED	IPR	RPM	FEED	IPR	RPM	FEED	IPR	RPM	FEED	IPR	RPM	FEED	IPR			
1.0	.0394	13000	0.04	.002	11250	0.04	.002	21300	0.04	.002	14200	0.04	.002						
2.0	.0787	13000	0.06	.002	11250	0.06	.002	21300	0.06	.002	14200	0.06	.002						
3.0	.1181	13000	0.13	.005	11000	0.13	.005	21000	0.13	.005	14000	0.13	.005						
4.0	.1575	9500	0.14	.006	8400	0.14	.006	16000	0.14	.006	10500	0.14	.006						
5.0	.1969	7600	0.15	.006	6700	0.15	.006	13000	0.15	.006	8300	0.15	.006						
6.0	.2362	6400	0.17	.007	5600	0.17	.007	11000	0.17	.007	6900	0.17	.007						
7.0	.2756	5500	0.19	.007	4800	0.19	.007	9100	0.19	.007	5900	0.19	.007						
8.0	.3150	4800	0.21	.008	4200	0.21	.008	8000	0.21	.008	5200	0.21	.008						
9.0	.3543	4200	0.23	.009	3700	0.23	.009	7100	0.23	.009	4600	0.23	.009						
10.0	.3937	3800	0.25	.010	3350	0.25	.010	6400	0.25	.010	4150	0.25	.010						
12.0	.4724	3200	0.27	.011	2800	0.27	.011	5300	0.27	.011	3450	0.27	.011						
14.0	.5512	2750	0.29	.011	2400	0.29	.011	4550	0.29	.011	3000	0.29	.011						
16.0	.6299	2400	0.31	.012	2100	0.31	.012	4000	0.31	.012	2600	0.31	.012						
18.0	.7087	2100	0.33	.013	1850	0.33	.013	3550	0.33	.013	2300	0.33	.013						
20.0	.7874	1900	0.35	.014	1650	0.35	.014	3200	0.35	.014	2100	0.35	.014						

► Recommend to reduce the feed rate as following
 DH404(3xD), DH423(3xD) : Feed 100%
 DH424(5xD) : Feed 85%

RPM = rev./min.
 FEED = mm/rev.
 IPR = inch/rev

CARBIDE



Being the best through innovation




DREAM DRILLS - HIGH FEED

WITH COOLANT HOLES
 - for Carbon Steels, Alloy Steels (up to HRc35) and Cast Iron

SELECTION GUIDE

SOLID CARBIDE DREAM DRILLS-HIGH FEED

SOLID CARBIDE DREAM DRILLS - HIGH FEED (with Coolant Holes)
- for Carbon Steels, Alloy Steels (up to HRC35) and Cast Iron

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
3xD DGR493 DGR496		CARBIDE, DREAM DRILLS - HIGH FEED with COOLANT HOLES	SHORT	.1969 .7874	94
5xD DGR495 DGR497		CARBIDE, DREAM DRILLS - HIGH FEED with COOLANT HOLES	LONG	.1969 .7874	98
RECOMMENDED CUTTING CONDITIONS					102

◎ : Excellent ○ : Good

P		H			M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○				◎					
◎	◎	○				◎					




DGR493 SERIES

DGR496 SERIES

CARBIDE, DREAM DRILLS - HIGH FEED with COOLANT HOLES SHORT

- ▶ Drilling for Carbon Steels, Alloy Steels(-HRc35) and Cast Iron
- ▶ Higher productivity due to 1.5 to 2 times faster feeding speed than 2-flute drill
- ▶ Multi-Layer coating delivers much better productivity and reliability
- ▶ Self centering and chip breaking by R-thinning and coolant holes



DIN 6537 MG h6 m7 140° 20 bar P.102 3 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
H-coating	D1			D2	L1	L2	H-coating	D1			D2	L1	L2
DGR493050	5.00		.1969	6	28	66	DGR496017	6.75	17/64	.2656	5/16	34	79
DGR493051	5.10		.2008	6	28	66	DGR493068	6.80		.2677	8	34	79
DGR496013	5.16	13/64	.2031	1/4	28	66	DGR493069	6.90		.2717	8	34	79
DGR493052	5.20		.2047	6	28	66	DGR496209	6.91	I	.2720	5/16	34	79
DGR493053	5.30		.2087	6	28	66	DGR493070	7.00		.2756	8	34	79
DGR493054	5.40		.2126	6	28	66	DGR493071	7.10		.2795	8	41	79
DGR496103	5.41	#3	.2130	1/4	28	66	DGR496018	7.14	9/32	.2813	5/16	41	79
DGR493055	5.50		.2165	6	28	66	DGR493072	7.20		.2835	8	41	79
DGR496014	5.56	7/32	.2188	1/4	28	66	DGR493073	7.30		.2874	8	41	79
DGR493056	5.60		.2205	6	28	66	DGR493074	7.40		.2913	8	41	79
DGR496102	5.61	#2	.2210	1/4	28	66	DGR493075	7.50		.2953	8	41	79
DGR493057	5.70		.2244	6	28	66	DGR496019	7.54	19/64	.2969	5/16	41	79
DGR496101	5.79	#1	.2280	1/4	28	66	DGR493076	7.60		.2992	8	41	79
DGR493058	5.80		.2283	6	28	66	DGR493077	7.70		.3031	8	41	79
DGR493059	5.90		.2323	6	28	66	DGR493078	7.80		.3071	8	41	79
DGR496015	5.95	15/64	.2344	1/4	28	66	DGR493079	7.90		.3110	8	41	79
DGR493060	6.00		.2362	6	28	66	DGR496020	7.94	5/16	.3125	5/16	41	79
DGR493061	6.10		.2402	8	34	79	DGR493080	8.00		.3150	8	41	79
DGR493062	6.20		.2441	8	34	79	DGR493081	8.10		.3189	10	47	89
DGR493063	6.30		.2480	8	34	79	DGR493082	8.20	P	.3228	10	47	89
DGR496016	6.35	1/4	.2500	1/4	34	79	DGR493083	8.30		.3268	10	47	89
DGR493064	6.40		.2520	8	34	79	DGR496021	8.33	21/64	.3281	3/8	47	89
DGR493065	6.50		.2559	8	34	79	DGR493084	8.40		.3307	10	47	89
DGR496206	6.53	F	.2570	5/16	34	79	DGR496217	8.43	Q	.3320	3/8	47	89
DGR493066	6.60		.2598	8	34	79	DGR493085	8.50		.3346	10	47	89
DGR493067	6.70		.2638	8	34	79	DGR493086	8.60		.3386	10	47	89

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			◎						




DGR493 SERIES

DGR496 SERIES

CARBIDE, DREAM DRILLS - HIGH FEED with COOLANT HOLES SHORT

- ▶ Drilling for Carbon Steels, Alloy Steels(-HRc35) and Cast Iron
- ▶ Higher productivity due to 1.5 to 2 times faster feeding speed than 2-flute drill
- ▶ Multi-Layer coating delivers much better productivity and reliability
- ▶ Self centering and chip breaking by R-thinning and coolant holes



DIN 6537 MG h6 m7 140° 20 bar P.102 3 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
H-coating	D1			D2	L1	L2	H-coating	D1			D2	L1	L2
DGR493087	8.70		.3425	10	47	89	DGR493107	10.70		.4213	12	55	102
DGR496022	8.73	11/32	.3437	3/8	47	89	DGR496027	10.72	27/64	.4219	7/16	55	102
DGR493088	8.80		.3465	10	47	89	DGR493108	10.80		.4252	12	55	102
DGR493089	8.90		.3504	10	47	89	DGR493109	10.90		.4291	12	55	102
DGR493090	9.00		.3543	10	47	89	DGR493110	11.00		.4331	12	55	102
DGR493091	9.10		.3583	10	47	89	DGR493111	11.10		.4370	12	55	102
DGR496023	9.13	23/64	.3594	3/8	47	89	DGR496028	11.11	7/16	.4375	7/16	55	102
DGR493092	9.20		.3622	10	47	89	DGR493112	11.20		.4409	12	55	102
DGR493093	9.30		.3661	10	47	89	DGR493113	11.30		.4449	12	55	102
DGR496221	9.35	U	.3680	3/8	47	89	DGR493114	11.40		.4488	12	55	102
DGR493094	9.40		.3701	10	47	89	DGR493115	11.50		.4528	12	55	102
DGR493095	9.50		.3740	10	47	89	DGR496029	11.51	29/64	.4531	1/2	55	102
DGR496024	9.53	3/8	.3750	3/8	47	89	DGR493116	11.60		.4567	12	55	102
DGR493096	9.60		.3780	10	47	89	DGR493117	11.70		.4606	12	55	102
DGR493097	9.70		.3819	10	47	89	DGR493118	11.80		.4646	12	55	102
DGR493098	9.80	W	.3858	10	47	89	DGR493119	11.90		.4685	12	55	102
DGR493099	9.90		.3898	10	47	89	DGR496030	11.91	15/32	.4688	1/2	55	102
DGR496025	9.92	25/64	.3906	7/16	47	89	DGR493120	12.00		.4724	12	55	102
DGR493100	10.00		.3937	10	47	89	DGR493121	12.10		.4764	14	60	107
DGR493101	10.10		.3976	12	55	102	DGR493122	12.20		.4803	14	60	107
DGR493102	10.20		.4016	12	55	102	DGR493123	12.30		.4843	14	60	107
DGR493103	10.30		.4055	12	55	102	DGR496031	12.30	31/64	.4844	1/2	60	107
DGR496026	10.32	13/32	.4063	7/16	55	102	DGR493124	12.40		.4882	14	60	107
DGR493104	10.40		.4094	12	55	102	DGR493125	12.50		.4921	14	60	107
DGR493105	10.50		.4134	12	55	102	DGR493126	12.60		.4961	14	60	107
DGR493106	10.60		.4173	12	55	102	DGR496032	12.70	1/2	.5000	1/2	60	107

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			◎						

CARBIDE, DREAM DRILLS - HIGH FEED with COOLANT HOLES *SHORT*

- ▶ Drilling for Carbon Steels, Alloy Steels(-HRc35) and Cast Iron
- ▶ Higher productivity due to 1.5 to 2 times faster feeding speed than 2-flute drill
- ▶ Multi-Layer coating delivers much better productivity and reliability
- ▶ Self centering and chip breaking by R-thinning and coolant holes



DIN 6537
MG
h6
m7
140°
20 bar
P.102
3 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
H-coating	D1			D2	L1	L2	H-coating	D1			D2	L1	L2
DGR493127	12.70		.5000	14	60	107	DGR493149	14.90		.5866	16	65	115
DGR493128	12.80		.5039	14	60	107	DGR493150	15.00		.5906	16	65	115
DGR493129	12.90		.5079	14	60	107	DGR496038	15.08	19/32	.5938	5/8	65	115
DGR493130	13.00		.5118	14	60	107	DGR493151	15.10		.5945	16	65	115
DGR493131	13.10	33/64	.5156	14	60	107	DGR493152	15.20		.5984	16	65	115
DGR493132	13.20		.5197	14	60	107	DGR493153	15.30		.6024	16	65	115
DGR493133	13.30		.5236	14	60	107	DGR493154	15.40		.6063	16	65	115
DGR493134	13.40		.5276	14	60	107	DGR496039	15.48	39/64	.6094	5/8	65	115
DGR496034	13.49	17/32	.5312	9/16	60	107	DGR493155	15.50		.6102	16	65	115
DGR493135	13.50		.5315	14	60	107	DGR493156	15.60		.6142	16	65	115
DGR493136	13.60		.5354	14	60	107	DGR493157	15.70		.6181	16	65	115
DGR493137	13.70		.5394	14	60	107	DGR493158	15.80		.6220	16	65	115
DGR493138	13.80		.5433	14	60	107	DGR496040	15.88	5/8	.6250	5/8	65	115
DGR496035	13.89	35/64	.5469	9/16	60	107	DGR493159	15.90		.6260	16	65	115
DGR493139	13.90		.5472	14	60	107	DGR493160	16.00		.6299	16	65	115
DGR493140	14.00		.5512	14	60	107	DGR493161	16.10		.6339	18	73	123
DGR493141	14.10		.5551	16	65	115	DGR496041	16.27	41/64	.6406	11/16	73	123
DGR493142	14.20		.5591	16	65	115	DGR493165	16.50		.6496	18	73	123
DGR496036	14.29	9/16	.5625	9/16	65	115	DGR496042	16.67	21/32	.6563	11/16	73	123
DGR493143	14.30		.5630	16	65	115	DGR493170	17.00		.6693	18	73	123
DGR493144	14.40		.5669	16	65	115	DGR496043	17.07	43/64	.6719	11/16	73	123
DGR493145	14.50		.5709	16	65	115	DGR496044	17.46	11/16	.6875	11/16	73	123
DGR493146	14.60		.5748	16	65	115	DGR493175	17.50		.6890	18	73	123
DGR496037	14.68	37/64	.5781	5/8	65	115	DGR496045	17.86	45/64	.7031	3/4	73	123
DGR493147	14.70		.5787	16	65	115	DGR493180	18.00		.7087	18	73	123
DGR493148	14.80		.5827	16	65	115	DGR496046	18.26	23/32	.7188	3/4	79	131


▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○				◎					

CARBIDE, DREAM DRILLS - HIGH FEED with COOLANT HOLES *SHORT*

- ▶ Drilling for Carbon Steels, Alloy Steels(-HRc35) and Cast Iron
- ▶ Higher productivity due to 1.5 to 2 times faster feeding speed than 2-flute drill
- ▶ Multi-Layer coating delivers much better productivity and reliability
- ▶ Self centering and chip breaking by R-thinning and coolant holes



DIN 6537
MG
h6
m7
140°
20 bar
P.102
3 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
H-coating	D1			D2	L1	L2	H-coating	D1			D2	L1	L2
DGR493185	18.50		.7283	20	79	131	DGR496048	19.05	3/4	.7500	3/4	79	131
DGR496047	18.65	47/64	.7344	3/4	79	131	DGR493195	19.50		.7677	20	79	131
DGR493190	19.00		.7480	20	79	131	DGR493200	20.00		.7874	20	79	131


◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○				◎					



CARBIDE, DREAM DRILLS - HIGH FEED with COOLANT HOLES LONG

- ▶ Drilling for Carbon Steels, Alloy Steels(-HRc35) and Cast Iron
- ▶ Higher productivity due to 1.5 to 2 times faster feeding speed than 2-flute drill
- ▶ Multi-Layer coating delivers much better productivity and reliability
- ▶ Self centering and chip breaking by R-thinning and coolant holes



DIN 6537 MG h6 m7 140° 20 bar P.102 5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
H-coating	D1			D2	L1	L2	H-coating	D1			D2	L1	L2
DGR495050	5.00		.1969	6	44	82	DGR497017	6.75	17/64	.2656	5/16	53	91
DGR495051	5.10		.2008	6	44	82	DGR495068	6.80		.2677	8	53	91
DGR497013	5.16	13/64	.2031	1/4	44	82	DGR495069	6.90		.2717	8	53	91
DGR495052	5.20		.2047	6	44	82	DGR497209	6.91	I	.2720	5/16	53	91
DGR495053	5.30		.2087	6	44	82	DGR495070	7.00		.2756	8	53	91
DGR495054	5.40		.2126	6	44	82	DGR495071	7.10		.2795	8	53	91
DGR497103	5.41	#3	.2130	1/4	44	82	DGR497018	7.14	9/32	.2813	5/16	53	91
DGR495055	5.50		.2165	6	44	82	DGR495072	7.20		.2835	8	53	91
DGR497014	5.56	7/32	.2188	1/4	44	82	DGR495073	7.30		.2874	8	53	91
DGR495056	5.60		.2205	6	44	82	DGR495074	7.40		.2913	8	53	91
DGR497102	5.61	#2	.2210	1/4	44	82	DGR495075	7.50		.2953	8	53	91
DGR495057	5.70		.2244	6	44	82	DGR497019	7.54	19/64	.2969	5/16	53	91
DGR497101	5.79	#1	.2280	1/4	44	82	DGR495076	7.60		.2992	8	53	91
DGR495058	5.80		.2283	6	44	82	DGR495077	7.70		.3031	8	53	91
DGR495059	5.90		.2323	6	44	82	DGR495078	7.80		.3071	8	53	91
DGR497015	5.95	15/64	.2344	1/4	44	82	DGR495079	7.90		.3110	8	53	91
DGR495060	6.00		.2362	6	44	82	DGR497020	7.94	5/16	.3125	5/16	53	91
DGR495061	6.10		.2402	8	53	91	DGR495080	8.00		.3150	8	53	91
DGR495062	6.20		.2441	8	53	91	DGR495081	8.10		.3189	10	61	103
DGR495063	6.30		.2480	8	53	91	DGR495082	8.20	P	.3228	10	61	103
DGR497016	6.35	1/4	.2500	1/4	53	91	DGR495083	8.30		.3268	10	61	103
DGR495064	6.40		.2520	8	53	91	DGR497021	8.33	21/64	.3281	3/8	61	103
DGR495065	6.50		.2559	8	53	91	DGR495084	8.40		.3307	10	61	103
DGR497206	6.53	F	.2570	5/16	53	91	DGR497217	8.43	Q	.3320	3/8	61	103
DGR495066	6.60		.2598	8	53	91	DGR495085	8.50		.3346	10	61	103
DGR495067	6.70		.2638	8	53	91	DGR495086	8.60		.3386	10	61	103

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			◎						



CARBIDE, DREAM DRILLS - HIGH FEED with COOLANT HOLES LONG

- ▶ Drilling for Carbon Steels, Alloy Steels(-HRc35) and Cast Iron
- ▶ Higher productivity due to 1.5 to 2 times faster feeding speed than 2-flute drill
- ▶ Multi-Layer coating delivers much better productivity and reliability
- ▶ Self centering and chip breaking by R-thinning and coolant holes



DIN 6537 MG h6 m7 140° 20 bar P.102 5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
H-coating	D1			D2	L1	L2	H-coating	D1			D2	L1	L2
DGR495087	8.70		.3425	10	61	103	DGR497026	10.32	13/32	.4063	7/16	71	118
DGR497022	8.73	11/32	.3437	3/8	61	103	DGR495104	10.40		.4094	12	71	118
DGR495088	8.80		.3465	10	61	103	DGR495105	10.50		.4134	12	71	118
DGR495089	8.90		.3504	10	61	103	DGR495106	10.60		.4173	12	71	118
DGR495090	9.00		.3543	10	61	103	DGR495107	10.70		.4213	12	71	118
DGR495091	9.10		.3583	10	61	103	DGR497027	10.72	27/64	.4219	7/16	71	118
DGR497023	9.13	23/64	.3594	3/8	61	103	DGR495108	10.80		.4252	12	71	118
DGR495092	9.20		.3622	10	61	103	DGR495109	10.90		.4291	12	71	118
DGR495093	9.30		.3661	10	61	103	DGR495110	11.00		.4331	12	71	118
DGR497221	9.35	U	.3680	3/8	61	103	DGR495111	11.10		.4370	12	71	118
DGR495094	9.40		.3701	10	61	103	DGR497028	11.11	7/16	.4375	7/16	71	118
DGR495095	9.50		.3740	10	61	103	DGR495112	11.20		.4409	12	71	118
DGR497024	9.53	3/8	.3750	3/8	61	103	DGR495113	11.30		.4449	12	71	118
DGR495096	9.60		.3780	10	61	103	DGR495114	11.40		.4488	12	71	118
DGR495097	9.70		.3819	10	61	103	DGR495115	11.50		.4528	12	71	118
DGR495098	9.80	W	.3858	10	61	103	DGR497029	11.51	29/64	.4531	1/2	71	118
DGR495099	9.90		.3898	10	61	103	DGR495116	11.60		.4567	12	71	118
DGR497025	9.92	25/64	.3906	7/16	61	103	DGR495117	11.70		.4606	12	71	118
DGR495100	10.00		.3937	10	61	103	DGR495118	11.80		.4646	12	71	118
DGR495101	10.10		.3976	12	71	118	DGR495119	11.90		.4685	12	71	118
DGR495102	10.20		.4016	12	71	118	DGR497030	11.91	15/32	.4688	1/2	71	118
DGR495103	10.30		.4055	12	71	118	DGR495120	12.00		.4724	12	71	118

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			◎						



CARBIDE, DREAM DRILLS - HIGH FEED with COOLANT HOLES *LONG*

- ▶ Drilling for Carbon Steels, Alloy Steels(-HRc35) and Cast Iron
- ▶ Higher productivity due to 1.5 to 2 times faster feeding speed than 2-flute drill
- ▶ Multi-Layer coating delivers much better productivity and reliability
- ▶ Self centering and chip breaking by R-thinning and coolant holes



DIN 6537
MG
h6
m7
140°
20 bar
P.102
5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
H-coating	D1			D2	L1	L2	H-coating	D1			D2	L1	L2
DGR495121	12.10		.4764	14	77	124	DGR495139	13.90		.5472	14	77	124
DGR495122	12.20		.4803	14	77	124	DGR495140	14.00		.5512	14	77	124
DGR495123	12.30		.4843	14	77	124	DGR495141	14.10		.5551	16	83	133
DGR497031	12.30	31/64	.4844	1/2	77	124	DGR495142	14.20		.5591	16	83	133
DGR495124	12.40		.4882	14	77	124	DGR497036	14.29	9/16	.5625	9/16	83	133
DGR495125	12.50		.4921	14	77	124	DGR495143	14.30		.5630	16	83	133
DGR495126	12.60		.4961	14	77	124	DGR495144	14.40		.5669	16	83	133
DGR497032	12.70	1/2	.5000	1/2	77	124	DGR495145	14.50		.5709	16	83	133
DGR495127	12.70		.5000	14	77	124	DGR495146	14.60		.5748	16	83	133
DGR495128	12.80		.5039	14	77	124	DGR497037	14.68	37/64	.5781	5/8	83	133
DGR495129	12.90		.5079	14	77	124	DGR495147	14.70		.5787	16	83	133
DGR495130	13.00		.5118	14	77	124	DGR495148	14.80		.5827	16	83	133
DGR495131	13.10	33/64	.5156	14	77	124	DGR495149	14.90		.5866	16	83	133
DGR495132	13.20		.5197	14	77	124	DGR495150	15.00		.5906	16	83	133
DGR495133	13.30		.5236	14	77	124	DGR497038	15.08	19/32	.5938	5/8	83	133
DGR495134	13.40		.5276	14	77	124	DGR495151	15.10		.5945	16	83	133
DGR497034	13.49	17/32	.5312	9/16	77	124	DGR495152	15.20		.5984	16	83	133
DGR495135	13.50		.5315	14	77	124	DGR495153	15.30		.6024	16	83	133
DGR495136	13.60		.5354	14	77	124	DGR495154	15.40		.6063	16	83	133
DGR495137	13.70		.5394	14	77	124	DGR497039	15.48	39/64	.6094	5/8	83	133
DGR495138	13.80		.5433	14	77	124	DGR495155	15.50		.6102	16	83	133
DGR497035	13.89	35/64	.5469	9/16	77	124	DGR495156	15.60		.6142	16	83	133

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	◎	○				◎					



CARBIDE, DREAM DRILLS - HIGH FEED with COOLANT HOLES *LONG*

- ▶ Drilling for Carbon Steels, Alloy Steels(-HRc35) and Cast Iron
- ▶ Higher productivity due to 1.5 to 2 times faster feeding speed than 2-flute drill
- ▶ Multi-Layer coating delivers much better productivity and reliability
- ▶ Self centering and chip breaking by R-thinning and coolant holes



DIN 6537
MG
h6
m7
140°
20 bar
P.102
5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
H-coating	D1			D2	L1	L2	H-coating	D1			D2	L1	L2
DGR495157	15.70		.6181	16	83	133	DGR497044	17.46	11/16	.6875	11/16	93	143
DGR495158	15.80		.6220	16	83	133	DGR495175	17.50		.6890	18	93	143
DGR497040	15.88	5/8	.6250	5/8	83	133	DGR497045	17.86	45/64	.7031	3/4	93	143
DGR495159	15.90		.6260	16	83	133	DGR495180	18.00		.7087	18	93	143
DGR495160	16.00		.6299	16	83	133	DGR497046	18.26	23/32	.7188	3/4	101	153
DGR495161	16.10		.6339	18	93	143	DGR495185	18.50		.7283	20	101	153
DGR497041	16.27	41/64	.6406	11/16	93	143	DGR497047	18.65	47/64	.7344	3/4	101	153
DGR495165	16.50		.6496	18	93	143	DGR495190	19.00		.7480	20	101	153
DGR497042	16.67	21/32	.6563	11/16	93	143	DGR497048	19.05	3/4	.7500	3/4	101	153
DGR495170	17.00		.6693	18	93	143	DGR495195	19.50		.7677	20	101	153
DGR497043	17.07	43/64	.6719	11/16	93	143	DGR495200	20.00		.7874	20	101	153

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	◎	○				◎					

CARBIDE

HSS

i-DREAM DRILLS

DREAM DRILLS -GENERAL

DREAM DRILLS -HIGH FEED

DREAM DRILLS -FLAT BOTTOM

DREAM DRILLS -INOX

DREAM DRILLS -ALU

DREAM DRILLS -MQL TYPE

DREAM DRILLS for HIGH HARDENED STEELS

STANDARD CARBIDE DRILLS

MULTI-1 DRILLS

HPD DRILLS

GOLD-P DRILLS

STRAIGHT SHANK DRILLS

AIRCRAFT DRILLS

SILVER & DEMING DRILLS

TAPER SHANK DRILLS

NC SPOTTING DRILLS

COMBINATION DRILLS & COUNTERSINK

SPADE DRILLS

TECHNICAL DATA



DREAM DRILLS -HIGH FEED

RECOMMENDED CUTTING CONDITIONS

CARBIDE, DREAM DRILLS - HIGH FEED with COOLANT HOLES, H-COATED

DGR493, DGR496, DGR495, DGR497 SERIES

WORK MATERIAL	P						K																		
	CARBON STEELS ALLOY STEELS			ALLOY STEELS			CAST IRON			DUCTILE CAST IRON															
	~ HRC20						HRC20 ~ 35																		
HARDNESS		329 ft/min						247 ft/min						329 ft/min						264 ft/min					
DRILLING SPEED		329 ft/min						247 ft/min						329 ft/min						264 ft/min					
DIAMETER		RPM		IPR		RPM		IPR		RPM		IPR		RPM		IPR									
Metric(mm)	Decimal	RPM	Min	Max	RPM	Min	Max	RPM	Min	Max	RPM	Min	Max	RPM	Min	Max									
5.0	.1969	6370	.0079	.0098	4780	.0079	.0098	6370	.0091	.0118	5100	.0079	.0098												
6.0	.2362	5310	.0094	.0118	3980	.0094	.0118	5310	.0106	.0142	4250	.0094	.0118												
7.0	.2756	4550	.0110	.0138	3420	.0110	.0138	4550	.0126	.0165	3640	.0110	.0138												
8.0	.3150	3980	.0126	.0157	2990	.0126	.0157	3980	.0142	.0189	3190	.0126	.0157												
9.0	.3543	3540	.0142	.0177	2660	.0142	.0177	3540	.0161	.0213	2840	.0142	.0177												
10.0	.3937	3190	.0157	.0197	2390	.0157	.0197	3190	.0177	.0236	2550	.0157	.0197												
12.0	.4724	2660	.0189	.0236	2000	.0189	.0213	2660	.0213	.0283	2130	.0189	.0236												
14.0	.5512	2280	.0220	.0276	1710	.0220	.0248	2280	.0248	.0331	1820	.0220	.0276												
16.0	.6299	1990	.0220	.0283	1500	.0220	.0252	1990	.0252	.0315	1600	.0220	.0283												
18.0	.7087	1770	.0248	.0319	1330	.0248	.0283	1770	.0283	.0354	1420	.0248	.0319												
20.0	.7874	1600	.0276	.0346	1190	.0268	.0319	1600	.0315	.0386	1280	.0276	.0354												

RPM = rev./min.
IPR = inch/rev.



Leading Through Innovation

CARBIDE



DREAM DRILLS -FLAT BOTTOM


- WITHOUT COOLANT HOLES**
- For holes on various angled surfaces
 - 180 degree point angle enables drilling of flat, inclined and curved surfaces

SELECTION GUIDE

SOLID CARBIDE DREAM DRILLS-FIAT BOTTOM

SOLID CARBIDE DREAM DRILLS - FLAT BOTTOM (without Coolant Holes)

- For holes on various angled surfaces
- 180 degree point angle enables drilling of flat, inclined and curved surfaces

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
2xD DPP447		CARBIDE, DREAM DRILLS - FLAT BOTTOM without COOLANT HOLES	SHORT	D3.0 D20.0	106
		RECOMMENDED CUTTING CONDITIONS			

◎ : Excellent ○ : Good

P			H		M	K	N			S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	◎	○		○	◎	○	○			


YG DREAM DRILLS -FLAT BOTTOM

DPP447 SERIES

CARBIDE, DREAM DRILLS - FLAT BOTTOM without COOLANT HOLES

SHORT

- ▶ Just ONE Drill 180 degree point angle enables drilling of horizontal surface and sloped surface
- ▶ Excellent chip evacuation by optimized flute shape
- ▶ High strength cutting edge to improve tool life and versatility drilling
- ▶ Variety of drilling can be used in a variety of drilling applications



2 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
X-Coating	D1			D2	L1	L2	X-Coating	D1			D2	L1	L2
DPP447030	3		.1181	6	16	50	DPP447051	5.1		.2008	6	24	60
DPP447031	3.1		.1220	6	16	50	DPP447052	5.2		.2047	6	24	60
DPP447008F	3.175	1/8	.1250	6	16	50	DPP447053	5.3		.2087	6	24	60
DPP447032	3.2		.1260	6	16	50	DPP447054	5.4		.2126	6	24	60
DPP447033	3.3		.1299	6	16	50	DPP447055	5.5		.2165	6	24	60
DPP447034	3.4		.1339	6	18	50	DPP447014F	5.556	7/32	.2188	6	24	60
DPP447035	3.5		.1378	6	18	50	DPP447056	5.6		.2205	6	24	60
DPP447036	3.6		.1417	6	18	50	DPP447057	5.7		.2244	6	26	60
DPP447037	3.7		.1457	6	18	50	DPP447058	5.8		.2283	6	26	60
DPP447038	3.8		.1496	6	18	50	DPP447059	5.9		.2323	6	26	60
DPP447039	3.9		.1535	6	18	50	DPP447060	6		.2362	6	26	60
DPP447010F	3.969	5/32	.1563	6	18	50	DPP447061	6.1		.2402	8	28	70
DPP447040	4		.1575	6	18	50	DPP447062	6.2		.2441	8	28	70
DPP447041	4.1		.1614	6	20	60	DPP447063	6.3		.2480	8	28	70
DPP447042	4.2		.1654	6	20	60	DPP447016F	6.35	1/4	.2500	8	30	70
DPP447043	4.3		.1693	6	20	60	DPP447064	6.4		.2520	8	30	70
DPP447044	4.4		.1732	6	20	60	DPP447065	6.5		.2559	8	30	70
DPP447045	4.5		.1772	6	22	60	DPP447066	6.6		.2598	8	30	70
DPP447046	4.6		.1811	6	22	60	DPP447067	6.7		.2638	8	30	70
DPP447047	4.7		.1850	6	22	60	DPP447068	6.8		.2677	8	30	70
DPP447012F	4.763	3/16	.1875	6	22	60	DPP447069	6.9		.2717	8	30	70
DPP447048	4.8		.1890	6	22	60	DPP447070	7		.2756	8	30	70
DPP447049	4.9		.1929	6	22	60	DPP447071	7.1		.2795	8	34	70
DPP447050	5		.1969	6	22	60	DPP447018F	7.144	9/32	.2812	8	34	70

▶ Other shank types are available on your request.

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55 HRc55~								
◎	◎	◎	○	○	◎	○	○	○			


YG DREAM DRILLS -FLAT BOTTOM

DPP447 SERIES

CARBIDE, DREAM DRILLS - FLAT BOTTOM without COOLANT HOLES

SHORT

- ▶ Just ONE Drill 180 degree point angle enables drilling of horizontal surface and sloped surface
- ▶ Excellent chip evacuation by optimized flute shape
- ▶ High strength cutting edge to improve tool life and versatility drilling
- ▶ Variety of drilling can be used in a variety of drilling applications



2 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
X-Coating	D1			D2	L1	L2	X-Coating	D1			D2	L1	L2
DPP447072	7.2		.2835	8	34	70	DPP447093	9.3		.3661	10	42	80
DPP447073	7.3		.2874	8	34	70	DPP447094	9.4		.3701	10	42	80
DPP447074	7.4		.2913	8	34	70	DPP447095	9.5		.3740	10	42	80
DPP447075	7.5		.2953	8	34	70	DPP447024F	9.525	3/8	.3750	10	42	80
DPP447076	7.6		.2992	8	34	70	DPP447096	9.6		.3780	10	42	80
DPP447077	7.7		.3031	8	34	70	DPP447097	9.7		.3819	10	45	80
DPP447078	7.8		.3071	8	34	70	DPP447098	9.8		.3858	10	45	80
DPP447079	7.9		.3110	8	34	70	DPP447099	9.9		.3898	10	45	80
DPP447020F	7.938	5/16	.3125	8	34	70	DPP447100	10		.3937	10	45	80
DPP447080	8		.3150	8	34	70	DPP447101	10.1		.3976	12	46	90
DPP447081	8.1		.3189	10	38	80	DPP447102	10.2		.4016	12	46	90
DPP447082	8.2		.3228	10	38	80	DPP447103	10.3		.4055	12	46	90
DPP447083	8.3		.3268	10	38	80	DPP447026F	10.319	13/32	.4062	12	46	90
DPP447021F	8.334	21/64	.3281	10	38	80	DPP447104	10.4		.4094	12	48	90
DPP447084	8.4		.3307	10	38	80	DPP447105	10.5		.4134	12	48	90
DPP447085	8.5		.3346	10	38	80	DPP447106	10.6		.4173	12	48	90
DPP447086	8.6		.3386	10	38	80	DPP447107	10.7		.4212	12	48	90
DPP447087	8.7		.3425	10	40	80	DPP447108	10.8		.4252	12	48	90
DPP447088	8.8		.3465	10	40	80	DPP447109	10.9		.4291	12	48	90
DPP447089	8.9		.3504	10	40	80	DPP447110	11		.4330	12	48	90
DPP447090	9		.3543	10	40	80	DPP447111	11.1		.4370	12	50	90
DPP447091	9.1		.3583	10	42	80	DPP447028F	11.113	7/16	.4375	12	50	90
DPP447023F	9.128	23/64	.3594	10	42	80	DPP447112	11.2		.4409	12	50	90
DPP447092	9.2		.3622	10	42	80	DPP447113	11.3		.4448	12	50	90

▶ Other shank types are available on your request.

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55 HRc55~								
◎	◎	◎	○	○	◎	○	○	○			


YG DREAM DRILLS -FLAT BOTTOM

DPP447 SERIES

CARBIDE, DREAM DRILLS - FLAT BOTTOM without COOLANT HOLES

SHORT

- ▶ Just ONE Drill 180 degree point angle enables drilling of horizontal surface and sloped surface
- ▶ Excellent chip evacuation by optimized flute shape
- ▶ High strength cutting edge to improve tool life and versatility drilling
- ▶ Variety of drilling can be used in a variety of drilling applications



2 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
X-Coating	D1			D2	L1	L2	X-Coating	D1			D2	L1	L2
DPP447114	11.4		.4488	12	50	90	DPP447136	13.6		.5354	14	58	100
DPP447115	11.5		.4527	12	50	90	DPP447137	13.7		.5394	14	58	100
DPP447029F	11.509	29/64	.4531	12	50	90	DPP447138	13.8		.5433	14	58	100
DPP447116	11.6		.4566	12	50	90	DPP447139	13.9		.5472	14	58	100
DPP447117	11.7		.4606	12	52	90	DPP447140	14		.5512	14	58	100
DPP447118	11.8		.4645	12	52	90	DPP447141	14.1		.5551	16	62	105
DPP447119	11.9		.4685	12	52	90	DPP447142	14.2		.5591	16	62	105
DPP447030F	11.906	15/32	.4688	12	52	90	DPP447036F	14.288	9/16	.5625	16	62	105
DPP447120	12		.4724	12	52	90	DPP447143	14.3		.5630	16	62	105
DPP447121	12.1		.4764	14	54	100	DPP447144	14.4		.5669	16	62	105
DPP447122	12.2		.4803	14	54	100	DPP447145	14.5		.5709	16	62	105
DPP447123	12.3		.4843	14	54	100	DPP447146	14.6		.5748	16	62	105
DPP447124	12.4		.4882	14	54	100	DPP447147	14.7		.5787	16	62	105
DPP447125	12.5		.4921	14	54	100	DPP447148	14.8		.5827	16	62	105
DPP447126	12.6		.4961	14	54	100	DPP447149	14.9		.5866	16	62	105
DPP447127	12.7		.5000	14	56	100	DPP447150	15		.5905	16	62	105
DPP447128	12.8		.5039	14	56	100	DPP447151	15.1		.5945	16	64	115
DPP447129	12.9		.5079	14	56	100	DPP447152	15.2		.5984	16	64	115
DPP447130	13		.5118	14	56	100	DPP447153	15.3		.6024	16	64	115
DPP447131	13.1		.5157	14	58	100	DPP447154	15.4		.6063	16	64	115
DPP447132	13.2		.5197	14	58	100	DPP447155	15.5		.6102	16	64	115
DPP447133	13.3		.5236	14	58	100	DPP447156	15.6		.6142	16	64	115
DPP447134	13.4		.5276	14	58	100	DPP447157	15.7		.6181	16	64	115
DPP447135	13.5		.5314	14	58	100	DPP447158	15.8		.6220	16	64	115

▶ Other shank types are available on your request.

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~							
◎	◎	◎	○	○	◎	○	○	○			

YG DREAM DRILLS -FLAT BOTTOM

DPP447 SERIES

CARBIDE, DREAM DRILLS - FLAT BOTTOM without COOLANT HOLES

SHORT

- ▶ Just ONE Drill 180 degree point angle enables drilling of horizontal surface and sloped surface
- ▶ Excellent chip evacuation by optimized flute shape
- ▶ High strength cutting edge to improve tool life and versatility drilling
- ▶ Variety of drilling can be used in a variety of drilling applications



2 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
X-Coating	D1			D2	L1	L2	X-Coating	D1			D2	L1	L2
DPP447040F	15.875	5/8	.6250	16	64	115	DPP447180	18		.7087	18	70	125
DPP447159	15.9		.6260	16	64	115	DPP447185	18.5		.7283	20	75	135
DPP447160	16		.6299	16	64	115	DPP447190	19		.7480	20	75	135
DPP447165	16.5		.6496	18	70	125	DPP447048F	19.05	3/4	.7500	20	75	135
DPP447170	17		.6693	18	70	125	DPP447195	19.5		.7677	20	75	145
DPP447044F	17.463	11/16	.6875	18	70	125	DPP447200	20		.7874	20	75	145
DPP447175	17.5		.6890	18	70	125							

▶ Other shank types are available on your request.

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~							
◎	◎	◎	○	○	◎	○	○	○			

Y/G DREAM DRILLS -FLAT BOTTOM


RECOMMENDED CUTTING CONDITIONS

CARBIDE, DREAM DRILL - FLAT BOTTOM without COOLANT HOLES, X-COATED

DPP447 SERIES

WORK MATERIAL	P								M		K		N			
	STRUCTURAL STEELS		CARBON STEELS ALLOY STEELS		PREHARDENED STEELS		HARDEND STEELS		STAINLESS STEELS		CAST IRON		ALUMINUM			
STRENGTH	<HB225								HRC30 ~ 40		HRC40 ~ 50		~ 200 HB			
DRILLING SPEED	80 m/min		70 m/min		38 m/min		25 m/min		30 m/min		68 m/min		165 m/min			
DIAMETER	RPM		FEED		RPM		FEED		RPM		FEED		RPM		FEED	
	Metric(mm)	Decimal														
3.0	.1181	8350	0.05	7250	0.05	3890	0.05	2790	0.03	3180	0.02	7250	0.04	17850	0.06	
4.0	.1575	6250	0.07	5410	0.07	2940	0.06	2100	0.04	2380	0.03	5410	0.06	13130	0.08	
5.0	.1969	5040	0.08	4360	0.08	2310	0.08	1680	0.05	1910	0.04	4360	0.07	10500	0.10	
6.0	.2362	4200	0.10	3630	0.10	1890	0.09	1370	0.06	1590	0.05	3630	0.09	8930	0.12	
8.0	.3150	3150	0.14	2730	0.13	1470	0.12	1050	0.08	1190	0.06	2730	0.12	6670	0.16	
10.0	.3937	2520	0.17	2160	0.17	1160	0.15	840	0.10	955	0.08	2160	0.15	5360	0.20	
12.0	.4724	2100	0.21	1790	0.21	1000	0.18	690	0.12	796	0.10	1790	0.18	4470	0.24	
16.0	.6299	1580	0.28	1370	0.28	740	0.24	530	0.16	597	0.12	1370	0.24	3360	0.32	
20.0	.7874	1260	0.35	1110	0.34	580	0.31	420	0.20	477	0.15	1110	0.30	2680	0.40	


RPM = rev./min.
FEED = mm/rev.



Surface Angle	Cutting Conditions	
	RPM	FEED
0° ~ 15°	100%	100%
15° ~ 30°	100%	50%
30° ~	70%	30%

- ▶ The cutting conditions are for 2xD.
- ▶ The rigid and precise machine and holder are required.
- ▶ The recommended depth of hole is measured from the highest point of the hole on drilling in inclined and angled surfaces.
- ▶ The recommended cutting conditions are those for drilling on flat and horizontal surfaces.
- ▶ Please adjust feed rate according to the above surface angle when drilling on an inclined surface.
 - The recommended feed rate 50% or lower, in case of 15°~30° of the incline angle.
 - The recommended feed rate 30% or lower and RPM 70%, in case of 30° ~ of the incline angle.
- ▶ Please decrease cutting speed as material hardness increases.
- ▶ Only use drilling tool. Side milling, traversing, helical milling are not usable.

VARIETY OF DRILLING



CARBIDE



Being the best through innovation



DREAM DRILLS -INOX

WITH COOLANT HOLES
- Stainless Steels, Nickel Alloys and Titanium up to HRC35

SELECTION GUIDE




SOLID CARBIDE DREAM DRILLS-INOX

SOLID CARBIDE DREAM DRILLS -INOX (with Coolant Holes)
- Stainless Steels, Nickel Alloys and Titanium up to HRc35

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
INCH					
3xD DH463 DH714		CARBIDE, DREAM DRILL - INOX with COOLANT HOLES	STUB	D1/8 D5/8	114
5xD DH464 DH715		CARBIDE, DREAM DRILL - INOX with COOLANT HOLES	LONG	D13/64 D/2	116
METRIC					
3xD DH451		CARBIDE, DREAM DRILL - INOX with COOLANT HOLES	SHORT	.1181 .7874	117
5xD DH452		CARBIDE, DREAM DRILL - INOX with COOLANT HOLES	LONG	.0394 .7874	122
8xD DH453		CARBIDE, DREAM DRILL - INOX with COOLANT HOLES	EXTRA LONG	.1181 .7874	127
RECOMMENDED CUTTING CONDITIONS					131

◎ : Excellent ○ : Good

P			H	M	K	N			S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	◎	○			◎		○				○
◎	◎	○			◎		○				○
◎	◎	○			◎		○				○
◎	◎	○			◎		○				○





DH463 SERIES
DH714 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES STUB

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life
- ▶ Tolerance : Dia. Tolerance ØD1 : See page 113
Shank Tolerance ØD2: -.0001-.0005



3 × D

EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length
	Fractional	Decimal					Fractional	Decimal			
TiAlN	D1		D2	L1	L2	TiAlN	D1		D2	L1	L2
DH714008	1/8	.1250	3/16	1.102	2.992	DH463020	5/16	.3125	5/16	1.575	3.701
DH463008	1/8	.1250	15/64	1.102	2.992	DH463021	21/64	.3281	11/32	1.673	3.937
DH714011	11/64	.1719	3/16	1.417	3.386	DH714021	21/64	.3281	3/8	1.673	3.937
DH463011	11/64	.1719	15/64	1.417	3.386	DH463217	Q	.3320	11/32	1.673	3.937
DH714012	3/16	.1875	3/16	1.575	3.543	DH714217	Q	.3320	3/8	1.673	3.937
DH463012	3/16	.1875	15/64	1.575	3.543	DH463022	11/32	.3438	11/32	1.772	3.937
DH463013	13/64	.2031	15/64	1.082	3.228	DH714022	11/32	.3438	3/8	1.772	3.937
DH714013	13/64	.2031	1/4	1.082	3.228	DH714023	23/64	.3594	3/8	1.870	4.174
DH463014	7/32	.2188	15/64	1.181	3.228	DH463023	23/64	.3594	25/64	1.870	4.174
DH714014	7/32	.2188	1/4	1.181	3.228	DH714221	U	.3680	3/8	1.870	4.174
DH463015	15/64	.2344	15/64	1.181	3.228	DH463221	U	.3680	25/64	1.870	4.174
DH714015	15/64	.2344	1/4	1.181	3.228	DH714024	3/8	.3750	3/8	1.969	4.174
DH714016	1/4	.2500	1/4	1.279	3.465	DH463024	3/8	.3750	25/64	1.969	4.174
DH463016	1/4	.2500	17/64	1.279	3.465	DH463025	25/64	.3906	25/64	1.969	4.174
DH463206	F	.2570	17/64	1.279	3.465	DH714025	25/64	.3906	7/16	1.969	4.174
DH714206	F	.2570	5/16	1.279	3.465	DH463026	13/32	.4062	27/64	2.067	4.567
DH463017	17/64	.2656	17/64	1.378	3.465	DH714026	13/32	.4062	7/16	2.067	4.567
DH714017	17/64	.2656	5/16	1.378	3.465	DH463027	27/64	.4219	27/64	2.165	4.567
DH463209	I	.2720	.2720	1.378	3.465	DH714027	27/64	.4219	7/16	2.165	4.567
DH714209	I	.2720	5/16	1.378	3.465	DH714028	7/16	.4375	7/16	2.264	4.803
DH463018	9/32	.2812	5/16	1.476	3.701	DH463028	7/16	.4375	15/32	2.264	4.803
DH463019	19/64	.2969	5/16	1.476	3.701	DH463029	29/64	.4531	15/32	2.264	4.803

Other shank types are available on your request.

▶ NEXT PAGE

P					H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~								
◎	◎	○			◎		○				○	



DH463 SERIES
DH714 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES STUB

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life
- ▶ Tolerance : Dia. Tolerance ØD1 : See page 113
Shank Tolerance ØD2: -.0001-.0005



3 × D

EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length
	Fractional	Decimal					Fractional	Decimal			
TiAlN	D1		D2	L1	L2	TiAlN	D1		D2	L1	L2
DH714029	29/64	.4531	1/2	2.264	4.803	DH463035	35/64	.5469	35/64	2.756	5.276
DH463030	15/32	.4688	15/32	2.362	4.803	DH714035	35/64	.5469	9/16	2.756	5.276
DH714030	15/32	.4688	1/2	2.362	4.803	DH714036	9/16	.5625	9/16	2.854	5.512
DH463031	31/64	.4844	1/2	2.461	5.039	DH463036	9/16	.5625	37/64	2.854	5.512
DH463032	1/2	.5000	1/2	2.559	5.039	DH463037	37/64	.5781	37/64	2.953	5.512
DH463033	33/64	.5156	35/64	2.657	5.276	DH714037	37/64	.5781	5/8	2.953	5.512
DH714033	33/64	.5156	9/16	2.657	5.276	DH463038	19/32	.5937	5/8	3.051	5.709
DH463034	17/32	.5312	35/64	2.756	5.276	DH463039	39/64	.6094	5/8	3.051	5.709
DH714034	17/32	.5312	9/16	2.756	5.276	DH463040	5/8	.6250	5/8	3.150	5.709

Other shank types are available on your request.

P					H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~								
◎	◎	○			◎		○				○	



DH464 SERIES
DH715 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES LONG

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life
- ▶ Tolerance : Dia. Tolerance ØD1 : See page 113
Shank Tolerance ØD2: -.0001-.0005



MG 140° 20 bar P.131 5 × D

EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length
	Fractional	Decimal					Fractional	Decimal			
TiAlN	D1		D2	L1	L2	TiAlN	D1		D2	L1	L2
DH464013	13/64	.2031	15/64	1-3/4	3-15/16	DH715022	11/32	.3438	3/8	2-27/32	5
DH715013	13/64	.2031	1/4	1-3/4	3-15/16	DH715023	23/64	.3594	3/8	3	5-23/64
DH464014	7/32	.2188	15/64	1-57/64	3-15/16	DH464023	23/64	.3594	25/64	3	5-23/64
DH715014	7/32	.2188	1/4	1-57/64	3-15/16	DH715221	U	.3680	3/8	3	5-23/64
DH464015	15/64	.2344	15/64	1-57/64	3-15/16	DH464221	U	.3680	25/64	3	5-23/64
DH715015	15/64	.2344	1/4	1-57/64	3-15/16	DH715024	3/8	.3750	3/8	3-5/32	5-23/64
DH715016	1/4	.2500	1/4	2-3/64	4-19/64	DH464024	3/8	.3750	25/64	3-5/32	5-23/64
DH464016	1/4	.2500	17/64	2-3/64	4-19/64	DH464025	25/64	.3906	25/64	3-5/32	5-23/64
DH464206	F	.2570	17/64	2-13/64	4-19/64	DH715025	25/64	.3906	7/16	3-5/32	5-23/64
DH715206	F	.2570	5/16	2-13/64	4-19/64	DH464026	13/32	.4062	27/64	3-5/16	5-7/8
DH464017	17/64	.2656	17/64	2-13/64	4-19/64	DH715026	13/32	.4062	7/16	3-5/16	5-7/8
DH715017	17/64	.2656	5/16	2-13/64	4-19/64	DH464027	27/64	.4219	27/64	3-15/32	5-7/8
DH464209	I	.2720	.2720	2-13/64	4-19/64	DH715027	27/64	.4219	7/16	3-15/32	5-7/8
DH715209	I	.2720	5/16	2-13/64	4-19/64	DH715028	7/16	.4375	7/16	3-5/8	6-7/32
DH464018	9/32	.2812	5/16	2-23/64	4-41/64	DH464028	7/16	.4375	15/32	3-5/8	6-7/32
DH464019	19/64	.2969	5/16	2-33/64	4-41/64	DH464029	29/64	.4531	15/32	3-25/32	6-7/32
DH464020	5/16	.3125	5/16	2-33/64	4-41/64	DH715029	29/64	.4531	1/2	3-25/32	6-7/32
DH464021	21/64	.3281	11/32	2-43/64	5	DH464030	15/32	.4688	15/32	3-25/32	6-7/32
DH715021	21/64	.3281	3/8	2-43/64	5	DH715030	15/32	.4688	1/2	3-25/32	6-7/32
DH464217	Q	.3320	11/32	2-43/64	5	DH464031	31/64	.4844	1/2	3-15/16	6-37/64
DH715217	Q	.3320	3/8	2-43/64	5	DH464032	1/2	.5000	1/2	4-3/32	6-37/64
DH464022	11/32	.3438	11/32	2-27/32	5						

Other shank types are available on your request.

◎ : Excellent ○ : Good


P			H		M	K	N			S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			◎		○				○



DH451 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES SHORT

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life



DIN 6537 MG h6 m7 140° 20 bar P.131 3 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH451030	3.0		.1181	6	20	62	DH451049	4.9		.1929	6	28	66
DH451031	3.1		.1220	6	20	62	DH451050	5.0		.1969	6	28	66
DH451008F	3.175	1/8	.1250	6	20	62	DH451051	5.1		.2008	6	28	66
DH451032	3.2		.1260	6	20	62	DH451013F	5.159	13/64	.2031	6	28	66
DH451033	3.3		.1299	6	20	62	DH451052	5.2		.2047	6	28	66
DH451034	3.4		.1339	6	20	62	DH451053	5.3		.2087	6	28	66
DH451035	3.5		.1378	6	20	62	DH451054	5.4		.2126	6	28	66
DH451009F	3.572	9/64	.1406	6	20	62	DH451055	5.5		.2165	6	28	66
DH451036	3.6		.1417	6	20	62	DH451014F	5.556	7/32	.2188	6	28	66
DH451037	3.7		.1457	6	20	62	DH451056	5.6		.2205	6	28	66
DH451038	3.8		.1496	6	24	66	DH451057	5.7		.2244	6	28	66
DH451039	3.9		.1535	6	24	66	DH451058	5.8		.2283	6	28	66
DH451010F	3.969	5/32	.1563	6	24	66	DH451059	5.9		.2323	6	28	66
DH451040	4.0		.1575	6	24	66	DH451015F	5.953	15/64	.2344	6	28	66
DH451041	4.1		.1614	6	24	66	DH451060	6.0		.2362	6	28	66
DH451042	4.2		.1654	6	24	66	DH451061	6.1		.2402	8	34	79
DH451043	4.3		.1693	6	24	66	DH451062	6.2		.2441	8	34	79
DH451011F	4.366	11/64	.1719	6	24	66	DH451063	6.3		.2480	8	34	79
DH451044	4.4		.1732	6	24	66	DH451016F	6.350	1/4	.2500	8	34	79
DH451045	4.5		.1772	6	24	66	DH451064	6.4		.2520	8	34	79
DH451046	4.6		.1811	6	24	66	DH451065	6.5		.2559	8	34	79
DH451047	4.7		.1850	6	24	66	DH451006L	6.528	F	.2570	8	34	79
DH451012F	4.763	3/16	.1875	6	24	66	DH451066	6.6		.2598	8	34	79
DH451048	4.8		.1890	6	28	66	DH451067	6.7		.2638	8	34	79

Other shank types are available on your request.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P			H		M	K	N			S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			◎		○				○



DH451 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES SHORT

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life



DIN 6537
MG
h6
m7
140°
20 bar
P.131
3 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH451017F	6.747	17/64	.2656	8	34	79	DH451085	8.5		.3346	10	47	89
DH451068	6.8		.2677	8	34	79	DH451086	8.6		.3386	10	47	89
DH451069	6.9		.2717	8	34	79	DH451087	8.7		.3425	10	47	89
DH451009L	6.909	I	.2720	8	34	79	DH451022F	8.731	11/32	.3438	10	47	89
DH451070	7.0		.2756	8	34	79	DH451088	8.8		.3465	10	47	89
DH451071	7.1		.2795	8	41	79	DH451089	8.9		.3504	10	47	89
DH451018F	7.144	9/32	.2812	8	41	79	DH451090	9.0		.3543	10	47	89
DH451072	7.2		.2835	8	41	79	DH451091	9.1		.3583	10	47	89
DH451073	7.3		.2874	8	41	79	DH451023F	9.128	23/64	.3594	10	47	89
DH451074	7.4		.2913	8	41	79	DH451092	9.2		.3622	10	47	89
DH451075	7.5		.2953	8	41	79	DH451093	9.3		.3661	10	47	89
DH451019F	7.541	19/64	.2969	8	41	79	DH451021L	9.347	U	.3680	10	47	89
DH451076	7.6		.2992	8	41	79	DH451094	9.4		.3701	10	47	89
DH451077	7.7		.3031	8	41	79	DH451095	9.5		.3740	10	47	89
DH451078	7.8		.3071	8	41	79	DH451024F	9.525	3/8	.3750	10	47	89
DH451079	7.9		.3110	8	41	79	DH451096	9.6		.3780	10	47	89
DH451020F	7.938	5/16	.3125	8	41	79	DH451097	9.7		.3819	10	47	89
DH451080	8.0		.3150	8	41	79	DH451098	9.8		.3858	10	47	89
DH451081	8.1		.3189	10	47	89	DH451099	9.9		.3898	10	47	89
DH451082	8.2		.3228	10	47	89	DH451025F	9.922	25/64	.3906	10	47	89
DH451083	8.3		.3268	10	47	89	DH451100	10.0		.3937	10	47	89
DH451021F	8.334	21/64	.3281	10	47	89	DH451101	10.1		.3976	12	55	102
DH451084	8.4		.3307	10	47	89	DH451102	10.2		.4016	12	55	102
DH451017L	8.433	Q	.3320	10	47	89	DH451103	10.3		.4055	12	55	102

Other shank types are available on your request.

▶ NEXT PAGE

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○		◎		○				○	



DH451 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES SHORT

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life



DIN 6537
MG
h6
m7
140°
20 bar
P.131
3 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH451026F	10.319	13/32	.4062	12	55	102	DH451123	12.3		.4843	14	60	107
DH451104	10.4		.4094	12	55	102	DH451031F	12.303	31/64	.4844	14	60	107
DH451105	10.5		.4134	12	55	102	DH451124	12.4		.4882	14	60	107
DH451106	10.6		.4173	12	55	102	DH451125	12.5		.4921	14	60	107
DH451107	10.7		.4212	12	55	102	DH451126	12.6		.4961	14	60	107
DH451027F	10.716	27/64	.4219	12	55	102	DH451032F	12.7	1/2	.5000	14	60	107
DH451108	10.8		.4252	12	55	102	DH451128	12.8		.5039	14	60	107
DH451109	10.9		.4291	12	55	102	DH451129	12.9		.5079	14	60	107
DH451110	11.0		.4330	12	55	102	DH451130	13.0		.5118	14	60	107
DH451111	11.1		.4370	12	55	102	DH451131	13.1		.5157	14	60	107
DH451028F	11.113	7/16	.4375	12	55	102	DH451132	13.2		.5197	14	60	107
DH451112	11.2		.4409	12	55	102	DH451133	13.3		.5236	14	60	107
DH451113	11.3		.4448	12	55	102	DH451134	13.4		.5276	14	60	107
DH451114	11.4		.4488	12	55	102	DH451135	13.5		.5314	14	60	107
DH451115	11.5		.4527	12	55	102	DH451136	13.6		.5354	14	60	107
DH451029F	11.509	29/64	.4531	12	55	102	DH451137	13.7		.5394	14	60	107
DH451116	11.6		.4566	12	55	102	DH451138	13.8		.5433	14	60	107
DH451117	11.7		.4606	12	55	102	DH451139	13.9		.5472	14	60	107
DH451118	11.8		.4645	12	55	102	DH451140	14.0		.5512	14	60	107
DH451119	11.9		.4685	12	55	102	DH451141	14.1		.5551	16	65	115
DH451030F	11.906	15/32	.4688	12	55	102	DH451142	14.2		.5591	16	65	115
DH451120	12.0		.4724	12	55	102	DH451036F	14.288	9/16	.5625	16	65	115
DH451121	12.1		.4764	14	60	107	DH451143	14.3		.5630	16	65	115
DH451122	12.2		.4803	14	60	107	DH451144	14.4		.5669	16	65	115

Other shank types are available on your request.

▶ NEXT PAGE


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○		◎		○				○	



DH451 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES SHORT

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life



DIN 6537
MG
h6
m7
140°
20 bar
P.131
3 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH451145	14.5		.5708	16	65	115	DH451168	16.8		.6614	18	73	123
DH451146	14.6		.5748	16	65	115	DH451169	16.9		.6654	18	73	123
DH451147	14.7		.5787	16	65	115	DH451170	17.0		.6692	18	73	123
DH451148	14.8		.5827	16	65	115	DH451171	17.1		.6732	18	73	123
DH451149	14.9		.5866	16	65	115	DH451172	17.2		.6772	18	73	123
DH451150	15.0		.5905	16	65	115	DH451173	17.3		.6811	18	73	123
DH451151	15.1		.5945	16	65	115	DH451174	17.4		.6850	18	73	123
DH451152	15.2		.5984	16	65	115	DH451044F	17.463	11/16	.6875	18	73	123
DH451153	15.3		.6024	16	65	115	DH451175	17.5		.6889	18	73	123
DH451154	15.4		.6063	16	65	115	DH451176	17.6		.6929	18	73	123
DH451155	15.5		.6102	16	65	115	DH451177	17.7		.6968	18	73	123
DH451156	15.6		.6142	16	65	115	DH451178	17.8		.7008	18	73	123
DH451157	15.7		.6181	16	65	115	DH451179	17.9		.7047	18	73	123
DH451158	15.8		.6220	16	65	115	DH451180	18.0		.7087	18	73	123
DH451040F	15.875	5/8	.6250	16	65	115	DH451181	18.1		.7126	20	79	131
DH451159	15.9		.6260	16	65	115	DH451182	18.2		.7165	20	79	131
DH451160	16.0		.6299	16	65	115	DH451183	18.3		.7205	20	79	131
DH451161	16.1		.6339	18	73	123	DH451184	18.4		.7244	20	79	131
DH451162	16.2		.6378	18	73	123	DH451185	18.5		.7283	20	79	131
DH451163	16.3		.6417	18	73	123	DH451186	18.6		.7323	20	79	131
DH451164	16.4		.6457	18	73	123	DH451187	18.7		.7362	20	79	131
DH451165	16.5		.6495	18	73	123	DH451188	18.8		.7402	20	79	131
DH451166	16.6		.6535	18	73	123	DH451189	18.9		.7441	20	79	131
DH451167	16.7		.6575	18	73	123	DH451190	19.0		.7480	20	79	131

Other shank types are available on your request.

▶ NEXT PAGE

P					H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~								
◎	◎	○			◎		○				○	



DH451 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES SHORT

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life



DIN 6537
MG
h6
m7
140°
20 bar
P.131
3 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH451048F	19.050	3/4	.7500	20	79	131	DH451196	19.6		.7717	20	79	131
DH451191	19.1		.7520	20	79	131	DH451197	19.7		.7756	20	79	131
DH451192	19.2		.7559	20	79	131	DH451198	19.8		.7795	20	79	131
DH451193	19.3		.7598	20	79	131	DH451199	19.9		.7835	20	79	131
DH451194	19.4		.7638	20	79	131	DH451200	20.0		.7874	20	79	131
DH451195	19.5		.7676	20	79	131							

Other shank types are available on your request.


P					H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~								
◎	◎	○			◎		○				○	



DH452 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES LONG

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life



DIN 6537
MG
h6
m7
140°
20 bar
P.131
5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH452010	1.0		.0394	3	8	55	DH452008F	3.175	1/8	.1250	6	28	66
DH452011	1.1		.0433	3	12	55	DH452032	3.2		.1260	6	28	66
DH452012	1.2		.0472	3	12	55	DH452033	3.3		.1299	6	28	66
DH452013	1.3		.0512	3	12	55	DH452034	3.4		.1339	6	28	66
DH452014	1.4		.0551	3	12	55	DH452035	3.5		.1378	6	28	66
DH452015	1.5		.0591	3	16	55	DH452009F	3.572	9/64	.1406	6	28	66
DH452004F	1.588	1/16	.0625	3	16	55	DH452036	3.6		.1417	6	28	66
DH452016	1.6		.0630	3	16	55	DH452037	3.7		.1457	6	28	66
DH452017	1.7		.0669	3	16	55	DH452038	3.8		.1496	6	36	74
DH452018	1.8		.0709	3	16	55	DH452039	3.9		.1535	6	36	74
DH452019	1.9		.0748	3	16	55	DH452010F	3.969	5/32	.1563	6	36	74
DH452005F	1.984	5/64	.0781	3	16	55	DH452040	4.0		.1575	6	36	74
DH452020	2.0		.0787	4	21	57	DH452041	4.1		.1614	6	36	74
DH452021	2.1		.0827	4	21	57	DH452042	4.2		.1654	6	36	74
DH452022	2.2		.0866	4	21	57	DH452043	4.3		.1693	6	36	74
DH452023	2.3		.0906	4	21	57	DH452011F	4.366	11/64	.1719	6	36	74
DH452006F	2.381	3/32	.0938	4	21	57	DH452044	4.4		.1732	6	36	74
DH452024	2.4		.0945	4	21	57	DH452045	4.5		.1772	6	36	74
DH452025	2.5		.0984	4	21	57	DH452046	4.6		.1811	6	36	74
DH452026	2.6		.1024	4	21	57	DH452047	4.7		.1850	6	36	74
DH452027	2.7		.1063	4	21	57	DH452012F	4.763	3/16	.1875	6	36	74
DH452007F	2.778	7/64	.1094	4	21	57	DH452048	4.8		.1890	6	44	82
DH452028	2.8		.1102	4	21	57	DH452049	4.9		.1929	6	44	82
DH452029	2.9		.1142	4	21	57	DH452050	5.0		.1969	6	44	82
DH452030	3.0		.1181	6	28	66	DH452051	5.1		.2008	6	44	82
DH452031	3.1		.1220	6	28	66	DH452013F	5.159	13/64	.2031	6	44	82

Other shank types are available on your request. ▶ NEXT PAGE


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○		◎		○				○	



DH452 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES LONG

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life



DIN 6537
MG
h6
m7
140°
20 bar
P.131
5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH452052	5.2		.2047	6	44	82	DH452018F	7.144	9/32	.2812	8	53	91
DH452053	5.3		.2087	6	44	82	DH452072	7.2		.2835	8	53	91
DH452054	5.4		.2126	6	44	82	DH452073	7.3		.2874	8	53	91
DH452055	5.5		.2165	6	44	82	DH452074	7.4		.2913	8	53	91
DH452014F	5.556	7/32	.2188	6	44	82	DH452075	7.5		.2953	8	53	91
DH452056	5.6		.2205	6	44	82	DH452019F	7.541	19/64	.2969	8	53	91
DH452057	5.7		.2244	6	44	82	DH452076	7.6		.2992	8	53	91
DH452058	5.8		.2283	6	44	82	DH452077	7.7		.3031	8	53	91
DH452059	5.9		.2323	6	44	82	DH452078	7.8		.3071	8	53	91
DH452015F	5.953	15/64	.2344	6	44	82	DH452079	7.9		.3110	8	53	91
DH452060	6.0		.2362	6	44	82	DH452020F	7.938	5/16	.3125	8	53	91
DH452061	6.1		.2402	8	53	91	DH452080	8.0		.3150	8	53	91
DH452062	6.2		.2441	8	53	91	DH452081	8.1		.3189	10	61	103
DH452063	6.3		.2480	8	53	91	DH452082	8.2		.3228	10	61	103
DH452016F	6.350	1/4	.2500	8	53	91	DH452083	8.3		.3268	10	61	103
DH452064	6.4		.2520	8	53	91	DH452021F	8.334	21/64	.3281	10	61	103
DH452065	6.5		.2559	8	53	91	DH452084	8.4		.3307	10	61	103
DH452006L	6.528	F	.2570	8	53	91	DH452017L	8.433	Q	.3320	10	61	103
DH452066	6.6		.2598	8	53	91	DH452085	8.5		.3346	10	61	103
DH452067	6.7		.2638	8	53	91	DH452086	8.6		.3386	10	61	103
DH452017F	6.747	17/64	.2656	8	53	91	DH452087	8.7		.3425	10	61	103
DH452068	6.8		.2677	8	53	91	DH452022F	8.731	11/32	.3438	10	61	103
DH452069	6.9		.2717	8	53	91	DH452088	8.8		.3465	10	61	103
DH452009L	6.909	I	.2720	8	53	91	DH452089	8.9		.3504	10	61	103
DH452070	7.0		.2756	8	53	91	DH452090	9.0		.3543	10	61	103
DH452071	7.1		.2795	8	53	91	DH452091	9.1		.3583	10	61	103

Other shank types are available on your request. ▶ NEXT PAGE


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○		◎		○				○	



DH452 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES LONG

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life



DIN 6537
MG
h6
m7
140°
20 bar
P.131
5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH452023F	9.128	23/64	.3594	10	61	103	DH452028F	11.113	7/16	.4375	12	71	118
DH452092	9.2		.3622	10	61	103	DH452112	11.2		.4409	12	71	118
DH452093	9.3		.3661	10	61	103	DH452113	11.3		.4448	12	71	118
DH452021L	9.347	U	.3680	10	61	103	DH452114	11.4		.4488	12	71	118
DH452094	9.4		.3701	10	61	103	DH452115	11.5		.4527	12	71	118
DH452095	9.5		.3740	10	61	103	DH452029F	11.509	29/64	.4531	12	71	118
DH452024F	9.525	3/8	.3750	10	61	103	DH452116	11.6		.4566	12	71	118
DH452096	9.6		.3780	10	61	103	DH452117	11.7		.4606	12	71	118
DH452097	9.7		.3819	10	61	103	DH452118	11.8		.4645	12	71	118
DH452098	9.8		.3858	10	61	103	DH452119	11.9		.4685	12	71	118
DH452099	9.9		.3898	10	61	103	DH452030F	11.906	15/32	.4688	12	71	118
DH452025F	9.922	25/64	.3906	10	61	103	DH452120	12.0		.4724	12	71	118
DH452100	10.0		.3937	10	61	103	DH452121	12.1		.4764	14	77	124
DH452101	10.1		.3976	12	71	118	DH452122	12.2		.4803	14	77	124
DH452102	10.2		.4016	12	71	118	DH452123	12.3		.4843	14	77	124
DH452103	10.3		.4055	12	71	118	DH452031F	12.303	31/64	.4844	14	77	124
DH452026F	10.319	13/32	.4062	12	71	118	DH452124	12.4		.4882	14	77	124
DH452104	10.4		.4094	12	71	118	DH452125	12.5		.4921	14	77	124
DH452105	10.5		.4134	12	71	118	DH452126	12.6		.4961	14	77	124
DH452106	10.6		.4173	12	71	118	DH452032F	12.7	1/2	.5000	14	77	124
DH452107	10.7		.4212	12	71	118	DH452128	12.8		.5039	14	77	124
DH452027F	10.716	27/64	.4219	12	71	118	DH452129	12.9		.5079	14	77	124
DH452108	10.8		.4252	12	71	118	DH452130	13.0		.5118	14	77	124
DH452109	10.9		.4291	12	71	118	DH452131	13.1		.5157	14	77	124
DH452110	11.0		.4330	12	71	118	DH452132	13.2		.5197	14	77	124
DH452111	11.1		.4370	12	71	118	DH452133	13.3		.5236	14	77	124

© : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55								HRC55~
◎	◎	○		◎		○				○	



DH452 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES LONG

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life



DIN 6537
MG
h6
m7
140°
20 bar
P.131
5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH452134	13.4		.5276	14	77	124	DH452040F	15.875	5/8	.6250	16	83	133
DH452135	13.5		.5314	14	77	124	DH452159	15.9		.6260	16	83	133
DH452136	13.6		.5354	14	77	124	DH452160	16.0		.6299	16	83	133
DH452137	13.7		.5394	14	77	124	DH452161	16.1		.6339	18	93	143
DH452138	13.8		.5433	14	77	124	DH452162	16.2		.6378	18	93	143
DH452139	13.9		.5472	14	77	124	DH452163	16.3		.6417	18	93	143
DH452140	14.0		.5512	14	77	124	DH452164	16.4		.6457	18	93	143
DH452141	14.1		.5551	16	83	133	DH452165	16.5		.6495	18	93	143
DH452142	14.2		.5591	16	83	133	DH452166	16.6		.6535	18	93	143
DH452036F	14.288	9/16	.5625	16	83	133	DH452167	16.7		.6575	18	93	143
DH452143	14.3		.5630	16	83	133	DH452168	16.8		.6614	18	93	143
DH452144	14.4		.5669	16	83	133	DH452169	16.9		.6654	18	93	143
DH452145	14.5		.5708	16	83	133	DH452170	17.0		.6692	18	93	143
DH452146	14.6		.5748	16	83	133	DH452171	17.1		.6732	18	93	143
DH452147	14.7		.5787	16	83	133	DH452172	17.2		.6772	18	93	143
DH452148	14.8		.5827	16	83	133	DH452173	17.3		.6811	18	93	143
DH452149	14.9		.5866	16	83	133	DH452174	17.4		.6850	18	93	143
DH452150	15.0		.5905	16	83	133	DH452175	17.5		.6889	18	93	143
DH452151	15.1		.5945	16	83	133	DH452176	17.6		.6929	18	93	143
DH452152	15.2		.5984	16	83	133	DH452177	17.7		.6968	18	93	143
DH452153	15.3		.6024	16	83	133	DH452178	17.8		.7008	18	93	143
DH452154	15.4		.6063	16	83	133	DH452179	17.9		.7047	18	93	143
DH452155	15.5		.6102	16	83	133	DH452180	18.0		.7087	18	93	143
DH452156	15.6		.6142	16	83	133	DH452181	18.1		.7126	20	101	153
DH452157	15.7		.6181	16	83	133	DH452182	18.2		.7165	20	101	151
DH452158	15.8		.6220	16	83	133	DH452183	18.3		.7205	20	101	151

© : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55								HRC55~
◎	◎	○		◎		○				○	



DH452 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES LONG

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life



DIN 6537
MG
h6
m7
140°
20 bar
P.131
5 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH452184	18.4		.7244	20	101	153	DH452192	19.2		.7559	20	101	151
DH452185	18.5		.7283	20	101	153	DH452193	19.3		.7598	20	101	151
DH452186	18.6		.7323	20	101	151	DH452194	19.4		.7638	20	101	151
DH452187	18.7		.7362	20	101	153	DH452195	19.5		.7676	20	101	153
DH452188	18.8		.7402	20	101	153	DH452196	19.6		.7717	20	101	151
DH452189	18.9		.7441	20	101	153	DH452197	19.7		.7756	20	101	151
DH452190	19.0		.7480	20	101	153	DH452198	19.8		.7795	20	101	153
DH452048F	19.050	3/4	.7500	20	101	153	DH452199	19.9		.7835	20	101	151
DH452191	19.1		.7520	20	101	151	DH452200	20.0		.7874	20	101	153

Other shank types are available on your request.

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~								
◎	◎	○		◎		○				○	



DH453 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES EXTRA LONG

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life



DIN 6537
MG
h6
m7
140°
20 bar
P.131
8 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH453030	3.0		.1181	6	34	72	DH453049	4.9		.1929	6	57	95
DH453031	3.1		.1220	6	34	72	DH453050	5.0		.1969	6	57	95
DH453008F	3.175	1/8	.1250	6	34	72	DH453051	5.1		.2008	6	57	95
DH453032	3.2		.1260	6	34	72	DH453013F	5.159	13/64	.2031	6	57	95
DH453033	3.3		.1299	6	34	72	DH453052	5.2		.2047	6	57	95
DH453034	3.4		.1339	6	34	72	DH453053	5.3		.2087	6	57	95
DH453229G	3.454	#29	.1360	6	34	72	DH453054	5.4		.2126	6	57	95
DH453035	3.5		.1378	6	34	72	DH453055	5.5		.2165	6	57	95
DH453009F	3.572	9/64	.1406	6	34	72	DH453014F	5.556	7/32	.2188	6	57	95
DH453036	3.6		.1417	6	34	72	DH453056	5.6		.2205	6	57	95
DH453037	3.7		.1457	6	34	72	DH453057	5.7		.2244	6	57	95
DH453038	3.8		.1496	6	43	81	DH453058	5.8		.2283	6	57	95
DH453039	3.9		.1535	6	43	81	DH453059	5.9		.2323	6	57	95
DH453010F	3.969	5/32	.1563	6	43	81	DH453015F	5.953	15/64	.2344	6	57	95
DH453040	4.0		.1575	6	43	81	DH453060	6.0		.2362	6	57	95
DH453221G	4.038	#21	.1590	6	43	81	DH453061	6.1		.2402	8	76	114
DH453041	4.1		.1614	6	43	81	DH453062	6.2		.2441	8	76	114
DH453042	4.2		.1654	6	43	81	DH453063	6.3		.2480	8	76	114
DH453043	4.3		.1693	6	43	81	DH453016F	6.350	1/4	.2500	8	76	114
DH453011F	4.366	11/64	.1719	6	43	81	DH453064	6.4		.2520	8	76	114
DH453044	4.4		.1732	6	43	81	DH453065	6.5		.2559	8	76	114
DH453045	4.5		.1772	6	43	81	DH453106L	6.527	F	.2570	8	76	114
DH453046	4.6		.1811	6	43	81	DH453066	6.6		.2598	8	76	114
DH453047	4.7		.1850	6	43	81	DH453067	6.7		.2638	8	76	114
DH453012F	4.763	3/16	.1875	6	57	95	DH453017F	6.747	17/64	.2656	8	76	114
DH453048	4.8		.1890	6	57	95	DH453068	6.8		.2677	8	76	114

Other shank types are available on your request.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~								
◎	◎	○		◎		○				○	



DH453 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES EXTRA LONG

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life



DIN 6537
MG
h6
m7
140°
20 bar
P.131
8 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH453069	6.9		.2717	8	76	114	DH453088	8.8		.3465	10	95	142
DH453009L	6.909	I	.2720	8	76	114	DH453089	8.9		.3504	10	95	142
DH453070	7.0		.2756	8	76	114	DH453090	9.0		.3543	10	95	142
DH453071	7.1		.2795	8	76	114	DH453091	9.1		.3583	10	95	142
DH453018F	7.144	9/32	.2813	8	76	114	DH453023F	9.128	23/64	.3594	10	95	142
DH453072	7.2		.2835	8	76	114	DH453092	9.2		.3622	10	95	142
DH453073	7.3		.2874	8	76	114	DH453093	9.3		.3661	10	95	142
DH453074	7.4		.2913	8	76	114	DH453121L	9.347	U	.3680	10	95	142
DH453075	7.5		.2953	8	76	114	DH453094	9.4		.3701	10	95	142
DH453019F	7.541	19/64	.2969	8	76	114	DH453095	9.5		.3740	10	95	142
DH453076	7.6		.2992	8	76	114	DH453024F	9.525	3/8	.3750	10	95	142
DH453077	7.7		.3031	8	76	114	DH453096	9.6		.3780	10	95	142
DH453078	7.8		.3071	8	76	114	DH453097	9.7		.3819	10	95	142
DH453079	7.9		.3110	8	76	114	DH453098	9.8		.3858	10	95	142
DH453020F	7.938	5/16	.3125	8	76	114	DH453099	9.9		.3898	10	95	142
DH453080	8.0		.3150	8	76	114	DH453025F	9.922	25/64	.3906	10	95	142
DH453081	8.1		.3189	10	95	142	DH453100	10.0		.3937	10	95	142
DH453082	8.2		.3228	10	95	142	DH453101	10.1		.3976	12	114	162
DH453083	8.3		.3268	10	95	142	DH453102	10.2		.4016	12	114	162
DH453021F	8.334	21/64	.3281	10	95	142	DH453103	10.3		.4055	12	114	162
DH453084	8.4		.3307	10	95	142	DH453026F	10.319	13/32	.4063	12	114	162
DH453117L	8.432	Q	.3320	10	95	142	DH453104	10.4		.4094	12	114	162
DH453085	8.5		.3346	10	95	142	DH453105	10.5		.4134	12	114	162
DH453086	8.6		.3386	10	95	142	DH453106	10.6		.4173	12	114	162
DH453087	8.7		.3425	10	95	142	DH453107	10.7		.4212	12	114	162
DH453022F	8.731	11/32	.3438	10	95	142	DH453027F	10.716	27/64	.4219	12	114	162

Other shank types are available on your request. ▶ NEXT PAGE


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~							
◎	◎	○		◎		○				○	



DH453 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES EXTRA LONG

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life



DIN 6537
MG
h6
m7
140°
20 bar
P.131
8 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH453108	10.8		.4252	12	114	162	DH453130	13.0		.5118	14	133	178
DH453109	10.9		.4291	12	114	162	DH453033F	13.097	33/64	.5156	14	133	178
DH453110	11.0		.4330	12	114	162	DH453131	13.1		.5157	14	133	178
DH453111	11.1		.4370	12	114	162	DH453132	13.2		.5197	14	133	178
DH453028F	11.113	7/16	.4375	12	114	162	DH453133	13.3		.5236	14	133	178
DH453112	11.2		.4409	12	114	162	DH453134	13.4		.5276	14	133	178
DH453113	11.3		.4448	12	114	162	DH453135	13.5		.5314	14	133	178
DH453114	11.4		.4488	12	114	162	DH453136	13.6		.5354	14	133	178
DH453115	11.5		.4527	12	114	162	DH453137	13.7		.5394	14	133	178
DH453029F	11.509	29/64	.4531	12	114	162	DH453138	13.8		.5433	14	133	178
DH453116	11.6		.4566	12	114	162	DH453139	13.9		.5472	14	133	178
DH453117	11.7		.4606	12	114	162	DH453140	14.0		.5512	14	133	178
DH453118	11.8		.4645	12	114	162	DH453141	14.1		.5551	16	152	203
DH453119	11.9		.4685	12	114	162	DH453142	14.2		.5591	16	152	203
DH453030F	11.906	15/32	.4688	12	114	162	DH453036F	14.288	9/16	.5625	16	152	203
DH453120	12.0		.4724	12	114	162	DH453143	14.3		.5630	16	152	203
DH453121	12.1		.4764	14	133	178	DH453144	14.4		.5669	16	152	203
DH453122	12.2		.4803	14	133	178	DH453145	14.5		.5709	16	152	203
DH453123	12.3		.4843	14	133	178	DH453146	14.6		.5748	16	152	203
DH453031F	12.303	31/64	.4844	14	133	178	DH453147	14.7		.5787	16	152	203
DH453124	12.4		.4882	14	133	178	DH453148	14.8		.5827	16	152	203
DH453125	12.5		.4921	14	133	178	DH453149	14.9		.5866	16	152	203
DH453126	12.6		.4961	14	133	178	DH453150	15.0		.5905	16	152	203
DH453032F	12.7	1/2	.5000	14	133	178	DH453151	15.1		.5945	16	152	203
DH453128	12.8		.5039	14	133	178	DH453152	15.2		.5984	16	152	203
DH453129	12.9		.5079	14	133	178	DH453153	15.3		.6024	16	152	203

Other shank types are available on your request. ▶ NEXT PAGE


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~							
◎	◎	○		◎		○				○	



DH453 SERIES

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES EXTRA LONG

- ▶ Special flute shape and geometry suitable for machining stainless steel
- ▶ Excellent chip evacuation from better surface treatment
- ▶ Point R-thinning achieves superior centering and chip curling
- ▶ TiAlN coating for better surface finishes and longer tool life



DIN 6537
MG
h6
m7
140°
20 bar
P.131
8 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
	D1			D2	L1	L2		D1			D2	L1	L2
	TiAlN							TiAlN					
DH453154	15.4		.6063	16	152	203	DH453178	17.8		.7008	18	171	222
DH453155	15.5		.6102	16	152	203	DH453179	17.9		.7047	18	171	222
DH453156	15.6		.6142	16	152	203	DH453180	18.0		.7087	18	171	222
DH453157	15.7		.6181	16	152	203	DH453181	18.1		.7126	20	190	243
DH453158	15.8		.6220	16	152	203	DH453182	18.2		.7165	20	190	243
DH453040F	15.875	5/8	.6250	16	152	203	DH453183	18.3		.7205	20	190	243
DH453159	15.9		.6260	16	152	203	DH453184	18.4		.7244	20	190	243
DH453160	16.0		.6299	16	152	203	DH453185	18.5		.7283	20	190	243
DH453161	16.1		.6339	18	171	222	DH453186	18.6		.7323	20	190	243
DH453162	16.2		.6378	18	171	222	DH453187	18.7		.7362	20	190	243
DH453163	16.3		.6417	18	171	222	DH453188	18.8		.7402	20	190	243
DH453164	16.4		.6457	18	171	222	DH453189	18.9		.7441	20	190	243
DH453165	16.5		.6496	18	171	222	DH453190	19.0		.7480	20	190	243
DH453166	16.6		.6535	18	171	222	DH453048F	19.050	3/4	.7500	20	190	243
DH453167	16.7		.6575	18	171	222	DH453191	19.1		.7520	20	190	243
DH453168	16.8		.6614	18	171	222	DH453192	19.2		.7559	20	190	243
DH453169	16.9		.6654	18	171	222	DH453193	19.3		.7598	20	190	243
DH453170	17.0		.6693	18	171	222	DH453194	19.4		.7638	20	190	243
DH453171	17.1		.6732	18	171	222	DH453195	19.5		.7677	20	190	243
DH453172	17.2		.6772	18	171	222	DH453196	19.6		.7717	20	190	243
DH453173	17.3		.6811	18	171	222	DH453197	19.7		.7756	20	190	243
DH453174	17.4		.6850	18	171	222	DH453198	19.8		.7795	20	190	243
DH453175	17.5		.6890	18	171	222	DH453199	19.9		.7835	20	190	243
DH453176	17.6		.6929	18	171	222	DH453200	20.0		.7874	20	190	243
DH453177	17.7		.6968	18	171	222							

Other shank types are available on your request.

P				H	M	K	N			S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			◎		○				○



RECOMMENDED CUTTING CONDITIONS

CARBIDE, DREAM DRILL - INOX with COOLANT HOLES, TiAlN-COATED

DH451, DH463, DH714, DH452, DH464, DH715, DH453 SERIES

WORK MATERIAL	P			M			N							
	CARBON STEELS ALLOY STEELS			STAINLESS STEELS			STAINLESS STEELS			ALUMINUM				
STRENGTH				< 800 N/mm ²			> 800 N/mm ²			< 10% Si				
DRILLING SPEED(SFM)	260 ~ 410 ft/min			120 ~ 230 ft/min			60 ~ 140 ft/min			490 ~ 720 ft/min				
DIAMETER			RPM	FEED	IPR	RPM	FEED	IPR	RPM	FEED	IPR	RPM	FEED	IPR
Metric(mm)	Decimal	Fractional												
1.0	.0394		26000	0.02	.001	12000	0.02	.001	6200	0.02	.001	48000	0.04	.002
1.5	.0591		18000	0.03	.001	9000	0.03	.001	5400	0.02	.001	43000	0.05	.002
2.5	.0984		10800	0.05	.002	7000	0.04	.002	4200	0.03	.001	25500	0.08	.003
3.0	.1181	1/8	13000	0.04	.002	7400	0.04	.002	4700	0.02	.001	23000	0.12	.005
4.0	.1575	5/32	10000	0.05	.002	5600	0.05	.002	3600	0.03	.001	17500	0.18	.007
5.0	.1969	13/64	8000	0.05	.002	4400	0.05	.002	2800	0.03	.001	14000	0.20	.008
6.0	.2362	15/64	6600	0.06	.002	3700	0.06	.002	2400	0.04	.002	11700	0.25	.010
8.0	.3150	5/16	5000	0.08	.003	2800	0.08	.003	1800	0.06	.002	8800	0.30	.012
10.0	.3937	25/64	4000	0.10	.004	2200	0.10	.004	1400	0.08	.003	7000	0.40	.016
12.0	.4724	15/32	3300	0.12	.005	1900	0.12	.005	1200	0.10	.004	5800	0.50	.020
14.0	.5512	35/64	2800	0.15	.006	1600	0.15	.006	1000	0.12	.005	5000	0.60	.024
16.0	.6299	5/8	2500	0.20	.008	1400	0.20	.008	900	0.15	.006	4380	0.80	.031
18.0	.7087	45/64	2200	0.22	.009	1250	0.22	.009	800	0.17	.007	3900	1.00	.039
20.0	.7874	25/32	2000	0.24	.009	1120	0.24	.009	720	0.19	.007	3500	1.20	.047

WORK MATERIAL	N			S							
	ALUMINUM			NON FERROUS			TITANIUM TITANIUM ALLOYS				
STRENGTH	< 10% Si										
DRILLING SPEED(SFM)	390 ~ 570 ft/min			390 ~ 490 ft/min			80 ~ 160 ft/min				
DIAMETER			RPM	FEED	IPR	RPM	FEED	IPR	RPM	FEED	IPR
Metric(mm)	Decimal	Fractional									
1.0	.0394		38000	0.03	.001	38000	0.02	.001	8100	0.01	.0004
1.5	.0591		32000	0.04	.002	25500	0.03	.001	7500	0.01	.0004
2.5	.0984		19500	0.06	.002	15500	0.05	.002	4500	0.02	.001
3.0	.1181	1/8	18500	0.10	.004	16000	0.08	.003	5300	0.03	.001
4.0	.1575	5/32	13900	0.15	.006	11900	0.10	.004	4000	0.04	.002
5.0	.1969	13/64	11000	0.18	.007	9500	0.12	.005	3200	0.05	.002
6.0	.2362	15/64	9300	0.25	.010	8000	0.15	.006	2650	0.06	.002
8.0	.3150	5/16	7000	0.30	.012	6000	0.18	.007	2000	0.07	.003
10.0	.3937	25/64	5600	0.35	.014	4800	0.22	.009	1600	0.08	.003
12.0	.4724	15/32	4600	0.40	.016	4000	0.26	.010	1300	0.10	.004
14.0	.5512	35/64	4000	0.50	.020	3400	0.30	.012	1100	0.12	.005
16.0	.6299	5/8	3500	0.60	.024	3000	0.40	.016	1000	0.14	.006
18.0	.7087	45/64	3100	0.70	.028	2650	0.45	.018	900	0.16	.006
20.0	.7874	25/32	2800	0.80	.031	2400	0.50	.020	800	0.18	.007


- ▶ Recommend to reduce the feed rate as following
- DH463/DH714/DH451(3xD), DH464/DH714/DH452(5xD) : Feed 100%
- DH453(8xD) : Feed 85%

RPM = rev./min.
FEED = mm/rev.
IPR = inch/rev



Being the best through innovation


CARBIDE



DREAM DRILLS -ALU

WITH COOLANT HOLES
- for Aluminum & Aluminum Alloys



Global Cutting Tool Leader **YG-1**



SELECTION GUIDE



SOLID CARBIDE DREAM DRILLS-ALU

SOLID CARBIDE DREAM DRILLS - ALU (with Coolant Holes)
- for Aluminum & Aluminum Alloys

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
INCH					
5xD DGE466 DGE718		CARBIDE, DREAM DRILL - ALU with COOLANT HOLES	LONG	D13/64 D1/2	136
METRIC					
5xD DGE433		CARBIDE, DREAM DRILL - ALU with COOLANT HOLES	LONG	.1181 .7874	137
		RECOMMENDED CUTTING CONDITIONS			141

⊙ : Excellent ○ : Good

Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		M	K	N			S	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
							⊙				
							⊙				





DGE466 SERIES
DGE718 SERIES

CARBIDE, DREAM DRILL - ALU with COOLANT HOLES LONG

- ▶ Optimized thinning for Aluminum & Aluminum Alloys to prevent any clogging from chip welding
- ▶ Wider and deeper flute gullets for maximum chip removal
- ▶ Special geometry and smooth coating reduces built up edge and improves finishes
- ▶ Tolerance : Dia. Tolerance ØD1 : See page 135
Shank Tolerance ØD2: -.0001 -.0005



MG h6 118° 20 bar P.141 5 × D

EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length
	Fractional	Decimal					Fractional	Decimal			
DLC	D1		D2	L1	L2	DLC	D1		D2	L1	L2
DGE466013	13/64	.2031	15/64	1-3/4	3-15/16	DGE718022	11/32	.3438	3/8	2-27/32	5
DGE718013	13/64	.2031	1/4	1-3/4	3-15/16	DGE718023	23/64	.3594	3/8	3	5-23/64
DGE466014	7/32	.2188	15/64	1-57/64	3-15/16	DGE466023	23/64	.3594	25/64	3	5-23/64
DGE718014	7/32	.2188	1/4	1-57/64	3-15/16	DGE718221	U	.3680	3/8	3	5-23/64
DGE466015	15/64	.2344	15/64	1-57/64	3-15/16	DGE466221	U	.3680	25/64	3	5-23/64
DGE718015	15/64	.2344	1/4	1-57/64	3-15/16	DGE718024	3/8	.3750	3/8	3-5/32	5-23/64
DGE718016	1/4	.2500	1/4	2-3/64	4-19/64	DGE466024	3/8	.3750	25/64	3-5/32	5-23/64
DGE466016	1/4	.2500	17/64	2-3/64	4-19/64	DGE466025	25/64	.3906	25/64	3-5/32	5-23/64
DGE466206	F	.2570	17/64	2-13/64	4-19/64	DGE718025	25/64	.3906	7/16	3-5/32	5-23/64
DGE718206	F	.2570	5/16	2-13/64	4-19/64	DGE466026	13/32	.4062	27/64	3-5/16	5-7/8
DGE466017	17/64	.2656	17/64	2-13/64	4-19/64	DGE718026	13/32	.4062	7/16	3-5/16	5-7/8
DGE718017	17/64	.2656	5/16	2-13/64	4-19/64	DGE466027	27/64	.4219	27/64	3-15/32	5-7/8
DGE466209	I	.2720	.272	2-13/64	4-19/64	DGE718027	27/64	.4219	7/16	3-15/32	5-7/8
DGE718209	I	.2720	5/16	2-13/64	4-19/64	DGE718028	7/16	.4375	7/16	3-5/8	6-7/32
DGE466018	9/32	.2812	5/16	2-23/64	4-41/64	DGE466028	7/16	.4375	15/32	3-5/8	6-7/32
DGE466019	19/64	.2969	5/16	2-33/64	4-41/64	DGE466029	29/64	.4531	15/32	3-25/32	6-7/32
DGE466020	5/16	.3125	5/16	2-33/64	4-41/64	DGE718029	29/64	.4531	1/2	3-25/32	6-7/32
DGE466021	21/64	.3281	11/32	2-43/64	5	DGE466030	15/32	.4688	15/32	3-25/32	6-7/32
DGE718021	21/64	.3281	3/8	2-43/64	5	DGE718030	15/32	.4688	1/2	3-25/32	6-7/32
DGE466217	Q	.3320	11/32	2-43/64	5	DGE466031	31/64	.4844	1/2	3-15/16	6-37/64
DGE718217	Q	.3320	3/8	2-43/64	5	DGE466032	1/2	.5000	1/2	4-3/32	6-37/64
DGE466022	11/32	.3438	11/32	2-27/32	5						

Other shank types are available on your request.

© : Excellent ○ : Good

P			H		M	K	N			S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							



DGE433 SERIES

CARBIDE, DREAM DRILL - ALU with COOLANT HOLES LONG

- ▶ Optimized thinning for Aluminum & Aluminum Alloys to prevent any clogging from chip welding
- ▶ Wider and deeper flute gullets for maximum chip removal
- ▶ Special geometry and smooth coating reduces built up edge and improves finishes



DIN 6537 MG h6 m7 118° 20 bar P.141 5 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
DLC	D1			D2	L1	L2	DLC	D1			D2	L1	L2
DGE433030	3.0		.1181	6	28	66	DGE433049	4.9		.1929	6	44	82
DGE433031	3.1		.1220	6	28	66	DGE433050	5.0		.1969	6	44	82
DGE433008F	3.175	1/8	.1250	6	28	66	DGE433051	5.1		.2008	6	44	82
DGE433032	3.2		.1260	6	28	66	DGE433013F	5.159	13/64	.2031	6	44	82
DGE433033	3.3		.1299	6	28	66	DGE433052	5.2		.2047	6	44	82
DGE433034	3.4		.1339	6	28	66	DGE433053	5.3		.2087	6	44	82
DGE433035	3.5		.1378	6	28	66	DGE433054	5.4		.2126	6	44	82
DGE433009F	3.572	9/64	.1406	6	28	66	DGE433055	5.5		.2165	6	44	82
DGE433036	3.6		.1417	6	28	66	DGE433014F	5.556	7/32	.2188	6	44	82
DGE433037	3.7		.1457	6	28	66	DGE433056	5.6		.2205	6	44	82
DGE433038	3.8		.1496	6	36	74	DGE433057	5.7		.2244	6	44	82
DGE433039	3.9		.1535	6	36	74	DGE433058	5.8		.2283	6	44	82
DGE433010F	3.969	5/32	.1563	6	36	74	DGE433059	5.9		.2323	6	44	82
DGE433040	4.0		.1575	6	36	74	DGE433015F	5.953	15/64	.2344	6	44	82
DGE433041	4.1		.1614	6	36	74	DGE433060	6.0		.2362	6	44	82
DGE433042	4.2		.1654	6	36	74	DGE433061	6.1		.2402	8	53	91
DGE433043	4.3		.1693	6	36	74	DGE433062	6.2		.2441	8	53	91
DGE433011F	4.366	11/64	.1719	6	36	74	DGE433063	6.3		.2480	8	53	91
DGE433044	4.4		.1732	6	36	74	DGE433016F	6.350	1/4	.2500	8	53	91
DGE433045	4.5		.1772	6	36	74	DGE433064	6.4		.2520	8	53	91
DGE433046	4.6		.1811	6	36	74	DGE433065	6.5		.2559	8	53	91
DGE433047	4.7		.1850	6	36	74	DGE433006L	6.528	F	.2570	8	53	9
DGE433012F	4.763	3/16	.1875	6	36	74	DGE433066	6.6		.2598	8	53	91
DGE433048	4.8		.1890	6	44	82	DGE433067	6.7		.2638	8	53	91

Other shank types are available on your request.

▶ NEXT PAGE

© : Excellent ○ : Good


P			H		M	K	N			S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							



DGE433 SERIES

CARBIDE, DREAM DRILL - ALU with COOLANT HOLES LONG

- ▶ Optimized thinning for Aluminum & Aluminum Alloys to prevent any clogging from chip welding
- ▶ Wider and deeper flute gullets for maximum chip removal
- ▶ Special geometry and smooth coating reduces built up edge and improves finishes



DIN 6537 MG h6 m7 118° 20 bar P.141 5 x D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
DLC	D1			D2	L1	L2	DLC	D1			D2	L1	L2
DGE433017F	6.747	17/64	.2656	8	53	91	DGE433087	8.7		.3425	10	61	103
DGE433068	6.8		.2677	8	53	91	DGE433022F	8.731	11/32	.3438	10	61	103
DGE433069	6.9		.2717	8	53	91	DGE433088	8.8		.3465	10	61	103
DGE433009L	6.909	I	.2720	8	53	91	DGE433089	8.9		.3504	10	61	103
DGE433070	7.0		.2756	8	53	91	DGE433090	9.0		.3543	10	61	103
DGE433071	7.1		.2795	8	53	91	DGE433091	9.1		.3583	10	61	103
DGE433018F	7.144	9/32	.2812	8	53	91	DGE433023F	9.128	23/64	.3594	10	61	103
DGE433072	7.2		.2835	8	53	91	DGE433092	9.2		.3622	10	61	103
DGE433073	7.3		.2874	8	53	91	DGE433093	9.3		.3661	10	61	103
DGE433074	7.4		.2913	8	53	91	DGE433021L	9.347	U	.3680	10	61	103
DGE433075	7.5		.2953	8	53	91	DGE433094	9.4		.3701	10	61	103
DGE433019F	7.541	19/64	.2969	8	53	91	DGE433095	9.5		.3740	10	61	103
DGE433076	7.6		.2992	8	53	91	DGE433024F	9.525	3/8	.3750	10	61	103
DGE433077	7.7		.3031	8	53	91	DGE433096	9.6		.3780	10	61	103
DGE433078	7.8		.3071	8	53	91	DGE433097	9.7		.3819	10	61	103
DGE433079	7.9		.3110	8	53	91	DGE433098	9.8		.3858	10	61	103
DGE433020F	7.938	5/16	.3125	8	53	91	DGE433099	9.9		.3898	10	61	103
DGE433080	8.0		.3150	8	53	91	DGE433025F	9.922	25/64	.3906	10	61	103
DGE433081	8.1		.3189	10	61	103	DGE433100	10.0		.3937	10	61	103
DGE433082	8.2		.3228	10	61	103	DGE433101	10.1		.3976	12	71	118
DGE433083	8.3		.3268	10	61	103	DGE433102	10.2		.4016	12	71	118
DGE433021F	8.334	21/64	.3281	10	61	103	DGE433103	10.3		.4055	12	71	118
DGE433084	8.4		.3307	10	61	103	DGE433026F	10.319	13/32	.4062	12	71	118
DGE433017L	8.433	Q	.3320	10	61	103	DGE433104	10.4		.4094	12	71	118
DGE433085	8.5		.3346	10	61	103	DGE433105	10.5		.4134	12	71	118
DGE433086	8.6		.3386	10	61	103	DGE433106	10.6		.4173	12	71	118

Other shank types are available on your request. ▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H		M	K	N			S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							



DGE433 SERIES

CARBIDE, DREAM DRILL - ALU with COOLANT HOLES LONG

- ▶ Optimized thinning for Aluminum & Aluminum Alloys to prevent any clogging from chip welding
- ▶ Wider and deeper flute gullets for maximum chip removal
- ▶ Special geometry and smooth coating reduces built up edge and improves finishes



DIN 6537 MG h6 m7 118° 20 bar P.141 5 x D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
DLC	D1			D2	L1	L2	DLC	D1			D2	L1	L2
DGE433107	10.7		.4212	12	71	118	DGE433128	12.8		.5039	14	77	124
DGE433027F	10.716	27/64	.4219	12	71	118	DGE433129	12.9		.5079	14	77	124
DGE433108	10.8		.4252	12	71	118	DGE433130	13.0		.5118	14	77	124
DGE433109	10.9		.4291	12	71	118	DGE433131	13.1		.5157	14	77	124
DGE433110	11.0		.4330	12	71	118	DGE433132	13.2		.5197	14	77	124
DGE433111	11.1		.4370	12	71	118	DGE433133	13.3		.5236	14	77	124
DGE433028F	11.113	7/16	.4375	12	71	118	DGE433134	13.4		.5276	14	77	124
DGE433112	11.2		.4409	12	71	118	DGE433135	13.5		.5314	14	77	124
DGE433113	11.3		.4448	12	71	118	DGE433136	13.6		.5354	14	77	124
DGE433114	11.4		.4488	12	71	118	DGE433137	13.7		.5394	14	77	124
DGE433115	11.5		.4527	12	71	118	DGE433138	13.8		.5433	14	77	124
DGE433029F	11.509	29/64	.4531	12	71	118	DGE433139	13.9		.5472	14	77	124
DGE433116	11.6		.4566	12	71	118	DGE433140	14.0		.5512	14	77	124
DGE433117	11.7		.4606	12	71	118	DGE433141	14.1		.5551	16	83	133
DGE433118	11.8		.4645	12	71	118	DGE433142	14.2		.5591	16	83	133
DGE433119	11.9		.4685	12	71	118	DGE433036F	14.288	9/16	.5625	16	83	133
DGE433030F	11.906	15/32	.4688	12	71	118	DGE433143	14.3		.5630	16	83	133
DGE433120	12.0		.4724	12	71	118	DGE433144	14.4		.5669	16	83	133
DGE433121	12.1		.4764	14	77	124	DGE433145	14.5		.5708	16	83	133
DGE433122	12.2		.4803	14	77	124	DGE433146	14.6		.5748	16	83	133
DGE433123	12.3		.4843	14	77	124	DGE433147	14.7		.5787	16	83	133
DGE433031F	12.303	31/64	.4844	14	77	124	DGE433148	14.8		.5827	16	83	133
DGE433124	12.4		.4882	14	77	124	DGE433149	14.9		.5866	16	83	133
DGE433125	12.5		.4921	14	77	124	DGE433150	15.0		.5905	16	83	133
DGE433126	12.6		.4961	14	77	124	DGE433151	15.1		.5945	16	83	133
DGE433032F	12.7	1/2	.5000	14	77	124	DGE433152	15.2		.5984	16	83	133

Other shank types are available on your request. ▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H		M	K	N			S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							

CARBIDE, DREAM DRILL - ALU with COOLANT HOLES LONG

- ▶ Optimized thinning for Aluminum & Aluminum Alloys to prevent any clogging from chip welding
- ▶ Wider and deeper flute gullets for maximum chip removal
- ▶ Special geometry and smooth coating reduces built up edge and improves finishes



DIN 6537
MG
h6
m7
118°
20 bar
P.141
5 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Fractional	Decimal					Metric	Fractional	Decimal			
DLC	D1			D2	L1	L2	DLC	D1			D2	L1	L2
DGE433153	15.3		.6024	16	83	133	DGE433177	17.7		.6968	18	93	143
DGE433154	15.4		.6063	16	83	133	DGE433178	17.8		.7008	18	93	143
DGE433155	15.5		.6102	16	83	133	DGE433179	17.9		.7047	18	93	143
DGE433156	15.6		.6142	16	83	133	DGE433180	18.0		.7087	18	93	143
DGE433157	15.7		.6181	16	83	133	DGE433181	18.1		.7126	20	101	153
DGE433158	15.8		.6220	16	83	133	DGE433182	18.2		.7165	20	101	153
DGE433040F	15.875	5/8	.6250	16	83	133	DGE433183	18.3		.7205	20	101	153
DGE433159	15.9		.6260	16	83	133	DGE433184	18.4		.7244	20	101	153
DGE433160	16.0		.6299	16	83	133	DGE433185	18.5		.7283	20	101	153
DGE433161	16.1		.6339	18	93	143	DGE433186	18.6		.7323	20	101	153
DGE433162	16.2		.6378	18	93	143	DGE433187	18.7		.7362	20	101	153
DGE433163	16.3		.6417	18	93	143	DGE433188	18.8		.7402	20	101	153
DGE433164	16.4		.6457	18	93	143	DGE433189	18.9		.7441	20	101	153
DGE433165	16.5		.6495	18	93	143	DGE433190	19.0		.7480	20	101	153
DGE433166	16.6		.6535	18	93	143	DGE433048F	19.050	3/4	.7500	20	101	153
DGE433167	16.7		.6575	18	93	143	DGE433191	19.1		.7520	20	101	153
DGE433168	16.8		.6614	18	93	143	DGE433192	19.2		.7559	20	101	153
DGE433169	16.9		.6654	18	93	143	DGE433193	19.3		.7598	20	101	153
DGE433170	17.0		.6692	18	93	143	DGE433194	19.4		.7638	20	101	153
DGE433171	17.1		.6732	18	93	143	DGE433195	19.5		.7676	20	101	153
DGE433172	17.2		.6772	18	93	143	DGE433196	19.6		.7717	20	101	153
DGE433173	17.3		.6811	18	93	143	DGE433197	19.7		.7756	20	101	153
DGE433174	17.4		.6850	18	93	143	DGE433198	19.8		.7795	20	101	153
DGE433175	17.5		.6889	18	93	143	DGE433199	19.9		.7835	20	101	153
DGE433176	17.6		.6929	18	93	143	DGE433200	20.0		.7874	20	101	153

! Other shank types are available on your request.

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
						◎					

CARBIDE, DREAM DRILLS - ALU with COOLANT HOLES, DLC-COATED

DGE466, DGE718, DGE433 SERIES

WORK MATERIAL	N						
	ALUMINUM ALLOY CASTING ALUMINUM DIE CASTING			WROUGHT ALUMINUM ALLOY			
DRILLING SPEED(SFM)	240 ~ 650 ft/min			240 ~ 650 ft/min			
DIAMETER		RPM	FEED	IPR	RPM	FEED	IPR
Metric(mm)	Decimal						
3.0~6.0	.1181 ~ .2362	8000 ~ 15000	0.2 ~ 0.5	.008 .020	8000 ~ 15000	0.15 ~ 0.3	.006 .012
~10.0	~.3937	6000 ~ 10500	0.3 ~ 1.0	.012 .039	6000 ~ 10500	0.20 ~ 0.4	.008 .016
~14.0	~.5512	4500 ~ 5800	0.3 ~ 1.0	.012 .039	4500 ~ 5800	0.20 ~ 0.4	.008 .016
~20.0	~.7874	3200 ~ 4600	0.3 ~ 1.0	.012 .039	3200 ~ 4600	0.30 ~ 1.0	.012 .039

RPM = rev./min.
FEED = mm/rev.
IPR = inch/rev.



Being the best through innovation

CARBIDE




DREAM DRILLS -MQL TYPE

WITH COOLANT HOLES

- Minimum Quantity Lubrication
- Drilling Deep Holes, 10D, 15D, 20D, 25D & 30D



Global Cutting Tool Leader **YG-1**











SELECTION GUIDE

SOLID CARBIDE DREAM DRILLS-MQL TYPE

SOLID CARBIDE DREAM DRILLS - MQL TYPE (with Coolant Holes)

- Minimum Quantity Lubrication
- Drilling Deep Holes, 10D, 15D, 20D, 25D & 30D

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
10xD DH510		CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES <i>EXTRA LONG</i>	D3.0	D14.0	146
15xD DH515		CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES <i>EXTRA LONG</i>	D3.0	D14.0	149
20xD DH520		CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES <i>EXTRA LONG</i>	D3.0	D12.0	152
10xD DHM10		CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES <i>EXTRA LONG</i>	D3.0	D12.0	155
15xD DHM15		CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES <i>EXTRA LONG</i>	D3.0	D12.0	155
20xD DHM20		CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES <i>EXTRA LONG</i>	D3.0	D12.0	155
25xD DHM25		CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES <i>EXTRA LONG</i>	D3.0	D10.0	156
30xD DHM30		CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES <i>EXTRA LONG</i>	D3.0	D8.0	158
RECOMMENDED CUTTING CONDITIONS					160


◎ : Excellent ○ : Good

P		H		M	K	N			S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	◎	○				○					
◎	◎	○				○					
◎	◎	○				○					
◎	◎	○				○					
◎	◎	○				○					
◎	◎	○				○					
◎	◎	○				○					

CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES

EXTRA LONG

- ▶ 4-Facet Point for good centering capability
- ▶ Optimized special flutes are ideal for removing chips and for productive drilling
- ▶ Enhanced chip evacuation by polished flute upgraded TiAlN nano layer full coating
- ▶ MQL system compatible (Minimum Quantity Lubrication)



10 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH510030	3.0		.1181	3	39	90	DH510055	5.5		.2165	6	72	127
DH510031	3.1		.1220	4	46	97	DH510056	5.6		.2205	6	78	133
DH510008F	3.175	1/8	.1250	4	46	97	DH510057	5.7		.2244	6	78	133
DH510032	3.2		.1260	4	46	97	DH510058	5.8		.2283	6	78	133
DH510033	3.3		.1299	4	46	97	DH510059	5.9		.2323	6	78	133
DH510034	3.4		.1339	4	46	97	DH510060	6.0		.2362	6	78	133
DH510035	3.5		.1378	4	46	97	DH510061	6.1		.2402	7	85	141
DH510036	3.6		.1417	4	52	103	DH510062	6.2		.2441	7	85	141
DH510037	3.7		.1457	4	52	103	DH510063	6.3		.2480	7	85	141
DH510038	3.8		.1496	4	52	103	DH510016F	6.350	1/4	.2500	7	85	141
DH510039	3.9		.1535	4	52	103	DH510064	6.4		.2520	7	85	141
DH510040	4.0		.1575	4	52	103	DH510065	6.5		.2559	7	85	141
DH510041	4.1		.1614	5	59	112	DH510206L	6.528	F	.2570	7	91	147
DH510042	4.2		.1654	5	59	112	DH510066	6.6		.2598	7	91	147
DH510043	4.3		.1693	5	59	112	DH510067	6.7		.2638	7	91	147
DH510044	4.4		.1732	5	59	112	DH510017F	6.746	17/64	.2656	7	91	147
DH510045	4.5		.1772	5	59	112	DH510068	6.8		.2677	7	91	147
DH510046	4.6		.1811	5	65	118	DH510069	6.9		.2717	7	91	147
DH510047	4.7		.1850	5	65	118	DH510209L	6.909	I	.2720	7	91	147
DH510048	4.8		.1890	5	65	118	DH510070	7.0		.2756	7	91	147
DH510049	4.9		.1929	5	65	118	DH510071	7.1		.2795	8	98	155
DH510050	5.0		.1969	5	65	118	DH510018F	7.142	9/32	.2812	8	98	155
DH510051	5.1		.2008	6	72	127	DH510072	7.2		.2835	8	98	155
DH510052	5.2		.2047	6	72	127	DH510073	7.3		.2874	8	98	155
DH510053	5.3		.2087	6	72	127	DH510074	7.4		.2913	8	98	155
DH510054	5.4		.2126	6	72	127	DH510075	7.5		.2953	8	98	155

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			○						

CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES

EXTRA LONG

- ▶ 4-Facet Point for good centering capability
- ▶ Optimized special flutes are ideal for removing chips and for productive drilling
- ▶ Enhanced chip evacuation by polished flute upgraded TiAlN nano layer full coating
- ▶ MQL system compatible (Minimum Quantity Lubrication)



10 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH510019F	7.541	19/64	.2969	8	104	161	DH510095	9.5		.3740	10	124	182
DH510076	7.6		.2992	8	104	161	DH510024F	9.525	3/8	.3750	10	130	188
DH510077	7.7		.3031	8	104	161	DH510096	9.6		.3780	10	130	188
DH510078	7.8		.3071	8	104	161	DH510097	9.7		.3819	10	130	188
DH510079	7.9		.3110	8	104	161	DH510098	9.8		.3858	10	130	188
DH510020F	7.938	5/16	.3125	8	104	161	DH510099	9.9		.3898	10	130	188
DH510080	8.0		.3150	8	104	161	DH510025F	9.921	25/64	.3906	10	130	188
DH510081	8.1		.3189	9	111	169	DH510100	10.0		.3937	10	130	188
DH510082	8.2		.3228	9	111	169	DH510101	10.1		.3976	11	137	201
DH510083	8.3		.3268	9	111	169	DH510102	10.2		.4016	11	137	201
DH510021F	8.334	21/64	.3281	9	111	169	DH510103	10.3		.4055	11	137	201
DH510084	8.4		.3307	9	111	169	DH510026F	10.318	13/32	.4062	11	137	201
DH510217L	8.433	Q	.3320	9	111	169	DH510104	10.4		.4094	11	137	201
DH510085	8.5		.3346	9	111	169	DH510105	10.5		.4134	11	137	201
DH510086	8.6		.3386	9	117	175	DH510106	10.6		.4173	11	143	207
DH510087	8.7		.3425	9	117	175	DH510107	10.7		.4213	11	143	207
DH510022F	8.733	11/32	.3438	9	117	175	DH510027F	10.716	27/64	.4219	11	143	207
DH510088	8.8		.3465	9	117	175	DH510108	10.8		.4252	11	143	207
DH510089	8.9		.3504	9	117	175	DH510109	10.9		.4291	11	143	207
DH510090	9.0		.3543	9	117	175	DH510110	11.0		.4331	11	143	207
DH510091	9.1		.3583	10	124	182	DH510111	11.1		.4370	12	150	215
DH510023F	9.129	23/64	.3594	10	124	182	DH510028F	11.113	7/16	.4375	12	150	215
DH510092	9.2		.3622	10	124	182	DH510112	11.2		.4409	12	150	215
DH510093	9.3		.3661	10	124	182	DH510113	11.3		.4449	12	150	215
DH510221L	9.347	U	.3680	10	124	182	DH510114	11.4		.4488	12	150	215
DH510094	9.4		.3701	10	124	182	DH510115	11.5		.4528	12	150	215

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			○						

CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES

EXTRA LONG

- ▶ 4-Facet Point for good centering capability
- ▶ Optimized special flutes are ideal for removing chips and for productive drilling
- ▶ Enhanced chip evacuation by polished flute upgraded TiAlN nano layer full coating
- ▶ MQL system compatible (Minimum Quantity Lubrication)



MG $\approx 30^\circ$ h6 h7 140° 20 bar P.160 10 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH510029F	11.509	29/64	.4531	12	156	221	DH510127	12.7	1/2	.5000	13	169	235
DH510116	11.6		.4567	12	156	221	DH510128	12.8		.5039	13	169	235
DH510117	11.7		.4606	12	156	221	DH510129	12.9		.5079	13	169	235
DH510118	11.8		.4646	12	156	221	DH510130	13.0		.5118	13	169	235
DH510119	11.9		.4685	12	156	221	DH510131	13.1		.5157	14	176	243
DH510030F	11.908	15/32	.4688	12	156	221	DH510132	13.2		.5197	14	176	243
DH510120	12.0		.4724	12	156	221	DH510133	13.3		.5236	14	176	243
DH510121	12.1		.4764	13	163	229	DH510134	13.4		.5276	14	176	243
DH510122	12.2		.4803	13	163	229	DH510135	13.5		.5315	14	176	243
DH510123	12.3		.4843	13	163	229	DH510136	13.6		.5354	14	182	249
DH510031F	12.304	31/64	.4844	13	163	229	DH510137	13.7		.5394	14	182	249
DH510124	12.4		.4882	13	163	229	DH510138	13.8		.5433	14	182	249
DH510125	12.5		.4921	13	163	229	DH510139	13.9		.5472	14	182	249
DH510126	12.6		.4961	13	169	235	DH510140	14.0		.5512	14	182	249


◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			○						

CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES

EXTRA LONG

- ▶ 4-Facet Point for good centering capability
- ▶ Optimized special flutes are ideal for removing chips and for productive drilling
- ▶ Enhanced chip evacuation by polished flute upgraded TiAlN nano layer full coating
- ▶ MQL system compatible (Minimum Quantity Lubrication)



MG $\approx 30^\circ$ h6 h7 140° 45 bar P.160 15 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH515030	3.0		.1181	3	54	105	DH515055	5.5		.2165	6	99	154
DH515031	3.1		.1220	4	63	114	DH515056	5.6		.2205	6	108	163
DH515008F	3.175	1/8	.1250	4	63	114	DH515057	5.7		.2244	6	108	163
DH515032	3.2		.1260	4	63	114	DH515058	5.8		.2283	6	108	163
DH515033	3.3		.1299	4	63	114	DH515059	5.9		.2323	6	108	163
DH515034	3.4		.1339	4	63	114	DH515060	6.0		.2362	6	108	163
DH515035	3.5		.1378	4	63	114	DH515061	6.1		.2402	7	117	173
DH515036	3.6		.1417	4	72	123	DH515062	6.2		.2441	7	117	173
DH515037	3.7		.1457	4	72	123	DH515063	6.3		.2480	7	117	173
DH515038	3.8		.1496	4	72	123	DH515016F	6.350	1/4	.2500	7	117	173
DH515039	3.9		.1535	4	72	123	DH515064	6.4		.2520	7	117	173
DH515040	4.0		.1575	4	72	123	DH515065	6.5		.2559	7	117	173
DH515041	4.1		.1614	5	81	134	DH515206L	6.528	F	.2570	7	126	182
DH515042	4.2		.1654	5	81	134	DH515066	6.6		.2598	7	126	182
DH515043	4.3		.1693	5	81	134	DH515067	6.7		.2638	7	126	182
DH515044	4.4		.1732	5	81	134	DH515017F	6.746	17/64	.2656	7	126	182
DH515045	4.5		.1772	5	81	134	DH515068	6.8		.2677	7	126	182
DH515046	4.6		.1811	5	90	143	DH515069	6.9		.2717	7	126	182
DH515047	4.7		.1850	5	90	143	DH515209L	6.909	I	.2720	7	126	182
DH515048	4.8		.1890	5	90	143	DH515070	7.0		.2756	7	126	182
DH515049	4.9		.1929	5	90	143	DH515071	7.1		.2795	8	135	192
DH515050	5.0		.1969	5	90	143	DH515018F	7.142	9/32	.2812	8	135	192
DH515051	5.1		.2008	6	99	154	DH515072	7.2		.2835	8	135	192
DH515052	5.2		.2047	6	99	154	DH515073	7.3		.2874	8	135	192
DH515053	5.3		.2087	6	99	154	DH515074	7.4		.2913	8	135	192
DH515054	5.4		.2126	6	99	154	DH515075	7.5		.2953	8	135	192

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			○						

CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES

EXTRA LONG

- ▶ 4-Facet Point for good centering capability
- ▶ Optimized special flutes are ideal for removing chips and for productive drilling
- ▶ Enhanced chip evacuation by polished flute upgraded TiAlN nano layer full coating
- ▶ MQL system compatible (Minimum Quantity Lubrication)



15 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH515019F	7.541	19/64	.2969	8	144	201	DH515095	9.5		.3740	10	171	229
DH515076	7.6		.2992	8	144	201	DH515024F	9.525	3/8	.3750	10	180	238
DH515077	7.7		.3031	8	144	201	DH515096	9.6		.3780	10	180	238
DH515078	7.8		.3071	8	144	201	DH515097	9.7		.3819	10	180	238
DH515079	7.9		.3110	8	144	201	DH515098	9.8		.3858	10	180	238
DH515020F	7.938	5/16	.3125	8	144	201	DH515099	9.9		.3898	10	180	238
DH515080	8.0		.3150	8	144	201	DH515025F	9.921	25/64	.3906	10	180	238
DH515081	8.1		.3189	9	153	211	DH515100	10.0		.3937	10	180	238
DH515082	8.2		.3228	9	153	211	DH515101	10.1		.3976	11	189	253
DH515083	8.3		.3268	9	153	211	DH515102	10.2		.4016	11	189	253
DH515021F	8.334	21/64	.3281	9	153	211	DH515103	10.3		.4055	11	189	253
DH515084	8.4		.3307	9	153	211	DH515026F	10.318	13/32	.4062	11	189	253
DH515217L	8.433	Q	.3320	9	153	211	DH515104	10.4		.4094	11	189	253
DH515085	8.5		.3346	9	153	211	DH515105	10.5		.4134	11	189	253
DH515086	8.6		.3386	9	162	220	DH515106	10.6		.4173	11	198	262
DH515087	8.7		.3425	9	162	220	DH515107	10.7		.4213	11	198	262
DH515022F	8.733	11/32	.3438	9	162	220	DH515027F	10.716	27/64	.4219	11	198	262
DH515088	8.8		.3465	9	162	220	DH515108	10.8		.4252	11	198	262
DH515089	8.9		.3504	9	162	220	DH515109	10.9		.4291	11	198	262
DH515090	9.0		.3543	9	162	220	DH515110	11.0		.4331	11	198	262
DH515091	9.1		.3583	10	171	229	DH515111	11.1		.4370	12	207	272
DH515023F	9.129	23/64	.3594	10	171	229	DH515028F	11.113	7/16	.4375	12	207	272
DH515092	9.2		.3622	10	171	229	DH515112	11.2		.4409	12	207	272
DH515093	9.3		.3661	10	171	229	DH515113	11.3		.4449	12	207	272
DH515221L	9.347	U	.3680	10	171	229	DH515114	11.4		.4488	12	207	272
DH515094	9.4		.3701	10	171	229	DH515115	11.5		.4527	12	207	272

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55								HRC55~
◎	◎	○			○						

CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES

EXTRA LONG

- ▶ 4-Facet Point for good centering capability
- ▶ Optimized special flutes are ideal for removing chips and for productive drilling
- ▶ Enhanced chip evacuation by polished flute upgraded TiAlN nano layer full coating
- ▶ MQL system compatible (Minimum Quantity Lubrication)



15 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH515029F	11.509	29/64	.4531	12	216	281	DH515127	12.7	1/2	.5000	13	234	300
DH515116	11.6		.4567	12	216	281	DH515128	12.8		.5039	13	234	300
DH515117	11.7		.4606	12	216	281	DH515129	12.9		.5079	13	234	300
DH515118	11.8		.4646	12	216	281	DH515130	13.0		.5118	13	234	300
DH515119	11.9		.4685	12	216	281	DH515131	13.1		.5157	14	243	310
DH515030F	11.908	15/32	.4688	12	216	281	DH515132	13.2		.5197	14	243	310
DH515120	12.0		.4724	12	216	281	DH515133	13.3		.5236	14	243	310
DH515121	12.1		.4764	13	225	291	DH515134	13.4		.5276	14	243	310
DH515122	12.2		.4803	13	225	291	DH515135	13.5		.5314	14	243	310
DH515123	12.3		.4843	13	225	291	DH515136	13.6		.5354	14	252	319
DH515031F	12.304	31/64	.4844	13	225	291	DH515137	13.7		.5394	14	252	319
DH515124	12.4		.4882	13	225	291	DH515138	13.8		.5433	14	252	319
DH515125	12.5		.4921	13	225	291	DH515139	13.9		.5472	14	252	319
DH515126	12.6		.4961	13	234	300	DH515140	14.0		.5512	14	252	319


◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55								HRC55~
◎	◎	○			○						

CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES

EXTRA LONG

- ▶ 4-Facet Point for good centering capability
- ▶ Optimized special flutes are ideal for removing chips and for productive drilling
- ▶ Enhanced chip evacuation by polished flute upgraded TiAlN nano layer full coating
- ▶ MQL system compatible (Minimum Quantity Lubrication)



20 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH520030	3.0		.1181	3	69	120	DH520055	5.5		.2165	6	127	182
DH520031	3.1		.1220	4	81	132	DH520056	5.6		.2205	6	138	193
DH520008F	3.175	1/8	.1250	4	81	132	DH520057	5.7		.2244	6	138	193
DH520032	3.2		.1260	4	81	132	DH520058	5.8		.2283	6	138	193
DH520033	3.3		.1299	4	81	132	DH520059	5.9		.2323	6	138	193
DH520034	3.4		.1339	4	81	132	DH520060	6.0		.2362	6	138	193
DH520035	3.5		.1378	4	81	132	DH520061	6.1		.2402	7	150	206
DH520036	3.6		.1417	4	92	143	DH520062	6.2		.2441	7	150	206
DH520037	3.7		.1457	4	92	143	DH520063	6.3		.2480	7	150	206
DH520038	3.8		.1496	4	92	143	DH520016F	6.350	1/4	.2500	7	150	206
DH520039	3.9		.1535	4	92	143	DH520064	6.4		.2520	7	150	206
DH520040	4.0		.1575	4	92	143	DH520065	6.5		.2559	7	150	206
DH520041	4.1		.1614	5	104	157	DH520206L	6.528	F	.2570	7	161	217
DH520042	4.2		.1654	5	104	157	DH520066	6.6		.2598	7	161	217
DH520043	4.3		.1693	5	104	157	DH520067	6.7		.2638	7	161	217
DH520044	4.4		.1732	5	104	157	DH520017F	6.746	17/64	.2656	7	161	217
DH520045	4.5		.1772	5	104	157	DH520068	6.8		.2677	7	161	217
DH520046	4.6		.1811	5	115	168	DH520069	6.9		.2717	7	161	217
DH520047	4.7		.1850	5	115	168	DH520209L	6.909	I	.2720	7	161	217
DH520048	4.8		.1890	5	115	168	DH520070	7.0		.2756	7	161	217
DH520049	4.9		.1929	5	115	168	DH520071	7.1		.2795	8	173	230
DH520050	5.0		.1969	5	115	168	DH520018F	7.142	9/32	.2812	8	173	230
DH520051	5.1		.2008	6	127	182	DH520072	7.2		.2835	8	173	230
DH520052	5.2		.2047	6	127	182	DH520073	7.3		.2874	8	173	230
DH520053	5.3		.2087	6	127	182	DH520074	7.4		.2913	8	173	230
DH520054	5.4		.2126	6	127	182	DH520075	7.5		.2953	8	173	230

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55								HRc55~
◎	◎	○			○						

CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES

EXTRA LONG

- ▶ 4-Facet Point for good centering capability
- ▶ Optimized special flutes are ideal for removing chips and for productive drilling
- ▶ Enhanced chip evacuation by polished flute upgraded TiAlN nano layer full coating
- ▶ MQL system compatible (Minimum Quantity Lubrication)



20 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH520019F	7.541	19/64	.2969	8	184	241	DH520095	9.5		.3740	10	219	277
DH520076	7.6		.2992	8	184	241	DH520024F	9.525	3/8	.3750	10	219	277
DH520077	7.7		.3031	8	184	241	DH520096	9.6		.3780	10	230	288
DH520078	7.8		.3071	8	184	241	DH520097	9.7		.3819	10	230	288
DH520079	7.9		.3110	8	184	241	DH520098	9.8		.3858	10	230	288
DH520020F	7.938	5/16	.3125	8	184	241	DH520099	9.9		.3898	10	230	288
DH520080	8.0		.3150	8	184	241	DH520025F	9.921	25/64	.3906	10	230	288
DH520081	8.1		.3189	9	196	254	DH520100	10.0		.3937	10	230	288
DH520082	8.2		.3228	9	196	254	DH520101	10.1		.3976	11	242	306
DH520083	8.3		.3268	9	196	254	DH520102	10.2		.4016	11	242	306
DH520021F	8.334	21/64	.3281	9	196	254	DH520103	10.3		.4055	11	242	306
DH520084	8.4		.3307	9	196	254	DH520026F	10.318	13/32	.4062	11	242	306
DH520217L	8.433	Q	.3320	9	196	254	DH520104	10.4		.4094	11	242	306
DH520085	8.5		.3346	9	196	254	DH520105	10.5		.4134	11	242	306
DH520086	8.6		.3386	9	207	265	DH520106	10.6		.4173	11	253	317
DH520087	8.7		.3425	9	207	265	DH520107	10.7		.4213	11	253	317
DH520022F	8.733	11/32	.3438	9	207	265	DH520027F	10.716	27/64	.4219	11	253	317
DH520088	8.8		.3465	9	207	265	DH520108	10.8		.4252	11	253	317
DH520089	8.9		.3504	9	207	265	DH520109	10.9		.4291	11	253	317
DH520090	9.0		.3543	9	207	265	DH520110	11.0		.4331	11	253	317
DH520091	9.1		.3583	10	219	277	DH520111	11.1		.4370	12	265	330
DH520023F	9.129	23/64	.3594	10	219	277	DH520028F	11.113	7/16	.4375	12	265	330
DH520092	9.2		.3622	10	219	277	DH520112	11.2		.4409	12	265	330
DH520093	9.3		.3661	10	219	277	DH520113	11.3		.4449	12	265	330
DH520221L	9.347	U	.3680	10	219	277	DH520114	11.4		.4488	12	265	330
DH520094	9.4		.3701	10	219	277	DH520115	11.5		.4527	12	265	330

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55								HRc55~
◎	◎	○			○						

CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES

EXTRA LONG

- ▶ 4-Facet Point for good centering capability
- ▶ Optimized special flutes are ideal for removing chips and for productive drilling
- ▶ Enhanced chip evacuation by polished flute upgraded TiAlN nano layer full coating
- ▶ MQL system compatible (Minimum Quantity Lubrication)



MG $\approx 30^\circ$ h6 h7 140° 45 bar P.160 20 × D

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DH520029F	11.509	29/64	.4531	12	276	341	DH520119	11.9		.4685	12	276	341
DH520116	11.6		.4567	12	276	341	DH520030F	11.908	15/32	.4688	12	276	341
DH520117	11.7		.4606	12	276	341	DH520120	12.0		.4724	12	276	341
DH520118	11.8		.4646	12	276	341							

Unit : mm


◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
-HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			○						

CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES

EXTRA LONG

- ▶ 4-Facet Point for good centering capability
- ▶ Optimized special flutes are ideal for removing chips and for productive drilling
- ▶ Enhanced chip evacuation by polished flute upgraded TiAlN nano layer full coating
- ▶ MQL system compatible (Minimum Quantity Lubrication)



MG $\approx 30^\circ$ h6 h7 140° 20 bar 45 bar P.160 10 × D (DHM10) 15 × D (DHM15) 20 × D (DHM20)

10 × D						15 × D					20 × D						
EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length
	Metric	Decimal					Metric	Decimal					Metric	Decimal			
TiAlN	D1		D2	L1	L2	TiAlN	D1		D2	L1	L2	TiAlN	D1		D2	L1	L2
DHM10030	3.0	.1181	6	40	80	DHM15030	3.0	.1181	6	55	95	DHM20030	3.0	.1181	6	70	110
DHM10033	3.3	.1299	6	47	87	DHM15035	3.5	.1378	6	64	104	DHM20035	3.5	.1378	6	82	122
DHM10035	3.5	.1378	6	47	87	DHM15040	4.0	.1575	6	73	113	DHM20040	4.0	.1575	6	93	133
DHM10040	4.0	.1575	6	53	93	DHM15045	4.5	.1772	6	82	122	DHM20045	4.5	.1772	6	105	145
DHM10042	4.2	.1654	6	60	100	DHM15050	5.0	.1969	6	91	131	DHM20050	5.0	.1969	6	116	156
DHM10045	4.5	.1772	6	60	100	DHM15055	5.5	.2165	6	100	140	DHM20055	5.5	.2165	6	128	168
DHM10050	5.0	.1969	6	66	106	DHM15060	6.0	.2362	6	109	149	DHM20060	6.0	.2362	6	139	179
DHM10055	5.5	.2165	6	73	113	DHM15070	7.0	.2756	8	127	167	DHM20070	7.0	.2756	8	162	202
DHM10060	6.0	.2362	6	79	119	DHM15080	8.0	.3150	8	145	185	DHM20080	8.0	.3150	8	185	225
DHM10065	6.5	.2559	8	86	126	DHM15090	9.0	.3543	10	163	207	DHM20090	9.0	.3543	10	208	252
DHM10068	6.8	.2677	8	92	132	DHM15100	10.0	.3937	10	182	226	DHM20100	10.0	.3937	10	232	276
DHM10070	7.0	.2756	8	92	132	DHM15110	11.0	.4330	12	200	249	DHM20110	11.0	.4330	12	255	304
DHM10075	7.5	.2953	8	99	139	DHM15120	12.0	.4724	12	218	267	DHM20120	12.0	.4724	12	278	327
DHM10080	8.0	.3150	8	105	145												
DHM10085	8.5	.3346	10	112	156												
DHM10090	9.0	.3543	10	118	162												
DHM10095	9.5	.3740	10	126	170												
DHM10100	10.0	.3937	10	132	176												
DHM10105	10.5	.4134	12	139	188												
DHM10110	11.0	.4330	12	145	194												
DHM10115	11.5	.4527	12	152	201												
DHM10120	12.0	.4724	12	158	207												
DHM10125	12.5	.4921	14	165	214												
DHM10130	13.0	.5118	14	171	220												
DHM10135	13.5	.5314	14	178	227												
DHM10140	14.0	.5512	14	184	233												

Unit : mm


◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
-HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			○						

CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES

EXTRA LONG

- ▶ 4-Facet Point for good centering capability
- ▶ Optimized special flutes are ideal for removing chips and for productive drilling
- ▶ Enhanced chip evacuation by polished flute upgraded TiAlN nano layer full coating
- ▶ MQL system compatible (Minimum Quantity Lubrication)



25 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DHM25030	3.0		.1181	6	85	125	DHM25055	5.5		.2165	6	155	195
DHM25031	3.1		.1220	6	99	139	DHM25056	5.6		.2205	6	169	209
DHM25008F	3.175	1/8	.1250	6	99	139	DHM25057	5.7		.2244	6	169	209
DHM25032	3.2		.1260	6	99	139	DHM25058	5.8		.2283	6	169	209
DHM25033	3.3		.1299	6	99	139	DHM25059	5.9		.2323	6	169	209
DHM25034	3.4		.1339	6	99	139	DHM25060	6.0		.2362	6	169	209
DHM25035	3.5		.1378	6	99	139	DHM25061	6.1		.2402	8	183	223
DHM25036	3.6		.1417	6	113	153	DHM25062	6.2		.2441	8	183	223
DHM25037	3.7		.1457	6	113	153	DHM25063	6.3		.2480	8	183	223
DHM25038	3.8		.1496	6	113	153	DHM25016F	6.350	1/4	.2500	8	183	223
DHM25039	3.9		.1535	6	113	153	DHM25064	6.4		.2520	8	183	223
DHM25040	4.0		.1575	6	113	153	DHM25065	6.5		.2559	8	183	223
DHM25041	4.1		.1614	6	127	167	DHM25206L	6.528	F	.2570	8	197	237
DHM25042	4.2		.1654	6	127	167	DHM25066	6.6		.2598	8	197	237
DHM25043	4.3		.1693	6	127	167	DHM25067	6.7		.2638	8	197	237
DHM25044	4.4		.1732	6	127	167	DHM25017F	6.746	17/64	.2656	8	197	237
DHM25045	4.5		.1772	6	127	167	DHM25068	6.8		.2677	8	197	237
DHM25046	4.6		.1811	6	141	181	DHM25069	6.9		.2717	8	197	237
DHM25047	4.7		.1850	6	141	181	DHM25209L	6.909	I	.2720	8	197	237
DHM25048	4.8		.1890	6	141	181	DHM25070	7.0		.2756	8	197	237
DHM25049	4.9		.1929	6	141	181	DHM25071	7.1		.2795	8	211	251
DHM25050	5.0		.1969	6	141	181	DHM25018F	7.142	9/32	.2812	8	211	251
DHM25051	5.1		.2008	6	155	195	DHM25072	7.2		.2835	8	211	251
DHM25052	5.2		.2047	6	155	195	DHM25073	7.3		.2874	8	211	251
DHM25053	5.3		.2087	6	155	195	DHM25074	7.4		.2913	8	211	251
DHM25054	5.4		.2126	6	155	195	DHM25075	7.5		.2953	8	211	251

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~							
◎	◎	○			○						

CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES

EXTRA LONG

- ▶ 4-Facet Point for good centering capability
- ▶ Optimized special flutes are ideal for removing chips and for productive drilling
- ▶ Enhanced chip evacuation by polished flute upgraded TiAlN nano layer full coating
- ▶ MQL system compatible (Minimum Quantity Lubrication)



25 × D

Unit : mm

EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DHM25019F	7.541	19/64	.2969	8	225	265	DHM25088	8.8		.3465	10	253	297
DHM25076	7.6		.2992	8	225	265	DHM25089	8.9		.3504	10	253	297
DHM25077	7.7		.3031	8	225	265	DHM25090	9.0		.3543	10	253	297
DHM25078	7.8		.3071	8	225	265	DHM25091	9.1		.3583	10	268	312
DHM25079	7.9		.3110	8	225	265	DHM25023F	9.129	23/64	.3594	10	268	312
DHM25020F	7.938	5/16	.3125	8	225	265	DHM25092	9.2		.3622	10	268	312
DHM25080	8.0		.3150	8	225	265	DHM25093	9.3		.3661	10	268	312
DHM25081	8.1		.3189	10	239	283	DHM25221L	9.347	U	.3680	10	268	312
DHM25082	8.2		.3228	10	239	283	DHM25094	9.4		.3701	10	268	312
DHM25083	8.3		.3268	10	239	283	DHM25095	9.5		.3740	10	268	312
DHM25021F	8.334	21/64	.3281	10	239	283	DHM25024F	9.525	3/8	.3750	10	282	326
DHM25084	8.4		.3307	10	239	283	DHM25096	9.6		.3780	10	282	326
DHM25217L	8.433	Q	.3320	10	239	283	DHM25097	9.7		.3819	10	282	326
DHM25085	8.5		.3346	10	239	283	DHM25098	9.8		.3858	10	282	326
DHM25086	8.6		.3386	10	253	297	DHM25099	9.9		.3898	10	282	326
DHM25087	8.7		.3425	10	253	297	DHM25025F	9.921	25/64	.3906	10	282	326
DHM25022F	8.733	11/32	.3438	10	253	297	DHM25100	10.0		.3937	10	282	326

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~							
◎	◎	○			○						





DHM30 SERIES

CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES

EXTRA LONG

- ▶ 4-Facet Point for good centering capability
- ▶ Optimized special flutes are ideal for removing chips and for productive drilling
- ▶ Enhanced chip evacuation by polished flute upgraded TiAlN nano layer full coating
- ▶ MQL system compatible (Minimum Quantity Lubrication)



EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DHM30030	3.0		.1181	6	100	140	DHM30053	5.3		.2087	6	183	223
DHM30031	3.1		.1220	6	117	157	DHM30054	5.4		.2126	6	183	223
DHM30008F	3.175	1/8	.1250	6	117	157	DHM30055	5.5		.2165	6	183	223
DHM30032	3.2		.1260	6	117	157	DHM30056	5.6		.2205	6	199	239
DHM30033	3.3		.1299	6	117	157	DHM30057	5.7		.2244	6	199	239
DHM30034	3.4		.1339	6	117	157	DHM30058	5.8		.2283	6	199	239
DHM30035	3.5		.1378	6	117	157	DHM30059	5.9		.2323	6	199	239
DHM30036	3.6		.1417	6	133	173	DHM30060	6.0		.2362	6	199	239
DHM30037	3.7		.1457	6	133	173	DHM30061	6.1		.2402	8	216	256
DHM30038	3.8		.1496	6	133	173	DHM30062	6.2		.2441	8	216	256
DHM30039	3.9		.1535	6	133	173	DHM30063	6.3		.2480	8	216	256
DHM30040	4.0		.1575	6	133	173	DHM30016F	6.350	1/4	.2500	8	216	256
DHM30041	4.1		.1614	6	150	190	DHM30064	6.4		.2520	8	216	256
DHM30042	4.2		.1654	6	150	190	DHM30065	6.5		.2559	8	216	256
DHM30043	4.3		.1693	6	150	190	DHM30206L	6.528	F	.2570	8	232	272
DHM30044	4.4		.1732	6	150	190	DHM30066	6.6		.2598	8	232	272
DHM30045	4.5		.1772	6	150	190	DHM30067	6.7		.2638	8	232	272
DHM30046	4.6		.1811	6	166	206	DHM30017F	6.746	17/64	.2656	8	232	272
DHM30047	4.7		.1850	6	166	206	DHM30068	6.8		.2677	8	232	272
DHM30048	4.8		.1890	6	166	206	DHM30069	6.9		.2717	8	232	272
DHM30049	4.9		.1929	6	166	206	DHM30209L	6.909	I	.2720	8	232	272
DHM30050	5.0		.1969	6	166	206	DHM30070	7.0		.2756	8	232	272
DHM30051	5.1		.2008	6	183	223	DHM30071	7.1		.2795	8	249	289
DHM30052	5.2		.2047	6	183	223	DHM30018F	7.142	9/32	.2812	8	249	289

▶ NEXT PAGE

© : Excellent ○ : Good

P				H		M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
-HB225	HB225~325	HRC30~45	HRC45~55	HRC55~								
◎	◎	○				○						





DHM30 SERIES

CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES

EXTRA LONG

- ▶ 4-Facet Point for good centering capability
- ▶ Optimized special flutes are ideal for removing chips and for productive drilling
- ▶ Enhanced chip evacuation by polished flute upgraded TiAlN nano layer full coating
- ▶ MQL system compatible (Minimum Quantity Lubrication)



EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter			Shank Diameter	Flute Length	Overall Length
	Metric	Inch	Decimal					Metric	Inch	Decimal			
TiAlN	D1			D2	L1	L2	TiAlN	D1			D2	L1	L2
DHM30072	7.2		.2835	8	249	289	DHM30077	7.7		.3031	8	265	305
DHM30073	7.3		.2874	8	249	289	DHM30078	7.8		.3071	8	265	305
DHM30074	7.4		.2913	8	249	289	DHM30079	7.9		.3110	8	265	305
DHM30075	7.5		.2953	8	249	289	DHM30020F	7.938	5/16	.3125	8	265	305
DHM30019F	7.541	19/64	.2969	8	265	305	DHM30080	8.0		.3150	8	265	305
DHM30076	7.6		.2992	8	265	305							

© : Excellent ○ : Good

P				H		M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
-HB225	HB225~325	HRC30~45	HRC45~55	HRC55~								
◎	◎	○				○						

Y/G DREAM DRILLS -MQL TYPE

RECOMMENDED CUTTING CONDITIONS

CARBIDE, DREAM DRILLS - MQL TYPE with COOLANT HOLES, TiAIN-COATED

DH510, DH515, DH520, DHM10, DHM15, DHM20 SERIES

WORK MATERIAL	P						K						
	CARBON STEELS						CAST IRON			DUCTILE CAST IRON			
STRENGTH	~ 1060 N/mm ²						250 ~ 350 N/mm ²			400 ~ 500 N/mm ²			
DRILLING SPEED(SFM)	230 ~ 290 ft/min						230 ~ 290 ft/min			220 ~ 240 ft/min			
DIAMETER	RPM		FEED		IPR		RPM		FEED		IPR		
	Metric(mm)	Decimal											
3.0	.1181	7500	0.06~0.12	.0024	.0047	7500	0.06~0.12	.0024	.0047	7500	0.06~0.12	.0024	.0047
4.0	.1575	6400	0.08~0.16	.0031	.0063	6400	0.08~0.16	.0031	.0063	5600	0.08~0.16	.0031	.0063
5.0	.1969	5800	0.10~0.20	.0039	.0079	5800	0.10~0.20	.0039	.0079	4500	0.10~0.20	.0039	.0079
6.0	.2362	4800	0.12~0.24	.0047	.0094	4800	0.12~0.24	.0047	.0094	3800	0.12~0.24	.0047	.0094
8.0	.3150	3600	0.16~0.28	.0063	.0110	3600	0.16~0.28	.0063	.0110	2800	0.16~0.28	.0063	.0110
10.0	.3937	2900	0.20~0.35	.0079	.0138	2900	0.20~0.35	.0079	.0138	2300	0.20~0.35	.0079	.0138
12.0	.4724	2400	0.24~0.42	.0094	.0165	2400	0.24~0.42	.0094	.0165	1900	0.24~0.42	.0094	.0165
14.0	.5512	2050	0.28~0.46	.0110	.0181	2050	0.28~0.46	.0110	.0181	1600	0.28~0.46	.0110	.0181

RPM = rev./min.
FEED = mm/rev.
IPR = inch/rev.

DHM25, DHM30 SERIES

WORK MATERIAL	P						K						
	CARBON STEELS						CAST IRON			DUCTILE CAST IRON			
STRENGTH	~ 1060 N/mm ²						250 ~ 350 N/mm ²			400 ~ 500 N/mm ²			
DRILLING SPEED(SFM)	230 ~ 290 ft/min						230 ~ 290 ft/min			220 ~ 240 ft/min			
DIAMETER	RPM		FEED		IPR		RPM		FEED		IPR		
	Metric(mm)	Decimal											
3.0	.1181	6400	0.06~0.12	.0024	.0047	6400	0.06~0.12	.0024	.0047	6400	0.06~0.12	.0024	.0047
4.0	.1575	5500	0.08~0.16	.0031	.0063	5500	0.08~0.16	.0031	.0063	4700	0.08~0.16	.0031	.0063
5.0	.1969	4900	0.10~0.20	.0039	.0079	4900	0.10~0.20	.0039	.0079	3800	0.10~0.20	.0039	.0079
6.0	.2362	4200	0.12~0.24	.0047	.0094	4200	0.12~0.24	.0047	.0094	3200	0.12~0.24	.0047	.0094
8.0	.3150	3000	0.16~0.28	.0063	.0110	3000	0.16~0.28	.0063	.0110	2400	0.16~0.28	.0063	.0110
10.0	.3937	2500	0.20~0.35	.0079	.0138	2500	0.20~0.35	.0079	.0138	1900	0.20~0.35	.0079	.0138

RPM = rev./min.
FEED = mm/rev.
IPR = inch/rev.


► Coolant Pressure : 900 PSI

1. Use a YG 3xD Drill to produce a guide hole no larger than .004 over the required drill size. Drill the pilot hole 2xD deep hole.
2. Enter the guide hole at 50 SFM surface and .010 feed rate / per rev.
3. Before hitting the bottom of the guide hole, Increase SFM and feed rate for normal drilling.
4. After drilling, to withdraw drill, reduce SFM to 50 @ 10 inches per minute.



Being the best through innovation

CARBIDE





DREAM DRILLS - For HIGH HARDENED STEELS

- HIGH HARDENED STEELS, HRc50~HRc70

SELECTION GUIDE

SOLID CARBIDE DREAM DRILLS for HIGH HARDENED STEELS

SOLID CARBIDE DREAM DRILLS for HIGH HARDENED STEELS
- High Hardened Steels, HRc50~HRc70

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
INCH					
DH501		CARBIDE, DREAM DRILLS for HIGH HARDENED STEELS (HRc50~70)	D1/8	D3/4	164
METRIC					
DH500		CARBIDE, DREAM DRILLS for HIGH HARDENED STEELS (HRc50~70)	D1.0	D14.0	166
		RECOMMENDED CUTTING CONDITIONS			167

◎ : Excellent ○ : Good

P			H		M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							

			◎	◎								
--	--	--	---	---	--	--	--	--	--	--	--	--


			◎	◎								
--	--	--	---	---	--	--	--	--	--	--	--	--

YG DREAM DRILLS for HIGH HARDENED STEELS

DH501 SERIES

CARBIDE, DREAM DRILLS for HIGH HARDENED STEELS (HRC50~70)

- ▶ Drilling for High Hardened Steels; Quenched Steels, Tempered Steels (under HRc 70)
- ▶ Special geometry design for Hardened Steels
- ▶ Minimum of cutting load through special thinning
- ▶ Performing good chip removal and powerful drilling
- ▶ Tolerance : Dia. Tolerance ØD1 : See page 135
Shank Tolerance ØD2: -.0001 -.0005



EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length
	Fractional	Decimal					Fractional	Decimal			
TiAIN	D1		D2	L1	L2	TiAIN	D1		D2	L1	L2
DH501001	1/8	.1250	1/8	21/32	2	DH501027	#4	.2090	1/4	1-9/32	2-7/8
DH501002	#30	.1285	3/16	23/32	2	DH501028	#3	.2130	1/4	1-13/32	3
DH501003	#29	.1360	3/16	13/16	2	DH501029	7/32	.2188	1/4	1-13/32	3
DH501004	#28	.1405	3/16	13/16	2	DH501030	#2	.2210	1/4	1-13/32	3
DH501005	9/64	.1406	3/16	13/16	2	DH501031	#1	.2280	1/4	1-13/32	3
DH501006	#27	.1440	3/16	13/16	2	DH501032	15/64	.2344	1/4	1-13/32	3
DH501007	#26	.1470	3/16	13/16	2	DH501033	B	.2380	1/4	1-19/32	3-1/8
DH501008	#25	.1495	3/16	7/8	2-1/16	DH501034	C	.2420	1/4	1-19/32	3-1/8
DH501009	#24	.1520	3/16	7/8	2-1/16	DH501035	D	.2460	1/4	1-19/32	3-1/8
DH501010	#23	.1540	3/16	7/8	2-1/16	DH501036	1/4	.2500	1/4	1-19/32	3-1/8
DH501011	5/32	.1562	3/16	7/8	2-1/16	DH501037	F	.2570	3/8	1-19/32	3-1/8
DH501012	#22	.1570	3/16	7/8	2-1/16	DH501038	G	.2610	3/8	1-19/32	3-1/8
DH501013	#21	.1590	3/16	7/8	2-1/16	DH501039	17/64	.2656	3/8	1-19/32	3-1/8
DH501014	#20	.1610	3/16	1	2-1/2	DH501040	I	.2720	3/8	1-25/32	3-3/8
DH501015	#19	.1660	3/16	1	2-1/2	DH501041	J	.2770	3/8	1-25/32	3-3/8
DH501016	11/64	.1719	3/16	1-1/8	2-3/4	DH501042	9/32	.2812	3/8	1-25/32	3-3/8
DH501017	#15	.1800	3/16	1-1/8	2-3/4	DH501043	L	.2900	3/8	1-25/32	3-3/8
DH501018	#14	.1820	3/16	1-1/8	2-3/4	DH501044	M	.2950	3/8	1-25/32	3-3/8
DH501019	3/16	.1875	3/16	1-1/8	2-3/4	DH501045	19/64	.2969	3/8	1-25/32	3-3/8
DH501020	#10	.1935	1/4	1-9/32	2-7/8	DH501046	N	.3020	3/8	1-31/32	3-7/8
DH501021	#9	.1960	1/4	1-9/32	2-7/8	DH501047	5/16	.3125	3/8	1-31/32	3-7/8
DH501022	#8	.1990	1/4	1-9/32	2-7/8	DH501048	O	.3160	3/8	1-31/32	3-7/8
DH501023	#7	.2010	1/4	1-9/32	2-7/8	DH501049	21/64	.3281	3/8	1-31/32	3-7/8
DH501024	13/64	.2031	1/4	1-9/32	2-7/8	DH501050	Q	.3320	3/8	1-31/32	3-7/8
DH501025	#6	.2040	1/4	1-9/32	2-7/8	DH501051	R	.3390	3/8	2-1/4	4-1/8
DH501026	#5	.2055	1/4	1-9/32	2-7/8	DH501052	11/32	.3438	3/8	2-1/4	4-1/8

▶ NEXT PAGE

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55 HRc55~								
			◎	◎							

YG DREAM DRILLS for HIGH HARDENED STEELS

DH501 SERIES

CARBIDE, DREAM DRILLS for HIGH HARDENED STEELS (HRC50~70)

- ▶ Drilling for High Hardened Steels; Quenched Steels, Tempered Steels (under HRc 70)
- ▶ Special geometry design for Hardened Steels
- ▶ Minimum of cutting load through special thinning
- ▶ Performing good chip removal and powerful drilling
- ▶ Tolerance : Dia. Tolerance ØD1 : See page 135
Shank Tolerance ØD2: -.0001 -.0005



EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length
	Fractional	Decimal					Fractional	Decimal			
TiAIN	D1		D2	L1	L2	TiAIN	D1		D2	L1	L2
DH501053	23/64	.3594	3/8	2-1/4	4-1/8	DH501069	17/32	.5312	5/8	3-1/16	5
DH501054	U	.3680	3/8	2-1/4	4-1/8	DH501070	35/64	.5469	5/8	3-1/16	5
DH501055	3/8	.3750	3/8	2-1/4	4-1/8	DH501071	9/16	.5625	5/8	3-1/16	5
DH501056	V	.3770	1/2	2-1/2	4-3/8	DH501072	37/64	.5781	5/8	3-9/32	5-1/4
DH501057	25/64	.3906	1/2	2-1/2	4-3/8	DH501073	19/32	.5937	5/8	3-9/32	5-1/4
DH501058	X	.3970	1/2	2-1/2	4-3/8	DH501074	39/64	.6094	5/8	3-9/32	5-1/4
DH501059	Y	.4040	1/2	2-1/2	4-3/8	DH501075	5/8	.6250	5/8	3-9/32	5-1/4
DH501060	13/32	.4062	1/2	2-1/2	4-3/8	DH501076	41/64	.6406	3/4	3-9/32	5-1/4
DH501061	Z	.4130	1/2	2-1/2	4-3/8	DH501077	21/32	.6563	3/4	3-11/16	5-5/8
DH501062	27/64	.4219	1/2	2-13/16	4-5/8	DH501078	43/64	.6719	3/4	3-11/16	5-5/8
DH501063	7/16	.4375	1/2	2-13/16	4-5/8	DH501079	11/16	.6875	3/4	3-11/16	5-5/8
DH501064	29/64	.4531	1/2	2-13/16	4-5/8	DH501080	45/64	.7031	3/4	3-11/16	5-5/8
DH501065	15/32	.4688	1/2	2-13/16	4-5/8	DH501081	23/32	.7188	3/4	3-3/4	6
DH501066	31/64	.4844	1/2	2-13/16	4-5/8	DH501082	47/64	.7344	3/4	3-3/4	6
DH501067	1/2	.5000	1/2	3-1/16	5	DH501083	3/4	.7500	3/4	3-3/4	6
DH501068	33/64	.5156	5/8	3-1/16	5						


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRc45~55 HRc55~								
			◎	◎							

YG DREAM DRILLS for HIGH HARDENED STEELS

DH500 SERIES

CARBIDE, DREAM DRILLS for HIGH HARDENED STEELS (HRC50~70)

- ▶ Drilling for High Hardened Steels; Quenched Steels, Tempered Steels (under HRc 70)
- ▶ Special geometry design for Hardened Steels
- ▶ Minimum of cutting load through special thinning
- ▶ Performing good chip removal and powerful drilling



Unit : mm

EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter		Shank Diameter	Flute Length	Overall Length
	Metric	Decimal					Metric	Decimal			
TiAIN	D1		D2	L1	L2	TiAIN	D1		D2	L1	L2
DH500010	1.0	.0394	3	6	40	DH500051	5.1	.2008	6	32	72
DH500011	1.1	.0433	3	6	40	DH500052	5.2	.2047	6	32	72
DH500012	1.2	.0472	3	6	40	DH500053	5.3	.2087	6	32	72
DH500013	1.3	.0512	3	8	40	DH500055	5.5	.2165	6	35	75
DH500014	1.4	.0551	3	8	40	DH500060	6.0	.2362	6	35	75
DH500015	1.5	.0591	3	8	40	DH500062	6.2	.2441	8	40	80
DH500016	1.6	.0630	3	10	40	DH500065	6.5	.2559	8	40	80
DH500017	1.7	.0669	3	10	40	DH500068	6.8	.2677	8	45	85
DH500018	1.8	.0709	3	10	40	DH500069	6.9	.2717	8	45	85
DH500019	1.9	.0748	3	10	40	DH500070	7.0	.2756	8	45	85
DH500020	2.0	.0787	3	12	42	DH500075	7.5	.2953	8	45	85
DH500025	2.5	.0984	3	14	44	DH500080	8.0	.3150	8	50	98
DH500026	2.6	.1024	3	16	44	DH500085	8.5	.3346	10	50	98
DH500028	2.8	.1102	3	16	46	DH500086	8.6	.3386	10	57	105
DH500030	3.0	.1181	3	18	46	DH500088	8.8	.3465	10	57	105
DH500033	3.3	.1299	4	18	48	DH500090	9.0	.3543	10	57	105
DH500034	3.4	.1339	4	20	50	DH500093	9.3	.3661	10	57	105
DH500035	3.5	.1378	4	20	50	DH500095	9.5	.3740	10	57	105
DH500038	3.8	.1496	4	22	52	DH500100	10.0	.3937	10	63	111
DH500040	4.0	.1575	4	22	52	DH500102	10.2	.4016	12	63	111
DH500041	4.1	.1614	6	25	65	DH500103	10.3	.4055	12	63	111
DH500042	4.2	.1654	6	25	65	DH500105	10.5	.4134	12	71	111
DH500043	4.3	.1693	6	28	68	DH500108	10.8	.4252	12	71	119
DH500044	4.4	.1732	6	28	68	DH500110	11.0	.4331	12	71	119
DH500045	4.5	.1772	6	28	68	DH500115	11.5	.4528	12	71	119
DH500046	4.6	.1811	6	28	68	DH500120	12.0	.4724	12	71	119
DH500048	4.8	.1890	6	32	72	DH500121	12.1	.4764	14	77	125
DH500049	4.9	.1929	6	32	72	DH500140	14.0	.5512	14	77	125
DH500050	5.0	.1969	6	32	72						

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
			◎	◎							

YG DREAM DRILLS for HIGH HARDENED STEELS

RECOMMENDED CUTTING CONDITIONS

CARBIDE, DREAM DRILLS for HIGH HARDENED STEELS (HRC50~70), TiAIN-COATED

DH501 SERIES

WORK MATERIAL			P			H					
			HARDENED STEELS			HIGH HARDENED STEELS			HIGH HARDENED STEELS		
			HRc 50~55			HRc 55~60			HRc 60~70		
DRILLING SPEED(SFM)			45 ~ 72 ft/min			32 ~ 52 ft/min			26 ~ 42 ft/min		
DIAMETER			RPM	FEED	IPR	RPM	FEED	IPR	RPM	FEED	IPR
Inch	Metric(mm)	Decimal									
5/64	1.984	.0781	2860	0.04	.0015	2000	0.04	.0015	1900	0.04	.0015
1/8	3.175	.1250	1900	0.04	.0015	1330	0.04	.0015	1250	0.04	.0015
5/32	3.969	.1563	1430	0.04	.0015	1000	0.04	.0015	950	0.04	.0015
13/64	5.159	.2031	1150	0.04	.0015	800	0.04	.0015	750	0.04	.0015
15/64	5.953	.2344	960	0.04	.0015	670	0.04	.0015	630	0.04	.0015
5/16	7.938	.3125	720	0.04	.0015	500	0.04	.0015	480	0.04	.0015
25/64	9.922	.3906	570	0.04	.0015	400	0.04	.0015	380	0.04	.0015
15/32	11.906	.4688	480	0.04	.0015	330	0.04	.0015	320	0.04	.0015
9/16	14.288	.5625	435	0.04	.0015	280	0.04	.0015	270	0.04	.0015
41/64	16.272	.6406	380	0.04	.0015	250	0.04	.0015	240	0.04	.0015
11/16	17.463	.6875	325	0.04	.0015	235	0.04	.0015	190	0.04	.0015
47/64	18.653	.7344	310	0.04	.0015	220	0.04	.0015	180	0.04	.0015

RPM = rev./min.
FEED = mm/rev.
IPR = inch/rev.

DH500 SERIES


WORK MATERIAL		P			H					
		HARDENED STEELS			HIGH HARDENED STEEL S			HIGH HARDENED STEEL S		
		HRc 50~55			HRc 55~60			HRc 60~70		
DRILLING SPEED(SFM)		45 ~ 72 ft/min			32 ~ 52 ft/min			26 ~ 42 ft/min		
DIAMETER		RPM	FEED	IPR	RPM	FEED	IPR	RPM	FEED	IPR
Metric(mm)	Inch									
1.0	.0394	5600	0.04	.0015	4000	0.04	.0015	3700	0.04	.0015
2.0	.0787	2900	0.04	.0015	2100	0.04	.0015	1900	0.04	.0015
3.0	.1181	1900	0.04	.0015	1330	0.04	.0015	1250	0.04	.0015
4.0	.1575	1430	0.04	.0015	1000	0.04	.0015	950	0.04	.0015
5.0	.1969	1150	0.04	.0015	800	0.04	.0015	750	0.04	.0015
6.0	.2362	960	0.04	.0015	670	0.04	.0015	630	0.04	.0015
8.0	.3150	720	0.04	.0015	500	0.04	.0015	480	0.04	.0015
10.0	.3937	570	0.04	.0015	400	0.04	.0015	380	0.04	.0015
12.0	.4724	480	0.04	.0015	330	0.04	.0015	320	0.04	.0015
14.0	.5512	438	0.04	.0015	282	0.04	.0015	272	0.04	.0015

RPM = rev./min.
FEED = mm/rev.
IPR = inch/rev.



Being the best through innovation

CARBIDE




STANDARD CARBIDE DRILLS

- General Purpose
- 118° Point



Global Cutting Tool Leader **YG-1**




SELECTION GUIDE

STANDARD SOLID CARBIDE DRILLS

STANDARD SOLID CARBIDE DRILLS

- General Purpose
- 118° Point

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
INCH					
D5412 DH412		CARBIDE DRILLS / Wire gauge sizes	JOBBER	#56 #1	172
D5413 DH413		CARBIDE DRILLS / Letter sizes	JOBBER	A Z	173
D5417 DH417		CARBIDE DRILLS / Fractional sizes	JOBBER	D3/64 D1/2	174
RECOMMENDED CUTTING CONDITIONS					175

◎ : Excellent ○ : Good

P			H		M	K	N			S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	○				○	○	○				○
◎	○				○	○	○				○
◎	○				○	○	○				○


STANDARD CARBIDE DRILLS

DH412 SERIES
D5412 SERIES

CARBIDE DRILLS

JOBBER

► **Application** : Drilling steels in general, cast steels, cast iron, chilled cast iron, malleable cast iron, non-ferrous heavy metals, non-ferrous light metals, abrasive plastics.



under .1181 inch .1181 inch & over



D₁=D₂

► **Wire gauge sizes**

Unit : Inch

EDP No.		Diameter		Flute Length	Overall Length	EDP No.		Diameter		Flute Length	Overall Length
Bright Finish	TiAIN	Wire gauge	Decimal	L ₁	L ₂	Bright Finish	TiAIN	Wire gauge	Decimal	L ₁	L ₂
		D ₁ = D ₂						D ₁ = D ₂			
D5412101	DH412101	1	.2280	1-3/4	3	D5412129	DH412129	29	.1360	1-3/8	2-1/2
D5412102	DH412102	2	.2210	1-3/4	3	D5412130	DH412130	30	.1285	1-1/4	2-1/4
D5412103	DH412103	3	.2130	1-3/4	3	D5412131	DH412131	31	.1200	1-1/4	2-1/4
D5412104	DH412104	4	.2090	1-3/4	3	D5412132	DH412132	32	.1160	1-1/4	2-1/4
D5412105	DH412105	5	.2055	1-3/4	3	D5412133	DH412133	33	.1130	1-1/4	2-1/4
D5412106	DH412106	6	.2040	1-3/4	3	D5412134	DH412134	34	.1110	1-1/4	2-1/4
D5412107	DH412107	7	.2010	1-3/4	3	D5412135	DH412135	35	.1100	1-1/4	2-1/4
D5412108	DH412108	8	.1990	1-3/4	3	D5412136	DH412136	36	.1065	1-1/4	2-1/4
D5412109	DH412109	9	.1960	1-3/4	3	D5412137	DH412137	37	.1040	1-1/4	2-1/4
D5412110	DH412110	10	.1935	1-5/8	2-3/4	D5412138	DH412138	38	.1015	1-1/4	2-1/4
D5412111	DH412111	11	.1910	1-5/8	2-3/4	D5412139	DH412139	39	.0995	1-1/4	2-1/4
D5412112	DH412112	12	.1890	1-5/8	2-3/4	D5412140	DH412140	40	.0980	1	2
D5412113	DH412113	13	.1850	1-5/8	2-3/4	D5412141	DH412141	41	.0960	1	2
D5412114	DH412114	14	.1820	1-5/8	2-3/4	D5412142	DH412142	42	.0935	1	2
D5412115	DH412115	15	.1800	1-5/8	2-3/4	D5412143	DH412143	43	.0890	1	2
D5412116	DH412116	16	.1770	1-5/8	2-3/4	D5412144	DH412144	44	.0860	1	2
D5412117	DH412117	17	.1730	1-5/8	2-3/4	D5412145	DH412145	45	.0820	7/8	1-3/4
D5412118	DH412118	18	.1695	1-5/8	2-3/4	D5412146	DH412146	46	.0810	7/8	1-3/4
D5412119	DH412119	19	.1660	1-5/8	2-3/4	D5412147	DH412147	47	.0785	7/8	1-3/4
D5412120	DH412120	20	.1610	1-3/8	2-1/2	D5412148	DH412148	48	.0760	7/8	1-3/4
D5412121	DH412121	21	.1590	1-3/8	2-1/2	D5412149	DH412149	49	.0730	7/8	1-3/4
D5412122	DH412122	22	.1570	1-3/8	2-1/2	D5412150	DH412150	50	.0700	7/8	1-3/4
D5412123	DH412123	23	.1540	1-3/8	2-1/2	D5412151	DH412151	51	.0670	3/4	1-1/2
D5412124	DH412124	24	.1520	1-3/8	2-1/2	D5412152	DH412152	52	.0635	3/4	1-1/2
D5412125	DH412125	25	.1495	1-3/8	2-1/2	D5412153	DH412153	53	.0595	3/4	1-1/2
D5412126	DH412126	26	.1470	1-3/8	2-1/2	D5412154	DH412154	54	.0550	3/4	1-1/2
D5412127	DH412127	27	.1440	1-3/8	2-1/2	D5412155	DH412155	55	.0520	3/4	1-1/2
D5412128	DH412128	28	.1405	1-3/8	2-1/2	D5412156	DH412156	56	.0465	3/4	1-1/2

► Other coating is available on you request.

◎ : Excellent ○ : Good

P		H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	○				○	○	○				○


STANDARD CARBIDE DRILLS

DH413 SERIES
D5413 SERIES

CARBIDE DRILLS

JOBBER

► **Application** : Drilling steels in general, cast steels, cast iron, chilled cast iron, malleable cast iron, non-ferrous heavy metals, non-ferrous light metals, abrasive plastics.



D₁=D₂

► **Letter sizes**

Unit : Inch

EDP No.		Diameter		Flute Length	Overall Length	EDP No.		Diameter		Flute Length	Overall Length
Bright Finish	TiAIN	Letter	Decimal	L ₁	L ₂	Bright Finish	TiAIN	Letter	Decimal	L ₁	L ₂
		D ₁ = D ₂						D ₁ = D ₂			
D5413201	DH413201	A	.2340	2	3-1/4	D5413214	DH413214	N	.3020	2-3/8	3-3/4
D5413202	DH413202	B	.2380	2	3-1/4	D5413215	DH413215	O	.3160	2-3/8	3-3/4
D5413203	DH413203	C	.2420	2	3-1/4	D5413216	DH413216	P	.3230	2-3/8	3-3/4
D5413204	DH413204	D	.2460	2	3-1/4	D5413217	DH413217	Q	.3320	2-1/2	4
D5413205	DH413205	E	.2500	2	3-1/4	D5413218	DH413218	R	.3390	2-1/2	4
D5413206	DH413206	F	.2570	2	3-1/4	D5413219	DH413219	S	.3480	2-1/2	4
D5413207	DH413207	G	.2610	2-1/8	3-1/2	D5413220	DH413220	T	.3580	2-3/4	4-1/4
D5413208	DH413208	H	.2660	2-1/8	3-1/2	D5413221	DH413221	U	.3680	2-3/4	4-1/4
D5413209	DH413209	I	.2720	2-1/8	3-1/2	D5413222	DH413222	V	.3770	2-3/4	4-1/4
D5413210	DH413210	J	.2770	2-1/8	3-1/2	D5413223	DH413223	W	.3860	2-7/8	4-1/2
D5413211	DH413211	K	.2810	2-1/8	3-1/2	D5413224	DH413224	X	.3970	2-7/8	4-1/2
D5413212	DH413212	L	.2900	2-1/8	3-1/2	D5413225	DH413225	Y	.4040	2-7/8	4-1/2
D5413213	DH413213	M	.2950	2-3/8	3-3/4	D5413226	DH413226	Z	.4130	2-7/8	4-1/2

► Other coating is available on you request.

◎ : Excellent ○ : Good

P		H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	○				○	○	○				○

YG STANDARD CARBIDE DRILLS


DH417 SERIES

D5417 SERIES

CARBIDE DRILLS

JOBBER

► **Application** : Drilling steels in general, cast steels, cast iron, chilled cast iron, malleable cast iron, non-ferrous heavy metals, non-ferrous light metals, abrasive plastics.



D1=D2

► **Fractional sizes**

Unit : Inch

EDP No.		Diameter		Flute Length	Overall Length	EDP No.		Diameter		Flute Length	Overall Length
Bright Finish	TiAlN	Fractional	Decimal	L1	L2	Bright Finish	TiAlN	Fractional	Decimal	L1	L2
		D1 = D2						D1 = D2			
D5417003	DH417003	3/64	.0469	3/4	1-1/2	D5417018	DH417018	9/32	.2813	2-1/8	3-1/2
D5417004	DH417004	1/16	.0625	3/4	1-1/2	D5417019	DH417019	19/64	.2969	2-3/8	3-3/4
D5417005	DH417005	5/64	.0781	7/8	1-3/4	D5417020	DH417020	5/16	.3125	2-3/8	3-3/4
D5417006	DH417006	3/32	.0938	1	2	D5417021	DH417021	21/64	.3281	2-1/2	4
D5417007	DH417007	7/64	.1094	1-1/4	2-1/4	D5417022	DH417022	11/32	.3438	2-1/2	4
D5417008	DH417008	1/8	.1250	1-1/4	2-1/4	D5417023	DH417023	23/64	.3594	2-3/4	4-1/4
D5417009	DH417009	9/64	.1406	1-3/8	2-1/2	D5417024	DH417024	3/8	.3750	2-3/4	4-1/4
D5417010	DH417010	5/32	.1563	1-3/8	2-1/2	D5417025	DH417025	25/64	.3906	2-7/8	4-1/2
D5417011	DH417011	11/64	.1719	1-5/8	2-3/4	D5417026	DH417026	13/32	.4063	2-7/8	4-1/2
D5417012	DH417012	3/16	.1875	1-5/8	2-3/4	D5417027	DH417027	27/64	.4219	2-7/8	4-1/2
D5417013	DH417013	13/64	.2031	1-3/4	3	D5417028	DH417028	7/16	.4375	2-7/8	4-1/2
D5417014	DH417014	7/32	.2188	1-3/4	3	D5417029	DH417029	29/64	.4531	3	4-3/4
D5417015	DH417015	15/64	.2344	2	3-1/4	D5417030	DH417030	15/32	.4688	3	4-3/4
D5417016	DH417016	1/4	.2500	2	3-1/4	D5417031	DH417031	31/64	.4844	3	4-3/4
D5417017	DH417017	17/64	.2656	2-1/8	3-1/2	D5417032	DH417032	1/2	.5000	3	4-3/4

► Other coating is available on you request.

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55								HRC55~
◎	○			○	○	○				○	

YG STANDARD CARBIDE DRILLS

RECOMMENDED CUTTING CONDITIONS

CARBIDE DRILLS

D5412, DH412, D5413, DH413, D5417, DH417 SERIES

WORK MATERIAL	P				K			
	NON-ALLOY STEELS		ALLOY STEELS		SOFT GREY CAST IRON		HARD GREY CAST IRON	
DIAMETER	N	S	N	S	N	S	N	S
3/64	23000	.0012	17200	.0012	32000	.0016	23000	.0016
5/64	11500	.0016	8600	.0016	16000	.0020	11500	.0020
1/8	7800	.0020	5750	.0020	10500	.0024	7600	.0024
5/32	5800	.0024	4300	.0024	7800	.0028	5700	.0028
13/64	4700	.0028	3450	.0028	6200	.0031	4550	.0031
15/64	3900	.0031	2850	.0031	5200	.0035	3800	.0035
9/32	3350	.0035	2450	.0035	4500	.0039	3250	.0039
5/16	2900	.0039	2150	.0039	3900	.0047	2850	.0047
23/64	2600	.0043	1900	.0043	3450	.0055	2550	.0055
25/64	2350	.0047	1700	.0047	3100	.0063	2300	.0063
7/16	2150	.0051	1600	.0051	2850	.0071	2100	.0071
15/32	1950	.0055	1450	.0055	2600	.0079	1900	.0079
33/64	1800	.0063	1350	.0063	2400	.0079	1750	.0079

WORK MATERIAL	M		N					
	STAINLESS STEELS		Al-Si ALLOY, Si<10%		Al-Si ALLOY, Si>10%		Ti, Ni ALLOY STEELS	
DIAMETER	N	S	N	S	N	S	N	S
3/64	12000	.0016	54000	.0020	42000	.0020	11800	.0008
5/64	6000	.0012	27000	.0024	21000	.0024	5900	.0012
1/8	4000	.0016	18000	.0028	14000	.0028	3900	.0016
5/32	3000	.0020	13000	.0031	10500	.0031	2950	.0020
13/64	2400	.0024	10500	.0035	8500	.0035	2350	.0024
15/64	2000	.0028	8800	.0043	7100	.0043	1950	.0028
9/32	1700	.0031	7600	.0051	6100	.0051	1700	.0031
5/16	1500	.0035	6600	.0059	5350	.0059	1450	.0035
23/64	1350	.0039	5900	.0067	4750	.0067	1300	.0039
25/64	1200	.0043	5300	.0075	4250	.0075	1200	.0043
7/16	1100	.0047	4850	.0083	3900	.0083	1050	.0047
15/32	1000	.0051	4450	.0091	3550	.0091	980	.0051
33/64	950	.0051	4100	.0098	3300	.0098	905	.0051

N = R.P.M
S = Inch per Revolution(inch/rev.)



Being the best through innovation

HSS




MULTI-1 DRILLS

HSS-PM MULTI-1 DRILLS

- Multi Purpose Drilling. Particularly for Stainless Steels, Titanium






Global Cutting Tool Leader **YG-1**



SELECTION GUIDE

HSS-PM MULTI-1 DRILLS

PREMIUM HSS-PM MULTI-1 DRILLS
 Premium HSS-PM Drills for wide range of applications
 - Carbon Steels, Alloy Steels, Stainless steels, Titanium etc.

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
INCH					
CDRA05		PREMIUM HSS-PM MULTI-1 DRILLS / M15 Fractional sizes	D3/32	D1/2	180
CDRA06		PREMIUM HSS-PM MULTI-1 DRILLS / M16 Wire gauge sizes	#45	#1	181
CDRA07		PREMIUM HSS-PM MULTI-1 DRILLS / M17 Letter sizes	B	Z	182
		RECOMMENDED CUTTING CONDITIONS			183

◎ : Excellent ○ : Good


P			H	M	K	N				S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			○	○	○				◎
◎	◎	○			○	○	○				◎
◎	◎	○			○	○	○				◎

Y/G MULTI-1 DRILLS

CDRA05 SERIES

PREMIUM HSS-PM, MULTI-1 DRILLS

- **Features :** Excellent wear resistance by using Premium powder metallurgy materials. With special point geometry, no centering required. Minimal drill wandering and improved hole tolerances. Better tool life with excellent coating.
- **Application :** Applicable to various materials including aluminum and stainless steel, as well carbon steel and structural steel.



► **M15 / Fractional sizes**

Unit : Inch

EDP No.	Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Diameter		Shank Diameter	Flute Length	Overall Length
	Fractional	Decimal					Fractional	Decimal			
TiAlN	D1		D2	L1	L2	TiAlN	D1		D2	L1	L2
M15006	3/32	.0938	1/8	1/2	1-3/4	M15020	5/16	.3125	3/8	1-1/2	3-3/8
M15007	7/64	.1094	1/8	5/8	1-7/8	M15021	21/64	.3281	3/8	1-1/2	3-3/8
M15008	1/8	.1250	1/8	3/4	2	M15022	11/32	.3438	3/8	1-5/8	3-1/2
M15009	9/64	.1406	3/16	13/16	2-1/8	M15023	23/64	.3594	3/8	1-5/8	3-1/2
M15010	5/32	.1563	3/16	13/16	2-1/8	M15024	3/8	.3750	3/8	1-5/8	3-1/2
M15011	11/64	.1719	3/16	1	2-3/8	M15025	25/64	.3906	1/2	1-11/16	3-7/8
M15012	3/16	.1875	3/16	1	2-3/8	M15026	13/32	.4063	1/2	1-11/16	3-7/8
M15013	13/64	.2031	1/4	1-1/8	2-7/8	M15027	27/64	.4219	1/2	1-7/8	4-1/8
M15014	7/32	.2188	1/4	1-1/8	2-7/8	M15028	7/16	.4375	1/2	1-7/8	4-1/8
M15015	15/64	.2344	1/4	1-1/4	3	M15029	29/64	.4531	1/2	1-7/8	4-1/8
M15016	1/4	.2500	1/4	1-1/4	3	M15030	15/32	.4688	1/2	2	4-1/4
M15017	17/64	.2656	3/8	1-3/8	3-3/16	M15031	31/64	.4844	1/2	2	4-1/4
M15018	9/32	.2813	3/8	1-3/8	3-3/16	M15032	1/2	.5000	1/2	2	4-1/4
M15019	19/64	.2969	3/8	1-3/8	3-3/16						

◎ : Excellent ○ : Good


P			H	M	K	N				S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			○	○	○				◎

Y/G MULTI-1 DRILLS

CDRA06 SERIES

PREMIUM HSS-PM, MULTI-1 DRILLS

- **Features :** Excellent wear resistance by using Premium powder metallurgy materials. With special point geometry, no centering required. Minimal drill wandering and improved hole tolerances. Better tool life with excellent coating.
- **Application :** Applicable to various materials including aluminum and stainless steel, as well carbon steel and structural steel.



► **M16 / Wire gauge sizes**

Unit : Inch

EDP No.	Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Diameter		Shank Diameter	Flute Length	Overall Length
	Wire gauge	Decimal					Wire gauge	Decimal			
TiAlN	D1		D2	L1	L2	TiAlN	D1		D2	L1	L2
M16045	45	.0820	1/8	3/4	2	M16022	22	.1570	3/16	1-1/16	2-1/2
M16044	44	.0860	1/8	3/4	2	M16021	21	.1590	3/16	1-1/16	2-1/2
M16043	43	.0890	1/8	3/4	2	M16020	20	.1610	3/16	1-1/16	2-1/2
M16042	42	.0935	1/8	3/4	2	M16019	19	.1660	3/16	1-1/16	2-1/2
M16041	41	.0960	1/8	13/16	2-1/16	M16018	18	.1695	3/16	1-1/16	2-1/2
M16040	40	.0980	1/8	13/16	2-1/16	M16017	17	.1730	3/16	1-1/8	2-9/16
M16039	39	.0995	1/8	13/16	2-1/4	M16016	16	.1770	3/16	1-1/8	2-9/16
M16038	38	.1015	1/8	13/16	2-1/4	M16015	15	.1800	3/16	1-1/8	2-9/16
M16037	37	.1040	1/8	13/16	2-1/4	M16014	14	.1820	3/16	1-1/8	2-9/16
M16036	36	.1065	1/8	13/16	2-1/4	M16013	13	.1850	3/16	1-1/8	2-9/16
M16035	35	.1100	1/8	7/8	2-5/16	M16012	12	.1890	1/4	1-3/16	3
M16034	34	.1110	1/8	7/8	2-5/16	M16011	11	.1910	1/4	1-3/16	3
M16033	33	.1130	1/8	7/8	2-5/16	M16010	10	.1935	1/4	1-3/16	3
M16032	32	.1160	1/8	7/8	2-5/16	M16009	9	.1960	1/4	1-3/16	3
M16031	31	.1120	1/8	7/8	2-5/16	M16008	8	.1990	1/4	1-3/16	3
M16030	30	.1285	3/16	15/16	2-3/8	M16007	7	.2010	1/4	1-3/16	3
M16029	29	.1360	3/16	15/16	2-3/8	M16006	6	.2040	1/4	1-1/4	3-1/16
M16028	28	.1405	3/16	15/16	2-3/8	M16005	5	.2055	1/4	1-1/4	3-1/16
M16027	27	.1440	3/16	1	2-7/16	M16004	4	.2090	1/4	1-1/4	3-1/16
M16026	26	.1470	3/16	1	2-7/16	M16003	3	.2130	1/4	1-1/4	3-1/16
M16025	25	.1495	3/16	1	2-7/16	M16002	2	.2210	1/4	1-5/16	3-1/8
M16024	24	.1520	3/16	1	2-7/16	M16001	1	.2280	1/4	1-5/16	3-1/8
M16023	23	.1540	3/16	1	2-7/16						

◎ : Excellent ○ : Good


P			H	M	K	N				S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			○	○	○				◎

YG MULTI-1 DRILLS

CDRA07 SERIES

PREMIUM HSS-PM, MULTI-1 DRILLS

- **Features :** Excellent wear resistance by using Premium powder metallurgy materials. With special point geometry, no centering required. Minimal drill wandering and improved hole tolerances. Better tool life with excellent coating.
- **Application :** Applicable to various materials including aluminum and stainless steel, as well carbon steel and structural steel.



► M17 / Letter sizes

EDP No.		Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.		Diameter		Shank Diameter	Flute Length	Overall Length
TiAIN	D1	Letter	Decimal				TiAIN	D1	Letter	Decimal			
M1700B	B	.2380	1/4	1-3/8	3-3/16	M1700N	N	.3020	3/8	1-5/8	3-7/16		
M1700C	C	.2420	1/4	1-3/8	3-3/16	M1700O	O	.3160	3/8	1-11/16	3-1/2		
M1700D	D	.2460	1/4	1-3/8	3-3/16	M1700Q	Q	.3320	3/8	1-11/16	3-1/2		
M1700F	F	.2570	3/8	1-7/16	3-1/4	M1700R	R	.3390	3/8	1-11/16	3-1/2		
M1700G	G	.2610	3/8	1-7/16	3-1/4	M1700U	U	.3680	3/8	1-13/16	3-5/8		
M1700I	I	.2720	3/8	1-1/2	3-5/16	M1700V	V	.3770	1/2	1-7/8	3-31/32		
M1700J	J	.2770	3/8	1-1/2	3-5/16	M1700X	X	.3970	1/2	1-15/16	4-1/32		
M1700L	L	.2900	3/8	1-9/16	3-3/8	M1700Y	Y	.4040	1/2	1-15/16	4-1/32		
M1700M	M	.2950	3/8	1-9/16	3-3/8	M1700Z	Z	.4130	1/2	2	4-1/32		

Unit : Inch

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
-HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			○	○	○			◎	

YG MULTI-1 DRILLS

RECOMMENDED CUTTING CONDITIONS

PREMIUM HSS-PM, MULTI-1 DRILLS

CDRA05, CDRA06, CDRA07 SERIES

WORK MATERIAL	P								
	STRUCTURAL STEEL CARBON STEEL			ALLOY STEEL			MOLD STEEL		
	DIAMETER	RPM	FEED		RPM	FEED		RPM	FEED
(IPR)			(inch/min)	(IPR)		(inch/min)	(IPR)		(inch/min)
3/32	5000	.0030	15.00	4000	.0030	12.00	1800	.0030	5.40
1/8	3800	.0050	19.00	3000	.0040	12.00	1400	.0040	5.60
5/32	3000	.0060	18.00	2400	.0050	12.00	1100	.0040	4.40
3/16	2500	.0070	17.50	2000	.0050	10.00	900	.0040	3.60
1/4	1900	.0080	15.20	1500	.0070	10.50	700	.0050	3.50
5/16	1500	.0090	13.50	1200	.0080	9.60	550	.0070	3.85
3/8	1250	.0100	12.50	1000	.0090	9.00	450	.0080	3.60
1/2	950	.0110	10.45	750	.0100	7.50	350	.0090	3.15

WORK MATERIAL	M			K			N		
	STAINLESS STEEL			CAST IRON			ALUMINIUM ALLOY COPPER ALLOY NONFERROUS ALLOY		
	DIAMETER	RPM	FEED		RPM	FEED		RPM	FEED
(IPR)			(inch/min)	(IPR)		(inch/min)	(IPR)		(inch/min)
3/32	1800	.0030	5.40	5700	.0040	22.80	8700	.0040	34.80
1/8	1400	.0040	5.60	4250	.0060	25.50	6500	.0060	39.00
5/32	1100	.0040	4.40	3400	.0070	23.80	5200	.0070	36.40
3/16	900	.0040	3.60	2850	.0080	22.80	4300	.0080	34.40
1/4	700	.0050	3.50	2100	.0100	21.00	3200	.0090	28.80
5/16	550	.0070	3.85	1750	.0120	21.00	2600	.0110	28.60
3/8	450	.0080	3.60	1450	.0120	17.40	2200	.0130	28.60
1/2	350	.0090	3.15	1100	.0150	16.50	1650	.0150	24.75

WORK MATERIAL	S		
	NICKEL ALLOY TITANIUM ALLOY		
	DIAMETER	RPM	FEED
(IPR)			(inch/min)
3/32	800	.0010	0.80
1/8	600	.0020	1.20
5/32	500	.0020	1.00
3/16	400	.0020	0.80
1/4	300	.0030	0.90
5/16	250	.0030	0.75
3/8	200	.0040	0.80
1/2	150	.0050	0.75


N = R.P.M
S = Inch per Revolution(inch/rev.)

i-DREAM DRILLS
DREAM DRILLS -GENERAL
DREAM DRILLS -HIGH FEED
DREAM DRILLS -FLAT BOTTOM
DREAM DRILLS -INOX
DREAM DRILLS -ALU
DREAM DRILLS -MQL TYPE
DREAM DRILLS for HIGH HARDENED STEELS
STANDARD CARBIDE DRILLS
MULTI-1 DRILLS
HPD DRILLS
GOLD-P DRILLS
STRAIGHT SHANK DRILLS
AIRCRAFT DRILLS
SILVER & DEMING DRILLS
TAPER SHANK DRILLS
NC SPOTTING DRILLS
COMBINATION DRILLS & COUNTERSINK
SPADE DRILLS
TECHNICAL DATA

i-DREAM DRILLS
DREAM DRILLS -GENERAL
DREAM DRILLS -HIGH FEED
DREAM DRILLS -FLAT BOTTOM
DREAM DRILLS -INOX
DREAM DRILLS -ALU
DREAM DRILLS -MQL TYPE
DREAM DRILLS for HIGH HARDENED STEELS
STANDARD CARBIDE DRILLS
MULTI-1 DRILLS
HPD DRILLS
GOLD-P DRILLS
STRAIGHT SHANK DRILLS
AIRCRAFT DRILLS
SILVER & DEMING DRILLS
TAPER SHANK DRILLS
NC SPOTTING DRILLS
COMBINATION DRILLS & COUNTERSINK
SPADE DRILLS
TECHNICAL DATA



Global Cutting Tool Leader **YG-1**



HSS



Being the best through innovation





HPD DRILLS

HSS-EX HPD STRAIGHT SHANK DRILLS
- for Stainless Steels

SELECTION GUIDE

HPD - HIGH PERFORMANCE DRILLS
 HPD-SUS Drills for High precision drilling in Stainless steels

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
METRIC					
DJ543		HSS-EX, HPD-SUS DRILLS	<i>STUB</i>	D2.0 D13.0	188
DJ544		HSS-EX, HPD-SUS DRILLS	<i>JOBBER</i>	D2.0 D20.0	190
		RECOMMENDED CUTTING CONDITIONS			193

PREMIUM HSS HPD STRAIGHT SHANK DRILLS

◎ : Excellent ○ : Good

P			H		M	K	N			S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎					◎		○	○			○
◎					◎		○	○			○




DJ543 SERIES

HSS-EX, HPD-SUS DRILLS

STUB

- ▶ **Application** : Designed for drilling in stainless steels, mild steels, aluminum, aluminum alloy, aluminum die cast, copper, copper alloy, etc.
- ▶ **Advantage** : Self centering - center drilling is not required
 Excellent positioning - bush is not necessary
 Special Design - reaming is not required
 - good chip removal
 - powerful drilling
- ▶ **Plain Shank** : DIN6535-HA



D1=D2

EDP No.	Diameter		Flute Length	Overall Length	EDP No.	Diameter		Flute Length	Overall Length
	Metric	Inch				Metric	Inch		
	D1 = D2		L1	L2		D1 = D2		L1	L2
0201JCN	2.0	.0787	12	44	0481JCN	4.8	.1890	26	70
0211JCN	2.1	.0827	12	44	0491JCN	4.9	.1929	26	70
0221JCN	2.2	.0866	13	45	0501JCN	5.0	.1969	26	70
0231JCN	2.3	.0906	13	45	0511JCN	5.1	.2008	26	70
0241JCN	2.4	.0945	14	46	0521JCN	5.2	.2047	26	70
0251JCN	2.5	.0984	14	46	0531JCN	5.3	.2087	26	70
0261JCN	2.6	.1024	14	46	0541JCN	5.4	.2126	28	72
0271JCN	2.7	.1063	16	48	0551JCN	5.5	.2165	28	72
0281JCN	2.8	.1102	16	48	0561JCN	5.6	.2205	28	72
0291JCN	2.9	.1142	16	48	0571JCN	5.7	.2244	28	72
0301JCN	3.0	.1181	16	48	0581JCN	5.8	.2283	28	72
0311JCN	3.1	.1220	18	50	0591JCN	5.9	.2323	28	72
0321JCN	3.2	.1260	18	50	0601JCN	6.0	.2362	28	72
0331JCN	3.3	.1299	18	50	0611JCN	6.1	.2402	31	75
0341JCN	3.4	.1339	20	52	0621JCN	6.2	.2441	31	75
0351JCN	3.5	.1378	20	52	0631JCN	6.3	.2480	31	75
0361JCN	3.6	.1417	20	52	0641JCN	6.4	.2520	31	75
0371JCN	3.7	.1457	20	52	0651JCN	6.5	.2559	31	75
0381JCN	3.8	.1496	22	54	0661JCN	6.6	.2598	31	75
0391JCN	3.9	.1535	22	54	0671JCN	6.7	.2638	31	75
0401JCN	4.0	.1575	22	54	0681JCN	6.8	.2677	34	78
0411JCN	4.1	.1614	22	66	0691JCN	6.9	.2717	34	78
0421JCN	4.2	.1654	22	66	0701JCN	7.0	.2756	34	78
0431JCN	4.3	.1693	24	68	0711JCN	7.1	.2795	34	78
0441JCN	4.4	.1732	24	68	0721JCN	7.2	.2835	34	78
0451JCN	4.5	.1772	24	68	0731JCN	7.3	.2874	34	78
0461JCN	4.6	.1811	24	68	0741JCN	7.4	.2913	34	78
0471JCN	4.7	.1850	24	68	0751JCN	7.5	.2953	34	78

* Individually packaged ▶ NEXT PAGE
 ◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~								
◎				◎		○	○			○	




DJ543 SERIES

HSS-EX, HPD-SUS DRILLS

STUB

- ▶ **Application** : Designed for drilling in stainless steels, mild steels, aluminum, aluminum alloy, aluminum die cast, copper, copper alloy, etc.
- ▶ **Advantage** : Self centering - center drilling is not required
 Excellent positioning - bush is not necessary
 Special Design - reaming is not required
 - good chip removal
 - powerful drilling
- ▶ **Plain Shank** : DIN6535-HA



D1=D2

EDP No.	Diameter		Flute Length	Overall Length	EDP No.	Diameter		Flute Length	Overall Length
	Metric	Inch				Metric	Inch		
	D1 = D2		L1	L2		D1 = D2		L1	L2
0761JCN	7.6	.2992	37	81	1041JCN	10.4	.4094	43	100
0771JCN	7.7	.3031	37	81	1051JCN	10.5	.4134	43	100
0781JCN	7.8	.3071	37	81	1061JCN	10.6	.4173	43	100
0791JCN	7.9	.3110	37	81	1071JCN	10.7	.4212	47	104
0801JCN	8.0	.3150	37	81	1081JCN	10.8	.4252	47	104
0811JCN	8.1	.3189	37	87	1091JCN	10.9	.4291	47	104
0821JCN	8.2	.3228	37	87	1101JCN	11.0	.4330	47	104
0831JCN	8.3	.3268	37	87	1111JCN	11.1	.4370	47	104
0841JCN	8.4	.3307	37	87	1121JCN	11.2	.4409	47	104
0851JCN	8.5	.3346	37	87	1131JCN	11.3	.4448	47	104
0861JCN	8.6	.3386	40	90	1141JCN	11.4	.4488	47	104
0871JCN	8.7	.3425	40	90	1151JCN	11.5	.4527	47	104
0881JCN	8.8	.3465	40	90	1161JCN	11.6	.4566	47	104
0891JCN	8.9	.3504	40	90	1171JCN	11.7	.4606	47	104
0901JCN	9.0	.3543	40	90	1181JCN	11.8	.4645	47	104
0911JCN	9.1	.3583	40	90	1191JCN	11.9	.4685	51	108
0921JCN	9.2	.3622	40	90	1201JCN	12.0	.4724	51	108
0931JCN	9.3	.3661	40	90	1211JCN	12.1	.4764	51	108
0941JCN	9.4	.3701	40	90	1221JCN	12.2	.4803	51	108
0951JCN	9.5	.3740	40	90	1231JCN	12.3	.4843	51	108
0961JCN	9.6	.3780	43	93	1241JCN	12.4	.4882	51	108
0971JCN	9.7	.3819	43	93	1251JCN	12.5	.4921	51	108
0981JCN	9.8	.3858	43	93	1261JCN	12.6	.4961	51	108
0991JCN	9.9	.3898	43	93	1271JCN	12.7	.5000	51	108
1001JCN	10.0	.3937	43	93	1281JCN	12.8	.5039	51	108
1011JCN	10.1	.3976	43	100	1291JCN	12.9	.5079	51	108
1021JCN	10.2	.4016	43	100	1301JCN	13.0	.5118	51	108
1031JCN	10.3	.4055	43	100					

* Individually packaged ◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~								
◎				◎		○	○			○	




DJ544 SERIES

HSS-EX, HPD-SUS DRILLS

JOBBER

Application: Designed for drilling in stainless steels, mild steels, aluminum, aluminum alloy, aluminum die cast, copper, copper alloy, etc. Advantage: High helix-sharp cutting edges to avoid built-up and to be suitable for high performance drilling. Wide flute and stub length-increasing chip removal and reducing vibration and deflection. High vanadium HSS-EX material with superior TiN coating - higher speed and feed, longer service life. High quality-good surface finishes, high productivity.



D1=D2

Table with 8 columns: EDP No., Diameter (Metric, Inch), Flute Length (L1, L2), Overall Length. Lists 44 drill bit models from 0201KCN to 0441KCN.

* Individually packaged

▶ NEXT PAGE

◎ : Excellent ○ : Good

Material compatibility table with columns P, H, M, K, N, S and rows for Carbon Steels, Alloy Steels, Prehardened Steels, Hardened Steels, Stainless Steels, Cast Iron, Aluminum, Copper, Bronze, CFRP, Titanium.




DJ544 SERIES

HSS-EX, HPD-SUS DRILLS

JOBBER

Application: Designed for drilling in stainless steels, mild steels, aluminum, aluminum alloy, aluminum die cast, copper, copper alloy, etc. Advantage: High helix-sharp cutting edges to avoid built-up and to be suitable for high performance drilling. Wide flute and stub length-increasing chip removal and reducing vibration and deflection. High vanadium HSS-EX material with superior TiN coating - higher speed and feed, longer service life. High quality-good surface finishes, high productivity.



D1=D2

Table with 8 columns: EDP No., Diameter (Metric, Inch), Flute Length (L1, L2), Overall Length. Lists 44 drill bit models from 0701KCN to 1191KCN.

* Individually packaged

▶ NEXT PAGE

◎ : Excellent ○ : Good

Material compatibility table with columns P, H, M, K, N, S and rows for Carbon Steels, Alloy Steels, Prehardened Steels, Hardened Steels, Stainless Steels, Cast Iron, Aluminum, Copper, Bronze, CFRP, Titanium.




DJ544 SERIES

HSS-EX, HPD-SUS DRILLS

JOBBER

- ▶ **Application** : Designed for drilling in stainless steels, mild steels, aluminum, aluminum alloy, aluminum die cast, copper, copper alloy, etc.
- ▶ **Advantage** : High helix-sharp cutting edges to avoid built-up and to be suitable for high performance drilling
Wide flute and stub length-increasing chip removal and reducing vibration and deflection.
High vanadium HSS-EX material with superior TiN coating - higher speed and feed, longer service life
High quality-good surface finishes, high productivity.



D₁=D₂

EDP No.	Diameter		Flute Length L ₁	Overall Length L ₂	EDP No.	Diameter		Flute Length L ₁	Overall Length L ₂
	Metric D ₁ = D ₂	Inch				Metric D ₁ = D ₂	Inch		
1201KCN	12.0	.4724	101	158	1501KCN	15.0	.5905	109	169
1211KCN	12.1	.4764	101	158	1551KCN	15.5	.6102	112	172
1221KCN	12.2	.4803	101	158	1561KCN	15.6	.6141	112	172
1231KCN	12.3	.4843	101	158	1601KCN	16.0	.6299	112	172
1241KCN	12.4	.4882	101	158	1651KCN	16.5	.6495	115	181
1251KCN	12.5	.4921	101	158	1701KCN	17.0	.6692	115	181
1261KCN	12.6	.4961	101	158	1751KCN	17.5	.6889	118	184
1271KCN	12.7	.5000	101	158	1761KCN	17.6	.6929	118	184
1281KCN	12.8	.5039	101	158	1801KCN	18.0	.7087	118	184
1291KCN	12.9	.5079	101	158	1851KCN	18.5	.7283	122	188
1301KCN	13.0	.5118	101	158	1901KCN	19.0	.7480	122	188
1351KCN	13.5	.5314	106	166	1951KCN	19.5	.7676	125	191
1401KCN	14.0	.5512	106	166	1961KCN	19.6	.7716	125	191
1411KCN	14.1	.5551	109	169	2001KCN	20.0	.7874	125	191
1451KCN	14.5	.5708	109	169					

* Individually packaged

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~								
◎				◎		○	○			○	



RECOMMENDED CUTTING CONDITIONS

HSS-EX, HPD-SUS DRILLS

DJ543, DJ544 SERIES

Please decrease the feed rate 15% in JOBBERS SERIES.
Please decrease the feed and speed 20% for cast surface.


WORK MATERIAL	P		M				N			
	MILD STEELS, LOW CARBON STEELS		STAINLESS STEELS (SUS304, 200)		STAINLESS STEELS (SUS420, 440)		ALUMINUM & ALUMINUM ALLOY		PLASTICS, COPPER, COPPER ALLOYS	
DIAMETER	N	S	N	S	N	S	N	S	N	S
2.0	6300	0.003	2600	0.003	3100	0.003	11000	0.004	5600	0.002
3.0	4200	0.005	1800	0.003	2100	0.003	7350	0.005	3750	0.003
4.0	3200	0.006	1300	0.004	1600	0.004	7050	0.007	2800	0.004
5.0	2500	0.006	1050	0.006	1250	0.006	5500	0.009	2250	0.005
6.0	2100	0.007	900	0.007	1050	0.007	4600	0.010	1850	0.006
8.0	1550	0.009	650	0.009	800	0.009	3500	0.013	1350	0.008
10.0	1250	0.010	550	0.010	630	0.012	2800	0.016	1100	0.010
12.0	1050	0.013	450	0.013	530	0.014	2300	0.020	950	0.012
14.0	900	0.014	400	0.014	450	0.017	2050	0.022	800	0.013
16.0	790	0.016	350	0.016	390	0.019	1750	0.024	700	0.014
18.0	700	0.018	300	0.017	350	0.020	1600	0.028	620	0.016
20.0	620	0.019	260	0.018	320	0.021	1450	0.030	560	0.016

N = R.P.M
S = Inch per Revolution (inch/rev.)




Being the best through innovation

HSS



Global Cutting Tool Leader **YG-1**



GOLD-P DRILLS












GOLD-P COATING

- Competitive price and same performance as full TiN coating

SELECTION GUIDE

HSS GOLD-P DRILLS

GOLD-P DRILLS (GOLD-P COATED)
 - Competitive price and same performance as full TiN coating

ITEM	MODEL	DESCRIPTION	JOBBER	SIZE		PAGE
				MIN	MAX	
INCH						
D1GP182 D8182		HSS, STRAIGHT SHANK, GOLD-P COATED / Fractional sizes	JOBBER	D3/64	D3/4	198
D1GP139		HSS, STRAIGHT SHANK, GOLD-P COATED / Letter sizes	JOBBER	A	Z	199
D1GP138		HSS, STRAIGHT SHANK, GOLD-P COATED / Wire gauge sizes	JOBBER	#56	#1	200
D2GP185		HSSCo8, STRAIGHT SHANK, GOLD-P COATED / Fractional sizes	JOBBER	D3/64	D1/2	201
D2GP186		HSSCo8, STRAIGHT SHANK, GOLD-P COATED / Letter sizes	JOBBER	A	Z	202
D2GP187		HSSCo8, STRAIGHT SHANK, GOLD-P COATED / Wire gauge sizes	JOBBER	#56	#1	203
DLGP511		HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE, GOLD-P COATED / Fractional sizes	JOBBER	D5/64	D1/2	204
DLGP513		HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE, GOLD-P COATED / Letter sizes	JOBBER	A	Z	205
DLGP512		HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE, GOLD-P COATED / Wire gauge sizes	JOBBER	#47	#1	206
METRIC						
DLGP195		HSSCo5, STRAIGHT SHANK DRILLS, GOLD-P COATED	JOBBER	D1.0	D13.0	207
DLGP506		HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE, GOLD-P COATED	JOBBER	D2.0	D13.0	209
RECOMMENDED CUTTING CONDITIONS						212

◎ : Excellent ○ : Good


P			H	M	K	N				S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~							
◎	◎				○		○				○
◎	◎				○		○				○
◎	◎				○		○				○
◎	◎				○		○				○
◎	◎				○		○				○
◎	◎					○					
◎	◎					○					
◎	◎					○					
◎	◎					○					



D1GP182 SERIES
D8182 SERIES

HSS, STRAIGHT SHANK, GOLD-P COATED JOBBER

- ▶ **Flute Geometry** : Right hand helix, wider flutes
- ▶ **Point Angle** : 135°
under 1/16 : Normal point
1/16 & over : Split point
- ▶ **Surface treatment** : Bright body TiN coating on working part
over TiN coating on flute length
- ▶ **Application** : Drilling in steel, cast steel alloyed and Non-alloyed, grey cast iron, graphite, malleable cast iron



▶ **Fractional sizes**

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Fractional	Decimal				Fractional	Decimal		
	D1					D1			
* D1GP113003	3/64	.0469	3/4	1-3/4	** D1GP182025	25/64	.3906	3-3/4	5-1/8
* D1GP182004	1/16	.0625	7/8	1-7/8	** D1GP182026	13/32	.4063	3-7/8	5-1/4
* D1GP182005	5/64	.0781	1	2	** D1GP182027	27/64	.4219	3-15/16	5-3/8
* D1GP182006	3/32	.0938	1-1/4	2-1/4	** D1GP182028	7/16	.4375	4-1/16	5-1/2
* D1GP182007	7/64	.1094	1-1/2	2-5/8	** D1GP182029	29/64	.4531	4-3/16	5-5/8
* D1GP182008	1/8	.1250	1-5/8	2-3/4	** D1GP182030	15/32	.4688	4-5/16	5-3/4
* D1GP182009	9/64	.1406	1-3/4	2-7/8	** D1GP182031	31/64	.4844	4-3/8	5-7/8
* D1GP182010	5/32	.1563	2	3-1/8	** D1GP182032	1/2	.5000	4-1/2	6
* D1GP182011	11/64	.1719	2-1/8	3-1/4	** D8182033	33/64	.5156	4-13/16	6-5/8
* D1GP182012	3/16	.1875	2-5/16	3-1/2	** D8182034	17/32	.5312	4-13/16	6-5/8
* D1GP182013	13/64	.2031	2-7/16	3-5/8	** D8182035	35/64	.5469	4-13/16	6-5/8
* D1GP182014	7/32	.2188	2-1/2	3-3/4	** D8182036	9/16	.5625	4-13/16	6-5/8
* D1GP182015	15/64	.2344	2-5/8	3-7/8	** D8182037	37/64	.5781	4-13/16	6-5/8
* D1GP182016	1/4	.2500	2-3/4	4	** D8182038	19/32	.5937	5-3/16	7-1/8
* D1GP182017	17/64	.2656	2-7/8	4-1/8	** D8182039	39/64	.6094	5-3/16	7-1/8
* D1GP182018	9/32	.2813	2-15/16	4-1/4	** D8182040	5/8	.6250	5-3/16	7-1/8
* D1GP182019	19/64	.2969	3-1/16	4-3/8	** D8182042	21/32	.6563	5-3/16	7-1/8
* D1GP182020	5/16	.3125	3-3/16	4-1/2	** D8182044	11/16	.6875	5-5/8	7-5/8
** D1GP182021	21/64	.3281	3-5/16	4-5/8	** D8182045	45/64	.7031	5-5/8	9-1/2
** D1GP182022	11/32	.3438	3-7/16	4-3/4	** D8182046	23/32	.7188	5-5/8	9-1/2
** D1GP182023	23/64	.3594	3-1/2	4-7/8	** D8182047	47/64	.7344	5-5/8	9-3/4
** D1GP182024	3/8	.3750	3-5/8	5	** D8182048	3/4	.7500	5-7/8	9-3/4

* 10pcs per package
** 5pcs per package
** 3pcs per package

Tolerance Diameter (Inch)	
up to 1/8(.1250)	0 ~ -.0005
over 1/8(.1250) up to 1/4(.2500)	0 ~ -.0007
over 1/4(.2500) up to 1/2(.5000)	0 ~ -.0010

◎ : Excellent ○ : Good


P		H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	◎				○						○



D1GP139 SERIES

HSS, STRAIGHT SHANK, GOLD-P COATED JOBBER

- ▶ **Flute Geometry** : Right hand helix, wider flutes
- ▶ **Point Angle** : 135°:Split point
- ▶ **Surface treatment** : Bright body TiN coating on working part
- ▶ **Application** : Drilling in steel, cast steel alloyed and Non-alloyed, grey cast iron, graphite, malleable cast iron



▶ **Letter sizes**

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Letter	Decimal				Letter	Decimal		
	D1					D1			
* D1GP139101	A	.2340	2-5/8	3-7/8	* D1GP139114	N	.3020	3-1/16	4-3/8
* D1GP139102	B	.2380	2-3/4	4	* D1GP139115	O	.3160	3-3/16	4-1/2
* D1GP139103	C	.2420	2-3/4	4	* D1GP139116	P	.3230	3-5/16	4-5/8
* D1GP139104	D	.2460	2-3/4	4	** D1GP139117	Q	.3320	3-7/16	4-3/4
* D1GP139105	E	.2500	2-3/4	4	** D1GP139118	R	.3390	3-7/16	4-3/4
* D1GP139106	F	.2570	2-7/8	4-1/8	** D1GP139119	S	.3480	3-1/2	4-7/8
* D1GP139107	G	.2610	2-7/8	4-1/8	** D1GP139120	T	.3580	3-1/2	4-7/8
* D1GP139108	H	.2660	2-7/8	4-1/8	** D1GP139121	U	.3680	3-5/8	5
* D1GP139109	I	.2720	2-7/8	4-1/8	** D1GP139122	V	.3770	3-5/8	5
* D1GP139110	J	.2770	2-7/8	4-1/8	** D1GP139123	W	.3860	3-3/4	5-1/8
* D1GP139111	K	.2810	2-15/16	4-1/4	** D1GP139124	X	.3970	3-3/4	5-1/8
* D1GP139112	L	.2900	2-15/16	4-1/4	** D1GP139125	Y	.4040	3-7/8	5-1/4
* D1GP139113	M	.2950	3-1/16	4-3/8	** D1GP139126	Z	.4130	3-7/8	5-1/4

* 10pcs per package
** 5pcs per package

Tolerance Diameter (Inch)	
up to 1/8(.1250)	0 ~ -.0005
over 1/8(.1250) up to 1/4(.2500)	0 ~ -.0007
over 1/4(.2500) up to 1/2(.5000)	0 ~ -.0010

◎ : Excellent ○ : Good


P		H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	◎				○						○



D1GP138 SERIES

HSS, STRAIGHT SHANK, GOLD-P COATED JOBBER

- Flute Geometry: Right hand helix, wider flutes
Point Angle: 135°, Split point
Surface treatment: Bright body TiN coating on working part
Application: Drilling in steel, cast steel alloyed and Non-alloyed, grey cast iron, graphite, malleable cast iron



Wire gauge sizes

Table with 8 columns: EDP No., Diameter (Wire gauge, Decimal, D1), Flute Length (L1), Overall Length (L2), EDP No., Diameter (Wire gauge, Decimal, D1), Flute Length (L1), Overall Length (L2). Lists various drill bit specifications.

Tolerance: See page 198 * 10pcs per package


Material compatibility table with columns P, H, M, K, N, S and rows for Carbon Steels, Alloy Steels, Prehardened Steels, Hardened Steels, Stainless Steels, Cast Iron, Aluminum, Copper, Bronze, CFRP, Titanium.



D2GP185 SERIES

HSSCo8, STRAIGHT SHANK, GOLD-P COATED JOBBER

- Flute Geometry: Right hand helix, wider flutes
Point Angle: 135°
Surface treatment: Bright body TiN coating on working part
Application: Drilling in steel, cast steel alloyed and Non-alloyed, grey cast iron, graphite, malleable cast iron



Fractional sizes

Table with 8 columns: EDP No., Diameter (Fractional, Decimal, D1), Flute Length (L1), Overall Length (L2), EDP No., Diameter (Fractional, Decimal, D1), Flute Length (L1), Overall Length (L2). Lists various drill bit specifications.

Tolerance table for Diameter (Inch) with ranges: up to 1/8(.1250), over 1/8(.1250) up to 1/4(.2500), over 1/4(.2500) up to 1/2(.5000).

* 10pcs per package
** 5pcs per package


Material compatibility table with columns P, H, M, K, N, S and rows for Carbon Steels, Alloy Steels, Prehardened Steels, Hardened Steels, Stainless Steels, Cast Iron, Aluminum, Copper, Bronze, CFRP, Titanium.



D2GP186 SERIES

HSSCo8, STRAIGHT SHANK, GOLD-P COATED JOBBER

- ▶ **Flute Geometry** : Right hand helix, wider flutes
- ▶ **Point Angle** : 135° : Split point
- ▶ **Surface treatment** : Bright body TiN coating on working part
- ▶ **Application** : Drilling in steel, cast steel alloyed and Non-alloyed, grey cast iron, graphite, malleable cast iron



▶ Letter sizes

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Letter	Decimal				Letter	Decimal		
	D1					D1			
* D2GP186101	A	.2340	2-5/8	3-7/8	* D2GP186114	N	.3020	3-1/16	4-3/8
* D2GP186102	B	.2380	2-3/4	4	* D2GP186115	O	.3160	3-3/16	4-1/2
* D2GP186103	C	.2420	2-3/4	4	* D2GP186116	P	.3230	3-5/16	4-5/8
* D2GP186104	D	.2460	2-3/4	4	** D2GP186117	Q	.3320	3-7/16	4-3/4
* D2GP185105	E	.2500	2-3/4	4	** D2GP186118	R	.3390	3-7/16	4-3/4
* D2GP186106	F	.2570	2-7/8	4-1/8	** D2GP186119	S	.3480	3-1/2	4-7/8
* D2GP186107	G	.2610	2-7/8	4-1/8	** D2GP186120	T	.3580	3-1/2	4-7/8
* D2GP186108	H	.2660	2-7/8	4-1/8	** D2GP186121	U	.3680	3-5/8	5
* D2GP186109	I	.2720	2-7/8	4-1/8	** D2GP186122	V	.3770	3-5/8	5
* D2GP186110	J	.2770	2-7/8	4-1/8	** D2GP186123	W	.3860	3-3/4	5-1/8
* D2GP186111	K	.2810	2-15/16	4-1/4	** D2GP186124	X	.3970	3-3/4	5-1/8
* D2GP186112	L	.2900	2-15/16	4-1/4	** D2GP186125	Y	.4040	3-7/8	5-1/4
* D2GP186113	M	.2950	3-1/16	4-3/8	** D2GP186126	Z	.4130	3-7/8	5-1/4

Tolerance Diameter (Inch)	
up to 1/8(.1250)	0 ~ -.0005
over 1/8(.1250) up to 1/4(.2500)	0 ~ -.0007
over 1/4(.2500) up to 1/2(.5000)	0 ~ -.0010

* 10pcs per package
** 5pcs per package

◎ : Excellent ○ : Good


P		H	M	K	N				S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~							
◎	◎			○		○				○



D2GP187 SERIES

HSSCo8, STRAIGHT SHANK, GOLD-P COATED JOBBER

- ▶ **Flute Geometry** : Right hand helix, wider flutes
- ▶ **Point Angle** : 135° : Split point
- Wire gauge size #53~#56 : Normal point
- Wire gauge size #1~#52 : Split point
- ▶ **Surface treatment** : Bright body TiN coating on working part
- ▶ **Application** : Drilling in steel, cast steel alloyed and Non-alloyed, grey cast iron, graphite, malleable cast iron



▶ Wire gauge sizes

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Wire gauge	Decimal				Wire gauge	Decimal		
	D1					D1			
* D2GP187256	1	.2280	2-5/8	3-7/8	* D2GP187228	29	.1360	1-3/4	2-7/8
* D2GP187255	2	.2210	2-5/8	3-7/8	* D2GP187227	30	.1285	1-5/8	2-3/4
* D2GP187254	3	.2130	2-1/2	3-3/4	* D2GP187226	31	.1200	1-5/8	2-3/4
* D2GP187253	4	.2090	2-1/2	3-3/4	* D2GP187225	32	.1160	1-5/8	2-3/4
* D2GP187252	5	.2055	2-1/2	3-3/4	* D2GP187224	33	.1130	1-1/2	2-5/8
* D2GP187251	6	.2040	2-1/2	3-3/4	* D2GP187223	34	.1110	1-1/2	2-5/8
* D2GP187250	7	.2010	2-7/16	3-5/8	* D2GP187222	35	.1100	1-1/2	2-5/8
* D2GP187249	8	.1990	2-7/16	3-5/8	* D2GP187221	36	.1065	1-7/16	2-1/2
* D2GP187248	9	.1960	2-7/16	3-5/8	* D2GP187220	37	.1040	1-7/16	2-1/2
* D2GP187247	10	.1935	2-7/16	3-5/8	* D2GP187219	38	.1015	1-7/16	2-1/2
* D2GP187246	11	.1910	2-5/16	3-1/2	* D2GP187218	39	.0995	1-3/8	2-3/8
* D2GP187245	12	.1890	2-5/16	3-1/2	* D2GP187217	40	.0980	1-3/8	2-3/8
* D2GP187244	13	.1850	2-5/16	3-1/2	* D2GP187216	41	.0960	1-3/8	2-3/8
* D2GP187243	14	.1820	2-3/16	3-3/8	* D2GP187215	42	.0935	1-1/4	2-1/4
* D2GP187242	15	.1800	2-3/16	3-3/8	* D2GP187214	43	.0890	1-1/4	2-1/4
* D2GP187241	16	.1770	2-3/16	3-3/8	* D2GP187213	44	.0860	1-1/8	2-1/8
* D2GP187240	17	.1730	2-3/16	3-3/8	* D2GP187212	45	.0820	1-1/8	2-1/8
* D2GP187239	18	.1695	2-1/8	3-1/4	* D2GP187211	46	.0810	1-1/8	2-1/8
* D2GP187238	19	.1660	2-1/8	3-1/4	* D2GP187210	47	.0785	1	2
* D2GP187237	20	.1610	2-1/8	3-1/4	* D2GP187209	48	.0760	1	2
* D2GP187236	21	.1590	2-1/8	3-1/4	* D2GP187208	49	.0730	1	2
* D2GP187235	22	.1570	2	3-1/8	* D2GP187207	50	.0700	1	2
* D2GP187234	23	.1540	2	3-1/8	* D2GP187206	51	.0670	1	2
* D2GP187233	24	.1520	2	3-1/8	* D2GP187205	52	.0635	7/8	1-7/8
* D2GP187232	25	.1495	1-7/8	3	* D2GP187204	53	.0595	7/8	1-7/8
* D2GP187231	26	.1470	1-7/8	3	* D2GP187203	54	.0550	7/8	1-7/8
* D2GP187230	27	.1440	1-7/8	3	* D2GP187202	55	.0520	7/8	1-7/8
* D2GP187229	28	.1405	1-3/4	2-7/8	* D2GP187201	56	.0465	3/4	1-3/4

▶ Tolerance : See page 198

* 10pcs per package

◎ : Excellent ○ : Good

P		H	M	K	N				S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~							
◎	◎			○		○				○


YG GOLD-P DRILLS

DLGP511 SERIES

HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE, GOLD-P COATED

JOBBER

- **Flute Geometry** : Right hand spiral, 38° helix, parabolic flute.
- **Point Angle** : 130° : Split point
- **Surface treatment** : Bright body TiN coating on working part
- **Application** : Improved chip removal in most materials, especially in deep drilling applications.



► Fractional sizes

Unit : Inch

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Fractional	Decimal				Fractional	Decimal		
	D1					D1			
* DLGP511005	5/64	.0781	1	2	* DLGP511019	19/64	.2969	3-1/16	4-3/8
* DLGP511006	3/32	.0938	1-1/4	2-1/4	* DLGP511020	5/16	.3125	3-3/16	4-1/2
* DLGP511007	7/64	.1094	1-1/2	2-5/8	** DLGP511021	21/64	.3281	3-5/16	4-5/8
* DLGP511008	1/8	.1250	1-5/8	2-3/4	** DLGP511022	11/32	.3438	3-7/16	4-3/4
* DLGP511009	9/64	.1406	1-3/4	2-7/8	** DLGP511023	23/64	.3594	3-1/2	4-7/8
* DLGP511010	5/32	.1563	2	3-1/8	** DLGP511024	3/8	.3750	3-5/8	5
* DLGP511011	11/64	.1719	2-1/8	3-1/4	** DLGP511025	25/64	.3906	3-3/4	5-1/8
* DLGP511012	3/16	.1875	2-5/16	3-1/2	** DLGP511026	13/32	.4063	3-7/8	5-1/4
* DLGP511013	13/64	.2031	2-7/16	3-5/8	** DLGP511027	27/64	.4219	3-15/16	5-3/8
* DLGP511014	7/32	.2188	2-1/2	3-3/4	** DLGP511028	7/16	.4375	4-1/16	5-1/2
* DLGP511015	15/64	.2344	2-5/8	3-7/8	** DLGP511029	29/64	.4531	4-3/16	5-5/8
* DLGP511016	1/4	.2500	2-3/4	4	** DLGP511030	15/32	.4688	4-5/16	5-3/4
* DLGP511017	17/64	.2656	2-7/8	4-1/8	** DLGP511031	31/64	.4844	4-3/8	5-7/8
* DLGP511018	9/32	.2813	2-15/16	4-1/4	** DLGP511032	1/2	.5000	4-1/2	6

* 10pcs per package
** 5pcs per package

Tolerance Diameter (Inch)	
up to 1/8(.1250)	0 ~ -.0005
over 1/8(.1250) up to 1/4(.2500)	0 ~ -.0007
over 1/4(.2500) up to 1/2(.5000)	0 ~ -.0010

◎ : Excellent ○ : Good

P		H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~							
◎	◎				○						

YG GOLD-P DRILLS

DLGP513 SERIES

HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE, GOLD-P COATED

JOBBER

- **Flute Geometry** : Right hand spiral, 38° helix, parabolic flute.
- **Point Angle** : 130° : Split point
- **Surface treatment** : Bright body TiN coating on working part
- **Application** : Improved chip removal in most materials, especially in deep drilling applications.



► Letter sizes

Unit : Inch

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Letter	Decimal				Letter	Decimal		
	D1					D1			
* DLGP513101	A	.2340	2-5/8	3-7/8	* DLGP513114	N	.3020	3-1/16	4-3/8
* DLGP513102	B	.2380	2-3/4	4	* DLGP513115	O	.3160	3-3/16	4-1/2
* DLGP513103	C	.2420	2-3/4	4	* DLGP513116	P	.3230	3-5/16	4-5/8
* DLGP513104	D	.2460	2-3/4	4	** DLGP513117	Q	.3320	3-7/16	4-3/4
* DLGP513105	E	.2500	2-3/4	4	** DLGP513118	R	.3390	3-7/16	4-3/4
* DLGP513106	F	.2570	2-7/8	4-1/8	** DLGP513119	S	.3480	3-1/2	4-7/8
* DLGP513107	G	.2610	2-7/8	4-1/8	** DLGP513120	T	.3580	3-1/2	4-7/8
* DLGP513108	H	.2660	2-7/8	4-1/8	** DLGP513121	U	.3680	3-5/8	5
* DLGP513109	I	.2720	2-7/8	4-1/8	** DLGP513122	V	.3770	3-5/8	5
* DLGP513110	J	.2770	2-7/8	4-1/8	** DLGP513123	W	.3860	3-3/4	5-1/8
* DLGP513111	K	.2810	2-15/16	4-1/4	** DLGP513124	X	.3970	3-3/4	5-1/8
* DLGP513112	L	.2900	2-15/16	4-1/4	** DLGP513125	Y	.4040	3-7/8	5-1/4
* DLGP513113	M	.2950	3-1/16	4-3/8	** DLGP513126	Z	.4130	3-7/8	5-1/4

* 10pcs per package
** 5pcs per package

Tolerance Diameter (Inch)	
up to 1/8(.1250)	0 ~ -.0005
over 1/8(.1250) up to 1/4(.2500)	0 ~ -.0007
over 1/4(.2500) up to 1/2(.5000)	0 ~ -.0010

◎ : Excellent ○ : Good

P		H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRc45~55	HRc55~							
◎	◎				○						


YG GOLD-P DRILLS

DLGP512 SERIES

HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE, GOLD-P COATED

JOBBER

- ▶ **Flute Geometry** : Right hand spiral, 38° helix, parabolic flute.
- ▶ **Point Angle** : 130° : Split point
- ▶ **Surface treatment** : Bright body TiN coating on working part
- ▶ **Application** : Improved chip removal in most materials, especially in deep drilling applications.



▶ Wire gauge sizes

Unit : Inch

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Wire gauge	Decimal				Wire gauge	Decimal		
	D1					D1			
* DLGP512247	1	.2280	2-5/8	3-7/8	* DLGP512223	25	.1495	1-7/8	3
* DLGP512246	2	.2210	2-5/8	3-7/8	* DLGP512222	26	.1470	1-7/8	3
* DLGP512245	3	.2130	2-1/2	3-3/4	* DLGP512221	27	.1440	1-7/8	3
* DLGP512244	4	.2090	2-1/2	3-3/4	* DLGP512220	28	.1405	1-3/4	2-7/8
* DLGP512243	5	.2055	2-1/2	3-3/4	* DLGP512219	29	.1360	1-3/4	2-7/8
* DLGP512242	6	.2040	2-1/2	3-3/4	* DLGP512218	30	.1285	1-5/8	2-3/4
* DLGP512241	7	.2010	2-7/16	3-5/8	* DLGP512217	31	.1200	1-5/8	2-3/4
* DLGP512240	8	.1990	2-7/16	3-5/8	* DLGP512216	32	.1160	1-5/8	2-3/4
* DLGP512239	9	.1960	2-7/16	3-5/8	* DLGP512215	33	.1130	1-1/2	2-5/8
* DLGP512238	10	.1935	2-7/16	3-5/8	* DLGP512214	34	.1110	1-1/2	2-5/8
* DLGP512237	11	.1910	2-5/16	3-1/2	* DLGP512213	35	.1100	1-1/2	2-5/8
* DLGP512236	12	.1890	2-5/16	3-1/2	* DLGP512212	36	.1065	1-7/16	2-1/2
* DLGP512235	13	.1850	2-5/16	3-1/2	* DLGP512211	37	.1040	1-7/16	2-1/2
* DLGP512234	14	.1820	2-3/16	3-3/8	* DLGP512210	38	.1015	1-7/16	2-1/2
* DLGP512233	15	.1800	2-3/16	3-3/8	* DLGP512209	39	.0995	1-3/8	2-3/8
* DLGP512232	16	.1770	2-3/16	3-3/8	* DLGP512208	40	.0980	1-3/8	2-3/8
* DLGP512231	17	.1730	2-3/16	3-3/8	* DLGP512207	41	.0960	1-3/8	2-3/8
* DLGP512230	18	.1695	2-1/8	3-1/4	* DLGP512206	42	.0935	1-1/4	2-1/4
* DLGP512229	19	.1660	2-1/8	3-1/4	* DLGP512205	43	.0890	1-1/4	2-1/4
* DLGP512228	20	.1610	2-1/8	3-1/4	* DLGP512204	44	.0860	1-1/8	2-1/8
* DLGP512227	21	.1590	2-1/8	3-1/4	* DLGP512203	45	.0820	1-1/8	2-1/8
* DLGP512226	22	.1570	2	3-1/8	* DLGP512202	46	.0810	1-1/8	2-1/8
* DLGP512225	23	.1540	2	3-1/8	* DLGP512201	47	.0785	1	2
* DLGP512224	24	.1520	2	3-1/8					

▶ Tolerance : See page 198

* 10pcs per package

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~								
◎	◎				○						


YG GOLD-P DRILLS

DLGP195 SERIES

HSSCo5, STRAIGHT SHANK DRILLS, GOLD-P COATED

JOBBER

- ▶ **Flute Geometry** : Right hand helix
- ▶ **Point Angle** : 135°
under 1.6mm : Normal point
1.6mm & over : Split point
- ▶ **Surface treatment** : Bright body, TiN coating on working area
- ▶ **Application** : Drilling to steels, cast steels alloyed and Non-alloyed, grey cast iron, graphite, malleable cast iron



▶ Wire gauge sizes

Unit : mm

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Metric	Inch				Metric	Inch		
	D1					D1			
* DLGP195010	1.0	.0394	12	34	* DLGP195042	4.2	.1654	43	75
* DLGP195011	1.1	.0433	14	36	* DLGP195043	4.3	.1693	47	80
* DLGP195012	1.2	.0472	16	38	* DLGP195044	4.4	.1732	47	80
* DLGP195013	1.3	.0512	16	38	* DLGP195045	4.5	.1772	47	80
* DLGP195014	1.4	.0551	18	40	* DLGP195046	4.6	.1811	47	80
* DLGP195015	1.5	.0591	18	40	* DLGP195047	4.7	.1850	47	80
* DLGP195016	1.6	.0630	20	43	* DLGP195048	4.8	.1890	52	86
* DLGP195017	1.7	.0669	20	43	* DLGP195049	4.9	.1929	52	86
* DLGP195018	1.8	.0709	22	46	* DLGP195050	5.0	.1969	52	86
* DLGP195019	1.9	.0748	22	46	* DLGP195051	5.1	.2008	52	86
* DLGP195020	2.0	.0787	24	49	* DLGP195052	5.2	.2047	52	86
* DLGP195021	2.1	.0827	24	49	* DLGP195053	5.3	.2087	52	86
* DLGP195022	2.2	.0866	27	53	* DLGP195054	5.4	.2126	57	93
* DLGP195023	2.3	.0906	27	53	* DLGP195055	5.5	.2165	57	93
* DLGP195024	2.4	.0945	30	57	* DLGP195056	5.6	.2205	57	93
* DLGP195025	2.5	.0984	30	57	* DLGP195057	5.7	.2244	57	93
* DLGP195026	2.6	.1024	30	57	* DLGP195058	5.8	.2283	57	93
* DLGP195027	2.7	.1063	33	61	* DLGP195059	5.9	.2323	57	93
* DLGP195028	2.8	.1102	33	61	* DLGP195060	6.0	.2362	57	93
* DLGP195029	2.9	.1142	33	61	* DLGP195061	6.1	.2402	63	101
* DLGP195030	3.0	.1181	33	61	* DLGP195062	6.2	.2441	63	101
* DLGP195031	3.1	.1220	36	65	* DLGP195063	6.3	.2480	63	101
* DLGP195032	3.2	.1260	36	65	* DLGP195064	6.4	.2520	63	101
* DLGP195033	3.3	.1299	36	65	* DLGP195065	6.5	.2559	63	101
* DLGP195034	3.4	.1339	39	70	* DLGP195066	6.6	.2598	63	101
* DLGP195035	3.5	.1378	39	70	* DLGP195067	6.7	.2638	63	101
* DLGP195036	3.6	.1417	39	70	* DLGP195068	6.8	.2677	69	109
* DLGP195037	3.7	.1457	39	70	* DLGP195069	6.9	.2717	69	109
* DLGP195038	3.8	.1496	43	75	* DLGP195070	7.0	.2756	69	109
* DLGP195039	3.9	.1535	43	75	* DLGP195071	7.1	.2795	69	109
* DLGP195040	4.0	.1575	43	75	* DLGP195072	7.2	.2835	69	109
* DLGP195041	4.1	.1614	43	75	* DLGP195073	7.3	.2874	69	109

* 10pcs per package

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~								
◎	◎				○						


YG GOLD-P DRILLS

DLGP195 SERIES

HSSCo5, STRAIGHT SHANK DRILLS, GOLD-P COATED

JOBBER

- **Flute Geometry** : Right hand helix
- **Point Angle** : 135°
under 1.6mm : Normal point
1.6mm & over : Split point
- **Surface treatment** : Bright body, TiN coating on working area
- **Application** : Drilling to steels, cast steels alloyed and Non-alloyed, grey cast iron, graphite, malleable cast iron



DIN 338 HSS Co5 33° h8 135° P.212

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Metric	Inch				Metric	Inch		
	D1		D1						
* DLGP195074	7.4	.2913	69	109	** DLGP195103	10.3	.4055	87	133
* DLGP195075	7.5	.2953	69	109	** DLGP195104	10.4	.4094	87	133
* DLGP195076	7.6	.2992	75	117	** DLGP195105	10.5	.4134	87	133
* DLGP195077	7.7	.3031	75	117	** DLGP195106	10.6	.4173	87	133
* DLGP195078	7.8	.3071	75	117	** DLGP195107	10.7	.4212	94	142
* DLGP195079	7.9	.3110	75	117	** DLGP195108	10.8	.4252	94	142
* DLGP195080	8.0	.3150	75	117	** DLGP195109	10.9	.4291	94	142
* DLGP195081	8.1	.3189	75	117	** DLGP195110	11.0	.4330	94	142
* DLGP195082	8.2	.3228	75	117	** DLGP195111	11.1	.4370	94	142
* DLGP195083	8.3	.3268	75	117	** DLGP195112	11.2	.4409	94	142
** DLGP195084	8.4	.3307	75	117	** DLGP195113	11.3	.4448	94	142
** DLGP195085	8.5	.3346	75	117	** DLGP195114	11.4	.4488	94	142
** DLGP195086	8.6	.3386	81	125	** DLGP195115	11.5	.4527	94	142
** DLGP195087	8.7	.3425	81	125	** DLGP195116	11.6	.4566	94	142
** DLGP195088	8.8	.3465	81	125	** DLGP195117	11.7	.4606	94	142
** DLGP195089	8.9	.3504	81	125	** DLGP195118	11.8	.4645	94	142
** DLGP195090	9.0	.3543	81	125	** DLGP195119	11.9	.4685	101	151
** DLGP195091	9.1	.3583	81	125	** DLGP195120	12.0	.4724	101	151
** DLGP195092	9.2	.3622	81	125	** DLGP195121	12.1	.4764	101	151
** DLGP195093	9.3	.3661	81	125	** DLGP195122	12.2	.4803	101	151
** DLGP195094	9.4	.3701	81	125	** DLGP195123	12.3	.4843	101	151
** DLGP195095	9.5	.3740	81	125	** DLGP195124	12.4	.4882	101	151
** DLGP195096	9.6	.3780	87	133	** DLGP195125	12.5	.4921	101	151
** DLGP195097	9.7	.3819	87	133	** DLGP195126	12.6	.4961	101	151
** DLGP195098	9.8	.3858	87	133	** DLGP195127	12.7	.5000	101	151
** DLGP195099	9.9	.3898	87	133	** DLGP195128	12.8	.5039	101	151
** DLGP195100	10.0	.3937	87	133	** DLGP195129	12.9	.5079	101	151
** DLGP195101	10.1	.3976	87	133	** DLGP195130	13.0	.5118	101	151
** DLGP195102	10.2	.4016	87	133					

* 10pcs per package
** 5pcs per package

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRc30~45	HRc45~55 HRc55~								
◎	◎			○		○				○	


YG GOLD-P DRILLS

DLGP506 SERIES

HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE, GOLD-P COATED

JOBBER

- **Flute Geometry** : Right hand, 38° helix, Parabolic flutes
- **Point Angle** : 130°, Split point giving higher chip removal.
- **Surface treatment** : Bright body, TiN coating on working area.
- **Application** : Drilling deep holes in non alloy steels, alloy steels, grey cast iron, malleable cast iron, Special aluminum or magnesium alloys.



DIN 338 HSS Co5 W 38° h8 130° P.213

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Metric	Inch				Metric	Inch		
	D1		D1						
* DLGP506020	2.0	.0787	24	49	* DLGP506048	4.8	.1890	52	86
* DLGP506021	2.1	.0827	24	49	* DLGP506049	4.9	.1929	52	86
* DLGP506022	2.2	.0866	27	53	* DLGP506050	5.0	.1969	52	86
* DLGP506023	2.3	.0906	27	53	* DLGP506051	5.1	.2008	52	86
* DLGP506024	2.4	.0945	30	57	* DLGP506052	5.2	.2047	52	86
* DLGP506025	2.5	.0984	30	57	* DLGP506053	5.3	.2087	52	86
* DLGP506026	2.6	.1024	30	57	* DLGP506054	5.4	.2126	57	93
* DLGP506027	2.7	.1063	33	61	* DLGP506055	5.5	.2165	57	93
* DLGP506028	2.8	.1102	33	61	* DLGP506056	5.6	.2205	57	93
* DLGP506029	2.9	.1142	33	61	* DLGP506057	5.7	.2244	57	93
* DLGP506030	3.0	.1181	33	61	* DLGP506058	5.8	.2283	57	93
* DLGP506031	3.1	.1220	36	65	* DLGP506059	5.9	.2323	57	93
* DLGP506032	3.2	.1260	36	65	* DLGP506060	6.0	.2362	57	93
* DLGP506033	3.3	.1299	36	65	* DLGP506061	6.1	.2402	63	101
* DLGP506034	3.4	.1339	39	70	* DLGP506062	6.2	.2441	63	101
* DLGP506035	3.5	.1378	39	70	* DLGP506063	6.3	.2480	63	101
* DLGP506036	3.6	.1417	39	70	* DLGP506064	6.4	.2520	63	101
* DLGP506037	3.7	.1457	39	70	* DLGP506065	6.5	.2559	63	101
* DLGP506038	3.8	.1496	43	75	* DLGP506066	6.6	.2598	63	101
* DLGP506039	3.9	.1535	43	75	* DLGP506067	6.7	.2638	63	101
* DLGP506040	4.0	.1575	43	75	* DLGP506068	6.8	.2677	69	109
* DLGP506041	4.1	.1614	43	75	* DLGP506069	6.9	.2717	69	109
* DLGP506042	4.2	.1654	43	75	* DLGP506070	7.0	.2756	69	109
* DLGP506043	4.3	.1693	47	80	* DLGP506071	7.1	.2795	69	109
* DLGP506044	4.4	.1732	47	80	* DLGP506072	7.2	.2835	69	109
* DLGP506045	4.5	.1772	47	80	* DLGP506073	7.3	.2874	69	109
* DLGP506046	4.6	.1811	47	80	* DLGP506074	7.4	.2913	69	109
* DLGP506047	4.7	.1850	47	80	* DLGP506075	7.5	.2953	69	109

* 10pcs per package

► NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRc30~45	HRc45~55 HRc55~								
◎	◎			○		○				○	

YG GOLD-P DRILLS

DLGP506 SERIES

HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE, GOLD-P COATED

JOBBER

- **Flute Geometry** : Right hand, 38° helix, Parabolic flutes
- **Point Angle** : 130°, Split point giving higher chip removal.
- **Surface treatment** : Bright body, TiN coating on working area.
- **Application** : Drilling deep holes in non alloy steels, alloy steels, grey cast iron, malleable cast iron, Special aluminum or magnesium alloys.



EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Metric	Inch				Metric	Inch		
	D1		D1						
* DLGP506076	7.6	.2992	75	117	** DLGP506104	10.4	.4094	87	133
* DLGP506077	7.7	.3031	75	117	** DLGP506105	10.5	.4134	87	133
* DLGP506078	7.8	.3071	75	117	** DLGP506106	10.6	.4173	87	133
* DLGP506079	7.9	.3110	75	117	** DLGP506107	10.7	.4212	94	142
* DLGP506080	8.0	.3150	75	117	** DLGP506108	10.8	.4252	94	142
* DLGP506081	8.1	.3189	75	117	** DLGP506109	10.9	.4291	94	142
* DLGP506082	8.2	.3228	75	117	** DLGP506110	11.0	.4330	94	142
* DLGP506083	8.3	.3268	75	117	** DLGP506111	11.1	.4370	94	142
** DLGP506084	8.4	.3307	75	117	** DLGP506112	11.2	.4409	94	142
** DLGP506085	8.5	.3346	75	117	** DLGP506113	11.3	.4448	94	142
** DLGP506086	8.6	.3386	81	125	** DLGP506114	11.4	.4488	94	142
** DLGP506087	8.7	.3425	81	125	** DLGP506115	11.5	.4527	94	142
** DLGP506088	8.8	.3465	81	125	** DLGP506116	11.6	.4566	94	142
** DLGP506089	8.9	.3504	81	125	** DLGP506117	11.7	.4606	94	142
** DLGP506090	9.0	.3543	81	125	** DLGP506118	11.8	.4645	94	142
** DLGP506091	9.1	.3583	81	125	** DLGP506119	11.9	.4685	101	151
** DLGP506092	9.2	.3622	81	125	** DLGP506120	12.0	.4724	101	151
** DLGP506093	9.3	.3661	81	125	** DLGP506121	12.1	.4764	101	151
** DLGP506094	9.4	.3701	81	125	** DLGP506122	12.2	.4803	101	151
** DLGP506095	9.5	.3740	81	125	** DLGP506123	12.3	.4843	101	151
** DLGP506096	9.6	.3780	87	133	** DLGP506124	12.4	.4882	101	151
** DLGP506097	9.7	.3819	87	133	** DLGP506125	12.5	.4921	101	151
** DLGP506098	9.8	.3858	87	133	** DLGP506126	12.6	.4921	101	151
** DLGP506099	9.9	.3898	87	133	** DLGP506127	12.7	.5000	101	151
** DLGP506100	10.0	.3937	87	133	** DLGP506128	12.8	.5039	101	151
** DLGP506101	10.1	.3976	87	133	** DLGP506129	12.9	.5079	101	151
** DLGP506102	10.2	.4016	87	133	** DLGP506130	13.0	.5118	101	151
** DLGP506103	10.3	.4055	87	133					

* 10pcs per package
** 5pcs per package

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
-HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎					○					

YG GOLD-P DRILLS

GOLD-P COATED DRILL SETS



EDP No.	Series No.	Description	SIZE	Q'TY
D1GP138 SET	D1GP SET924	HSS Straight Shank, Split Point (#53 ~#56 : NORMAL point)	# 1~#56(Wire gauge)	56 pcs
D1GP139 SET	D1GP SET925	HSS Straight Shank, Split Point	A~Z(Letter)	26 pcs
D1GP182 SET	D1GP SET926	HSS Straight Shank, Split Point	Ø1/16~Ø1/2(Fractional)	29 pcs
D2GP185 SET	D2GP SET927	HSSCo8 Straight Shank, Split Point	Ø1/16~Ø1/2(Fractional)	29 pcs
D2GP186 SET	D2GP SET928	HSSCo8 Straight Shank, Split Point	A~Z(Letter)	26 pcs
D2GP187 SET	D2GP SET930	HSSCo8 Straight Shank, Split Point (#53 ~#56 : NORMAL point)	# 1~#56(Wire gauge)	56 pcs
DLGP511 SET	DLGP SET931	HSSCo5 Straight Shank, Split Point	Ø5/64~Ø1/2(Fractional)	28 pcs
DLGP512 SET	DLGP SET932	HSSCo5 Straight Shank, Split Point	# 1~#47(Wire gauge)	47 pcs
DLGP513 SET	DLGP SET933	HSSCo5 Straight Shank, Split Point	A~Z(Letter)	26 pcs



RECOMMENDED CUTTING CONDITIONS

HSS, HSSCo5 & HSSCo8 STRAIGHT SHANK, GOLD-P COATED

D1GP182, D1GP139, D1GP138, D2GP185, D2GP186, D2GP187, DLGP195, SERIES

WORK MATERIAL			P				M			
			CARBON STEELS		CARBON STEELS		ALLOY STEELS		STAINLESS STEELS	
HARDNESS					~ HRC23		HRC23 ~ 34		~ HRC23	
STRENGTH			~ 570N/mm ²		~ 830N/mm ²		830~1110N/mm ²		~ 830N/mm ²	
DIAMETER			N	S	N	S	N	S	N	S
Fractional	Decimal	Metric								
3/64	.0469	1.0	14000	.0008	12500	.0008	7700	.0008	7000	.0008
#47	.0785	2.0	7000	.0023	6100	.0024	3850	.0024	3500	.0024
#32	.1160	3.0	4650	.0038	4100	.0031	2550	.0031	2350	.0031
#22	.1570	4.0	3500	.0044	3050	.0043	1950	.0039	1750	.0039
#9	.1960	5.0	2800	.0049	2450	.0043	1550	.0039	1400	.0039
B	.2380	6.0	2350	.0056	2050	.0051	1300	.0047	1150	.0047
J	.2770	7.0	2000	.0064	1750	.0059	1100	.0055	1000	.0055
O	.3160	8.0	1750	.0072	1550	.0071	960	.0059	875	.0059
T	.3580	9.0	1550	.0077	1350	.0087	855	.0071	780	.0071
X	.3970	10.0	1400	.0084	1250	.0087	770	.0071	700	.0071
7/16	.4375	11.0	1250	.0087	1100	.0087	700	.0071	650	.0071
15/32	.4688	12.0	1150	.0090	1000	.0087	650	.0079	585	.0079
1/2	.5000	13.0	1050	.0090	950	.0087	595	.0079	540	.0079

WORK MATERIAL			N		S			
			ALUMINUM ALLOYS, ZINC ALLOYS		MAGNESIUM ALLOYS		TITANIUM ALLOYS	
HARDNESS								
STRENGTH							~410N/mm ²	
DIAMETER			N	S	N	S	N	S
Fractional	Decimal	Metric						
3/64	.0469	1.0	30000	.0008	11500	.0012	8050	.0008
#47	.0785	2.0	15000	.0023	5800	.0035	4050	.0024
#32	.1160	3.0	9900	.0038	3850	.0051	2700	.0031
#22	.1570	4.0	7450	.0044	2900	.0059	2000	.0035
#9	.1960	5.0	5950	.0049	2300	.0067	1600	.0039
B	.2380	6.0	14950	.0056	1950	.0075	1350	.0047
J	.2770	7.0	4250	.0064	1650	.0087	1150	.0055
O	.3160	8.0	3700	.0072	1450	.0094	1000	.0059
T	.3580	9.0	3300	.0079	1280	.0106	895	.0067
X	.3970	10.0	3000	.0090	1150	.0114	805	.0071
7/16	.4375	11.0	2700	.0090	1050	.0118	730	.0071
15/32	.4688	12.0	2480	.0090	960	.0122	670	.0079
1/2	.5000	13.0	2300	.0090	890	.0122	620	.0079

N = R.P.M
S = Inch per Revolution (inch/rev.)



RECOMMENDED CUTTING CONDITIONS

HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE, GOLD-P COATED

DLGP511, DLGP513, DLGP512, DLGP506 SERIES

WORK MATERIAL			P				K			
			CARBON STEELS ALLOY STEELS		TOOL STEELS HARDENED STEELS		SOFT GREY CAST IRON		HARD GREY CAST IRON	
HARDNESS			HRC15 ~ 30		HRC20 ~ 40					
STRENGTH			700 ~ 1000N/mm ²		800~1200N/mm ²					
DIAMETER			N	S	N	S	N	S	N	S
Fractional	Decimal	Metric								
3/64	.0469	1.0	8750	.0008	6300	.0008	16000	.0008	9800	.0008
#47	.0785	2.0	4400	.0022	3150	.0022	7900	.0027	4900	.0027
#32	.1160	3.0	2900	.0032	2100	.0032	5250	.0043	3250	.0043
#22	.1570	4.0	2200	.0036	1600	.0036	3950	.0054	2450	.0054
#9	.1960	5.0	1750	.0041	1250	.0041	3150	.0054	1950	.0054
B	.2380	6.0	1450	.0047	1050	.0047	2650	.0069	1650	.0069
J	.2770	7.0	1250	.0054	900	.0054	2250	.0078	1400	.0078
O	.3160	8.0	1100	.0060	790	.0060	1950	.0087	1250	.0087
T	.3580	9.0	975	.0066	700	.0066	1750	.0095	1100	.0095
X	.3970	10.0	875	.0071	630	.0071	1600	.0108	980	.0108
7/16	.4375	11.0	800	.0077	575	.0077	1450	.0108	890	.0108
15/32	.4688	12.0	730	.0077	525	.0077	1300	.0108	815	.0108
1/2	.5000	13.0	675	.0077	485	.0077	1200	.0108	755	.0108

N = R.P.M
S = Inch per Revolution (inch/rev.)



Being the best through innovation

HSS




STRAIGHT SHANK DRILLS

- HSS Drills for soft materials & HSS cobalt Drills for tough materials



Global Cutting Tool Leader **YG-1**














SELECTION GUIDE

HSS STRAIGHT SHANK DRILLS

STRAIGHT SHANK TWIST DRILLS

- HSS Drills for soft materials & HSS cobalt Drills for tough materials

ITEM	MODEL	DESCRIPTION	SIZE		PAGE	
			MIN	MAX		
INCH						
D1118		HSS, STRAIGHT SHANK SCREW MACHINE / Fractional sizes	D3/64	D1/2	218	
D1115		HSS, STRAIGHT SHANK SCREW MACHINE / Letter sizes	A	Z	219	
D1119		HSS, STRAIGHT SHANK SCREW MACHINE / Wire gauge sizes	#60	#1	220	
D2146 D4146		HSSCo8, STRAIGHT SHANK SCREW MACHINE / Fractional sizes	D3/64	D1/2	221	
D2147 D4147		HSSCo8, STRAIGHT SHANK SCREW MACHINE / Letter sizes	A	Z	222	
D2148 D4148		HSSCo8, STRAIGHT SHANK SCREW MACHINE / Wire gauge sizes	#60	#1	223	
DN514		HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE SCREW MACHINE, TiN COATED / Fractional sizes	D3/32	D1/2	225	
DN516		HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE SCREW MACHINE, TiN COATED / Letter sizes	A	Z	226	
DN515		HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE SCREW MACHINE, TiN COATED / Wire gauge sizes	#47	#1	227	
DL517 DX517		HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE TAPER LENGTH / Fractional sizes	D5/64	D1/2	228	
METRIC						
D4107		HSSCo8, STRAIGHT SHANK DRILL	STUB	D1.0	D31.0	229
RECOMMENDED CUTTING CONDITIONS					232	

◎ : Excellent ○ : Good


P			H	M	K	N			S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	◎				○	○	○				○
◎	◎				○	○	○				○
◎	◎				○	○	○				○
◎	◎				○		○				○
◎	◎				○		○				○
◎	◎					○					
◎	◎					○					
◎	◎						○				
◎	◎						○				
◎	◎						○				

YG STRAIGHT SHANK DRILLS

D1118 SERIES

HSS, STRAIGHT SHANK SCREW MACHINE

- ▶ **Flute Geometry** : Right hand spiral, wider flutes
- ▶ **Point Angle** : 135°
under 1/16 : Normal point
1/16 & over : Split point
- ▶ **Application** : Drilling in steel, cast steel alloyed and Non-alloyed, grey cast iron, graphite, malleable cast iron



▶ Fractional sizes

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Fractional	Decimal				Fractional	Decimal		
	D1					D1			
* D1118003	3/64	.0469	1/2	1-3/8	* D1118018	9/32	.2813	1-1/2	2-11/16
* D1118004	1/16	.0625	5/8	1-5/8	* D1118019	19/64	.2969	1-9/16	2-3/4
* D1118005	5/64	.0781	11/16	1-11/16	* D1118020	5/16	.3125	1-5/8	2-13/16
* D1118006	3/32	.0938	3/4	1-3/4	* D1118021	21/64	.3281	1-11/16	2-15/16
* D1118007	7/64	.1094	13/16	1-13/16	** D1118022	11/32	.3438	1-11/16	3
* D1118008	1/8	.1250	7/8	1-7/8	** D1118023	23/64	.3594	1-3/4	3-1/16
* D1118009	9/64	.1406	15/16	1-15/16	** D1118024	3/8	.3750	1-13/16	3-1/8
* D1118010	5/32	.1563	1	2-1/16	** D1118025	25/64	.3906	1-7/8	3-1/4
* D1118011	11/64	.1719	1-1/16	2-1/8	** D1118026	13/32	.4063	1-15/16	3-5/16
* D1118012	3/16	.1875	1-1/8	2-3/16	** D1118027	27/64	.4219	2	3-3/8
* D1118013	13/64	.2031	1-3/16	2-1/4	** D1118028	7/16	.4375	2-1/16	3-7/16
* D1118014	7/32	.2188	1-1/4	2-3/8	** D1118029	29/64	.4531	2-1/8	3-9/16
* D1118015	15/64	.2344	1-5/16	2-7/16	** D1118030	15/32	.4688	2-1/8	3-5/8
* D1118016	1/4	.2500	1-3/8	2-1/2	** D1118031	31/64	.4844	2-3/16	3-11/16
* D1118017	17/64	.2656	1-7/16	2-5/8	** D1118032	1/2	.5000	2-1/4	3-3/4

* 10pcs per package
** 5pcs per package

Tolerance Diameter (Inch)	
up to 1/8(.1250)	0 ~ -.0005
over 1/8(.1250) up to 1/4(.2500)	0 ~ -.0007
over 1/4(.2500) up to 1/2(.5000)	0 ~ -.0010

◎ : Excellent ○ : Good


P		H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	◎				○	○	○				○

YG STRAIGHT SHANK DRILLS

D1115 SERIES

HSS, STRAIGHT SHANK SCREW MACHINE

- ▶ **Flute Geometry** : Right hand spiral, wider flutes
- ▶ **Point Angle** : 135° : Split point
- ▶ **Application** : Drilling in steel, cast steel alloyed and Non-alloyed, grey cast iron, graphite, malleable cast iron



▶ Letter sizes

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Letter	Decimal				Letter	Decimal		
	D1					D1			
* D1115201	A	.2340	1-5/16	2-7/16	* D1115214	N	.3020	1-5/8	2-13/16
* D1115202	B	.2380	1-3/8	2-1/2	* D1115215	O	.3160	1-11/16	2-15/16
* D1115203	C	.2420	1-3/8	2-1/2	* D1115216	P	.3230	1-11/16	2-15/16
* D1115204	D	.2460	1-3/8	2-1/2	** D1115217	Q	.3320	1-11/16	3
* D1115205	E	.2500	1-3/8	2-1/2	** D1115218	R	.3390	1-11/16	3
* D1115206	F	.2570	1-7/16	2-5/8	** D1115219	S	.3480	1-3/4	3-1/16
* D1115207	G	.2610	1-7/16	2-5/8	** D1115220	T	.3580	1-3/4	3-1/16
* D1115208	H	.2660	1-1/2	2-11/16	** D1115221	U	.3680	1-13/16	3-1/8
* D1115209	I	.2720	1-1/2	2-11/16	** D1115222	V	.3770	1-7/8	3-1/4
* D1115210	J	.2770	1-1/2	2-11/16	** D1115223	W	.3860	1-7/8	3-1/4
* D1115211	K	.2810	1-1/2	2-11/16	** D1115224	X	.3970	1-15/16	3-5/16
* D1115212	L	.2900	1-9/16	2-3/4	** D1115225	Y	.4040	1-15/16	3-5/16
* D1115213	M	.2950	1-9/16	2-3/4	** D1115226	Z	.4130	2	3-3/8

* 10pcs per package
** 5pcs per package

Tolerance Diameter (Inch)	
up to 1/8(.1250)	0 ~ -.0005
over 1/8(.1250) up to 1/4(.2500)	0 ~ -.0007
over 1/4(.2500) up to 1/2(.5000)	0 ~ -.0010

◎ : Excellent ○ : Good


P		H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	◎				○	○	○				○

STRAIGHT SHANK DRILLS

D1119 SERIES

HSS, STRAIGHT SHANK SCREW MACHINE

- **Flute Geometry** : Right hand spiral, wider flutes
- **Point Angle** : 135° : Split point
Wire gauge size #53~#60 : Normal point
Wire gauge size #1~#52 : Split point
- **Application** : Drilling in steel, cast steel alloyed and Non-alloyed, grey cast iron, graphite, malleable cast iron



► Wire gauge sizes

Unit : Inch

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Wire gauge	Decimal				Wire gauge	Decimal		
* D1119201	1	.2280	1-5/16	2-7/16	* D1119231	31	.1200	7/8	1-7/8
* D1119202	2	.2210	1-5/16	2-7/16	* D1119232	32	.1160	7/8	1-7/8
* D1119203	3	.2130	1-1/4	2-3/8	* D1119233	33	.1130	7/8	1-7/8
* D1119204	4	.2090	1-1/4	2-3/8	* D1119234	34	.1110	7/8	1-7/8
* D1119205	5	.2055	1-1/4	2-3/8	* D1119235	35	.1100	7/8	1-7/8
* D1119206	6	.2040	1-1/4	2-3/8	* D1119236	36	.1065	13/16	1-13/16
* D1119207	7	.2010	1-3/16	2-1/4	* D1119237	37	.1040	13/16	1-13/16
* D1119208	8	.1990	1-3/16	2-1/4	* D1119238	38	.1015	13/16	1-13/16
* D1119209	9	.1960	1-3/16	2-1/4	* D1119239	39	.0995	13/16	1-13/16
* D1119210	10	.1935	1-3/16	2-1/4	* D1119240	40	.0980	13/16	1-13/16
* D1119211	11	.1910	1-3/16	2-1/4	* D1119241	41	.0960	13/16	1-13/16
* D1119212	12	.1890	1-3/16	2-1/4	* D1119242	42	.0935	3/4	1-3/4
* D1119213	13	.1850	1-1/8	2-3/16	* D1119243	43	.0890	3/4	1-3/4
* D1119214	14	.1820	1-1/8	2-3/16	* D1119244	44	.0860	3/4	1-3/4
* D1119215	15	.1800	1-1/8	2-3/16	* D1119245	45	.0820	3/4	1-3/4
* D1119216	16	.1770	1-1/8	2-3/16	* D1119246	46	.0810	3/4	1-3/4
* D1119217	17	.1730	1-1/8	2-3/16	* D1119247	47	.0785	11/16	1-11/16
* D1119218	18	.1695	1-1/16	2-1/8	* D1119248	48	.0760	11/16	1-11/16
* D1119219	19	.1660	1-1/16	2-1/8	* D1119249	49	.0730	11/16	1-11/16
* D1119220	20	.1610	1-1/16	2-1/8	* D1119250	50	.0700	11/16	1-11/16
* D1119221	21	.1590	1-1/16	2-1/8	* D1119251	51	.0670	11/16	1-11/16
* D1119222	22	.1570	1-1/16	2-1/8	* D1119252	52	.0635	11/16	1-11/16
* D1119223	23	.1540	1	2-1/16	* D1119253	53	.0595	5/8	1-5/8
* D1119224	24	.1520	1	2-1/16	* D1119254	54	.0550	5/8	1-5/8
* D1119225	25	.1495	1	2-1/16	* D1119255	55	.0520	5/8	1-5/8
* D1119226	26	.1470	1	2-1/16	* D1119256	56	.0465	1/2	1-3/8
* D1119227	27	.1440	1	2-1/16	* D1119257	57	.0430	1/2	1-3/8
* D1119228	28	.1405	15/16	1-15/16	* D1119258	58	.0420	1/2	1-3/8
* D1119229	29	.1360	15/16	1-15/16	* D1119259	59	.0410	1/2	1-3/8
* D1119230	30	.1285	15/16	1-15/16	* D1119260	60	.0400	1/2	1-3/8

► **Tolerance** : See page 218 / * 10pcs per package ◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRc30~45	HRc45~55 HRc55~								
◎	◎			○	○	○				○	

STRAIGHT SHANK DRILLS

D2146 SERIES UN-COATED D4146 SERIES TIN-COATED

HSSCo8, STRAIGHT SHANK SCREW MACHINE

- **Flute Geometry** : Right hand spiral, wider flutes
- **Point Angle** : 135°
under 1/16 : Normal point
1/16 & over : Split point
- **Application** : Drilling in steel, cast steel alloyed and Non-alloyed, grey cast iron, graphite, malleable cast iron



► Fractional sizes

Unit : Inch

EDP No.	Diameter		Flute Length L1	Overall Length L2	
	Fractional	Decimal			
UN-COATED	D1				
TIN-COATED	D1				
* D2146003	D4146003	3/64	.0469	1/2	1-3/8
* D2146004	D4146004	1/16	.0625	5/8	1-5/8
* D2146005	D4146005	5/64	.0781	11/16	1-11/16
* D2146006	D4146006	3/32	.0938	3/4	1-3/4
** D2146007	D4146007	7/64	.1094	13/16	1-13/16
** D2146008	D4146008	1/8	.1250	7/8	1-7/8
** D2146009	D4146009	9/64	.1406	15/16	1-15/16
** D2146010	D4146010	5/32	.1563	1	2-1/16
** D2146011	D4146011	11/64	.1719	1-1/16	2-1/8
** D2146012	D4146012	3/16	.1875	1-1/8	2-3/16
** D2146013	D4146013	13/64	.2031	1-3/16	2-1/4
** D2146014	D4146014	7/32	.2188	1-1/4	2-3/8
** D2146015	D4146015	15/64	.2344	1-5/16	2-7/16
** D2146016	D4146016	1/4	.2500	1-3/8	2-1/2
** D2146017	D4146017	17/64	.2656	1-7/16	2-5/8
** D2146018	D4146018	9/32	.2813	1-1/2	2-11/16
** D2146019	D4146019	19/64	.2969	1-9/16	2-3/4
** D2146020	D4146020	5/16	.3125	1-5/8	2-13/16
** D2146021	D4146021	21/64	.3281	1-11/16	2-15/16
** D2146022	D4146022	11/32	.3438	1-11/16	3
** D2146023	D4146023	23/64	.3594	1-3/4	3-1/16
** D2146024	D4146024	3/8	.3750	1-13/16	3-1/8
** D2146025	D4146025	25/64	.3906	1-7/8	3-1/4
** D2146026	D4146026	13/32	.4063	1-15/16	3-5/16
** D2146027	D4146027	27/64	.4219	2	3-3/8
** D2146028	D4146028	7/16	.4375	2-1/16	3-7/16
** D2146029	D4146029	29/64	.4531	2-1/8	3-9/16
** D2146030	D4146030	15/32	.4688	2-1/8	3-5/8
** D2146031	D4146031	31/64	.4844	2-3/16	3-11/16
** D2146032	D4146032	1/2	.5000	2-1/4	3-3/4

► **Tolerance** : See page 218 / * 10pcs per package ** 5pcs per package ◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRc30~45	HRc45~55 HRc55~								
◎	◎			○	○	○				○	



D2147 SERIES UN-COATED
D4147 SERIES TIN-COATED

HSSCo8, STRAIGHT SHANK SCREW MACHINE

- ▶ **Flute Geometry** : Right hand spiral, wider flutes
- ▶ **Point Angle** : 135° : Split point
- ▶ **Application** : Drilling in steel, cast steel alloyed and Non-alloyed, grey cast iron, graphite, malleable cast iron



▶ **Letter sizes**

Unit : Inch

EDP No.		Diameter		Flute Length	Overall Length
UN-COATED	TIN-COATED	Letter	Decimal		
** D2147201	D4147201	A	.2340	1-5/16	2-7/16
** D2147202	D4147202	B	.2380	1-3/8	2-1/2
** D2147203	D4147203	C	.2420	1-3/8	2-1/2
** D2147204	D4147204	D	.2460	1-3/8	2-1/2
** D2147205	D4147205	E	.2500	1-3/8	2-1/2
** D2147206	D4147206	F	.2570	1-7/16	2-5/8
** D2147207	D4147207	G	.2610	1-7/16	2-5/8
** D2147208	D4147208	H	.2660	1-1/2	2-11/16
** D2147209	D4147209	I	.2720	1-1/2	2-11/16
** D2147210	D4147210	J	.2770	1-1/2	2-11/16
** D2147211	D4147211	K	.2810	1-1/2	2-11/16
** D2147212	D4147212	L	.2900	1-9/16	2-3/4
** D2147213	D4147213	M	.2950	1-9/16	2-3/4
** D2147214	D4147214	N	.3020	1-5/8	2-13/16
** D2147215	D4147215	O	.3160	1-11/16	2-15/16
** D2147216	D4147216	P	.3230	1-11/16	2-15/16
** D2147217	D4147217	Q	.3320	1-11/16	3
** D2147218	D4147218	R	.3390	1-11/16	3
** D2147219	D4147219	S	.3480	1-3/4	3-1/16
** D2147220	D4147220	T	.3580	1-3/4	3-1/16
** D2147221	D4147221	U	.3680	1-13/16	3-1/8
** D2147222	D4147222	V	.3770	1-7/8	3-1/4
** D2147223	D4147223	W	.3860	1-7/8	3-1/4
** D2147224	D4147224	X	.3970	1-15/16	3-5/16
** D2147225	D4147225	Y	.4040	1-15/16	3-5/16
** D2147226	D4147226	Z	.4130	2	3-3/8

▶ **Tolerance** : See page 218 / ** 5pcs per package

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~								○



D2148 SERIES UN-COATED
D4148 SERIES TIN-COATED

HSSCo8, STRAIGHT SHANK SCREW MACHINE

- ▶ **Flute Geometry** : Right hand spiral, wider flutes
- ▶ **Point Angle** : 135° : Split point
Wire gauge size #53~#60 : Normal point
Wire gauge size #1~#52 : Split point
- ▶ **Application** : Drilling in steel, cast steel alloyed and Non-alloyed, grey cast iron, graphite, malleable cast iron



▶ **Wire gauge sizes**

Unit : Inch

EDP No.		Diameter		Flute Length	Overall Length
UN-COATED	TIN-COATED	Wire gauge	Decimal		
** D2148101	D4148101	1	.2280	1-5/16	2-7/16
** D2148102	D4148102	2	.2210	1-5/16	2-7/16
** D2148103	D4148103	3	.2130	1-1/4	2-3/8
** D2148104	D4148104	4	.2090	1-1/4	2-3/8
** D2148105	D4148105	5	.2055	1-1/4	2-3/8
** D2148106	D4148106	6	.2040	1-1/4	2-3/8
** D2148107	D4148107	7	.2010	1-3/16	2-1/4
** D2148108	D4148108	8	.1990	1-3/16	2-1/4
** D2148109	D4148109	9	.1960	1-3/16	2-1/4
** D2148110	D4148110	10	.1935	1-3/16	2-1/4
** D2148111	D4148111	11	.1910	1-3/16	2-1/4
** D2148112	D4148112	12	.1890	1-3/16	2-1/4
** D2148113	D4148113	13	.1850	1-1/8	2-3/16
** D2148114	D4148114	14	.1820	1-1/8	2-3/16
** D2148115	D4148115	15	.1800	1-1/8	2-3/16
** D2148116	D4148116	16	.1770	1-1/8	2-3/16
** D2148117	D4148117	17	.1730	1-1/8	2-3/16
** D2148118	D4148118	18	.1695	1-1/16	2-1/8
** D2148119	D4148119	19	.1660	1-1/16	2-1/8
** D2148120	D4148120	20	.1610	1-1/16	2-1/8
** D2148121	D4148121	21	.1590	1-1/16	2-1/8
** D2148122	D4148122	22	.1570	1-1/16	2-1/8
** D2148123	D4148123	23	.1540	1	2-1/16
** D2148124	D4148124	24	.1520	1	2-1/16
** D2148125	D4148125	25	.1495	1	2-1/16
** D2148126	D4148126	26	.1470	1	2-1/16
** D2148127	D4148127	27	.1440	1	2-1/16
** D2148128	D4148128	28	.1405	15/16	1-15/16
** D2148129	D4148129	29	.1360	15/16	1-15/16
** D2148130	D4148130	30	.1285	15/16	1-15/16

▶ **Tolerance** : See page 218 / ** 5pcs per package

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~								○

Y/G STRAIGHT SHANK DRILLS

D2148 SERIES UN-COATED
D4148 SERIES TIN-COATED

HSSCo8, STRAIGHT SHANK SCREW MACHINE

- **Flute Geometry** : Right hand spiral, wider flutes
- **Point Angle** : 135° : Split point
Wire gauge size #53~#60 : Normal point
Wire gauge size #1~#52 : Split point
- **Application** : Drilling in steel, cast steel alloyed and Non-alloyed, grey cast iron, graphite, malleable cast iron



► Wire gauge sizes

Unit : Inch

EDP No.		Diameter		Flute Length	Overall Length
UN-COATED	TiN-COATED	Wire gauge	Decimal		
		D1		L1	L2
** D2148131	D4148131	31	.1200	7/8	1-7/8
** D2148132	D4148132	32	.1160	7/8	1-7/8
** D2148133	D4148133	33	.1130	7/8	1-7/8
** D2148134	D4148134	34	.1110	7/8	1-7/8
** D2148135	D4148135	35	.1100	7/8	1-7/8
** D2148136	D4148136	36	.1065	13/16	1-13/16
* D2148137	D4148137	37	.1040	13/16	1-13/16
* D2148138	D4148138	38	.1015	13/16	1-13/16
* D2148139	D4148139	39	.0995	13/16	1-13/16
* D2148140	D4148140	40	.0980	13/16	1-13/16
* D2148141	D4148141	41	.0960	13/16	1-13/16
* D2148142	D4148142	42	.0935	3/4	1-3/4
* D2148143	D4148143	43	.0890	3/4	1-3/4
* D2148144	D4148144	44	.0860	3/4	1-3/4
* D2148145	D4148145	45	.0820	3/4	1-3/4
* D2148146	D4148146	46	.0810	3/4	1-3/4
* D2148147	D4148147	47	.0785	11/16	1-11/16
* D2148148	D4148148	48	.0760	11/16	1-11/16
* D2148149	D4148149	49	.0730	11/16	1-11/16
* D2148150	D4148150	50	.0700	11/16	1-11/16
* D2148151	D4148151	51	.0670	11/16	1-11/16
* D2148152	D4148152	52	.0635	11/16	1-11/16
* D2148153	D4148153	53	.0595	5/8	1-5/8
* D2148154	D4148154	54	.0550	5/8	1-5/8
* D2148155	D4148155	55	.0520	5/8	1-5/8
* D2148156	D4148156	56	.0465	1/2	1-3/8
* D2148157	D4148157	57	.0430	1/2	1-3/8
* D2148158	D4148158	58	.0420	1/2	1-3/8
* D2148159	D4148159	59	.0410	1/2	1-3/8
* D2148160	D4148160	60	.0400	1/2	1-3/8

► **Tolerance** : See page 218 / * 10pcs per package ** 5pcs per package

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRc30~45	HRc45~55 HRc55~								
◎	◎			○		○				○	

Y/G STRAIGHT SHANK DRILLS

DN514 SERIES

HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE SCREW MACHINE, TiN COATED

- **Flute Geometry** : Right hand spiral, Parabolic flute
38° helix
- **Point Angle** : 130° : Split point
- **Application** : Improved chip removal in most materials, especially in deep drilling applications.



► Fractional sizes

Unit : Inch

EDP No.	Diameter		Flute Length	Overall Length	EDP No.	Diameter		Flute Length	Overall Length
	Fractional	Decimal				Fractional	Decimal		
	D1		L1	L2		D1		L1	L2
* DN514006	3/32	.0938	3/4	1-3/4	** DN514020	5/16	.3125	1-5/8	2-13/16
** DN514007	7/64	.1094	13/16	1-13/16	** DN514021	21/64	.3281	1-11/16	2-15/16
** DN514008	1/8	.1250	7/8	1-7/8	** DN514022	11/32	.3438	1-11/16	3
** DN514009	9/64	.1406	15/16	1-15/16	** DN514023	23/64	.3594	1-3/4	3-1/16
** DN514010	5/32	.1563	1	2-1/16	** DN514024	3/8	.3750	1-13/16	3-1/8
** DN514011	11/64	.1719	1-1/16	2-1/8	** DN514025	25/64	.3906	1-7/8	3-1/4
** DN514012	3/16	.1875	1-1/8	2-3/16	** DN514026	13/32	.4063	1-15/16	3-5/16
** DN514013	13/64	.2031	1-3/16	2-1/4	** DN514027	27/64	.4219	2	3-3/8
** DN514014	7/32	.2188	1-1/4	2-3/8	** DN514028	7/16	.4375	2-1/16	3-7/16
** DN514015	15/64	.2344	1-5/16	2-7/16	** DN514029	29/64	.4531	2-1/8	3-9/16
** DN514016	1/4	.2500	1-3/8	2-1/2	** DN514030	15/32	.4688	2-1/8	3-5/8
** DN514017	17/64	.2656	1-7/16	2-5/8	** DN514031	31/64	.4844	2-3/16	3-11/16
** DN514018	9/32	.2813	1-1/2	2-11/16	** DN514032	1/2	.5000	2-1/4	3-3/4
** DN514019	19/64	.2969	1-9/16	2-3/4					

* 10pcs per package
** 5pcs per package

Tolerance Diameter (Inch)	
up to 1/8(.1250)	0 ~ -.0005
over 1/8(.1250) up to 1/4(.2500)	0 ~ -.0007
over 1/4(.2500) up to 1/2(.5000)	0 ~ -.0010

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRc30~45	HRc45~55 HRc55~								
◎	◎			○							

YG STRAIGHT SHANK DRILLS

DN516 SERIES

HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE SCREW MACHINE, TIN COATED

- ▶ **Flute Geometry** : Right hand spiral, Parabolic flute
38° helix
- ▶ **Point Angle** : 130° : Split point
- ▶ **Application** : Improved chip removal in most materials, especially in deep drilling applications.



▶ Letter sizes

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Letter	Decimal				Letter	Decimal		
TiN	D1				TiN	D1			
** DN516101	A	.2340	1-5/16	2-7/16	** DN516114	N	.3020	1-5/8	2-13/16
** DN516102	B	.2380	1-3/8	2-1/2	** DN516115	O	.3160	1-11/16	2-15/16
** DN516103	C	.2420	1-3/8	2-1/2	** DN516116	P	.3230	1-11/16	2-15/16
** DN516104	D	.2460	1-3/8	2-1/2	** DN516117	Q	.3320	1-11/16	3
** DN516105	E	.2500	1-3/8	2-1/2	** DN516118	R	.3390	1-11/16	3
** DN516106	F	.2570	1-7/16	2-5/8	** DN516119	S	.3480	1-3/4	3-1/16
** DN516107	G	.2610	1-7/16	2-5/8	** DN516120	T	.3580	1-3/4	3-1/16
** DN516108	H	.2660	1-1/2	2-11/16	** DN516121	U	.3680	1-13/16	3-1/8
** DN516109	I	.2720	1-1/2	2-11/16	** DN516122	V	.3770	1-7/8	3-1/4
** DN516110	J	.2770	1-1/2	2-11/16	** DN516123	W	.3860	1-7/8	3-1/4
** DN516111	K	.2810	1-1/2	2-11/16	** DN516124	X	.3970	1-15/16	3-5/16
** DN516112	L	.2900	1-9/16	2-3/4	** DN516125	Y	.4040	1-15/16	3-5/16
** DN516113	M	.2950	1-9/16	2-3/4	** DN516126	Z	.4130	2	3-3/8

** 5pcs per package

Tolerance Diameter (Inch)	
up to 1/8(.1250)	0 ~ -.0005
over 1/8(.1250) up to 1/4(.2500)	0 ~ -.0007
over 1/4(.2500) up to 1/2(.5000)	0 ~ -.0010

◎ : Excellent ○ : Good


P		H	M	K	N				S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55 HRc55~							
◎	◎				○					

YG STRAIGHT SHANK DRILLS

DN515 SERIES

HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE SCREW MACHINE, TIN COATED

- ▶ **Flute Geometry** : Right hand spiral, Parabolic flute
38° helix
- ▶ **Point Angle** : 130° : Split point
- ▶ **Application** : Improved chip removal in most materials, especially in deep drilling applications.



▶ Wire gauge sizes

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Wire gauge	Decimal				Wire gauge	Decimal		
TiN	D1				TiN	D1			
** DN515201	1	.2280	1-5/16	2-7/16	** DN515225	25	.1495	1	2-1/16
** DN515202	2	.2210	1-5/16	2-7/16	** DN515226	26	.1470	1	2-1/16
** DN515203	3	.2130	1-1/4	2-3/8	** DN515227	27	.1440	1	2-1/16
** DN515204	4	.2090	1-1/4	2-3/8	** DN515228	28	.1405	15/16	1-15/16
** DN515205	5	.2055	1-1/4	2-3/8	** DN515229	29	.1360	15/16	1-15/16
** DN515206	6	.2040	1-1/4	2-3/8	** DN515230	30	.1285	15/16	1-15/16
** DN515207	7	.2010	1-3/16	2-1/4	** DN515231	31	.1200	7/8	1-7/8
** DN515208	8	.1990	1-3/16	2-1/4	** DN515232	32	.1160	7/8	1-7/8
** DN515209	9	.1960	1-3/16	2-1/4	** DN515233	33	.1130	7/8	1-7/8
** DN515210	10	.1935	1-3/16	2-1/4	** DN515234	34	.1110	7/8	1-7/8
** DN515211	11	.1910	1-3/16	2-1/4	** DN515235	35	.1100	7/8	1-7/8
** DN515212	12	.1890	1-3/16	2-1/4	** DN515236	36	.1065	13/16	1-13/16
** DN515213	13	.1850	1-1/8	2-3/16	** DN515237	37	.1040	13/16	1-13/16
** DN515214	14	.1820	1-1/8	2-3/16	** DN515238	38	.1015	13/16	1-13/16
** DN515215	15	.1800	1-1/8	2-3/16	** DN515239	39	.0995	13/16	1-13/16
** DN515216	16	.1770	1-1/8	2-3/16	** DN515240	40	.0980	13/16	1-13/16
** DN515217	17	.1730	1-1/8	2-3/16	** DN515241	41	.0960	13/16	1-13/16
** DN515218	18	.1695	1-1/16	2-1/8	** DN515242	42	.0935	3/4	1-3/4
** DN515219	19	.1660	1-1/16	2-1/8	** DN515243	43	.0890	3/4	1-3/4
** DN515220	20	.1610	1-1/16	2-1/8	** DN515244	44	.0860	3/4	1-3/4
** DN515221	21	.1590	1-1/16	2-1/8	** DN515245	45	.0820	3/4	1-3/4
** DN515222	22	.1570	1-1/16	2-1/8	** DN515246	46	.0810	3/4	1-3/4
** DN515223	23	.1540	1	2-1/16	** DN515247	47	.0785	11/16	1-11/16
** DN515224	24	.1520	1	2-1/16					

* 10pcs per package
** 5pcs per package

Tolerance Diameter (Inch)	
up to 1/8(.1250)	0 ~ -.0005
over 1/8(.1250) up to 1/4(.2500)	0 ~ -.0007
over 1/4(.2500) up to 1/2(.5000)	0 ~ -.0010

◎ : Excellent ○ : Good


P		H	M	K	N				S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55 HRc55~							
◎	◎				○					

YG STRAIGHT SHANK DRILLS

DL517 SERIES UN-COATED
DX517 SERIES TiCN-COATED

HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE TAPER LENGTH

- ▶ Flute Geometry : Right hand spiral, Parabolic flute
38° helix
- ▶ Point Angle : 130° : Split point
- ▶ Application : Improved chip removal in most materials, especially in deep drilling applications.



Fractional sizes

Unit : Inch

EDP No.		Diameter		Flute Length	Overall Length
UN-COATED	TiCN-COATED	Fractional	Decimal		
		D1		L1	L2
* DL517005	DX517005	5/64	.0781	2	3-3/4
* DL517006	DX517006	3/32	.0938	2-1/4	4-1/4
* DL517007	DX517007	7/64	.1094	2-1/2	4-5/8
* DL517008	DX517008	1/8	.1250	2-3/4	5-1/8
* DL517009	DX517009	9/64	.1406	3	5-3/8
* DL517010	DX517010	5/32	.1563	3	5-3/8
* DL517011	DX517011	11/64	.1719	3-3/8	5-3/4
* DL517012	DX517012	3/16	.1875	3-3/8	5-3/4
* DL517013	DX517013	13/64	.2031	3-5/8	6
* DL517014	DX517014	7/32	.2188	3-5/8	6
* DL517015	DX517015	15/64	.2344	3-3/4	6-1/8
** DL517016	DX517016	1/4	.2500	3-3/4	6-1/8
** DL517017	DX517017	17/64	.2656	3-7/8	6-1/4
** DL517018	DX517018	9/32	.2813	3-7/8	6-1/4
** DL517019	DX517019	19/64	.2969	4	6-3/8
** DL517020	DX517020	5/16	.3125	4	6-3/8
** DL517021	DX517021	21/64	.3281	4-1/8	6-1/2
** DL517022	DX517022	11/32	.3438	4-1/8	6-3/4
** DL517023	DX517023	23/64	.3594	4-1/4	6-3/4
** DL517024	DX517024	3/8	.3750	4-1/4	6-3/4
** DL517025	DX517025	25/64	.3906	4-3/8	7
** DL517026	DX517026	13/32	.4063	4-3/8	7
** DL517027	DX517027	27/64	.4219	4-5/8	7-1/4
** DL517028	DX517028	7/16	.4375	4-5/8	7-1/4
** DL517029	DX517029	29/64	.4531	4-3/4	7-1/2
** DL517030	DX517030	15/32	.4688	4-3/4	7-1/2
** DL517031	DX517031	31/64	.4844	4-3/4	7-3/4
** DL517032	DX517032	1/2	.5000	4-3/4	7-3/4

▶ Tolerance : See page 218 * 10pcs per package ** 5pcs per package

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~								
◎	◎				○						


YG STRAIGHT SHANK DRILLS

D4107 SERIES

HSSCo8, STRAIGHT SHANK DRILL

STUB

- ▶ Flute Geometry : Right hand spiral helix
- ▶ Point Angle : 135°
under 1.6mm : Normal point
1.6mm & over : Split point
- ▶ Surface Treatment : TiN Coating
- ▶ Application : Drills suitable for drilling in thin materials with portable drills. Special twist drills for automatic and turret lathes.



EDP No.	Diameter		Flute Length	Overall Length	EDP No.	Diameter		Flute Length	Overall Length
	Metric	Inch				Metric	Inch		
	D1		L1	L2		D1		L1	L2
* D4107010	1.0	.0394	6	26	** D4107035	3.5	.1378	20	52
* D4107011	1.1	.0433	7	28	** D4107036	3.6	.1417	20	52
* D4107012	1.2	.0472	8	30	** D4107037	3.7	.1457	20	52
* D4107013	1.25	.0492	8	30	** D4107038	3.75	.1476	20	52
* D4107014	1.3	.0512	8	30	** D4107039	3.8	.1496	22	55
* D4107015	1.4	.0551	9	32	** D4107040	3.9	.1535	22	55
* D4107016	1.5	.0591	9	32	** D4107041	4.0	.1575	22	55
* D4107017	1.6	.0630	10	34	** D4107042	4.1	.1614	22	55
* D4107018	1.7	.0669	10	34	** D4107043	4.2	.1654	22	55
* D4107019	1.75	.0689	11	36	** D4107044	4.25	.1673	22	55
* D4107020	1.8	.0709	11	36	** D4107045	4.3	.1693	24	58
* D4107021	1.9	.0748	11	36	** D4107046	4.4	.1732	24	58
* D4107022	2.0	.0787	12	38	** D4107047	4.4	.1732	24	58
* D4107023	2.1	.0827	12	38	** D4107048	4.5	.1772	24	58
* D4107024	2.2	.0866	13	40	** D4107049	4.6	.1811	24	58
* D4107025	2.25	.0886	13	40	** D4107050	4.65	.1831	24	58
* D4107026	2.3	.0906	13	40	** D4107051	4.7	.1850	24	58
* D4107027	2.4	.0945	14	43	** D4107052	4.75	.1870	24	58
* D4107028	2.5	.0984	14	43	** D4107053	4.8	.1890	26	62
* D4107029	2.6	.1024	14	43	** D4107054	4.8	.1890	26	62
* D4107030	2.7	.1063	16	46	** D4107055	4.9	.1929	26	62
* D4107031	2.75	.1083	16	46	** D4107056	5.0	.1969	26	62
* D4107032	2.8	.1102	16	46	** D4107057	5.1	.2008	26	62
* D4107033	2.9	.1142	16	46	** D4107058	5.2	.2047	26	62
* D4107034	3.0	.1181	16	46	** D4107059	5.25	.2067	26	62
** D4107035	3.1	.1220	18	49	** D4107060	5.3	.2087	26	62
** D4107036	3.2	.1260	18	49	** D4107061	5.4	.2126	28	66
** D4107037	3.25	.1280	18	49	** D4107062	5.5	.2165	28	66
** D4107038	3.3	.1299	18	49	** D4107063	5.55	.2185	28	66
** D4107039	3.4	.1339	20	52	** D4107064	5.6	.2205	28	66
** D4107040					** D4107065	5.7	.2244	28	66
** D4107041					** D4107066	5.75	.2264	28	66

▶ The HSSCo5(DL107) is available when you need. * 10pcs per package ** 5pcs per package
The TiN(D4107), TiCN(D7107) and TiAlN(DQ107) are available on your request.

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~								
◎	◎				○						

YG STRAIGHT SHANK DRILLS

D4107 SERIES

HSSCo8, STRAIGHT SHANK DRILL STUB

- ▶ **Flute Geometry** : Right hand spiral helix
- ▶ **Point Angle** : 135°
under 1.6mm : Normal point
1.6mm & over : Split point
- ▶ **Surface Treatment** : TiN Coating
- ▶ **Application** : Drills suitable for drilling in thin materials with portable drills. Special twist drills for automatic and turret lathes.



DIN 1897 HSS Co8 33° h8 135° P.235

EDP No.	Diameter		Flute Length	Overall Length	EDP No.	Diameter		Flute Length	Overall Length
	Metric	Inch				Metric	Inch		
TiN	D1		L1	L2	TiN	D1		L1	L2
** D4107058	5.8	.2283	28	66	** D4107982	8.25	.3248	37	79
** D4107059	5.9	.2323	28	66	** D4107083	8.3	.3268	37	79
** D4107060	6.0	.2362	28	66	** D4107084	8.4	.3307	37	79
** D4107061	6.1	.2402	31	70	** D4107085	8.5	.3346	37	79
** D4107062	6.2	.2441	31	70	** D4107086	8.6	.3386	40	84
** D4107962	6.25	.2461	31	70	** D4107087	8.7	.3425	40	84
** D4107063	6.3	.2480	31	70	** D4107987	8.75	.3445	40	84
** D4107064	6.4	.2520	31	70	** D4107088	8.8	.3465	40	84
** D4107065	6.5	.2559	31	70	** D4107089	8.9	.3504	40	84
** D4107066	6.6	.2598	31	70	** D4107090	9.0	.3543	40	84
** D4107067	6.7	.2638	31	70	** D4107091	9.1	.3583	40	84
** D4107967	6.75	.2657	34	74	** D4107092	9.2	.3622	40	84
** D4107068	6.8	.2677	34	74	** D4107992	9.25	.3642	40	84
** D4107069	6.9	.2717	34	74	** D4107093	9.3	.3661	40	84
** D4107070	7.0	.2756	34	74	** D4107993	9.35	.3681	40	84
** D4107071	7.1	.2795	34	74	** D4107094	9.4	.3701	40	84
** D4107072	7.2	.2835	34	74	** D4107095	9.5	.3740	40	84
** D4107972	7.25	.2854	34	74	** D4107096	9.6	.3780	43	89
** D4107073	7.3	.2874	34	74	** D4107097	9.7	.3819	43	89
** D4107074	7.4	.2913	34	74	** D4107997	9.75	.3839	43	89
** D4107974	7.45	.2933	34	74	** D4107098	9.8	.3858	43	89
** D4107075	7.5	.2953	34	74	** D4107099	9.9	.3898	43	89
** D4107076	7.6	.2992	37	79	** D4107100	10.0	.3937	43	89
** D4107077	7.7	.3031	37	79	** D4107102	10.2	.4016	43	89
** D4107977	7.75	.3051	37	79	** D4107802	10.25	.4035	43	89
** D4107078	7.8	.3071	37	79	** D4107105	10.5	.4134	43	89
** D4107079	7.9	.3110	37	79	** D4107807	10.75	.4232	47	95
** D4107080	8.0	.3150	37	79	** D4107110	11.0	.4330	47	95
** D4107081	8.1	.3189	37	79	** D4107812	11.25	.4429	47	95
** D4107082	8.2	.3228	37	79	** D4107115	11.5	.4527	47	95

▶ The HSSCo5(DL107) is available when you need. ** 5pcs per package
The TiN(D4107), TiCN(D7107) and TiAlN(DQ107) are available on your request.


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎			○	○	○				○	

YG STRAIGHT SHANK DRILLS

D4107 SERIES

HSSCo8, STRAIGHT SHANK DRILL STUB

- ▶ **Flute Geometry** : Right hand spiral helix
- ▶ **Point Angle** : 135°
under 1.6mm : Normal point
1.6mm & over : Split point
- ▶ **Surface Treatment** : TiN Coating
- ▶ **Application** : Drills suitable for drilling in thin materials with portable drills. Special twist drills for automatic and turret lathes.



DIN 1897 HSS Co8 33° h8 135° P.235

EDP No.	Diameter		Flute Length	Overall Length	EDP No.	Diameter		Flute Length	Overall Length
	Metric	Inch				Metric	Inch		
TiN	D1		L1	L2	TiN	D1		L1	L2
** D4107817	11.75	.4626	47	95	- D4107877	17.75	.6907	62	123
** D4107118	11.8	.4645	47	95	- D4107180	18.0	.7087	62	123
** D4107120	12.0	.4724	51	102	- D4107882	18.25	.7185	64	127
** D4107822	12.25	.4823	51	102	- D4107185	18.5	.7283	64	127
** D4107125	12.5	.4921	51	102	- D4107887	18.75	.7382	64	127
** D4107827	12.75	.5020	51	102	- D4107190	19.0	.7480	64	127
** D4107130	13.0	.5118	51	102	- D4107892	19.25	.7579	66	131
- D4107832	13.25	.5217	54	107	- D4107195	19.5	.7676	66	131
- D4107135	13.5	.5314	54	107	- D4107897	19.75	.7776	66	131
- D4107837	13.75	.5413	54	107	- D4107200	20.0	.7874	66	131
- D4107138	13.8	.5433	54	107	- D4107205	20.5	.8071	68	136
- D4107140	14.0	.5512	54	107	- D4107210	21.0	.8268	68	136
- D4107842	14.25	.5610	56	111	- D4107215	21.5	.8465	70	141
- D4107145	14.5	.5708	56	111	- D4107220	22.0	.8661	70	141
- D4107847	14.75	.5807	56	111	- D4107225	22.5	.8858	72	146
- D4107150	15.0	.5905	56	111	- D4107230	23.0	.9055	72	146
- D4107852	15.25	.6004	58	115	- D4107235	23.5	.9252	72	146
- D4107155	15.5	.6102	58	115	- D4107240	24.0	.9449	75	151
- D4107857	15.75	.6201	58	115	- D4107245	24.5	.9646	75	151
- D4107160	16.0	.6299	58	115	- D4107250	25.0	.9843	75	151
- D4107862	16.25	.6398	60	119	- D4107260	26.0	1.0236	78	156
- D4107165	16.5	.6495	60	119	- D4107270	27.0	1.0630	81	162
- D4107867	16.75	.6594	60	119	- D4107280	28.0	1.1024	81	162
- D4107170	17.0	.6692	60	119	- D4107290	29.0	1.1417	84	168
- D4107872	17.25	.6791	62	123	- D4107300	30.0	1.1811	84	168
- D4107175	17.5	.6889	62	123	- D4107310	31.0	1.2205	87	174

▶ The HSSCo5(DL107) is available when you need. ** 5pcs per package
The TiN(D4107), TiCN(D7107) and TiAlN(DQ107) are available on your request. - 1pcs per package

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎			○	○	○				○	



RECOMMENDED CUTTING CONDITIONS

HSS & HSSCo8, STRAIGHT SHANK SCREW MACHINE DRILLS

D1118, D1115, D1119, D2146, D2147, D2148 SERIES

WORK MATERIAL	P									
	CARBON STEELS		CARBON STEELS		CARBON STEELS		ALLOY STEELS		ALLOY STEELS	
	~ HRC23		~ HRC23		~ HRC23 ~ 28		HRC23 ~ 34		HRC34 ~ 38	
HARDNESS	~ 570 N/mm ²		~ 830 N/mm ²		830 ~ 950 N/mm ²		830 ~ 1110 N/mm ²		1110 ~ 1260 N/mm ²	
STRENGTH										
DIAMETER	N	S	N	S	N	S	N	S	N	S
~ 3/32	3380	.0010	2550	.0010	1900	.0006	2380	.0008	1400	.0006
3/32 ~ 5/32	2700	.0020	2000	.0020	1500	.0010	1880	.0020	1100	.0008
11/64 ~ 1/4	1700	.0025	1280	.0025	960	.0015	1190	.0025	700	.0010
17/64 ~ 23/64	1050	.0051	780	.0051	590	.0030	730	.0051	430	.0015
3/8 ~ 37/64	750	.0059	560	.0060	425	.0030	520	.0070	310	.0020
19/32 ~ 1	440	.0090	330	.0090	255	.0051	300	.0090	180	.0020
1 ~	260	.0110	195	.0110	145	.0070	180	.0070	107	.0030

WORK MATERIAL	P		M		K		N			
	TOOL STEELS		STAINLESS STEELS		CAST IRON		ALUMINUM ALLOYS		MAGNESIUM ALLOYS	
	~ 270 N/mm ²		830 N/mm ²		~ HRC21					
HARDNESS			HRC23							
STRENGTH			830 N/mm ²		~ 800 N/mm ²					
DIAMETER	N	S	N	S	N	S	N	S	N	S
~ 3/32	3180	.0016	2550	.0010	2250	.0010	6400	.0015	8600	.0015
3/32 ~ 5/32	2500	.0020	2000	.0020	2000	.0020	5000	.0025	6800	.0025
11/64 ~ 1/4	1590	.0025	1280	.0025	1280	.0025	3200	.0030	4300	.0030
17/64 ~ 23/64	970	.0051	780	.0051	780	.0051	2000	.0070	2600	.0070
3/8 ~ 37/64	700	.0070	560	.0060	560	.0060	1400	.0078	1900	.0078
19/32 ~ 1	440	.0090	330	.0090	330	.0090	820	.0118	1100	.0118
1 ~	240	.1180	195	.0110	195	.0110	490	.0150	660	.0150

WORK MATERIAL	N				S	
	ZINC ALLOYS		PLASTIC		TITANIUM ALLOYS	
					410 N/mm ²	
HARDNESS						
STRENGTH					410 N/mm ²	
DIAMETER	N	S	N	S	N	S
~ 3/32	6400	.0015	3380	.0010	1400	.0008
3/32 ~ 5/32	5000	.0025	2700	.0020	1100	.0010
11/64 ~ 1/4	3200	.0030	1700	.0025	700	.0015
17/64 ~ 23/64	2000	.0070	1050	.0051	430	.0030
3/8 ~ 37/64	1400	.0078	750	.0060	430	.0030
19/32 ~ 1	820	.0118	440	.0090	180	.0051
1 ~	490	.0150	260	.0110	107	.0070

N = R.P.M
S = Inch per Revolution (inch/rev.)



RECOMMENDED CUTTING CONDITIONS

HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE SCREW MACHINE, TIN COATED

DN514, DN516, DN515 SERIES

WORK MATERIAL	P				K			
	CARBON STEELS ALLOY STEELS		TOOL STEELS HARDENED STEELS		SOFT GREY CAST IRON		HARD GREY CAST IRON	
	HRC15 ~ 30		HRC20 ~ 40					
HARDNESS	700 ~ 1000 N/mm ²		800 ~ 1200 N/mm ²					
STRENGTH								
DIAMETER	N	S	N	S	N	S	N	S
~ 5/64	2630	.0012	2100	.0010	4200	.0023	1680	.0500
3/32 ~ 7/64	2100	.0015	1680	.0012	3300	.0031	1310	.0023
1/8 ~ 5/32	1680	.0020	1310	.0015	2630	.0039	1050	.0031
11/64 ~ 3/16	1310	.0023	1050	.0019	2100	.0051	840	.0039
13/64 ~ 15/64	1050	.0023	840	.0019	1680	.0051	660	.0039
1/4 ~ 9/32	840	.0031	660	.0023	1310	.0063	530	.0051
19/64 ~ 11/32	660	.0039	530	.0031	1050	.0078	420	.0067
23/64 ~ 7/16	530	.0051	420	.0039	840	.0098	330	.0082
29/64 ~ 9/16	420	.0051	330	.0039	660	.0098	260	.0082
37/64 ~ 45/64	330	.0059	260	.0051	530	.0118	210	.0098
23/32 ~ 7/8	260	.0078	210	.0059	420	.0157	170	.0118
57/64 ~ 1-1/8	210	.0098	170	.0078	330	.0196	130	.0196
1-9/64 ~	170	.0098	130	.0078	260	.0196	110	.0196

N = R.P.M
S = Inch per Revolution (inch/rev.)



STRAIGHT SHANK DRILLS

RECOMMENDED CUTTING CONDITIONS

HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE TAPER LENGTH, TiCN COATED

DX517 SERIES

WORK MATERIAL	P				K			
	CARBON STEELS ALLOY STEELS		TOOL STEELS HARDENED STEELS		SOFT GREY CAST IRON		HARD GREY CAST IRON	
	HRC15 ~ 30		HRC20 ~ 40					
STRENGTH	700 ~ 1000 N/mm ²		800 ~ 1200 N/mm ²					
DIAMETER	N	S	N	S	N	S	N	S
~ 5/64	4900	.0023	3400	.0023	8500	.0027	5400	.0027
3/32 ~ 7/64	3000	.0031	2350	.0031	5700	.0043	3500	.0043
1/8 ~ 5/32	2440	.0035	1800	.0035	4300	.0055	2700	.0055
11/64 ~ 15/64	1950	.0039	1400	.0039	3450	.0055	2150	.0055
1/4 ~ 9/32	1400	.0055	1000	.0055	2450	.0078	1550	.0078
19/64 ~ 5/16	1200	.0059	850	.0059	2100	.0086	1350	.0086
21/64 ~ 23/64	1100	.0066	800	.0066	1950	.0094	1200	.0094
3/8 ~ 25/64	950	.0071	660	.0071	1750	.0110	1050	.0110
13/32 ~ 7/16	900	.0078	630	.0078	1600	.0110	960	.0110
29/64 ~ 15/32	800	.0078	575	.0078	1450	.0110	900	.0110
31/64 ~ 1/2	720	.0078	500	.0078	1300	.0110	830	.0110

N = R.P.M
S = Inch per Revolution (inch/rev.)

HSSCo5, STRAIGHT SHANK PARABOLIC FLUTE TAPER LENGTH

DL517 SERIES

WORK MATERIAL	P				K			
	CARBON STEELS ALLOY STEELS		TOOL STEELS HARDENED STEELS		SOFT GREY CAST IRON		HARD GREY CAST IRON	
	HRC15 ~ 30		HRC20 ~ 40					
STRENGTH	700 ~ 1000 N/mm ²		800 ~ 1200 N/mm ²					
DIAMETER	N	S	N	S	N	S	N	S
~ 5/64	3990	.0023	2770	.0023	6920	.0027	4400	.0027
3/32 ~ 7/64	2440	.0031	1910	.0031	4640	.0043	2850	.0043
1/8 ~ 5/32	1990	.0035	1470	.0035	3500	.0055	2200	.0055
11/64 ~ 15/64	1590	.0039	1140	.0039	2810	.0055	1750	.0055
1/4 ~ 9/32	1140	.0055	810	.0055	1990	.0078	1260	.0078
19/64 ~ 5/16	980	.0059	690	.0059	1710	.0086	1100	.0086
21/64 ~ 23/64	900	.0066	650	.0066	1590	.0094	980	.0094
3/8 ~ 25/64	770	.0071	540	.0071	1420	.0110	850	.0110
13/32 ~ 7/16	730	.0078	510	.0078	1300	.0110	780	.0110
29/64 ~ 15/32	650	.0078	470	.0078	1180	.0110	730	.0110
31/64 ~ 1/2	590	.0078	410	.0078	1060	.0110	680	.0110

N = R.P.M
S = Inch per Revolution (inch/rev.)



STRAIGHT SHANK DRILLS

RECOMMENDED CUTTING CONDITIONS

HSSCo8, STRAIGHT SHANK DRILL, STUB

D4107 SERIES

WORK MATERIAL	P										M			
	CARBON STEELS		CARBON STEELS		CARBON STEELS		ALLOY STEELS		ALLOY STEELS		TOOL STEELS		STAINLESS STEELS	
	~ HRC23		~ HRC23 ~ 28		HRC23 ~ 34		HRC34 ~ 38						HRC23	
STRENGTH	~ 570 N/mm ²		~ 830 N/mm ²		830 ~ 950 N/mm ²		830 ~ 1110 N/mm ²		1110 ~ 1260 N/mm ²		~ 270 N/mm ²		830 N/mm ²	
DIAMETER	N	S	N	S	N	S	N	S	N	S	N	S	N	S
2.5	4225	.0010	3200	.0010	2500	.0006	2980	.0008	1750	.0006	3975	.0017	3200	.0010
3.0	3375	.0020	2500	.0020	2000	.0010	2350	.0020	1375	.0008	3125	.0020	2500	.0020
5.0	2125	.0025	1600	.0025	1280	.0015	1500	.0025	875	.0010	2000	.0025	1600	.0025
8.0	1310	.0051	975	.0051	785	.0030	910	.0051	535	.0015	1210	.0051	975	.0051
11.0	935	.0059	700	.0059	565	.0030	650	.0071	385	.0020	875	.0071	700	.0059
19.0	550	.0091	410	.0091	340	.0051	375	.0091	225	.0020	550	.0091	410	.0091
31.0	325	.0110	244	.0110	193	.0071	225	.0071	134	.0030	300	.0118	244	.0110

WORK MATERIAL	K		N						S			
	CAST IRON		ALUMINUM ALLOYS		MAGNESIUM ALLOYS		ZINC ALLOYS		PLASTIC		TITANIUM ALLOYS	
	~ HRC21										410 N/mm ²	
STRENGTH	~ 800 N/mm ²											
DIAMETER	N	S	N	S	N	S	N	S	N	S	N	S
2.5	2800	.0010	7950	.0015	10700	.0015	7950	.0015	4225	.0010	1750	.0008
3.0	2500	.0020	6200	.0025	8450	.0025	6200	.0025	3350	.0020	1375	.0010
5.0	1600	.0025	3950	.0030	5350	.0030	3950	.0030	2125	.0025	875	.0015
8.0	975	.0051	2490	.0071	3240	.0071	2490	.0071	1310	.0051	535	.0030
11.0	700	.0059	1740	.0079	2365	.0079	1740	.0079	935	.0059	535	.0030
19.0	410	.0091	1020	.0118	1370	.0118	1020	.0118	550	.0091	225	.0051
31.0	244	.0110	610	.0150	820	.0150	610	.0150	325	.0110	134	.0071

N = R.P.M
S = Inch per Revolution (inch/rev.)

- i-DREAM DRILLS
- DREAM DRILLS -GENERAL
- DREAM DRILLS -HIGH FEED
- DREAM DRILLS -FLAT BOTTOM
- DREAM DRILLS -INOX
- DREAM DRILLS -ALU
- DREAM DRILLS -MQL TYPE
- DREAM DRILLS for HIGH HARDENED STEELS
- STANDARD CARBIDE DRILLS
- MULTI-1 DRILLS
- HPD DRILLS
- GOLD-P DRILLS
- STRAIGHT SHANK DRILLS
- AIRCRAFT DRILLS
- SILVER & DEMING DRILLS
- TAPER SHANK DRILLS
- NC SPOTTING DRILLS
- COMBINATION DRILLS & COUNTERSINK
- SPADE DRILLS
- TECHNICAL DATA

- i-DREAM DRILLS
- DREAM DRILLS -GENERAL
- DREAM DRILLS -HIGH FEED
- DREAM DRILLS -FLAT BOTTOM
- DREAM DRILLS -INOX
- DREAM DRILLS -ALU
- DREAM DRILLS -MQL TYPE
- DREAM DRILLS for HIGH HARDENED STEELS
- STANDARD CARBIDE DRILLS
- MULTI-1 DRILLS
- HPD DRILLS
- GOLD-P DRILLS
- STRAIGHT SHANK DRILLS
- AIRCRAFT DRILLS
- SILVER & DEMING DRILLS
- TAPER SHANK DRILLS
- NC SPOTTING DRILLS
- COMBINATION DRILLS & COUNTERSINK
- SPADE DRILLS
- TECHNICAL DATA



Being the best through innovation

HSS




AIRCRAFT DRILLS

- 6 and 12 inch Length Drills



Global Cutting Tool Leader **YG-1**



AIRCRAFT DRILLS - 6 and 12 inch Length Drills

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
INCH					
DL601 DL604		HSSCo5, AIRCRAFT EXTENSION DRILL 135° SPLIT POINT COLORING / Fractional sizes	D5/64	D1/2	240
DL602 DL605		HSSCo5, AIRCRAFT EXTENSION DRILL 135° SPLIT POINT COLORING / Letter sizes	A	Z	241
DL603 DL606		HSSCo5, AIRCRAFT EXTENSION DRILL 135° SPLIT POINT COLORING / Wire gauge sizes	#43	#1	242
D1631 D1634		HSS, AIRCRAFT EXTENSION DRILL 135° SPLIT POINT STEAM OXIDE / Fractional sizes	D5/64	D1/2	243
D1632 D1635		HSS, AIRCRAFT EXTENSION DRILL 135° SPLIT POINT STEAM OXIDE / Letter sizes	A	Z	244
D1633 D1636		HSS, AIRCRAFT EXTENSION DRILL 135° SPLIT POINT STEAM OXIDE / Wire gauge sizes	#43	#1	245
RECOMMENDED CUTTING CONDITIONS					246

◎ : Excellent ○ : Good



P				H	M	K	N			S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	○				○	○	○	○	○		
◎	○				○	○	○	○	○		
◎	○				○	○	○	○	○		
◎	◎	○			○	○	○	○	○		○
◎	◎	○			○	○	○	○	○		○
◎	◎	○			○	○	○	○	○		○



DL601 SERIES
DL604 SERIES

HSSCo5, AIRCRAFT EXTENSION DRILL 135° SPLIT POINT COLORING

- ▶ **Flute Geometry** : Right hand spiral, 30° helix
- ▶ **Point Angle** : 135° : Split point
- ▶ **Application** : Improved chip removal in most materials, especially in deep drilling applications.



▶ Fractional sizes

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Fractional	Decimal				Fractional	Decimal		
	D1					D1			
* DL601005	5/64	.0781	1	6	** DL601029	29/64	.4531	4-3/16	6
* DL601006	3/32	.0938	1-1/4	6	** DL601030	15/32	.4688	4-5/16	6
* DL601007	7/64	.1094	1-1/2	6	** DL601031	31/64	.4844	4-3/8	6
* DL601008	1/8	.1250	1-5/8	6	** DL601032	1/2	.5000	4-1/2	6
* DL601009	9/64	.1406	1-3/4	6	** DL604014	7/32	.2188	2-1/2	12
* DL601010	5/32	.1563	2	6	** DL604015	15/64	.2344	2-5/8	12
* DL601011	11/64	.1719	2-1/8	6	** DL604016	1/4	.2500	2-3/4	12
* DL601012	3/16	.1875	2-5/16	6	** DL604017	17/64	.2656	2-7/8	12
* DL601013	13/64	.2031	2-7/16	6	** DL604018	9/32	.2813	2-15/16	12
* DL601014	7/32	.2188	2-1/2	6	** DL604019	19/64	.2969	3-1/16	12
* DL601015	15/64	.2344	2-5/8	6	** DL604020	5/16	.3125	3-3/16	12
** DL601016	1/4	.2500	2-3/4	6	** DL604021	21/64	.3281	3-5/16	12
** DL601017	17/64	.2656	2-7/8	6	** DL604022	11/32	.3438	3-7/16	12
** DL601018	9/32	.2813	2-15/16	6	** DL604023	23/64	.3594	3-1/2	12
** DL601019	19/64	.2969	3-1/16	6	** DL604024	3/8	.3750	3-5/8	12
** DL601020	5/16	.3125	3-3/16	6	** DL604025	25/64	.3906	3-3/4	12
** DL601021	21/64	.3281	3-5/16	6	** DL604026	13/32	.4063	3-7/8	12
** DL601022	11/32	.3438	3-7/16	6	** DL604027	27/64	.4219	3-15/16	12
** DL601023	23/64	.3594	3-1/2	6	** DL604028	7/16	.4375	4-1/16	12
** DL601024	3/8	.3750	3-5/8	6	** DL604029	29/64	.4531	4-3/16	12
** DL601025	25/64	.3906	3-3/4	6	** DL604030	15/32	.4688	4-5/16	12
** DL601026	13/32	.4063	3-7/8	6	** DL604031	31/64	.4844	4-3/8	12
** DL601027	27/64	.4219	3-15/16	6	** DL604032	1/2	.5000	4-1/2	12
** DL601028	7/16	.4375	4-1/16	6					

Tolerance Diameter (Inch)	
up to 1/8(.1250)	0 ~ -.0005
over 1/8(.1250) up to 1/4(.2500)	0 ~ -.0007
over 1/4(.2500) up to 1/2(.5000)	0 ~ -.0010

* 10pcs per package
** 5pcs per package

◎ : Excellent ○ : Good



P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55 HRc55~								
◎	○				○	○	○	○	○		



DL602 SERIES
DL605 SERIES

HSSCo5, AIRCRAFT EXTENSION DRILL 135° SPLIT POINT COLORING

- ▶ **Flute Geometry** : Right hand spiral, 30° helix
- ▶ **Point Angle** : 135° : Split point
- ▶ **Application** : Improved chip removal in most materials, especially in deep drilling applications.



▶ Letter sizes

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Letter	Decimal				Letter	Decimal		
	D1					D1			
* DL602101	A	.2340	2-5/8	6	* DL605101	A	.2340	2-5/8	12
** DL602102	B	.2380	2-3/4	6	** DL605102	B	.2380	2-3/4	12
** DL602103	C	.2420	2-3/4	6	** DL605103	C	.2420	2-3/4	12
** DL602104	D	.2460	2-3/4	6	** DL605104	D	.2460	2-3/4	12
** DL602105	E	.2500	2-3/4	6	** DL605105	E	.2500	2-3/4	12
** DL602106	F	.2570	2-7/8	6	** DL605106	F	.2570	2-7/8	12
** DL602107	G	.2610	2-7/8	6	** DL605107	G	.2610	2-7/8	12
** DL602108	H	.2660	2-7/8	6	** DL605108	H	.2660	2-7/8	12
** DL602109	I	.2720	2-7/8	6	** DL605109	I	.2720	2-7/8	12
** DL602110	J	.2770	2-7/8	6	** DL605110	J	.2770	2-7/8	12
** DL602111	K	.2810	2-15/16	6	** DL605111	K	.2810	2-15/16	12
** DL602112	L	.2900	2-15/16	6	** DL605112	L	.2900	2-15/16	12
** DL602113	M	.2950	3-1/16	6	** DL605113	M	.2950	3-1/16	12
** DL602114	N	.3020	3-1/16	6	** DL605114	N	.3020	3-1/16	12
** DL602115	O	.3160	3-3/16	6	** DL605115	O	.3160	3-3/16	12
** DL602116	P	.3230	3-5/16	6	** DL605116	P	.3230	3-5/16	12
** DL602117	Q	.3320	3-7/16	6	** DL605117	Q	.3320	3-7/16	12
** DL602118	R	.3390	3-7/16	6	** DL605118	R	.3390	3-7/16	12
** DL602119	S	.3480	3-1/2	6	** DL605119	S	.3480	3-1/2	12
** DL602120	T	.3580	3-1/2	6	** DL605120	T	.3580	3-1/2	12
** DL602121	U	.3680	3-5/8	6	** DL605121	U	.3680	3-5/8	12
** DL602122	V	.3770	3-5/8	6	** DL605122	V	.3770	3-5/8	12
** DL602123	W	.3860	3-3/4	6	** DL605123	W	.3860	3-3/4	12
** DL602124	X	.3970	3-3/4	6	** DL605124	X	.3970	3-3/4	12
** DL602125	Y	.4040	3-7/8	6	** DL605125	Y	.4040	3-7/8	12
** DL602126	Z	.4130	3-7/8	6	** DL605126	Z	.4130	3-7/8	12

▶ Tolerance : See page 240

* 10pcs per package
** 5pcs per package

◎ : Excellent ○ : Good



P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55 HRc55~								
◎	○				○	○	○	○	○		



DL603 SERIES
DL606 SERIES

HSSCo5, AIRCRAFT EXTENSION DRILL 135° SPLIT POINT COLORING

- ▶ **Flute Geometry** : Right hand spiral, parabolic flute
30° helix
- ▶ **Point Angle** : 135° : Split point
- ▶ **Application** : Improved chip removal in most materials, especially in deep drilling applications.



Wire gauge sizes

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Wire gauge	Decimal				Wire gauge	Decimal		
	D1					D1			
* DL603256	1	.2280	2-5/8	6	* DL603233	24	.1520	2	6
* DL603255	2	.2210	2-5/8	6	* DL603232	25	.1495	1-7/8	6
* DL603254	3	.2130	2-1/2	6	* DL603231	26	.1470	1-7/8	6
* DL603253	4	.2090	2-1/2	6	* DL603230	27	.1440	1-7/8	6
* DL603252	5	.2055	2-1/2	6	* DL603229	28	.1405	1-3/4	6
* DL603251	6	.2040	2-1/2	6	* DL603228	29	.1360	1-3/4	6
* DL603250	7	.2010	2-7/16	6	* DL603227	30	.1280	1-5/8	6
* DL603249	8	.1990	2-7/16	6	* DL603226	31	.1200	1-5/8	6
* DL603248	9	.1960	2-7/16	6	* DL603225	32	.1160	1-5/8	6
* DL603247	10	.1935	2-7/16	6	* DL603224	33	.1130	1-1/2	6
* DL603246	11	.1910	2-5/16	6	* DL603223	34	.1110	1-1/2	6
* DL603245	12	.1890	2-5/16	6	* DL603222	35	.1100	1-1/2	6
* DL603244	13	.1850	2-5/16	6	* DL603221	36	.1065	1-7/16	6
* DL603243	14	.1820	2-3/16	6	* DL603220	37	.1040	1-7/16	6
* DL603242	15	.1800	2-3/16	6	* DL603219	38	.1015	1-7/16	6
* DL603241	16	.1770	2-3/16	6	* DL603218	39	.0995	1-3/8	6
* DL603240	17	.1730	2-3/16	6	* DL603217	40	.0980	1-3/8	6
* DL603239	18	.1695	2-1/8	6	* DL603216	41	.0960	1-3/8	6
* DL603238	19	.1660	2-1/8	6	* DL603215	42	.0935	1-1/4	6
* DL603237	20	.1610	2-1/8	6	* DL603214	43	.0890	1-1/4	6
* DL603236	21	.1590	2-1/8	6	* DL606256	1	.2280	2-5/8	12
* DL603235	22	.1570	2	6	* DL606254	3	.2130	2-1/2	12
* DL603234	23	.1540	2	6					

* 10pcs per package

Tolerance Diameter (Inch)	
up to 1/8(.1250)	0 ~ -.0005
over 1/8(.1250) up to 1/4(.2500)	0 ~ -.0007
over 1/4(.2500) up to 1/2(.5000)	0 ~ -.0010

◎ : Excellent ○ : Good



P		H	M	K	N				S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~							
◎	○			○	○	○	○	○		○



D1631 SERIES
D1634 SERIES

HSS, AIRCRAFT EXTENSION DRILL 135° SPLIT POINT STEAM OXIDE

- ▶ **Flute Geometry** : Right hand spiral, 30° helix
- ▶ **Point Angle** : 135° : Split point
- ▶ **Application** : Improved chip removal in most materials, especially in deep drilling applications.



Fractional sizes

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Fractional	Decimal				Fractional	Decimal		
	D1					D1			
* D1631005	5/64	.0781	1	6	** D1631029	29/64	.4531	4-3/16	6
* D1631006	3/32	.0938	1-1/4	6	** D1631030	15/32	.4688	4-5/16	6
* D1631007	7/64	.1094	1-1/2	6	** D1631031	31/64	.4844	4-3/8	6
* D1631008	1/8	.1250	1-5/8	6	** D1631032	1/2	.5000	4-1/2	6
* D1631009	9/64	.1406	1-3/4	6	* D1634014	7/32	.2188	2-1/2	12
* D1631010	5/32	.1563	2	6	* D1634015	15/64	.2344	2-5/8	12
* D1631011	11/64	.1719	2-1/8	6	** D1634016	1/4	.2500	2-3/4	12
* D1631012	3/16	.1875	2-5/16	6	** D1634017	17/64	.2656	2-7/8	12
* D1631013	13/64	.2031	2-7/16	6	** D1634018	9/32	.2813	2-15/16	12
* D1631014	7/32	.2188	2-1/2	6	** D1634019	19/64	.2969	3-1/16	12
* D1631015	15/64	.2344	2-5/8	6	** D1634020	5/16	.3125	3-3/16	12
** D1631016	1/4	.2500	2-3/4	6	** D1634021	21/64	.3281	3-5/16	12
** D1631017	17/64	.2656	2-7/8	6	** D1634022	11/32	.3438	3-7/16	12
** D1631018	9/32	.2813	2-15/16	6	** D1634023	23/64	.3594	3-1/2	12
** D1631019	19/64	.2969	3-1/16	6	** D1634024	3/8	.3750	3-5/8	12
** D1631020	5/16	.3125	3-3/16	6	** D1634025	25/64	.3906	3-3/4	12
** D1631021	21/64	.3281	3-5/16	6	** D1634026	13/32	.4063	3-7/8	12
** D1631022	11/32	.3438	3-7/16	6	** D1634027	27/64	.4219	3-15/16	12
** D1631023	23/64	.3594	3-1/2	6	** D1634028	7/16	.4375	4-1/16	12
** D1631024	3/8	.3750	3-5/8	6	** D1634029	29/64	.4531	4-3/16	12
** D1631025	25/64	.3906	3-3/4	6	** D1634030	15/32	.4688	4-5/16	12
** D1631026	13/32	.4063	3-7/8	6	** D1634031	31/64	.4844	4-3/8	12
** D1631027	27/64	.4219	3-15/16	6	** D1634032	1/2	.5000	4-1/2	12
** D1631028	7/16	.4375	4-1/16	6					

* 10pcs per package
** 5pcs per package

Tolerance Diameter (Inch)	
up to 1/8(.1250)	0 ~ -.0005
over 1/8(.1250) up to 1/4(.2500)	0 ~ -.0007
over 1/4(.2500) up to 1/2(.5000)	0 ~ -.0010

◎ : Excellent ○ : Good



P		H	M	K	N				S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~							
◎	◎	○		○	○	○	○	○		○



D1632 SERIES
D1635 SERIES

HSS, AIRCRAFT EXTENSION DRILL 135° SPLIT POINT STEAM OXIDE

- ▶ Flute Geometry : Right hand spiral, 30° helix
- ▶ Point Angle : 135° : Split point
- ▶ Application : Improved chip removal in most materials, especially in deep drilling applications.



▶ Letter sizes

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Letter	Decimal				Letter	Decimal		
	D1					D1			
* D1632101	A	.2340	2-5/8	6	* D1635101	A	.2340	2-5/8	12
** D1632102	B	.2380	2-3/4	6	** D1635102	B	.2380	2-3/4	12
** D1632103	C	.2420	2-3/4	6	** D1635103	C	.2420	2-3/4	12
** D1632104	D	.2460	2-3/4	6	** D1635104	D	.2460	2-3/4	12
** D1632105	E	.2500	2-3/4	6	** D1635105	E	.2500	2-3/4	12
** D1632106	F	.2570	2-7/8	6	** D1635106	F	.2570	2-7/8	12
** D1632107	G	.2610	2-7/8	6	** D1635107	G	.2610	2-7/8	12
** D1632108	H	.2660	2-7/8	6	** D1635108	H	.2660	2-7/8	12
** D1632109	I	.2720	2-7/8	6	** D1635109	I	.2720	2-7/8	12
** D1632110	J	.2770	2-7/8	6	** D1635110	J	.2770	2-7/8	12
** D1632111	K	.2810	2-15/16	6	** D1635111	K	.2810	2-15/16	12
** D1632112	L	.2900	2-15/16	6	** D1635112	L	.2900	2-15/16	12
** D1632113	M	.2950	3-1/16	6	** D1635113	M	.2950	3-1/16	12
** D1632114	N	.3020	3-1/16	6	** D1635114	N	.3020	3-1/16	12
** D1632115	O	.3160	3-3/16	6	** D1635115	O	.3160	3-3/16	12
** D1632116	P	.3230	3-5/16	6	** D1635116	P	.3230	3-5/16	12
** D1632117	Q	.3320	3-7/16	6	** D1635117	Q	.3320	3-7/16	12
** D1632118	R	.3390	3-7/16	6	** D1635118	R	.3390	3-7/16	12
** D1632119	S	.3480	3-1/2	6	** D1635119	S	.3480	3-1/2	12
** D1632120	T	.3580	3-1/2	6	** D1635120	T	.3580	3-1/2	12
** D1632121	U	.3680	3-5/8	6	** D1635121	U	.3680	3-5/8	12
** D1632122	V	.3770	3-5/8	6	** D1635122	V	.3770	3-5/8	12
** D1632123	W	.3860	3-3/4	6	** D1635123	W	.3860	3-3/4	12
** D1632124	X	.3970	3-3/4	6	** D1635124	X	.3970	3-3/4	12
** D1632125	Y	.4040	3-7/8	6	** D1635125	Y	.4040	3-7/8	12
** D1632126	Z	.4130	3-7/8	6	** D1635126	Z	.4130	3-7/8	12

▶ Tolerance : See page 240

* 10pcs per package
** 5pcs per package

◎ : Excellent ○ : Good



P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRc30~45	HRc45~55 HRc55~								
◎	◎	○		○	○	○	○	○	○	○	



D1633 SERIES
D1636 SERIES

HSS, AIRCRAFT EXTENSION DRILL 135° SPLIT POINT STEAM OXIDE

- ▶ Flute Geometry : Right hand spiral, 30° helix
- ▶ Point Angle : 135° : Split point
- ▶ Application : Improved chip removal in most materials, especially in deep drilling applications.



▶ Wire gauge sizes

EDP No.	Diameter		Flute Length L1	Overall Length L2	EDP No.	Diameter		Flute Length L1	Overall Length L2
	Wire gauge	Decimal				Wire gauge	Decimal		
	D1					D1			
* D1633256	1	.2280	2-5/8	6	* D1633233	24	.1520	2	6
* D1633255	2	.2210	2-5/8	6	* D1633232	25	.1495	1-7/8	6
* D1633254	3	.2130	2-1/2	6	* D1633231	26	.1470	1-7/8	6
* D1633253	4	.2090	2-1/2	6	* D1633230	27	.1440	1-7/8	6
* D1633252	5	.2055	2-1/2	6	* D1633229	28	.1405	1-3/4	6
* D1633251	6	.2040	2-1/2	6	* D1633228	29	.1360	1-3/4	6
* D1633250	7	.2010	2-7/16	6	* D1633227	30	.1280	1-5/8	6
* D1633249	8	.1990	2-7/16	6	* D1633226	31	.1200	1-5/8	6
* D1633248	9	.1960	2-7/16	6	* D1633225	32	.1160	1-5/8	6
* D1633247	10	.1935	2-7/16	6	* D1633224	33	.1130	1-1/2	6
* D1633246	11	.1910	2-5/16	6	* D1633223	34	.1110	1-1/2	6
* D1633245	12	.1890	2-5/16	6	* D1633222	35	.1100	1-1/2	6
* D1633244	13	.1850	2-5/16	6	* D1633221	36	.1065	1-7/16	6
* D1633243	14	.1820	2-3/16	6	* D1633220	37	.1040	1-7/16	6
* D1633242	15	.1800	2-3/16	6	* D1633219	38	.1015	1-7/16	6
* D1633241	16	.1770	2-3/16	6	* D1633218	39	.0995	1-3/8	6
* D1633240	17	.1730	2-3/16	6	* D1633217	40	.0980	1-3/8	6
* D1633239	18	.1695	2-1/8	6	* D1633216	41	.0960	1-3/8	6
* D1633238	19	.1660	2-1/8	6	* D1633215	42	.0935	1-1/4	6
* D1633237	20	.1610	2-1/8	6	* D1633214	43	.0890	1-1/4	6
* D1633236	21	.1590	2-1/8	6	* D1636256	1	.2280	2-5/8	12
* D1633235	22	.1570	2	6	* D1636254	3	.2130	2-1/2	12
* D1633234	23	.1540	2	6					

* 10pcs per package

Tolerance Diameter (Inch)	
up to 1/8(.1250)	0 ~ -.0005
over 1/8(.1250) up to 1/4(.2500)	0 ~ -.0007
over 1/4(.2500) up to 1/2(.5000)	0 ~ -.0010

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium	
~HB225	HB225~325	HRc30~45	HRc45~55 HRc55~								
◎	◎	○		○	○	○	○	○	○	○	

HSS & HSSCo5, AIRCRAFT EXTENSION DRILL 135° SPLIT POINT

DL601, DL602, DL603, D1631, D1632, D1633 SERIES

WORK MATERIAL	P									
	CARBON STEELS		CARBON STEELS		CARBON STEELS		ALLOY STEELS		ALLOY STEELS	
	~ 570 N/mm ²		~ 830 N/mm ²		830 ~ 950 N/mm ²		830 ~ 1110 N/mm ²		1110 ~ 1260 N/mm ²	
HARDNESS	~ HRc23				~ HRc23 ~ 28		HRc23 ~ 34		HRc34 ~ 38	
STRENGTH	~ 570 N/mm ²				~ 830 N/mm ²		830 ~ 950 N/mm ²		1110 ~ 1260 N/mm ²	
DIAMETER	N	S	N	S	N	S	N	S	N	S
~ 3/32	3380	.0010	2550	.0010	1900	.0006	2380	.0008	1400	.0006
3/32 ~ 5/32	2700	.0020	2000	.0020	1500	.0010	1880	.0020	1100	.0008
11/64 ~ 1/4	1700	.0025	1280	.0025	960	.0015	1190	.0025	700	.0010
17/64 ~ 23/64	1050	.0051	780	.0051	590	.0030	730	.0051	430	.0015
3/8 ~ 37/64	750	.0059	560	.0060	425	.0030	520	.0070	310	.0020
19/32 ~ 1	440	.0090	330	.0090	255	.0051	300	.0090	180	.0020
1 ~	260	.0110	195	.0110	145	.0070	180	.0070	107	.0030

WORK MATERIAL	P		M		K		N			
	TOOL STEELS		STAINLESS STEELS		CAST IRON		ALUMINUM ALLOYS		MAGNESIUM ALLOYS	
	~ 270 N/mm ²		830 N/mm ²		~ 800 N/mm ²					
HARDNESS	HRc23				~ HRc21					
STRENGTH	~ 270 N/mm ²				~ 800 N/mm ²					
DIAMETER	N	S	N	S	N	S	N	S	N	S
~ 3/32	3180	.0016	2550	.0010	2250	.0010	6400	.0015	8600	.0015
3/32 ~ 5/32	2500	.0020	2000	.0020	2000	.0020	5000	.0025	6800	.0025
11/64 ~ 1/4	1590	.0025	1280	.0025	1280	.0025	3200	.0030	4300	.0030
17/64 ~ 23/64	970	.0051	780	.0051	780	.0051	2000	.0070	2600	.0070
3/8 ~ 37/64	700	.0070	560	.0060	560	.0060	1400	.0078	1900	.0078
19/32 ~ 1	440	.0090	330	.0090	330	.0090	820	.0118	1100	.0118
1 ~	240	.1180	195	.0110	195	.0110	490	.0150	660	.0150

WORK MATERIAL	N				S	
	ZINC ALLOYS		PLASTIC		TITANIUM ALLOYS	
	410 N/mm ²					
HARDNESS						
STRENGTH	410 N/mm ²					
DIAMETER	N	S	N	S	N	S
~ 3/32	6400	.0015	3380	.0010	1400	.0008
3/32 ~ 5/32	5000	.0025	2700	.0020	1100	.0010
11/64 ~ 1/4	3200	.0030	1700	.0025	700	.0015
17/64 ~ 23/64	2000	.0070	1050	.0051	430	.0030
3/8 ~ 37/64	1400	.0078	750	.0060	430	.0030
19/32 ~ 1	820	.0118	440	.0090	180	.0051
1 ~	490	.0150	260	.0110	107	.0070

N = R.P.M
S = Inch per Revolution (inch/rev.)



Being the best through innovation

HSS



SILVER & DEMING DRILLS

- 118° Split Point
- 3 Flats Black and Gold


- i-DREAM DRILLS
- DREAM DRILLS -GENERAL
- DREAM DRILLS -HIGH FEED
- DREAM DRILLS -FLAT BOTTOM
- DREAM DRILLS -INOX
- DREAM DRILLS -ALU
- DREAM DRILLS -MQL TYPE
- DREAM DRILLS for HIGH HARDENED STEELS
- STANDARD CARBIDE DRILLS
- MULTI-1 DRILLS
- HPD DRILLS
- GOLD-P DRILLS
- STRAIGHT SHANK DRILLS
- AIRCRAFT DRILLS
- SILVER & DEMING DRILLS
- TAPER SHANK DRILLS
- NC SPOTTING DRILLS
- COMBINATION DRILLS & COUNTERSINK
- SPADE DRILLS
- TECHNICAL DATA

SELECTION GUIDE

HSS SILVER & DEMING DRILLS

HSS SILVER & DEMING DRILLS

- 118° Split Point
- 3 Flat Black and Gold

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
INCH					
D1191		HSS(M2), 118° SPLIT POINT 3FLAT BLACK&GOLD SILVER & DEMING DRILLS	D1/2	D1-1/2	250
		RECOMMENDED CUTTING CONDITIONS			251


◎ : Excellent ○ : Good

P			H	M	K	N			S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	◎				○	○	○				



D1191 SERIES

HSS(M2), 118° SPLIT POINT 3FLAT BLACK & GOLD SILVER & DEMING DRILLS



Unit : Inch											
EDP No.	Diameter		Shank Diameter	Flute Length	Overall Length	EDP No.	Diameter		Shank Diameter	Flute Length	Overall Length
	D1	D2					L1	L2			
D1191032	1/2	1/2	1/2	3	6	D1191061	61/64	1/2	1/2	3	6
D1191033	33/64	1/2	1/2	3	6	D1191062	31/32	1/2	1/2	3	6
D1191034	17/32	1/2	1/2	3	6	D1191063	63/64	1/2	1/2	3	6
D1191035	35/64	1/2	1/2	3	6	D1191064	1	1/2	1/2	3	6
D1191036	9/16	1/2	1/2	3	6	D1191101	1-1/64	1/2	1/2	3	6
D1191037	37/64	1/2	1/2	3	6	D1191102	1-1/32	1/2	1/2	3	6
D1191038	19/32	1/2	1/2	3	6	D1191103	1-3/64	1/2	1/2	3	6
D1191039	39/64	1/2	1/2	3	6	D1191104	1-1/16	1/2	1/2	3	6
D1191040	5/8	1/2	1/2	3	6	D1191105	1-5/64	1/2	1/2	3	6
D1191041	41/64	1/2	1/2	3	6	D1191106	1-3/32	1/2	1/2	3	6
D1191042	21/32	1/2	1/2	3	6	D1191107	1-7/64	1/2	1/2	3	6
D1191043	43/64	1/2	1/2	3	6	D1191108	1-1/8	1/2	1/2	3	6
D1191044	11/16	1/2	1/2	3	6	D1191109	1-9/64	1/2	1/2	3	6
D1191045	45/64	1/2	1/2	3	6	D1191110	1-5/32	1/2	1/2	3	6
D1191046	23/32	1/2	1/2	3	6	D1191111	1-11/64	1/2	1/2	3	6
D1191047	47/64	1/2	1/2	3	6	D1191112	1-3/16	1/2	1/2	3	6
D1191048	3/4	1/2	1/2	3	6	D1191113	1-13/64	1/2	1/2	3	6
D1191049	49/64	1/2	1/2	3	6	D1191114	1-7/32	1/2	1/2	3	6
D1191050	25/32	1/2	1/2	3	6	D1191115	1-15/64	1/2	1/2	3	6
D1191051	51/64	1/2	1/2	3	6	D1191116	1-1/4	1/2	1/2	3	6
D1191052	13/16	1/2	1/2	3	6	D1191118	1-9/32	1/2	1/2	3	6
D1191053	53/64	1/2	1/2	3	6	D1191120	1-5/16	1/2	1/2	3	6
D1191054	27/32	1/2	1/2	3	6	D1191122	1-11/32	1/2	1/2	3	6
D1191055	55/64	1/2	1/2	3	6	D1191124	1-3/8	1/2	1/2	3	6
D1191056	7/8	1/2	1/2	3	6	D1191126	1-13/32	1/2	1/2	3	6
D1191057	57/64	1/2	1/2	3	6	D1191128	1-7/16	1/2	1/2	3	6
D1191058	29/32	1/2	1/2	3	6	D1191130	1-15/32	1/2	1/2	3	6
D1191059	59/64	1/2	1/2	3	6	D1191132	1-1/2	1/2	1/2	3	6
D1191060	15/16	1/2	1/2	3	6						

* Individually packaged

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55 HRC55~								
◎	◎				○	○	○				



RECOMMENDED CUTTING CONDITIONS

HSS(M2), 118° SPLIT POINT 3FLAT BLACK & GOLD SILVER & DEMING DRILLS

D1191 SERIES

WORK MATERIAL	P											
	CARBON STEELS		CARBON STEELS		CARBON STEELS		ALLOY STEELS		ALLOY STEELS		TOOL STEELS	
HARDNESS			~ HRC23		~ HRC23 ~ 28		HRC23 ~ 34		HRC34 ~ 38			
STRENGTH	~ 570 N/mm ²		~ 830 N/mm ²		830 ~ 950 N/mm ²		830 ~ 1110 N/mm ²		1110 ~ 1260 N/mm ²		~ 270 N/mm ²	
DIAMETER	N	S	N	S	N	S	N	S	N	S	N	S
1/2	645	.0067	480	.0067	370	.0035	440	.0067	265	.0020	645	.0067
3/4	440	.0091	330	.0091	255	.0051	300	.0091	180	.0020	440	.0091
1	325	.0110	245	.0110	185	.0063	220	.0110	133	.0030	325	.0110
1-9/32	260	.0110	195	.0110	145	.0071	180	.0110	107	.0030	240	.0118
1-1/2	220	.0130	165	.0130	120	.0076	150	.0130	90	.0030	198	.0121

WORK MATERIAL	M				N							
	STAINLESS STEELS		CAST IRON		ALUMINUM ALLOYS		MAGNESIUM ALLOYS		ZINC ALLOYS		PLASTIC	
HARDNESS	HRc23		~ HRc21									
STRENGTH	830 N/mm ²		~ 800 N/mm ²									
DIAMETER	N	S	N	S	N	S	N	S	N	S	N	S
1/2	480	.0067	480	.0067	1200	.0100	1600	.0100	1200	.0100	645	.0067
3/4	330	.0091	330	.0091	820	.0118	1100	.0118	820	.0118	440	.0091
1	245	.0110	245	.0110	605	.0146	810	.0150	605	.0146	325	.0110
1-9/32	195	.0110	195	.0110	490	.0150	660	.0150	490	.0150	260	.0110
1-1/2	165	.0130	165	.0130	410	.0172	550	.0180	410	.0172	220	.0130

N = R.P.M
S = Inch per Revolution(inch/rev.)

i-DREAM DRILLS
DREAM DRILLS -GENERAL
DREAM DRILLS -HIGH FEED
DREAM DRILLS -FLAT BOTTOM
DREAM DRILLS -INOX
DREAM DRILLS -ALU
DREAM DRILLS -MQL TYPE
DREAM DRILLS for HIGH HARDENED STEELS
STANDARD CARBIDE DRILLS
MULTI-1 DRILLS
HPD DRILLS
GOLD-P DRILLS
STRAIGHT SHANK DRILLS
AIRCRAFT DRILLS
SILVER & DEMING DRILLS
TAPER SHANK DRILLS
NC SPOTTING DRILLS
COMBINATION DRILLS & COUNTERSINK
SPADE DRILLS
TECHNICAL DATA

i-DREAM DRILLS
DREAM DRILLS -GENERAL
DREAM DRILLS -HIGH FEED
DREAM DRILLS -FLAT BOTTOM
DREAM DRILLS -INOX
DREAM DRILLS -ALU
DREAM DRILLS -MQL TYPE
DREAM DRILLS for HIGH HARDENED STEELS
STANDARD CARBIDE DRILLS
MULTI-1 DRILLS
HPD DRILLS
GOLD-P DRILLS
STRAIGHT SHANK DRILLS
AIRCRAFT DRILLS
SILVER & DEMING DRILLS
TAPER SHANK DRILLS
NC SPOTTING DRILLS
COMBINATION DRILLS & COUNTERSINK
SPADE DRILLS
TECHNICAL DATA




Being the best through innovation

HSS



Global Cutting Tool Leader **YG-1**



MORSE TAPER SHANK DRILLS

- General Purpose
- Standard Length

SELECTION GUIDE

HSS MORSE TAPER SHANK DRILLS

HSS MORSE TAPER SHANK DRILLS

- General Purpose
- Standard Length

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
INCH					
D1211		HSS(M2), MORSE TAPER SHANK TWIST DRILL	D1/2	D2-1/2	256
RECOMMENDED CUTTING CONDITIONS					258

◎ : Excellent ○ : Good


P			H	M	K	N			S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	◎	○			○	○	○				

YG MORSE TAPER SHANK DRILLS

D1211 SERIES

HSS(M2) MORSE TAPER SHANK TWIST DRILL

► **Surface treatment** : Steam Tempered(Black Oxide Finish)
 ► **Application** : Drilling steels, cast steels alloyed and non-alloyed, grey cast iron, malleable cast iron, graphite.



ANSI HSS 30~35° 2~5 h8 118° P.258

Unit : Inch

EDP No.	Diameter	Flute Length	Overall Length	Morse Taper No.	EDP No.	Diameter	Flute Length	Overall Length	Morse Taper No.
	D ₁	L ₁	L ₂			D ₁	L ₁	L ₂	
D1211032	1/2	4-3/8	8-1/4	2	D1211061	61/64	6-3/8	11	3
D1211033	33/64	4-5/8	8-1/2	2	D1211062	31/32	6-3/8	11	3
D1211034	17/32	4-5/8	8-1/2	2	D1211063	63/64	6-3/8	11	3
D1211035	35/64	4-7/8	8-3/4	2	D1211100	1	6-3/8	11	3
D1211036	9/16	4-7/8	8-3/4	2	D1211101	1-1/64	6-1/2	11-1/8	3
D1211037	37/64	4-7/8	8-3/4	2	D1211102	1-1/32	6-1/2	11-1/8	3
D1211038	19/32	4-7/8	8-3/4	2	D1211103	1-3/64	6-5/8	11-1/4	3
D1211039	39/64	4-7/8	8-3/4	2	D1211104	1-1/16	6-5/8	11-1/4	3
D1211040	5/8	4-7/8	8-3/4	2	D1211105	1-5/64	6-7/8	12-1/2	4
D1211041	41/64	5-1/8	9	2	D1211106	1-3/32	6-7/8	12-1/2	4
D1211042	21/32	5-1/8	9	2	D1211107	1-7/64	7-1/8	12-3/4	4
D1211043	43/64	5-3/8	9-1/4	2	D1211108	1-1/8	7-1/8	12-3/4	4
D1211044	11/16	5-3/8	9-1/4	2	D1211109	1-9/64	7-1/4	12-7/8	4
D1211045	45/64	5-5/8	9-1/2	2	D1211110	1-5/32	7-1/4	12-7/8	4
D1211046	23/32	5-5/8	9-1/2	2	D1211111	1-11/64	7-3/8	13	4
D1211047	47/64	5-7/8	9-3/4	2	D1211112	1-3/16	7-3/8	13	4
D1211048	3/4	5-7/8	9-3/4	2	D1211113	1-13/64	7-1/2	13-1/8	4
D1211049	49/64	6	9-7/8	2	D1211114	1-7/32	7-1/2	13-1/8	4
D1211050	25/32	6	9-7/8	2	D1211115	1-15/64	7-7/8	13-1/2	4
D1211051	51/64	6-1/8	10-3/4	3	D1211116	1-1/4	7-7/8	13-1/2	4
D1211052	13/16	6-1/8	10-3/4	3	D1211117	1-17/64	8-1/2	14-1/8	4
D1211053	53/64	6-1/8	10-3/4	3	D1211118	1-9/32	8-1/2	14-1/8	4
D1211054	27/32	6-1/8	10-3/4	3	D1211119	1-19/64	8-5/8	14-1/4	4
D1211055	55/64	6-1/8	10-3/4	3	D1211120	1-5/16	8-5/8	14-1/4	4
D1211056	7/8	6-1/8	10-3/4	3	D1211121	1-21/64	8-3/4	14-3/8	4
D1211057	57/64	6-1/8	10-3/4	3	D1211122	1-11/32	8-3/4	14-3/8	4
D1211058	29/32	6-1/8	10-3/4	3	D1211123	1-23/64	8-7/8	14-1/2	4
D1211059	59/64	6-1/8	10-3/4	3	D1211124	1-3/8	8-7/8	14-1/2	4
D1211060	15/16	6-1/8	10-3/4	3	D1211126	1-13/32	9	14-5/8	4

◎ : Excellent ○ : Good


P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			○	○	○				

YG MORSE TAPER SHANK DRILLS

D1211 SERIES

HSS(M2) MORSE TAPER SHANK TWIST DRILL

► **Surface treatment** : Steam Tempered(Black Oxide Finish)
 ► **Application** : Drilling steels, cast steels alloyed and non-alloyed, grey cast iron, malleable cast iron, graphite.



ANSI HSS 30~35° 2~5 h8 118° P.258

Unit : Inch

EDP No.	Diameter	Flute Length	Overall Length	Morse Taper No.	EDP No.	Diameter	Flute Length	Overall Length	Morse Taper No.
	D ₁	L ₁	L ₂			D ₁	L ₁	L ₂	
D1211128	1-7/16	9-1/8	14-3/4	4	D1211160	1-15/16	10-3/8	17-3/8	5
D1211130	1-15/32	9-1/4	14-7/8	4	D1211162	1-31/32	10-3/8	17-3/8	5
D1211132	1-1/2	9-3/8	15	4	D1211200	2	10-3/8	17-3/8	5
D1211133	1-33/64	9-3/8	16-3/8	4	D1211202	2-1/32	10-3/8	17-3/8	5
D1211134	1-17/32	9-3/8	16-3/8	5	D1211204	2-1/16	10-1/4	17-3/8	5
D1211136	1-9/16	9-5/8	16-5/8	5	D1211206	2-3/32	10-1/4	17-3/8	5
D1211138	1-19/32	9-7/8	16-7/8	5	D1211208	2-1/8	10-1/4	17-3/8	5
D1211140	1-5/8	10	17	5	D1211210	2-5/32	10-1/4	17-3/8	5
D1211142	1-21/32	10-1/8	17-1/8	5	D1211212	2-3/16	10-1/4	17-3/8	5
D1211144	1-11/16	10-1/8	17-1/8	5	D1211214	2-7/32	10-1/8	17-3/8	5
D1211146	1-23/32	10-1/8	17-1/8	5	D1211216	2-1/4	10-1/8	17-3/8	5
D1211148	1-3/4	10-1/8	17-1/8	5	D1211220	2-5/16	10-1/8	17-3/8	5
D1211152	1-13/16	10-1/8	17-1/8	5	D1211224	2-3/8	10-1/8	17-3/8	5
D1211154	1-27/32	10-1/8	17-1/8	5	D1211228	2-7/16	11-1/4	18-3/4	5
D1211156	1-7/8	10-3/8	17-3/8	5	D1211232	2-1/2	11-1/4	18-3/4	5

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRC30~45	HRC45~55	HRC55~							
◎	◎	○			○	○	○				

Y/G MORSE TAPER SHANK DRILLS

RECOMMENDED CUTTING CONDITIONS

HSS(M2) MORSE TAPER SHANK TWIST DRILL

D1211 SERIES

WORK MATERIAL	P											
	CARBON STEELS		CARBON STEELS		CARBON STEELS		ALLOY STEELS		ALLOY STEELS		TOOL STEELS	
HARDNESS			~ HRC23		~ HRC23 ~ 28		HRC23 ~ 34		HRC34 ~ 38			
STRENGTH	~ 570 N/mm ²		~ 830 N/mm ²		830 ~ 950 N/mm ²		830 ~ 1110 N/mm ²		1110 ~ 1260 N/mm ²		~ 270 N/mm ²	
DIAMETER	N	S	N	S	N	S	N	S	N	S	N	S
1/2	645	.0067	480	.0067	370	.0035	440	.0067	265	.0020	645	.0067
3/4	440	.0091	330	.0091	255	.0051	300	.0091	180	.0020	440	.0091
1	325	.0110	245	.0110	185	.0063	220	.0110	133	.0030	325	.0110
1-17/64	260	.0110	195	.0110	145	.0071	180	.0110	107	.0030	240	.0118
1-1/2	220	.0130	165	.0130	120	.0076	150	.0130	90	.0030	198	.0121
1-31/32	165	.0130	125	.0130	93	.0079	115	.0130	68	.0030	150	.0169
2-3/8	140	.0157	105	.0157	78	.0091	95	.0157	57	.0039	125	.0188

WORK MATERIAL	M		K		N							
	STAINLESS STEELS		CAST IRON		ALUMINUM ALLOYS		MAGNESIUM ALLOYS		ZINC ALLOYS		PLASTIC	
HARDNESS	HRC23		~ HRC21									
STRENGTH	830 N/mm ²		~ 800 N/mm ²									
DIAMETER	N	S	N	S	N	S	N	S	N	S	N	S
1/2	480	.0067	480	.0067	1200	.0100	1600	.0100	1200	.0100	645	.0067
3/4	330	.0091	330	.0091	820	.0118	1100	.0118	820	.0118	440	.0091
1	245	.0110	245	.0110	605	.0146	810	.0150	605	.0146	325	.0110
1-17/64	195	.0110	195	.0110	490	.0150	660	.0150	490	.0150	260	.0110
1-1/2	165	.0130	165	.0130	410	.0172	550	.0180	410	.0172	220	.0130
1-31/32	125	.0130	125	.0130	310	.0181	415	.0181	310	.0181	165	.0130
2-3/8	105	.0157	105	.0157	260	.0196	345	.0196	260	.0196	140	.0157

N = R.P.M
S = Inch per Revolution (inch/rev.)



Being the best through innovation



HSS



NC SPOTTING DRILLS

- HSS(8% COBALT)
- Centering and Chamfering of Holes

HSS(8% Cobalt) NC SPOTTING DRILLS - Centering and Chamfering of Holes


ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
INCH					
D2N90		HSSCo8, NC SPOTTING DRILLS 90°	D1/8	D1	262
		HSSCo8, NC SPOTTING DRILLS 120°	D1/8	D1	262
	RECOMMENDED CUTTING CONDITIONS				263

◎ : Excellent ○ : Good

P				H	M	K	N			S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	◎				○		○		○		
◎	◎				○		○		○		

HSSCo8, NC SPOTTING DRILLS

► **Application** : For more precise centering work on NC/CNC machine. A larger diameter in respect to the subsequent drilling tool permit to obtain the centering and chamfering simultaneously.



NC Spotting drills 90°

NC Spotting drills 120°

Unit : Inch

EDP No.	Diameter	Flute Length	Overall Length	EDP No.	Diameter	Flute Length	Overall Length
	D1	L1	L2		D1	L1	L2
0081L	1/8	.472	1.93	2081L	1/8	.472	1.93
0121L	3/16	.590	2.44	2121L	3/16	.590	2.44
0161L	1/4	.669	2.76	2161L	1/4	.669	2.76
0201L	5/16	.984	3.11	2201L	5/16	.984	3.11
0241L	3/8	.827	3.50	2241L	3/8	.827	3.50
0321L	1/2	.984	4.02	2321L	1/2	.984	4.02
0401L	5/8	1.575	4.53	2401L	5/8	1.575	4.53
0481L	3/4	1.968	5.16	2481L	3/4	1.968	5.16
0641L	1	1.968	6.14	2641L	1	1.968	6.14

* Individually packaged

◎ : Excellent ○ : Good

P				H	M	K	N				S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	◎				○		○		○		

HSSCo8, NC SPOTTING DRILLS

D2N90 SERIES

WORK MATERIAL	P				M		N			
	CARBON STEELS		ALLOY STEELS		ALLOY STEELS, TOOL STEELS, HARDENED STEELS		STAINLESS STEELS		ALUMINUM, ALUMINUM ALLOYS	
DIAMETER	N	S	N	S	N	S	N	S	N	S
1/8 ~ 5/32	2460	.002	2110	.002	1080	.002	940	.002	7040	.005
11/64 ~ 3/16	1850	.002	1580	.002	800	.002	700	.002	5280	.006
13/64 ~ 15/64	1510	.003	1300	.003	670	.003	580	.003	4400	.006
1/4 ~ 5/16	1170	.003	1030	.003	540	.003	460	.003	3520	.007
21/64 ~ 25/64	880	.004	790	.004	400	.004	350	.004	2640	.008
13/32 ~ 15/32	700	.004	630	.004	320	.004	290	.004	2110	.009
31/64 ~ 5/8	590	.005	530	.005	260	.005	240	.005	1760	.011
41/64 ~ 47/64	460	.007	400	.007	200	.007	180	.007	1320	.012
3/4 ~ 1	350	.009	320	.009	150	.009	140	.009	1060	.017

N = R.P.M
S = Inch per Revolution (inch/rev.)

- i-DREAM DRILLS
- DREAM DRILLS -GENERAL
- DREAM DRILLS -HIGH FEED
- DREAM DRILLS -FLAT BOTTOM
- DREAM DRILLS -INOX
- DREAM DRILLS -ALU
- DREAM DRILLS -MQL TYPE
- DREAM DRILLS for HIGH HARDENED STEELS
- STANDARD CARBIDE DRILLS
- MULTI-1 DRILLS
- HPD DRILLS
- GOLD-P DRILLS
- STRAIGHT SHANK DRILLS
- AIRCRAFT DRILLS
- SILVER & DEMING DRILLS
- TAPER SHANK DRILLS
- NC SPOTTING DRILLS
- COMBINATION DRILLS & COUNTERSINK
- SPADE DRILLS
- TECHNICAL DATA

- i-DREAM DRILLS
- DREAM DRILLS -GENERAL
- DREAM DRILLS -HIGH FEED
- DREAM DRILLS -FLAT BOTTOM
- DREAM DRILLS -INOX
- DREAM DRILLS -ALU
- DREAM DRILLS -MQL TYPE
- DREAM DRILLS for HIGH HARDENED STEELS
- STANDARD CARBIDE DRILLS
- MULTI-1 DRILLS
- HPD DRILLS
- GOLD-P DRILLS
- STRAIGHT SHANK DRILLS
- AIRCRAFT DRILLS
- SILVER & DEMING DRILLS
- TAPER SHANK DRILLS
- NC SPOTTING DRILLS
- COMBINATION DRILLS & COUNTERSINK
- SPADE DRILLS
- TECHNICAL DATA



Being the best through innovation


HSS



COMBINATION DRILL & COUNTER SINK / CENTER DRILL

- Regular and Long Length


Global Cutting Tool Leader **YG-1**



SELECTION GUIDE

HSS COMBINATION DRILL & COUNTER SINK / CENTER DRILL

HSS COMBINATION DRILL & COUNTER SINK / CENTER DRILL
- Regular and Long Length

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
INCH					
D1C90		HSS(M2), COMBINATION DRILL & COUNTER SINK / CENTER DRILL	D3/64	D7/32	268
RECOMMENDED CUTTING CONDITIONS					268

◎ : Excellent ○ : Good

P				H	M	K	N			S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
~HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	◎				○	○	○	○	○		○


CARBIDE

HSS

COMBINATION DRILL & COUNTER SINK

D1C90 SERIES

HSS(M2), COMBINATION DRILL & COUNTER SINK / CENTER DRILL



HSS
h8
k12
120°
P.268

60°

EDP No.	Size	Diameter	Shank Diameter		Drill Length		Overall Length	
		D1	D2	L1	L2			
* D1C90079	1	3/64	1/8	1/16	1-1/2			
* D1C90080	2	1/16	3/16	5/64	1-3/4			
* D1C90081	3	3/32	1/4	1/8	2			
* D1C90082	4	1/8	5/16	5/32	2-1/4			
* D1C90083	5	3/16	7/16	1/4	2-1/2			
* D1C90084	6	7/32	1/2	7/32	3			

* 10pcs per package
★ Individually package

60°


EDP No.	Size	Diameter	Shank Diameter		Drill Length		Overall Length	
		D1	D2	L1	L2			
* D1C90141	1	3/64	1/8	3/64	1-1/4			
* D1C90142	2	5/64	3/16	5/64	1-7/8			
* D1C90143	3	7/64	1/4	7/64	2			
* D1C90144	4	1/8	5/16	1/8	2-1/8			
* D1C90145	5	3/16	7/16	3/16	2-3/4			

* 10pcs per package

LONG LENGTH (60°)

Unit : Inch

EDP No.	Size	Diameter	Shank Diameter		Drill Length		Overall Length	
		D1	D2	L1	L2			
D1C90085	1	3/64	1/8	3/64	3			
D1C90086	1	3/64	1/8	3/64	4			
D1C90087	1	3/64	1/8	3/64	5			
D1C90088	1	3/64	1/8	3/64	6			
D1C90089	2	5/64	3/16	5/64	3			
D1C90090	2	5/64	3/16	5/64	4			
D1C90091	2	5/64	3/16	5/64	5			
D1C90092	2	5/64	3/16	5/64	6			
D1C90093	3	7/64	1/4	7/64	4			
D1C90094	3	7/64	1/4	7/64	5			
D1C90095	3	7/64	1/4	7/64	6			
D1C90096	4	1/8	5/16	1/8	4			
D1C90097	4	1/8	5/16	1/8	5			
D1C90098	4	1/8	5/16	1/8	6			
D1C90099	5	3/16	7/16	3/16	4			
D1C90100	5	3/16	7/16	3/16	5			
D1C90101	5	3/16	7/16	3/16	6			
D1C90102	6	7/32	1/2	7/32	4			
D1C90103	6	7/32	1/2	7/32	5			
D1C90104	6	7/32	1/2	7/32	6			



◎ : Excellent ○ : Good

P			H	M	K	N				S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		Stainless Steels	Cast Iron	Aluminum	Copper	Bronze	CFRP	Titanium
-HB225	HB225~325	HRc30~45	HRc45~55	HRc55~							
◎	◎				○	○	○	○	○		○



Being the best through innovation













INSERTS & HOLDERS



SPADE DRILLS

- Carbide for Long Tool Life, and HSS-PM for General Machines and Large Diameters Higher Productivity than Other Drilling Tools

◎ : Excellent ○ : Good

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
SERIES 1~8		SPADE DRILL INSERTS - HSS (M4)	.7031 (#1)	4.5000 (#8)	272
SERIES Y,Z,0,1~8		SPADE DRILL INSERTS - SUPER COBALT (T15)	.3740 (#Y)	4.5000 (#8)	276
SERIES Y,Z,0,1,2		SPADE DRILL INSERTS - PREMIUM COBALT (M48)	.3740 (#Y)	1.3780 (#2)	283
SERIES Y,Z,0,1~3		CARBIDE BLADE INSERTS C2 (K20)	.3740 (#Y)	1.8750 (#3)	286
SERIES Y,Z,0,1~3		CARBIDE BLADE INSERTS C5 (P40)	.3740 (#Y)	1.8750 (#3)	286
SERIES Y,Z,0,1~2		CARBIDE BLADE INSERTS C3 (K10)	.3740 (#Y)	1.3780 (#2)	286
SERIES Y,Z,0,1~8		SM-POINT SPADE DRILL INSERTS - SUPER COBALT (T15)	.3740 (#Y)	4.5000 (#8)	292
SERIES Y,Z,0,1~3		SM-POINT SPADE DRILL INSERTS - CARBIDE C5 (P40)	.3740 (#Y)	1.8750 (#3)	296
SERIES Y,Z,0,1,2		SPADE DRILL FLAT BOTTOM INSERTS - SUPER COBALT (T15)	.3750 (#Y)	1.3750 (#2)	298
STRAIGHT SHANK		STRAIGHT SHANK HOLDER, STRAIGHT FLUTE			299
TAPER SHANK		TAPER SHANK HOLDER, STRAIGHT FLUTE / HELICAL FLUTE			303
FLANGED SHANK		FLANGED STRAIGHT SHANK HOLDER, STRAIGHT FLUTE			305
		HOLDER ACCESSORIES			307
		RECOMMENDED CUTTING CONDITIONS			308

P											M	K		N	
Non-alloyed Steels, Free Machining Steels	Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron		Aluminum	Copper Alloys
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc37 (~HB350)	HRc37~ (HB350~)	~HRc24 (~HB250)	HRc24~ (HB250~)	~HRc13 (~HB200)	HRc13~ (HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (HB220~)	~HRc8 (~HB180)	~HB110
○	○	○	○		○		○	○			◎	◎	○	◎	◎
◎	◎	◎	◎	○	○	○	◎	◎	○	○	○	○	◎	○	○
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	○	○	◎	○	○
○	○	○	○	○	◎	◎	○	○	○	○	◎	○	○	◎	◎
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	○	○	○	○	○
												◎	◎		
◎	◎	◎	◎	○	○	○	◎	◎	○	○	○	○	◎	○	○
◎	◎	◎	◎	○	○	○	◎	◎	○	○	○	○	◎	○	○

YG SPADE DRILLS

SERIES 1,2

SPADE DRILL INSERTS - HSS (M4)

- ▶ General purpose insert for most materials
- ▶ Not recommended for tool steels and high temperature alloys
- ▶ High toughness for loose or manual machines

POINT ANGLE Series Y~4 : 132 degree
Series 5~8 : 144 degree



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. HSS (M4)		
	Fractional (inch)	Metric (mm)	Decimal (inch)		TiN	TiAlN	Hardslick
1 .690 (17.53) to .960 (24.38)	45/64	17.86	.7031	5/32 (4.0)	S01101	S03101	S04101
		18.00	.7087		S01102	S03102	S04102
	23/32	18.26	.7188		S01103	S03103	S04103
		18.50	.7283		S01104	S03104	S04104
	47/64	18.65	.7344		S01105	S03105	S04105
		19.00	.7480		S01106	S03106	S04106
	3/4	19.05	.7500		S01107	S03107	S04107
		19.45	.7656		S01108	S03108	S04108
	49/64	19.50	.7677		S01109	S03109	S04109
		19.84	.7813		S01110	S03110	S04110
	25/32	20.00	.7874		S01111	S03111	S04111
		20.24	.7969		S01112	S03112	S04112
	51/64	20.50	.8071		S01113	S03113	S04113
		20.64	.8125		S01114	S03114	S04114
	13/16	21.00	.8268		S01115	S03115	S04115
		21.43	.8438		S01116	S03116	S04116
	27/32	21.83	.8594		S01117	S03117	S04117
		22.00	.8661		S01118	S03118	S04118
55/64	22.23	.8750	S01119	S03119	S04119		
	22.62	.8906	S01120	S03120	S04120		
2 .961 (24.41) to 1.380 (35.05)	31/32	23.00	.9055	3/16 (4.8)	S01121	S03121	S04121
		23.42	.9219		S01122	S03122	S04122
	63/64	24.00	.9449		S01201	S03201	S04201
		24.61	.9688		S01202	S03202	S04202
	1	25.00	1.0000		S01203	S03203	S04203
		25.40	1.0156		S01204	S03204	S04204
	1-1/64	25.80	1.0156		S01205	S03205	S04205
		26.00	1.0236		S01206	S03206	S04206
	1-1/32	26.19	1.0313		S01207	S03207	S04207
		26.59	1.0469		S01208	S03208	S04208
	1-3/64	26.99	1.0625				
		27.00	1.0630				

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels	Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels	Stainless Steels	Cast Iron	Aluminum	Copper Alloys		
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
○	○	○	○	○	○	○	○	○	○	○	◎	◎	○	◎	◎

YG SPADE DRILLS

SERIES 2,3

SPADE DRILL INSERTS - HSS (M4)

- ▶ General purpose insert for most materials
- ▶ Not recommended for tool steels and high temperature alloys
- ▶ High toughness for loose or manual machines

POINT ANGLE Series Y~4 : 132 degree
Series 5~8 : 144 degree



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. HSS (M4)		
	Fractional (inch)	Metric (mm)	Decimal (inch)		TiN	TiAlN	Hardslick
2 .961 (24.41) to 1.380 (35.05)	1-3/32	27.78	1.0938	3/16 (4.8)	S01209	S03209	S04209
		28.00	1.1024		S01210	S03210	S04210
	1-7/64	28.18	1.1094		S01261	S03261	S04261
		28.58	1.1250		S01211	S03211	S04211
	1-1/8	29.00	1.1417		S01212	S03212	S04212
		29.37	1.1563		S01213	S03213	S04213
	1-5/32	30.00	1.1811		S01214	S03214	S04214
		30.16	1.1875		S01215	S03215	S04215
	1-3/16	30.96	1.2188		S01216	S03216	S04216
		31.00	1.2205		S01217	S03217	S04217
	1-1/4	31.75	1.2500		S01218	S03218	S04218
		32.00	1.2598		S01219	S03219	S04219
	1-9/32	32.54	1.2813		S01220	S03220	S04220
		33.00	1.2992		S01221	S03221	S04221
	1-5/16	33.34	1.3125		S01222	S03222	S04222
		34.00	1.3386		S01223	S03223	S04223
	1-11/32	34.13	1.3438		S01224	S03224	S04224
		34.93	1.3750		S01225	S03225	S04225
1-3/8	35.00	1.3780	S01226	S03226	S04226		
	35.72	1.4063	S01301	S03301	S04301		
3 1.353 (34.37) to 1.882 (47.80)	1-13/32	36.00	1.4173	1/4 (6.4)	S01302	S03302	S04302
		36.51	1.4375		S01303	S03303	S04303
	1-7/16	37.00	1.4567		S01304	S03304	S04304
		37.31	1.4688		S01305	S03305	S04305
	1-15/32	38.00	1.4961		S01306	S03306	S04306
		38.10	1.5000		S01307	S03307	S04307
	1-1/2	38.89	1.5313		S01308	S03308	S04308
		39.00	1.5354		S01309	S03309	S04309
	1-9/16	39.69	1.5625		S01310	S03310	S04310
		40.00	1.5748		S01311	S03311	S04311
	1-19/32	40.48	1.5938		S01312	S03312	S04312
		41.00	1.6142		S01313	S03313	S04313
	1-5/8	41.28	1.6250		S01314	S03314	S04314
		42.00	1.6535		S01315	S03315	S04315

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels	Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels	Stainless Steels	Cast Iron	Aluminum	Copper Alloys		
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
○	○	○	○	○	○	○	○	○	○	○	◎	◎	○	◎	◎

YG SPADE DRILLS

SERIES 3,4

SPADE DRILL INSERTS - HSS (M4)

- ▶ General purpose insert for most materials
- ▶ Not recommended for tool steels and high temperature alloys
- ▶ High toughness for loose or manual machines

POINT ANGLE Series Y~4 : 132 degree
Series 5~8 : 144 degree



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. HSS (M4)		
	Fractional (inch)	Metric (mm)	Decimal (inch)		TiN	TiAlN	Hardslick
3 1.353 (34.37) to 1.882 (47.80)	1-21/32	42.07	1.6563	1/4 (6.4)	S01316	S03316	S04316
	1-11/16	42.86	1.6875		S01317	S03317	S04317
		43.00	1.6929		S01318	S03318	S04318
	1-23/32	43.66	1.7188		S01319	S03319	S04319
		44.00	1.7323		S01320	S03320	S04320
	1-3/4	44.45	1.7500		S01321	S03321	S04321
		45.00	1.7717		S01322	S03322	S04322
	1-25/32	45.24	1.7813		S01323	S03323	S04323
		46.00	1.8110		S01324	S03324	S04324
	1-13/16	46.04	1.8125		S01325	S03325	S04325
4 1.850 (46.99) to 2.570 (65.28)	1-27/32	46.83	1.8438	5/16 (7.9)	S01326	S03326	S04326
		47.00	1.8504		S01327	S03327	S04327
	1-7/8	47.63	1.8750		S01328	S03328	S04328
	1-29/32	48.42	1.9063		S01402	S03402	S04402
	1-15/16	49.21	1.9375		S01404	S03404	S04404
	1-31/32	50.01	1.9688		S01406	S03406	S04406
	2	50.80	2.0000		S01407	S03407	S04407
	2-1/32	51.59	2.0313		S01409	S03409	S04409
	2-3/64	52.00	2.0472		S01410	S03410	S04410
	2-1/16	52.39	2.0625		S01411	S03411	S04411
	2-3/32	53.18	2.0938		S01413	S03413	S04413
	2-1/8	53.98	2.1250		S01414	S03414	S04414
	2-5/32	54.77	2.1563		S01416	S03416	S04416
	2-3/16	55.56	2.1875		S01418	S03418	S04418
	2-7/32	56.36	2.2188		S01420	S03420	S04420
	2-1/4	57.15	2.2500		S01422	S03422	S04422
	2-9/32	57.94	2.2813		S01423	S03423	S04423
	2-5/16	58.74	2.3125		S01425	S03425	S04425
	2-11/32	59.53	2.3438		S01427	S03427	S04427
	2-3/8	60.33	2.3750		S01429	S03429	S04429
2-13/32	61.12	2.4063	S01431	S03431	S04431		
2-7/16	61.91	2.4375	S01432	S03432	S04432		
2-15/32	62.71	2.4688	S01434	S03434	S04434		
2-1/2	63.50	2.5000	S01436	S03436	S04436		

◎ : Excellent ○ : Good

P										M	K	N				
Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron		Aluminum	Copper Alloys
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110	
○	○	○	○	○	○	○	○	○	○	○	◎	◎	○	◎	◎	

YG SPADE DRILLS

SERIES 4,5,6,7,8

SPADE DRILL INSERTS - HSS (M4)

- ▶ General purpose insert for most materials
- ▶ Not recommended for tool steels and high temperature alloys
- ▶ High toughness for loose or manual machines

POINT ANGLE Series Y~4 : 132 degree
Series 5~8 : 144 degree



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. HSS (M4)		
	Fractional (inch)	Metric (mm)	Decimal (inch)		TiN	TiAlN	Hardslick
4	2-17/32	64.29	2.5313	5/16 (7.9)	S01438	S03438	S04438
	2-9/16	65.09	2.5625		S01440	S03440	S04440
5 2.456 (62.38) to 3.000 (76.20)	2-1/2	63.50	2.5000	7/16 (11.1)	S01501	S03501	S04501
	2-5/8	66.68	2.6250		S01507	S03507	S04507
	2-3/4	69.85	2.7500		S01512	S03512	S04512
	2-25/32	70.64	2.7813		S01514	S03514	S04514
	2-13/16	71.44	2.8125		S01515	S03515	S04515
	2-27/32	72.23	2.8438		S01517	S03517	S04517
	2-7/8	73.03	2.8750		S01518	S03518	S04518
	2-29/32	73.82	2.9063		S01519	S03519	S04519
	2-15/16	74.61	2.9375		S01521	S03521	S04521
	2-31/32	75.41	2.9688		S01522	S03522	S04522
6 3.001(76.23) to 3.507(89.08)	3	76.20	3.0000	7/16 (11.1)	S01524	S03524	S04524
	3-1/16	77.79	3.0625		S01602	S03602	S04602
	3-1/8	79.38	3.1250		S01605	S03605	S04605
	3-1/4	82.55	3.2500		S01611	S03611	S04611
	3-3/8	85.73	3.3750		S01616	S03616	S04616
7 3.455(87.76) to 4.000(101.60)	3-7/16	87.31	3.4375	7/16 (11.1)	S01619	S03619	S04619
	3-1/2	88.90	3.5000		S01622	S03622	S04622
	3-9/16	90.49	3.5625		S01703	S03703	S04703
	3-5/8	92.08	3.6250		S01706	S03706	S04706
	3-3/4	95.25	3.7500		S01711	S03711	S04711
8 4.001(101.63) to 4.507(114.48)	3-7/8	98.43	3.8750	7/16 (11.1)	S01717	S03717	S04717
	4	101.60	4.0000		S01722	S03722	S04722
	4-1/8	104.78	4.1250		S01804	S03804	S04804
	4-1/4	107.95	4.2500		S01807	S03807	S04807
	4-3/8	111.13	4.3750		S01811	S03811	S04811
4-1/2	114.30	4.5000	S01815	S03815	S04815		

◎ : Excellent ○ : Good

P										M	K	N				
Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron		Aluminum	Copper Alloys
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110	
○	○	○	○	○	○	○	○	○	○	○	◎	◎	○	◎	◎	

i-DREAM DRILLS
DREAM DRILLS -GENERAL
DREAM DRILLS -HIGH FEED
DREAM DRILLS -FLAT BOTTOM
DREAM DRILLS -INOX
DREAM DRILLS -ALU
DREAM DRILLS -MQL TYPE
DREAM DRILLS for HIGH HARDENED STEELS
STANDARD CARBIDE DRILLS
MULTI-1 DRILLS
HPD DRILLS
GOLD-P DRILLS
STRAIGHT SHANK DRILLS
AIRCRAFT DRILLS
SILVER & DEMING DRILLS
TAPER SHANK DRILLS
NC SPOTTING DRILLS
COMBINATION DRILLS & COUNTERSINK
SPADE DRILLS
TECHNICAL DATA

i-DREAM DRILLS
DREAM DRILLS -GENERAL
DREAM DRILLS -HIGH FEED
DREAM DRILLS -FLAT BOTTOM
DREAM DRILLS -INOX
DREAM DRILLS -ALU
DREAM DRILLS -MQL TYPE
DREAM DRILLS for HIGH HARDENED STEELS
STANDARD CARBIDE DRILLS
MULTI-1 DRILLS
HPD DRILLS
GOLD-P DRILLS
STRAIGHT SHANK DRILLS
AIRCRAFT DRILLS
SILVER & DEMING DRILLS
TAPER SHANK DRILLS
NC SPOTTING DRILLS
COMBINATION DRILLS & COUNTERSINK
SPADE DRILLS
TECHNICAL DATA

YG SPADE DRILLS

SERIES Y,Z,0

SPADE DRILL INSERTS - SUPER COBALT (T15)

- ▶ Increase wear resistance over M4
- ▶ For use in medium carbon steel to high temperature alloys
- ▶ Performs best in rigid setups

POINT ANGLE Series Y~4 : 132 degree
Series 5~8 : 144 degree



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No.		
	Fractional (inch)	Metric (mm)	Decimal (inch)		SUPER COBALT (T15)		
					TiN	TiAlN	Hardslck
Y .374 (9.50) to .436 (11.07)	3/8	9.50	.3740	3/32 (2.4)	*S06Y01	*S08Y01	*S09Y01
		9.53	.3750		*S06Y02	*S08Y02	*S09Y02
	25/64	9.80	.3860		*S06Y03	*S08Y03	*S09Y03
		9.92	.3906		*S06Y04	*S08Y04	*S09Y04
		10.00	.3937		*S06Y05	*S08Y05	*S09Y05
		10.20	.4016		*S06Y06	*S08Y06	*S09Y06
	13/32	10.32	.4063		*S06Y07	*S08Y07	*S09Y07
		10.50	.4134		*S06Y08	*S08Y08	*S09Y08
	27/64	10.72	.4219		*S06Y09	*S08Y09	*S09Y09
		10.80	.4252		*S06Y10	*S08Y10	*S09Y10
Z .437 (11.11) to .510 (12.95)	7/16	11.11	.4375	3/32 (2.4)	*S06Z01	*S08Z01	*S09Z01
		11.50	.4528		*S06Z02	*S08Z02	*S09Z02
	29/64	11.51	.4531		*S06Z03	*S08Z03	*S09Z03
	15/32	11.91	.4688		*S06Z04	*S08Z04	*S09Z04
	31/64	12.00	.4724		*S06Z05	*S08Z05	*S09Z05
		12.30	.4844		*S06Z06	*S08Z06	*S09Z06
	12.50	.4921	*S06Z07		*S08Z07	*S09Z07	
		12.70	.5000		*S06Z08	*S08Z08	*S09Z08
	13.00	.5118	*S06001		*S08001	*S09001	
		13.10	.5156		*S06002	*S08002	*S09002
17/32	13.49	.5313	*S06003	*S08003	*S09003		
	13.50	.5315	*S06004	*S08004	*S09004		
35/64	13.89	.5469	*S06060	*S08060	*S09060		
	14.00	.5512	*S06005	*S08005	*S09005		
9/16	14.29	.5625	*S06006	*S08006	*S09006		
	14.50	.5709	*S06007	*S08007	*S09007		
37/64	14.68	.5781	*S06008	*S08008	*S09008		
	15.00	.5906	*S06009	*S08009	*S09009		
19/32	15.08	.5938	*S06010	*S08010	*S09010		
	39/64	15.48	.6094	*S06061	*S08061	*S09061	
	15.50	.6102	*S06011	*S08011	*S09011		
	5/8	15.88	.6250	*S06012	*S08012	*S09012	

* 2pcs per package

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	○	○	○	◎	◎	○	○	○	○	◎	○	○

YG SPADE DRILLS

SERIES 0,1

SPADE DRILL INSERTS - SUPER COBALT (T15)

- ▶ Increase wear resistance over M4
- ▶ For use in medium carbon steel to high temperature alloys
- ▶ Performs best in rigid setups

POINT ANGLE Series Y~4 : 132 degree
Series 5~8 : 144 degree



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No.				
	Fractional (inch)	Metric (mm)	Decimal (inch)		SUPER COBALT (T15)				
					TiN	TiAlN	Hardslck		
0 .511 (12.98) to .695 (17.65)	41/64	16.00	.6299	1/8 (3.2)	*S06013	*S08013	*S09013		
		16.27	.6406		*S06062	*S08062	*S09062		
		16.50	.6496		*S06014	*S08014	*S09014		
		21/32	16.67		.6563	*S06015	*S08015	*S09015	
		17.00	.6693		*S06016	*S08016	*S09016		
		43/64	17.07		.6719	*S06063	*S08063	*S09063	
	11/16	17.46	.6875		*S06017	*S08017	*S09017		
		17.50	.6890		*S06018	*S08018	*S09018		
	1 .690 (17.53) to .960 (24.38)	45/64	17.86		.7031	5/32 (4.0)	S06101	S08101	S09101
			18.00		.7087		S06102	S08102	S09102
23/32		18.26	.7188	S06103	S08103		S09103		
		18.50	.7283	S06104	S08104		S09104		
47/64		18.65	.7344	S06105	S08105		S09105		
		19.00	.7480	S06106	S08106		S09106		
3/4		19.05	.7500	S06107	S08107		S09107		
49/64		19.45	.7656	S06108	S08108		S09108		
		19.50	.7677	S06109	S08109		S09109		
25/32		19.84	.7813	S06110	S08110		S09110		
	20.00	.7874	S06111	S08111	S09111				
51/64	20.24	.7969	S06160	S08160	S09160				
	20.50	.8071	S06112	S08112	S09112				
13/16	20.64	.8125	S06113	S08113	S09113				
	21.00	.8268	S06114	S08114	S09114				
27/32	21.43	.8438	S06115	S08115	S09115				
55/64	21.83	.8594	S06161	S08161	S09161				
	22.00	.8661	S06116	S08116	S09116				
7/8	22.23	.8750	S06117	S08117	S09117				
57/64	22.62	.8906	S06162	S08162	S09162				
	23.00	.9055	S06118	S08118	S09118				
29/32	23.02	.9063	S06119	S08119	S09119				
59/64	23.42	.9219	S06120	S08120	S09120				
15/16	23.81	.9375	S06121	S08121	S09121				
	24.00	.9449	S06122	S08122	S09122				

* 2pcs per package

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	○	○	○	◎	◎	○	○	○	○	◎	○	○

- i-DREAM DRILLS
- DREAM DRILLS -GENERAL
- DREAM DRILLS -HIGH FEED
- DREAM DRILLS -FLAT BOTTOM
- DREAM DRILLS -INOX
- DREAM DRILLS -ALU
- DREAM DRILLS -MQL TYPE
- DREAM DRILLS for HIGH HARDENED STEELS
- STANDARD CARBIDE DRILLS
- MULTI-1 DRILLS
- HPD DRILLS
- GOLD-P DRILLS
- STRAIGHT SHANK DRILLS
- AIRCRAFT DRILLS
- SILVER & DEMING DRILLS
- TAPER SHANK DRILLS
- NC SPOTTING DRILLS
- COMBINATION DRILLS & COUNTERSINK
- SPADE DRILLS
- TECHNICAL DATA

- i-DREAM DRILLS
- DREAM DRILLS -GENERAL
- DREAM DRILLS -HIGH FEED
- DREAM DRILLS -FLAT BOTTOM
- DREAM DRILLS -INOX
- DREAM DRILLS -ALU
- DREAM DRILLS -MQL TYPE
- DREAM DRILLS for HIGH HARDENED STEELS
- STANDARD CARBIDE DRILLS
- MULTI-1 DRILLS
- HPD DRILLS
- GOLD-P DRILLS
- STRAIGHT SHANK DRILLS
- AIRCRAFT DRILLS
- SILVER & DEMING DRILLS
- TAPER SHANK DRILLS
- NC SPOTTING DRILLS
- COMBINATION DRILLS & COUNTERSINK
- SPADE DRILLS
- TECHNICAL DATA

YG SPADE DRILLS

SERIES 2,3

SPADE DRILL INSERTS - SUPER COBALT (T15)

- ▶ Increase wear resistance over M4
- ▶ For use in medium carbon steel to high temperature alloys
- ▶ Performs best in rigid setups

POINT ANGLE Series Y~4 : 132 degree
Series 5~8 : 144 degree



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No.		
	Fractional (inch)	Metric (mm)	Decimal (inch)		SUPER COBALT (T15)		
					TiN	TiAIN	Hardslick
2 .961 (24.41) to 1.380 (35.05)	31/32	24.61	.9688	3/16 (4.8)	S06201	S08201	S09201
	63/64	25.00	.9843		S06202	S08202	S09202
	1	25.40	1.0000		S06203	S08203	S09203
	1-1/64	25.80	1.0156		S06204	S08204	S09204
		26.00	1.0236		S06205	S08205	S09205
	1-1/32	26.19	1.0313		S06206	S08206	S09206
	1-3/64	26.59	1.0469		S06260	S08260	S09260
	1-1/16	26.99	1.0625		S06207	S08207	S09207
		27.00	1.0630		S06208	S08208	S09208
	1-3/32	27.78	1.0938		S06209	S08209	S09209
		28.00	1.1024		S06210	S08210	S09210
	1-7/64	28.18	1.1094		S06261	S08261	S09261
	1-1/8	28.58	1.1250		S06211	S08211	S09211
		29.00	1.1417		S06212	S08212	S09212
	1-5/32	29.37	1.1563		S06213	S08213	S09213
		30.00	1.1811		S06214	S08214	S09214
	1-3/16	30.16	1.1875		S06215	S08215	S09215
	1-7/32	30.96	1.2188		S06216	S08216	S09216
		31.00	1.2205		S06217	S08217	S09217
	3	1-1/4	31.75		1.2500	S06218	S08218
		32.00	1.2598	S06219	S08219	S09219	
1-9/32		32.54	1.2813	S06220	S08220	S09220	
		33.00	1.2992	S06221	S08221	S09221	
1-5/16		33.34	1.3125	S06222	S08222	S09222	
		34.00	1.3386	S06223	S08223	S09223	
1-11/32		34.13	1.3438	S06224	S08224	S09224	
1-3/8		34.93	1.3750	S06225	S08225	S09225	
		35.00	1.3780	S06226	S08226	S09226	
1-13/32		35.72	1.4063	S06301	S08301	S09301	
		36.00	1.4173	S06302	S08302	S09302	
1-7/16		36.51	1.4375	S06303	S08303	S09303	
		37.00	1.4567	S06304	S08304	S09304	
1-15/32		37.31	1.4688	S06305	S08305	S09305	

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	○	○	○	◎	◎	○	○	○	○	◎	○	○

YG SPADE DRILLS

SERIES 3,4

SPADE DRILL INSERTS - SUPER COBALT (T15)

- ▶ Increase wear resistance over M4
- ▶ For use in medium carbon steel to high temperature alloys
- ▶ Performs best in rigid setups

POINT ANGLE Series Y~4 : 132 degree
Series 5~8 : 144 degree



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No.		
	Fractional (inch)	Metric (mm)	Decimal (inch)		SUPER COBALT (T15)		
					TiN	TiAIN	Hardslick
3 1.353 (34.37) to 1.882 (47.80)		38.00	1.4961	1/4 (6.4)	S06306	S08306	S09306
	1-1/2	38.10	1.5000		S06307	S08307	S09307
	1-17/32	38.89	1.5313		S06308	S08308	S09308
		39.00	1.5354		S06309	S08309	S09309
	1-9/16	39.69	1.5625		S06310	S08310	S09310
		40.00	1.5748		S06311	S08311	S09311
	1-19/32	40.48	1.5938		S06312	S08312	S09312
		41.00	1.6142		S06313	S08313	S09313
	1-5/8	41.28	1.6250		S06314	S08314	S09314
		42.00	1.6535		S06315	S08315	S09315
	1-21/32	42.07	1.6563		S06316	S08316	S09316
	1-11/16	42.86	1.6875		S06317	S08317	S09317
		43.00	1.6929		S06318	S08318	S09318
	1-23/32	43.66	1.7188		S06319	S08319	S09319
		44.00	1.7323		S06320	S08320	S09320
	1-3/4	44.45	1.7500		S06321	S08321	S09321
		45.00	1.7717		S06322	S08322	S09322
	1-25/32	45.24	1.7813		S06323	S08323	S09323
		46.00	1.8110		S06324	S08324	S09324
	4 1.850 (46.99) to 2.570 (65.28)	1-13/16	46.04		1.8125	S06325	S08325
1-27/32		46.83	1.8438	S06326	S08326	S09326	
		47.00	1.8504	S06327	S08327	S09327	
1-7/8		47.63	1.8750	S06328	S08328	S09328	
1-29/32		48.42	1.9062	S06402	S08402	S09402	
1-15/16		49.21	1.9375	S06404	S08404	S09404	
1-31/32		50.01	1.9688	S06406	S08406	S09406	
2		50.80	2.0000	S06407	S08407	S09407	
2-1/32		51.59	2.0312	S06409	S08409	S09409	
2-3/64		52.00	2.0472	S06410	S08410	S09410	
2-1/16		52.39	2.0625	S06411	S08411	S09411	
2-3/32		53.18	2.0938	S06413	S08413	S09413	
2-1/8		53.98	2.1250	S06414	S08414	S09414	
2-5/32		54.77	2.1562	S06416	S08416	S09416	

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	○	○	○	◎	◎	○	○	○	○	◎	○	○

- i-DREAM DRILLS
- DREAM DRILLS -GENERAL
- DREAM DRILLS -HIGH FEED
- DREAM DRILLS -FLAT BOTTOM
- DREAM DRILLS -INOX
- DREAM DRILLS -ALU
- DREAM DRILLS -MQL TYPE
- DREAM DRILLS for HIGH HARDENED STEELS
- STANDARD CARBIDE DRILLS
- MULTI-1 DRILLS
- HPD DRILLS
- GOLD-P DRILLS
- STRAIGHT SHANK DRILLS
- AIRCRAFT DRILLS
- SILVER & DEMING DRILLS
- TAPER SHANK DRILLS
- NC SPOTTING DRILLS
- COMBINATION DRILLS & COUNTERSINK
- SPADE DRILLS
- TECHNICAL DATA

- i-DREAM DRILLS
- DREAM DRILLS -GENERAL
- DREAM DRILLS -HIGH FEED
- DREAM DRILLS -FLAT BOTTOM
- DREAM DRILLS -INOX
- DREAM DRILLS -ALU
- DREAM DRILLS -MQL TYPE
- DREAM DRILLS for HIGH HARDENED STEELS
- STANDARD CARBIDE DRILLS
- MULTI-1 DRILLS
- HPD DRILLS
- GOLD-P DRILLS
- STRAIGHT SHANK DRILLS
- AIRCRAFT DRILLS
- SILVER & DEMING DRILLS
- TAPER SHANK DRILLS
- NC SPOTTING DRILLS
- COMBINATION DRILLS & COUNTERSINK
- SPADE DRILLS
- TECHNICAL DATA

YG SPADE DRILLS

SERIES 4,5

SPADE DRILL INSERTS - SUPER COBALT (T15)

- ▶ Increase wear resistance over M4
- ▶ For use in medium carbon steel to high temperature alloys
- ▶ Performs best in rigid setups

POINT ANGLE Series Y~4 : 132 degree
Series 5~8 : 144 degree



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. SUPER COBALT (T15)		
	Fractional (inch)	Metric (mm)	Decimal (inch)		TiN	TiAlN	Hardslick
4 1.850 (46.99) to 2.570 (65.28)	2-3/16	55.56	2.1875	5/16 (7.9)	S06418	S08418	S09418
	2-7/32	56.36	2.2188		S06420	S08420	S09420
	2-1/4	57.15	2.2500		S06422	S08422	S09422
	2-9/32	57.94	2.2812		S06423	S08423	S09423
	2-5/16	58.74	2.3125		S06425	S08425	S09425
	2-11/32	59.53	2.3438		S06427	S08427	S09427
	2-3/8	60.33	2.3750		S06429	S08429	S09429
	2-13/32	61.12	2.4062		S06431	S08431	S09431
	2-7/16	61.91	2.4375		S06432	S08432	S09432
	2-15/32	62.71	2.4688		S06434	S08434	S09434
	2-1/2	63.50	2.5000		S06436	S08436	S09436
	2-17/32	64.29	2.5312		S06438	S08438	S09438
	2-9/16	65.09	2.5625		S06440	S08440	S09440
	5 2.456 (62.38) to 3.000 (76.20)	2-1/2	63.50		2.5000	7/16 (11.1)	—
		64.00	2.5197	—	—		S09502
2-17/32		64.29	2.5312	—	—		S09503
2-9/16		65.09	2.5625	—	—		S09504
2-19/32		65.88	2.5938	—	—		S09505
		66.00	2.5984	—	—		S09506
2-5/8		66.68	2.6250	—	—		S09507
2-21/32		67.47	2.6562	—	—		S09508
		68.00	2.6772	—	—		S09509
2-11/16		68.26	2.6875	—	—		S09510
2-23/32		69.09	2.7188	—	—		S09511
2-3/4		69.85	2.7500	—	—		S09512
		70.00	2.7559	—	—		S09513
2-25/32		70.64	2.7812	—	—		S09514
2-13/16		71.44	2.8125	—	—		S09515
		72.00	2.8346	—	—		S09516
2-27/32		72.23	2.8438	—	—		S09517
2-7/8		73.03	2.8750	—	—		S09518
2-29/32	73.82	2.9062	—	—	S09519		
	74.00	2.9134	—	—	S09520		

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	○	○	○	◎	◎	○	○	○	○	◎	○	○

YG SPADE DRILLS

SERIES 5,6,7

SPADE DRILL INSERTS - SUPER COBALT (T15)

- ▶ Increase wear resistance over M4
- ▶ For use in medium carbon steel to high temperature alloys
- ▶ Performs best in rigid setups

POINT ANGLE Series Y~4 : 132 degree
Series 5~8 : 144 degree



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. SUPER COBALT (T15)		
	Fractional (inch)	Metric (mm)	Decimal (inch)		TiN	TiAlN	Hardslick
5	2-15/16	74.61	2.9375	7/16 (11.1)	—	—	S09521
	2-31/32	75.41	2.8688		—	—	S09522
		76.00	2.9921		—	—	S09523
	3	76.20	3.0000		—	—	S09524
6 3.001 (76.23) to 3.507 (89.08)	3-1/32	76.99	3.0312	7/16 (11.1)	—	—	S09601
	3-1/16	77.79	3.0625		—	—	S09602
		78.00	3.0709		—	—	S09603
	3-3/32	78.58	3.0938		—	—	S09604
	3-1/8	79.38	3.1250		—	—	S09605
		80.00	3.1496		—	—	S09606
	3-5/32	80.17	3.1562		—	—	S09607
	3-3/16	80.96	3.1875		—	—	S09608
	3-7/32	81.76	3.2188		—	—	S09609
		82.00	3.2283		—	—	S09610
	3-1/4	82.55	3.2500		—	—	S09611
	3-9/32	83.34	3.2812		—	—	S09612
		84.00	3.3071		—	—	S09613
	3-5/16	84.14	3.3125		—	—	S09614
3-11/32	84.93	3.3438	—	—	S09615		
3-3/8	85.73	3.3750	—	—	S09616		
	86.00	3.3858	—	—	S09617		
3-13/32	86.52	3.3062	—	—	S09618		
3-7/16	87.31	3.4375	—	—	S09619		
	88.00	3.4646	—	—	S09620		
3-15/32	88.11	3.4688	—	—	S09621		
3-1/2	88.90	3.5000	—	—	S09622		
7 3.455(87.76) to 4.000(101.60)	3-17/32	89.69	3.5312	7/16 (11.1)	—	—	S09701
		90.00	3.5433		—	—	S09702
	3-9/16	90.49	3.5625		—	—	S09703
	3-19/32	91.28	3.5938		—	—	S09704
		92.00	3.6221		—	—	S09705
	3-5/8	92.08	3.6250		—	—	S09706
	92.87	3.6563	—	—	S09707		

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	○	○	○	◎	◎	○	○	○	○	◎	○	○

i-DREAM DRILLS
DREAM DRILLS -GENERAL
DREAM DRILLS -HIGH FEED
DREAM DRILLS -FLAT BOTTOM
DREAM DRILLS -INOX
DREAM DRILLS -ALU
DREAM DRILLS -MQL TYPE
DREAM DRILLS for HIGH HARDENED STEELS
STANDARD CARBIDE DRILLS
MULTI-1 DRILLS
HPD DRILLS
GOLD-P DRILLS
STRAIGHT SHANK DRILLS
AIRCRAFT DRILLS
SILVER & DEMING DRILLS
TAPER SHANK DRILLS
NC SPOTTING DRILLS
COMBINATION DRILLS & COUNTERSINK
SPADE DRILLS
TECHNICAL DATA

i-DREAM DRILLS
DREAM DRILLS -GENERAL
DREAM DRILLS -HIGH FEED
DREAM DRILLS -FLAT BOTTOM
DREAM DRILLS -INOX
DREAM DRILLS -ALU
DREAM DRILLS -MQL TYPE
DREAM DRILLS for HIGH HARDENED STEELS
STANDARD CARBIDE DRILLS
MULTI-1 DRILLS
HPD DRILLS
GOLD-P DRILLS
STRAIGHT SHANK DRILLS
AIRCRAFT DRILLS
SILVER & DEMING DRILLS
TAPER SHANK DRILLS
NC SPOTTING DRILLS
COMBINATION DRILLS & COUNTERSINK
SPADE DRILLS
TECHNICAL DATA

YG SPADE DRILLS

SERIES 7,8

SPADE DRILL INSERTS - SUPER COBALT (T15)

- ▶ Increase wear resistance over M4
- ▶ For use in medium carbon steel to high temperature alloys
- ▶ Performs best in rigid setups

POINT ANGLE Series Y~4 : 132 degree
Series 5~8 : 144 degree



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No.		
	Fractional (inch)	Metric (mm)	Decimal (inch)		SUPER COBALT (T15)		
					TiN	TiAIN	Hardslick
7 3.455 (87.76) to 4.000 (101.60)	3-11/16	93.66	3.6875	7/16 (11.1)	—	—	S09708
		94.00	3.7008		—	—	S09709
	3-23/32	94.46	3.7188		—	—	S09710
		3-3/4	95.25		3.7500	—	—
	96.00		3.7795		—	—	S09712
	3-25/32	96.04	3.7812		—	—	S09713
	3-13/16	96.84	3.8125		—	—	S09714
	3-27/32	97.63	3.8438		—	—	S09715
	98.00	3.8583	—		—	—	S09716
	3-7/8	98.43	3.8750		—	—	S09717
	3-29/32	99.22	3.9062		—	—	S09718
	100.00	3.9370	—		—	—	S09719
	3-15/16	100.01	3.9375		—	—	S09720
	3-31/32	100.81	3.9688		—	—	S09721
4	101.60	4.0000	—	—	S09722		
8 4.001 (101.63) to 4.507 (114.48)	4-1/64	102.00	4.0156	7/16 (11.1)	—	—	S09801
		103.19	4.0625		—	—	S09802
	4-3/32	104.00	4.0945		—	—	S09803
	4-1/8	104.78	4.1250		—	—	S09804
	106.00	4.1732	—		—	—	S09805
	4-3/16	106.36	4.1875		—	—	S09806
	4-1/4	107.95	4.2500		—	—	S09807
	108.00	4.2520	—		—	—	S09808
	4-5/16	109.54	4.3125		—	—	S09809
	110.00	4.3307	—		—	—	S09810
	4-3/8	111.13	4.3750		—	—	S09811
	112.00	4.4094	—		—	—	S09812
	4-7/16	112.71	4.4375		—	—	S09813
	114.00	4.4882	—		—	—	S09814
4-1/2	114.30	4.5000	—	—	S09815		

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc37 (~HB350)	HRc37~ (HB350~)	~HRc24 (~HB250)	HRc24~ (HB250~)	~HRc13 (~HB200)	HRc13~ (HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	○	○	○	◎	◎	○	○	○	○	◎	○	○

YG SPADE DRILLS

SERIES Y,Z,0

SPADE DRILL INSERTS - PREMIUM COBALT (M48)

- ▶ Increased tool life over T15
- ▶ For use in high temperature alloys and materials including medium carbon, Alloy and tool steels
- ▶ Rigid set up needed

POINT ANGLE : 132 degree



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No.		
	Fractional (inch)	Metric (mm)	Decimal (inch)		PREMIUM COBALT (M48)		
					TiN	TiAIN	Hardslick
Y .374 (9.50) to .436 (11.07)	3/8	9.50	.3740	3/32 (2.4)	*S11Y01	*S13Y01	*S14Y01
		9.53	.3750		*S11Y02	*S13Y02	*S14Y02
	25/64	9.80	.3860		*S11Y03	*S13Y03	*S14Y03
		9.92	.3906		*S11Y04	*S13Y04	*S14Y04
	10.00	.3937	*S11Y05		*S13Y05	*S14Y05	
	10.20	.4016	*S11Y06		*S13Y06	*S14Y06	
	13/32	10.32	.4063		*S11Y07	*S13Y07	*S14Y07
	10.50	.4134	*S11Y08		*S13Y08	*S14Y08	
	27/64	10.72	.4219		*S11Y09	*S13Y09	*S14Y09
	10.80	.4252	*S11Y10		*S13Y10	*S14Y10	
	11.00	.4331	*S11Y11		*S13Y11	*S14Y11	
Z .437 (11.11) to .510 (12.95)	7/16	11.11	.4375	3/32 (2.4)	*S11Z01	*S13Z01	*S14Z01
	11.50	.4528	*S11Z02		*S13Z02	*S14Z02	
	29/64	11.51	.4531		*S11Z03	*S13Z03	*S14Z03
	15/32	11.91	.4688		*S11Z04	*S13Z04	*S14Z04
	31/64	12.30	.4844		*S11Z05	*S13Z05	*S14Z05
	12.50	.4921	*S11Z06		*S13Z06	*S14Z06	
	1/2	12.70	.5000		*S11Z07	*S13Z07	*S14Z07
0 .511 (12.98) to .695 (17.65)	13.00	.5118	1/8 (3.2)	*S11001	*S13001	*S14001	
	33/64	.5156		*S11002	*S13002	*S14002	
	17/32	.5313		*S11003	*S13003	*S14003	
	13.50	.5315		*S11004	*S13004	*S14004	
	35/64	.5469		*S11060	*S13060	*S14060	
	14.00	.5512		*S11005	*S13005	*S14005	
	9/16	.5625		*S11006	*S13006	*S14006	
	14.50	.5709		*S11007	*S13007	*S14007	
	37/64	.5781		*S11008	*S13008	*S14008	
	15.00	.5906		*S11009	*S13009	*S14009	
	19/32	.5938		*S11010	*S13010	*S14010	
	39/64	.6094		*S11061	*S13061	*S14061	
	15.50	.6102		*S11011	*S13011	*S14011	
	5/8	.6250		*S11012	*S13012	*S14012	

* 2pcs per package

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc37 (~HB350)	HRc37~ (HB350~)	~HRc24 (~HB250)	HRc24~ (HB250~)	~HRc13 (~HB200)	HRc13~ (HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	○	○	◎	○	○

YG SPADE DRILLS

SERIES 0,1

SPADE DRILL INSERTS - PREMIUM COBALT (M48)

- ▶ Increased tool life over T15
- ▶ For use in high temperature alloys and materials including medium carbon, Alloy and tool steels
- ▶ Rigid set up needed



POINT ANGLE : 132 degree

cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No.		
	Fractional (inch)	Metric (mm)	Decimal (inch)		PREMIUM COBALT (M48)		
					TiN	TiAlN	Hardslick
0 .511 (12.98) to .695 (17.65)	16.00	16.00	.6299	1/8 (3.2)	* S11013	* S13013	* S14013
	41/64		.6406		* S11062	* S13062	* S14062
	16.50	16.50	.6496		* S11014	* S13014	* S14014
	21/32		.6563		* S11015	* S13015	* S14015
	17.00	17.00	.6693		* S11016	* S13016	* S14016
	43/64		.6719		* S11063	* S13063	* S14063
	11/16		.6875		* S11017	* S13017	* S14017
	17.50	17.50	.6890		* S11018	* S13018	* S14018
	45/64	17.86	.7031		S11101	S13101	S14101
	18.00	18.00	.7087		S11102	S13102	S14102
1 .690 (17.53) to .960 (24.38)	23/32	18.26	.7188	5/32 (4.0)	S11103	S13103	S14103
	18.50	18.50	.7283		S11104	S13104	S14104
	47/64	18.65	.7344		S11105	S13105	S14105
	19.00	19.00	.7480		S11106	S13106	S14106
	3/4	19.05	.7500		S11107	S13107	S14107
	49/64	19.45	.7656		S11108	S13108	S14108
	19.50	19.50	.7677		S11109	S13109	S14109
	25/32	19.84	.7812		S11110	S13110	S14110
	20.00	20.00	.7874		S11111	S13111	S14111
	51/64	20.24	.7969		S11112	S13112	S14112
	20.50	20.50	.8071		S11113	S13113	S14113
	13/16	20.64	.8125		S11114	S13114	S14114
	21.00	21.00	.8268		S11115	S13115	S14115
	27/32	21.43	.8438		S11116	S13116	S14116
	55/64	21.83	.8594		S11117	S13117	S14117
	22.00	22.00	.8661		S11118	S13118	S14118
	7/8	22.23	.8750		S11119	S13119	S14119
	57/64	22.62	.8906		S11120	S13120	S14120
	23.00	23.00	.9055		S11121	S13121	S14121
	29/32	23.02	.9062		S11122	S13122	S14122
59/64	23.42	.9219					
15/16	23.81	.9375					
24.00	24.00	.9449					

* 2pcs per package

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels	Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels	Stainless Steels	Cast Iron	Aluminum	Copper Alloys		
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	○	○	◎	○	○

YG SPADE DRILLS

SERIES 2

SPADE DRILL INSERTS - PREMIUM COBALT (M48)

- ▶ Increased tool life over T15
- ▶ For use in high temperature alloys and materials including medium carbon, Alloy and tool steels
- ▶ Rigid set up needed



POINT ANGLE : 132 degree

cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No.		
	Fractional (inch)	Metric (mm)	Decimal (inch)		PREMIUM COBALT (M48)		
					TiN	TiAlN	Hardslick
2 .961 (24.41) to 1.380 (35.05)	31/32	24.61	.9688	3/16 (4.8)	S11201	S13201	S14201
	63/64	25.00	.9843		S11202	S13202	S14202
	1	25.40	1.0000		S11203	S13203	S14203
	1-1/64	25.80	1.0156		S11204	S13204	S14204
		26.00	1.0236		S11205	S13205	S14205
	1-1/32	26.19	1.0312		S11206	S13206	S14206
	1-3/64	26.59	1.0469		S11260	S13260	S14260
	1-1/16	26.99	1.0625		S11207	S13207	S14207
		27.00	1.0630		S11208	S13208	S14208
	1-3/32	27.78	1.0938		S11209	S13209	S14209
		28.00	1.1024		S11210	S13210	S14210
	1-7/64	28.18	1.1094		S11261	S13261	S14261
	1-1/8	28.58	1.1250		S11211	S13211	S14211
		29.00	1.1417		S11212	S13212	S14212
	1-5/32	29.37	1.1562		S11213	S13213	S14213
		30.00	1.1811		S11214	S13214	S14214
	1-3/16	30.16	1.1875		S11215	S13215	S14215
	1-7/32	30.96	1.2188		S11216	S13216	S14216
		31.00	1.2205		S11217	S13217	S14217
	1-1/4	31.75	1.2500		S11218	S13218	S14218
		32.00	1.2598		S11219	S13219	S14219
	1-9/32	32.54	1.2812		S11220	S13220	S14220
		33.00	1.2992		S11221	S13221	S14221
	1-5/16	33.34	1.3125		S11222	S13222	S14222
		34.00	1.3386		S11223	S13223	S14223
	1-11/32	34.13	1.3438		S11224	S13224	S14224
	1-3/8	34.93	1.3750		S11225	S13225	S14225
		35.00	1.3780		S11226	S13226	S14226

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels	Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels	Stainless Steels	Cast Iron	Aluminum	Copper Alloys		
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	○	○	◎	○	○

YG SPADE DRILLS

SERIES Y,Z

CARBIDE BLADE INSERTS C2 (K20), C5 (P40), C3 (K10)

- ▶ High performance on Gray cast iron over 220 Brinell, malleable cast iron with short chips, silicon aluminum and copper alloys. (C3)
- ▶ For general use in carbon steels and alloys steels. (C5)
- ▶ For use in Gray cast iron, nonferrous metals, copper, brass and aluminum. (C2)



POINT ANGLE : 132 degree

cutting conditions : p.309

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No.					
	Fractional (inch)	Metric (mm)	Decimal (inch)		Multi purpose Geometry				Cast Iron Geometry	
					C2 (K20)		C5 (P40)		C3 (K10)	
				TiN	TiAlN	TiN	TiAlN	TiN	TiAlN	
Y .374 (9.50) to .436 (11.07)		9.50	.3740	3/32 (2.4)	*S21Y01	*S23Y01	*S26Y01	*S28Y01	*S16Y01	*S18Y01
	3/8	9.53	.3750		*S21Y02	*S23Y02	*S26Y02	*S28Y02	*S16Y02	*S18Y02
		9.80	.3860		*S21Y03	*S23Y03	*S26Y03	*S28Y03	*S16Y03	*S18Y03
	25/64	9.92	.3906		*S21Y04	*S23Y04	*S26Y04	*S28Y04	*S16Y04	*S18Y04
		10.00	.3937		*S21Y05	*S23Y05	*S26Y05	*S28Y05	*S16Y05	*S18Y05
		10.20	.4016		*S21Y06	*S23Y06	*S26Y06	*S28Y06	*S16Y06	*S18Y06
	13/32	10.32	.4063		*S21Y07	*S23Y07	*S26Y07	*S28Y07	*S16Y07	*S18Y07
		10.50	.4134		*S21Y08	*S23Y08	*S26Y08	*S28Y08	*S16Y08	*S18Y08
	27/64	10.72	.4219		*S21Y09	*S23Y09	*S26Y09	*S28Y09	*S16Y09	*S18Y09
		10.80	.4252		*S21Y10	*S23Y10	*S26Y10	*S28Y10	*S16Y10	*S18Y10
		11.00	.4331		*S21Y11	*S23Y11	*S26Y11	*S28Y11	*S16Y11	*S18Y11
Z .437 (11.11) to .510 (12.95)	7/16	11.11	.4375	3/32 (2.4)	*S21Z01	*S23Z01	*S26Z01	*S28Z01	*S16Z01	*S18Z01
		11.50	.4528		*S21Z02	*S23Z02	*S26Z02	*S28Z02	*S16Z02	*S18Z02
	29/64	11.51	.4531		*S21Z03	*S23Z03	*S26Z03	*S28Z03	*S16Z03	*S18Z03
	15/32	11.91	.4688		*S21Z04	*S23Z04	*S26Z04	*S28Z04	*S16Z04	*S18Z04
		12.00	.4724		*S21Z05	*S23Z05	*S26Z05	*S28Z05	*S16Z05	*S18Z05
	31/64	12.30	.4844		*S21Z06	*S23Z06	*S26Z06	*S28Z06	*S16Z06	*S18Z06
		12.50	.4921		*S21Z07	*S23Z07	*S26Z07	*S28Z07	*S16Z07	*S18Z07
	1/2	12.70	.5000		*S21Z08	*S23Z08	*S26Z08	*S28Z08	*S16Z08	*S18Z08

* 2pcs per package

◎ : Excellent ○ : Good

	P										M	K	N			
	Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
	~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc37 (~HB350)	HRc37~ (HB350~)	~HRc24 (~HB250)	HRc24~ (HB250~)	~HRc13 (~HB200)	HRc13~ (HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (HB220~)	~HRc8 (~HB180)	~HB110
C2(K20)	○	○	○	○	○	◎	◎	○	○	○	○	◎	○	○	◎	◎
C5(P40)	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	○	○	○	○	○
C3(K10)													◎	◎		

YG SPADE DRILLS

SERIES 0

CARBIDE BLADE INSERTS C2 (K20), C5 (P40), C3 (K10)

- ▶ High performance on Gray cast iron over 220 Brinell, malleable cast iron with short chips, silicon aluminum and copper alloys. (C3)
- ▶ For general use in carbon steels and alloys steels. (C5)
- ▶ For use in Gray cast iron, nonferrous metals, copper, brass and aluminum. (C2)



POINT ANGLE : 132 degree

cutting conditions : p.309

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No.					
	Fractional (inch)	Metric (mm)	Decimal (inch)		Multi purpose Geometry				Cast Iron Geometry	
					C2 (K20)		C5 (P40)		C3 (K10)	
				TiN	TiAlN	TiN	TiAlN	TiN	TiAlN	
0 .511 (12.98) to .695 (17.65)		13.00	.5118	1/8 (3.2)	*S21001	*S23001	*S26001	*S28001	*S16001	*S18001
	33/64	13.10	.5156		*S21002	*S23002	*S26002	*S28002	*S16002	*S18002
	17/32	13.49	.5313		*S21003	*S23003	*S26003	*S28003	*S16003	*S18003
		13.50	.5315		*S21004	*S23004	*S26004	*S28004	*S16004	*S18004
	35/64	13.89	.5469		*S21060	*S23060	*S26060	*S28060	*S16060	*S18060
		14.00	.5512		*S21005	*S23005	*S26005	*S28005	*S16005	*S18005
	9/16	14.29	.5625		*S21006	*S23006	*S26006	*S28006	*S16006	*S18006
		14.50	.5709		*S21007	*S23007	*S26007	*S28007	*S16007	*S18007
	37/64	14.68	.5781		*S21008	*S23008	*S26008	*S28008	*S16008	*S18008
		15.00	.5906		*S21009	*S23009	*S26009	*S28009	*S16009	*S18009
	19/32	15.08	.5938		*S21010	*S23010	*S26010	*S28010	*S16010	*S18010
	39/64	15.48	.6094		*S21061	*S23061	*S26061	*S28061	*S16061	*S18061
		15.50	.6102		*S21011	*S23011	*S26011	*S28011	*S16011	*S18011
		15.70	.6181		*S21064	*S23064	*S26064	*S28064	*S16064	*S18064
	5/8	15.88	.6250		*S21012	*S23012	*S26012	*S28012	*S16012	*S18012
		16.00	.6299		*S21013	*S23013	*S26013	*S28013	*S16013	*S18013
	41/64	16.27	.6406		*S21062	*S23062	*S26062	*S28062	*S16062	*S18062
		16.50	.6496		*S21014	*S23014	*S26014	*S28014	*S16014	*S18014
21/32	16.67	.6563	*S21015	*S23015	*S26015	*S28015	*S16015	*S18015		
	17.00	.6693	*S21016	*S23016	*S26016	*S28016	*S16016	*S18016		
43/64	17.07	.6719	*S21063	*S23063	*S26063	*S28063	*S16063	*S18063		
11/16	17.46	.6875	*S21017	*S23017	*S26017	*S28017	*S16017	*S18017		
	17.50	.6890	*S21018	*S23018	*S26018	*S28018	*S16018	*S18018		

* 2pcs per package

◎ : Excellent ○ : Good

	P										M	K	N			
	Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
	~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc37 (~HB350)	HRc37~ (HB350~)	~HRc24 (~HB250)	HRc24~ (HB250~)	~HRc13 (~HB200)	HRc13~ (HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (HB220~)	~HRc8 (~HB180)	~HB110
C2(K20)	○	○	○	○	○	◎	◎	○	○	○	○	◎	○	○	◎	◎
C5(P40)	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	○	○	○	○	○
C3(K10)													◎	◎		

YG SPADE DRILLS

SERIES 1

CARBIDE BLADE INSERTS C2 (K20), C5 (P40), C3 (K10)

- ▶ High performance on Gray cast iron over 220 Brinell, malleable cast iron with short chips, silicon aluminum and copper alloys. (C3)
- ▶ For general use in carbon steels and alloys steels. (C5)
- ▶ For use in Gray cast iron, nonferrous metals, copper, brass and aluminum. (C2)



POINT ANGLE : 132 degree

cutting conditions : p.309

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No.					
	Fractional (inch)	Metric (mm)	Decimal (inch)		Multi purpose Geometry				Cast Iron Geometry	
					C2 (K20)		C5 (P40)		C3 (K10)	
				TiN	TiAlN	TiN	TiAlN	TiN	TiAlN	
1 .690 (17.53) to .960 (24.38)	45/64	17.86	.7031	5/32 (4.0)	S21101	S23101	S26101	S28101	S16101	S18101
		18.00	.7087		S21102	S23102	S26102	S28102	S16102	S18102
	23/32	18.26	.7188		S21103	S23103	S26103	S28103	S16103	S18103
		18.50	.7283		S21104	S23104	S26104	S28104	S16104	S18104
	47/64	18.65	.7344		S21105	S23105	S26105	S28105	S16105	S18105
		19.00	.7480		S21106	S23106	S26106	S28106	S16106	S18106
	3/4	19.05	.7500		S21107	S23107	S26107	S28107	S16107	S18107
	49/64	19.45	.7656		S21108	S23108	S26108	S28108	S16108	S18108
		19.50	.7677		S21109	S23109	S26109	S28109	S16109	S18109
	25/32	19.84	.7813		S21110	S23110	S26110	S28110	S16110	S18110
		20.00	.7874		S21111	S23111	S26111	S28111	S16111	S18111
	51/64	20.24	.7969		S21112	S23112	S26112	S28112	S16112	S18112
		20.50	.8071		S21113	S23113	S26113	S28113	S16113	S18113
	13/16	20.64	.8125		S21114	S23114	S26114	S28114	S16114	S18114
		21.00	.8268		S21115	S23115	S26115	S28115	S16115	S18115
	27/32	21.43	.8438		S21116	S23116	S26116	S28116	S16116	S18116
		21.83	.8594		S21117	S23117	S26117	S28117	S16117	S18117
	7/8	22.23	.8750		S21118	S23118	S26118	S28118	S16118	S18118
		22.62	.8906		S21119	S23119	S26119	S28119	S16119	S18119
	57/64	23.00	.9055		S21120	S23120	S26120	S28120	S16120	S18120
		23.02	.9063		S21121	S23121	S26121	S28121	S16121	S18121
	29/32	23.42	.9219		S21122	S23122	S26122	S28122	S16122	S18122
	23.81	.9375								
	24.00	.9449								

◎ : Excellent ○ : Good

	P										M	K	N			
	Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
	~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc37 (~HB350)	HRc37~ (HB350~)	~HRc24 (~HB250)	HRc24~ (HB250~)	~HRc13 (~HB200)	HRc13~ (HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (HB220~)	~HRc8 (~HB180)	~HB110
C2(K20)	○	○	○	○	○	◎	◎	○	○	○	○	◎	○	○	◎	◎
C5(P40)	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	○	○	○	○	○
C3(K10)													◎	◎		

YG SPADE DRILLS

SERIES 2

CARBIDE BLADE INSERTS C2 (K20), C5 (P40), C3 (K10)

- ▶ High performance on Gray cast iron over 220 Brinell, malleable cast iron with short chips, silicon aluminum and copper alloys. (C3)
- ▶ For general use in carbon steels and alloys steels. (C5)
- ▶ For use in Gray cast iron, nonferrous metals, copper, brass and aluminum. (C2)



POINT ANGLE : 132 degree

cutting conditions : p.309

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No.					
	Fractional (inch)	Metric (mm)	Decimal (inch)		Multi purpose Geometry				Cast Iron Geometry	
					C2 (K20)		C5 (P40)		C3 (K10)	
				TiN	TiAlN	TiN	TiAlN	TiN	TiAlN	
2 .961 (24.41) to 1.380 (35.05)	31/32	24.61	.9688	3/16 (4.8)	S21201	S23201	S26201	S28201	S16201	S18201
	63/64	25.00	.9843		S21202	S23202	S26202	S28202	S16202	S18202
	1	25.40	1.0000		S21203	S23203	S26203	S28203	S16203	S18203
	1-1/64	25.80	1.0156		S21204	S23204	S26204	S28204	S16204	S18204
		26.00	1.0236		S21205	S23205	S26205	S28205	S16205	S18205
	1-1/32	26.19	1.0313		S21206	S23206	S26206	S28206	S16206	S18206
	1-3/64	26.59	1.0469		S21207	S23207	S26207	S28207	S16207	S18207
	1-1/16	26.99	1.0625		S21208	S23208	S26208	S28208	S16208	S18208
		27.00	1.0630		S21209	S23209	S26209	S28209	S16209	S18209
	1-3/32	27.78	1.0938		S21210	S23210	S26210	S28210	S16210	S18210
		28.00	1.1024		S21211	S23211	S26211	S28211	S16211	S18211
	1-7/64	28.18	1.1094		S21212	S23212	S26212	S28212	S16212	S18212
	1-1/8	28.58	1.1250		S21213	S23213	S26213	S28213	S16213	S18213
		29.00	1.1417		S21214	S23214	S26214	S28214	S16214	S18214
	1-5/32	29.37	1.1563		S21215	S23215	S26215	S28215	S16215	S18215
		30.00	1.1811		S21216	S23216	S26216	S28216	S16216	S18216
	1-3/16	30.16	1.1875		S21217	S23217	S26217	S28217	S16217	S18217
	1-7/32	30.96	1.2188		S21218	S23218	S26218	S28218	S16218	S18218
		31.00	1.2205		S21219	S23219	S26219	S28219	S16219	S18219
	1-1/4	31.75	1.2500		S21220	S23220	S26220	S28220	S16220	S18220
		32.00	1.2598		S21221	S23221	S26221	S28221	S16221	S18221
	1-9/32	32.54	1.2813		S21222	S23222	S26222	S28222	S16222	S18222
		33.00	1.2992		S21223	S23223	S26223	S28223	S16223	S18223
	1-5/16	33.34	1.3125		S21224	S23224	S26224	S28224	S16224	S18224
		34.00	1.3386		S21225	S23225	S26225	S28225	S16225	S18225
	1-11/32	34.13	1.3438		S21226	S23226	S26226	S28226	S16226	S18226
1-3/8	34.93	1.3750								
	35.00	1.3780								

◎ : Excellent ○ : Good

	P										M	K	N			
	Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
	~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc37 (~HB350)	HRc37~ (HB350~)	~HRc24 (~HB250)	HRc24~ (HB250~)	~HRc13 (~HB200)	HRc13~ (HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (HB220~)	~HRc8 (~HB180)	~HB110
C2(K20)	○	○	○	○	○	◎	◎	○	○	○	○	◎	○	○	◎	◎
C5(P40)	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	○	○	○	○	○
C3(K10)													◎	◎		

YG SPADE DRILLS

SERIES 3

CARBIDE BLADE INSERTS C2 (K20), C5 (P40), C3 (K10)

- ▶ High performance on Gray cast iron over 220 Brinell, malleable cast iron with short chips, silicon aluminum and copper alloys. (C3)
- ▶ For general use in carbon steels and alloys steels. (C5)
- ▶ For use in Gray cast iron, nonferrous metals, copper, brass and aluminum. (C2)



POINT ANGLE : 132 degree

cutting conditions : p.309

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No.				Cast Iron Geometry	
	Fractional (inch)	Metric (mm)	Decimal (inch)		Multi purpose Geometry				C3 (K10)	
					C2 (K20)		C5 (P40)		TiN	TiAlN
3 1.353 (34.37) to 1.882 (47.80)	1-13/32	35.72	1.4063	1/4 (6.4)	S21301	S23301	S26301	S28301	Special or non-standard inserts available on request	
		36.00	1.4173		S21302	S23302	S26302	S28302		
	1-7/16	36.51	1.4375		S21303	S23303	S26303	S28303		
		37.00	1.4567		S21304	S23304	S26304	S28304		
	1-15/32	37.31	1.4688		S21305	S23305	S26305	S28305		
		38.00	1.4961		S21306	S23306	S26306	S28306		
	1-1/2	38.10	1.5000		S21307	S23307	S26307	S28307		
	1-17/32	38.89	1.5313		S21308	S23308	S26308	S28308		
		39.00	1.5354		S21309	S23309	S26309	S28309		
	1-9/16	39.69	1.5625		S21310	S23310	S26310	S28310		
		40.00	1.5748		S21311	S23311	S26311	S28311		
	1-19/32	40.48	1.5938		S21312	S23312	S26312	S28312		
		41.00	1.6142		S21313	S23313	S26313	S28313		
	1-5/8	41.28	1.6250		S21314	S23314	S26314	S28314		
		42.00	1.6535		S21315	S23315	S26315	S28315		
	1-21/32	42.07	1.6563		S21316	S23316	S26316	S28316		
		42.86	1.6875		S21317	S23317	S26317	S28317		
	1-11/16	43.00	1.6929		S21318	S23318	S26318	S28318		
		43.66	1.7188		S21319	S23319	S26319	S28319		
	1-23/32	44.00	1.7323		S21320	S23320	S26320	S28320		
		44.45	1.7500		S21321	S23321	S26321	S28321		
	1-3/4	45.00	1.7717		S21322	S23322	S26322	S28322		
		45.24	1.7813		S21323	S23323	S26323	S28323		
	1-25/32	46.00	1.8110		S21324	S23324	S26324	S28324		
46.04		1.8125	S21325	S23325	S26325	S28325				
1-13/16	46.83	1.8438	S21326	S23326	S26326	S28326				
	47.00	1.8504	S21327	S23327	S26327	S28327				
1-7/8	47.63	1.8750	S21328	S23328	S26328	S28328				

◎ : Excellent ○ : Good

	P										M	K	N			
	Non-alloyed Steels, Free Machining Steels		Carbon Steels		Alloy Steels		High Alloyed steels		Structural Steels		Tool Steels		Stainless Steels	Cast Iron	Aluminum	Copper Alloys
	~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc37 (~HB350)	HRc37~ (HB350~)	~HRc24 (~HB250)	HRc24~ (HB250~)	~HRc13 (~HB200)	HRc13~ (HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (HB220~)	~HRc8 (~HB180)	~HB110
C2(K20)	○	○	○	○	○	◎	◎	○	○	○	○	◎	○	○	◎	◎
C5(P40)	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	○	○	○	○	○
C3(K10)													◎	◎		




Special features of SM-Point Spade Drill

This "Hybrid Point" combines the strength of the standard point with additional "Web Thinning".

This point increases stability, reduces thrust, improves centering and allows increased speeds and feeds.

Multiple thinning form at the bottom of the large thinning.

- ▶ The optimum thinning for the difference from the cutting speed, the cutting quantity and the cutting load according to the distance from the drill point to the cutting edge.




Radius back face
▶ Wide chip space

Multiple web thinning with the cutting edge of small web thinning.

- ▶ Good self-centering
- ▶ Less tool lead off
- ▶ Reduction in bell mouching, thrust
- ▶ Increased stability

Four-facet point

- ▶ Self-centering
- ▶ Less thrust force



Y/G SPADE DRILLS

SERIES Y,Z,0,1

SM-POINT SPADE DRILL INSERTS - SUPER COBALT (T15)

- ▶ Improved stability and hole straightness by newly developed thinning design.
- ▶ Less thrust force and excellent self-centering.
- ▶ Any non-standard size available.

POINT ANGLE - 132 degree
(Series 5-8 : 144 degree)



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. TiAIN	Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. TiAIN
	Fractional (inch)	Metric (mm)	Decimal (inch)				Fractional (inch)	Metric (mm)	Decimal (inch)		
Y .374 (9.50) to .436 (11.07)	3/8	9.50	.3740	3/32 (2.4)	*SM08Y01	0 .511 (12.98) to .695 (17.65)	41/64	16.00	.6299	1/8 (3.2)	*SM08013
		9.53	.3750		*SM08Y02			16.27	.6406		*SM08062
		9.80	.3858		*SM08Y03			16.50	.6496		*SM08014
	25/64	9.92	.3906		*SM08Y04		16.67	.6562	*SM08015		
		10.00	.3937		*SM08Y05		17.00	.6693	*SM08016		
	13/32	10.20	.4016		*SM08Y06		17.07	.6719	*SM08063		
		10.32	.4062		*SM08Y07		17.46	.6875	*SM08017		
	27/64	10.50	.4134		*SM08Y08		17.50	.6890	*SM08018		
		10.72	.4219		*SM08Y09		17.86	.7031	SM08101		
		10.80	.4252		*SM08Y10		18.00	.7087	SM08102		
	Z .437 (11.11) to .510 (12.95)	7/16	11.11		.4375		*SM08Z01	18.26	.7188		SM08103
11.50			.4528	*SM08Z02	18.50	.7283	SM08104				
29/64		11.51	.4531	*SM08Z03	18.65	.7344	SM08105				
		11.91	.4688	*SM08Z04	19.00	.7480	SM08106				
15/32		12.00	.4724	*SM08Z05	3/4	19.05	.7500	SM08107			
		12.30	.4844	*SM08Z06	49/64	19.45	.7656	SM08108			
31/64		12.50	.4921	*SM08Z07	19.50	.7677	SM08109				
		12.70	.5000	*SM08Z08	25/32	19.84	.7812	SM08110			
0 .511 (12.98) to .695 (17.65)	13/32	13.00	.5118	*SM08001	20.00	.7874	SM08111				
		13.10	.5156	*SM08002	51/64	20.24	.7969	SM08160			
		13.49	.5312	*SM08003	13/16	20.64	.8125	SM08112			
		13.50	.5315	*SM08004	21.00	.8268	SM08114				
	35/64	13.89	.5469	*SM08060	27/32	21.43	.8438	SM08115			
		14.00	.5512	*SM08005	55/64	21.83	.8594	SM08161			
	9/16	14.29	.5625	*SM08006	22.00	.8661	SM08116				
		14.50	.5709	*SM08007	7/8	22.23	.8750	SM08117			
	37/64	14.68	.5781	*SM08008	57/64	22.62	.8906	SM08162			
		15.00	.5906	*SM08009	23.00	.9055	SM08118				
	19/32	15.08	.5938	*SM08010	29/32	23.02	.9062	SM08119			
		15.48	.6094	*SM08061	59/64	23.42	.9219	SM08120			
	39/64	15.50	.6102	*SM08011	15/16	23.81	.9375	SM08121			
		15.88	.6250	*SM08012	24.00	.9449	SM08122				

* 2pcs per package

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels										Stainless Steels	Cast Iron	Aluminum	Copper Alloys		
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎

Y/G SPADE DRILLS

SERIES 2,3

SM-POINT SPADE DRILL INSERTS - SUPER COBALT (T15)

- ▶ Improved stability and hole straightness by newly developed thinning design.
- ▶ Less thrust force and excellent self-centering.
- ▶ Any non-standard size available.

POINT ANGLE - 132 degree
(Series 5-8 : 144 degree)



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. TiAIN	Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. TiAIN
	Fractional (inch)	Metric (mm)	Decimal (inch)				Fractional (inch)	Metric (mm)	Decimal (inch)		
2 .961 (24.41) to 1.380 (35.05)	31/32	24.61	.9688	3/16 (4.8)	SM08201	3 1.353 (34.37) to 1.882 (47.80)	1-13/32	35.72	1.4062	1/4 (6.4)	SM08301
		63/64	25.00		.9843			SM08202	36.00		1.4173
	1	25.40	1.0000		SM08203		1-7/16	36.51	1.4375		SM08303
		25.80	1.0156		SM08204			37.00	1.4567		SM08304
	1-1/64	26.00	1.0236		SM08205		1-15/32	37.31	1.4688		SM08305
		26.19	1.0312		SM08206			38.00	1.4961		SM08306
	1-1/32	26.59	1.0469		SM08260		1-1/2	38.10	1.5000		SM08307
		26.99	1.0625		SM08207			38.89	1.5312		SM08308
	1-1/16	27.00	1.0630		SM08208		1-17/32	39.00	1.5354		SM08309
		27.78	1.0938		SM08209			39.69	1.5625		SM08310
	1-3/32	28.00	1.1024		SM08210		1-9/16	40.00	1.5748		SM08311
		28.18	1.1094		SM08261			40.48	1.5938		SM08312
	1-7/64	28.58	1.1250		SM08211		1-19/32	41.00	1.6142		SM08313
		29.00	1.1417		SM08212			41.28	1.6250		SM08314
	1-5/32	29.37	1.1562		SM08213		1-5/8	42.00	1.6535		SM08315
		30.00	1.1811		SM08214			42.07	1.6562		SM08316
	1-3/16	30.16	1.1875		SM08215		1-21/32	42.86	1.6875		SM08317
		30.96	1.2188		SM08216			43.00	1.6929		SM08318
	1-7/32	31.00	1.2205		SM08217		1-11/16	43.66	1.7188		SM08319
		31.75	1.2500		SM08218			44.00	1.7323		SM08320
	1-1/4	32.00	1.2598		SM08219		1-3/4	44.45	1.7500		SM08321
		32.54	1.2812		SM08220			45.00	1.7717		SM08322
1-9/32	33.00	1.2992	SM08221	1-25/32	45.24	1.7812	SM08323				
	33.34	1.3125	SM08222		46.00	1.8110	SM08324				
1-5/16	34.00	1.3386	SM08223	1-13/16	46.04	1.8125	SM08325				
	34.13	1.3438	SM08224		46.83	1.8438	SM08326				
1-11/32	34.93	1.3750	SM08225	1-27/32	47.00	1.8504	SM08327				
	35.00	1.3780	SM08226		47.63	1.8750	SM08328				

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels										Stainless Steels	Cast Iron	Aluminum	Copper Alloys		
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎

YG SPADE DRILLS

SERIES 4,5

SM-POINT SPADE DRILL INSERTS - SUPER COBALT (T15)

- ▶ Improved stability and hole straightness by newly developed thinning design.
- ▶ Less thrust force and excellent self-centering.
- ▶ Any non-standard size available.

POINT ANGLE - 132 degree
(Series 5-8 : 144 degree)



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. TiAlN	Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. TiAlN
	Fractional (inch)	Metric (mm)	Decimal (inch)				Fractional (inch)	Metric (mm)	Decimal (inch)		
4 1.850 (46.99) to 2.570 (65.28)	1-29/32	48.00	1.8898	5/16 (7.9)	SM08401	4 1.850 (46.99) to 2.570 (65.28)	2-15/32	62.00	2.4409	7/16 (11.1)	SM08433
		48.42	1.9062		62.71			2.4688	SM08434		
	1-15/16	49.00	1.9291		63.00		2.4803	SM08435			
		49.21	1.9375		63.50		2.5000	SM08436			
	1-31/32	50.00	1.9685		64.00		2.5197	SM08437			
		50.01	1.9688		64.29		2.5312	SM08438			
	2	50.80	2.0000		65.00		2.5591	SM08439			
		51.00	2.0079		65.09		2.5625	SM08440			
	2-1/32	51.59	2.0312		65.09		2.5625	SM08440			
		52.00	2.0472		66.00		2.5984	SM08506			
	2-1/16	52.39	2.0625		66.68	2.6250	SM08507				
		53.00	2.0866		67.47	2.6562	SM08508				
	2-3/32	53.18	2.0938		68.00	2.6772	SM08509				
		53.98	2.1250		68.26	2.6875	SM08510				
	2-5/32	54.77	2.1562		69.05	2.7188	SM08511				
		55.00	2.1654		69.85	2.7500	SM08512				
	2-3/16	55.56	2.1875		70.00	2.7559	SM08513				
		56.00	2.2047		70.64	2.7812	SM08514				
	2-7/32	56.36	2.2188		71.44	2.8125	SM08515				
		57.00	2.2441		72.00	2.8346	SM08516				
2-1/4	57.15	2.2500	72.23	2.8438	SM08517						
	57.94	2.2812	73.03	2.8750	SM08518						
2-9/32	58.00	2.2835	73.82	2.9062	SM08519						
	58.74	2.3125	74.00	2.9134	SM08520						
2-5/16	59.00	2.3228	74.61	2.9375	SM08521						
	59.53	2.3438	75.41	2.9688	SM08522						
2-11/32	60.00	2.3622	76.00	2.9921	SM08523						
	60.33	2.3750	76.20	3.0000	SM08524						
2-3/8	61.00	2.4016									
	61.12	2.4062									
2-13/32	61.12	2.4062									
	61.91	2.4375									

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels										Stainless Steels	Cast Iron	Aluminum	Copper Alloys		
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	○	○	○	◎	◎	○	○	○	○	◎	○	○

YG SPADE DRILLS

SERIES 6,7,8

SM-POINT SPADE DRILL INSERTS - SUPER COBALT (T15)

- ▶ Improved stability and hole straightness by newly developed thinning design.
- ▶ Less thrust force and excellent self-centering.
- ▶ Any non-standard size available.

POINT ANGLE - 132 degree
(Series 5-8 : 144 degree)



cutting conditions : p.308

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. TiAlN	Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. TiAlN
	Fractional (inch)	Metric (mm)	Decimal (inch)				Fractional (inch)	Metric (mm)	Decimal (inch)		
6 3.001 (76.23) to 3.507 (89.08)	3-1/32	76.99	3.0312	7/16 (11.1)	SM08601	7 3.455 (87.76) to 4.000 (101.60)	3-23/32	94.00	3.7008	7/16 (11.1)	SM08709
		77.79	3.0625		94.46			3.7188	SM08710		
	3-1/16	78.00	3.0709		95.25		3.7500	SM08711			
		78.58	3.0938		96.00		3.7795	SM08712			
	3-3/32	79.38	3.1250		96.04		3.7812	SM08713			
		80.00	3.1496		96.84		3.8125	SM08714			
	3-1/8	80.17	3.1562		97.63		3.8438	SM08715			
		80.96	3.1875		98.00		3.8583	SM08716			
	3-5/32	81.76	3.2188		98.43		3.8750	SM08717			
		82.00	3.2283		99.22		3.9062	SM08718			
	3-3/16	82.55	3.2500		100.00		3.9370	SM08719			
		83.34	3.2812		100.01		3.9375	SM08720			
	3-7/32	84.00	3.3071		100.81		3.9688	SM08721			
		84.14	3.3125		101.60		4.0000	SM08722			
	7 3.455 (87.76) to 4.000 (101.60)	3-5/16	84.14		3.3125		7/16 (11.1)	SM08614	8 4.001 (101.63) to 4.507 (114.48)		4-1/64
84.93			3.3438	103.19	4.0625	SM08802					
3-11/32		85.73	3.3750	104.00	4.0945	SM08803					
		86.00	3.3858	104.78	4.1250	SM08804					
3-3/8		86.52	3.4063	106.00	4.1732	SM08805					
		87.31	3.4375	106.36	4.1875	SM08806					
3-13/32		88.00	3.4646	107.95	4.2500	SM08807					
		88.11	3.4688	108.00	4.2520	SM08808					
3-7/16		88.90	3.5000	109.54	4.3125	SM08809					
		89.69	3.5312	110.00	4.3307	SM08810					
3-9/16		90.00	3.5433	111.13	4.3750	SM08811					
		90.49	3.5625	112.00	4.4094	SM08812					
3-19/32		91.28	3.5938	112.71	4.4375	SM08813					
		92.00	3.6221	114.00	4.4882	SM08814					
3-5/8		92.08	3.6250	114.30	4.5000	SM08815					
	92.87	3.6562									
3-21/32	92.87	3.6562									
	93.66	3.6875									

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels										Stainless Steels	Cast Iron	Aluminum	Copper Alloys		
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	○	○	○	◎	◎	○	○	○	○	◎	○	○

Y/G SPADE DRILLS

SERIES Y,Z,0,1

SM-POINT SPADE DRILL INSERTS - CARBIDE C5 (P40)

- ▶ Improved stability and hole straightness by newly developed chip thinning design.
- ▶ Less thrust force and excellent self-centering.
- ▶ Any non-standard size available.
- ▶ Increased speeds & feeds



POINT ANGLE : 132 degree

cutting conditions : p.309

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. TiAIN	Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. TiAIN
	Fractional (inch)	Metric (mm)	Decimal (inch)				Fractional (inch)	Metric (mm)	Decimal (inch)		
Y .374 (9.50) to .436 (11.07)		9.50	.3740	3/32 (2.4)	*SM28Y01	0 .511 (12.98) to .695 (17.65)		16.00	.6299	1/8 (3.2)	*SM28013
	3/8	9.53	.3750		*SM28Y02		41/64	16.27	.6406		*SM28062
		9.80	.3858		*SM28Y03			16.50	.6496		*SM28014
	25/64	9.92	.3906		*SM28Y04		21/32	16.67	.6562		*SM28015
		10.00	.3937		*SM28Y05			17.00	.6693		*SM28016
		10.20	.4016		*SM28Y06		43/64	17.07	.6719		*SM28063
	13/32	10.32	.4062		*SM28Y07		11/16	17.46	.6875		*SM28017
		10.50	.4134		*SM28Y08			17.50	.6890		*SM28018
	27/64	10.72	.4219		*SM28Y09		45/64	17.86	.7031		SM28101
		10.80	.4252		*SM28Y10			18.00	.7087		SM28102
		11.00	.4331		*SM28Y11		23/32	18.26	.7188		SM28103
Z .437 (11.11) to .510 (12.95)	7/16	11.11	.4375	3/32 (2.4)	*SM28Z01	1 .690 (17.53) to .960 (24.38)		18.50	.7283	5/32 (4.0)	SM28104
		11.50	.4528		*SM28Z02		47/64	18.65	.7344		SM28105
	29/64	11.51	.4531		*SM28Z03			19.00	.7480		SM28106
	15/32	11.91	.4688		*SM28Z04		3/4	19.05	.7500		SM28107
		12.00	.4724		*SM28Z05		49/64	19.45	.7656		SM28108
	31/64	12.30	.4844		*SM28Z06			19.50	.7677		SM28109
		12.50	.4921		*SM28Z07		25/32	19.84	.7812		SM28110
	1/2	12.70	.5000		*SM28Z08			20.00	.7874		SM28111
0 .511 (12.98) to .695 (17.65)		13.00	.5118	1/8 (3.2)	*SM28001		51/64	20.24	.7969		SM28160
	33/64	13.10	.5156		*SM28002			20.50	.8071		SM28112
	17/32	13.49	.5312		*SM28003		13/16	20.64	.8125		SM28113
		13.50	.5315		*SM28004		21.00	.8268	SM28114		
	35/64	13.89	.5469		*SM28060	27/32	21.43	.8438	SM28115		
		14.00	.5512		*SM28005	55/64	21.83	.8594	SM28161		
	9/16	14.29	.5625		*SM28006		22.00	.8661	SM28116		
		14.50	.5709		*SM28007	7/8	22.23	.8750	SM28117		
	37/64	14.68	.5781		*SM28008	57/64	22.62	.8906	SM28162		
		15.00	.5906		*SM28009		23.00	.9055	SM28118		
	19/32	15.08	.5938		*SM28010	29/32	23.02	.9062	SM28119		
	39/64	15.48	.6094		*SM28061	59/64	23.42	.9219	SM28120		
		15.50	.6102		*SM28011	15/16	23.81	.9375	SM28121		
	5/8	15.88	.6250		*SM28012		24.00	.9449	SM28122		

* 2pcs per package

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels										Stainless Steels	Cast Iron	Aluminum	Copper Alloys		
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎

Y/G SPADE DRILLS

SERIES 2,3

SM-POINT SPADE DRILL INSERTS - CARBIDE C5 (P40)

- ▶ Improved stability and hole straightness by newly developed chip thinning design.
- ▶ Less thrust force and excellent self-centering.
- ▶ Any non-standard size available.
- ▶ Increased speeds & feeds



POINT ANGLE : 132 degree

cutting conditions : p.309

Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. TiAIN	Series Min. to Max. (inch/mm)	Diameter			Thick Fractional [Metric]	EDP No. TiAIN
	Fractional (inch)	Metric (mm)	Decimal (inch)				Fractional (inch)	Metric (mm)	Decimal (inch)		
2 .961 (24.41) to 1.380 (35.05)	31/32	24.61	.9688	3/16 (4.8)	SM28201	3 1.353 (34.37) to 1.882 (47.80)	1-13/32	35.72	1.4062	1/4 (6.4)	SM28301
	63/64	25.00	.9843		SM28202			36.00	1.4173		SM28302
	1	25.40	1.0000		SM28203		1-7/16	36.51	1.4375		SM28303
	1-1/64	25.80	1.0156		SM28204			37.00	1.4567		SM28304
		26.00	1.0236		SM28205		1-15/32	37.31	1.4688		SM28305
	1-1/32	26.19	1.0312		SM28206			38.00	1.4961		SM28306
	1-3/64	26.59	1.0469		SM28260		1-1/2	38.10	1.5000		SM28307
	1-1/16	26.99	1.0625		SM28207		1-17/32	38.89	1.5312		SM28308
		27.00	1.0630		SM28208			39.00	1.5354		SM28309
	1-3/32	27.78	1.0938		SM28209		1-9/16	39.69	1.5625		SM28310
		28.00	1.1024		SM28210			40.00	1.5748		SM28311
	1-7/64	28.18	1.1094		SM28261		1-19/32	40.48	1.5938		SM28312
	1-1/8	28.58	1.1250		SM28211			41.00	1.6142		SM28313
		29.00	1.1417		SM28212		1-5/8	41.28	1.6250		SM28314
	1-5/32	29.37	1.1562		SM28213			42.00	1.6535		SM28315
		30.00	1.1811		SM28214		1-21/32	42.07	1.6562		SM28316
	1-3/16	30.16	1.1875		SM28215		1-11/16	42.86	1.6875		SM28317
	1-7/32	30.96	1.2188		SM28216			43.00	1.6929		SM28318
		31.00	1.2205		SM28217		1-23/32	43.66	1.7188		SM28319
	1-1/4	31.75	1.2500		SM28218			44.00	1.7323		SM28320
		32.00	1.2598		SM28219		1-3/4	44.45	1.7500		SM28321
	1-9/32	32.54	1.2812		SM28220			45.00	1.7717		SM28322
	33.00	1.2992	SM28221	1-25/32	45.24	1.7812	SM28323				
1-5/16	33.34	1.3125	SM28222		46.00	1.8110	SM28324				
	34.00	1.3386	SM28223	1-13/16	46.04	1.8125	SM28325				
1-11/32	34.13	1.3438	SM28224	1-27/32	46.83	1.8438	SM28326				
1-3/8	34.93	1.3750	SM28225		47.00	1.8504	SM28327				
	35.00	1.3780	SM28226	1-7/8	47.63	1.8750	SM28328				

◎ : Excellent ○ : Good

P										M	K	N			
Non-alloyed Steels, Free Machining Steels										Stainless Steels	Cast Iron	Aluminum	Copper Alloys		
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc28 (~HB275)	HRc28~ (~HB275~)	~HRc37 (~HB350)	HRc37~ (~HB350~)	~HRc24 (~HB250)	HRc24~ (~HB250~)	~HRc13 (~HB200)	HRc13~ (~HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (~HB220~)	~HRc8 (~HB180)	~HB110
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎

YG SPADE DRILLS

SERIES Y,Z,0,1,2

SPADE DRILL FLAT BOTTOM INSERTS - SUPER COBALT (T15)

POINT ANGLE : 180 degree



cutting conditions : p.309

Series	Diameter		Thick	EDP No.		Series	Diameter		Thick	EDP No.	
	Fractional (inch)	Decimal (inch)		Fractional [Metric]	TiN		TiAlN	Fractional (inch)		Decimal (inch)	Fractional [Metric]
Y	3/8	.3750	3/32 (2.4)	SF05024	SF15024	2	31/32	.9688	3/16 (4.8)	SF05062	SF15062
	13/32	.4063		SF05026	SF15026		1	1.0000		SF05100	SF15100
Z	7/16	.4375	3/32 (2.4)	SF05028	SF15028		1-1/32	1.0313		SF05102	SF15102
	15/32	.4688		SF05030	SF15030		1-1/16	1.0625		SF05104	SF15104
	1/2	.5000		SF05032	SF15032		1-3/32	1.0938		SF05106	SF15106
0	17/32	.5313	1/8 (3.2)	SF05034	SF15034		1-1/8	1.1250		SF05108	SF15108
	9/16	.5625		SF05036	SF15036		1-5/32	1.1563		SF05110	SF15110
	19/32	.5938		SF05038	SF15038		1-3/16	1.1875		SF05112	SF15112
	5/8	.6250		SF05040	SF15040		1-7/32	1.2188		SF05114	SF15114
1	21/32	.6563	5/32 (4.0)	SF05042	SF15042		1-1/4	1.2500		SF05116	SF15116
	11/16	.6875		SF05044	SF15044		1-9/32	1.2813		SF05118	SF15118
	23/32	.7188		SF05046	SF15046		1-5/16	1.3125		SF05120	SF15120
	3/4	.7500		SF05048	SF15048	1-11/32	1.3438	SF05122	SF15122		
	25/32	.7813		SF05050	SF15050	1-3/8	1.3750	SF05124	SF15124		
	13/16	.8125		SF05052	SF15052						
	27/32	.8438	SF05054	SF15054							
	7/8	.8750	SF05056	SF15056							
	29/32	.9063	SF05058	SF15058							
	15/16	.9375	SF05060	SF15060							


◎ : Excellent ○ : Good

P										M	K	N				
Non-alloyed Steels, Free Machining Steels					Alloy Steels					High Alloyed steels	Structural Steels	Tool Steels	Stainless Steels	Cast Iron	Aluminum	Copper Alloys
~HRc24 (~HB250)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc28 (~HB275)	HRc28~ (HB275~)	~HRc37 (~HB350)	HRc37~ (HB350~)	~HRc24 (~HB250)	HRc24~ (HB250~)	~HRc13 (~HB200)	HRc13~ (HB200~)	~HRc28 (~HB275)	~HRc19 (~HB220)	HRc19~ (HB220~)	~HRc8 (~HB180)		~HB110
◎	◎	◎	◎	◎	○	○	○	○	○	○	○	○	○	◎	○	○

YG SPADE DRILLS


P13 SERIES
P14 SERIES

STRAIGHT SHANK HOLDER, STRAIGHT FLUTE



SHORT LENGTH

Series	EDP No.	Drill Insert Range	Max. Drill Depth	Flute Length	Ref. Length	Overall Length	Shank		Pipe Tap
							Dia.	Length	
		A	B	C	D	E	F	G	
Y	P13Y01	3/8 - 27/64	1-1/4	2-1/32	2-1/8	4-13/32	3/4	2-3/8	1/8
Z	P13Z01	7/16 - 1/2	1-1/4	2-1/32	2-1/8	4-13/32	3/4	2-3/8	1/8
0	P13001	33/64 - 11/16	1-3/8	2-3/16	2-19/64	4-9/16	3/4	2-3/8	1/8
0.5	P13051	39/64 - 11/16	1-3/8	2-3/16	2-19/64	4-9/16	3/4	2-3/8	1/8
1	P13101	45/64 - 15/16	2-5/8	3-7/8	4-1/64	6-7/8	3/4	3	1/8
	P13102	45/64 - 15/16	2-5/8	3-7/8	4-1/64	6-7/8	1	3	1/8
1.5	P13151	55/64 - 15/16	2-5/8	3-7/8	4-1/64	6-7/8	3/4	3	1/8
	P13152	55/64 - 15/16	2-5/8	3-7/8	4-1/64	6-7/8	1	3	1/8
2	P13202	31/32 - 1-3/8	3-3/8	4-1/2	4-41/64	8	1	3-1/2	1/8
	P13203	31/32 - 1-3/8	3-3/8	4-1/2	4-41/64	8	1-1/4	3-1/2	1/8
2.5	P13252	1-3/16 - 1-3/8	3-3/8	4-1/2	4-41/64	8	1	3-1/2	1/8
	P13253	1-3/16 - 1-3/8	3-3/8	4-1/2	4-41/64	8	1-1/4	3-1/2	1/8
3	P13303	1-13/32 - 1-7/8	4-3/4	6	6-3/16	10	1-1/4	4	1/4
	P13304	1-13/32 - 1-7/8	4-3/4	6	6-3/16	10	1-1/2	4	1/4
4	P13404	1-29/32 - 2-9/16	5-1/8	6-1/2	6-11/16	10-1/2	1-1/2	4	1/4
	P13405	1-29/32 - 2-9/16	5-1/8	6-1/2	6-11/16	10-1/2	1-3/4	4	1/4
5-6	P13506	2-1/2 - 3-1/2	6-3/4	8-1/2	8-3/4	12-1/2	2	4	1/2
7-8	P13708	3-17/32 - 4-1/2	6-3/4	8-7/8	9-1/8	13-7/8	3	5	1/2




INTERMEDIATE LENGTH

Series	EDP No.	Drill Insert Range	Max. Drill Depth	Flute Length	Ref. Length	Overall Length	Shank		Pipe Tap
							Dia.	Length	
		A	B	C	D	E	F	G	
1	P14102	45/64 - 15/16	4-5/8	5-7/8	6-1/64	8-7/8	1	3	1/8
1.5	P14152	55/64 - 15/16	4-5/8	5-7/8	6-1/64	8-7/8	1	3	1/8
2	P14203	31/32 - 1-3/8	5-3/8	6-1/2	6-41/64	10	1-1/4	3-1/2	1/8
2.5	P14253	1-3/16 - 1-3/8	5-3/8	6-1/2	6-41/64	10	1-1/4	3-1/2	1/8
3	P14304	1-13/32 - 1-7/8	6-1/2	7-3/4	7-15/16	11-3/4	1-1/2	4	1/4

- i-DREAM DRILLS
- DREAM DRILLS -GENERAL
- DREAM DRILLS -HIGH FEED
- DREAM DRILLS -FLAT BOTTOM
- DREAM DRILLS -INOX
- DREAM DRILLS -ALU
- DREAM DRILLS -MQL TYPE
- DREAM DRILLS for HIGH HARDENED STEELS
- STANDARD CARBIDE DRILLS
- MULTI-1 DRILLS
- HPD DRILLS
- GOLD-P DRILLS
- STRAIGHT SHANK DRILLS
- AIRCRAFT DRILLS
- SILVER & DEMING DRILLS
- TAPER SHANK DRILLS
- NC SPOTTING DRILLS
- COMBINATION DRILLS & COUNTERSINK
- SPADE DRILLS
- TECHNICAL DATA

STRAIGHT SHANK HOLDER, STRAIGHT FLUTE




STANDARD LENGTH

Unit : Inch

Series	EDP No.	Drill Insert Range A	Max. Drill Depth B	Flute Length C	Ref. Length D	Overall Length E	Shank		Pipe Tap G
							Dia.	Length F	
Y	P15Y01	3/8 - 27/64	2-3/8	3-5/32	3-1/4	5-17/32	3/4	2-3/8	1/8
Z	P15Z01	7/16 - 1/2	2-3/8	3-5/32	3-1/4	5-17/32	3/4	2-3/8	1/8
O	P15O01	33/64 - 11/16	2-1/2	3-5/16	3-27/64	5-11/16	3/4	2-3/8	1/8
0.5	P15051	39/64 - 11/16	2-1/2	3-5/16	3-27/64	5-11/16	3/4	2-3/8	1/8
1	P15101	45/64 - 15/16	6-5/8	7-7/8	8-1/64	10-7/8	3/4	3	1/8
	P15102	45/64 - 15/16	6-5/8	7-7/8	8-1/64	10-7/8	1	3	1/8
1.5	P15151	55/64 - 15/16	6-5/8	7-7/8	8-1/64	10-7/8	3/4	3	1/8
	P15152	55/64 - 15/16	6-5/8	7-7/8	8-1/64	10-7/8	1	3	1/8
2	P15202	31/32 - 1-3/8	7-3/8	8-1/2	8-41/64	12	1	3-1/2	1/8
	P15203	31/32 - 1-3/8	7-3/8	8-1/2	8-41/64	12	1-1/4	3-1/2	1/8
2.5	P15252	1-3/16 - 1-3/8	7-3/8	8-1/2	8-41/64	12	1	3-1/2	1/8
	P15253	1-3/16 - 1-3/8	7-3/8	8-1/2	8-41/64	12	1-1/4	3-1/2	1/8
3	P15303	1-13/32 - 1-7/8	8-1/4	9-1/2	9-11/16	13-1/2	1-1/4	4	1/4
	P15304	1-13/32 - 1-7/8	8-1/4	9-1/2	9-11/16	13-1/2	1-1/2	4	1/4
4	P15404	1-29/32 - 2-9/16	9-1/8	10-1/2	10-11/16	14-1/2	1-1/2	4	1/4
	P15405	1-29/32 - 2-9/16	9-1/8	10-1/2	10-11/16	14-1/2	1-3/4	4	1/4
5-6	P15506	2-1/2 - 3-1/2	10-3/4	12-1/2	12-3/4	16-1/2	2	4	1/2
7-8	P15708	3-17/32 - 4-1/2	10-3/4	12-7/8	13-1/8	17-7/8	3	5	1/2

STRAIGHT SHANK HOLDER, STRAIGHT FLUTE



EXTENDED LENGTH


Unit : Inch

Series	EDP No.	Drill Insert Range A	Max. Drill Depth B	Flute Length C	Ref. Length D	Overall Length E	Shank		Pipe Tap G
							Dia.	Length F	
Y	P16Y01	3/8 - 27/64	4-3/8	5-5/32	5-1/4	7-17/32	3/4	2-3/8	1/8
Z	P16Z01	7/16 - 1/2	4-3/8	5-5/32	5-1/4	7-17/32	3/4	2-3/8	1/8
O	P16O01	33/64 - 11/16	4-1/2	5-5/16	5-27/64	7-11/16	3/4	2-3/8	1/8
0.5	P16051	39/64 - 11/16	4-1/2	5-5/16	5-27/64	7-11/16	3/4	2-3/8	1/8
1	P16102	45/64 - 15/16	10-5/8	11-7/8	12-1/64	14-7/8	1	3	1/8
1.5	P16152	55/64 - 15/16	10-5/8	11-7/8	12-1/64	14-7/8	1	3	1/8
2	P16203	31/32 - 1-3/8	11-3/8	12-1/2	12-41/64	16	1-1/4	3-1/2	1/8
2.5	P16253	1-3/16 - 1-3/8	11-3/8	12-1/2	12-41/64	16	1-1/4	3-1/2	1/8
3	P16303	1-13/32 - 1-7/8	13-3/4	15	15-3/16	19	1-1/4	4	1/4
4	P16404	1-29/32 - 2-9/16	16-5/8	18	18-3/16	22	1-1/2	4	1/4
5-6	P16506	2-1/2 - 3-1/2	18-1/4	20	20-1/4	24	2	4	1/2
7-8	P16708	3-17/32 - 4-1/2	21-7/8	24	24-1/4	29	3	5	1/2

Y/G SPADE DRILLS

P17 SERIES


STRAIGHT SHANK HOLDER, STRAIGHT FLUTE



LONG LENGTH

Unit : Inch

Series	EDP No.	Drill Insert Range A	Max. Drill Depth B	Flute Length C	Ref. Length D	Overall Length E	Shank		Pipe Tap G
							Dia. F	Length	
O	P17001	33/64 - 11/16	7	7-13/16	7-59/64	10-3/16	3/4	2-3/8	1/8
O.5	P17051	39/64 - 11/16	7	7-13/16	7-59/64	10-3/16	3/4	2-3/8	1/8



EXTRA LONG LENGTH


Unit : Inch

Series	EDP No.	Drill Insert Range A	Max. Drill Depth B	Flute Length C	Ref. Length D	Overall Length E	Shank		Pipe Tap G
							Dia. F	Length	
1	P17101	45/64 - 15/16	18	19-1/4	19-25/64	22-1/4	1	3	1/8
2	P17202	31/32 - 1-3/8	20-1/8	21-1/4	21-25/64	24-3/4	1-1/4	3-1/2	1/8
3	P17303	1-13/32 - 1-7/8	22	23-1/4	23-7/16	27-1/4	1-1/2	4	1/4
4	P17404	1-29/32 - 2-9/16	24-5/8	26	26-3/16	30	1-1/2	4	1/4
5	P17506	2-1/2 - 3-1/2	26	27-3/4	28	31-3/4	2	4	1/2
7	P17708	3-17/32 - 4-1/2	27	29-1/8	29-3/8	34-1/8	3	5	1/2

Y/G SPADE DRILLS

P01 SERIES
P08 SERIES

TAPER SHANK HOLDER, STRAIGHT FLUTE / HELICAL FLUTE




SHORT LENGTH

Unit : Inch

Series	EDP No.	Drill Insert Range A	Max. Drill Depth B	Flute Length C	Ref. Length D	Overall Length E	MT F	Pipe Tap G	RCI H
Z	P01Z02	7/16 - 1/2	1-1/4	2-1/32	3-15/32	6-5/16	#2	1/16	PR1030
O	P01002	33/64 - 11/16	1-3/8	2-3/16	3-41/64	6-15/32	#2	1/16	PR1030
O.5	P01052	39/64 - 11/16	1-3/8	2-3/16	3-41/64	6-15/32	#2	1/16	PR1030
1	P01103	45/64 - 15/16	2-3/4	3-7/8	5-39/64	9-5/32	#3	1/8	PR1031
	P01104	45/64 - 15/16	2-3/4	3-7/8	5-43/64	10-5/32	#4	1/8	PR1031
1.5	P01153	55/64 - 15/16	2-3/4	3-7/8	5-39/64	9-5/32	#3	1/8	PR1031
	P01154	55/64 - 15/16	2-3/4	3-7/8	5-43/64	10-5/32	#4	1/8	PR1031
2	P01203	31/32 - 1-3/8	3-3/8	4-1/2	6-15/64	9-25/32	#3	1/8	PR1031
	P01204	31/32 - 1-3/8	3-3/8	4-1/2	6-19/64	10-25/32	#4	1/8	PR1031
2.5	P01253	1-3/16 - 1-3/8	3-3/8	4-1/2	6-15/64	9-25/32	#3	1/8	PR1031
	P01254	1-3/16 - 1-3/8	3-3/8	4-1/2	6-37/64	11-1/16	#4	1/4	PR1042
3	P01304	1-13/32 - 1-7/8	4-3/4	6	8-1/8	12-9/16	#4	1/4	PR1042
	P01305	1-13/32 - 1-7/8	4-3/4	6	8-1/8	13-13/16	#5	1/4	PR1043
4	P01404	1-29/32 - 2-9/16	5-1/8	6-1/2	8-5/8	13-1/16	#4	1/4	PR1042
	P01405	1-29/32 - 2-9/16	5-1/8	6-1/2	8-5/8	14-5/16	#5	1/4	PR1043
5-6	P01505	2-1/2 - 3-1/2	6-3/4	8-1/2	11-5/16	16-15/16	#5	1/2	PR1054
7-8	P01705	3-17/32 - 4-1/2	6-3/4	8-7/8	11-11/16	17-5/16	#5	1/2	PR1054

► You can also apply RCI(Rotary Coolant Inducer) for internal cooling. (See page 307)



INTERMEDIATE LENGTH

Unit : Inch


Series	EDP No.	Drill Insert Range A	Max. Drill Depth B	Flute Length C	Ref. Length D	Overall Length E	MT F	Pipe Tap G	RCI H
1.5	P08153	55/64 - 15/16	4-3/4	5-7/8	7-39/64	11-5/32	#3	1/8	PR1031
2	P08204	31/32 - 1-3/8	5-3/8	6-1/2	8-19/64	12-25/32	#4	1/8	PR1031
2.5	P08254	1-3/16 - 1-3/8	5-3/8	6-1/2	8-37/64	13-1/16	#4	1/4	PR1042

► You can also apply RCI(Rotary Coolant Inducer) for internal cooling. (See page 307)

- i-DREAM DRILLS
- DREAM DRILLS -GENERAL
- DREAM DRILLS -HIGH FEED
- DREAM DRILLS -FLAT BOTTOM
- DREAM DRILLS -INOX
- DREAM DRILLS -ALU
- DREAM DRILLS -MQL TYPE
- DREAM DRILLS for HIGH HARDENED STEELS
- STANDARD CARBIDE DRILLS
- MULTI-1 DRILLS
- HPD DRILLS
- GOLD-P DRILLS
- STRAIGHT SHANK DRILLS
- AIRCRAFT DRILLS
- SILVER & DEMING DRILLS
- TAPER SHANK DRILLS
- NC SPOTTING DRILLS
- COMBINATION DRILLS & COUNTERSINK
- SPADE DRILLS
- TECHNICAL DATA

- i-DREAM DRILLS
- DREAM DRILLS -GENERAL
- DREAM DRILLS -HIGH FEED
- DREAM DRILLS -FLAT BOTTOM
- DREAM DRILLS -INOX
- DREAM DRILLS -ALU
- DREAM DRILLS -MQL TYPE
- DREAM DRILLS for HIGH HARDENED STEELS
- STANDARD CARBIDE DRILLS
- MULTI-1 DRILLS
- HPD DRILLS
- GOLD-P DRILLS
- STRAIGHT SHANK DRILLS
- AIRCRAFT DRILLS
- SILVER & DEMING DRILLS
- TAPER SHANK DRILLS
- NC SPOTTING DRILLS
- COMBINATION DRILLS & COUNTERSINK
- SPADE DRILLS
- TECHNICAL DATA

TAPER SHANK HOLDER, TAPER FLUTE




STANDARD LENGTH

Unit : Inch

Series	EDP No.	Drill Insert Range A	Max. Drill Depth B	Flute Length C	Ref. Length D	Overall Length E	MT F	Pipe Tap G	RCI H
Z	P03Z02	7/16 - 1/2	2-3/8	3-5/32	4-19/32	7-7/16	#2	1/16	PR1030
0	P03002	33/64 - 11/16	2-1/2	3-5/16	4-49/64	7-19/32	#2	1/16	PR1030
0.5	P03052	39/64 - 11/16	2-1/2	3-5/16	4-49/64	7-19/32	#2	1/16	PR1030
1	P03103	45/64 - 15/16	6-3/4	7-7/8	9-39/64	13-5/32	#3	1/8	PR1031
	P03104	45/64 - 15/16	6-3/4	7-7/8	9-43/64	14-5/32	#4	1/8	PR1031
1.5	P03153	55/64 - 15/16	6-3/4	7-7/8	9-39/64	13-5/32	#3	1/8	PR1031
	P03154	55/64 - 15/16	6-3/4	7-7/8	9-43/64	14-5/32	#4	1/8	PR1031
2	P03203	31/32 - 1-3/8	7-3/8	8-1/2	10-15/64	13-25/32	#3	1/8	PR1031
	P03204	31/32 - 1-3/8	7-3/8	8-1/2	10-19/64	14-25/32	#4	1/8	PR1031
2.5	P03253	1-3/16 - 1-3/8	7-3/8	8-1/2	10-15/64	13-25/32	#3	1/8	PR1031
	P03254	1-3/16 - 1-3/8	7-3/8	8-1/2	10-37/64	15-1/16	#4	1/4	PR1042
3	P03304	1-13/32 - 1-7/8	8-1/4	9-1/2	11-5/8	16-1/16	#4	1/4	PR1042
	P03305	1-13/32 - 1-7/8	8-1/4	9-1/2	11-5/8	17-5/16	#5	1/4	PR1043
4	P03404	1-29/32 - 2-9/16	9-1/8	10-1/2	12-5/8	17-1/16	#4	1/4	PR1042
	P03405	1-29/32 - 2-9/16	9-1/8	10-1/2	12-5/8	18-5/16	#5	1/4	PR1043
5-6	P03505	2-1/2 - 3-1/2	10-3/4	12-1/2	15-5/16	20-15/16	#5	1/2	PR1054
7-8	P03705	3-17/32 - 4-1/2	10-3/4	12-7/8	15-11/16	21-5/16	#5	1/2	PR1054

► You can also apply RCI(Rotary Coolant Inducer) for internal cooling. (See page 307)


FLANGED STRAIGHT SHANK HOLDER, STRAIGHT FLUTE



SHORT LENGTH

Unit : Inch

Series	EDP No.	Drill Insert Range A	Max. Drill Depth B	Flute Length C	Ref. Length D	Overall Length E	Shank		Pipe Tap G
							Dia. F	Length	
Y	P25Y01	3/8 - 27/64	1-1/4	2-13/32	2-1/2	4-7/16	3/4	2-1/32	1/8
Z	P25Y01	7/16 - 1/2	1-1/4	2-13/32	2-1/2	4-7/16	3/4	2-1/32	1/8
0	P25001	33/64 - 11/16	1-3/8	2-1/2	2-39/64	4-17/32	3/4	2-1/32	1/8
0.5	P25051	39/64 - 11/16	1-3/8	2-1/2	2-39/64	4-17/32	3/4	2-1/32	1/8
1	P25102	45/64 - 15/16	2-5/8	4-7/32	4-23/64	6-1/2	1	2-9/32	1/8
1.5	P25152	55/64 - 15/16	2-5/8	4-7/32	4-23/64	6-1/2	1	2-9/32	1/8
2	P25203	31/32 - 1-3/8	3-3/8	5-1/16	5-13/64	7-11/32	1-1/4	2-9/32	1/4
2.5	P25253	1-3/16 - 1-3/8	3-3/8	5-1/16	5-13/64	7-11/32	1-1/4	2-9/32	1/4
3	P25303	1-13/32 - 1-7/8	4-3/4	6-13/16	7	9-1/2	1-1/2	2-11/16	1/4
4	P25404	1-29/32 - 2-9/16	5-1/8	7-1/16	7-1/4	9-3/4	1-1/2	2-11/16	1/4



INTERMEDIATED LENGTH

Unit : Inch


Series	EDP No.	Drill Insert Range A	Max. Drill Depth B	Flute Length C	Ref. Length D	Overall Length E	Shank		Pipe Tap G
							Dia. F	Length	
1	P26102	45/64 ~ 15/16	4-5/8	6-3/32	6-15/64	8-3/8	1	2-9/32	1/8
1.5	P26152	55/64 ~ 15/16	4-5/8	6-3/32	6-15/64	8-3/8	1	2-9/32	1/8
2	P26203	31/32 ~ 1-3/8	5-3/8	7-1/16	7-13/64	9-11/32	1-1/4	2-9/32	1/4
2.5	P26253	1-3/16 ~ 1-3/8	5-3/8	7-1/16	7-13/64	9-11/32	1-1/4	2-9/32	1/4
3	P26304	1-13/32 ~ 1-7/8	6-1/2	8-9/16	8-3/4	11-1/4	1-1/2	2-11/32	1/4



P27 SERIES

P28 SERIES


FLANGED STRAIGHT SHANK HOLDER, STRAIGHT FLUTE



STANDARD LENGTH

Unit : Inch

Series	EDP No.	Drill Insert Range	Max. Drill Depth	Flute Length	Ref. Length	Overall Length	Shank		Pipe Tap
							Dia.	Length	
		A	B	C	D	E	F		G
Y	P27Y01	3/8 ~ 27/64	2-3/8	3-17/32	3-5/8	5-9/16	3/4	2-1/32	1/8
Z	P27Z01	7/16 ~ 1/2	2-3/8	3-17/32	3-5/8	5-9/16	3/4	2-1/32	1/8
O	P27O01	33/64 ~ 11/16	2-1/2	3-5/8	3-47/64	5-21/32	3/4	2-1/32	1/8
0.5	P27O51	39/64 ~ 11/16	2-1/2	3-5/8	3-47/64	5-21/32	3/4	2-1/32	1/8
1	P27102	45/64 ~ 15/16	6-5/8	8-3/32	8-15/64	10-3/8	1	2-9/32	1/8
1.5	P27152	55/64 ~ 15/16	6-5/8	8-3/32	8-15/64	10-3/8	1	2-9/32	1/8
2	P27203	31/32 ~ 1-3/8	7-3/8	9-1/16	9-13/64	11-11/32	1-1/4	2-9/32	1/4
2.5	P27253	1-3/16 ~ 1-3/8	7-3/8	9-1/16	9-13/64	11-11/32	1-1/4	2-9/32	1/4
3	P27303	1-13/32 ~ 1-7/8	8-1/4	10-5/16	10-1/2	13	1-1/2	2-11/16	1/4
4	P27404	1-29/32 ~ 2-9/16	9-1/8	11-1/16	11-1/4	13-3/4	1-1/2	2-11/16	1/4



EXTENDED LENGTH

Unit : Inch

Series	EDP No.	Drill Insert Range	Max. Drill Depth	Flute Length	Ref. Length	Overall Length	Shank		Pipe Tap
							Dia.	Length	
		A	B	C	D	E	F		G
Y	P28Y01	3/8 ~ 27/64	4-3/8	5-17/32	5-5/8	7-9/16	3/4	2-1/32	1/8
Z	P28Y01	7/16 ~ 1/2	4-3/8	5-17/32	5-5/8	7-9/16	3/4	2-1/32	1/8
O	P28O01	33/64 ~ 11/16	4-1/2	5-5/8	5-47/64	7-21/32	3/4	2-1/32	1/8
0.5	P28O51	39/64 ~ 11/16	4-1/2	5-5/8	5-47/64	7-21/32	3/4	2-1/32	1/8
1	P28102	45/64 ~ 15/16	10-5/8	12-3/32	12-15/64	14-3/8	1	2-9/32	1/8
1.5	P28152	55/64 ~ 15/16	10-5/8	12-3/32	12-15/64	14-3/8	1	2-9/32	1/8
2	P28203	31/32 ~ 1-3/8	11-3/8	13-1/16	13-13/64	15-11/32	1-1/4	2-9/32	1/4
2.5	P28253	1-3/16 ~ 1-3/8	11-3/8	13-1/16	13-13/64	15-11/32	1-1/4	2-9/32	1/4




RECOMMENDED CUTTING CONDITIONS

HOLDER ACCESSORIES

TORX SCREWS AND PREMIUM TORX HAND DRIVERS

Series	Torx Screws		Torx Screws (Nylon Locking)		Premium Torx Drivers	Drill Range		Torque in Lbs. 5.5
	Item	PKG EDP No. (10 Screws)	Item	PKG EDP No. (10 Screws)		Inch	Metric	
					EDP No.	inch	mm	
Y	2XT7	J7Y001	2XT7N	J7Y006	J5Y007	3/8 - 27/64	9.5 - 11.0	5.5
Z	2LXT7	J7Z011	2LXT7N	J7Z016	J5Y007	7/16 - 1/2	11.5 - 12.5	5.5
O	2.5XT8	J8O021	2.5XT8N	J8O026	J5O008	33/64 - 11/16	13.0 - 17.5	11.0
0.5	2.5LXT8	J8O531	2.5LXT8N	J8O536	J5O008	39/64 - 11/16	15.5 - 17.5	11.0
1	3XT9	J91O41	3XT9N	J91O46	J51O09	45/64 - 15/16	18.0 - 24.0	20.0
1.5	3LXT9	J91551	3LXT9N	J91556	J51O09	55/64 - 15/16	22.0 - 24.0	20.0
2	4XT15	JB2O61	4XT15N	JB2O66	J52O15	31/32 - 1-3/8	25.0 - 35.0	45.0
2.5	4XT15	JB2O61	4XT15N	JB2O66	J52O15	31/32 - 1-3/8	30.0 - 35.0	45.0
3-4	5XT20	JC3O81	5XT20N	JC3O86	J53O20	1-13/32 - 2-9/16	36.0 - 65.0	90.0
5-8	6XT25	JD5O91	6XT25N	JD5O96	J55O25	2-1/2 - 4-1/2	64.0 - 114.0	155.0

NOTE : Replacement screws sold in packages (10 screws per package)



ROTARY COOLANT INDUCER (RCI) AND ACCESSORIES



Complete with O'Rings, Flat Washers and Locking Clips.


EDP No.	I.D.	Pipe O.D.	Length	Tap	Thread for Driving Rod
	A	B			
PR1030	1-3/4	3/4	7/8	1/8	5/16 - NC
PR1031	2-1/8	1	1-1/8	1/8	5/16 - NC
PR1042	2-1/2	1-1/4	1-3/8	1/4	3/8 - NC
PR1043	3	1-3/4	1-3/8	1/4	3/8 - NC
PR1054	3-3/4	2-1/4	1-3/4	1/2	1/2 - NC




RECOMMENDED CUTTING CONDITIONS

SPADE BLADE INSERTS SELECTION & APPLICATIONS HSS

Toughness Values



Wear Values



- WHEN TO USE M4
WHEN TO USE T15
WHEN TO USE M48
WHEN TO USE SM POINT

SPEEDS - FEED RECOMMENDATIONS (STD POINT-SM POINT)

STANDARD GEOMETRY
SM POINT

Table with columns for Material, Material Hardness (BHN), SFM Surface Footage, and Feed (IPR) for various materials like Free Machining Steel, Low & Medium Carbon Steel, Alloy Steel, High Strength Alloy Steel, Structural Steel, High Temp Alloy, Stainless Steel, Tool Steel, Aluminum, and Cast Iron.


The recommendations for speed, feeds and other parameters presented in this chart are nominal recommendations and should be considered only as good starting points.



RECOMMENDED CUTTING CONDITIONS

SPADE BLADE INSERTS SELECTION & APPLICATIONS CARBIDE

Toughness Values



Wear Values




Table with columns for Grade, Geometry and Application, and Stocked Coatings. Grades include P40 & C5, C3, and P40 & C2.

Note: Carbide has a lower transverse rupture strength than HSS and is prone to chipping and breakage. Recutting of chips or lack of rigidity can cause breakage. Check Coolant Recommendations Chart on Page 312 for flow rates.

If C5 chips try C2 at 10% - 20% lower S.F.M. than C5 rating

SPEEDS - FEED RECOMMENDATIONS (STD POINT-SM POINT)

STANDARD GEOMETRY
SM POINT

Table with columns for Material, Material Hardness (BHN), SFM Surface Footage, and Feed (IPR) for various materials like Free Machining Steel, Low & Medium Carbon Steel, Alloy Steel, High Strength Alloy Steel, Structural Steel, High Temp Alloy, Stainless Steel, Tool Steel, Aluminum, and Cast Iron.

The recommendations for speed, feeds and other parameters presented in this chart are nominal recommendations and should be considered only as good starting points.

SUPER COBALT (T15) FLAT BOTTOM

Material	Material Hardness (BHN)	Speed (SFM)		Feed			
		TiN	TiAlN	3/8 ~ 1/2	33/64 ~ 11/16	45/64 ~ 15/16	31/32 ~ 1-3/8
Free machining Steel 1213, 12L13, 1215 12L14, 1118	100 - 150	165	220	0.005	0.007	0.010	0.013
	150 - 200	150	215	0.005	0.007	0.010	0.013
	200 - 250	135	190	0.004	0.007	0.010	0.012
Low Carbon Steel 1015, 1020, 1140, 1025	85 - 125	140	195	0.005	0.007	0.009	0.012
	125 - 175	135	190	0.005	0.007	0.009	0.012
	175 - 225	125	180	0.004	0.006	0.008	0.011
	225 - 275	115	175	0.004	0.006	0.008	0.011
Medium Carbon Steel 1035, 1050, 1045 1055, 1140	125 - 175	135	195	0.004	0.007	0.009	0.011
	175 - 225	125	180	0.004	0.006	0.007	0.011
	225 - 275	115	165	0.004	0.006	0.007	0.011
	275 - 325	105	150	0.003	0.005	0.007	0.009
Structural Steel A36, A516, A182	100 - 150	115	165	0.004	0.007	0.009	0.011
	150 - 250	100	140	0.004	0.007	0.008	0.009
	250 - 350	80	115	0.003	0.006	0.007	0.008
Cast Iron / S,G Iron A48-76 GR30/GR45 A536-72 60-40-18 A220-76 GR40010	120 - 150	145	215	0.005	0.010	0.014	0.016
	150 - 200	130	190	0.005	0.008	0.011	0.016
	200 - 220	110	165	0.005	0.008	0.010	0.014
	220 - 260	95	150	0.004	0.006	0.008	0.010
	260 - 320	80	120	0.004	0.005	0.006	0.008
Alloy Steel 8620, 4130, 4137 4140, 6150	125 - 175	125	165	0.005	0.006	0.008	0.011
	175 - 225	115	150	0.004	0.006	0.008	0.011
	225 - 275	105	145	0.004	0.005	0.007	0.011
	275 - 325	100	140	0.003	0.005	0.007	0.009
Tool Steel H13, H21, A2, S1	150 - 200	65	90	0.003	0.005	0.006	0.008
	200 - 250	45	75	0.003	0.005	0.006	0.008
High Temp. Alloy Hastelloy B, Inconel	140 - 220	20	30	0.003	0.005	0.006	0.008
	220 - 310	15	25	0.003	0.004	0.006	0.006
	225 - 300	65	90	0.004	0.006	0.007	0.008
High Strength Alloy 9840, 4340, 4330V	300 - 350	45	70	0.003	0.006	0.007	0.008
	350 - 400	40	60	0.003	0.005	0.006	0.007
Aluminium 2014, 6061, 7075	30	520	700	0.007	0.011	0.014	0.017
	180	255	390	0.007	0.011	0.014	0.016
Stainless Steel 310, 316, 410, 330	135 - 185	60	90	0.005	0.007	0.008	0.009
	185 - 275	50	80	0.004	0.006	0.007	0.009

RPM = revolution per minute (rev/min)

SFM = surface feet per minute (ft/min)

DIA = diameter of drill (inch)

IPR = feed rate (in/rev)

IPM = inch per minute penetration rate

* Formulas :

$$SFM = (RPM) \cdot (.262) \cdot (DIA.)$$

$$IPM = (RPM) \cdot (IPR)$$

$$RPM = \frac{(SFM) \cdot (3.82)}{(DIA.)}$$

The recommendations for speeds, feeds and other parameters presented in this chart are nominal recommendations and should be considered only as good starting points. Speed and feed reductions (20% reduction in speed and 10% reduction in feed) are recommended.

SPADE BLADE INSERTS HORSEPOWER CONSUMPTION RATE

Metal Removal Rates (MRR)


Example : 1.50 Dia. Drill @ 6.412 I.P.M.

Volume of Cylinder Method : $D^2 \times .785 \times L$

D = Hole Diameter

L = Length in I.P.M.

.785 is Constant



Material Drilled 4140 250 BHN :

Cutting Data : 180 S.F.M. (458 R.P.M.) x .014 Feed per Rev.

$$458 \text{ R.P.M.} \times .014 = 6.412 \text{ I.P.M. (L)}$$

$$D^2 (1.5)^2 \times .785 \times L (6.412) = 11.3 \text{ C.U.In./ Min (MRR)}$$

MRR of 11.3 x 1.4 Energy Value = 15.8HP.

metal removal rates (mrR)

• Cubic inches of metal removal per unit of horsepower.

• Unit horsepower (HP_u) is the amount of power to remove a volume of metal in a period of time.

• HP_u = power to cut 1 cubic inch per minute – found in tables

Average Unit Horsepower Values of Energy Per Unit Volume		
Material	BHN	HP _u (HP/(in ³ /min.))
Carbon Steels	150-200	1.0
	200-250	1.4
	250-350	1.6
Leaded Steels	150-175	0.7
Cast Irons	125-190	0.5
	190-250	1.6
Stainless Steels	135-275	1.5
Aluminum Alloys	50-100	0.3
Magnesium Alloys	40-90	0.2
Copper	125-140	0.7
Copper Alloys	100-150	0.7

CARBIDE

HSS

Y/G SPADE DRILLS

RECOMMENDED CUTTING CONDITIONS


COOLANT RECOMMENDATIONS (SPADE BLADE)

Material	Material Hardness (BHN)	Coolant Pressure (PSi)						
		Coolant Volumetric Flowrate (GPM)						
		3/8 ~ 1/2	33/64 ~ 11/16	23/32 ~ 1	1 ~ 1-1/4	1-1/4 ~ 2	2 ~ 3	3 ~ 4
Free Machining Steel 1118, 1215, 12L14, etc.	100 - 250	175-185 2.5-2.6	100-120 2.8-3.0	105-140 4.4-5.2	80-115 7-8	75-100 12-14	40-50 30-33	65-90 38-44
Low Carbon Steel 1010, 1020, 1025, 1522, etc.	85 - 275	165-170 2.4-2.5	75-90 2.4-2.6	75-95 3.7-4.2	60-80 6-7	55-75 11-12	30-40 26-30	50-65 33-38
Medium Carbon Steel 1030,1040,1050,1527,1140,1151,etc.	125 - 325	160-165 2.3-2.4	70-85 2.3-2.6	70-90 3.6-4.1	55-75 5-6	50-70 10-12	30-40 26-30	50-65 33-38
Alloy Steel 4140, 5140, 8640, etc.	125 - 375	160-165 2.3-2.4	66-75 2.2-2.4	65-80 3.5-3.9	50-70 5-6	45-60 10-11	30-35 26-28	40-50 30-33
High Strength Alloy 4340, 4330V, 300M, etc.	225 - 400	150-155 2.3-2.4	55-60 2.1-2.2	45-50 2.9-3.1	25-30 4-5	25-30 7-8	20-25 21-23	25-30 23-26
Structural Steel A36, A285, A516, etc.	100 - 350	160-165 2.3-2.4	75-85 2.4-2.6	65-80 3.5-3.9	40-55 5-6	40-50 9-10	25-30 23-26	40-50 30-33
High Temp. Alloy Hastelloy B, Inconel 600, etc.	140 - 310	150-155 2.3-2.4	60-65 2.2-2.3	50-55 3.1-3.2	30-35 4-5	25-30 7-8	25-30 23-26	- -
Stainless Steel 301, 316, 330, 17-4PH, etc.	135 - 275	165-170 2.4-2.5	70-85 2.3-2.6	65-75 3.5-3.7	40-55 5-6	40-50 9-10	25-30 23-26	35-45 28-31
Tool Steel H-13, H-21, A-4, O-2, S-3, etc.	150 - 250	150-155 2.3-2.4	55-60 2.1-2.2	45-50 2.9-3.1	25-30 4-5	25-30 7-8	20-25 21-23	25-30 23-26
Aluminum	30 - 180	190-210 2.6-2.7	140-180 3.3-3.7	150-200 5.3-6.1	115-160 8-9	90-125 14-16	40-50 30-33	60-80 36-42
Cast Iron	120 - 320	155-160 2.3-2.4	60-65 2.2-2.3	50-60 3.1-3.3	30-40 4-5	30-35 8-9	25-30 23-26	30-35 26-28



Being the best through innovation


DRILLS




TECHNICAL DATA

- i-DREAM DRILLS
- DREAM DRILLS -GENERAL
- DREAM DRILLS -HIGH FEED
- DREAM DRILLS -FLAT BOTTOM
- DREAM DRILLS -INOX
- DREAM DRILLS -ALU
- DREAM DRILLS -MQL TYPE
- DREAM DRILLS for HIGH HARDENED STEELS
- STANDARD CARBIDE DRILLS
- MULTI-1 DRILLS
- HPD DRILLS
- GOLD-P DRILLS
- STRAIGHT SHANK DRILLS
- AIRCRAFT DRILLS
- SILVER & DEMING DRILLS
- TAPER SHANK DRILLS
- NC SPOTTING DRILLS
- COMBINATION DRILLS & COUNTERSINK
- SPADE DRILLS
- TECHNICAL DATA


1 Twist Drill with parallel shank



2 Twist Drill with taper shank




3 General dimensions of morse taper shanks



Morse Taper Shank	A mm	B mm	C(h13) mm	D mm	E mm	F(max.) mm	G mm	H(max.) mm	$\alpha/2$
No.1	12.065	9	5.2	12.2	62	13.5	3.5	8.7	1° 25' 43"
No.2	17.780	14	6.3	18.0	75	16	5	13.5	1° 25' 50"
No.3	23.825	19.1	7.9	24.1	94	20	5	18.5	1° 26' 16"
No.4	31.267	25.2	11.9	31.6	117.5	24	6.5	24.5	1° 29' 15"
No.5	44.399	36.5	15.9	44.7	149.5	29	6.5	35.7	1° 30' 26"
No.6	63.348	52.4	19	63.8	210	40	8	51	1° 29' 36"

4 Cutting portion




σ = Point angle (sigma)

Ψ = Chisel edge angle (psi)

* In the context of cutting technology, land width b_a is the body clearance land width which is to be by b_{fan} , see DIN 6581.

5 Angle at the cutting edges

The corner has been adopted as the observed edge point.



α_x = Side clearance angle (alpha)

α_{xe} = Effective side clearance angle

β_x = Side wedge angle (beta)

γ_x = Front rake angle (gamma)

γ_{xe} = Working front rake angle

η = Resultant cutting speed angle (eta)

Clearance angle α , wedge angle β and rake angle γ are measured in the tool orthogonal plane. For details, see DIN 6581, definitions of metal-cutting technology; geometry at the tool edge.

6

Web thickness k

Test values : The web thickness according to Fig. 1 shall not be less than the minimum value k_{min} indicated in Fig. 2.

Test point : At the point of the drill.

Testing equipment : Slide gauge with measuring points.




Figure 1. Web thickness k




Figure 2. Web thickness k_{min}

7

Margin width b_α

Test values : The land width as in Fig. 3 shall lie within the limited values indicated in Fig. 4.

Test point : 5mm behind the corner

Testing equipment : Slide gauge




Figure 3. Margin width b_α




Figure 4. Margin width b_α

8

Angle on Twist Drills

(1) Side rake angle γ_f (Helix angle)

Recommended test value : Recommended ranges depending on the tool types N,H and W according to DIN 1836 and the diameter of the drill included in Fig. 5.

Test point : At the corner, see Fig. 6.

Testing equipment : According to VDI Guideline 3331 Part 1, Section Margin width b_α

Note : The side rake angle γ_f is measured in place of the orthogonal rake angle γ_o found in the wedge measuring plane (see DIN 6581), as this changes along the cutting edge (becoming smaller towards the point of the drill).




Figure 6. Side rake angle γ_f




Figure 5. Side rake angle γ_f

(2) Point angle σ

Test value : Usual executin for tool types N and H : $\sigma = 118^\circ$, for tool type W : $\sigma = 130^\circ$

Test point : At the cutting, see Fig. 7.

Testing equipment : According to VDI Guideline 3331 Part 1, Section Margin width b_α




Figure 7. Point angle σ



Resharpener Twist Drills

(1) Drills are worn off irregularly. It should be sharpened prior to developing into excessive wear.

(2) Resharpener

- ① Grind the correct point angle to suit your application. (figure 8)
- ② Check that both cutting lips have the same angle. On a 130° point, each lip should be 65° toward the axis. The point must be on center, i.e., the chisel edge must produce cutting lips of equal length. (figure 8)
- ③ Grind Primary relief and Secondary clearance. (figure 9)
- ④ Grind web thinning. (figure 10)




Figure 8




Figure 9





Figure 10



Web thinning


(1) Without thinning

Suitable for drill of general purpose.
Thanks to thin web thickness, web thinning is not needed.
This without web thinning type is applied to design of drills for mild steels, alloy steels, cast iron, stainless steels, titanium, inconel, etc. and conventional cutting conditons.




(2) Type C thinning (DIN1412 FORM C, SPLIT POINT)

Because Split point enables good centering when drilling and breaks the chips, chip removals are easy.
Suitable for drill design in high hardened tough materials, i.e., heat treated steels, titanium alloys, stainless steels, inconel, etc.




(3) Type R thinning (HELICAL THINNING)

Helical thinning ensures to frequent chip breaking and removal.
The different direction force of cutting edges and helical thinning parts enable that chips curl, break and remove through the flutes.
In addition, helical thinning makes the chip room up to center, remove the chisel and enables good centering




(4) Type A thinning (DIN1412 FORM A)

A type thinning makes thin chisel, good chip removal and favorable centering.
This type is the easiest type to grind the thinning. In narrow web and wide fluted drills, keeping of the rigidity and smooth chip removal are possible.




(5) Type B thinning (DIN1412 FORM B)

In case of work materials with low cutting resistance and good chip removal, i.e., cast iron, aluminum, plastic etc., B type thinning is suitable.
Especially when drills for high hardened steels are designed, this type is applied to decrease rake angle and avoid chipping of cutting lips.




(6) Type D thinning (DIN1412 FORM D)

Grey cast iron thinning; bevelling of external edges strengthens the cutting edge.
Used for medium to high grey cast iron hardness and for abrasives.



(7) Type E thinning (DIN1412 FORM E)

Center drill bit thinning; ensures optimal center drilling and does not leave burrs in through holes.
As the bit and cutting edges are delicate, this bit should be used for drilling thin sheet metal.



Surface Finishes for high speed steels Twist Drills

(1) Bright Finish

Drills with a bright finish are without surface treatment and ground condition.
Especially bright finished drills are used in machining of non ferrous materials.

(2) Coloring (Gold color)

The coloring is a thin oxide layer formed on the tool surfaces.
This is often applied to cobalt high speed steels twist drills.

(3) Steam Tempered (black oxide finish)

This is a black oxide layer 1-2 μ m formed on the tool surfaces.
Steam Tempered treated drill is the result of a steam tempering operation. Because the oxide layer retains some coolant on the tool surface, and aids chip flow, helps to dissipate heat, steam homo treated drills are recommended for ferrous applications.



Coating

The use of coated cutting tools reduce production costs.

For example

- Avoidance of machine downtime due to premature tool wear.
- Higher cutting capabilities to reduce actual machining times.
- Reproducible tool life.
- Improvement of component surface quality.

(1) TiN (Titanium Nitride) coating

Titanium Nitride gives the tool a higher performance in comparison to traditional non-coated drills.

TiN coating, with good all-around properties, is recommended for the general application, i.e., attack by abrasive, adhesive and chemical wear in equal proportions.

(2) TiCN (Titanium Carbon Nitride) coating

TiCN coating should be employed when severe thermodynamic stress is expected, for example when drilling in high hardened steels or in mild steels with high speed and feed.


(3) TiAlN (Titanium Aluminum Nitride) coating

The addition of Aluminum to the Titanium Nitride produces an increase in hardness and an exceptional increase in resistance to oxidation at high temperature.

TiAlN coating is applied to drilling with severe thermal stress on cutting edges when continuous non-step feed, dry cutting or high speed cutting.

(4) Properties of coating

Properties	TiN	TiCN	TiAlN
Coating color	gold - yellow	blue - grey	violet - grey
Hardness (Hv 0.05)	2300	3000	3000
Coating thickness(μm)	1~4	1~4	1~5
Max. working temperature (°C)	600	400	800
Coefficient of friction against steels(dry)	0.4	0.4	0.4



(5) Selection of coating

Work-material	HSS TWIST DRILLS	CARBIDE DRILLS
Unalloyed steels	TiCN, TiAlN	TiCN, TiAlN
Steels < 1000 N/mm ²	TiCN, TiAlN	TiCN, TiAlN
Steels > 1000 N/mm ²	TiCN, TiAlN	TiCN, TiAlN
Stainless steels	TiCN, TiAlN	TiCN, TiAlN
Cast iron	TiCN, TiAlN	TiAlN
Al-wrought alloys	TiN	TiN
Al-cast alloys	TiCN	TiCN
Copper (pure)	CrN	CrN
Brass	TiCN	TiCN
Bronze	TiCN	TiCN



Drill sizes before Tapping

(1) Metric - ISO threads coarse pitch

Nominal diameter	Drill diameter	Nominal diameter	Drill diameter	Nominal diameter	Drill diameter	Nominal diameter	Drill diameter
		M3	2.5	M11	9.5	M30	26.5
M1	0.75	M3.5	2.9	M12	10.2	M33	29.5
M1.2	0.95	M4	3.3	M14	12.0	M36	32.0
M1.4	1.1	M5	4.2	M16	14.0	M39	35.0
M1.6	1.25	M6	5.0	M18	15.5	M42	37.5
M1.8	1.45	M7	6.0	M20	17.5	M45	40.5
M2	1.6	M8	6.8	M22	19.5	M48	43.0
M2.2	1.75	M9	7.8	M24	21.0	M52	47.0
M2.5	2.05	M10	8.5	M27	24.0	M56	50.5

(2) Metric ISO threads fine pitch

Nominal diameter	Tap Pitch	Drill diameter	Nominal diameter	Tap Pitch	Drill diameter	Nominal diameter	Tap Pitch	Drill diameter
2.5	0.35	2.15	17	1.5	15.5	33	1.5	31.5
3	0.35	2.65	18	1	17	33	2	31
3.5	0.35	3.15	18	1.5	16.5	33	3	30
4	0.5	3.5	18	2	16	35	1.5	33.5
4.5	0.5	4	20	1	19	36	1.5	34.5
5	0.5	4.5	20	1.5	18.5	36	2	34
5.5	0.5	5	20	2	18	36	3	33
6	0.75	5.2	22	1	21	38	1.5	36.5
7	0.75	6.2	22	1.5	20.5	39	1.5	37.5
8	0.75	7.2	22	2	20	39	2	37
8	1	7	24	1	23	39	3	36
9	0.75	8.2	24	1.5	22.5	40	1.5	38.5
9	1	8	24	2	22	40	2	38
10	0.75	9.2	25	1	24	40	3	37
10	1	9	25	1.5	23.5	42	1.5	40.5
10	1.25	8.8	25	2	23	42	2	40
11	0.75	10.2	26	1.5	24.5	42	3	39
11	1	10	27	1	26	45	1.5	43.5
12	1	11	27	1.5	25.5	45	2	43
12	1.25	10.8	27	2	25	45	3	42
12	1.5	10.5	28	1	27	48	1.5	46.5
14	1	13	28	1.5	26.5	48	2	46
14	1.25	12.8	28	2	26	48	3	45
14	1.5	12.5	30	1	29	50	1.5	48.5
15	1	14	30	1.5	28.5	50	2	48
15	1.5	13.5	30	2	28	50	3	47
16	1	15	30	3	27	52	1.5	50.5
16	1.5	14.5	32	1.5	30.5	52	2	50
17	1	16	32	2	30	52	3	49

(3) WITHWORTH pipe threads (BSP)

Nominal size inches	Drill diameter mm	Nominal size inches	Drill diameter mm
G1/8	8.8	G1 * 1/4	39.5
G1/4	11.8	G1 * 3/8	42.0
G3/8	15.25	G1 * 1/2	45.0
G1/2	19.0	G1 * 3/4	51.0
G5/8	21.0	G2	57.0
G3/4	24.5	G2 * 1/4	63.0
G7/8	28.25	G2 * 1/2	73.0
G1	30.75	G2 * 3/4	79.0
G1 1/8	35.5	G3	85.0

(4) American unified coarse threads

UNC	Drill diameter		UNC	Drill diameter	
	inches	mm		inches	mm
No. 1	53	1.51	7/16	U	9.35
No. 2	50	1.78	1/2	27/64	10.71
No. 3	47	1.99	9/16	31/64	12.30
No. 4	43	2.26	5/8	17/32	13.49
No. 5	38	2.58	3/4	21/32	16.67
No. 6	36	2.71	7/8	49/64	19.44
No. 8	29	3.45	1	7/8	22.22
No. 10	25	3.8	1 * 1/8	63/64	25.00
No. 12	16	4.5	1 * 1/4	1 * 7/64	28.18
1/4	7	5.11	1 * 3/8	1 * 7/32	30.95
5/16	F	6.53	1 * 1/2	1 * 11/32	34.13
3/8	5/16	7.94			

(5) American unified fine threads

NF	Drill diameter		NF	Drill diameter	
	inches	mm		inches	mm
No. 0	3/64	1.19	3/8	Q	8.43
No. 1	53	1.51	7/16	25/64	9.92
No. 2	50	1.78	1/2	29/64	11.51
No. 3	45	2.08	9/16	33/64	13.10
No. 4	42	2.37	5/8	37/64	14.86
No. 5	37	2.64	3/4	11/16	17.46
No. 6	33	2.87	7/8	13/16	20.64
No. 8	29	3.45	1	59/64	23.42
No. 10	21	4.04	1 * 1/8	1 * 3/64	26.59
No. 12	14	4.62	1 * 1/4	1 * 11/32	29.76
1/4	3	5.41	1 * 3/8	1 * 19/32	32.94
5/16	1	6.91	1 * 1/2	1 * 27/64	36.11

14 ISO Tolerance

Drill Diameter Tolerance Inch

up to .118	over .118 up to .236	over .236 up to .394	over .394 up to .709
+0 -.00055	+0 -.00071	+0 -.00087	+0 -.00106

Drill Diameter Tolerance Metric

Diameter (mm)	1 - 3 from to	3 - 6 over to	6 - 10 over to	10 - 18 over to	18 - 30 over to
h6	0 -.00024	0 -.00032	0 -.00036	0 -.00044	0 -.00052
h7	0 -.0004	0 -.00048	0 -.00059	0 -.00071	0 -.00083
h8	0 -.00056	0 -.00071	0 -.00087	0 -.00107	0 -.00130
m7	+0.00048 +.00007	+0.00063 +.00015	+0.00083 +.00023	+0.00099 +.00027	+0.00114 +.00031

15 Trouble Shooting in Drilling


Occurrence of trouble	Cause of trouble	Countermeasures
Drill will not enter work	1. Drill is dull. 2. Lip relief too small. 3. Too thick a web.	1. Grind lip relief sufficiently. 2. Grind web thinning. 3. Choose a drill with narrow web.
Margin chipping	1. Oversized jig bushing.	1. Choose the suitable jig bushing for drill diameter
Cutting lip breaks	1. Lip relief too much. 2. Feed too heavy.	1. Grind lip relief sufficiently. 2. Decrease feed rate.
Tang breaks Bruch der	1. Imperfect fit between taper shank and socket. 2. Burred or Badly worn sockets.	1. Clean the dirt or chips in sockets. 2. Change the worn sockets to new ones.
Drill breaks in brass	1. Unsuitable drill 2. Flutes clogged with chips	1. Choose the suitable drill for work material.
Chipping of drill center	1. Lip relief too much. 2. Feed too heavy.	1. Grind lip relief sufficiently. 2. Decrease feed rate.
Hole oversize	1. Unequal angle or length of cutting edges. 2. Loosen spindle.	1. Resharpener point, choose correct drills. 2. Tighten spindle sufficiently.
Outer corners broken down	1. Cutting speed too high. 2. Hard spots in work material. 3. Flutes clogged with chips. 4. Too wear of drills.	1. Grind point to suit work material. 2. Decrease the feed rates. 3. Resharpener early before too wear.
Large chip of one flute and small chip of other flute	1. Improperly ground point. 2. Only one lip doing all the cutting	1. Properly grind point. 2. Grind point with same point angle and length of lip 3. Grind with small lip height.
Hole rough	1. Improperly ground point. 2. Unenough coolant supply 3. Too much feed. 4. Fixture not rigid.	1. Properly grind point. 2. Supply coolant enough. 3. Decrease the feed rate. 4. Tighten the fixture or replace.

16 Characteristic of DREAM DRILLS


- YG-1's Dream Drill Series are suitable for high speed and accurate drilling operations by special design and high quality.
- Good performance for Steels, Cast Irons, Tool steels, Alloy steels and Stainless steels.
- Rapid chip evacuation and excellent chip breaking can be achieved by special designed cutting edges on point and chip breakers on leading edges.
- High accuracy and stability.
- Longer tool life with TiAlN coating.
- Self-centering

17 Honing Guide of DREAM DRILLS

■ Dimension of Honing



■ Scraper




for Roughing (#140)

for Finishing (#230 ~ #400)



Work Material	Alloy Steels	Mild Steels	Cast Iron
W(mm)	0.15 ~ 0.2	0.1 ~ 0.15	0.03

▶ The dimension W of stocked products is 0.1 ~ 0.15.

18 Use of DREAM DRILLS




- ▶ Chucking with spring collet correctly.
- ▶ Radial run out at cutting lip must not exceed 0.025 mm.
- ▶ Tighten clamp of work piece.



- ▶ Supply coolant enough to the entrance of hole.
- ▶ When using Dream Drills with Coolant holes, Supply high pressure coolant.

19 Shank Type DREAM DRILLS with Coolant Holes



- ▶ Shank Type of stocked products is Form HA.
- ▶ If you need other Shank Type, we can supply them.

THREADING TOOLS

SOLID CARBIDE THREAD MILLS

COMBO TAPS(Spiral Point & Spiral Flute)

SPIRAL FLUTE TAPS

SPIRAL POINT TAPS

STRAIGHT FLUTE TAPS

FORMING TAPS

SCREW THREAD INSERT TAPS (STI)

PIPE TAPS

TECHNICAL DATA

Contents

THREADING TOOLS

Contents / THREADING TOOLS

CARBIDE THREAD MILLS

SOLID CARBIDE THREAD MILLS

For blind holes and through holes with one single tool / Higher cutting speed and feed than taps

THREAD MILLS

COMBO TAPS

Multi Purpose tapping / YG-1's Patent / Super HSS & HSS-EX for Prevention of Oversized Threads

COMBO TAPS

SPIRAL FLUTE TAPS

Tapping Blind Holes / Super HSS, P-HSS, HSSE-V3, HSS-V & HSS

SPIRAL FLUTE TAPS

SPIRAL POINT TAPS

Tapping Through Holes / Super HSS, P-HSS, HSSE-V3, HSS-V & HSS

SPIRAL POINT TAPS

STRAIGHT FLUTE TAPS

Tapping Through & Blind Holes / Carbide, Super HSS & HSS

STRAIGHT FLUTE TAPS

FORMING TAPS

Tapping by Forming Soft Materials (NO Chips)

FORMING TAPS

SCREW THREAD INSERT TAPS (STI)

Tapping STI Threads of Soft Materials (HSSE-V3 & HSS)

SCREW THREAD INSERT TAPS

PIPE TAPS

Tapping NPT, NPTF, NPS & NPSF Threads


PIPE TAPS

CARBIDE & HSS TAPS

TECHNICAL DATA

TECHNICAL DATA




TECHNICAL DATA



THREADING TOOLS APPLICATION TABLE



















SOLID CARBIDE THREAD MILL

INCH

EDP No.	MODEL	Description	Page
TE		Solid Carbide Thread mill for Unified Internal Threads - ANSI B 1.1	357
TD		Solid Carbide Thread mill for Metric Internal Threads - DIN 13	358
TF TG		Solid Carbide Thread mill for Unified Internal Threads - ANSI B 1.20.1(NPT) / ANSI B1.20.3(NPTF)	359

COMBO TAPS

INCH/METRIC

EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page
T2 T2-S T2-C		HSS-EX	UNC/UNF	MU	USCTI 302A	H	2 ~ 3P	2.5D	Bright Steam Oxide TiCN	365
T5 T5-S T5-C		HSS-EX	M/MF	MU	USCTI 302A	D	2 ~ 3P		Bright Steam Oxide TiCN	367
T6 T6-N	with Internal Coolant 	HSS-EX	UNC/UNF	MU	USCTI 302A	H	2 ~ 3P		Bright TiN	368
T8 T8-N	with Internal Coolant 	HSS-EX	M	MU	USCTI 302A	D	2 ~ 3P		Bright TiN	369
T7 T7-C	Short Chamfer 	HSS-EX	UNC/UNF	MU	USCTI 302A	H	1 ~ 2P		Bright TiCN	370
T9 T9-C	Short Chamfer 	HSS-EX	M/MF	MU	USCTI 302A	D	1 ~ 2P		Bright TiCN	372
T1-S T1-C		HSS-EX	UNC/UNF	MU	DIN Length-ANSI Shank	H	2 ~ 3P		Steam Oxide TiCN	373
TA-S TA-C		HSS-EX	M/MF	MU	DIN Length-ANSI Shank	D	2 ~ 3P		Steam Oxide TiCN	374
TCA-S/C TCB-S/C		Super HSS HSS-EX	UNC/UNF	VA	USCTI 302A	H	2 ~ 3P		Steam Oxide TiCN	375
TCC-S/C TCD-S/C		Super HSS HSS-EX	M/MF	VA	USCTI 302A	D	2 ~ 3P		Steam Oxide TiCN	377
T4 T4-S T4-C		HSS-EX	UNC/UNF	MU	USCTI 302A	H	4 ~ 5P	3.0D	Bright Steam Oxide TiCN	378
T3 T3-S T3-C		HSS-EX	M/MF	MU	USCTI 302A	D	4 ~ 5P		Bright Steam Oxide TiCN	380
TB TB-N	with Internal Coolant 	HSS-EX	UNC/UNF	MU	USCTI 302A	H	4 ~ 5P		Bright TiN	381
TH TH-N	with Internal Coolant 	HSS-EX	M	MU	USCTI 302A	D	4 ~ 5P		Bright TiN	382
TC-S TC-C		HSS-EX	UNC/UNF	MU	DIN Length-ANSI Shank	H	4 ~ 5P		Steam Oxide TiCN	383
TK-S TK-C		HSS-EX	M/MF	MU	DIN Length-ANSI Shank	D	4 ~ 5P		Steam Oxide TiCN	384
TCE-S/C TCF-S/C		Super HSS HSS-EX	UNC/UNF	VA	USCTI 302A	H	4P		Steam Oxide TiCN	385
TCG-S/C TCH-S/C		Super HSS HSS-EX	M/MF	VA	USCTI 302A	D	4P		Steam Oxide TiCN	387

THREADING TOOLS APPLICATION TABLE

SPIRAL FLUTE TAPS

INCH/METRIC








EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page
BB/BI		Super HSS	UNC/UNF	VG	USCTI 302A	H	2 ~ 3P	2.5D	Steam Oxide Hardslick	392
BH/BM		Super HSS	M/MF	VG	USCTI 302A	D	2 ~ 3P		Steam Oxide Hardslick	394
BF/BK		Super HSS	UNC/UNF	VG	DIN Length-ANSI Shank	H	2 ~ 3P		Steam Oxide Hardslick	395
BD/BO		Super HSS	M/MF	VG	DIN Length-ANSI Shank	D	2 ~ 3P		Steam Oxide Hardslick	396
H6/H7/H8		P-HSS	UNC/UNF	HR	USCTI 302A	H	2 ~ 3P		Bright TiCN Hardslick	397
TQ858/TK858/TR858		P-HSS	M/MF	HR	USCTI 302A	H	2 ~ 3P		Steam Oxide TiCN Hardslick	398
B3/B5/D6		P-HSS	UNC/UNF	Ti Ni	USCTI 302A	H	2 ~ 3P		Steam Oxide TiCN Hardslick	399
G7/G8/G9/H0		P-HSS	UNC/UNF	VA	USCTI Long Shank	H	2 ~ 3P		TiN Hardslick	401
H2/H4		P-HSS	UNC/UNF	VA	USCTI Long Shank (Left hand Spiral, Right hand Cut)	H	4 ~ 5P		3.0D TiN Hardslick	402
BG/BG-GB		HSSE-V3	UNC/UN8	VG	DIN Length-ANSI Shank	2B	2 ~ 3P		Hardslick Gold & Black	403
B1/B0/B2/D2		HSSE-V3	UNC/UNF	VA	USCTI 302A	H	2 ~ 3P	Bright Steam Oxide TiN/Hardslick	404	
BS/BT		HSSE-V3	M/MF	VA	USCTI 302A	D	2 ~ 3P	Steam Oxide Hardslick	407	
E6/E8/E9		HSSE-V3	M/MF	VA	DIN Length-ANSI Shank	D	2 ~ 3P	Steam Oxide TiCN Hardslick	408	
D3/E0		HSSE-V3	UNC/UNF	VG	USCTI 302A	H	2 ~ 3P	2.5D Hardslick Steam Oxide	409	
BU/BV		HSSE-V3	M/MF	VG	USCTI 302A	D	2 ~ 3P	Steam Oxide Hardslick	412	
E2/E4/E5		HSSE-V3	M/MF	VG	DIN Length-ANSI Shank	D	2 ~ 3P	Steam Oxide TiCN Hardslick	414	
C0/D8		HSSE-V3	UNC/UNF	AI	USCTI 302A	H	2 ~ 3P	Bright Hardslick	415	
BW/BX		HSSE-V3	M/MF	AI	USCTI 302A	D	2 ~ 3P	Bright Hardslick	416	

EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page
C2/C3/C4/D9		HSSE-V3	UNC/UNF	GS	USCTI 302	H	1.5 ~ 2P	2.5D	Steam Oxide Bright/TiN Hardslick	417
F4/F8/F6		HSS-V	UNC/UNF	GS	USCTI 302A	H	1.5 ~ 2P		Steam Oxide TiN Hardslick	418
G4/G5/G6		HSS-V	M/MF	GS	USCTI 302A	D	1.5 ~ 2P		Bright TiCN Hardslick	420
G0/G1/G2		HSS-V	UNC/UNF	GS	DIN Length-ANSI Shank	H	2 ~ 3P		Bright TiN Hardslick	421
T7A96/T6A96/T8A96 T7295/T6295/T8295		HSS	UNC/UNF	GS	USCTI 302	H	4 ~ 5P 1.5 ~ 2P		Bright Steam Oxide TiN	423
T7A86/T6A86/T8A86 T7A85/T6A85/T8A85		HSS	M/MF	GS	USCTI 302	D	4 ~ 5P 1.5 ~ 2P		Bright Steam Oxide TiN	424
T7D01/T8D01 T7D02/T8D02		HSS	UNC/UNF	GS	USCTI Long Shank	H	4 ~ 5P 1.5 ~ 2P		Bright TiN	425

THREADING TOOLS APPLICATION TABLE

SPIRAL POINT TAPS

INCH/METRIC

EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page
M9/O1		Super HSS	UNC/UNF	VG	USCTI 302A	H	4 ~ 5P	3.0D	Steam Oxide Hardslick	430
N7/N8		Super HSS	M/MF	VG	USCTI 302A	D	4 ~ 5P		Steam Oxide Hardslick	432
N4/O5		Super HSS	UNC/UNF	VG	DIN Length-ANSI Shank	H	4 ~ 5P		Steam Oxide Hardslick	433
N3/O3		Super HSS	M/MF	VG	DIN Length-ANSI Shank	D	4 ~ 5P		Steam Oxide Hardslick	434
M4/M5/M6/M7		P-HSS	UNC/UNF	HR	USCTI 302A	H	4 ~ 5P		Steam Oxide Bright/TiCN Hardslick	435
TQ808/TK808/TR808		P-HSS	M/MF	HR	USCTI 302A	H	4 ~ 5P		Steam Oxide TiCN Hardslick	436
I3/M8/I5/J6		P-HSS	UNC/UNF	Ti Ni	USCTI 302A	H	4 ~ 5P		Steam Oxide Bright/TiCN Hardslick	437
M0/M1/M2/M3		P-HSS	UNC/UNF	VA	USCTI Long Shank	H	4 ~ 5P		TiN Hardslick	439
I0/I2/J2		HSSE-V3	UNC/UNF	VA	USCTI 302A	H	4 ~ 5P		Steam Oxide TiN Hardslick	440
O9/IA		HSSE-V3	M/MF	VA	USCTI 302A	D	4 ~ 5P		Steam Oxide Hardslick	443
K3/K5/K6		HSSE-V3	M/MF	VA	DIN Length-ANSI Shank	D	4 ~ 5P		Steam Oxide TiCN Hardslick	444
J3/J4/J8		HSSE-V3	UNC/UNF	VG	USCTI 302A	H	4 ~ 5P		Steam Oxide Bright Hardslick	445
IB/IC		HSSE-V3	M/MF	VG	USCTI 302A	D	4 ~ 5P		Steam Oxide Hardslick	449
J9/K7/K2		HSSE-V3	M/MF	VG	DIN Length-ANSI Shank	D	4 ~ 5P		Steam Oxide TiCN Hardslick	451
T2496		HSSE-V3	UNC/UNF	AI	USCTI 302A	H	4 ~ 5P		Bright	452
T2K01		HSSE-V3	M/MF	AI	USCTI 302A	D	4 ~ 5P		Bright	453
I9/J0/J1/J7		HSSE-V3	UNC/UNF	GS	USCTI 302	H	4 ~ 5P	Steam Oxide Bright/TiN Hardslick	454	
K9/L0/L1		HSS-V	UNC/UNF	GS	USCTI 302A	H	4 ~ 5P	Bright TiN Hardslick	455	

EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page
L7/L8/L9		HSS-V	M/MF	GS	USCTI 302A	D	4 ~ 5P	3.0D	Bright TiCN Hardslick	456
L3/L4/L5		HSS-V	UNC/UNF	GS	DIN Length-ANSI Shank	H	4 ~ 5P		Bright TiN Hardslick	457
T7216/T6216/T8216 T7C16/T6C16/T8C16		HSS	UNC/UNF	GS	USCTI 302	H	4 ~ 5P		Bright Steam Oxide TiN	458
T7256/T6256		HSS	UNC/UNF	GS	USCTI 302	H	1.5 ~ 2P		Bright Steam Oxide	462
T7217/T6217/T8217		HSS	M/MF	GS	USCTI 302	D	4 ~ 5P		Bright Steam Oxide TiN	464
T7226/T6226/T8226		HSS	UNC/UNF	GS	USCTI 302	+ .005" oversize	4 ~ 5P		Bright Steam Oxide TiN	465
T7B17/T6B17/T8B17		HSS	M/MF	GS	USCTI 302	+ .127mm oversize	4 ~ 5P		Bright Steam Oxide TiN	466
T7236/T6236/T8236 T7G36/T6G36/T8G36		HSS	UNC/UNF	GS	USCTI Long Shank	H	4 ~ 5P		Bright Steam Oxide TiN	467

THREADING TOOLS APPLICATION TABLE

STRAIGHT FLUTE TAPS

INCH/METRIC

EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page	
T0C01		Carbide	UNC/UNF	GG	USCTI 302A	2B	1.5 ~ 2P	2.0D	Bright	471	
TR		Super HSS	UNC/UNF	GG	USCTI 302A	H	2 ~ 3P		TiAlN	472	
	M/MF		GG	D		2 ~ 3P					
TR-A, TR-R		Super HSS	UNC/UNF	GG	USCTI 302A	H	2 ~ 3P		TiAlN	474	
			M/MF	GG		D	2 ~ 3P				
T7316/T6316/ T8316/T7A16 T7B16		HSS	UNC/ UNF/ UNS	GS	USCTI 302	H	9P/5P/2P		2.0D	Bright Steam Oxide TiN	476
			M/MF	GS		D	9P/5P/2P			Bright Steam Oxide TiN	482
T7326		HSS	UNC/UNF	GS	USCTI 302	+ .005" oversize	5P/2P		Bright	483	
T7B15		HSS	M/MF	GS	USCTI 302	+ .127mm oversize	5P/2P		Bright	484	
T7336		HSS	UNC/UNF	GS	USCTI 302 (Left Hand)	H	5P/2P		Bright	485	
T7A15		HSS	UNC/UNF	GS	USCTI 302 (Left Hand)	D	5P/2P		Bright	486	
T7616/T6616/ T8616		HSS	UNC/UNF	GS	USCTI Long Shank	H	4 ~ 5P		Bright Steam Oxide TiN	487	

FORMING TAPS

INCH/METRIC

EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page
TKR03		Super HSS	UNC/UNF	GV	USCTI 302A	H	2 ~ 3P	3.0D	TiCN	491
ZF		HSSE-V3	UNC/UNF	GV	USCTI 302	H	2 ~ 3P		Bright	492
Z0/Z1/Z2/Z3		HSSE-V3	UNC/UNF	GV	USCTI 302A	H	4 ~ 5P 1.5 ~ 2P		Bright TiN	493
Z4/Z5/Z6/Z7		HSSE-V3	UNC/UNF	GV	USCTI 302A	H	4 ~ 5P 1.5 ~ 2P		Bright TiN	495
Z8/ZA/ZC Z9/ZB/ZD		HSSE-V3	M/MF	GV	USCTI 302A	D	4 ~ 5P 1.5 ~ 2P		Bright TiN / TiCN	497
T7R01/T8R01/ THR01 T7R02/T8R02/ THR02		HSS	UNC/UNF	GV	USCTI 302A	H	4 ~ 5P 1.5 ~ 2P		Bright TiN / TiCN	498

SCREW THREAD INSERT TAPS

INCH/METRIC

EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page
ST/SI		HSSE-V3	UNC/UNF	GS	USCTI 322	2B	1.5 ~ 2P	2.5D	Hardslick	501
T7406		HSS	UNC/UNF	GS	USCTI 322	H	1.5 ~ 2P		Bright	502
T7425		HSS	M/MF	GS	USCTI 322A	D	1.5 ~ 2P		Bright	503
ST/SI		HSSE-V3	UNC/UNF	GS	USCTI 322	2B	4 ~ 5P	3.0D	Hardslick	504
T7436		HSS	UNC/UNF	GS	USCTI 322	H	4 ~ 5P		Bright	505
T7415		HSS	M/MF	GS	USCTI 322A	D	4 ~ 5P		Bright	506
T7426		HSS	UNC/UNF	GS	USCTI 322	H	4 ~ 5P 1.5 ~ 2P	2.0D	Bright	507
T7405		HSS	M/MF	GS	USCTI 322A	D	4 ~ 5P 1.5 ~ 2P		Bright	508

PIPE TAPS

INCH

EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Chamfer	Thread Depth	Surface Treatment	Page
Q1/Q0/Q6		HSSE-V3	NPTF	VA	USCTI 311	2 ~ 3P	2.5D	Bright Steam Oxide Hardslick	511
Q9/R0/R1		HSSE-V3	NPTF	GG	USCTI 311	2 ~ 3P		Bright TiN Hardslick	512
R7/R8/R9/S0		HSSE-V3	NPTF	GG	USCTI 311	2 ~ 3P	2.0D	Bright TiN Hardslick Nitrided-Steam Oxide	513
S1/S2		HSSE-V3	NPTF	GG	USCTI 311	2 ~ 3P		Bright TiCN	514
T7L36/T6L36 T7536/T6536		HSS	NPS/NPSF	GS	USCTI 311	4 ~ 5P		Bright Steam Oxide	515
T7505/T6505/ TH505		HSS	NPT	GS	USCTI 311	2 ~ 3P		Bright Steam Oxide TiCN	516
T7546/T8546		HSS	NPTF	GS	USCTI 311	2 ~ 3P		Bright TiN	517



HIGH PERFORMANCE TAPS RECOMMENDATION TABLE

Super HSS : Premium HSS Metallurgy
 P-HSS : Powdered Metallurgy
 HSSE-V3 : 3% Vanadium Alloy HSS-EX
 HSS-V : Vanadium Alloy HSS

⊙ = RECOMMENDED
 ○ = SUITABLE

COOLANT
 A = Cutting Oil
 T = Oil Emulsion
 X = Cutting Oil/Oil Emulsion

Material Group	Material Sub-Group	ISO	Hardness (HRC)	Hardness (BHN)	Cutting Speed (SFM)		COOLANT	MU			MU			MU			
					Uncoated	Coated		T2	T2-S	T2-C	T5	T5-S	T5-C	T6	T6-N	T6-N	
Steel	Low carbon steels Free machining carbon steels	P	< 15	< 180	25 - 50	50 - 80	T	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
	Medium to high carbon steels Low alloyed steels	P	< 23	< 240	25 - 50	50 - 80	T	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
	Steel castings & forgings Heat-treatable alloy steels	P	> 24 ≤ 38	> 250 ≤ 350	6 - 30	10 - 35	X	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
	Alloyed tool steels Mold steels	P	> 38 ≤ 44	> 350 ≤ 420	6 - 12	-	A	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
Stainless Steel	Free machining stainless steels	M	< 23	< 240	12 - 35	20 - 50	A	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
	Heat-and corrosion-resistant stainless steels Valve stainless steels	M	> 24 ≤ 38	> 250 ≤ 350	12 - 15	12 - 15	A	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
	Stainless steel castings Precipitation hardening stainless steels	M	> 38 ≤ 44	> 350 ≤ 420	12 - 15	-	A	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
Cast Iron	Grey cast iron	K	-	≤ 220	35 - 50	50 - 65	T	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
	Nodular cast iron / Chilled cast iron Meehanite iron / Ductile iron	K	-	≥ 250	12 - 45	25 - 55	X	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
Copper	Pure and alloyed copper	N	-	-	50 - 60	65 - 100	T	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
Brass	Free machining brass Alloyed brass	N	-	-	30 - 65	-	T	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
Bronze		N	44	< 420	12 - 20	35 - 80	T	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
Aluminum	Pure Aluminum Aluminum alloys	N	-	-	50 - 65	-	T	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
	Aluminum alloy castings	N	-	-	40 - 65	45 - 90	T	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
Zinc		N	-	-	25 - 65	50 - 80	T	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
Magnesium		N	-	-	-	45 - 100	T	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙
Nickel Alloys	718 & 625 INCONEL / Waspaloy Hastelloy / Invar Monel / Incoloy	S	≤ 38	≤ 350	10 - 15	-	A										
	718 Inconel A286	S	> 38 ≤ 44	> 350 ≤ 420	10 - 12	-	A										
Titanium		S	≤ 38	≤ 350	3 - 15	-	A										

MU		MU		MU		MU		MU		VA		VA		MU			MU		
T8 T8-N	T7 T7-C	T9 T9-C	T1-S	T1-C	TA-S	TA-C	TCA-S/C TCB-S/C	TCC-S/C TCD-S/C	T4	T4-S	T4-C	T3	T3-S	T3-C	T3	T3-S	T3-C		
USCTI 302A	USCTI 302A	USCTI 302A	DIN Length-ANSI Shank	DIN Length-ANSI Shank	USCTI 302A	USCTI 302A	USCTI 302A	USCTI 302A	USCTI 302A	USCTI 302A	USCTI 302A	USCTI 302A	USCTI 302A	USCTI 302A	USCTI 302A	USCTI 302A	USCTI 302A		
369	370	372	373	374	375	377	378	380											
M	UNC/UNF	M/MF	UNC/UNF	M/MF	UNC/UNF	M/MF	UNC/UNF	M/MF	UNC/UNF	M/MF	UNC/UNF	M/MF	UNC/UNF	M/MF	UNC/UNF	M/MF	UNC/UNF		
HSS-EX	HSS-EX	HSS-EX	HSS-EX	HSS-EX	Super HSS HSS-EX	Super HSS HSS-EX	HSS-EX	HSS-EX											
2-3P	1-2P	1-2P	2-3P	2-3P	2-3P	2-3P	4-5P	4-5P											
Bright TiN	Bright TiCN	Bright TiCN	Steam Oxide	TiCN	Steam Oxide	TiCN	Steam Oxide TiCN	Steam Oxide TiCN	Bright Steam Oxide	TiCN	Bright Steam Oxide	TiCN	Bright Steam Oxide	TiCN					
R40°	R40°	R40°	R40°	R40°	R40°	R40°	R45°	R45°	-	-	-	-	-	-	-	-	-		
2.5D	2.5D	2.5D	2.5D	2.5D	2.5D	2.5D	2.5D	2.5D	3.0D	3.0D	3.0D	3.0D	3.0D	3.0D	3.0D	3.0D	3.0D		
Blind	Blind	Blind	Blind	Blind	Blind	Blind	Blind	Blind	Through	Through	Through	Through	Through	Through	Through	Through	Through		



HIGH PERFORMANCE TAPS RECOMMENDATION TABLE

Super HSS : Premium HSS Metallurgy
 P-HSS : Powdered Metallurgy
 HSSE-V3 : 3% Vanadium Alloy HSS-EX
 HSS-V : Vanadium Alloy HSS

⊙ = RECOMMENDED
 ○ = SUITABLE

COOLANT
 A = Cutting Oil
 T = Oil Emulsion
 X = Cutting Oil/Oil Emulsion

Material Group	Material Sub-Group	ISO	Hardness (HRc)	Hardness (BHN)	Cutting Speed (SFM)		COOLANT	SERIES			
					Uncoated	Coated		TB-TB-N	TH-TH-N	TC-S	TC-C
Steel	Low carbon steels Free machining carbon steels	P	< 15	< 180	25 - 50	50 - 80	T	⊙	⊙	⊙	⊙
	Medium to high carbon steels Low alloyed steels	P	< 23	< 240	25 - 50	50 - 80	T	⊙	⊙	⊙	⊙
	Steel castings & forgings Heat-treatable alloy steels	P	> 24 ≤ 38	> 250 ≤ 350	6 - 30	10 - 35	X	⊙	⊙	⊙	⊙
	Alloyed tool steels Mold steels	P	> 38 ≤ 44	> 350 ≤ 420	6 - 12	-	A	⊙	⊙	⊙	⊙
Stainless Steel	Free machining stainless steels	M	< 23	< 240	12 - 35	20 - 50	A	⊙	⊙	⊙	⊙
	Heat-and corrosion-resistant stainless steels Valve stainless steels	M	> 24 ≤ 38	> 250 ≤ 350	12 - 15	12 - 15	A	⊙	⊙	⊙	⊙
	Stainless steel castings Precipitation hardening stainless steels	M	> 38 ≤ 44	> 350 ≤ 420	12 - 15	-	A	⊙	⊙	⊙	⊙
Cast Iron	Grey cast iron	K	-	≤ 220	35 - 50	50 - 65	T	⊙	⊙	⊙	⊙
	Nodular cast iron / Chilled cast iron Meehanite iron / Ductile iron	K	-	≥ 250	12 - 45	25 - 55	X	⊙	⊙	⊙	⊙
Copper	Pure and alloyed copper	N	-	-	50 - 60	65 - 100	T	⊙	⊙	⊙	⊙
Brass	Free machining brass Alloyed brass	N	-	-	30 - 65	-	T	⊙	⊙	⊙	⊙
Bronze		N	44	< 420	12 - 20	35 - 80	T	⊙	⊙	⊙	⊙
Aluminum	Pure Aluminum Aluminum alloys	N	-	-	50 - 65	-	T	⊙	⊙	⊙	⊙
	Aluminum alloy castings	N	-	-	40 - 65	45 - 90	T	⊙	⊙	⊙	⊙
Zinc		N	-	-	25 - 65	50 - 80	T	⊙	⊙	⊙	⊙
Magnesium		N	-	-	-	45 - 100	T	⊙	⊙	⊙	⊙
Nickel Alloys	718 & 625 INCONel / Waspaloy Hastelloy / Invar Monel / Incoloy	S	≤ 38	≤ 350	10 - 15	-	A				
	718 Inconel A286	S	> 38 ≤ 44	> 350 ≤ 420	10 - 12	-	A				
Titanium		S	≤ 38	≤ 350	3 - 15	-	A				

MU		VA	VA	VG	VG	VG	VG	HR	HR
TK-S	TK-C	TCE-S/C TCF-S/C	TCG-S/C TCH-S/C	BB/BI	BH/BM	BF/BK	BD/BO	H6/H7/H8	TQ858/ TK858/ TR858
DIN Length-ANSI Shank		USCTI 302A	USCTI 302A	USCTI 302A	USCTI 302A	DIN Length-ANSI Shank	DIN Length-ANSI Shank	USCTI 302A	USCTI 302A
384		385	387	392	394	395	396	397	398
M/MF		UNC/UNF	M/MF	UNC/UNF	M/MF	UNC/UNF	M/MF	UNC/UNF	M/MF
HSS-EX		Super HSS HSS-EX	Super HSS HSS-EX	Super HSS	Super HSS	Super HSS	Super HSS	P-HSS	P-HSS
4-5P		4P	4P	2-3P	2-3P	2-3P	2-3P	2-3P	2-3P
Steam Oxide	TiCN	Steam Oxide TiCN	Steam Oxide TiCN	Steam Oxide Hardslick	Steam Oxide Hardslick	Steam Oxide Hardslick	Steam Oxide Hardslick	Bright TiCN Hardslick	Steam Oxide TiCN Hardslick
-		-	-	R40°	R40°	R40°	R40°	R15°	R15°
3.0D		3.0D	3.0D	2.5D	2.5D	2.5D	2.5D	2.5D	2.5D
Through		Through	Through	Blind	Blind	Blind	Blind	Blind	Blind
⊙	⊙	○	○	○	○	○	○		
⊙	⊙	○	○	⊙	⊙	⊙	⊙		
⊙	⊙			⊙	⊙	⊙	⊙	○	○
⊙	⊙							⊙	⊙
⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙		
⊙	⊙			⊙	⊙	⊙	⊙	○	○
⊙	⊙								
⊙	⊙			○	○	○	○		
⊙	⊙			○	○	○	○		
⊙	⊙			○	○	○	○		
								○	○
								○	○
								○	○



HIGH PERFORMANCE TAPS RECOMMENDATION TABLE

Super HSS : Premium HSS Metallurgy
 P-HSS : Powdered Metallurgy
 HSSE-V3 : 3% Vanadium Alloy HSS-EX
 HSS-V : Vanadium Alloy HSS

◎ = RECOMMENDED
 ○ = SUITABLE

COOLANT
 A = Cutting Oil
 T = Oil Emulsion
 X = Cutting Oil/Oil Emulsion

Material Group	Material Sub-Group	ISO	Hardness (HRC)	Hardness (BHN)	Cutting Speed (SFM)		COOLANT	Ti / Ni	VA	VA
					Uncoated	Coated				
Steel	Low carbon steels Free machining carbon steels	P	< 15	< 180	25 - 50	50 - 80	T			
	Medium to high carbon steels Low alloyed steels	P	< 23	< 240	25 - 50	50 - 80	T			
	Steel castings & forgings Heat-treatable alloy steels	P	> 24 ≤ 38	> 250 ≤ 350	6 - 30	10 - 35	X			
	Alloyed tool steels Mold steels	P	> 38 ≤ 44	> 350 ≤ 420	6 - 12	-	A			
Stainless Steel	Free machining stainless steels	M	< 23	< 240	12 - 35	20 - 50	A			
	Heat-and corrosion-resistant stainless steels Valve stainless steels	M	> 24 ≤ 38	> 250 ≤ 350	12 - 15	12 - 15	A			
	Stainless steel castings Precipitation hardening stainless steels	M	> 38 ≤ 44	> 350 ≤ 420	12 - 15	-	A			
Cast Iron	Grey cast iron	K	-	≤ 220	35 - 50	50 - 65	T			
	Nodular cast iron / Chilled cast iron Meehanite iron / Ductile iron	K	-	≥ 250	12 - 45	25 - 55	X			
Copper	Pure and alloyed copper	N	-	-	50 - 60	65 - 100	T			
Brass	Free machining brass Alloyed brass	N	-	-	30 - 65	-	T			
Bronze		N	44	< 420	12 - 20	35 - 80	T			
Aluminum	Pure Aluminum Aluminum alloys	N	-	-	50 - 65	-	T			
	Aluminum alloy castings	N	-	-	40 - 65	45 - 90	T			
Zinc		N	-	-	25 - 65	50 - 80	T			
Magnesium		N	-	-	-	45 - 100	T			
Nickel Alloys	718 & 625 INCONEL / Waspaloy Hastelloyn / Invar Monel / Incoloy	S	≤ 38	≤ 350	10 - 15	-	A			
	718 Inconel A286	S	> 38 ≤ 44	> 350 ≤ 420	10 - 12	-	A			
Titanium		S	≤ 38	≤ 350	3 - 15	-	A			

VG	VA	VA	VA	VG	VG	VG	AI
BG/BG-GB	B1/B0/B2/D2	BS/BT	E6/E8/E9	D3/E0	BU/BV	E2/E4/E5	C0/D8
DIN Length-ANSI Shank	USCTI 302A	USCTI 302A	DIN Length-ANSI Shank	USCTI 302A	USCTI 302A	DIN Length-ANSI Shank	USCTI 302A
403	404	407	408	409	412	414	415
UNC/UN8	UNC/UNF	M/MF	M/MF	UNC/UNF	M/MF	M/MF	UNC/UNF
HSSE-V3	HSSE-V3	HSSE-V3	HSSE-V3	HSSE-V3	HSSE-V3	HSSE-V3	HSSE-V3
2-3P	2-3P	2-3P	2-3P	2-3P	2-3P	2-3P	2-3P
Hardslick Gold & Black	Bright Steam Oxide TiN Hardslick	Steam Oxide Hardslick	Steam Oxide TiCN Hardslick	Steam Oxide Hardslick	Steam Oxide Hardslick	Steam Oxide TiCN Hardslick	Bright Hardslick
R40°	R45°	R45°	R45°	R45°	R45°	R45°	R50°
2.5D	2.5D	2.5D	2.5D	2.5D	2.5D	2.5D	2.5D
Blind	Blind	Blind	Blind	Blind	Blind	Blind	Blind



HIGH PERFORMANCE TAPS RECOMMENDATION TABLE

Super HSS : Premium HSS Metallurgy
 P-HSS : Powdered Metallurgy
 HSSE-V3 : 3% Vanadium Alloy HSS-EX
 HSS-V : Vanadium Alloy HSS

⊙ = RECOMMENDED
 ○ = SUITABLE

COOLANT
 A = Cutting Oil
 T = Oil Emulsion
 X = Cutting Oil/Oil Emulsion

Material Group	Material Sub-Group	ISO	Hardness (HRc)	Hardness (BHN)	Cutting Speed (SFM)		COOLANT	Uncoated	Coated
					Uncoated	Coated			
Steel	Low carbon steels Free machining carbon steels	P	< 15	< 180	25 - 50	50 - 80	T	○	○
	Medium to high carbon steels Low alloyed steels	P	< 23	< 240	25 - 50	50 - 80	T	○	○
	Steel castings & forgings Heat-treatable alloy steels	P	> 24 ≤ 38	> 250 ≤ 350	6 - 30	10 - 35	X		
	Alloyed tool steels Mold steels	P	> 38 ≤ 44	> 350 ≤ 420	6 - 12	-	A		
Stainless Steel	Free machining stainless steels	M	< 23	< 240	12 - 35	20 - 50	A		
	Heat-and corrosion-resistant stainless steels Valve stainless steels	M	> 24 ≤ 38	> 250 ≤ 350	12 - 15	12 - 15	A		
	Stainless steel castings Precipitation hardening stainless steels	M	> 38 ≤ 44	> 350 ≤ 420	12 - 15	-	A		
Cast Iron	Grey cast iron	K	-	≤ 220	35 - 50	50 - 65	T	○	○
	Nodular cast iron / Chilled cast iron Meehanite iron / Ductile iron	K	-	≥ 250	12 - 45	25 - 55	X		
Copper	Pure and alloyed copper	N	-	-	50 - 60	65 - 100	T		
Brass	Free machining brass	N	-	-	30 - 65	-	T		
	Alloyed brass	N	-	-	30 - 65	-	T		
Bronze		N	44	< 420	12 - 20	35 - 80	T		
Aluminum	Pure Aluminum Aluminum alloys	N	-	-	50 - 65	-	T	○	○
	Aluminum alloy castings	N	-	-	40 - 65	45 - 90	T	○	○
Zinc		N	-	-	25 - 65	50 - 80	T		
Magnesium		N	-	-	-	45 - 100	T		
Nickel Alloys	718 & 625 INCO _n / Waspaloy Hastelloyn / Invar Monel _n / Incoloy	S	≤ 38	≤ 350	10 - 15	-	A		
	718 Inconel A286	S	> 38 ≤ 44	> 350 ≤ 420	10 - 12	-	A		
Titanium		S	≤ 38	≤ 350	3 - 15	-	A		



CARBIDE

Being the best through innovation






SOLID CARBIDE THREAD MILL

SELECTION GUIDE

- For blind holes and through holes with one single tool.
- Higher cutting speed and feed than taps.


INCH

EDP No.	MODEL	Description	Page
TE		Solid Carbide Thread mill for Unified Internal Threads - ANSI B 1.1	357
TD		Solid Carbide Thread mill for Metric Internal Threads - DIN 13	358
TF TG		Solid Carbide Thread mill for Unified Internal Threads - ANSI B 1.20.1(NPT) / ANSI B1.20.3(NPTF)	359

YG SOLID CARBIDE THREAD MILLS

TE SERIES

SOLID CARBIDE THREAD MILL FOR UNIFIED INTERNAL THREADS - ANSI B 1.1



- ▶ Material : Solid Carbide
- ▶ Shank : Plain Straight
- ▶ Spiral Angle : 15°

Unit : Inch

SIZE	Pitch	Cutter Diameter	Shank Diameter	Thread Length	Overall Length	No. of Flute	EDP No.
	TPI	D ₁	D ₂	L ₁	L ₂	Z	TAIN
#2	56	.065	.125	.125	2.000	3	TE080
#3	48	.075	.125	.167	2.000	3	TE120
#5	44	.095	.125	.228	2.000	3	TE220
#4	40	.085	.125	.175	2.000	3	TE160
#8	36	.115	.125	.250	2.000	3	TE300
#6	32	.100	.125	.218	2.000	3	TE240
#8	32	.115	.125	.250	2.000	3	TE280
#10	32	.120	.125	.312	2.000	3	TE340
1/2	32	.370	.375	1.000	3.500	4	TEF90
#10	28	.120	.125	.312	2.000	3	TEK90
1/4	28	.180	.187	.500	2.500	3	TE420
1/2	28	.370	.375	1.000	3.500	4	TE590
#10	24	.120	.125	.312	2.000	3	TE320
5/16	24	.235	.250	.625	2.500	3	TE460
3/8	24	.285	.312	.750	3.000	4	TE500
1/2	24	.370	.375	1.000	3.500	4	TE570
1/4	20	.180	.187	.500	2.500	3	TE400
7/16	20	.335	.375	.875	3.500	4	TE540
1/2	20	.370	.375	1.000	3.500	4	TE580
5/16	18	.235	.250	.625	2.500	3	TE440
9/16	18	.370	.375	.875	3.500	4	TE620
3/8	16	.285	.312	.750	3.000	4	TE480
3/4	16	.490	.500	1.250	3.500	4	TE720
7/16	14	.305	.312	.750	3.000	4	TE520
7/8	14	.490	.500	1.250	3.500	4	TE760
1/2	13	.350	.375	.875	3.500	4	TE560
9/16	12	.370	.375	.875	3.500	4	TE600
3/4	12	.495	.500	1.250	3.500	4	TE710
5/8	11	.470	.500	1.250	3.500	4	TE640
3/4	10	.495	.500	1.250	3.500	4	TE700
7/8	9	.620	.625	1.375	4.000	4	TE740
1	8	.620	.625	1.375	4.000	4	TE780
1	12	.745	.750	1.500	4.000	5	TE800
1-1/8 & 1-1/4	7	.745	.750	1.572	4.500	5	TE820

◎ : Excellent ○ : Good

P			M	K	N	S	
Carbon Steels	Alloy Steels	Heat Treated Steels	Stainless Steels	Cast Iron	Non Ferrous Materials	Titanium Alloy	Chrome-Nickel Alloy
◎	◎	◎	○	◎	◎	○	○

HSS

CARBIDE

THREAD MILLS

COMBO TAPS

SPIRAL FLUTE TAPS

SPIRAL POINT TAPS

STRAIGHT FLUTE TAPS

FORMING TAPS

SCREW THREAD INSERT TAPS


PIPE TAPS

TECHNICAL DATA

Y/G SOLID CARBIDE THREAD MILLS

TD SERIES

SOLID CARBIDE THREAD MILL FOR METRIC INTERNAL THREADS - DIN 13



- Material : Solid Carbide
- Shank : Plain Straight
- Spiral Angle : 15°

Unit : Inch

SIZE	Pitch (mm)	Cutter Diameter	Shank Diameter	Thread Length	Overall Length	No. of Flute	EDP No.
	P	D ₁	D ₂	L ₁	L ₂	Z	TiAIN
M3	0.50	.085	.125	.178	2.000	3	TD200
M4	0.70	.115	.125	.276	2.000	3	TD240
M4.5	0.75	.120	.125	.250	2.000	3	TD260
M8	0.75	.235	.250	.625	2.500	3	TD380
M5	0.80	.120	.125	.312	2.000	3	TD280
M6	1.00	.170	.187	.500	2.500	3	TD310
M12	1.00	.360	.375	.875	3.500	4	TD530
M8	1.25	.235	.250	.625	2.500	3	TD360
M10	1.50	.300	.312	.750	3.000	4	TD420
M14	1.50	.370	.375	.875	3.500	4	TD550
M18	1.50	.490	.500	1.250	3.500	4	TD670
M12	1.75	.360	.375	.875	3.500	4	TD500
M16	2.00	.470	.500	1.250	3.500	4	TD600
M20	2.50	.495	.500	1.250	3.500	4	TD700
M24	3.00	.620	.625	1.375	4.000	4	TD780


◎ : Excellent ○ : Good

P			M	K	N	S	
Carbon Steels	Alloy Steels	Heat Treated Steels	Stainless Steels	Cast Iron	Non Ferrous Materials	Titanium Alloy	Chrome-Nickel Alloy
◎	◎	◎	○	◎	◎	○	○

Y/G SOLID CARBIDE THREAD MILLS

TF/TG SERIES

SOLID CARBIDE THREAD MILL FOR UNIFIED INTERNAL THREADS - ANSI B 1.20.1(NPT) / ANSI B1.20.3(NPTF)



- Material : Solid Carbide
- Shank : Plain Straight
- Spiral Angle : 15°

Unit : Inch

TF Series (NPT)

SIZE	Pitch	Cutter Diameter	Shank Diameter	Thread Length	Overall Length	No. of Flute	EDP No.
	T.P.I.	D ₁	D ₂	L ₁	L ₂	Z	TiAIN
1/16 & 1/8	27	.245	.250	.437	2.500	3	TF020
1/4 & 3/8	18	.305	.312	.625	3.000	4	TF400
1/4 & 3/8	18	.363	.375	.680	3.500	4	TF480
1/2 & 3/4	14	.495	.500	.875	3.500	4	TF560
1" - 2"	11.5	.620	.625	1.125	4.000	4	TF780
2-1/2" - 6"	8	.745	.750	1.500	5.000	4	TFF40

TG Series (NPTF)

SIZE	Pitch	Cutter Diameter	Shank Diameter	Thread Length	Overall Length	No. of Flute	EDP No.
	T.P.I.	D ₁	D ₂	L ₁	L ₂	Z	TiAIN
1/16 & 1/8	27	.245	.250	.437	2.500	3	TG020
1/4 & 3/8	18	.305	.312	.625	3.000	4	TG400
1/2 & 3/4	14	.495	.500	.875	3.500	4	TG560
1" - 2"	11.5	.620	.625	1.125	4.000	4	TG780
2-1/2" - 6"	8	.745	.750	1.500	5.000	4	TGF40

◎ : Excellent ○ : Good

P			M	K	N	S	
Carbon Steels	Alloy Steels	Heat Treated Steels	Stainless Steels	Cast Iron	Non Ferrous Materials	Titanium Alloy	Chrome-Nickel Alloy
◎	◎	◎	○	◎	◎	○	○

YG SOLID CARBIDE THREAD MILLS

RECOMMENDED CUTTING SPEED

Unit : Inch

Material	Cutting Speed (SFM)	Feed per Tooth (fz)	
		Cutter Diameter < 5/16	Cutter Diameter > 5/16
Low Carbon Steels Medium Carbon Steels	250 - 400	.0008 - .0016	.0016 - .0040
High Carbon Steels	250 - 350	.0008 - .0016	.0016 - .0040
Alloy Steels	250 - 300	.0008 - .0016	.0016 - .0040
Heat Treated Steels	200 - 300	.0008 - .0016	.0016 - .0040
Stainless Steels	150 - 250	.0004 - .0008	.0008 - .0024
Cast Iron	200 - 350	.0008 - .0016	.0016 - .0040
Chrome-Nickel Alloys Titanium Alloys	70 - 200	.0004 - .0008	.0008 - .0024
Non Ferrous Material	350 - 1000	.0012 - .0020	.0020 - .0040

RECOMMENDED CUTTING SPEED

Calculate R.P.M of cutter

$$N = \frac{12 \times \text{SFM}}{d \times \pi}$$

Calculate Feed per Revolution

$$F_1 = fz \times Z \times N$$

Calculate Feed at Tool Center Line

$$F_2 = \frac{F_1 \times (D - d)}{D}$$

- N : R.P.M
- SFM : Recommended Cutting Speed
- d : Diameter of Cutter
- fz : Recommended Feed per Tooth
- Z : Number of Teeth
- F₁ : Feed at Cutting Edge
- F₂ : Feed at Center Line of Cutting
- D : Major Diameter of Component

YG-1 SMART TOOL RECOMMENDATION for the Total Solution of Cutting Tools

SCAN QR CODE TO YG-1 SMART TOOL RECOMMENDATION

HARD *slick*

ULTIMATE TAP PERFORMANCE

Application Range

SOFT 70 BHN ————— HARD 340 BHN

**STEEL • STAINLESS STEEL
NICKEL ALLOYS
ALUMINUM**

- Reduces Galling & Seizing
- Extends Life with Minimal Coolant
- Reduces Tap Inventory

TAP SUBSTRATE -
67Rc .8 Coefficient of Friction

TIALN - 90Rc

WC/C - .2 Coefficient of Friction



Being the best through innovation

HSS



COMBO TAPS

- Spiral Point and Spiral Flute Taps
Multi Purpose tapping / YG-1's Patent / Super HSS & HSS-EX for Prevention of Oversized Threads

SELECTION GUIDE

Spiral Point and Spiral Flute Taps

Multi Purpose tapping / YG-1's Patent / Super HSS & HSS-EX for Prevention of Oversized Threads

INCH/METRIC


EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page	
T2 T2-S T2-C		HSS-EX	UNC/UNF	MU	USCTI 302A	H	2 ~ 3P	2.5D	Bright Steam Oxide TiCN	365	
T5 T5-S T5-C		HSS-EX	M/MF	MU	USCTI 302A	D	2 ~ 3P		Bright Steam Oxide TiCN	367	
T6 T6-N	with Internal Coolant 	HSS-EX	UNC/UNF	MU	USCTI 302A	H	2 ~ 3P		Bright TiN	368	
T8 T8-N	with Internal Coolant 	HSS-EX	M	MU	USCTI 302A	D	2 ~ 3P		Bright TiN	369	
T7 T7-C	Short Chamfer 	HSS-EX	UNC/UNF	MU	USCTI 302A	H	1 ~ 2P		Bright TiCN	370	
T9 T9-C	Short Chamfer 	HSS-EX	M/MF	MU	USCTI 302A	D	1 ~ 2P		Bright TiCN	372	
T1-S T1-C		HSS-EX	UNC/UNF	MU	DIN Length-ANSI Shank	H	2 ~ 3P		Steam Oxide TiCN	373	
TA-S TA-C		HSS-EX	M/MF	MU	DIN Length-ANSI Shank	D	2 ~ 3P		Steam Oxide TiCN	374	
TCA-S/C TCB-S/C		Super HSS HSS-EX	UNC/UNF	VA	USCTI 302A	H	2 ~ 3P		Steam Oxide TiCN	375	
TCC-S/C TCB-S/C		Super HSS HSS-EX	M/MF	VA	USCTI 302A	D	2 ~ 3P		Steam Oxide TiCN	377	
T4 T4-S T4-C		HSS-EX	UNC/UNF	MU	USCTI 302A	H	4 ~ 5P		3.0D	Bright Steam Oxide TiCN	378
T3 T3-S T3-C		HSS-EX	M/MF	MU	USCTI 302A	D	4 ~ 5P			Bright Steam Oxide TiCN	380
TB TB-N	with Internal Coolant 	HSS-EX	UNC/UNF	MU	USCTI 302A	H	4 ~ 5P	Bright TiN		381	
TH TH-N	with Internal Coolant 	HSS-EX	M	MU	USCTI 302A	D	4 ~ 5P	Bright TiN		382	
TC-S TC-C		HSS-EX	UNC/UNF	MU	DIN Length-ANSI Shank	H	4 ~ 5P	Steam Oxide TiCN		383	
TK-S TK-C		HSS-EX	M/MF	MU	DIN Length-ANSI Shank	D	4 ~ 5P	Steam Oxide TiCN		384	
TCE-S/C TCF-S/C		Super HSS HSS-EX	UNC/UNF	VA	USCTI 302A	H	4P	Steam Oxide TiCN		385	
TCG-S/C TCH-S/C		Super HSS HSS-EX	M/MF	VA	USCTI 302A	D	4P	Steam Oxide TiCN		387	

COMBO TAPS


Combo TAP

T2/T2-S/T2-C SERIES

SPIRAL FLUTE TAPS for Multi-Purpose



Thread Depth / Hole Type
2.5×D



MU HSS-EX UNC UNF USCTI 302A 2P~3P Bright Steam Oxide TiCN R40

SIZE & TPI	Limit	Overall Length L	Thread Length Lt	Shank Diameter D	Square Size K	Square Length kl	No. of Flute	EDP No.		
								Bright	Steam Oxide	TiCN
#4 - 40 UNC	H2	1.88	.236	.141	.110	.188	2	T2162	T2162S	T2162C
#4 - 48 UNF	H2	1.88	.236	.141	.110	.188	2	T2182	T2182S	T2182C
#5 - 40 UNC	H2	1.94	.236	.141	.110	.188	3	T2202	T2202S	T2202C
#5 - 44 UNF	H2	1.94	.236	.141	.110	.188	3	T2222	T2222S	T2222C
#6 - 32 UNC	H3	2.00	.276	.141	.110	.188	3	T2243	T2243S	T2243C
#6 - 40 UNF	H2	2.00	.276	.141	.110	.188	3	T2262	T2262S	T2262C
#8 - 32 UNC	H3	2.13	.276	.168	.131	.250	3	T2283	T2283S	T2283C
#8 - 36 UNF	H2	2.13	.276	.168	.131	.250	3	T2302	T2302S	T2302C
#10 - 24 UNC	H3	2.38	.354	.194	.152	.250	3	T2323	T2323S	T2323C
#10 - 32 UNF	H3	2.38	.276	.194	.152	.250	3	T2343	T2343S	T2343C
#12 - 24 UNC	H3	2.38	.354	.220	.165	.281	3	T2363	T2363S	T2363C
#12 - 28 UNF	H3	2.38	.276	.220	.165	.281	3	T2383	T2383S	T2383C
1/4 - 20 UNC	H3	2.50	.433	.255	.191	.312	3	T2403	T2403S	T2403C
1/4 - 20 UNC	H5	2.50	.433	.255	.191	.312	3	T2405	T2405S	T2405C
1/4 - 28 UNF	H3	2.50	.354	.255	.191	.312	3	T2423	T2423S	T2423C
1/4 - 28 UNF	H4	2.50	.354	.255	.191	.312	3	T2424	T2424S	T2424C
5/16 - 18 UNC	H3	2.72	.472	.318	.238	.375	3	T2443	T2443S	T2443C
5/16 - 18 UNC	H5	2.72	.472	.318	.238	.375	3	T2445	T2445S	T2445C
5/16 - 24 UNF	H3	2.72	.394	.318	.238	.375	3	T2463	T2463S	T2463C
5/16 - 24 UNF	H5	2.72	.394	.318	.238	.375	3	T2465	T2465S	T2465C

► Coating (TiN, TiAlN or Hardslick) is available on your request.

► Coating Codes for Combo Tap
Bright Finish No. + N (TiN), F (TiAlN), H (Hardslick)

► Steam Oxide is not recommended for Aluminum and Aluminum alloys.


► NEXT PAGE

P				M				K		
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)			
○	○	○	○	○	○	○	○	○	○	
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
○	○	○	○	○	○	○	○	○	○	



T2/T2-S/T2-C SERIES

SPIRAL FLUTE TAPS for Multi-Purpose



Material and coating options: MU, HSS-EX, UNC UNF, USCTI 302A, 2P~3P, Bright, Steam Oxide, TiCN, R40.

Table with columns: SIZE & TPI, Limit, Overall Length, Thread Length, Shank Diameter, Square Size, Square Length, No. of Flute, EDP No. (Bright, Steam Oxide, TiCN).


Coating (TiN, TiAlN or Hardslick) is available on your request. Coating Codes for Combo Tap: Bright Finish No. + N(TiN), F(TiAlN), H(Hardslick). Steam Oxide is not recommended for Aluminum and Aluminum alloys.

Material compatibility table with columns P, M, K, N, S and rows for various materials like carbon steels, stainless steels, and cast irons.



T5/T5-S/T5-C SERIES

SPIRAL FLUTE TAPS for Multi-Purpose



Material and coating options: MU, HSS-EX, M/MF, USCTI 302A, 2P~3P, Bright, Steam Oxide, TiCN, R40.

Table with columns: SIZE & TPI, Limit, Overall Length, Thread Length, Shank Diameter, Square Size, Square Length, No. of Flute, EDP No. (Bright, Steam Oxide, TiCN).

Coating (TiN, TiAlN or Hardslick) is available on your request. Coating Codes for Combo Tap: Bright Finish No. + N(TiN), F(TiAlN), H(Hardslick).

Steam Oxide is not recommended for Aluminum and Aluminum alloys. © : Excellent ○ : Good



Material compatibility table with columns P, M, K, N, S and rows for various materials like carbon steels, stainless steels, and cast irons.




T6/T6-N SERIES

SPIRAL FLUTE TAPS for Multi-Purpose

with Internal Coolant



Thread Depth / Hole Type
2.5×D



MU HSS-EX UNC UNF USCTI 302A 2P~3P Bright TiN R40

Unit : Inch

SIZE & TPI	Limit	Overall Length L	Thread Length Lt	Shank Diameter D	Square Size K	Square Length kl	No. of Flute	EDP No.	
								Bright	TiN
1/4 - 20 UNC	H5	2.50	.433	.255	.191	.312	3	T6405	T6405N
1/4 - 28 UNF	H4	2.50	.354	.255	.191	.312	3	T6424	T6424N
5/16 - 18 UNC	H5	2.72	.472	.318	.238	.375	3	T6445	T6445N
5/16 - 24 UNF	H4	2.72	.394	.318	.238	.375	3	T6464	T6464N
3/8 - 16 UNC	H5	2.94	.551	.381	.286	.438	3	T6485	T6485N
3/8 - 24 UNF	H4	2.94	.394	.381	.286	.438	3	T6504	T6504N
7/16 - 14 UNC	H5	3.16	.591	.323	.242	.406	3	T6525	T6525N
7/16 - 20 UNF	H5	3.16	.472	.323	.242	.406	3	T6545	T6545N
1/2 - 13 UNC	H5	3.38	.630	.367	.275	.438	3	T6565	T6565N
1/2 - 20 UNF	H5	3.38	.472	.367	.275	.438	3	T6585	T6585N
9/16 - 12 UNC	H5	3.59	.709	.429	.322	.500	3	T6605	T6605N
9/16 - 18 UNF	H5	3.59	.512	.429	.322	.500	3	T6625	T6625N
5/8 - 11 UNC	H5	3.81	.748	.480	.360	.562	4	T6645	T6645N
5/8 - 18 UNF	H5	3.81	.512	.480	.360	.562	4	T6665	T6665N
3/4 - 10 UNC	H5	4.25	.827	.590	.442	.688	4	T6705	T6705N
3/4 - 16 UNF	H5	4.25	.591	.590	.442	.688	4	T6725	T6725N
7/8 - 9 UNC	H6	4.69	.827	.697	.523	.750	4	T6746	T6746N
7/8 - 14 UNF	H6	4.69	.709	.697	.523	.750	4	T6766	T6766N
1 - 8 UNC	H6	5.13	.984	.800	.600	.812	4	T6786	T6786N
1 - 12 UNF	H6	5.13	.709	.800	.600	.812	4	T6806	T6806N

► Coating(TiCN, TiAlN or Hardslick) or Surface Treatment(Steam Oxide) is available on your request.
Coating Codes for Combo Tap
Bright Finish No. + C(TiCN), F(TiAlN), H(Hardslick), S(Steam Oxide)

◎ : Excellent ○ : Good



P				M				K		
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)			
◎	◎	◎	◎	◎	◎	◎	◎			
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎




T8/T8-N SERIES

SPIRAL FLUTE TAPS for Multi-Purpose

with Internal Coolant



Thread Depth / Hole Type
2.5×D



MU HSS-EX M USCTI 302A 2P~3P Bright TiN R40

Unit : Inch

SIZE & TPI	Limit	Overall Length L	Thread Length Lt	Shank Diameter D	Square Size K	Square Length kl	No. of Flute	EDP No.	
								Bright	TiN
M6 x 1.0	D5	2.50	.433	.255	.191	.312	3	T8315	T8315N
M8 x 1.25	D5	2.72	.472	.318	.238	.375	3	T8365	T8365N
M10 x 1.5	D6	2.94	.512	.381	.286	.438	3	T8426	T8426N
M12 x 1.75	D6	3.38	.591	.367	.275	.438	3	T8506	T8506N
M14 x 2.0	D7	3.59	.709	.429	.322	.500	3	T8547	T8547N
M16 x 2.0	D7	3.81	.709	.480	.360	.562	3	T8607	T8607N
M18 x 2.5	D7	4.03	.787	.542	.406	.625	4	T8657	T8657N
M20 x 2.5	D7	4.47	.787	.652	.489	.688	4	T8707	T8707N

► Coating(TiCN, TiAlN or Hardslick) or Surface Treatment(Steam Oxide) is available on your request.
Coating Codes for Combo Tap
Bright Finish No. + C(TiCN), F(TiAlN), H(Hardslick), S(Steam Oxide)

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)			
◎	◎	◎	◎	◎	◎	◎	◎			
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎




T7/T7-C SERIES

SPIRAL FLUTE TAPS for Multi-Purpose

Short Chamfer



Thread Depth / Hole Type 2.5xD



MU HSS-EX UNC UNF USCTI 302A 1P~2P Bright TiCN R40

Unit : Inch

Table with columns: SIZE & TPI, Limit, Overall Length (L), Thread Length (Lt), Shank Diameter (D), Square Size (K), Square Length (kl), No. of Flute, EDP No. (Bright, TiCN). Rows include sizes like #4 - 40 UNC, #4 - 48 UNF, #5 - 40 UNC, etc.

Coating(TiN, TiAlN or Hardslick) or Surface Treatment(Steam Oxide) is available on your request. Coating Codes for Combo Tap Bright Finish No. + N(TiN), F(TiAlN), H(Hardslick), S(Steam Oxide)

NEXT PAGE

⊙ : Excellent ○ : Good



Material compatibility table with columns P, M, K, N, S. Rows list materials like Low carbon steels, Steel castings, Alloyed tool steels, Free machining stainless steels, Heat and corrosion resistant stainless steels, Stainless steel castings, Grey cast iron, Nodular cast iron, Pure and alloyed copper, Free machining brass, Bronze, Pure Aluminum/Aluminum alloy, Aluminum alloy castings, Zinc, Magnesium, 718 & 625 INCO, Waspaloy / Hastelloy / Invar / Monel / Incoloy, 718 Inconel / A286, Titanium.




T7/T7-C SERIES

SPIRAL FLUTE TAPS for Multi-Purpose

Short Chamfer



Thread Depth / Hole Type 2.5xD



MU HSS-EX UNC UNF USCTI 302A 1P~2P Bright TiCN R40

Unit : Inch

Table with columns: SIZE & TPI, Limit, Overall Length (L), Thread Length (Lt), Shank Diameter (D), Square Size (K), Square Length (kl), No. of Flute, EDP No. (Bright, TiCN). Rows include sizes like 9/16 - 12 UNC, 9/16 - 18 UNF, 5/8 - 11 UNC, etc.

Coating(TiN, TiAlN or Hardslick) or Surface Treatment(Steam Oxide) is available on your request. Coating Codes for Combo Tap Bright Finish No. + N(TiN), F(TiAlN), H(Hardslick), S(Steam Oxide)

⊙ : Excellent ○ : Good


Material compatibility table with columns P, M, K, N, S. Rows list materials like Low carbon steels, Medium to high carbon steels, Steel castings & forgings, Alloyed tool steels, Free machining stainless steels, Heat and corrosion resistant stainless steels, Stainless steel castings, Grey cast iron, Nodular cast iron, Pure and alloyed copper, Free machining brass, Bronze, Pure Aluminum/Aluminum alloy, Aluminum alloy castings, Zinc, Magnesium, 718 & 625 INCO, Waspaloy / Hastelloy / Invar / Monel / Incoloy, 718 Inconel / A286, Titanium.



T9/T9-C SERIES

SPIRAL FLUTE TAPS for Multi-Purpose

Short Chamfer



Thread Depth / Hole Type 2.5xD

Material and coating options: MU, HSS-EX, M/MF, USCTI 302A, 1P~2P, Bright, TiCN, R40

Unit : Inch

Table with columns: SIZE & TPI, Limit, Overall Length, Thread Length, Shank Diameter, Square Size, Square Length, No. of Flute, EDP No. (Bright, TiCN)

Coating (TiN, TiAlN or Hardslick) or Surface Treatment (Steam Oxide) is available on your request. Coating Codes for Combo Tap: Bright Finish No. + N (TiN), F (TiAlN), H (Hardslick), S (Steam Oxide)


Material compatibility chart with columns P, M, K, N, S and rows for various materials like carbon steels, stainless steels, cast irons, and alloys.



T1-S/T1-C SERIES

SPIRAL FLUTE TAPS for Multi-Purpose

DIN Length-ANSI Shank



Thread Depth / Hole Type 2.5xD

Material and coating options: MU, HSS-EX, UNC UNF, 2P~3P, Steam Oxide, TiCN, R40

Unit : Inch

Table with columns: SIZE & TPI, Limit, Overall Length, Thread Length, Shank Diameter, Square Size, Square Length, No. of Flute, EDP No. (Steam Oxide, TiCN)

Steam Oxide is not recommended for Aluminum and Aluminum alloys.


Material compatibility chart with columns P, M, K, N, S and rows for various materials like carbon steels, stainless steels, cast irons, and alloys.



TA-S / TA-C SERIES

SPIRAL FLUTE TAPS for Multi-Purpose

DIN Length-ANSI Shank



Thread Depth / Hole Type
2.5×D

MU **HSS-EX** **M/MF** **2P~3P** **Steam Oxide** **TICN** **R40**

Unit : Inch

SIZE & TPI	Limit	Overall Length L	Thread Length Lt	Shank Diameter D	Square Size K	Square Length kl	No. of Flute	EDP No.	
								Steam Oxide	TiCN
M3 x 0.5	D3	2.21	.197	.141	.110	.188	3	TA203S	TA203C
M3.5 x 0.6	D4	2.21	.276	.141	.110	.188	3	TA224S	TA224C
M4 x 0.7	D4	2.48	.276	.168	.131	.250	3	TA244S	TA244C
M5 x 0.8	D4	2.76	.354	.194	.152	.250	3	TA284S	TA284C
M6 x 1.0	D5	3.15	.433	.255	.191	.312	3	TA315S	TA315C
M8 x 1.25	D5	3.54	.472	.318	.238	.375	3	TA365S	TA365C
M10 x 1.5	D6	3.94	.512	.381	.286	.438	3	TA426S	TA426C
M10 x 1.25	D5	3.94	.472	.381	.286	.438	3	TA435S	TA435C
M12 x 1.75	D6	4.33	.591	.367	.275	.438	3	TA506S	TA506C
M12 x 1.25	D5	3.94	.551	.367	.275	.438	3	TA525S	TA525C
M14 x 2.0	D7	4.33	.709	.429	.322	.500	3	TA547S	TA547C
M14 x 1.5	D6	3.94	.551	.429	.322	.500	3	TA556S	TA556C
M16 x 2.0	D7	4.33	.709	.480	.360	.562	3	TA607S	TA607C
M16 x 1.5	D6	3.94	.551	.480	.360	.562	3	TA616S	TA616C
M18 x 2.5	D7	4.92	.787	.542	.406	.625	4	TA657S	TA657C
M18 x 1.5	D6	4.33	.551	.542	.406	.625	4	TA676S	TA676C

► Steam Oxide is not recommended for Aluminum and Aluminum alloys.


◎ : Excellent ○ : Good

P				M				K	
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)	◎	◎
K		N				S			
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎



TCA-S / TCB-S / TCA-C / TCB-C SERIES

SPIRAL FLUTE TAPS for Stainless Steels



Thread Depth / Hole Type
2.5×D

VA **Super HSS** **HSS-EX** **UNC UNF** **USCTI 302A** **2P~3P** **Steam Oxide** **TICN** **R45**

Unit : Inch

SIZE & TPI	Limit	Overall Length L	Thread Length Lt	Shank Diameter D	Square Size K	Square Length kl	No. of Flute	EDP No.	
								Steam Oxide	TiCN
#5 - 40 UNC	H2	1.94	.236	.141	.110	.188	3	TCA202S	TCA202C
#6 - 32 UNC	H3	2.00	.276	.141	.110	.188	3	TCA243S	TCA243C
#8 - 32 UNC	H3	2.13	.276	.141	.131	.250	3	TCA283S	TCA283C
#10 - 24 UNC	H3	2.38	.354	.141	.152	.250	3	TCA323S	TCA323C
#10 - 32 UNF	H3	2.38	.276	.141	.152	.250	3	TCA343S	TCA343C
1/4 - 20 UNC	H3	2.50	.433	.141	.191	.312	3	TCA403S	TCA403C
1/4 - 20 UNC	H5	2.50	.433	.168	.191	.312	3	TCA405S	TCA405C
1/4 - 28 UNF	H3	2.50	.354	.168	.191	.312	3	TCA423S	TCA423C
5/16 - 18 UNC	H3	2.72	.472	.194	.238	.375	3	TCA443S	TCA443C
5/16 - 18 UNC	H5	2.72	.472	.194	.238	.375	3	TCA445S	TCA445C
5/16 - 24 UNF	H3	2.72	.394	.220	.238	.375	3	TCA463S	TCA463C
3/8 - 16 UNC	H3	2.94	.551	.220	.286	.438	3	TCA483S	TCA483C
3/8 - 16 UNC	H5	2.94	.551	.255	.286	.438	3	TCA485S	TCA485C
3/8 - 24 UNF	H3	2.94	.394	.255	.286	.438	3	TCA503S	TCA503C
7/16 - 14 UNC	H3	3.16	.591	.255	.242	.406	3	TCA523S	TCA523C
7/16 - 14 UNC	H5	3.16	.591	.255	.242	.406	3	TCA525S	TCA525C
7/16 - 20 UNF	H3	3.16	.472	.318	.242	.406	3	TCA543S	TCA543C
7/16 - 20 UNF	H5	3.16	.472	.318	.242	.406	3	TCA545S	TCA545C
1/2 - 13 UNC	H3	3.38	.630	.318	.275	.438	3	TCA563S	TCA563C
1/2 - 13 UNC	H5	3.38	.630	.318	.275	.438	3	TCA565S	TCA565C
1/2 - 20 UNF	H3	3.38	.472	.381	.275	.438	3	TCA583S	TCA583C
9/16 - 12 UNC	H3	3.59	.709	.381	.322	.500	3	TCB603S	TCB603C
9/16 - 18 UNF	H3	3.59	.512	.381	.322	.500	3	TCB623S	TCB623C

Super HSS(#5~1/2) and HSS-EX(9/16~1")


► NEXT PAGE

◎ : Excellent ○ : Good

P				M				K	
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)	◎	◎
K		N				S			
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
◎	◎	◎	◎	◎	◎	◎	◎	◎	◎



SPIRAL FLUTE TAPS for Stainless Steels



VA Super HSS HSS-EX UNC UNF USCTI 302A 2P~3P Steam Oxide TiCN R45

Unit : Inch

SIZE & TPI	Limit	Overall Length L	Thread Length Lt	Shank Diameter D	Square Size K	Square Length kl	No. of Flute	EDP No.	
								Steam Oxide	TiCN
9/16 - 18 UNF	H5	3.59	.512	.381	.322	.500	3	TCB625S	TCB625C
5/8 - 11UNC	H3	3.81	.748	.323	.360	.562	4	TCB643S	TCB643C
5/8 - 11 UNC	H5	3.81	.748	.323	.360	.562	4	TCB645S	TCB645C
5/8 - 18 UNF	H3	3.81	.512	.323	.360	.562	4	TCB663S	TCB663C
5/8 - 18 UNF	H5	3.81	.512	.323	.360	.562	4	TCB665S	TCB665C
3/4 - 10 UNC	H3	4.25	.827	.367	.442	.688	4	TCB703S	TCB703C
3/4 - 10 UNC	H5	4.25	.827	.367	.442	.688	4	TCB705S	TCB705C
3/4 - 16 UNF	H3	4.25	.591	.429	.442	.688	4	TCB723S	TCB723C
3/4 - 16 UNF	H5	4.25	.591	.429	.442	.688	4	TCB725S	TCB725C
7/8 - 9 UNC	H4	4.69	.827	.480	.523	.750	4	TCB744S	TCB744C
7/8 - 9 UNC	H6	4.69	.827	.480	.523	.750	4	TCB746S	TCB746C
7/8 - 14 UNF	H4	4.69	.709	.590	.523	.750	4	TCB764S	TCB764C
7/8 - 14 UNF	H6	4.69	.709	.590	.523	.750	4	TCB766S	TCB766C
1 - 8 UNC	H4	5.13	.984	.697	.600	.812	4	TCB784S	TCB784C
1 - 8 UNC	H6	5.13	.984	.697	.600	.812	4	TCB786S	TCB786C
1 - 12 UNF	H4	5.13	.709	.800	.600	.812	4	TCB804S	TCB804C
1 - 12 UNF	H6	5.13	.709	.800	.600	.812	4	TCB806S	TCB806C


Super HSS(#5~1/2) and HSS-EX(9/16~1")

◎ : Excellent ○ : Good

P				M				K	
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)		
○	○			◎					
K		N				S			
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium



SPIRAL FLUTE TAPS for Stainless Steels



VA Super HSS HSS-EX M/MF USCTI 302A 2P~3P Steam Oxide TiCN R45

Unit : Inch

SIZE & TPI	Limit	Overall Length L	Thread Length Lt	Shank Diameter D	Square Size K	Square Length kl	No. of Flute	EDP No.	
								Steam Oxide	TiCN
M3 x 0.5	D3	1.94	.197	.141	.110	.188	3	TCC203S	TCC203C
M3.5 x 0.6	D4	2.00	.276	.141	.110	.188	3	TCC224S	TCC224C
M4 x 0.7	D4	2.13	.276	.168	.131	.250	3	TCC244S	TCC244C
M5 x 0.8	D4	2.38	.354	.194	.152	.250	3	TCC284S	TCC284C
M6 x 1.0	D5	2.50	.433	.255	.191	.312	3	TCC315S	TCC315C
M7 x 1.0	D5	2.72	.433	.318	.238	.375	3	TCC345S	TCC345C
M8 x 1.25	D5	2.72	.472	.318	.238	.375	3	TCC365S	TCC365C
M8 x 1.0	D5	2.72	.433	.318	.238	.375	3	TCC375S	TCC375C
M10 x 1.5	D6	2.94	.512	.381	.286	.438	3	TCC426S	TCC426C
M10 x 1.25	D5	2.94	.472	.381	.286	.438	3	TCC435S	TCC435C
M12 x 1.75	D6	3.38	.591	.367	.275	.438	3	TCC506S	TCC506C
M12 x 1.25	D5	3.38	.551	.367	.275	.438	3	TCC525S	TCC525C
M14 x 2.0	D7	3.59	.709	.429	.322	.500	3	TCD547S	TCD547C
M14 x 1.5	D6	3.59	.551	.429	.322	.500	3	TCD556S	TCD556C
M16 x 2.0	D7	3.81	.709	.480	.360	.562	3	TCD607S	TCD607C
M16 x 1.5	D6	3.81	.551	.480	.360	.562	3	TCD616S	TCD616C
M18 x 2.5	D7	4.03	.787	.542	.406	.625	4	TCD657S	TCD657C
M18 x 1.5	D6	4.03	.551	.542	.406	.625	4	TCD676S	TCD676C

► Super HSS(M3~M12) and HSS-EX(M14~M18)



◎ : Excellent ○ : Good

P				M				K	
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)		
○	○			◎					
K		N				S			
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium



T4/T4-S/T4-C SERIES

SPIRAL POINT TAPS for Multi-Purpose



Thread Depth / Hole Type 3.0xD

- MU, HSS-EX, UNC UNF, USCTI 302A, 4P~5P, Bright, Steam Oxide, TiCN

Table with 12 columns: SIZE & TPI, Limit, Overall Length (L), Thread Length (Lt), Shank Diameter (D), Square Size (K), Square Length (kl), No. of Flute, EDP No. (Bright, Steam Oxide, TiCN). Rows include sizes #4 to #12 and 1/4 to 3/8 in various UNF and UNC threads.

Coating (TiN, TiAlN or Hardslick) is available on your request. Coating Codes for Combo Tap Bright Finish No. + N(TiN), F(TiAlN), H(Hardslick)


Steam Oxide is not recommended for Aluminum and Aluminum alloys.

Material compatibility table with columns P, M, K, N, S. Rows list materials like Low carbon steels, Stainless steel castings, Nodular cast iron, etc., with hardness ranges and compatibility symbols (O for Good, @ for Excellent).



T4/T4-S/T4-C SERIES

SPIRAL POINT TAPS for Multi-Purpose



Thread Depth / Hole Type 3.0xD

- MU, HSS-EX, UNC UNF, USCTI 302A, 4P~5P, Bright, Steam Oxide, TiCN

Table with 12 columns: SIZE & TPI, Limit, Overall Length (L), Thread Length (Lt), Shank Diameter (D), Square Size (K), Square Length (kl), No. of Flute, EDP No. (Bright, Steam Oxide, TiCN). Rows include sizes 3/8 to 1 in various UNF and UNC threads.

Coating (TiN, TiAlN or Hardslick) is available on your request. Coating Codes for Combo Tap Bright Finish No. + N(TiN), F(TiAlN), H(Hardslick)


Steam Oxide is not recommended for Aluminum and Aluminum alloys.

Material compatibility table with columns P, M, K, N, S. Rows list materials like Low carbon steels, Stainless steel castings, Nodular cast iron, etc., with hardness ranges and compatibility symbols (O for Good, @ for Excellent).



T3 / T3-S / T3-C SERIES

SPIRAL POINT TAPS for Multi-Purpose



Thread Depth / Hole Type 3.0xD

- MU, HSS-EX, M/MF, USCTI 302A, 4P~5P, Bright, Steam Oxide, TiCN

Table with columns: SIZE & TPI, Limit, Overall Length, Thread Length, Shank Diameter, Square Size, Square Length, No. of Flute, EDP No. (Bright, Steam Oxide, TiCN)

Coating(TiN, TiAlN or Hardslick) is available on your request. Coating Codes for Combo Tap Bright Finish No. + N(TiN), F(TiAlN), H(Hardslick)

Steam Oxide is not recommended for Aluminum and Aluminum alloys.

Material compatibility table with columns P, M, K, N, S and rows for various materials like Low carbon steels, Stainless steel castings, etc.




TB / TB-N SERIES

SPIRAL POINT TAPS for Multi-Purpose



with Internal Coolant



Thread Depth / Hole Type 3.0xD

- MU, HSS-EX, UNC UNF, USCTI 302A, 4P~5P, Bright, TiN

Table with columns: SIZE & TPI, Limit, Overall Length, Thread Length, Shank Diameter, Square Size, Square Length, No. of Flute, EDP No. (Bright, TiN)

Coating(TiCN, TiAlN or Hardslick) or Surface Treatment(Steam Oxide) is available on your request.



Material compatibility table with columns P, M, K, N, S and rows for various materials like Low carbon steels, Stainless steel castings, etc.



TH / TH-N SERIES

SPIRAL POINT TAPS for Multi-Purpose

with Internal Coolant



- MU
- HSS-EX
- M
- USCTI 302A
- 4P~5P
- Bright
- TiN

Unit : Inch

SIZE & TPI	Limit	Overall Length L	Thread Length Lt	Shank Diameter D	Square Size K	Square Length kl	No. of Flute	EDP No.	
								Bright	TiN
M6 x 1.0	D5	2.50	.591	.255	.191	.312	3	TH315	TH315N
M8 x 1.25	D5	2.72	.669	.318	.238	.375	3	TH365	TH365N
M10 x 1.5	D6	2.94	.748	.381	.286	.438	3	TH426	TH426N
M12 x 1.75	D6	3.38	.984	.367	.275	.438	3	TH506	TH506N
M14 x 2.0	D7	3.59	.984	.429	.322	.500	3	TH547	TH547N
M16 x 2.0	D7	3.81	1.083	.480	.360	.562	3	TH607	TH607N
M18 x 2.5	D7	4.03	1.083	.542	.406	.625	3	TH657	TH657N
M20 x 2.5	D7	4.47	1.201	.652	.489	.688	3	TH707	TH707N

► Coating(TiCN, TiAlN or Hardslick) or Surface Treatment(Steam Oxide) is available on your request.
Coating Codes for Combo Tap
Bright Finish No. + C(TiCN), F(TiAlN), H(Hardslick), S(Steam Oxide)

◎ : Excellent ○ : Good



P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎	◎	◎	◎	◎	◎	◎			
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
◎	◎	◎	◎	◎	◎	◎	◎			



TC-S / TC-C SERIES

SPIRAL POINT TAPS for Multi-Purpose

DIN Length-ANSI Shank



- MU
- HSS-EX
- UNC UNF
- 4P~5P
- Steam Oxide
- TiCN

Unit : Inch

SIZE & TPI	Limit	Overall Length L	Thread Length Lt	Shank Diameter D	Square Size K	Square Length kl	No. of Flute	EDP No.	
								Steam Oxide	TiCN
#4 - 40 UNC	H2	2.21	.335	.141	.110	.188	2	TC162S	TC162C
#5 - 40 UNC	H2	2.21	.374	.141	.110	.188	3	TC202S	TC202C
#6 - 32 UNC	H3	2.21	.413	.141	.110	.188	3	TC243S	TC243C
#8 - 32 UNC	H3	2.48	.453	.168	.131	.250	3	TC283S	TC283C
#10 - 24 UNC	H3	2.76	.531	.194	.152	.250	3	TC323S	TC323C
#10 - 32 UNF	H3	2.76	.531	.194	.152	.250	3	TC343S	TC343C
#12 - 24 UNC	H3	3.15	.571	.220	.165	.281	3	TC363S	TC363C
#12 - 28 UNF	H3	3.15	.571	.220	.165	.281	3	TC383S	TC383C
1/4 - 20 UNC	H5	3.15	.591	.255	.191	.312	3	TC405S	TC405C
1/4 - 28 UNF	H4	3.15	.591	.255	.191	.312	3	TC424S	TC424C
5/16 - 18 UNC	H5	3.54	.669	.318	.238	.375	3	TC445S	TC445C
5/16 - 24 UNF	H4	3.54	.669	.318	.238	.375	3	TC464S	TC464C
3/8 - 16 UNC	H5	3.94	.748	.381	.286	.438	3	TC485S	TC485C
3/8 - 24 UNF	H4	3.94	.748	.381	.286	.438	3	TC504S	TC504C
7/16 - 14 UNC	H5	3.94	.866	.323	.242	.406	3	TC525S	TC525C
7/16 - 20 UNF	H5	3.94	.866	.323	.242	.406	3	TC545S	TC545C
1/2 - 13 UNC	H5	4.33	.984	.367	.275	.438	3	TC565S	TC565C
1/2 - 20 UNF	H5	3.94	.984	.367	.275	.438	3	TC585S	TC585C
9/16 - 12 UNC	H5	4.33	.984	.429	.322	.500	3	TC605S	TC605C
9/16 - 18 UNF	H5	3.94	.984	.429	.322	.500	3	TC625S	TC625C
5/8 - 11 UNC	H5	4.33	1.083	.480	.360	.562	3	TC645S	TC645C
5/8 - 18 UNF	H5	3.94	1.083	.480	.360	.562	3	TC665S	TC665C
3/4 - 10 UNC	H5	4.92	1.201	.590	.442	.688	3	TC705S	TC705C
3/4 - 16 UNF	H5	4.33	1.201	.590	.442	.688	3	TC725S	TC725C
7/8 - 9 UNC	H6	5.51	1.339	.697	.523	.750	3	TC746S	TC746C
7/8 - 14 UNF	H6	4.92	1.339	.697	.523	.750	3	TC766S	TC766C
1 - 8 UNC	H6	6.30	1.496	.800	.600	.812	3	TC786S	TC786C
1 - 12 UNF	H6	5.51	1.496	.800	.600	.812	3	TC806S	TC806C

► Steam Oxide is not recommended for Aluminum and Aluminum alloys.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎	◎	◎	◎	◎	◎	◎			
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
◎	◎	◎	◎	◎	◎	◎	◎			



TK-S / TK-C SERIES

SPIRAL POINT TAPS for Multi-Purpose

DIN Length-ANSI Shank



Thread Depth / Hole Type 3.0xD

- MU, HSS-EX, M/MF, 4P~5P, Steam Oxide, TiCN

Table with 10 columns: SIZE & TPI, Limit, Overall Length, Thread Length, Shank Diameter, Square Size, Square Length, No. of Flute, EDP No. (Steam Oxide, TiCN). Rows include sizes M3 to M18.


► Steam Oxide is not recommended for Aluminum and Aluminum alloys.

Material compatibility chart with columns P, M, K, N, S and rows for various materials like Low carbon steels, Stainless steel castings, etc.



TCE-S / TCF-S / TCE-C / TCF-C SERIES

SPIRAL POINT TAPS for Stainless Steels



Thread Depth / Hole Type 3.0xD

- VA, Super HSS, HSS-EX, UNC UNF, USCTI 302A, 4P, Steam Oxide, TiCN

Table with 10 columns: SIZE & TPI, Limit, Overall Length, Thread Length, Shank Diameter, Square Size, Square Length, No. of Flute, EDP No. (Steam Oxide, TiCN). Rows include sizes #5 to 1/2.


► Super HSS(#5~1/2) and HSS-EX(9/16~1")

► NEXT PAGE

Material compatibility chart with columns P, M, K, N, S and rows for various materials like Low carbon steels, Stainless steel castings, etc.



SPIRAL POINT TAPS for Stainless Steels



Thread Depth / Hole Type
3.0×D

- VA
- Super HSS
- HSS-EX
- UNC UNF
- USCTI 302A
- 4P
- Steam Oxide
- TiCN

Unit : Inch

SIZE & TPI	Limit	Overall Length L	Thread Length Lt	Shank Diameter D	Square Size K	Square Length kl	No. of Flute	EDP No.	
								Steam Oxide	TiCN
9/16 - 12 UNC	H3	3.59	.984	.429	.322	.500	3	TCF603S	TCF603C
9/16 - 18 UNF	H3	3.59	.984	.429	.322	.500	3	TCF623S	TCF623C
5/8 - 11 UNC	H3	3.81	1.083	.480	.360	.562	3	TCF643S	TCF643C
5/8 - 11 UNC	H5	3.81	1.083	.480	.360	.562	3	TCF645S	TCF645C
5/8 - 18 UNF	H5	3.81	1.083	.480	.360	.562	3	TCF665S	TCF665C
3/4 - 10 UNC	H3	4.25	1.201	.590	.442	.688	3	TCF703S	TCF703C
3/4 - 10 UNC	H5	4.25	1.201	.590	.442	.688	3	TCF705S	TCF705C
7/8 - 9 UNC	H4	4.69	1.339	.697	.523	.750	3	TCF744S	TCF744C
7/8 - 9 UNC	H6	4.69	1.339	.697	.523	.750	3	TCF746S	TCF746C
7/8 - 14 UNF	H6	4.69	1.339	.697	.523	.750	3	TCF766S	TCF766C
1 - 8 UNC	H4	5.13	1.496	.800	.600	.812	3	TCF784S	TCF784C
1 - 8 UNC	H6	5.13	1.496	.800	.600	.812	3	TCF786S	TCF786C
1 - 12 UNF	H6	5.13	1.496	.800	.600	.812	3	TCF806S	TCF806C


▶ Super HSS(#5~1/2) and HSS-EX(9/16~1")

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)		~HRc19 (~HB220)		
○	○			◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										



SPIRAL POINT TAPS for Stainless Steels



Thread Depth / Hole Type
3.0×D

- VA
- Super HSS
- HSS-EX
- M/MF
- USCTI 302A
- 4P
- Steam Oxide
- TiCN

Unit : Inch

SIZE & TPI	Limit	Overall Length L	Thread Length Lt	Shank Diameter D	Square Size K	Square Length kl	No. of Flute	EDP No.	
								Steam Oxide	TiCN
M3 x 0.5	D3	1.94	.374	.141	.110	.188	3	TCG203S	TCG203C
M3.5x 0.6	D4	2.00	.413	.141	.110	.188	3	TCG224S	TCG224C
M4 x 0.7	D4	2.13	.453	.168	.131	.250	3	TCG244S	TCG244C
M5 x 0.8	D4	2.38	.531	.194	.152	.250	3	TCG284S	TCG284C
M6 x 1.0	D5	2.50	.591	.255	.191	.312	3	TCG315S	TCG315C
M7 x 1.0	D5	2.72	.669	.318	.238	.375	3	TCG345S	TCG345C
M8 x 1.25	D5	2.72	.669	.318	.238	.375	3	TCG365S	TCG365C
M8 x 1.0	D5	2.72	.669	.318	.238	.375	3	TCG375S	TCG375C
M10 x 1.5	D6	2.94	.748	.381	.286	.438	3	TCG426S	TCG426C
M10 x 1.25	D5	2.94	.748	.381	.286	.438	3	TCG435S	TCG435C
M12 x 1.75	D6	3.38	.984	.367	.275	.438	3	TCG506S	TCG506C
M12 x 1.25	D5	3.38	.984	.367	.275	.438	3	TCG525S	TCG525C
M14 x 2.0	D7	3.59	.984	.429	.322	.500	3	TCH547S	TCH547C
M14 x 1.5	D6	3.59	.984	.429	.322	.500	3	TCH556S	TCH556C
M16 x 2.0	D7	3.81	1.083	.480	.360	.562	3	TCH607S	TCH607C
M16 x 1.5	D6	3.81	1.083	.480	.360	.562	3	TCH616S	TCH616C
M18 x 2.5	D7	4.03	1.083	.542	.406	.625	3	TCH657S	TCH657C
M18 x 1.5	D6	4.03	1.083	.542	.406	.625	3	TCH676S	TCH676C

▶ Super HSS(M3~M12) and HSS-EX(M14~M18)

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)		~HRc19 (~HB220)		
○	○			◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										

HSS

CARBIDE

YIG COMBO TAPS

Combo TAP

SPIRAL FLUTE COMBO TAP SETS

THREAD MILLS

COMBO TAPS

SPIRAL FLUTE TAPS

SPIRAL POINT TAPS

STRAIGHT FLUTE TAPS

FORMING TAPS

SCREW THREAD INSERT TAPS

PIPE TAPS

TECHNICAL DATA



TAP SETS SPIRAL FLUTE COMBO

Series	Series	Standard	Surface Treatment	Size	Q'ty
T2836SET8	T2	UNC/F	Bright	1/4-20, 1/4-28, 5/16-18, 5-16-24, 3/8-16, 3/8-24, 7/16-14, 7/16-20	8 pcs
TG836SET8	T2-C	UNC/F	TiCN	1/4-20, 1/4-28, 5/16-18, 5-16-24, 3/8-16, 3/8-24, 7/16-14, 7/16-20	8 pcs
T2836SET8 -1	T2	UNC/F	Bright	1/4-20, 1/4-28, 5/16-18, 5-16-24, 3/8-16, 3/8-24, 1/2-13, 1/2-20	8 pcs
TG836SET8 -1	T2-C	UNC/F	TiCN	1/4-20, 1/4-28, 5/16-18, 5-16-24, 3/8-16, 3/8-24, 1/2-13, 1/2-20	8 pcs
T2805SET7	T5	M/MF	Bright	M3, M4, M5, M6, M8, M10, M12	7 pcs
TG805SET7	T5-C	M/MF	TiCN	M3, M4, M5, M6, M8, M10, M12	7 pcs

*Hardslick Coated Set available upon request



Being the best through innovation

HSS



SPIRAL FLUTE TAPS













- Tapping Blind Holes / Super HSS, P-HSS, HSSE-V3, HSS-V & HSS








SELECTION GUIDE

SPIRAL FLUTE TAPS

Tapping Blind Holes / Super HSS, P-HSS, HSSE-V3, HSS-V & HSS

INCH/METRIC


EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page
BB/BI		Super HSS	UNC/UNF	VG	USCTI 302A	H	2 ~ 3P	2.5D	Steam Oxide Hardslick	392
BH/BM		Super HSS	M/MF	VG	USCTI 302A	D	2 ~ 3P		Steam Oxide Hardslick	394
BF/BK		Super HSS	UNC/UNF	VG	DIN Length-ANSI Shank	H	2 ~ 3P		Steam Oxide Hardslick	395
BD/BO		Super HSS	M/MF	VG	DIN Length-ANSI Shank	D	2 ~ 3P		Steam Oxide Hardslick	396
H6/H7/H8		P-HSS	UNC/UNF	HR	USCTI 302A	H	2 ~ 3P		Bright TiCN Hardslick	397
TQ858/TK858/TR858		P-HSS	M/MF	HR	USCTI 302A	H	2 ~ 3P		Steam Oxide TiCN Hardslick	398
B3/B5/D6		P-HSS	UNC/UNF	Ti Ni	USCTI 302A	H	2 ~ 3P		Steam Oxide TiCN Hardslick	399
G7/G8/G9/H0		P-HSS	UNC/UNF	VA	USCTI Long Shank	H	2 ~ 3P		TiN Hardslick	401
H2/H4		P-HSS	UNC/UNF	VA	USCTI Long Shank (Left hand Spiral, Right hand Cut)	H	4 ~ 5P		3.0D TiN Hardslick	402
BG/BG-GB		HSSE-V3	UNC/UN8	VG	DIN Length-ANSI Shank	2B	2 ~ 3P		Hardslick Gold & Black	403
B1/B0/B2/D2		HSSE-V3	UNC/UNF	VA	USCTI 302A	H	2 ~ 3P	Bright Steam Oxide TiN/Hardslick	404	
BS/BT		HSSE-V3	M/MF	VA	USCTI 302A	D	2 ~ 3P	Steam Oxide Hardslick	407	
E6/E8/E9		HSSE-V3	M/MF	VA	DIN Length-ANSI Shank	D	2 ~ 3P	Steam Oxide TiCN Hardslick	408	
D3/E0		HSSE-V3	UNC/UNF	VG	USCTI 302A	H	2 ~ 3P	2.5D Hardslick Steam Oxide	409	
BU/BV		HSSE-V3	M/MF	VG	USCTI 302A	D	2 ~ 3P	Steam Oxide Hardslick	412	
E2/E4/E5		HSSE-V3	M/MF	VG	DIN Length-ANSI Shank	D	2 ~ 3P	Steam Oxide TiCN Hardslick	414	
C0/D8		HSSE-V3	UNC/UNF	AI	USCTI 302A	H	2 ~ 3P	Bright Hardslick	415	
BW/BX		HSSE-V3	M/MF	AI	USCTI 302A	D	2 ~ 3P	Bright Hardslick	416	

EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page
C2/C3/C4/D9		HSSE-V3	UNC/UNF	GS	USCTI 302	H	1.5 ~ 2P	2.5D	Steam Oxide Bright/TiN Hardslick	417
F4/F8/F6		HSS-V	UNC/UNF	GS	USCTI 302A	H	1.5 ~ 2P		Steam Oxide TiN Hardslick	418
G4/G5/G6		HSS-V	M/MF	GS	USCTI 302A	D	1.5 ~ 2P		Bright TiCN Hardslick	420
G0/G1/G2		HSS-V	UNC/UNF	GS	DIN Length-ANSI Shank	H	2 ~ 3P		Bright TiN Hardslick	421
T7A96/T6A96/T8A96 T7295/T6295/T8295		HSS	UNC/UNF	GS	USCTI 302	H	4 ~ 5P 1.5 ~ 2P		Bright Steam Oxide TiN	423
T7A86/T6A86/T8A86 T7A85/T6A85/T8A85		HSS	M/MF	GS	USCTI 302	D	4 ~ 5P 1.5 ~ 2P		Bright Steam Oxide TiN	424
T7D01/T8D01 T7D02/T8D02		HSS	UNC/UNF	GS	USCTI Long Shank	H	4 ~ 5P 1.5 ~ 2P		Bright TiN	425

YG SPIRAL FLUTE TAPS

BB/BI SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Steels & Stainless Steels



YG
Super HSS
UNC UNF
USCTI 302A
2P~3P
Steam Oxide
Hardslick
R40

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.	
	UNC	UNF			Steam Oxide	Hardslick
#2	56	—	H2	2	BB082	BI082
#4	40	—	H2	2	BB162	BI162
#4	40	—	H3	2	BB163	BI163
#4	40	—	H4	2	BB164	BI164
#5	40	—	H2	3	BB202	BI202
#6	32	—	H2	3	BB242	BI242
#6	32	—	H3	3	BB243	BI243
#6	32	—	H4	3	BB244	BI244
#6	32	—	H5	3	BB245	BI245
#8	32	—	H2	3	BB282	BI282
#8	32	—	H3	3	BB283	BI283
#8	32	—	H4	3	BB284	BI284
#8	32	—	H5	3	BB285	BI285
#8	32	—	H6	3	BB286	BI286
#10	24	—	H3	3	BB323	BI323
#10	24	—	H5	3	BB325	BI325
#10	—	32	H2	3	BB342	BI342
#10	—	32	H3	3	BB343	BI343
#10	—	32	H4	3	BB344	BI344
#10	—	32	H5	3	BB345	BI345
#10	—	32	H6	3	BB346	BI346
1/4	20	—	H3	3	BB403	BI403
1/4	20	—	H5	3	BB405	BI405
1/4	—	28	H3	3	BB423	BI423
1/4	—	28	H4	3	BB424	BI424
1/4	—	28	H5	3	BB425	BI425
1/4	—	28	H6	3	BB426	BI426
5/16	18	—	H3	3	BB443	BI443
5/16	18	—	H5	3	BB445	BI445
5/16	—	24	H3	3	BB463	BI463
5/16	—	24	H4	3	BB464	BI464
5/16	—	24	H5	3	BB465	BI465
5/16	—	24	H6	3	BB466	BI466

▶ Refer to technical data on page 520~554.

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎	◎		◎	◎					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL FLUTE TAPS

BB/BI SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Steels & Stainless Steels



YG
Super HSS
UNC UNF
USCTI 302A
2P~3P
Steam Oxide
Hardslick
R40

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.	
	UNC	UNF			Steam Oxide	Hardslick
3/8	16	—	H3	3	BB483	BI483
3/8	16	—	H5	3	BB485	BI485
3/8	—	24	H3	3	BB503	BI503
3/8	—	24	H4	3	BB504	BI504
3/8	—	24	H5	3	BB505	BI505
3/8	—	24	H6	3	BB506	BI506
7/16	14	—	H3	3	BB523	BI523
7/16	14	—	H5	3	BB525	BI525
7/16	—	20	H3	3	BB543	BI543
7/16	—	20	H5	3	BB545	BI545
1/2	13	—	H3	3	BB563	BI563
1/2	13	—	H5	3	BB565	BI565
1/2	—	20	H3	3	BB583	BI583
1/2	—	20	H5	3	BB585	BI585
9/16	12	—	H5	3	BB605	BI605
9/16	—	18	H5	3	BB625	BI625
5/8	11	—	H3	4	BB643	BI643
5/8	11	—	H5	4	BB645	BI645
5/8	—	18	H3	4	BB663	BI663
5/8	—	18	H5	4	BB665	BI665
3/4	10	—	H3	4	BB703	BI703
3/4	10	—	H5	4	BB705	BI705
3/4	—	16	H3	4	BB723	BI723
3/4	—	16	H5	4	BB725	BI725
7/8	9	—	H6	4	BB746	BI746
7/8	—	14	H6	4	BB766	BI766
1	8	—	H6	4	BB786	BI786
1	—	12	H6	4	BB806	BI806
1-1/8	8	—	H6	4	BB836	BI836
1-1/4	8	—	H6	4	BB876	BI876
1-3/8	8	—	H6	4	BB916	BI916
1-1/2	8	—	H6	4	BB956	BI956

▶ Refer to technical data on page 520~554.


◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎	◎		◎	◎					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL FLUTE TAPS

BH / BM SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Steels & Stainless Steels



VG Super HSS M MF USCTI 302A 2P~3P Steam Oxide Hardslick R40

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Steam Oxide	Hardslick
M3	0.5	D3	3	BH203	BM203
M3.5	0.6	D4	3	BH224	BM224
M4	0.7	D4	3	BH244	BM244
M5	0.8	D4	3	BH284	BM284
M6	1.0	D5	3	BH315	BM315
M7	1.0	D5	3	BH345	BM345
M8	1.25	D5	3	BH365	BM365
M8	1.0	D5	3	BH375	BM375
M10	1.5	D6	3	BH426	BM426
M10	1.25	D5	3	BH435	BM435
M12	1.75	D6	3	BH506	BM506
M12	1.25	D5	3	BH525	BM525
M14	2.0	D7	3	BH547	BM547
M14	1.5	D6	3	BH556	BM556
M16	2.0	D7	3	BH607	BM607
M16	1.5	D6	3	BH616	BM616
M18	2.5	D7	4	BH657	BM657
M18	1.5	D6	4	BH676	BM676

Refer to technical data on page 520~554.


◎ : Excellent ○ : Good

P			M				K		
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)		
○	◎	◎	◎	◎	◎				
K	N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
	○	○		○		○	○		

YG SPIRAL FLUTE TAPS

BF / BK SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Steels & Stainless Steels



VG Super HSS UNC UNF 2P~3P Steam Oxide Hardslick R40

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.	
	UNC	UNF			Steam Oxide	Hardslick
#2	56	—	H2	2	BF082	BK082
#4	40	—	H2	2	BF162	BK162
#5	40	—	H2	3	BF202	BK202
#6	32	—	H3	3	BF243	BK243
#8	32	—	H3	3	BF283	BK283
#10	24	—	H3	3	BF323	BK323
#10	—	32	H3	3	BF343	BK343
1/4	20	—	H3	3	BF403	BK403
1/4	20	—	H5	3	BF405	BK405
1/4	—	28	H3	3	BF423	BK423
1/4	—	28	H4	3	BF424	BK424
5/16	18	—	H5	3	BF445	BK445
5/16	—	24	H4	3	BF464	BK464
3/8	16	—	H5	3	BF485	BK485
3/8	—	24	H4	3	BF504	BK504
7/16	14	—	H5	3	BF525	BK525
7/16	—	20	H5	3	BF545	BK545
1/2	13	—	H5	3	BF565	BK565
1/2	—	20	H5	3	BF585	BK585
9/16	12	—	H5	3	BF605	BK605
9/16	—	18	H5	3	BF625	BK625
5/8	11	—	H5	4	BF645	BK645
5/8	—	18	H5	4	BF665	BK665
3/4	10	—	H5	4	BF705	BK705
3/4	—	16	H5	4	BF725	BK725
7/8	9	—	H6	4	BF746	BK746
7/8	—	14	H6	4	BF766	BK766
1	8	—	H6	4	BF786	BK786
1	—	12	H6	4	BF806	BK806
1-1/8	8	—	H6	4	BF836	BK836
1-1/4	8	—	H6	4	BF876	BK876
1-3/8	8	—	H6	4	BF916	BK916
1-1/2	8	—	H6	4	BF956	BK956

Refer to technical data on page 520~554.



◎ : Excellent ○ : Good

P			M				K		
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)		
○	◎	◎	◎	◎	◎				
K	N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
	○	○		○		○	○		

YG SPIRAL FLUTE TAPS

BD / BO SERIES

METRIC SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Steels & Stainless Steels



- VG Super HSS M MF 2P~3P Steam Oxide Hardslick R40

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Steam Oxide	Hardslick
M3	0.5	D3	3	BD203	BO203
M3.5	0.6	D4	3	BD224	BO224
M4	0.7	D4	3	BD244	BO244
M5	0.8	D4	3	BD284	BO284
M6	1.0	D5	3	BD315	BO315
M7	1.0	D5	3	BD345	BO345
M8	1.25	D5	3	BD365	BO365
M8	1.0	D5	3	BD375	BO375
M10	1.5	D6	3	BD426	BO426
M10	1.25	D5	3	BD435	BO435
M12	1.75	D6	3	BD506	BO506
M12	1.25	D5	3	BD525	BO525
M14	2.0	D7	3	BD547	BO547
M14	1.5	D6	3	BD556	BO556
M16	2.0	D7	3	BD607	BO607
M16	1.5	D6	3	BD616	BO616
M18	2.5	D7	4	BD657	BO657
M18	1.5	D6	4	BD676	BO676

Refer to technical data on page 520~554.



◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)		~HRc19 (~HB220)		
○	◎	◎		◎	◎					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL FLUTE TAPS

H6 / H7 / H8 SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Steels up to 25 ~ 45HRc



- HR P-HSS UNC UNF USCTI 302A 2P~3P Bright TiCN Hardslick R15

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Bright	TiCN	Hardslick
#2	56	—	H2	3	H6082	H7082	H8082
#4	40	—	H2	3	H6162	H7162	H8162
#5	40	—	H2	3	H6202	H7202	H8202
#6	32	—	H3	3	H6243	H7243	H8243
#8	32	—	H3	3	H6283	H7283	H8283
#10	24	—	H3	3	H6323	H7323	H8323
#10	—	32	H3	3	H6343	H7343	H8343
1/4	20	—	H5	3	H6405	H7405	H8405
1/4	—	28	H4	3	H6424	H7424	H8424
5/16	18	—	H5	3	H6445	H7445	H8445
5/16	—	24	H4	3	H6464	H7464	H8464
3/8	16	—	H5	3	H6485	H7485	H8485
3/8	—	24	H4	3	H6504	H7504	H8504
7/16	14	—	H5	3	H6525	H7525	H8525
7/16	—	20	H5	3	H6545	H7545	H8545
1/2	13	—	H5	3	H6565	H7565	H8565
1/2	—	20	H5	3	H6585	H7585	H8585
5/8	11	—	H5	4	H6645	H7645	H8645
5/8	—	18	H5	4	H6665	H7665	H8665
3/4	10	—	H5	4	H6705	H7705	H8705
3/4	—	16	H5	4	H6725	H7725	H8725

Refer to technical data on page 520~554.




◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)		~HRc19 (~HB220)		
		○	◎		○	◎				
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
			◎					○	○	○

YG SPIRAL FLUTE TAPS

TQ858 / TK858 / TR858 SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Steels up to 25 ~ 45HRc



- HR
- P-HSS
- M MF
- USCTI 302A
- 2P~3P
- Steam Oxide
- TiCN
- Hardslick
- R15

SIZE	Pitch	Limit	No. of Flute	EDP No.		
				Steam Oxide	TiCN	Hardslick
M3	0.50	D3	3	TQ858203	TK858203	TR858203HAR
M4	0.50	D3	3	TQ858253	TK858253	TR858253HAR
M4	0.70	D4	3	TQ858244	TK858244	TR858244HAR
M5	0.50	D3	3	TQ858293	TK858293	TR858293HAR
M5	0.80	D4	3	TQ858284	TK858284	TR858284HAR
M6	0.50	D3	3	TQ858333	TK858333	TR858333HAR
M6	0.75	D4	3	TQ858324	TK858324	TR858324HAR
M6	1.00	D5	3	TQ858315	TK858315	TR858315HAR
M8	1.00	D5	3	TQ858375	TK858375	TR858375HAR
M8	1.25	D5	3	TQ858365	TK858365	TR858365HAR
M10	1.00	D5	3	TQ858445	TK858445	TR858445HAR
M10	1.25	D5	3	TQ858435	TK858435	TR858435HAR
M10	1.50	D6	3	TQ858426	TK858426	TR858426HAR
M12	1.00	D5	3	TQ858535	TK858535	TR858535HAR
M12	1.25	D6	3	TQ858526	TK858526	TR858526HAR
M12	1.50	D6	3	TQ858516	TK858516	TR858516HAR
M12	1.75	D6	3	TQ858506	TK858506	TR858506HAR
M14	1.50	D6	3	TQ858556	TK858556	TR858556HAR
M14	2.00	D7	3	TQ858547	TK858547	TR858547HAR
M16	1.5	D6	4	TQ858616	TK858616	TR858616HAR
M16	2.0	D7	4	TQ858607	TK858607	TR858607HAR
M18	1.5	D6	4	TQ858676	TK858676	TR858676HAR
M18	2.5	D7	4	TQ858657	TK858657	TR858657HAR
M20	1.5	D6	4	TQ858726	TK858726	TR858726HAR
M20	2.5	D7	4	TQ858707	TK858707	TR858707HAR
M22	1.5	D6	4	TQ858766	TK858766	TR858766HAR
M22	2.5	D7	4	TQ858747	TK858747	TR858747HAR
M24	1.5	D6	4	TQ858806	TK858806	TR858806HAR
M24	3.0	D8	4	TQ858788	TK858788	TR858788HAR



Refer to technical data on page 520~554.

P				M				K		
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)			
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium

YG SPIRAL FLUTE TAPS

B3/B5/D6 SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Titanium Alloys & Nickel Base Alloys up to 38 ~ 45HRc



- Ti Ni
- P-HSS
- UNC UNF
- USCTI 302A
- 2P~3P
- Steam Oxide
- TiCN
- Hardslick
- R15

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Steam Oxide	TiCN	Hardslick
#2	56	—	H2	3	B3082	B5082	D6082
#4	40	—	H2	3	B3162	B5162	D6162
#5	40	—	H2	3	B3202	B5202	D6202
#6	32	—	H3	3	B3243	B5243	D6243
#8	32	—	H3	3	B3283	B5283	D6283
#10	24	—	H3	3	B3323	B5323	D6323
#10	—	32	H3	3	B3343	B5343	D6343
1/4	20	—	H3	3	B3403	B5403	D6403
1/4	20	—	H5	3	B3405	B5405	D6405
1/4	—	28	H3	3	B3423	B5423	D6423
1/4	—	28	H4	3	B3424	B5424	D6424
5/16	18	—	H3	3	B3443	B5443	D6443
5/16	18	—	H5	3	B3445	B5445	D6445
5/16	—	24	H3	3	B3463	B5463	D6463
3/8	16	—	H3	3	B3483	B5483	D6483
3/8	16	—	H5	3	B3485	B5485	D6485
3/8	—	24	H3	3	B3503	B5503	D6503
3/8	—	24	H4	3	B3504	B5504	D6504
7/16	14	—	H3	3	B3523	B5523	D6523
7/16	14	—	H5	3	B3525	B5525	D6525
7/16	—	20	H3	3	B3543	B5543	D6543
7/16	—	20	H5	3	B3545	B5545	D6545
1/2	13	—	H3	3	B3563	B5563	D6563
1/2	13	—	H5	3	B3565	B5565	D6565
1/2	—	20	H3	3	B3583	B5583	D6583
1/2	—	20	H5	3	B3585	B5585	D6585

TiN Coated Available: H9 Series
Refer to technical data on page 520~554.

NEXT PAGE

P				M				K		
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)			
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium

YG SPIRAL FLUTE TAPS

B3/B5/D6 SERIES

SPIRAL FLUTE TAPS MODIFIED STYLE for Titanium Alloys & Nickel Base Alloys up to 38 ~ 45HRc



Ti Ni
P-HSS
UNC UNF
USCTI 302A
2P~3P
Steam Oxide
TiCN
Hardslick
R15

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Steam Oxide	TiCN	Hardslick
9/16	12	—	H3	3	B3603	B5603	D6603
9/16	12	—	H5	3	B3605	B5605	D6605
9/16	—	18	H3	3	B3623	B5623	D6623
9/16	—	18	H5	3	B3625	B5625	D6625
5/8	11	—	H3	4	B3643	B5643	D6643
5/8	11	—	H5	4	B3645	B5645	D6645
5/8	—	18	H3	4	B3663	B5663	D6663
5/8	—	18	H5	4	B3665	B5665	D6665
3/4	10	—	H3	4	B3703	B5703	D6703
3/4	10	—	H5	4	B3705	B5705	D6705
3/4	—	16	H3	4	B3723	B5723	D6723
3/4	—	16	H5	4	B3725	B5725	D6725

▶ TiN Coated Available: H9 Series
▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)	Grey cast iron		
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium

YG SPIRAL FLUTE TAPS

G7/G8/G9/H0 SERIES

EXTENDED LENGTH SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Stainless Steels

Extended length for greater reach



VA
P-HSS
UNC UNF
USCTI Long Shank
2P~3P
TiN
Hardslick
R45

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.			
	UNC	UNF			TiN 4" OAL	TiN 6" OAL	Hardslick 4" OAL	Hardslick 6" OAL
#4	40	—	H2	3	G7162	—	G9162	—
#6	32	—	H3	3	G7243	G8243	G9243	H0243
#8	32	—	H3	3	G7283	G8283	G9283	H0283
#10	24	—	H3	3	G7323	G8323	G9323	H0323
#10	—	32	H3	3	G7343	G8343	G9343	H0343
1/4	20	—	H3	3	G7403	G8403	G9403	H0403
1/4	—	28	H3	3	—	G8423	—	H0423
5/16	18	—	H3	3	—	G8443	—	H0443
5/16	—	24	H3	3	—	G8463	—	H0463
3/8	16	—	H3	3	—	G8483	—	H0483
3/8	—	24	H3	3	—	G8503	—	H0503
7/16	14	—	H3	3	—	G8523	—	H0523
7/16	—	20	H3	3	—	G8543	—	H0543
1/2	13	—	H3	3	—	G8563	—	H0563
1/2	—	20	H3	3	—	G8583	—	H0583
5/8	11	—	H3	4	—	G8643	—	H0643

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good



P				M				K		
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)	Grey cast iron		
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium

YG SPIRAL FLUTE TAPS

H2/H4 SERIES

EXTENDED LENGTH SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE LEFT HAND SPIRAL FLUTE, RIGHT HAND CUT

Left hand spiral, right hand cut. Reduces chip packing in deep holes Maximum. Tapping Depth is 50% Deeper than Standard USCTI Taps.



- VA
- P-HSS
- UNC UNF
- USCTI Long Shank
- 4P~5P
- TIN
- Hardslick
- L15

SIZE	Thread Per Inch		Limit	Overall	No. of Flute	EDP No.	
	UNC	UNF				TiN	Hardslick
1/4	20	—	H3	6	2	H2403	H4403
1/4	—	28	H3	6	3	H2423	H4423
5/16	18	—	H3	6	3	H2443	H4443
3/8	16	—	H3	6	3	H2483	H4483
7/16	14	—	H3	6	3	H2523	H4523
1/2	13	—	H3	6	3	H2563	H4563
5/8	11	—	H3	6	3	H2643	H4643



Refer to technical data on page 520~554.

YG SPIRAL FLUTE TAPS

BG/BG-GB SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Stainless Steels

Oil Field



- VG
- HSSE-V3
- UNC UN8
- 2P~3P
- Hardslick
- Gold&Black
- R40

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.	
	UNC	UN			Hardslick	Gold-Black
1/2	13	—	2B	3	BG562H	BG562GB
5/8	11	—	2B	3	BG642H	BG642GB
3/4	10	—	2B	3	BG702H	BG702GB
7/8	9	—	2B	4	BG742H	BG742GB
1	—	8	2B	4	BG782H	BG782GB
1-1/8	7	—	2B	4	BG822H	BG822GB
1-1/8	—	8	2B	4	BG832H	BG832GB
1-1/4	7	—	2B	4	BG862H	BG862GB
1-1/4	—	8	2B	4	BG872H	BG872GB
1-3/8	—	8	2B	5	BG912H	BG912GB
1-1/2	—	8	2B	5	BG952H	BG952GB
1-5/8	—	8	2B	5	BGB22H	BGB22GB
1-3/4	—	8	2B	6	BGC02H	BGC02GB
1-7/8	—	8	2B	6	BGC62H	BGC62GB
2	—	8	2B	6	BGD42H	BGD42GB

Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels / Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) / ~HRc38 (~HB350)	Alloyed tool steels / Mold steels ~HRc38 (~HB350) / ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) / ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)	Grey cast iron		
○	◎			◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
	○	○		○		○	○			

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels / Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) / ~HRc38 (~HB350)	Alloyed tool steels / Mold steels ~HRc38 (~HB350) / ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) / ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)	Grey cast iron		
	○	◎		◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
					◎					

YG SPIRAL FLUTE TAPS

B1/B0/B2/D2 SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Stainless Steels



VA HSSE-V3 UNC UNF USCTI 302A 2P~3P Bright Steam Oxide TIN Hardslick R45

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.			
	UNC	UNF			Bright	Steam Oxide	TiN	Hardslick
#2	56	—	H2	2	B1082	B0082	B2082	D2082
#3	48	—	H2	2	—	B0122	—	D2122
#4	40	—	H2	2	B1162	B0162	B2162	D2162
#4	40	—	H3	2	—	B0163	—	D2163
#4	40	—	H4	2	—	B0164	—	D2164
#4	40	—	H5	2	B1165	B0165	—	D2165
#4	40	—	H6	2	B1166	B0166	—	D2166
#4	—	48	H2	2	—	B0182	—	D2182
#5	40	—	H2	3	B1202	B0202	B2202	D2202
#6	32	—	H2	3	—	B0242	—	D2242
#6	32	—	H3	3	B1243	B0243	B2243	D2243
#6	32	—	H4	3	—	B0244	—	D2244
#6	32	—	H5	3	—	B0245	—	D2245
#6	32	—	H7	3	—	B0247	—	D2247
#6	—	40	H2	3	—	B0262	—	D2262
#6	—	40	H3	3	—	B0263	—	D2263
#8	32	—	H2	3	—	B0282	—	D2282
#8	32	—	H3	3	B1283	B0283	B2283	D2283
#8	32	—	H4	3	—	B0284	—	D2284
#8	32	—	H5	3	—	B0285	—	D2285
#8	32	—	H6	3	—	B0286	—	D2286
#8	32	—	H7	3	—	B0287	—	D2287
#8	—	36	H3	3	—	B0303	—	D2303
#10	24	—	H2	3	—	B0322	—	D2322
#10	24	—	H3	3	B1323	B0323	B2323	D2323
#10	24	—	H5	3	—	B0325	—	D2325
#10	24	—	H7	3	—	B0327	—	D2327
#10	—	32	H2	3	—	B0342	—	D2342
#10	—	32	H3	3	B1343	B0343	B2343	D2343

▶ Refer to technical data on page 520~554. ▶ NEXT PAGE

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎			◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL FLUTE TAPS

B1/B0/B2/D2 SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Stainless Steels



VA HSSE-V3 UNC UNF USCTI 302A 2P~3P Bright Steam Oxide TIN Hardslick R45

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.			
	UNC	UNF			Bright	Steam Oxide	TiN	Hardslick
#10	—	32	H4	3	—	B0344	—	D2344
#10	—	32	H5	3	—	B0345	—	D2345
#10	—	32	H6	3	—	B0346	—	D2346
#10	—	32	H7	3	—	B0347	—	D2347
#12	24	—	H3	3	—	B0363	—	D2363
#12	28	—	H3	3	—	B0383	—	D2383
1/4	20	—	H2	3	—	B0402	—	D2402
1/4	20	—	H3	3	B1403	B0403	B2403	D2403
1/4	20	—	H5	3	B1405	B0405	B2405	D2405
1/4	20	—	H7	3	—	B0407	—	D2407
1/4	—	28	H2	3	—	B0422	—	D2422
1/4	—	28	H3	3	B1423	B0423	B2423	D2423
1/4	—	28	H4	3	—	B0424	—	D2424
1/4	—	28	H5	3	—	B0425	—	D2425
1/4	—	28	H6	3	—	B0426	—	D2426
1/4	—	28	H7	3	—	B0427	—	D2427
5/16	18	—	H3	3	B1443	B0443	B2443	D2443
5/16	18	—	H5	3	B1445	B0445	B2445	D2445
5/16	18	—	H7	3	—	B0447	—	D2447
5/16	—	24	H3	3	B1463	B0463	B2463	D2463
5/16	—	24	H4	3	—	B0464	—	D2464
5/16	—	24	H5	3	—	B0465	—	D2465
5/16	—	24	H7	3	—	B0467	—	D2467
3/8	16	—	H3	3	B1483	B0483	B2483	D2483
3/8	16	—	H5	3	B1485	B0485	B2485	D2485
3/8	16	—	H7	3	—	B0487	—	D2487
3/8	—	24	H3	3	B1503	B0503	B2503	D2503
3/8	—	24	H4	3	—	B0504	—	D2504
3/8	—	24	H5	3	—	B0505	—	D2505

▶ Refer to technical data on page 520~554. ▶ NEXT PAGE

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎			◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL FLUTE TAPS

B1/B0/B2/D2 SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Stainless Steels



- VA
- HSSE-V3
- UNC UNF
- USCTI 302A
- 2P~3P
- Bright
- Steam Oxide
- TiN
- Hardslick
- R45

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.			
	UNC	UNF			Bright	Steam Oxide	TiN	Hardslick
7/16	14	—	H3	3	B1523	B0523	B2523	D2523
7/16	14	—	H5	3	B1525	B0525	B2525	D2525
7/16	14	—	H7	3	—	B0527	—	D2527
7/16	—	20	H3	3	B1543	B0543	B2543	D2543
7/16	—	20	H5	3	B1545	B0545	B2545	D2545
7/16	—	20	H7	3	—	B0547	—	D2547
1/2	13	—	H3	3	B1563	B0563	B2563	D2563
1/2	13	—	H5	3	B1565	B0565	B2565	D2565
1/2	13	—	H7	3	—	B0567	—	D2567
1/2	—	20	H3	3	B1583	B0583	B2583	D2583
1/2	—	20	H5	3	—	B0585	—	D2585
1/2	—	20	H6	3	—	B0586	—	D2586
1/2	—	20	H7	3	—	B0587	—	D2587
9/16	12	—	H3	3	B1603	B0603	B2603	D2603
9/16	—	18	H3	3	B1623	B0623	B2623	D2623
5/8	11	—	H3	4	B1643	B0643	B2643	D2643
5/8	11	—	H5	4	B1645	B0645	B2645	D2645
5/8	—	18	H3	4	B1663	B0663	B2663	D2663
5/8	—	18	H5	4	B1665	B0665	B2665	D2665
3/4	10	—	H3	4	B1703	B0703	B2703	D2703
3/4	10	—	H6	4	—	B0706	—	D2706
3/4	—	16	H3	4	B1723	B0723	B2723	D2723
3/4	—	16	H5	4	B1725	B0725	B2725	D2725
7/8	9	—	H4	4	B1744	B0744	B2744	D2744
7/8	—	14	H4	4	B1764	B0764	B2764	D2764
1	8	—	H4	4	B1784	B0784	B2784	D2784
1	—	12	H4	4	B1804	B0804	B2804	D2804

Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎			◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL FLUTE TAPS

BS/BT SERIES

METRIC SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Stainless Steels



- VA
- HSSE-V3
- M MF
- USCTI 302A
- 2P~3P
- Steam Oxide
- Hardslick
- R45

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Steam Oxide	Hardslick
M3	0.5	D3	3	BS203	BT203
M3.5	0.6	D4	3	BS224	BT224
M4	0.7	D4	3	BS244	BT244
M5	0.8	D4	3	BS284	BT284
M6	1.0	D5	3	BS315	BT315
M7	1.0	D5	3	BS345	BT345
M8	1.25	D5	3	BS365	BT365
M8	1.0	D5	3	BS375	BT375
M10	1.5	D6	3	BS426	BT426
M10	1.25	D5	3	BS435	BT435
M12	1.75	D6	3	BS506	BT506
M12	1.25	D5	3	BS525	BT525
M14	2.0	D7	3	BS547	BT547
M14	1.5	D6	3	BS556	BT556
M16	2.0	D7	3	BS607	BT607
M16	1.5	D6	3	BS616	BT616
M18	2.5	D7	4	BS657	BT657
M18	1.5	D6	4	BS676	BT676

Refer to technical data on page 520~554.



◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎			◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL FLUTE TAPS

E6/E8/E9 SERIES

METRIC SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Stainless Steels



- VA
- HSSE-V3
- M MF
- 2P~3P
- Steam Oxide
- TiCN
- Hardslick
- R45

SIZE	Pitch	Limit	No. of Flute	EDP No.		
				Steam Oxide	TiCN	Hardslick
M3	0.5	D3	3	E6203	E8203	E9203
M3.5	0.6	D4	3	E6224	E8224	E9224
M4	0.7	D4	3	E6244	E8244	E9244
M5	0.8	D4	3	E6284	E8284	E9284
M6	1.0	D5	3	E6315	E8315	E9315
M7	1.0	D5	3	E6345	E8345	E9345
M8	1.25	D5	3	E6365	E8365	E9365
M8	1.0	D5	3	E6375	E8375	E9375
M10	1.5	D6	3	E6426	E8426	E9426
M10	1.25	D5	3	E6435	E8435	E9435
M12	1.75	D6	3	E6506	E8506	E9506
M12	1.25	D5	3	E6525	E8525	E9525
M14	2.0	D7	3	E6547	E8547	E9547
M14	1.5	D6	3	E6556	E8556	E9556
M16	2.0	D7	3	E6607	E8607	E9607
M16	1.5	D6	4	E6616	E8616	E9616
M18	2.5	D7	4	E6657	E8657	E9657
M18	1.5	D6	4	E6676	E8676	E9676

Refer to technical data on page 520~554.



P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎			◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			○

YG SPIRAL FLUTE TAPS

D3/E0 SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Steels

A variety of H Limit



- VG
- HSSE-V3
- UNC UNF
- USCTI 302A
- 2P~3P
- Steam Oxide
- Hardslick
- R45

SIZE	Thread Per Inch			Limit	No. of Flute	EDP No.	
	UNC	UNF	UN			Steam Oxide	Hardslick
#2	56	—	—	H2	2	D3082	E0082
#3	48	—	—	H2	2	D3122	E0122
#4	40	—	—	H2	3	D3162	E0162
#4	40	—	—	H3	3	D3163	E0163
#4	40	—	—	H4	3	D3164	E0164
#4	40	—	—	H5	3	D3165	E0165
#4	—	48	—	H2	3	D3162	E0162
#5	40	—	—	H2	3	D3202	E0202
#6	32	—	—	H2	3	D3242	E0242
#6	32	—	—	H3	3	D3243	E0243
#6	32	—	—	H5	3	D3245	E0245
#6	32	—	—	H7	3	D3247	E0247
#6	32	—	—	H11	3	D324A	E024A
#6	—	40	—	H2	3	D3262	E0262
#8	32	—	—	H2	3	D3282	E0282
#8	32	—	—	H3	3	D3283	E0283
#8	32	—	—	H5	3	D3285	E0285
#8	32	—	—	H7	3	D3287	E0287
#8	32	—	—	H11	3	D328A	E028A
#10	24	—	—	H3	3	D3323	E0323
#10	24	—	—	H5	3	D3325	E0325
#10	24	—	—	H11	3	D332A	E032A
#10	—	32	—	H2	3	D3342	E0342
#10	—	32	—	H3	3	D3343	E0343
#10	—	32	—	H5	3	D3345	E0345
#10	—	32	—	H7	3	D3347	E0347
#10	—	32	—	H11	3	D334A	E034A
#12	24	—	—	H3	3	D3363	E0363
#12	—	28	—	H3	3	D3383	E0383
1/4	20	—	—	H2	3	D3402	E0402
1/4	20	—	—	H3	3	D3403	E0403
1/4	20	—	—	H5	3	D3405	E0405
1/4	20	—	—	H7	3	D3407	E0407
1/4	20	—	—	H11	3	D340A	E040A

Refer to technical data on page 520~554.

Bright Finish Available: D4 Series

NEXT PAGE



P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
	◎			○						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
										○

YG SPIRAL FLUTE TAPS

D3/E0 SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Steels

A variety of H Limit



VG
HSSE-V3
UNC UNF
USCTI 302A
2P~3P
Steam Oxide
Hardslick
R45

SIZE	Thread Per Inch			Limit	No. of Flute	EDP No.	
	UNC	UNF	UN			Steam Oxide	Hardslick
1/4	—	28	—	H2	3	D3422	E0422
1/4	—	28	—	H3	3	D3423	E0423
1/4	—	28	—	H4	3	D3424	E0424
1/4	—	28	—	H5	3	D3425	E0425
1/4	—	28	—	H7	3	D3427	E0427
1/4	—	28	—	H11	3	D342A	E042A
5/16	18	—	—	H2	3	D3442	E0442
5/16	18	—	—	H3	3	D3443	E0443
5/16	18	—	—	H5	3	D3445	E0445
5/16	18	—	—	H7	3	D3447	E0447
5/16	18	—	—	H11	3	D344A	E044A
5/16	—	24	—	H2	3	D3462	E0462
5/16	—	24	—	H3	3	D3463	E0463
5/16	—	24	—	H4	3	D3464	E0464
5/16	—	24	—	H5	3	D3465	E0465
5/16	—	24	—	H6	3	D3466	E0466
5/16	—	24	—	H7	3	D3467	E0467
5/16	—	24	—	H11	3	D346A	E046A
3/8	16	—	—	H2	3	D3482	E0482
3/8	16	—	—	H3	3	D3483	E0483
3/8	16	—	—	H5	3	D3485	E0485
3/8	16	—	—	H7	3	D3487	E0487
3/8	16	—	—	H11	3	D348A	E048A
3/8	—	24	—	H2	3	D3502	E0502
3/8	—	24	—	H3	3	D3503	E0503
3/8	—	24	—	H4	3	D3504	E0504
3/8	—	24	—	H5	3	D3505	E0505
3/8	—	24	—	H7	3	D3507	E0507
3/8	—	24	—	H11	3	D350A	E050A
7/16	14	—	—	H3	3	D3523	E0523
7/16	14	—	—	H5	3	D3525	E0525
7/16	14	—	—	H7	3	D3527	E0527
7/16	14	—	—	H11	3	D352A	E052A
7/16	—	20	—	H3	3	D3543	E0543
7/16	—	20	—	H5	3	D3545	E0545

Refer to technical data on page 520~554. BRIGHT FINISH AVAILABLE: D4 SERIES



P		M					K			
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
	◎	◎		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
										○

YG SPIRAL FLUTE TAPS

D3/E0 SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Steels

A variety of H Limit



VG
HSSE-V3
UNC UNF
USCTI 302A
2P~3P
Steam Oxide
Hardslick
R45

SIZE	Thread Per Inch			Limit	No. of Flute	EDP No.	
	UNC	UNF	UN			Steam Oxide	Hardslick
7/16	—	20	—	H7	3	D3547	E0547
7/16	—	20	—	H11	3	D354A	E054A
1/2	13	—	—	H3	3	D3563	E0563
1/2	13	—	—	H5	3	D3565	E0565
1/2	13	—	—	H7	3	D3567	E0567
1/2	13	—	—	H11	3	D356A	E056A
1/2	—	20	—	H3	3	D3583	E0583
1/2	—	20	—	H5	3	D3585	E0585
1/2	—	20	—	H7	3	D3587	E0587
1/2	—	20	—	H11	3	D358A	E058A
9/16	12	—	—	H3	4	D3603	E0603
9/16	—	18	—	H3	4	D3623	E0623
5/8	11	—	—	H3	4	D3643	E0643
5/8	11	—	—	H5	4	D3645	E0645
5/8	—	18	—	H3	4	D3663	E0663
3/4	10	—	—	H3	4	D3703	E0703
3/4	10	—	—	H5	4	D3705	E0705
3/4	—	16	—	H3	4	D3723	E0723
3/4	—	16	—	H5	4	D3725	E0725
7/8	9	—	—	H5	4	D3745	E0745
7/8	—	14	—	H4	4	D3764	E0764
1	8	—	—	H5	4	D3785	E0785
1	—	12	—	H4	4	D3804	E0804
1-1/8	7	—	—	H6	4	D3826	E0826
1-1/8	—	12	—	H5	4	D3845	E0845
1-1/8	—	—	8	H6	4	D3836	E0836
1-1/4	7	—	—	H6	4	D3866	E0866
1-1/4	—	12	—	H5	4	D3885	E0885
1-1/4	—	—	8	H6	4	D3876	E0876
1-3/8	6	—	—	H6	4	D3906	E0906
1-3/8	—	12	—	H5	4	D3925	E0925
1-3/8	—	—	8	H6	4	D3916	E0916
1-1/2	6	—	—	H6	4	D3946	E0946
1-1/2	—	12	—	H5	4	D3965	E0965
1-1/2	—	—	8	H6	4	D3956	E0956

Refer to technical data on page 520~554. BRIGHT FINISH AVAILABLE: D4 SERIES



P		M					K			
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
	◎	◎		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
										○

YG SPIRAL FLUTE TAPS

BU / BV SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Steels

A variety of D Limit



VG **HSSE-V3** **M MF** **USCTI 302A** **2P~3P** **Steam Oxide** **Hardslick** **R45**

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Steam Oxide	Hardslick
M3	0.50	D3	3	BU203	BV203
M3	0.50	D11	3	BU20A	BV20A
M3.5	0.60	D4	3	BU224	BV224
M3.5	0.60	D11	3	BU22A	BV22A
M4	0.70	D4	3	BU244	BV244
M4	0.70	D11	3	BU24A	BV24A
M5	0.80	D4	3	BU284	BV284
M5	0.80	D11	3	BU28A	BV28A
M6	1.00	D5	3	BU315	BV315
M6	1.00	D11	3	BU31A	BV31A
M7	1.00	D5	3	BU345	BV345
M7	1.00	D11	3	BU34A	BV34A
M8	1.00	D5	3	BU375	BV375
M8	1.00	D11	3	BU37A	BV37A
M8	1.25	D5	3	BU365	BV365
M8	1.25	D11	3	BU36A	BV36A
M10	1.00	D5	3	BU445	BV445
M10	1.00	D11	3	BU44A	BV44A
M10	1.25	D5	3	BU435	BV435
M10	1.25	D11	3	BU43A	BV43A
M10	1.50	D6	3	BU426	BV426
M10	1.50	D11	3	BU42A	BV42A
M12	1.25	D5	3	BU525	BV525
M12	1.25	D11	3	BU52A	BV52A
M12	1.50	D6	3	BU516	BV516
M12	1.50	D11	3	BU51A	BV51A
M12	1.75	D6	3	BU506	BV506

Refer to technical data on page 520~554.

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				M				K		
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)			
	◎	◎		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
										○

YG SPIRAL FLUTE TAPS

BU / BV SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Steels

A variety of D Limit



VG **HSSE-V3** **M MF** **USCTI 302A** **2P~3P** **Steam Oxide** **Hardslick** **R45**

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Steam Oxide	Hardslick
M12	1.75	D11	3	BU50A	BV50A
M14	1.50	D6	3	BU556	BV556
M14	2.00	D7	3	BU547	BV547
M16	1.50	D6	3	BU616	BV616
M16	2.00	D7	3	BU607	BV607
M18	1.50	D6	4	BU676	BV676
M18	2.50	D7	4	BU657	BV657
M20	1.50	D6	4	BU726	BV726
M20	2.50	D8	4	BU708	BV708
M22	1.50	D6	4	BU766	BV766
M22	2.50	D8	4	BU748	BV748
M24	1.50	D6	4	BU806	BV806
M24	3.00	D8	4	BU788	BV788
M27	1.50	D6	4	BU886	BV886
M27	3.00	D8	4	BU868	BV868
M30	1.50	D6	4	BU976	BV976
M30	3.50	D9	4	BU949	BV949

Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)			
	◎	◎		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
										○

YG SPIRAL FLUTE TAPS

E2/E4/E5 SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Steels



VG
HSSE-V3
M MF
2P~3P
Steam Oxide
TiCN
Hardslick
R45

SIZE	Pitch	Limit	No. of Flute	EDP No.		
				Steam Oxide	TiCN	Hardslick
M3	0.5	D3	3	E2203	E4203	E5203
M3.5	0.6	D4	3	E2224	E4224	E5224
M4	0.7	D4	3	E2244	E4244	E5244
M5	0.8	D4	3	E2284	E4284	E5284
M6	1.0	D5	3	E2315	E4315	E5315
M7	1.0	D5	3	E2345	E4345	E5345
M8	1.25	D5	3	E2365	E4365	E5365
M8	1.0	D5	3	E2375	E4375	E5375
M10	1.5	D6	3	E2426	E4426	E5426
M10	1.25	D5	3	E2435	E4435	E5435
M12	1.75	D6	3	E2506	E4506	E5506
M12	1.25	D5	3	E2525	E4525	E5525
M14	2.0	D7	3	E2547	E4547	E5547
M14	1.5	D6	3	E2556	E4556	E5556
M16	2.0	D7	3	E2607	E4607	E5607
M16	1.5	D6	3	E2616	E4616	E5616
M18	2.5	D7	4	E2657	E4657	E5657
M18	1.5	D6	4	E2676	E4676	E5676

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)		~HRc19 (~HB220)		
	◎	◎		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
								○		

YG SPIRAL FLUTE TAPS

CO/D8 SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Aluminum Alloys or Die Cast Aluminum



AI
HSSE-V3
UNC UNF
USCTI 302A
2P~3P
Bright
Hardslick
R50

◇ Call for Availability

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.	
	UNC	UNF			Bright	Hardslick
#4	40	—	H2	2	C0162	D8162
#4	40	—	H3	2	◇ C0163	D8163
#6	32	—	H2	2	C0242	D8242
#6	32	—	H3	2	C0243	D8243
#8	32	—	H2	2	◇ C0282	D8282
#8	32	—	H3	2	C0283	D8283
#10	24	—	H3	2	C0323	D8323
#10	32	—	H2	2	◇ C0342	D8342
#10	—	32	H3	2	C0343	D8343
#10	—	32	H5	2	◇ C0345	D8345
1/4	20	—	H3	2	C0403	D8403
1/4	20	—	H5	2	C0405	D8405
1/4	—	28	H3	2	C0423	D8423
5/16	18	—	H3	2	C0443	D8443
5/16	18	—	H5	2	C0445	D8445
5/16	—	24	H3	2	C0463	D8463
5/16	—	24	H5	2	C0465	D8465
3/8	16	—	H3	2	C0483	D8483
3/8	16	—	H5	2	C0485	D8485
3/8	—	24	H3	2	C0503	D8503
3/8	—	24	H5	2	C0505	D8505
1/2	13	—	H3	2	◇ C0563	D8563
1/2	13	—	H5	2	◇ C0565	D8565
1/2	—	20	H3	2	◇ C0583	D8583
5/8	11	—	H3	3	◇ C0643	D8643
5/8	—	18	H3	3	◇ C0663	D8663
3/4	10	—	H3	3	◇ C0703	D8703
3/4	—	16	H3	3	◇ C0723	D8723
7/8	9	—	H4	3	◇ C0744	D8744
7/8	—	14	H4	3	◇ C0764	D8764
1	8	—	H4	3	◇ C0784	D8784

▶ Refer to technical data on page 520~554.


◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)		~HRc19 (~HB220)		
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
								○	◎	

YG SPIRAL FLUTE TAPS

BW / BX SERIES

SPIRAL FLUTE TAPS MODIFIED BOTTOMING STYLE for Aluminum Alloys or Die Cast Aluminum



AI HSSE-V3 M MF USCTI 302A 2P~3P Bright Hardslick R50 ◆ Call for Availability

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Bright	Hardslick
M3	0.5	D3	2	BW203	BX203
M4	0.7	D4	2	BW244	BX244
M5	0.8	D5	2	BW285	BX285
M6	1.0	D5	2	BW315	BX315
M8	1.25	D5	2	BW365	BX365
M10	1.50	D6	2	BW426	BX426
M10	1.25	D5	2	BW435	BX435
M12	1.75	D6	2	BW506	◆ BX506
M12	1.50	D5	2	BW515	◆ BX515
M12	1.25	D5	2	BW525	◆ BX525

▶ DIN Length available: Bright Finish F1 Series & Hardslick coated F3 Series
 ▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K	
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)		
K	N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)									
				◎	◎				

YG SPIRAL FLUTE TAPS

C2/C3/C4/D9 SERIES

STANDARD TAPS : SPIRAL FLUTE TAPS BOTTOMING STYLE for General Purpose



GS HSSE-V3 UNC UNF USCTI 302 1.5P~2P Steam Oxide Bright TiN Hardslick R45

SIZE	Thread Per Inch		Limit	No of Flute	EDP No.			
	UNC	UNF			Steam Oxide	Bright	TiN	Hardslick
#4	40	—	H2	2	C2162	C3162	C4162	D9162
#5	40	—	H2	3	C2202	C3202	C4202	D9202
#6	32	—	H3	3	C2243	C3243	C4243	D9243
#8	32	—	H3	3	C2283	C3283	C4283	D9283
#10	24	—	H3	3	C2323	C3323	C4323	D9323
#10	—	32	H3	3	C2343	C3343	C4343	D9343
1/4	20	—	H3	3	C2403	C3403	C4403	D9403
1/4	20	—	H5	3	C2405	C3405	C4405	D9405
1/4	—	28	H3	3	C2423	C3423	C4423	D9423
5/16	18	—	H3	3	C2443	C3443	C4443	D9443
5/16	18	—	H5	3	C2445	C3445	C4445	D9445
5/16	—	24	H3	3	C2463	C3463	C4463	D9463
3/8	16	—	H3	3	C2483	C3483	C4483	D9483
3/8	16	—	H5	3	C2485	C3485	C4485	D9485
3/8	—	24	H3	3	C2503	C3503	C4503	D9503
7/16	14	—	H3	3	C2523	C3523	C4523	D9523
7/16	14	—	H5	3	C2525	C3525	C4525	D9525
7/16	—	20	H3	3	C2543	C3543	C4543	D9543
7/16	—	20	H5	3	C2545	C3545	C4545	D9545
1/2	13	—	H3	3	C2563	C3563	C4563	D9563
1/2	13	—	H5	3	C2565	C3565	C4565	D9565
1/2	—	20	H3	3	C2583	C3583	C4583	D9583
1/2	—	20	H5	3	C2585	C3585	C4585	D9585
9/16	12	—	H5	3	C2605	C3605	C4605	D9605
9/16	—	18	H5	3	C2625	C3625	C4625	D9625
5/8	11	—	H3	4	C2643	C3643	C4643	D9643
5/8	11	—	H5	4	C2645	C3645	C4645	D9645
5/8	—	18	H3	4	C2663	C3663	C4663	D9663
3/4	10	—	H3	4	C2703	C3703	C4703	D9703
3/4	10	—	H5	4	C2705	C3705	C4705	D9705
3/4	—	16	H3	4	C2723	C3723	C4723	D9723
7/8	9	—	H4	4	C2744	C3744	C4744	D9744
7/8	—	14	H6	4	C2766	C3766	C4766	D9766
1	8	—	H4	4	C2784	C3784	C4784	D9784

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K	
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)		
K	N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)									

YG SPIRAL FLUTE TAPS

F4/F8/F6 SERIES

SPIRAL FLUTE TAPS BOTTOMING STYLE for General Purpose



- GS
- HSS-V
- UNC UNF
- USCTI 302A
- Steam Oxide
- TiN
- Hardslick
- R50

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Steam Oxide	TiN	Hardslick
#2	56	—	H2	2	F4082	F8082	F6082
#4	40	—	H2	2	F4162	F8162	F6162
#5	40	—	H2	2	F4202	F8202	F6202
#6	32	—	H3	3	F4243	F8243	F6243
#8	32	—	H3	3	F4283	F8283	F6283
#10	24	—	H3	3	F4323	F8323	F6323
#10	—	32	H3	3	F4343	F8343	F6343
1/4	20	—	H3	3	F4403	F8403	F6403
1/4	20	—	H5	3	F4405	F8405	F6405
1/4	—	28	H3	3	F4423	F8423	F6423
5/16	18	—	H3	3	F4443	F8443	F6443
5/16	18	—	H5	3	F4445	F8445	F6445
5/16	—	24	H3	3	F4463	F8463	F6463
3/8	16	—	H3	3	F4483	F8483	F6483
3/8	16	—	H5	3	F4485	F8485	F6485
3/8	—	24	H3	3	F4503	F8503	F6503
7/16	14	—	H3	3	F4523	F8523	F6523
7/16	14	—	H5	3	F4525	F8525	F6525
7/16	—	20	H3	3	F4543	F8543	F6543
7/16	—	20	H5	3	F4545	F8545	F6545
1/2	13	—	H3	3	F4563	F8563	F6563
1/2	13	—	H5	3	F4565	F8565	F6565
1/2	—	20	H3	3	F4583	F8583	F6583
1/2	—	20	H5	3	F4585	F8585	F6585
9/16	12	—	H3	3	F4603	F8603	F6603
9/16	12	—	H5	3	F4605	F8605	F6605
9/16	—	18	H3	3	F4623	F8623	F6623

Refer to technical data on page 520~554. ▶ NEXT PAGE

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	○	○		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					

YG SPIRAL FLUTE TAPS

F4/F8/F6 SERIES

SPIRAL FLUTE TAPS BOTTOMING STYLE for General Purpose



- GS
- HSS-V
- UNC UNF
- USCTI 302A
- 1.5P~2P
- Steam Oxide
- TiN
- Hardslick
- R50

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Steam Oxide	TiN	Hardslick
9/16	—	18	H5	3	F4625	F8625	F6625
5/8	11	—	H3	4	F4643	F8643	F6643
5/8	11	—	H5	4	F4645	F8645	F6645
5/8	—	18	H3	4	F4663	F8663	F6663
5/8	—	18	H5	4	F4665	F8665	F6665
3/4	10	—	H3	4	F4703	F8703	F6703
3/4	10	—	H5	4	F4705	F8705	F6705
3/4	—	16	H3	4	F4723	F8723	F6723
3/4	—	16	H5	4	F4725	F8725	F6725
7/8	9	—	H4	4	F4744	F8744	F6744
7/8	9	—	H6	4	F4746	F8746	F6746
7/8	—	14	H4	4	F4764	F8764	F6764
7/8	—	14	H6	4	F4766	F8766	F6766
1	8	—	H4	4	F4784	F8784	F6784
1	8	—	H6	4	F4786	F8786	F6786
1	—	12	H6	4	F4806	F8806	F6806

Refer to technical data on page 520~554.

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	○	○		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					

YG SPIRAL FLUTE TAPS

G4/G5/G6 SERIES

SPIRAL FLUTE TAPS BOTTOMING STYLE for General Purpose



GS HSS-V M MF USCTI 302A 1.5P~2P Bright TiCN Hardslick R50

SIZE	Pitch	Limit	No. of Flute	EDP No.		
				Bright	TiCN	Hardslick
M3	0.5	D3	2	G4203	G5203	G6203
M3.5	0.6	D4	2	G4224	G5224	G6224
M4	0.7	D4	3	G4244	G5244	G6244
M5	0.8	D4	3	G4284	G5284	G6284
M6	1.0	D5	3	G4315	G5315	G6315
M7	1.0	D5	3	G4345	G5345	G6345
M8	1.25	D5	3	G4365	G5365	G6365
M8	1.0	D5	3	G4375	G5375	G6375
M10	1.5	D6	3	G4426	G5426	G6426
M10	1.25	D5	3	G4435	G5435	G6435
M12	1.75	D6	3	G4506	G5506	G6506
M12	1.25	D5	3	G4525	G5525	G6525

Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)		~HRc19 (~HB220)		
◎	◎	○		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					

YG SPIRAL FLUTE TAPS

G0/G1/G2 SERIES

SPIRAL FLUTE TAPS BOTTOMING STYLE for General Purpose



GS HSS-V UNC UNF 2P~3P Bright TiN Hardslick R45

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Bright	TiN	Hardslick
#2	56	—	H2	2	G0082	G1082	G2082
#4	40	—	H2	2	G0162	G1162	G2162
#5	40	—	H2	3	G0202	G1202	G2202
#6	32	—	H3	3	G0243	G1243	G2243
#8	32	—	H3	3	G0283	G1283	G2283
#10	24	—	H3	3	G0323	G1323	G2323
#10	—	32	H3	3	G0343	G1343	G2343
1/4	20	—	H3	3	G0403	G1403	G2403
1/4	20	—	H5	3	G0405	G1405	G2405
1/4	—	28	H3	3	G0423	G1423	G2423
5/16	18	—	H3	3	G0443	G1443	G2443
5/16	18	—	H5	3	G0445	G1445	G2445
5/16	—	24	H3	3	G0463	G1463	G2463
3/8	16	—	H3	3	G0483	G1483	G2483
3/8	16	—	H5	3	G0485	G1485	G2485
3/8	—	24	H3	3	G0503	G1503	G2503
7/16	14	—	H3	3	G0523	G1523	G2523
7/16	14	—	H5	3	G0525	G1525	G2525
7/16	—	20	H3	3	G0543	G1543	G2543
7/16	—	20	H5	3	G0545	G1545	G2545
1/2	13	—	H3	3	G0563	G1563	G2563
1/2	13	—	H5	3	G0565	G1565	G2565
1/2	—	20	H3	3	G0583	G1583	G2583
1/2	—	20	H5	3	G0585	G1585	G2585
9/16	12	—	H3	3	G0603	G1603	G2603
9/16	12	—	H5	3	G0605	G1605	G2605
9/16	—	18	H3	3	G0623	G1623	G2623

Refer to technical data on page 520~554.

NEXT PAGE

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)		~HRc19 (~HB220)		
◎	◎	○		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					

YG SPIRAL FLUTE TAPS

GO / G1 / G2 SERIES

SPIRAL FLUTE TAPS BOTTOMING STYLE for General Purpose



GS
HSS-V
UNC UNF
2P~3P
Bright
TiN
Hardslick
R45

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Bright	TiN	Hardslick
9/16	—	18	H5	3	G0625	G1625	G2625
5/8	11	—	H3	4	G0643	G1643	G2643
5/8	11	—	H5	4	G0645	G1645	G2645
5/8	—	18	H3	4	G0663	G1663	G2663
5/8	—	18	H5	4	G0665	G1665	G2665
3/4	10	—	H3	4	G0703	G1703	G2703
3/4	10	—	H5	4	G0705	G1705	G2705
3/4	—	16	H3	4	G0723	G1723	G2723
3/4	—	16	H5	4	G0725	G1725	G2725
7/8	9	—	H6	4	G0746	G1746	G2746
7/8	—	14	H4	4	G0764	G1764	G2764
7/8	—	14	H6	4	G0766	G1766	G2766
1	8	—	H6	4	G0786	G1786	G2786
1	—	12	H4	4	G0804	G1804	G2804
1	—	12	H6	4	G0806	G1806	G2806

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎	○		○	○					
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					

YG SPIRAL FLUTE TAPS

T7A96 / T6A96 / T8A96 SERIES
T7295 / T6295 / T8295 SERIES

STANDARD TAPS : SPIRAL FLUTE TAPS for General Purpose



GS
HSS
UNC UNF
USCTI 302
4P~5P Plug
1.5P~2P Bottoming
Bright
Steam Oxide
TiN
R50

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.					
	UNC	UNF			Bright	Plug		Bottoming		
#3	48	—	H2	2	T7A96122	T6A96122	T8A96122	T7295122	T6295122	T8295122
#4	40	—	H2	2	T7A96162	T6A96162	T8A96162	T7295162	T6295162	T8295162
#5	40	—	H2	2	T7A96202	T6A96202	T8A96202	T7295202	T6295202	T8295202
#6	32	—	H2	2	T7A96242	T6A96242	T8A96242	T7295242	T6295242	T8295242
#6	32	—	H3	2	T7A96243	T6A96243	T8A96243	T7295243	T6295243	T8295243
#8	32	—	H2	3	T7A96282	T6A96282	T8A96282	T7295282	T6295282	T8295282
#8	32	—	H3	3	T7A96283	T6A96283	T8A96283	T7295283	T6295283	T8295283
#10	24	—	H3	3	T7A96323	T6A96323	T8A96323	T7295323	T6295323	T8295323
#10	—	32	H2	3	T7A96342	T6A96342	T8A96342	T7295342	T6295342	T8295342
#10	—	32	H3	3	T7A96343	T6A96343	T8A96343	T7295343	T6295343	T8295343
#12	24	—	H3	3	T7A96363	T6A96363	T8A96363	T7295363	T6295363	T8295363
1/4	20	—	H3	3	T7A96403	T6A96403	T8A96403	T7295403	T6295403	T8295403
1/4	20	—	H5	3	T7A96405	T6A96405	T8A96405	T7295405	T6295405	T8295405
1/4	—	28	H3	3	T7A96423	T6A96423	T8A96423	T7295423	T6295423	T8295423
5/16	18	—	H3	3	T7A96443	T6A96443	T8A96443	T7295443	T6295443	T8295443
5/16	18	—	H5	3	T7A96445	T6A96445	T8A96445	T7295445	T6295445	T8295445
5/16	—	24	H3	3	T7A96463	T6A96463	T8A96463	T7295463	T6295463	T8295463
3/8	16	—	H3	3	T7A96483	T6A96483	T8A96483	T7295483	T6295483	T8295483
3/8	16	—	H5	3	T7A96485	T6A96485	T8A96485	T7295485	T6295485	T8295485
3/8	—	24	H3	3	T7A96503	T6A96503	T8A96503	T7295503	T6295503	T8295503
7/16	14	—	H3	3	T7A96523	T6A96523	T8A96523	T7295523	T6295523	T8295523
7/16	14	—	H5	3	—	—	—	T7295525	T6295525	T8295525
7/16	—	20	H3	3	T7A96543	T6A96543	T8A96543	T7295543	T6295543	T8295543
1/2	13	—	H3	3	T7A96563	T6A96563	T8A96563	T7295563	T6295563	T8295563
1/2	13	—	H5	3	T7A96565	T6A96565	T8A96565	T7295565	T6295565	T8295565
1/2	—	20	H3	3	T7A96583	T6A96583	T8A96583	T7295583	T6295583	T8295583
5/8	11	—	H3	4	T7A96643	T6A96643	T8A96643	T7295643	T6295643	T8295643
5/8	—	18	H3	4	T7A96663	T6A96663	T8A96663	T7295663	T6295663	T8295663
3/4	10	—	H3	4	T7A96703	T6A96703	T8A96703	T7295703	T6295703	T8295703
3/4	—	16	H3	4	T7A96723	T6A96723	T8A96723	T7295723	T6295723	T8295723

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎	○		○	○					
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					

YG SPIRAL FLUTE TAPS

T7A86 / T6A86 / T8A86 SERIES
T7A85 / T6A85 / T8A85 SERIES

STANDARD TAPS : METRIC SPIRAL FLUTE TAPS for General Purpose



GS HSS M MF USCTI 302 4P~5P Plug 1.5P~2P Bottoming Bright Steam Oxide TiN R50

SIZE	Pitch	Limit	No. of Flute	EDP No.					
				Plug			Bottoming		
				Bright	Steam Oxide	TiN	Bright	Steam Oxide	TiN
M3	0.5	D3	2	T7A86203	T6A86203	T8A86203	T7A85203	T6A85203	T8A85203
M4	0.7	D4	3	T7A86244	T6A86244	T8A86244	T7A85244	T6A85244	T8A85244
M5	0.8	D4	3	T7A86284	T6A86284	T8A86284	T7A85284	T6A85284	T8A85284
M6	1.0	D5	3	T7A86315	T6A86315	T8A86315	T7A85315	T6A85315	T8A85315
M8	1.25	D5	3	T7A86365	T6A86365	T8A86365	T7A85365	T6A85365	T8A85365
M10	1.5	D6	3	T7A86426	T6A86426	T8A86426	T7A85426	T6A85426	T8A85426
M12	1.75	D6	3	T7A86506	T6A86506	T8A86506	T7A85506	T6A85506	T8A85506

Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)		~HRc19 (~HB220)		
◎	◎	○		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					

YG SPIRAL FLUTE TAPS

T7D01 / T8D01 SERIES
T7D02 / T8D02 SERIES

SPIRAL FLUTE TAP, 6" EXTENSION

Extended length for greater reach



GS HSS UNC UNF USCTI Long Shank 4P~5P Plug 1.5P~2P Bottoming Bright TiN R50

SIZE	UNC	UNF	Limit	Overall Length	No. of Flutes	EDP No.			
						Plug		Bottoming	
						Bright	TiN	Bright	TiN
#6	32	—	H3	6	2	T7D01243	T8D01243	T7D02243	T8D02243
#8	32	—	H3	6	3	T7D01283	T8D01283	T7D02283	T8D02283
#10	24	—	H3	6	3	T7D01323	T8D01323	T7D02323	T8D02323
#10	—	32	H3	6	3	T7D01343	T8D01343	T7D02343	T8D02343
1/4	20	—	H3	6	3	T7D01403	T8D01403	T7D02403	T8D02403
1/4	—	28	H3	6	3	T7D01423	T8D01423	T7D02423	T8D02423
5/16	18	—	H3	6	3	T7D01443	T8D01443	T7D02443	T8D02443
3/8	16	—	H3	6	3	T7D01483	T8D01483	T7D02483	T8D02483
7/16	14	—	H3	6	3	T7D01523	T8D01523	T7D02523	T8D02523
1/2	13	—	H3	6	3	T7D01563	T8D01563	T7D02563	T8D02563
5/8	11	—	H3	6	4	T7D01643	T8D01643	T7D02643	T8D02643

Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)		~HRc19 (~HB220)		
◎	◎	○		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					



Being the best through innovation

HSS




SPIRAL POINT TAPS

- Tapping Through Holes / Super HSS, P-HSS, HSSE-V3, HSS-V & HSS



Global Cutting Tool Leader **YG-1**



SELECTION GUIDE

SPIRAL POINT TAPS

Tapping Through Holes / Super HSS, P-HSS, HSSE-V3, HSS-V & HSS

INCH/METRIC

EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page
M9/O1		Super HSS	UNC/UNF	VG	USCTI 302A	H	4 ~ 5P	3.0D	Steam Oxide Hardslick	430
N7/N8		Super HSS	M/MF	VG	USCTI 302A	D	4 ~ 5P		Steam Oxide Hardslick	432
N4/O5		Super HSS	UNC/UNF	VG	DIN Length-ANSI Shank	H	4 ~ 5P		Steam Oxide Hardslick	433
N3/O3		Super HSS	M/MF	VG	DIN Length-ANSI Shank	D	4 ~ 5P		Steam Oxide Hardslick	434
M4/M5/M6/M7		P-HSS	UNC/UNF	HR	USCTI 302A	H	4 ~ 5P		Steam Oxide Bright/TiCN Hardslick	435
TQ808/TK808/TR808		P-HSS	M/MF	HR	USCTI 302A	H	4 ~ 5P		Steam Oxide TiCN Hardslick	436
I3/M8/I5/J6		P-HSS	UNC/UNF	Ti Ni	USCTI 302A	H	4 ~ 5P		Steam Oxide Bright/TiCN Hardslick	437
M0/M1/M2/M3		P-HSS	UNC/UNF	VA	USCTI Long Shank	H	4 ~ 5P		TiN Hardslick	439
I0/I2/J2		HSSE-V3	UNC/UNF	VA	USCTI 302A	H	4 ~ 5P		Steam Oxide TiN Hardslick	440
O9/IA		HSSE-V3	M/MF	VA	USCTI 302A	D	4 ~ 5P		Steam Oxide Hardslick	443
K3/K5/K6		HSSE-V3	M/MF	VA	DIN Length-ANSI Shank	D	4 ~ 5P		Steam Oxide TiCN Hardslick	444
J3/J4/J8		HSSE-V3	UNC/UNF	VG	USCTI 302A	H	4 ~ 5P		Steam Oxide Bright Hardslick	445
IB/IC		HSSE-V3	M/MF	VG	USCTI 302A	D	4 ~ 5P		Steam Oxide Hardslick	449
J9/K7/K2		HSSE-V3	M/MF	VG	DIN Length-ANSI Shank	D	4 ~ 5P		Steam Oxide TiCN Hardslick	451
T2496		HSSE-V3	UNC/UNF	AI	USCTI 302A	H	4 ~ 5P		Bright	452
T2K01		HSSE-V3	M/MF	AI	USCTI 302A	D	4 ~ 5P		Bright	453
I9/J0/J1/J7		HSSE-V3	UNC/UNF	GS	USCTI 302	H	4 ~ 5P		Steam Oxide Bright/TiN Hardslick	454
K9/L0/L1		HSS-V	UNC/UNF	GS	USCTI 302A	H	4 ~ 5P		Bright TiN Hardslick	455

EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page
L7/L8/L9		HSS-V	M/MF	GS	USCTI 302A	D	4 ~ 5P	3.0D	Bright TiCN Hardslick	456
L3/L4/L5		HSS-V	UNC/UNF	GS	DIN Length-ANSI Shank	H	4 ~ 5P		Bright TiN Hardslick	457
T7216/T6216/T8216/T7C16/T6C16/T8C16		HSS	UNC/UNF	GS	USCTI 302	H	4 ~ 5P		Bright Finish Steam Oxide TiN	458
T7256/T6256		HSS	UNC/UNF	GS	USCTI 302	H	1.5 ~ 2P		Bright Finish Steam Oxide	462
T7217/T6217/T8217		HSS	M/MF	GS	USCTI 302	D	4 ~ 5P		Bright Finish Steam Oxide TiN	464
T7226/T6226/T8226		HSS	UNC/UNF	GS	USCTI 302	+0.005" oversize	4 ~ 5P		Bright Finish Steam Oxide TiN	465
T7B17/T6B17/T8B17		HSS	M/MF	GS	USCTI 302	+0.127mm oversize	4 ~ 5P		Bright Finish Steam Oxide TiN	466
T7236/T6236/T8236/T7G36/T6G36/T8G36		HSS	UNC/UNF	GS	USCTI Long Shank	H	4 ~ 5P		Bright Finish Steam Oxide TiN	467

YG SPIRAL POINT TAPS


M9/01 SERIES

SPIRAL POINT TAPS PLUG STYLE for Steels & Stainless Steels

Thread Depth / Hole Type 3.0×D



USCTI



- VG
- Super HSS
- UNC UNF
- USCTI 302A
- 4P~5P
- Steam Oxide
- Hardslick

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.	
	UNC	UNF			Steam Oxide	Hardslick
#2	56	—	H2	2	M9082	O1082
#4	40	—	H2	2	M9162	O1162
#4	40	—	H3	2	M9163	O1163
#4	40	—	H4	2	M9164	O1164
#4	40	—	H5	2	M9165	O1165
#5	40	—	H2	3	M9202	O1202
#6	32	—	H2	3	M9242	O1242
#6	32	—	H3	3	M9243	O1243
#6	32	—	H4	3	M9244	O1244
#6	32	—	H5	3	M9245	O1245
#6	32	—	H6	3	M9246	O1246
#8	32	—	H2	3	M9282	O1282
#8	32	—	H3	3	M9283	O1283
#8	32	—	H4	3	M9284	O1284
#8	32	—	H5	3	M9285	O1285
#8	32	—	H6	3	M9286	O1286
#10	24	—	H3	3	M9323	O1323
#10	24	—	H5	3	M9325	O1325
#10	—	32	H2	3	M9342	O1342
#10	—	32	H3	3	M9343	O1343
#10	—	32	H4	3	M9344	O1344
#10	—	32	H5	3	M9345	O1345
#10	—	32	H6	3	M9346	O1346
1/4	20	—	H3	3	M9403	O1403
1/4	20	—	H5	3	M9405	O1405
1/4	—	28	H3	3	M9423	O1423
1/4	—	28	H4	3	M9424	O1424
1/4	—	28	H5	3	M9425	O1425
1/4	—	28	H6	3	M9426	O1426
5/16	18	—	H3	3	M9443	O1443
5/16	18	—	H5	3	M9445	O1445
5/16	—	24	H3	3	M9463	O1463
5/16	—	24	H4	3	M9464	O1464

Refer to technical data on page 520~554.

NEXT PAGE

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎	◎		◎	◎					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL POINT TAPS


M9/01 SERIES

SPIRAL POINT TAPS PLUG STYLE for Steels & Stainless Steels

Thread Depth / Hole Type 3.0×D



USCTI



- VG
- Super HSS
- UNC UNF
- USCTI 302A
- 4P~5P
- Steam Oxide
- Hardslick

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.	
	UNC	UNF			Steam Oxide	Hardslick
5/16	—	24	H5	3	M9465	O1465
5/16	—	24	H6	3	M9466	O1466
3/8	16	—	H3	3	M9483	O1483
3/8	16	—	H5	3	M9485	O1485
3/8	—	24	H3	3	M9503	O1503
3/8	—	24	H4	3	M9504	O1504
3/8	—	24	H5	3	M9505	O1505
3/8	—	24	H6	3	M9506	O1506
7/16	14	—	H3	3	M9523	O1523
7/16	14	—	H5	3	M9525	O1525
7/16	—	20	H3	3	M9543	O1543
7/16	—	20	H5	3	M9545	O1545
1/2	13	—	H3	3	M9563	O1563
1/2	13	—	H5	3	M9565	O1565
1/2	—	20	H3	3	M9583	O1583
1/2	—	20	H5	3	M9585	O1585
9/16	12	—	H5	3	M9605	O1605
9/16	—	18	H5	3	M9625	O1625
5/8	11	—	H3	3	M9643	O1643
5/8	11	—	H5	3	M9645	O1645
5/8	—	18	H3	3	M9663	O1663
5/8	—	18	H5	3	M9665	O1665
3/4	10	—	H3	3	M9703	O1703
3/4	10	—	H5	3	M9705	O1705
3/4	—	16	H3	3	M9723	O1723
3/4	—	16	H5	3	M9725	O1725
7/8	9	—	H6	3	M9746	O1746
7/8	—	14	H6	3	M9766	O1766
1	8	—	H6	3	M9786	O1786
1	—	12	H6	3	M9806	O1806
1-1/8	8	—	H6	4	M9836	O1836
1-1/4	8	—	H6	4	M9876	O1876
1-3/8	8	—	H6	4	M9916	O1916
1-1/2	8	—	H6	4	M9956	O1956

Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎	◎		◎	◎					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL POINT TAPS


N7/N8 SERIES

METRIC SPIRAL POINT TAPS PLUG STYLE for Steels & Stainless Steels

Thread Depth / Hole Type 3.0×D



USCTI



- VG
- Super HSS
- M MF
- USCTI 302A
- 4P~5P
- Steam Oxide
- Hardslick

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Steam Oxide	Hardslick
M3	0.5	D3	3	N7203	N8203
M3.5	0.6	D4	3	N7224	N8224
M4	0.7	D4	3	N7244	N8244
M5	0.8	D4	3	N7284	N8284
M6	1.0	D5	3	N7315	N8315
M7	1.0	D5	3	N7345	N8345
M8	1.25	D5	3	N7365	N8365
M8	1.0	D5	3	N7375	N8375
M10	1.5	D6	3	N7426	N8426
M10	1.25	D5	3	N7435	N8435
M12	1.75	D6	3	N7506	N8506
M12	1.25	D5	3	N7525	N8525
M14	2.0	D7	3	N7547	N8547
M14	1.5	D6	3	N7556	N8556
M16	2.0	D7	3	N7607	N8607
M16	1.5	D6	3	N7616	N8616
M18	2.5	D7	3	N7657	N8657
M18	1.5	D6	3	N7676	N8676

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎	◎		◎	◎					
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL POINT TAPS


N4/O5 SERIES

SPIRAL POINT TAPS PLUG STYLE for Steels & Stainless Steels

Thread Depth / Hole Type 3.0×D



DIN Length-ANSI Shank



- VG
- Super HSS
- UNC UNF
- 4P~5P
- Steam Oxide
- Hardslick

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.	
	UNC	UNF			Steam Oxide	Hardslick
#2	56	—	H2	2	N4082	05082
#4	40	—	H2	2	N4162	05162
#5	40	—	H2	3	N4202	05202
#6	32	—	H3	3	N4243	05243
#8	32	—	H3	3	N4283	05283
#10	24	—	H3	3	N4323	05323
#10	—	32	H3	3	N4343	05343
1/4	20	—	H3	3	N4403	05403
1/4	20	—	H5	3	N4405	05405
1/4	—	28	H3	3	N4423	05423
5/16	18	—	H5	3	N4445	05445
5/16	—	24	H4	3	N4464	05464
3/8	16	—	H5	3	N4485	05485
3/8	—	24	H4	3	N4504	05504
7/16	14	—	H5	3	N4525	05525
7/16	—	20	H5	3	N4545	05545
1/2	13	—	H5	3	N4565	05565
1/2	—	20	H5	3	N4585	05585
9/16	12	—	H5	3	N4605	05605
9/16	—	18	H5	3	N4625	05625
5/8	11	—	H5	3	N4645	05645
5/8	—	18	H5	3	N4665	05665
3/4	10	—	H5	3	N4705	05705
3/4	—	16	H5	3	N4725	05725
7/8	9	—	H6	3	N4746	05746
7/8	—	14	H6	3	N4766	05766
1	8	—	H6	3	N4786	05786
1	—	12	H6	3	N4806	05806
1-1/8	8	—	H6	4	N4836	05836
1-1/4	8	—	H6	4	N4876	05876
1-3/8	8	—	H6	4	N4916	05916
1-1/2	8	—	H6	4	N4956	05956

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎	◎		◎	◎					
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL POINT TAPS


N3/O3 SERIES

METRIC SPIRAL POINT TAPS PLUG STYLE for Steels & Stainless Steels

Thread Depth / Hole Type 3.0×D



DIN Length-ANSI Shank



- HR
- Super HSS
- M MF
- 4P~5P
- Steam Oxide
- Hardslick

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Steam Oxide	Hardslick
M3	0.5	D3	3	N3203	03203
M3.5	0.6	D4	3	N3224	03224
M4	0.7	D4	3	N3244	03244
M5	0.8	D4	3	N3284	03284
M6	1.0	D5	3	N3315	03315
M7	1.0	D5	3	N3345	03345
M8	1.25	D5	3	N3365	03365
M8	1.0	D5	3	N3375	03375
M10	1.5	D6	3	N3426	03426
M10	1.25	D5	3	N3435	03435
M12	1.75	D6	3	N3506	03506
M12	1.25	D5	3	N3525	03525
M14	2.0	D7	3	N3547	03547
M14	1.5	D6	3	N3556	03556
M16	2.0	D7	3	N3607	03607
M16	1.5	D6	3	N3616	03616
M18	2.5	D7	3	N3657	03657
M18	1.5	D6	3	N3676	03676

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎	◎		◎	◎					
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL POINT TAPS


M4/M5/M6/M7 SERIES

SPIRAL POINT TAPS PLUG STYLE for Steels up to 25 ~ 45HRc

Thread Depth / Hole Type 3.0×D



USCTI



- HR
- P-HSS
- UNC UNF
- USCTI 302A
- 4P~5P
- Steam Oxide
- Bright
- TiCN
- Hardslick

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.			
	UNC	UNF			Steam Oxide	Bright	TiCN	Hardslick
#2	56	—	H2	2	M4082	M5082	M6082	M7082
#4	40	—	H2	2	M4162	M5162	M6162	M7162
#5	40	—	H2	3	M4202	M5202	M6202	M7202
#6	32	—	H3	3	M4243	M5243	M6243	M7243
#8	32	—	H3	3	M4283	M5283	M6283	M7283
#10	24	—	H3	3	M4323	M5323	M6323	M7323
#10	—	32	H3	3	M4343	M5343	M6343	M7343
1/4	20	—	H5	3	M4405	M5405	M6405	M7405
1/4	—	28	H4	3	M4424	M5424	M6424	M7424
5/16	18	—	H5	3	M4445	M5445	M6445	M7445
5/16	—	24	H4	3	M4464	M5464	M6464	M7464
3/8	16	—	H5	3	M4485	M5485	M6485	M7485
3/8	—	24	H4	3	M4504	M5504	M6504	M7504
7/16	14	—	H5	3	M4525	M5525	M6525	M7525
7/16	—	20	H5	3	M4545	M5545	M6545	M7545
1/2	13	—	H5	3	M4565	M5565	M6565	M7565
1/2	—	20	H5	3	M4585	M5585	M6585	M7585
9/16	12	—	H5	3	M4605	M5605	M6605	M7605
9/16	—	18	H5	3	M4625	M5625	M6625	M7625
5/8	11	—	H5	3	M4645	M5645	M6645	M7645
5/8	—	18	H5	3	M4665	M5665	M6665	M7665
3/4	10	—	H5	3	M4705	M5705	M6705	M7705
3/4	—	16	H5	3	M4725	M5725	M6725	M7725

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										

YG SPIRAL POINT TAPS


TQ808 / TK808 / TR808 SERIES

SPIRAL POINT TAPS PLUG STYLE for Steels up to 25 ~ 45HRc

Thread Depth / Hole Type 3.0×D



USCTI



- HR
- P-HSS
- M MF
- USCTI 302A
- 4P~5P
- Steam Oxide
- TiCN
- Hardslick

SIZE	Pitch	Limit	No. of Flute	EDP No.		
				Steam Oxide	TiCN	Hardslick
M3	0.5	D3	3	TQ808203	TK808203	TR808203HAR
M4	0.5	D3	3	TQ808253	TK808253	TR808253HAR
M4	0.7	D4	3	TQ808244	TK808244	TR808244HAR
M5	0.5	D3	3	TQ808293	TK808293	TR808293HAR
M5	0.8	D4	3	TQ808284	TK808284	TR808284HAR
M6	0.5	D3	3	TQ808333	TK808333	TR808333HAR
M6	0.75	D4	3	TQ808324	TK808324	TR808324HAR
M6	1	D5	3	TQ808315	TK808315	TR808315HAR
M8	1	D5	3	TQ808375	TK808375	TR808375HAR
M8	1.25	D5	3	TQ808365	TK808365	TR808365HAR
M10	1	D5	3	TQ808445	TK808445	TR808445HAR
M10	1.25	D5	3	TQ808435	TK808435	TR808435HAR
M10	1.5	D6	3	TQ808426	TK808426	TR808426HAR
M12	1	D5	3	TQ808535	TK808535	TR808535HAR
M12	1.25	D6	3	TQ808526	TK808526	TR808526HAR
M12	1.5	D6	3	TQ808516	TK808516	TR808516HAR
M12	1.75	D6	3	TQ808506	TK808506	TR808506HAR
M14	1.5	D6	3	TQ808556	TK808556	TR808556HAR
M14	2	D7	3	TQ808547	TK808547	TR808547HAR
M16	1.5	D6	4	TQ808616	TK808616	TR808616HAR
M16	2	D7	4	TQ808607	TK808607	TR808607HAR
M18	1.5	D6	4	TQ808676	TK808676	TR808676HAR
M18	2.5	D7	4	TQ808657	TK808657	TR808657HAR
M20	1.5	D6	4	TQ808726	TK808726	TR808726HAR
M20	2.5	D7	4	TQ808707	TK808707	TR808707HAR
M22	1.5	D6	4	TQ808766	TK808766	TR808766HAR
M22	2.5	D7	4	TQ808747	TK808747	TR808747HAR
M24	1.5	D6	4	TQ808806	TK808806	TR808806HAR
M24	3	D8	4	TQ808788	TK808788	TR808788HAR

Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)		~HRc19 (~HB220)		
		○	◎		○	◎				
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
			◎					○	○	○

YG SPIRAL POINT TAPS


13/M8/I5/J6 SERIES

SPIRAL POINT TAPS PLUG STYLE for Titanium Alloys & Nickel Base Alloys up to 38 ~ 45HRc

Thread Depth / Hole Type 3.0×D



USCTI



- Ti Ni
- P-HSS
- UNC UNF
- USCTI 302A
- 4P~5P
- Steam Oxide
- Bright
- TiCN
- Hardslick

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.			
	UNC	UNF			Steam Oxide	Bright	TiCN	Hardslick
#2	56	—	H2	2	I3082	M8082	I5082	J6082
#4	40	—	H2	2	I3162	M8162	I5162	J6162
#5	40	—	H2	3	I3202	M8202	I5202	J6202
#6	32	—	H3	3	I3243	M8243	I5243	J6243
#8	32	—	H3	3	I3283	M8283	I5283	J6283
#10	24	—	H3	3	I3323	M8323	I5323	J6323
#10	—	32	H3	3	I3343	M8343	I5343	J6343
1/4	20	—	H3	3	I3403	M8403	I5403	J6403
1/4	20	—	H5	3	I3405	M8405	I5405	J6405
1/4	—	28	H3	3	I3423	M8423	I5423	J6423
1/4	—	28	H4	3	I3424	M8424	I5424	J6424
5/16	18	—	H3	3	I3443	M8443	I5443	J6443
5/16	18	—	H5	3	I3445	M8445	I5445	J6445
5/16	—	24	H3	3	I3463	M8463	I5463	J6463
3/8	16	—	H3	3	I3483	M8483	I5483	J6483
3/8	16	—	H5	3	I3485	M8485	I5485	J6485
3/8	—	24	H3	3	I3503	M8503	I5503	J6503
3/8	—	24	H4	3	I3504	M8504	I5504	J6504
7/16	14	—	H3	3	I3523	M8523	I5523	J6523
7/16	14	—	H5	3	I3525	M8525	I5525	J6525
7/16	—	20	H3	3	I3543	M8543	I5543	J6543
7/16	—	20	H5	3	I3545	M8545	I5545	J6545
1/2	13	—	H3	3	I3563	M8563	I5563	J6563
1/2	13	—	H5	3	I3565	M8565	I5565	J6565
1/2	—	20	H3	3	I3583	M8583	I5583	J6583
1/2	—	20	H5	3	I3585	M8585	I5585	J6585

Refer to technical data on page 520~554.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)		~HRc19 (~HB220)		
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
								○	◎	◎

YG SPIRAL POINT TAPS


13/M8/I5/J6 SERIES

SPIRAL POINT TAPS PLUG STYLE for Titanium Alloys & Nickel Base Alloys up to 38 ~ 45HRc

Thread Depth / Hole Type 3.0×D



USCTI



- Ti Ni
- P-HSS
- UNC UNF
- USCTI 302A
- 4P~5P
- Steam Oxide
- Bright
- TiCN
- Hardslick

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.			
	UNC	UNF			Steam Oxide	Bright	TiCN	Hardslick
9/16	12	—	H3	3	I3603	M8603	I5603	J6603
9/16	12	—	H5	3	I3605	M8605	I5605	J6605
9/16	—	18	H3	3	I3623	M8623	I5623	J6623
9/16	—	18	H5	3	I3625	M8625	I5625	J6625
5/8	11	—	H3	3	I3643	M8643	I5643	J6643
5/8	11	—	H5	3	I3645	M8645	I5645	J6645
5/8	—	18	H3	3	I3663	M8663	I5663	J6663
5/8	—	18	H5	3	I3665	M8665	I5665	J6665
3/4	10	—	H3	3	I3703	M8703	I5703	J6703
3/4	10	—	H5	3	I3705	M8705	I5705	J6705
3/4	—	16	H3	3	I3723	M8723	I5723	J6723
3/4	—	16	H5	3	I3725	M8725	I5725	J6725

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										


YG SPIRAL POINT TAPS

M0/M1/M2/M3 SERIES


EXTENDED LENGTH SPIRAL POINT TAPS PLUG STYLE for Stainless Steels

Extended length for greater reach

Thread Depth / Hole Type 3.0×D



USCTI Long Shank



- VA
- P-HSS
- UNC UNF
- USCTI Long Shank
- 4P~5P
- TiN
- Hardslick

SIZE	Thread Per Inch		Limit	No. of Flute	Maximum Tapping Depth	EDP No.			
	UNC	UNF				TiN 4" OAL	TiN 6" OAL	Hardslick 4" OAL	Hardslick 6" OAL
#4	40	—	H2	2	0.844	M0162	—	M2162	—
#6	32	—	H3	2	1.031	M0243	M1243	M2243	M3243
#8	32	—	H3	3	1.125	M0283	M1283	M2283	M3283
#10	24	—	H3	3	1.312	M0323	M1323	M2323	M3323
#10	—	32	H3	3	1.312	M0343	M1343	M2343	M3343
1/4	20	—	H3	3	1.500	M0403	M1403	M2403	M3403
1/4	—	28	H3	3	1.500	—	M1423	—	M3423
5/16	18	—	H3	3	1.688	—	M1443	—	M3443
5/16	—	24	H3	3	1.688	—	M1463	—	M3463
3/8	16	—	H3	3	1.875	—	M1483	—	M3483
3/8	—	24	H3	3	—	—	M1503	—	M3503
7/16	14	—	H3	3	—	—	M1523	—	M3523
7/16	—	20	H3	3	—	—	M1543	—	M3543
1/2	13	—	H3	3	—	—	M1563	—	M3563
1/2	—	20	H3	3	—	—	M1583	—	M3583
9/16	12	—	H3	3	—	—	M1603	—	M3603
9/16	—	18	H3	3	—	—	M1623	—	M3623
5/8	11	—	H3	3	—	—	M1643	—	M3643

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										

YG SPIRAL POINT TAPS


10/I2/J2 SERIES

SPIRAL POINT TAPS PLUG STYLE for Stainless Steels

Thread Depth / Hole Type 3.0×D



USCTI



- VA
- HSSE-V3
- UNC UNF
- USCTI 302A
- 4P~5P
- Steam Oxide
- TiN
- Hardslick

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Steam Oxide	TiN	Hardslick
#2	56	—	H2	2	I0082	I2082	J2082
#2	56	—	H3	2	I0083	—	J2083
#2	56	—	H4	2	I0084	—	J2084
#3	48	—	H2	2	I0122	—	J2122
#4	40	—	H2	2	I0162	I2162	J2162
#4	40	—	H3	2	I0163	—	J2163
#4	40	—	H4	2	I0164	—	J2164
#4	40	—	H5	2	I0165	—	J2165
#4	40	—	H6	2	I0166	—	J2166
#4	—	48	H2	2	I0182	—	J2182
#4	—	48	H4	2	I0184	—	J2184
#5	40	—	H2	3	I0202	I2202	J2202
#6	32	—	H3	3	I0243	I2243	J2243
#6	32	—	H3	3	I0244	—	J2244
#6	32	—	H4	3	I0245	—	J2245
#6	32	—	H7	3	I0247	—	J2247
#6	—	40	H2	3	I0262	—	J2262
#6	—	40	H3	3	I0263	—	J2263
#8	32	—	H2	3	I0282	—	J2282
#8	32	—	H3	3	I0283	I2283	J2283
#8	32	—	H4	3	I0284	—	J2284
#8	32	—	H5	3	I0285	—	J2286
#8	32	—	H7	3	I0287	—	J2287
#8	—	36	H2	3	I0302	—	J2302
#10	24	—	H3	3	I0323	I2323	J2323
#10	24	—	H4	3	I0324	—	J2324
#10	24	—	H5	3	I0325	—	J2325
#10	—	32	H2	3	I0342	—	J2342
#10	—	32	H3	3	I0343	I2343	J2343
#10	—	32	H4	3	I0344	—	J2344

Refer to technical data on page 520~554.

NEXT PAGE

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎			◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL POINT TAPS


10/I2/J2 SERIES

SPIRAL POINT TAPS PLUG STYLE for Stainless Steels

Thread Depth / Hole Type 3.0×D



USCTI



- VA
- HSSE-V3
- UNC UNF
- USCTI 302A
- 4P~5P
- Steam Oxide
- TiN
- Hardslick

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Steam Oxide	TiN	Hardslick
#10	—	32	H5	3	I0345	—	J2345
#10	—	32	H6	3	I0346	—	J2346
#10	—	32	H7	3	I0347	—	J2347
#12	24	—	H3	3	I0363	—	J2363
#12	—	28	H3	3	I0383	—	J2383
1/4	20	—	H2	3	I0402	—	J2402
1/4	20	—	H3	3	I0403	I2403	J2403
1/4	20	—	H5	3	I0405	I2405	J2405
1/4	20	—	H7	3	I0407	—	J2407
1/4	—	28	H2	3	I0422	—	J2422
1/4	—	28	H3	3	I0423	I2423	J2423
1/4	—	28	H4	3	I0424	—	J2424
1/4	—	28	H5	3	I0425	—	J2425
1/4	—	28	H6	3	I0426	—	J2426
1/4	—	28	H7	3	I0427	—	J2427
5/16	18	—	H3	3	I0443	I2443	J2443
5/16	18	—	H5	3	I0445	I2445	J2445
5/16	18	—	H7	3	I0447	—	J2447
5/16	—	24	H3	3	I0463	I2463	J2463
5/16	—	24	H4	3	I0464	—	J2464
5/16	—	24	H5	3	I0465	—	J2465
5/16	—	24	H6	3	I0466	—	J2466
5/16	—	24	H7	3	I0467	—	J2467
3/8	16	—	H3	3	I0483	I2483	J2483
3/8	16	—	H5	3	I0485	I2485	J2485
3/8	16	—	H7	3	I0487	—	J2487
3/8	—	24	H3	3	I0503	I2503	J2503
3/8	—	24	H4	3	I0504	—	J2504
3/8	—	24	H5	3	I0505	—	J2505
3/8	—	24	H7	3	I0507	—	J2507

Refer to technical data on page 520~554.

NEXT PAGE

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎			◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL POINT TAPS


10/12/J2 SERIES

SPIRAL POINT TAPS PLUG STYLE for Stainless Steels

Thread Depth / Hole Type 3.0×D



USCTI



- VA
- HSSE-V3
- UNC UNF
- USCTI 302A
- 4P~5P
- Steam Oxide
- TiN
- Hardslick

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Steam Oxide	TiN	Hardslick
7/16	14	—	H3	3	I0523	I2523	J2523
7/16	14	—	H5	3	I0525	I2525	J2525
7/16	—	20	H3	3	I0543	I2543	J2543
7/16	—	20	H5	3	I0545	I2545	J2545
1/2	13	—	H3	3	I0563	I2563	J2563
1/2	13	—	H5	3	I0565	I2565	J2565
1/2	13	—	H7	3	I0567	—	J2567
1/2	—	20	H3	3	I0583	I2583	J2583
1/2	—	20	H5	3	I0585	—	J2585
9/16	12	—	H3	3	I0603	I2603	J2603
9/16	—	18	H3	3	I0623	I2623	J2623
5/8	11	—	H3	3	I0643	I2643	J2643
5/8	11	—	H5	3	I0645	I2645	J2645
5/8	11	—	H7	3	I0647	—	J2647
5/8	—	18	H3	3	I0663	—	J2663
5/8	—	18	H5	3	I0665	I2665	J2665
5/8	—	18	H7	3	I0667	—	J2667
3/4	10	—	H3	3	I0703	I2703	J2703
3/4	—	16	H5	3	I0725	I2725	J2725
7/8	9	—	H4	3	I0744	I2744	J2744
7/8	—	14	H6	3	I0766	I2766	J2766
1	8	—	H4	3	I0784	I2784	J2784
1	—	12	H6	3	I0806	I2806	J2806

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎			◎						
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL POINT TAPS


09/1A SERIES

METRIC SPIRAL POINT TAPS PLUG STYLE for Stainless Steels

Thread Depth / Hole Type 3.0×D



USCTI



- VA
- HSSE-V3
- M MF
- USCTI 302A
- 4P~5P
- Steam Oxide
- Hardslick

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Steam Oxide	Hardslick
M3	0.5	D3	3	O9203	IA203
M3.5	0.6	D4	3	O9224	IA224
M4	0.7	D4	3	O9244	IA244
M5	0.8	D4	3	O9284	IA284
M6	1.0	D5	3	O9315	IA315
M7	1.0	D5	3	O9345	IA345
M8	1.25	D5	3	O9365	IA365
M8	1.0	D5	3	O9375	IA375
M10	1.5	D6	3	O9426	IA426
M10	1.25	D5	3	O9435	IA435
M12	1.75	D6	3	O9506	IA506
M12	1.25	D5	3	O9525	IA525
M14	2.0	D7	3	O9547	IA547
M14	1.5	D6	3	O9556	IA556
M16	2.0	D7	3	O9607	IA607
M16	1.5	D6	3	O9616	IA616
M18	2.5	D7	3	O9657	IA657
M18	1.5	D6	3	O9676	IA676

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎			◎						
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			

YG SPIRAL POINT TAPS


K3/K5/K6 SERIES

METRIC SPIRAL POINT TAPS PLUG STYLE for Stainless Steels

Thread Depth / Hole Type 3.0×D



DIN Length-ANSI Shank



- VA
- HSSE-V3
- M MF
- 4P~5P
- Steam Oxide
- TiCN
- Hardslick

SIZE	Pitch	Limit	No. of Flute	EDP No.		
				Steam Oxide	TiCN	Hardslick
M3	0.5	D3	3	K3203	K5203	K6203
M3.5	0.6	D4	3	K3224	K5224	K6224
M4	0.7	D4	3	K3244	K5244	K6244
M5	0.8	D4	3	K3284	K5284	K6284
M6	1.0	D5	3	K3315	K5315	K6315
M7	1.0	D5	3	K3345	K5345	K6345
M8	1.25	D5	3	K3365	K5365	K6365
M8	1.0	D5	3	K3375	K5375	K6375
M10	1.5	D6	3	K3426	K5426	K6426
M10	1.25	D5	3	K3435	K5435	K6435
M12	1.75	D6	3	K3506	K5506	K6506
M12	1.25	D5	3	K3525	K5525	K6525
M14	2.0	D7	3	K3547	K5547	K6547
M14	1.5	D6	3	K3556	K5556	K6556
M16	2.0	D7	3	K3607	K5607	K6607
M16	1.5	D6	3	K3616	K5616	K6616
M18	2.5	D7	3	K3657	K5657	K6657
M18	1.5	D6	3	K3676	K5676	K6676

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	◎			◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	○	○		○		○	○			○

YG SPIRAL POINT TAPS

J3/J4/J8 SERIES


SPIRAL POINT TAPS PLUG STYLE for Steels

A variety of H Limit

Thread Depth / Hole Type 3.0×D



USCTI



- VG
- HSSE-V3
- UNC UNF
- USCTI 302A
- 4P~5P
- Steam Oxide
- Bright
- Hardslick

SIZE	Thread Per Inch			Limit	No. of Flute	EDP No.		
	UNC	UNF	UN			Steam Oxide	Bright	Hardslick
#2	56	—	—	H2	2	J3082	J4082	J8082
#3	48	—	—	H2	2	J3122	J4122	J8122
#4	40	—	—	H2	2	J3162	J4162	J8162
#4	40	—	—	H3	2	J3163	J4163	J8163
#4	40	—	—	H4	2	J3164	J4164	J8164
#4	40	—	—	H5	2	J3165	J4165	J8165
#4	—	48	—	H2	2	J3182	J4182	J8182
#5	40	—	—	H2	2	J3202	J4202	J8202
#6	32	—	—	H2	2	J3242	J4242	J8242
#6	32	—	—	H3	2	J3243	J4243	J8243
#6	32	—	—	H4	2	J3244	J4244	J8244
#6	32	—	—	H5	2	J3245	J4245	J8245
#6	32	—	—	H6	2	J3246	J4246	J8246
#6	32	—	—	H7	2	J3247	J4247	J8247
#6	32	—	—	H11	2	J324A	J424A	J824A
#6	—	40	—	H2	2	J3262	J4262	J8262
#8	32	—	—	H2	3	J3282	J4282	J8282
#8	32	—	—	H3	3	J3283	J4283	J8283
#8	32	—	—	H4	3	J3284	J4284	J8284
#8	32	—	—	H5	3	J3285	J4285	J8285
#8	32	—	—	H6	3	J3286	J4286	J8286
#8	32	—	—	H7	3	J3287	J4287	J8287
#8	32	—	—	H11	3	J328A	J428A	J828A
#8	—	36	—	H2	3	J3302	J4302	J8302
#10	24	—	—	H3	3	J3323	J4323	J8323
#10	24	—	—	H5	3	J3325	J4325	J8325
#10	24	—	—	H11	3	J332A	J432A	J832A
#10	—	32	—	H2	3	J3342	J4342	J8342
#10	—	32	—	H3	3	J3343	J4343	J8343
#10	—	32	—	H4	3	J3344	J4344	J8344

▶ Refer to technical data on page 520~554.

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
	◎			○						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
										○


YG SPIRAL POINT TAPS

J3/J4/J8 SERIES


SPIRAL POINT TAPS PLUG STYLE for Steels

A variety of H Limit

Thread Depth / Hole Type 3.0×D



USCTI



- VG
- HSSE-V3
- UNC UNF
- USCTI 302A
- 4P~5P
- Steam Oxide
- Bright
- Hardslick

SIZE	Thread Per Inch			Limit	No. of Flute	EDP No.		
	UNC	UNF	UN			Steam Oxide	Bright	Hardslick
#10	—	32	—	H5	3	J3345	J4345	J8345
#10	—	32	—	H6	3	J3346	J4346	J8346
#10	—	32	—	H7	3	J3347	J4347	J8347
#10	—	32	—	H11	3	J334A	J434A	J834A
#12	24	—	—	H3	3	J3363	J4363	J8363
#12	—	28	—	H3	3	J3383	J4383	J8383
1/4	20	—	—	H2	3	J3402	J4402	J8402
1/4	20	—	—	H3	3	J3403	J4403	J8403
1/4	20	—	—	H5	3	J3405	J4405	J8405
1/4	20	—	—	H7	3	J3407	J4407	J8407
1/4	20	—	—	H11	3	J340A	J440A	J840A
1/4	—	28	—	H2	3	J3422	J4422	J8422
1/4	—	28	—	H3	3	J3423	J4423	J8423
1/4	—	28	—	H4	3	J3424	J4424	J8424
1/4	—	28	—	H5	3	J3425	J4425	J8425
1/4	—	28	—	H6	3	J3426	J4426	J8426
1/4	—	28	—	H7	3	J3427	J4427	J8427
1/4	—	28	—	H11	3	J342A	J442A	J842A
5/16	18	—	—	H3	3	J3443	J4443	J8443
5/16	18	—	—	H5	3	J3445	J4445	J8445
5/16	18	—	—	H7	3	J3447	J4447	J8447
5/16	18	—	—	H11	3	J344A	J444A	J844A
5/16	—	24	—	H2	3	J3462	J4462	J8462
5/16	—	24	—	H3	3	J3463	J4463	J8463
5/16	—	24	—	H4	3	J3464	J4464	J8464
5/16	—	24	—	H5	3	J3465	J4465	J8465
5/16	—	24	—	H6	3	J3466	J4466	J8466
5/16	—	24	—	H7	3	J3467	J4467	J8467
5/16	—	24	—	H11	3	J346A	J446A	J846A
3/8	16	—	—	H3	3	J3483	J4483	J8483

▶ Refer to technical data on page 520~554.

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
	◎	◎		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
									○	


YG SPIRAL POINT TAPS

J3/J4/J8 SERIES


SPIRAL POINT TAPS PLUG STYLE for Steels

A variety of H Limit

Thread Depth / Hole Type 3.0×D



USCTI



- VG
- HSSE-V3
- UNC UNF
- USCTI 302A
- 4P~5P
- Steam Oxide
- Bright
- Hardslick

SIZE	Thread Per Inch			Limit	No. of Flute	EDP No.		
	UNC	UNF	UN			Steam Oxide	Bright	Hardslick
3/8	16	—	—	H5	3	J3485	J4485	J8485
3/8	16	—	—	H7	3	J3487	J4487	J8487
3/8	16	—	—	H11	3	J348A	J448A	J848A
3/8	—	24	—	H2	3	J3502	J4502	J8502
3/8	—	24	—	H3	3	J3503	J4503	J8503
3/8	—	24	—	H4	3	J3504	J4504	J8504
3/8	—	24	—	H5	3	J3505	J4505	J8505
3/8	—	24	—	H6	3	J3506	J4506	J8506
3/8	—	24	—	H7	3	J3507	J4507	J8507
3/8	—	24	—	H11	3	J350A	J450A	J850A
7/16	14	—	—	H3	3	J3523	J4523	J8523
7/16	14	—	—	H5	3	J3525	J4525	J8525
7/16	14	—	—	H7	3	J3527	J4527	J8527
7/16	14	—	—	H11	3	J352A	J452A	J852A
7/16	—	20	—	H3	3	J3543	J4543	J8543
7/16	—	20	—	H5	3	J3545	J4545	J8545
7/16	—	20	—	H7	3	J3547	J4547	J8547
7/16	—	20	—	H11	3	J354A	J454A	J854A
1/2	13	—	—	H3	3	J3563	J4563	J8563
1/2	13	—	—	H5	3	J3565	J4565	J8565
1/2	13	—	—	H7	3	J3567	J4567	J8567
1/2	13	—	—	H11	3	J356A	J456A	J856A
1/2	—	20	—	H2	3	J3582	J4582	J8582
1/2	—	20	—	H3	3	J3583	J4583	J8583
1/2	—	20	—	H5	3	J3585	J4585	J8585
1/2	—	20	—	H7	3	J3587	J4587	J8587
1/2	—	20	—	H11	3	J358A	J458A	J858A
9/16	12	—	—	H5	3	J3605	J4605	J8605
9/16	—	18	—	H5	3	J3625	J4625	J8625
5/8	11	—	—	H3	3	J3643	J4643	J8643

▶ Refer to technical data on page 520~554.

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
	◎	◎		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
									○	

YG SPIRAL POINT TAPS

J3/J4/J8 SERIES


SPIRAL POINT TAPS PLUG STYLE for Steels

A variety of H Limit

Thread Depth / Hole Type 3.0×D



USCTI



- VG
- HSSE-V3
- UNC UNF
- USCTI 302A
- 4P~5P
- Steam Oxide
- Bright
- Hardslick

SIZE	Thread Per Inch			Limit	No. of Flute	EDP No.		
	UNC	UNF	UN			Steam Oxide	Bright	Hardslick
5/8	11	—	—	H5	3	J3645	J4645	J8645
5/8	—	18	—	H3	3	J3663	J4663	J8663
5/8	—	18	—	H5	3	J3665	J4665	J8665
5/8	—	18	—	H7	3	J3667	J4667	J8667
3/4	10	—	—	H3	3	J3703	J4703	J8703
3/4	10	—	—	H5	3	J3705	J4705	J8705
3/4	—	16	—	H3	3	J3723	J4723	J8723
3/4	—	16	—	H5	3	J3725	J4725	J8725
7/8	9	—	—	H5	3	J3745	J4745	J8745
7/8	—	14	—	H4	3	J3764	J4764	J8764
1	8	—	—	H4	4	J3784	J4784	J8784
1	—	12	—	H4	4	J3804	J4804	J8804
1-1/8	7	—	—	H6	4	J3826	J4826	J8826
1-1/8	—	12	—	H5	4	J3845	J4845	J8845
1-1/8	—	—	8	H6	4	J3836	J4836	J8836
1-1/4	7	—	—	H6	4	J3866	J4866	J8866
1-1/4	—	12	—	H5	4	J3885	J4885	J8885
1-1/4	—	—	8	H6	4	J3876	J4876	J8876
1-3/8	6	—	—	H6	4	J3906	J4906	J8906
1-3/8	—	12	—	H5	4	J3925	J4925	J8925
1-3/8	—	—	8	H6	4	J3916	J4916	J8916
1-1/2	6	—	—	H6	4	J3946	J4946	J8946
1-1/2	—	12	—	H5	4	J3965	J4965	J8965
1-1/2	—	—	8	H6	4	J3956	J4956	J8956

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
	◎	◎		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
									○	

YG SPIRAL POINT TAPS

IB/IC SERIES


SPIRAL POINT TAPS PLUG STYLE for Steels

A variety of D Limit

Thread Depth / Hole Type 3.0×D



USCTI



- VG
- HSSE-V3
- M MF
- USCTI 302A
- 4P~5P
- Steam Oxide
- Hardslick

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Steam Oxide	Hardslick
M3	0.5	D3	3	IB203	IC203
M3	0.5	D11	3	IB20A	IC20A
M3.5	0.6	D4	3	IB224	IC224
M3.5	0.6	D11	3	IB22A	IC22A
M4	0.7	D4	3	IB244	IC244
M4	0.7	D11	3	IB24A	IC24A
M5	0.8	D4	3	IB284	IC284
M5	0.8	D11	3	IB28A	IC28A
M6	1.0	D5	3	IB315	IC315
M6	1.0	D11	3	IB31A	IC31A
M7	1.0	D5	3	IB345	IC345
M7	1.0	D11	3	IB34A	IC34A
M8	1.0	D5	3	IB375	IC375
M8	1.0	D11	3	IB37A	IC37A
M8	1.25	D5	3	IB365	IC365
M8	1.25	D11	3	IB36A	IC36A
M10	1.0	D5	3	IB445	IC445
M10	1.0	D11	3	IB44A	IC44A
M10	1.25	D5	3	IB435	IC435
M10	1.25	D11	3	IB43A	IC43A
M10	1.5	D6	3	IB426	IC426
M10	1.5	D11	3	IB42A	IC42A
M12	1.25	D5	3	IB525	IC525
M12	1.25	D11	3	IB52A	IC52A
M12	1.5	D6	3	IB516	IC516
M12	1.5	D11	3	IB51A	IC51A
M12	1.75	D6	3	IB506	IC506
M12	1.75	D11	3	IB50A	IC50A
M14	1.5	D6	3	IB556	IC556
M14	2.0	D7	3	IB547	IC547

▶ Refer to technical data on page 520~554.

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
	◎	◎		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
									○	


YG SPIRAL POINT TAPS

IB/IC SERIES


METRIC SPIRAL POINT TAPS PLUG STYLE for Steels

A variety of D Limit

Thread Depth / Hole Type 3.0×D



USCTI



- VG
- HSSE-V3
- M MF
- USCTI 302A
- 4P~5P
- Steam Oxide
- Hardslick

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Steam Oxide	Hardslick
M16	1.5	D6	3	IB616	IC616
M16	2.0	D7	3	IB607	IC607
M18	1.5	D6	4	IB676	IC676
M18	2.5	D7	4	IB657	IC657
M20	1.5	D6	3	IB726	IC726
M20	2.5	D8	3	IB708	IC708
M22	1.5	D6	3	IB766	IC766
M22	2.5	D8	3	IB748	IC748
M24	1.5	D6	4	IB806	IC806
M24	3.0	D8	4	IB788	IC788
M27	1.5	D6	4	IB886	IC886
M27	3.0	D8	4	IB868	IC868
M30	1.5	D6	4	IB976	IC976
M30	3.5	D9	4	IB949	IC949

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
	◎	◎		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
										○

YG SPIRAL POINT TAPS


J9/K7/K2 SERIES

METRIC SPIRAL POINT TAPS PLUG STYLE for Steels

Thread Depth / Hole Type 3.0×D



DIN Length-ANSI Shank



- VG
- HSSE-V3
- M MF
- 4P~5P
- Steam Oxide
- TiCN
- Hardslick

SIZE	Pitch	Limit	No. of Flute	EDP No.		
				Steam Oxide	TiCN	Hardslick
M3	0.5	D3	3	J9203	K7203	K2203
M3.5	0.6	D4	3	J9224	K7224	K2224
M4	0.7	D4	3	J9244	K7244	K2244
M5	0.8	D4	3	J9284	K7284	K2284
M6	1.0	D5	3	J9315	K7315	K2315
M7	1.0	D5	3	J9345	K7345	K2345
M8	1.25	D5	3	J9365	K7365	K2365
M8	1.0	D5	3	J9375	K7375	K2375
M10	1.5	D6	3	J9426	K7426	K2426
M10	1.25	D5	3	J9435	K7435	K2435
M12	1.75	D6	3	J9506	K7506	K2506
M12	1.25	D5	3	J9525	K7525	K2525
M14	2.0	D7	3	J9547	K7547	K2547
M14	1.5	D6	3	J9556	K7556	K2556
M16	2.0	D7	3	J9607	K7607	K2607
M16	1.5	D6	3	J9616	K7616	K2616
M18	2.5	D7	4	J9657	K7657	K2657
M18	1.5	D6	4	J9676	K7676	K2676

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
	◎	◎		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
										○

YG SPIRAL POINT TAPS


T2496 SERIES

SPIRAL POINT TAPS PLUG STYLE
for Aluminum Alloys or Die Cast Aluminum

Thread Depth / Hole Type 3.0×D



USCTI



- AI
- HSSE-V3
- UNC UNF
- USCTI 302A
- 4P~5P
- Bright

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.
	UNC	UNF			
#4	40	—	H2	2	T2496162
#4	40	—	H3	2	T2496163
#6	32	—	H2	2	T2496242
#6	32	—	H3	2	T2496243
#8	32	—	H2	2	T2496282
#8	32	—	H3	2	T2496283
#10	24	—	H3	2	T2496323
#10	—	32	H2	2	T2496342
#10	—	32	H3	2	T2496343
#10	—	32	H5	2	T2496345
1/4	20	—	H3	2	T2496403
1/4	20	—	H5	2	T2496405
1/4	—	28	H3	2	T2496423
5/16	18	—	H3	2	T2496443
5/16	18	—	H5	2	T2496445
5/16	—	24	H3	2	T2496463
5/16	—	24	H5	2	T2496465
3/8	16	—	H3	3	T2496483
3/8	16	—	H5	3	T2496485
3/8	—	24	H3	3	T2496503
3/8	—	24	H5	3	T2496505
1/2	13	—	H3	3	T2496563
1/2	13	—	H5	3	T2496565
1/2	—	20	H3	3	T2496583
5/8	11	—	H3	3	T2496643
5/8	—	18	H3	3	T2496663
3/4	10	—	H3	3	T2496703
3/4	—	16	H3	3	T2496723
7/8	9	—	H4	3	T2496744
7/8	—	14	H4	3	T2496764
1	1	—	H4	3	T2496784

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron	
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)	
K		N				S		
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc / Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286 / Titanium
~HRc24 (~HB250)								
				◎	◎			

YG SPIRAL POINT TAPS


T2K01 SERIES

METRIC SPIRAL POINT TAPS PLUG STYLE
for Aluminum Alloys or Die Cast Aluminum

Thread Depth / Hole Type 3.0×D



USCTI



- AI
- HSSE-V3
- M MF
- USCTI 302A
- 4P~5P
- Bright

SIZE	Pitch	Limit	No. of Flute	EDP No.
M3	0.5	D3	2	T2K01203
M4	0.7	D4	2	T2K01244
M5	0.8	D4	2	T2K01284
M6	1.0	D5	2	T2K01315
M8	1.25	D5	2	T2K01365
M10	1.25	D5	3	T2K01435
M10	1.5	D6	3	T2K01426
M12	1.25	D5	3	T2K01525
M12	1.5	D5	3	T2K01515
M12	1.75	D6	3	T2K01506

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron	
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)	
K		N				S		
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc / Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286 / Titanium
~HRc24 (~HB250)								
				◎	◎			

YG SPIRAL POINT TAPS

I9/J0/J1/J7 SERIES

STANDARD TAPS : SPIRAL POINT PLUG STYLE for General Purpose



- GS
- HSSE-V3
- UNC UNF
- USCTI 302
- 4P~5P
- Steam Oxide
- Bright
- TiN
- Hardslick

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.			
	UNC	UNF			Steam Oxide	Bright	TiN	Hardslick
#2	56	—	H2	2	I9082	J0082	J1082	J7082
#4	40	—	H2	2	I9162	J0162	J1162	J7162
#5	40	—	H2	2	I9202	J0202	J1202	J7202
#6	32	—	H3	2	I9243	J0243	J1243	J7243
#8	32	—	H3	2	I9283	J0283	J1283	J7283
#10	24	—	H3	2	I9323	J0323	J1323	J7323
#10	—	32	H3	2	I9343	J0343	J1343	J7343
1/4	20	—	H3	2	I9403	J0403	J1403	J7403
1/4	20	—	H5	2	I9405	J0405	J1405	J7405
1/4	—	28	H3	2	I9423	J0423	J1423	J7423
5/16	18	—	H3	2	I9443	J0443	J1443	J7443
5/16	18	—	H5	2	I9445	J0445	J1445	J7445
5/16	—	24	H3	2	I9463	J0463	J1463	J7463
3/8	16	—	H3	3	I9483	J0483	J1483	J7483
3/8	16	—	H5	3	I9485	J0485	J1485	J7485
3/8	—	24	H3	3	I9503	J0503	J1503	J7503
7/16	14	—	H3	3	I9523	J0523	J1523	J7523
7/16	14	—	H5	3	I9525	J0525	J1525	J7525
7/16	—	20	H3	3	I9543	J0543	J1543	J7543
7/16	—	20	H5	3	I9545	J0545	J1545	J7545
1/2	13	—	H3	3	I9563	J0563	J1563	J7563
1/2	13	—	H5	3	I9565	J0565	J1565	J7565
1/2	—	20	H3	3	I9583	J0583	J1583	J7583
1/2	—	20	H5	3	I9585	J0585	J1585	J7585
9/16	12	—	H3	3	I9603	J0603	J1603	J7603
9/16	—	18	H5	3	I9625	J0625	J1625	J7625
5/8	11	—	H3	3	I9643	J0643	J1643	J7643
5/8	11	—	H5	3	I9645	J0645	J1645	J7645
5/8	—	18	H5	3	I9665	J0665	J1665	J7665
3/4	10	—	H3	3	I9703	J0703	J1703	J7703
3/4	10	—	H5	3	I9705	J0705	J1705	J7705
3/4	—	16	H5	3	I9725	J0725	J1725	J7725
7/8	9	—	H4	3	I9744	J0744	J1744	J7744
7/8	—	14	H6	3	I9766	J0766	J1766	J7766
1	8	—	H4	3	I9784	J0784	J1784	J7784

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K			
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)	◎	○		
K		N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium	○

YG SPIRAL POINT TAPS

K9/L0/L1 SERIES

SPIRAL POINT TAPS PLUG STYLE for General Purpose



- GS
- HSS-V
- UNC UNF
- USCTI 302A
- 4P~5P
- Bright
- TiN
- Hardslick

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Bright	TiN	Hardslick
#2	56	—	H2	2	K9082	L0082	L1082
#4	40	—	H2	2	K9162	L0162	L1162
#5	40	—	H2	2	K9202	L0202	L1202
#6	32	—	H3	2	K9243	L0243	L1243
#8	32	—	H3	2	K9283	L0283	L1283
#10	24	—	H3	2	K9323	L0323	L1323
#10	—	32	H3	2	K9343	L0343	L1343
1/4	20	—	H3	2	K9403	L0403	L1403
1/4	20	—	H5	2	K9405	L0405	L1405
1/4	—	28	H3	3	K9423	L0423	L1423
5/16	18	—	H3	2	K9443	L0443	L1443
5/16	18	—	H5	3	K9445	L0445	L1445
5/16	—	24	H3	3	K9463	L0463	L1463
3/8	16	—	H3	3	K9483	L0483	L1483
3/8	16	—	H5	3	K9485	L0485	L1485
3/8	—	24	H3	3	K9503	L0503	L1503
7/16	14	—	H3	3	K9523	L0523	L1523
7/16	14	—	H5	3	K9525	L0525	L1525
7/16	—	20	H3	3	K9543	L0543	L1543
7/16	—	20	H5	3	K9545	L0545	L1545
1/2	13	—	H3	3	K9563	L0563	L1563
1/2	13	—	H5	3	K9565	L0565	L1565
1/2	—	20	H3	3	K9583	L0583	L1583
1/2	—	20	H5	3	K9585	L0585	L1585
9/16	12	—	H3	3	K9603	L0603	L1603
9/16	—	18	H3	3	K9623	L0623	L1623
9/16	—	18	H5	3	K9625	L0625	L1625
5/8	11	—	H3	3	K9643	L0643	L1643
5/8	11	—	H5	3	K9645	L0645	L1645
5/8	—	18	H3	3	K9663	L0663	L1663
5/8	—	18	H5	3	K9665	L0665	L1665
3/4	10	—	H3	3	K9703	L0703	L1703
3/4	10	—	H5	3	K9705	L0705	L1705
3/4	—	16	H3	3	K9723	L0723	L1723
3/4	—	16	H5	3	K9725	L0725	L1725
7/8	9	—	H6	3	K9746	L0746	L1746
7/8	—	14	H4	3	K9764	L0764	L1764
7/8	—	14	H6	3	K9766	L0766	L1766
1	8	—	H6	3	K9786	L0786	L1786
1	—	12	H6	3	K9806	L0806	L1806

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K			
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)	◎	○		
K		N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium	○

YG SPIRAL POINT TAPS


L7/L8/L9 SERIES

METRIC SPIRAL POINT TAPS PLUG STYLE for General Purpose

Thread Depth / Hole Type 3.0×D



USCTI



- GS
- HSS-V
- M MF
- USCTI 302A
- 4P~5P
- Bright
- TiCN
- Hardslick

SIZE	Pitch	Limit	No. of Flute	EDP No.		
				Bright	TiCN	Hardslick
M3	0.5	D3	2	L7203	L8203	L9203
M3.5	0.6	D4	2	L7224	L8224	L9224
M4	0.7	D4	2	L7244	L8244	L9244
M5	0.8	D4	2	L7284	L8284	L9284
M6	1.0	D5	3	L7315	L8315	L9315
M7	1.0	D5	3	L7345	L8345	L9345
M8	1.25	D5	3	L7365	L8365	L9365
M8	1.0	D5	3	L7375	L8375	L9375
M10	1.5	D6	3	L7426	L8426	L9426
M10	1.25	D5	3	L7435	L8435	L9435
M12	1.75	D6	3	L7506	L8506	L9506
M12	1.25	D5	3	L7525	L8525	L9525

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P			M				K			
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎	○		○	○					
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					

YG SPIRAL POINT TAPS


L3/L4/L5 SERIES

SPIRAL POINT TAPS PLUG STYLE for General Purpose

Thread Depth / Hole Type 3.0×D



DIN Length-ANSI Shank



- GS
- HSS-V
- UNC UNF
- 4P~5P
- Bright
- TiN
- Hardslick

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Bright	TiN	Hardslick
#2	56	—	H2	2	L3082	L4082	L5082
#4	40	—	H2	2	L3162	L4162	L5162
#5	40	—	H2	3	L3202	L4202	L5202
#6	32	—	H3	3	L3243	L4243	L5243
#8	32	—	H3	3	L3283	L4283	L5283
#10	24	—	H3	3	L3323	L4323	L5323
#10	—	32	H3	3	L3343	L4343	L5343
1/4	20	—	H3	3	L3403	L4403	L5403
1/4	20	—	H5	3	L3405	L4405	L5405
1/4	—	28	H3	3	L3423	L4423	L5423
5/16	18	—	H3	3	L3443	L4443	L5443
5/16	18	—	H5	3	L3445	L4445	L5445
5/16	—	24	H3	3	L3463	L4463	L5463
3/8	16	—	H3	3	L3483	L4483	L5483
3/8	16	—	H5	3	L3485	L4485	L5485
3/8	—	24	H3	3	L3503	L4503	L5503
7/16	14	—	H3	3	L3523	L4523	L5523
7/16	14	—	H5	3	L3525	L4525	L5525
7/16	—	20	H3	3	L3543	L4543	L5543
7/16	—	20	H5	3	L3545	L4545	L5545
1/2	13	—	H3	3	L3563	L4563	L5563
1/2	13	—	H5	3	L3565	L4565	L5565
1/2	—	20	H3	3	L3583	L4583	L5583
1/2	—	20	H5	3	L3585	L4585	L5585
9/16	12	—	H5	3	L3605	L4605	L5605
9/16	—	18	H5	3	L3625	L4625	L5625
5/8	11	—	H3	3	L3643	L4643	L5643
5/8	11	—	H5	3	L3645	L4645	L5645
3/4	10	—	H3	3	L3703	L4703	L5703
3/4	10	—	H5	3	L3705	L4705	L5705
3/4	—	16	H5	3	L3725	L4725	L5725
7/8	9	—	H6	3	L3746	L4746	L5746
7/8	—	14	H6	3	L3766	L4766	L5766
1	8	—	H6	3	L3786	L4786	L5786
1	—	12	H6	3	L3806	L4806	L5806

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P			M				K			
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎	○		○	○					
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					

YG SPIRAL POINT TAPS


T7216 / T6216 / T8216 SERIES
T7C16 / T6C16 / T8C16 SERIES

STANDARD TAPS : SPIRAL POINT PLUG STYLE
for General Purpose

Thread Depth / Hole Type 3.0×D



USCTI



- GS HSS UNC UNF USCTI 302 4P~5P Bright Steam Oxide TiN

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Bright	Steam Oxide	TiN
#0	—	80	H1	2	T7216021	T6216021	T8216021
#0	—	80	H2	2	T7216022	T6216022	T8216022
#0	—	80	H3	2	T7216023	T6216023	T8216023
#1	64	—	H1	2	T7216041	T6216041	T8216041
#1	64	—	H2	2	T7216042	T6216042	T8216042
#1	—	72	H1	2	T7216061	T6216061	T8216061
#1	—	72	H2	2	T7216062	T6216062	T8216062
#2	56	—	H1	2	T7216081	T6216081	T8216081
#2	56	—	H2	2	T7216082	T6216082	T8216082
#2	56	—	H3	2	T7216083	T6216083	T8216083
#2	56	—	H5	2	T7216085	T6216085	T8216085
#2	—	64	H1	2	T7216101	T6216101	T8216101
#2	—	64	H2	2	T7216102	T6216102	T8216102
#3	48	—	H1	2	T7216121	T6216121	T8216121
#3	48	—	H2	2	T7216122	T6216122	T8216122
#3	48	—	H3	2	T7216123	T6216123	T8216123
#3	48	—	H5	2	T7216125	T6216125	T8216125
#3	—	56	H1	2	T7216141	T6216141	T8216141
#3	—	56	H2	2	T7216142	T6216142	T8216142
#4	40	—	H1	2	T7216161	T6216161	T8216161
#4	40	—	H2	2	T7216162	T6216162	T8216162
#4	40	—	H3	2	T7216163	T6216163	T8216163
#4	40	—	H5	2	T7216165	T6216165	T8216165
#4	—	48	H1	2	T7216181	T6216181	T8216181
#4	—	48	H2	2	T7216182	T6216182	T8216182
#5	40	—	H1	2	T7216201	T6216201	T8216201
#5	40	—	H2	2	T7216202	T6216202	T8216202
#5	40	—	H5	2	T7216205	T6216205	T8216205
#5	—	44	H2	2	T7216222	T6216222	T8216222
#6	32	—	H1	2	T7216241	T6216241	T8216241
#6	32	—	H2	2	T7216242	T6216242	T8216242

▶ Refer to technical data on page 520~554.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎	○		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					

YG SPIRAL POINT TAPS


T7216 / T6216 / T8216 SERIES
T7C16 / T6C16 / T8C16 SERIES

STANDARD TAPS : SPIRAL POINT PLUG STYLE
for General Purpose

Thread Depth / Hole Type 3.0×D



USCTI



- GS HSS UNC UNF USCTI 302 4P~5P Bright Steam Oxide TiN

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Bright	Steam Oxide	TiN
#6	32	—	H3	2	T7216243	T6216243	T8216243
#6	32	—	H4	2	T7216244	T6216244	T8216244
#6	32	—	H5	2	T7216245	T6216245	T8216245
#6	32	—	H7	2	T7216247	T6216247	T8216247
#6	32	—	H3	3	T7C16243	T6C16243	T8C16243
#6	—	40	H1	2	T7216261	T6216261	T8216261
#6	—	40	H2	2	T7216262	T6216262	T8216262
#6	—	40	H5	2	T7216265	T6216265	T8216265
#8	32	—	H1	2	T7216281	T6216281	T8216281
#8	32	—	H2	2	T7216282	T6216282	T8216282
#8	32	—	H3	2	T7216283	T6216283	T8216283
#8	32	—	H4	2	T7216284	T6216284	T8216284
#8	32	—	H5	2	T7216285	T6216285	T8216285
#8	32	—	H7	2	T7216287	T6216287	T8216287
#8	32	—	H3	3	T7C16283	T6C16283	T8C16283
#8	—	36	H1	2	T7216301	T6216301	T8216301
#8	—	36	H2	2	T7216302	T6216302	T8216302
#10	24	—	H1	2	T7216321	T6216321	T8216321
#10	24	—	H2	2	T7216322	T6216322	T8216322
#10	24	—	H3	2	T7216323	T6216323	T8216323
#10	24	—	H4	2	T7216324	T6216324	T8216324
#10	24	—	H5	2	T7216325	T6216325	T8216325
#10	24	—	H7	2	T7216327	T6216327	T8216327
#10	24	—	H3	3	T7C16323	T6C16323	T8C16323
#10	—	32	H1	2	T7216341	T6216341	T8216341
#10	—	32	H2	2	T7216342	T6216342	T8216342
#10	—	32	H3	2	T7216343	T6216343	T8216343
#10	—	32	H4	2	T7216344	T6216344	T8216344
#10	—	32	H5	2	T7216345	T6216345	T8216345
#10	—	32	H7	2	T7216347	T6216347	T8216347
#10	—	32	H3	3	T7C16343	T6C16343	T8C16343
#12	24	—	H1	2	T7216361	T6216361	T8216361

▶ Refer to technical data on page 520~554.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎	○		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					

YG SPIRAL POINT TAPS


T7216 / T6216 / T8216 SERIES
T7C16 / T6C16 / T8C16 SERIES

STANDARD TAPS : SPIRAL POINT PLUG STYLE:
for General Purpose

Thread Depth / Hole Type 3.0×D



USCTI



- GS HSS UNC UNF USCTI 302 4P~5P Bright Steam Oxide TiN

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Bright	Steam Oxide	TiN
#12	24	—	H3	2	T7216363	T6216363	T8216363
#12	—	28	H3	2	T7216383	T6216383	T8216383
1/4	20	—	H1	2	T7216401	T6216401	T8216401
1/4	20	—	H2	2	T7216402	T6216402	T8216402
1/4	20	—	H3	2	T7216403	T6216403	T8216403
1/4	20	—	H5	2	T7216405	T6216405	T8216405
1/4	20	—	H3	3	T7C16403	T6C16403	T8C16403
1/4	20	—	H5	3	T7C16405	T6C16405	T8C16405
1/4	—	28	H1	2	T7216421	T6216421	T8216421
1/4	—	28	H2	2	T7216422	T6216422	T8216422
1/4	—	28	H3	2	T7216423	T6216423	T8216423
1/4	—	28	H4	2	T7216424	T6216424	T8216424
1/4	—	28	H2	3	T7C16422	T6C16422	T8C16422
1/4	—	28	H4	3	T7C16424	T6C16424	T8C16424
5/16	18	—	H1	2	T7216441	T6216441	T8216441
5/16	18	—	H2	2	T7216442	T6216442	T8216442
5/16	18	—	H3	2	T7216443	T6216443	T8216443
5/16	18	—	H5	2	T7216445	T6216445	T8216445
5/16	18	—	H3	3	T7C16443	T6C16443	T8C16443
5/16	18	—	H5	3	T7C16445	T6C16445	T8C16445
5/16	—	24	H1	2	T7216461	T6216461	T8216461
5/16	—	24	H2	2	T7216462	T6216462	T8216462
5/16	—	24	H3	2	T7216463	T6216463	T8216463
5/16	—	24	H4	2	T7216464	T6216464	T8216464
5/16	—	24	H2	3	T7C16462	T6C16462	T8C16462
5/16	—	24	H4	3	T7C16464	T6C16464	T8C16464
3/8	16	—	H1	3	T7216481	T6216481	T8216481
3/8	16	—	H2	3	T7216482	T6216482	T8216482
3/8	16	—	H3	3	T7216483	T6216483	T8216483
3/8	16	—	H5	3	T7216485	T6216485	T8216485
3/8	—	24	H1	3	T7216501	T6216501	T8216501
3/8	—	24	H2	3	T7216502	T6216502	T8216502

▶ Refer to technical data on page 520~554.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎	○		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					

YG SPIRAL POINT TAPS


T7216 / T6216 / T8216 SERIES
T7C16 / T6C16 / T8C16 SERIES

STANDARD TAPS : SPIRAL POINT PLUG STYLE
for General Purpose

Thread Depth / Hole Type 3.0×D



USCTI



- GS HSS UNC UNF USCTI 302 4P~5P Bright Steam Oxide TiN

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.		
	UNC	UNF			Bright	Steam Oxide	TiN
3/8	—	24	H3	3	T7216503	T6216503	T8216503
3/8	—	24	H4	3	T7216504	T6216504	T8216504
7/16	14	—	H2	3	T7216522	T6216522	T8216522
7/16	14	—	H3	3	T7216523	T6216523	T8216523
7/16	14	—	H5	3	T7216525	T6216525	T8216525
7/16	—	20	H2	3	T7216542	T6216542	T8216542
7/16	—	20	H3	3	T7216543	T6216543	T8216543
7/16	—	20	H5	3	T7216545	T6216545	T8216545
1/2	13	—	H1	3	T7216561	T6216561	T8216561
1/2	13	—	H2	3	T7216562	T6216562	T8216562
1/2	13	—	H3	3	T7216563	T6216563	T8216563
1/2	13	—	H5	3	T7216565	T6216565	T8216565
1/2	—	20	H1	3	T7216581	T6216581	T8216581
1/2	—	20	H2	3	T7216582	T6216582	T8216582
1/2	—	20	H3	3	T7216583	T6216583	T8216583
1/2	—	20	H5	3	T7216585	T6216585	T8216585
9/16	12	—	H3	3	T7216603	T6216603	T8216603
9/16	12	—	H5	3	T7216605	T6216605	T8216605
9/16	—	18	H3	3	T7216623	T6216623	T8216623
9/16	—	18	H5	3	T7216625	T6216625	T8216625
5/8	11	—	H3	3	T7216643	T6216643	T8216643
5/8	11	—	H5	3	T7216645	T6216645	T8216645
5/8	—	18	H3	3	T7216663	T6216663	T8216663
5/8	—	18	H5	3	T7216665	T6216665	T8216665
3/4	10	—	H3	3	T7216703	T6216703	T8216703
3/4	10	—	H5	3	T7216705	T6216705	T8216705
3/4	—	16	H3	3	T7216723	T6216723	T8216723
3/4	—	16	H5	3	T7216725	T6216725	T8216725

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎	○		○	○					
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					

YG SPIRAL POINT TAPS


T7256/T6256 SERIES

STANDARD TAPS : SPIRAL POINT BOTTOMING STYLE for General Purpose

Thread Depth / Hole Type 3.0×D



USCTI



- GS HSS UNC UNF USCTI 302 1.5P~2P Bright Steam Oxide

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.	
	UNC	UNF			Bright	Steam Oxide
#0	—	80	H1	2	T7256021	T6256021
#0	—	80	H2	2	T7256022	T6256022
#1	64	—	H2	2	T7256042	T6256042
#1	—	72	H1	2	T7256061	T6256061
#1	—	72	H2	2	T7256062	T6256062
#2	56	—	H1	2	T7256081	T6256081
#2	56	—	H2	2	T7256082	T6256082
#3	48	—	H2	2	T7256122	T6256122
#3	—	56	H2	2	T7256142	T6256142
#4	40	—	H2	2	T7256162	T6256162
#4	—	48	H2	2	T7256182	T6256182
#5	40	—	H2	2	T7256202	T6256202
#5	—	44	H2	2	T7256222	T6256222
#6	32	—	H2	2	T7256242	T6256242
#6	32	—	H3	2	T7256243	T6256243
#6	32	—	H7	2	T7256247	T6256247
#6	—	40	H2	2	T7256262	T6256262
#8	32	—	H2	2	T7256282	T6256282
#8	32	—	H3	2	T7256283	T6256283
#8	32	—	H7	2	T7256287	T6256287
#8	—	36	H2	2	T7256302	T6256302
#10	24	—	H2	2	T7256322	T6256322
#10	24	—	H3	2	T7256323	T6256323
#10	—	32	H1	2	T7256341	T6256341
#10	—	32	H2	2	T7256342	T6256342
#10	—	32	H3	2	T7256343	T6256343
#12	24	—	H3	2	T7256363	T6256363
#12	—	28	H3	2	T7256383	T6256383
1/4	20	—	H3	2	T7256403	T6256403

▶ Refer to technical data on page 520~554.

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎	○		○	○					
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					

YG SPIRAL POINT TAPS


T7256/T6256 SERIES

STANDARD TAPS : SPIRAL POINT BOTTOMING STYLE for General Purpose

Thread Depth / Hole Type 3.0×D



USCTI



- GS HSS UNC UNF USCTI 302 1.5P~2P Bright Steam Oxide

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.	
	UNC	UNF			Bright	Steam Oxide
1/4	—	28	H2	2	T7256422	T6256422
1/4	—	28	H3	2	T7256423	T6256423
5/16	18	—	H3	2	T7256443	T6256443
5/16	—	24	H3	2	T7256463	T6256463
3/8	16	—	H3	3	T7256483	T6256483
3/8	—	24	H3	3	T7256503	T6256503
7/16	14	—	H3	3	T7256523	T6256523
7/16	—	20	H3	3	T7256543	T6256543
1/2	13	—	H3	3	T7256563	T6256563
1/2	—	20	H3	3	T7256583	T6256583
5/8	11	—	H3	3	T7256643	T6256643
5/8	—	18	H3	3	T7256663	T6256663
3/4	10	—	H3	3	T7256703	T6256703
3/4	—	16	H3	3	T7256723	T6256723

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎	○		○	○					
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
○					○					

YG SPIRAL POINT TAPS


T7217/T6217/T8217 SERIES

METRIC STANDARD TAPS : SPIRAL POINT PLUG STYLE
for General Purpose

Thread Depth / Hole Type 3.0×D



USCTI



- GS HSS M MF USCTI 302 4P~5P Bright Steam Oxide TIN

SIZE	Pitch	Limit	No. of Flute	EDP No.		
				Bright	Steam Oxide	TiN
M1.6	0.35	D3	2	T7217093	T6217093	T8217093
M2	0.40	D3	2	T7217133	T6217133	T8217133
M2.5	0.45	D3	2	T7217173	T6217173	T8217173
M3	0.50	D3	2	T7217203	T6217203	T8217203
M3.5	0.60	D4	2	T7217224	T6217224	T8217224
M4	0.70	D4	2	T7217244	T6217244	T8217244
M4.5	0.75	D4	2	T7217264	T6217264	T8217264
M5	0.80	D4	2	T7217284	T6217284	T8217284
M6	1.00	D5	2	T7217315	T6217315	T8217315
M7	1.00	D5	2	T7217345	T6217345	T8217345
M8	1.25	D5	2	T7217365	T6217365	T8217365
M8	1.00	D5	3	T7217375	T6217375	T8217375
M10	1.50	D6	3	T7217426	T6217426	T8217426
M10	1.25	D5	3	T7217435	T6217435	T8217435
M12	1.75	D6	3	T7217506	T6217506	T8217506
M12	1.25	D5	3	T7217525	T6217525	T8217525
M14	2.00	D7	3	T7217547	T6217547	T8217547
M14	1.50	D6	3	T7217556	T6217556	T8217556
M16	2.00	D7	3	T7217607	T6217607	T8217607
M16	1.50	D6	3	T7217616	T6217616	T8217616
M18	2.50	D7	3	T7217657	T6217657	T8217657
M20	2.50	D7	3	T7217707	T6217707	T8217707

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)	◎	○	
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
○					○					

YG SPIRAL POINT TAPS


T7226/T6226/T8226 SERIES

STANDARD TAPS : SPIRAL POINT PLUG STYLE
Oversize Tap

Thread Depth / Hole Type 3.0×D



USCTI



- GS HSS UNC UNF USCTI 302 4P~5P Bright Steam Oxide TiN +.005" oversize

SIZE	Thread Per Inch		No. of Flute	EDP No.		
	UNC	UNF		Bright	Steam Oxide	TiN
#6	32	—	2	T7226240	T6226240	T8226240
#8	32	—	2	T7226280	T6226280	T8226280
#10	24	—	2	T7226320	T6226320	T8226320
#10	—	32	2	T7226340	T6226340	T8226340
1/4	20	—	2	T7226400	T6226400	T8226400
1/4	—	28	2	T7226420	T6226420	T8226420
5/16	18	—	2	T7226440	T6226440	T8226440
5/16	—	24	2	T7226460	T6226460	T8226460
3/8	16	—	3	T7226480	T6226480	T8226480
3/8	—	24	3	T7226500	T6226500	T8226500
7/16	14	—	3	T7226520	T6226520	T8226520
7/16	—	20	3	T7226540	T6226540	T8226540
1/2	13	—	3	T7226560	T6226560	T8226560
1/2	—	20	3	T7226580	T6226580	T8226580
5/8	11	—	3	T7226640	T6226640	T8226640
3/4	10	—	3	T7226700	T6226700	T8226700

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)	◎	○	
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
○					○					

YG SPIRAL POINT TAPS


T7B17/T6B17/T8B17 SERIES

STANDARD TAPS : SPIRAL POINT PLUG STYLE
Oversize Tap

Thread Depth / Hole Type 3.0×D



USCTI



GS HSS M MF USCTI 302 4P~5P Bright Steam Oxide TIN +.127mm oversize

SIZE	Pitch	No. of Flute	EDP No.		
			Bright	Steam Oxide	TiN
M4	0.7	2	T7B17240	T6B17240	T8B17240
M5	0.8	2	T7B17280	T6B17280	T8B17280
M6	1	2	T7B17310	T6B17310	T8B17310
M8	1.25	2	T7B17360	T6B17360	T8B17360
M8	1	2	T7B17370	T6B17370	T8B17370
M10	1.5	3	T7B17420	T6B17420	T8B17420
M10	1.25	3	T7B17430	T6B17430	T8B17430
M12	1.75	3	T7B17500	T6B17500	T8B17500
M16	2	3	T7B17600	T6B17600	T8B17600

▶ Refer to technical data on page 520~554.

YG SPIRAL POINT TAPS


T7236/T6236/T8236 SERIES

T7G36/T6G36/T8G36 SERIES


SPIRAL POINTED TAP, 6" EXTENSION

Extended length for greater reach

Thread Depth / Hole Type 3.0×D



USCTI Long Shank



GS HSS UNC UNF USCTI Long Shank 4P~5P Bright Steam Oxide TIN

SIZE	Thread Per Inch		Limit	Overall Length	No. of Flutes	EDP No.		
	UNC	UNF				Bright	Steam Oxide	TiN
#6	32	—	H3	6	2	T7236243	T6236243	T8236243
#8	32	—	H3	6	2	T7236283	T6236283	T8236283
#10	24	—	H3	6	2	T7236323	T6236323	T8236323
#10	—	32	H3	6	2	T7236343	T6236343	T8236343
1/4	20	—	H3	6	2	T7236403	T6236403	T8236403
1/4	—	28	H3	6	2	T7236423	T6236423	T8236423
5/16	18	—	H3	6	2	T7236443	T6236443	T8236443
5/16	18	—	H3	6	3	T7G36443	T6G36443	T8G36443
5/16	—	24	H3	6	2	T7236463	T6236463	T8236463
5/16	—	24	H3	6	3	T7G36463	T6G36463	T8G36463
3/8	16	—	H3	6	3	T7236483	T6236483	T8236483
3/8	—	24	H3	6	3	T7236503	T6236503	T8236503
7/16	14	—	H3	6	3	T7236523	T6236523	T8236523
7/16	—	20	H3	6	3	T7236543	T6236543	T8236543
1/2	13	—	H3	6	3	T7236563	T6236563	T8236563
1/2	—	20	H3	6	3	T7236583	T6236583	T8236583
5/8	11	—	H3	6	3	T7236643	T6236643	T8236643

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K	
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)		
◎	◎	○		○	○				
K	N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
○				○					

◎ : Excellent ○ : Good

P				M				K	
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)		
◎	◎	○		○	○				
K	N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
○				○					



Global Cutting Tool Leader **YG-1**



CARBIDE & HSS



Being the best through innovation



STRAIGHT FLUTE TAPS

- Tapping Through & Blind Holes / Carbide, Super HSS & HSS

SELECTION GUIDE

STRAIGHT FLUTE TAPS

Tapping Through & Blind Holes / Carbide, Super HSS & HSS

INCH/METRIC


EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page
TOC01		Carbide	UNC/UNF	GG	USCTI 302A	2B	1.5 ~ 2P	2.0D	Bright	471
TR		Super HSS	UNC/UNF	GG	USCTI 302A	H	2 ~ 3P		TiAIN	472
			M/MF	GG		D	2 ~ 3P			
TR-A, TR-R		Super HSS	UNC/UNF	GG	USCTI 302A	H	2 ~ 3P		TiAIN	474
			M/MF	GG		D	2 ~ 3P			
T7316/T6316/ T8316/T7A16/ T7B16		HSS	UNC/ UNF/ UNS	GS	USCTI 302	H	9P/5P/2P		Bright Steam Oxide TiN	476
			M/MF	GS		D	9P/5P/2P			
T7315/T6315/ T8315		HSS	M/MF	GS	USCTI 302	D	9P/5P/2P		Bright Steam Oxide TiN	482
T7326		HSS	UNC/UNF	GS	USCTI 302	+ .005" oversize	5P/2P		Bright	483
T7B15		HSS	M/MF	GS	USCTI 302	+ .127mm oversize	5P/2P		Bright	484
T7336		HSS	UNC/UNF	GS	USCTI 302 (Left Hand)	H	5P/2P		Bright	485
T7A15		HSS	UNC/UNF	GS	USCTI 302 (Left Hand)	D	5P/2P		Bright	486
T7616/T6616/ T8616		HSS	UNC/UNF	GS	USCTI Long Shank	H	4 ~ 5P		Bright Steam Oxide TiN	487

STRAIGHT FLUTE TAPS


TOC01 SERIES

STRAIGHT FLUTE TAP BOTTOMING STYLE for Aluminum Alloy & Cast Iron

Thread Depth / Hole Type 2.0×D



USCTI



GG Carbide **UNC UNF** **USCTI 302A** **1.5P~2P** **Bright**

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.
	UNC	UNF			Bright
#10	24	—	2B	4	TOC01322
#10	—	32	2B	4	TOC01342
#12	24	—	2B	4	TOC01362
1/4	20	—	2B	4	TOC01402
1/4	—	28	2B	4	TOC01422
5/16	18	—	2B	4	TOC01442
5/16	—	24	2B	4	TOC01462
3/8	16	—	2B	4	TOC01482
3/8	—	24	2B	4	TOC01502

▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K	
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)		
							◎		
K	N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
○	◎				○				

HSS

CARBIDE

THREAD
MILLS

COMBO
TAPS

SPIRAL
FLUTE TAPS

SPIRAL
POINT TAPS

STRAIGHT
FLUTE TAPS

FORMING
TAPS

SCREW
THREAD
INSERT TAPS

PIPE TAPS

TECHNICAL
DATA

YG STRAIGHT FLUTE TAPS

TR SERIES

STRAIGHT FLUTE TAP MODIFIED BOTTOMING STYLE for Cast Iron



- GG
- Super HSS
- M/MF
- USCTI 302A
- 2P~3P
- TiAIN

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.	
	UNC	UNF			TiAIN	
#10	24	—	H3	4		TR323
#10	24	—	H5	4		TR325
#10	—	32	H3	4		TR343
1/4	20	—	H3	4		TR403
1/4	20	—	H5	4		TR405
1/4	—	28	H3	4		TR423
5/16	18	—	H3	4		TR443
5/16	18	—	H5	4		TR445
5/16	—	24	H3	4		TR463
3/8	16	—	H3	4		TR483
3/8	16	—	H5	4		TR485
3/8	—	24	H3	4		TR503
7/16	14	—	H3	4		TR523
7/16	14	—	H5	4		TR525
7/16	—	20	H3	4		TR543
7/16	—	20	H5	4		TR545
1/2	13	—	H3	4		TR563
1/2	13	—	H5	4		TR565
1/2	—	20	H3	4		TR583
1/2	—	20	H5	4		TR585
9/16	12	—	H3	4		TR603
9/16	12	—	H5	4		TR605
9/16	—	18	H3	4		TR623
9/16	—	18	H5	4		TR625
5/8	11	—	H3	4		TR643
5/8	11	—	H5	4		TR645
5/8	—	18	H3	4		TR663
5/8	—	18	H5	4		TR665
3/4	10	—	H3	4		TR703
3/4	10	—	H5	4		TR705
3/4	—	16	H3	4		TR723
3/4	—	16	H5	4		TR725

▶ Refer to technical data on page 520~554. ▶ NEXT PAGE

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)		~HRc19 (~HB220)		
								◎		
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
								◎		

YG STRAIGHT FLUTE TAPS

TR SERIES

METRIC STRAIGHT FLUTE TAP MODIFIED BOTTOMING STYLE for Cast Iron



- GG
- Super HSS
- M/MF
- USCTI 302A
- 2P~3P
- TiAIN

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				TiAIN	
M5	0.8	D4	4		TR284
M6	1	D5	4		TR315
M8	1.25	D5	4		TR365
M10	1.5	D6	4		TR426
M12	1.25	D6	4		TR526
M12	1.75	D6	4		TR506
M14	1.25	D6	4		TR566
M14	1.5	D6	4		TR556
M16	1.5	D6	4		TR616
M18	1.5	D6	4		TR676

▶ Refer to technical data on page 520~554.

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)		~HRc19 (~HB220)		
								◎		
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
								◎		

YG STRAIGHT FLUTE TAPS

TR-A, TR-R SERIES

STRAIGHT FLUTE TAP MODIFIED BOTTOMING STYLE for Cast Iron



GG Super HSS 2P~3P USCTI 302A

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.	
	UNC	UNF			Through Coolant Hole	Radial Coolant Hole
#10	24	—	H3	4	TR323A	TR323R
#10	24	—	H5	4	TR325A	TR325R
#10	—	32	H3	4	TR343A	TR343R
1/4	20	—	H3	4	TR403A	TR403R
1/4	20	—	H5	4	TR405A	TR405R
1/4	—	28	H3	4	TR423A	TR423R
5/16	18	—	H3	4	TR443A	TR443R
5/16	18	—	H5	4	TR445A	TR445R
5/16	—	24	H3	4	TR463A	TR463R
3/8	16	—	H3	4	TR483A	TR483R
3/8	16	—	H5	4	TR485A	TR485R
3/8	—	24	H3	4	TR503A	TR503R
7/16	14	—	H3	4	TR523A	TR523R
7/16	14	—	H5	4	TR525A	TR525R
7/16	—	20	H3	4	TR543A	TR543R
7/16	—	20	H5	4	TR545A	TR545R
1/2	13	—	H3	4	TR563A	TR563R
1/2	13	—	H5	4	TR565A	TR565R
1/2	—	20	H3	4	TR583A	TR583R
1/2	—	20	H5	4	TR585A	TR585R
9/16	12	—	H3	4	TR603A	TR603R
9/16	12	—	H5	4	TR605A	TR605R
9/16	—	18	H3	4	TR623A	TR623R
9/16	—	18	H5	4	TR625A	TR625R
5/8	11	—	H3	4	TR643A	TR643R
5/8	11	—	H5	4	TR645A	TR645R
5/8	—	18	H3	4	TR663A	TR663R
5/8	—	18	H5	4	TR665A	TR665R
3/4	10	—	H3	4	TR703A	TR703R
3/4	10	—	H5	4	TR705A	TR705R
3/4	—	16	H3	4	TR723A	TR723R
3/4	—	16	H5	4	TR725A	TR725R

▶ Refer to technical data on page 520~554. ▶ NEXT PAGE

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc24 (~HB250)	~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)		~HRc19 (~HB220)	◎	
								◎		
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										◎

YG STRAIGHT FLUTE TAPS

TR-A, TR-R SERIES

METRIC STRAIGHT FLUTE TAP MODIFIED BOTTOMING STYLE for Cast Iron



GG Super HSS M/MF USCTI 302A 2P~3P TiAlN

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Through Coolant Hole	Radial Coolant Hole
M5	0.8	D4	4	TR284A	TR284R
M6	1	D5	4	TR315A	TR315R
M8	1.25	D5	4	TR365A	TR365R
M10	1.5	D6	4	TR426A	TR426R
M12	1.25	D6	4	TR526A	TR526R
M12	1.75	D6	4	TR506A	TR506R
M14	1.25	D6	4	TR566A	TR566R
M14	1.5	D6	4	TR556A	TR556R
M16	1.5	D6	4	TR616A	TR616R
M18	1.5	D6	4	TR676A	TR676R

▶ Refer to technical data on page 520~554.

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc24 (~HB250)	~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)		~HRc19 (~HB220)	◎	
								◎		
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										◎



YG STRAIGHT FLUTE TAPS

T7316/T6316/T8316 SERIES


T7A16/T7B16 SERIES

HAND TAP TAPER, PLUG & BOTTOMING STYLE

Thread Depth / Hole Type 2.0xD



USCTI



GS **HSS** **UNC UNF UNS** **USCTI 302** **9P/5P/2P** **Bright** **Steam Oxide** **TiN**

SIZE	Thread Per Inch			Limit	No. of Flute	EDP No.							
	UNC	UNF	UNS			Bright			Steam Oxide			TiN	
						Taper	Plug	Bottoming	Taper	Plug	Bottoming	Plug	Bottoming
#0	—	80	—	H1	2	T7316026	T7316027	T7316028	T6316026	T6316027	T6316028	T8316027	T8316028
#0	—	80	—	H2	2	—	T7316027H2	T7316028H2	—	—	—	—	—
#1	64	—	—	H1	2	T7316046	T7316047	T7316048	T6316046	T6316047	T6316048	T8316047	T8316048
#1	64	—	—	H2	2	—	T7316047H2	T7316048H2	—	—	—	—	—
#1	—	72	—	H1	2	T7316066	T7316067	T7316068	T6316066	T6316067	T6316068	T8316067	T8316068
#1	—	72	—	H2	2	—	T7316067H2	T7316068H2	—	—	—	—	—
#2	56	—	—	H1	2	—	T7A16087H1	T7A16088H1	—	—	—	—	—
#2	56	—	—	H1	3	T7316086H1	T7316087H1	T7316088H1	—	—	—	—	—
#2	56	—	—	H2	2	—	T7A16087	T7A16088	—	—	—	—	—
#2	56	—	—	H2	3	T7316086	T7316087	T7316088	T6316086	T6316087	T6316088	T8316087	T8316088
#2	—	64	—	H2	3	T7316106	T7316107	T7316108	—	—	—	—	—
#3	48	—	—	H1	3	—	T7316127H1	—	—	—	—	—	—
#3	48	—	—	H2	2	—	T7A16127	T7A16128	—	—	—	—	—
#3	48	—	—	H2	3	T7316126	T7316127	T7316128	T6316126	T6316127	T6316128	—	—
#3	—	56	—	H2	3	T7316146	T7316147	T7316148	T6316146	T6316147	T6316148	—	—
#4	—	—	36	H2	3	T7316156	T7316157	T7316158	T6316156	T6316157	T6316158	—	—
#4	40	—	—	H1	2	—	T7A16167H1	T7A16168H1	—	—	—	—	—
#4	40	—	—	H1	3	T7316166H1	T7316167H1	T7316168H1	T6316166H1	T6316167H1	T6316168H1	—	—
#4	40	—	—	H2	2	—	T7A16167	T7A16168	—	—	—	—	—
#4	40	—	—	H2	3	T7316166	T7316167	T7316168	T6316166	T6316167	T6316168	T8316167	T8316168
#4	—	48	—	H1	3	—	T7316187H1	—	—	—	—	—	—
#4	—	48	—	H2	3	T7316186	T7316187	T7316188	—	—	—	—	—
#5	40	—	—	H1	3	—	T7316207H1	T7316208H1	—	—	—	—	—
#5	40	—	—	H2	2	—	T7A16207	T7A16208	—	—	—	—	—
#5	40	—	—	H2	3	T7316206	T7316207	T7316208	T6316206	T6316207	T6316208	T8316207	T8316208
#5	—	44	—	H2	3	T7316226	T7316227	T7316228	T6316226	T6316227	T6316228	—	—
#6	32	—	—	H1	2	—	T7A16247H1	T7A16248H1	—	—	—	—	—
#6	32	—	—	H1	3	T7316246H1	T7316247H1	T7316248H1	T6316246H1	T6316247H1	T6316248H1	—	—

▶ Refer to technical data on page 520~554.

▶ NEXT PAGE

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRC15 (~HB180)	~HRC23 (~HB240)	~HRC24 (~HB250) ~HRC38 (~HB350)	~HRC38 (~HB350) ~HRC44 (~HB420)	~HRC23 (~HB240)	~HRC24 (~HB250) ~HRC38 (~HB350)	~HRC38 (~HB350) ~HRC44 (~HB420)	~HRC19 (~HB220)			
◎	◎			◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRC24 (~HB250)										
	◎	◎		◎	◎	◎	◎			



YG STRAIGHT FLUTE TAPS

T7316/T6316/T8316 SERIES


T7A16/T7B16 SERIES

HAND TAP TAPER, PLUG & BOTTOMING STYLE

Thread Depth / Hole Type 2.0xD



USCTI



GS **HSS** **UNC UNF UNS** **USCTI 302** **9P/5P/2P** **Bright** **Steam Oxide** **TiN**

SIZE	Thread Per Inch			Limit	No. of Flute	EDP No.							
	UNC	UNF	UNS			Bright			Steam Oxide			TiN	
						Taper	Plug	Bottoming	Taper	Plug	Bottoming	Plug	Bottoming
#6	32	—	—	H2	2	—	T7A16247H2	T7A16248H2	—	—	—	—	—
#6	32	—	—	H2	3	T7316246H2	T7316247H2	T7316248H2	T6316246H2	T6316247H2	T6316248H2	—	—
#6	32	—	—	H3	2	—	T7A16247	T7A16248	—	—	—	—	—
#6	32	—	—	H3	3	T7316246	T7316247	T7316248	T6316246	T6316247	T6316248	T8316247	T8316248
#6	32	—	—	H7	3	—	T7B16247H7	T7B16248H7	—	—	—	—	—
#6	—	40	—	H1	3	—	T7B16267H1	—	—	—	—	—	—
#6	—	40	—	H2	2	—	T7A16267	T7A16268	—	—	—	—	—
#6	—	40	—	H2	3	T7316266	T7316267	T7316268	T6316266	T6316267	T6316268	T8316267	T8316268
#8	32	—	—	H1	2	—	T7A16287H1	—	—	—	—	—	—
#8	32	—	—	H1	4	T7316286H1	T7316287H1	T7316288H1	T6316286H1	T6316287H1	T6316288H1	—	—
#8	32	—	—	H2	2	—	T7A16287H2	T7A16288H2	—	—	—	—	—
#8	32	—	—	H2	3	—	T7B16287H2	T7B16288H2	—	—	—	—	—
#8	32	—	—	H2	4	T7316286H2	T7316287H2	T7316288H2	T6316286H2	T6316287H2	T6316288H2	—	—
#8	32	—	—	H3	2	—	T7A16287	T7A16288	—	—	—	—	—
#8	32	—	—	H3	3	—	T7B16287	T7B16288	—	—	—	—	—
#8	32	—	—	H3	4	T7316286	T7316287	T7316288	T6316286	T6316287	T6316288	T8316287	T8316288
#8	32	—	—	H7	3	—	T7B16287H7	T7B16288H7	—	—	—	—	—
#8	32	—	—	H7	4	—	T7316287H7	T7316288H7	—	—	—	—	—
#8	—	36	—	H2	4	T7316306	T7316307	T7316308	T6316306	T6316307	T6316308	T8316307	T8316308
#10	24	—	—	H1	4	T7316326H1	T7316327H1	T7316328H1	T6316326H1	T6316327H1	T6316328H1	—	—
#10	24	—	—	H2	2	—	T7A16327H2	T7A16328H2	—	—	—	—	—
#10	24	—	—	H2	3	—	T7B16327H2	—	—	—	—	—	—
#10	24	—	—	H2	4	T7316326H2	T7316327H2	T7316328H2	T6316326H2	T6316327H2	T6316328H2	—	—
#10	24	—	—	H3	2	—	T7A16327	T7A16328	—	—	—	—	—
#10	24	—	—	H3	3	—	T7B16327	T7B16328	—	—	—	—	—
#10	24	—	—	H3	4	T7316326	T7316327	T7316328	T6316326	T6316327	T6316328	T8316327	T8316328
#10	24	—	—	H7	3	—	T7B16327H7	T7B16328H7	—	—	—	—	—
#10	24	—	—	H7	4	—	T7316327H7	T7316328H7	—	—	—	—	—

▶ Refer to technical data on page 520~554.

▶ NEXT PAGE

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRC15 (~HB180)	~HRC23 (~HB240)	~HRC24 (~HB250) ~HRC38 (~HB350)	~HRC38 (~HB350) ~HRC44 (~HB420)	~HRC23 (~HB240)	~HRC24 (~HB250) ~HRC38 (~HB350)	~HRC38 (~HB350) ~HRC44 (~HB420)	~HRC19 (~HB220)			
◎	◎			◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRC24 (~HB250)										
	◎	◎		◎	◎	◎	◎			




YG STRAIGHT FLUTE TAPS

T7316/T6316/T8316 SERIES

T7A16/T7B16 SERIES

HAND TAP TAPER, PLUG & BOTTOMING STYLE

Thread Depth / Hole Type 2.0xD



USCTI

GS **HSS** **UNC UNF UNS** **USCTI 302** **9P/5P/2P** **Bright** **Steam Oxide** **TiN**

SIZE	Thread Per Inch			Limit	No. of Flute	EDP No.								
	UNC	UNF	UNS			Bright			Steam Oxide			TiN		
						Taper	Plug	Bottoming	Taper	Plug	Bottoming	Plug	Bottoming	
#10	—	32	—	H1	2	—	T7A16347H1	T7A16348H1	—	—	—	—	—	—
#10	—	32	—	H1	4	T7316346H1	T7316347H1	T7316348H1	T6316346H1	T6316347H1	T6316348H1	—	—	—
#10	—	32	—	H2	2	—	T7A16347H2	T7A16348H2	—	—	—	—	—	—
#10	—	32	—	H2	3	—	T7B16347H2	T7B16348H2	—	—	—	—	—	—
#10	—	32	—	H2	4	T7316346H2	T7316347H2	T7316348H2	T6316346H2	T6316347H2	T6316348H2	—	—	—
#10	—	32	—	H3	2	—	T7A16347	T7A16348	—	—	—	—	—	—
#10	—	32	—	H3	3	—	T7B16347	T7B16348	—	—	—	—	—	—
#10	—	32	—	H3	4	T7316346	T7316347	T7316348	T6316346	T6316347	T6316348	T8316347	T8316348	—
#10	—	32	—	H7	3	—	T7B16347H7	T7B16348H7	—	—	—	—	—	—
#10	—	32	—	H7	4	—	T7316347H7	T7316348H7	—	—	—	—	—	—
#12	24	—	—	H3	4	T7316366	T7316367	T7316368	T6316366	T6316367	T6316368	T8316367	T8316368	—
#12	—	28	—	H1	4	—	T7316387H1	—	—	—	—	—	—	—
#12	—	28	—	H3	4	T7316386	T7316387	T7316388	T6316386	T6316387	T6316388	T8316387	T8316388	—
1/4	20	—	—	H1	3	—	T7B16407H1	—	—	—	—	—	—	—
1/4	20	—	—	H1	4	T7316406H1	T7316407H1	T7316408H1	—	—	—	—	—	—
1/4	20	—	—	H2	3	—	T7B16407H2	T7B16408H2	—	—	—	—	—	—
1/4	20	—	—	H2	4	T7316406H2	T7316407H2	T7316408H2	—	—	—	—	—	—
1/4	20	—	—	H3	2	—	T7A16407	T7A16408	—	—	—	—	—	—
1/4	20	—	—	H3	3	—	T7B16407	T7B16408	—	—	—	—	—	—
1/4	20	—	—	H3	4	T7316406	T7316407	T7316408	T6316406	T6316407	T6316408	T8316407	T8316408	—
1/4	20	—	—	H5	3	—	T7B16407H5	T7B16408H5	—	—	—	—	—	—
1/4	20	—	—	H5	4	—	T7316407H5	T7316408H5	—	—	—	—	—	—
1/4	—	28	—	H1	4	—	T7316427H1	T7316428H1	—	—	—	—	—	—
1/4	—	28	—	H2	4	—	T7316427H2	T7316428H2	—	—	—	—	—	—
1/4	—	28	—	H3	2	—	T7A16427	T7A16428	—	—	—	—	—	—
1/4	—	28	—	H3	3	—	T7B16427	T7B16428	—	—	—	—	—	—
1/4	—	28	—	H3	4	T7316426	T7316427	T7316428	T6316426	T6316427	T6316428	T8316427	T8316428	—
1/4	—	28	—	H4	4	—	T7316427H4	T7316428H4	—	—	—	—	—	—

Refer to technical data on page 520~554.

NEXT PAGE

⊙ : Excellent ○ : Good

P				M				K								
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)	⊙	⊙							
K		N				S										
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium	⊙	⊙	⊙	⊙	⊙	⊙




YG STRAIGHT FLUTE TAPS

T7316/T6316/T8316 SERIES

T7A16/T7B16 SERIES

HAND TAP TAPER, PLUG & BOTTOMING STYLE

Thread Depth / Hole Type 2.0xD



USCTI

GS **HSS** **UNC UNF UNS** **USCTI 302** **9P/5P/2P** **Bright** **Steam Oxide** **TiN**

SIZE	Thread Per Inch			Limit	No. of Flute	EDP No.								
	UNC	UNF	UNS			Bright			Steam Oxide			TiN		
						Taper	Plug	Bottoming	Taper	Plug	Bottoming	Plug	Bottoming	
5/16	18	—	—	H1	4	—	T7316447H1	T7316448H1	—	—	—	—	—	—
5/16	18	—	—	H2	4	T7316446H2	T7316447H2	T7316448H2	T6316446H2	T6316447H2	T6316448H2	—	—	—
5/16	18	—	—	H3	2	—	T7A16447	T7A16448	—	—	—	—	—	—
5/16	18	—	—	H3	3	—	T7B16447	T7B16448	—	—	—	—	—	—
5/16	18	—	—	H3	4	T7316446	T7316447	T7316448	T6316446	T6316447	T6316448	T8316447	T8316448	—
5/16	18	—	—	H5	3	—	T7B16447H5	T7B16448H5	—	—	—	—	—	—
5/16	18	—	—	H5	4	—	T7316447H5	T7316448H5	—	—	—	—	—	—
5/16	—	24	—	H1	4	—	T7316467H1	T7316468H1	—	—	—	—	—	—
5/16	—	24	—	H2	4	—	T7316467H2	T7316468H2	—	—	—	—	—	—
5/16	—	24	—	H3	3	—	T7B16467	T7B16468	—	—	—	—	—	—
5/16	—	24	—	H3	4	T7316466	T7316467	T7316468	T6316466	T6316467	T6316468	T8316467	T8316468	—
5/16	—	24	—	H4	4	—	T7316467H4	T7316468H4	—	—	—	—	—	—
3/8	16	—	—	H1	3	—	T7B16487H1	T7B16488H1	—	—	—	—	—	—
3/8	16	—	—	H1	4	—	T7316487H1	T7316488H1	—	—	—	—	—	—
3/8	16	—	—	H2	4	—	T7316487H2	T7316488H2	—	—	—	—	—	—
3/8	16	—	—	H3	3	—	T7B16487	T7B16488	—	—	—	—	—	—
3/8	16	—	—	H3	4	T7316486	T7316487	T7316488	T6316486	T6316487	T6316488	T8316487	T8316488	—
3/8	16	—	—	H5	3	—	T7B16487H5	T7B16488H5	—	—	—	—	—	—
3/8	16	—	—	H5	4	—	T7316487H5	T7316488H5	—	—	—	—	—	—
3/8	—	24	—	H1	4	—	T7316507H1	T7316508H1	—	—	—	—	—	—
3/8	—	24	—	H2	4	—	T7316507H2	T7316508H2	—	—	—	—	—	—
3/8	—	24	—	H3	3	—	T7B16507	T7B16508	—	—	—	—	—	—
3/8	—	24	—	H3	4	T7316506	T7316507	T7316508	T6316506	T6316507	T6316508	T8316507	T8316508	—
3/8	—	24	—	H4	4	—	T7316507H4	T7316508H4	—	—	—	—	—	—
7/16	14	—	—	H2	4	—	T7316527H2	—	—	—	—	—	—	—
7/16	14	—	—	H3	3	—	T7B16527	T7B16528	—	—	—	—	—	—
7/16	14	—	—	H3	4	T7316526	T7316527	T7316528	T6316526	T6316527	T6316528	T8316527	T8316528	—
7/16	14	—	—	H5	4	—	T7316527H5	T7316528H5	—	—	—	—	—	—

Refer to technical data on page 520~554.

NEXT PAGE

⊙ : Excellent ○ : Good

P				M				K								
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)	⊙	⊙							
K		N				S										
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium	⊙	⊙	⊙	⊙	⊙	⊙



STRAIGHT FLUTE TAPS

T7316/T6316/T8316 SERIES

T7A16/T7B16 SERIES

HAND TAP TAPER, PLUG & BOTTOMING STYLE

Thread Depth / Hole Type 2.0xD



USCTI

- GS
- HSS
- UNC UNF UNS
- USCTI 302
- 9P/5P/2P
- Bright
- Steam Oxide
- TiN

SIZE	Thread Per Inch			Limit	No. of Flute	EDP No.								
	UNC	UNF	UNS			Bright			Steam Oxide			TiN		
						Taper	Plug	Bottoming	Taper	Plug	Bottoming	Plug	Bottoming	
7/16	—	20	—	H2	4	—	T7316547H2	—	—	—	—	—	—	—
7/16	—	20	—	H3	3	—	T7B16547	T7B16548	—	—	—	—	—	—
7/16	—	20	—	H3	4	T7316546	T7316547	T7316548	T6316546	T6316547	T6316548	T8316547	T8316548	—
7/16	—	20	—	H5	4	—	T7316547H5	T7316548H5	—	—	—	—	—	—
1/2	13	—	—	H1	4	—	T7316567H1	T7316568H1	—	—	—	—	—	—
1/2	13	—	—	H2	4	—	T7316567H2	T7316568H2	—	—	—	—	—	—
1/2	13	—	—	H3	3	—	T7B16567	T7B16568	—	—	—	—	—	—
1/2	13	—	—	H3	4	T7316566	T7316567	T7316568	T6316566	T6316567	T6316568	T8316567	T8316568	—
1/2	13	—	—	H5	4	—	T7316567H5	T7316568H5	—	—	—	—	—	—
1/2	—	20	—	H1	4	—	T7316587H1	T7316588H1	—	—	—	—	—	—
1/2	—	20	—	H3	3	—	T7B16587	T7B16588	—	—	—	—	—	—
1/2	—	20	—	H3	4	T7316586	T7316587	T7316588	T6316586	T6316587	T6316588	T8316587	T8316588	—
1/2	—	20	—	H5	4	—	T7316587H5	T7316588H5	—	—	—	—	—	—
9/16	12	—	—	H3	4	T7316606	T7316607	T7316608	T6316606	T6316607	T6316608	T8316607	T8316608	—
9/16	12	—	—	H5	4	—	T7316607H5	T7316608H5	—	—	—	—	—	—
9/16	—	18	—	H2	4	—	T7316627H2	—	—	—	—	—	—	—
9/16	—	18	—	H3	4	T7316626	T7316627	T7316628	T6316626	T6316627	T6316628	T8316627	T8316628	—
9/16	—	18	—	H5	4	—	T7316627H5	T7316628H5	—	—	—	—	—	—
5/8	11	—	—	H1	4	—	T7316647H1	—	—	—	—	—	—	—
5/8	11	—	—	H2	4	—	T7316647H2	T7316648H2	—	—	—	—	—	—
5/8	11	—	—	H3	4	T7316646	T7316647	T7316648	T6316646	T6316647	T6316648	T8316647	T8316648	—
5/8	11	—	—	H5	4	—	T7316647H5	T7316648H5	—	—	—	—	—	—
5/8	—	18	—	H1	4	—	T7316667H1	—	—	—	—	—	—	—
5/8	—	18	—	H2	4	—	T7316667H2	—	—	—	—	—	—	—
5/8	—	18	—	H3	4	T7316666	T7316667	T7316668	T6316666	T6316667	T6316668	T8316667	T8316668	—
5/8	—	18	—	H5	4	—	T7316667H5	T7316668H5	—	—	—	—	—	—
11/16	—	—	11	H3	4	T7316A06	T7316A07	T7316A08	T6316A06	T6316A07	T6316A08	—	—	—
11/16	—	—	16	H3	4	T7316A26	T7316A27	T7316A28	T6316A26	T6316A27	T6316A28	—	—	—

Refer to technical data on page 520~554.

NEXT PAGE

⊙ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
⊙	⊙			⊙						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	⊙	⊙		⊙	⊙	⊙	⊙			




STRAIGHT FLUTE TAPS

T7316/T6316/T8316 SERIES

T7A16/T7B16 SERIES

HAND TAP TAPER, PLUG & BOTTOMING STYLE

Thread Depth / Hole Type 2.0xD



USCTI

- GS
- HSS
- UNC UNF UNS
- USCTI 302
- 9P/5P/2P
- Bright
- Steam Oxide
- TiN

SIZE	Thread Per Inch			Limit	No. of Flute	EDP No.								
	UNC	UNF	UNS			Bright			Steam Oxide			TiN		
						Taper	Plug	Bottoming	Taper	Plug	Bottoming	Plug	Bottoming	
3/4	10	—	—	H1	4	—	T7316707H1	T7316708H1	—	—	—	—	—	—
3/4	10	—	—	H2	4	—	T7316707H2	—	—	—	—	—	—	—
3/4	10	—	—	H3	4	T7316706	T7316707	T7316708	T6316706	T6316707	T6316708	T8316707	T8316708	—
3/4	10	—	—	H5	4	—	T7316707H5	T7316708H5	—	—	—	—	—	—
3/4	—	16	—	H1	4	—	T7316727H1	—	—	—	—	—	—	—
3/4	—	16	—	H2	4	—	T7316727H2	—	—	—	—	—	—	—
3/4	—	16	—	H3	4	T7316726	T7316727	T7316728	T6316726	T6316727	T6316728	T8316727	T8316728	—
3/4	—	16	—	H5	4	—	T7316727H5	T7316728H5	—	—	—	—	—	—
7/8	9	—	—	H4	4	T7316746	T7316747	T7316748	T6316746	T6316747	T6316748	T8316747	T8316748	—
7/8	9	—	—	H6	4	—	T7316747H6	—	—	—	—	—	—	—
7/8	—	14	—	H2	4	—	T7316767H2	—	—	—	—	—	—	—
7/8	—	14	—	H4	4	T7316766	T7316767	T7316768	T6316766	T6316767	T6316768	T8316767	T8316768	—
7/8	—	14	—	H6	4	—	T7316767H6	—	—	—	—	—	—	—
1	8	—	—	H1	4	—	T7316787H1	T7316788H1	—	—	—	—	—	—
1	8	—	—	H2	4	—	T7316787H2	—	—	—	—	—	—	—
1	8	—	—	H4	4	T7316786	T7316787	T7316788	T6316786	T6316787	T6316788	T8316787	T8316788	—
1	8	—	—	H6	4	—	T7316787H6	—	—	—	—	—	—	—
1	—	12	—	H4	4	T7316806	T7316807	T7316808	T6316806	T6316807	T6316808	T8316807	T8316808	—
1	—	—	14	H2	4	—	T7316817H2	—	—	—	—	—	—	—
1	—	—	14	H4	4	T7316816	T7316817	T7316818	—	—	—	T8316817	T8316818	—
1-1/8	7	—	—	H4	4	T7316826	T7316827	T7316828	—	—	—	T8316827	T8316828	—
1-1/8	—	12	—	H4	4	T7316846	T7316847	T7316848	—	—	—	T8316847	T8316848	—
1-1/4	7	—	—	H4	4	T7316886	T7316887	T7316888	—	—	—	T8316887	T8316888	—
1-1/4	—	12	—	H4	6	T7316886	T7316887	T7316888	—	—	—	T8316887	T8316888	—
1-3/8	6	—	—	H4	4	T7316906	T7316907	T7316908	—	—	—	T8316907	T8316908	—
1-3/8	—	12	—	H4	6	T7316926	T7316927	T7316928	—	—	—	T8316927	T8316928	—
1-1/2	6	—	—	H4	4	T7316946	T7316947	T7316948	—	—	—	T8316947	T8316948	—
1-1/2	—	12	—	H4	6	T7316966	T7316967	T7316968	—	—	—	T8316967	T8316968	—

Refer to technical data on page 520~554.

⊙ : Excellent ○ : Good




P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
⊙	⊙			⊙						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	⊙	⊙		⊙	⊙	⊙	⊙			

YG STRAIGHT FLUTE TAPS

T7315/T6315/T8315 SERIES

METRIC HAND TAP TAPER, PLUG & BOTTOMING STYLE

Thread Depth / Hole Type 2.0xD



USCTI

GS
HSS
M MF
USCTI 302
9P/5P/2P
Bright
Steam Oxide
TiN

SIZE	Pitch	Limit	No. of Flute	EDP No.								
				Bright			Steam Oxide			TiN		
				Taper	Plug	Bottoming	Taper	Plug	Bottoming	Plug	Bottoming	
M1.6	0.35	D3	3	—	T7315097	—	—	—	—	—	—	—
M2	0.40	D3	3	—	T7315137	T7315138	—	T6315137	T6315138	T8315137	T8315138	—
M2.5	0.45	D3	3	—	T7315177	T7315178	—	T6315177	T6315178	T8315177	T8315178	—
M3	0.50	D3	3	T7315206	T7315207	T7315208	T6315206	T6315207	T6315208	T8315207	T8315208	—
M3.5	0.60	D4	3	—	T7315227	T7315228	—	—	—	—	—	—
M4	0.70	D4	4	T7315246	T7315247	T7315248	T6315246	T6315247	T6315248	T8315247	T8315248	—
M4.5	0.75	D4	4	—	T7315267	T7315268	—	T6315267	T6315268	T8315267	T8315268	—
M5	0.80	D4	4	T7315286	T7315287	T7315288	T6315286	T6315287	T6315288	T8315287	T8315288	—
M6	1.00	D5	4	T7315316	T7315317	T7315318	T6315316	T6315317	T6315318	T8315317	T8315318	—
M7	1.00	D5	4	—	T7315347	T7315348	—	T6315347	T6315348	T8315347	T8315348	—
M8	1.25	D5	4	T7315366	T7315367	T7315368	T6315366	T6315367	T6315368	T8315367	T8315368	—
M8	1.00	D5	4	—	T7315377	T7315378	—	T6315377	T6315378	T8315377	T8315378	—
M10	1.00	D5	4	—	T7315447	T7315448	—	—	—	—	—	—
M10	1.50	D6	4	T7315426	T7315427	T7315428	T6315426	T6315427	T6315428	T8315427	T8315428	—
M10	1.25	D5	4	T7315436	T7315437	T7315438	T6315436	T6315437	T6315438	T8315437	T8315438	—
M12	1.50	D6	4	—	T7315517	T7315518	—	—	—	—	—	—
M12	1.75	D6	4	T7315506	T7315507	T7315508	T6315506	T6315507	T6315508	T8315507	T8315508	—
M12	1.25	D5	4	T7315526	T7315527	T7315528	T6315526	T6315527	T6315528	T8315527	T8315528	—
M14	2.00	D7	4	T7315546	T7315547	T7315548	T6315546	T6315547	T6315548	T8315547	T8315548	—
M14	1.50	D6	4	—	T7315557	T7315558	—	—	—	—	—	—
M14	1.25	D5	4	—	T7315567	T7315568	—	—	—	—	—	—
M16	2.00	D7	4	T7315606	T7315607	T7315608	T6315606	T6315607	T6315608	T8315607	T8315608	—
M16	1.50	D6	4	T7315616	T7315617	T7315618	T6315616	T6315617	T6315618	T8315617	T8315618	—
M18	2.50	D7	4	—	T7315657	T7315658	—	—	—	—	—	—
M18	1.50	D6	4	T7315676	T7315677	T7315678	T6315676	T6315677	T6315678	T8315677	T8315678	—
M20	2.50	D7	4	T7315706	T7315707	T7315708	T6315706	T6315707	T6315708	T8315707	T8315708	—
M20	1.50	D6	4	T7315726	T7315727	T7315728	T6315726	T6315727	T6315728	T8315727	T8315728	—
M24	3.00	D8	4	T7315786	T7315787	T7315788	T6315786	T6315787	T6315788	T8315787	T8315788	—
M30	3.50	D9	4	T7315946	T7315947	T7315948	T6315946	T6315947	T6315948	—	—	—
M36	4.00	D9	4	—	T7315837	T7315838	—	—	—	—	—	—

Refer to technical data on page 520~554.

⊙ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron	~HRc15 (~HB180)	~HRc19 (~HB220)	
~HRc23 (~HB240)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)	~HRc15 (~HB180)	~HRc23 (~HB240)	
⊙	⊙			⊙						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	⊙	⊙		⊙	⊙	⊙	⊙			

YG STRAIGHT FLUTE TAPS


T7326 SERIES

METRIC HAND TAP Oversize Tap

Thread Depth / Hole Type 2.0xD



USCTI



GS
HSS
UNC UNF
USCTI 302
5P/2P
Bright
+.005" oversize

SIZE	Thread Per Inch		No. of Flute	EDP No.	
	UNC	UNF		Bright	
				Plug	Bottoming
#6	32	—	3	T7326247	—
#8	32	—	4	T7326287	—
#10	24	—	4	T7326327	—
#10	—	32	4	T7326347	—
1/4	20	—	4	T7326407	T7326408
1/4	—	28	4	T7326427	—
5/16	18	—	4	T7326447	T7326448
5/16	—	24	4	T7326467	—
3/8	16	—	4	T7326487	T7326488
3/8	—	24	4	T7326507	—
7/16	14	—	4	T7326527	—
1/2	13	—	4	T7326567	—
1/2	—	20	4	T7326587	—
5/8	11	—	4	T7326647	—
3/4	10	—	4	T7326707	—

Refer to technical data on page 520~554.

⊙ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron	~HRc15 (~HB180)	~HRc19 (~HB220)	
~HRc23 (~HB240)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)	~HRc15 (~HB180)	~HRc23 (~HB240)	
⊙	⊙			⊙						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	⊙	⊙		⊙	⊙	⊙	⊙			

YG STRAIGHT FLUTE TAPS


T7B15 SERIES

METRIC HAND TAP Oversize Tap

Thread Depth / Hole Type 2.0xD



USCTI



GS **HSS** **M MF** **USCTI 302** **5P/2P** **Bright** **+ .127mm oversize**

SIZE	Pitch	No. of Flute	EDP No.	
			Bright	
			Plug	Bottoming
M4	0.70	4	T7B15247	T7B15248
M4.5	0.75	4	T7B15267	T7B15268
M5	0.80	4	T7B15287	T7B15288
M6	1.00	4	T7B15317	T7B15318
M7	1.00	4	T7B15347	T7B15348
M8	1.25	4	T7B15367	T7B15368
M8	1.00	4	T7B15377	T7B15378
M10	1.50	4	T7B15427	T7B15428
M10	1.25	4	T7B15437	T7B15438
M12	1.75	4	T7B15507	T7B15508
M12	1.25	4	T7B15527	T7B15528
M16	2.00	4	T7B15607	T7B15608
M20	2.50	4	T7B15707	T7B15708
M24	3.00	4	T7B15787	T7B15788

Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎			◎						
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	◎	◎		◎	◎	◎	◎			

YG STRAIGHT FLUTE TAPS


T7336 SERIES

LEFT HAND TAP

Thread Depth / Hole Type 2.0xD



USCTI



GS **HSS** **UNC UNF** **USCTI 302** **5P/2P** **Bright**

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.	
	Bright					
	UNC	UNF			Plug	Bottoming
#6	32	—	H3	3	T7336247	T7336248
#6	—	40	H2	3	T7336267	T7336268
#8	32	—	H3	4	T7336287	T7336288
#8	—	36	H2	4	T7336307	T7336308
#10	24	—	H3	4	T7336327	T7336328
#10	—	32	H3	4	T7336347	T7336348
1/4	20	—	H3	4	T7336407	T7336408
1/4	—	28	H3	4	T7336427	T7336428
5/16	18	—	H3	4	T7336447	T7336448
5/16	—	24	H3	4	T7336467	T7336468
3/8	16	—	H3	4	T7336487	T7336488
3/8	—	24	H3	4	T7336507	T7336508
7/16	14	—	H3	4	T7336527	T7336528
7/16	—	20	H3	4	T7336547	T7336548
1/2	13	—	H3	4	T7336567	T7336568
1/2	—	20	H3	4	T7336587	T7336588
9/16	12	—	H3	4	T7336607	T7336608
9/16	—	18	H3	4	T7336627	T7336628
5/8	11	—	H3	4	T7336647	T7336648
5/8	—	18	H3	4	T7336667	T7336668
3/4	10	—	H3	4	T7336707	T7336708
3/4	—	16	H3	4	T7336727	T7336728
7/8	9	—	H4	4	T7336747	T7336748
7/8	—	14	H4	4	T7336767	T7336768
1	8	—	H4	4	T7336787	T7336788
1	—	12	H4	4	T7336807	T7336808

Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎			◎						
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	◎	◎		◎	◎	◎	◎			

YG STRAIGHT FLUTE TAPS


T7A15 SERIES

METRIC LEFT HAND TAP

Thread Depth / Hole Type 2.0xD



USCTI



- GS
- HSS
- UNC UNF
- USCTI 302
- 5P/2P
- Bright

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Bright	
				Plug	Bottoming
M3.5	0.6	D4	3	T7A15227	T7A15228
M4	0.7	D4	4	T7A15247	T7A15248
M4.5	0.75	D4	4	T7A15267	T7A15268
M5	0.8	D4	4	T7A15287	T7A15288
M6	1.0	D5	4	T7A15317	T7A15318
M7	1.0	D5	4	T7A15347	T7A15348
M8	1.25	D5	4	T7A15367	T7A15368
M8	1.0	D5	4	T7A15377	T7A15378
M10	1.5	D6	4	T7A15427	T7A15428
M10	1.25	D5	4	T7A15437	T7A15438
M12	1.75	D6	4	T7A15507	T7A15508
M12	1.25	D5	4	T7A15527	T7A15528
M14	2.0	D7	4	T7A15547	T7A15548
M14	1.5	D6	4	T7A15557	T7A15558
M16	2.0	D7	4	T7A15607	T7A15608
M16	1.5	D6	4	T7A15617	T7A15618
M18	2.5	D7	4	T7A15657	T7A15658
M18	1.5	D6	4	T7A15677	T7A15678
M20	2.5	D7	4	T7A15707	T7A15708
M20	1.5	D6	4	T7A15727	T7A15728
M22	2.5	D7	4	T7A15747	T7A15748
M22	1.5	D6	4	T7A15767	T7A15768
M24	3.0	D8	4	T7A15787	T7A15788
M24	2.0	D7	4	T7A15797	T7A15798

Refer to technical data on page 520~554.

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎			◎						
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	◎	◎		◎	◎	◎	◎			

YG STRAIGHT FLUTE TAPS


T7616/T6616/T8616 SERIES

PULLEY TAPS, 6" EXTENSION PLUG STYLE

Thread Depth / Hole Type 2.0xD



USCTI Long Shank



- GS
- HSS
- UNC UNF
- USCTI Long Shank
- 4P~5P
- Bright
- Steam Oxide
- TiN

SIZE	UNC	Overall Length	Limit	No. of Flute	EDP No.		
					Bright		
					Bright	Steam Oxide	TiN
1/4	20	6	H3	4	T7616403	T6616403	T8616403
5/16	18	6	H3	4	T7616443	T6616443	T8616443
3/8	16	6	H3	4	T7616483	T6616483	T8616483
7/16	14	6	H3	4	T7616523	T6616523	T8616523
1/2	13	6	H3	4	T7616563	T6616563	T8616563
5/8	11	6	H3	4	T7616643	T6616643	T8616643

Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎			◎						
K	N				S					
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
	◎	◎		◎	◎	◎	◎			



Being the best through innovation

HSS




FORMING TAPS

- Tapping by Forming Soft Materials (No Chips)









Global Cutting Tool Leader **YG-1**



SELECTION GUIDE

FORMING TAPS Tapping by Forming Soft Materials

INCH/METRIC


EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page
TKR03		Super HSS	UNC/UNF	GV	USCTI 302A	H	2 ~ 3P	3.0D	TiCN	491
ZF		HSSE-V3	UNC/UNF	GV	USCTI 302	H	2 ~ 3P		Bright	492
Z0/Z1/Z2/Z3		HSSE-V3	UNC/UNF	GV	USCTI 302A	H	4 ~ 5P 1.5 ~ 2P		Bright TiN	493
Z4/Z5/Z6/Z7		HSSE-V3	UNC/UNF	GV	USCTI 302A	H	4 ~ 5P 1.5 ~ 2P		Bright TiN	495
Z8/ZA/ZC Z9/ZB/ZD		HSSE-V3	M/MF	GV	USCTI 302A	D	4 ~ 5P 1.5 ~ 2P		Bright TiN / TiCN	497
T7R01/T8R01/ THR01 T7R02/T8R02/ THR02		HSS	UNC/UNF	GV	USCTI 302A	H	4 ~ 5P 1.5 ~ 2P		Bright TiN / TiCN	498

YG FORMING TAPS


TKR03 SERIES

FORMING TAPS MODIFIED BOTTOMING STYLE

Thread Depth / Hole Type 3.0×D



USCTI



GV Super HSS **UNC UNF** **USCTI 302A** **2P~3P** **TiCN**

SIZE	Thread Per Inch		No. of Lobe	EDP No.			
	UNC	UNF		Class of fit			
				2B (TiCN)		3B (TiCN)	
#4	40	—	4	TKR03165	H5	TKR03163	H3
#5	40	—	4	TKR03205	H5	TKR03203	H3
#6	32	—	4	TKR03245	H5	TKR03243	H3
#8	32	—	4	TKR03285	H5	TKR03283	H3
#10	24	—	4	TKR03326	H6	TKR03324	H4
#10	—	32	4	TKR03346	H6	TKR03344	H4
1/4	20	—	4	TKR03406	H6	TKR03404	H4
1/4	—	28	4	TKR03426	H6	TKR03424	H4
5/16	18	—	4	TKR03447	H7	TKR03445	H5
5/16	—	24	4	TKR03467	H7	TKR03465	H5
3/8	16	—	4	TKR03487	H7	TKR03485	H5
3/8	—	24	4	TKR03507	H7	TKR03505	H5

► Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K	
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)		
◎	◎			◎					
K	N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
	◎	◎		◎	◎	◎			


- HSS
- CARBIDE
- THREAD MILLS
- COMBO TAPS
- SPIRAL FLUTE TAPS
- SPIRAL POINT TAPS
- STRAIGHT FLUTE TAPS
- FORMING TAPS
- SCREW THREAD INSERT TAPS
- PIPE TAPS
- TECHNICAL DATA




ZF SERIES

MINIATURE FORMING TAPS MODIFIED BOTTOMING STYLE

Thread Depth / Hole Type 3.0xD



USCTI



- GV
- HSSE-V3
- UNC UNF
- USCTI 302
- 2P~3P
- Bright

SIZE	Nominal Size (mm)	Pitch		Limit	No. of Lobe	EDP No.
		UNC	UNF			
#00	1.1938	90	—	H2	4	ZFM52
#00	1.1938	90	—	H3	4	ZFM53
#00	1.1938	—	96	H2	4	ZFM82
#00	1.1938	—	96	H3	4	ZFM83
#0	1.5240	—	80	H2	4	ZF022
#0	1.5240	—	80	H3	4	ZF023
#0	1.5240	—	80	H4	4	ZF024
#1	1.8540	64	—	H2	4	ZF042
#1	1.8540	64	—	H3	4	ZF043
#1	1.8540	64	—	H4	4	ZF044
#1	1.8540	—	72	H2	4	ZF062
#1	1.8540	—	72	H3	4	ZF063
#1	1.8540	—	72	H4	4	ZF064
#2	2.1844	56	—	H2	4	ZF082
#2	2.1844	56	—	H3	4	ZF083
#2	2.1844	56	—	H4	4	ZF084
#2	2.1844	—	64	H2	4	ZF102
#2	2.1844	—	64	H3	4	ZF103
#2	2.1844	—	64	H4	4	ZF104
#3	2.5146	48	—	H2	4	ZF122
#3	2.5146	48	—	H3	4	ZF123
#3	2.5146	48	—	H4	4	ZF124
#3	2.5146	48	—	H5	4	ZF125
#3	2.5146	—	56	H2	4	ZF142
#3	2.5146	—	56	H3	4	ZF143
#3	2.5146	—	56	H4	4	ZF144
#3	2.5146	—	56	H5	4	ZF145

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎				◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
				◎	◎					




Z0/Z1/Z2/Z3 SERIES


FORMING TAPS PLUG & BOTTOMING STYLE

A variety of H Limit

Thread Depth / Hole Type 3.0xD



USCTI



- GV
- HSSE-V3
- UNC UNF
- USCTI 302A
- 4P~5P Plug
- 1.5P~2P Bottoming
- Bright
- TiN

SIZE	Thread Per Inch		Limit	No. of Lobe	EDP No.			
	UNC	UNF			Plug		Bottoming	
					Bright	TiN	Bright	TiN
#0	—	80	H2	4	—	—	Z2022	Z3022
#0	—	80	H3	4	—	—	Z2023	Z3023
#1	64	—	H2	4	—	—	Z2042	Z3042
#1	—	72	H2	4	—	—	Z2062	Z3062
#1	—	72	H3	4	—	—	Z2063	Z3063
#2	56	—	H2	4	—	—	Z2082	Z3082
#2	56	—	H3	4	—	—	Z2083	Z3083
#2	—	64	H2	4	—	—	Z2102	Z3102
#3	48	—	H2	4	—	—	Z2122	Z3122
#3	48	—	H3	4	—	—	Z2123	Z3123
#3	—	56	H3	4	—	—	Z2143	Z3143
#4	40	—	H3	4	Z0163	Z1163	Z2163	Z3163
#4	40	—	H5	4	Z0165	Z1165	Z2165	Z3165
#4	—	48	H3	4	Z0183	Z1183	Z2183	Z3183
#4	—	48	H5	4	Z0185	Z1185	Z2185	Z3185
#5	40	—	H3	4	Z0203	Z1203	Z2203	Z3203
#5	40	—	H5	4	Z0205	Z1205	Z2205	Z3205
#5	—	44	H5	4	Z0225	Z1225	Z2225	Z3225
#6	32	—	H3	4	Z0243	Z1243	Z2243	Z3243
#6	32	—	H5	4	Z0245	Z1245	Z2245	Z3245
#6	—	40	H3	4	Z0263	Z1263	Z2263	Z3263
#6	—	40	H5	4	Z0265	Z1265	Z2265	Z3265
#8	32	—	H3	4	Z0283	Z1283	Z2283	Z3283
#8	32	—	H5	4	Z0285	Z1285	Z2285	Z3285
#8	—	36	H3	4	Z0303	Z1303	Z2303	Z3303
#8	—	36	H5	4	Z0305	Z1305	Z2305	Z3305
#10	24	—	H4	4	Z0324	Z1324	Z2324	Z3324
#10	24	—	H6	4	Z0326	Z1326	Z2326	Z3326
#10	—	32	H4	4	Z0344	Z1344	Z2344	Z3344
#10	—	32	H6	4	Z0346	Z1346	Z2346	Z3346
#12	24	—	H4	4	Z0364	Z1364	Z2364	Z3364

Refer to technical data on page 520-554.

Hardslck coating is available on your request (Bright Finish EDP No + H)

◎ : Excellent ○ : Good


P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
◎	◎			◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
				◎	◎	◎	◎			




Z0/Z1/Z2/Z3 SERIES

FORMING TAPS PLUG & BOTTOMING STYLE

Thread Depth / Hole Type 3.0xD



USCTI



- GV, HSSE-V3, UNC UNF, USCTI 302A, 4P~5P Plug, 1.5P~2P Bottoming, Bright, TiN

Table with columns: SIZE, Thread Per Inch (UNC, UNF), Limit, No. of Lobe, EDP No. (Plug, Bottoming) with sub-columns for Bright and TiN.

Refer to technical data on page 520~554. Hardslick coating is available on your request (Bright Finish EDP No + H)


Material compatibility table with columns P, M, K, N, S and rows for various materials like carbon steels, stainless steels, cast irons, etc.




Z4/Z5/Z6/Z7 SERIES

FORMING TAPS WITH OIL GROOVE PLUG & BOTTOMING STYLE

Thread Depth / Hole Type 3.0xD



USCTI



- GV, HSSE-V3, UNC UNF, USCTI 302A, 4P~5P Plug, 1.5P~2P Bottoming, Bright, TiN

Table with columns: SIZE, Thread Per Inch (UNC, UNF), Limit, No. of Lobe, EDP No. (Plug, Bottoming) with sub-columns for Bright and TiN.

Refer to technical data on page 520~554. Hardslick coating is available on your request (Bright Finish EDP No + H)

Material compatibility table with columns P, M, K, N, S and rows for various materials like carbon steels, stainless steels, cast irons, etc.

Refer to technical data on page 520~554. Hardslick coating is available on your request (Bright Finish EDP No + H)


NEXT PAGE




Z4/Z5/Z6/Z7 SERIES

FORMING TAPS WITH OIL GROOVE PLUG & BOTTOMING STYLE

Thread Depth / Hole Type 3.0x D



USCTI



- GV, HSSE-V3, UNC UNF, USCTI 302A, 4P~5P Plug, 1.5P~2P Bottoming, Bright, TiN

Table with columns: SIZE, Thread Per Inch (UNC, UNF), Limit, No. of Lobe, EDP No. (Plug: Bright, TiN; Bottoming: Bright, TiN)

Refer to technical data on page 520~554. Hardslick coating is available on your request (Bright Finish EDP No + H)


Material compatibility table with columns: P, M, K, N, S and rows for various materials like Low carbon steels, Stainless steel castings, etc.




Z8/ZA/ZC SERIES, Z9/ZB/ZD SERIES

FORMING TAPS WITH OIL GROOVE PLUG & BOTTOMING STYLE

Thread Depth / Hole Type 3.0x D



USCTI



- GV, HSSE-V3, M MF, USCTI 302A, 4P~5P Plug, 1.5P~2P Bottoming, Bright, TiN, TiCN

Table with columns: SIZE, Pitch, Limit, No. of Lobe, EDP No. (Plug: Bright, TiN, TiCN; Bottoming: Bright, TiN, TiCN)

Refer to technical data on page 520~554. Hardslick coating is available on your request (Bright Finish EDP No + H)

Material compatibility table with columns: P, M, K, N, S and rows for various materials like Low carbon steels, Stainless steel castings, etc.

HSS

CARBIDE

THREAD MILLS

COMBO TAPS

SPIRAL FLUTE TAPS

SPIRAL POINT TAPS

STRAIGHT FLUTE TAPS

FORMING TAPS

SCREW THREAD INSERT TAPS

PIPE TAPS

TECHNICAL DATA


FORMING TAPS

T7R01/T8R01/THR01 SERIES


T7R02/T8R02/THR02 SERIES

FORMING TAPS PLUG & BOTTOMING STYLE for General Purpose

Thread Depth / Hole Type 3.0×D



USCTI



- GV
- HSS
- UNC UNF
- USCTI 302A
- 4P~5P Plug
- 1.5P~2P Bottoming
- Bright
- TiN
- TiCN

SIZE	Thread Per Inch			EDP No.					
	UNC	UNF	Limit	Plug			Bottoming		
				Bright	TiN	TiCN	Bright	TiN	TiCN
#0	—	80	H2	—	—	—	T7R02022	T8R02022	THR02022
#2	56	—	H2	—	—	—	T7R02082	T8R02082	THR02082
#3	48	—	H3	—	—	—	T7R02123	T8R02123	THR02123
#4	40	—	H3	T7R01163	T8R01163	THR01163	T7R02163	T8R02163	THR02163
#5	40	—	H3	T7R01203	T8R01203	THR01203	T7R02203	T8R02203	THR02203
#6	32	—	H3	T7R01243	T8R01243	THR01243	T7R02243	T8R02243	THR02243
#8	32	—	H3	T7R01283	T8R01283	THR01283	T7R02283	T8R02283	THR02283
#10	24	—	H4	T7R01324	T8R01324	THR01324	T7R02324	T8R02324	THR02324
#10	—	32	H4	T7R01344	T8R01344	THR01344	T7R02344	T8R02344	THR02344
1/4	20	—	H4	T7R01404	T8R01404	THR01404	T7R02404	T8R02404	THR02404
1/4	—	28	H4	T7R01424	T8R01424	THR01424	T7R02424	T8R02424	THR02424
5/16	18	—	H5	T7R01445	T8R01445	THR01445	T7R02445	T8R02445	THR02445
3/8	16	—	H5	T7R01485	T8R01485	THR01485	T7R02485	T8R02485	THR02485

Refer to technical data on page 520~554.


◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels / Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels / Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc24 (~HB250)	~HRc38 (~HB350)	~HRc19 (~HB220)	
◎	◎			◎						
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
	◎	◎		◎	◎	◎	◎			



Being the best through innovation

HSS



SCREW THREAD INSERT TAPS

- Tapping STI Threads of Soft Materials (HSSE-V3 & HSS)

SELECTION GUIDE

SCREW THREAD INSERT TAPS

Tapping STI Threads of Soft Materials (HSSE-V3 & HSS)


INCH/METRIC

EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page
ST/SI		HSSE-V3	UNC/UNF	GS	USCTI 322	2B	1.5 ~ 2P	2.5D	Hardslick	501
T7406		HSS	UNC/UNF	GS	USCTI 322	H	1.5 ~ 2P		Bright	502
T7425		HSS	M/MF	GS	USCTI 322A	D	1.5 ~ 2P	3.0D	Bright	503
ST/SI		HSSE-V3	UNC/UNF	GS	USCTI 322	2B	4 ~ 5P		Hardslick	504
T7436		HSS	UNC/UNF	GS	USCTI 322	H	4 ~ 5P	3.0D	Bright	505
T7415		HSS	M/MF	GS	USCTI 322A	D	4 ~ 5P		Bright	506
T7426		HSS	UNC/UNF	GS	USCTI 322	H	4 ~ 5P 1.5 ~ 2P	2.0D	Bright	507
T7405		HSS	M/MF	GS	USCTI 322A	D	4 ~ 5P 1.5 ~ 2P		Bright	508


YG SCREW THREAD INSERT TAPS

ST/SI SERIES

SPIRAL FLUTE STI TAPS BOTTOMING STYLE



USCTI



GS
HSSE-V3
UNC UNF
USCTI 322
1.5P~2P
Hardslick
R40

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.
	UNC	UNF			
#4	40	—	2B	3	ST162
#4	—	48	2B	3	SI182
#5	40	—	2B	3	ST202
#5	—	44	2B	3	SI222
#6	32	—	2B	3	ST242
#6	—	40	2B	3	SI262
#8	32	—	2B	3	ST282
#8	—	36	2B	3	SI302
#10	24	—	2B	3	ST322
#10	—	32	2B	3	SI342
#12	24	—	2B	3	ST362
#12	—	28	2B	3	SI382
1/4	20	—	2B	3	ST402
1/4	—	28	2B	3	SI422
5/16	18	—	2B	3	ST442
5/16	—	24	2B	3	SI462
3/8	16	—	2B	3	ST482
3/8	—	24	2B	3	SI502
7/16	14	—	2B	3	ST522
7/16	—	20	2B	3	SI542
1/2	13	—	2B	3	ST562
1/2	—	20	2B	3	SI582
9/16	12	—	2B	4	ST602
9/16	—	18	2B	4	SI622
5/8	11	—	2B	4	ST642
5/8	—	18	2B	4	SI662
3/4	10	—	2B	4	ST702
3/4	—	16	2B	4	SI722

► Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)	
◎	◎	○					○	
K		N			S			
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy 718 Inconel / A286 Titanium	
				○	○			

HSS

CARBIDE

THREAD
MILLS

COMBO
TAPS

SPIRAL
FLUTE TAPS

SPIRAL
POINT TAPS

STRAIGHT
FLUTE TAPS

FORMING
TAPS

SCREW
THREAD
INSERT TAPS

PIPE TAPS


TECHNICAL
DATA

YG SCREW THREAD INSERT TAPS


T7406 SERIES

SPIRAL FLUTE STI TAPS BOTTOMING STYLE HIGH HELIX for General Purpose

Thread Depth / Hole Type 2.5xD



USCTI



GS
HSS
UNC UNF
USCTI 322
1.5P~2P
Bright
R50

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.	
	UNC	UNF			Bright	
#2	56	—	H2	2	T7406082	
#3	48	—	H2	2	T7406122	
#4	40	—	H2	2	T7406162	
#4	—	48	H2	3	T7406182	
#6	32	—	H2	3	T7406242	
#6	32	—	H3	3	T7406243	
#6	—	40	H2	3	T7406262	
#8	32	—	H2	3	T7406282	
#8	32	—	H3	3	T7406283	
#8	—	36	H2	3	T7406302	
#10	24	—	H2	3	T7406322	
#10	24	—	H3	3	T7406323	
#10	—	32	H2	3	T7406342	
#10	—	32	H3	3	T7406343	
1/4	20	—	H2	3	T7406402	
1/4	20	—	H3	3	T7406403	
1/4	—	28	H2	3	T7406422	
1/4	—	28	H3	3	T7406423	
5/16	18	—	H3	3	T7406443	
5/16	18	—	H4	3	T7406444	
5/16	—	24	H2	3	T7406462	
5/16	—	24	H3	3	T7406463	
3/8	16	—	H3	3	T7406483	
3/8	16	—	H4	3	T7406484	
3/8	—	24	H2	3	T7406502	
3/8	—	24	H3	3	T7406503	
7/16	14	—	H3	4	T7406523	
7/16	14	—	H4	4	T7406524	
7/16	—	20	H3	3	T7406543	
7/16	—	20	H4	3	T7406544	
1/2	13	—	H3	4	T7406563	
1/2	13	—	H4	4	T7406564	
1/2	—	20	H3	4	T7406583	
1/2	—	20	H4	4	T7406584	

Refer to technical data on page 520~554. ◎ : Excellent ○ : Good


P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	○						○			
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
				○	○					

YG SCREW THREAD INSERT TAPS


T7425 SERIES

METRIC SPIRAL FLUTE STI TAPS BOTTOMING STYLE HIGH HELIX for General Purpose

Thread Depth / Hole Type 2.5xD



USCTI



GS
HSS
M MF
USCTI 322A
1.5P~2P
Bright
R50

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Bright	
M2	0.40	D2	2	T7425132	
M2.5	0.45	D2	2	T7425172	
M3	0.50	D2	3	T7425202	
M4	0.70	D3	3	T7425243	
M5	0.80	D3	3	T7425283	
M6	1.00	D3	3	T7425313	
M8	1.25	D3	3	T7425363	
M10	1.50	D4	3	T7425424	
M12	1.75	D4	3	T7425504	

Refer to technical data on page 520~554.



Refer to technical data on page 520~554. ◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	○						○			
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
				○	○					

YG SCREW THREAD INSERT TAPS

ST/SI SERIES

SPIRAL POINT STI TAPS PLUG STYLE



- GS
- HSSE-V3
- UNC UNF
- USCTI 322
- 4P~5P
- Hardslick

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.
	UNC	UNF			
#4	40	—	2B	3	SI162
#4	—	48	2B	3	ST182
#6	32	—	2B	3	SI242
#6	—	40	2B	3	ST262
#8	32	—	2B	3	SI282
#8	—	36	2B	3	ST302
#10	24	—	2B	3	SI322
#10	—	32	2B	3	ST342
1/4	20	—	2B	3	SI402
1/4	—	28	2B	3	ST422
5/16	18	—	2B	3	SI442
5/16	—	24	2B	3	ST462
3/8	16	—	2B	3	SI482
3/8	—	24	2B	3	ST502
7/16	14	—	2B	3	SI522
7/16	—	20	2B	3	ST542
1/2	13	—	2B	3	SI562
1/2	—	20	2B	3	ST582
9/16	12	—	2B	3	SI602
9/16	—	18	2B	3	ST622
5/8	11	—	2B	3	SI642
5/8	—	18	2B	3	ST662
3/4	10	—	2B	3	SI702
3/4	—	16	2B	3	ST722

▶ Refer to technical data on page 520~554.



◎ : Excellent ○ : Good

P				M				K
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)	
○	○	○					○	
K		N				S		
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy 718 Inconel / A286 Titanium	
				○	○			

YG SCREW THREAD INSERT TAPS

T7436 SERIES

SPIRAL POINT STI TAPS PLUG STYLE for General Purpose



- GS
- HSS
- UNC UNF
- USCTI 322
- 4P~5P
- Bright

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.
	UNC	UNF			
#2	56	—	H2	2	T7436082
#3	48	—	H2	2	T7436122
#4	40	—	H1	2	T7436161
#4	40	—	H2	2	T7436162
#4	—	48	H2	2	T7436182
#5	40	—	H2	2	T7436202
#6	32	—	H2	2	T7436242
#6	32	—	H3	2	T7436243
#6	—	40	H2	2	T7436262
#8	32	—	H2	2	T7436282
#8	32	—	H3	2	T7436283
#8	—	36	H2	2	T7436302
#10	24	—	H2	2	T7436322
#10	24	—	H3	2	T7436323
#10	—	32	H2	2	T7436342
#10	—	32	H3	2	T7436343
1/4	20	—	H2	3	T7436402
1/4	20	—	H3	3	T7436403
1/4	—	28	H2	3	T7436422
1/4	—	28	H3	3	T7436423
5/16	18	—	H3	3	T7436443
5/16	18	—	H4	3	T7436444
5/16	—	24	H2	3	T7436462
5/16	—	24	H3	3	T7436463
3/8	16	—	H3	3	T7436483
3/8	16	—	H4	3	T7436484
3/8	—	24	H2	3	T7436502
3/8	—	24	H3	3	T7436503
7/16	14	—	H3	3	T7436523
7/16	14	—	H4	3	T7436524
7/16	—	20	H3	3	T7436543
7/16	—	20	H4	3	T7436544
1/2	13	—	H3	4	T7436563
1/2	13	—	H4	4	T7436564
1/2	—	20	H3	4	T7436583
1/2	—	20	H4	4	T7436584

▶ Refer to technical data on page 520~554.



◎ : Excellent ○ : Good

P				M				K
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)	
○	○	○					○	
K		N				S		
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy 718 Inconel / A286 Titanium	
				○	○			

YG SCREW THREAD INSERT TAPS

T7415 SERIES

METRIC SPIRAL POINT STI TAPS PLUG STYLE for General Purpose



- GS
- HSS
- M MF
- USCTI 322A
- 4P~5P
- Bright

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Bright	
M2	0.4	D2	2	T7415132	
M2.5	0.45	D2	2	T7415172	
M3	0.5	D2	3	T7415202	
M4	0.7	D3	3	T7415243	
M5	0.8	D3	3	T7415283	
M6	1.0	D3	3	T7415313	
M8	1.25	D3	3	T7415363	
M10	1.5	D4	3	T7415424	
M12	1.75	D4	3	T7415504	

Refer to technical data on page 520~554.



◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	○						○			
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
				○	○					

YG SCREW THREAD INSERT TAPS

T7426 SERIES

STRAIGHT FLUTE STI TAPS PLUG AND BOTTOMING STYLE for General Purpose



- GS
- HSS
- UNC UNF
- USCTI 322
- 4P~5P Plug
- 1.5P~2P Bottoming
- Bright

SIZE	Thread Per Inch		Limit	No. of Flute	EDP No.	
	UNC	UNF			Plug	Bottoming
#2	56	—	H2	3	T7426087	T7426088
#3	48	—	H2	3	T7426127	T7426128
#4	40	—	H1	3	T7426167H1	T7426168H1
#4	40	—	H2	3	T7426167	T7426168
#4	—	48	H2	3	T7426187	T7426188
#5	40	—	H2	3	T7426207	T7426208
#6	32	—	H2	3	T7426247H2	T7426248H2
#6	32	—	H3	3	T7426247	T7426248
#6	—	40	H2	3	T7426267	T7426268
#8	32	—	H2	3	T7426287H2	T7426288H2
#8	32	—	H3	3	T7426287	T7426288
#8	—	36	H2	3	T7426307	T7426308
#10	24	—	H2	3	T7426327H2	T7426328H2
#10	24	—	H3	3	T7426327	T7426328
#10	—	32	H2	3	T7426347H2	T7426348H2
#10	—	32	H3	3	T7426347	T7426348
1/4	20	—	H2	3	T7426407H2	T7426408H2
1/4	20	—	H3	3	T7426407	T7426408
1/4	—	28	H2	3	T7426427H2	T7426428H2
1/4	—	28	H3	3	T7426427	T7426428
5/16	18	—	H3	4	T7426447	T7426448
5/16	18	—	H4	4	T7426447H4	T7426448H4
5/16	—	24	H2	4	T7426467H2	T7426468H2
5/16	—	24	H3	4	T7426467	T7426468
3/8	16	—	H3	4	T7426487	T7426488
3/8	16	—	H4	4	T7426487H4	T7426488H4
3/8	—	24	H2	4	T7426507H2	T7426508H2
3/8	—	24	H3	4	T7426507	T7426508
7/16	14	—	H3	4	T7426527	T7426528
7/16	14	—	H4	4	T7426527H4	T7426528H4
7/16	—	20	H3	4	T7426547	T7426548
7/16	—	20	H4	4	T7426547H4	T7426548H4
1/2	13	—	H3	4	T7426567	T7426568
1/2	13	—	H4	4	T7426567H4	T7426568H4
1/2	—	20	H3	4	T7426587	T7426588
1/2	—	20	H4	4	T7426587H4	T7426588H4

Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	○						○			
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
				○	○					

HSS

CARBIDE

THREAD MILLS

COMBO TAPS

SPIRAL FLUTE TAPS

SPIRAL POINT TAPS

STRAIGHT FLUTE TAPS

FORMING TAPS

SCREW THREAD INSERT TAPS

PIPE TAPS


TECHNICAL DATA

Y/G SCREW THREAD INSERT TAPS


T7405 SERIES

METRIC STRAIGHT FLUTE STI TAPS PLUG AND BOTTOMING STYLE for General Purpose

Thread Depth / Hole Type 2.0xD



USCTI



GS HSS M USCTI 322A 4P~5P Plug 1.5P~2P Bottoming Bright

SIZE	Pitch	Limit	No. of Flute	EDP No.	
				Plug	Bottoming
M2	0.4	D2	2	T7405137	T7405138
M2.5	0.45	D2	2	T7405177	T7405178
M3	0.5	D2	3	T7405207	T7405208
M4	0.7	D3	3	T7405247	T7405248
M5	0.8	D3	3	T7405287	T7405288
M6	1.0	D3	3	T7405317	T7405318
M8	1.25	D3	3	T7405367	T7405368
M10	1.5	D4	3	T7405427	T7405428
M12	1.75	D4	3	T7405507	T7405508

Refer to technical data on page 520~554.



Being the best through innovation

HSS



PIPE TAPS

- Tapping NPT, NPTF, NPS & NPSF threads

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels / Free machining carbon steels	Medium to high carbon steels / Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels / Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels		Grey cast iron		
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) / ~HRc38 (~HB350)	~HRc38 (~HB350) / ~HRc44 (~HB420)		~HRc19 (~HB220)		
○	○							○		
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum / Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
				○	○					

SELECTION GUIDE

PIPE TAPS

Tapping NPT, NPTF, NPS & NPSF threads

INCH


EDP No.	MODEL	Tool Material	Standard	Work Material	Dimensions	Tolerance	Chamfer	Thread Depth	Surface Treatment	Page
Q1/Q0/Q6		HSSE-V3	NPTF	VA	USCTI 311		2 ~ 3P	2.5D	Bright Steam Oxide Hardslick	511
Q9/R0/R1		HSSE-V3	NPTF	GG	USCTI 311		2 ~ 3P		Bright TiN Hardslick	512
R7/R8/R9/S0		HSSE-V3	NPTF	GG	USCTI 311		2 ~ 3P	2.0D	Bright TiN Hardslick Nitrided- Steam Oxide	513
S1/S2		HSSE-V3	NPTF	GG	USCTI 311		2 ~ 3P		Bright TiCN	514
T7L36/T6L36 T7536/T6536		HSS	NPS/NPSF	GS	USCTI 311		4 ~ 5P		Bright Steam Oxide	515
T7505/T6505/ TH505		HSS	NPT	GS	USCTI 311		2 ~ 3P	Bright Steam Oxide TiCN	516	
T7546/T8546		HSS	NPTF	GS	USCTI 311		2 ~ 3P	Bright TiN	517	

YG PIPE TAPS


Q1/Q0/Q6 SERIES

TAPER PIPE TAPS : SPIRAL FLUTE STANDARD PROJECTION for Steels & Stainless Steels

Thread Depth / Hole Type 2.5×D



USCTI



VA
HSSE-V3
NPTF
USCTI 311
2P~3P
Bright
Steam Oxide
Hardslick
R15

SIZE	Thread Per Inch	No. of Flute	EDP No.		
			Bright	Steam Oxide	Hardslick
1/16	27	4	Q1020	Q0020	Q6020
1/8(Lg.)	27	4	Q1200	Q0200	Q6200
1/8(Sm.)	27	4	Q1210	Q0210	Q6210
1/4	18	4	Q1400	Q0400	Q6400
3/8	18	4	Q1480	Q0480	Q6480
1/2	14	4	Q1560	Q0560	Q6560
3/4	14	4	Q1700	Q0700	Q6700
1	11-1/2	4	Q1780	Q0780	Q6780
1-1/4	11-1/2	5	Q1860	Q0860	Q6860
1-1/2	11-1/2	7	Q1960	Q0960	Q6960
2	11-1/2	7	Q1D20	Q0D20	Q6D20

▶ These Taps meet both NPT and NPTF Standards.
 ▶ Refer to technical data on page 520-554.

◎ : Excellent ○ : Good

P				M				K	
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)		
○	◎	○		◎	○				
K	N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
○					○				

YG PIPE TAPS

Q9/R0/R1 SERIES

TAPER PIPE TAPS : SPIRAL FLUTE STANDARD PROJECTION for Cast Iron & Steels



GG HSSE-V3 NPTF USCTI 311 2P~3P Bright TiN Hardslick R15

SIZE	Thread Per Inch	No. of Flute	EDP No.		
			Bright	TiN	Hardslick
1/16	27	4	Q9020	R0020	R1020
1/8(Lg.)	27	4	Q9200	R0200	R1200
1/8(Sm.)	27	4	Q9210	R0210	R1210
1/4	18	4	Q9400	R0400	R1400
3/8	18	4	Q9480	R0480	R1480
1/2	14	4	Q9560	R0560	R1560
3/4	14	4	Q9700	R0700	R1700
1	11-1/2	4	Q9780	R0780	R1780
1-1/4	11-1/2	5	Q9860	R0860	R1860
1-1/2	11-1/2	7	Q9960	R0960	R1960
2	11-1/2	7	Q9D20	R0D20	R1D20

▶ These Taps meet both NPT and NPTF Standards.
▶ Refer to technical data on page 520~554.

YG PIPE TAPS

R7/R8/R9/S0 SERIES

TAPER PIPE TAPS : STRAIGHT FLUTE STANDARD PROJECTION for Cast Iron & Steels



GG HSSE-V3 NPTF USCTI 311 2P~3P Bright TiN Hardslick Nitrided Steam Oxide

SIZE	Thread Per Inch	No. of Flute	EDP No.			
			Bright	TiN	Hardslick	Nitrided Steam Oxide
1/16	27	4	R7020	R8020	R9020	S0020
1/8(Lg.)	27	4	R7200	R8200	R9200	S0200
1/8(Sm.)	27	4	R7210	R8210	R9210	S0210
1/4	18	4	R7400	R8400	R9400	S0400
3/8	18	4	R7480	R8480	R9480	S0480
1/2	14	4	R7560	R8560	R9560	S0560
3/4	14	5	R7700	R8700	R9700	S0700
1	11-1/2	5	R7780	R8780	R9780	S0780
1-1/4	11-1/2	5	R7860	R8860	R9860	S0860
1-1/2	11-1/2	7	R7960	R8960	R9960	S0960
2	11-1/2	7	R7D20	R8D20	R9D20	S0D20

▶ These Taps meet both NPT and NPTF Standards.
▶ Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels ~HRC15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRC23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRC24 (~HB250) ~HRC38 (~HB350)	Alloyed tool steels/ Mold steels ~HRC38 (~HB350) ~HRC44 (~HB420)	Free machining stainless steels ~HRC23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRC24 (~HB250) ~HRC38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRC38 (~HB350) ~HRC44 (~HB420)	~HRC19 (~HB220)	Grey cast iron		
◎	◎	○						◎		
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRC24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
◎										

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels ~HRC15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRC23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRC24 (~HB250) ~HRC38 (~HB350)	Alloyed tool steels/ Mold steels ~HRC38 (~HB350) ~HRC44 (~HB420)	Free machining stainless steels ~HRC23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRC24 (~HB250) ~HRC38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRC38 (~HB350) ~HRC44 (~HB420)	~HRC19 (~HB220)	Grey cast iron		
◎	◎	○						○		
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRC24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
◎										

YIG PIPE TAPS

S1/S2 SERIES

TAPER PIPE TAPS : STRAIGHT FLUTE INTERRUPTED THREAD STANDARD PROJECTION for Cast Iron & Steels



- GG
- HSSE-V3
- NPTF
- USCTI 311
- 2P~3P
- Bright
- TiCN

SIZE	Thread Per Inch	No. of Flute	EDP No.	
			Bright	TiCN
1/16	27	5	S1020	S2020
1/8(Lg.)	27	5	S1200	S2200
1/8(Sm.)	27	5	S1210	S2210
1/4	18	5	S1400	S2400
3/8	18	5	S1480	S2480
1/2	14	5	S1560	S2560
3/4	14	5	S1700	S2700
1	11-1/2	5	S1780	S2780

► These Taps meet both NPT and NPTF Standards.
 ► Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K	
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)		
○	○	○					○		
K	N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
○									○

YIG PIPE TAPS

T7L36/T6L36 SERIES
T7536/T6536 SERIES

STRAIGHT PIPE TAPS for General Purpose



- GS
- HSS
- NPS NPSF
- USCTI 311
- 4P~5P
- Bright
- Steam Oxide

T7L36 / T6L36 Series (NPS)

SIZE	Thread Per Inch	No. of Flute	EDP No.	
			Bright	Steam Oxide
1/8 (Lg.)	27	4	T7L36200	T6L36200
1/8 (Sm.)	27	4	T7L36210	T6L36210
1/4	18	4	T7L36400	T6L36400
3/8	18	4	T7L36480	T6L36480
1/2	14	4	T7L36560	T6L36560
3/4	14	5	T7L36700	T6L36700
1	11-1/2	5	T7L36780	T6L36780

T7536 / T6536 Series (NPSF)

SIZE	Thread Per Inch	No. of Flute	EDP No.	
			Bright	Steam Oxide
1/8 (Lg.)	27	4	T7536200	T6536200
1/8 (Sm.)	27	4	T7536210	T6536210
1/4	18	4	T7536400	T6536400
3/8	18	4	T7536480	T6536480
1/2	14	4	T7536560	T6536560
3/4	14	5	T7536700	T6536700
1	11-1/2	5	T7536780	T6536780

► Refer to technical data on page 520~554.

◎ : Excellent ○ : Good

P				M				K	
Low carbon steels/ Free machining carbon steels ~HRc15 (~HB180)	Medium to high carbon steels/ Low alloyed steels ~HRc23 (~HB240)	Steel castings & forgings / Heat-treatable alloy steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Alloyed tool steels/ Mold steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Free machining stainless steels ~HRc23 (~HB240)	Heat and corrosion resistant stainless steels / Valve stainless steels ~HRc24 (~HB250) ~HRc38 (~HB350)	Stainless steel castings / Precipitation hardening stainless steels ~HRc38 (~HB350) ~HRc44 (~HB420)	Grey cast iron ~HRc19 (~HB220)		
○	○						○		
K	N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron ~HRc24 (~HB250)	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
									○

YIG PIPE TAPS

T7505/T6505/TH505 SERIES

TAPER PIPE TAPS: STRAIGHT FLUTE INTERRUPTED STANDARD PROJECTION for General Purpose



- GS
- HSS
- NPT
- USCTI 311
- 2P~3P
- Bright
- Steam Oxide
- TiCN

SIZE	Thread Per Inch	No. of Flute	EDP No.		
			Bright	Steam Oxide	TiCN
1/8 (Lg.)	27	5	T7505200	T6505200	TH505200
1/8 (Sm.)	27	5	T7505210	T6505210	TH505210
1/4	18	5	T7505400	T6505400	TH505400
3/8	18	5	T7505480	T6505480	TH505480
1/2	14	5	T7505560	T6505560	TH505560
3/4	14	5	T7505700	T6505700	TH505700
1	11-1/2	5	T7505780	T6505780	TH505780

Refer to technical data on page 520~554.

YIG PIPE TAPS

T7546/T8546 SERIES

TAPER PIPE TAPS: STRAIGHT FLUTE STANDARD PROJECTION 6" EXTENSION for General Purpose



- GS
- HSS
- NPTF
- USCTI 311
- 2P~3P
- Bright
- TiN

SIZE	Threads Per Inch	Overall Length L	Thread Length Lt	Shank Diameter D	No. of Flute	EDP No.	
						Bright	TiN
1/8	27	6.0	3/4	.4375	4	T7546200	T8546200
1/4	18	6.0	1-1/16	.5625	4	T7546400	T8546400
3/8	18	6.0	1-1/16	.7000	4	T7546480	T8546480
1/2	14	6.0	1-3/8	.6875	4	T7546560	T8546560
3/4	14	6.0	1-3/8	.9063	5	T7546700	T8546700
1	11-1/2	6.0	1-3/4	1.1250	5	T7546780	T8546780

Refer to technical data on page 520~554. These Taps meet both NPT and NPTF Standards.

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	○						○			
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
				○	○					

◎ : Excellent ○ : Good

P				M				K		
Low carbon steels/ Free machining carbon steels	Medium to high carbon steels/ Low alloyed steels	Steel castings & forgings / Heat-treatable alloy steels	Alloyed tool steels/ Mold steels	Free machining stainless steels	Heat and corrosion resistant stainless steels / Valve stainless steels	Stainless steel castings / Precipitation hardening stainless steels	Grey cast iron			
~HRc15 (~HB180)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc23 (~HB240)	~HRc24 (~HB250) ~HRc38 (~HB350)	~HRc38 (~HB350) ~HRc44 (~HB420)	~HRc19 (~HB220)			
○	○						○			
K		N				S				
Nodular cast iron / Chilled cast iron / Meehanite iron / Ductile iron	Pure and alloyed copper	Free machining brass / Alloyed brass	Bronze	Pure Aluminum/ Aluminum alloy	Aluminum alloy castings	Zinc	Magnesium	718 & 625 INCO / Waspaloy / Hastelloy / Invar / Monel / Incoloy	718 Inconel / A286	Titanium
~HRc24 (~HB250)										
				○	○					



Being the best through innovation


TAPS




TECHNICAL DATA




Global Cutting Tool Leader **YG-1**



TAPS TERMINOLOGY




- d₁ Major diameter
- d₂ Shank diameter
- d₃ Chamfer diameter
- d₄ Neck diameter
- L Total length
- L₁ Thread length
- L₂ Shank length
- L₃ Square length
- L₄ Neck length
- L₅ Chamfer length
- L₆ Flutes length
- a Square size
- Cm Center male
- Cf Center female



- d₁ Major diameter
- d_m Flank diameter
- d Minor diameter
- d₃ Chamfer diameter
- P Pitch
- a Flank angle
- β Chamfer angle
- φ Gun nose angle
- γ Gun nose rake angle in front
- Δ Chamfer relief
- Δ₁ Pitch diameter relief on the land
- τ Rake angle
- T Width of land
- S Flute width
- d_s Web thickness
- ε Angle of spiral flute

MODI TAP BLANK DIMENSION




Unified Tap Blank

Nominal Size	Overall Length [L]	Thread Length [L-1]		Length to neck [L-2]		Shank Diameter [D]	Neck Diameter [d1]	Square Length [L-3]	Square Size [a]	Blank Design No.
		SF	SP	SF	SP					
#2	1.75	.157	.256	.433		.141	.061	.19	.110	1
#3	1.81	.197	.295	.492		.141	.069	.19	.110	1
#4	1.88	.236	.335	.563		.141	.077	.19	.110	1
#5	1.94	.236	.374	.626		.141	.090	.19	.110	1
#6	2.00	.276	.413	.689		.141	.094	.19	.110	1
#8	2.13	.276	.453	.752		.168	.120	.25	.131	1
#10-24	2.38	.354	.531	.906		.194	.131	.25	.152	1
#10-32		.276					.146			1
#12-24	2.38	.354	.571	.906		.220	.157	.28	.165	1
#12-28		.276					.166			1
1/4-20	2.50	.433	.591	1.000		.255	.180	.31	.191	2
1/4-28		.354					.200			2
5/16-18	2.72	.472	.669	1.126		.318	.234	.38	.238	2
5/16-24		.394					.254			2
3/8-16	2.94	.551	.748	1.252		.381	.287	.44	.286	2
3/8-24		.394					.316			2
7/16-14	3.16	.591	.866	1.850	1.437	.323	.311	.41	.242	3
7/16-20		.472								3
1/2-13	3.38	.630	.984	2.067	1.657	.367	.354	.44	.275	3
1/2-20		.472								3
9/16-12	3.59	.709	.984	2.067	1.657	.429	.417	.50	.322	3
9/16-18		.512								3
5/8-11	3.81	.748	1.083	2.205	1.811	.480	.469	.56	.360	3
5/8-18		.512								3
3/4-10	4.25	.827	1.201	2.480	2.000	.590	.577	.69	.442	3
3/4-10		.591								3
7/8-9	4.69	.827	1.339	2.815	2.220	.697	.685	.75	.523	3
7/8-14		.709								3
1-8	5.13	.984	1.496	3.091	2.500	.800	.787	.81	.600	3
1-12		.709								3
1-1/8-7	5.44	1.024	1.535	3.15	2.563	.896	.878	.88	.672	3
1-1/8-12		.787								3
1-1/4-7	5.75	1.024	1.535	3.15	2.563	1.021	1.002	1.00	.766	3
1-1/4-12		.787								3
1-3/8-6	6.06	1.181	1.791	3.583	3.000	1.108	1.089	1.06	.831	3
1-3/8-12		.866								3
1-1/2-6	6.38	1.181	1.791	3.583	3.000	1.233	1.213	1.13	.925	3
1-1/2-12		.866								3

*SF : Spiral Fluted Taps
 *SP : Spiral Pointed Taps

3 MODI TAP BLANK DIMENSION - METRIC




Metric Tap Blank

Nominal Size	Overall Length [L]	Thread Length		Length to neck		Shank Diameter [D]	Neck Diameter [d1]	Square Length [L3]	Square Size [a]	Blank Design No.
		SF	SP	SF	SP					
M3	1.94	.197	.374	.646		.141	.090	.19	.110	1
M3.5	2.00	.276	.413	.646		.141	.104	.19	.110	1
M4	2.13	.276	.453	.768		.168	.119	.25	.131	1
M4.5	2.38	.354	.531	.933		.194	.135	.25	.152	1
M5	2.38	.354	.531	.933		.194	.152	.25	.152	1
M5.5	2.38	.354	.571	1.000		.220	.189	.28	.165	2
M6	2.50	.433	.591	1.000		.255	.181	.31	.191	2
M7	2.72	.433	.669	1.126		.318	.220	.38	.238	2
M8x 1.25	2.72	.472	.669	1.126		.318	.246	.38	.238	2
M8x 1.0		.433								2
M10x 1.5	2.94	.512	.748	1.252		.381	.310	.44	.286	2
M10x 1.25		.472								2
M12x 1.75	3.38	.591	.984	2.067	1.657	.367	.354	.44	.275	3
M12x 1.25		.551								3
M14x 2.0	3.59	.709	.984	2.067	1.657	.429	.417	.50	.322	3
M14x 1.5		.551								3
M16x 2.0	3.81	.709	1.083	2.205	1.811	.480	.469	.56	.360	3
M16x 1.5		.551								3
M18x 2.5	4.03	.787	1.083	2.205	1.811	.542	.530	.63	.406	3
M18x 1.5		.551								3
M20x 1.5	4.47	.551	1.201	2.48	2.000	.652	.64	.69	.489	3
M20x 2.5		.787								3
M22x 1.5	4.69	.551	1.339	2.815	2.220	.697	.685	.75	.523	3
M22x 2.5		.787								3
M24x 1.5	4.91	.551	1.339	2.815	2.220	.760	.748	.75	.57	3
M24x 3		.945								3
M27x 1.5	5.13	.591	1.496	3.091	2.500	.896	.878	.88	.672	3
M27x 3		.945								3
M30x 1.5	5.44	.591	1.713	3.15	2.854	1.021	1.002	1.00	.766	3
M30x 3.5		1.102								3

*SF : Spiral Fluted Taps
*SP : Spiral Pointed Taps


4 HIGH PERFORMANCE TAPS DIN LENGTH / ANSI SHANK - INCH



Nominal Size	Overall Length [L]	Thread Length		Length to neck		Shank Diameter [D]	Neck Diameter [d1]	Square Length [L3]	Square Size [a]	Blank Design No.
		SF	SP	SF	SP					
#2	1.772	.157	.256	.433		.141	.061	.19	.110	1
#3	1.969	.197	.295	.492		.141	.069	.19	.110	1
#4	2.205	.236	.335	.563		.141	.077	.19	.110	1
#5	2.205	.236	.374	.626		.141	.090	.19	.110	1
#6	2.205	.276	.413	.689		.141	.094	.19	.110	1
#8	2.480	.276	.453	.752		.168	.120	.25	.131	1
#10-24	2.756	.354	.531	.906		.194	.131	.25	.152	1
#10-32		.276					1			
#12-24	3.150	.354	.571	.906		.220	.157	.28	.165	1
#12-28		.276					1			
1/4-20	3.150	.433	.591	1.000		.255	.180	.31	.191	2
1/4-28		.354					2			
5/16-18	3.543	.472	.669	1.126		.318	.234	.38	.238	2
5/16-24		.394					2			
3/8-16	3.937	.551	.748	1.252		.381	.287	.44	.286	2
3/8-24		.394					2			
7/16-14	3.937	.591	.866	1.850	1.437	.323	.311	.41	.242	3
7/16-20		.472					3			
1/2-13	4.331	.630	.984	2.067	1.657	.367	.354	.44	.275	3
1/2-20	3.937	.472	.984	2.067	1.657	.367	.354	.44	.275	3
9/16-12	4.331	.709	.984	2.067	1.657	.429	.417	.50	.322	3
9/16-18	3.937	.512	.984	2.067	1.657	.429	.417	.50	.322	3
5/8-11	4.331	.748	1.083	2.205	1.811	.480	.469	.56	.360	3
5/8-18	3.937	.512	1.083	2.205	1.811	.480	.469	.56	.360	3
3/4-10	4.921	.827	1.201	2.480	2.000	.590	.577	.69	.442	3
3/4-10	4.331	.591	1.201	2.480	2.000	.590	.577	.69	.442	3
7/8-9	5.512	.827	1.339	2.815	2.220	.697	.685	.75	.523	3
7/8-14	4.921	.709	1.339	2.815	2.220	.697	.685	.75	.523	3
1-8	6.299	.984	1.496	3.091	2.500	.800	.787	.81	.600	3
1-12	5.512	.709	1.496	3.091	2.500	.800	.787	.81	.600	3

*SF : Spiral Fluted Taps
*SP : Spiral Pointed Taps


5 HIGH PERFORMANCE TAPS DIN LENGTH / ANSI SHANK - METRIC



Nominal Size	Overall Length [L]	Thread Length [L1]		Length to neck [L2]		Shank Diameter [D]	Neck Diameter [d1]	Square Length [L3]	Square Size [a]	Blank Design No.
		SF	SP	SF	SP					
M3	2.205	.197	.374	.646		.141	.090	.19	.110	1
M3.5	2.205	.276	.413	.646		.141	.104	.19	.110	1
M4	2.480	.276	.453	.768		.168	.119	.25	.131	1
M5	2.756	.354	.531	.933		.194	.152	.25	.152	1
M6	3.150	.433	.591	1.000		.255	.181	.28	.191	2
M8x 1.25	3.543	.472	.669	1.126		.318	.246	.38	.238	2
M8x 1.0		.433								2
M10x 1.5	3.937	.512	.748	1.252		.381	.310	.44	.286	2
M10x 1.25		.472								2
M12x 1.75	4.331	.591	.984	2.067	1.657	.367	.354	.44	.275	3
M12x 1.25	3.937	.551	.984	2.067	1.657	.429	.417	.50	.322	3
M14x 2.0	4.331	.709	.984	2.067	1.657	.429	.417	.50	.322	3
M14x 1.5	3.937	.551	.984	2.067	1.657	.429	.417	.50	.322	3
M16x 2.0	4.331	.709	1.083	2.205	1.811	.480	.469	.56	.360	3
M16x 1.5	3.937	.551	1.083	2.205	1.811	.480	.469	.56	.360	3
M18x 2.5	4.921	.787	1.083	2.205	1.811	.542	.530	.63	.406	3
M18x 1.5	4.331	.551	1.083	2.205	1.811	.542	.530	.63	.406	3

*SF : Spiral Fluted Taps
*SP : Spiral Pointed Taps

6 YG-1 USCTI 302 TAP BLANK DIMENSION




Unified Tap Blank

Nominal Size	Overall Length [L]	Thread Length [L1]	Shank Diameter [D]	Square Length [L3]	Square Size [a]	Blank Design No.
#0	1.63	.31	.141	.19	.110	1
#1	1.69	.38	.141	.19	.110	1
#2	1.75	.44	.141	.19	.110	1
#3	1.81	.50	.141	.19	.110	1
#4	1.88	.56	.141	.19	.110	1
#5	1.94	.63	.141	.19	.110	1
#6	2.00	.69	.141	.19	.110	1
#8	2.13	.75	.168	.25	.131	1
#10	2.38	.88	.194	.25	.152	1
#12	2.38	.94	.220	.28	.165	1
1/4	2.50	1.00	.255	.31	.191	2
5/16	2.72	1.13	.318	.38	.238	2
3/8	2.94	1.25	.381	.44	.286	2
7/16	3.16	1.44	.323	.41	.242	3
1/2	3.38	1.66	.367	.44	.275	3
9/16	3.59	1.66	.429	.50	.322	3
5/8	3.81	1.81	.480	.56	.360	3
11/16	4.03	1.81	.542	.63	.406	3
3/4	4.25	2.00	.590	.69	.442	3
13/16	4.47	2.00	.652	.69	.489	3
7/8	4.69	2.22	.697	.75	.523	3
15/16	4.91	2.22	.760	.75	.570	3
1	5.13	2.50	.800	.81	.600	3
1-1/8	5.44	2.56	.896	.88	.672	3
1-1/4	5.75	2.56	1.021	1.00	.766	3
1-3/8	6.06	3.00	1.108	1.06	.831	3
1-1/2	6.38	3.00	1.233	1.13	.925	3

Metric Tap Blank

Nominal Size	Overall Length [L]	Thread Length [L1]	Shank Diameter [D]	Square Length [L3]	Square Size [a]	Blank Design No.
M1.6	1.63	.310	.141	.19	.110	1
M1.8	1.69	.380	.141	.19	.110	1
M2	1.75	.440	.141	.19	.110	1
M2.5	1.81	.500	.141	.19	.110	1
M3	1.94	.630	.141	.19	.110	1
M3.5	2.00	.690	.141	.19	.110	1
M4	2.13	.750	.168	.25	.131	1
M4.5	2.38	.880	.194	.25	.152	1
M5	2.38	.880	.194	.25	.152	1
M6	2.50	1.00	.255	.31	.191	2
M7	2.72	1.13	.318	.38	.238	2
M8	2.72	1.13	.318	.38	.238	2
M10	2.94	1.25	.381	.44	.286	2
M12	3.38	1.66	.367	.44	.275	3
M14	3.59	1.66	.429	.50	.322	3
M16	3.81	1.81	.480	.56	.360	3
M18	4.03	1.81	.542	.63	.406	3
M20	4.47	2.00	.652	.69	.489	3
M22	4.69	2.22	.697	.75	.523	3
M24	4.91	2.22	.760	.75	.570	3
M30	5.44	2.56	1.021	1.00	.766	3
M33	5.75	2.56	1.108	1.06	.831	3
M36	6.06	3.00	1.233	1.13	.925	3

7 STANDARD PIPE TAP DIMENSION (STRAIGHT AND TAPER, GROUND THREAD)




Blank Design (1)

Blank Design (2)

Blank Design (3)

Nominal Size	Overall Length	Thread Length	Shank Diameter	Square Length	Square Size	Optional Neck Length
	[L]	[L ₁]				[L ₂]
1/16	2.13	.69	.3125	.38	.234	.375
1/8	2.13	.75	.3125	.38	.234	...
1/8	2.13	.75	.4375	.38	.328	.375
1/4	2.44	1.06	.5625	.44	.421	.375
3/8	2.56	1.06	.7000	.50	.531	.375
1/2	3.13	1.38	.6875	.63	.515	...
3/4	3.25	1.38	.9063	.69	.679	...
1	3.75	1.75	1.1250	.81	.843	...
1-1/4	4.00	1.75	1.3125	.94	.984	...
1-1/2	4.25	1.75	1.5000	1.00	1.125	...
2	4.25	1.75	1.8750	1.13	1.406	...
2-1/2	5.50	2.56	2.2500	1.25	1.687	...
3	6.00	2.63	2.6250	1.38	1.968	...
3-1/2	6.50	2.69	2.8125	1.50	2.108	...
4	6.75	2.75	3.0000	1.56	2.250	...

8 STANDARD FORMING TAP DIMENSION



Blank Design (1)

Blank Design (2)

Blank Design (3)


Forming Tap Blank (Inch)

Nominal Size	Overall Length	Thread Length	Neck Length	Shank Diameter	Square Length	Square Size	Blank Design No.
	[L]	[L ₁]	[L ₂]				
#0	1.63	.31	-	.141	.19	.110	1
#1	1.69	.38	-	.141	.19	.110	1
#2	1.75	.44	-	.141	.19	.110	1
#3	1.81	.50	-	.141	.19	.110	1
#4	1.88	.56	-	.141	.19	.110	1
#5	1.94	.63	-	.141	.19	.110	1
#6	2.00	.48	.69	.141	.19	.110	1
#8	2.13	.50	.75	.168	.25	.131	1
#10	2.38	.63	.88	.194	.25	.152	1
#12	2.38	.63	.94	.220	.28	.165	1
1/4	2.50	.86	1.00	.255	.31	.191	2
5/16	2.72	.93	1.13	.318	.38	.238	2
3/8	2.94	.98	1.25	.381	.44	.286	2
7/16	3.16	.95	1.44	.323	.41	.242	3
1/2	3.38	1.00	1.60	.367	.44	.275	3
9/16	3.59	1.00	1.66	.429	.50	.322	3
5/8	3.81	1.00	1.81	.480	.56	.360	3
3/4	4.25	1.00	2.0	.590	.69	.442	3

Forming Tap Blank (Metric)

Nominal Size	Overall Length	Thread Length	Neck Length	Shank Diameter	Square Length	Square Size	Blank Design No.
	[L]	[L ₁]	[L ₂]				
M2	1.75	.40	-	.141	.19	.110	1
M3	1.94	.63	-	.141	.19	.110	1
M4	2.13	.50	.75	.168	.25	.131	1
M5	2.38	.63	.88	.194	.25	.152	1
M6	2.50	.86	1.0	.255	.31	.191	2
M8	2.72	.93	1.13	.318	.38	.238	2
M10	2.94	.98	1.25	.381	.44	.286	2
M12	3.38	1.00	1.60	.367	.44	.275	3

9 STI STRAIGHT TAP DIMENSION




STI Tap blank (Inch)

Nominal Size (STI)	Threads per Inch		Overall Length (L)	Thread Length (L ₂)	Shank Diameter (D)	Square Length (L ₃)	Square Size (a)	Blank Design No.	Table 302 Blank Equivalent
	UNC	UNF							
	#2	56							
#2		64	1.88	.560	.141	.190	.110	1	No.4
#3	48	-	1.94	.630	.141	.190	.110	1	No.5
#3		56	1.94	.630	.141	.190	.110	1	No.5
#4	40	-	2.00	.690	.141	.190	.110	1	No.6
#4		48	2.00	.690	.141	.190	.110	1	No.6
#5	40	-	2.13	.750	.168	.250	.131	1	No.8
#6	32	-	2.38	.880	.194	.250	.152	1	No.10
#6		40	2.13	.750	.168	.250	.131	1	No.8
#8	32	-	2.38	.940	.220	.280	.165	1	No.12
#8		36	2.38	.940	.220	.280	.165	1	No.12
#10	24	-	2.50	1.000	.255	.310	.191	2	1/4
#10		32	2.50	1.000	.255	.310	.191	2	1/4
#12	24	-	2.72	1.130	.318	.380	.238	2	5/16
1/4	20	-	2.72	1.130	.318	.380	.238	2	5/16
1/4		28	2.72	1.130	.318	.380	.238	2	5/16
5/16	18	-	2.94	1.250	.381	.440	.286	2	3/8
5/16		24	2.94	1.250	.381	.440	.286	2	3/8
3/8	16	-	3.38	1.660	.367	.440	.275	3	1/2
3/8		24	3.16	1.440	.323	.410	.242	3	7/16
7/16	14	-	3.59	1.660	.429	.500	.322	3	9/16
7/16		20	3.38	1.660	.367	.440	.275	3	1/2
1/2	13	-	3.81	1.810	.480	.560	.360	3	5/8
1/2		20	3.59	1.660	.429	.500	.322	3	9/16

STI Tap blank (Metric)

Nominal Size (STI)	Thread Pitch (mm)	Overall Length (L)	Thread Length (L ₂)	Shank Diameter (D)	Square Length (L ₃)	Square Size (a)	Blank Design No.	Table 302 Blank Equivalent									
									M2	0.4	1.81	.50	.141	.190	.110	1	No.3
									M2.5	0.45	1.94	.630	.141	.190	.110	1	No.5
M3	0.5	2.00	.690	.141	.190	.110	1	No.6									
M4	0.7	2.38	.880	.194	.250	.152	1	No.10									
M5	0.8	2.50	1.000	.255	.310	.191	2	1/4									
M6	1	2.72	1.130	.318	.380	.238	2	5/16									
M8	1.25	2.94	1.250	.381	.440	.286	2	3/8									
M10	1.5	3.38	1.660	.367	.440	.275	3	1/2									
M12	1.75	3.59	1.660	.429	.500	.322	3	9/16									

10 STI SPIRAL FLUTE & SPIRAL POINT TAP DIMENSION



STI Tap blank (Inch)

Nominal Size (STI)	Threads per Inch		Overall Length (L)	Thread Length		Neck Length (L ₂)	Shank Diameter (D)	Square Length (L ₃)	Square Size (a)	Blank Design No.	Table 302 Blank Equivalent
	UNC	UNF		SP	SF						
	#2	56		-	1.88						
#2		64	1.88	.335	.236	.56	.141	.190	.110	1	No.4
#3	48	-	1.94	.374	.236	.63	.141	.190	.110	1	No.5
#3		56	1.94	.374	.236	.63	.141	.190	.110	1	No.5
#4	40	-	2.00	.413	.276	.68	.141	.190	.110	1	No.6
#4		48	2.00	.413	.276	.68	.141	.190	.110	1	No.6
#5	40	-	2.13	.453	.276	.75	.168	.250	.131	1	No.8
#6	32	-	2.38	.531	.354	.88	.194	.250	.152	1	No.10
#6		40	2.13	.453	.276	.75	.168	.250	.131	1	No.8
#8	32	-	2.38	.571	.354	.94	.220	.280	.165	1	No.12
#8		36	2.38	.571	.354	.94	.220	.280	.165	1	No.12
#10	24	-	2.50	.591	.433	1.0	.255	.310	.191	2	1/4
#10		32	2.50	.591	.433	1.0	.255	.310	.191	2	1/4
#12	24	-	2.72	.669	.472	1.13	.318	.380	.238	2	5/16
1/4	20	-	2.72	.669	.472	1.13	.318	.380	.238	2	5/16
1/4		28	2.72	.669	.472	1.13	.318	.380	.238	2	5/16
5/16	18	-	2.94	.748	.551	1.25	.381	.440	.286	2	3/8
5/16		24	2.94	.748	.551	1.25	.381	.440	.286	2	3/8
3/8	16	-	3.38	.984	.630	1.66	.367	.440	.275	3	1/2
3/8		24	3.16	.866	.591	1.44	.323	.410	.242	3	7/16
7/16	14	-	3.59	.984	.709	1.66	.429	.500	.322	3	9/16
7/16		20	3.38	.984	.630	1.66	.367	.440	.275	3	1/2
1/2	13	-	3.81	1.083	.748	1.81	.480	.560	.360	3	5/8
1/2		20	3.59	.984	.709	1.66	.429	.500	.322	3	9/16

STI Tap blank (Metric)

Nominal Size (STI)	Thread Pitch (mm)	Overall Length (L)	Thread Length		Neck Length (L ₂)	Shank Diameter (D)	Square Length (L ₃)	Square Size (a)	Blank Design No.	Table 302 Blank Equivalent
			SP	SF						
			M2	0.4						
M2.5	0.45	1.94	.374	.197	.63	.141	.190	.110	1	No.5
M3	0.5	2.00	.413	.276	.69	.141	.190	.110	1	No.6
M4	0.7	2.38	.531	.354	.93	.194	.250	.152	1	No.10
M5	0.8	2.50	.591	.433	1.0	.255	.310	.191	2	1/4
M6	1	2.72	.669	.433	1.13	.318	.380	.238	2	5/16
M8	1.25	2.94	.748	.512	1.25	.381	.440	.286	2	3/8
M10	1.5	3.38	.984	.591	2.07	.367	.440	.275	3	1/2
M12	1.75	3.59	.984	.709	2.07	.429	.500	.322	3	9/16



11 TAP RECOMMENDATIONS FOR CLASSES OF THREAD - INCH

Internal Screw Thread Classes and Tap Recommendations

Size	Threads per Inch		Recommended Tap for Class of Thread				Pitch Diameter Limits for Class of Thread				
	UNC	UNF	Unified Class of Thread		American National Class of Thread		Min. All Class (Basic)	Unified Class of Thread		American National Class of Thread	
			Class 2	Class 3	Class 2B	Class 3B		Max. Class 2	Max. Class 3	Max. Class 2B	Max. Class 3B
#0	-	80	GH1	GH1	GH2	GH1	.0519	.0536	.0532	.0542	.0536
#1	64	-	GH1	GH1	GH2	GH1	.0629	.0648	.0643	.0655	.0648
#1	-	72	GH1	GH1	GH2	GH1	.0640	.0658	.0653	.0665	.0659
#2	56	-	GH1	GH1	GH2	GH1	.0744	.0764	.0759	.0772	.0765
#2	-	64	GH1	GH1	GH2	GH1	.0759	.0778	.0773	.0786	.0779
#3	48	-	GH1	GH1	GH2	GH1	.0855	.0877	.0871	.0885	.0877
#3	-	56	GH1	GH1	GH2	GH1	.0874	.0894	.8890	.0902	.0895
#4	40	-	GH2	GH1	GH2	GH2	.0958	.0982	.0975	.0991	.0982
#4	-	48	GH1	GH1	GH2	GH1	.0985	.1007	.1001	.1016	.1008
#5	40	-	GH2	GH1	GH2	GH2	.1088	.1112	.1105	.1121	.1113
#5	-	44	GH1	GH1	GH2	GH1	.1102	.1125	.1118	.1134	.1126
#6	32	-	GH2	GH1	GH3	GH2	.1177	.1204	.1196	.1214	.1204
#6	-	40	GH2	GH1	GH2	GH2	.1218	.1242	.1235	.1252	.1243
#8	32	-	GH2	GH1	GH3	GH2	.1437	.1464	.1456	.1475	.1465
#8	-	36	GH2	GH1	GH2	GH2	.1460	.1485	.1478	.1496	.1487
#10	24	-	GH3	GH1	GH3	GH3	.1629	.1662	.1653	.1672	.1661
#10	-	32	GH2	GH1	GH3	GH2	.1697	.1724	.1716	.1736	.1726
#12	24	-	GH3	GH1	GH3	GH3	.1889	.1922	.1913	.1933	.1922
#12	-	28	GH3	GH1	GH3	GH3	.1928	.1959	.1950	.1970	.1959
1/4	20	-	GH3	GH2	GH5	GH3	.2175	.2211	.2201	.2223	.2211
1/4	-	28	GH3	GH1	GH4	GH3	.2268	.2299	.2290	.2311	.2300
5/16	18	-	GH3	GH2	GH5	GH3	.2764	.2805	.2794	.2817	.2803
5/16	-	24	GH3	GH1	GH4	GH3	.2854	.2887	.2878	.2902	.2890
3/8	16	-	GH3	GH2	GH5	GH3	.3344	.3389	.3376	.3401	.3387
3/8	-	24	GH3	GH1	GH4	GH3	.3479	.3512	.3503	.3528	.3516
7/16	14	-	GH5	GH3	GH5	GH3	.3911	.3960	.3947	.3972	.3957
7/16	-	20	GH3	GH1	GH5	GH3	.4050	.4086	.4076	.4104	.4091
1/2	13	-	GH5	GH3	GH5	GH3	.4500	.4552	.4537	.4565	.4548
1/2	-	20	GH3	GH1	GH5	GH3	.4675	.4711	.4701	.4731	.4717
9/16	12	-	GH5	GH3	GH5	GH3	.5084	.5140	.5124	.5152	.5135
9/16	-	18	GH3	GH2	GH5	GH3	.5264	.5305	.5294	.5323	.5308
5/8	11	-	GH5	GH3	GH5	GH3	.5660	.5719	.5702	.5732	.5714
5/8	-	18	GH3	GH2	GH5	GH3	.5889	.5930	.5919	.5949	.5934
3/4	10	-	GH5	GH3	GH5	GH3	.6850	.6914	.6895	.6927	.6907
3/4	-	16	GH3	GH2	GH5	GH3	.7094	.7139	.7126	.7159	.7143
7/8	9	-	GH6	GH4	GH6	GH4	.8028	.8098	.8077	.8110	.8089
7/8	-	14	GH4	GH2	GH6	GH4	.8286	.8335	.8322	.8356	.8339
1	8	-	GH6	GH4	GH6	GH4	.9188	.9264	.9242	.9276	.9254
1	-	12	GH4	GH2	GH6	GH4	.9459	.9515	.9499	.9535	.9516

The above recommended taps normally produce the Class of Thread indicated in average materials when used with reasonable care. However, if the tap specified does not give a satisfactory gage fit in the work, a choice of some other limit tap will be necessary.



12 TAP RECOMMENDATIONS FOR CLASSES OF THREAD - METRIC

Size	Pitch	Recommended Tap for Class of Thread		Pitch Diameter Limits for Class of Thread (mm)			Pitch Diameter Limits for Class of Thread (inch)		
		4H	6H	Min. (Basic)	Max. 4H	Max. 6H	Min. (Basic)	Max. 4H	Max. 6H
M1.6	0.35	D1	D3	1.373	1.426	1.458	.05406	.05614	.05740
M2	0.40	D1	D3	1.740	1.796	1.830	.06850	.07071	.07205
M2.5	0.45	D1	D3	2.208	2.268	2.303	.08693	.08929	.09067
M3	0.50	D1	D3	2.675	2.738	2.775	.10531	.10780	.10925
M3.5	0.60	D1	D4	3.110	3.181	3.222	.12244	.12524	.12685
M4	0.70	D2	D4	3.545	3.620	3.663	.13957	.14252	.14421
M4.5	0.75	D2	D4	4.013	4.088	4.131	.15789	.16094	.16264
M5	0.80	D2	D4	4.480	4.560	4.605	.17638	.17953	.18130
M6	1.00	D3	D5	5.350	5.445	5.500	.21063	.21437	.21654
M7	1.00	D3	D5	6.350	6.445	6.500	.25000	.25374	.25591
M8	1.25	D3	D5	7.188	7.288	7.348	.28299	.28693	.28929
M10	1.50	D3	D6	9.026	9.138	9.206	.35535	.35976	.36244
M12	1.75	D3	D6	10.863	10.988	11.063	.42768	.43260	.43555
M14	2.00	D3	D7	12.701	12.833	12.913	.50004	.50524	.50839
M16	2.00	D4	D7	14.701	14.833	14.913	.57878	.58398	.58713
M20	2.50	D4	D7	18.376	18.516	18.600	.72346	.72898	.73228
M24	3.00	D4	D8	22.051	22.221	22.316	.86815	.87484	.87858
M30	3.50	D5	D9	27.727	27.907	28.007	1.09161	1.0987	1.10264
M36	4.00	D5	D9	33.402	33.592	33.702	1.31504	1.32252	1.32685

13 TOLERANCE CHART - USCTI

Element	Nominal Diameter Range in Inches		Direction	Tolerance (Inches)
	Over	To (Inc.)		
Overall Length - L	.0520	1.0100	Plus or Minus	.031
	1.0100	4.0100	Plus or Minus	.063
Thread Length - L1	.0520	.2230	Plus or Minus	.047
	.2230	.5100	Plus or Minus	.063
	.5100	1.5100	Plus or Minus	.094
Square Length - L3	1.5100	4.0100	Plus or Minus	.125
	.0520	1.0100	Plus or Minus	.031
Shank Diameter - D	1.0100	4.0100	Plus or Minus	.063
	.0520	.2230	Minus	.0015
	.2230	.6350	Minus	.0015
	.6350	1.0100	Minus	.0020
	1.0100	1.5100	Minus	.0020
	1.5100	2.0100	Minus	.0030
Square Size - a	2.0100	4.0100	Minus	.0030
	.0520	.5100	Minus	.004
	.5100	1.0100	Minus	.006
	1.0100	2.0100	Minus	.008
	2.0100	4.0100	Minus	.010

14 THREAD LIMITS

Unified Thread, Machine Screw Size - Ground Thread

Size	Thread per Inch			Major Diameter (Inches)			Pitch Diameter Limits (Inches)									
	UNC	UNF	UNS	Basic	Min.	Max.	Basic Pitch Dia.	H1 Limit		H2 Limit		H3 Limit		H7 Limit		
								Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.	
#0	-	80	-	.0600	.0605	.0615	.0519	.0519	.0524	.0524	.0529	-	-	-	-	
#1	64	-	-	.0730	.0735	.0745	.0629	.0629	.0634	.0634	.0639	-	-	-	-	
	-	72	-	.0730	.0735	.0745	.0640	.0640	.0645	.0645	.0650	-	-	-	-	
#2	56	-	-	.0860	.0865	.0875	.0744	.0744	.0749	.0749	.0754	-	-	-	-	
	-	64	-	.0860	.0865	.0875	.0759	-	-	.0764	.0769	-	-	-	-	
#3	48	-	-	.0990	.0100	.1010	.0855	.0855	.0860	.0860	.0865	-	-	-	-	
	-	56	-	.0990	.0995	.1005	.0874	.0874	.0879	.0879	.0884	-	-	-	-	
#4	-	-	36	.1120	.1135	.1145	.0940	-	-	.0945	.0950	-	-	-	-	
	40	-	-	.1120	.1135	.1145	.0958	.0958	.0963	.0963	.0968	-	-	-	-	
#5	-	48	-	.1250	.1265	.1275	.1088	.1088	.1093	.1093	.1098	-	-	-	-	
	40	-	-	.1250	.1260	.1270	.1102	-	-	.1107	.1112	-	-	-	-	
#6	32	-	-	.1380	.1400	.1410	.1177	.1177	.1182	.1182	.1187	.1187	.1192	.1207	.1212	
	-	40	-	.1380	.1395	.1405	.1218	.1218	.1223	.1223	.1228	-	-	-	-	
#8	32	-	-	.1640	.1660	.1670	.1437	.1437	.1442	.1442	.1447	.1447	.1452	.1467	.1472	
	-	36	-	.1640	.1655	.1665	.1460	-	-	.1465	.1470	-	-	-	-	
#10	24	-	-	.1900	.1930	.1940	.1629	.1629	.1634	.1634	.1639	.1639	.1644	.1659	.1664	
	-	32	-	.1900	.1920	.1930	.1697	.1697	.1702	.1702	.1707	.1707	.1712	.1727	.1732	
#12	24	-	-	.2160	.2190	.2200	.1889	-	-	-	-	.1899	.1904	-	-	
	-	28	-	.2160	.2185	.2195	.1928	-	-	-	-	.1938	.1943	-	-	

Lead Tolerance

A maximum lead deviation of plus or minus .0005" within any two threads not farther apart than 1" is permitted

Pitch Diameter Limits

- H1 = Basic to basic plus .0005"
- H2 = Basic plus .0005" to basic plus .001"
- H3 = Basic plus .001" to basic plus .0015"
- H7 = Basic plus .003" to basic plus .0035"

Angle Tolerance

24 to 80 threads per inch incl. = 30 plus or minus in 1/2 angle.

Unified Thread, Machine Screw Size - Ground Thread

Size	Thread per Inch			Major Diameter (Inches)			Pitch Diameter Limits (Inches)												
	UNC	UNF	UNS	Basic	Min.	Max.	Basic Pitch Dia.	H1 Limit		H2 Limit		H3 Limit		H4 Limit		H5 Limit		H6 Limit	
								Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.		
1/4	20	-	-	.2500	.2540	.2550	.2175	.2175	.2180	.2180	.2185	.2185	.2190	-	-	.2195	.2200	-	-
	-	28	-	.2500	.2525	.2535	.2268	.2268	.2273	.2273	.2278	.2278	.2283	.2283	.2288	-	-	-	-
5/16	18	-	-	.3125	.3170	.3180	.2764	.2764	.2769	.2769	.2774	.2774	.2779	-	-	.2784	.2789	-	-
	-	24	-	.3125	.3155	.3165	.2854	.2854	.2859	.2859	.2864	.2864	.2869	.2869	.2874	-	-	-	-
3/8	16	-	-	.3750	.3800	.3810	.3344	.3344	.3349	.3349	.3354	.3354	.3359	-	-	.3364	.3369	-	-
	-	24	-	.3750	.3780	.3790	.3479	.3479	.3484	.3484	.3489	.3489	.3494	.3494	.3499	-	-	-	-
7/16	14	-	-	.4375	.4435	.4445	.3911	-	-	.3916	.3921	.3921	.3926	-	-	.3931	.3936	-	-
	-	20	-	.4375	.4415	.4425	.4050	-	-	-	-	.4060	.4065	-	-	.4070	.4075	-	-
1/2	13	-	-	.5000	.5065	.5075	.4500	.4500	.4505	.4505	.4510	.4510	.4515	-	-	.4520	.4525	-	-
	-	20	-	.5000	.5040	.5050	.4675	.4675	.4680	.4680	.4685	.4685	.4690	-	-	.4695	.4700	-	-
9/16	12	-	-	.5625	.5690	.5700	.5084	-	-	.5089	.5094	.5094	.5099	-	-	.5104	.5109	-	-
	-	18	-	.5625	.5670	.5680	.5264	-	-	.5269	.5274	.5274	.5279	-	-	.5284	.5289	-	-
5/8	11	-	-	.6250	.6320	.6330	.5660	-	-	.5665	.5670	.5670	.5675	-	-	.5680	.5685	-	-
	-	18	-	.6250	.6295	.6305	.5889	-	-	.5894	.5899	.5899	.5904	-	-	.5909	.5914	-	-
11/16	-	-	11	.6875	.6945	.6955	.6285	-	-	-	-	.6295	.6300	-	-	-	-	-	-
	-	-	16	.6875	.6925	.6935	.6469	-	-	.6855	.6860	.6479	.6484	-	-	-	-	-	-
3/4	10	-	-	.7500	.7525	.7590	.6850	.6850	.6855	.7099	.7104	.6860	.6865	-	-	.6870	.6875	-	-
	-	16	-	.7500	.7550	.7560	.7094	.7094	.7099	-	-	.7104	.7109	-	-	.7114	.7119	.8053	-
7/8	9	-	-	.8750	.8835	.8850	.8028	-	-	.8291	.8296	-	-	.8043	.8048	-	-	.8311	.8058
	-	14	-	.8750	.8810	.8820	.8286	-	-	.9193	.9198	-	-	.8301	.8306	-	-	.9213	.8318
1	8	-	-	1.0000	1.0095	1.0110	.9188	-	-	-	-	-	-	.9203	.9208	-	-	-	.9218
	-	12	-	1.0000	1.0065	1.0075	.9459	-	-	-	-	-	-	.9474	.9479	-	-	-	-
1	-	-	14	1.0000	1.0060	1.0070	.9536	-	-	-	-	-	-	.9551	.9556	-	-	-	-

Lead Tolerance

A maximum lead deviation of plus or minus .0005" within any two threads not farther apart than 1" is permitted

Pitch Diameter Limits

- H1 = Basic to basic plus .0005"
- H2 = Basic plus .0005" to basic plus .001"
- H3 = Basic plus .001" to basic plus .0015"
- H4 = Basic plus .0015" to basic plus .0020"
- H5 = Basic plus .0020" to basic plus .0025"
- H6 = Basic plus .0025" to basic plus .0030"

Angle Tolerance

Threads per Inch	Deviation in Half Angle
6 to 9 Incl.	25' Plus or Minus
10 to 28 Incl.	30' Plus or Minus



Metric Thread - Ground Thread

Table with columns: Size, Pitch (Coarse, Fine), Major Diameter (Inches) (Basic, Min., Max.), and Pitch Diameter Limits (Inches) (D2, D3, D4, D5, D6) (Min., Max.).

Lead Tolerance

The tap major and pitch diameter conversions have been rounded upward. A maximum lead deviation of +/- .0005" within any two threads not further apart than 1" is permitted

Angle Tolerance

Table with columns: Pitch(mm) and Deviation in Half Angle. Rows: Over 0.25 to 2.5 Incl. (30' Plus or Minus), Over 2.5 to 4.0 Incl. (25' Plus or Minus)




Metric Thread - Ground Thread

Table with columns: Size, Pitch (Coarse, Fine), Major Diameter (Inches) (Basic, Min., Max.), and Pitch Diameter Limits (Inches) (D2, D3, D4, D5) (Min., Max.).

Pipe Tap (Limit)

Nominal Size Inches	Threads per Inch	Tap Thread Limits		Taper per Foot Limits		Reference Dimensions	
		Projection* Inches	Projection Tolerance + or -	Min.	Max.	Length (L ₁)	Tap Drill Size** NPT, ANPT, NPTF
1/16	27	.312	.063	.719	.781	.160	C
1/8	27	.312	.063	.719	.781	.1615	Q
1/8	18	.459	.063	.719	.781	.2278	7/16
3/8	18	.454	.063	.719	.781	.240	9/16
1/2	14	.579	.063	.719	.781	.320	45/64
3/4	14	.565	.063	.719	.781	.339	29/32
1	11-1/2	.678	.094	.719	.781	.400	1-9/64
1-1/4	11-1/2	.686	.094	.719	.781	.420	1-31/64
1-1/2	11-1/2	.699	.094	.719	.781	.420	1-23/32
2	11-1/2	.667	.094	.719	.781	.436	2-3/16
2-1/2	8	.925	.094	.734	.781	.682	2-39/64
3	8	.925	.094	.734	.781	.766	3-15/64
3-1/2	8	.938	.125	.734	.781	.821	...
4	8	.950	.125	.734	.781	.844	...

* Distance small end of tap projects through L1 Taper Thread Ring Gage.
 ** Recommended size given permit direct tapping without reaming the hole, but only give a full thread for approx. the L1 length.



15 TAP DRILL SIZES - UNIFIED THREAD

Size	Threads Per Inch				Minor Diameter			Tap Drill Diameter (Cutting Tap)				
	UNC	UNF	UNEF	UN	Min. 2B&3B	Max. 2B	Max. 3B	80% Thread	75% Thread	70% Thread	65% Thread	60% Thread
#0	-	80	-	-	.0465	.0514	.0514	.0470	.0478	.0486	.0494	.0503
#1	64	-	-	-	.0561	.0623	.0623	.0568	.0578	.0588	.0598	.0608
	-	72	-	-	.0580	.0635	.0635	.0586	.0595	.0604	.0613	.0622
#2	56	-	-	-	.0667	.0737	.0737	.0674	.0686	.0698	.0709	.0721
	-	64	-	-	.0691	.0753	.0753	.0698	.0708	.0718	.0728	.0738
#3	48	-	-	-	.0764	.0845	.0845	.0774	.0787	.0801	.0814	.0828
	-	56	-	-	.0797	.0865	.0865	.0804	.0816	.0828	.0839	.0851
#4	40	-	-	-	.0849	.0939	.0939	.0860	.0876	.0893	.0909	.0925
	-	48	-	-	.0894	.0968	.0968	.0904	.0917	.0931	.0944	.0958
#5	40	-	-	-	.0979	.1062	.1062	.0990	.1006	.1023	.1039	.1055
	-	44	-	-	.1004	.1079	.1079	.1014	.1029	.1043	.1058	.1073
#6	32	-	-	-	.1040	.1140	.1140	.1055	.1076	.1096	.1116	.1136
	-	40	-	-	.1110	.1190	.1186	.1120	.1136	.1153	.1169	.1185
#8	32	-	-	-	.1300	.1390	.1389	.1315	.1336	.1356	.1376	.1396
	-	36	-	-	.1340	.1420	.1416	.1351	.1369	.1387	.1405	.1424
#10	24	-	-	-	.1450	.1560	.1555	.1467	.1494	.1521	.1548	.1575
	-	32	-	-	.1560	.1640	.1641	.1575	.1596	.1616	.1636	.1656
#12	24	-	-	-	.1710	.1810	.1807	.1727	.1754	.1781	.1808	.1835
	-	28	-	-	.1770	.1860	.1857	.1789	.1812	.1835	.1858	.1882
1/4	-	-	32	-	.1820	.1900	.1895	.1835	.1856	.1876	.1896	.1916
	20	-	-	-	.1960	.2070	.2067	.1980	.2013	.2045	.2078	.2110
1/4	-	28	-	-	.2110	.2200	.2190	.2129	.2152	.2175	.2198	.2222
	-	-	32	-	.2160	.2240	.2229	.2175	.2196	.2216	.2236	.2256
5/16	18	-	-	-	.2520	.2650	.2630	.2548	.2584	.2620	.2656	.2692
	-	-	-	20	.2580	.2700	.2680	.2605	.2638	.2670	.2703	.2735
5/16	-	24	-	-	.2670	.2770	.2754	.2692	.2719	.2746	.2773	.2800
	-	-	-	28	.2740	.2820	.2807	.2754	.2777	.2800	.2823	.2847
5/16	-	-	32	-	.2790	.2860	.2847	.2800	.2821	.2841	.2861	.2881
	16	-	-	-	.3070	.3210	.3182	.3101	.3141	.3182	.3222	.3263
3/8	-	-	-	20	.3210	.3320	.3297	.3230	.3263	.3295	.3328	.3360
	-	24	-	-	.3300	.3400	.3372	.3317	.3344	.3371	.3398	.3425
3/8	-	-	-	28	.3360	.3450	.3426	.3379	.3402	.3425	.3448	.3472
	-	-	32	-	.3410	.3490	.3469	.3425	.3446	.3466	.3486	.3506
7/16	14	-	-	-	.3600	.3760	.3717	.3633	.3679	.3726	.3772	.3818
	-	-	-	16	.3700	.3840	.3800	.3726	.3766	.3807	.3847	.3888
7/16	-	20	-	-	.3830	.3950	.3916	.3855	.3888	.3920	.3953	.3985
	-	-	28	-	.3990	.4070	.4051	.4004	.4027	.4050	.4073	.4097
7/16	-	-	-	32	.4040	.4110	.4094	.4050	.4071	.4091	.4111	.4131
	13	-	-	-	.4170	.4340	.4284	.4201	.4251	.4301	.4351	.4400
1/2	-	-	-	16	.4320	.4460	.4419	.4351	.4391	.4432	.4472	.4513
	-	20	-	-	.4460	.4570	.4537	.4480	.4513	.4545	.4578	.4610
1/2	-	-	28	-	.4610	.4700	.4676	.4629	.4652	.4675	.4698	.4722
	-	-	-	32	.4660	.4740	.4719	.4675	.4696	.4716	.4736	.4756
9/16	12	-	-	-	.4720	.4900	.4843	.4759	.4813	.4867	.4921	.4976
	-	-	-	16	.4950	.5090	.5040	.4976	.5016	.5057	.5097	.5138
9/16	-	18	-	-	.5020	.5150	.5106	.5048	.5084	.5120	.5156	.5192
	-	-	-	20	.5080	.5200	.5162	.5105	.5138	.5170	.5203	.5235
9/16	-	-	24	-	.5170	.5270	.5244	.5192	.5219	.5246	.5273	.5300
	-	-	-	28	.5240	.5320	.5301	.5254	.5277	.5300	.5323	.5347
9/16	-	-	-	32	.5290	.5360	.5344	.5300	.5321	.5341	.5361	.5381
	5/8	11	-	-	.5270	.5460	.5391	.5305	.5364	.5423	.5482	.5541



Size	Threads Per Inch				Minor Diameter			Tap Drill Diameter (Cutting Tap)				
	UNC	UNF	UNEF	UN	Min. 2B&3B	Max. 2B	Max. 3B	80% Thread	75% Thread	70% Thread	65% Thread	60% Thread
5/8	-	-	-	12	.5350	.5530	.5463	.5384	.5438	.5492	.5546	.5601
	-	-	-	16	.5570	.5710	.5662	.5601	.5641	.5682	.5722	.5763
	-	18	-	-	.5650	.5780	.5730	.5673	.5709	.5745	.5781	.5817
	-	-	-	20	.5710	.5820	.5787	.5730	.5763	.5795	.5828	.5860
	-	-	24	-	.5800	.5900	.5869	.5817	.5844	.5871	.5898	.5925
	-	-	-	28	.5860	.5950	.5926	.5879	.5902	.5925	.5948	.5972
11/16	-	-	-	32	.5910	.5980	.5969	.5925	.5946	.5966	.5986	.6006
	-	-	-	12	.5970	.6150	.6085	.6009	.6063	.6117	.6171	.6226
	-	-	-	16	.6200	.6340	.6284	.6226	.6266	.6307	.6347	.6388
	-	-	-	20	.6330	.6450	.6412	.6355	.6388	.6420	.6453	.6485
	-	-	24	-	.6420	.6520	.6494	.6442	.6469	.6496	.6523	.6550
	-	-	-	28	.6490	.6570	.6551	.6504	.6527	.6550	.6573	.6597
3/4	-	-	-	32	.6540	.6610	.6594	.6550	.6571	.6591	.6611	.6631
	10	-	-	-	.6420	.6630	.6545	.6461	.6526	.6591	.6656	.6721
	-	-	-	12	.6600	.6780	.6707	.6634	.6688	.6742	.6796	.6851
	-	16	-	-	.6820	.6960	.6908	.6851	.6891	.6932	.6972	.7013
	-	-	20	-	.6960	.7070	.7037	.6980	.7013	.7045	.7078	.7110
	-	-	-	28	.7110	.7200	.7176	.7129	.7152	.7175	.7198	.7222
13/16	-	-	-	32	.7160	.7240	.7219	.7175	.7196	.7216	.7236	.7256
	-	-	-	12	.7220	.7400	.7329	.7259	.7313	.7367	.7421	.7476
	-	-	-	16	.7450	.7590	.7533	.7476	.7516	.7557	.7597	.7638
	-	-	20	-	.7580	.7700	.7662	.7605	.7638	.7670	.7703	.7735
	-	-	-	28	.7740	.7820	.7801	.7754	.7777	.7800	.7823	.7847
	-	-	-	32	.7790	.7860	.7844	.7800	.7821	.7841	.7861	.7881
7/8	9	-	-	-	.7550	.7780	.7681	.7595	.7668	.7740	.7812	.7884
	-	-	-	12	.7850	.8030	.7948	.7884	.7938	.7992	.8046	.8101
	-	14	-	-	.7980	.8140	.8068	.8008	.8054	.8101	.8147	.8193
	-	-	-	16	.8070	.8210	.8158	.8101	.8141	.8182	.8222	.8263
	-	-	20	-	.8210	.8320	.8287	.8230	.8263	.8295	.8328	.8360
	-	-	-	28	.8360	.8450	.8426	.8379	.8402	.8425	.8448	.8472
15/16	-	-	-	32	.8410	.8490	.8469	.8425	.8446	.8466	.8486	.8506
	-	-	-	12	.8470	.8650	.8575	.8509	.8563	.8617	.8671	.8726
	-	-	-	16	.8700	.8840	.8783	.8726	.8766	.8807	.8847	.8888
	-	-	20	-	.8830	.8950	.8912	.8855	.8888	.8920	.8953	.8985
	-	-	-	28	.8990	.9070	.9051	.9004	.9027	.9050	.9073	.9097
	-	-	-	32	.9040	.9110	.9094	.9050	.9071	.9091	.9111	.9131
1	8	-	-	-	.8650	.8900	.8797	.8701	.8782	.8863	.8945	.9026
	-	12	-	-	.9100	.9280	.9198	.9134	.9188	.9242	.9296	.9351
	-	-	-	16	.9320	.9460	.9408	.9351	.9391	.9432	.9472	.9513
	-	-	20	-	.9460	.9570	.9537	.9480	.9513	.9545	.9578	.9610
	-	-	-	28	.9610	.9700	.9676	.9629	.9652	.9675	.9698	.9722
	-	-	-	32	.9660	.9740	.9719	.9675	.9696	.9716	.9736	.9756
1-1/16	-	-	-	8	.9270	.9520	.9422	.9326	.9407	.9488	.9570	.9651
	-	-	-	12	.9720	.9900	.9823	.9759	.9813	.9867	.9921	.9976
	-	-	-	16	.9950	1.0090	1.0033	.9976	1.0016	1.0057	1.0097	1.0138
	-	-	18	-	1.0020	1.0150	1.0105	1.0048	1.0084	1.0120	1.0156	1.0192
	-	-	-	20	1.0080	1.0200	1.0162	1.0105	1.0138	1.0170	1.0203	1.0235
	-	-	-	28	1.0240	1.0320	1.0301	1.0254	1.0277	1.0300	1.0323	1.0347
1-1/8	7	-	-	-	.9700	.9980	.9875	.9765	.9858	.9951	1.0044	1.0137
	-	-	-	8	.9900	1.0150	1.0047	.9951	1.0032	1.0113	1.0195	1.0276
	-	12	-	-	1.0350	1.0530	1.0448	1.0384	1.0438	1.0492	1.0546	1.0601
	-	-	-	16	1.0570	1.0710	1.0658	1.0601	1.0641	1.0682	1.0722	1.0763
	-	-	18	-	1.0650	1.0780	1.0730	1.0673	1.0709	1.0745	1.0781	1.0817
	-	-	-	20	1.0710	1.0820	1.0787	1.0730	1.0763	1.0795	1.0828	1.0860



Size	Threads Per Inch				Minor Diameter			Tap Drill Diameter (Cutting Tap)				
	UNC	UNF	UNEF	UN	Min. 2B&3B	Max. 2B	Max. 3B	80% Thread	75% Thread	70% Thread	65% Thread	60% Thread
1-1/8	-	-	-	28	1.0860	1.0950	1.0926	1.0879	1.0902	1.0925	1.0948	1.0972
1-3/16	-	-	-	8	1.0520	1.0770	1.0672	1.0576	1.0657	1.0738	1.0820	1.0901
	-	-	-	12	1.0970	1.1150	1.1073	1.1009	1.1063	1.1117	1.1171	1.1226
	-	-	-	16	1.1200	1.1340	1.1283	1.1226	1.1266	1.1307	1.1347	1.1388
	-	-	18	-	1.1270	1.1400	1.1355	1.1298	1.1334	1.1370	1.1406	1.1442
	-	-	-	20	1.1330	1.1450	1.1412	1.1355	1.1388	1.1420	1.1453	1.1485
	-	-	-	28	1.1490	1.1570	1.1551	1.1504	1.1527	1.1550	1.1573	1.1597
1-1/4	7	-	-	-	1.0950	1.1230	1.1125	1.1015	1.1108	1.1201	1.1294	1.1387
	-	-	-	8	1.1150	1.1400	1.1297	1.1201	1.1282	1.1363	1.1445	1.1526
	-	12	-	-	1.1600	1.1780	1.1698	1.1634	1.1688	1.1742	1.1796	1.1851
	-	-	-	16	1.1820	1.1960	1.1908	1.1851	1.1891	1.1932	1.1972	1.2013
	-	-	18	-	1.1900	1.2030	1.1980	1.1923	1.1959	1.1995	1.2031	1.2067
	-	-	-	20	1.1960	1.2070	1.2037	1.1980	1.2013	1.2045	1.2078	1.2110
1-5/16	-	-	-	28	1.2110	1.2200	1.2176	1.2129	1.2152	1.2175	1.2198	1.2222
	-	-	-	8	1.1770	1.2020	1.1922	1.1826	1.1907	1.1988	1.2070	1.2151
	-	-	-	12	1.2220	1.2400	1.2323	1.2259	1.2313	1.2367	1.2421	1.2476
	-	-	-	16	1.2450	1.2590	1.2533	1.2476	1.2516	1.2557	1.2597	1.2638
	-	-	18	-	1.2520	1.2650	1.2605	1.2548	1.2584	1.2620	1.2656	1.2692
	-	-	-	20	1.2580	1.2700	1.2662	1.2605	1.2638	1.2670	1.2703	1.2735
1-3/8	-	-	-	28	1.2740	1.2820	1.2801	1.2754	1.2777	1.2800	1.2823	1.2847
	6	-	-	-	1.1950	1.2250	1.2146	1.2018	1.2126	1.2235	1.2343	1.2451
	-	-	-	8	1.2400	1.2650	1.2547	1.2451	1.2532	1.2613	1.2695	1.2776
	-	12	-	-	1.2850	1.3030	1.2948	1.2884	1.2938	1.2992	1.3046	1.3101
	-	-	-	16	1.3070	1.3210	1.3158	1.3101	1.3141	1.3182	1.3222	1.3263
	-	-	18	-	1.3150	1.3280	1.3230	1.3173	1.3209	1.3245	1.3281	1.3317
1-7/16	-	-	-	20	1.3210	1.3320	1.3287	1.3230	1.3263	1.3295	1.3328	1.3360
	-	-	-	28	1.3360	1.3450	1.3426	1.3379	1.3402	1.3425	1.3448	1.3472
	-	-	-	6	1.2570	1.2880	1.2771	1.2643	1.2751	1.2860	1.2968	1.3076
	-	-	-	8	1.3020	1.3270	1.3172	1.3076	1.3157	1.3238	1.3320	1.3401
	-	-	-	12	1.3470	1.3650	1.3573	1.3509	1.3563	1.3617	1.3671	1.3726
	-	-	-	16	1.3700	1.3840	1.3783	1.3726	1.3766	1.3807	1.3847	1.3888
1-9/16	-	-	18	-	1.3770	1.3900	1.3855	1.3798	1.3834	1.3870	1.3906	1.3942
	-	-	-	20	1.3830	1.3950	1.3912	1.3855	1.3888	1.3920	1.3953	1.3985
	-	-	-	28	1.3990	1.4070	1.4051	1.4004	1.4027	1.4050	1.4073	1.4097
	6	-	-	-	1.3200	1.3500	1.3396	1.3268	1.3376	1.3485	1.3593	1.3701
	-	-	-	8	1.3650	1.3900	1.3797	1.3701	1.3782	1.3863	1.3945	1.4026
	-	12	-	-	1.4100	1.4280	1.4198	1.4134	1.4188	1.4242	1.4296	1.4351
1-1/2	-	-	-	16	1.4320	1.4460	1.4408	1.4351	1.4391	1.4432	1.4472	1.4513
	-	-	18	-	1.4400	1.4520	1.4480	1.4423	1.4459	1.4495	1.4531	1.4567
	-	-	-	20	1.4460	1.4570	1.4537	1.4480	1.4513	1.4545	1.4578	1.4610
	-	-	-	28	1.4610	1.4700	1.4676	1.4629	1.4652	1.4675	1.4698	1.4722
	-	-	-	6	1.3820	1.4130	1.4021	1.3893	1.4001	1.4110	1.4218	1.4326
	-	-	-	8	1.4270	1.4520	1.4422	1.4326	1.4407	1.4488	1.4570	1.4651
1-5/8	-	-	-	12	1.4720	1.4900	1.4823	1.4759	1.4813	1.4867	1.4921	1.4976
	-	-	-	16	1.4950	1.5090	1.5033	1.4976	1.5016	1.5057	1.5097	1.5138
	-	-	-	18	1.5020	1.5150	1.5105					



Size	Threads Per Inch				Minor Diameter			Tap Drill Diameter (Cutting Tap)				
	UNC	UNF	UNEF	UN	Min. 2B&3B	Max. 2B	Max. 3B	80% Thread	75% Thread	70% Thread	65% Thread	60% Thread
1-11/16	-	-	-	8	1.5520	1.5770	1.5672	1.5576	1.5657	1.5738	1.5820	1.5901
	-	-	-	12	1.5970	1.6150	1.6073	1.6009	1.6063	1.6117	1.6171	1.6226
	-	-	-	16	1.6200	1.6340	1.6283	1.6226	1.6266	1.6307	1.6347	1.6388
	-	-	18	-	1.6270	1.6400	1.6355	1.6298	1.6334	1.6370	1.6406	1.6442
1-3/4	-	-	-	20	1.6330	1.6450	1.6412	1.6355	1.6388	1.6420	1.6453	1.6485
	5	-	-	-	1.5340	1.5680	1.5575	1.5422	1.5552	1.5681	1.5811	1.5941
	-	-	-	6	1.5700	1.6000	1.5896	1.5768	1.5876	1.5985	1.6093	1.6201
	-	-	-	8	1.6150	1.6400	1.6297	1.6201	1.6282	1.6363	1.6445	1.6526
1-13/16	-	-	-	12	1.6600	1.6780	1.6698	1.6634	1.6688	1.6742	1.6796	1.6851
	-	-	-	16	1.6820	1.6960	1.6908	1.6851	1.6891	1.6932	1.6972	1.7013
	-	-	-	20	1.6960	1.7070	1.7037	1.6980	1.7013	1.7045	1.7078	1.7110
	-	-	-	6	1.6320	1.6630	1.6521	1.6393	1.6501	1.6610	1.6718	1.6826
1-7/8	-	-	-	8	1.6770	1.7020	1.6922	1.6826	1.6907	1.6988	1.7070	1.7151
	-	-	-	12	1.7220	1.7400	1.7323	1.7259	1.7313	1.7367	1.7421	1.7476
	-	-	-	16	1.7450	1.7590	1.7533	1.7476	1.7516	1.7557	1.7597	1.7638
	-	-	-	20	1.7580	1.7700	1.7662	1.7605	1.7638	1.7670	1.7703	1.7735
1-15/16	-	-	-	6	1.6950	1.7250	1.7146	1.7018	1.7126	1.7235	1.7343	1.7451
	-	-	-	8	1.7400	1.7650	1.7547	1.7451	1.7532	1.7613	1.7695	1.7776
	-	-	-	12	1.7850	1.8030	1.7948	1.7884	1.7938	1.7992	1.8046	1.8101
	-	-	-	16	1.8070	1.8210	1.8158	1.8101	1.8141	1.8182	1.8222	1.8263
2	-	-	-	20	1.8210	1.8320	1.8287	1.8230	1.8263	1.8295	1.8328	1.8360
	-	-	-	6	1.7570	1.7880	1.7771	1.7643	1.7751	1.7860	1.7968	1.8076
	-	-	-	8	1.8020	1.8270	1.8172	1.8076	1.8157	1.8238	1.8320	1.8401
	-	-	-	12	1.8470	1.8650	1.8573	1.8509	1.8563	1.8617	1.8671	1.8726
2-1/8	-	-	-	16	1.8700	1.8840	1.8783	1.8726	1.8766	1.8807	1.8847	1.8888
	-	-	-	20	1.8830	1.8950	1.8912	1.8855	1.8888	1.8920	1.8953	1.8985
	4 1/2	-	-	-	1.7590	1.7950	1.7861	1.7691	1.7835	1.7979	1.8124	1.8268
	-	-	-	6	1.8200	1.8500	1.8396	1.8268	1.8376	1.8485	1.8593	1.8701
2-1/4	-	-	-	8	1.8650	1.8900	1.8797	1.8701	1.8782	1.8863	1.8945	1.9026
	-	-	-	12	1.9100	1.9280	1.9198	1.9134	1.9188	1.9242	1.9296	1.9351
	-	-	-	16	1.9320	1.9460	1.9408	1.9351	1.9391	1.9432	1.9472	1.9513
	-	-	-	20	1.9460	1.9570	1.9537	1.9480	1.9513	1.9545	1.9578	1.9610
2-3/8	-	-	-	6	1.9450	1.9750	1.9646	1.9518	1.9626	1.9735	1.9843	1.9951
	-	-	-	8	1.9900	2.0150	2.0047	1.9951	2.0032	2.0113	2.0195	2.0276
	-	-	-	12	2.0350	2.0530	2.0448	2.0384	2.0438	2.0492	2.0546	2.0601
	-	-	-	16	2.0570	2.0710	2.0658	2.0601	2.0641	2.0682	2.0722	2.0763
2-1/2	-	-	-	20	2.0710	2.0820	2.0787	2.0730	2.0763	2.0795	2.0828	2.0860
	4 1/2	-	-	-	2.0090	2.0450	2.0361	2.0191	2.0335	2.0479	2.0624	2.0768
	-	-	-	6	2.0700	2.1000	2.0896	2.0768	2.0876	2.0985	2.1093	2.1201
	-	-	-	8	2.1150	2.1400	2.1297	2.1201	2.1282	2.1363	2.1445	2.1526
2-5/8	-	-	-	12	2.1600	2.1780	2.1698	2.1634	2.1688	2.1742	2.1796	2.1851
	-	-	-	16	2.1820	2.1960	2.1908	2.1851	2.1891	2.1932	2.1972	2.2013
	-	-	-	20	2.1960	2.2070	2.2037	2.1980	2.2013	2.2045	2.2078	2.2110
	-	-	-	6	2.1950	2.2260	2.2146	2.2018	2.2126	2.2235	2.2343	2.2451
2-3/4	-	-	-	8	2.2400	2.2650	2.2547	2.2451	2.2532	2.2613	2.2695	2.2776
	-	-	-	12	2.2850	2.3030	2.2948	2.2884	2.2938	2.2992	2.3046	2.3101
	-	-	-	16	2.3070	2.3210	2.3158	2.3101	2.3141	2.3182	2.3222	2.3263
	-	-	-	20	2.3210	2.3320	2.3287	2.3230	2.3263	2.3295	2.3328	2.3360
2-7/8	4	-	-	-	2.2290	2.2670	2.2594	2.2402	2.2564	2.2727	2.2889	2.3052
	-	-	-	6	2.3200	2.3500	2.3396	2.3268	2.3376	2.3485	2.3593	2.3701
	-	-	-	8	2.3650	2.3900	2.3797	2.3701	2.3782	2.3863	2.3945	2.4026
	-	-	-	12	2.4100	2.4280	2.4198	2.4134	2.4188	2.4242	2.4296	2.4351
2-1/2	-	-	-	16	2.4320	2.4460	2.4408	2.4351	2.4391	2.4432	2.4472	2.4513
	-	-	-	20	2.4460	2.4570	2.4537	2.4480	2.4513	2.4545	2.4578	2.4610



16 TAP DRILL SIZES - METRIC THREAD

Size	Pitch		Minor dia.		Tap Drill Diameter									
	M	MF	Min. 6H	Max. 6H	80% Thread		75% Thread		70% Thread		65% Thread		60% Thread	
					mm	Inch	mm	Inch	mm	Inch	mm	Inch	mm	Inch
M1	0.25	-	.729	.798	0.74	.0291	0.76	.0298	0.77	.0304	0.79	.0311	0.81	.0317
	-	0.2	.783	.841	0.79	.0312	0.81	.0317	0.82	.0322	0.83	.0327	0.84	.0332
M1.1	0.25	-	.829	.898	0.84	.0331	0.86	.0337	0.87	.0344	0.89	.0350	0.91	.0356
	-	0.2	.883	.941	0.89	.0351	0.91	.0356	0.92	.0361	0.93	.0367	0.94	.0372
M1.2	0.25	-	.929	.998	0.94	.0370	0.96	.0377	0.97	.0383	0.99	.0389	1.01	.0396
	-	0.2	.983	1.041	0.99	.0391	1.01	.0396	1.02	.0401	1.03	.0406	1.04	.0411
M1.4	0.3	-	1.075	1.159	1.09	.0428	1.11	.0436	1.13	.0444	1.15	.0451	1.17	.0459
	-	0.2	1.183	1.241	1.19	.0469	1.21	.0474	1.22	.0480	1.23	.0485	1.24	.0490
M1.6	0.35	-	1.221	1.321	1.24	.0487	1.26	.0496	1.28	.0505	1.30	.0514	1.33	.0523
	-	0.2	1.383	1.441	1.39	.0548	1.41	.0553	1.42	.0558	1.43	.0563	1.44	.0569
M1.7	0.35	-	1.321	1.421	1.34	.0526	1.36	.0535	1.38	.0544	1.40	.0553	1.43	.0562
	-	0.3	1.375	1.459	1.39	.0547	1.41	.0554	1.43	.0562	1.45	.0570	1.47	.0577
M1.8	-	0.25	1.429	1.498	1.44	.0567	1.46	.0573	1.47	.0580	1.49	.0586	1.51	.0593
	0.35	-	1.421	1.541	1.44	.0567	1.46	.0573	1.47	.0580	1.49	.0586	1.51	.0593
M2	0.35	-	1.483	1.541	1.49	.0587	1.51	.0593	1.52	.0598	1.53	.0603	1.54	.0608
	-	0.2	1.483	1.541	1.44	.0565	1.46	.0574	1.48	.0583	1.50	.0592	1.53	.0601
M2.2	0.4	-	1.567	1.679	1.58	.0624	1.61	.0634	1.64	.0644	1.66	.0654	1.69	.0665
	-	0.25	1.729	1.798	1.74	.0685	1.76	.0692	1.77	.0698	1.79	.0704	1.81	.0711
M2.3	0.45	-	1.713	1.838	1.73	.0682	1.76	.0694	1.79	.0705	1.82	.0717	1.85	.0728
	-	0.25	1.929	1.998	1.94	.0764	1.96	.0770	1.97	.0777	1.99	.0783	2.01	.0789
M2.5	0.4	-	1.867	1.979	1.88	.0742	1.91	.0752	1.94	.0762	1.96	.0773	1.99	.0783
	-	0.35	1.921	2.021	1.94	.0762	1.96	.0771	1.98	.0780	2.00	.0789	2.03	.0798
M2.6	0.45	-	2.029	2.098	2.04	.0803	2.06	.0810	2.07	.0816	2.09	.0822	2.11	.0829
	-	0.25	2.029	2.098	2.04	.0803	2.06	.0810	2.07	.0816	2.09	.0822	2.11	.0829
M3	0.45	-	2.013	2.138	2.03	.0800	2.06	.0812	2.09	.0823	2.12	.0835	2.15	.0846
	-	0.35	2.121	2.221	2.14	.0841	2.16	.0850	2.18	.0859	2.20	.0868	2.23	.0877
M3.5	0.45	-	2.113	2.238	2.13	.0840	2.16	.0851	2.19	.0863	2.22	.0874	2.25	.0886
	-	0.35	2.221	2.321	2.24	.0880	2.26	.0889	2.28	.0898	2.30	.0907	2.33	.0916
M4	0.5	-	2.459	2.599	2.48	.0977	2.51	.0989	2.55	.1002	2.58	.1015	2.61	.1028
	-	0.35	2.621	2.721	2.64	.1038	2.66	.1047	2.68	.1056	2.70	.1065	2.73	.1074
M4.5	0.6	-	2.850	3.010	2.88	.1132	2.92	.1148	2.95	.1163	2.99	.1178	3.03	.1194
	-	0.35	3.121	3.221	3.14	.1235	3.16	.1244	3.18	.1253	3.20	.1262	3.23	.1271
M5	0.7	-	3.242	3.422	3.27	.1288	3.32	.1306	3.36	.1324	3.41	.1342	3.45	.1360
	-	0.5</												



Size	Pitch		Minor dia.		Tap Drill Diameter									
	M	MF	Min. 6H	Max. 6H	80% Thread		75% Thread		70% Thread		65% Thread		60% Thread	
					mm	Inch	mm	Inch	mm	Inch	mm	Inch	mm	Inch
M9	1.25	-	7.647	7.912	7.70	.3032	7.78	.3064	7.86	.3096	7.94	.3128	8.03	.3160
	-	1	7.917	8.153	7.96	.3134	8.03	.3160	8.09	.3185	8.16	.3211	8.22	.3236
	-	0.75	8.188	8.378	8.22	.3236	8.27	.3256	8.32	.3275	8.37	.3294	8.42	.3313
M10	-	0.5	8.459	8.599	8.48	.3339	8.51	.3352	8.55	.3364	8.58	.3377	8.61	.3390
	1.5	-	8.376	8.676	8.44	.3323	8.54	.3362	8.64	.3400	8.73	.3438	8.83	.3477
	-	1.25	8.647	8.912	8.70	.3426	8.78	.3458	8.86	.3490	8.94	.3521	9.03	.3553
M11	-	1	8.917	9.153	8.96	.3528	9.03	.3553	9.09	.3579	9.16	.3605	9.22	.3630
	-	0.75	9.188	9.378	9.22	.3630	9.27	.3649	9.32	.3669	9.37	.3688	9.42	.3707
	-	0.5	9.459	9.599	9.48	.3732	9.51	.3745	9.55	.3758	9.58	.3771	9.61	.3784
M12	1.5	-	9.376	9.676	9.44	.3717	9.54	.3755	9.64	.3794	9.73	.3832	9.83	.3870
	-	1	9.917	10.153	9.96	.3922	10.03	.3947	10.09	.3973	10.16	.3998	10.22	.4024
	-	0.75	10.188	10.378	10.22	.4024	10.27	.4043	10.32	.4062	10.37	.4081	10.42	.4101
M13	-	0.5	10.459	10.599	10.48	.4126	10.51	.4139	10.55	.4152	10.58	.4164	10.61	.4177
	1.75	-	10.106	10.441	10.18	.4008	10.30	.4053	10.41	.4098	10.52	.4143	10.64	.4187
	-	1.5	10.376	10.676	10.44	.4111	10.54	.4149	10.64	.4187	10.73	.4226	10.83	.4264
M14	-	1.25	10.647	10.912	10.70	.4213	10.78	.4245	10.86	.4277	10.94	.4309	11.03	.4341
	-	1	10.917	11.153	10.96	.4315	11.03	.4341	11.09	.4366	11.16	.4392	11.22	.4418
	-	0.75	11.188	11.378	11.22	.4418	11.27	.4437	11.32	.4456	11.37	.4475	11.42	.4494
M15	-	0.5	11.459	11.599	11.48	.4520	11.51	.4533	11.55	.4545	11.58	.4558	11.61	.4571
	-	1.75	11.106	11.441	11.18	.4402	11.30	.4447	11.41	.4492	11.52	.4536	11.64	.4581
	-	1.5	11.376	11.676	11.44	.4504	11.54	.4543	11.64	.4581	11.73	.4619	11.83	.4658
M16	-	1.25	11.647	11.912	11.70	.4607	11.78	.4639	11.86	.4671	11.94	.4703	12.03	.4735
	-	1	11.917	12.153	11.96	.4709	12.03	.4735	12.09	.4760	12.16	.4786	12.22	.4811
	-	0.75	12.188	12.378	12.22	.4811	12.27	.4830	12.32	.4850	12.37	.4869	12.42	.4888
M17	-	0.5	12.459	12.599	12.48	.4914	12.51	.4926	12.55	.4939	12.58	.4952	12.61	.4965
	2	-	11.835	12.210	11.92	.4694	12.05	.4745	12.18	.4796	12.31	.4847	12.44	.4898
	-	1.5	12.376	12.676	12.44	.4898	12.54	.4936	12.64	.4975	12.73	.5013	12.83	.5052
M18	-	1.25	12.647	12.912	12.70	.5000	12.78	.5032	12.86	.5064	12.94	.5096	13.03	.5128
	-	1	12.917	13.153	12.96	.5103	13.03	.5128	13.09	.5154	13.16	.5179	13.22	.5205
	-	0.75	13.188	13.378	13.22	.5205	13.27	.5224	13.32	.5243	13.37	.5262	13.42	.5282
M19	-	0.5	13.459	13.599	13.48	.5307	13.51	.5320	13.55	.5333	13.58	.5346	13.61	.5358
	-	2	12.835	13.210	12.92	.5087	13.05	.5138	13.18	.5190	13.31	.5241	13.44	.5292
	-	1.5	13.376	13.676	13.44	.5292	13.54	.5330	13.64	.5369	13.73	.5407	13.83	.5445
M20	-	1.25	13.647	13.912	13.70	.5394	13.78	.5426	13.86	.5458	13.94	.5490	14.03	.5522
	-	1	13.917	14.153	13.96	.5496	14.03	.5522	14.09	.5548	14.16	.5573	14.22	.5599
	-	0.75	14.188	14.378	14.22	.5599	14.27	.5618	14.32	.5637	14.37	.5656	14.42	.5675
M21	-	0.5	14.459	14.599	14.48	.5701	14.51	.5714	14.55	.5727	14.58	.5739	14.61	.5752
	2.5	-	13.835	14.210	13.92	.5481	14.05	.5532	14.18	.5583	14.31	.5634	14.44	.5685
	-	1.5	14.376	14.676	14.44	.5685	14.54	.5724	14.64	.5762	14.73	.5801	14.83	.5839
M22	-	1	14.917	15.153	14.96	.5890	15.03	.5916	15.09	.5941	15.16	.5967	15.22	.5992
	-	2	14.835	15.210	14.92	.5875	15.05	.5926	15.18	.5977	15.31	.6028	15.44	.6079
	-	1.5	15.376	15.676	15.44	.6079	15.54	.6118	15.64	.6156	15.73	.6194	15.83	.6233
M23	-	1.25	15.647	15.912	15.70	.6181	15.78	.6213	15.86	.6245	15.94	.6277	16.03	.6309
	-	1	15.917	16.153	15.96	.6284	16.03	.6309	16.09	.6335	16.16	.6360	16.22	.6386
	-	0.75	16.188	16.378	16.22	.6386	16.27	.6405	16.32	.6424	16.37	.6444	16.42	.6463
M24	-	0.5	16.459	16.599	16.48	.6488	16.51	.6501	16.55	.6514	16.58	.6527	16.61	.6539
	2.5	-	15.294	15.744	15.40	.6064	15.56	.6128	15.73	.6192	15.89	.6256	16.05	.6319
	-	2	15.835	16.210	15.92	.6268	16.05	.6319	16.18	.6371	16.31	.6422	16.44	.6473
M25	-	1.5	16.376	16.676	16.44	.6473	16.54	.6511	16.64	.6550	16.73	.6588	16.83	.6626
	-	1	16.917	17.153	16.96	.6677	17.03	.6703	17.09	.6729	17.16	.6754	17.22	.6780
	-	2.5	16.294	16.744	16.40	.6064	16.56	.6128	16.73	.6192	16.89	.6256	17.05	.6319
M26	-	2	16.835	17.210	16.92	.6662	17.05	.6713	17.18	.6764	17.31	.6815	17.44	.6867
	-	1.5	17.376	17.676	17.44	.6867	17.54	.6905	17.64	.6943	17.73	.6982	17.83	.7020
	-	1.25	17.647	17.912	17.70	.6969	17.78	.7001	17.86	.7033	17.94	.7065	18.03	.7097
M27	-	1	17.917	18.153	17.96	.7071	18.03	.7097	18.09	.7122	18.16	.7148	18.22	.7173
	-	0.75	18.188	18.378	18.22	.7173	18.27	.7193	18.32	.7212	18.37	.7231	18.42	.7250
	-	0.5	18.459	18.599	18.48	.7276	18.51	.7289	18.55	.7301	18.58	.7314	18.61	.7327
M28	2.5	-	17.294	17.744	17.40	.6851	17.56	.6915	17.73	.6979	17.89	.7043	18.05	.7107
	-	2	17.835	18.210	17.92	.7056	18.05	.7107	18.18	.7158	18.31	.7209	18.44	.7260
	-	1.5	18.376	18.676	18.44	.7260	18.54	.7299	18.64	.7337	18.73	.7375	18.83	.7414
M29	-	1	18.917	19.153	18.96	.7465	19.03	.7490	19.09	.7516	19.16	.7542	19.22	.7567
	-	2.5	18.294	18.744	18.40	.7245	18.56	.7309	18.73	.7373	18.89	.7437	19.05	.7501
	-	1.5	19.376	19.676	19.44	.7654	19.54	.7692	19.64	.7731	19.73	.7769	19.83	.7807
M30	-	1	19.917	20.153	19.96	.7859	20.03	.7884	20.09	.7910	20.16	.7935	20.22	.7961
	2.5	-	19.294	19.744	19.40	.7639	19.56	.7702	19.73	.7766	19.89	.7830	20.05	.7894
	-	2	19.835	20.210	19.92	.7843	20.05	.7894	20.18	.7945	20.31	.7997	20.44	.8048
M31	-	1.5	20.376	20.676	20.44	.8048	20.54	.8086	20.64	.8124	20.73	.8163	20.83	.8201
	-	1	20.917	21.153	20.96	.8252	21.03	.8278	21.09	.8303	21.16	.8329	21.22	.8355
	-	2.5	20.294	20.744	20.40	.8032	20.56	.8096	20.73	.8160	20.89	.8224	21.05	.8288
M32	-	2	20.835	21.210	20.92	.8237	21.05	.8288	21.18	.8339	21.31	.8390	21.44	.8441
	-	1.5	21.376	21.676	21.44	.8441	21.54	.8480	21.64	.8518	21.73	.8556	21.83	.8595
	-	1	21.917	22.153	21.96	.8646	22.03	.8672	22.09	.8697	22.16	.8723	22.22	.8748
M33	3	-	20.752	21.252	20.88	.8221	21.08	.8298	21.27	.8375	21.47	.8452	21.66	.8528
	-	2	21.835	22.210	21.92	.8631	22.05	.8682	22.18	.8733	22.31	.8784	22.44	.8835
	-	1.5	22.376	22.676	22.44	.8835	22.54	.8873	22.64	.8912	22.73	.8950	22.83	.8989
M34	-	1	22.917	23.153	22.96	.9040	23.03	.9065	23.09	.9091	23.16	.9116	23.22	.9142
	-	3	21.752	22.252	21.88	.8615	22.08	.8692	22.27	.8769	22.47	.8845	22.66	.8922
	-	2	22.835	23.210	22.92	.9024	23.05	.9075	23.18	.9127	23.31	.9178	23.44	.9229
M35	-	1.5	23.376	23.676	23.44	.9229	23.54	.9267	23.64	.9306	23.73	.9344	23.83	.9382
	-	1	23.917	24.153	23.96	.9433	24.03	.9459	24.09	.9485	24.16	.9510	24.22	.9536
	-	3	22.752	23.252	22.88	.9009	23.08	.9085	23.27	.9162	23.47	.9239	23.66	.9316
M36	-	2	23.835	24.210	23.92	.9418	24.05	.9469	24.18	.9520	24.31	.9571	24.44	.9623
	-	1.5	24.376	24.676	24.44	.9623	24.54	.9661	24.64	.9699	24.73	.9738	24.83	.9776
	-	3	23.752	24.252	23.88	.9402	24.08	.9479	24.27	.9556	24.47	.9633	24.66	.9709
M37	-	2.5	24.294	24.744	24.40	.9607	24.56	.9671	24.73	.9735	24.89	.9		

Size	Pitch		Minor dia.		Tap Drill Diameter									
	M	MF	Min. 6H	Max. 6H	80% Thread		75% Thread		70% Thread		65% Thread		60% Thread	
					mm	Inch	mm	Inch	mm	Inch	mm	Inch	mm	Inch
M34	-	3	30.752	31.252	30.88	1.2158	31.08	1.2235	31.27	1.2312	31.47	1.2389	31.66	1.2465
	-	2	31.835	32.210	31.92	1.2568	32.05	1.2619	32.18	1.2670	32.31	1.2721	32.44	1.2772
	-	1.5	32.376	32.676	32.44	1.2772	32.54	1.2810	32.64	1.2849	32.73	1.2887	32.83	1.2926
M35	-	1	32.917	33.153	32.96	1.2977	33.03	1.3002	33.09	1.3028	33.16	1.3053	33.22	1.3079
	-	3	31.752	32.252	31.88	1.2552	32.08	1.2629	32.27	1.2706	32.47	1.2782	32.66	1.2859
	-	1.5	33.376	33.676	33.44	1.3166	33.54	1.3204	33.64	1.3243	33.73	1.3281	33.83	1.3319
M36	-	1	33.917	34.153	33.96	1.3370	34.03	1.3396	34.09	1.3422	34.16	1.3447	34.22	1.3473
	4	-	31.670	32.270	31.84	1.2537	32.10	1.2639	32.36	1.2741	32.62	1.2844	32.88	1.2946
	-	3	32.752	33.252	32.88	1.2946	33.08	1.3023	33.27	1.3099	33.47	1.3176	33.66	1.3253
M37	-	2	33.835	34.210	33.92	1.3355	34.05	1.3406	34.18	1.3457	34.31	1.3508	34.44	1.3560
	-	1.5	34.376	34.676	34.44	1.3560	34.54	1.3598	34.64	1.3636	34.73	1.3675	34.83	1.3713
	-	1	34.917	35.153	34.96	1.3764	35.03	1.3790	35.09	1.3815	35.16	1.3841	35.22	1.3866
M38	-	1.5	35.376	35.676	35.44	1.3953	35.54	1.3992	35.64	1.4030	35.73	1.4068	35.83	1.4107
	-	1	35.917	36.153	35.96	1.4158	36.03	1.4183	36.09	1.4209	36.16	1.4234	36.22	1.4260
	-	4	33.670	34.270	33.84	1.3324	34.10	1.3426	34.36	1.3529	34.62	1.3631	34.88	1.3733
M39	-	3	34.752	35.252	34.88	1.3733	35.08	1.3810	35.27	1.3887	35.47	1.3963	35.66	1.4040
	-	2	35.835	36.210	35.92	1.4142	36.05	1.4193	36.18	1.4245	36.31	1.4296	36.44	1.4347
	-	1.5	36.376	36.676	36.44	1.4347	36.54	1.4385	36.64	1.4424	36.73	1.4462	36.83	1.4500
M40	4	-	34.670	35.270	34.84	1.3718	35.10	1.3820	35.36	1.3922	35.62	1.4025	35.88	1.4127
	-	3	35.752	36.252	35.88	1.4127	36.08	1.4204	36.27	1.4280	36.47	1.4357	36.66	1.4434
	-	2	36.835	37.210	36.92	1.4536	37.05	1.4587	37.18	1.4638	37.31	1.4689	37.44	1.4741
M42	-	1.5	37.376	37.676	37.44	1.4741	37.54	1.4779	37.64	1.4817	37.73	1.4856	37.83	1.4894
	-	1	37.917	38.153	37.96	1.4945	38.03	1.4971	38.09	1.4996	38.16	1.5022	38.22	1.5047
	-	4	35.670	36.270	35.84	1.4111	36.10	1.4214	36.36	1.4316	36.62	1.4418	36.88	1.4521
M45	-	3	36.752	37.252	36.88	1.4521	37.08	1.4597	37.27	1.4674	37.47	1.4751	37.66	1.4827
	-	2	37.835	38.210	37.92	1.4930	38.05	1.4981	38.18	1.5032	38.31	1.5083	38.44	1.5134
	-	1.5	38.376	38.676	38.44	1.5134	38.54	1.5173	38.64	1.5211	38.73	1.5249	38.83	1.5288
M48	-	1	38.917	39.153	38.96	1.5339	39.03	1.5364	39.09	1.5390	39.16	1.5416	39.22	1.5441
	4.5	-	37.129	37.799	37.32	1.4694	37.62	1.4809	37.91	1.4924	38.20	1.5039	38.49	1.5155
	-	4	37.670	38.270	37.84	1.4899	38.10	1.5001	38.36	1.5103	38.62	1.5206	38.88	1.5308
M50	-	3	38.752	39.252	38.88	1.5308	39.08	1.5385	39.27	1.5461	39.47	1.5538	39.66	1.5615
	-	2	39.835	40.210	39.92	1.5717	40.05	1.5768	40.18	1.5819	40.31	1.5871	40.44	1.5922
	-	1.5	40.376	40.676	40.44	1.5922	40.54	1.5960	40.64	1.5998	40.73	1.6037	40.83	1.6075
M52	4.5	-	40.129	40.799	40.32	1.5875	40.62	1.5990	40.91	1.6106	41.20	1.6221	41.49	1.6336
	-	4	40.670	41.270	40.84	1.6080	41.10	1.6182	41.36	1.6285	41.62	1.6387	41.88	1.6489
	-	3	41.752	42.252	41.88	1.6489	42.08	1.6566	42.27	1.6643	42.47	1.6719	42.66	1.6796
M55	-	2	42.835	43.210	42.92	1.6898	43.05	1.6949	43.18	1.7001	43.31	1.7052	43.44	1.7103
	-	1.5	43.376	43.676	43.44	1.7103	43.54	1.7141	43.64	1.7180	43.73	1.7218	43.83	1.7256
	-	1	43.917	44.153	43.96	1.7307	44.03	1.7333	44.09	1.7359	44.16	1.7384	44.22	1.7410
M58	-	1.5	44.376	44.676	44.44	1.7497	44.54	1.7535	44.64	1.7573	44.73	1.7612	44.83	1.7650
	5	-	42.587	43.297	42.80	1.6852	43.13	1.6980	43.45	1.7108	43.78	1.7235	44.10	1.7363
	-	4	43.670	44.270	43.84	1.7261	44.10	1.7363	44.36	1.7466	44.62	1.7568	44.88	1.7670
M60	-	3	44.752	45.252	44.88	1.7670	45.08	1.7747	45.27	1.7824	45.47	1.7900	45.66	1.7977
	-	2	45.835	46.210	45.92	1.8079	46.05	1.8130	46.18	1.8182	46.31	1.8233	46.44	1.8284
	-	1.5	46.376	46.676	46.44	1.8284	46.54	1.8322	46.64	1.8361	46.73	1.8399	46.83	1.8437
M62	-	1	46.917	47.153	46.96	1.8488	47.03	1.8514	47.09	1.8540	47.16	1.8565	47.22	1.8591
	-	5	44.587	45.297	44.80	1.7639	45.13	1.7767	45.45	1.7895	45.78	1.8023	46.10	1.8151
	-	3	46.752	47.252	46.88	1.8458	47.08	1.8534	47.27	1.8611	47.47	1.8688	47.66	1.8764
M64	-	2	47.835	48.210	47.92	1.8867	48.05	1.8918	48.18	1.8969	48.31	1.9020	48.44	1.9071
	-	1.5	48.376	48.676	48.44	1.9071	48.54	1.9110	48.64	1.9148	48.73	1.9186	48.83	1.9225
	-	1	48.917	49.153	48.96	1.9276	49.03	1.9301	49.09	1.9327	49.16	1.9353	49.22	1.9378

Size	Pitch		Minor dia.		Tap Drill Diameter									
	M	MF	Min. 6H	Max. 6H	80% Thread		75% Thread		70% Thread		65% Thread		60% Thread	
					mm	Inch	mm	Inch	mm	Inch	mm	Inch	mm	Inch
M52	5	-	46.587	47.297	46.80	1.8427	47.13	1.8555	47.45	1.8682	47.78	1.8810	48.10	1.8938
	-	4	47.670	48.270	47.84	1.8836	48.10	1.8938	48.36	1.9040	48.62	1.9143	48.88	1.9245
	-	3	48.752	49.252	48.88	1.9245	49.08	1.9322	49.27	1.9398	49.47	1.9475	49.66	1.9552
M55	-	2	49.835	50.210	49.92	1.9654	50.05	1.9705	50.18	1.9756	50.31	1.9808	50.44	1.9859
	-	1.5	50.376	50.676	50.44	1.9859	50.54	1.9897	50.64	1.9935	50.73	1.9974	50.83	2.0012
	-	4	50.670	51.270	50.84	2.0017	51.10	2.0119	51.36	2.0222	51.62	2.0324	51.88	2.0426
M56	-	3	51.752	52.252	51.88	2.0426	52.08	2.0503	52.27	2.0580	52.47	2.0656	52.66	2.0733
	-	2	52.835	53.210	52.92	2.0835	53.05	2.0886	53.18	2.0938	53.31	2.0989	53.44	2.1040
	-	1.5	53.376	53.676	53.44	2.1040	53.54	2.1078	53.64	2.1117	53.73	2.1155	53.83	2.1193
M58	5.5	-	50.046	50.796	50.28	1.9797	50.64	1.9938	51.00	2.0078	51.36	2.0219	51.71	2.0360
	-	4	51.670	52.270	51.84	2.0411	52.10	2.0513	52.36	2.0615	52.62	2.0718	52.88	2.0820
	-	3	52.752	53.252	52.88	2.0820	53.08	2.0897	53.27	2.0973	53.47	2.1050	53.66	2.1127
M60	-	2	53.835	54.210	53.92	2.1229	54.05	2.1280	54.18	2.1331	54.31	2.1382	54.44	2.1434
	-	1.5	54.376	54.676	54.44	2.1434	54.54	2.1472	54.64	2.1510	54.73	2.1549	54.83	2.1587
	-	4	53.670	54.270	53.84	2.1198	54.10	2.1300	54.36	2.1403	54.62	2.1505	54.88	2.1607
M62	-	3	54.752	55.252	54.88	2.1607	55.08	2.1684	55.27	2.1761	55.47	2.1837	55.66	2.1914
	-	2	55.835	56.210	55.92	2.2016	56.05	2.2067	56.18	2.2119	56.31	2.2170	56.44	2.2221
	-	1.5	56.376	56.676	56.44	2.2221	56.54	2.2259	56.64	2.2298	56.73	2.2336	56.83	2.2374
M64	5.5	-	54.046	54.796	54.28	2.1372	54.64	2.1512	55.00	2.1653	55.36	2.1794	55.71	2.1934
	-	4	55.670	56.270	55.84	2.1985	56.10	2.2088	56.36	2.2190	56.62	2.2292	56.88	2.2395
	-	3	56.752	57.252	56.88	2.2395	57.08	2.2471	57.27	2.2548	57.47	2.2625	57.66	2.2701
M65	-	2	57.835	58.210	57.92	2.2804	58.05	2.2855	58.18	2.2906	58.31	2.2957	58.44	2.3008
	-	1.5	58.376	58.676	58.44	2.3008	58.54	2.3047	58					



17 TAP DRILL SIZES - UNIFIED THREAD / FORMING TAPS

Table with 12 columns: Size, Threads Per Inch (UNC, UNF, UNEF), Minor Diameter (Min. 2B&3B, Max. 2B, Max. 3B), and Tap Drill Diameter (Cutting Tap) (75% Thread, 70% Thread, 65% Thread, 60% Thread, 55% Thread). Rows include sizes #0 through 3/4.



Table with 12 columns: Size, Threads Per Inch (UNC, UNF, UNEF), Minor Diameter (Min. 2B&3B, Max. 2B, Max. 3B), and Tap Drill Diameter (Cutting Tap) (75% Thread, 70% Thread, 65% Thread, 60% Thread, 55% Thread). Rows include sizes 7/8, 1, 1-1/8, and 1-1/4.



18 TAP DRILL SIZES - METRIC THREAD / FORMING TAPS

Size	Pitch		Minor dia.		Tap Drill Diameter									
	M	MF	Min. 6H	Max. 6H	75% Thread		70% Thread		65% Thread		60% Thread		55% Thread	
					mm	Inch	mm	Inch	mm	Inch	mm	Inch	mm	Inch
M1	0.25	-	0.729	0.798	0.87	.0344	0.88	.0347	0.89	.0350	0.90	.0354	0.91	.0357
	-	0.2	0.783	0.841	0.90	.0354	0.90	.0356	0.91	.0359	0.92	.0362	0.93	.0364
M1.1	0.25	-	0.829	0.898	0.97	.0383	0.98	.0386	0.99	.0390	1.00	.0393	1.01	.0396
	-	0.2	0.883	0.941	1.00	.0393	1.00	.0396	1.01	.0398	1.02	.0401	1.03	.0404
M1.2	0.25	-	0.929	0.998	1.07	.0422	1.08	.0426	1.09	.0429	1.10	.0432	1.11	.0436
	-	0.2	0.983	1.041	1.10	.0432	1.10	.0435	1.11	.0438	1.12	.0440	1.13	.0443
M1.4	0.3	-	1.075	1.159	1.25	.0491	1.26	.0495	1.27	.0499	1.28	.0503	1.29	.0507
	-	0.2	1.183	1.241	1.30	.0511	1.30	.0514	1.31	.0516	1.32	.0519	1.33	.0522
M1.6	0.35	-	1.221	1.321	1.42	.0560	1.43	.0564	1.45	.0569	1.46	.0574	1.47	.0578
	-	0.2	1.383	1.441	1.50	.0590	1.50	.0592	1.51	.0595	1.52	.0598	1.53	.0600
M1.7	0.35	-	1.321	1.421	1.52	.0599	1.53	.0604	1.55	.0608	1.56	.0613	1.57	.0618
	-	0.3	1.375	1.459	1.55	.0609	1.56	.0613	1.57	.0617	1.58	.0621	1.59	.0625
	-	0.25	1.429	1.498	1.57	.0619	1.58	.0622	1.59	.0626	1.60	.0629	1.61	.0632
M1.8	-	0.2	1.483	1.541	1.60	.0629	1.60	.0632	1.61	.0634	1.62	.0637	1.63	.0640
	0.35	-	1.421	1.521	1.62	.0638	1.63	.0643	1.65	.0648	1.66	.0652	1.67	.0657
	-	0.2	1.583	1.641	1.70	.0669	1.70	.0671	1.71	.0674	1.72	.0677	1.73	.0679
M2	0.4	-	1.567	1.679	1.80	.0707	1.81	.0712	1.82	.0718	1.84	.0723	1.85	.0729
	-	0.25	1.729	1.798	1.87	.0737	1.88	.0741	1.89	.0744	1.90	.0747	1.91	.0751
M2.2	0.45	-	1.713	1.838	1.97	.0776	1.99	.0782	2.00	.0788	2.02	.0794	2.03	.0800
	-	0.25	1.929	1.998	2.07	.0816	2.08	.0819	2.09	.0823	2.10	.0826	2.11	.0829
M2.3	0.4	-	1.867	1.979	2.10	.0825	2.11	.0831	2.12	.0836	2.14	.0841	2.15	.0847
	-	0.35	1.921	2.021	2.12	.0835	2.13	.0840	2.15	.0845	2.16	.0849	2.17	.0854
	-	0.25	2.029	2.098	2.17	.0855	2.18	.0859	2.19	.0862	2.20	.0865	2.21	.0869
M2.5	0.45	-	2.013	2.138	2.27	.0894	2.29	.0900	2.30	.0906	2.32	.0912	2.33	.0918
	-	0.35	2.121	2.221	2.32	.0914	2.33	.0919	2.35	.0923	2.36	.0928	2.37	.0933
M2.6	0.45	-	2.113	2.238	2.37	.0933	2.39	.0939	2.40	.0945	2.42	.0951	2.43	.0957
	-	0.35	2.221	2.321	2.42	.0953	2.43	.0958	2.45	.0963	2.46	.0967	2.47	.0972
M3	0.5	-	2.459	2.599	2.75	.1081	2.76	.1087	2.78	.1094	2.80	.1101	2.81	.1107
	-	0.35	2.621	2.721	2.82	.1111	2.83	.1116	2.85	.1120	2.86	.1125	2.87	.1130
M3.5	0.6	-	2.850	3.010	3.19	.1257	3.21	.1266	3.23	.1274	3.26	.1282	3.28	.1290
	-	0.35	3.121	3.221	3.32	.1308	3.33	.1312	3.35	.1317	3.36	.1322	3.37	.1326
M4	0.7	-	3.242	3.422	3.64	.1434	3.67	.1444	3.69	.1453	3.71	.1462	3.74	.1472
	-	0.5	3.459	3.599	3.75	.1474	3.76	.1481	3.78	.1488	3.80	.1494	3.81	.1501
M4.5	0.75	-	3.688	3.878	4.12	.1621	4.14	.1631	4.17	.1641	4.19	.1651	4.22	.1661
	-	0.5	3.959	4.099	4.25	.1671	4.26	.1678	4.28	.1685	4.30	.1691	4.31	.1698
M5	0.9	-	4.026	4.226	4.54	.1788	4.57	.1800	4.60	.1812	4.63	.1824	4.66	.1836
	-	0.8	4.134	4.334	4.59	.1808	4.62	.1819	4.65	.1829	4.67	.1840	4.70	.1851
	-	0.5	4.459	4.599	4.75	.1868	4.76	.1875	4.78	.1881	4.80	.1888	4.81	.1895
M6	1	-	4.917	5.153	5.49	.2161	5.52	.2175	5.56	.2188	5.59	.2202	5.63	.2215
	-	0.75	5.188	5.378	5.62	.2212	5.64	.2222	5.67	.2232	5.69	.2242	5.72	.2252
	-	0.5	5.459	5.599	5.75	.2262	5.76	.2269	5.78	.2275	5.80	.2282	5.81	.2289
M7	1	-	5.917	6.153	6.49	.2555	6.52	.2569	6.56	.2582	6.59	.2595	6.63	.2609
	-	0.75	6.188	6.378	6.62	.2605	6.64	.2615	6.67	.2625	6.69	.2635	6.72	.2645
	-	0.5	6.459	6.599	6.75	.2656	6.76	.2662	6.78	.2669	6.80	.2676	6.81	.2682
M8	1.25	-	6.647	6.912	7.36	.2899	7.41	.2915	7.45	.2932	7.49	.2949	7.53	.2966
	-	1	6.917	7.153	7.49	.2949	7.52	.2962	7.56	.2976	7.59	.2989	7.63	.3002
	-	0.75	7.188	7.378	7.62	.2999	7.64	.3009	7.67	.3019	7.69	.3029	7.72	.3039
	-	0.5	7.459	7.599	7.75	.3049	7.76	.3056	7.78	.3063	7.80	.3069	7.81	.3076
M9	1.25	-	7.647	7.912	8.36	.3292	8.41	.3309	8.45	.3326	8.49	.3343	8.53	.3359
	-	1	7.917	8.153	8.49	.3343	8.52	.3356	8.56	.3369	8.59	.3383	8.63	.3396
	-	0.75	8.188	8.378	8.62	.3393	8.64	.3403	8.67	.3413	8.69	.3423	8.72	.3433
	-	0.5	8.459	8.599	8.75	.3443	8.76	.3450	8.78	.3456	8.80	.3463	8.81	.3470



Size	Pitch		Minor dia.		Tap Drill Diameter									
	M	MF	Min. 6H	Max. 6H	75% Thread		70% Thread		65% Thread		60% Thread		55% Thread	
					mm	Inch	mm	Inch	mm	Inch	mm	Inch	mm	Inch
M10	1.5	-	8.376	8.676	9.24	.3636	9.29	.3656	9.34	.3676	9.39	.3696	9.44	.3716
	-	1.25	8.647	8.912	9.36	.3686	9.41	.3703	9.45	.3719	9.49	.3736	9.53	.3753
	-	1	8.917	9.153	9.49	.3736	9.52	.3750	9.56	.3763	9.59	.3776	9.63	.3790
	-	0.75	9.188	9.378	9.62	.3786	9.64	.3796	9.67	.3806	9.69	.3817	9.72	.3827
M12	-	0.5	9.459	9.599	9.75	.3837	9.76	.3843	9.78	.3850	9.80	.3857	9.81	.3863
	1.75	-	10.106	10.441	11.11	.4373	11.17	.4396	11.23	.4420	11.29	.4443	11.35	.4467
	-	1.5	10.376	10.676	11.24	.4423	11.29	.4443	11.34	.4463	11.39	.4483	11.44	.4504
	-	1.25	10.647	10.912	11.36	.4473	11.41	.4490	11.45	.4507	11.49	.4524	11.53	.4540
M14	-	1	10.917	11.153	11.49	.4524	11.52	.4537	11.56	.4550	11.59	.4564	11.63	.4577
	-	0.75	11.188	11.378	11.62	.4574	11.64	.4584	11.67	.4594	11.69	.4604	11.72	.4614
	-	0.5	11.459	11.599	11.75	.4624	11.76	.4631	11.78	.4637	11.80	.4644	11.81	.4651
	2	-	11.835	12.210	12.98	.5110	13.05	.5137	13.12	.5164	13.18	.5191	13.25	.5217
M16	-	1.5	12.376	12.676	13.24	.5211	13.29	.5231	13.34	.5251	13.39	.5271	13.44	.5291
	-	1.25	12.647	12.912	13.36	.5261	13.41	.5278	13.45	.5294	13.49	.5311	13.53	.5328
	-	1	12.917	13.153	13.49	.5311	13.52	.5324	13.56	.5338	13.59	.5351	13.63	.5365
	-	0.75	13.188	13.378	13.62	.5361	13.64	.5371	13.67	.5381	13.69	.5391	13.72	.5401
M18	-	0.5	13.459	13.599	13.75	.5411	13.76	.5418	13.78	.5425	13.80	.5431	13.81	.5438
	2	-	13.835	14.210	14.98	.5898	15.05	.5924	15.12	.5951	15.18	.5978	15.25	.6005
	-	1.5	14.376	14.676	15.24	.5998	15.29	.6018	15.34	.6038	15.39	.6058	15.44	.6078
	-	1	14.917	15.153	15.49	.6098	15.52	.6112	15.56	.6125	15.59	.6139	15.63	.6152
M20	2.5	-	15.294	15.744	16.73	.6585	16.81	.6618	16.90	.6652	16.98	.6685	17.07	.6719
	-	2	15.835	16.210	16.98	.6685	17.05	.6712	17.12	.6739	17.18	.6765	17.25	.6792
	-	1.5	16.376	16.676	17.24	.6785	17.29	.6806	17.34	.6826	17.39	.6846	17.44	.6866
	-	1	16.917	17.153	17.49	.6886	17.52	.6899	17.56	.6913	17.59	.6926	17.63	.6939
M22	2.5	-	17.294	17.744	18.73	.7372	18.81	.7406	18.90	.7439	18.98	.7472	19.07	.7506
	-	2	17.835	18.210	18.98	.7472	19.05	.7499	19.12	.7526	19.18	.7553	19.25	.7580
	-	1.5	18.376	18.676	19.24	.7573	19.29	.7593	19.34	.7613	19.39	.7633	19.44	.7653
	-	1	18.917	19.153	19.49	.7673	19.52	.7687	19.56	.7700	19.59	.7713	19.63	.7727
M24	2.5	-	19.294	19.744	20.73	.8159	20.81	.8193	20.90	.8226	20.98	.8260	21.07	.8293
	-	2	19.835	20.210	20.98	.8260	21.05	.8287	21.12	.8313	21.18	.8340	21.25	.8367
	-	1.5	20.376	20.676	21.24	.8360	21.29	.8380	21.34	.8400	21.39	.8420	21.44	.8441
	-	1	20.917	21.153	21.49	.8461	21.52	.8474	21.56	.8487	21.59	.8501	21.63	.8514
M26	3	-	20.752	21.252	22.47	.8846	22.57	.8887	22.67	.8927	22.78	.8967	22.88	.9007
	-	2	21.835	22.210										



19 TAP DRILL SIZES – METRIC, UNIFIED THREAD / STI

Metric			Unified		
Size	RECOMMENDATION		Size	RECOMMENDATION	
	Drill Size			Drill Size	
	Inch	metric (mm)		Inch	metric (mm)
M2 x 0.4	.0827	2.10	#2 - 56 UNC	.0906	2.30
M2.2 x 0.45	.0906	2.30	#3 - 48 UNC	.1063	2.70
M2.5 x 0.45	.1024	2.60	#3 - 56 UNF	.1043	2.65
M3 x 0.5	.1240	3.15	#4 - 40 UNC	.1181	3.00
M3.5 x 0.6	.1457	3.70	#4 - 48 UNF	.1181	3.00
M4 x 0.7	.1654	4.20	#5 - 40 UNC	.1339	3.40
M5 x 0.8	.2047	5.20	#5 - 44 UNF	.1299	3.30
M6 x 1.0	.2480	6.30	#6 - 32 UNC	.1457	3.70
M7 x 1.0	.2874	7.30	#6 - 40 UNF	.1457	3.70
M8 x 1.0	.3268	8.30	#8 - 32 UNC	.1732	4.40
M8 x 1.25	.3307	8.40	#8 - 36 UNF	.1732	4.40
M9 x 1.25	.3701	9.40	#10 - 24 UNC	.2008	5.10
M10 x 1.25	.4094	10.40	#10 - 32 UNF	.2008	5.10
M10 x 1.5	.4134	10.50	#12 - 24 UNC	.2283	5.80
M11 x 1.5	.4528	11.50	1/4 - 20 UNC	.2638	6.70
M12 x 1.25	.4882	12.40	1/4 - 28 UNF	.2598	6.60
M12 x 1.5	.4921	12.50	5/16 - 18 UNC	.3307	8.40
M12 x 1.75	.4921	12.50	5/16 - 24 UNF	.3228	8.20
M14 x 1.5	.5709	14.50	3/8 - 16 UNC	.3937	10.00
M14 x 2.0	.5709	14.50	3/8 - 24 UNF	.3858	9.80
M16 x 1.5	.6496	16.50	7/16 - 14 UNC	.4528	11.50
M16 x 2.0	.6496	16.50	7/16 - 20 UNF	.4528	11.50
M18 x .5	.7283	18.50	1/2 - 13 UNC	.5236	13.30
M18 x 2.0	.7283	18.50	1/2 - 20 UNF	.5157	13.10
M18 x 2.5	.7382	18.75	9/16 - 12 UNC	.5866	14.90
M20 x 1.5	.8071	20.50	9/16 - 18 UNF	.5787	14.70
M20 x 2.0	.8071	20.50	5/8 - 11 UNC	.6496	16.50
M20 x 2.5	.8169	20.75	5/8 - 18 UNF	.6417	16.30
M22 x 1.5	.8858	22.50	3/4 - 10 UNC	.7795	19.80
M22 x 2.0	.8858	22.50	3/4 - 16 UNF	.7677	19.50
M22 x 2.5	.8957	22.75	7/8 - 9 UNC	.9055	23.00
M24 x 2.0	.9646	24.50	7/8 - 14 UNF	.8858	22.50
M24 x 3.0	.9843	25.00	1 - 8 UNC	1.0433	26.50
M27 x 3.0	1.1024	28.00	1 - 12 UNF	1.0236	26.00
M30 x 3.5	1.2205	31.00	1-1/8 - 7 UNC	1.1713	29.75
			1-1/8 - 8 UN	1.1417	29.00
			1-1/8 - 12 UNF	1.1516	29.25
			1-1/4 - 7 UNC	1.2992	33.00
			1-1/4 - 8 UN	1.2795	32.50
			1-1/4 - 12 UNF	1.2795	32.50
			1-3/8 - 6 UNC	1.4173	36.00
			1-3/8 - 8 UN	1.3976	35.50
			1-3/8 - 12 UNF	1.4173	36.00
			1-1/2 - 6 UNC	1.5354	39.00
			1-1/2 - 8 UN	1.5354	39.00
			1-1/2 - 12 UNF	1.5354	39.00



20 CONVERSION TABLE

SURFACE FEET PER MINUTE TO REVOLUTIONS PER MINUTE

Surface Feet Per Minute	20	25	30	40	50	60	70	80	90	100	110	120	130	140	150
Tap Size	Revolutions Per Minute														
#0	1273	1592	1910	2546	3183	3820	4456	5093	5730	6366	7003	7639	8276	8913	9549
#1	1047	1308	1570	2093	2617	3140	3663	4186	4710	5233	5756	6279	6808	7326	7849
#2	888	1110	1333	1777	2221	2665	3109	3554	3999	4422	4886	5330	5774	6218	6662
#3	772	964	1157	1543	1929	2315	2701	3086	3472	3858	4244	4629	5015	5401	5787
#4	682	853	1023	1364	1705	2046	2387	2728	3069	3411	3751	4092	4434	4775	5116
#5	611	764	917	1222	1528	1833	2139	2445	2750	3056	3361	3667	3973	4278	4584
#6	553	691	829	1106	1382	1658	1934	2211	2487	2764	3040	3316	3592	3869	4145
#8	466	583	699	932	1165	1398	1631	1864	2097	2330	2563	2796	3029	3262	3495
#10	402	502	603	804	1005	1205	1406	1607	1808	2009	2210	2411	2612	2813	3014
#12	354	442	531	707	884	1061	1238	1415	1592	1769	1945	2122	2300	2476	2653
1/4	306	382	458	611	764	917	1070	1222	1375	1528	1681	1833	1986	2139	2292
5/16	245	306	367	486	611	733	856	978	1100	1222	1345	1467	1589	1711	1833
3/8	204	255	306	407	509	611	713	815	917	1019	1120	1222	1324	1426	1528
7/16	175	219	262	349	437	524	611	698	786	873	960	1048	1135	1222	1310
1/2	153	191	229	306	382	458	535	611	688	764	840	917	993	1070	1146
9/16	137	172	206	275	344	412	481	550	619	687	756	825	893	963	1031
5/8	122	153	183	244	306	367	428	489	550	611	672	733	794	856	917
3/4	102	128	153	203	255	306	357	407	458	509	560	611	662	713	764
7/8	87	109	131	175	218	252	306	350	392	437	480	524	568	611	655
1	76	96	115	153	191	230	268	306	344	382	420	458	497	535	573


TROUBLE SHOOTING GUIDE

Specific Problem	Cause	Solution
Dimensional Accuracy		
Oversize Pitch Diameter	Tap	<ol style="list-style-type: none"> 1. Use proper limits of taps 2. Use longer chamfered taps
	Chip Packing	<ol style="list-style-type: none"> 1. Use spiral point or spiral fluted taps 2. Reduce number of flutes to provide extra chip room 3. Use larger hole size 4. If tapping a hole, allow deeper hole where applicable or shorten the thread length of the parts 5. Use proper lubricant
	Galling	<ol style="list-style-type: none"> 1. Apply proper surface treatment such as Hardslick or chrome 2. Use proper cutting lubricant 3. Reduce tapping speed 4. Use proper cutting angle in accordance with material being tapped 5. Use large hole size
	Operating Conditions	<ol style="list-style-type: none"> 1. Apply proper tapping speed 2. Correct alignment of tap and drill hole 3. Free cutting either tap or workpiece 4. Use proper tapping speed to avoid torn or rough threads 5. Use lead screw tapper 6. Use proper tapping machine with suitable power 7. Avoid misalignment of the tap and drill hole from loose spindle or worn holder
	Tool Condition	<ol style="list-style-type: none"> 1. Obtain proper indexing angle for the flutes at the cutting edge 2. Grind proper cutting angle and chamfer angle 3. Avoid too narrow a land width 4. Remove burrs from regrinding
	Hole Size	<ol style="list-style-type: none"> 1. Use minimum hole size 2. Avoid tapered hole 3. Use proper chamfered taps
Oversize Internal Diameter	Galling	1. Galling solutions 1 through 4 above can be applied to this specific problem
	Incorrect Tap	<ol style="list-style-type: none"> 1. Use oversize taps 2. Apply proper chamfer angle 3. Increase cutting angle
Undersize Pitch Diameter	Damaged Thread	1. Use proper reversing speed to avoid damaging tapped thread on the way out of the hole
	Left-over Chips	<ol style="list-style-type: none"> 1. Increase cutting performance to avoid any left over chips in the hole 2. Remove left over chips from the hole for gage checking
	Hole Size	1. Use maximum drill size
Undersize Internal Diameter	Hole Size	1. Use maximum drill size

Specific Problem	Cause	Solution
Tool Life		
Breakage	Incorrect Tap Selection	<ol style="list-style-type: none"> 1. Avoid chip packing in the flutes or the bottom of the hole. Use spiral pointed or spiral fluted taps or fluteless taps. 2. Apply correct surface treatment such as Hardslick or bright
	Excessive Tapping Torque	<ol style="list-style-type: none"> 1. Use larger drill size 2. Try to shorten thread length 3. Increase cutting angle 4. Apply a tap with more thread relief and reduced land width 5. Apply correct surface treatment such as Hardslick
	Operating Conditions	<ol style="list-style-type: none"> 1. Reduce tapping speed 2. Avoid misalignment between tap and the hole and tapered hole 3. Use floating type of tapping holder 4. Use tapping holder with torque adjustment 5. Avoid hitting bottom of the hole with tap
	Tool Condition	<ol style="list-style-type: none"> 1. Do not grind the bottom of the flute 2. Avoid too narrow a land width 3. Remove all worn sections when regrinding the flutes 4. Regrind tool more frequently
Chipping	Incorrect Tap Selection	<ol style="list-style-type: none"> 1. Reduce cutting angle 2. Use a different kind of high-speed steel tap 3. Reduce hardness of the tap 4. Increase chamfer length 5. Avoid chip packing in the flutes or in the bottom of the hole by using spiral fluted or spiral pointed taps
	Wear	<ol style="list-style-type: none"> 1. Reduce tapping speed 2. Avoid misalignment between tap and hole 3. Avoid sudden return of reverse in blind hole tapping 4. Avoid galling 5. Use larger hole size
Wearx	Incorrect Tap Selection	<ol style="list-style-type: none"> 1. Apply specially designed tap for tapping heat treated material 2. Change to a type of high-speed steel tap that contains vanadium 3. Apply special surface treatment such as TiCN or Hardslick 4. Increase chamfer length
	Operating Conditions	<ol style="list-style-type: none"> 1. Reduce tapping speed 2. Apply proper cutting lubricants 3. Avoid work hardened hole 4. Use larger hole size
	Tool Condition	<ol style="list-style-type: none"> 1. Grind proper cutting angle 2. Avoid hardness reduction from grinding process
Torn or Rough Thread	Chamfer Too Short	1. Increase chamfer length
	Wrong Cutting Angle	1. Apply proper cutting angle

Specific Problem	Cause	Solution
Surface Finish		
Torn or Rough Thread	Galling	<ol style="list-style-type: none"> 1. Use thread relieved taps 2. Reduce land width 3. Apply surface treatment such as Hardslick or chrome 4. Use proper cutting lubricant 5. Reduce tapping speed 6. Use larger hole size 7. Obtain proper alignment between tap and work
	Chip Packing	<ol style="list-style-type: none"> 1. Use spiral pointed or spiral fluted taps 2. Use larger drill size
Chattering on Tapped Thread	Tool Free Cutting	<ol style="list-style-type: none"> 1. Reduce cutting angle 2. Reduce amount of thread relief
	Tool Condition	<ol style="list-style-type: none"> 1. Do not grind the bottom of the flute 2. Avoid too narrow a land width

MILLING TOOLS

CBN END MILLS

i-Xmills, CARBIDE INSERT END MILLS

i-SMART, MODULAR CARBIDE HEAD END MILLS

X5070 NANO SOLID CARBIDE END MILLS

4G MILL SOLID CARBIDE END MILLS

X-POWER SOLID CARBIDE END MILLS

JET-POWER SOLID CARBIDE & HSS-PM END MILLS

TitaNox-POWER SOLID CARBIDE END MILLS

V7 PLUS A SOLID CARBIDE END MILLS

V7 Mill INOX SOLID CARBIDE END MILLS

ALU-POWER HPC SOLID CARBIDE END MILLS

ALU-POWER SOLID CARBIDE & HSS-PM END MILLS

D-POWER GRAPHITE DIAMOND COATED SOLID CARBIDE END MILLS

D-POWER CFRP DIAMOND COATED SOLID CARBIDE END MILLS

SOLID CARBIDE ROUTERS CFRP

STANDARD CARBIDE END MILLS

ONLY ONE COATED PM60 END MILLS

SINE-POWER HSS END MILLS

TANK-POWER HSS-PM END MILLS

COBALT & HSS END MILLS

TECHNICAL DATA

CBN END MILLS

CBN END MILLS

Machining High Hardened Steels up to HRc70 / Mirror Finish

CBN
END MILLS

CARBIDE INSERT END MILLS

i-Xmills, CARBIDE INSERT END MILLS

Available for General Steels(~HRc50), Hardened Steels(up to HRc65) and Graphite

i-Xmill
END MILLS

i-Smart, MODULAR CARBIDE HEAD END MILLS

Exchangeable Modular Head for Semi-finishing and finishing on Pre-Hardened Steels up to HRc55

i-SMART
MODULAR
TYPE END MILLS

SOLID CARBIDE END MILLS

X5070 NANO SOLID CARBIDE END MILLS

High Hardened Steels HRc45 to HRc70 / High Speed Machining / Dry Cutting

X5070
END MILLS

4G MILL SOLID CARBIDE END MILLS

High Speed Cutting for Pre-Hardened Steels up to HRc55

4G MILL
END MILLS

X-POWER SOLID CARBIDE END MILLS

Medium Steels to High Hardened Steels up to HRc70

X-POWER
END MILLS

JET-POWER SOLID CARBIDE & HSS-PM END MILLS

Exotic materials like Stainless Steels, Nickel alloys and Titanium

JET-POWER
END MILLS

TitaNox-POWER SOLID CARBIDE END MILLS

High Speed Machining for Exotic Materials: Titanium, Inconel and Stainless Steels

TitaNox
-POWER
END MILLS

V7 PLUS A SOLID CARBIDE END MILLS

Silent Cutting of Steels up to HRc40 / Designed as Unequal Leads

V7 PLUS A
END MILLS

V7 Mill INOX SOLID CARBIDE END MILLS

Stainless Steels in Heavy and Silent Cutting Materials up to HRc40
Designed as Variable Leads / YG-1's Patent

V7 MILL INOX
END MILLS

ALU-POWER HPC SOLID CARBIDE END MILLS

Aluminum, Non-Ferrous and Non-Metallic Materials / Heavy Cutting

ALU-POWER
HPC
END MILLS

ALU-POWER SOLID CARBIDE & HSS-PM END MILLS

Aluminium Alloys and Silent Cutting / Mirror Surface

ALU-POWER
END MILLS

D-POWER GRAPHITE DIAMOND COATED SOLID CARBIDE END MILLS

Diamond Coated Carbide End Mills for Graphite

D-POWER
GRAPHITE
END MILLS

D-POWER CFRP DIAMOND COATED SOLID CARBIDE END MILLS

Diamond Coated Carbide End Mills for composite materials including CFRP, GFRP

D-POWER
CFRP
END MILLS

HSS END MILLS

SOLID CARBIDE ROUTERS CFRP

For composite materials including CFRP, GFRP

ROUTERS
CFRP

STANDARD CARBIDE END MILLS

General Purpose / Any Coating Available

STANDARD
CARBIDE
END MILLS

TECHNICAL DATA

ONLY ONE COATED PM60 END MILLS

The optimal solution for unstable cutting condition

ONLY ONE
COATED PM60
END MILLS

SINE-POWER HSS END MILLS

High Performance HSS Rougher for Titanium and Titanium Alloys

SINE-POWER
END MILLS

TANK-POWER HSS-PM END MILLS

Next Generation of Powdered Metal End Mills / Higher Edge Strength & Feed Rates

TANK-POWER
END MILLS

COBALT & HSS END MILLS

General Purpose / Non-coated / Any Coating Available

STANDARD
COBALT & HSS
END MILLS

TECHNICAL DATA

TECHNICAL
DATA

◎ : Excellent ○ : Good

ITEM	MODEL	DESCRIPTION	PAGE
------	-------	-------------	------

INCH

i-Xmill	XB1A		i-Xmill BALL INSERT FOR GENERAL PURPOSE	598
	XB2C		i-Xmill BALL INSERT FOR HARDENED STEEL	
	XB1D		i-Xmill BALL INSERT FOR GRAPHITE	
	ZBT / ZBS		i-Xmill BALL HOLDERS - STEEL	599
	ZBC		i-Xmill BALL HOLDERS - CARBIDE	600
	XR1A		i-Xmill CORNER RADIUS INSERTS FOR GENERAL PURPOSE	601
	XR2A		i-Xmill CORNER RADIUS INSERTS FOR HARDENED STEEL	
	XR1D		i-Xmill CORNER RADIUS INSERTS FOR GRAPHITE	
ZRT / ZRS		i-Xmill CORNER RADIUS HOLDERS - STEEL	602	

METRIC

i-Xmill	XB1N		i-Xmill BALL INSERT FOR GENERAL PURPOSE	603
	XB2N		i-Xmill BALL INSERT FOR HARDENED STEEL	
	XBAD		i-Xmill BALL INSERT FOR GRAPHITE	
	ZBT / ZBS		i-Xmill BALL HOLDERS - STEEL	604
	ZBC		i-Xmill BALL HOLDERS - CARBIDE	605
	XRAA		i-Xmill CORNER RADIUS INSERTS FOR GENERAL PURPOSE	606
	XRBA		i-Xmill CORNER RADIUS INSERTS FOR HARDENED STEEL	
	XRAD		i-Xmill CORNER RADIUS INSERTS FOR GRAPHITE	
ZRT / ZRS		i-Xmill CORNER RADIUS HOLDERS - STEEL	608	
			ASSEMBLY RECOMMENDATIONS	609
			RECOMMENDED CUTTING CONDITIONS	610

ITEM	MODEL	DESCRIPTION	SIZE RANGE		PAGE
			MIN	MAX	
i-Smart	XGMF15		R3/16	R5/8	616
	XGMF17		R3/16	R5/8	617
	XGMF20		D3/8	D1-1/4	618
	XGMF25		D3/8	D1-1/4	619
	XGMF29		D3/8	D1-1/4	620





























P						M	K	N		
Carbon Steels		Alloy Steels		Tool Steels		Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Graphite
~HRc35	HRc35~	~HRc35	HRc35~	~HRc35	HRc35~	HRc50~	~HRc28	~HRc35	~HRc8	
◎	○	◎	○	◎	○		○	○	○	
○	◎	○	◎	○	◎	◎		◎		
○		○		○					○	◎
◎	○	◎	○	◎	○		○	○	○	
○	◎	○	◎	○	◎	◎		◎		
○		○		○					○	◎

◎	○	◎	○	◎	○		○	○	○	
○	◎	○	◎	○	◎	◎		◎		
○		○		○					○	◎
◎	○	◎	○	◎	○		○	○	○	
○	◎	○	◎	○	◎	◎		◎		
○		○		○					○	◎

◎ : Excellent ○ : Good





























P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○							
○	◎	◎	◎	○			○							
◎	◎	◎	◎	○			○							
◎	◎	◎	◎	○		○	○							
◎	◎	◎	◎	○			○							

◎ : Excellent ○ : Good

	ITEM	MODEL	FLUTES	HELIX	INCH / METRIC	TYPE	SIZE RANGE		PAGE
							MIN	MAX	
CBN	ESB94		2Flute	30°	Metric	Ball	R0.2	R1.5	592
	ESD02		2Flute	0°	Metric	Radius	D0.5	D2.0	593
X5070	G826	High Feed End Mill 	4Flute	0°	Inch	Radius	D1/8	D1/2	630
	G8A43		2Flute	30°	Inch	Ball	R1/64	R1/4	631
	G850		4Flute	30°	Inch	Radius	D1/16	D3/4	632
	G851		6&8Flute	45°	Inch	Radius	D1/4	D1	633
	G859	High Feed End Mill 	4Flute	0°	Metric	Radius	D2.0	D16.0	634
	G854	High Feed End Mill 	4Flute	0°	Metric	Radius	D2.0	D16.0	635
	G8A46		2Flute	30°	Metric	Ball for Rib	R0.05	R2.0	636
	G8A54		2Flute	30°	Metric	Ball for Rib	R0.25	R1.0	640
	G8A28		2Flute	30°	Metric	Ball	R0.05	R6.0	641
	G8A38		2Flute	30°	Metric	Stub Ball with Extended Neck	R0.5	R12.5	642
	G8A53		2Flute	30°	Metric	Miniature Ball	R0.2	R1.0	643
	G8A59		3Flute	30°	Metric	Ball	R1.5	R10.0	644
	G8A36		2Flute	30°	Metric	Stub Radius with Extended Neck	D0.3	D20.0	645
	G8A50		2Flute	30°	Metric	Miniature Radius	D0.3	D2.0	647
	G8A47		4Flute	30°	Metric	Radius	D3.0	D12.0	648
	G8A37		4Flute	30°	Metric	Stub Radius with Extended Neck	D1.0	D20.0	649
	G8A39		6Flute	45°	Metric	Radius	D6.0	D20.0	650
	4G Mill	GMF15		2Flute	30°	Inch	Ball	R.002	R3/8
GMF16			2Flute	30°	Inch	Ball with Neck	R.004	R1/4	668
GMF17			4Flute	30°	Inch	Ball	R1/16	R1/4	671
GMF18			2Flute	30°	Inch	Radius	D3/64	D3/4	672
GMF19			2Flute	30°	Inch	Radius with Neck	D.008	D3/4	675
GMF20			4Flute	27°/30°	Inch	Radius	D3/64	D3/4	681
GMF21			4Flute	27°/30°	Inch	Radius with Neck	D3/64	D3/4	683
GMF22			2Flute	30°	Inch	with Neck	D.008	D1/2	688
GMF23			2Flute	30°	Inch	Square	D.004	D.120	691

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
				◎	◎									
				◎	◎									
		○	○	◎	◎									
		○	○	◎	◎									
		○	○	◎	◎									
		○	○	◎	◎									
		○	○	◎	◎									
		○	○	◎	◎									
		○	○	◎	◎									
		○	○	◎	◎									
		○	○	◎	◎									
		○	○	◎	◎									
		○	○	◎	◎									
		○	○	◎	◎									
○	◎	◎	◎	○			○							
○	◎	◎	◎	○			○							
○	◎	◎	◎	○			○							
◎	◎	◎	◎	○			○							
◎	◎	◎	◎	○			○							
◎	◎	◎	◎	○			○							
◎	◎	◎	◎	○			○							
◎	◎	◎	◎	○			○							
◎	◎	◎	◎	○			○							

◎ : Excellent ○ : Good

ITEM	MODEL	FLUTES	HELIX	INCH / METRIC	TYPE	SIZE RANGE		PAGE
						MIN	MAX	
EM154		2Flute	30°	Inch	Regular	D1/16	D1	856
EM206		2Flute	30°	Inch	Long	D1/8	D1	856
EM959		2Flute	30°	Inch	Miniature	D.016	D.062	857
EM153		4Flute	30°	Inch	Regular	D1/16	D1	858
EM207		4Flute	30°	Inch	Long	D1/8	D1	858
EM636		2Flute	30°	Inch	Short Radius	D1/16	D1/2	859
EM639		4Flute	30°	Inch	Short Radius	D1/16	D1/2	859
EM637		2Flute	30°	Inch	Regular Radius	D1/16	D1/2	860
EM649		4Flute	30°	Inch	Regular Radius	D1/16	D1/2	860
EM211		2Flute	30°	Inch	Long Radius	D1/4	D1/2	861
EM212		4Flute	30°	Inch	Long Radius	D1/4	D1/2	861
EM102		4Flute	45°	Inch	Long	D3/8	D7/8	862
EM103		4Flute	45°	Inch	Long Reach Radius	D3/8	D7/8	863
EM965		4Flute	55°	Inch	Stub Radius	D1/4	D1/2	864
EM208		6&8Flute	45°	Inch	Long	D1/4	D1	865
EM218		6&8Flute	45°	Inch	Extra Long	D1/4	D1	865
EM668		6&8Flute	45°	Inch	Long Radius	D1/4	D3/4	866
EM209		2Flute	30°	Inch	Long Ball	R1/64	R1/2	867
EM210		4Flute	30°	Inch	Long Ball	R1/16	R1/2	867
EM961		2Flute	30°	Inch	Medium Ball	R1/16	R1/2	868
EM962		2Flute	30°	Inch	Long Reach Ball	R3/64	R3/8	869
EM960		2Flute	30°	Inch	Miniature Ball	R.012	R.031	870
EM109		2Flute	15°	Inch	Stub Ball	R1/64	R1/4	871
EM963		2Flute	30°	Inch	Ball with Taper Neck	R1/32	R1/4	872
EM979		2Flute	30°	Inch	Ball with Pencil Neck	R3/32	R1/4	873
EM084		2Flute	30°	Inch	Long Ball	R1/16	R5/16	875
EM093		4Flute	30°	Inch	Long Ball	R1/16	R5/16	876
EM096		2Flute	30°	Inch	Long Ball	R1/16	R5/16	877





























X-POWER

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○			○							
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○			○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○										
○	◎	◎	◎	○		○	○							

MILLING TOOLS APPLICATION TABLE

SOLID

⊙ : Excellent ○ : Good




ITEM	MODEL	FLUTES	HELIX	INCH / METRIC	TYPE	SIZE RANGE		PAGE		
						MIN	MAX			
V7 PLUS A	GMG55		4Flute	35°/37°	Metric	Ball	D3.0	D25.0	996	
	GMF53 GMF57		4Flute	35°/37°	Metric	Chamfer	D3.0	D25.0	998	
	GMF55 GMF59		4Flute	35°/37°	Metric	Corner Radius	D3.0	D25.0	998	
	GMG56		4Flute	35°/37°	Metric	Ball	D3.0	D25.0	998	
	GMF60		4Flute	35°/37°	Metric	Chamfer with Neck	D3.0	D20.0	1000	
	GMF62		4Flute	35°/37°	Metric	Radius with Neck	D3.0	D20.0	1000	
	GMF61		4Flute	35°/37°	Metric	Chamfer with Neck	D3.0	D20.0	1002	
	GMF63		4Flute	35°/37°	Metric	Radius with Neck	D3.0	D20.0	1002	
	GMG12 GMG14		6Flute	45°	Metric	Square	D6.0	D25.0	1004	
	GMG16 GMG18		6Flute	45°	Metric	Corner Radius	D6.0	D25.0	1004	
	GMG13 GMG15		6Flute	45°	Metric	Square	D6.0	D25.0	1005	
	GMG17 GMG19		6Flute	45°	Metric	Corner Radius	D6.0	D25.0	1005	
	V7 Mill INOX	EMC75 EMD60		4Flute	Sinusoidal	Inch	Stub Square	D1/8	D1	1020
EMC76 EMD61			4Flute	Sinusoidal	Inch	Stub Radius	D1/8	D1	1021	
EMB12 EMB37			4Flute	Sinusoidal	Inch	Regular Square	D1/8	D1	1022	
EMB13 EMB38			4Flute	Sinusoidal	Inch	Regular Radius	D1/8	D1	1023	
EMB20			4Flute	Sinusoidal	Inch	Extended Long Reach	D1/4	D1	1024	
EMB78 EMB79			4Flute	Sinusoidal	Inch	Regular Ball	R1/16	R1/2	1025	
EMB76 EMB77			5Flute	Sinusoidal	Inch	Regular Square	D1/4	D1	1026	
EMB41 EMB42			4Flute	Sinusoidal	Metric	Short Square	D3.0	D20.0	1027	
EMB43 EMB44			4Flute	Sinusoidal	Metric	Short Radius	D3.0	D20.0	1028	
EMB14 EMB39			4Flute	Sinusoidal	Metric	Regular Square	D3.0	D25.0	1029	
EMB15 EMB40			4Flute	Sinusoidal	Metric	Regular Radius	D3.0	D25.0	1030	
EMB74 EMB75			4Flute	Sinusoidal	Metric	Regular Ball	R1.5	R12.5	1031	
EMB72 EMB73			5Flute	Sinusoidal	Metric	Regular Square	D6.0	D25.0	1032	
ALU-POWER HPC		JAG95		3Flute	37°	Inch	Square	D1/8	D1	1038
		JAG97		3Flute	37°	Inch	Corner Radius	D1/8	D1	1038
	E5G95		3Flute	37°	Inch	Square	D1/8	D1	1040	

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45	HRc45~55	HRc55~70									
⊙	⊙	⊙	○			⊙	⊙					○	○	
⊙	⊙	⊙	○			⊙	⊙					○	○	
⊙	⊙	⊙	○			⊙	⊙					○	○	
⊙	⊙	⊙	○			⊙	⊙					○	○	
⊙	⊙	⊙	○			⊙	⊙					○	○	
⊙	⊙	⊙	○			⊙	⊙					○	○	
⊙	⊙	⊙	○			⊙	⊙					○	○	
○	⊙	⊙	○			⊙	⊙					○	○	
⊙	⊙	⊙	○			⊙	⊙					○	○	
⊙	⊙	⊙	○			⊙	⊙					○	○	
⊙	○	○				⊙	⊙					⊙	○	
⊙	○	○				⊙	⊙					⊙	○	
⊙	○	○				⊙	⊙					⊙	○	
⊙	○	○				⊙	⊙					⊙	○	
⊙	○	○				⊙	⊙					⊙	○	
⊙	○	○				⊙	⊙					⊙	○	
												⊙		
												⊙		
												⊙		

MILLING TOOLS APPLICATION TABLE







SOLID

◎ : Excellent ○ : Good

ITEM	MODEL	FLUTES	HELIX	INCH / METRIC	TYPE	SIZE RANGE		PAGE	
						MIN	MAX		
CARBIDE	E5068		5Flute	45°	Inch	Long Square	D1/4	D1	1152
	E5073		5Flute	45°	Inch	Extra Long Square	D5/16	D1	1154
	E5058		6Flute	40°	Inch	Regular Square	D3/16	D3/4	1155
	E5056 E5057		5Flute	45°	Inch	Stub & Regular Roughing	D3/8	D1	1156
	E5077		3Flute	30°	Inch	Taper	D3/32	D1/4	1157
	E5078		3Flute	30°	Inch	Taper Ball	R.047	R.125	1158
	EH527		2Flute	30°	Metric	Long	D3.5	D20.0	1159
	EH540		4Flute	30°	Metric	Long	D3.5	D20.0	1160
	EH882		3Flute	35°	Metric	Radius	D3.0	D20.0	1161
ONLY ONE	GYG64		2Flute	30°	Inch	Square	D1/8	D1	1174
	GYG67		4Flute	30°	Inch	Ball	R1/16	R1/2	1175
	GYG65		4Flute	30°	Inch	Square	D1/8	D1	1176
	GYG66		4Flute	M-Helix	Inch	Square	D1/8	D1	1177
	GYG69		4&5Flute	M-Helix	Inch	Roughing Radius	D1/4	D1	1178
	GYG68		3-6Flute	30°	Inch	Roughing	D1/4	D1-1/4	1179
	GYG70		3-6Flute	30°	Inch	Roughing	D1/4	D1-1/4	1180
SINE-POWER	E2F64		4&6Flute	35°	Inch	Square	D3/4	D2	1190
TANK-POWER	E9983		2Flute	30°	Inch	Regular Square	D1/8	D1	1196
	E9984		2Flute	30°	Inch	Regular Double Square	D1/8	D1	1197
	E9985		4Flute	30°	Inch	Regular Square	D1/8	D1	1198
	E9986		4Flute	30°	Inch	Regular Double Square	D1/8	D1	1199
	E9988		3&4Flute	60°	Inch	Regular Square	D1/4	D1	1200
	E9992		2Flute	30°	Inch	Regular Ball	R1/16	R1/2	1201
	E9990		3~6Flute	30°	Inch	Regular Roughing	D1/4	D1-1/4	1202
	E9991		3~6Flute	30°	Inch	Regular Roughing	D1/4	D1-1/4	1203
	E9A86		3~6Flute	30°	Inch	Long Roughing	D5/16	D1-1/4	1204
	E9A87		3~6Flute	30°	Inch	Long Roughing	D5/16	D1-1/4	1205
	E9921		5~6Flute	35°	Inch	Long Roughing with Neck	D1/2	D1-1/4	1206

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45	HRC45~55	HRC55~70									
◎	◎	◎	○			◎	○	○					○	○
◎	◎	◎	○			◎	○	○					○	○
◎	◎	◎	○			◎	○	○					○	○
○	◎	◎	○			◎							○	
◎	◎	◎				○	○	○		○				
◎	◎	◎	○			○	○	○		○				
◎	◎	◎	○			○	○	○		○				
◎	◎	◎	○				○	◎		◎				
◎	◎	○	○			◎	◎	○						
◎	◎	○	○			◎	◎	○						
◎	◎	○	○			◎	◎	○						
◎	◎	○	○			◎	◎	○					◎	
◎	◎	◎				◎	◎	○						
◎	◎	◎				◎	◎	○						
◎	◎	◎				◎	◎	○						
◎	◎	◎				◎	◎	○						
◎	◎	◎				◎	◎	○						
◎	◎	◎				◎	◎	○						
◎	◎	◎				◎	◎	○						

◎ : Excellent ○ : Good

	ITEM	MODEL	FLUTES	HELIX	INCH / METRIC	TYPE	SIZE RANGE		PAGE
							MIN	MAX	
COBALT & HSS	E2120 E2121		3&4Flute	60°	Inch	Regular Square	D1/4 D7/8	D3/4 D2	1274
	E2160		3Flute	30°	Inch	Short Square	D1/16	D1/4	1275
	E2161		3Flute	30°	Inch	Long Square	D1/16	D1/4	1275
	E2237 E1237		4Flute	0°	Inch	Corner Rounding	D1/4	D5/8	1276
	E2482 E1482		4Flute	30°	Inch	Regular Square	D2.0 (.0787)	D45.0 (1.772)	1277
	E2483 E1483		2Flute	30°	Inch	Regular Square	D2.0 (.0787)	D45.0 (1.772)	1278


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45	HRC45~55	HRC55~70									
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				



Being the best through innovation





Global Cutting Tool Leader **YG-1**



CBN (Cubic Boron Nitride) END MILLS

- Cubic Boron Nitride, Machining High Hardened Steels up to HRC70, Mirror Finish

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
ESB94		CBN, 2 FLUTE BALL NOSE	R0.2	R1.5	592
ESD02		CBN, 2 FLUTE CORNER RADIUS	D0.5	D2.0	593
RECOMMENDED CUTTING CONDITIONS					594

◎ : Excellent ○ : Good


Carbon Steels	Alloy Steels	P			High Hardened Steels	M	K	N					S		
		Prehardened Steels	Hardened Steels					Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70										
				◎	◎										
				◎	◎										



ESB94 SERIES PLAIN SHANK

CBN, 2 FLUTE BALL NOSE

- ▶ Higher accuracy, better finishes, longer tool life.
- ▶ Special geometry improves tool rigidity at high Speed.
- ▶ Tighter radius tolerance ($\pm 0.005\text{mm}$) assures higher accuracy.



Unit : mm

EDP No.	Radius of Ball Nose R (± 0.005)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
ESB94004012	RO.2	0.4	.0157	4	0.3	1.2	50	0.37
ESB94005015	RO.25	0.5	.0197	4	0.4	1.5	50	0.46
ESB94006015	RO.3	0.6	.0236	4	0.5	1.5	50	0.56
ESB94008020	RO.4	0.8	.0315	4	0.6	2	50	0.76
ESB94010025	RO.5	1.0	.0394	4	0.6	2.5	50	0.95
ESB94010040	RO.5	1.0	.0394	4	0.6	4	50	0.95
ESB94010060	RO.5	1.0	.0394	4	0.6	6	50	0.95
ESB94012030	RO.6	1.2	.0472	4	0.8	3	50	1.15
ESB94015030	RO.75	1.5	.0591	4	0.95	3	50	1.45
ESB94015040	RO.75	1.5	.0591	4	0.95	4	50	1.45
ESB94015060	RO.75	1.5	.0591	4	0.95	6	50	1.45
ESB94020050	R1.0	2.0	.0787	4	1.2	5	50	1.95
ESB94020060	R1.0	2.0	.0787	4	1.2	6	50	1.95
ESB94030060	R1.5	3.0	.1181	4	1.8	6	50	2.85

Radius Tolerance(mm)	Shank Dia. Tolerance
± 0.005	h5

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
					◎									



ESD02 SERIES PLAIN SHANK

CBN, 2 FLUTE CORNER RADIUS

- ▶ Higher accuracy, better finishes, longer tool life.
- ▶ Special geometry improves tool rigidity at high Speed.
- ▶ Tighter radius tolerance ($\pm 0.005\text{mm}$) assures higher accuracy.



Unit : mm

EDP No.	Corner Radius R (± 0.005)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
ESD02005052	RO.05	0.5	.0197	4	0.3	2	50	0.46
ESD02005053	RO.05	0.5	.0197	4	0.3	3	50	0.46
ESD02010053	RO.05	1.0	.0394	4	0.7	3	50	0.95
ESD02010055	RO.05	1.0	.0394	4	0.7	5	50	0.95
ESD02010103	RO.1	1.0	.0394	4	0.7	3	50	0.95
ESD02010105	RO.1	1.0	.0394	4	0.7	5	50	0.95
ESD02015105	RO.1	1.5	.0591	4	1.0	5	50	1.45
ESD02015108	RO.1	1.5	.0591	4	1.0	8	50	1.45
ESD02015205	RO.2	1.5	.0591	4	1.0	5	50	1.45
ESD02015208	RO.2	1.5	.0591	4	1.0	8	50	1.45
ESD02020106	RO.1	2.0	.0787	4	1.2	6	50	1.95
ESD02020100	RO.1	2.0	.0787	4	1.2	10	50	1.95
ESD02020206	RO.2	2.0	.0787	4	1.2	6	50	1.95
ESD02020200	RO.2	2.0	.0787	4	1.2	10	50	1.95

Corner Radius Tolerance(mm)	Shank Dia. Tolerance
± 0.005	h5

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
					◎									

CARBIDE

HSS




RECOMMENDED CUTTING CONDITIONS

CBN, 2 FLUTE BALL NOSE

ESB94 SERIES

MATERIAL	P		H	
	HARDENED STEELS		HIGH HARDENED STEELS	
	HRc50 ~ HRc60		HRc60 ~ HRc70	
HARDNESS				
DIAMETER	RPM	FEED	RPM	FEED
R0.2 × 0.4	50,000	47.2	50,000	47.2
R0.25 × 0.5	50,000	59.1	50,000	59.1
R0.3 × 0.6	50,000	78.7	50,000	78.7
R0.4 × 0.8	50,000	78.7	50,000	78.7
R0.5 × 1.0	50,000	118.1	50,000	118.1
R0.6 × 1.2	50,000	118.1	50,000	118.1
R0.75 × 1.5	50,000	118.1	50,000	118.1
R1.0 × 2.0	40,000	126.0	32,000	98.4
R1.5 × 3.0	26,500	82.7	21,500	66.9




RPM = rev./min.
 FEED = inch/min.

CBN, 2 FLUTE CORNER RADIUS

ESD02 SERIES

MATERIAL	P				H			
	HARDENED STEELS				HIGH HARDENED STEELS			
	HRc50 ~ HRc60				HRc60 ~ HRc70			
DIAMETER	RPM	FEED	DEPTH OF CUT		RPM	FEED	DEPTH OF CUT	
			ae[mm]	ap[mm]			ae[mm]	ap[mm]
0.5	50,000	27.6	0.10	0.01	50,000	21.7	0.06	0.005
1.0	43,000	39.4	0.20	0.01	30,000	27.6	0.10	0.10
1.5	30,000	39.4	0.40	0.02	19,000	27.6	0.20	0.20
2.0	22,000	35.4	0.60	0.03	14,000	31.5	0.30	0.30



RPM = rev./min.
 FEED = inch/min.



Being the best through innovation

CARBIDE INSERT & HOLDER










i-Xmill

- Available for General Steels(~HRc50) Hardened Steels (up to HRc65) and Graphite

SELECTION GUIDE

i-Xmill END MILLS

◎ : Excellent ○ : Good

ITEM	MODEL	DESCRIPTION	PAGE
INCH			
XB1A		i-Xmill BALL INSERT FOR GENERAL PURPOSE	598
XB2C		i-Xmill BALL INSERT FOR HARDENED STEEL	
XB1D		i-Xmill BALL INSERT FOR GRAPHITE	
ZBT / ZBS		i-Xmill BALL HOLDERS - STEEL	599
ZBC		i-Xmill BALL HOLDERS - CARBIDE	600
XR1A		i-Xmill CORNER RADIUS INSERTS FOR GENERAL PURPOSE	601
XR2A		i-Xmill CORNER RADIUS INSERTS FOR HARDENED STEEL	
XR1D		i-Xmill CORNER RADIUS INSERTS FOR GRAPHITE	
ZRT / ZRS		i-Xmill CORNER RADIUS HOLDERS - STEEL	602

METRIC			
XB1N		i-Xmill BALL INSERT FOR GENERAL PURPOSE	603
XB2N		i-Xmill BALL INSERT FOR HARDENED STEEL	
XBAD		i-Xmill BALL INSERT FOR GRAPHITE	
ZBT / ZBS		i-Xmill BALL HOLDERS - STEEL	604
ZBC		i-Xmill BALL HOLDERS - CARBIDE	605
XRAA		i-Xmill CORNER RADIUS INSERTS FOR GENERAL PURPOSE	606
XRBA		i-Xmill CORNER RADIUS INSERTS FOR HARDENED STEEL	
XRAD		i-Xmill CORNER RADIUS INSERTS FOR GRAPHITE	
ZRT / ZRS		i-Xmill CORNER RADIUS HOLDERS - STEEL	608
		ASSEMBLY RECOMMENDATIONS	609
		RECOMMENDED CUTTING CONDITIONS	610

P						M	K	N		
Carbon Steels		Alloy Steels		Tool Steels		Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Graphite
~HRC35	HRC35~	~HRC35	HRC35~	~HRC35	HRC35~	HRC50~	~HRC28	~HRC35	~HRC8	
◎	○	◎	○	◎	○		○	○	○	
○	◎	○	◎	○	◎	◎		◎		
○		○		○					○	◎
◎	○	◎	○	◎	○		○	○	○	
○	◎	○	◎	○	◎	◎		◎		
○		○		○					○	◎

◎	○	◎	○	◎	○		○	○	○	
○	◎	○	◎	○	◎	◎		◎		
○		○		○					○	◎
◎	○	◎	○	◎	○		○	○	○	
○	◎	○	◎	○	◎	◎		◎		
○		○		○					○	◎




XB1A SERIES

XB2C SERIES

XB1D SERIES

i-Xmill BALL INSERTS

- ▶ Exchangeable End Mill for economic use
- ▶ Three Types of Inserts are available
 - For General Purpose (~HRc50)
 - For Hardened Material (HRc40~HRc65)
 - For Graphite
- ▶ Special Geometry and extremely abrasive resistant Coating for Excellent Performance



cutting conditions : p.610

Unit : Inch

EDP No.			Radius of Ball Nose	Mill Diameter	Height	Thickness
For General Material	For Hardened Material	For Graphite	R	D	H	T
XB1A020	XB2C020	XB1D020	R5/32	5/16	5/16	.094
XB1A024	XB2C024	XB1D024	R3/16	3/8	3/8	.106
XB1A032	XB2C032	XB1D032	R1/4	1/2	7/16	.126
XB1A040	XB2C040	XB1D040	R5/16	5/8	1/2	.165
XB1A048	XB2C048	XB1D048	R3/8	3/4	5/8	.205
XB1A100	XB2C100	XB1D100	R1/2	1	3/4	.244
XB1A116	XB2C116	XB1D116	R5/8	1-1/4	31/32	.283

• The ball radius tolerance is ±.0004" and the set-up accuracy is ±.0008"

◎ : Excellent ○ : Good

	P				M		K	N		Graphite
	Carbon Steels		Alloy Steels		Tool Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	
	~HRc35	HRc35~	~HRc35	HRc35~	~HRc35	HRc35~	HRc50~	~HRc28	~HRc35	
XB1A	◎	○	◎	○	◎	○		○	○	○
XB2C	○	◎	○	◎	○	◎	◎		◎	
XB1D	○		○		○				○	◎




ZBT SERIES

ZBS SERIES

i-Xmill BALL HOLDERS - STEEL

- ▶ Premium alloy steel with excellent strength.
- ▶ Precise shank, Tolerance (h6).
- ▶ Nickel plated, to prevent corrosion and improve lubricity.




Taper neck Type

Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Interference Angle	Length Type	Wrench No.	Screw No.
	D1	D2	L1	L3	L2	D3	θ°			
ZBT1020	5/16	1/2	1/2	1-5/8	3-5/8	9/32	4° 33'	Short	TWF07	TX0807
ZBT2020			1	2-1/2	4-3/8		3° 25'	Regular		
ZBT1024	3/8	1/2	5/8	1-1/2	3-9/16	11/32	3° 49'	Short	TWF08	TX1008
ZBT2024			1-1/4	2-5/16	4-3/8		3° 08'	Regular		
ZBT1032	1/2	5/8	11/16	2-3/16	4-3/8	7/16	2° 49'	Short	TWF10	TX1210
ZBT1040	5/8	3/4	13/16	2-9/16	5	9/16	2° 25'	Short	TWF15	TX1615
ZBT1048	3/4	1	1	3-1/8	6	43/64	3° 53'	Short	● TWB20	TX2020
ZBT1100	1	1-1/4	1-1/4	3-9/16	7	29/32	3° 45'	Short	● TWB25	TX2525
ZBT1116	1-1/4	1-1/4	1-9/16	4-3/8	8	1-1/16	1° 30'	Short	● TWB30	TX3030

● Need to use T Handle : TWH600 (See page 52)



Straight neck Type

Unit :Inch


EDP No.	Mill Diameter	Shank Diameter	Length Below Shank	Overall Length	Neck Diameter	Length Type	Wrench No.	Screw No.
	D1	D2	L3	L2	D3			
ZBS1032	1/2	1/2	1-3/8	3-1/2	7/16	Short	TWF10	TX1210
ZBS2032			2-3/16	4-3/8		Regular		
ZBS1040	5/8	5/8	1-3/8	3-3/4	9/16	Short	TWF15	TX1615
ZBS2040			2-9/16	5		Regular		
ZBS1048	3/4	3/4	1-9/16	4-3/8	43/64	Short	● TWB20	TX2020
ZBS2048			3	6		Regular		
ZBS1100	1	1	1-3/4	5	29/32	Short	● TWB25	TX2525
ZBS2100			3-9/16	6-3/4		Regular		
ZBS1116	1-1/4	1-1/4	2-1/4	5-1/2	1-1/16	Short	● TWB30	TX3030
ZBS2116			4-3/8	7-3/4		Regular		

● Need to use T Handle : TWH600 (See page 52)



i-Xmill BALL HOLDERS - CARBIDE

- ▶ Equal tool rigidity like solid carbide end mill that makes the stable and high finishing machining with less vibration.
- ▶ The high finishing machining for the deeper part of mold.
- ▶ The tool's life of carbide ball holders is longer than steel holder.
- ▶ Shrink Fit Holding system can be applied.
- ▶ Upon request, the worn holder is able to be regenerated.



Unit : Inch


EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Length Type	Wrench No.	Screw No.
	D1	D2	L1	L3	L2	D3			
ZBCB020	5/16	5/16	1/2	1-9/16	5-1/8	19/64	Long	TWFO7	TX0807
ZBCB024	3/8	3/8	5/8	2	5-1/2	23/64	Long	TWFO8	TX1008
ZBCB032	1/2	1/2	11/16	2-3/8	5-15/16	31/64	Long	TWF10	TX1210
ZBCB040	5/8	5/8	13/16	3-3/16	7-15/16	39/64	Long	TWF15	TX1615
ZBCD040					9-7/8				
ZBCB048	3/4	3/4	1	3-3/16	7-15/16	47/64	Long	TWB20	TX2020
ZBCC048				4	9-7/8				
ZBCB100	1	1	1-3/16	4-3/4	9-7/8	63/64	Long	TWB25	TX2525
ZBCB116	1-1/4	1-1/4	1-9/16	5-15/16	11-7/8	1-15/64	Long	TWB30	TX3030

● Need to use T Handle : TWH600 (See page 52)



i-Xmill CORNER RADIUS INSERTS

- ▶ The optimum geometry of the tool to achieve the better reliability and less vibration and cutting load.
- ▶ Interchangeability with i-Xmill ball holder, but the precise cutting is possible with i-Xmill corner radius holder due to higher stability and strength of tool.
- ▶ The various and wide cutting range makes it possible to machine over the roughing and finishing.
- ▶ Special coating makes high hardness with high thermal stability against oxidation.
- ▶ Three Types of Inserts are available
 - For General Purpose (~HRC50)
 - For Hardened Material (HRC40~HRC65)
 - For Graphite



cutting conditions : p.611

Unit : Inch

EDP No.	Radius of Ball Nose			Mill Diameter	Height	Thickness	OD Straight Length
	For General Material	For Hardened Material	For Graphite				
XR1A020 01	XR2A020 01	XR1D020 01	R1/64	5/16	5/16	.094	.079
XR1A020 02	XR2A020 02	XR1D020 02	R1/32				
XR1A024 01	XR2A024 01	XR1D024 01	R1/64	3/8	3/8	.106	.118
XR1A024 02	XR2A024 02	XR1D024 02	R1/32				
XR1A024 04	XR2A024 04	XR1D024 04	R1/16	1/2	7/16	.126	.118
XR1A032 01	XR2A032 01	XR1D032 01	R1/64				
XR1A032 02	XR2A032 02	XR1D032 02	R1/32	5/8	1/2	.165	.157
XR1A032 04	XR2A032 04	XR1D032 04	R1/16				
XR1A040 01	XR2A040 01	XR1D040 01	R1/64	3/4	5/8	.205	.157
XR1A040 02	XR2A040 02	XR1D040 02	R1/32				
XR1A040 04	XR2A040 04	XR1D040 04	R1/16	1	3/4	.244	.157
XR1A040 08	XR2A040 08	XR1D040 08	R1/8				
XR1A048 01	XR2A048 01	XR1D048 01	R1/64	1-1/4	29/32	.283	.157
XR1A048 02	XR2A048 02	XR1D048 02	R1/32				
XR1A048 04	XR2A048 04	XR1D048 04	R1/16	1-1/4	29/32	.283	.157
XR1A048 08	XR2A048 08	XR1D048 08	R1/8				
XR1A100 01	XR2A100 01	XR1D100 01	R1/64	1	3/4	.244	.157
XR1A100 02	XR2A100 02	XR1D100 02	R1/32				
XR1A100 04	XR2A100 04	XR1D100 04	R1/16	1-1/4	29/32	.283	.157
XR1A100 08	XR2A100 08	XR1D100 08	R1/8				
XR1A116 01	XR2A116 01	XR1D116 01	R1/64	1-1/4	29/32	.283	.157
XR1A116 02	XR2A116 02	XR1D116 02	R1/32				
XR1A116 04	XR2A116 04	XR1D116 04	R1/16	1-1/4	29/32	.283	.157
XR1A116 08	XR2A116 08	XR1D116 08	R1/8				


- The other corner radius values are available on request.
- The corner radius tolerance is ±.0006" and the set-up accuracy is ±.0008"

◎ : Excellent ○ : Good

	P						M	K	N		
	Carbon Steels		Alloy Steels		Tool Steels		Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Graphite
	~HRC35	HRC35~	~HRC35	HRC35~	~HRC35	HRC35~	HRC50~	~HRC28	~HRC35	~HRC8	
XR1A	◎	○	◎	○	◎	○		○	○	○	
XR2A	○	◎	○	◎	○	◎	◎		◎		
XR1D	○		○		○					○	◎

i-Xmill CORNER RADIUS HOLDERS - STEEL


- ▶ Premium alloy steel with excellent strength.
- ▶ Precise shank, Tolerance (h6).
- ▶ Nickel plated, to prevent corrosion and improve lubricity.



Taper neck Type

Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Interference Angle	Length Type	Wrench No.	Screw No.
	D1	D2	L1	L3	L2	D3	θ°			
ZRT1032	5/16	1/2	13/32	7/8	4	17/64	13° 58'	Regular	TWF07	TX0807
ZRT2032				2	5-1/8		4° 12'	Long		
ZRT2410	3/8	1/2	17/32	1	4	5/16	9° 27'	Regular	TWF08	TX1008
ZRT2420				2	5-15/16		3° 6'	Long		
ZRT3220	1/2	5/8	5/8	2-3/8	6-5/16	27/64	3° 19'	Long	TWF10	TX1210



Straight neck Type

Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Length Type	Wrench No.	Screw No.
	D1	D2	L1	L3	L2	D3			
ZRS1032	1/2	1/2	17/32	1-3/16	4-3/8	7/16	Regular	TWF10	TX1210
ZRS1040	5/8	5/8	5/8	2	5-1/8	19/32	Regular	TWF15	TX1615
ZRS2040				2-9/16	6-1/2		Intermediate		
ZRS1048	3/4	3/4	23/32	2-3/8	5-1/2	23/32	Regular	TWB20	TX2020
ZRS2048				3-1/8	7-1/8		Intermediate		
ZRS1100	1	1	29/32	2-3/4	5-15/16	31/32	Regular	TWB25	TX2525
ZRS2100				3-9/16	8		Intermediate		
ZRS1116	1-1/4	1-1/4	1-1/8	3-1/8	6-5/16	1-7/32	Regular	TWB30	TX3030
ZRS2116				4	8-11/16		Intermediate		

● Need to use T Handle : TWH600 (See page 52)

i-Xmill BALL INSERTS

- ▶ Indexable Ball End Mill for economic use
- ▶ Three Types of Inserts are available
 - For General Purpose (~HRc50)
 - For Hardened Material (HRc40~HRc65)
 - For Graphite
- ▶ Special Geometry and extremely abrasive resistant Coating for Excellent Performance



cutting conditions : p.610

Unit : mm

EDP No.			Radius of Ball Nose	Mill Diameter	Height	Thickness
For General Material	For Hardened Material	For Graphite				
			R	D	H	T
XB1N080	XB2N080	XBAD080	R4.0	8.0	8	2.4
XB1N100	XB2N100	XBAD100	R5.0	10.0	9.5	2.7
XB1N120	XB2N120	XBAD120	R6.0	12.0	11	3.2
XB1N160	XB2N160	XBAD160	R8.0	16.0	13	4.2
XB1N200	XB2N200	XBAD200	R10.0	20.0	16	5.2
XB1N250	XB2N250	XBAD250	R12.5	25.0	19.5	6.2
XB1N300	XB2N300	XBAD300	R15.0	30.0	23.5	7.2
XB1N320	XB2N320	XBAD320	R16.0	32.0	24.5	7.2

• The ball radius tolerance is ±0.01mm and the set-up accuracy is ±0.02mm

◎ : Excellent ○ : Good

	P							M	K	N	
	Carbon Steels		Alloy Steels		Tool Steels		Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Graphite
	~HRc35	HRc35~	~HRc35	HRc35~	~HRc35	HRc35~	HRc50~	~HRc28	~HRc35	~HRc8	
XB1N	◎	○	◎	○	◎	○		○	○	○	
XB2N	○	◎	○	◎	○	◎	◎		◎		
XBAD	○		○		○					○	◎



i-Xmill BALL HOLDERS - STEEL

- ▶ Premium alloy steel with excellent strength.
- ▶ Precise shank, Tolerance (h6).
- ▶ Nickel plated, to prevent corrosion and improve lubricity.




Taper neck Type

Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Interference Angle	Length Type	Wrench No.	Screw No.
	D1	D2	L1	L3	L2	D3	θ°			
ZBT0801	8.0	12	12	35	90	7.2	4. 43'	Short	TWFO7	TX0807
ZBT0802			25	55	110		3. 37'	Regular		
ZBT1001	10.0	12	15	35	90	9	2. 51'	Short	TWFO8	TX1008
ZBT1002			30	55	110		2. 17'	Regular		
ZBT1201	12.0	16	17	55	110	10.5	3. 23'	Short	TWF10	TX1210
ZBT1601	16.0	20	20	65	125	14.5	2. 51'	Short	TWF15	TX1615
ZBT2001	20.0	25	25	75	145	18	3. 26'	Short	● TWB20	TX2020
ZBT2501	25.0	32	30	90	170	22.5	4. 03'	Short	● TWB25	TX2525
ZBT3001	30.0 32.0	32	40	110	195	27	1. 38'	Short	● TWB30	TX3030

● Need to use T Handle : TWH600 (See page 52)



Straight neck Type

Unit : mm


EDP No.	Mill Diameter	Shank Diameter	Length Below Shank	Overall Length	Neck Diameter	Length Type	Wrench No.	Screw No.
	D1	D2	L3	L2	D3			
ZBS1201	12.0	12	35	90	10.5	Short	TWF10	TX1210
ZBS1202			55	110		Regular		
ZBS1601	16.0	16	35	95	14.5	Short	TWF15	TX1615
ZBS1602			65	125		Regular		
ZBS2001	20.0	20	40	110	18	Short	● TWB20	TX2020
ZBS2002			75	145		Regular		
ZBS2501	25.0	25	45	125	22.5	Short	● TWB25	TX2525
ZBS2502			90	170		Regular		
ZBS3001	30.0	32	55	140	27	Short	● TWB30	TX3030
ZBS3002	32.0		110	195		Regular		

● Need to use T Handle : TWH600 (See page 52)



i-Xmill BALL HOLDERS - CARBIDE

- ▶ Equal tool rigidity like solid carbide end mill that makes the stable and high finishing machining with less vibration.
- ▶ The high finishing machining for the deeper part of mold.
- ▶ The tool's life of carbide ball holders is longer than steel holder.
- ▶ Shrink Fit Holding system can be applied.
- ▶ Upon request, the worn holder is able to be regenerated.



Unit : mm



EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Length Type	Wrench No.	Screw No.
	D1	D2	L1	L3	L2	D3			
ZBC1080	8.0	8	12	25	130	7.7	Long	TWFO7	TX0807
ZBC1100	10.0	10	15	30	140	9.7	Long	TWFO8	TX1008
ZBC1120	12.0	12	17	35	150	11.7	Long	TWF10	TX1210
ZBC1160	16.0	16	20	50	200	15.7	Long	TWF15	TX1615
ZBC1200	20.0	20	25	60	200	19.7	Long	● TWB20	TX2020
ZBC1250	25.0	25	30	75	200	24.7	Long	● TWB25	TX2525
ZBC1320	30.0 32.0	32	40	90	250	29.7	Long	● TWB30	TX3030

● Need to use T Handle : TWH600 (See page 52)



i-Xmill CORNER RADIUS INSERTS

- ▶ The optimum geometry of the tool to achieve the better reliability and less vibration and cutting load.
- ▶ Interchangeability with i-Xmill ball holder, but the precise cutting is possible with i-Xmill corner radius holder due to higher stability and strength of tool.
- ▶ The various and wide cutting range makes it possible to machine over the roughing and finishing.
- ▶ Special coating makes high hardness with high thermal stability against oxidation.
- ▶ Three Types of Inserts are available
 - For General Purpose (~HRc50)
 - For Hardened Material (HRc40~HRc65)
 - For Graphite



cutting conditions : p.611

Unit : mm

EDP No.			Corner Radius R	Mill Diameter D	Height H	Thickness T	OD Straight Length
For General Material	For Hardened Material	For Graphite					
XRAA080 03	XRBA080 03	XRAD080 03	R0.3	8.0	8	2.4	2
XRAA080 05	XRBA080 05	XRAD080 05	R0.5				
XRAA080 10	XRBA080 10	XRAD080 10	R1.0				
XRAA100 05	XRBA100 05	XRAD100 05	R0.5	10.0	9.5	2.7	3
XRAA100 10	XRBA100 10	XRAD100 10	R1.0				
XRAA100 20	XRBA100 20	XRAD100 20	R2.0				
XRAA120 05	XRBA120 05	XRAD120 05	R0.5	12.0	11	3.2	3
XRAA120 10	XRBA120 10	XRAD120 10	R1.0				
XRAA120 20	XRBA120 20	XRAD120 20	R2.0				
XRAA130 05	XRBA130 05	XRAD130 05	R0.5	13.0	11.2	3.2	3
XRAA130 10	XRBA130 10	XRAD130 10	R1.0				
XRAA130 20	XRBA130 20	XRAD130 20	R2.0				
XRAA160 05	XRBA160 05	XRAD160 05	R0.5	16.0	13	4.2	4
XRAA160 10	XRBA160 10	XRAD160 10	R1.0				
XRAA160 20	XRBA160 20	XRAD160 20	R2.0				
XRAA170 05	XRBA170 05	XRAD170 05	R0.5	17.0	13	4.2	4
XRAA170 10	XRBA170 10	XRAD170 10	R1.0				
XRAA170 20	XRBA170 20	XRAD170 20	R2.0				

- The other corner radius values are available on request.
- The corner radius tolerance is ±0.015mm and the set-up accuracy is ±0.02mm

▶ NEXT PAGE


◎ : Excellent ○ : Good

	P				M		K		N	
	Carbon Steels		Alloy Steels		Tool Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Graphite
	~HRc35	HRc35~	~HRc35	HRc35~	~HRc35	HRc35~	HRc50~	~HRc28	~HRc35	~HRc8
XRAA	◎	○	◎	○	◎	○	○	○	○	○
XRBA	○	◎	○	◎	○	◎	◎	◎	○	○
XRAD	○	○	○	○	○	○	○	○	○	◎



i-Xmill CORNER RADIUS INSERTS

- ▶ The optimum geometry of the tool to achieve the better reliability and less vibration and cutting load.
- ▶ Interchangeability with i-Xmill ball holder, but the precise cutting is possible with i-Xmill corner radius holder due to higher stability and strength of tool.
- ▶ The various and wide cutting range makes it possible to machine over the roughing and finishing.
- ▶ Special coating makes high hardness with high thermal stability against oxidation.
- ▶ Three Types of Inserts are available
 - For General Purpose (~HRc50)
 - For Hardened Material (HRc40~HRc65)
 - For Graphite



cutting conditions : p.611

Unit : mm

EDP No.			Corner Radius R	Mill Diameter D	Height H	Thickness T	OD Straight Length
For General Material	For Hardened Material	For Graphite					
XRAA200 05	XRBA200 05	XRAD200 05	R0.5	20.0	16	5.2	4
XRAA200 10	XRBA200 10	XRAD200 10	R1.0				
XRAA200 20	XRBA200 20	XRAD200 20	R2.0				
XRAA210 05	XRBA210 05	XRAD210 05	R0.5	21.0	16	5.2	4
XRAA210 10	XRBA210 10	XRAD210 10	R1.0				
XRAA210 20	XRBA210 20	XRAD210 20	R2.0				
XRAA250 05	XRBA250 05	XRAD250 05	R0.5	25.0	19.5	6.2	4
XRAA250 10	XRBA250 10	XRAD250 10	R1.0				
XRAA250 20	XRBA250 20	XRAD250 20	R2.0				
XRAA260 05	XRBA260 05	XRAD260 05	R0.5	26.0	19.5	6.2	4
XRAA260 10	XRBA260 10	XRAD260 10	R1.0				
XRAA260 20	XRBA260 20	XRAD260 20	R2.0				
XRAA300 05	XRBA300 05	XRAD300 05	R0.5	30.0	23.5	7.2	4
XRAA300 10	XRBA300 10	XRAD300 10	R1.0				
XRAA300 20	XRBA300 20	XRAD300 20	R2.0				
XRAA320 05	XRBA320 05	XRAD320 05	R0.5	32.0	23.5	7.2	4
XRAA320 10	XRBA320 10	XRAD320 10	R1.0				
XRAA320 20	XRBA320 20	XRAD320 20	R2.0				

- The other corner radius values are available on request.
- The corner radius tolerance is ±0.015mm and the set-up accuracy is ±0.02mm


◎ : Excellent ○ : Good

	P				M		K		N	
	Carbon Steels		Alloy Steels		Tool Steels	Hardened Steels	Stainless Steels	Cast Iron	Aluminum	Graphite
	~HRc35	HRc35~	~HRc35	HRc35~	~HRc35	HRc35~	HRc50~	~HRc28	~HRc35	~HRc8
XRAA	◎	○	◎	○	◎	○	○	○	○	○
XRBA	○	◎	○	◎	○	◎	◎	◎	○	○
XRAD	○	○	○	○	○	○	○	○	○	◎



i-Xmill CORNER RADIUS HOLDERS - STEEL


- ▶ Premium alloy steel with excellent strength.
- ▶ Precise shank, Tolerance (h6).
- ▶ Nickel plated, to prevent corrosion and improve lubricity.



Taper neck Type

Unit : mm

EDP No.	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Interference Angle θ°	Length Type	Wrench No.	Screw No.
ZRT8011	8.0	12	10	22	100	6.7	9°	Regular	TWFO7	TX0807
ZRT8021				50	130		2° 43'	Long		
ZRT1001	10.0	12	13	25	100	8.6	4° 45'	Regular	TWFO8	TX1008
ZRT1002				50	150		1° 32'	Long		
ZRT1202	12.0 13.0	16	15	60	160	10.2	2° 32'	Long	TWF10	TX1210



Straight neck Type

Unit : mm


EDP No.	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Length Type	Wrench No.	Screw No.
ZRS1120	12.0 13.0	12	13	30	110	11	Regular	TWF10	TX1210
ZRS1160	16.0	16	15	50	130	15	Regular	TWF15	TX1615
ZRS2160	17.0			65	165		Intermediate		
ZRS1200	20.0	20	18	60	140	19	Regular	TWB20	TX2020
ZRS2200	21.0			80	180		Intermediate		
ZRS1250	25.0	25	23	70	150	24	Regular	TWB25	TX2525
ZRS2250	26.0			90	200		Intermediate		
ZRS1300	30.0	32	27	80	160	29	Regular	TWB30	TX3030
ZRS2300				100	220		Intermediate		
ZRS1320	32.0	32	28	80	160	31	Regular	TWB30	TX3030
ZRS2320				100	220		Intermediate		

● Need to use T Handle : TWH600 (See page 52)




RECOMMENDED CUTTING CONDITIONS

ASSEMBLY OF i-Xmill



◀ Make sure to clean the insert and insert seat.




◀ Slide the insert into the slot of the holder.
Tighten the screw using anti-seize compound.

SIZE ØD	CLAMPING TORQUE [in • lbs]
Ø5/16 [Ø8]	9.0
Ø3/8 [Ø10]	13.5
Ø1/2 [Ø12~Ø13]	22.5
Ø5/8 [Ø16~Ø17]	31.5
Ø3/4 [Ø20~Ø21]	44.5
Ø1 [Ø25~Ø26]	53.0
Ø1-1/4 [Ø30~Ø32]	58.0

- * When the screw is worn out, please change the new screw.
- * Please tighten up the screw with recommended torque. (Please refer to the table)
- * Don't press down the insert, when the screw is tightened.



CUTTING CONDITION



- RPM = revolution per minute (rev/min)
- SFM = surface feet per minute (ft/min)
- Dia. = diameter of insert (inch)
- IPR = feed rate (inch/rev)
- IPM = inch per minute penetration rate
- De = effective tool diameter (inch)
- ap = axial depth of cut (inch)
- ae = radial depth of cut (inch)

$$\text{SFM [ft/min]} = \frac{(\text{RPM}) \cdot (\pi) \cdot (\text{Dia.})}{12}$$

$$\text{IPM [inch/min]} = (\text{RPM}) \cdot (\text{IPR})$$

$$\text{RPM [rev/min]} = \frac{(\text{SFM}) \cdot (12)}{(\pi) \cdot (\text{Dia.})}$$

$$\text{De [inch]} = 2 \sqrt{(\text{ap}) \cdot (\text{Dia.} - \text{ap})}$$




RECOMMENDED CUTTING CONDITIONS

i-Xmill BALL INSERTS

XB1A, XB2C, XB1N, XB2N SERIES

WORK MATERIAL	P								
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON				ALLOY STEELS HEAT RESISTANT STEELS				
HARDNESS	HB	~280				280~380			
	HRc	~30				30~40			
STRENGTH	N/mm ²	~1000				1000~1250			
i-Xmill TYPE		XB1A, XB1N				XB1A, XB1N			
CUTTING CONDITION		RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz
Roughing~Finishing		[rev/min]	[inch/min]	[ft/min]	[inch/t]	[rev/min]	[inch/min]	[ft/min]	[inch/t]
Ø5/16(Ø8)		6370~12730	100~200	525~1050	.008~.008	4770~11140	80~180	394~919	.008~.008
Ø3/8(Ø10)		5090~11460	80~180	525~1181	.008~.008	3820~9550	60~150	394~984	.008~.008
Ø1/2(Ø12, Ø13)		4240~10080	70~160	525~1247	.008~.008	3180~9280	50~150	394~1148	.008~.008
Ø5/8(Ø16, Ø17)		3180~9550	60~230	525~1575	.010~.012	2390~7560	50~180	394~1247	.010~.012
Ø3/4(Ø20, Ø21)		2550~9230	50~290	525~1903	.010~.016	1910~6680	40~210	394~1378	.010~.016
Ø1(Ø25, Ø26)		2040~7640	40~300	525~1969	.010~.020	1530~6110	30~240	394~1575	.010~.020
Ø1-1/4(Ø30, Ø32)		1700~7430	30~350	525~2297	.010~.024	1270~5840	30~280	394~1804	.010~.024

P								N			
DIE TOOL STEELS PRE-HARDENED				HARDENED STEELS				GRAPHITE			
380~480				480~740							
40~50				50~65							
1250~1500				1500~							
XB1A, XB1N XB2C, XB2N				XB2C, XB2N				XB1D, XBAD			
RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz
[rev/min]	[inch/min]	[ft/min]	[inch/t]	[rev/min]	[inch/min]	[ft/min]	[inch/t]	[rev/min]	[inch/min]	[ft/min]	[inch/t]
3980~8750	50~140	328~722	.006~.008	3180~7160	30~110	262~591	.004~.008	11940~15920	190~250	984~1312	.008~.008
3180~8280	40~130	328~853	.006~.008	2550~6370	20~100	262~656	.004~.008	9550~12730	150~200	984~1312	.008~.008
2650~7430	30~120	328~919	.006~.008	2120~5840	20~90	262~722	.004~.008	7960~10610	130~170	984~1312	.008~.008
1990~6960	30~160	328~1148	.008~.012	1590~5170	20~120	262~853	.006~.012	5970~7960	120~190	984~1312	.010~.012
1590~6370	30~200	328~1312	.008~.016	1270~5090	20~160	262~1050	.006~.016	4770~7640	110~210	984~1575	.012~.014
1270~5730	20~230	328~1476	.008~.020	1020~4580	10~180	262~1181	.006~.020	3820~7130	110~220	984~1837	.014~.016
1060~5310	20~250	328~1640	.008~.024	850~4240	10~200	262~1312	.006~.024	3180~6900	100~270	984~2133	.016~.020



ae : Roughing - 0.1 x D
Finishing - Under Ø1/2 : 0.01
Under Ø3/4 : 0.012
From Ø3/4 : 0.016

ap : Roughing - Under Ø5/8 : 0.025 x D
From Ø5/8 : 0.05 x D
Finishing - 0.004

► Recommend to reduce the feed rate to 70 ~ 85% when you use long (long & intermediate Type Holder)

RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

i-Xmill CORNER RADIUS INSERTS

XR1A, XR2A, XRAA, XRBA SERIES

WORK MATERIAL	P								
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON				ALLOY STEELS HEAT RESISTANT STEELS				
HARDNESS	HB	~280				280~380			
	HRc	~30				30~40			
STRENGTH	N/mm ²	~1000				1000~1250			
i-Xmill TYPE		XR1A, XRAA				XR1A, XRAA			
CUTTING CONDITION		RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz
Roughing~Finishing		[rev/min]	[inch/min]	[ft/min]	[inch/t]	[rev/min]	[inch/min]	[ft/min]	[inch/t]
Ø5/16(Ø8)		6370~11940	100~140	525~984	.008~.006	4770~11140	80~130	394~919	.008~.006
Ø3/8(Ø10)		5090~9550	80~110	525~984	.008~.006	3820~8910	60~110	394~919	.008~.006
Ø1/2(Ø12, Ø13)		4240~7960	70~90	525~984	.008~.006	3180~7430	50~90	394~919	.008~.006
Ø5/8(Ø16, Ø17)		3180~5970	60~90	525~984	.010~.008	2390~5570	50~90	394~919	.010~.008
Ø3/4(Ø20, Ø21)		2550~4770	50~80	525~984	.010~.008	1910~4460	40~70	394~919	.010~.008
Ø1(Ø25, Ø26)		2040~3820	40~60	525~984	.010~.008	1530~3570	30~60	394~919	.010~.008
Ø1-1/4(Ø30, Ø32)		1700~3180	30~50	525~984	.010~.008	1270~2970	30~50	394~919	.010~.008

P								N			
DIE TOOL STEELS PRE-HARDENED				HARDENED STEELS				GRAPHITE			
380~480				480~740							
40~50				50~65							
1250~1500				1500~							
XR1A, XRAA XR2A, XRBA				XR2A, XRBA				XR1D, XRAD			
RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz
[rev/min]	[inch/min]	[ft/min]	[inch/t]	[rev/min]	[inch/min]	[ft/min]	[inch/t]	[rev/min]	[inch/min]	[ft/min]	[inch/t]
3980~11140	40~52	328~919	.005~.002	3180~7160	25~34	262~722	.004~.002	11940~15920	190~250	984~1312	.008~.008
3180~8910	30~42	328~919	.005~.002	2550~6370	20~28	262~722	.004~.002	9550~12730	150~200	984~1312	.008~.008
2650~7430	25~35	328~919	.005~.002	2120~5840	18~24	262~722	.004~.002	7960~10610	130~170	984~1312	.008~.008
1990~5570	24~34	328~919	.006~.003	1590~5170	18~22	262~722	.006~.002	5970~7960	90~130	984~1312	.008~.008
1590~4460	20~26	328~919	.006~.003	1270~5090	15~18	262~722	.006~.002	4770~6370	90~130	984~1312	.010~.010
1270~3570	15~20	328~919	.006~.003	1020~4580	12~14	262~722	.006~.002	3820~5090	80~100	984~1312	.010~.010
1060~2970	14~18	328~919	.006~.003	850~4240	10~12	262~722	.006~.002	3180~4240	60~80	984~1312	.010~.010



ae : Roughing - 0.1 x D
Finishing - 0.008

ap : Roughing - Under Ø5/8 : 0.025 x D
From Ø5/8 : 0.05 x D
Finishing - Under Ø5/8 : 0.004
From Ø5/8 : 0.008

► Recommend to reduce the feed rate to 70 ~ 85% when you use long (long & intermediate Type Holder)

CARBIDE MODULAR HEAD & HOLDER



i-Smart MODULAR CARBIDE HEAD END MILLS

- Exchangeable Modular Head for Semi-finishing and finishing on Pre-Hardened Steels up to HRC55











Global Cutting Tool Leader **YG-1**



SELECTION GUIDE

i-Smart MODULAR CARBIDE HEAD END MILLS

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
XGMF15		CARBIDE MODULAR HEAD, 2 FLUTE BALL NOSE	R3/16	R5/8	616
XGMF17		CARBIDE MODULAR HEAD, 4 FLUTE BALL NOSE	R3/16	R5/8	617
XGMF20		CARBIDE MODULAR HEAD, 4 FLUTE MULTIPLE HELIX CORNER RADIUS	D3/8	D1-1/4	618
XGMF25		CARBIDE MODULAR HEAD, 4 FLUTE MULTIPLE HELIX	D3/8	D1-1/4	619
XGMF29		CARBIDE MODULAR HEAD, 6 FLUTE 45° HELIX	D3/8	D1-1/4	620
ZMC		CARBIDE HOLDER, STRAIGHT NECK TYPE			621
ZMS		STEEL HOLDER, STRAIGHT NECK TYPE			622
ZMT		STEEL HOLDER, TAPER NECK TYPE			623
RECOMMENDED CUTTING CONDITIONS					624


◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○							
○	◎	◎	◎	○			○							
◎	◎	◎	◎	○			○							
◎	◎	◎	◎	○		○	○							
◎	◎	◎	◎	○			○							



XGMF15 SERIES

CARBIDE MODULAR HEAD, 2 FLUTE BALL NOSE



Unit: Inch

EDP No.	Radius of Ball Nose	Mill Diameter	Neck Diameter	Length of Cut	Length Below Shank	Coupling Diameter	Wrench Width	Thread	Wrench
	R	D1	D2	L1	L2	d1	W	M	
XGMF15024	R3/16	3/8	.351	3/8	.689	.256	.315	M6	SPIS0810
XGMF15032	R1/4	1/2	.469	1/2	.835	.256	.394	M6	SPIS0810
XGMF15040	R5/16	5/8	.591	5/8	1.004	.335	.512	M8	SPIS1300
XGMF15048	R3/8	3/4	.711	3/4	1.144	.413	.669	M10	SPIS1700
XGMF15100	R1/2	1	.961	1	1.472	.492	.866	M12	SPIS2200
XGMF15116	R5/8	1-1/4	1.221	1-1/4	1.772	.669	1.063	M16	SPIS2700

Radius Tolerance(Inch)	Mill Dia. Tolerance(Inch)
±.0004	0~-.0008



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45	HRC45~55	HRC55~70									
○	◎	◎	◎	○			○							



XGMF17 SERIES

CARBIDE MODULAR HEAD, 4 FLUTE BALL NOSE



Unit: Inch

EDP No.	Radius of Ball Nose	Mill Diameter	Neck Diameter	Length of Cut	Length Below Shank	Coupling Diameter	Wrench Width	Thread	Wrench
	R	D1	D2	L1	L2	d1	W	M	
XGMF17024	R3/16	3/8	.351	3/8	.689	.256	.315	M6	SPIS0810
XGMF17032	R1/4	1/2	.469	1/2	.835	.256	.394	M6	SPIS0810
XGMF17040	R5/16	5/8	.591	5/8	1.004	.335	.512	M8	SPIS1300
XGMF17048	R3/8	3/4	.711	3/4	1.144	.413	.669	M10	SPIS1700
XGMF17100	R1/2	1	.961	1	1.472	.492	.866	M12	SPIS2200
XGMF17116	R5/8	1-1/4	1.221	1-1/4	1.772	.669	1.063	M16	SPIS2700

Radius Tolerance(Inch)	Mill Dia. Tolerance(Inch)
±.0004	0~-.0008


◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45	HRC45~55	HRC55~70									
○	◎	◎	◎	○			○							



XGMF20 SERIES

CARBIDE MODULAR HEAD, 4 FLUTE MULTIPLE HELIX CORNER RADIUS



Unit: Inch

EDP No.	Corner Radius	Mill Diameter	Neck Diameter	Length of Cut	Length Below Shank	Coupling Diameter	Wrench Width	Thread	Wrench
	R	D1	D2	L1	L2	d1	W	M	
XGMF20024 012	R.012	3/8	.351	3/8	.689	.256	.315	M6	SPIS0810
XGMF20024 020	R.020	3/8	.351	3/8	.689	.256	.315	M6	SPIS0810
XGMF20024 030	R.030	3/8	.351	3/8	.689	.256	.315	M6	SPIS0810
XGMF20024 040	R.040	3/8	.351	3/8	.689	.256	.315	M6	SPIS0810
XGMF20024 050	R.050	3/8	.351	3/8	.689	.256	.315	M6	SPIS0810
XGMF20024 060	R.060	3/8	.351	3/8	.689	.256	.315	M6	SPIS0810
XGMF20024 080	R.080	3/8	.351	3/8	.689	.256	.315	M6	SPIS0810
XGMF20032 020	R.020	1/2	.469	1/2	.835	.256	.394	M6	SPIS0810
XGMF20032 030	R.030	1/2	.469	1/2	.835	.256	.394	M6	SPIS0810
XGMF20032 040	R.040	1/2	.469	1/2	.835	.256	.394	M6	SPIS0810
XGMF20032 060	R.060	1/2	.469	1/2	.835	.256	.394	M6	SPIS0810
XGMF20032 080	R.080	1/2	.469	1/2	.835	.256	.394	M6	SPIS0810
XGMF20040 020	R.020	5/8	.591	5/8	1.004	.335	.512	M8	SPIS1300
XGMF20040 030	R.030	5/8	.591	5/8	1.004	.335	.512	M8	SPIS1300
XGMF20040 040	R.040	5/8	.591	5/8	1.004	.335	.512	M8	SPIS1300
XGMF20040 060	R.060	5/8	.591	5/8	1.004	.335	.512	M8	SPIS1300
XGMF20040 080	R.080	5/8	.591	5/8	1.004	.335	.512	M8	SPIS1300
XGMF20048 030	R.030	3/4	.711	3/4	1.144	.413	.669	M10	SPIS1700
XGMF20048 040	R.040	3/4	.711	3/4	1.144	.413	.669	M10	SPIS1700
XGMF20048 080	R.080	3/4	.711	3/4	1.144	.413	.669	M10	SPIS1700
XGMF20100 030	R.030	1	.961	1	1.472	.492	.866	M12	SPIS2200
XGMF20100 040	R.040	1	.961	1	1.472	.492	.866	M12	SPIS2200
XGMF20100 080	R.080	1	.961	1	1.472	.492	.866	M12	SPIS2200
XGMF20116 030	R.030	1-1/4	1.221	1-1/4	1.772	.669	1.063	M16	SPIS2700
XGMF20116 040	R.040	1-1/4	1.221	1-1/4	1.772	.669	1.063	M16	SPIS2700
XGMF20116 080	R.080	1-1/4	1.221	1-1/4	1.772	.669	1.063	M16	SPIS2700

Corner Radius Tolerance(Inch)	Mill Dia. Tolerance(Inch)
±.0008	0~-.0012


◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○			○							



XGMF25 SERIES

CARBIDE MODULAR HEAD, 4 FLUTE MULTIPLE HELIX



Unit: Inch

EDP No.	Mill Diameter	Neck Diameter	Length of Cut	Length Below Shank	Coupling Diameter	Wrench Width	Thread	Wrench
	D1	D2	L1	L2	d1	W	M	
XGMF25024	3/8	.351	3/8	.689	.256	.315	M6	SPIS0810
XGMF25032	1/2	.469	1/2	.835	.256	.394	M6	SPIS0810
XGMF25040	5/8	.591	5/8	1.004	.335	.512	M8	SPIS1300
XGMF25048	3/4	.711	3/4	1.144	.413	.669	M10	SPIS1700
XGMF25100	1	.961	1	1.472	.492	.866	M12	SPIS2200
XGMF25116	1-1/4	1.221	1-1/4	1.772	.669	1.063	M16	SPIS2700

Mill Dia. Tolerance(Inch)
0~-.0012


◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



XGMF29 SERIES

CARBIDE MODULAR HEAD, 6 FLUTE 45° HELIX



Unit: Inch

EDP No.	Mill Diameter	Neck Diameter	Length of Cut	Length Below Shank	Coupling Diameter	Wrench Width	Thread	Wrench
	D1	D2	L1	L2	d1	W	M	
XGMF29024	3/8	.351	3/8	.689	.256	.315	M6	SPIS0810
XGMF29032	1/2	.469	1/2	.835	.256	.394	M6	SPIS0810
XGMF29040	5/8	.591	5/8	1.004	.335	.512	M8	SPIS1300
XGMF29048	3/4	.711	3/4	1.144	.413	.669	M10	SPIS1700
XGMF29100	1	.961	1	1.472	.492	.866	M12	SPIS2200
XGMF29116	1-1/4	1.221	1-1/4	1.772	.669	1.063	M16	SPIS2700

Mill Dia. Tolerance(Inch)
0~- .0012


◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45 HRC45~55	HRC55~70									
○	◎	◎	◎	○		○							



ZMC SERIES


CARBIDE HOLDER, STRAIGHT NECK TYPE



Unit: Inch

EDP No.	Mill Diameter	Shank Diameter	Overall Length	Neck Length	Neck Diameter	Thread Size	Wrench No.	Coolant Hole
		SD	L	L1	D	M		
ZMC024A024	3/8	3/8	2-3/4	25/32	23/64	M6	SPIS0810	5/64
ZMC024B024			3-15/16	1-37/64				
ZMC024C024			5-1/8	2-3/4				
ZMC032A032	1/2	1/2	3-1/8	25/32	29/64	M6	SPIS0810	5/64
ZMC032B032			3-15/16	1-37/64				
ZMC032C032			5-1/8	2-3/4				
ZMC040A040	5/8	5/8	3-15/16	1-37/64	19/32	M8	SPIS1300	1/8
ZMC040B040			5-7/8	3-5/32				
ZMC040C040			7-7/8	4-23/32				
ZMC048A048	3/4	3/4	3-15/16	1-37/64	45/64	M10	SPIS1700	5/32
ZMC048B048			5-7/8	3-5/32				
ZMC048C048			7-7/8	4-23/32				
ZMC048D048			9-13/16	6-19/64				
ZMC100A100	1	1	5-7/8	2-3/4	61/64	M12	SPIS2200	13/64
ZMC100B100			7-7/8	3-15/16				
ZMC100C100			9-13/16	5-29/32				
ZMC100D100			11-13/16	7-7/8				
ZMC116A116	1-1/4	1-1/4	5-7/8	2-3/4	1-9/64	M16	SPIS2700	15/64
ZMC116B116			7-7/8	4-23/32				
ZMC116C116			9-13/16	5-29/32				
ZMC116D116			11-13/16	7-7/8				
ZMC116E116			13-3/4	9-27/32				

STEEL HOLDER, STRAIGHT NECK TYPE




Unit: Inch

EDP No.	Mill Diameter	Shank Diameter	Overall Length	Neck Length	Neck Diameter	Thread Size	Coolant Hole
		SD					
ZMS024A024	3/8	3/8	2-3/4	25/32	23/64	M6	1/8
ZMS032A032	1/2	1/2	3-35/64	1-3/16	29/64	M6	1/8
ZMS040A040	5/8	5/8	3-15/16	1-3/16	19/32	M8	5/32
ZMS048A048	3/4	3/4	3-15/16	1-3/16	45/64	M10	13/64
ZMS100A100	1	1	4-17/32	1-37/64	61/64	M12	13/64
ZMS116A116	1-1/4	1-1/4	4-59/64	1-37/64	1-9/64	M16	15/64

Wrench

Model	Wrench No.	Wrench Width	Mill Diameter	Clamping Torque [in·lbs]
	SPIS0810	.315	3/8	57.6
		.394	1/2	57.6
	SPIS1300	.512	5/8	88.6
	SPIS1700	.669	3/4	106.3
	SPIS2200	.866	1	132.9
	SPIS2700	1.063	1-1/4	177.1

STEEL HOLDER, TAPER NECK TYPE



Unit: Inch

EDP No.	Mill Diameter	Shank Diameter	Overall Length	Neck Length	Neck Diameter	Thread Size	Coolant Hole
		SD					
ZMT024A032	3/8	1/2	3-15/16	1-31/32	23/64	M6	1/8
ZMT032A040	1/2	5/8	5-1/8	2-3/4	29/64	M6	1/8
ZMT040A048	5/8	3/4	5-29/32	3-35/64	19/32	M8	5/32
ZMT048A100	3/4	1	6-11/16	3-15/16	45/64	M10	13/64
ZMT100A116	1	1-1/4	7-7/8	4-21/64	61/64	M12	13/64
ZMT116A116	1-1/4	1-1/4	7-7/8	4-21/64	1-9/64	M16	15/64

Wrench

Model	Wrench No.	Wrench Width	Mill Diameter	Clamping Torque [in·lbs]
	SPIS0810	.315	3/8	57.6
		.394	1/2	57.6
	SPIS1300	.512	5/8	88.6
	SPIS1700	.669	3/4	106.3
	SPIS2200	.866	1	132.9
	SPIS2700	1.063	1-1/4	177.1




RECOMMENDED CUTTING CONDITIONS

CARBIDE MODULAR HEAD, 2 FLUTE BALL NOSE

XGMF15 SERIES

MATERIAL	P											
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON				ALLOY STEELS HEAT RESISTANT STEELS				HARDENED STEELS			
	~ HRC35 ~ 1100N/mm ²				HRC35~ HRC45 1110 ~ 1500N/mm ²				HRC45~ HRC55 1500 ~ 2000N/mm ²			
STRENGTH	RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz
R3/16 x3/8	5860	91.7	575	.008	5610	77.0	551	.007	4720	59.5	463	.006
R1/4 x1/2	4200	65.8	550	.008	4050	55.7	530	.007	3390	42.3	444	.006
R5/16 x5/8	3370	63.2	551	.009	3240	52.4	530	.008	2720	40.6	445	.007
R3/8 x3/4	2800	58.3	550	.010	2710	48.4	532	.009	2270	37.2	446	.008
R1/2 x1	2100	46.5	550	.011	2020	42.5	529	.011	1700	32.5	445	.010
R1-1/8x1-1/4	1680	38.0	550	.011	1620	36.5	530	.011	1360	28.5	445	.010




RPM = rev./min. FEED = inch/min.
Vc = ft/min. fz = inch/tooth

CARBIDE MODULAR HEAD, 4 FLUTE BALL NOSE

XGMF17 SERIES

MATERIAL	P											
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON				ALLOY STEELS HEAT RESISTANT STEELS				HARDENED STEELS			
	~ HRC35 ~ 1100N/mm ²				HRC35~ HRC45 1110 ~ 1500N/mm ²				HRC45~ HRC55 1500 ~ 2000N/mm ²			
STRENGTH	RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz
R3/16 x3/8	9600	189.8	942	.005	7720	142.5	758	.005	6990	118.7	686	.004
R1/4 x1/2	7200	158.5	942	.006	5790	118.7	758	.005	5230	89.4	685	.004
R5/16 x5/8	5760	138.2	942	.006	4630	92.6	758	.005	4180	66.9	684	.004
R3/8 x3/4	4800	134.4	942	.007	3860	92.6	758	.006	3480	69.6	683	.005
R1/2 x1	3600	115.2	942	.008	2890	69.4	757	.006	2610	52.2	683	.005
R1-1/8x1-1/4	2880	103.7	942	.009	2310	64.7	756	.007	2090	50.2	684	.006



RPM = rev./min. FEED = inch/min.
Vc = ft/min. fz = inch/tooth




RECOMMENDED CUTTING CONDITIONS


CARBIDE MODULAR HEAD, 4 FLUTE MULTIPLE HELIX
CORNER RADIUS

XGMF20 SERIES

MATERIAL	P											
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON				ALLOY STEELS HEAT RESISTANT STEELS				HARDENED STEELS			
	~ HRC35 ~ 1100N/mm ²				HRC35~ HRC45 1110 ~ 1500N/mm ²				HRC45~ HRC55 1500 ~ 2000N/mm ²			
STRENGTH	RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz
3/8	5300	19.1	520	.001	3440	15	338	.001	2120	7.1	208	.001
1/2	3900	13.4	511	.001	2630	11.8	344	.001	1590	5.1	208	.001
5/8	3100	11.0	507	.001	2120	9.1	347	.001	1290	4.5	211	.001
3/4	2600	9.5	511	.001	1720	7.5	338	.001	1050	3.7	206	.001
1	1950	11.7	511	.002	1290	7.7	338	.002	780	4.7	204	.002
1-1/4	1560	9.4	511	.002	1030	6.2	337	.002	620	3.7	203	.002



* 1.5xD Axial cutting depth should be for DIA over 5/8inch




RPM = rev./min. FEED = inch/min.
Vc = ft/min. fz = inch/tooth

CARBIDE MODULAR HEAD, 4 FLUTE MULTIPLE HELIX

XGMF25 SERIES

MATERIAL	P												M			
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON				ALLOY STEELS HEAT RESISTANT STEELS				HARDENED STEELS				STAINLESS STEELS			
	~ HRC35 ~ 1100N/mm ²				HRC35~ HRC45 1110 ~ 1500N/mm ²				HRC45~ HRC55 1500 ~ 2000N/mm ²							
STRENGTH	RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz
3/8	4280	26.5	420	.002	2620	13	257	.001	1780	3.9	175	.001	2200	13	216	.001
1/2	3240	20.7	424	.002	1980	9.9	259	.001	1370	3.2	179	.001	1610	9.5	211	.001
5/8	2770	17.6	453	.002	1710	8.5	280	.001	1140	2.5	187	.001	1390	8.3	227	.001
3/4	2200	13.9	432	.002	1400	7	275	.001	890	1.8	175	.001	1100	6.4	216	.001
1	1650	16.5	432	.003	1050	6.3	275	.002	680	1.6	178	.001	820	4.9	215	.002
1-1/4	1320	13.2	432	.003	835	5.0	273	.002	530	1.5	173	.001	655	3.9	214	.002



RPM = rev./min. FEED = inch/min.
Vc = ft/min. fz = inch/tooth

CARBIDE

HSS

CBN
END MILLS

i-Xmill
END MILLS

i-SMART
MODULAR
TYPE END MILLS

X5070
END MILLS

4G MILL
END MILLS

X-POWER
END MILLS

JET-POWER
END MILLS

TitaNox
-POWER
END MILLS

V7 PLUS A
END MILLS

V7 MILL INOX
END MILLS

ALU-POWER
HPC
END MILLS

ALU-POWER
END MILLS

D-POWER
GRAPHITE
END MILLS

D-POWER
CFRP
END MILLS

ROUTERS
CFRP

STANDARD
CARBIDE
END MILLS

ONLY ONE
COATED PM60
END MILLS

SINE -POWER
END MILLS

TANK-POWER
END MILLS

STANDARD
COBALT & HSS
END MILLS

TECHNICAL
DATA






RECOMMENDED CUTTING CONDITIONS

CARBIDE MODULAR HEAD, 6 FLUTE 45° HELIX

XGMF29 SERIES

NORMAL SPEED



MATERIAL	P											
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON				ALLOY STEELS HEAT RESISTANT STEELS				HARDENED STEELS			
HARDNESS	~ HRC35				HRC35~ HRC45				HRC45~ HRC55			
STRENGTH	~ 1100N/mm ²				1110 ~ 1500N/mm ²				1500 ~ 2000N/mm ²			
DIAMETER	RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz
3/8	3705	86.8	364	.004	2560	59.5	251	.004	1105	9.1	108	.001
1/2	2780	58.5	364	.004	1950	40.7	255	.003	840	6.3	110	.001
5/8	2225	44.7	364	.003	1565	31.2	256	.003	670	4.6	110	.001
3/4	1850	37.2	363	.003	1280	25.4	251	.003	545	4.1	107	.001
1	1390	33.4	364	.004	960	23.0	251	.004	420	3.8	110	.002
1-1/4	1110	26.6	363	.004	770	18.5	252	.004	330	3.0	108	.002



RPM = rev./min.
FEED = inch/min.
Vc = ft/min.
fz = inch/tooth

HIGH SPEED

MATERIAL	P							
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON				HARDENED STEELS			
HARDNESS	~ HRC50				HRC50~ HRC60			
STRENGTH	1750N/mm ²				1750 ~ 2080N/mm ²			
DIAMETER	RPM	Feed (IPM)	Vc (SFM)	fz	RPM	Feed (IPM)	Vc (SFM)	fz
3/8	11005	260.0	1080	.004	5555	132.3	545	.004
1/2	8330	175.4	1090	.004	4180	87.7	547	.003
5/8	6670	133.9	1091	.003	3340	67.0	547	.003
3/4	5555	112.4	1091	.003	2785	54.2	547	.003
1	4165	100.0	1090	.004	2090	50.2	547	.004
1-1/4	3330	79.9	1090	.004	1670	40.1	547	.004




RPM = rev./min.
FEED = inch/min.
Vc = ft/min.
fz = inch/tooth

CARBIDE



Being the best through innovation



X5070 END MILLS

- High Hardened Steels HRC45 to HRC70, High Speed Machining, Dry Cutting





SELECTION GUIDE

SOLID CARBIDE X5070 END MILLS

◎ : Excellent ○ : Good














ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	

INCH

G826	 High Feed End Mill	CARBIDE, 4FLUTE STUB LENGTH CORNER RADIUS HIGH FEED	◆	D1/8	D1/2	630
G8A43		CARBIDE, 2 FLUTE STUB LENGTH BALL NOSE with EXTENDED NECK	◆	R1/64	R1/4	631
G850		CARBIDE, 4 FLUTE STUB LENGTH CORNER RADIUS with EXTENDED NECK	◆	D1/16	D3/4	632
G851		CARBIDE, 6&8 FLUTE 45° HELIX CORNER RADIUS	◆	D1/4	D1	633

METRIC

◆ U.S.A Stock

G859	 High Feed End Mill	CARBIDE, 4FLUTE STUB LENGTH CORNER RADIUS HIGH FEED	◇	D2.0	D16.0	634
G854		CARBIDE, 4FLUTE STUB LENGTH CORNER RADIUS HIGH FEED	◇	D2.0	D16.0	635
G8A46		CARBIDE, 2 FLUTE BALL NOSE for RIB PROCESSING	◇	R0.05	R2.0	636
G8A54		CARBIDE, 2 FLUTE BALL NOSE for RIB PROCESSING	◇	R0.25	R1.0	640
G8A28		CARBIDE, 2 FLUTE BALL NOSE	◇	R0.05	R6.0	641
G8A38		CARBIDE, 2 FLUTE STUB LENGTH BALL NOSE with EXTENDED NECK	◇	R0.5	R12.5	642
G8A53		CARBIDE, 2 FLUTE MINIATURE BALL NOSE	◇	R0.2	R1.0	643
G8A59		CARBIDE, 3 FLUTE BALL NOSE	◇	R1.5	R10.0	644
G8A36		CARBIDE, 2 FLUTE STUB LENGTH CORNER RADIUS with EXTENDED NECK	◇	D0.3	D20.0	645
G8A50		CARBIDE, 2 FLUTE MINIATURE CORNER RADIUS	◇	D0.3	D2.0	647
G8A47		CARBIDE, 4 FLUTE CORNER RADIUS with EXTENDED NECK	◇	D3.0	D12.0	648
G8A37		CARBIDE, 4 FLUTE STUB LENGTH CORNER RADIUS with EXTENDED NECK	◇	D1.0	D20.0	649
G8A39		CARBIDE, 6 FLUTE 45° HELIX CORNER RADIUS with EXTENDED NECK	◇	D6.0	D20.0	650
RECOMMENDED CUTTING CONDITIONS						651

◇ Call for Availability

P					H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									

			○	○	◎	◎									
			○	○	◎	◎									
			○	○	◎	◎									
			○	○	◎	◎									

			○	○	◎	◎									
			○	○	◎	◎									
			○	○	◎	◎									
			○	○	◎	◎									
			○	○	◎	◎									
			○	○	◎	◎									
			○	○	◎	◎									
			○	○	◎	◎									
			○	○	◎	◎									
			○	○	◎	◎									

YG X5070 END MILLS

G826 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE STUB LENGTH CORNER RADIUS HIGH FEED

- ▶ Excellent wear resistance at heavy feed rates on high hardened material.
- ▶ Designed with reduced clearance angles and short flutes for strength.
- ▶ High hardness & heat resistance coating for long life in dry applications.



High Feed End Mill ◆ U.S.A Stock

Unit : Inch

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
G826082	R1/32	1/8	1/4	.050	3/8	2-1/4	.110
G826124	R1/16	3/16	1/4	.075	3/8	2-1/4	.180
G826164	R1/16	1/4	1/4	.100	1/2	2-1/2	.220
G826206	R3/32	5/16	5/16	.130	5/8	2-1/2	.280
G826246	R3/32	3/8	3/8	.150	3/4	2-3/4	.330
G826328	R1/8	1/2	1/2	.200	1	3-1/4	.460

↘ The original bright blue color may discolor during use, however, the performance will not be negatively affected

Mill Dia. Tolerance (inch)	Corner Radius Tolerance (inch)	Shank Dia. Tolerance
0~-.0008	±.0002	h6

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
		○	○	◎	◎								

YG X5070 END MILLS

G8A43 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE STUB CUT LENGTH BALL NOSE with EXTENDED NECK

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting due to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Designed for high precision milling operation.
- ▶ Higher wear-resistance.



◆ U.S.A Stock

R1/64-R1/8 R5/32-R1/4

Unit : Inch

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
G8A43002	R1/64	1/32	1/4	1/32	1/16	2	.029
G8A43004	R1/32	1/16	1/4	1/16	1/8	2	.059
G8A43006	R3/64	3/32	1/4	3/32	3/16	2	.090
G8A43008	R1/16	1/8	1/4	1/8	1/4	2-1/2	.121
G8A43012	R3/32	3/16	1/4	3/16	3/8	3	.184
G8A43016	R1/8	1/4	1/4	1/4	1/2	3-1/2	.246
G8A43020	R5/32	5/16	5/16	5/16	5/8	4	.309
G8A43024	R3/16	3/8	3/8	3/8	3/4	4	.371
G8A43032	R1/4	1/2	1/2	1/2	1	4-1/2	.496

↘ The original bright blue color may discolor during use, however, the performance will not be negatively affected

Size	Radius Tolerance (Inch)	Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
up to Ø1/4	±.0002	0~-.0005	h6
over Ø1/4	±.0004	0~-.0006	

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
		○	○	◎	◎								



G850 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE STUB LENGTH CORNER RADIUS with EXTENDED NECK

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting due to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Deep slotting is possible by reduced neck.
- ▶ Corner radius for preventing the chipping in high speed machining.
- ▶ Higher wear-resistance.



◆ U.S.A Stock

Unit : Inch

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
G85004	R.004	1/16	1/8	3/32	-	1-1/2	-
G85008	R.004	1/8	1/4	5/32	1/4	2	.119
G85012	R.004	3/16	1/4	1/4	3/8	2	.181
G85016	R.008	1/4	1/4	5/16	9/16	2	.238
G85020	R.008	5/16	5/16	3/8	3/4	2-1/2	.301
G85024	R.008	3/8	3/8	1/2	1	3	.363
G85032	R.012	1/2	1/2	5/16	1-3/16	3	.488
G85040	R.012	5/8	5/8	3/4	1-1/2	3-1	.613
G85048	R.012	3/4	3/4	1	1-3/4	4	.738

↘ The original bright blue color may discolor during use, however, the performance will not be negatively affected

Size	Corner Radius Tolerance (Inch)	Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
up to Ø1/4	±.0002	0~- .0005	h6
over Ø1/4	±.0004	0~- .0006	

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
		○	○	◎	◎								



G851 SERIES PLAIN SHANK

CARBIDE, 6&8 FLUTE 45° HELIX CORNER RADIUS

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting due to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Deep slotting is possible by reduced neck.
- ▶ Corner radius for preventing the chipping in high speed machining.
- ▶ Higher wear-resistance.



◆ U.S.A Stock

Unit : Inch

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
	R	D1	D2	L1	L2	
G85116	R.02	1/4	1/4	1/2	2-1/4	6
G85120	R.02	5/16	5/16	3/4	2-1/2	6
G85125	R.03	3/8	3/8	7/8	2-7/8	6
G85133	R.03	1/2	1/2	1	3-1/4	6
G85140	R.03	5/8	5/8	1-1/4	3-5/8	6
G85141	R.06	5/8	5/8	1-1/4	3-5/8	6
G85148	R.03	3/4	3/4	1-1/2	4-1/8	8
G85149	R.06	3/4	3/4	1-1/2	4-1/8	8
G85164	R.03	1	1	1-3/4	4-1/4	8
G85165	R.06	1	1	1-3/4	4-1/4	8
G85167	R.03	1	1	4-1/8	7	8
G85168	R.06	1	1	4-1/8	7	8

↘ The original bright blue color may discolor during use, however, the performance will not be negatively affected

Size	Corner Radius Tolerance (Inch)	Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
up to Ø1/4	±.0002	0~- .0005	h6
over Ø1/4	±.0004	0~- .0006	

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
		○	○	◎	◎								



G859 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE STUB LENGTH CORNER RADIUS HIGH FEED

- ▶ Excellent wear resistance at heavy feed rates on high hardened material.
- ▶ Designed with reduced clearance angles and short flutes for strength.
- ▶ High hardness & heat resistance coating for long life in dry applications.



High Feed End Mill
◇ Call for Availability

Unit : mm

EDP No.	Corner Radius R	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
G859020	R0.5	2.0	.0787	6	1	6	50	1.8
G859030	R0.5	3.0	.1181	6	1.2	8	50	2.8
G859040	R0.5	4.0	.1575	6	1.5	10	50	3.8
G859060	R0.5	6.0	.2362	6	2.5	12	60	5.4
G859061	R1.0	6.0	.2362	6	2.5	12	60	5.4
G859081	R1.0	8.0	.3150	8	3.5	16	60	7.2
G859082	R2.0	8.0	.3150	8	3.5	16	60	7.2
G859101	R1.0	10.0	.3937	10	4	20	70	9
G859102	R2.0	10.0	.3937	10	4	20	70	9
G859122	R2.0	12.0	.4724	12	5	25	80	11
G859123	R3.0	12.0	.4724	12	5	25	80	11
G859163	R3.0	16.0	.6299	16	6.5	30	90	15

↙ The original bright blue color may discolor during use, however, the performance will not be negatively affected

Mill Dia. Tolerance (inch)	Corner Radius Tolerance (inch)	Shank Dia. Tolerance
0 ~ -.0008	±.0002	h6

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
		○	○	◎	◎									



G854 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE STUB LENGTH CORNER RADIUS HIGH FEED

- ▶ Excellent wear resistance at heavy feed rates on high hardened material.
- ▶ Designed with reduced clearance angles and short flutes for strength.
- ▶ High hardness & heat resistance coating for long life in dry applications.



High Feed End Mill
◇ Call for Availability

Unit : mm

EDP No.	Corner Radius R	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
G854020	R0.5	2.0	.0787	6	1	6	70	1.8
G854030	R0.5	3.0	.1181	6	1.2	8	70	2.8
G854040	R0.5	4.0	.1575	6	1.5	10	70	3.8
G854050	R1.0	5.0	.1969	6	2	10	70	4.6
G854060	R0.5	6.0	.2362	6	2.5	12	90	5.4
G854061	R1.0	6.0	.2362	6	2.5	12	90	5.4
G854062	R1.5	6.0	.2362	6	2.5	12	90	5.4
G854081	R1.0	8.0	.3150	8	3.5	16	100	7.2
G854082	R2.0	8.0	.3150	8	3.5	16	100	7.2
G854101	R1.0	10.0	.3937	10	4	20	100	9
G854102	R2.0	10.0	.3937	10	4	20	100	9
G854122	R2.0	12.0	.4724	12	5	25	110	11
G854123	R3.0	12.0	.4724	12	5	25	110	11
G854163	R3.0	16.0	.6299	16	6.5	30	130	15

↙ The original bright blue color may discolor during use, however, the performance will not be negatively affected

Mill Dia. Tolerance (inch)	Corner Radius Tolerance (inch)	Shank Dia. Tolerance
0 ~ -.0008	±.0002	h6

◎ : Excellent ○ : Good



P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
		○	○	◎	◎									



G8A46 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE for RIB PROCESSING

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting thanks to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Designed for high precision milling operation.
- ▶ Higher wear-resistance.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.005)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
G8A46805	RO.05	0.1	.0039	4	0.1	0.3	45	0.085
G8A46806	RO.05	0.1	.0039	4	0.1	0.5	45	0.085
G8A46002	RO.1	0.2	.0079	4	0.2	0.5	45	0.17
G8A46977	RO.1	0.2	.0079	4	0.2	1	45	0.17
G8A46958	RO.1	0.2	.0079	4	0.2	1.5	45	0.17
G8A46003	RO.15	0.3	.0118	4	0.3	1	45	0.27
G8A46959	RO.15	0.3	.0118	4	0.3	2	45	0.27
G8A46986	RO.15	0.3	.0118	4	0.3	3	45	0.27
G8A46004	RO.2	0.4	.0157	4	0.4	1	45	0.37
G8A46960	RO.2	0.4	.0157	4	0.4	2	45	0.37
G8A46961	RO.2	0.4	.0157	4	0.4	3	45	0.37
G8A46981	RO.2	0.4	.0157	4	0.4	4	45	0.37
G8A46987	RO.2	0.4	.0157	4	0.4	5	45	0.37
G8A46005	RO.25	0.5	.0197	4	0.4	2	45	0.45
G8A46804	RO.25	0.5	.0197	4	0.4	2.5	45	0.45
G8A46962	RO.25	0.5	.0197	4	0.4	4	45	0.45
G8A46963	RO.25	0.5	.0197	4	0.4	6	45	0.45
G8A46964	RO.25	0.5	.0197	4	0.4	8	45	0.45
G8A46957	RO.3	0.6	.0236	4	0.5	2	45	0.55
G8A46988	RO.3	0.6	.0236	4	0.5	3	45	0.55
G8A46915	RO.3	0.6	.0236	4	0.5	4	45	0.55
G8A46989	RO.3	0.6	.0236	4	0.5	5	45	0.55

↙ The original bright blue color may discolor during use, however, the performance will not be negatively affected

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
		○	○	◎	◎								



G8A46 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE for RIB PROCESSING

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting thanks to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Designed for high precision milling operation.
- ▶ Higher wear-resistance.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.005)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
G8A46916	RO.3	0.6	.0236	4	0.5	6	45	0.55
G8A46917	RO.3	0.6	.0236	4	0.5	8	45	0.55
G8A46990	RO.3	0.6	.0236	4	0.5	10	45	0.55
G8A46918	RO.4	0.8	.0315	4	0.6	2	45	0.75
G8A46919	RO.4	0.8	.0315	4	0.6	4	45	0.75
G8A46008	RO.4	0.8	.0315	4	0.6	6	45	0.75
G8A46901	RO.4	0.8	.0315	4	0.6	8	45	0.75
G8A46965	RO.4	0.8	.0315	4	0.6	10	45	0.75
G8A46920	RO.5	1.0	.0394	4	0.8	3	45	0.95
G8A46921	RO.5	1.0	.0394	4	0.8	4	45	0.95
G8A46923	RO.5	1.0	.0394	4	0.8	5	45	0.95
G8A46010	RO.5	1.0	.0394	4	0.8	6	45	0.95
G8A46924	RO.5	1.0	.0394	4	0.8	7	45	0.95
G8A46902	RO.5	1.0	.0394	4	0.8	8	45	0.95
G8A46925	RO.5	1.0	.0394	4	0.8	9	45	0.95
G8A46903	RO.5	1.0	.0394	4	0.8	10	45	0.95
G8A46904	RO.5	1.0	.0394	4	0.8	12	45	0.95
G8A46926	RO.5	1.0	.0394	4	0.8	14	50	0.95
G8A46927	RO.5	1.0	.0394	4	0.8	16	50	0.95
G8A46966	RO.5	1.0	.0394	4	0.8	20	55	0.95
G8A46982	RO.6	1.2	.0472	4	1.0	6	45	1.15
G8A46012	RO.6	1.2	.0472	4	1.0	8	45	1.15

↙ The original bright blue color may discolor during use, however, the performance will not be negatively affected

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
		○	○	◎	◎								



G8A46 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE for RIB PROCESSING

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting thanks to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Designed for high precision milling operation.
- ▶ Higher wear-resistance.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.005)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
G8A46983	R0.6	1.2	.0472	4	1.0	10	45	1.15
G8A46905	R0.6	1.2	.0472	4	1.0	12	45	1.15
G8A46930	R0.75	1.5	.0472	4	1.2	6	45	1.45
G8A46015	R0.75	1.5	.0472	4	1.2	8	45	1.45
G8A46931	R0.75	1.5	.0472	4	1.2	10	45	1.45
G8A46906	R0.75	1.5	.0472	4	1.2	12	45	1.45
G8A46992	R0.75	1.5	.0472	4	1.2	14	50	1.45
G8A46907	R0.75	1.5	.0472	4	1.2	16	50	1.45
G8A46932	R0.75	1.5	.0472	4	1.2	20	55	1.45
G8A46939	R1.0	2.0	.0787	4	1.6	4	45	1.95
G8A46940	R1.0	2.0	.0787	4	1.6	6	45	1.95
G8A46020	R1.0	2.0	.0787	4	1.6	8	45	1.95
G8A46941	R1.0	2.0	.0787	4	1.6	10	45	1.95
G8A46942	R1.0	2.0	.0787	4	1.6	12	50	1.95
G8A46943	R1.0	2.0	.0787	4	1.6	14	50	1.95
G8A46909	R1.0	2.0	.0787	4	1.6	16	50	1.95
G8A46993	R1.0	2.0	.0787	4	1.6	18	55	1.95
G8A46910	R1.0	2.0	.0787	4	1.6	20	55	1.95
G8A46944	R1.0	2.0	.0787	4	1.6	22	60	1.95
G8A46945	R1.0	2.0	.0787	4	1.6	25	60	1.95
G8A46967	R1.0	2.0	.0787	4	1.6	30	70	1.95
G8A46948	R1.5	3.0	.1181	6	2.4	12	50	2.85

▶ The original bright blue color may discolor during use, however, the performance will not be negatively affected

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
		○	○	◎	◎								



G8A46 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE for RIB PROCESSING

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting thanks to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Designed for high precision milling operation.
- ▶ Higher wear-resistance.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.005)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
G8A46984	R1.5	3.0	.1181	6	2.4	14	55	2.85
G8A46030	R1.5	3.0	.1181	6	2.4	16	55	2.85
G8A46985	R1.5	3.0	.1181	6	2.4	18	60	2.85
G8A46911	R1.5	3.0	.1181	6	2.4	20	60	2.85
G8A46968	R1.5	3.0	.1181	6	2.4	25	65	2.85
G8A46969	R1.5	3.0	.1181	6	2.4	30	70	2.85
G8A46970	R1.5	3.0	.1181	6	2.4	35	80	2.85
G8A46950	R2.0	4.0	.1575	6	3.2	12	60	3.85
G8A46040	R2.0	4.0	.1575	6	3.2	16	60	3.85
G8A46912	R2.0	4.0	.1575	6	3.2	20	65	3.85
G8A46913	R2.0	4.0	.1575	6	3.2	25	70	3.85
G8A46971	R2.0	4.0	.1575	6	3.2	30	70	3.85
G8A46972	R2.0	4.0	.1575	6	3.2	35	80	3.85
G8A46973	R2.0	4.0	.1575	6	3.2	40	90	3.85
G8A46974	R2.0	4.0	.1575	6	3.2	45	90	3.85
G8A46975	R2.0	4.0	.1575	6	3.2	50	100	3.85

▶ The original bright blue color may discolor during use, however, the performance will not be negatively affected

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.012	h6

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
		○	○	◎	◎								



G8A54 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE for RIB PROCESSING

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting thanks to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Designed for high precision milling operation.
- ▶ Higher wear-resistance.



◇ Call for Availability

EDP No.	Radius of Ball Nose R (±0.005)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
G8A54005	R0.25	0.5	.0197	6	0.5	1.5	50	0.45
G8A54901	R0.25	0.5	.0197	6	0.5	3.3	50	0.45
G8A54006	R0.3	0.6	.0236	6	0.6	2	50	0.55
G8A54902	R0.3	0.6	.0236	6	0.6	4	50	0.55
G8A54008	R0.4	0.8	.0315	6	0.8	2.5	50	0.75
G8A54903	R0.4	0.8	.0315	6	0.8	5.5	50	0.75
G8A54010	R0.5	1.0	.0394	6	1	3.3	50	0.95
G8A54904	R0.5	1.0	.0394	6	1	6.7	50	0.95
G8A54905	R0.5	1.0	.0394	6	1	12	50	0.95
G8A54012	R0.6	1.2	.0472	6	1.2	4.4	50	1.15
G8A54906	R0.6	1.2	.0472	6	1.2	8	50	1.15
G8A54015	R0.75	1.5	.0591	6	1.5	5	50	1.45
G8A54907	R0.75	1.5	.0591	6	1.5	9.7	50	1.45
G8A54908	R0.75	1.5	.0591	6	1.5	15	50	1.45
G8A54020	R1.0	2.0	.0787	6	2	6	50	1.95
G8A54909	R1.0	2.0	.0787	6	2	13	50	1.95
G8A54910	R1.0	2.0	.0787	6	2	20	60	1.95

↙ The original bright blue color may discolor during use, however, the performance will not be negatively affected

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.012	h6

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
			○	○	◎	◎							



G8A28 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting thanks to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Designed for high precision milling operation.
- ▶ Higher wear-resistance.



◇ Call for Availability

EDP No.	Radius of Ball Nose R	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
G8A28001	R0.05	0.1	.0039	4	0.2	-	40	-
G8A28002	R0.1	0.2	.0079	4	0.3	-	40	-
G8A28003	R0.15	0.3	.0118	4	0.5	-	40	-
G8A28004	R0.2	0.4	.0157	4	0.6	-	40	-
G8A28005	R0.25	0.5	.0197	4	0.7	-	40	-
G8A28006	R0.3	0.6	.0236	4	0.9	-	40	-
G8A28007	R0.35	0.7	.0276	4	1.1	-	40	-
G8A28008	R0.4	0.8	.0315	4	1.2	-	40	-
G8A28009	R0.45	0.9	.0354	4	1.4	-	40	-
G8A280104S	R0.5	1.0	.0394	4	1.5	3	50	0.95
G8A28010	R0.5	1.0	.0394	6	1.5	3	50	0.95
G8A280154S	R0.75	1.5	.0591	4	2	4	50	1.45
G8A28015	R0.75	1.5	.0591	6	2	4	50	1.45
G8A280204S	R1.0	2.0	.0787	4	2.5	5	50	1.95
G8A28020	R1.0	2.0	.0787	6	2.5	5	50	1.95
G8A280254S	R1.25	2.5	.0984	4	3	7	50	2.4
G8A28025	R1.25	2.5	.0984	6	3	7	50	2.4
G8A28030	R1.5	3.0	.1181	6	4	10	60	2.85
G8A28035	R1.75	3.5	.1378	6	4.5	10	60	3.35
G8A28040	R2.0	4.0	.1575	6	5	10	60	3.85
G8A28045	R2.25	4.5	.1772	6	5.5	10	60	4.35
G8A28050	R2.5	5.0	.1969	6	6	12	60	4.85
G8A28055	R2.75	5.5	.2165	6	6.5	12	60	5.35
G8A28060	R3.0	6.0	.2362	6	7	15	60	5.85
G8A28903	R3.0	6.0	.2362	6	9	30	90	5.85
G8A28901	R4.0	8.0	.3150	8	9	15	60	7.7
G8A28080	R4.0	8.0	.3150	8	9	15	80	7.7
G8A28904	R4.0	8.0	.3150	8	12	30	100	7.7
G8A28902	R5.0	10.0	.3937	10	11	25	60	9.7
G8A28100	R5.0	10.0	.3937	10	11	25	80	9.7
G8A28905	R5.0	10.0	.3937	10	15	30	100	9.7
G8A28120	R6.0	12.0	.4724	12	14	25	80	11.7

↙ The original bright blue color may discolor during use, however, the performance will not be negatively affected

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
			○	○	◎	◎							



G8A38 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE STUB LENGTH BALL NOSE with EXTENDED NECK

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting due to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Designed for high precision milling operation.
- ▶ Higher wear-resistance.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
G8A38010	R0.5	1.0	.0394	4	1	2.2	50	0.95
G8A38012	R0.6	1.2	.0472	4	1.2	2.6	50	1.15
G8A38015	R0.75	1.5	.0591	4	1.5	3	50	1.45
G8A380204S	R1.0	2.0	.0787	4	2	4	50	1.95
G8A38020	R1.0	2.0	.0787	6	2	4	50	1.95
G8A38030	R1.5	3.0	.1181	6	3	6	60	2.85
G8A38040	R2.0	4.0	.1575	6	4	8	70	3.85
G8A38050	R2.5	5.0	.1969	6	5	10	80	4.85
G8A38060	R3.0	6.0	.2362	6	6	12	90	5.85
G8A38070	R3.5	7.0	.2756	8	7	14	90	6.7
G8A38080	R4.0	8.0	.3150	8	8	16	100	7.7
G8A38090	R4.5	9.0	.3543	10	9	18	100	8.7
G8A38100	R5.0	10.0	.3937	10	10	20	100	9.7
G8A38120	R6.0	12.0	.4724	12	12	24	110	11.7
G8A38140	R7.0	14.0	.5512	14	14	28	110	13.7
G8A38160	R8.0	16.0	.6299	16	16	32	140	15.7
G8A38180	R9.0	18.0	.7087	18	18	36	140	17.7
G8A38200	R10.0	20.0	.7874	20	20	40	160	19.7
G8A38250	R12.5	25.0	.9843	25	25	50	180	24.7

↙ The original bright blue color may discolor during use, however, the performance will not be negatively affected

Size	Radius Tolerance (mm)	Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
up to R3	±0.005	0~-0.012	h6
over R3	±0.010	0~-0.015	

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
		○	○	◎	◎								



G8A53 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE MINIATURE BALL NOSE

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting thanks to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Designed for high precision milling operation.
- ▶ Higher wear-resistance.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.005)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Overall Length L2
		Metric D1	Inch			
G8A53004	R0.2	0.4	.0157	6	0.4	50
G8A53005	R0.25	0.5	.0197	6	0.5	50
G8A53006	R0.3	0.6	.0236	6	0.6	50
G8A53008	R0.4	0.8	.0315	6	0.8	50
G8A53010	R0.5	1.0	.0394	6	1.0	50
G8A53012	R0.6	1.2	.0472	6	1.2	50
G8A53015	R0.75	1.5	.0591	6	1.5	50
G8A53020	R1.0	2.0	.0787	6	2.0	50

↙ The original bright blue color may discolor during use, however, the performance will not be negatively affected

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.012	h6

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
		○	○	◎	◎								



G8A59 SERIES PLAIN SHANK

CARBIDE, 3 FLUTE BALL NOSE

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting thanks to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Designed for high precision milling operation.
- ▶ Higher wear-resistance.



◇ Call for Availability

EDP No.	Radius of Ball Nose R	Mill Diameter		Shank Diameter D2	Length of Cut L1	Overall Length L2
		Metric D1	Inch			
G8A59030	R1.5	3.0	.1181	6	8	60
G8A59040	R2.0	4.0	.1575	6	8	70
G8A59050	R2.5	5.0	.1969	6	10	80
G8A59060	R3.0	6.0	.2362	6	12	90
G8A59080	R4.0	8.0	.3150	8	14	100
G8A59100	R5.0	10.0	.3937	10	18	100
G8A59120	R6.0	12.0	.4724	12	22	110
G8A59160	R8.0	16.0	.6299	16	30	140
G8A59200	R10.0	20.0	.7874	20	38	160

↙ The original bright blue color may discolor during use, however, the performance will not be negatively affected

Size	Radius Tolerance (mm)	Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
up to R3	±0.005	0~-0.012	h6
over R3	±0.010	0~-0.015	

◎ : Excellent ○ : Good



P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
		○	○	◎	◎								



G8A36 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE STUB LENGTH CORNER RADIUS with EXTENDED NECK

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting due to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Deep slotting is possible by reduced neck.
- ▶ Corner radius for preventing the chipping in high speed machining.
- ▶ Higher wear-resistance.



◇ Call for Availability

EDP No.	Corner Radius R	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
G8A36003	-	0.3	.0118	3	0.45	-	40	-
G8A36004	-	0.4	.0157	3	0.6	-	40	-
G8A36005	RO.05	0.5	.0197	3	0.7	-	40	-
G8A36907	RO.05	0.5	.0197	4	1	-	40	-
G8A36006	RO.05	0.6	.0236	3	0.9	-	40	-
G8A36908	RO.05	0.6	.0236	4	1.2	-	40	-
G8A36909	RO.05	0.7	.0276	4	1.4	-	40	-
G8A36008	RO.05	0.8	.0315	3	1.2	-	40	-
G8A36910	RO.05	0.8	.0315	4	1.6	-	40	-
G8A36911	RO.05	0.9	.0354	4	2	-	40	-
G8A36010	RO.1	1.0	.0394	3	1.5	-	40	-
G8A36901	RO.1	1.0	.0394	4	1.5	-	40	-
G8A36903	RO.1	1.0	.0394	6	1.5	-	40	-
G8A36015	RO.1	1.5	.0591	3	2.2	-	40	-
G8A36904	RO.1	1.5	.0591	6	2.2	-	40	-
G8A36020	RO.1	2.0	.0787	3	3	6	40	1.95
G8A36902	RO.1	2.0	.0787	4	3	6	40	1.95
G8A36905	RO.1	2.0	.0787	6	3	6	40	1.95
G8A36025	RO.1	2.5	.0984	3	4	6	40	2.4
G8A36906	RO.1	2.5	.0984	6	4	6	40	2.4

↙ The original bright blue color may discolor during use, however, the performance will not be negatively affected

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
		○	○	◎	◎								



G8A36 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE STUB LENGTH CORNER RADIUS with EXTENDED NECK

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting due to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Deep slotting is possible by reduced neck.
- ▶ Corner radius for preventing the chipping in high speed machining.
- ▶ Higher wear-resistance.



◇ Call for Availability

Unit : mm

EDP No.	Corner Radius R	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
G8A36030	RO.1	3.0	.1181	6	4	7	45	2.85
G8A36035	RO.1	3.5	.1378	6	5	9	45	3.35
G8A36040	RO.1	4.0	.1575	6	5	9	45	3.85
G8A36045	RO.1	4.5	.1772	6	6	10	45	4.35
G8A36050	RO.2	5.0	.1969	6	6	11	50	4.85
G8A36060	RO.2	6.0	.2362	6	7	14	50	5.85
G8A36080	RO.2	8.0	.3150	8	9	18	60	7.7
G8A36100	RO.2	10.0	.3937	10	12	25	75	9.7
G8A36120	RO.3	12.0	.4724	12	15	30	75	11.7
G8A36160	RO.3	16.0	.6299	16	18	38	90	15.7
G8A36200	RO.3	20.0	.7874	20	24	45	100	19.7

↙ The original bright blue color may discolor during use, however, the performance will not be negatively affected

Size	Corner Radius Tolerance (mm)	Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
up to Ø6	±0.010	0~-0.012	h6
over Ø6	±0.015	0~-0.015	

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
		○	○	◎	◎									



G8A50 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE MINIATURE CORNER RADIUS

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting thanks to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Deep slotting is possible by reduced neck.
- ▶ Corner radius for preventing the chipping in high speed machining.
- ▶ Higher wear-resistance.



◇ Call for Availability

Unit : mm

EDP No.	Corner Radius R (±0.010)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Overall Length L2
		Metric D1	Inch			
G8A50003	-	0.3	.0118	6	0.45	50
G8A50004	-	0.4	.0157	6	0.6	50
G8A50005	RO.05	0.5	.0197	6	0.7	50
G8A50006	RO.05	0.6	.0236	6	0.9	50
G8A50008	RO.05	0.8	.0315	6	1.2	50
G8A50010	RO.1	1.0	.0394	6	1.5	50
G8A50012	RO.1	1.2	.0472	6	1.8	50
G8A50015	RO.15	1.5	.0591	6	2.2	50
G8A50020	RO.15	2.0	.0787	6	2.2	50

↙ The original bright blue color may discolor during use, however, the performance will not be negatively affected

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.012	h6

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
		○	○	◎	◎									



G8A47 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE CORNER RADIUS with EXTENDED NECK

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting thanks to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Deep slotting is possible by reduced neck.
- ▶ Corner radius for preventing the chipping in high speed machining.
- ▶ Higher wear-resistance.



NG 4 BLUE 30° ±0.010 ±0.015 PLAIN P.659 ◇ Call for Availability

EDP No.	Corner Radius R	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric	Inch					
		D1						
G8A47916	RO.3	3.0	.1181	6	4	12	55	2.85
G8A47917	RO.3	3.0	.1181	6	4	16	55	2.85
G8A47918	RO.3	3.0	.1181	6	4	20	55	2.85
G8A47030	RO.5	3.0	.1181	6	4	10	55	2.85
G8A47901	RO.5	3.0	.1181	6	4	16	55	2.85
G8A47902	RO.5	3.0	.1181	6	4	20	55	2.85
G8A47919	RO.3	4.0	.1575	6	5	12	55	3.85
G8A47920	RO.3	4.0	.1575	6	5	16	55	3.85
G8A47921	RO.3	4.0	.1575	6	5	20	55	3.85
G8A47040	RO.5	4.0	.1575	6	5	12	55	3.85
G8A47903	RO.5	4.0	.1575	6	5	16	55	3.85
G8A47904	RO.5	4.0	.1575	6	5	20	55	3.85
G8A47922	R1.0	4.0	.1575	6	5	12	55	3.85
G8A47060	RO.5	6.0	.2362	6	7	20	60	5.85
G8A47905	R1.0	6.0	.2362	6	7	20	60	5.85
G8A47906	R1.5	6.0	.2362	6	7	20	60	5.85
G8A47910	RO.5	8.0	.3150	8	9	25	60	7.7
G8A47080	R1.0	8.0	.3150	8	9	25	60	7.7
G8A47907	R1.5	8.0	.3150	8	9	25	60	7.7
G8A47913	R2.0	8.0	.3150	8	9	25	60	7.7
G8A47911	RO.5	10.0	.3937	10	11	32	70	9.7
G8A47100	R1.0	10.0	.3937	10	11	32	70	9.7
G8A47908	R1.5	10.0	.3937	10	11	32	70	9.7
G8A47914	R2.0	10.0	.3937	10	11	32	70	9.7
G8A47912	RO.5	12.0	.4724	12	12	38	80	11.7
G8A47120	R1.0	12.0	.4724	12	12	38	80	11.7
G8A47909	R1.5	12.0	.4724	12	12	38	80	11.7
G8A47915	R2.0	12.0	.4724	12	12	38	80	11.7

Size	Corner Radius Tolerance (mm)	Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
up to Ø6	±0.010	0~-0.012	h6
over Ø6	±0.015	0~-0.015	

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
		○	○	◎	◎								



G8A37 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE STUB LENGTH CORNER RADIUS with EXTENDED NECK

- ▶ Designed to machine high hardened materials.
- ▶ Suitable for dry cutting, high speed cutting due to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Deep slotting is possible by reduced neck.
- ▶ Corner radius for preventing the chipping in high speed machining.
- ▶ Higher wear-resistance.



NG 4 BLUE 30° ±0.010 ±0.015 PLAIN P.660 ◇ Call for Availability

EDP No.	Corner Radius R	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric	Inch					
		D1						
G8A37010	RO.1	1.0	.0394	3	1.5	-	40	-
G8A37901	RO.1	1.0	.0394	6	1.5	-	40	-
G8A37015	RO.1	1.5	.0591	3	2.2	-	40	-
G8A37902	RO.1	1.5	.0591	6	2.2	-	40	-
G8A37020	RO.1	2.0	.0787	3	3	6	40	1.95
G8A37903	RO.1	2.0	.0787	6	3	6	40	1.95
G8A37025	RO.1	2.5	.0984	3	4	6	40	2.4
G8A37904	RO.1	2.5	.0984	6	4	6	40	2.4
G8A37030	RO.1	3.0	.1181	6	4	7	45	2.85
G8A37035	RO.1	3.5	.1378	6	5	9	45	3.35
G8A37040	RO.1	4.0	.1575	6	5	9	45	3.85
G8A37045	RO.1	4.5	.1772	6	6	10	45	4.35
G8A37050	RO.2	5.0	.1969	6	6	11	50	4.85
G8A37060	RO.2	6.0	.2362	6	7	14	50	5.85
G8A37080	RO.2	8.0	.3150	8	9	18	60	7.7
G8A37100	RO.2	10.0	.3937	10	12	25	75	9.7
G8A37120	RO.3	12.0	.4724	12	15	30	75	11.7
G8A37160	RO.3	16.0	.6299	16	18	38	90	15.7
G8A37200	RO.3	20.0	.7874	20	24	45	100	19.7

↙ The original bright blue color may discolor during use, however, the performance will not be negatively affected

Size	Corner Radius Tolerance (mm)	Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
up to Ø6	±0.010	0~-0.012	h6
over Ø6	±0.015	0~-0.015	



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
		○	○	◎	◎								



G8A39 SERIES PLAIN SHANK

CARBIDE, 6 FLUTE 45° HELIX CORNER RADIUS with EXTENDED NECK

- ▶ Designed to machine high hardened materials
- ▶ Suitable for dry cutting, high speed cutting due to newly developed raw-material and new coating.
- ▶ Excellent workpiece finish.
- ▶ Deep slotting is possible by reduced neck.
- ▶ Corner radius for preventing the chipping in high speed machining
- ▶ Higher wear-resistance.



◇ Call for Availability

EDP No.	Corner Radius R	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
G8A39916	R0.25	6.0	.2362	6	6	14	50	5.85
G8A39060	R0.5	6.0	.2362	6	6	14	50	5.85
G8A39901	R0.5	6.0	.2362	6	13	-	70	-
* G8A39910	R0.5	6.0	.2362	6	26	-	70	-
G8A39080	R0.5	8.0	.3150	8	8	24	60	7.7
G8A39902	R0.5	8.0	.3150	8	19	-	90	-
* G8A39911	R0.5	8.0	.3150	8	36	-	90	-
G8A39903	R0.5	10.0	.3937	10	22	-	100	-
G8A39100	R1.0	10.0	.3937	10	10	30	70	9.7
G8A39904	R1.0	10.0	.3937	10	22	-	100	-
* G8A39912	R1.0	10.0	.3937	10	46	-	100	-
G8A39905	R0.5	12.0	.4724	12	26	-	110	-
G8A39120	R1.0	12.0	.4724	12	12	30	75	11.7
G8A39906	R1.0	12.0	.4724	12	26	-	110	-
* G8A39913	R1.0	12.0	.4724	12	56	-	110	-
G8A39160	R1.0	16.0	.6299	16	32	-	130	-
G8A39907	R1.5	16.0	.6299	16	32	-	130	-
* G8A39914	R1.5	16.0	.6299	16	66	-	130	-
G8A39200	R1.0	20.0	.7874	20	38	-	140	-
G8A39908	R1.5	20.0	.7874	20	38	-	140	-
G8A39909	R2.0	20.0	.7874	20	38	-	140	-
* G8A39915	R2.0	20.0	.7874	20	76	-	140	-

↙ The original bright blue color may discolor during use, however, the performance will not be negatively affected

Size	Corner Radius Tolerance (mm)	Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
up to Ø6	±0.010	0~-0.02	h6
over Ø6	±0.015	(* Extra Long Type : 0~-0.03)	

◎ : Excellent ○ : Good

P				H		M	K	N					S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
		○	○	◎	◎								




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE STUB LENGTH CORNER RADIUS HIGH FEED

G826 SERIES

■ NORMAL SPEED



MATERIAL	P						H			
	HARDENED STEELS						HIGH HARDENED STEELS			
	~ HRc40		HRc40 ~ HRc50		HRc50 ~ HRc55		HRc55 ~ HRc60		HRc60 ~ HRc65	
HARDNESS	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8 × R1/32	9000	245	6500	155	4300	100	2700	43	1800	23
3/16 × R1/16	7500	310	5100	200	3800	140	2350	70	1650	30
1/4 × R1/16	5500	310	3900	200	2800	140	1750	70	1250	30
5/16 × R3/32	4500	310	3100	200	2200	140	1400	70	1000	30
3/8 × R3/32	3800	310	2600	200	1850	140	1170	70	840	30
1/2 × R1/8	2800	310	1950	200	1400	140	880	70	630	30



RPM = rev./min.
FEED = inch/min.

■ HIGH SPEED

MATERIAL	P						H			
	HARDENED STEELS						HIGH HARDENED STEELS			
	~ HRc40		HRc40 ~ HRc50		HRc50 ~ HRc55		HRc55 ~ HRc60		HRc60 ~ HRc65	
HARDNESS	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8 × R1/32	21000	600	16000	380	12000	300	9000	170	6500	92
3/16 × R1/16	16500	720	13500	550	11500	420	8000	250	5700	150
1/4 × R1/16	12500	720	10000	550	8500	420	6000	250	4300	150
5/16 × R3/32	10000	720	8000	550	6800	420	4800	250	3400	150
3/8 × R3/32	8500	720	6700	550	5700	420	4000	250	2850	150
1/2 × R1/8	6500	720	5000	550	4300	420	3000	250	2150	150



RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE BALL NOSE with EXTENDED NECK

G8A43 SERIES

MATERIAL	P						H					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS				HIGH HARDENED STEELS					
	HRC30 ~ HRC40		HRC40 ~ HRC50		HRC50 ~ HRC55		HRC55 ~ HRC60		HRC60 ~ HRC65		HRC65 ~ HRC70	
HARDNESS DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
R1/64 x 1/32	50000	189.0	50000	165.4	45000	149.6	40000	118.1	35000	102.4	35000	90.6
R1/32 x 1/16	49700	224.4	47800	189.0	40000	157.5	35000	124.0	32000	110.2	28500	90.6
R3/64 x 3/32	49700	224.4	47800	189.0	40000	157.5	35000	124.0	32000	110.2	28500	90.6
R1/16 x 1/8	33100	236.2	31800	208.7	26500	157.5	23500	124.0	21000	110.2	19000	90.6
R3/32 x 3/16	18600	228.4	17800	192.9	15000	147.6	13500	120.1	11500	100.4	10500	82.7
R1/8 x 1/14	13900	190.9	13400	161.4	11000	122.1	10000	98.4	8800	84.7	8000	68.9
R5/32 x 5/16	11100	165.4	10700	137.8	9000	106.3	8000	84.7	7000	72.8	6500	61.0
R3/16 x 3/8	9300	145.7	8900	122.1	7500	94.5	6600	74.8	5800	65.0	5300	54.3
R1/4 x 1/2	6950	116.1	6680	98.4	5600	74.8	5000	61.0	4400	49.2	4000	41.3



※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE STUB LENGTH CORNER RADIUS

G850 SERIES

MATERIAL	P						H					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS				HIGH HARDENED STEELS					
	HRC30 ~ HRC40		HRC40 ~ HRC50		HRC50 ~ HRC55		HRC55 ~ HRC60		HRC60 ~ HRC65		HRC65 ~ HRC70	
HARDNESS DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/16	41950	69.4	32750	49.6	22050	33.3	18250	20.6	13850	12.7	11950	9.1
1/8	20600	52.1	16350	37.2	10850	25.0	9000	15.5	7100	9.5	6050	6.9
3/16	16500	66.2	13100	49.5	8700	33.0	6700	19.1	5350	12.2	4650	8.9
1/4	12400	58.1	9800	41.8	6500	28.2	5000	16.6	3950	10.4	3500	7.8
5/16	9950	59.6	7850	42.8	5250	28.6	4050	16.6	3250	10.6	2800	7.6
3/8	8200	57.9	6450	41.6	4300	27.8	3350	15.8	2700	10.3	2300	7.2
1/2	6300	52.2	4950	37.4	3300	24.9	2500	14.3	2000	9.0	1750	6.5
5/8	4950	47.7	3950	35.1	2600	23.0	2000	13.2	1600	8.5	1400	6.3
3/4	4100	43.0	3250	32.0	2150	21.5	1700	12.7	1350	8.2	1150	5.9





RPM = rev./min.
FEED = inch/min.

CARBIDE, 6&8 FLUTE 45° HELIX CORNER RADIUS

G851 SERIES

MATERIAL	P						H					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS				HIGH HARDENED STEELS					
	HRC30 ~ HRC40		HRC40 ~ HRC50		HRC50 ~ HRC55		HRC55 ~ HRC60		HRC60 ~ HRC65		HRC65 ~ HRC70	
HARDNESS DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	23450	199.2	22200	182.2	15100	182.1	12750	122.7	9900	78.0	7550	53.9
5/16	20650	191.3	19600	174.8	13200	171.8	11150	115.3	8700	73.3	6600	51.2
3/8	17900	183.4	17000	167.3	11350	161.6	9500	108.0	7450	68.7	5700	48.5
1/2	12300	167.6	11800	152.4	7550	141.2	6250	93.2	5000	59.4	3800	43.0
5/8	10100	159.1	9800	147.2	6050	135.0	5050	91.5	4050	49.8	3000	34.3
3/4	8850	140.7	8600	133.3	5300	123.2	4400	82.7	3550	43.7	2650	30.0
1	6300	103.9	6150	105.5	3800	99.7	3150	65.1	2500	31.4	1900	21.5



※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.





RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE STUB LENGTH CORNER RADIUS HIGH FEED

G859, G854 SERIES

NORMAL SPEED



MATERIAL	P						H			
	HARDENED STEELS						HIGH HARDENED STEELS			
	~ HRC40		HRC40 ~ HRC50		HRC50 ~ HRC55		HRC55 ~ HRC60		HRC60 ~ HRC65	
HARDNESS DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
2.0 x RO.5	13500	255.9	9550	149.6	5500	86.6	3200	39.4	2200	21.7
3.0 x RO.5	9550	255.9	6900	163.4	4550	108.3	2850	45.3	1900	24.0
4.0 x RO.5	7950	275.6	5750	181.1	4000	126.0	2550	53.2	1750	27.6
5.0 x RO.5	6500	287.4	4800	189.0	3400	126.0	2200	63.0	1500	27.6
6.0 x RO.5	5800	301.2	4100	192.9	2900	137.8	1850	72.8	1350	31.3
6.0 x R1.0	5800	301.2	4100	192.9	2900	137.8	1850	72.8	1350	31.3
8.0 x R1.0	4350	301.2	3050	192.9	2200	137.8	1400	72.8	995	31.3
8.0 x R2.0	4350	301.2	3050	192.9	2200	137.8	1400	72.8	995	31.3
10.0 x R1.0	3500	301.2	2450	192.9	1750	137.8	1100	72.8	795	31.3
10.0 x R2.0	3500	301.2	2450	192.9	1750	137.8	1100	72.8	795	31.3
12.0 x R2.0	2900	301.2	2050	192.9	1450	137.8	925	72.8	665	31.3
12.0 x R3.0	2900	301.2	2050	192.9	1450	137.8	925	72.8	665	31.3
16.0 x R3.0	2200	301.2	1550	192.9	1100	137.8	700	72.8	500	31.3



RPM = rev./min.
FEED = inch/min.

HIGH SPEED

MATERIAL	P						H			
	HARDENED STEELS						HIGH HARDENED STEELS			
	~ HRC40		HRC40 ~ HRC50		HRC50 ~ HRC55		HRC55 ~ HRC60		HRC60 ~ HRC65	
HARDNESS DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
2.0 x RO.5	29000	590.6	22000	385.8	15000	309.1	11000	175.2	8700	96.5
3.0 x RO.5	22000	629.9	17000	393.7	12500	315.0	9500	181.1	6900	98.4
4.0 x RO.5	17000	689.0	13000	472.4	11000	362.2	8000	216.5	5600	114.2
5.0 x RO.5	15000	708.7	11000	472.4	10000	393.7	7000	236.2	4900	122.1
6.0 x RO.5	13500	728.4	10500	543.3	9000	433.1	6400	252.0	4500	141.7
6.0 x R1.0	13500	728.4	10500	543.3	9000	433.1	6400	252.0	4500	141.7
8.0 x R1.0	10000	728.4	8000	551.2	6800	433.1	4800	263.8	3400	161.4
8.0 x R2.0	10000	728.4	8000	551.2	6800	433.1	4800	263.8	3400	161.4
10.0 x R1.0	8000	728.4	6400	551.2	5400	433.1	3800	267.7	2700	149.6
10.0 x R2.0	8000	728.4	6400	551.2	5400	433.1	3800	267.7	2700	149.6
12.0 x R2.0	6600	728.4	5300	551.2	4500	433.1	3200	275.6	2250	141.7
12.0 x R3.0	6600	728.4	5300	551.2	4500	433.1	3200	275.6	2250	141.7
16.0 x R3.0	5000	728.4	3900	551.2	3300	433.1	2400	275.6	1650	129.9



RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE BALL NOSE for RIB PROCESSING

G8A46, G8A54 SERIES

MATERIAL	P						H			N		
	ALLOY STEELS HEAT RESISTANT STEELS			HARDENED STEELS			HIGH HARDENED STEELS			COPPER		
	HRC30 ~ HRC45			HRC45 ~ HRC55			HRC55 ~ HRC65					
HARDNESS DIAMETER	RPM	FEED	ap (mm)	RPM	FEED	ap (mm)	RPM	FEED	ap (mm)	RPM	FEED	ap (mm)
R0.1 x 0.2	50000	11.8-13.8	0.006-0.016	50000	10.4-12.2	0.005-0.013	50000	8.9-10.4	0.005-0.012	50000	17.9-20.9	0.010-0.022
R0.15 x 0.3	48000-50000	18.9-20.5	0.010-0.017	48000-50000	17.3-18.1	0.008-0.014	48000-50000	15.4-16.5	0.007-0.013	48000-50000	27.2-31.1	0.002-0.023
R0.2 x 0.4	48000-50000	28.4-31.1	0.013-0.032	48000-50000	17.7-21.7	0.011-0.026	48000-50000	15.8-18.1	0.010-0.024	48000-50000	39.4-45.3	0.019-0.048
R0.25 x 0.5	34100-49500	23.6-34.3	0.007-0.028	31900-35200	19.3-21.3	0.005-0.023	31900-35200	17.3-18.9	0.005-0.021	49000-50000	39.4-55.1	0.010-0.042
R0.3 x 0.6	28600-40700	23.2-33.5	0.007-0.034	26400-29700	18.9-21.3	0.006-0.028	26400-29700	15.8-18.9	0.006-0.025	42000-50000	43.3-66.9	0.011-0.050
R0.4 x 0.8	22000-30800	25.2-35.0	0.016-0.064	19800-22000	19.3-21.7	0.013-0.052	19800-22000	17.3-19.7	0.012-0.048	31000-50000	43.3-88.6	0.024-0.096
R0.5 x 1.0	17600-24200	23.6-33.5	0.008-0.080	15400-17600	18.5-21.3	0.007-0.065	15400-17600	17.3-19.7	0.006-0.060	24000-49500	43.3-86.6	0.012-0.120
R0.6 x 1.2	14300-18700	23.2-30.7	0.024-0.032	12000-14000	18.9-21.3	0.020-0.026	12000-14000	16.5-18.9	0.018-0.024	28500-38500	58.3-76.8	0.036-0.048
R0.75 x 1.5	11000-14300	22.8-29.9	0.031-0.048	10000-11500	18.9-21.3	0.025-0.039	10000-11500	16.5-18.9	0.023-0.036	17000-28500	43.3-76.8	0.046-0.072
R1.0 x 2.0	8500-11000	23.2-31.5	0.024-0.160	7900-8800	18.5-20.9	0.020-0.130	7900-8800	17.3-18.9	0.018-0.120	12600-24000	43.3-84.7	0.036-0.240
R1.5 x 3.0	5700-8200	28.7-39.4	0.064-0.240	5300-5800	23.2-25.6	0.052-0.195	5300-5800	21.7-24.4	0.048-0.120	11900-17000	72.8-106.3	0.096-0.360
R2.0 x 4.0	4300-6200	26.8-39.0	0.080-0.320	3950-4400	21.7-24.4	0.065-0.026	3850-4400	20.9-22.4	0.060-0.240	6600-12500	49.6-98.4	0.120-0.480




RPM = rev./min.
FEED = inch/min.

CARBIDE, 3 FLUTE BALL NOSE

G8A59 SERIES

MATERIAL	P				H					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HIGH HARDENED STEELS					
	HRC30 ~ HRC45		HRC45 ~ HRC55		HRC55 ~ HRC60		HRC60 ~ HRC65		HRC65 ~ HRC70	
HARDNESS DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
R1.5 x 3.0	32000	338.6	26840	228.4	19840	168.5	18680	159.1	12780	108.7
R2.0 x 4.0	24080	303.2	20130	213.8	14880	152.8	14220	143.7	9580	98.4
R2.5 x 5.0	20000	285.4	16780	213.8	12400	145.3	11670	136.6	8000	93.3
R3.0 x 6.0	18000	337.4	15200	244.9	12200	177.2	11100	150.8	7590	96.9
R4.0 x 8.0	13500	289.4	11300	206.7	9200	156.7	8320	131.9	5690	83.9
R5.0 x 10.0	10800	257.1	9100	180.7	7350	135.8	6660	113.0	4550	77.2
R6.0 x 12.0	9050	240.2	7590	167.7	6130	125.6	5530	94.5	3800	64.6
R8.0 x 16.0	6700	181.1	5690	128.0	4600	97.6	4160	70.9	2850	48.4
R10.0x20.0	5400	141.7	4550	103.2	3670	78.0	3300	56.7	2280	38.6



RPM = rev./min.
FEED = inch/min.





RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE - SLOTTING

G8A36 SERIES

MATERIAL	P						H					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS				HIGH HARDENED STEELS					
	HRc30 ~ HRc40		HRc40 ~ HRc50		HRc50 ~ HRc55		HRc55 ~ HRc60		HRc60 ~ HRc65		HRc65 ~ HRc70	
HARDNESS DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
0.2	50000	5.1	45000	4.5	40000	3.7	33000	2.4	33000	1.8	26400	1.2
0.3	50000	7.5	45000	5.5	40000	4.5	33000	2.8	25000	2.0	20000	1.4
0.4	50000	9.3	45000	7.1	40000	5.5	33000	3.5	25000	2.2	20000	1.6
0.5	50000	14.6	45000	11.0	40000	8.7	33000	5.5	25000	3.4	20000	2.4
0.6	50000	18.5	45000	14.2	40000	11.2	30000	6.3	25000	4.1	20000	3.0
0.8	50000	23.6	40000	17.3	30000	11.6	25000	7.3	19000	4.3	15200	3.2
0.9	49000	25.8	39000	20.5	27800	13.0	22700	8.1	17500	4.9	14000	3.5
1.0	48000	29.5	38000	22.4	25500	14.2	20500	8.5	16000	5.3	12500	3.4
2.0	33300	33.5	26000	26.8	17500	16.5	14500	10.2	11000	6.3	9500	4.5
3.0	21800	33.5	17300	26.8	11500	16.5	9500	10.2	7500	6.3	6400	4.5
4.0	16700	34.7	13200	27.6	8800	17.3	7200	10.6	5600	6.7	4750	4.7
5.0	15700	39.4	12500	31.7	8300	19.7	6400	11.2	5100	7.1	4450	5.2
6.0	13100	37.4	10350	30.3	6900	18.9	5300	11.0	4200	7.1	3700	5.1
8.0	9880	36.6	7800	28.4	5200	17.5	4000	10.0	3200	6.5	2800	4.7
10.0	7800	33.5	6150	26.8	4100	16.3	3200	9.5	2550	6.1	2200	4.4
12.0	6650	33.5	5250	26.8	3500	16.3	2650	9.5	2100	6.1	1860	4.4
16.0	4900	28.7	3900	22.8	2600	14.4	2000	8.3	1600	5.3	1400	3.7
20.0	3900	26.0	3100	20.7	2050	14.4	1600	7.7	1300	4.9	1100	3.4



RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE - SIDE CUTTING

G8A36 SERIES

MATERIAL	P						H					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS				HIGH HARDENED STEELS					
	HRc30 ~ HRc40		HRc40 ~ HRc50		HRc50 ~ HRc55		HRc55 ~ HRc60		HRc60 ~ HRc65		HRc65 ~ HRc70	
HARDNESS DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1.0	48000	41.3	38000	32.3	25500	20.1	20500	12.2	16000	7.5	12500	4.9
2.0	33300	47.2	26000	38.2	17500	23.6	14500	14.6	11000	9.1	9500	6.5
3.0	21800	47.2	17300	38.2	11500	23.6	9500	14.6	7500	9.1	6400	6.5
4.0	16700	49.2	13200	39.4	8800	24.6	7200	15.2	5600	9.5	4750	6.7
5.0	15700	57.1	12500	45.3	8300	28.0	6400	16.1	5100	10.2	4450	7.5
6.0	13100	53.2	10350	43.3	6900	27.2	5300	15.8	4200	10.0	3700	7.3
8.0	9880	52.0	7800	40.6	5200	25.0	4000	14.4	3200	9.3	2800	6.7
10.0	7800	47.2	6150	38.2	4100	23.2	3200	13.4	2550	8.7	2200	6.3
12.0	6650	47.2	5250	38.2	3500	23.2	2650	13.4	2100	8.7	1860	6.3
16.0	4900	41.3	3900	33.1	2600	20.5	2000	11.8	1600	7.5	1400	5.5
20.0	3900	37.4	3100	29.5	2050	18.7	1600	10.8	1300	6.9	1100	4.2



RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE BALL NOSE

G8A38, G8A28, G8A53 SERIES

MATERIAL	P						H					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS				HIGH HARDENED STEEL					
	HRC30 ~ HRC40		HRC40 ~ HRC50		HRC50 ~ HRC55		HRC55 ~ HRC60		HRC60 ~ HRC65		HRC65 ~ HRC70	
HARDNESS DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
R0.1 x0.2	50000	47.2	50000	41.3	45000	37.8	40000	30.3	35000	26.54	31500	22.4
R0.15x0.3	50000	59.1	50000	53.6	45000	47.2	40000	37.9	35000	33.1	31500	27.6
R0.2 x0.4	50000	74.8	50000	66.9	45000	59.1	40000	47.2	35000	41.3	31500	35.0
R0.25x0.5	50000	94.5	50000	82.7	45000	74.8	40000	59.1	35000	51.2	31500	43.3
R0.3 x0.6	50000	114.2	50000	98.4	45000	86.6	40000	70.9	35000	63.0	31500	55.1
R0.4 x0.8	50000	153.5	50000	129.9	45000	118.1	40000	94.5	35000	82.7	31500	70.9
R0.5 x1.0	50000	189.0	50000	165.4	45000	149.6	40000	118.1	35000	102.4	35000	90.6
R0.6 x1.2	50000	200.8	48000	169.3	43000	151.6	38000	118.1	34000	106.3	30600	90.6
R0.75x1.5	50000	212.6	48000	177.2	43000	157.5	37000	122.1	33000	106.3	29700	90.6
R1.0 x2.0	49700	224.4	47800	189.0	40000	157.5	35000	124.0	32000	110.2	28500	90.6
R1.5 x3.0	33100	236.2	31800	208.7	26500	157.5	23500	124.0	21000	110.2	19000	90.6
R2.0 x4.0	24900	236.2	23900	208.7	20000	157.5	17500	124.0	16000	110.2	14500	90.6
R2.5 x5.0	18600	228.4	17800	192.9	15000	147.6	13500	120.1	11500	100.4	10500	82.7
R3.0 x6.0	13900	190.9	13400	161.4	11000	122.1	10000	98.4	8800	84.7	8000	68.9
R4.0 x8.0	11100	165.4	10700	137.8	9000	106.3	8000	84.7	7000	72.8	6500	61.0
R5.0 x10.0	9300	145.7	8900	122.1	7500	94.5	6600	74.8	5800	65.0	5300	54.3
R6.0 x12.0	6950	116.1	6680	98.4	5600	74.8	5000	61.0	4400	49.2	4000	41.3
R8.0 x16.0	5570	104.3	5350	86.6	4500	66.9	4000	53.2	3500	39.4	3200	33.5
R10.0x20.0	4450	92.5	4300	76.8	3600	59.1	3200	47.2	2800	31.5	2550	26.0



RPM = rev./min.
FEED = inch/min.





RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE MINIATURE CORNER RADIUS - SLOTTING

G8A50 SERIES

MATERIAL	P						H			
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS				HIGH HARDENED STEELS			
	HRC30 ~ HRC40		HRC40 ~ HRC50		HRC50 ~ HRC55		HRC55 ~ HRC60		HRC60 ~ HRC65	
HARDNESS DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
0.3	50000	7.5	45000	5.5	40000	4.5	33000	2.8	25000	1.6
0.4	50000	9.3	45000	7.1	40000	5.5	33000	3.5	25000	2.2
0.5	50000	14.6	45000	11.0	40000	8.7	33000	5.5	25000	3.4
0.6	50000	18.5	45000	14.2	40000	11.2	30000	6.3	25000	4.1
0.8	50000	23.6	40000	17.3	30000	11.6	25000	7.3	19000	4.3
1.0	48000	29.5	38000	22.4	25500	14.2	20500	8.5	16000	5.3
1.2	42000	31.1	34000	25.2	22500	15.0	20000	9.8	14500	5.7
1.5	37000	31.0	30500	26.4	21000	16.1	17000	9.8	13000	6.2
2.0	33300	33.5	26000	26.8	17500	16.5	14500	10.2	11000	6.3




RPM = rev./min.
FEED = inch/min.

CARBIDE, 4 FLUTE CORNER RADIUS

G8A47 SERIES

MATERIAL	P						H					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS				HIGH HARDENED STEELS					
	HRC30 ~ HRC40		HRC40 ~ HRC50		HRC50 ~ HRC55		HRC55 ~ HRC60		HRC60 ~ HRC65		HRC65 ~ HRC70	
HARDNESS DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1.0	48000	46.6	38000	33.1	25500	22.4	20500	13.5	16000	8.5	12500	5.5
2.0	33300	55.1	26000	39.4	17500	26.5	14500	16.4	11000	10.1	9500	7.2
3.0	21800	55.1	17300	39.4	11500	26.5	9500	16.4	7500	10.1	6400	7.2
4.0	16700	56.7	13200	40.9	8800	27.7	7200	17.0	5600	10.6	4750	7.6
5.0	15700	63.0	12500	47.2	8300	31.5	6400	18.3	5100	11.7	4450	8.5
6.0	13100	61.4	10350	44.1	6900	29.9	5300	17.6	4200	11.0	3700	8.2
8.0	9880	59.2	7800	42.5	5200	28.4	4000	16.4	3200	10.4	2800	7.6
10.0	7800	55.1	6150	39.7	4100	26.5	3200	15.1	2550	9.8	2200	6.9
12.0	6650	55.1	5250	39.7	3500	26.5	2650	15.1	2100	9.5	1860	6.9
16.0	4900	47.2	3900	34.7	2600	23.0	2000	13.2	1600	8.5	1400	6.3
20.0	3900	40.9	3100	30.6	2050	20.5	1600	12.0	1300	7.9	1100	5.7



RPM = rev./min. FEED = inch/min.

CARBIDE

HSS

CBN
END MILLS

i-Xmill
END MILLS

i-SMART
MODULAR
TYPE END MILLS

X5070
END MILLS

4G MILL
END MILLS

X-POWER
END MILLS

JET-POWER
END MILLS

TitaNox
-POWER
END MILLS

V7 PLUS A
END MILLS

V7 MILL INOX
END MILLS

ALU-POWER
HPC
END MILLS

ALU-POWER
END MILLS

D-POWER
GRAPHITE
END MILLS

D-POWER
CFRP
END MILLS

ROUTERS
CFRP

STANDARD
CARBIDE
END MILLS

ONLY ONE
COATED PM60
END MILLS

SINE -POWER
END MILLS

TANK-POWER
END MILLS

STANDARD
COBALT & HSS
END MILLS

TECHNICAL
DATA


YG X5070 END MILLS

RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE STUB LENGTH CORNER RADIUS with EXTENDED NECK

G8A37 SERIES

MATERIAL	P						H					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS				HIGH HARDENED STEELS					
	HRc30 ~ HRc40		HRc40 ~ HRc50		HRc50 ~ HRc55		HRc55 ~ HRc60		HRc60 ~ HRc65		HRc65 ~ HRc70	
HARDNESS	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
DIAMETER												
1.0	48000	58.3	38000	41.3	25500	28.0	20500	16.9	16000	10.6	12500	6.9
2.0	33300	68.9	26000	49.2	17500	33.1	14500	20.5	11000	12.6	9500	9.1
3.0	21800	68.9	17300	49.2	11500	33.1	9500	20.5	7500	12.6	6400	9.1
4.0	16700	70.9	13200	51.2	8800	34.7	7200	21.3	5600	13.2	4750	9.5
5.0	15700	78.7	12500	59.1	8300	39.4	6400	22.8	5100	14.6	4450	10.6
6.0	13100	76.8	10350	55.1	6900	37.4	5300	22.1	4200	13.8	3700	10.2
8.0	9880	74.0	7800	53.2	5200	35.4	4000	20.5	3200	13.0	2800	9.5
10.0	7800	68.9	6150	49.6	4100	33.1	3200	18.9	2550	12.2	2200	8.7
12.0	6650	68.9	5250	49.6	3500	33.1	2650	18.9	2100	11.8	1860	8.7
16.0	4900	59.1	3900	43.3	2600	28.7	2000	16.5	1600	10.6	1400	7.9
20.0	3900	51.2	3100	38.2	2050	25.6	1600	15.0	1300	9.8	1100	7.1





RPM = rev./min.
FEED = inch/min.

CARBIDE, 6 FLUTE 45° HELIX CORNER RADIUS

G8A39 SERIES

MATERIAL	P						H					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS				HIGH HARDENED STEELS					
	HRc30 ~ HRc40		HRc40 ~ HRc50		HRc50 ~ HRc55		HRc55 ~ HRc60		HRc60 ~ HRc65		HRc65 ~ HRc70	
HARDNESS	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
DIAMETER												
6.0	24800	210.6	23500	192.9	16000	192.9	13500	129.9	10500	82.7	8000	57.1
8.0	20000	216.5	19000	196.9	12000	181.1	10000	122.1	8000	78.7	6000	55.1
10.0	16000	192.9	15500	177.2	9500	161.4	8000	114.2	6400	70.9	4800	51.2
12.0	13000	177.2	12500	161.4	8000	149.6	6600	98.4	5300	63.0	4000	45.3
16.0	10000	157.5	9700	145.7	6000	133.9	5000	90.6	4000	49.2	3000	34.3
20.0	8000	131.9	7800	133.9	4800	126.0	4000	82.7	3200	40.2	2400	27.2



※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.




Being the best through innovation

CARBIDE



4G MILLS



- High Speed Cutting for Pre-Hardened Steels up to HRc55



GMF15 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Unique ball nose geometry with superior cutting edges result in decreased cutting forces.
- ▶ Excellent performance when cutting steels, up to HRc55



R<1/8 R>1/8


Unit : Inch

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	R	D1	D2	L1	L2
GMF15901	R.002	.004	3/16	.008	1-1/2
GMF15902	R.004	.008	3/16	1/64	1-1/2
GMF15903	R.006	.012	3/16	1/32	1-1/2
GMF15904	R.075	.015	3/16	1/32	1-1/2
GMF15905	R.010	.020	3/16	3/64	1-1/2
GMF15906	R.012	.024	3/16	3/64	1-1/2
GMF15907	R.014	.028	3/16	1/16	1-1/2
GMF15908	R.0155	.031	3/16	1/16	1-1/2
GMF15909	R.0175	.035	3/16	5/64	1-1/2
GMF15003	R.0234	3/64	3/16	3/32	2
GMF15910	R.0234	3/64	1/4	3/32	2
GMF15911	R.0234	3/64	1/4	3/32	2-3/4
GMF15004	R1/32	1/16	3/16	5/32	2
GMF15912	R1/32	1/16	1/4	5/32	2
GMF15913	R1/32	1/16	1/4	5/32	2-3/4
GMF15005	R.0391	5/64	1/4	1/8	1-1/2
GMF15914	R.0391	5/64	3/16	3/16	2
GMF15915	R.0391	5/64	1/4	3/16	2
GMF15916	R.0391	5/64	1/4	3/16	3-1/8
GMF15006	R3/64	3/32	1/4	1/4	2-3/8
GMF15917	R3/64	3/32	1/4	1/4	3-1/8
GMF15008	R1/16	1/8	1/4	3/16	1-1/2
GMF15918	R1/16	1/8	3/16	1/4	2-3/8
GMF15919	R1/16	1/8	1/4	1/4	2-3/8
GMF15920	R1/16	1/8	1/4	1/4	3-1/8
GMF15921	R1/16	1/8	1/4	1/4	4
GMF15012	R3/32	3/16	1/4	1/4	2
GMF15922	R3/32	3/16	3/16	5/16	2-3/4
GMF15923	R3/32	3/16	1/4	5/16	2-3/4
GMF15924	R3/32	3/16	3/16	5/16	4
GMF15925	R3/32	3/16	1/4	5/16	4
GMF15926	R3/32	3/16	1/4	5/16	4-1/2
GMF15013	R.102	13/64	1/4	5/16	2-3/8

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



GMF15 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Unique ball nose geometry with superior cutting edges result in decreased cutting forces.
- ▶ Excellent performance when cutting steels, up to HRc55



R<1/8 R>1/8

Unit : Inch

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	R	D1	D2	L1	L2
GMF15927	R.102	13/64	1/4	3/8	3-1/8
GMF15016	R1/8	1/4	1/4	3/8	2
GMF15928	R1/8	1/4	1/4	3/8	3-1/8
GMF15929	R1/8	1/4	1/4	1/2	3-1/2
GMF15930	R1/8	1/4	1/4	1/2	5
GMF15018	R9/64	9/32	5/16	9/16	3-1/2
GMF15020	R5/32	5/16	5/16	1/2	2
GMF15931	R5/32	5/16	5/16	1/2	3-1/2
GMF15932	R5/32	5/16	5/16	9/16	4
GMF15933	R5/32	5/16	5/16	9/16	6
GMF15024	R3/16	3/8	3/8	5/8	2-3/8
GMF15934	R3/16	3/8	3/8	5/8	3-1/2
GMF15935	R3/16	3/8	3/8	11/16	4
GMF15936	R3/16	3/8	3/8	11/16	5
GMF15937	R3/16	3/8	3/8	11/16	6
GMF15938	R3/16	3/8	3/8	11/16	7
GMF15032	R1/4	1/2	1/2	11/16	3-1/8
GMF15939	R1/4	1/2	1/2	11/16	4
GMF15940	R1/4	1/2	1/2	7/8	4-1/4
GMF15941	R1/4	1/2	1/2	7/8	6
GMF15942	R1/4	1/2	1/2	7/8	8
GMF15036	R9/32	9/16	9/16	1	4
GMF15040	R5/16	5/8	5/8	1	4
GMF15943	R5/16	5/8	5/8	1-3/16	6
GMF15048	R3/8	3/4	3/4	1-3/16	4
GMF15944	R3/8	3/4	3/4	1-1/2	6

Size	Radius Tolerance (Inch)	Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
up to Ø1/4	±.0002	0~-0.0005	h6
over Ø1/4	±.0004	0~-0.0006	

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



GMF16 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Unique ball nose geometry with superior cutting edges result in decreased cutting forces.
- ▶ Excellent performance when cutting steels, up to HRC55



EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
GMF16901	R.004	.008	3/16	.008	1/64	1-1/2	.006
GMF16902	R.004	.008	3/16	.008	3/64	1-1/2	.006
GMF16903	R.006	.012	3/16	.010	3/64	1-1/2	.010
GMF16904	R.006	.012	3/16	.010	5/64	1-1/2	.010
GMF16905	R.006	.012	3/16	.010	1/8	1-1/2	.010
GMF16906	R.0075	.015	3/16	1/64	3/64	1-1/2	.013
GMF16907	R.0075	.015	3/16	1/64	5/64	1-1/2	.013
GMF16908	R.0075	.015	3/16	1/64	1/8	1-1/2	.013
GMF16909	R.0075	.015	3/16	1/64	5/32	1-1/2	.013
GMF16910	R.010	.020	3/16	1/64	3/64	1-3/4	.018
GMF16911	R.010	.020	3/16	1/64	5/64	1-3/4	.018
GMF16912	R.010	.020	3/16	1/64	1/8	1-3/4	.018
GMF16913	R.010	.020	3/16	1/64	5/32	1-3/4	.018
GMF16914	R.010	.020	3/16	1/64	3/16	1-3/4	.018
GMF16915	R.010	.020	3/16	1/64	1/4	1-3/4	.018
GMF16916	R.010	.020	3/16	1/64	5/16	1-3/4	.018
GMF16917	R.010	.020	3/16	1/64	3/8	1-3/4	.018
GMF16918	R.012	.024	3/16	1/32	5/64	1-3/4	.022
GMF16919	R.012	.024	3/16	1/32	1/8	1-3/4	.022
GMF16920	R.012	.024	3/16	1/32	5/32	1-3/4	.022
GMF16921	R.012	.024	3/16	1/32	3/16	1-3/4	.022
GMF16922	R.012	.024	3/16	1/32	1/4	1-3/4	.022
GMF16923	R.012	.024	3/16	1/32	5/16	1-3/4	.022
GMF16924	R.012	.024	3/16	1/32	3/8	1-3/4	.022
GMF16925	R.012	.024	3/16	1/32	1/2	1-3/4	.022
GMF16002	R1/64	1/32	3/16	1/32	5/64	1-3/4	.029
GMF16926	R1/64	1/32	3/16	1/32	1/8	1-3/4	.029
GMF16927	R1/64	1/32	3/16	1/32	5/32	1-3/4	.029
GMF16928	R1/64	1/32	3/16	1/32	3/16	1-3/4	.029
GMF16929	R1/64	1/32	3/16	1/32	1/4	1-3/4	.029
GMF16930	R1/64	1/32	3/16	1/32	5/16	1-3/4	.029
GMF16931	R1/64	1/32	3/16	1/32	3/8	1-3/4	.029

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45	HRC45~55	HRC55~70								
○	◎	◎	◎	○		○							



GMF16 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Unique ball nose geometry with superior cutting edges result in decreased cutting forces.
- ▶ Excellent performance when cutting steels, up to HRC55



EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
GMF16003	R.0234	3/64	3/16	3/64	1/8	2	.044
GMF16932	R.0234	3/64	3/16	3/64	5/32	2	.044
GMF16933	R.0234	3/64	3/16	3/64	3/16	2	.044
GMF16934	R.0234	3/64	3/16	3/64	1/4	2	.044
GMF16935	R.0234	3/64	3/16	3/64	5/16	2	.044
GMF16936	R.0234	3/64	3/16	3/64	3/8	2	.044
GMF16937	R.0234	3/64	3/16	3/64	1/2	2	.044
GMF16938	R.0234	3/64	3/16	3/64	9/16	2	.044
GMF16939	R.0234	3/64	3/16	3/64	5/8	2	.044
GMF16940	R.0234	3/64	3/16	3/64	3/4	2	.044
GMF16004	R1/32	1/16	3/16	1/16	5/32	2	.060
GMF16941	R1/32	1/16	3/16	1/16	1/4	2	.060
GMF16942	R1/32	1/16	3/16	1/16	5/16	2	.060
GMF16943	R1/32	1/16	3/16	1/16	3/8	2	.060
GMF16944	R1/32	1/16	3/16	1/16	1/2	2	.060
GMF16945	R1/32	1/16	3/16	1/16	9/16	2	.060
GMF16946	R1/32	1/16	3/16	1/16	5/8	2	.060
GMF16947	R1/32	1/16	3/16	1/16	3/4	2	.060
GMF16005	R.0391	5/64	3/16	5/64	1/4	2	.076
GMF16948	R.0391	5/64	3/16	5/64	5/16	2	.076
GMF16949	R.0391	5/64	3/16	5/64	3/8	2	.076
GMF16950	R.0391	5/64	3/16	5/64	1/2	2	.076
GMF16951	R.0391	5/64	3/16	5/64	9/16	2	.076
GMF16952	R.0391	5/64	3/16	5/64	5/8	2	.076
GMF16953	R.0391	5/64	3/16	5/64	11/16	2	.076
GMF16954	R.0391	5/64	3/16	5/64	3/4	2	.076
GMF16955	R.0391	5/64	3/16	5/64	1	2-3/8	.076
GMF16956	R.0391	5/64	3/16	5/64	1-3/16	2-3/4	.076
GMF16006	R3/64	3/32	3/16	3/32	3/8	2	.089
GMF16957	R3/64	3/32	3/16	3/32	3/4	2	.089
GMF16008	R1/16	1/8	1/4	1/8	5/16	2	.119
GMF16958	R1/16	1/8	1/4	1/8	3/8	2	.119

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45	HRC45~55	HRC55~70								
○	◎	◎	◎	○		○							



GMF16 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Unique ball nose geometry with superior cutting edges result in decreased cutting forces.
- ▶ Excellent performance when cutting steels, up to HRc55




NG 2 30° ±.0002 ±.0004 PLAIN P.796~798 R<1/8 R>1/8

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
GMF16959	R1/16	1/8	1/4	1/8	1/2	2	.119
GMF16960	R1/16	1/8	1/4	1/8	9/16	2-3/8	.119
GMF16961	R1/16	1/8	1/4	1/8	5/8	2-3/8	.119
GMF16962	R1/16	1/8	1/4	1/8	11/16	2-3/8	.119
GMF16963	R1/16	1/8	1/4	1/8	3/4	2-3/8	.119
GMF16964	R1/16	1/8	1/4	1/8	1	2-3/4	.119
GMF16965	R1/16	1/8	1/4	1/8	1-3/16	2-3/4	.119
GMF16966	R1/16	1/8	1/4	1/8	1-3/8	2-3/4	.119
GMF16012	R3/32	3/16	1/4	5/32	3/8	2	.181
GMF16967	R3/32	3/16	1/4	5/32	1/2	2	.181
GMF16968	R3/32	3/16	1/4	5/32	9/16	2-3/8	.181
GMF16969	R3/32	3/16	1/4	5/32	5/8	2-3/8	.181
GMF16970	R3/32	3/16	1/4	5/32	11/16	2-3/8	.181
GMF16971	R3/32	3/16	1/4	5/32	3/4	2-3/8	.181
GMF16972	R3/32	3/16	1/4	5/32	1	2-3/4	.181
GMF16973	R3/32	3/16	1/4	5/32	1-3/16	2-3/4	.181
GMF16974	R3/32	3/16	1/4	5/32	1-3/8	2-3/4	.181
GMF16975	R3/32	3/16	1/4	5/32	1-1/2	3-1/8	.181
GMF16013	R.102	13/64	1/4	1/4	1-3/16	2-3/4	.197
GMF16016	R1/8	1/4	1/4	5/16	3/4	2-3/8	.244
GMF16976	R1/8	1/4	1/4	5/16	1-3/16	2-3/8	.244
GMF16020	R5/32	5/16	5/16	3/8	1	2-3/4	.300
GMF16977	R5/32	5/16	5/16	9/16	1-3/8	4	.300
GMF16024	R3/16	3/8	3/8	1/2	1-3/16	3	.363
GMF16978	R3/16	3/8	3/8	11/16	1-3/16	4	.363
GMF16979	R3/16	3/8	3/8	11/16	1-1/2	4	.363
GMF16032	R1/4	1/2	1/2	9/16	1-1/4	3-1/8	.488
GMF16980	R1/4	1/2	1/2	7/8	1-1/4	4-1/4	.488

Size	Radius Tolerance (Inch)	Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
up to Ø1/4	±.0002	0~- .0005	h6
over Ø1/4	±.0004	0~- .0006	

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



GMF17 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE BALL NOSE

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Unique ball nose geometry with superior cutting edges result in decreased cutting forces.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Cutting edge strength is increased and part finish is improved due to new End Geometry




NG 4 30° ±.0002 ±.0004 PLAIN P.798 R1/8 R>1/8

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	R	D1	D2	L1	L2
GMF17008	R1/16	1/8	1/4	1/8	2-3/8
GMF17012	R3/32	3/16	1/4	5/32	2-3/4
GMF17016	R1/8	1/4	1/4	1/4	3-1/2
GMF17020	R5/32	5/16	5/16	5/16	4
GMF17024	R3/16	3/8	3/8	3/8	4
GMF17032	R1/4	1/2	1/2	1/2	4-1/4

Size	Radius Tolerance (Inch)	Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
up to Ø1/4	±.0002	0~- .0008	h6
over Ø1/4	±.0004		

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



GMF18 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE CORNER RADIUS

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Available in various length shanks and corner radiuses.



D₁ ≤ 1/4 D₂ > 1/4


Unit : Inch

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	R	D ₁	D ₂	L ₁	L ₂
GMF18003	R.008	3/64	1/4	3/32	2
GMF18901	R.012	3/64	1/4	3/32	2
GMF18004	R.008	1/16	1/4	5/32	2
GMF18902	R.012	1/16	1/4	5/32	2
GMF18903	R.020	1/16	1/4	5/32	2
GMF18005	R.008	5/64	1/4	1/4	2
GMF18904	R.012	5/64	1/4	1/4	2
GMF18905	R.020	5/64	1/4	1/4	2
GMF18008	R.008	1/8	1/4	5/16	2-3/8
GMF18906	R.012	1/8	1/4	5/16	2-3/8
GMF18907	R.020	1/8	1/4	5/16	2-3/8
GMF18940	R.030	1/8	1/4	5/16	2-3/8
GMF18009	R.008	9/64	1/4	3/8	2-3/4
GMF18908	R.012	9/64	1/4	3/8	2-3/4
GMF18909	R.020	9/64	1/4	3/8	2-3/4
GMF18941	R.030	9/64	1/4	3/8	2-3/4
GMF18910	R.040	9/64	1/4	3/8	2-3/4
GMF18013	R.008	13/64	1/4	1/2	3-1/2
GMF18911	R.012	13/64	1/4	1/2	3-1/2
GMF18912	R.020	13/64	1/4	1/2	3-1/2
GMF18942	R.030	13/64	1/4	1/2	3-1/2
GMF18913	R.040	13/64	1/4	1/2	3-1/2
GMF18016	R.008	1/4	1/4	5/8	2-3/8
GMF18914	R.012	1/4	1/4	5/8	2-3/8
GMF18915	R.020	1/4	1/4	5/8	2-3/8
GMF18943	R.030	1/4	1/4	5/8	2-3/8
GMF18916	R.040	1/4	1/4	5/8	2-3/8
GMF18917	R.008	1/4	1/4	5/8	3-1/2
GMF18918	R.012	1/4	1/4	5/8	3-1/2

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF18 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE CORNER RADIUS

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Available in various length shanks and corner radiuses.



D₁ ≤ 1/4 D₂ > 1/4

Unit : Inch

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	R	D ₁	D ₂	L ₁	L ₂
GMF18919	R.020	1/4	1/4	5/8	3-1/2
GMF18944	R.030	1/4	1/4	5/8	3-1/2
GMF18920	R.040	1/4	1/4	5/8	3-1/2
GMF18020	R.020	5/16	5/16	3/4	2-3/4
GMF18945	R.030	5/16	5/16	3/4	2-3/4
GMF18921	R.040	5/16	5/16	3/4	2-3/4
GMF18922	R.020	5/16	5/16	3/4	4
GMF18946	R.030	5/16	5/16	3/4	4
GMF18923	R.040	5/16	5/16	3/4	4
GMF18924	R.060	5/16	5/16	3/4	4
GMF18925	R.080	5/16	5/16	3/4	4
GMF18024	R.020	3/8	3/8	1	3
GMF18947	R.030	3/8	3/8	1	3
GMF18926	R.040	3/8	3/8	1	3
GMF18927	R.020	3/8	3/8	1	4
GMF18948	R.030	3/8	3/8	1	4
GMF18928	R.040	3/8	3/8	1	4
GMF18929	R.060	3/8	3/8	1	4
GMF18930	R.080	3/8	3/8	1	4
GMF18032	R.020	1/2	1/2	1-3/16	3-1/8
GMF18949	R.030	1/2	1/2	1-3/16	3-1/8
GMF18931	R.040	1/2	1/2	1-3/16	3-1/8
GMF18932	R.020	1/2	1/2	1-3/16	4-1/4
GMF18950	R.030	1/2	1/2	1-3/16	4-1/4
GMF18933	R.040	1/2	1/2	1-3/16	4-1/4
GMF18934	R.060	1/2	1/2	1-3/16	4-1/4
GMF18935	R.080	1/2	1/2	1-3/16	4-1/4
GMF18936	R.100	1/2	1/2	1-3/16	4-1/4
GMF18937	R.118	1/2	1/2	1-3/16	4-1/4

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF18 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE CORNER RADIUS

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Available in various length shanks and corner radiuses.



MG 2 30° ±.0004 ±.0006 PLAIN P.799

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	R	D1	D2	L1	L2
GMF18951	R.030	9/16	5/8	1-3/8	6
GMF18036	R.040	9/16	5/8	1-3/8	6
GMF18952	R.030	5/8	5/8	1-1/4	6
GMF18040	R.040	5/8	5/8	1-1/4	6
GMF18938	R.080	5/8	5/8	1-1/4	6
GMF18953	R.030	3/4	3/4	1-1/2	6
GMF18048	R.040	3/4	3/4	1-1/2	6
GMF18939	R.080	3/4	3/4	1-1/2	6

Size	Radius Tolerance (Inch)	Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
up to Ø1/4	±.0004	0--.0005	h6
over Ø1/4	±.0006	0--.0006	

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF19 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE CORNER RADIUS WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Available in many more various length shanks and corner radiuses.




MG 2 30° ±.0004 ±.0006 PLAIN P.800~801

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
GMF19901	R.001	.008	3/16	.010	3/64	1-1/2	.006
GMF19902	R.002	.008	3/16	.010	3/64	1-1/2	.006
GMF19903	R.001	.012	3/16	1/64	3/64	1-1/2	.010
GMF19904	R.001	.012	3/16	1/64	5/64	1-1/2	.010
GMF19905	R.002	.012	3/16	1/64	3/64	1-1/2	.010
GMF19906	R.002	.012	3/16	1/64	5/64	1-1/2	.010
GMF19907	R.002	.015	3/16	1/32	3/64	1-1/2	.013
GMF19908	R.002	.015	3/16	1/32	1/16	1-1/2	.013
GMF19909	R.002	.015	3/16	1/32	5/64	1-1/2	.013
GMF19910	R.002	.015	3/16	1/32	3/32	1-1/2	.013
GMF19911	R.004	.015	3/16	1/32	3/64	1-1/2	.013
GMF19912	R.004	.015	3/16	1/32	5/64	1-1/2	.013
GMF19913	R.002	.020	3/16	1/32	3/64	1-3/4	.018
GMF19914	R.002	.020	3/16	1/32	1/16	1-3/4	.018
GMF19915	R.002	.020	3/16	1/32	5/64	1-3/4	.018
GMF19916	R.002	.020	3/16	1/32	5/32	1-3/4	.018
GMF19917	R.004	.020	3/16	1/32	5/64	1-3/4	.018
GMF19918	R.004	.020	3/16	1/32	1/8	1-3/4	.018
GMF19919	R.002	.024	3/16	1/32	1/8	1-3/4	.022
GMF19920	R.002	.024	3/16	1/32	1/4	1-3/4	.022
GMF19921	R.004	.024	3/16	1/32	5/64	1-3/4	.022
GMF19922	R.004	.024	3/16	1/32	5/32	1-3/4	.022
GMF19923	R.004	.024	3/16	1/32	1/4	1-3/4	.022
GMF19924	R.008	.024	3/16	1/32	5/64	1-3/4	.022
GMF19925	R.008	.024	3/16	1/32	5/32	1-3/4	.022
GMF19926	R.008	.024	3/16	1/32	1/4	1-3/4	.022
GMF19927	R.002	.031	3/16	3/64	5/64	1-3/4	.029
GMF19928	R.002	.031	3/16	3/64	5/32	1-3/4	.029
GMF19929	R.002	.031	3/16	3/64	1/4	1-3/4	.029
GMF19930	R.004	.031	3/16	3/64	5/64	1-3/4	.029
GMF19931	R.004	.031	3/16	3/64	5/32	1-3/4	.029

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF19 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE CORNER RADIUS WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Available in many more various length shanks and corner radiuses.




MG 2 30° ±.0004 ±.0006 PLAIN P.800~801

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
GMF19932	R.004	.031	3/16	3/64	1/4	1-3/4	.029
GMF19933	R.004	.031	3/16	3/64	5/16	1-3/4	.029
GMF19934	R.008	.031	3/16	3/64	5/32	1-3/4	.029
GMF19935	R.008	.031	3/16	3/64	1/4	1-3/4	.029
GMF19936	R.008	.031	3/16	3/64	5/16	1-3/4	.029
GMF19003	R.002	3/64	3/16	1/16	1/8	2	.044
GMF19937	R.002	3/64	3/16	1/16	5/32	2	.044
GMF19938	R.002	3/64	3/16	1/16	1/4	2	.044
GMF19939	R.004	3/64	3/16	1/16	1/8	2	.044
GMF19940	R.004	3/64	3/16	1/16	5/32	2	.044
GMF19941	R.004	3/64	3/16	1/16	1/4	2	.044
GMF19942	R.004	3/64	3/16	1/16	5/16	2	.044
GMF19943	R.004	3/64	3/16	1/16	3/8	2	.044
GMF19944	R.008	3/64	3/16	1/16	1/8	2	.044
GMF19945	R.008	3/64	3/16	1/16	5/32	2	.044
GMF19946	R.008	3/64	3/16	1/16	1/4	2	.044
GMF19947	R.008	3/64	3/16	1/16	5/16	2	.044
GMF19948	R.008	3/64	3/16	1/16	3/8	2	.044
GMF19949	R.012	3/64	3/16	1/16	5/32	2	.044
GMF19950	R.012	3/64	3/16	1/16	1/4	2	.044
GMF19951	R.012	3/64	3/16	1/16	5/16	2	.044
GMF19952	R.012	3/64	3/16	1/16	3/8	2	.044
GMF19004	R.002	1/16	3/16	3/32	5/32	2	.060
GMF19953	R.002	1/16	3/16	3/32	1/4	2	.060
GMF19954	R.002	1/16	3/16	3/32	5/16	2	.060
GMF19955	R.004	1/16	3/16	3/32	5/32	2	.060
GMF19956	R.004	1/16	3/16	3/32	1/4	2	.060
GMF19957	R.004	1/16	3/16	3/32	5/16	2	.060
GMF19958	R.008	1/16	3/16	3/32	5/32	2	.060
GMF19959	R.008	1/16	3/16	3/32	1/4	2	.060
GMF19960	R.008	1/16	3/16	3/32	5/16	2	.060

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF19 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE CORNER RADIUS WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Available in many more various length shanks and corner radiuses.



MG 2 30° ±.0004 ±.0006 PLAIN P.800~801

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
GMF19961	R.008	1/16	3/16	3/32	3/8	2	.060
GMF19962	R.008	1/16	3/16	3/32	1/2	2	.060
GMF19963	R.012	1/16	3/16	3/32	5/32	2	.060
GMF19964	R.012	1/16	3/16	3/32	1/4	2	.060
GMF19965	R.012	1/16	3/16	3/32	5/16	2	.060
GMF19966	R.012	1/16	3/16	3/32	3/8	2	.060
GMF19967	R.012	1/16	3/16	3/32	1/2	2	.060
GMF19005	R.004	5/64	3/16	1/8	1/4	2	.076
GMF19968	R.004	5/64	3/16	1/8	5/16	2	.076
GMF19969	R.004	5/64	3/16	1/8	3/8	2	.076
GMF19970	R.004	5/64	3/16	1/8	1/2	2	.076
GMF19971	R.008	5/64	3/16	1/8	1/4	2	.076
GMF19972	R.008	5/64	3/16	1/8	5/16	2	.076
GMF19973	R.008	5/64	3/16	1/8	3/8	2	.076
GMF19974	R.008	5/64	3/16	1/8	1/2	2	.076
GMF19975	R.008	5/64	3/16	1/8	5/8	2	.076
GMF19976	R.012	5/64	3/16	1/8	1/4	2	.076
GMF19977	R.012	5/64	3/16	1/8	5/16	2	.076
GMF19978	R.012	5/64	3/16	1/8	3/8	2	.076
GMF19979	R.012	5/64	3/16	1/8	1/2	2	.076
GMF19980	R.012	5/64	3/16	1/8	5/8	2	.076
GMF19981	R.020	5/64	3/16	1/8	1/4	2	.076
GMF19982	R.020	5/64	3/16	1/8	5/16	2	.076
GMF19983	R.020	5/64	3/16	1/8	3/8	2	.076
GMF19984	R.020	5/64	3/16	1/8	1/2	2	.076
GMF19985	R.020	5/64	3/16	1/8	9/16	2	.076
GMF19008	R.004	1/8	1/4	3/16	3/8	2	.119
GMF19986	R.004	1/8	1/4	3/16	1/2	2	.119
GMF19987	R.004	1/8	1/4	3/16	5/8	2-3/8	.119
GMF19988	R.008	1/8	1/4	3/16	5/16	2	.119
GMF19989	R.008	1/8	1/4	3/16	3/8	2	.119

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF19 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE CORNER RADIUS WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Available in many more various length shanks and corner radii.




MG 2 30° ±.0004 ±.0006 PLAIN P.800~801

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
GMF19990	R.008	1/8	1/4	3/16	1/2	2	.119
GMF19991	R.008	1/8	1/4	3/16	5/8	2-3/8	.119
GMF19992	R.008	1/8	1/4	3/16	3/4	2-3/8	.119
GMF19993	R.008	1/8	1/4	3/16	1	2-3/4	.119
GMF19994	R.012	1/8	1/4	3/16	5/16	2	.119
GMF19995	R.012	1/8	1/4	3/16	3/8	2	.119
GMF19996	R.012	1/8	1/4	3/16	1/2	2	.119
GMF19997	R.012	1/8	1/4	3/16	5/8	2-3/8	.119
GMF19998	R.012	1/8	1/4	3/16	3/4	2-3/8	.119
GMF19999	R.020	1/8	1/4	3/16	5/16	2	.119
GMF19801	R.020	1/8	1/4	3/16	3/8	2	.119
GMF19802	R.020	1/8	1/4	3/16	1/2	2	.119
GMF19803	R.020	1/8	1/4	3/16	5/8	2-3/8	.119
GMF19804	R.020	1/8	1/4	3/16	3/4	2-3/8	.119
GMF19805	R.020	1/8	1/4	3/16	1	2-3/4	.119
GMF19845	R.030	1/8	1/4	3/16	3/8	2	.119
GMF19846	R.030	1/8	1/4	3/16	1/2	2	.119
GMF19847	R.030	1/8	1/4	3/16	5/16	2	.119
GMF19848	R.030	1/8	1/4	3/16	3/4	2-3/8	.119
GMF19849	R.030	1/8	1/4	3/16	5/8	2-3/8	.119
GMF19850	R.030	1/8	1/4	3/16	1	2-3/4	.119
GMF19806	R.040	1/8	1/4	3/16	5/16	2	.119
GMF19807	R.040	1/8	1/4	3/16	3/8	2	.119
GMF19808	R.040	1/8	1/4	3/16	1/2	2	.119
GMF19809	R.040	1/8	1/4	3/16	5/8	2-3/8	.119
GMF19810	R.040	1/8	1/4	3/16	3/4	2-3/8	.119
GMF19012	R.004	3/16	1/4	1/4	3/8	2	.181
GMF19811	R.004	3/16	1/4	1/4	1/2	2	.181
GMF19812	R.004	3/16	1/4	1/4	5/8	2-3/8	.181
GMF19813	R.008	3/16	1/4	1/4	3/8	2	.181
GMF19814	R.008	3/16	1/4	1/4	1/2	2	.181

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF19 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE CORNER RADIUS WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Available in many more various length shanks and corner radii.



MG 2 30° ±.0004 ±.0006 PLAIN P.800~801

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
GMF19815	R.008	3/16	1/4	1/4	5/8	2-3/8	.181
GMF19816	R.008	3/16	1/4	1/4	3/4	2-3/8	.181
GMF19817	R.008	3/16	1/4	1/4	1	2-3/4	.181
GMF19818	R.012	3/16	1/4	1/4	1/2	2	.181
GMF19819	R.012	3/16	1/4	1/4	5/8	2-3/8	.181
GMF19820	R.012	3/16	1/4	1/4	3/4	2-3/8	.181
GMF19821	R.012	3/16	1/4	1/4	1	2-3/4	.181
GMF19822	R.020	3/16	1/4	1/4	3/8	2	.181
GMF19823	R.020	3/16	1/4	1/4	1/2	2	.181
GMF19824	R.020	3/16	1/4	1/4	5/8	2-3/8	.181
GMF19825	R.020	3/16	1/4	1/4	3/4	2-3/8	.181
GMF19826	R.020	3/16	1/4	1/4	1	2-3/4	.181
GMF19827	R.020	3/16	1/4	1/4	1-3/16	2-3/4	.181
GMF19851	R.030	3/16	1/4	1/4	3/8	2	.181
GMF19852	R.030	3/16	1/4	1/4	1/2	2	.181
GMF19853	R.030	3/16	1/4	1/4	5/8	2-3/8	.181
GMF19854	R.030	3/16	1/4	1/4	3/4	2-3/8	.181
GMF19855	R.030	3/16	1/4	1/4	1	2-3/4	.181
GMF19856	R.030	3/16	1/4	1/4	1-3/16	2-3/4	.181
GMF19828	R.040	3/16	1/4	1/4	3/8	2	.181
GMF19829	R.040	3/16	1/4	1/4	1/2	2	.181
GMF19830	R.040	3/16	1/4	1/4	5/8	2-3/8	.181
GMF19831	R.040	3/16	1/4	1/4	3/4	2-3/8	.181
GMF19016	R.008	1/4	1/4	3/8	3/4	2-3/8	.244
GMF19832	R.012	1/4	1/4	3/8	3/4	2-3/8	.244
GMF19833	R.020	1/4	1/4	3/8	3/4	2-3/8	.244
GMF19834	R.040	1/4	1/4	3/8	3/4	2-3/8	.244
GMF19835	R.020	1/4	1/4	5/8	1-3/16	3-1/2	.244
GMF19857	R.030	1/4	1/4	3/8	3/4	2-3/8	.244
GMF19858	R.030	1/4	1/4	5/8	1-3/16	3-1/2	.244
GMF19020	R.008	5/16	5/16	1/2	1	2-3/4	.300

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF19 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE CORNER RADIUS WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Available in many more various length shanks and corner radiuses.




MG 2 30° ±.0004 ±.0006 PLAIN P.800~801

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
GMF19836	R.012	5/16	5/16	1/2	1	2-3/4	.300
GMF19837	R.020	5/16	5/16	1/2	1	2-3/4	.300
GMF19859	R.030	5/16	5/16	1/2	1	2-3/4	.300
GMF19838	R.040	5/16	5/16	1/2	1	2-3/4	.300
GMF19024	R.012	3/8	3/8	5/8	1-3/16	3	.363
GMF19839	R.020	3/8	3/8	5/8	1-3/16	3	.363
GMF19860	R.030	3/8	3/8	5/8	1-3/16	3	.363
GMF19840	R.040	3/8	3/8	5/8	1-3/16	3	.363
GMF19032	R.020	1/2	1/2	11/16	1-1/4	3-1/8	.488
GMF19861	R.030	1/2	1/2	11/16	1-1/4	3-1/8	.488
GMF19841	R.040	1/2	1/2	11/16	1-1/4	3-1/8	.488
GMF19842	R.060	1/2	1/2	11/16	1-1/4	3-1/8	.488
GMF19040	R.020	5/8	5/8	3/4	1-3/8	4	.613
GMF19862	R.030	5/8	5/8	3/4	1-3/8	4	.613
GMF19843	R.040	5/8	5/8	3/4	1-3/8	4	.613
GMF19048	R.020	3/4	3/4	1	1-1/2	4	.738
GMF19863	R.030	3/4	3/4	1	1-1/2	4	.738
GMF19844	R.040	3/4	3/4	1	1-1/2	4	.738

Size	Radius Tolerance (Inch)	Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
up to Ø1/4	±.0004	0~-.0005	h6
over Ø1/4	±.0006	0~-.0006	

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF20 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE CORNER RADIUS

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Available in many more various length shanks and corner radiuses.
- ▶ Due to Multiple Helix on 1/8" and over diameter end mills, vibration is minimized and tool life increased.
- ▶ 4 flute series has new designs to reduce vibrations



MG 4 27°/30° ±.0008 PLAIN P.801

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	R	D1	D2	L1	L2
GMF20003	R.004	3/64	1/4	3/32	2
GMF20005	R.004	5/64	1/4	1/4	2
GMF20901	R.008	5/64	1/4	1/4	2
GMF20008	R.008	1/8	1/4	5/16	2-3/8
GMF20902	R.012	1/8	1/4	5/16	2-3/8
GMF20903	R.020	1/8	1/4	5/16	2-3/8
GMF20933	R.030	1/8	1/4	5/16	2-3/8
GMF20012	R.008	3/16	1/4	3/8	2-3/4
GMF20904	R.012	3/16	1/4	3/8	2-3/4
GMF20905	R.020	3/16	1/4	3/8	2-3/4
GMF20934	R.030	3/16	1/4	3/8	2-3/4
GMF20906	R.040	3/16	1/4	3/8	2-3/4
GMF20013	R.012	13/64	1/4	1/2	3-1/2
GMF20907	R.020	13/64	1/4	1/2	3-1/2
GMF20935	R.030	13/64	1/4	1/2	3-1/2
GMF20016	R.008	1/4	1/4	5/8	3-1/2
GMF20908	R.012	1/4	1/4	5/8	3-1/2
GMF20909	R.020	1/4	1/4	5/8	3-1/2
GMF20936	R.030	1/4	1/4	5/8	3-1/2
GMF20910	R.040	1/4	1/4	5/8	3-1/2
GMF20020	R.012	5/16	5/16	3/4	2-3/4
GMF20911	R.020	5/16	5/16	3/4	2-3/4
GMF20937	R.030	5/16	5/16	3/4	2-3/4
GMF20912	R.040	5/16	5/16	3/4	2-3/4
GMF20913	R.008	5/16	5/16	3/4	4
GMF20914	R.012	5/16	5/16	3/4	4
GMF20915	R.020	5/16	5/16	3/4	4
GMF20938	R.030	5/16	5/16	3/4	4
GMF20916	R.040	5/16	5/16	3/4	4
GMF20917	R.060	5/16	5/16	3/4	4
GMF20918	R.080	5/16	5/16	3/4	4

▶ NEXT PAGE ◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF20 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE CORNER RADIUS

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Available in many more various length shanks and corner radii.
- ▶ Due to Multiple Helix on 1/8" and over diameter end mills, vibration is minimized and tool life increased.
- ▶ 4 flute series has new designs to reduce vibrations



MG 4 27°/30° ±.0008 PLAIN P.801

D1≤ 0.125, 30° Helix Unit : Inch

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	R	D1	D2	L1	L2
GMF20024	R.020	3/8	3/8	1	3
GMF20939	R.030	3/8	3/8	1	3
GMF20919	R.012	3/8	3/8	1	4
GMF20920	R.020	3/8	3/8	1	4
GMF20940	R.030	3/8	3/8	1	4
GMF20921	R.040	3/8	3/8	1	4
GMF20922	R.060	3/8	3/8	1	4
GMF20923	R.080	3/8	3/8	1	4
GMF20032	R.020	1/2	1/2	1-3/16	3-1/8
GMF20924	R.040	1/2	1/2	1-3/16	3-1/8
GMF20925	R.020	1/2	1/2	1-3/16	4-1/4
GMF20941	R.030	1/2	1/2	1-3/16	3-1/8
GMF20942	R.030	1/2	1/2	1-3/16	4-1/4
GMF20926	R.040	1/2	1/2	1-3/16	4-1/4
GMF20927	R.060	1/2	1/2	1-3/16	4-1/4
GMF20928	R.080	1/2	1/2	1-3/16	4-1/4
GMF20040	R.020	5/8	5/8	1-1/4	6
GMF20943	R.030	5/8	5/8	1-1/4	6
GMF20929	R.040	5/8	5/8	1-1/4	6
GMF20930	R.060	5/8	5/8	1-1/4	6
GMF20931	R.080	5/8	5/8	1-1/4	6
GMF20944	R.030	3/4	3/4	1-1/2	6
GMF20048	R.040	3/4	3/4	1-1/2	6
GMF20932	R.080	3/4	3/4	1-1/2	6

Mill Dia. Tolerance (Inch)	Corner Radius Tolerance (Inch)	Shank Dia. Tolerance
0--.0012	±.0008	h6

© : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF21 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE CORNER RADIUS WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Due to Multiple Helix on 1/8" and over diameter end mills, vibration is minimized and tool life increased.
- ▶ 4 flute series has new designs to reduce vibrations




MG 4 27°/30° ±.0008 PLAIN P.802

D1≤ 0.125, 30° Helix Unit : Inch

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
GMF21003	R.004	3/64	3/16	1/16	5/32	2	.044
GMF21901	R.004	3/64	3/16	1/16	1/4	2	.044
GMF21902	R.004	3/64	3/16	1/16	5/16	2	.044
GMF21903	R.008	3/64	3/16	1/16	5/32	2	.044
GMF21904	R.008	3/64	3/16	1/16	1/4	2	.044
GMF21905	R.008	3/64	3/16	1/16	5/16	2	.044
GMF21906	R.012	3/64	3/16	1/16	5/32	2	.044
GMF21907	R.012	3/64	3/16	1/16	1/4	2	.044
GMF21908	R.012	3/64	3/16	1/16	5/16	2	.044
GMF21004	R.004	1/16	3/16	3/32	1/4	2	.060
GMF21909	R.004	1/16	3/16	3/32	5/16	2	.060
GMF21910	R.004	1/16	3/16	3/32	3/8	2	.060
GMF21911	R.004	1/16	3/16	3/32	1/2	2	.060
GMF21912	R.008	1/16	3/16	3/32	1/4	2	.060
GMF21913	R.008	1/16	3/16	3/32	5/16	2	.060
GMF21914	R.008	1/16	3/16	3/32	3/8	2	.060
GMF21915	R.008	1/16	3/16	3/32	1/2	2	.060
GMF21916	R.012	1/16	3/16	3/32	1/4	2	.060
GMF21917	R.012	1/16	3/16	3/32	5/16	2	.060
GMF21918	R.012	1/16	3/16	3/32	3/8	2	.060
GMF21919	R.012	1/16	3/16	3/32	1/2	2	.060
GMF21920	R.020	1/16	3/16	3/32	1/4	2	.060
GMF21921	R.020	1/16	3/16	3/32	5/16	2	.060
GMF21922	R.020	1/16	3/16	3/32	3/8	2	.060
GMF21923	R.020	1/16	3/16	3/32	1/2	2	.060
GMF21005	R.004	5/64	3/16	1/8	1/4	2	.076
GMF21924	R.004	5/64	3/16	1/8	5/16	2	.076
GMF21925	R.004	5/64	3/16	1/8	3/8	2	.076
GMF21926	R.004	5/64	3/16	1/8	1/2	2	.076
GMF21927	R.008	5/64	3/16	1/8	1/4	2	.076

▶ NEXT PAGE © : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF21 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE CORNER RADIUS WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Due to Multiple Helix on 1/8" and over diameter end mills, vibration is minimized and tool life increased.
- ▶ 4 flute series has new designs to reduce vibrations



EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
GMF21928	R.008	5/64	3/16	1/8	5/16	2	.076
GMF21929	R.008	5/64	3/16	1/8	3/8	2	.076
GMF21930	R.008	5/64	3/16	1/8	1/2	2	.076
GMF21931	R.012	5/64	3/16	1/8	1/4	2	.076
GMF21932	R.012	5/64	3/16	1/8	5/16	2	.076
GMF21933	R.012	5/64	3/16	1/8	3/8	2	.076
GMF21934	R.012	5/64	3/16	1/8	1/2	2	.076
GMF21935	R.020	5/64	3/16	1/8	1/4	2	.076
GMF21936	R.020	5/64	3/16	1/8	5/16	2	.076
GMF21937	R.020	5/64	3/16	1/8	3/8	2	.076
GMF21938	R.020	5/64	3/16	1/8	1/2	2	.076
GMF21008	R.004	1/8	1/4	3/16	5/16	2	.119
GMF21939	R.004	1/8	1/4	3/16	3/8	2	.119
GMF21940	R.004	1/8	1/4	3/16	1/2	2	.119
GMF21941	R.004	1/8	1/4	3/16	5/8	2-3/8	.119
GMF21942	R.008	1/8	1/4	3/16	3/8	2	.119
GMF21943	R.008	1/8	1/4	3/16	1/2	2	.119
GMF21944	R.008	1/8	1/4	3/16	5/8	2-3/8	.119
GMF21945	R.008	1/8	1/4	3/16	3/4	2-3/8	.119
GMF21946	R.012	1/8	1/4	3/16	5/16	2	.119
GMF21947	R.012	1/8	1/4	3/16	3/8	2	.119
GMF21948	R.012	1/8	1/4	3/16	1/2	2	.119
GMF21949	R.012	1/8	1/4	3/16	5/8	2-3/8	.119
GMF21950	R.012	1/8	1/4	3/16	3/4	2-3/8	.119
GMF21951	R.020	1/8	1/4	3/16	5/16	2	.119
GMF21952	R.020	1/8	1/4	3/16	3/8	2	.119
GMF21953	R.020	1/8	1/4	3/16	1/2	2	.119
GMF21954	R.020	1/8	1/4	3/16	5/8	2-3/8	.119
GMF21955	R.020	1/8	1/4	3/16	3/4	2-3/8	.119
GMF21956	R.020	1/8	1/4	3/16	1	2-3/4	.119

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF21 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE CORNER RADIUS WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Due to Multiple Helix on 1/8" and over diameter end mills, vibration is minimized and tool life increased.
- ▶ 4 flute series has new designs to reduce vibrations




EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
GMF21999	R.030	1/8	1/4	3/16	5/16	2	.119
GMF21801	R.030	1/8	1/4	3/16	3/8	2	.119
GMF21802	R.030	1/8	1/4	3/16	1/2	2	.119
GMF21803	R.030	1/8	1/4	3/16	5/8	2-3/8	.119
GMF21804	R.030	1/8	1/4	3/16	3/4	2-3/8	.119
GMF21805	R.030	1/8	1/4	3/16	1	2-3/4	.119
GMF21957	R.040	1/8	1/4	3/16	5/16	2-3/4	.119
GMF21958	R.040	1/8	1/4	3/16	3/8	2	.119
GMF21959	R.040	1/8	1/4	3/16	1/2	2	.119
GMF21960	R.040	1/8	1/4	3/16	5/8	2-3/8	.119
GMF21012	R.004	3/16	1/4	1/4	3/8	2	.181
GMF21961	R.004	3/16	1/4	1/4	1/2	2	.181
GMF21962	R.004	3/16	1/4	1/4	5/8	2-3/8	.181
GMF21963	R.004	3/16	1/4	1/4	3/4	2-3/8	.181
GMF21964	R.008	3/16	1/4	1/4	3/8	2	.181
GMF21965	R.008	3/16	1/4	1/4	1/2	2	.181
GMF21966	R.008	3/16	1/4	1/4	5/8	2-3/8	.181
GMF21967	R.008	3/16	1/4	1/4	3/4	2-3/8	.181
GMF21968	R.008	3/16	1/4	1/4	1	2-3/4	.181
GMF21969	R.012	3/16	1/4	1/4	3/8	2	.181
GMF21970	R.012	3/16	1/4	1/4	1/2	2	.181
GMF21971	R.012	3/16	1/4	1/4	5/8	2-3/8	.181
GMF21972	R.012	3/16	1/4	1/4	3/4	2-3/8	.181
GMF21973	R.012	3/16	1/4	1/4	1	2-3/4	.181
GMF21974	R.020	3/16	1/4	1/4	3/8	2	.181
GMF21975	R.020	3/16	1/4	1/4	1/2	2	.181
GMF21976	R.020	3/16	1/4	1/4	5/8	2-3/8	.181
GMF21977	R.020	3/16	1/4	1/4	3/4	2-3/8	.181
GMF21978	R.020	3/16	1/4	1/4	1	2-3/4	.181
GMF21806	R.030	3/16	1/4	1/4	3/8	2	.181

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF21 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE CORNER RADIUS WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Due to Multiple Helix on 1/8" and over diameter end mills, vibration is minimized and tool life increased.
- ▶ 4 flute series has new designs to reduce vibrations



D1ϕ1/8, 30° Helix


Unit : Inch

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
GMF21807	R.030	3/16	1/4	1/4	1/2	2	.181
GMF21808	R.030	3/16	1/4	1/4	5/8	2-3/8	.181
GMF21809	R.030	3/16	1/4	1/4	3/4	2-3/8	.181
GMF21810	R.030	3/16	1/4	1/4	1	2-3/4	.181
GMF21979	R.040	3/16	1/4	1/4	3/8	2	.181
GMF21980	R.040	3/16	1/4	1/4	1/2	2	.181
GMF21981	R.040	3/16	1/4	1/4	5/8	2-3/8	.181
GMF21982	R.040	3/16	1/4	1/4	3/4	2-3/8	.181
GMF21983	R.040	3/16	1/4	1/4	1	2-3/4	.181
GMF21016	R.012	1/4	1/4	3/8	3/4	2-3/8	.244
GMF21984	R.020	1/4	1/4	3/8	3/4	2-3/8	.244
GMF21811	R.030	1/4	1/4	3/8	3/4	2-3/8	.244
GMF21985	R.040	1/4	1/4	3/8	3/4	2-3/8	.244
GMF21020	R.008	5/16	5/16	1/2	1	2-3/4	.300
GMF21986	R.012	5/16	5/16	1/2	1	2-3/4	.300
GMF21987	R.020	5/16	5/16	1/2	1	2-3/4	.300
GMF21988	R.040	5/16	5/16	1/2	1	2-3/4	.300
GMF21989	R.020	5/16	5/16	3/4	1-3/8	4	.300
GMF21812	R.030	5/16	5/16	1/2	1	2-3/4	.300
GMF21813	R.030	5/16	5/16	3/4	1-3/8	4	.300
GMF21024	R.020	3/8	3/8	5/8	1-3/16	3	.363
GMF21990	R.040	3/8	3/8	5/8	1-3/16	3	.363
GMF21991	R.060	3/8	3/8	5/8	1-3/16	3	.363
GMF21992	R.020	3/8	3/8	1	1-1/2	4	.363
GMF21814	R.030	3/8	3/8	5/8	1-3/16	3	.363
GMF21815	R.030	3/8	3/8	1	1-1/2	4	.363
GMF21032	R.020	1/2	1/2	11/16	1-1/4	3-1/8	.488
GMF21816	R.030	1/2	1/2	11/16	1-1/4	3-1/8	.488
GMF21817	R.030	1/2	1/2	1-3/16	1-3/4	4-1/4	.488
GMF21993	R.040	1/2	1/2	11/16	1-1/4	3-1/8	.488

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF21 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE CORNER RADIUS WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Due to Multiple Helix on 1/8" and over diameter end mills, vibration is minimized and tool life increased.
- ▶ 4 flute series has new designs to reduce vibrations



D1ϕ1/8, 30° Helix

Unit : Inch

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
GMF21994	R.060	1/2	1/2	11/16	1-1/4	3-1/8	.488
GMF21995	R.080	1/2	1/2	11/16	1-1/4	3-1/8	.488
GMF21996	R.020	1/2	1/2	1-3/16	1-3/4	4-1/4	.488
GMF21040	R.020	5/8	5/8	3/4	1-3/8	4	.613
GMF21818	R.030	5/8	5/8	3/4	1-3/8	4	.613
GMF21997	R.040	5/8	5/8	3/4	1-3/8	4	.613
GMF21048	R.020	3/4	3/4	1	1-1/2	4	.738
GMF21819	R.030	3/4	3/4	1	1-1/2	4	.738
GMF21998	R.040	3/4	3/4	1	1-1/2	4	.738

Mill Dia. Tolerance (Inch)	Corner Radius Tolerance (Inch)	Shank Dia. Tolerance
0~-.0012	±.0008	h6

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF22 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRC55
- ▶ Due to Multiple Helix on 1/8" and over diameter end mills, vibration is minimized and tool life increased.
- ▶ For 1/32" and under 1/32" diameter sizes, double neck increases tool rigidity and minimizes vibration.
- ▶ Excellent for Rib Processing of various depths



Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	D1	D2	L1	L3	L2	D3
GMF22901	.008	3/16	.010	3/64	1-1/2	.006
GMF22902	.015	3/16	1/32	3/64	1-1/2	.013
GMF22903	.015	3/16	1/32	5/64	1-1/2	.013
GMF22904	.015	3/16	1/32	1/8	1-1/2	.013
GMF22905	.015	3/16	1/32	5/32	1-1/2	.013
GMF22906	.015	3/16	1/32	3/16	1-1/2	.013
GMF22907	.020	3/16	1/32	5/64	1-3/4	.018
GMF22908	.020	3/16	1/32	1/8	1-3/4	.018
GMF22909	.020	3/16	1/32	5/32	1-3/4	.018
GMF22910	.020	3/16	1/32	3/16	1-3/4	.018
GMF22911	.020	3/16	1/32	1/4	1-3/4	.018
GMF22912	.024	3/16	1/32	5/64	1-3/4	.022
GMF22913	.024	3/16	1/32	1/8	1-3/4	.022
GMF22914	.024	3/16	1/32	5/32	1-3/4	.022
GMF22915	.024	3/16	1/32	3/16	1-3/4	.022
GMF22916	.024	3/16	1/32	1/4	1-3/4	.022
GMF22917	.024	3/16	1/32	5/16	1-3/4	.022
GMF22918	.024	3/16	1/32	3/8	1-3/4	.022
GMF22002	1/32	3/16	3/64	5/64	1-3/4	.029
GMF22919	1/32	3/16	3/64	1/8	1-3/4	.029
GMF22920	1/32	3/16	3/64	5/32	1-3/4	.029
GMF22921	1/32	3/16	3/64	3/16	1-3/4	.029
GMF22922	1/32	3/16	3/64	1/4	1-3/4	.029
GMF22923	1/32	3/16	3/64	5/16	1-3/4	.029
GMF22924	1/32	3/16	3/64	3/8	1-3/4	.029
GMF22003	3/64	3/16	1/16	1/8	2	.044
GMF22925	3/64	3/16	1/16	5/32	2	.044
GMF22926	3/64	3/16	1/16	3/16	2	.044
GMF22927	3/64	3/16	1/16	1/4	2	.044
GMF22928	3/64	3/16	1/16	5/16	2	.044

▶ NEXT PAGE
◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	○	○							



GMF22 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRC55
- ▶ Due to Multiple Helix on 1/8" and over diameter end mills, vibration is minimized and tool life increased.
- ▶ For 1/32" and under 1/32" diameter sizes, double neck increases tool rigidity and minimizes vibration.
- ▶ Excellent for Rib Processing of various depths



Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	D1	D2	L1	L3	L2	D3
GMF22929	3/64	3/16	1/16	3/8	2	.044
GMF22930	3/64	3/16	1/16	1/2	2	.044
GMF22931	3/64	3/16	1/16	9/16	2	.044
GMF22932	3/64	3/16	1/16	5/8	2	.044
GMF22933	3/64	3/16	1/16	3/4	2	.044
GMF22004	1/16	3/16	3/32	5/32	2	.060
GMF22934	1/16	3/16	3/32	1/4	2	.060
GMF22935	1/16	3/16	3/32	5/16	2	.060
GMF22936	1/16	3/16	3/32	3/8	2	.060
GMF22937	1/16	3/16	3/32	1/2	2	.060
GMF22938	1/16	3/16	3/32	9/16	2	.060
GMF22939	1/16	3/16	3/32	5/8	2	.060
GMF22940	1/16	3/16	3/32	3/4	2	.060
GMF22005	5/64	3/16	1/8	1/4	2	.076
GMF22941	5/64	3/16	1/8	5/16	2	.076
GMF22942	5/64	3/16	1/8	3/8	2	.076
GMF22943	5/64	3/16	1/8	1/2	2	.076
GMF22944	5/64	3/16	1/8	9/16	2	.076
GMF22945	5/64	3/16	1/8	5/8	2	.076
GMF22946	5/64	3/16	1/8	3/4	2	.076
GMF22006	3/32	3/16	5/32	5/16	2	.089
GMF22947	3/32	3/16	5/32	1/2	2	.089
GMF22948	3/32	3/16	5/32	5/8	2	.089
GMF22949	3/32	3/16	5/32	3/4	2	.089
GMF22008	1/8	1/4	3/16	5/16	2	.119
GMF22950	1/8	1/4	3/16	3/8	2	.119
GMF22951	1/8	1/4	3/16	1/2	2	.119
GMF22952	1/8	1/4	3/16	9/16	2-3/8	.119
GMF22953	1/8	1/4	3/16	5/8	2-3/8	.119
GMF22954	1/8	1/4	3/16	11/16	2-3/8	.119

▶ NEXT PAGE
◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	○	○							

YG 4G MILL END MILLS

GMF22 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRC55
- ▶ Due to Multiple Helix on 1/8" and over diameter end mills, vibration is minimized and tool life increased.
- ▶ For 1/32" and under 1/32" diameter sizes, double neck increases tool rigidity and minimizes vibration.
- ▶ Excellent for Rib Processing of various depths



Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	D1	D2	L1	L3	L2	D3
GMF22955	1/8	1/4	3/16	3/4	2-3/8	.119
GMF22956	1/8	1/4	3/16	1	2-3/4	.119
GMF22012	3/16	1/4	1/4	3/8	2	.181
GMF22957	3/16	1/4	1/4	1/2	2	.181
GMF22958	3/16	1/4	1/4	5/8	2-3/8	.181
GMF22959	3/16	1/4	1/4	11/16	2-3/8	.181
GMF22960	3/16	1/4	1/4	3/4	2-3/8	.181
GMF22961	3/16	1/4	1/4	1	2-3/4	.181
GMF22962	3/16	1/4	1/4	1-3/16	2-3/4	.181
GMF22013	13/64	1/4	5/16	3/4	2-3/8	.197
GMF22963	13/64	1/4	5/16	1-3/16	2-3/4	.197
GMF22964	13/64	1/4	5/16	1-3/8	3	.197
GMF22965	13/64	1/4	5/16	1-1/2	3-1/8	.197
GMF22966	13/64	1/4	5/16	2	3-1/2	.197
GMF22016	1/4	1/4	3/8	5/8	2-3/8	.244
GMF22967	1/4	1/4	3/8	3/4	2-3/8	.244
GMF22968	1/4	1/4	3/8	1-3/16	2-3/4	.244
GMF22020	5/16	5/16	1/2	1	2-3/4	.300
GMF22024	3/8	3/8	5/8	1-3/16	3	.363
GMF22969	3/8	3/8	5/8	1-3/4	4	.363
GMF22032	1/2	1/2	3/4	1-3/8	3-1/8	.488
GMF22970	1/2	1/2	3/4	2	4-1/4	.488

Size	Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
up to Ø1/4	0--.0005	h6
over Ø1/4	0--.0006	

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70	○	○							

YG 4G MILL END MILLS

GMF23 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRC55
- ▶ Sharp End tooth geometry allows more efficient cutting



Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
GMF23901	.004	3/16	.008	1-1/2
GMF23902	.008	3/16	1/64	1-1/2
GMF23903	.012	3/16	1/32	1-1/2
GMF23904	.015	3/16	1/32	1-1/2
GMF23905	.020	3/16	3/64	1-1/2
GMF23906	.024	3/16	3/64	1-1/2
GMF23907	.028	3/16	1/16	1-1/2
GMF23908	.031	3/16	1/16	1-1/2
GMF23909	.035	3/16	5/64	1-1/2
GMF23910	.040	1/4	3/32	2
GMF23911	.047	1/4	1/8	2
GMF23004	1/16	1/4	5/32	2
GMF23005	5/64	1/4	1/4	2
GMF23006	3/32	1/4	1/4	2
GMF23008	1/8	1/4	5/16	2
GMF23009	9/64	1/4	3/8	2
GMF23012	3/16	1/4	3/8	2
GMF23013	13/64	1/4	5/8	2-3/8
GMF23016	1/4	1/4	5/8	2-3/8
GMF23017	17/64	5/16	11/16	2-3/8
GMF23018	9/32	5/16	3/4	2-3/8
GMF23020	5/16	5/16	3/4	2-3/4
GMF23022	11/32	3/8	7/8	2-3/4
GMF23023	23/64	3/8	7/8	2-3/4
GMF23024	3/8	3/8	1	3
GMF23026	13/32	1/2	1	3
GMF23028	7/16	1/2	1-3/16	3
GMF23032	1/2	1/2	1-3/16	3-1/8
GMF23036	9/16	9/16	1-3/8	4
GMF23912	9/16	5/8	1-3/8	4
GMF23040	5/8	5/8	1-1/2	4
GMF23048	3/4	3/4	1-3/4	4

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70	○	○							



GMF23 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE (3/16 SHANK)

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRC55
- ▶ Sharp End tooth geometry allows more efficient cutting



Unit : Inch

EDP No.	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2
GMF23913	.040	3/16	3/32	2
GMF23914	.047	3/16	1/8	2
GMF23915	.050	3/16	1/8	2
GMF23916	.055	3/16	5/32	2
GMF23917	.060	3/16	5/32	2
GMF23918	.063	3/16	5/32	2
GMF23919	.070	3/16	3/16	2
GMF23920	.079	3/16	1/4	2
GMF23921	.087	3/16	1/4	2
GMF23922	.094	3/16	1/4	2
GMF23923	.098	3/16	5/16	2
GMF23924	.102	3/16	5/16	2
GMF23925	.106	3/16	5/16	2
GMF23926	.110	3/16	5/16	2
GMF23927	.120	3/16	5/16	2

Size	Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
up to Ø1/4	0~- .0005	h6
over Ø1/4	0~- .0006	

▶ NEXT PAGE

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○	○							



GMF23 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE (1/8 Shank)

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRC55
- ▶ Sharp End tooth geometry allows more efficient cutting




Unit : Inch

EDP No.	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2
GMF23928	.004	1/8	.008	1-1/2
GMF23929	.008	1/8	1/64	1-1/2
GMF23930	.012	1/8	1/32	1-1/2
GMF23931	.015	1/8	1/32	1-1/2
GMF23932	.020	1/8	3/64	1-1/2
GMF23933	.024	1/8	3/64	1-1/2
GMF23934	.028	1/8	1/16	1-1/2
GMF23935	.031	1/8	1/16	1-1/2
GMF23936	.035	1/8	5/64	1-1/2
GMF23937	.040	1/8	3/32	2
GMF23938	.047	1/8	1/8	2
GMF23939	.060	1/8	5/32	2
GMF23940	.079	1/8	1/4	2
GMF23941	.098	1/8	1/4	2
GMF23942	.120	1/8	5/16	2

Size	Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
up to Ø1/4	0~- .0005	h6
over Ø1/4	0~- .0006	

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○	○							



GMF24 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG LENGTH

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Various length of cut and overall length end mills.




Unit : Inch

EDP No.	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2
GMF24003	3/64	1/4	1/8	2-3/8
GMF24901	3/64	1/4	5/32	2-3/8
GMF24902	3/64	1/4	1/4	2-3/8
GMF24903	3/64	1/4	5/16	2-3/8
GMF24904	3/64	1/4	3/8	2-3/8
GMF24004	1/16	1/4	1/4	2-3/8
GMF24905	1/16	1/4	5/16	2-3/8
GMF24906	1/16	1/4	3/8	2-3/8
GMF24907	1/16	1/4	1/2	2-3/8
GMF24908	1/16	1/4	5/8	2-3/8
GMF24005	5/64	1/4	5/16	2-3/8
GMF24909	5/64	1/4	3/8	2-3/8
GMF24910	5/64	1/4	1/2	2-3/8
GMF24911	5/64	1/4	5/8	2-3/8
GMF24006	3/32	1/4	5/8	2-3/8
GMF24008	1/8	1/4	3/8	2-3/4
GMF24912	1/8	1/4	1/2	2-3/4
GMF24913	1/8	1/4	5/8	2-3/4
GMF24914	1/8	1/4	3/4	2-3/4
GMF24915	1/8	1/4	1	2-3/4
GMF24012	3/16	1/4	1/2	2-3/4
GMF24916	3/16	1/4	5/8	2-3/4
GMF24917	3/16	1/4	3/4	2-3/4
GMF24918	3/16	1/4	1	2-3/4
GMF24919	3/16	1/4	1-3/16	2-3/4
GMF24013	13/64	1/4	3/4	2-3/4
GMF24920	13/64	1/4	1	2-3/4
GMF24921	13/64	1/4	1-3/16	3-1/8
GMF24922	13/64	1/4	1-1/2	4
GMF24016	1/4	1/4	5/8	2-3/8
GMF24923	1/4	1/4	5/8	3-1/8
GMF24924	1/4	1/4	3/4	2-3/4
GMF24925	1/4	1/4	3/4	3-1/2
GMF24926	1/4	1/4	1	3

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○	○	○							



GMF24 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG LENGTH

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Various length of cut and overall length end mills.



Unit : Inch

EDP No.	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2
GMF24927	1/4	1/4	1-3/16	3-1/8
GMF24928	1/4	1/4	1-3/16	4
GMF24929	1/4	1/4	1-3/16	6
GMF24930	1/4	1/4	1-3/8	3-1/2
GMF24931	1/4	1/4	1-1/2	3-1/2
GMF24932	1/4	1/4	1-3/4	6
GMF24020	5/16	5/16	1	3-1/8
GMF24933	5/16	5/16	1-3/16	3-1/8
GMF24934	5/16	5/16	1-3/8	3-1/2
GMF24935	5/16	5/16	1-1/2	3-1/2
GMF24936	5/16	5/16	1-1/2	4-1/2
GMF24937	5/16	5/16	1-3/4	4
GMF24938	5/16	5/16	2	4
GMF24024	3/8	3/8	1-3/16	3-1/8
GMF24939	3/8	3/8	1-3/16	4
GMF24940	3/8	3/8	1-3/8	3-1/2
GMF24941	3/8	3/8	1-1/2	3-1/2
GMF24942	3/8	3/8	1-1/2	4-1/2
GMF24943	3/8	3/8	1-3/4	4
GMF24944	3/8	3/8	2	4
GMF24945	3/8	3/8	2-3/8	4-1/4
GMF24032	1/2	1/2	1-3/8	3-1/2
GMF24946	1/2	1/2	1-1/2	4
GMF24947	1/2	1/2	1-1/2	4-1/2
GMF24948	1/2	1/2	1-3/4	5
GMF24949	1/2	1/2	2	4
GMF24950	1/2	1/2	2-1/8	4-1/4
GMF24951	1/2	1/2	2-3/8	4-1/4
GMF24952	1/2	1/2	2-3/8	6
GMF24040	5/8	5/8	1-1/2	6
GMF24048	3/4	3/4	3-1/2	8
GMF24953	3/4	3/4	4-1/4	8

Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
0~-0.012	h6

◎ : Excellent ○ : Good


P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○	○	○							

YG 4G MILL END MILLS

GMF25 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Due to Multiple Helix on 1/8" and over diameter end mills, vibration will be minimized and tool life increased.



MG 4 27°/30° PLAIN P.808

D1<math>< 0.18, 30^\circ</math> Helix Unit : Inch

EDP No.	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2
GMF25003	3/64	1/4	3/32	2
GMF25004	1/16	1/4	5/32	2
GMF25005	5/64	1/4	1/4	2
GMF25006	3/32	1/4	1/4	2
GMF25008	1/8	1/4	5/16	2
GMF25009	9/64	1/4	3/8	2
GMF25012	3/16	1/4	3/8	2
GMF25013	13/64	1/4	5/8	2-3/8
GMF25014	7/32	1/4	5/8	2-3/8
GMF25016	1/4	1/4	5/8	2-3/8
GMF25017	17/64	5/16	11/16	2-3/8
GMF25018	9/32	5/16	3/4	2-3/8
GMF25019	19/64	5/16	3/4	2-3/8
GMF25020	5/16	5/16	3/4	2-3/4
GMF25022	11/32	3/8	7/8	2-3/4
GMF25023	23/64	3/8	7/8	2-3/4
GMF25024	3/8	3/8	1	3
GMF25028	7/16	1/2	1-3/16	3
GMF25032	1/2	1/2	1-3/16	3-1/8
GMF25036	9/16	9/16	1-3/8	4
GMF25901	9/16	5/8	1-3/8	4
GMF25040	5/8	5/8	1-1/2	4
GMF25044	11/16	5/8	1-3/4	4
GMF25048	3/4	3/4	1-3/4	4

Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
0~-0.012	h6

© : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	○	○							

YG 4G MILL END MILLS

GMF26 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
 - ▶ Excellent performance when cutting steels, up to HRc55
 - ▶ Due to Multiple Helix on 1/8" and over diameter end mills, vibration will be minimized and tool life increased.
 - ▶ Due to gash land geometry used at end tooth, heavy duty cutting can be achieved.
- Various length products Available




MG 4 35°/38° PLAIN P.808

D1<math>< 0.18, 38^\circ</math> Helix Unit : Inch


EDP No.	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2
GMF26003	3/64	1/4	3/32	2
GMF26004	1/16	1/4	5/32	2
GMF26005	5/64	1/4	1/4	2
GMF26006	3/32	1/4	1/4	2
GMF26008	1/8	1/4	5/16	2
GMF26012	3/16	1/4	3/8	2
GMF26013	13/64	1/4	5/8	2-3/8
GMF26016	1/4	1/4	5/8	2-3/8
GMF26020	5/16	5/16	3/4	2-3/4
GMF26024	3/8	3/8	1	3
GMF26032	1/2	1/2	1-3/16	3-1/8
GMF26040	5/8	5/8	1-1/4	4
GMF26048	3/4	3/4	1-3/4	4

Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
0~-0.012	h6



© : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	○	○							



GMF27 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG LENGTH

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Various length of cut and overall length products available




Unit : Inch

EDP No.	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2
GMF27003	3/64	1/4	1/8	2-3/8
GMF27901	3/64	1/4	5/32	2-3/8
GMF27902	3/64	1/4	3/16	2-3/8
GMF27903	3/64	1/4	1/4	2-3/8
GMF27004	1/16	1/4	1/4	2-3/8
GMF27005	5/64	1/4	5/16	2-3/8
GMF27904	5/64	1/4	3/8	2-3/8
GMF27905	5/64	1/4	1/2	2-3/8
GMF27906	5/64	1/4	9/16	2-3/8
GMF27006	3/32	1/4	3/8	2-3/8
GMF27907	3/32	1/4	1/2	2-3/8
GMF27008	1/8	1/4	3/8	2-3/4
GMF27908	1/8	1/4	1/2	2-3/4
GMF27909	1/8	1/4	5/8	2-3/4
GMF27910	1/8	1/4	3/4	2-3/4
GMF27911	1/8	1/4	1	2-3/4
GMF27912	1/8	1/4	1-3/16	2-3/4
GMF27012	3/16	1/4	1/2	2-3/4
GMF27913	3/16	1/4	5/8	2-3/4
GMF27914	3/16	1/4	3/4	2-3/4
GMF27915	3/16	1/4	1	2-3/4
GMF27916	3/16	1/4	1-3/16	2-3/4
GMF27013	13/64	1/4	3/4	2-3/4
GMF27917	13/64	1/4	1	2-3/4
GMF27918	13/64	1/4	1-3/16	3-1/8
GMF27016	1/4	1/4	5/8	2-3/8
GMF27919	1/4	1/4	3/4	2-3/4
GMF27920	1/4	1/4	3/4	3-1/2
GMF27921	1/4	1/4	1	3
GMF27922	1/4	1/4	1-3/16	3-1/8
GMF27923	1/4	1/4	1-3/16	4
GMF27924	1/4	1/4	1-3/8	3-1/2
GMF27925	1/4	1/4	1-1/2	3-1/2

▶ NEXT PAGE
◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF27 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG LENGTH

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Various length of cut and overall length products available




Unit : Inch

EDP No.	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2
GMF27926	1/4	1/4	1-1/2	4-1/2
GMF27927	1/4	1/4	1-3/4	6
GMF27020	5/16	5/16	1	3-1/8
GMF27928	5/16	5/16	1-3/16	3-1/8
GMF27929	5/16	5/16	1-3/8	3-1/2
GMF27930	5/16	5/16	1-1/2	3-1/2
GMF27931	5/16	5/16	1-3/4	4
GMF27932	5/16	5/16	2	4
GMF27933	5/16	5/16	2	6
GMF27024	3/8	3/8	1-3/16	3-1/8
GMF27934	3/8	3/8	1-3/16	4
GMF27935	3/8	3/8	1-3/8	3-1/2
GMF27936	3/8	3/8	1-1/2	3-1/2
GMF27937	3/8	3/8	1-3/4	4
GMF27938	3/8	3/8	2	4
GMF27032	1/2	1/2	1-3/8	3-1/2
GMF27939	1/2	1/2	1-1/2	4
GMF27940	1/2	1/2	1-3/4	5
GMF27941	1/2	1/2	2	4
GMF27942	1/2	1/2	2-1/8	4-1/4
GMF27943	1/2	1/2	2-3/8	4-1/4
GMF27944	1/2	1/2	2-3/8	6
GMF27036	9/16	5/8	2	4-1/4
GMF27040	5/8	5/8	2	4-1/4
GMF27945	5/8	5/8	2-3/8	4-1/2
GMF27946	5/8	5/8	2-3/4	5
GMF27947	5/8	5/8	2-3/4	6
GMF27048	3/4	3/4	2-3/8	5
GMF27948	3/4	3/4	3-1/2	8
GMF27064	1	1	3-1/2	6

Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
0~-0.012	h6

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



GMF28 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE WITH NECK

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Many more various effective lengths and overall lengths than previous standard products.




EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	D1	D2	L1	L3	L2	D3
GMF28003	3/64	3/16	1/16	5/32	2	.044
GMF28901	3/64	3/16	1/16	3/16	2	.044
GMF28902	3/64	3/16	1/16	1/4	2	.044
GMF28903	3/64	3/16	1/16	5/16	2	.044
GMF28004	1/16	3/16	3/32	1/4	2	.060
GMF28904	1/16	3/16	3/32	5/16	2	.060
GMF28905	1/16	3/16	3/32	3/8	2	.060
GMF28906	1/16	3/16	3/32	1/2	2	.060
GMF28907	1/16	3/16	3/32	5/8	2	.060
GMF28005	5/64	3/16	1/8	5/16	2	.076
GMF28908	5/64	3/16	1/8	3/8	2	.076
GMF28909	5/64	3/16	1/8	1/2	2	.076
GMF28910	5/64	3/16	1/8	5/8	2	.076
GMF28008	1/8	1/4	3/16	3/8	2	.119
GMF28911	1/8	1/4	3/16	1/2	2	.119
GMF28912	1/8	1/4	3/16	5/8	2-3/8	.119
GMF28913	1/8	1/4	3/16	3/4	2-3/8	.119
GMF28914	1/8	1/4	3/16	1-3/16	2-3/4	.119
GMF28012	3/16	1/4	1/4	1/2	2	.181
GMF28915	3/16	1/4	1/4	5/8	2-3/8	.181
GMF28916	3/16	1/4	1/4	3/4	2-3/8	.181
GMF28917	3/16	1/4	1/4	1-3/16	2-3/4	.181
GMF28918	3/16	1/4	1/4	1-1/2	3-1/8	.181
GMF28013	13/64	1/4	5/16	3/4	2-3/8	.197
GMF28919	13/64	1/4	5/16	1-1/2	3-1/8	.197
GMF28016	1/4	1/4	3/8	5/8	2-3/8	.244
GMF28920	1/4	1/4	3/8	1-3/16	2-3/4	.244
GMF28020	5/16	5/16	1/2	1	2-3/4	.300
GMF28921	5/16	5/16	1/2	1-5/8	4	.300
GMF28024	3/8	3/8	5/8	1-3/16	3	.363
GMF28922	3/8	3/8	5/8	1-3/4	4	.363
GMF28032	1/2	1/2	3/4	1-3/8	3-1/8	.488
GMF28923	1/2	1/2	3/4	2	4-1/4	.488

Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
0~- .0012	h6

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	○	○							



GMF29 SERIES PLAIN SHANK

CARBIDE, 6 FLUTE 45° HELIX

- ▶ New coating and new tool geometry gives outstanding cutting performance and wear resistance.
- ▶ Excellent performance when cutting steels, up to HRc55
- ▶ Due to 45 helix angle, better surface finish can be achieved when side cutting.
- ▶ Various effective length and overall length products.




EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
GMF29016	1/4	1/4	5/8	2-3/8
GMF29901	1/4	1/4	1-3/16	3-1/8
GMF29020	5/16	5/16	3/4	2-3/4
GMF29902	5/16	5/16	1-1/2	3-1/2
GMF29024	3/8	3/8	1	3
GMF29903	3/8	3/8	1-1/2	3-1/2
GMF29032	1/2	1/2	1-3/16	3-1/8
GMF29904	1/2	1/2	2	4
GMF29040	5/8	5/8	1-1/2	4
GMF29905	5/8	5/8	2-3/8	4-1/2
GMF29048	3/4	3/4	1-3/4	4
GMF29906	3/4	3/4	2-3/8	4-1/2

Mill Dia. Tolerance (Inch)	Shank Dia. Tolerance
0~- .0012	h6

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	○	○							




X-SPEED ROUGHER

G907 SERIES PLAIN SHANK
G928 SERIES FLAT SHANK

CARBIDE, 4&5 FLUTE STUB LENGTH ROUGHING CORNER RADIUS - FINE

- ▶ Unique flute design for excellent chip evacuation and vibration reduction.
- ▶ Optimal roughing tooth profile to reduce cutting forces.
- ▶ Special tool geometry for high feed rate and heavy cutting.
- ▶ Strong end tooth design for plunge and pocket milling.
- ▶ Custom engineered coating to allow long tool life and excellent chip evacuation.



5 Flute: 44°/44.5°/45° Unit : Inch

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
PLAIN	FLAT	R	D1	D2	L1	L2	
G90716	-	R.020	1/4	1/4	3/8	2	4
G90720	-	R.020	5/16	5/16	7/16	2	4
G90724	G92824	R.020	3/8	3/8	1/2	2-1/4	4
G90732	G92832	R.020	1/2	1/2	5/8	2-1/2	4
G90740	G92840	R.040	5/8	5/8	3/4	3	5
G90748	G92848	R.040	3/4	3/4	1	3-1/4	5
G90764	G92864	R.040	1	1	1-1/4	4	5

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~.002	h6

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		○	◎	○						




X-SPEED ROUGHER

G908 SERIES PLAIN SHANK
G929 SERIES FLAT SHANK

CARBIDE, 4&5 FLUTE REGULAR LENGTH ROUGHING CORNER RADIUS - FINE

- ▶ Unique flute design for excellent chip evacuation and vibration reduction.
- ▶ Optimal roughing tooth profile to reduce cutting forces.
- ▶ Special tool geometry for high feed rate and heavy cutting.
- ▶ Strong end tooth design for plunge and pocket milling.
- ▶ Custom engineered coating to all ng tool life and excellent chip evacuation.




5 Flute: 44°/44.5°/45° Unit : Inch

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
PLAIN	FLAT	R	D1	D2	L1	L2	
G90816	-	R.020	1/4	1/4	5/8	2-1/2	4
G90820	-	R.020	5/16	5/16	3/4	2-1/2	4
G90824	G92924	R.020	3/8	3/8	7/8	2-1/2	4
G90832	G92932	R.020	1/2	1/2	1	3	4
G90840	G92940	R.040	5/8	5/8	1-1/4	3-1/2	5
G90848	G92948	R.040	3/4	3/4	1-5/8	4	5
G90864	G92964	R.040	1	1	1-3/4	4-1/4	5

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~.002	h6

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		○	◎	○						




X-SPEED ROUGHER

G909 SERIES PLAIN SHANK
G930 SERIES FLAT SHANK

CARBIDE, MULTI FLUTE EXTENDED REACH ROUGHING CORNER RADIUS - FINE


- ▶ Unique flute design for excellent chip evacuation and vibration reduction.
- ▶ Optimal roughing tooth profile to reduce cutting forces.
- ▶ Special tool geometry for high feed rate and heavy cutting.
- ▶ Strong end tooth design for plunge and pocket milling.
- ▶ Custom engineered coating to allow long tool life and excellent chip evacuation.



EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	No. of Flute
PLAIN	FLAT	R	D1	D2	L1	L3	L2	D3	
G90916	-	R.020	1/4	1/4	3/8	7/8	2-1/2	.230	4
G90920	-	R.020	5/16	5/16	7/16	1	2-1/2	.292	4
G90924	G93024	R.020	3/8	3/8	1/2	1	2-3/4	.355	4
G90932	G93032	R.020	1/2	1/2	5/8	1-1/4	3-1/4	.480	4
G90940	G93040	R.040	5/8	5/8	3/4	2	4	.605	5
G90948	G93048	R.040	3/4	3/4	1	2-3/8	4-1/2	.718	5

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-.002	h6


P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		○	◎	○						



SEMD98 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.



Call for Availability

EDP No.	Radius of Ball Nose R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2	Remark
SEMD98001S	RO.05	0.1	4	0.1	40	Short
SEMD98001	RO.05	0.1	4	0.2	40	Regular
SEMD980013S	RO.05	0.1	3	0.2	40	3mm Shank
SEMD980015S	RO.075	0.15	4	0.15	40	Short
SEMD980015	RO.075	0.15	4	0.3	40	Regular
SEMD9800153S	RO.075	0.15	3	0.3	40	3mm Shank
SEMD98002S	RO.1	0.2	4	0.2	40	Short
SEMD98002	RO.1	0.2	4	0.4	40	Regular
SEMD980023S	RO.1	0.2	3	0.4	40	3mm Shank
SEMD98003S	RO.15	0.3	4	0.3	40	Short
SEMD98003	RO.15	0.3	4	0.6	40	Regular
SEMD980033S	RO.15	0.3	3	0.6	40	3mm Shank
SEMD98004S	RO.2	0.4	4	0.4	40	Short
SEMD98004	RO.2	0.4	4	0.8	40	Regular
SEMD980043S	RO.2	0.4	3	0.8	40	3mm Shank
SEMD98005S	RO.25	0.5	4	0.5	40	Short
SEMD98005	RO.25	0.5	4	1.0	40	Regular
SEMD980053S	RO.25	0.5	3	1.0	40	3mm Shank
SEMD98006S	RO.3	0.6	4	0.6	40	Short
SEMD98006	RO.3	0.6	4	1.2	40	Regular
SEMD980063S	RO.3	0.6	3	1.2	40	3mm Shank
SEMD98007S	RO.35	0.7	4	0.7	40	Short
SEMD98007	RO.35	0.7	4	1.4	40	Regular
SEMD980073S	RO.35	0.7	3	1.4	40	3mm Shank
SEMD98008S	RO.4	0.8	4	0.8	40	Short
SEMD98008	RO.4	0.8	4	1.6	40	Regular
SEMD980083S	RO.4	0.8	3	1.6	40	3mm Shank
SEMD98009S	RO.45	0.9	4	0.9	40	Short
SEMD98009	RO.45	0.9	4	1.8	40	Regular
SEMD980093S	RO.45	0.9	3	1.8	40	3mm Shank

▶ NEXT PAGE



P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○			○						



SEMD98 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.



Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	Remark
	R	D1	D2	L1	L2	
SEMD98010040	R0.5	1.0	6	1.5	40	Short
SEMD980103S	R0.5	1.0	3	2.5	50	3mm Shank
SEMD980104S	R0.5	1.0	4	2.5	50	Regular
SEMD98010	R0.5	1.0	6	2.5	50	Regular
SEMD98010070	R0.5	1.0	6	2.5	70	Long Shank
SEMD98010100	R0.5	1.0	6	2.5	100	Long Shank
SEMD98012040	R0.6	1.2	6	2	40	Short
SEMD980123S	R0.6	1.2	3	3	50	3mm Shank
SEMD980124S	R0.6	1.2	4	3	50	Regular
SEMD98012	R0.6	1.2	6	3	50	Regular
SEMD98012070	R0.6	1.2	6	3	70	Long Shank
SEMD98012100	R0.6	1.2	6	3	100	Long Shank
SEMD98015040	R0.75	1.5	6	2.5	40	Short
SEMD980153S	R0.75	1.5	3	4	50	3mm Shank
SEMD980154S	R0.75	1.5	4	4	50	Regular
SEMD98015	R0.75	1.5	6	4	50	Regular
SEMD98015070	R0.75	1.5	6	4	70	Long Shank
SEMD98015100	R0.75	1.5	6	4	100	Long Shank
SEMD98020040	R1.0	2.0	6	3	40	Short
SEMD980203S	R1.0	2.0	3	5	50	3mm Shank
SEMD980204S	R1.0	2.0	4	5	50	Regular
SEMD98020	R1.0	2.0	6	5	50	Regular
SEMD98020080	R1.0	2.0	6	5	80	Long Shank
SEMD98020100	R1.0	2.0	6	5	100	Long Shank
SEMD98025040	R1.25	2.5	6	4	40	Short
SEMD980253S	R1.25	2.5	3	6	60	3mm Shank
SEMD980254S	R1.25	2.5	4	6	60	Regular
SEMD98025	R1.25	2.5	6	6	60	Regular
SEMD98025080	R1.25	2.5	6	6	80	Long Shank
SEMD98025100	R1.25	2.5	6	6	100	Long Shank

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N						S
Carbon Steels	Alloy Steels	Pearhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45 HRC45~55	HRC55~70									
○	◎	◎	◎	○		○							



SEMD98 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.



Call for Availability


Unit : mm

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	Remark
	R	D1	D2	L1	L2	
SEMD98030040	R1.5	3.0	6	4.5	40	Short
SEMD980303S	R1.5	3.0	3	6	60	3mm Shank
SEMD980304S	R1.5	3.0	4	6	60	Regular
SEMD98030	R1.5	3.0	6	6	60	Regular
SEMD98030080	R1.5	3.0	6	6	80	Long Shank
SEMD98030100	R1.5	3.0	6	6	100	Long Shank
SEMD98035	R1.75	3.5	6	8	70	-
SEMD98040050	R2.0	4.0	6	6	50	Short
SEMD980404S	R2.0	4.0	4	8	70	Regular
SEMD98040	R2.0	4.0	6	8	70	Regular
SEMD980401004S	R2.0	4.0	4	8	100	Long Shank
SEMD980401204S	R2.0	4.0	4	8	120	Long Shank
SEMD98040100	R2.0	4.0	6	8	100	Long Shank
SEMD98040120	R2.0	4.0	6	8	120	Long Shank
SEMD98045	R2.25	4.5	6	9	80	-
SEMD98050060	R2.5	5.0	6	7.5	60	Short
SEMD98050	R2.5	5.0	6	10	80	Regular
SEMD980505S	R2.5	5.0	5	10	80	5mmShank
SEMD98055	R2.75	5.5	6	11	90	-
SEMD98060050	R3.0	6.0	6	9	50	Short
SEMD98060060	R3.0	6.0	6	9	60	Short
SEMD98060080	R3.0	6.0	6	9	80	Short
SEMD98060	R3.0	6.0	6	12	90	Regular
SEMD98060110	R3.0	6.0	6	12	110	Long Shank
SEMD98060130	R3.0	6.0	6	12	130	Long Shank
SEMD98060150	R3.0	6.0	6	12	150	Long Shank
SEMD98065	R3.25	6.5	8	13	90	-
SEMD98070	R3.5	7.0	8	14	90	-
SEMD98080050	R4.0	8.0	8	12	50	Short
SEMD98080060	R4.0	8.0	8	12	60	Short

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N						S
Carbon Steels	Alloy Steels	Pearhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45 HRC45~55	HRC55~70									
○	◎	◎	◎	○		○							



SEMD98 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.



◇ Call for Availability


Unit : mm

EDP No.	Radius of Ball Nose R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2	Remark
SEMD98080080	R4.0	8.0	8	12	80	Short
SEMD98080090	R4.0	8.0	8	12	90	Short
SEMD98080	R4.0	8.0	8	14	100	Regular
SEMD98080130	R4.0	8.0	8	14	130	Long Shank
SEMD98080150	R4.0	8.0	8	14	150	Long Shank
SEMD98085	R4.25	8.5	10	16	100	-
SEMD98090	R4.5	9.0	10	18	100	-
SEMD98100050	R5.0	10.0	10	15	50	Short
SEMD98100060	R5.0	10.0	10	15	60	Short
SEMD98100080	R5.0	10.0	10	15	80	Short
SEMD98100090	R5.0	10.0	10	15	90	Short
SEMD98100	R5.0	10.0	10	18	100	Regular
SEMD98100130	R5.0	10.0	10	18	130	Long Shank
SEMD98100150	R5.0	10.0	10	18	150	Long Shank
SEMD98100180	R5.0	10.0	10	18	180	Long Shank
SEMD98100200	R5.0	10.0	10	18	200	Long Shank
SEMD98110	R5.5	11.0	12	20	100	-
SEMD98120060	R6.0	12.0	12	18	60	Short
SEMD98120080	R6.0	12.0	12	18	80	Short
SEMD98120090	R6.0	12.0	12	18	90	Short
SEMD98120100	R6.0	12.0	12	18	100	Short
SEMD98120	R6.0	12.0	12	22	110	Regular
SEMD98120130	R6.0	12.0	12	22	130	Long Shank
SEMD98120150	R6.0	12.0	12	22	150	Long Shank
SEMD98120180	R6.0	12.0	12	22	180	Long Shank
SEMD98120220	R6.0	12.0	12	22	200	Long Shank
SEMD98130	R6.5	13.0	12	24	100	-
SEMD98140	R7.0	14.0	12	26	100	Regular
SEMD9814014S	R7.0	14.0	14	26	100	-
SEMD9814016S	R7.0	14.0	16	26	100	-

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N						S
Carbon Steels	Alloy Steels	Pearhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



SEMD98 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2	Remark
SEMD98150	R7.5	15.0	16	28	140	-
SEMD98160100	R8.0	16.0	16	24	100	Short
SEMD98160130	R8.0	16.0	16	24	130	Short
SEMD98160	R8.0	16.0	16	30	150	Regular
SEMD98160180	R8.0	16.0	16	30	180	Long Shank
SEMD98160200	R8.0	16.0	16	30	200	Long Shank
SEMD98180	R9.0	18.0	16	34	150	Regular
SEMD9818018S	R9.0	18.0	18	34	150	-
SEMD98200100	R10.0	20.0	20	30	100	Short
SEMD98200130	R10.0	20.0	20	30	130	Short
SEMD98200	R10.0	20.0	20	38	150	Regular
SEMD98200200	R10.0	20.0	20	38	200	Long Shank
SEMD98250120	R12.5	25.0	25	50	120	Short
SEMD98250	R12.5	25.0	25	50	180	Regular

Size	Radius Tolerance (mm)	Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
up to R3	±0.005	0~-0.012	h6
over R3	±0.010	0~-0.015	



P				H	M	K	N						S
Carbon Steels	Alloy Steels	Pearhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



SEM846 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK BALL NOSE

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
SEM846001002	RO.05	0.1	4	0.1	0.2	40	0.085
SEM846001003	RO.05	0.1	4	0.1	0.3	40	0.085
SEM846001005	RO.05	0.1	4	0.1	0.5	40	0.085
SEM84600101	RO.05	0.1	4	0.1	1	40	0.085
SEM846002005	RO.1	0.2	4	0.2	0.5	40	0.17
SEM84600201	RO.1	0.2	4	0.2	1	40	0.17
SEM846002015	RO.1	0.2	4	0.2	1.5	40	0.17
SEM84600202	RO.1	0.2	4	0.2	2	40	0.17
SEM84600203	RO.1	0.2	4	0.2	3	40	0.17
SEM84600301	RO.15	0.3	4	0.3	1	40	0.27
SEM846003015	RO.15	0.3	4	0.3	1.5	40	0.27
SEM84600302	RO.15	0.3	4	0.3	2	40	0.27
SEM846003025	RO.15	0.3	4	0.3	2.5	40	0.27
SEM84600303	RO.15	0.3	4	0.3	3	40	0.27
SEM84600304	RO.15	0.3	4	0.3	4	40	0.27
SEM84600305	RO.15	0.3	4	0.3	5	40	0.27
SEM84600401	RO.2	0.4	4	0.4	1	40	0.37
SEM846004015	RO.2	0.4	4	0.4	1.5	40	0.37
SEM84600402	RO.2	0.4	4	0.4	2	40	0.37
SEM846004025	RO.2	0.4	4	0.4	2.5	40	0.37
SEM84600403	RO.2	0.4	4	0.4	3	40	0.37
SEM84600404	RO.2	0.4	4	0.4	4	40	0.37
SEM84600405	RO.2	0.4	4	0.4	5	40	0.37
SEM84600406	RO.2	0.4	4	0.4	6	40	0.37
SEM84600408	RO.2	0.4	4	0.4	8	40	0.37
SEM84600410	RO.2	0.4	4	0.4	10	40	0.37
SEM84600501	RO.25	0.5	4	0.5	1	45	0.45
SEM846005015	RO.25	0.5	4	0.5	1.5	45	0.45
SEM84600502	RO.25	0.5	4	0.5	2	45	0.45
SEM846005025	RO.25	0.5	4	0.5	2.5	45	0.45

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



SEM846 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK BALL NOSE

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
SEM84600503	RO.25	0.5	4	0.5	3	45	0.45
SEM84600504	RO.25	0.5	4	0.5	4	45	0.45
SEM84600505	RO.25	0.5	4	0.5	5	45	0.45
SEM84600506	RO.25	0.5	4	0.5	6	45	0.45
SEM84600508	RO.25	0.5	4	0.5	8	45	0.45
SEM84600510	RO.25	0.5	4	0.5	10	45	0.45
SEM84600512	RO.25	0.5	4	0.5	12	45	0.45
SEM84600514	RO.25	0.5	4	0.5	14	45	0.45
SEM84600516	RO.25	0.5	4	0.5	16	45	0.45
SEM84600601	RO.3	0.6	4	0.6	1	45	0.55
SEM84600602	RO.3	0.6	4	0.6	2	45	0.55
SEM84600603	RO.3	0.6	4	0.6	3	45	0.55
SEM84600604	RO.3	0.6	4	0.6	4	45	0.55
SEM84600605	RO.3	0.6	4	0.6	5	45	0.55
SEM84600606	RO.3	0.6	4	0.6	6	45	0.55
SEM84600608	RO.3	0.6	4	0.6	8	45	0.55
SEM84600610	RO.3	0.6	4	0.6	10	45	0.55
SEM84600612	RO.3	0.6	4	0.6	12	45	0.55
SEM84600614	RO.3	0.6	4	0.6	14	45	0.55
SEM84600616	RO.3	0.6	4	0.6	16	45	0.55
SEM84600702	RO.35	0.7	4	0.7	2	45	0.65
SEM84600704	RO.35	0.7	4	0.7	4	45	0.65
SEM84600706	RO.35	0.7	4	0.7	6	45	0.65
SEM84600708	RO.35	0.7	4	0.7	8	45	0.65
SEM84600710	RO.35	0.7	4	0.7	10	45	0.65
SEM84600712	RO.35	0.7	4	0.7	12	45	0.65
SEM84600801	RO.4	0.8	4	0.8	1	45	0.75
SEM84600802	RO.4	0.8	4	0.8	2	45	0.75
SEM84600803	RO.4	0.8	4	0.8	3	45	0.75
SEM84600804	RO.4	0.8	4	0.8	4	45	0.75

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



SEM846 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK BALL NOSE

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.



NG
2
30°
±0.005
±0.010
PLAIN
P.815~819

◇ Call for Availability


Unit : mm

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
SEM84600805	RO.4	0.8	4	0.8	5	45	0.75
SEM84600806	RO.4	0.8	4	0.8	6	45	0.75
SEM84600808	RO.4	0.8	4	0.8	8	45	0.75
SEM84600810	RO.4	0.8	4	0.8	10	45	0.75
SEM84600812	RO.4	0.8	4	0.8	12	45	0.75
SEM84600814	RO.4	0.8	4	0.8	14	45	0.75
SEM84600816	RO.4	0.8	4	0.8	16	45	0.75
SEM84600820	RO.4	0.8	4	0.8	20	45	0.75
SEM84600904	RO.45	0.9	4	0.9	4	45	0.85
SEM84600906	RO.45	0.9	4	0.9	6	45	0.85
SEM84600908	RO.45	0.9	4	0.9	8	45	0.85
SEM84600910	RO.45	0.9	4	0.9	10	45	0.85
SEM84601002	RO.5	1.0	4	1	2	50	0.95
SEM84601003	RO.5	1.0	4	1	3	50	0.95
SEM84601004	RO.5	1.0	4	1	4	50	0.95
SEM84601005	RO.5	1.0	4	1	5	50	0.95
SEM84601006	RO.5	1.0	4	1	6	50	0.95
SEM84601007	RO.5	1.0	4	1	7	50	0.95
SEM84601008	RO.5	1.0	4	1	8	50	0.95
SEM84601009	RO.5	1.0	4	1	9	50	0.95
SEM84601010	RO.5	1.0	4	1	10	50	0.95
SEM84601012	RO.5	1.0	4	1	12	50	0.95
SEM84601014	RO.5	1.0	4	1	14	50	0.95
SEM84601016	RO.5	1.0	4	1	16	50	0.95
SEM84601018	RO.5	1.0	4	1	18	50	0.95
SEM84601020	RO.5	1.0	4	1	20	50	0.95
SEM84601022	RO.5	1.0	4	1	22	60	0.95
SEM84601026	RO.5	1.0	4	1	26	60	0.95
SEM84601030	RO.5	1.0	4	1	30	70	0.95
SEM84601040	RO.5	1.0	4	1	40	80	0.95

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



SEM846 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK BALL NOSE

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.



NG
2
30°
±0.005
±0.010
PLAIN
P.815~819

◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
SEM84601050	RO.5	1.0	4	1	50	100	0.95
SEM84601204	RO.6	1.2	4	1.2	4	50	1.15
SEM84601206	RO.6	1.2	4	1.2	6	50	1.15
SEM84601208	RO.6	1.2	4	1.2	8	50	1.15
SEM84601210	RO.6	1.2	4	1.2	10	50	1.15
SEM84601212	RO.6	1.2	4	1.2	12	50	1.15
SEM84601216	RO.6	1.2	4	1.2	16	50	1.15
SEM84601220	RO.6	1.2	4	1.2	20	50	1.15
SEM84601226	RO.6	1.2	4	1.2	26	60	1.15
SEM84601406	RO.7	1.4	4	1.4	6	50	1.35
SEM84601408	RO.7	1.4	4	1.4	8	50	1.35
SEM84601410	RO.7	1.4	4	1.4	10	50	1.35
SEM84601412	RO.7	1.4	4	1.4	12	50	1.35
SEM84601416	RO.7	1.4	4	1.4	16	50	1.35
SEM84601503	RO.75	1.5	4	1.5	3	50	1.45
SEM84601504	RO.75	1.5	4	1.5	4	50	1.45
SEM84601505	RO.75	1.5	4	1.5	5	50	1.45
SEM84601506	RO.75	1.5	4	1.5	6	50	1.45
SEM84601507	RO.75	1.5	4	1.5	7	50	1.45
SEM84601508	RO.75	1.5	4	1.5	8	50	1.45
SEM84601510	RO.75	1.5	4	1.5	10	50	1.45
SEM84601512	RO.75	1.5	4	1.5	12	50	1.45
SEM84601514	RO.75	1.5	4	1.5	14	50	1.45
SEM84601516	RO.75	1.5	4	1.5	16	50	1.45
SEM84601518	RO.75	1.5	4	1.5	18	50	1.45
SEM84601520	RO.75	1.5	4	1.5	20	50	1.45
SEM84601522	RO.75	1.5	4	1.5	22	60	1.45
SEM84601526	RO.75	1.5	4	1.5	26	60	1.45
SEM84601530	RO.75	1.5	4	1.5	30	70	1.45
SEM84601535	RO.75	1.5	4	1.5	35	70	1.45

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



SEM846 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK BALL NOSE

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.



NG
2
30°
±0.005
±0.010
PLAIN
P.815~819

◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
SEM84601540	RO.75	1.5	4	1.5	40	80	1.45
SEM84601604	RO.8	1.6	4	1.6	4	50	1.55
SEM84601606	RO.8	1.6	4	1.6	6	50	1.55
SEM84601608	RO.8	1.6	4	1.6	8	50	1.55
SEM84601610	RO.8	1.6	4	1.6	10	50	1.55
SEM84601612	RO.8	1.6	4	1.6	12	50	1.55
SEM84601616	RO.8	1.6	4	1.6	16	50	1.55
SEM84601620	RO.8	1.6	4	1.6	20	50	1.55
SEM84601804	RO.9	1.8	4	1.8	4	50	1.75
SEM84601806	RO.9	1.8	4	1.8	6	50	1.75
SEM84601808	RO.9	1.8	4	1.8	8	50	1.75
SEM84601810	RO.9	1.8	4	1.8	10	50	1.75
SEM84601812	RO.9	1.8	4	1.8	12	50	1.75
SEM84601816	RO.9	1.8	4	1.8	16	50	1.75
SEM84601820	RO.9	1.8	4	1.8	20	50	1.75
SEM84602004	R1.0	2.0	4	2	4	50	1.95
SEM84602006	R1.0	2.0	4	2	6	50	1.95
SEM84602008	R1.0	2.0	4	2	8	50	1.95
SEM84602010	R1.0	2.0	4	2	10	50	1.95
SEM84602012	R1.0	2.0	4	2	12	50	1.95
SEM84602014	R1.0	2.0	4	2	14	50	1.95
SEM84602016	R1.0	2.0	4	2	16	50	1.95
SEM84602018	R1.0	2.0	4	2	18	50	1.95
SEM84602020	R1.0	2.0	4	2	20	50	1.95
SEM84602022	R1.0	2.0	4	2	22	60	1.95
SEM84602026	R1.0	2.0	4	2	26	60	1.95
SEM84602030	R1.0	2.0	4	2	30	70	1.95
SEM84602035	R1.0	2.0	4	2	35	70	1.95
SEM84602040	R1.0	2.0	4	2	40	80	1.95
SEM84602045	R1.0	2.0	4	2	45	90	1.95

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pearhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



SEM846 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK BALL NOSE

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.



NG
2
30°
±0.005
±0.010
PLAIN
P.815~819

◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
SEM84602050	R1.0	2.0	4	2	50	100	1.95
SEM84602060	R1.0	2.0	4	2	60	110	1.95
SEM84602508	R1.25	2.5	4	2.5	8	50	2.40
SEM84602510	R1.25	2.5	4	2.5	10	50	2.40
SEM84602512	R1.25	2.5	4	2.5	12	50	2.40
SEM84602516	R1.25	2.5	4	2.5	16	50	2.40
SEM84602520	R1.25	2.5	4	2.5	20	50	2.40
SEM84602522	R1.25	2.5	4	2.5	22	60	2.40
SEM84602526	R1.25	2.5	4	2.5	26	60	2.40
SEM84602530	R1.25	2.5	4	2.5	30	70	2.40
SEM84602535	R1.25	2.5	4	2.5	35	70	2.40
SEM84602540	R1.25	2.5	4	2.5	40	80	2.40
SEM84602545	R1.25	2.5	4	2.5	45	90	2.40
SEM84602550	R1.25	2.5	4	2.5	50	100	2.40
SEM84603006	R1.5	3.0	6	3	6	50	2.85
SEM84603008	R1.5	3.0	6	3	8	50	2.85
SEM84603010	R1.5	3.0	6	3	10	50	2.85
SEM84603012	R1.5	3.0	6	3	12	50	2.85
SEM84603014	R1.5	3.0	6	3	14	60	2.85
SEM84603016	R1.5	3.0	6	3	16	60	2.85
SEM84603018	R1.5	3.0	6	3	18	60	2.85
SEM84603020	R1.5	3.0	6	3	20	60	2.85
SEM84603022	R1.5	3.0	6	3	22	65	2.85
SEM84603026	R1.5	3.0	6	3	26	65	2.85
SEM84603030	R1.5	3.0	6	3	30	70	2.85
SEM84603035	R1.5	3.0	6	3	35	70	2.85
SEM84603040	R1.5	3.0	6	3	40	80	2.85
SEM84603045	R1.5	3.0	6	3	45	90	2.85
SEM84603050	R1.5	3.0	6	3	50	100	2.85
SEM84603060	R1.5	3.0	6	3	60	100	2.85

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pearhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



SEM846 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK BALL NOSE

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.



◇ Call for Availability

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
SEM84604008	R2.0	4.0	6	4	8	50	3.85
SEM84604010	R2.0	4.0	6	4	10	50	3.85
SEM84604012	R2.0	4.0	6	4	12	50	3.85
SEM84604014	R2.0	4.0	6	4	14	60	3.85
SEM84604016	R2.0	4.0	6	4	16	60	3.85
SEM84604018	R2.0	4.0	6	4	18	60	3.85
SEM84604020	R2.0	4.0	6	4	20	60	3.85
SEM84604022	R2.0	4.0	6	4	22	65	3.85
SEM84604026	R2.0	4.0	6	4	26	65	3.85
SEM84604030	R2.0	4.0	6	4	30	70	3.85
SEM84604035	R2.0	4.0	6	4	35	70	3.85
SEM84604040	R2.0	4.0	6	4	40	80	3.85
SEM84604045	R2.0	4.0	6	4	45	90	3.85
SEM84604050	R2.0	4.0	6	4	50	100	3.85
SEM84604055	R2.0	4.0	6	4	55	100	3.85
SEM84604060	R2.0	4.0	6	4	60	100	3.85
SEM84605015	R2.5	5.0	6	6	15	60	4.85
SEM84605020	R2.5	5.0	6	6	20	60	4.85
SEM84605026	R2.5	5.0	6	6	26	65	4.85
SEM84605030	R2.5	5.0	6	6	30	70	4.85
SEM84605035	R2.5	5.0	6	6	35	70	4.85
SEM84605040	R2.5	5.0	6	6	40	80	4.85
SEM84605045	R2.5	5.0	6	6	45	90	4.85
SEM84605050	R2.5	5.0	6	6	50	100	4.85
SEM84605055	R2.5	5.0	6	6	55	100	4.85
SEM84605060	R2.5	5.0	6	6	60	100	4.85
SEM84606020	R3.0	6.0	6	8	20	60	5.85
SEM84606030	R3.0	6.0	6	8	30	60	5.85
SEM84606020090	R3.0	6.0	6	12	20	90	5.85
SEM84606030090	R3.0	6.0	6	12	30	90	5.85

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



SEM846 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK BALL NOSE

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.



◇ Call for Availability

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
SEM84608025	R4.0	8.0	8	10	25	70	7.70
SEM84608035	R4.0	8.0	8	10	35	70	7.70
SEM84608025100	R4.0	8.0	8	14	25	100	7.70
SEM84608035100	R4.0	8.0	8	14	35	100	7.70
SEM84610030	R5.0	10.0	10	12	30	75	9.70
SEM84610040	R5.0	10.0	10	12	40	75	9.70
SEM84610030100	R5.0	10.0	10	18	30	100	9.70
SEM84610040100	R5.0	10.0	10	18	40	100	9.70
SEM84612032	R6.0	12.0	12	14	32	80	11.70
SEM84612045	R6.0	12.0	12	14	45	80	11.70
SEM84612032110	R6.0	12.0	12	22	32	110	11.70
SEM84612045110	R6.0	12.0	12	22	45	110	11.70

Size	Radius Tolerance (mm)	Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
up to R3	±0.005	0~-0.012	h6
over R3	±0.010	0~-0.015	

◎ : Excellent ○ : Good


P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



SEM846 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK BALL NOSE (6mm shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.



P.815~819

◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
SEM846005016S	RO.25	0.5	6	0.5	1	45	0.45
SEM846005026S	RO.25	0.5	6	0.5	2	45	0.45
SEM846005046S	RO.25	0.5	6	0.5	4	45	0.45
SEM846006016S	RO.3	0.6	6	0.6	1	45	0.55
SEM846006026S	RO.3	0.6	6	0.6	2	45	0.55
SEM846006036S	RO.3	0.6	6	0.6	3	45	0.55
SEM846006046S	RO.3	0.6	6	0.6	4	45	0.55
SEM846006056S	RO.3	0.6	6	0.6	5	45	0.55
SEM846006066S	RO.3	0.6	6	0.6	6	45	0.55
SEM846006086S	RO.3	0.6	6	0.6	8	45	0.55
SEM846006106S	RO.3	0.6	6	0.6	10	45	0.55
SEM846006126S	RO.3	0.6	6	0.6	12	45	0.55
SEM846006146S	RO.3	0.6	6	0.6	14	45	0.55
SEM846006166S	RO.3	0.6	6	0.6	16	45	0.55
SEM846008016S	RO.4	0.8	6	0.8	1	45	0.75
SEM846008026S	RO.4	0.8	6	0.8	2	45	0.75
SEM846008036S	RO.4	0.8	6	0.8	3	45	0.75
SEM846008046S	RO.4	0.8	6	0.8	4	45	0.75
SEM846008056S	RO.4	0.8	6	0.8	5	45	0.75
SEM846008066S	RO.4	0.8	6	0.8	6	45	0.75
SEM846008086S	RO.4	0.8	6	0.8	8	45	0.75
SEM846008106S	RO.4	0.8	6	0.8	10	45	0.75
SEM846008126S	RO.4	0.8	6	0.8	12	45	0.75
SEM846008146S	RO.4	0.8	6	0.8	14	45	0.75
SEM846008166S	RO.4	0.8	6	0.8	16	45	0.75
SEM846008206S	RO.4	0.8	6	0.8	20	45	0.75
SEM846010026S	RO.5	1.0	6	1	2	50	0.95
SEM846010036S	RO.5	1.0	6	1	3	50	0.95
SEM846010046S	RO.5	1.0	6	1	4	50	0.95
SEM846010056S	RO.5	1.0	6	1	5	50	0.95

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



SEM846 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK BALL NOSE (6mm shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.



P.815~819

◇ Call for Availability


Unit : mm

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
SEM846010066S	RO.5	1.0	6	1	6	50	0.95
SEM846010076S	RO.5	1.0	6	1	7	50	0.95
SEM846010086S	RO.5	1.0	6	1	8	50	0.95
SEM846010096S	RO.5	1.0	6	1	9	50	0.95
SEM846010106S	RO.5	1.0	6	1	10	50	0.95
SEM846010126S	RO.5	1.0	6	1	12	50	0.95
SEM846010146S	RO.5	1.0	6	1	14	50	0.95
SEM846010166S	RO.5	1.0	6	1	16	50	0.95
SEM846010186S	RO.5	1.0	6	1	18	50	0.95
SEM846010206S	RO.5	1.0	6	1	20	50	0.95
SEM846010226S	RO.5	1.0	6	1	22	60	0.95
SEM846010266S	RO.5	1.0	6	1	26	60	0.95
SEM846010306S	RO.5	1.0	6	1	30	70	0.95
SEM846015036S	RO.75	1.5	6	1.5	3	50	1.45
SEM846015046S	RO.75	1.5	6	1.5	4	50	1.45
SEM846015066S	RO.75	1.5	6	1.5	6	50	1.45
SEM846015086S	RO.75	1.5	6	1.5	8	50	1.45
SEM846015106S	RO.75	1.5	6	1.5	10	50	1.45
SEM846015126S	RO.75	1.5	6	1.5	12	50	1.45
SEM846015146S	RO.75	1.5	6	1.5	14	50	1.45
SEM846015166S	RO.75	1.5	6	1.5	16	50	1.45
SEM846015186S	RO.75	1.5	6	1.5	18	50	1.45
SEM846015206S	RO.75	1.5	6	1.5	20	50	1.45
SEM846015226S	RO.75	1.5	6	1.5	22	60	1.45
SEM846015266S	RO.75	1.5	6	1.5	26	60	1.45
SEM846015306S	RO.75	1.5	6	1.5	30	70	1.45
SEM846015356S	RO.75	1.5	6	1.5	35	70	1.45
SEM846015406S	RO.75	1.5	6	1.5	40	80	1.45
SEM846020046S	R1.0	2.0	6	2	4	50	1.95
SEM846020066S	R1.0	2.0	6	2	6	50	1.95

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEM846 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK BALL NOSE (6mm shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Due to unique ball nose geometry and cutting edges, cutting force decreased, and wear resistance increased.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.



◇ Call for Availability


Unit : mm

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R	D1	D2	L1	L3	L2	D3
SEM846020086S	R1.0	2.0	6	2	8	50	1.95
SEM846020106S	R1.0	2.0	6	2	10	50	1.95
SEM846020126S	R1.0	2.0	6	2	12	50	1.95
SEM846020146S	R1.0	2.0	6	2	14	50	1.95
SEM846020166S	R1.0	2.0	6	2	16	50	1.95
SEM846020186S	R1.0	2.0	6	2	18	50	1.95
SEM846020206S	R1.0	2.0	6	2	20	50	1.95
SEM846020226S	R1.0	2.0	6	2	22	60	1.95
SEM846020266S	R1.0	2.0	6	2	26	60	1.95
SEM846020306S	R1.0	2.0	6	2	30	70	1.95
SEM846020356S	R1.0	2.0	6	2	35	70	1.95
SEM846020406S	R1.0	2.0	6	2	40	80	1.95
SEM846020456S	R1.0	2.0	6	2	45	90	1.95
SEM846020506S	R1.0	2.0	6	2	50	100	1.95

Mill Dia. Tolerance (mm)	Radius Tolerance (mm)	Shank Dia. Tolerance
0~-0.012	±0.005	h6

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEMD99 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE CORNER RADIUS (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available aashort, regular and long shank end mills.
- ▶ Available various corner radius end mills, from 0.02 mm to 5.0mm corner radius.



◇ Call for Availability

Unit : mm

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2	Remark
SEMD99002002	RO.02	0.2	4	0.4	40	-
SEMD99002005	RO.05	0.2	4	0.4	40	-
SEMD99003002	RO.02	0.3	4	0.6	40	-
SEMD99003005	RO.05	0.3	4	0.6	40	-
SEMD99004005	RO.05	0.4	4	0.8	40	-
SEMD9900401	RO.1	0.4	4	0.8	40	-
SEMD99005005	RO.05	0.5	4	1.0	40	-
SEMD9900501	RO.1	0.5	4	1.0	40	-
SEMD99006005	RO.05	0.6	4	1.2	40	-
SEMD9900601	RO.1	0.6	4	1.2	40	-
SEMD9900602	RO.2	0.6	4	1.2	40	-
SEMD99007005	RO.05	0.7	4	1.4	40	-
SEMD9900701	RO.1	0.7	4	1.4	40	-
SEMD9900702	RO.2	0.7	4	1.4	40	-
SEMD99008005	RO.05	0.8	4	1.6	40	-
SEMD9900801	RO.1	0.8	4	1.6	40	-
SEMD9900802	RO.2	0.8	4	1.6	40	-
SEMD99009005	RO.05	0.9	4	1.8	40	-
SEMD9900901	RO.1	0.9	4	1.8	40	-
SEMD99010005	RO.05	1.0	6	2.5	50	-
SEMD9901001	RO.1	1.0	6	2.5	50	-
SEMD9901002	RO.2	1.0	6	2.5	50	-
SEMD9901003	RO.3	1.0	6	2.5	50	-
SEMD99012005	RO.05	1.2	6	3	50	-
SEMD9901201	RO.1	1.2	6	3	50	-
SEMD9901202	RO.2	1.2	6	3	50	-
SEMD9901203	RO.3	1.2	6	3	50	-
SEMD99015005	RO.05	1.5	6	4	50	-
SEMD9901501	RO.1	1.5	6	4	50	-

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEMD99 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE CORNER RADIUS (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available short, regular and long shank end mills.
- ▶ Available various corner radius end mills, from 0.02 mm to 5.0mm corner radius.



◇ Call for Availability


Unit : mm

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	Remark
	R	D1	D2	L1	L2	
SEMD9901502	RO.2	1.5	6	4	50	-
SEMD9901503	RO.3	1.5	6	4	50	-
SEMD9901505	RO.5	1.5	6	4	50	-
SEMD9902001	RO.1	2.0	6	6	50	-
SEMD9902002	RO.2	2.0	6	6	50	-
SEMD9902003	RO.3	2.0	6	6	50	-
SEMD9902005	RO.5	2.0	6	6	50	-
SEMD9902501	RO.1	2.5	6	7	60	-
SEMD9902502	RO.2	2.5	6	7	60	-
SEMD9902503	RO.3	2.5	6	7	60	-
SEMD9902505	RO.5	2.5	6	7	60	-
SEMD9903001	RO.1	3.0	6	8	60	-
SEMD9903002	RO.2	3.0	6	8	60	-
SEMD9903003	RO.3	3.0	6	8	60	-
SEMD9903005	RO.5	3.0	6	8	60	-
SEMD9903010	R1.0	3.0	6	8	60	-
SEMD9903501	RO.1	3.5	6	10	70	-
SEMD9903502	RO.2	3.5	6	10	70	-
SEMD9903503	RO.3	3.5	6	10	70	-
SEMD9903505	RO.5	3.5	6	10	70	-
SEMD99040014S	RO.1	4.0	4	10	70	4mm Shank
SEMD99040024S	RO.2	4.0	4	10	70	4mm Shank
SEMD99040034S	RO.3	4.0	4	10	70	4mm Shank
SEMD99040054S	RO.5	4.0	4	10	70	4mm Shank
SEMD99040104S	R1.0	4.0	4	10	70	4mm Shank
SEMD99040011004S	RO.1	4.0	4	10	100	4mm Shank
SEMD99040021004S	RO.2	4.0	4	10	100	4mm Shank
SEMD99040031004S	RO.3	4.0	4	10	100	4mm Shank
SEMD99040051004S	RO.5	4.0	4	10	100	4mm Shank

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEMD99 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE CORNER RADIUS (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available short, regular and long shank end mills.
- ▶ Available various corner radius end mills, from 0.02 mm to 5.0mm corner radius.



◇ Call for Availability


Unit : mm

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	Remark
	R	D1	D2	L1	L2	
SEMD99040101004S	R1.0	4.0	4	10	100	4mm Shank
SEMD9904001	RO.1	4.0	6	10	70	Regular
SEMD9904002	RO.2	4.0	6	10	70	Regular
SEMD9904003	RO.3	4.0	6	10	70	Regular
SEMD9904005	RO.5	4.0	6	10	70	Regular
SEMD9904010	R1.0	4.0	6	10	70	Regular
SEMD9904501	RO.1	4.5	6	11	80	-
SEMD9904502	RO.2	4.5	6	11	80	-
SEMD9904503	RO.3	4.5	6	11	80	-
SEMD9904505	RO.5	4.5	6	11	80	-
SEMD9905001	RO.1	5.0	6	13	90	-
SEMD9905002	RO.2	5.0	6	13	90	-
SEMD9905003	RO.3	5.0	6	13	90	-
SEMD9905005	RO.5	5.0	6	13	90	-
SEMD9905010	R1.0	5.0	6	13	90	-
SEMD9905501	RO.1	5.5	6	13	90	-
SEMD9905502	RO.2	5.5	6	13	90	-
SEMD9905503	RO.3	5.5	6	13	90	-
SEMD9905505	RO.5	5.5	6	13	90	-
SEMD9905510	R1.0	5.5	6	13	90	-
SEMD9906002060	RO.2	6.0	6	15	60	Short
SEMD9906003060	RO.3	6.0	6	15	60	Short
SEMD9906005060	RO.5	6.0	6	15	60	Short
SEMD9906010060	R1.0	6.0	6	15	60	Short
SEMD9906001	RO.1	6.0	6	15	90	Regular
SEMD9906002	RO.2	6.0	6	15	90	Regular
SEMD9906003	RO.3	6.0	6	15	90	Regular
SEMD9906005	RO.5	6.0	6	15	90	Regular
SEMD9906010	R1.0	6.0	6	15	90	Regular

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEMD99 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE CORNER RADIUS (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available short, regular and long shank end mills.
- ▶ Available various corner radius end mills, from 0.02 mm to 5.0mm corner radius.



◇ Call for Availability

Unit : mm

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	Remark
	R	D1	D2	L1	L2	
SEMD9906015	R1.5	6.0	6	15	90	Regular
SEMD9906020	R2.0	6.0	6	15	90	Regular
SEMD9906005	R0.5	6.0	6	15	110	Long Shank
SEMD9906010110	R1.0	6.0	6	15	110	Long Shank
SEMD9906005130	R0.5	6.0	6	15	130	Long Shank
SEMD9906010130	R1.0	6.0	6	15	130	Long Shank
SEMD9907001	R0.1	7.0	8	16	90	-
SEMD9907002	R0.2	7.0	8	16	90	-
SEMD9907003	R0.3	7.0	8	16	90	-
SEMD9907005	R0.5	7.0	8	16	90	-
SEMD9907010	R1.0	7.0	8	16	90	-
SEMD9907020	R2.0	7.0	8	16	90	-
SEMD9908003070	R0.3	8.0	8	20	70	Short
SEMD9908005070	R0.5	8.0	8	20	70	Short
SEMD9908010070	R1.0	8.0	8	20	70	Short
SEMD9908001	R0.1	8.0	8	20	100	Regular
SEMD9908002	R0.2	8.0	8	20	100	Regular
SEMD9908003	R0.3	8.0	8	20	100	Regular
SEMD9908005	R0.5	8.0	8	20	100	Regular
SEMD9908010	R1.0	8.0	8	20	100	Regular
SEMD9908015	R1.5	8.0	8	20	100	Regular
SEMD9908020	R2.0	8.0	8	20	100	Regular
SEMD9908025	R2.5	8.0	8	20	100	Regular
SEMD9908030	R3.0	8.0	8	20	100	Regular
SEMD9908005120	R0.5	8.0	8	20	120	Long Shank
SEMD9908010120	R1.0	8.0	8	20	120	Long Shank
SEMD9908015150	R0.5	8.0	8	20	150	Long Shank
SEMD9908010150	R1.0	8.0	8	20	150	Long Shank
SEMD9910003075	R0.3	10.0	10	25	75	Short

▶ NEXT PAGE

◎ : Excellent ○ : Good



P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	◎	○			○							



SEMD99 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE CORNER RADIUS (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available short, regular and long shank end mills.
- ▶ Available various corner radius end mills, from 0.02 mm to 5.0mm corner radius.



◇ Call for Availability

Unit : mm

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	Remark
	R	D1	D2	L1	L2	
SEMD9910005075	R0.5	10.0	10	25	75	Short
SEMD9910010075	R1.0	10.0	10	25	75	Short
SEMD9910001	R0.1	10.0	10	25	100	Regular
SEMD9910002	R0.2	10.0	10	25	100	Regular
SEMD9910003	R0.3	10.0	10	25	100	Regular
SEMD9910005	R0.5	10.0	10	25	100	Regular
SEMD9910010	R1.0	10.0	10	25	100	Regular
SEMD9910015	R1.5	10.0	10	25	100	Regular
SEMD9910020	R2.0	10.0	10	25	100	Regular
SEMD9910025	R2.5	10.0	10	25	100	Regular
SEMD9910030	R3.0	10.0	10	25	100	Regular
SEMD9910040	R4.0	10.0	10	25	100	Regular
SEMD9910005130	R0.5	10.0	10	25	130	Long Shank
SEMD9910010130	R1.0	10.0	10	25	130	Long Shank
SEMD9910005150	R0.5	10.0	10	25	150	Long Shank
SEMD9910010150	R1.0	10.0	10	25	150	Long Shank
SEMD9911002	R0.2	11.0	12	25	110	-
SEMD9911003	R0.3	11.0	12	25	110	-
SEMD9911005	R0.5	11.0	12	25	110	-
SEMD9911010	R1.0	11.0	12	25	110	-
SEMD9911020	R2.0	11.0	12	25	110	-
SEMD9912003080	R0.3	12.0	12	30	80	Short
SEMD9912005080	R0.5	12.0	12	30	80	Short
SEMD9912010080	R1.0	12.0	12	30	80	Short
SEMD9912001	R0.1	12.0	12	30	110	Regular
SEMD9912002	R0.2	12.0	12	30	110	Regular
SEMD9912003	R0.3	12.0	12	30	110	Regular
SEMD9912005	R0.5	12.0	12	30	110	Regular
SEMD9912010	R1.0	12.0	12	30	110	Regular

▶ NEXT PAGE

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	◎	○			○							

YG 4G MILL END MILLS

SEMD99 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE CORNER RADIUS (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available short, regular and long shank end mills.
- ▶ Available various corner radius end mills, from 0.02 mm to 5.0mm corner radius.



MG 2 30° ±0.010 ±0.015 PLAIN P.820

◇ Call for Availability

Unit : mm

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2	Remark
SEMD9912015	R1.5	12.0	12	30	110	Regular
SEMD9912020	R2.0	12.0	12	30	110	Regular
SEMD9912025	R2.5	12.0	12	30	110	Regular
SEMD9912030	R3.0	12.0	12	30	110	Regular
SEMD9912040	R4.0	12.0	12	30	110	Regular
SEMD9912050	R5.0	12.0	12	30	110	Regular
SEMD9912005130	RO.5	12.0	12	30	130	Long Shank
SEMD9912010130	R1.0	12.0	12	30	130	Long Shank
SEMD9912005150	RO.5	12.0	12	30	150	Long Shank
SEMD9912010150	R1.0	12.0	12	30	150	Long Shank
SEMD9914005	RO.5	14.0	16	35	150	-
SEMD9914010	R1.0	14.0	16	35	150	-
SEMD9914020	R2.0	14.0	16	35	150	-
SEMD9916005	RO.5	16.0	16	32	150	-
SEMD9916010	R1.0	16.0	16	32	150	-
SEMD9916015	R1.5	16.0	16	32	150	-
SEMD9916020	R2.0	16.0	16	32	150	-
SEMD9920005	RO.5	20.0	20	38	150	-
SEMD9920010	R1.0	20.0	20	38	150	-
SEMD9920015	R1.5	20.0	20	38	150	-
SEMD9920020	R2.0	20.0	20	38	150	-

Size	Corner Radius Tolerance (mm)	Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
up to Ø6	±0.010	0~-0.012	h6
over Ø6	±0.015	0~-0.015	

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							

YG 4G MILL END MILLS

SEME61 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available various products like regular length and long shank end mills etc.
- ▶ Available various corner radius end mills, from min. 0.02mm corner radius to max. 2.0 mm corner radius.
- ▶ Available more various effective length and overall length end mills than previous standard products.



MG 2 30° ±0.010 ±0.015 PLAIN P.821~823

◇ Call for Availability

Unit : mm

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Remark
SEME61002002005	RO.02	0.2	4	0.3	0.5	40	0.17	-
SEME6100200201	RO.02	0.2	4	0.3	1	40	0.17	-
SEME61002002015	RO.02	0.2	4	0.3	1.5	40	0.17	-
SEME6100200202	RO.02	0.2	4	0.3	2	40	0.17	-
SEME61002005005	RO.05	0.2	4	0.3	0.5	40	0.17	-
SEME6100200501	RO.05	0.2	4	0.3	1	40	0.17	-
SEME61002005015	RO.05	0.2	4	0.3	1.5	40	0.17	-
SEME6100200502	RO.05	0.2	4	0.3	2	40	0.17	-
SEME6100300201	RO.02	0.3	4	0.5	1	40	0.27	-
SEME6100300202	RO.02	0.3	4	0.5	2	40	0.27	-
SEME6100300203	RO.02	0.3	4	0.5	3	40	0.27	-
SEME6100300501	RO.05	0.3	4	0.5	1	40	0.27	-
SEME6100300502	RO.05	0.3	4	0.5	2	40	0.27	-
SEME6100300503	RO.05	0.3	4	0.5	3	40	0.27	-
SEME6100400501	RO.05	0.4	4	0.6	1	40	0.37	-
SEME61004005015	RO.05	0.4	4	0.6	1.5	40	0.37	-
SEME6100400502	RO.05	0.4	4	0.6	2	40	0.37	-
SEME61004005025	RO.05	0.4	4	0.6	2.5	40	0.37	-
SEME6100400503	RO.05	0.4	4	0.6	3	40	0.37	-
SEME6100400504	RO.05	0.4	4	0.6	4	40	0.37	-
SEME610040101	RO.1	0.4	4	0.6	1	40	0.37	-
SEME6100401015	RO.1	0.4	4	0.6	1.5	40	0.37	-
SEME610040102	RO.1	0.4	4	0.6	2	40	0.37	-
SEME6100401025	RO.1	0.4	4	0.6	2.5	40	0.37	-
SEME610040103	RO.1	0.4	4	0.6	3	40	0.37	-
SEME610040104	RO.1	0.4	4	0.6	4	40	0.37	-
SEME6100500501	RO.05	0.5	4	0.7	1	45	0.45	-
SEME61005005015	RO.05	0.5	4	0.7	1.5	45	0.45	-
SEME6100500502	RO.05	0.5	4	0.7	2	45	0.45	-
SEME61005005025	RO.05	0.5	4	0.7	2.5	45	0.45	-

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME61 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available various products like regular length and long shank end mills etc.
- ▶ Available various corner radius end mills, from min. 0.02mm corner radius to max. 2.0 mm corner radius.
- ▶ Available more various effective length and overall length end mills than previous standard products.



Call for Availability

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Remark
	R	D1	D2	L1	L3	L2	D3	
SEME6100500503	RO.05	0.5	4	0.7	3	45	0.45	-
SEME6100500504	RO.05	0.5	4	0.7	4	45	0.45	-
SEME6100500505	RO.05	0.5	4	0.7	5	45	0.45	-
SEME6100500506	RO.05	0.5	4	0.7	6	45	0.45	-
SEME610050101	RO.1	0.5	4	0.7	1	45	0.45	-
SEME6100501015	RO.1	0.5	4	0.7	1.5	45	0.45	-
SEME610050102	RO.1	0.5	4	0.7	2	45	0.45	-
SEME6100501025	RO.1	0.5	4	0.7	2.5	45	0.45	-
SEME610050103	RO.1	0.5	4	0.7	3	45	0.45	-
SEME610050104	RO.1	0.5	4	0.7	4	45	0.45	-
SEME610050105	RO.1	0.5	4	0.7	5	45	0.45	-
SEME610050106	RO.1	0.5	4	0.7	6	45	0.45	-
SEME6100600502	RO.05	0.6	4	0.9	2	45	0.55	-
SEME6100600503	RO.05	0.6	4	0.9	3	45	0.55	-
SEME6100600504	RO.05	0.6	4	0.9	4	45	0.55	-
SEME6100600506	RO.05	0.6	4	0.9	6	45	0.55	-
SEME6100600508	RO.05	0.6	4	0.9	8	45	0.55	-
SEME6100600510	RO.05	0.6	4	0.9	10	45	0.55	-
SEME610060102	RO.1	0.6	4	0.9	2	45	0.55	-
SEME610060103	RO.1	0.6	4	0.9	3	45	0.55	-
SEME610060104	RO.1	0.6	4	0.9	4	45	0.55	-
SEME610060106	RO.1	0.6	4	0.9	6	45	0.55	-
SEME610060108	RO.1	0.6	4	0.9	8	45	0.55	-
SEME610060110	RO.1	0.6	4	0.9	10	45	0.55	-
SEME610060202	RO.2	0.6	4	0.9	2	45	0.55	-
SEME610060203	RO.2	0.6	4	0.9	3	45	0.55	-
SEME610060204	RO.2	0.6	4	0.9	4	45	0.55	-
SEME610060206	RO.2	0.6	4	0.9	6	45	0.55	-
SEME610060208	RO.2	0.6	4	0.9	8	45	0.55	-
SEME610060210	RO.2	0.6	4	0.9	10	45	0.55	-

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME61 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available various products like regular length and long shank end mills etc.
- ▶ Available various corner radius end mills, from min. 0.02mm corner radius to max. 2.0 mm corner radius.
- ▶ Available more various effective length and overall length end mills than previous standard products.




Call for Availability

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Remark
	R	D1	D2	L1	L3	L2	D3	
SEME6100700502	RO.05	0.7	4	1.2	2	45	0.65	-
SEME6100700504	RO.05	0.7	4	1.2	4	45	0.65	-
SEME6100700506	RO.05	0.7	4	1.2	6	45	0.65	-
SEME6100700508	RO.05	0.7	4	1.2	8	45	0.65	-
SEME6100700510	RO.05	0.7	4	1.2	10	45	0.65	-
SEME610070102	RO.1	0.7	4	1.2	2	45	0.65	-
SEME610070104	RO.1	0.7	4	1.2	4	45	0.65	-
SEME610070106	RO.1	0.7	4	1.2	6	45	0.65	-
SEME610070108	RO.1	0.7	4	1.2	8	45	0.65	-
SEME610070110	RO.1	0.7	4	1.2	10	45	0.65	-
SEME610070202	RO.2	0.7	4	1.2	2	45	0.65	-
SEME610070204	RO.2	0.7	4	1.2	4	45	0.65	-
SEME610070206	RO.2	0.7	4	1.2	6	45	0.65	-
SEME610070208	RO.2	0.7	4	1.2	8	45	0.65	-
SEME610070210	RO.2	0.7	4	1.2	10	45	0.65	-
SEME6100800502	RO.05	0.8	4	1.2	2	45	0.75	-
SEME6100800503	RO.05	0.8	4	1.2	3	45	0.75	-
SEME6100800504	RO.05	0.8	4	1.2	4	45	0.75	-
SEME6100800506	RO.05	0.8	4	1.2	6	45	0.75	-
SEME6100800508	RO.05	0.8	4	1.2	8	45	0.75	-
SEME6100800510	RO.05	0.8	4	1.2	10	45	0.75	-
SEME610080102	RO.1	0.8	4	1.2	2	45	0.75	-
SEME610080103	RO.1	0.8	4	1.2	3	45	0.75	-
SEME610080104	RO.1	0.8	4	1.2	4	45	0.75	-
SEME610080106	RO.1	0.8	4	1.2	6	45	0.75	-
SEME610080108	RO.1	0.8	4	1.2	8	45	0.75	-
SEME610080110	RO.1	0.8	4	1.2	10	45	0.75	-
SEME610080202	RO.2	0.8	4	1.2	2	45	0.75	-
SEME610080203	RO.2	0.8	4	1.2	3	45	0.75	-
SEME610080204	RO.2	0.8	4	1.2	4	45	0.75	-

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME61 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available various products like regular length and long shank end mills etc.
- ▶ Available various corner radius end mills, from min. 0.02mm corner radius to max. 2.0 mm corner radius.
- ▶ Available more various effective length and overall length end mills than previous standard products.



Call for Availability

Unit : mm

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Remark
	R	D1	D2	L1	L3	L2	D3	
SEME610080206	RO.2	0.8	4	1.2	6	45	0.75	-
SEME610080208	RO.2	0.8	4	1.2	8	45	0.75	-
SEME610080210	RO.2	0.8	4	1.2	10	45	0.75	-
SEME6101000503	RO.05	1.0	4	1.5	3	50	0.95	-
SEME6101000504	RO.05	1.0	4	1.5	4	50	0.95	-
SEME6101000506	RO.05	1.0	4	1.5	6	50	0.95	-
SEME6101000508	RO.05	1.0	4	1.5	8	50	0.95	-
SEME6101000510	RO.05	1.0	4	1.5	10	50	0.95	-
SEME6101000512	RO.05	1.0	4	1.5	12	50	0.95	-
SEME6101000514	RO.05	1.0	4	1.5	14	50	0.95	-
SEME6101000516	RO.05	1.0	4	1.5	16	50	0.95	-
SEME6101000520	RO.05	1.0	4	1.5	20	50	0.95	-
SEME610100103	RO.1	1.0	4	1.5	3	50	0.95	-
SEME610100104	RO.1	1.0	4	1.5	4	50	0.95	-
SEME610100106	RO.1	1.0	4	1.5	6	50	0.95	-
SEME610100108	RO.1	1.0	4	1.5	8	50	0.95	-
SEME610100110	RO.1	1.0	4	1.5	10	50	0.95	-
SEME610100112	RO.1	1.0	4	1.5	12	50	0.95	-
SEME610100114	RO.1	1.0	4	1.5	14	50	0.95	-
SEME610100116	RO.1	1.0	4	1.5	16	50	0.95	-
SEME610100120	RO.1	1.0	4	1.5	20	50	0.95	-
SEME610100203	RO.2	1.0	4	1.5	3	50	0.95	-
SEME610100204	RO.2	1.0	4	1.5	4	50	0.95	-
SEME610100206	RO.2	1.0	4	1.5	6	50	0.95	-
SEME610100208	RO.2	1.0	4	1.5	8	50	0.95	-
SEME610100210	RO.2	1.0	4	1.5	10	50	0.95	-
SEME610100212	RO.2	1.0	4	1.5	12	50	0.95	-
SEME610100214	RO.2	1.0	4	1.5	14	50	0.95	-
SEME610100216	RO.2	1.0	4	1.5	16	50	0.95	-
SEME610100220	RO.2	1.0	4	1.5	20	50	0.95	-

▶ NEXT PAGE

◎ : Excellent ○ : Good



P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	◎	○			○							



SEME61 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available various products like regular length and long shank end mills etc.
- ▶ Available various corner radius end mills, from min. 0.02mm corner radius to max. 2.0 mm corner radius.
- ▶ Available more various effective length and overall length end mills than previous standard products.



Call for Availability

Unit : mm

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Remark
	R	D1	D2	L1	L3	L2	D3	
SEME610100303	RO.3	1.0	4	1.5	3	50	0.95	-
SEME610100304	RO.3	1.0	4	1.5	4	50	0.95	-
SEME610100306	RO.3	1.0	4	1.5	6	50	0.95	-
SEME610100308	RO.3	1.0	4	1.5	8	50	0.95	-
SEME610100310	RO.3	1.0	4	1.5	10	50	0.95	-
SEME610100312	RO.3	1.0	4	1.5	12	50	0.95	-
SEME610100314	RO.3	1.0	4	1.5	14	50	0.95	-
SEME610100316	RO.3	1.0	4	1.5	16	50	0.95	-
SEME610100320	RO.3	1.0	4	1.5	20	50	0.95	-
SEME6101200503	RO.05	1.2	4	1.8	3	50	1.15	-
SEME6101200504	RO.05	1.2	4	1.8	4	50	1.15	-
SEME6101200506	RO.05	1.2	4	1.8	6	50	1.15	-
SEME6101200508	RO.05	1.2	4	1.8	8	50	1.15	-
SEME6101200510	RO.05	1.2	4	1.8	10	50	1.15	-
SEME6101200512	RO.05	1.2	4	1.8	12	50	1.15	-
SEME6101200516	RO.05	1.2	4	1.8	16	50	1.15	-
SEME6101200520	RO.05	1.2	4	1.8	20	50	1.15	-
SEME610120103	RO.1	1.2	4	1.8	3	50	1.15	-
SEME610120104	RO.1	1.2	4	1.8	4	50	1.15	-
SEME610120106	RO.1	1.2	4	1.8	6	50	1.15	-
SEME610120108	RO.1	1.2	4	1.8	8	50	1.15	-
SEME610120110	RO.1	1.2	4	1.8	10	50	1.15	-
SEME610120112	RO.1	1.2	4	1.8	12	50	1.15	-
SEME610120116	RO.1	1.2	4	1.8	16	50	1.15	-
SEME610120120	RO.1	1.2	4	1.8	20	50	1.15	-
SEME610120203	RO.2	1.2	4	1.8	3	50	1.15	-
SEME610120204	RO.2	1.2	4	1.8	4	50	1.15	-
SEME610120206	RO.2	1.2	4	1.8	6	50	1.15	-
SEME610120208	RO.2	1.2	4	1.8	8	50	1.15	-
SEME610120210	RO.2	1.2	4	1.8	10	50	1.15	-

▶ NEXT PAGE

◎ : Excellent ○ : Good



P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	◎	○			○							



SEME61 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available various products like regular length and long shank end mills etc.
- ▶ Available various corner radius end mills, from min. 0.02mm corner radius to max. 2.0 mm corner radius.
- ▶ Available more various effective length and overall length end mills than previous standard products.



Call for Availability

Unit : mm

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Remark
	R	D1	D2	L1	L3	L2	D3	
SEME610120212	RO.2	1.2	4	1.8	12	50	1.15	-
SEME610120216	RO.2	1.2	4	1.8	16	50	1.15	-
SEME610120220	RO.2	1.2	4	1.8	20	50	1.15	-
SEME610120303	RO.3	1.2	4	1.8	3	50	1.15	-
SEME610120304	RO.3	1.2	4	1.8	4	50	1.15	-
SEME610120306	RO.3	1.2	4	1.8	6	50	1.15	-
SEME610120308	RO.3	1.2	4	1.8	8	50	1.15	-
SEME610120310	RO.3	1.2	4	1.8	10	50	1.15	-
SEME610120312	RO.3	1.2	4	1.8	12	50	1.15	-
SEME610120316	RO.3	1.2	4	1.8	16	50	1.15	-
SEME610120320	RO.3	1.2	4	1.8	20	50	1.15	-
SEME6101500504	RO.05	1.5	4	2.3	4	50	1.45	-
SEME6101500506	RO.05	1.5	4	2.3	6	50	1.45	-
SEME6101500508	RO.05	1.5	4	2.3	8	50	1.45	-
SEME6101500510	RO.05	1.5	4	2.3	10	50	1.45	-
SEME6101500512	RO.05	1.5	4	2.3	12	50	1.45	-
SEME6101500514	RO.05	1.5	4	2.3	14	50	1.45	-
SEME6101500516	RO.05	1.5	4	2.3	16	50	1.45	-
SEME6101500520	RO.05	1.5	4	2.3	20	50	1.45	-
SEME6101500522	RO.05	1.5	4	2.3	22	60	1.45	-
SEME6101500526	RO.05	1.5	4	2.3	26	60	1.45	-
SEME610150104	RO.1	1.5	4	2.3	4	50	1.45	-
SEME610150106	RO.1	1.5	4	2.3	6	50	1.45	-
SEME610150108	RO.1	1.5	4	2.3	8	50	1.45	-
SEME610150110	RO.1	1.5	4	2.3	10	50	1.45	-
SEME610150112	RO.1	1.5	4	2.3	12	50	1.45	-
SEME610150114	RO.1	1.5	4	2.3	14	50	1.45	-
SEME610150116	RO.1	1.5	4	2.3	16	50	1.45	-
SEME610150120	RO.1	1.5	4	2.3	20	50	1.45	-
SEME610150122	RO.1	1.5	4	2.3	22	60	1.45	-

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME61 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available various products like regular length and long shank end mills etc.
- ▶ Available various corner radius end mills, from min. 0.02mm corner radius to max. 2.0 mm corner radius.
- ▶ Available more various effective length and overall length end mills than previous standard products.



Call for Availability


Unit : mm

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Remark
	R	D1	D2	L1	L3	L2	D3	
SEME610150126	RO.1	1.5	4	2.3	26	60	1.45	-
SEME610150204	RO.2	1.5	4	2.3	4	50	1.45	-
SEME610150206	RO.2	1.5	4	2.3	6	50	1.45	-
SEME610150208	RO.2	1.5	4	2.3	8	50	1.45	-
SEME610150210	RO.2	1.5	4	2.3	10	50	1.45	-
SEME610150212	RO.2	1.5	4	2.3	12	50	1.45	-
SEME610150214	RO.2	1.5	4	2.3	14	50	1.45	-
SEME610150216	RO.2	1.5	4	2.3	16	50	1.45	-
SEME610150220	RO.2	1.5	4	2.3	20	50	1.45	-
SEME610150222	RO.2	1.5	4	2.3	22	60	1.45	-
SEME610150226	RO.2	1.5	4	2.3	26	60	1.45	-
SEME610150304	RO.3	1.5	4	2.3	4	50	1.45	-
SEME610150306	RO.3	1.5	4	2.3	6	50	1.45	-
SEME610150308	RO.3	1.5	4	2.3	8	50	1.45	-
SEME610150310	RO.3	1.5	4	2.3	10	50	1.45	-
SEME610150312	RO.3	1.5	4	2.3	12	50	1.45	-
SEME610150314	RO.3	1.5	4	2.3	14	50	1.45	-
SEME610150316	RO.3	1.5	4	2.3	16	50	1.45	-
SEME610150320	RO.3	1.5	4	2.3	20	50	1.45	-
SEME610150322	RO.3	1.5	4	2.3	22	60	1.45	-
SEME610150326	RO.3	1.5	4	2.3	26	60	1.45	-
SEME610150504	RO.5	1.5	4	2.3	4	50	1.45	-
SEME610150506	RO.5	1.5	4	2.3	6	50	1.45	-
SEME610150508	RO.5	1.5	4	2.3	8	50	1.45	-
SEME610150510	RO.5	1.5	4	2.3	10	50	1.45	-
SEME610150512	RO.5	1.5	4	2.3	12	50	1.45	-
SEME610150514	RO.5	1.5	4	2.3	14	50	1.45	-
SEME610150516	RO.5	1.5	4	2.3	16	50	1.45	-
SEME610150520	RO.5	1.5	4	2.3	20	50	1.45	-
SEME610150522	RO.5	1.5	4	2.3	22	60	1.45	-

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME61 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available various products like regular length and long shank end mills etc.
- ▶ Available various corner radius end mills, from min. 0.02mm corner radius to max. 2.0 mm corner radius.
- ▶ Available more various effective length and overall length end mills than previous standard products.




MG 2 30° ±0.010 ±0.015 PLAIN P.821~823 ◆ Call for Availability

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Remark
	R	D1	D2	L1	L3	L2	D3	
SEME610150526	RO.5	1.5	4	2.3	26	60	1.45	-
SEME610200106	RO.1	2.0	4	3	6	50	1.95	-
SEME610200108	RO.1	2.0	4	3	8	50	1.95	-
SEME610200110	RO.1	2.0	4	3	10	50	1.95	-
SEME610200112	RO.1	2.0	4	3	12	50	1.95	-
SEME610200114	RO.1	2.0	4	3	14	50	1.95	-
SEME610200116	RO.1	2.0	4	3	16	50	1.95	-
SEME610200120	RO.1	2.0	4	3	20	50	1.95	-
SEME610200122	RO.1	2.0	4	3	22	60	1.95	-
SEME610200126	RO.1	2.0	4	3	26	60	1.95	-
SEME610200130	RO.1	2.0	4	3	30	70	1.95	-
SEME610200206	RO.2	2.0	4	3	6	50	1.95	-
SEME610200208	RO.2	2.0	4	3	8	50	1.95	-
SEME610200210	RO.2	2.0	4	3	10	50	1.95	-
SEME610200212	RO.2	2.0	4	3	12	50	1.95	-
SEME610200214	RO.2	2.0	4	3	14	50	1.95	-
SEME610200216	RO.2	2.0	4	3	16	50	1.95	-
SEME610200220	RO.2	2.0	4	3	20	50	1.95	-
SEME610200222	RO.2	2.0	4	3	22	60	1.95	-
SEME610200226	RO.2	2.0	4	3	26	60	1.95	-
SEME610200230	RO.2	2.0	4	3	30	70	1.95	-
SEME610200306	RO.3	2.0	4	3	6	50	1.95	-
SEME610200308	RO.3	2.0	4	3	8	50	1.95	-
SEME610200310	RO.3	2.0	4	3	10	50	1.95	-
SEME610200312	RO.3	2.0	4	3	12	50	1.95	-
SEME610200314	RO.3	2.0	4	3	14	50	1.95	-
SEME610200316	RO.3	2.0	4	3	16	50	1.95	-
SEME610200320	RO.3	2.0	4	3	20	50	1.95	-
SEME610200322	RO.3	2.0	4	3	22	60	1.95	-
SEME610200326	RO.3	2.0	4	3	26	60	1.95	-

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME61 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available various products like regular length and long shank end mills etc.
- ▶ Available various corner radius end mills, from min. 0.02mm corner radius to max. 2.0 mm corner radius.
- ▶ Available more various effective length and overall length end mills than previous standard products.




MG 2 30° ±0.010 ±0.015 PLAIN P.821~823 ◆ Call for Availability

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Remark
	R	D1	D2	L1	L3	L2	D3	
SEME610200330	RO.3	2.0	4	3	30	70	1.95	-
SEME610200506	RO.5	2.0	4	3	6	50	1.95	-
SEME610200508	RO.5	2.0	4	3	8	50	1.95	-
SEME610200510	RO.5	2.0	4	3	10	50	1.95	-
SEME610200512	RO.5	2.0	4	3	12	50	1.95	-
SEME610200514	RO.5	2.0	4	3	14	50	1.95	-
SEME610200516	RO.5	2.0	4	3	16	50	1.95	-
SEME610200520	RO.5	2.0	4	3	20	50	1.95	-
SEME610200522	RO.5	2.0	4	3	22	60	1.95	-
SEME610200526	RO.5	2.0	4	3	26	60	1.95	-
SEME610200530	RO.5	2.0	4	3	30	70	1.95	-
SEME610250108	RO.1	2.5	4	4	8	50	2.40	-
SEME610250110	RO.1	2.5	4	4	10	50	2.40	-
SEME610250112	RO.1	2.5	4	4	12	50	2.40	-
SEME610250114	RO.1	2.5	4	4	14	50	2.40	-
SEME610250116	RO.1	2.5	4	4	16	50	2.40	-
SEME610250120	RO.1	2.5	4	4	20	50	2.40	-
SEME610250126	RO.1	2.5	4	4	26	60	2.40	-
SEME610250130	RO.1	2.5	4	4	30	70	2.40	-
SEME610250208	RO.2	2.5	4	4	8	50	2.40	-
SEME610250210	RO.2	2.5	4	4	10	50	2.40	-
SEME610250212	RO.2	2.5	4	4	12	50	2.40	-
SEME610250214	RO.2	2.5	4	4	14	50	2.40	-
SEME610250216	RO.2	2.5	4	4	16	50	2.40	-
SEME610250220	RO.2	2.5	4	4	20	50	2.40	-
SEME610250226	RO.2	2.5	4	4	26	60	2.40	-
SEME610250230	RO.2	2.5	4	4	30	70	2.40	-
SEME610250308	RO.3	2.5	4	4	8	50	2.40	-
SEME610250310	RO.3	2.5	4	4	10	50	2.40	-
SEME610250312	RO.3	2.5	4	4	12	50	2.40	-

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME61 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available various products like regular length and long shank end mills etc.
- ▶ Available various corner radius end mills, from min. 0.02mm corner radius to max. 2.0 mm corner radius.
- ▶ Available more various effective length and overall length end mills than previous standard products.




Call for Availability

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Remark
	R	D1	D2	L1	L3	L2	D3	
SEME610250314	RO.3	2.5	4	4	14	50	2.40	-
SEME610250316	RO.3	2.5	4	4	16	50	2.40	-
SEME610250320	RO.3	2.5	4	4	20	50	2.40	-
SEME610250326	RO.3	2.5	4	4	26	60	2.40	-
SEME610250330	RO.3	2.5	4	4	30	70	2.40	-
SEME610250508	RO.5	2.5	6	4	8	50	2.40	-
SEME610250510	RO.5	2.5	6	4	10	50	2.40	-
SEME610250512	RO.5	2.5	6	4	12	50	2.40	-
SEME610250514	RO.5	2.5	6	4	14	50	2.40	-
SEME610250516	RO.5	2.5	6	4	16	50	2.40	-
SEME610250520	RO.5	2.5	6	4	20	50	2.40	-
SEME610250526	RO.5	2.5	6	4	26	60	2.40	-
SEME610250530	RO.5	2.5	6	4	30	70	2.40	-
SEME610300108	RO.1	3.0	6	4.5	8	50	2.85	-
SEME610300110	RO.1	3.0	6	4.5	10	50	2.85	-
SEME610300112	RO.1	3.0	6	4.5	12	50	2.85	-
SEME610300114	RO.1	3.0	6	4.5	14	60	2.85	-
SEME610300116	RO.1	3.0	6	4.5	16	60	2.85	-
SEME610300120	RO.1	3.0	6	4.5	20	60	2.85	-
SEME610300126	RO.1	3.0	6	4.5	26	65	2.85	-
SEME610300130	RO.1	3.0	6	4.5	30	70	2.85	-
SEME610300135	RO.1	3.0	6	4.5	35	70	2.85	-
SEME610300140	RO.1	3.0	6	4.5	40	80	2.85	-
SEME610300208	RO.2	3.0	6	4.5	8	50	2.85	-
SEME610300210	RO.2	3.0	6	4.5	10	50	2.85	-
SEME610300212	RO.2	3.0	6	4.5	12	50	2.85	-
SEME610300214	RO.2	3.0	6	4.5	14	60	2.85	-
SEME610300216	RO.2	3.0	6	4.5	16	60	2.85	-
SEME610300220	RO.2	3.0	6	4.5	20	60	2.85	-
SEME610300226	RO.2	3.0	6	4.5	26	65	2.85	-

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME61 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available various products like regular length and long shank end mills etc.
- ▶ Available various corner radius end mills, from min. 0.02mm corner radius to max. 2.0 mm corner radius.
- ▶ Available more various effective length and overall length end mills than previous standard products.



Call for Availability

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Remark
	R	D1	D2	L1	L3	L2	D3	
SEME610300230	RO.2	3.0	6	4.5	30	70	2.85	-
SEME610300235	RO.2	3.0	6	4.5	35	70	2.85	-
SEME610300240	RO.2	3.0	6	4.5	40	80	2.85	-
SEME610300308	RO.3	3.0	6	4.5	8	50	2.85	-
SEME610300310	RO.3	3.0	6	4.5	10	50	2.85	-
SEME610300312	RO.3	3.0	6	4.5	12	50	2.85	-
SEME610300314	RO.3	3.0	6	4.5	14	60	2.85	-
SEME610300316	RO.3	3.0	6	4.5	16	60	2.85	-
SEME610300320	RO.3	3.0	6	4.5	20	60	2.85	-
SEME610300326	RO.3	3.0	6	4.5	26	65	2.85	-
SEME610300330	RO.3	3.0	6	4.5	30	70	2.85	-
SEME610300335	RO.3	3.0	6	4.5	35	70	2.85	-
SEME610300340	RO.3	3.0	6	4.5	40	80	2.85	-
SEME610300508	RO.5	3.0	6	4.5	8	50	2.85	-
SEME610300510	RO.5	3.0	6	4.5	10	50	2.85	-
SEME610300512	RO.5	3.0	6	4.5	12	50	2.85	-
SEME610300514	RO.5	3.0	6	4.5	14	60	2.85	-
SEME610300516	RO.5	3.0	6	4.5	16	60	2.85	-
SEME610300520	RO.5	3.0	6	4.5	20	60	2.85	-
SEME610300526	RO.5	3.0	6	4.5	26	65	2.85	-
SEME610300530	RO.5	3.0	6	4.5	30	70	2.85	-
SEME610300535	RO.5	3.0	6	4.5	35	70	2.85	-
SEME610300540	RO.5	3.0	6	4.5	40	80	2.85	-
SEME610301008	R1.0	3.0	6	4.5	8	50	2.85	-
SEME610301010	R1.0	3.0	6	4.5	10	50	2.85	-
SEME610301012	R1.0	3.0	6	4.5	12	50	2.85	-
SEME610301014	R1.0	3.0	6	4.5	14	60	2.85	-
SEME610301016	R1.0	3.0	6	4.5	16	60	2.85	-
SEME610301020	R1.0	3.0	6	4.5	20	60	2.85	-
SEME610301026	R1.0	3.0	6	4.5	26	65	2.85	-

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME61 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available various products like regular length and long shank end mills etc.
- ▶ Available various corner radius end mills, from min. 0.02mm corner radius to max. 2.0 mm corner radius.
- ▶ Available more various effective length and overall length end mills than previous standard products.



Call for Availability


Unit : mm

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Remark
SEME610301030	R1.0	3.0	6	4.5	30	70	2.85	-
SEME610301035	R1.0	3.0	6	4.5	35	70	2.85	-
SEME610301040	R1.0	3.0	6	4.5	40	80	2.85	-
SEME610400110	RO.1	4.0	6	6	10	50	3.85	-
SEME610400112	RO.1	4.0	6	6	12	50	3.85	-
SEME610400114	RO.1	4.0	6	6	14	60	3.85	-
SEME610400116	RO.1	4.0	6	6	16	60	3.85	-
SEME610400120	RO.1	4.0	6	6	20	60	3.85	-
SEME610400126	RO.1	4.0	6	6	26	65	3.85	-
SEME610400130	RO.1	4.0	6	6	30	70	3.85	-
SEME610400135	RO.1	4.0	6	6	35	70	3.85	-
SEME610400140	RO.1	4.0	6	6	40	80	3.85	-
SEME610400145	RO.1	4.0	6	6	45	90	3.85	-
SEME610400150	RO.1	4.0	6	6	50	100	3.85	-
SEME610400210	RO.2	4.0	6	6	10	50	3.85	-
SEME610400212	RO.2	4.0	6	6	12	50	3.85	-
SEME610400214	RO.2	4.0	6	6	14	60	3.85	-
SEME610400216	RO.2	4.0	6	6	16	60	3.85	-
SEME610400220	RO.2	4.0	6	6	20	60	3.85	-
SEME610400226	RO.2	4.0	6	6	26	65	3.85	-
SEME610400230	RO.2	4.0	6	6	30	70	3.85	-
SEME610400235	RO.2	4.0	6	6	35	70	3.85	-
SEME610400240	RO.2	4.0	6	6	40	80	3.85	-
SEME610400245	RO.2	4.0	6	6	45	90	3.85	-
SEME610400250	RO.2	4.0	6	6	50	100	3.85	-
SEME610400310	RO.3	4.0	6	6	10	50	3.85	-
SEME610400312	RO.3	4.0	6	6	12	50	3.85	-
SEME610400314	RO.3	4.0	6	6	14	50	3.85	-
SEME610400316	RO.3	4.0	6	6	16	50	3.85	-
SEME610400320	RO.3	4.0	6	6	20	50	3.85	-

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME61 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available various products like regular length and long shank end mills etc.
- ▶ Available various corner radius end mills, from min. 0.02mm corner radius to max. 2.0 mm corner radius.
- ▶ Available more various effective length and overall length end mills than previous standard products.



Call for Availability

Unit : mm

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Remark
SEME610400326	RO.3	4.0	6	6	26	65	3.85	-
SEME610400330	RO.3	4.0	6	6	30	70	3.85	-
SEME610400335	RO.3	4.0	6	6	35	70	3.85	-
SEME610400340	RO.3	4.0	6	6	40	80	3.85	-
SEME610400345	RO.3	4.0	6	6	45	90	3.85	-
SEME610400350	RO.3	4.0	6	6	50	100	3.85	-
SEME610400510	RO.5	4.0	6	6	10	50	3.85	-
SEME610400512	RO.5	4.0	6	6	12	50	3.85	-
SEME610400514	RO.5	4.0	6	6	14	60	3.85	-
SEME610400516	RO.5	4.0	6	6	16	60	3.85	-
SEME610400520	RO.5	4.0	6	6	20	60	3.85	-
SEME610400526	RO.5	4.0	6	6	26	65	3.85	-
SEME610400530	RO.5	4.0	6	6	30	70	3.85	-
SEME610400535	RO.5	4.0	6	6	35	70	3.85	-
SEME610400540	RO.5	4.0	6	6	40	80	3.85	-
SEME610400545	RO.5	4.0	6	6	45	90	3.85	-
SEME610400550	RO.5	4.0	6	6	50	100	3.85	-
SEME610401010	R1.0	4.0	6	6	10	50	3.85	-
SEME610401012	R1.0	4.0	6	6	12	50	3.85	-
SEME610401014	R1.0	4.0	6	6	14	60	3.85	-
SEME610401016	R1.0	4.0	6	6	16	60	3.85	-
SEME610401020	R1.0	4.0	6	6	20	60	3.85	-
SEME610401026	R1.0	4.0	6	6	26	65	3.85	-
SEME610401030	R1.0	4.0	6	6	30	70	3.85	-
SEME610401035	R1.0	4.0	6	6	35	70	3.85	-
SEME610401040	R1.0	4.0	6	6	40	80	3.85	-
SEME610401045	R1.0	4.0	6	6	45	90	3.85	-
SEME610401050	R1.0	4.0	6	6	50	100	3.85	-
SEME6105001	RO.1	5.0	6	8	15	60	4.85	-
SEME6105002	RO.2	5.0	6	8	15	60	4.85	-

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME61 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available various products like regular length and long shank end mills etc.
- ▶ Available various corner radius end mills, from min. 0.02mm corner radius to max. 2.0 mm corner radius.
- ▶ Available more various effective length and overall length end mills than previous standard products.



Call for Availability

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Remark
	R	D1	D2	L1	L3	L2	D3	
SEME6105003	RO.3	5.0	6	8	15	60	4.85	-
SEME6105005	RO.5	5.0	6	8	15	60	4.85	-
SEME6105010	R1.0	5.0	6	8	15	60	4.85	-
SEME6105015	R1.5	5.0	6	8	15	60	4.85	-
SEME6105020	R2.0	5.0	6	8	15	60	4.85	-
SEME6106001	RO.1	6.0	6	9	20	60	5.85	Regular
SEME6106002	RO.2	6.0	6	9	20	60	5.85	Regular
SEME6106003	RO.3	6.0	6	9	20	60	5.85	Regular
SEME6106005	RO.5	6.0	6	9	20	60	5.85	Regular
SEME6106010	R1.0	6.0	6	9	20	60	5.85	Regular
SEME6106015	R1.5	6.0	6	9	20	60	5.85	Regular
SEME6106020	R2.0	6.0	6	9	20	60	5.85	Regular
SEME6106003090	RO.3	6.0	6	15	30	90	5.85	Long Shank
SEME6106005090	RO.5	6.0	6	15	30	90	5.85	Long Shank
SEME6106010090	R1.0	6.0	6	15	30	90	5.85	Long Shank
SEME6108001	RO.1	8.0	8	12	25	70	7.70	Regular
SEME6108002	RO.2	8.0	8	12	25	70	7.70	Regular
SEME6108003	RO.3	8.0	8	12	25	70	7.70	Regular
SEME6108005	RO.5	8.0	8	12	25	70	7.70	Regular
SEME6108010	R1.0	8.0	8	12	25	70	7.70	Regular
SEME6108015	R1.5	8.0	8	12	25	70	7.70	Regular
SEME6108020	R2.0	8.0	8	12	25	70	7.70	Regular
SEME6108003100	RO.3	8.0	8	20	35	100	7.70	Long Shank
SEME6108005100	RO.5	8.0	8	20	35	100	7.70	Long Shank
SEME6108010100	R1.0	8.0	8	20	35	100	7.70	Long Shank
SEME6110001	RO.1	10.0	10	15	30	75	9.70	Regular
SEME6110002	RO.2	10.0	10	15	30	75	9.70	Regular
SEME6110003	RO.3	10.0	10	15	30	75	9.70	Regular
SEME6110005	RO.5	10.0	10	15	30	75	9.70	Regular
SEME6110010	R1.0	10.0	10	15	30	75	9.70	Regular

▶ NEXT PAGE

◎ : Excellent ○ : Good



P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	◎	○			○							



SEME61 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Available various products like regular length and long shank end mills etc.
- ▶ Available various corner radius end mills, from min. 0.02mm corner radius to max. 2.0 mm corner radius.
- ▶ Available more various effective length and overall length end mills than previous standard products.




Call for Availability

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Remark
	R	D1	D2	L1	L3	L2	D3	
SEME6110015	R1.5	10.0	10	15	30	75	9.70	Regular
SEME6110020	R2.0	10.0	10	15	30	75	9.70	Regular
SEME6110003100	RO.3	10.0	10	25	40	100	9.70	Long Shank
SEME6110005100	RO.5	10.0	10	25	40	100	9.70	Long Shank
SEME6110010100	R1.0	10.0	10	25	40	100	9.70	Long Shank
SEME6112002	RO.2	12.0	12	18	32	80	11.70	Regular
SEME6112003	RO.3	12.0	12	18	32	80	11.70	Regular
SEME6112005	RO.5	12.0	12	18	32	80	11.70	Regular
SEME6112010	R1.0	12.0	12	18	32	80	11.70	Regular
SEME6112015	R1.5	12.0	12	18	32	80	11.70	Regular
SEME6112020	R2.0	12.0	12	18	32	80	11.70	Regular
SEME6112003110	RO.3	12.0	12	30	50	110	11.70	Long Shank
SEME6112005110	RO.5	12.0	12	30	50	110	11.70	Long Shank
SEME6112010110	R1.0	12.0	12	30	50	110	11.70	Long Shank
SEME6116005	RO.5	16.0	16	20	35	100	15.70	Regular
SEME6116010	R1.0	16.0	16	20	35	100	15.70	Regular
SEME6116005150	RO.5	16.0	16	35	50	150	15.70	Long Shank
SEME6116010150	R1.0	16.0	16	35	50	150	15.70	Long Shank
SEME6120005	RO.5	20.0	20	25	40	100	19.70	Regular
SEME6120010	R1.0	20.0	20	25	40	100	19.70	Regular
SEME6120005150	RO.5	20.0	20	40	55	150	19.70	Long Shank
SEME6120010150	R1.0	20.0	20	40	55	150	19.70	Long Shank

Size	Corner Radius Tolerance (mm)	Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
up to Ø6	±0.010	0~-0.012	h6
over Ø6	±0.015	0~-0.015	

◎ : Excellent ○ : Good



P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	◎	○			○							



SEME01 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE CORNER RADIUS (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.
- ▶ Available various products like short, regular and long shank end mills etc.



◇ Call for Availability


Unit : mm

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2	Remark
SEME01010005	RO.05	1.0	6	2.5	50	-
SEME0101001	RO.1	1.0	6	2.5	50	-
SEME0101002	RO.2	1.0	6	2.5	50	-
SEME0101003	RO.3	1.0	6	2.5	50	-
SEME01012005	RO.05	1.2	6	3	50	-
SEME0101201	RO.1	1.2	6	3	50	-
SEME0101202	RO.2	1.2	6	3	50	-
SEME0101203	RO.3	1.2	6	3	50	-
SEME01015005	RO.05	1.5	6	4	50	-
SEME0101501	RO.1	1.5	6	4	50	-
SEME0101502	RO.2	1.5	6	4	50	-
SEME0101503	RO.3	1.5	6	4	50	-
SEME0101505	RO.5	1.5	6	4	50	-
SEME0102001	RO.1	2.0	6	6	50	-
SEME0102002	RO.2	2.0	6	6	50	-
SEME0102003	RO.3	2.0	6	6	50	-
SEME0102005	RO.5	2.0	6	6	50	-
SEME0102501	RO.1	2.5	6	7	60	-
SEME0102502	RO.2	2.5	6	7	60	-
SEME0102503	RO.3	2.5	6	7	60	-
SEME0102505	RO.5	2.5	6	7	60	-
SEME0103001	RO.1	3.0	6	8	60	-
SEME0103002	RO.2	3.0	6	8	60	-
SEME0103003	RO.3	3.0	6	8	60	-
SEME0103005	RO.5	3.0	6	8	60	-
SEME0103010	R1.0	3.0	6	8	60	-
SEME0103501	RO.1	3.5	6	10	70	-
SEME0103502	RO.2	3.5	6	10	70	-
SEME0103503	RO.3	3.5	6	10	70	-
SEME0103505	RO.5	3.5	6	10	70	-

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME01 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE CORNER RADIUS (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.
- ▶ Available various products like short, regular and long shank end mills etc.



◇ Call for Availability


Unit : mm

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2	Remark
SEME01040014S	RO.1	4.0	4	10	70	4mm Shank
SEME01040024S	RO.2	4.0	4	10	70	4mm Shank
SEME01040034S	RO.3	4.0	4	10	70	4mm Shank
SEME01040054S	RO.5	4.0	4	10	70	4mm Shank
SEME01040104S	R1.0	4.0	4	10	70	4mm Shank
SEME01040011004S	RO.1	4.0	4	10	100	4mm Shank
SEME01040021004S	RO.2	4.0	4	10	100	4mm Shank
SEME01040031004S	RO.3	4.0	4	10	100	4mm Shank
SEME01040051004S	RO.5	4.0	4	10	100	4mm Shank
SEME01040101004S	R1.0	4.0	4	10	100	4mm Shank
SEME0104001	RO.1	4.0	6	10	70	Regular
SEME0104002	RO.2	4.0	6	10	70	Regular
SEME0104003	RO.3	4.0	6	10	70	Regular
SEME0104005	RO.5	4.0	6	10	70	Regular
SEME0104010	R1.0	4.0	6	10	70	Regular
SEME0104501	RO.1	4.5	6	11	80	-
SEME0104502	RO.2	4.5	6	11	80	-
SEME0104503	RO.3	4.5	6	11	80	-
SEME0104505	RO.5	4.5	6	11	80	-
SEME0105001	RO.1	5.0	6	13	90	-
SEME0105002	RO.2	5.0	6	13	90	-
SEME0105003	RO.3	5.0	6	13	90	-
SEME0105005	RO.5	5.0	6	13	90	-
SEME0105010	R1.0	5.0	6	13	90	-
SEME0105501	RO.1	5.5	6	13	90	-
SEME0105502	RO.2	5.5	6	13	90	-
SEME0105503	RO.3	5.5	6	13	90	-
SEME0105505	RO.5	5.5	6	13	90	-
SEME0105510	R1.0	5.5	6	13	90	-
SEME0106001060	RO.1	6.0	6	15	60	Short

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME01 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE CORNER RADIUS (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.
- ▶ Available various products like short, regular and long shank end mills etc.



Call for Availability


Unit : mm

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2	Remark
SEME0106002060	R0.2	6.0	6	15	60	Short
SEME0106001	R0.1	6.0	6	15	90	Regular
SEME0106002	R0.2	6.0	6	15	90	Regular
SEME0106003	R0.3	6.0	6	15	90	Regular
SEME0106005	R0.5	6.0	6	15	90	Regular
SEME0106010	R1.0	6.0	6	15	90	Regular
SEME0106015	R1.5	6.0	6	15	90	Regular
SEME0106020	R2.0	6.0	6	15	90	Regular
SEME0106005110	R0.5	6.0	6	15	110	Long Shank
SEME0106010110	R1.0	6.0	6	15	110	Long Shank
SEME0106005130	R0.5	6.0	6	15	130	Long Shank
SEME0106010130	R1.0	6.0	6	15	130	Long Shank
SEME0107001	R0.1	7.0	8	16	90	-
SEME0107002	R0.2	7.0	8	16	90	-
SEME0107003	R0.3	7.0	8	16	90	-
SEME0107005	R0.5	7.0	8	16	90	-
SEME0107010	R1.0	7.0	8	16	90	-
SEME0107020	R2.0	7.0	8	16	90	-
SEME0108003070	R0.3	8.0	8	20	70	Short
SEME0108005070	R0.5	8.0	8	20	70	Short
SEME0108010070	R1.0	8.0	8	20	70	Short
SEME0108001	R0.1	8.0	8	20	100	Regular
SEME0108002	R0.2	8.0	8	20	100	Regular
SEME0108003	R0.3	8.0	8	20	100	Regular
SEME0108005	R0.5	8.0	8	20	100	Regular
SEME0108010	R1.0	8.0	8	20	100	Regular
SEME0108015	R1.5	8.0	8	20	100	Regular
SEME0108020	R2.0	8.0	8	20	100	Regular
SEME0108025	R2.5	8.0	8	20	100	Regular
SEME0108030	R3.0	8.0	8	20	100	Regular

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○		○							



SEME01 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE CORNER RADIUS (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.
- ▶ Available various products like short, regular and long shank end mills etc.



Call for Availability

Unit : mm

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2	Remark
SEME0108005120	R0.5	8.0	8	20	120	Long Shank
SEME0108010120	R1.0	8.0	8	20	120	Long Shank
SEME0108005150	R0.5	8.0	8	20	150	Long Shank
SEME0108010150	R1.0	8.0	8	20	150	Long Shank
SEME0110003075	R0.3	10.0	10	25	75	Short
SEME0110005075	R0.5	10.0	10	25	75	Short
SEME0110010075	R1.0	10.0	10	25	75	Short
SEME0110001	R0.1	10.0	10	25	100	Regular
SEME0110002	R0.2	10.0	10	25	100	Regular
SEME0110003	R0.3	10.0	10	25	100	Regular
SEME0110005	R0.5	10.0	10	25	100	Regular
SEME0110010	R1.0	10.0	10	25	100	Regular
SEME0110015	R1.5	10.0	10	25	100	Regular
SEME0110020	R2.0	10.0	10	25	100	Regular
SEME0110025	R2.5	10.0	10	25	100	Regular
SEME0110030	R3.0	10.0	10	25	100	Regular
SEME0110040	R4.0	10.0	10	25	100	Regular
SEME0110005130	R0.5	10.0	10	22	130	Long Shank
SEME0110010130	R1.0	10.0	10	22	130	Long Shank
SEME0110005150	R0.5	10.0	10	22	150	Long Shank
SEME0110010150	R1.0	10.0	10	22	150	Long Shank
SEME0111002	R0.2	11.0	12	25	110	-
SEME0111003	R0.3	11.0	12	25	110	-
SEME0111005	R0.5	11.0	12	25	110	-
SEME0111010	R1.0	11.0	12	25	110	-
SEME0111020	R2.0	11.0	12	25	110	-
SEME0112003080	R0.3	12.0	12	30	80	Short
SEME0112005080	R0.5	12.0	12	30	80	Short
SEME0112010080	R1.0	12.0	12	30	80	Short
SEME0112001	R0.1	12.0	12	30	110	Regular

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○		○							



SEME01 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE CORNER RADIUS (Short, Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.
- ▶ Available various products like short, regular and long shank end mills etc.



Call for Availability

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	Remark
	R	D1	D2	L1	L2	
SEME0112002	R0.2	12.0	12	30	110	Regular
SEME0112003	R0.3	12.0	12	30	110	Regular
SEME0112005	R0.5	12.0	12	30	110	Regular
SEME0112010	R1.0	12.0	12	30	110	Regular
SEME0112015	R1.5	12.0	12	30	110	Regular
SEME0112020	R2.0	12.0	12	30	110	Regular
SEME0112025	R2.5	12.0	12	30	110	Regular
SEME0112030	R3.0	12.0	12	30	110	Regular
SEME0112040	R4.0	12.0	12	30	110	Regular
SEME0112050	R5.0	12.0	12	30	110	Regular
SEME0112005130	R0.5	12.0	12	30	130	Long Shank
SEME0112010130	R1.0	12.0	12	30	130	Long Shank
SEME0112005150	R0.5	12.0	12	30	130	Long Shank
SEME0112010150	R1.0	12.0	12	30	130	Long Shank
SEME0114005	R0.5	14.0	16	35	150	-
SEME0114010	R1.0	14.0	16	35	150	-
SEME0114020	R2.0	14.0	16	35	150	-
SEME0116005	R0.5	16.0	16	32	150	-
SEME0116010	R1.0	16.0	16	32	150	-
SEME0116015	R1.5	16.0	16	32	150	-
SEME0116020	R2.0	16.0	16	32	150	-
SEME0120005	R0.5	20.0	20	38	150	-
SEME0120010	R1.0	20.0	20	38	150	-
SEME0120015	R1.5	20.0	20	38	150	-
SEME0120020	R2.0	20.0	20	38	150	-

Mill Dia. Tolerance (mm)	Corner Radius Tolerance (mm)	Shank Dia. Tolerance
0~-0.03	±0.02	h6

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○		○							



SEME64 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.



Call for Availability

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Remark
	R	D1	D2	L1	L3	L2	D3	
SEME6401000503	R0.05	1.0	4	1.5	3	50	0.95	-
SEME6401000504	R0.05	1.0	4	1.5	4	50	0.95	-
SEME6401000506	R0.05	1.0	4	1.5	6	50	0.95	-
SEME6401000508	R0.05	1.0	4	1.5	8	50	0.95	-
SEME6401000510	R0.05	1.0	4	1.5	10	50	0.95	-
SEME6401000512	R0.05	1.0	4	1.5	12	50	0.95	-
SEME6401000514	R0.05	1.0	4	1.5	14	50	0.95	-
SEME6401000516	R0.05	1.0	4	1.5	16	50	0.95	-
SEME6401000520	R0.05	1.0	4	1.5	20	50	0.95	-
SEME640100103	R0.1	1.0	4	1.5	3	50	0.95	-
SEME640100104	R0.1	1.0	4	1.5	4	50	0.95	-
SEME640100106	R0.1	1.0	4	1.5	6	50	0.95	-
SEME640100108	R0.1	1.0	4	1.5	8	50	0.95	-
SEME640100110	R0.1	1.0	4	1.5	10	50	0.95	-
SEME640100112	R0.1	1.0	4	1.5	12	50	0.95	-
SEME640100114	R0.1	1.0	4	1.5	14	50	0.95	-
SEME640100116	R0.1	1.0	4	1.5	16	50	0.95	-
SEME640100120	R0.1	1.0	4	1.5	20	50	0.95	-
SEME640100203	R0.2	1.0	4	1.5	3	50	0.95	-
SEME640100204	R0.2	1.0	4	1.5	4	50	0.95	-
SEME640100206	R0.2	1.0	4	1.5	6	50	0.95	-
SEME640100208	R0.2	1.0	4	1.5	8	50	0.95	-
SEME640100210	R0.2	1.0	4	1.5	10	50	0.95	-
SEME640100212	R0.2	1.0	4	1.5	12	50	0.95	-
SEME640100214	R0.2	1.0	4	1.5	14	50	0.95	-
SEME640100216	R0.2	1.0	4	1.5	16	50	0.95	-
SEME640100220	R0.2	1.0	4	1.5	20	50	0.95	-
SEME640100303	R0.3	1.0	4	1.5	3	50	0.95	-
SEME640100304	R0.3	1.0	4	1.5	4	50	0.95	-
SEME640100306	R0.3	1.0	4	1.5	6	50	0.95	-

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○		○							



SEME64 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.




Call for Availability

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Remark
SEME640100308	RO.3	1.0	4	1.5	8	50	0.95	-
SEME640100310	RO.3	1.0	4	1.5	10	50	0.95	-
SEME640100312	RO.3	1.0	4	1.5	12	50	0.95	-
SEME640100314	RO.3	1.0	4	1.5	14	50	0.95	-
SEME640100316	RO.3	1.0	4	1.5	16	50	0.95	-
SEME640100320	RO.3	1.0	4	1.5	20	50	0.95	-
SEME6401200503	RO.05	1.2	4	1.8	3	50	1.15	-
SEME6401200504	RO.05	1.2	4	1.8	4	50	1.15	-
SEME6401200506	RO.05	1.2	4	1.8	6	50	1.15	-
SEME6401200508	RO.05	1.2	4	1.8	8	50	1.15	-
SEME6401200510	RO.05	1.2	4	1.8	10	50	1.15	-
SEME6401200512	RO.05	1.2	4	1.8	12	50	1.15	-
SEME6401200516	RO.05	1.2	4	1.8	16	50	1.15	-
SEME6401200520	RO.05	1.2	4	1.8	20	50	1.15	-
SEME640120103	RO.1	1.2	4	1.8	3	50	1.15	-
SEME640120104	RO.1	1.2	4	1.8	4	50	1.15	-
SEME640120106	RO.1	1.2	4	1.8	6	50	1.15	-
SEME640120108	RO.1	1.2	4	1.8	8	50	1.15	-
SEME640120110	RO.1	1.2	4	1.8	10	50	1.15	-
SEME640120112	RO.1	1.2	4	1.8	12	50	1.15	-
SEME640120116	RO.1	1.2	4	1.8	16	50	1.15	-
SEME640120120	RO.1	1.2	4	1.8	20	50	1.15	-
SEME640120203	RO.2	1.2	4	1.8	3	50	1.15	-
SEME640120204	RO.2	1.2	4	1.8	4	50	1.15	-
SEME640120206	RO.2	1.2	4	1.8	6	50	1.15	-
SEME640120208	RO.2	1.2	4	1.8	8	50	1.15	-
SEME640120210	RO.2	1.2	4	1.8	10	50	1.15	-
SEME640120212	RO.2	1.2	4	1.8	12	50	1.15	-
SEME640120216	RO.2	1.2	4	1.8	16	50	1.15	-
SEME640120220	RO.2	1.2	4	1.8	20	50	1.15	-

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○		○							



SEME64 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.



Call for Availability

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Remark
SEME640120303	RO.3	1.2	4	1.8	3	50	1.15	-
SEME640120304	RO.3	1.2	4	1.8	4	50	1.15	-
SEME640120306	RO.3	1.2	4	1.8	6	50	1.15	-
SEME640120308	RO.3	1.2	4	1.8	8	50	1.15	-
SEME640120310	RO.3	1.2	4	1.8	10	50	1.15	-
SEME640120312	RO.3	1.2	4	1.8	12	50	1.15	-
SEME640120316	RO.3	1.2	4	1.8	16	50	1.15	-
SEME640120320	RO.3	1.2	4	1.8	20	50	1.15	-
SEME6401500504	RO.05	1.5	4	2.3	4	50	1.45	-
SEME6401500506	RO.05	1.5	4	2.3	6	50	1.45	-
SEME6401500508	RO.05	1.5	4	2.3	8	50	1.45	-
SEME6401500510	RO.05	1.5	4	2.3	10	50	1.45	-
SEME6401500512	RO.05	1.5	4	2.3	12	50	1.45	-
SEME6401500514	RO.05	1.5	4	2.3	14	50	1.45	-
SEME6401500516	RO.05	1.5	4	2.3	16	50	1.45	-
SEME6401500520	RO.05	1.5	4	2.3	20	50	1.45	-
SEME6401500522	RO.05	1.5	4	2.3	22	60	1.45	-
SEME6401500526	RO.05	1.5	4	2.3	26	60	1.45	-
SEME640150104	RO.1	1.5	4	2.3	4	50	1.45	-
SEME640150106	RO.1	1.5	4	2.3	6	50	1.45	-
SEME640150108	RO.1	1.5	4	2.3	8	50	1.45	-
SEME640150110	RO.1	1.5	4	2.3	10	50	1.45	-
SEME640150112	RO.1	1.5	4	2.3	12	50	1.45	-
SEME640150114	RO.1	1.5	4	2.3	14	50	1.45	-
SEME640150116	RO.1	1.5	4	2.3	16	50	1.45	-
SEME640150120	RO.1	1.5	4	2.3	20	50	1.45	-
SEME640150122	RO.1	1.5	4	2.3	22	60	1.45	-
SEME640150126	RO.1	1.5	4	2.3	26	60	1.45	-
SEME640150204	RO.2	1.5	4	2.3	4	50	1.45	-
SEME640150206	RO.2	1.5	4	2.3	6	50	1.45	-

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○		○							

YG 4G MILL END MILLS

SEME64 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.



MG 4 27°/30° ±0.02 PLAIN P.825~826

◇ Call for Availability

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Remark
SEME640150208	RO.2	1.5	4	2.3	8	50	1.45	-
SEME640150210	RO.2	1.5	4	2.3	10	50	1.45	-
SEME640150212	RO.2	1.5	4	2.3	12	50	1.45	-
SEME640150214	RO.2	1.5	4	2.3	14	50	1.45	-
SEME640150216	RO.2	1.5	4	2.3	16	50	1.45	-
SEME640150220	RO.2	1.5	4	2.3	20	50	1.45	-
SEME640150222	RO.2	1.5	4	2.3	22	60	1.45	-
SEME640150226	RO.2	1.5	4	2.3	26	60	1.45	-
SEME640150304	RO.3	1.5	4	2.3	4	50	1.45	-
SEME640150306	RO.3	1.5	4	2.3	6	50	1.45	-
SEME640150308	RO.3	1.5	4	2.3	8	50	1.45	-
SEME640150310	RO.3	1.5	4	2.3	10	50	1.45	-
SEME640150312	RO.3	1.5	4	2.3	12	50	1.45	-
SEME640150314	RO.3	1.5	4	2.3	14	50	1.45	-
SEME640150316	RO.3	1.5	4	2.3	16	50	1.45	-
SEME640150320	RO.3	1.5	4	2.3	20	50	1.45	-
SEME640150322	RO.3	1.5	4	2.3	22	60	1.45	-
SEME640150326	RO.3	1.5	4	2.3	26	60	1.45	-
SEME640150504	RO.5	1.5	4	2.3	4	50	1.45	-
SEME640150506	RO.5	1.5	4	2.3	6	50	1.45	-
SEME640150508	RO.5	1.5	4	2.3	8	50	1.45	-
SEME640150510	RO.5	1.5	4	2.3	10	50	1.45	-
SEME640150512	RO.5	1.5	4	2.3	12	50	1.45	-
SEME640150514	RO.5	1.5	4	2.3	14	50	1.45	-
SEME640150516	RO.5	1.5	4	2.3	16	50	1.45	-
SEME640150520	RO.5	1.5	4	2.3	20	50	1.45	-
SEME640150522	RO.5	1.5	4	2.3	22	60	1.45	-
SEME640150526	RO.5	1.5	4	2.3	26	60	1.45	-
SEME640200106	RO.1	2.0	4	3	6	50	1.95	-
SEME640200108	RO.1	2.0	4	3	8	50	1.95	-

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○		○							

YG 4G MILL END MILLS

SEME64 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.



MG 4 27°/30° ±0.02 PLAIN P.825~826


◇ Call for Availability

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Remark
SEME640200110	RO.1	2.0	4	3	10	50	1.95	-
SEME640200112	RO.1	2.0	4	3	12	50	1.95	-
SEME640200114	RO.1	2.0	4	3	14	50	1.95	-
SEME640200116	RO.1	2.0	4	3	16	50	1.95	-
SEME640200120	RO.1	2.0	4	3	20	50	1.95	-
SEME640200122	RO.1	2.0	4	3	22	60	1.95	-
SEME640200126	RO.1	2.0	4	3	26	60	1.95	-
SEME640200130	RO.1	2.0	4	3	30	70	1.95	-
SEME640200206	RO.2	2.0	4	3	6	50	1.95	-
SEME640200208	RO.2	2.0	4	3	8	50	1.95	-
SEME640200210	RO.2	2.0	4	3	10	50	1.95	-
SEME640200212	RO.2	2.0	4	3	12	50	1.95	-
SEME640200214	RO.2	2.0	4	3	14	50	1.95	-
SEME640200216	RO.2	2.0	4	3	16	50	1.95	-
SEME640200220	RO.2	2.0	4	3	20	50	1.95	-
SEME640200222	RO.2	2.0	4	3	22	60	1.95	-
SEME640200226	RO.2	2.0	4	3	26	60	1.95	-
SEME640200230	RO.2	2.0	4	3	30	70	1.95	-
SEME640200306	RO.3	2.0	4	3	6	50	1.95	-
SEME640200308	RO.3	2.0	4	3	8	50	1.95	-
SEME640200310	RO.3	2.0	4	3	10	50	1.95	-
SEME640200312	RO.3	2.0	4	3	12	50	1.95	-
SEME640200314	RO.3	2.0	4	3	14	50	1.95	-
SEME640200316	RO.3	2.0	4	3	16	50	1.95	-
SEME640200320	RO.3	2.0	4	3	20	50	1.95	-
SEME640200322	RO.3	2.0	4	3	22	60	1.95	-
SEME640200326	RO.3	2.0	4	3	26	60	1.95	-
SEME640200330	RO.3	2.0	4	3	30	70	1.95	-
SEME640200506	RO.5	2.0	4	3	6	50	1.95	-
SEME640200508	RO.5	2.0	4	3	8	50	1.95	-

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○		○							



CARBIDE, 4 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.



◇ Call for Availability


Unit : mm

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Remark
SEME640200510	RO.5	2.0	4	3	10	50	1.95	-
SEME640200512	RO.5	2.0	4	3	12	50	1.95	-
SEME640200514	RO.5	2.0	4	3	14	50	1.95	-
SEME640200516	RO.5	2.0	4	3	16	50	1.95	-
SEME640200520	RO.5	2.0	4	3	20	50	1.95	-
SEME640200522	RO.5	2.0	4	3	22	60	1.95	-
SEME640200526	RO.5	2.0	4	3	26	60	1.95	-
SEME640200530	RO.5	2.0	4	3	30	70	1.95	-
SEME640250108	RO.1	2.5	4	4	8	50	2.40	-
SEME640250110	RO.1	2.5	4	4	10	50	2.40	-
SEME640250112	RO.1	2.5	4	4	12	50	2.40	-
SEME640250114	RO.1	2.5	4	4	14	50	2.40	-
SEME640250116	RO.1	2.5	4	4	16	50	2.40	-
SEME640250120	RO.1	2.5	4	4	20	50	2.40	-
SEME640250126	RO.1	2.5	4	4	26	60	2.40	-
SEME640250130	RO.1	2.5	4	4	30	70	2.40	-
SEME640250208	RO.2	2.5	4	4	8	50	2.40	-
SEME640250210	RO.2	2.5	4	4	10	50	2.40	-
SEME640250212	RO.2	2.5	4	4	12	50	2.40	-
SEME640250214	RO.2	2.5	4	4	14	50	2.40	-
SEME640250216	RO.2	2.5	4	4	16	50	2.40	-
SEME640250220	RO.2	2.5	4	4	20	50	2.40	-
SEME640250226	RO.2	2.5	4	4	26	60	2.40	-
SEME640250230	RO.2	2.5	4	4	30	70	2.40	-
SEME640250308	RO.3	2.5	4	4	8	50	2.40	-
SEME640250310	RO.3	2.5	4	4	10	50	2.40	-
SEME640250312	RO.3	2.5	4	4	12	50	2.40	-
SEME640250314	RO.3	2.5	4	4	14	50	2.40	-
SEME640250316	RO.3	2.5	4	4	16	50	2.40	-
SEME640250320	RO.3	2.5	4	4	20	50	2.40	-

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○		○							



CARBIDE, 4 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.



◇ Call for Availability

Unit : mm

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Remark
SEME640250326	RO.3	2.5	4	4	26	60	2.40	-
SEME640250330	RO.3	2.5	4	4	30	70	2.40	-
SEME640250508	RO.5	2.5	4	4	8	50	2.40	-
SEME640250510	RO.5	2.5	4	4	10	50	2.40	-
SEME640250512	RO.5	2.5	4	4	12	50	2.40	-
SEME640250514	RO.5	2.5	4	4	14	50	2.40	-
SEME640250516	RO.5	2.5	4	4	16	50	2.40	-
SEME640250520	RO.5	2.5	4	4	20	50	2.40	-
SEME640250526	RO.5	2.5	4	4	26	60	2.40	-
SEME640250530	RO.5	2.5	4	4	30	70	2.40	-
SEME640300108	RO.1	3.0	6	4.5	8	50	2.85	-
SEME640300110	RO.1	3.0	6	4.5	10	50	2.85	-
SEME640300112	RO.1	3.0	6	4.5	12	50	2.85	-
SEME640300114	RO.1	3.0	6	4.5	14	60	2.85	-
SEME640300116	RO.1	3.0	6	4.5	16	60	2.85	-
SEME640300120	RO.1	3.0	6	4.5	20	60	2.85	-
SEME640300126	RO.1	3.0	6	4.5	26	65	2.85	-
SEME640300130	RO.1	3.0	6	4.5	30	70	2.85	-
SEME640300135	RO.1	3.0	6	4.5	35	70	2.85	-
SEME640300140	RO.1	3.0	6	4.5	40	80	2.85	-
SEME640300208	RO.2	3.0	6	4.5	8	50	2.85	-
SEME640300210	RO.2	3.0	6	4.5	10	50	2.85	-
SEME640300212	RO.2	3.0	6	4.5	12	50	2.85	-
SEME640300214	RO.2	3.0	6	4.5	14	60	2.85	-
SEME640300216	RO.2	3.0	6	4.5	16	60	2.85	-
SEME640300220	RO.2	3.0	6	4.5	20	60	2.85	-
SEME640300226	RO.2	3.0	6	4.5	26	65	2.85	-
SEME640300230	RO.2	3.0	6	4.5	30	70	2.85	-
SEME640300235	RO.2	3.0	6	4.5	35	70	2.85	-
SEME640300240	RO.2	3.0	6	4.5	40	80	2.85	-

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○		○							



SEME64 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.




Call for Availability

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Remark
SEME640300308	RO.3	3.0	6	4.5	8	50	2.85	-
SEME640300310	RO.3	3.0	6	4.5	10	50	2.85	-
SEME640300312	RO.3	3.0	6	4.5	12	50	2.85	-
SEME640300314	RO.3	3.0	6	4.5	14	60	2.85	-
SEME640300316	RO.3	3.0	6	4.5	16	60	2.85	-
SEME640300320	RO.3	3.0	6	4.5	20	60	2.85	-
SEME640300326	RO.3	3.0	6	4.5	26	65	2.85	-
SEME640300330	RO.3	3.0	6	4.5	30	70	2.85	-
SEME640300335	RO.3	3.0	6	4.5	35	70	2.85	-
SEME640300340	RO.3	3.0	6	4.5	40	80	2.85	-
SEME640300508	RO.5	3.0	6	4.5	8	50	2.85	-
SEME640300510	RO.5	3.0	6	4.5	10	50	2.85	-
SEME640300512	RO.5	3.0	6	4.5	12	50	2.85	-
SEME640300514	RO.5	3.0	6	4.5	14	60	2.85	-
SEME640300516	RO.5	3.0	6	4.5	16	60	2.85	-
SEME640300520	RO.5	3.0	6	4.5	20	60	2.85	-
SEME640300526	RO.5	3.0	6	4.5	26	65	2.85	-
SEME640300530	RO.5	3.0	6	4.5	30	70	2.85	-
SEME640300535	RO.5	3.0	6	4.5	35	70	2.85	-
SEME640300540	RO.5	3.0	6	4.5	40	80	2.85	-
SEME640301008	R1.0	3.0	6	4.5	8	50	2.85	-
SEME640301010	R1.0	3.0	6	4.5	10	50	2.85	-
SEME640301012	R1.0	3.0	6	4.5	12	50	2.85	-
SEME640301014	R1.0	3.0	6	4.5	14	60	2.85	-
SEME640301016	R1.0	3.0	6	4.5	16	60	2.85	-
SEME640301020	R1.0	3.0	6	4.5	20	60	2.85	-
SEME640301026	R1.0	3.0	6	4.5	26	65	2.85	-
SEME640301030	R1.0	3.0	6	4.5	30	70	2.85	-
SEME640301035	R1.0	3.0	6	4.5	35	70	2.85	-
SEME640301040	R1.0	3.0	6	4.5	40	80	2.85	-

▶ NEXT PAGE

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○		○							



SEME64 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.



Call for Availability

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Remark
SEME640400110	RO.1	4.0	6	6	10	50	3.85	-
SEME640400112	RO.1	4.0	6	6	12	50	3.85	-
SEME640400114	RO.1	4.0	6	6	14	60	3.85	-
SEME640400116	RO.1	4.0	6	6	16	60	3.85	-
SEME640400120	RO.1	4.0	6	6	20	60	3.85	-
SEME640400126	RO.1	4.0	6	6	26	65	3.85	-
SEME640400130	RO.1	4.0	6	6	30	70	3.85	-
SEME640400135	RO.1	4.0	6	6	35	70	3.85	-
SEME640400140	RO.1	4.0	6	6	40	80	3.85	-
SEME640400145	RO.1	4.0	6	6	45	90	3.85	-
SEME640400150	RO.1	4.0	6	6	50	100	3.85	-
SEME640400210	RO.2	4.0	6	6	10	50	3.85	-
SEME640400212	RO.2	4.0	6	6	12	50	3.85	-
SEME640400214	RO.2	4.0	6	6	14	60	3.85	-
SEME640400216	RO.2	4.0	6	6	16	60	3.85	-
SEME640400220	RO.2	4.0	6	6	20	60	3.85	-
SEME640400226	RO.2	4.0	6	6	26	65	3.85	-
SEME640400230	RO.2	4.0	6	6	30	70	3.85	-
SEME640400235	RO.2	4.0	6	6	35	70	3.85	-
SEME640400240	RO.2	4.0	6	6	40	80	3.85	-
SEME640400245	RO.2	4.0	6	6	45	90	3.85	-
SEME640400250	RO.2	4.0	6	6	50	100	3.85	-
SEME640400310	RO.3	4.0	6	6	10	50	3.85	-
SEME640400312	RO.3	4.0	6	6	12	50	3.85	-
SEME640400314	RO.3	4.0	6	6	14	60	3.85	-
SEME640400316	RO.3	4.0	6	6	16	60	3.85	-
SEME640400320	RO.3	4.0	6	6	20	60	3.85	-
SEME640400326	RO.3	4.0	6	6	26	65	3.85	-
SEME640400330	RO.3	4.0	6	6	30	70	3.85	-
SEME640400335	RO.3	4.0	6	6	35	70	3.85	-

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○		○							



SEME64 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.



Call for Availability

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Remark
SEME640400340	RO.3	4.0	6	6	40	80	3.85	-
SEME640400345	RO.3	4.0	6	6	45	90	3.85	-
SEME640400350	RO.3	4.0	6	6	50	100	3.85	-
SEME640400510	RO.5	4.0	6	6	10	50	3.85	-
SEME640400512	RO.5	4.0	6	6	12	50	3.85	-
SEME640400514	RO.5	4.0	6	6	14	60	3.85	-
SEME640400516	RO.5	4.0	6	6	16	60	3.85	-
SEME640400520	RO.5	4.0	6	6	20	60	3.85	-
SEME640400526	RO.5	4.0	6	6	26	65	3.85	-
SEME640400530	RO.5	4.0	6	6	30	70	3.85	-
SEME640400535	RO.5	4.0	6	6	35	70	3.85	-
SEME640400540	RO.5	4.0	6	6	40	80	3.85	-
SEME640400545	RO.5	4.0	6	6	45	90	3.85	-
SEME640400550	RO.5	4.0	6	6	50	100	3.85	-
SEME640401010	R1.0	4.0	6	6	10	50	3.85	-
SEME640401012	R1.0	4.0	6	6	12	50	3.85	-
SEME640401014	R1.0	4.0	6	6	14	60	3.85	-
SEME640401016	R1.0	4.0	6	6	16	60	3.85	-
SEME640401020	R1.0	4.0	6	6	20	60	3.85	-
SEME640401026	R1.0	4.0	6	6	26	65	3.85	-
SEME640401030	R1.0	4.0	6	6	30	70	3.85	-
SEME640401035	R1.0	4.0	6	6	35	70	3.85	-
SEME640401040	R1.0	4.0	6	6	40	80	3.85	-
SEME640401045	R1.0	4.0	6	6	45	90	3.85	-
SEME640401050	R1.0	4.0	6	6	50	100	3.85	-
SEME6405001	RO.1	5.0	6	8	15	60	4.85	-
SEME6405002	RO.2	5.0	6	8	15	60	4.85	-
SEME6405003	RO.3	5.0	6	8	15	60	4.85	-
SEME6405005	RO.5	5.0	6	8	15	60	4.85	-
SEME6405010	R1.0	5.0	6	8	15	60	4.85	-

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○		○							



SEME64 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.



Call for Availability

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Remark
SEME6405015	R1.5	5.0	6	8	15	60	4.85	-
SEME6405020	R2.0	5.0	6	8	15	60	4.85	-
SEME6406001	RO.1	6.0	6	9	20	60	5.85	Regular
SEME6406002	RO.2	6.0	6	9	20	60	5.85	Regular
SEME6406003	RO.3	6.0	6	9	20	60	5.85	Regular
SEME6406005	RO.5	6.0	6	9	20	60	5.85	Regular
SEME6406010	R1.0	6.0	6	9	20	60	5.85	Regular
SEME6406015	R1.5	6.0	6	9	20	60	5.85	Regular
SEME6406020	R2.0	6.0	6	9	20	60	5.85	Regular
SEME6406003090	RO.3	6.0	6	15	30	90	5.85	Long Shank
SEME6406005090	RO.5	6.0	6	15	30	90	5.85	Long Shank
SEME6406010090	R1.0	6.0	6	15	30	90	5.85	Long Shank
SEME6408001	RO.1	8.0	8	12	25	70	7.70	Regular
SEME6408002	RO.2	8.0	8	12	25	70	7.70	Regular
SEME6408003	RO.3	8.0	8	12	25	70	7.70	Regular
SEME6408005	RO.5	8.0	8	12	25	70	7.70	Regular
SEME6408010	R1.0	8.0	8	12	25	70	7.70	Regular
SEME6408015	R1.5	8.0	8	12	25	70	7.70	Regular
SEME6408020	R2.0	8.0	8	12	25	70	7.70	Regular
SEME6408003100	RO.3	8.0	8	20	35	100	7.70	Long Shank
SEME6408005100	RO.5	8.0	8	20	35	100	7.70	Long Shank
SEME6408010100	R1.0	8.0	8	20	35	100	8.70	Long Shank
SEME6410001	RO.1	10.0	10	15	30	75	9.70	Regular
SEME6410002	RO.2	10.0	10	15	30	75	9.70	Regular
SEME6410003	RO.3	10.0	10	15	30	75	9.70	Regular
SEME6410005	RO.5	10.0	10	15	30	75	9.70	Regular
SEME6410010	R1.0	10.0	10	15	30	75	9.70	Regular
SEME6410015	R1.5	10.0	10	15	30	75	9.70	Regular
SEME6410020	R2.0	10.0	10	15	30	75	9.70	Regular
SEME6410003100	RO.3	10.0	10	25	40	100	9.70	Long Shank

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○		○							



SEME64 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG NECK CORNER RADIUS

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.




Call for Availability

EDP No.	Corner Radius R	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Remark
SEME6410005100	R0.5	10.0	10	25	40	100	9.70	Long Shank
SEME6410010100	R1.0	10.0	10	25	40	100	9.70	Long Shank
SEME6412002	R0.2	12.0	12	18	32	80	11.70	Regular
SEME6412003	R0.3	12.0	12	18	32	80	11.70	Regular
SEME6412005	R0.5	12.0	12	18	32	80	11.70	Regular
SEME6412010	R1.0	12.0	12	18	32	80	11.70	Regular
SEME6412015	R1.5	12.0	12	18	32	80	11.70	Regular
SEME6412020	R2.0	12.0	12	18	32	80	11.70	Regular
SEME6412003110	R0.3	12.0	12	30	45	110	11.70	Long Shank
SEME6412005110	R0.5	12.0	12	30	45	110	11.70	Long Shank
SEME6412010110	R1.0	12.0	12	30	45	110	11.70	Long Shank
SEME6416005	R0.5	16.0	16	20	35	100	15.70	Regular
SEME6416010	R1.0	16.0	16	20	35	100	15.70	Regular
SEME6416005150	R0.5	16.0	20	35	50	150	15.70	Long Shank
SEME6416010150	R1.0	16.0	20	35	50	150	15.70	Long Shank
SEME641600515020	R0.5	16.0	20	35	50	150	15.70	Long Shank
SEME641601015020	R1.0	16.0	20	35	50	150	15.70	Long Shank
SEME6420005	R0.5	20.0	20	25	40	100	19.70	Regular
SEME6420010	R1.0	20.0	20	25	40	100	19.70	Regular
SEME6420005150	R0.5	20.0	20	40	55	150	19.70	Long Shank
SEME6420010150	R1.0	20.0	20	40	55	150	19.70	Long Shank

Mill Dia. Tolerance (mm)	Corner Radius Tolerance (mm)	Shank Dia. Tolerance
0~-0.03	±0.02	h6

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45 HRC45~55	HRC55~70									
◎	◎	◎	◎	○		○							



SEME35 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to sharp edge geometry at end tooth, cutting ability at working is increased.




Call for Availability

EDP No.	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2
SEME35001	0.1	4	0.2	40
SEME350015	0.15	4	0.3	40
SEME35002	0.2	4	0.4	40
SEME350025	0.25	4	0.5	40
SEME35003	0.3	4	0.6	40
SEME350035	0.35	4	0.7	40
SEME35004	0.4	4	0.8	40
SEME350045	0.45	4	0.9	40
SEME35005	0.5	4	1.0	40
SEME350055	0.55	4	1.1	40
SEME35006	0.6	4	1.2	40
SEME350065	0.65	4	1.3	40
SEME35007	0.7	4	1.4	40
SEME350075	0.75	4	1.5	40
SEME35008	0.8	4	1.6	40
SEME350085	0.85	4	1.7	40
SEME35009	0.9	4	1.8	40
SEME350095	0.95	4	2	40
SEME35010	1.0	6	2.5	50
SEME35012	1.2	6	3	50

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45 HRC45~55	HRC55~70									
◎	◎	◎	◎	○		○	○						



SEME35 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to sharp edge geometry at end tooth, cutting ability at working is increased.



Call for Availability

Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
SEME35015	1.5	6	4	50
SEME35020	2.0	6	6	50
SEME35025	2.5	6	7	50
SEME35030	3.0	6	8	50
SEME35035	3.5	6	10	50
SEME35040	4.0	6	10	50
SEME35045	4.5	6	14	50
SEME35050	5.0	6	15	60
SEME35055	5.5	6	15	60
SEME35060	6.0	6	15	60
SEME35065	6.5	8	18	60
SEME35070	7.0	8	20	60
SEME35075	7.5	8	20	60
SEME35080	8.0	8	20	70
SEME35085	8.5	10	22	70
SEME35090	9.0	10	22	70
SEME35095	9.5	10	24	70
SEME35100	10.0	10	25	75
SEME35105	10.5	12	26	75
SEME35110	11.0	12	30	75
SEME35115	11.5	12	30	80
SEME35120	12.0	12	30	80
SEME35130	13.0	12	35	100
SEME3514012S	14.0	12	35	100
SEME3514014S	14.0	14	35	100
SEME35140	14.0	16	35	100
SEME35150	15.0	16	38	100

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45 HRC45~55	HRC55~70	○	○							



SEME35 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to sharp edge geometry at end tooth, cutting ability at working is increased.



Call for Availability

Unit : mm


EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
SEME35160	16.0	16	40	100
SEME35170	17.0	16	42	100
SEME35180	18.0	16	45	100
SEME3518018S	18.0	18	45	100
SEME35190	19.0	20	45	100
SEME35200	20.0	20	45	100
SEME35210	21.0	20	45	100
SEME35220	22.0	20	45	100
SEME35230	23.0	25	50	120
SEME35240	24.0	25	50	120
SEME35250	25.0	25	50	120

▶ NEXT PAGE

Size	Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
up to Ø6	0~-0.012	h6
over Ø6	0~-0.015	

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45 HRC45~55	HRC55~70	○	○							



SEME35 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE (0.1mm a Unit / 4mm Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.
- ▶ Due to sharp edge geometry at end tooth, cutting ability at working is increased.



◇ Call for Availability

Unit : mm


EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
SEME350104S	1.0	1.0	2.5	50
SEME350114S	1.1	1.1	3	50
SEME350124S	1.2	1.2	3	50
SEME350134S	1.3	1.3	3	50
SEME350144S	1.4	1.4	4	50
SEME350154S	1.5	1.5	4	50
SEME350164S	1.6	1.6	4	50
SEME350174S	1.7	1.7	4	50
SEME350184S	1.8	1.8	5	50
SEME350194S	1.9	1.9	5	50
SEME350204S	2.0	2.0	6	50
SEME350214S	2.1	2.1	6	50
SEME350224S	2.2	2.2	6	50
SEME350234S	2.3	2.3	6	50
SEME350244S	2.4	2.4	6	50
SEME350254S	2.5	2.5	8	50
SEME350264S	2.6	2.6	8	50
SEME350274S	2.7	2.7	8	50
SEME350284S	2.8	2.8	8	50
SEME350294S	2.9	2.9	8	50
SEME350304S	3.0	3.0	8	50
SEME350354S	3.5	3.5	10	50
SEME350404S	4.0	4.0	10	50
SEME350404S080	4.0	4.0	10	80

▶ NEXT PAGE

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.012	h6

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	○	○							



SEME35 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE (3mm Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.
- ▶ Due to sharp edge geometry at end tooth, cutting ability at working is increased.



◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
SEME350013S	0.1	3	0.2	40
SEME350023S	0.2	3	0.4	40
SEME350033S	0.3	3	0.6	40
SEME350043S	0.4	3	0.8	40
SEME350053S	0.5	3	1.0	40
SEME350063S	0.6	3	1.2	40
SEME350073S	0.7	3	1.4	40
SEME350083S	0.8	3	1.6	40
SEME350093S	0.9	3	1.8	40
SEME350103S	1.0	3	2.5	50
SEME350123S	1.2	3	3	50
SEME350153S	1.5	3	4	50
SEME350203S	2.0	3	6	50
SEME350253S	2.5	3	7	50
SEME350303S	3.0	3	8	50

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.012	h6

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	○	○							



SEME70 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG LENGTH

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.
- ▶ Available various length of cut and overall length end mills.



◇ Call for Availability


Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
SEME7001003	1.0	6	3	60
SEME7001004	1.0	6	4	60
SEME7001005	1.0	6	5	60
SEME7001006	1.0	6	6	60
SEME7001007	1.0	6	7	60
SEME7001008	1.0	6	8	60
SEME7001010	1.0	6	10	60
SEME7001012	1.0	6	12	60
SEME7001204	1.2	6	4	60
SEME7001206	1.2	6	6	60
SEME7001208	1.2	6	8	60
SEME7001210	1.2	6	10	60
SEME7001212	1.2	6	12	60
SEME7001506	1.5	6	6	60
SEME7001508	1.5	6	8	60
SEME7001510	1.5	6	10	60
SEME7001512	1.5	6	12	60
SEME7001514	1.5	6	14	60
SEME7001516	1.5	6	16	60
SEME7002008	2.0	6	8	60
SEME7002010	2.0	6	10	60
SEME7002012	2.0	6	12	60
SEME7002014	2.0	6	14	60
SEME7002016	2.0	6	16	60
SEME7002510	2.5	6	10	60
SEME7002512	2.5	6	12	60
SEME7002516	2.5	6	16	60

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME70 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG LENGTH

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.
- ▶ Available various length of cut and overall length end mills.



◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
SEME7002520	2.5	6	20	60
SEME7002526	2.5	6	26	60
SEME70030163S	3.0	3	16	100
SEME7003010	3.0	6	10	70
SEME7003012	3.0	6	12	70
SEME7003014	3.0	6	14	70
SEME7003016	3.0	6	16	70
SEME7003020	3.0	6	20	70
SEME7003026	3.0	6	26	70
SEME7003030	3.0	6	30	70
SEME70040204S	4.0	4	20	100
SEME7004012	4.0	6	12	70
SEME7004016	4.0	6	16	70
SEME7004020	4.0	6	20	70
SEME7004026	4.0	6	26	70
SEME7004030	4.0	6	30	70
SEME7005020	5.0	6	20	70
SEME7005025	5.0	6	25	70
SEME7005025100	5.0	6	25	100
SEME7005030	5.0	6	30	80
SEME7005035	5.0	6	35	90
SEME7005040	5.0	6	40	100
SEME7006015	6.0	6	15	60
SEME7006015080	6.0	6	15	80
SEME7006020	6.0	6	20	70
SEME7006020090	6.0	6	20	90
SEME7006025	6.0	6	25	75

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME70 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG LENGTH

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.
- ▶ Available various length of cut and overall length end mills.



◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
SEME7006030	6.0	6	30	80
SEME7006030100	6.0	6	30	100
SEME7006030150	6.0	6	30	150
SEME7006035	6.0	6	35	90
SEME7006040	6.0	6	40	90
SEME7006040120	6.0	6	40	120
SEME7006045	6.0	6	45	150
SEME7008025	8.0	8	25	80
SEME7008030	8.0	8	30	80
SEME7008030100	8.0	8	30	100
SEME7008035	8.0	8	35	90
SEME7008040	8.0	8	40	90
SEME7008040120	8.0	8	40	120
SEME7008040150	8.0	8	40	150
SEME7008045	8.0	8	45	100
SEME7008050	8.0	8	50	100
SEME7008050150	8.0	8	50	150
SEME7010030	10.0	10	30	80
SEME7010030100	10.0	10	30	100
SEME7010035	10.0	10	35	90
SEME7010040	10.0	10	40	90
SEME7010040120	10.0	10	40	120
SEME7010045	10.0	10	45	100
SEME7010050	10.0	10	50	100
SEME7010050150	10.0	10	50	150
SEME7010050200	10.0	10	50	200
SEME7010055	10.0	10	55	150

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME70 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG LENGTH

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.
- ▶ Available various length of cut and overall length end mills.



◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
SEME7010060	10.0	10	60	110
SEME7010060200	10.0	10	60	200
SEME7012035	12.0	12	35	90
SEME7012040	12.0	12	40	100
SEME7012040120	12.0	12	40	120
SEME7012045	12.0	12	45	130
SEME7012050	12.0	12	50	100
SEME7012050150	12.0	12	50	150
SEME7012055	12.0	12	55	110
SEME7012060	12.0	12	60	110
SEME7012060150	12.0	12	60	150
SEME7012060200	12.0	12	60	200
SEME7012065	12.0	12	65	150
SEME7012070	12.0	12	70	120
SEME7012070200	12.0	12	70	200
SEME7014050	14.0	16	50	110
SEME7014060	14.0	16	60	150
SEME7016040	16.0	16	40	150
SEME7016050	16.0	16	50	110
SEME7016050150	16.0	16	50	150
SEME7016060	16.0	16	60	120
SEME7016070	16.0	16	70	130
SEME7016070150	16.0	16	70	150
SEME7016070200	16.0	16	70	200
SEME7016080	16.0	16	80	150
SEME7016090	16.0	16	90	150
SEME70160110	16.0	16	110	200

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME70 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG LENGTH

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Available various length of cut and overall length end mills.



Call for Availability

Unit : mm

EDP No.	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2
SEME70160120	16.0	16	120	250
SEME7018050	18.0	20	50	120
SEME7018070	18.0	20	70	130
SEME70180100	18.0	20	100	200
SEME7020050	20.0	20	50	110
SEME7020050150	20.0	20	50	150
SEME7020060	20.0	20	60	130
SEME7020070	20.0	20	70	130
SEME7020080	20.0	20	80	150
SEME7020090	20.0	20	90	150
SEME7020090200	20.0	20	90	200
SEME70200110	20.0	20	110	200
SEME70200120	20.0	20	120	250
SEME7022075	22.0	20	75	150
SEME70220110	22.0	20	110	200
SEME7025070	25.0	25	70	150
SEME7025090	25.0	25	90	150
SEME70250110	25.0	25	110	200
SEME70250120	25.0	25	120	250

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45 HRC45~55	HRC55~70									
◎	◎	◎	◎	○		○							



SEM845 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRC55 and machine parts.
- ▶ For 1.0mm and under 1.0mm diameter sizes, designed double neck for increasing tool rigidity and minimizing vibration at working.
- ▶ Available various rib processing due to supplying various effective length and overall length products.



Call for Availability


Unit : mm

EDP No.	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
SEM845001003	0.1	4	0.15	0.3	40	0.085
SEM845001005	0.1	4	0.15	0.5	40	0.085
SEM84500101	0.1	4	0.15	1	40	0.085
SEM845002005	0.2	4	0.3	0.5	40	0.17
SEM84500201	0.2	4	0.3	1	40	0.17
SEM845002015	0.2	4	0.3	1.5	40	0.17
SEM84500202	0.2	4	0.3	2	40	0.17
SEM84500301	0.3	4	0.5	1	40	0.27
SEM845003015	0.3	4	0.5	1.5	40	0.27
SEM84500302	0.3	4	0.5	2	40	0.27
SEM845003025	0.3	4	0.5	2.5	40	0.27
SEM84500303	0.3	4	0.5	3	40	0.27
SEM84500304	0.3	4	0.5	4	40	0.27
SEM84500305	0.3	4	0.5	5	40	0.27
SEM84500401	0.4	4	0.6	1	40	0.37
SEM845004015	0.4	4	0.6	1.5	40	0.37
SEM84500402	0.4	4	0.6	2	40	0.37
SEM845004025	0.4	4	0.6	2.5	40	0.37
SEM84500403	0.4	4	0.6	3	40	0.37
SEM84500404	0.4	4	0.6	4	40	0.37
SEM84500405	0.4	4	0.6	5	40	0.37
SEM84500406	0.4	4	0.6	6	40	0.37
SEM84500408	0.4	4	0.6	8	40	0.37
SEM84500410	0.4	4	0.6	10	40	0.37
SEM84500501	0.5	4	0.7	1	45	0.45
SEM845005015	0.5	4	0.7	1.5	45	0.45
SEM84500502	0.5	4	0.7	2	45	0.45
SEM845005025	0.5	4	0.7	2.5	45	0.45
SEM84500503	0.5	4	0.7	3	45	0.45
SEM84500504	0.5	4	0.7	4	45	0.45

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45 HRC45~55	HRC55~70									
◎	◎	◎	◎	○		○							



SEM845 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRC55 and machine parts.
- ▶ For 1.0mm and under 1.0mm diameter sizes, designed double neck for increasing tool rigidity and minimizing vibration at working.
- ▶ Available various rib processing due to supplying various effective length and overall length products.



◇ Call for Availability

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	D1	D2	L1	L3	L2	D3
SEM84500505	0.5	4	0.7	5	45	0.45
SEM84500506	0.5	4	0.7	6	45	0.45
SEM84500508	0.5	4	0.7	8	45	0.45
SEM84500510	0.5	4	0.7	10	45	0.45
SEM84500512	0.5	4	0.7	12	45	0.45
SEM84500514	0.5	4	0.7	14	45	0.45
SEM84500516	0.5	4	0.7	16	45	0.45
SEM84500602	0.6	4	0.9	2	45	0.55
SEM84500603	0.6	4	0.9	3	45	0.55
SEM84500604	0.6	4	0.9	4	45	0.55
SEM84500605	0.6	4	0.9	5	45	0.55
SEM84500606	0.6	4	0.9	6	45	0.55
SEM84500608	0.6	4	0.9	8	45	0.55
SEM84500610	0.6	4	0.9	10	45	0.55
SEM84500612	0.6	4	0.9	12	45	0.55
SEM84500614	0.6	4	0.9	14	45	0.55
SEM84500616	0.6	4	0.9	16	45	0.55
SEM84500702	0.7	4	1.2	2	45	0.65
SEM84500704	0.7	4	1.2	4	45	0.65
SEM84500706	0.7	4	1.2	6	45	0.65
SEM84500708	0.7	4	1.2	8	45	0.65
SEM84500710	0.7	4	1.2	10	45	0.65
SEM84500712	0.7	4	1.2	12	45	0.65
SEM84500802	0.8	4	1.2	2	45	0.75
SEM84500803	0.8	4	1.2	3	45	0.75
SEM84500804	0.8	4	1.2	4	45	0.75
SEM84500805	0.8	4	1.2	5	45	0.75
SEM84500806	0.8	4	1.2	6	45	0.75
SEM84500808	0.8	4	1.2	8	45	0.75
SEM84500810	0.8	4	1.2	10	45	0.75

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○	○	○							



SEM845 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRC55 and machine parts.
- ▶ For 1.0mm and under 1.0mm diameter sizes, designed double neck for increasing tool rigidity and minimizing vibration at working.
- ▶ Available various rib processing due to supplying various effective length and overall length products.




◇ Call for Availability

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	D1	D2	L1	L3	L2	D3
SEM84500812	0.8	4	1.2	12	45	0.75
SEM84500814	0.8	4	1.2	14	45	0.75
SEM84500816	0.8	4	1.2	16	45	0.75
SEM84500820	0.8	4	1.2	20	45	0.75
SEM84500906	0.9	4	1.3	6	45	0.85
SEM84500908	0.9	4	1.3	8	45	0.85
SEM84500910	0.9	4	1.3	10	45	0.85
SEM84501002	1.0	4	1.5	2	50	0.95
SEM84501003	1.0	4	1.5	3	50	0.95
SEM84501004	1.0	4	1.5	4	50	0.95
SEM84501005	1.0	4	1.5	5	50	0.95
SEM84501006	1.0	4	1.5	6	50	0.95
SEM84501007	1.0	4	1.5	7	50	0.95
SEM84501008	1.0	4	1.5	8	50	0.95
SEM84501010	1.0	4	1.5	10	50	0.95
SEM84501012	1.0	4	1.5	12	50	0.95
SEM84501014	1.0	4	1.5	14	50	0.95
SEM84501016	1.0	4	1.5	16	50	0.95
SEM84501018	1.0	4	1.5	18	50	0.95
SEM84501020	1.0	4	1.5	20	50	0.95
SEM84501022	1.0	4	1.5	22	60	0.95
SEM84501026	1.0	4	1.5	26	60	0.95
SEM84501030	1.0	4	1.5	30	70	0.95
SEM84501040	1.0	4	1.5	40	80	0.95
SEM84501050	1.0	4	1.5	50	100	0.95
SEM84501204	1.2	4	1.8	4	50	1.15
SEM84501206	1.2	4	1.8	6	50	1.15
SEM84501208	1.2	4	1.8	8	50	1.15
SEM84501210	1.2	4	1.8	10	50	1.15
SEM84501212	1.2	4	1.8	12	50	1.15

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○	○	○							



CARBIDE, 2 FLUTE LONG NECK

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ For 1.0mm and under 1.0mm diameter sizes, designed double neck for increasing tool rigidity and minimizing vibration at working.
- ▶ Available various rib processing due to supplying various effective length and overall length products.




◇ Call for Availability

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	D1	D2	L1	L3	L2	D3
SEM84501214	1.2	4	1.8	14	50	1.15
SEM84501216	1.2	4	1.8	16	50	1.15
SEM84501220	1.2	4	1.8	20	50	1.15
SEM84501226	1.2	4	1.8	26	60	1.15
SEM84501230	1.2	4	1.8	30	70	1.15
SEM84501406	1.4	4	2.1	6	50	1.35
SEM84501408	1.4	4	2.1	8	50	1.35
SEM84501410	1.4	4	2.1	10	50	1.35
SEM84501414	1.4	4	2.1	14	50	1.35
SEM84501416	1.4	4	2.1	16	50	1.35
SEM84501420	1.4	4	2.1	20	50	1.35
SEM84501504	1.5	4	2.3	4	50	1.45
SEM84501505	1.5	4	2.3	5	50	1.45
SEM84501506	1.5	4	2.3	6	50	1.45
SEM84501507	1.5	4	2.3	7	50	1.45
SEM84501508	1.5	4	2.3	8	50	1.45
SEM84501510	1.5	4	2.3	10	50	1.45
SEM84501512	1.5	4	2.3	12	50	1.45
SEM84501514	1.5	4	2.3	14	50	1.45
SEM84501516	1.5	4	2.3	16	50	1.45
SEM84501518	1.5	4	2.3	18	50	1.45
SEM84501520	1.5	4	2.3	20	50	1.45
SEM84501522	1.5	4	2.3	22	60	1.45
SEM84501526	1.5	4	2.3	26	60	1.45
SEM84501530	1.5	4	2.3	30	70	1.45
SEM84501608	1.6	4	2.3	8	50	1.55
SEM84501610	1.6	4	2.3	10	50	1.55
SEM84501612	1.6	4	2.3	12	50	1.55
SEM84501616	1.6	4	2.3	16	50	1.55
SEM84501620	1.6	4	2.3	20	50	1.55

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○	○	○							



CARBIDE, 2 FLUTE LONG NECK

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ For 1.0mm and under 1.0mm diameter sizes, designed double neck for increasing tool rigidity and minimizing vibration at working.
- ▶ Available various rib processing due to supplying various effective length and overall length products.



◇ Call for Availability

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	D1	D2	L1	L3	L2	D3
SEM84501808	1.8	4	2.7	8	50	1.75
SEM84501810	1.8	4	2.7	10	50	1.75
SEM84501812	1.8	4	2.7	12	50	1.75
SEM84501816	1.8	4	2.7	16	50	1.75
SEM84501820	1.8	4	2.7	20	50	1.75
SEM84502006	2.0	4	3	6	50	1.95
SEM84502008	2.0	4	3	8	50	1.95
SEM84502010	2.0	4	3	10	50	1.95
SEM84502012	2.0	4	3	12	50	1.95
SEM84502014	2.0	4	3	14	50	1.95
SEM84502016	2.0	4	3	16	50	1.95
SEM84502018	2.0	4	3	18	50	1.95
SEM84502020	2.0	4	3	20	50	1.95
SEM84502022	2.0	4	3	22	60	1.95
SEM84502026	2.0	4	3	26	60	1.95
SEM84502030	2.0	4	3	30	70	1.95
SEM84502035	2.0	4	3	35	70	1.95
SEM84502040	2.0	4	3	40	80	1.95
SEM84502045	2.0	4	3	45	90	1.95
SEM84502050	2.0	4	3	50	100	1.95
SEM84502060	2.0	4	3	60	110	1.95
SEM84502508	2.5	4	4	8	50	2.40
SEM84502510	2.5	4	4	10	50	2.40
SEM84502512	2.5	4	4	12	50	2.40
SEM84502514	2.5	4	4	14	50	2.40
SEM84502516	2.5	4	4	16	50	2.40
SEM84502518	2.5	4	4	18	50	2.40
SEM84502520	2.5	4	4	20	50	2.40
SEM84502522	2.5	4	4	22	60	2.40
SEM84502526	2.5	4	4	26	60	2.40

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○	○	○							



SEM845 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ For 1.0mm and under 1.0mm diameter sizes, designed double neck for increasing tool rigidity and minimizing vibration at working.
- ▶ Available various rib processing due to supplying various effective length and overall length products.



Call for Availability

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	D1	D2	L1	L3	L2	D3
SEM84502530	2.5	4	4	30	70	2.40
SEM84502535	2.5	4	4	35	70	2.40
SEM84502540	2.5	4	4	40	80	2.40
SEM84502545	2.5	4	4	45	90	2.40
SEM84502550	2.5	4	4	50	100	2.40
SEM84503006	3.0	6	4.5	6	50	2.85
SEM84503008	3.0	6	4.5	8	50	2.85
SEM84503010	3.0	6	4.5	10	50	2.85
SEM84503012	3.0	6	4.5	12	50	2.85
SEM84503014	3.0	6	4.5	14	60	2.85
SEM84503016	3.0	6	4.5	16	60	2.85
SEM84503018	3.0	6	4.5	18	60	2.85
SEM84503020	3.0	6	4.5	20	60	2.85
SEM84503022	3.0	6	4.5	22	65	2.85
SEM84503026	3.0	6	4.5	26	65	2.85
SEM84503030	3.0	6	4.5	30	70	2.85
SEM84503035	3.0	6	4.5	35	70	2.85
SEM84503040	3.0	6	4.5	40	80	2.85
SEM84503045	3.0	6	4.5	45	90	2.85
SEM84503050	3.0	6	4.5	50	100	2.85
SEM84503060	3.0	6	4.5	60	100	2.85
SEM84504008	4.0	6	6	8	50	3.85
SEM84504010	4.0	6	6	10	50	3.85
SEM84504012	4.0	6	6	12	50	3.85
SEM84504014	4.0	6	6	14	60	3.85
SEM84504016	4.0	6	6	16	60	3.85
SEM84504018	4.0	6	6	18	60	3.85
SEM84504020	4.0	6	6	20	60	3.85
SEM84504022	4.0	6	6	22	65	3.85
SEM84504026	4.0	6	6	26	65	3.85

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	○	○							



SEM845 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG NECK

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ For 1.0mm and under 1.0mm diameter sizes, designed double neck for increasing tool rigidity and minimizing vibration at working.
- ▶ Available various rib processing due to supplying various effective length and overall length products.




Call for Availability

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	D1	D2	L1	L3	L2	D3
SEM84504030	4.0	6	6	30	70	3.85
SEM84504035	4.0	6	6	35	70	3.85
SEM84504040	4.0	6	6	40	80	3.85
SEM84504045	4.0	6	6	45	90	3.85
SEM84504050	4.0	6	6	50	100	3.85
SEM84504060	4.0	6	6	60	100	3.85
SEM84505016	5.0	6	8	16	60	4.85
SEM84505020	5.0	6	8	20	60	4.85
SEM84505026	5.0	6	8	26	65	4.85
SEM84505030	5.0	6	8	30	70	4.85
SEM84505035	5.0	6	8	35	75	4.85
SEM84505040	5.0	6	8	40	80	4.85
SEM84505050	5.0	6	8	50	90	4.85
SEM84505060	5.0	6	8	60	100	4.85
SEM84506015	6.0	6	9	15	60	5.85
SEM84506020	6.0	6	9	20	60	5.85
SEM84506030	6.0	6	9	30	70	5.85
SEM84506032	6.0	6	9	32	90	5.85
SEM84508025	8.0	8	12	25	70	7.70
SEM84508030	8.0	8	12	30	80	7.70
SEM84508042	8.0	8	12	42	100	7.70
SEM84510030	10.0	10	15	30	75	9.70
SEM84510035	10.0	10	15	35	80	9.70
SEM84510045	10.0	10	15	45	100	9.70
SEM84512035	12.0	12	20	35	80	11.70
SEM84512040	12.0	12	20	40	90	11.70
SEM84512050	12.0	12	20	50	110	11.70

Size	Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
up to Ø6	0~-0.012	h6
over Ø6	0~-0.015	

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	○	○							



SEME36 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRC55 and machine parts.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.



Call for Availability


Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
SEME36008	0.8	4	1.6	40
SEME36009	0.9	4	1.8	40
SEME36010	1.0	6	2.5	50
SEME36012	1.2	6	3	50
SEME36015	1.5	6	4	50
SEME36020	2.0	6	6	50
SEME36025	2.5	6	7	50
SEME36030	3.0	6	8	50
SEME36035	3.5	6	10	50
SEME36040	4.0	6	10	50
SEME36045	4.5	6	14	50
SEME36050	5.0	6	15	60
SEME36055	5.5	6	15	60
SEME36060	6.0	6	15	60
SEME36065	6.5	8	18	60
SEME36070	7.0	8	20	60
SEME36075	7.5	8	20	60
SEME36080	8.0	8	20	70
SEME36085	8.5	10	22	70
SEME36090	9.0	10	22	70
SEME36095	9.5	10	24	70
SEME36100	10.0	10	25	75
SEME36105	10.5	12	26	75
SEME36110	11.0	12	30	75

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	○	○							



SEME36 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRC55 and machine parts.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.



Call for Availability

Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
SEME36115	11.5	12	30	80
SEME36120	12.0	12	30	80
SEME36130	13.0	12	35	100
SEME3614012S	14.0	12	35	100
SEME3614014S	14.0	14	35	100
SEME36140	14.0	16	35	100
SEME36150	15.0	16	38	100
SEME36160	16.0	16	40	100
SEME36170	17.0	16	42	100
SEME36180	18.0	16	45	100
SEME3618018S	18.0	18	45	100
SEME36190	19.0	20	45	100
SEME36200	20.0	20	45	100
SEME36210	21.0	20	45	100
SEME36220	22.0	20	45	100
SEME36230	23.0	25	50	120
SEME36240	24.0	25	50	120
SEME36250	25.0	25	50	120

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	○	○							



SEME71 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE


- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRC55 and machine parts.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.
 - Designed equal index flute for long length end mills.
- ▶ Due to gash land geometry used at end tooth, heavy duty cutting can be achieved.
- ▶ Available various length products like short, regular and long length end mills etc.



Call for Availability

Unit : mm


EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	Remark
	D1	D2	L1	L2	
SEME7101001	1.0	6	1	40	Short
SEME7101002	1.0	6	2	40	Short
SEME71010	1.0	6	2.5	50	Regular
SEME7101003	1.0	6	3	50	Long
SEME7101004	1.0	6	4	50	Long
SEME7101006	1.0	6	6	50	Long
SEME7101202	1.2	6	2	40	Short
SEME71012	1.2	6	3	50	Regular
SEME7101204	1.2	6	4	50	Long
SEME7101206	1.2	6	6	50	Long
SEME71015015	1.5	6	1.5	40	Short
SEME7101503	1.5	6	3	40	Short
SEME71015	1.5	6	4	50	Regular
SEME7101506	1.5	6	6	50	Long
SEME7101508	1.5	6	8	50	Long
SEME7101510	1.5	6	10	50	Long
SEME7102002	2.0	6	2	40	Short
SEME7102004	2.0	6	4	40	Short
SEME71020	2.0	6	6	50	Regular
SEME7102008	2.0	6	8	50	Long
SEME7102010	2.0	6	10	50	Long
SEME7102012	2.0	6	12	50	Long
SEME71025025	2.5	6	2.5	40	Short
SEME7102505	2.5	6	5	40	Short
SEME71025	2.5	6	7	50	Regular
SEME7102510	2.5	6	10	50	Long



▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
○	◎	◎	◎	○		○							



SEME71 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE


- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRC55 and machine parts.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.
 - Designed equal index flute for long length end mills.
- ▶ Due to gash land geometry used at end tooth, heavy duty cutting can be achieved.
- ▶ Available various length products like short, regular and long length end mills etc.



Call for Availability

Unit : mm


EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	Remark
	D1	D2	L1	L2	
SEME7102512	2.5	6	12	50	Long
SEME7103003	3.0	6	3	40	Short
SEME7103006	3.0	6	6	40	Short
SEME71030	3.0	6	8	50	Regular
SEME7103010	3.0	6	10	50	Long
SEME7103012	3.0	6	12	50	Long
SEME7103014	3.0	6	14	50	Long
SEME7104004	4.0	6	4	40	Short
SEME7104008	4.0	6	8	40	Short
SEME71040	4.0	6	10	50	Regular
SEME7104012	4.0	6	12	50	Long
SEME7104014	4.0	6	14	50	Long
SEME7104016	4.0	6	16	50	Long
SEME7105005	5.0	6	5	50	Short
SEME7105010	5.0	6	10	50	Short
SEME71050	5.0	6	15	60	Regular
SEME7105020	5.0	6	20	60	Long
SEME7105025	5.0	6	25	60	Long
SEME7106006	6.0	6	6	50	Short
SEME7106012	6.0	6	12	50	Short
SEME71060	6.0	6	15	60	Regular
SEME7106020	6.0	6	20	60	Long
SEME7106025	6.0	6	25	60	Long
SEME7108016	8.0	8	16	60	Short
SEME71080	8.0	8	20	70	Regular
SEME7108025	8.0	8	25	70	Long



▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRc40~45 HRc45~55	HRC55~70									
○	◎	◎	◎	○		○							



SEME71 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE


- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent for cutting prehardened steels, carbon steels, alloy steels of molds and dies, up to HRc55 and machine parts.
- ▶ Due to Multiple Helix for 3.0mm and over 3.0mm diameter end mills, vibration can be minimized at cutting, and wear of cutting tool can be decreased too.
 - Designed equal index flute for long length end mills.
- ▶ Due to gash land geometry used at end tooth, heavy duty cutting can be achieved.
- ▶ Available various length products like short, regular and long length end mills etc.



◇ Call for Availability

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	Remark
	D1	D2	L1	L2	
SEME7108030	8.0	8	30	70	Long
SEME7110022	10.0	10	22	65	Short
SEME711100	10.0	10	25	75	Regular
SEME7110030	10.0	10	30	75	Long
SEME7110035	10.0	10	35	75	Long
SEME7112026	12.0	12	26	70	Short
SEME71120	12.0	12	30	80	Regular
SEME7112035	12.0	12	35	80	Long
SEME7112040	12.0	12	40	80	Long
SEME71140	14.0	16	35	100	Regular
SEME7116032	16.0	16	32	100	Short
SEME71160	16.0	16	40	100	Regular
SEME71180	18.0	20	45	100	Regular
SEME71200	20.0	20	45	100	Regular

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6



◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



SEME72 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG LENGTH

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.
- ▶ Available various length of cut and overall length products.



◇ Call for Availability

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
SEME7201003	1.0	6	3	60
SEME7201004	1.0	6	4	60
SEME7201005	1.0	6	5	60
SEME7201006	1.0	6	6	60
SEME7201007	1.0	6	7	60
SEME7201008	1.0	6	8	60
SEME7201010	1.0	6	10	60
SEME7201012	1.0	6	12	60
SEME7201204	1.2	6	4	60
SEME7201206	1.2	6	6	60
SEME7201208	1.2	6	8	60
SEME7201210	1.2	6	10	60
SEME7201212	1.2	6	12	60
SEME7201506	1.5	6	6	60
SEME7201508	1.5	6	8	60
SEME7201510	1.5	6	10	60
SEME7201512	1.5	6	12	60
SEME7201514	1.5	6	14	60
SEME7201516	1.5	6	16	60
SEME7202008	2.0	6	8	60
SEME7202010	2.0	6	10	60
SEME7202012	2.0	6	12	60
SEME7202014	2.0	6	14	60
SEME7202016	2.0	6	16	60
SEME7202510	2.5	6	10	60
SEME7202512	2.5	6	12	60
SEME7202516	2.5	6	16	60
SEME7202520	2.5	6	20	60

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME72 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG LENGTH

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.
- ▶ Available various length of cut and overall length products.



Call for Availability


Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
SEME7202526	2.5	6	26	60
SEME72030163S	3.0	3	16	100
SEME7203010	3.0	6	10	70
SEME7203012	3.0	6	12	70
SEME7203014	3.0	6	14	70
SEME7203016	3.0	6	16	70
SEME7203020	3.0	6	20	70
SEME7203026	3.0	6	26	70
SEME7203030	3.0	6	30	70
SEME72040204S	4.0	4	20	100
SEME7204012	4.0	6	12	70
SEME7204016	4.0	6	16	70
SEME7204020	4.0	6	20	70
SEME7204026	4.0	6	26	70
SEME7204030	4.0	6	30	70
SEME7205020	5.0	6	20	70
SEME7205025	5.0	6	25	70
SEME7205025100	5.0	6	25	100
SEME7205030	5.0	6	30	80
SEME7205035	5.0	6	35	90
SEME7205040	5.0	6	40	100
SEME7206015	6.0	6	15	60
SEME7206015080	6.0	6	15	80
SEME7206020	6.0	6	20	70
SEME7206020090	6.0	6	20	90
SEME7206025	6.0	6	25	75
SEME7206030	6.0	6	30	80
SEME7206030100	6.0	6	30	100

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME72 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG LENGTH

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.
- ▶ Available various length of cut and overall length products.



Call for Availability

Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
SEME7206030150	6.0	6	30	150
SEME7206035	6.0	6	35	90
SEME7206040	6.0	6	40	90
SEME7206040120	6.0	6	40	120
SEME7206045	6.0	6	45	150
SEME7208025	8.0	8	25	80
SEME7208030	8.0	8	30	80
SEME7208030100	8.0	8	30	100
SEME7208035	8.0	8	35	90
SEME7208040	8.0	8	40	90
SEME7208040120	8.0	8	40	120
SEME7208040150	8.0	8	40	150
SEME7208045	8.0	8	45	100
SEME7208050	8.0	8	50	100
SEME7208050150	8.0	8	50	150
SEME7210030	10.0	10	30	80
SEME7210030100	10.0	10	30	100
SEME7210035	10.0	10	35	90
SEME7210040	10.0	10	40	90
SEME7210040120	10.0	10	40	120
SEME7210045	10.0	10	45	100
SEME7210050	10.0	10	50	100
SEME7210050150	10.0	10	50	150
SEME7210050200	10.0	10	50	200
SEME7210055	10.0	10	55	150
SEME7210060	10.0	10	60	110
SEME7210060200	10.0	10	60	200
SEME7212035	12.0	12	35	90

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME72 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG LENGTH

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.
- ▶ Available various length of cut and overall length products.



Call for Availability

Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
SEME7212040	12.0	12	40	100
SEME7212040120	12.0	12	40	120
SEME7212045	12.0	12	45	130
SEME7212050	12.0	12	50	100
SEME7212050150	12.0	12	50	150
SEME7212055	12.0	12	55	110
SEME7212060	12.0	12	60	110
SEME7212060150	12.0	12	60	150
SEME7212060200	12.0	12	60	200
SEME7212065	12.0	12	65	150
SEME7212070	12.0	12	70	120
SEME7212070200	12.0	12	70	200
SEME7214050	14.0	16	50	110
SEME7214060	14.0	16	60	150
SEME7216040	16.0	16	40	150
SEME7216050	16.0	16	50	110
SEME7216050150	16.0	16	50	150
SEME7216060	16.0	16	60	120
SEME7216070	16.0	16	70	130
SEME7216070150	16.0	16	70	150
SEME7216070200	16.0	16	70	200
SEME7216080	16.0	16	80	150
SEME7216090	16.0	16	90	150
SEME72160110	16.0	16	110	200
SEME72160120	16.0	16	120	250
SEME7218050	18.0	20	50	120
SEME7218070	18.0	20	70	130
SEME72180100	18.0	20	100	200

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME72 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG LENGTH

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.
- ▶ Available various length of cut and overall length products.



Call for Availability

Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
SEME7220050	20.0	20	50	110
SEME7220050150	20.0	20	50	150
SEME7220060	20.0	20	60	130
SEME7220070	20.0	20	70	130
SEME7220080	20.0	20	80	150
SEME7220090	20.0	20	90	150
SEME7220090200	20.0	20	90	200
SEME72200110	20.0	20	110	200
SEME72200120	20.0	20	120	250
SEME7222075	22.0	20	75	150
SEME72220110	22.0	20	110	200
SEME7225070	25.0	25	70	150
SEME7225090	25.0	25	90	150
SEME72250110	25.0	25	110	200
SEME72250120	25.0	25	120	250

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Pearlhardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○		○							



SEME73 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG NECK

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.
- ▶ Available various length of cut and overall length products.



◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	D1	D2	L1	L3	L2	D3
SEME7301002	1.0	4	1.5	2	50	0.95
SEME7301003	1.0	4	1.5	3	50	0.95
SEME7301004	1.0	4	1.5	4	50	0.95
SEME7301005	1.0	4	1.5	5	50	0.95
SEME7301006	1.0	4	1.5	6	50	0.95
SEME7301007	1.0	4	1.5	7	50	0.95
SEME7301008	1.0	4	1.5	8	50	0.95
SEME7301010	1.0	4	1.5	10	50	0.95
SEME7301012	1.0	4	1.5	12	50	0.95
SEME7301014	1.0	4	1.5	14	50	0.95
SEME7301016	1.0	4	1.5	16	50	0.95
SEME7301018	1.0	4	1.5	18	50	0.95
SEME7301020	1.0	4	1.5	20	50	0.95
SEME7301022	1.0	4	1.5	22	60	0.95
SEME7301026	1.0	4	1.5	26	60	0.95
SEME7301030	1.0	4	1.5	30	70	0.95
SEME7301040	1.0	4	1.5	40	80	0.95
SEME7301050	1.0	4	1.5	50	100	0.95
SEME7301204	1.2	4	1.8	4	50	1.15
SEME7301206	1.2	4	1.8	6	50	1.15
SEME7301208	1.2	4	1.8	8	50	1.15
SEME7301210	1.2	4	1.8	10	50	1.15
SEME7301212	1.2	4	1.8	12	50	1.15
SEME7301214	1.2	4	1.8	14	50	1.15
SEME7301216	1.2	4	1.8	16	50	1.15
SEME7301220	1.2	4	1.8	20	50	1.15
SEME7301226	1.2	4	1.8	26	60	1.15
SEME7301230	1.2	4	1.8	30	70	1.15
SEME7301504	1.5	4	2.3	4	50	1.45
SEME7301505	1.5	4	2.3	5	50	1.45
SEME7301506	1.5	4	2.3	6	50	1.45
SEME7301507	1.5	4	2.3	7	50	1.45

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○	○	○							



SEME73 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG NECK

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.
- ▶ Available various length of cut and overall length products.



◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	D1	D2	L1	L3	L2	D3
SEME7301508	1.5	4	2.3	8	50	1.45
SEME7301510	1.5	4	2.3	10	50	1.45
SEME7301512	1.5	4	2.3	12	50	1.45
SEME7301514	1.5	4	2.3	14	50	1.45
SEME7301516	1.5	4	2.3	16	50	1.45
SEME7301518	1.5	4	2.3	18	50	1.45
SEME7301520	1.5	4	2.3	20	50	1.45
SEME7301522	1.5	4	2.3	22	60	1.45
SEME7301526	1.5	4	2.3	26	60	1.45
SEME7301530	1.5	4	2.3	30	70	1.45
SEME7302006	2.0	4	3	6	50	1.95
SEME7302008	2.0	4	3	8	50	1.95
SEME7302010	2.0	4	3	10	50	1.95
SEME7302012	2.0	4	3	12	50	1.95
SEME7302014	2.0	4	3	14	50	1.95
SEME7302016	2.0	4	3	16	50	1.95
SEME7302018	2.0	4	3	18	50	1.95
SEME7302020	2.0	4	3	20	50	1.95
SEME7302022	2.0	4	3	22	60	1.95
SEME7302026	2.0	4	3	26	60	1.95
SEME7302030	2.0	4	3	30	70	1.95
SEME7302035	2.0	4	3	35	70	1.95
SEME7302040	2.0	4	3	40	80	1.95
SEME7302045	2.0	4	3	45	90	1.95
SEME7302050	2.0	4	3	50	100	1.95
SEME7302060	2.0	4	3	60	110	1.95
SEME7302508	2.5	4	4	8	50	2.40
SEME7302510	2.5	4	4	10	50	2.40
SEME7302512	2.5	4	4	12	50	2.40
SEME7302514	2.5	4	4	14	50	2.40
SEME7302516	2.5	4	4	16	50	2.40
SEME7302518	2.5	4	4	18	50	2.40

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	◎	○	○	○							



SEME73 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG NECK

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.
- ▶ Available various length of cut and overall length products.




Call for Availability

Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	D1	D2	L1	L3	L2	D3
SEME7302520	2.5	4	4	20	50	2.40
SEME7302522	2.5	4	4	22	60	2.40
SEME7302526	2.5	4	4	26	60	2.40
SEME7302530	2.5	4	4	30	70	2.40
SEME7302535	2.5	4	4	35	70	2.40
SEME7302540	2.5	4	4	40	80	2.40
SEME7302545	2.5	4	4	45	90	2.40
SEME7302550	2.5	4	4	50	100	2.40
SEME7303006	3.0	6	4.5	6	50	2.85
SEME7303008	3.0	6	4.5	8	50	2.85
SEME7303010	3.0	6	4.5	10	50	2.85
SEME7303012	3.0	6	4.5	12	50	2.85
SEME7303014	3.0	6	4.5	14	60	2.85
SEME7303016	3.0	6	4.5	16	60	2.85
SEME7303018	3.0	6	4.5	18	60	2.85
SEME7303020	3.0	6	4.5	20	60	2.85
SEME7303022	3.0	6	4.5	22	65	2.85
SEME7303026	3.0	6	4.5	26	65	2.85
SEME7303030	3.0	6	4.5	30	70	2.85
SEME7303035	3.0	6	4.5	35	70	2.85
SEME7303040	3.0	6	4.5	40	80	2.85
SEME7303045	3.0	6	4.5	45	90	2.85
SEME7303050	3.0	6	4.5	50	100	2.85
SEME7303060	3.0	6	4.5	60	100	2.85
SEME7304008	4.0	6	6	8	50	3.85
SEME7304010	4.0	6	6	10	50	3.85
SEME7304012	4.0	6	6	12	50	3.85
SEME7304014	4.0	6	6	14	60	3.85
SEME7304016	4.0	6	6	16	60	3.85
SEME7304018	4.0	6	6	18	60	3.85
SEME7304020	4.0	6	6	20	60	3.85
SEME7304022	4.0	6	6	22	65	3.85

▶ NEXT PAGE
◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	○	○							



SEME73 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG NECK

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRc55 which are used for molds & dies.
- ▶ Available various length of cut and overall length products.



Call for Availability


Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	D1	D2	L1	L3	L2	D3
SEME7304026	4.0	6	6	26	65	3.85
SEME7304030	4.0	6	6	30	70	3.85
SEME7304035	4.0	6	6	35	70	3.85
SEME7304040	4.0	6	6	40	80	3.85
SEME7304045	4.0	6	6	45	90	3.85
SEME7304050	4.0	6	6	50	100	3.85
SEME7304060	4.0	6	6	60	100	3.85
SEME7305016	5.0	6	8	16	60	4.85
SEME7305020	5.0	6	8	20	60	4.85
SEME7305026	5.0	6	8	26	65	4.85
SEME7305030	5.0	6	8	30	70	4.85
SEME7305035	5.0	6	8	35	75	4.85
SEME7305040	5.0	6	8	40	80	4.85
SEME7305050	5.0	6	8	50	90	4.85
SEME7305060	5.0	6	8	60	100	4.85
SEME7306015	6.0	6	9	15	60	5.85
SEME7306020	6.0	6	9	20	60	5.85
SEME7306030	6.0	6	9	30	70	5.85
SEME7306032	6.0	6	9	32	90	5.85
SEME7308025	8.0	8	12	25	70	7.70
SEME7308030	8.0	8	12	30	80	7.70
SEME7308042	8.0	8	12	42	100	7.70
SEME7310030	10.0	10	15	30	75	9.70
SEME7310035	10.0	10	15	35	80	9.70
SEME7310045	10.0	10	15	45	100	9.70
SEME7312035	12.0	12	20	35	80	11.70
SEME7312040	12.0	12	20	40	90	11.70
SEME7312050	12.0	12	20	50	110	11.70

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	○	○							



CARBIDE, 6 FLUTE 45° HELIX (Regular, Long Shank)

- ▶ Due to new coating and new tool geometry, outstanding cutting ability and wear resistance.
- ▶ Excellent performance when cutting prehardened steels, up to HRC55 which are used for molds & dies.
- ▶ Due to 45 helix angle, better surface roughness can be achieved at side cutting.
- ▶ Available various effective length and overall length products.



◇ Call for Availability



Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	Remark
	D1	D2	L1	L2	
SEME75060	6.0	6	15	60	Regular
SEME7506020	6.0	6	20	70	Long
SEME7506030	6.0	6	30	80	Long
SEME7506030110	6.0	6	30	110	Long
SEME75080	8.0	8	20	70	Regular
SEME7508030	8.0	8	30	80	Long
SEME7508035	8.0	8	35	90	Long
SEME7508040	8.0	8	40	90	Long
SEME7508040130	8.0	8	40	130	Long
SEME75100	10.0	10	25	75	Regular
SEME7510030	10.0	10	30	80	Long
SEME7510040	10.0	10	40	90	Long
SEME7510050	10.0	10	50	100	Long
SEME7510050150	10.0	10	50	150	Long
SEME75120	12.0	12	30	80	Regular
SEME7512040	12.0	12	40	90	Long
SEME7512050	12.0	12	50	100	Long
SEME7512060	12.0	12	60	110	Long
SEME7512060150	12.0	12	60	150	Long
SEME75160	16.0	16	40	100	Regular
SEME7516050	16.0	16	50	110	Long
SEME7516060	16.0	16	60	120	Long
SEME7516090	16.0	16	90	150	Long
SEME75160110	16.0	16	110	200	Long
SEME75160110250	16.0	16	110	250	Long
SEME75200	20.0	20	45	100	Regular
SEME7520060	20.0	20	60	120	Long
SEME7520070	20.0	20	70	130	Long
SEME75200110	20.0	20	110	200	Long
SEME75200110250	20.0	20	110	250	Long
SEME75200110300	20.0	20	110	300	Long

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6


◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45 HRc45~55	HRC55~70									
◎	◎	◎	◎	○		○							



CARBIDE, 4&5 FLUTE MULTIPLE HELIX SHORT LENGTH ROUGHING CORNER RADIUS

- ▶ Unique flute design for excellent chip evacuation and vibration reduction.
- ▶ Optimal roughing tooth profile to reduce cutting forces.
- ▶ Special tool geometry for high feed rate and heavy cutting.
- ▶ Strong end tooth design for plunge and pocket milling.
- ▶ Custom engineered coating to allow long tool life and excellent chip evacuation.



◇ Call for Availability

5 Flute, 44°/45°/45°

Unit : mm

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
PLAIN	FLAT	R	D1	D2	L1	L2	
G9D75060	G9D67060	RO.5	6.0	6	9	57	4
G9D75080	G9D67080	RO.5	8.0	8	12	63	4
G9D75100	G9D67100	RO.5	10.0	10	15	72	4
G9D75120	G9D67120	RO.5	12.0	12	18	83	4
G9D75160	G9D67160	R1.0	16.0	16	24	92	5
G9D75200	G9D67200	R1.0	20.0	20	30	104	5

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.05	h6

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRC30~40	HRC40~45 HRc45~55	HRC55~70									
◎	◎	◎	○		○	◎	○						




X-SPEED ROUGHER

G9D76 SERIES PLAIN SHANK
G9D68 SERIES FLAT SHANK

CARBIDE, 4&5 FLUTE MULTIPLE HELIX LONG LENGTH ROUGHING CORNER RADIUS

- ▶ Unique flute design for excellent chip evacuation and vibration reduction.
- ▶ Optimal roughing tooth profile to reduce cutting forces.
- ▶ Special tool geometry for high feed rate and heavy cutting.
- ▶ Strong end tooth design for plunge and pocket milling.
- ▶ Custom engineered coating to allow long tool life and excellent chip evacuation.



◇ Call for Availability

5 Flute, 44°/45°


Unit : mm

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
PLAIN	FLAT	R	D1	D2	L1	L2	
G9D76060	G9D68060	R0.5	6.0	6	9	57	4
G9D76080	G9D68080	R0.5	8.0	8	12	63	4
G9D76100	G9D68100	R0.5	10.0	10	15	72	4
G9D76120	G9D68120	R0.5	12.0	12	18	83	4
G9D76160	G9D68160	R1.0	16.0	16	24	92	5
G9D76200	G9D68200	R1.0	20.0	20	30	104	5

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.05	h6

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		○	◎	○						




X-SPEED ROUGHER

G9D77 SERIES PLAIN SHANK
G9D69 SERIES FLAT SHANK

CARBIDE, 4&5 FLUTE MULTIPLE HELIX LONG REACH ROUGHING CORNER RADIUS

- ▶ Unique flute design for excellent chip evacuation and vibration reduction.
- ▶ Optimal roughing tooth profile to reduce cutting forces.
- ▶ Special tool geometry for high feed rate and heavy cutting.
- ▶ Strong end tooth design for plunge and pocket milling.
- ▶ Custom engineered coating to allow long tool life and excellent chip evacuation.



◇ Call for Availability

5 Flute, 44°/45°


Unit : mm

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	No. of Flute
PLAIN	FLAT	R	D1	D2	L1	L3	L2	D3	
G9D77060	G9D69060	R0.5	6.0	6	9	18	57	5.50	4
G9D77080	G9D69080	R0.5	8.0	8	12	24	63	7.50	4
G9D77100	G9D69100	R0.5	10.0	10	15	30	72	9.50	4
G9D77120	G9D69120	R0.5	12.0	12	18	36	83	11.50	4
G9D77160	G9D69160	R1.0	16.0	16	24	48	100	15.50	5
G9D77200	G9D69200	R1.0	20.0	20	30	60	110	19.20	5

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.05	h6

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		○	◎	○						




X-SPEED ROUGHER

GAE53 SERIES FLAT SHANK

HSS-PM, 4&5 FLUTE MULTIPLE HELIX SHORT LENGTH ROUGHING CORNER RADIUS

- Unique flute design for excellent chip evacuation and vibration reduction.
- Optimal roughing tooth profile to reduce cutting forces.
- Special tool geometry for high feed rate and heavy cutting.
- Strong end tooth design for plunge and pocket milling.
- Custom engineered coating to allow long tool life and excellent chip evacuation.



◇ Call for Availability

EDP No.	Corner Radius	Mill Diameter		Shank Diameter	Length of Cut	Overall Length	No. of Flute
		Metric	Inch				
FLAT	R	D1(js12)		D2(h6)	L1	L2	
GAE53060	R0.5	6.0	.2362	6	13	57	4
GAE53070	R0.5	7.0	.2756	10	16	66	4
GAE53080	R0.5	8.0	.3150	10	19	69	4
GAE53090	R0.5	9.0	.3543	10	19	69	4
GAE53100	R0.5	10.0	.3937	10	22	72	4
GAE53120	R0.5	12.0	.4724	12	26	83	4
GAE53140	R1.0	14.0	.5512	16	26	83	5
GAE53160	R1.0	16.0	.6299	16	32	92	5
GAE53180	R1.0	18.0	.7087	20	32	92	5
GAE53200	R1.0	20.0	.7874	20	38	104	5

Tolerances according to DIN 7160 & 7161

Tolerance range in μm						
Nominal-Diameter in mm						
	from 1 to 3	over 3 to 6	over 6 to 10	over 10 to 18	over 18 to 30	over 30 to 50
js12	± 50	± 60	± 75	± 90	± 105	± 125
h6	0 - 6	0 - 8	0 - 9	0 - 11	0 - 13	0 - 16

◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○			◎	◎	○						




CARBIDE, 2 FLUTE BALL NOSE

GMF15 SERIES

MATERIAL	P					
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS	
HARDNESS	~ HRc35		HRc35 ~ HRc45		HRc45 ~ HRc55	
STRENGTH	~ 1100N/mm ²		1110 ~ 1500N/mm ²		1500 ~ 2000N/mm ²	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
R.002 × .004	39400	21.3	39370	19.3	32480	15.6
R.004 × .008	29530	28.0	29530	24.4	26570	22.2
R.006 × .012	29530	34.8	29530	31.3	26570	28.0
R.075 × .015	29490	44.1	31500	42.1	28350	37.2
R.010 × .020	29530	55.7	29530	48.8	26570	44.1
R.012 × .024	29530	67.5	29530	58.1	26570	51.2
R.014 × .028	29530	79.1	29530	67.5	26570	60.4
R.0155 × .031	30480	93.5	30480	79.1	27430	72.1
R.0175 × .035	30370	103.9	30370	89.8	27330	81.3
R.0234 × 3/64	30240	121.5	29030	102.4	26000	91.7
R1/32 × 1/16	28350	120.5	27210	100.4	24380	89.4
R.0391 × 5/64	30050	135.6	28910	114.4	24190	95.3
R3/64 × 3/32	24990	145.1	24040	125.2	20160	99.2
R1/16 × 1/8	18770	133.9	18030	118.3	15120	89.4
R3/32 × 3/16	12310	131.7	11820	113.8	9920	86.4
R.102 × 13/64	10820	132.9	10350	112.2	8720	85.8
R1/8 × 1/4	7880	108.3	7600	91.5	6240	69.1
R9/64 × 9/32	7070	102.2	6820	85.6	5680	65.6
R5/32 × 5/16	6710	100.0	6470	83.3	5440	64.4
R3/16 × 3/8	5860	91.7	5610	77.0	4720	59.5
R1/4 × 1/2	3940	65.8	3780	55.7	3170	42.3
R9/32 × 9/16	3670	64.8	3530	57.9	2970	41.7
R5/16 × 5/8	3370	63.2	3240	52.4	2720	40.6
R3/8 × 3/4	2800	58.3	2710	48.4	2270	37.2



RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE BALL NOSE WITH NECK

GMF16 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Sub-columns include HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Ap(inch).

DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = inch/min.



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE BALL NOSE WITH NECK

GMF16 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Sub-columns include HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Ap(inch).

DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE BALL NOSE WITH NECK

GMF16 SERIES

MATERIAL		P								
		NON-ALLOYED STEELS ALLOY STEELS CAST IRON			ALLOY STEELS HEAT RESISTANT STEELS			HARDENED STEELS		
HARDNESS		~ HRc35			HRc35 ~ HRc45			HRc45 ~ HRc55		
STRENGTH		~ 1100N/mm ²			1110 ~ 1500N/mm ²			1500 ~ 2000N/mm ²		
DIA.	LBS	RPM	FEED	Ap(inch)	RPM	FEED	Ap(inch)	RPM	FEED	Ap(inch)
1/4	1-3/16	6140	70.7	.0157	5860	59.5	.0131	5200	49.4	.0087
5/16	1	4890	71.5	.0197	4640	59.5	.0164	4030	50.8	.0109
5/16	1-3/8	4890	71.5	.0197	4640	59.5	.0164	4030	50.8	.0109
3/8	1-3/16	4040	68.1	.0236	3860	57.9	.0197	3360	49.6	.0131
3/8	1-3/16	4040	68.1	.0236	3860	57.9	.0197	3360	49.6	.0131
3/8	1-1/2	4040	68.1	.0236	3860	57.9	.0197	3360	49.6	.0131
1/2	1-1/4	3020	56.5	.0450	2880	48.4	.0375	2500	40.9	.0250
1/2	1-1/4	3020	56.5	.0450	2880	48.4	.0375	2500	40.9	.0250




DIA. = Diameter
LBS = Length Below Shank
RPM = rev./min.
FEED = inch/min.

CARBIDE, 4 FLUTE BALL NOSE

GMF17 SERIES

MATERIAL		P					
		NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS	
HARDNESS		~ HRc35		HRc35 ~ HRc45		HRc45 ~ HRc55	
STRENGTH		~ 1100N/mm ²		1110 ~ 1500N/mm ²		1500 ~ 2000N/mm ²	
DIAMETER		RPM	FEED	RPM	FEED	RPM	FEED
R1/16	× 1/8	22700	202.0	16540	144.3	15120	135.8
R3/32	× 3/16	17600	224.4	13020	152.6	12250	143.5
R1/8	× 1/4	14400	231.3	11530	167.3	10490	142.5
R5/32	× 5/16	11400	208.3	9270	157.9	8390	132.9
R3/16	× 3/8	9600	189.8	7720	142.5	6990	118.7
R1/4	× 1/2	7200	158.5	5790	118.7	5230	89.4



RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE CORNER RADIUS

GMF18 SERIES

MATERIAL		P					
		NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS	
HARDNESS		~ HRc35		HRc35 ~ HRc45		HRc45 ~ HRc55	
STRENGTH		~ 1100N/mm ²		1110 ~ 1500N/mm ²		1500 ~ 2000N/mm ²	
DIAMETER		RPM	FEED	RPM	FEED	RPM	FEED
3/64		25000	9.7	15870	4.1	9830	2.4
1/16		20800	9.3	12760	4.1	8030	2.2
5/64		18100	10.2	11650	4.7	7260	2.8
1/8		12500	10.4	8090	5.1	4990	2.6
9/64		11700	12.0	7540	5.9	4690	3.0
13/64		8900	15.9	5620	7.7	3680	3.7
1/4		7500	18.5	4760	9.3	3100	4.5
5/16		6000	21.5	3830	9.8	2540	4.7
3/8		5300	22.2	3440	10.2	2120	4.9
1/2		3900	15.6	2630	8.5	1590	3.7
9/16		3500	15.0	2390	7.7	1450	3.5
5/8		3100	14.4	2120	6.7	1290	3.2
3/4		2600	11.6	1720	4.9	1050	2.6



RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE CORNER RADIUS WITH NECK

GMF19 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Sub-columns: HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Ap(inch). Rows list various mill sizes and materials.

DIA. = Diameter
LBS = Length Below Shank
RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE CORNER RADIUS WITH NECK

GMF19 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Sub-columns: HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Ap(inch). Rows list various mill sizes and materials.

DIA. = Diameter
LBS = Length Below Shank
RPM = rev./min.
FEED = inch/min.




CARBIDE, 4 FLUTE CORNER RADIUS


GMF20 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Sub-columns: HARDNESS, STRENGTH, DIAMETER, RPM, FEED. Rows list various mill diameters and materials.

* 1.5XD Axial cutting depth should be for DIA over 5/8 inch



RPM = rev./min.
FEED = inch/min.






RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE CORNER RADIUS WITH NECK

GMF21 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Sub-columns: HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Ap(inch).



DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE WITH NECK


GMF22 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Sub-columns: HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Ap(inch).



DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = inch/min.

(Depth of Cut per one pass)



RECOMMENDED CUTTING CONDITIONS



CARBIDE, 2 FLUTE WITH NECK

GMF22 SERIES

MATERIAL		P								
		NON-ALLOYED STEELS ALLOY STEELS CAST IRON			ALLOY STEELS HEAT RESISTANT STEELS			HARDENED STEELS		
HARDNESS		~ HRC35			HRC35 ~ HRC45			HRC45 ~ HRC55		
STRENGTH		~ 1100N/mm ²			1110 ~ 1500N/mm ²			1500 ~ 2000N/mm ²		
DIA.	LBS	RPM	FEED	Ap(inch)	RPM	FEED	Ap(inch)	RPM	FEED	Ap(inch)
1/16	3/4	14510	21.5	.0014	13680	15.2	.0011	12090	11.2	.0008
5/64	1/4	14510	32.5	.0049	13710	24.6	.0038	12090	18.9	.0027
5/64	5/16	14510	32.5	.0049	13710	24.6	.0038	12090	18.9	.0027
5/64	3/8	14510	32.5	.0049	13710	24.6	.0038	12090	18.9	.0027
5/64	1/2	13060	26.4	.0028	12340	19.9	.0022	10890	15.4	.0016
5/64	9/16	13060	26.4	.0028	12340	19.9	.0022	10890	15.4	.0016
5/64	5/8	13060	26.4	.0028	12340	19.9	.0022	10890	15.4	.0016
5/64	3/4	13060	26.4	.0018	12340	19.9	.0014	10890	15.4	.0010
3/32	5/16	12910	40.2	.0059	12180	28.2	.0046	10810	21.1	.0033
3/32	1/2	11620	32.5	.0034	10960	22.8	.0026	9730	17.1	.0019
3/32	5/8	11620	32.5	.0034	10960	22.8	.0026	9730	17.1	.0019
3/32	3/4	11620	32.5	.0034	10960	22.8	.0026	9730	17.1	.0019
1/8	5/16	10300	32.1	.0113	9730	22.4	.0087	6240	16.7	.0063
1/8	3/8	10300	32.1	.0113	9730	22.4	.0087	6240	16.7	.0063
1/8	1/2	10300	32.1	.0079	9730	22.4	.0061	6240	16.7	.0044
1/8	9/16	10300	32.1	.0079	9730	22.4	.0061	6240	16.7	.0044
1/8	5/8	10300	32.1	.0079	9730	22.4	.0061	6240	16.7	.0044
1/8	11/16	9270	26.0	.0045	8760	18.3	.0035	5610	13.6	.0025
1/8	3/4	9270	26.0	.0045	8760	18.3	.0035	5610	13.6	.0025
1/8	1	9270	26.0	.0045	8760	18.3	.0035	5610	13.6	.0025
3/16	3/8	6720	42.9	.0169	6380	38.4	.0131	5630	25.4	.0094
3/16	1/2	6720	42.9	.0169	6380	38.4	.0131	5630	25.4	.0094
3/16	5/8	6720	42.9	.0118	6380	38.4	.0092	5630	25.4	.0066
3/16	11/16	6720	42.9	.0118	6380	38.4	.0092	5630	25.4	.0066
3/16	3/4	6720	42.9	.0118	6380	38.4	.0092	5630	25.4	.0066
3/16	1	6050	34.8	.0067	5740	31.1	.0052	5060	20.7	.0037
3/16	1-3/16	6050	34.8	.0067	5740	31.1	.0052	5060	20.7	.0037
13/64	3/4	6200	44.1	.0128	5910	34.3	.0100	5230	23.0	.0071
13/64	1-3/16	5580	35.6	.0073	5320	27.8	.0057	4710	18.7	.0041
13/64	1-3/8	5580	35.6	.0073	5320	27.8	.0057	4710	18.7	.0041
13/64	1-1/2	5580	35.6	.0073	5320	27.8	.0057	4710	18.7	.0041
13/64	2	5580	35.6	.0046	5320	27.8	.0035	4710	18.7	.0025
1/4	5/8	5010	39.2	.0225	4720	30.5	.0175	4160	20.5	.0125
1/4	3/4	5010	39.2	.0225	4720	30.5	.0175	4160	20.5	.0125
1/4	1-3/16	5010	39.2	.0157	4720	30.5	.0122	4160	20.5	.0087
5/16	1	4030	37.6	.0197	3830	29.7	.0153	3330	19.9	.0109
3/8	1-3/16	3360	37.2	.0236	3200	28.2	.0184	2760	16.5	.0131
3/8	1-3/4	3360	37.2	.0236	3200	28.2	.0184	2760	16.5	.0131
1/2	1-3/8	2500	29.7	.0450	2380	22.2	.0350	2060	13.0	.0250
1/2	2	2500	29.7	.0315	2380	22.2	.0245	2060	13.0	.0175

DIA. = Diameter
LBS = Length Below Shank
RPM = rev./min.
FEED = inch/min.

(Depth of Cut per one pass)





RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE

GMF23 SERIES

MATERIAL	P						M	
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		STAINLESS STEELS	
HARDNESS	~ HRC35		HRC35 ~ HRC45		HRC45 ~ HRC55			
STRENGTH	~ 1100N/mm ²		1110 ~ 1500N/mm ²		1500 ~ 2000N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
.004	41300	3.5	24800	2.1	16540	0.7	20670	1.7
.008	41300	3.8	24800	2.1	16540	0.7	20670	1.7
.012	38400	4.0	23000	2.4	15350	0.7	19190	1.9
.015	40900	4.5	24600	2.6	16380	1.0	20470	2.1
.020	35400	5.0	21300	2.8	14170	1.0	17720	2.4
.024	31500	5.7	18900	3.3	12600	1.2	15750	2.8
.028	27600	6.4	16500	3.8	11020	1.2	13780	3.1
.031	25400	7.1	15200	4.3	10160	1.4	12700	3.5
.035	23800	7.3	14300	4.5	9520	1.4	11900	3.8
.040	21200	7.3	12700	4.5	8460	1.4	10580	3.8
.047	18100	7.8	10900	4.7	7240	1.7	9050	4.0
1/16	14200	7.6	8500	4.5	5670	1.4	7090	3.8
5/64	11700	8.2	7600	5.2	5080	1.5	6350	3.9
3/32	10800	9.1	6900	5.8	4410	1.7	5730	4.8
1/8	8400	8.7	5300	5.6	3170	1.7	4370	5.0
9/64	8100	10.8	5000	6.7	3090	1.7	4160	5.6
3/16	6500	12.8	4000	7.6	2490	2.0	3330	6.3
13/64	6100	13.4	3700	8.0	2250	2.2	3060	6.7
1/4	5300	14.3	3200	9.1	1890	2.2	2680	7.4
17/64	5000	14.4	3000	8.7	1850	2.5	2560	7.4
9/32	4800	14.9	2900	8.5	1800	2.7	2420	7.2
5/16	4200	15.9	2500	8.3	1690	3.1	2120	7.4
11/32	3900	14.7	2300	7.6	1560	2.9	1940	7.0
23/64	3700	14.5	2200	7.2	1500	2.7	1860	7.0
3/8	3400	14.3	2100	7.0	1430	2.7	1760	7.0
13/32	3200	13.2	2000	6.4	1330	2.5	1630	6.4
7/16	3000	12.4	1800	6.0	1250	2.3	1500	6.0
1/2	2600	11.2	1600	5.3	1100	2.1	1290	5.3
9/16	2400	10.1	1500	5.0	1010	1.9	1190	5.0
5/8	2200	9.1	1400	4.6	910	1.7	1070	4.6
3/4	1800	7.4	1100	3.5	710	1.2	880	3.5



RPM = rev./min.
FEED = inch/min.






RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG

GMF24 SERIES

MATERIAL		P					
		NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS	
		~ HRC35 ~ 1100N/mm ²		HRC35 ~ HRC45 1110 ~ 1500N/mm ²		HRC45 ~ HRC55 1500 ~ 2000N/mm ²	
HARDNESS	STRENGTH						
DIA.	LOC	RPM	FEED	RPM	FEED	RPM	FEED
3/64	1/8	13710	3.0	10970	2.6	6860	1.2
3/64	5/32	13710	3.0	10970	2.6	6860	1.2
3/64	1/4	12340	2.8	9870	2.4	6170	1.0
3/64	5/16	12340	2.4	9870	2.2	6170	1.0
3/64	3/8	12340	2.2	9870	2.0	6170	0.8
1/16	1/4	10000	2.8	8000	2.4	5000	1.0
1/16	5/16	10000	2.8	8000	2.4	5000	1.0
1/16	3/8	9000	2.4	7200	2.0	4500	0.8
1/16	1/2	9000	2.0	7200	1.8	4500	0.8
1/16	5/8	9000	2.0	7200	1.8	4500	0.8
5/64	5/16	9210	3.4	7370	2.8	4610	1.4
5/64	3/8	9210	3.4	7370	2.8	4610	1.4
5/64	1/2	8290	2.8	6640	2.4	4150	1.2
5/64	5/8	8290	2.4	6640	2.0	4150	1.0
3/32	5/8	7640	3.4	6150	2.8	3820	1.4
1/8	3/8	5670	3.5	4600	3.0	2830	1.4
1/8	1/2	5670	3.5	4600	3.0	2830	1.4
1/8	5/8	5670	3.5	4600	3.0	2830	1.4
1/8	3/4	5100	2.8	4140	2.4	2550	1.2
1/8	1	5100	2.6	4140	2.2	2550	1.0
3/16	1/2	3630	3.4	2890	2.8	1820	1.4
3/16	5/8	3630	3.4	2890	2.8	1820	1.4
3/16	3/4	3630	3.4	2890	2.8	1820	1.4
3/16	1	3270	3.0	2600	2.6	1640	1.2
3/16	1-3/16	3270	2.8	2600	2.2	1640	1.2
13/64	3/4	4130	5.5	3270	4.5	2140	2.0
13/64	1	4130	5.5	3270	4.5	2140	2.0
13/64	1-3/16	3720	4.5	2940	3.7	1930	1.6
13/64	1-1/2	3720	4.5	2940	3.7	1930	1.6
1/4	5/8	3390	6.3	2720	5.3	1760	2.4
1/4	3/4	3390	6.3	2720	5.3	1760	2.4
1/4	1	3390	6.3	2720	5.3	1760	2.4
1/4	1-3/16	3390	5.3	2720	4.5	1760	2.2
1/4	1-3/8	3050	4.9	2450	3.9	1580	2.0
1/4	1-1/2	3050	4.3	2450	3.5	1580	1.6
1/4	1-3/4	3050	4.3	2450	3.5	1580	1.6
5/16	1	2930	7.7	2320	5.9	1530	2.8
5/16	1-3/16	2930	7.7	2320	5.9	1530	2.8
5/16	1-3/8	2930	7.7	2320	5.9	1530	2.8
5/16	1-1/2	2930	6.5	2320	5.1	1530	2.4

DIA. = Diameter
LOC = Length of Cut
RPM = rev./min.
FEED = inch/min.





RECOMMENDED CUTTING CONDITIONS


CARBIDE, 2 FLUTE LONG

GMF24 SERIES

MATERIAL		P					
		NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS	
		~ HRC35 ~ 1100N/mm ²		HRC35 ~ HRC45 1110 ~ 1500N/mm ²		HRC45 ~ HRC55 1500 ~ 2000N/mm ²	
HARDNESS	STRENGTH						
DIA.	LOC	RPM	FEED	RPM	FEED	RPM	FEED
5/16	1-3/4	2630	5.9	2080	4.5	1380	2.2
5/16	2	2630	5.1	2080	4.1	1380	2.0
3/8	1-3/16	2700	8.3	2200	6.5	1330	3.0
3/8	1-3/8	2700	8.3	2200	6.5	1330	3.0
3/8	1-1/2	2700	8.3	2200	6.5	1330	3.0
3/8	1-3/4	2700	7.1	2200	5.5	1330	2.6
3/8	2	2430	6.3	1980	4.9	1200	2.4
3/8	2-3/8	2430	5.5	1980	4.3	1200	2.0
1/2	1-3/8	1790	5.3	1490	4.7	900	2.0
1/2	1-1/2	1790	5.3	1490	4.7	900	2.0
1/2	1-3/4	1790	5.3	1490	4.7	900	2.0
1/2	2	1790	4.5	1490	3.9	900	1.6
1/2	2-1/8	1790	4.5	1490	3.9	900	1.6
1/2	2-3/8	1790	4.5	1490	3.9	900	1.6
5/8	1-1/2	1730	5.5	1300	4.1	810	2.0
3/4	3-1/2	1340	3.4	1050	2.4	660	1.2
3/4	4-1/4	1210	3.0	940	2.1	600	1.0



DIA. = Diameter
LOC = Length of Cut
RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE

GMF25, GMF26 SERIES

MATERIAL	P						M	
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		STAINLESS STEELS	
	~ HRc35		HRc35 ~ HRc45		HRc45 ~ HRc55			
STRENGTH	~ 1100N/mm ²		1110 ~ 1500N/mm ²		1500 ~ 2000N/mm ²			
DIA.	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/64	22680	11.8	13610	7.1	9070	2.1	11340	5.9
1/16	17720	11.3	10630	6.9	7090	2.1	8860	5.9
5/64	14560	12.1	9520	7.4	6350	2.2	7940	6.1
3/32	13440	13.6	8610	8.5	5510	2.6	7170	7.2
1/8	10540	13.0	6570	8.2	3970	2.4	5460	6.9
9/64	10090	18.8	6230	11.7	3860	2.6	5200	9.5
3/16	8180	24.0	4960	14.5	3110	2.6	4160	11.9
13/64	7640	25.1	4580	15.2	2810	3.0	3830	12.6
7/32	7330	27.1	4410	16.5	2670	3.3	3710	13.4
1/4	6570	27.1	3970	16.7	2360	3.3	3350	13.4
17/64	6290	27.5	3800	16.5	2310	3.6	3200	13.8
9/32	5980	27.7	3610	15.9	2250	3.9	3030	13.9
19/64	5650	28.7	3390	16.1	2190	4.3	2840	14.3
5/16	5290	29.6	3170	15.9	2120	4.6	2650	14.7
11/32	4830	27.5	2910	14.5	1950	4.1	2420	13.6
23/64	4590	26.9	2790	13.9	1870	4.1	2330	13.2
3/8	4280	26.5	2620	13.0	1780	3.9	2200	13.0
7/16	3710	23.2	2280	11.2	1560	3.5	1880	11.0
1/2	3240	20.7	1980	9.9	1370	3.2	1610	9.5
9/16	3030	18.8	1860	9.1	1260	2.9	1510	8.9
5/8	2770	17.6	1710	8.5	1140	2.5	1390	8.3
3/4	2200	13.9	1400	7.0	890	1.6	1100	6.4



RPM = rev./min.
FEED = inch/min.





RECOMMENDED CUTTING CONDITIONS


CARBIDE, 4 FLUTE LONG

GMF27 SERIES

MATERIAL	P						
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		
	~ HRc35		HRc35 ~ HRc45		HRc45 ~ HRc55		
STRENGTH	~ 1100N/mm ²		1110 ~ 1500N/mm ²		1500 ~ 2000N/mm ²		
DIA.	LOC	RPM	FEED	RPM	FEED	RPM	FEED
3/64	1/8	16330	8.1	9310	3.2	5710	1.6
3/64	5/32	16330	8.1	9310	3.2	5710	1.6
3/64	3/16	16330	8.1	9310	3.2	5710	1.6
3/64	1/4	14690	7.3	8380	3.0	5140	1.4
1/16	1/4	13040	8.1	7430	3.2	4560	1.6
5/64	5/16	10670	9.5	6100	3.7	3810	2.2
5/64	3/8	10670	9.5	6100	3.7	3810	2.2
5/64	1/2	9600	7.7	5490	3.2	3430	1.8
5/64	9/16	9600	7.7	5490	3.2	3430	1.8
3/32	3/8	9440	10.6	5420	4.5	3370	2.6
3/32	1/2	8500	9.7	4880	3.9	3030	2.2
1/8	3/8	7000	10.2	4050	4.5	2490	2.4
1/8	1/2	7000	10.2	4050	4.5	2490	2.4
1/8	5/8	7000	10.2	4050	4.5	2490	2.4
1/8	3/4	6300	8.3	3640	3.5	2250	2.0
1/8	1	6300	7.5	3640	3.2	2250	1.8
1/8	1-3/16	6300	7.5	3640	3.2	2250	1.8
3/16	1/2	5040	11.0	2860	4.5	1800	2.4
3/16	5/8	5040	11.0	2860	4.5	1800	2.4
3/16	3/4	5040	11.0	2860	4.5	1800	2.4
3/16	1	4540	10.0	2580	4.1	1620	2.2
3/16	1-3/16	4540	9.1	2580	3.7	1620	2.0
13/64	3/4	4970	16.5	2810	6.5	1840	3.2
13/64	1	4970	16.5	2810	6.5	1840	3.2
13/64	1-3/16	4470	13.4	2530	5.1	1650	2.6
1/4	5/8	4170	19.3	2380	8.1	1550	3.9
1/4	3/4	4170	19.3	2380	8.1	1550	3.9
1/4	1	4170	19.3	2380	8.1	1550	3.9
1/4	1-3/16	4170	16.3	2380	6.9	1550	3.4
1/4	1-3/8	3760	14.8	2140	6.1	1400	3.2
1/4	1-1/2	3760	13.0	2140	5.5	1400	2.8
1/4	1-3/4	3760	13.0	2140	5.5	1400	2.8
5/16	1	3390	21.9	1910	8.7	1270	4.3
5/16	1-3/16	3390	21.9	1910	8.7	1270	4.3
5/16	1-3/8	3390	21.9	1910	8.7	1270	4.3
5/16	1-1/2	3390	18.7	1910	7.3	1270	3.7
5/16	1-3/4	3050	16.7	1720	6.5	1140	3.4
5/16	2	3050	14.8	1720	5.7	1140	3.0
3/8	1-3/16	2960	22.8	1730	8.9	1060	4.5
3/8	1-3/8	2960	22.8	1730	8.9	1060	4.5



DIA. = Diameter
LOC = Length of Cut
RPM = rev./min.
FEED = inch/min.





RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE LONG

GMF27 SERIES

MATERIAL		P					
		NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS	
		~ HRC35 ~ 1100N/mm ²		HRC35 ~ HRC45 1110 ~ 1500N/mm ²		HRC45 ~ HRC55 1500 ~ 2000N/mm ²	
DIA.	LOC	RPM	FEED	RPM	FEED	RPM	FEED
3/8	1-1/2	2960	22.8	1730	8.9	1060	4.5
3/8	1-3/4	2960	19.5	1730	7.7	1060	3.7
3/8	2	2660	17.5	1550	6.9	950	3.4
1/2	1-3/8	2180	16.1	1320	7.1	790	3.2
1/2	1-1/2	2180	16.1	1320	7.1	790	3.2
1/2	1-3/4	2180	16.1	1320	7.1	790	3.2
1/2	2	2180	13.6	1320	6.1	790	2.6
1/2	2-1/8	2180	13.6	1320	6.1	790	2.6
1/2	2-3/8	2180	13.6	1320	6.1	790	2.6
9/16	2	2080	13.4	1210	5.5	740	2.6
5/8	2	1960	15.2	1080	5.9	680	3.0
5/8	2-3/8	1960	13.0	1080	5.1	680	2.4
5/8	2-3/4	1960	13.0	1080	5.1	680	2.4
3/4	2-3/8	1490	9.7	860	3.7	530	2.0
3/4	3-1/2	1490	8.5	860	3.4	530	1.8
1	3-1/2	1090	7.1	800	3.5	500	1.8



DIA. = Diameter
LOC = Length of Cut
RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS


CARBIDE, 4 FLUTE WITH NECK

GMF28 SERIES

MATERIAL		P								
		NON-ALLOYED STEELS ALLOY STEELS CAST IRON			ALLOY STEELS HEAT RESISTANT STEELS			HARDENED STEELS		
		~ HRC35 ~ 1100N/mm ²			HRC35 ~ HRC45 1110 ~ 1500N/mm ²			HRC45 ~ HRC55 1500 ~ 2000N/mm ²		
DIA.	LBS	RPM	FEED	Ae(inch)	RPM	FEED	Ae(inch)	RPM	FEED	Ae(inch)
3/64	5/32	19650	12.4	.0007	12200	7.3	.0005	7560	2.0	.0004
3/64	3/16	19650	12.4	.0007	12200	7.3	.0005	7560	2.0	.0004
3/64	1/4	17690	10.0	.0004	10980	5.9	.0003	6800	1.6	.0002
3/64	5/16	17690	10.0	.0004	10980	5.9	.0003	6800	1.6	.0002
1/16	1/4	16060	11.8	.0009	10110	7.1	.0007	6140	1.8	.0006
1/16	5/16	16060	11.8	.0009	10110	7.1	.0007	6140	1.8	.0006
1/16	3/8	14460	9.7	.0005	9100	5.7	.0004	5530	1.6	.0003
1/16	1/2	14460	9.7	.0005	9100	5.7	.0004	5530	1.6	.0003
1/16	5/8	14460	9.7	.0003	9100	5.7	.0002	5530	1.6	.0002
5/64	5/16	14010	13.2	.0011	9140	7.9	.0009	6050	2.4	.0007
5/64	3/8	14010	13.2	.0011	9140	7.9	.0009	6050	2.4	.0007
5/64	1/2	12610	10.6	.0007	8230	6.5	.0005	5440	2.0	.0004
5/64	5/8	12610	10.6	.0007	8230	6.5	.0005	5440	2.0	.0004
1/8	3/8	10110	14.2	.0026	6300	8.9	.0020	3810	2.6	.0016
1/8	1/2	10110	14.2	.0019	6300	8.9	.0014	3810	2.6	.0011
1/8	5/8	10110	14.2	.0019	6300	8.9	.0014	3810	2.6	.0011
1/8	3/4	9100	11.4	.0011	5670	7.3	.0008	3430	2.2	.0006
1/8	1-3/16	9100	11.4	.0007	5670	7.3	.0005	3430	2.2	.0004
3/16	1/2	7620	22.4	.0039	4650	14.0	.0030	2960	2.4	.0024
3/16	5/8	7620	22.4	.0028	4650	14.0	.0021	2960	2.4	.0017
3/16	3/4	7620	22.4	.0028	4650	14.0	.0021	2960	2.4	.0017
3/16	1-3/16	6860	18.3	.0016	4190	11.2	.0012	2670	2.0	.0009
3/16	1-1/2	6860	18.3	.0016	4190	11.2	.0012	2670	2.0	.0009
13/64	3/4	7330	27.6	.0030	4390	16.3	.0022	2690	3.2	.0018
13/64	1-1/2	6590	22.2	.0017	3950	13.4	.0013	2420	2.6	.0010
1/4	5/8	6300	29.3	.0052	3810	18.3	.0039	2270	3.5	.0031
1/4	1-3/16	6300	29.3	.0037	3810	18.3	.0028	2270	3.5	.0022
5/16	1	5080	33.7	.0046	3040	17.9	.0035	2030	5.1	.0028
5/16	1-5/8	4570	27.4	.0026	2740	14.4	.0020	1820	4.1	.0016
3/8	1-3/16	4100	30.1	.0055	2520	15.0	.0041	1710	4.3	.0033
3/8	1-3/4	4100	30.1	.0055	2520	15.0	.0041	1710	4.3	.0033
1/2	1-3/8	3120	23.0	.0105	1900	11.2	.0079	1320	3.5	.0063
1/2	2	3120	23.0	.0074	1900	11.2	.0055	1320	3.5	.0044



DIA. = Diameter
LBS = Length Below Shank
RPM = rev./min.
FEED = inch/min.



RECOMMENDED CUTTING CONDITIONS


CARBIDE, 6 FLUTE 45° HELIX

GMF29 SERIES

- NORMAL SPEED

MATERIAL		P					
		NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS	
HARDNESS		~ HRC35		HRC35 ~ HRC45		HRC45 ~ HRC55	
STRENGTH		~ 1100N/mm ²		1110 ~ 1500N/mm ²		1500 ~ 2000N/mm ²	
DIA.	LOC	RPM	FEED	RPM	FEED	RPM	FEED
1/4	5/8	5775	81.9	4035	56.1	1640	8.7
1/4	1-3/16	5775	69.5	4035	47.6	1640	7.4
5/16	3/4	4440	83.3	3110	57.1	1230	8.7
5/16	1-1/2	4440	70.9	3110	48.6	1230	7.4
3/8	1	3705	86.8	2560	59.5	1105	9.1
3/8	1-1/2	3705	86.8	2560	59.5	1105	9.1
1/2	1-3/16	2950	68.6	2080	47.4	870	7.4
1/2	2	2950	58.5	2080	40.3	870	6.3
5/8	1-1/2	2225	52.5	1565	36.6	685	5.4
5/8	2-3/8	2225	44.7	1565	31.2	685	4.6
3/4	1-3/4	1850	43.8	1280	30.0	545	4.8
3/4	2-3/8	1850	37.2	1280	25.4	545	4.1


DIA. = Diameter
LOC = Length of Cut
RPM = rev./min.
FEED = inch/min.



- HIGH SPEED

MATERIAL		P			
		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS	
HARDNESS		HRC35 ~ HRC45		HRC45 ~ HRC55	
STRENGTH		1110 ~ 1500N/mm ²		1500 ~ 2000N/mm ²	
DIA.	LOC	RPM	FEED	RPM	FEED
1/4	5/8	17455	249.2	8735	124.7
1/4	1-3/16	17455	211.8	8735	106.1
5/16	3/4	13335	253.8	6670	127.1
5/16	1-1/2	13335	215.6	6670	108.1
3/8	1	11005	260.0	5555	132.3
3/8	1-1/2	11005	260.0	5555	132.3
1/2	1-3/16	8735	206.1	4365	103.1
1/2	2	8735	175.4	4365	87.7
5/8	1-1/2	6670	157.5	3340	78.8
5/8	2-3/8	6670	133.9	3340	67.0
3/4	1-3/4	5555	132.3	2785	63.9
3/4	2-3/8	5555	112.4	2785	54.2

RPM = rev./min.
FEED = inch/min.





X-SPEED ROUGHER
RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4&5 FLUTE MULTIPLE HELIX CORNER RADIUS - SLOTTING

G907, G928, G908, G929, G909, G930 SERIES

MATERIAL		P			
		ALLOY STEELS, CARBON STEELS TOOL STEELS CAST IRON		ALLOY STEELS, CARBON STEELS TOOL STEELS, CAST IRON PREHARDENED STEELS	
HARDNESS		~ HRC25		HRC25 ~ HRC40	
DIAMETER		RPM	FEED	RPM	FEED
INCH	METRIC				
1/4	6.0	12000	61.0	10600	43.3
5/16	8.0	9000	65.0	8100	46.5
3/8	10.0	7200	65.0	6400	46.5
1/2	12.0	6000	60.6	5400	44.9
5/8	16.0	4500	59.1	4100	41.3
3/4	20.0	3600	52.4	3200	35.4
1	-	2900	46.4	2600	32.5





RPM = rev./min.
FEED = inch/min.

CARBIDE, 4&5 FLUTE MULTIPLE HELIX CORNER RADIUS - SIDE CUTTING

G907, G928, G908, G929, G909, G930 SERIES

MATERIAL		P			
		ALLOY STEELS, CARBON STEELS TOOL STEELS CAST IRON		ALLOY STEELS, CARBON STEELS TOOL STEELS, CAST IRON PREHARDENED STEELS	
HARDNESS		~ HRC25		HRC25 ~ HRC40	
DIAMETER		RPM	FEED	RPM	FEED
INCH	METRIC				
1/4	6.0	15800	101.2	14300	72.8
5/16	8.0	11900	106.3	10700	76.8
3/8	10.0	9500	106.3	8500	76.8
1/2	12.0	8000	101.2	7100	72.8
5/8	16.0	6000	96.5	5400	69.9
3/4	20.0	4800	84.3	4300	59.1
1	-	3800	75.3	3400	49.3



RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS


CARBIDE, 2 FLUTE BALL NOSE

SEMD98 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Rows include hardness, strength, and cutting parameters (RPM, FEED, Vc, Fz) for diameters from 0.1 to 25.0.



RPM = rev./min. FEED = mm/min. Vc = m/min. fz = mm/t



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG NECK BALL NOSE

SEM846 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Rows include hardness, strength, and cutting parameters (DIA., LBS, RPM, FEED, Vc, fz, Ap(mm)) for diameters from 0.1 to 16.

DIA. = Diameter LBS = Length Below Shank RPM = rev./min. FEED = mm/min. Vc = m/min. fz = mm/tooth



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG NECK BALL NOSE

SEM846 SERIES

Table with columns for MATERIAL, HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Vc, fz, Ap(mm) and sub-columns for NON-ALLOYED STEELS, ALLOY STEELS, and HARDENED STEELS.

DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG NECK BALL NOSE

SEM846 SERIES

Table with columns for MATERIAL, HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Vc, fz, Ap(mm) and sub-columns for NON-ALLOYED STEELS, ALLOY STEELS, and HARDENED STEELS.

DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG NECK BALL NOSE

SEM846 SERIES

Table with columns: MATERIAL, HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Vc, fz, Ap(mm) for NON-ALLOYED STEELS, ALLOY STEELS, and HARDENED STEELS.

DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG NECK BALL NOSE

SEM846 SERIES

Table with columns: MATERIAL, HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Vc, fz, Ap(mm) for NON-ALLOYED STEELS, ALLOY STEELS, and HARDENED STEELS.



DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE CORNER RADIUS

SEMD99 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Rows include hardness, strength, and diameter with corresponding RPM, FEED, Vc, fz values.



RPM = rev./min. FEED = mm/min. Vc = m/min. fz = mm/tooth



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

SEME61 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Rows include hardness, strength, and diameter with corresponding RPM, FEED, Vc, fz, Ap values.

DIA. = Diameter LBS = Length Below Shank RPM = rev./min. FEED = mm/min. Vc = m/min. fz = mm/tooth




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

SEME61 SERIES

Table with columns: MATERIAL, HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Vc, fz, Ap(mm) for NON-ALLOYED STEELS, ALLOY STEELS, and HARDENED STEELS.

DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG NECK CORNER RADIUS

SEME61 SERIES

Table with columns: MATERIAL, HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Vc, fz, Ap(mm) for NON-ALLOYED STEELS, ALLOY STEELS, and HARDENED STEELS.



DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth




RECOMMENDED CUTTING CONDITIONS


CARBIDE, 4 FLUTE CORNER RADIUS

SEME01 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Rows include hardness, strength, and cutting parameters (RPM, FEED, Vc, fz) for diameters 1.0 to 20.0.



* 1.5XD Axial cutting depth should be for diameter over 16mm



RPM = rev./min. FEED = mm/min. Vc = m/min. fz = mm/tooth



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE LONG NECK CORNER RADIUS

SEME64 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Rows include hardness, strength, and cutting parameters (DIA, LBS, RPM, FEED, Vc, fz, Ae) for diameters 1.0 to 2.5.

DIA = Diameter LBS = Length Below Shank RPM = rev./min. FEED = mm/min. Vc = m/min. fz = mm/tooth




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE LONG NECK CORNER RADIUS

SEME64 SERIES

Table with columns: MATERIAL, HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Vc, fz, Ae(mm) for NON-ALLOYED STEELS, ALLOY STEELS, and HARDENED STEELS.



DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth





RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE

SEME35 SERIES

Table with columns: MATERIAL, HARDNESS, STRENGTH, DIA., RPM, FEED, Vc, fz for NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS, and STAINLESS STEELS.



RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG LENGTH

SEME70 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Sub-columns include HARDNESS, STRENGTH, DIA., LOC, RPM, FEED, Vc, fz. Rows list various material types and their recommended cutting parameters.

DIA. = Diameter, LOC = Length of Cut, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG LENGTH

SEME70 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Sub-columns include HARDNESS, STRENGTH, DIA., LOC, RPM, FEED, Vc, fz. Rows list various material types and their recommended cutting parameters.

DIA. = Diameter, LOC = Length of Cut, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth





RECOMMENDED CUTTING CONDITIONS


CARBIDE, 2 FLUTE LONG LENGTH

SEME70 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Sub-columns include HARDNESS, STRENGTH, DIA., LOC, RPM, FEED, Vc, fz.



DIA. = Diameter, LOC = Length of Cut, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG NECK

SEM845 SERIES

Table with columns: MATERIAL, NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS. Sub-columns include HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Vc, fz, Ap(mm).

DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG NECK

SEM845 SERIES

Table with columns for MATERIAL, HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Vc, fz, Ap(mm) under categories NON-ALLOYED STEELS, ALLOY STEELS, and HARDENED STEELS.

DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG NECK

SEM845 SERIES

Table with columns for MATERIAL, HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Vc, fz, Ap(mm) under categories NON-ALLOYED STEELS, ALLOY STEELS, and HARDENED STEELS.

DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG NECK

SEM845 SERIES

Table with columns: MATERIAL, HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Vc, fz, Ap(mm) for NON-ALLOYED STEELS, ALLOY STEELS, and HARDENED STEELS.

DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG NECK

SEM845 SERIES

Table with columns: MATERIAL, HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Vc, fz, Ap(mm) for NON-ALLOYED STEELS, ALLOY STEELS, and HARDENED STEELS.

DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth






RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE

SEME36, SEME71 SERIES

Table with columns for MATERIAL, HARDNESS, STRENGTH, and cutting parameters (RPM, FEED, Vc, fz) for various materials and hardness levels.



RPM = rev./min. FEED = mm/min. Vc = m/min. fz = mm/tooth



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE LONG LENGTH

SEME72 SERIES

Table with columns for MATERIAL, HARDNESS, STRENGTH, and cutting parameters (RPM, FEED, Vc, fz) for various materials and hardness levels.

DIA. = Diameter LOC = Length of Cut RPM = rev./min. FEED = mm/min. Vc = m/min. fz = mm/tooth





RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE LONG LENGTH

SEME72 SERIES

Table with columns: MATERIAL, P (NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS), HARDNESS, STRENGTH, DIA., LOC, RPM, FEED, Vc, fz. Contains detailed cutting parameters for various materials and diameters.



DIA. = Diameter, LOC = Length of Cut, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE LONG NECK

SEME73 SERIES

Table with columns: MATERIAL, P (NON-ALLOYED STEELS, ALLOY STEELS, HARDENED STEELS), HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Vc, fz, Ap(mm). Contains detailed cutting parameters for various materials and diameters.

DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE LONG NECK

SEME73 SERIES

Table with columns: MATERIAL, HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Vc, fz, ae(mm) for NON-ALLOYED STEELS, ALLOY STEELS, and HARDENED STEELS.

DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE LONG NECK

SEME73 SERIES

Table with columns: MATERIAL, HARDNESS, STRENGTH, DIA., LBS, RPM, FEED, Vc, fz, ae(mm) for NON-ALLOYED STEELS, ALLOY STEELS, and HARDENED STEELS.



DIA. = Diameter, LBS = Length Below Shank, RPM = rev./min., FEED = mm/min., Vc = m/min., fz = mm/tooth






RECOMMENDED CUTTING CONDITIONS

CARBIDE, 6 FLUTE 45° HELIX

SEME75 SERIES

■ NORMAL SPEED

MATERIAL	P												
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON				ALLOY STEELS HEAT RESISTANT STEELS				HARDENED STEELS				
	~ HRC35 ~ 1100N/mm ²				HRC35 ~ HRC45 1110 ~ 1500N/mm ²				HRC45 ~ HRC55 1500 ~ 2000N/mm ²				
DIA.	LOC	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz
6.0	15	5840	2100	110	0.060	4075	1440	77	0.059	1660	220	31	0.022
6.0	20	5840	2100	110	0.060	4075	1440	77	0.059	1660	220	31	0.022
6.0	30	5840	1785	110	0.051	4075	1225	77	0.050	1660	190	31	0.019
8.0	20	4410	2100	111	0.079	3085	1440	78	0.078	1220	220	31	0.030
8.0	30	4410	2100	111	0.079	3085	1440	78	0.078	1220	220	31	0.030
8.0	35	4410	2100	111	0.079	3085	1440	78	0.078	1220	220	31	0.030
8.0	40	4410	1785	111	0.067	3085	1225	78	0.066	1220	190	31	0.026
10.0	25	3530	2100	111	0.099	2435	1440	76	0.099	1050	220	33	0.035
10.0	30	3530	2100	111	0.099	2435	1440	76	0.099	1050	220	33	0.035
10.0	40	3530	2100	111	0.099	2435	1440	76	0.099	1050	220	33	0.035
10.0	50	3530	1785	111	0.084	2435	1225	76	0.084	1050	190	33	0.030
12.0	30	2980	1765	112	0.099	2100	1220	79	0.097	880	190	33	0.036
12.0	40	2980	1765	112	0.099	2100	1220	79	0.097	880	190	33	0.036
12.0	50	2980	1500	112	0.084	2100	1035	79	0.082	880	165	33	0.031
12.0	60	2980	1325	112	0.074	2100	915	79	0.073	880	140	33	0.027
16.0	40	2205	1325	111	0.100	1555	925	78	0.099	670	135	34	0.034
16.0	50	2205	1325	111	0.100	1555	925	78	0.099	670	135	34	0.034
16.0	60	2205	1125	111	0.085	1555	790	78	0.085	670	115	34	0.029
16.0	90	1985	895	100	0.075	1395	625	70	0.075	610	95	31	0.026
16.0	110	1985	895	100	0.075	1395	625	70	0.075	610	95	31	0.026
20.0	45	1765	1060	111	0.100	1220	725	77	0.099	525	115	33	0.037
20.0	60	1765	1060	111	0.100	1220	725	77	0.099	525	115	33	0.037
20.0	70	1765	905	111	0.085	1220	615	77	0.084	525	100	33	0.032
20.0	110	1585	715	100	0.075	1090	490	68	0.075	475	80	30	0.028



DIA. = Diameter
LOC = Length of Cut
RPM = rev./min.
FEED = mm/min.
Vc = m/min.
fz = mm/tooth





RECOMMENDED CUTTING CONDITIONS

CARBIDE, 6 FLUTE 45° HELIX


SEME75 SERIES

■ HIGH SPEED

MATERIAL	P												
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON				ALLOY STEELS HEAT RESISTANT STEELS				HARDENED STEELS				
	~ HRC35 ~ HRC45 1100 ~ 1500N/mm ²				HRC45 ~ HRC55 1500 ~ 2000N/mm ²				HRC45 ~ HRC55 1500 ~ 2000N/mm ²				
DIA.	LOC	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz
6.0	15	17640	6395	333	0.060	8820	3205	166	0.061	8820	3205	166	0.061
6.0	20	17640	6395	333	0.060	8820	3205	166	0.061	8820	3205	166	0.061
6.0	30	17640	5435	333	0.051	8820	2720	166	0.051	8820	2720	166	0.051
8.0	20	13230	6395	333	0.081	6615	3205	166	0.081	6615	3205	166	0.081
8.0	30	13230	6395	333	0.081	6615	3205	166	0.081	6615	3205	166	0.081
8.0	35	13230	6395	333	0.081	6615	3205	166	0.081	6615	3205	166	0.081
8.0	40	13230	5435	333	0.068	6615	2725	166	0.069	6615	2725	166	0.069
10.0	25	10480	6290	329	0.100	5290	3205	166	0.101	5290	3205	166	0.101
10.0	30	10480	6290	329	0.100	5290	3205	166	0.101	5290	3205	166	0.101
10.0	40	10480	6290	329	0.100	5290	3205	166	0.101	5290	3205	166	0.101
10.0	50	10480	5345	329	0.085	5290	2720	166	0.086	5290	2720	166	0.086
12.0	30	8820	5290	333	0.100	4410	2645	166	0.100	4410	2645	166	0.100
12.0	40	8820	5290	333	0.100	4410	2645	166	0.100	4410	2645	166	0.100
12.0	50	8820	4500	333	0.085	4410	2245	166	0.085	4410	2245	166	0.085
12.0	60	8820	3970	333	0.075	4410	1985	166	0.075	4410	1985	166	0.075
16.0	40	6615	3970	333	0.100	3320	1985	167	0.100	3320	1985	167	0.100
16.0	50	6615	3970	333	0.100	3320	1985	167	0.100	3320	1985	167	0.100
16.0	60	6615	3375	333	0.085	3320	1685	167	0.085	3320	1685	167	0.085
16.0	90	5955	2680	299	0.075	2980	1340	150	0.075	2980	1340	150	0.075
16.0	110	5955	2680	299	0.075	2980	1340	150	0.075	2980	1340	150	0.075
20.0	45	5290	3205	332	0.101	2645	1545	166	0.097	2645	1545	166	0.097
20.0	60	5290	3205	332	0.101	2645	1545	166	0.097	2645	1545	166	0.097
20.0	70	5290	2720	332	0.086	2645	1315	166	0.083	2645	1315	166	0.083
20.0	110	4765	2165	299	0.076	2385	1040	150	0.073	2385	1040	150	0.073



DIA. = Diameter
LOC = Length of Cut
RPM = rev./min.
FEED = mm/min.
Vc = m/min.
fz = mm/tooth





RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4&5 FLUTE MULTIPLE HELIX CORNER RADIUS - SLOTTING

G9D75, G9D67, G9D76, G9D68, G9D77, G9D69 SERIES

MATERIAL	P							
	ALLOYED STEELS CARBON STEELS TOOL STEELS, CAST IRON ~ HRc 25				ALLOYED STEELS, CARBON STEELS TOOL STEELS, CAST IRON PREHARDENED STEELS HRc 25 ~ HRc 40			
HARDNESS								
DIAMETER	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz
6.0	12000	1550	225	0.032	10600	1100	200	0.026
8.0	9000	1650	225	0.046	8100	1180	205	0.036
10.0	7200	1650	225	0.057	6400	1180	200	0.046
12.0	6000	1540	225	0.064	5400	1140	205	0.053
16.0	4500	1500	225	0.067	4100	1050	205	0.051
20.0	3600	1330	225	0.074	3200	900	200	0.056





RPM = rev./min.
FEED = mm/min.
Vc = m/min.
fz = mm/tooth

CARBIDE, 4&5 FLUTE MULTIPLE HELIX CORNER RADIUS - SIDE CUTTING

G9D75, G9D67, G9D76, G9D68, G9D77, G9D69 SERIES

MATERIAL	P							
	ALLOYED STEELS CARBON STEELS TOOL STEELS, CAST IRON ~ HRc 25				ALLOYED STEELS, CARBON STEELS TOOL STEELS, CAST IRON PREHARDENED STEELS HRc 25 ~ HRc 40			
HARDNESS								
DIAMETER	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz
6.0	15800	2570	300	0.041	14300	1850	270	0.032
8.0	11900	2700	300	0.057	10700	1950	270	0.046
10.0	9500	2700	300	0.071	8500	1950	265	0.057
12.0	8000	2570	300	0.080	7100	1850	270	0.065
16.0	6000	2450	300	0.082	5400	1750	270	0.065
20.0	4800	2140	300	0.089	4300	1500	270	0.070



RPM = rev./min.
FEED = mm/min.
Vc = m/min.
fz = mm/tooth




RECOMMENDED CUTTING CONDITIONS

HSS-PM, 4&5 FLUTE MULTIPLE HELIX SHORT LENGTH CORNER RADIUS

GAE53 SERIES

MATERIAL	P											
	STRUCTURAL STEELS CARBON STEELS ~ 500N/mm ²				STRUCTURAL STEELS CARBON STEELS, CAST IRONS ~ HRc 20 500 ~ 800N/mm ²				CARBON STEELS ALLOY STEELS, TOOL STEELS HRc 20 ~ 30 800 ~ 1000N/mm ²			
HARDNESS												
STRENGTH												
DIAMETER	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz
6.0	3250	240	60	0.019	2500	185	48	0.018	1800	120	34	0.017
8.0	2750	300	70	0.027	2150	240	54	0.028	1550	170	38	0.027
10.0	2150	430	70	0.050	1700	330	54	0.049	1200	205	38	0.043
12.0	1800	430	70	0.060	1400	350	54	0.063	1000	240	38	0.059
14.0	1550	430	70	0.055	1200	350	54	0.073	850	240	38	0.069
16.0	1400	430	70	0.063	1100	350	54	0.081	750	240	38	0.080
18.0	1200	430	70	0.072	1000	350	54	0.085	700	240	38	0.086
20.0	1100	445	70	0.080	850	350	54	0.101	600	240	38	0.100

MATERIAL	P				M			
	PREHARDENED STEELS ALLOY STEELS, TOOL STEELS HRc 30 ~ 40 1000 ~ 1300N/mm ²				STAINLESS STEELS			
HARDNESS								
STRENGTH								
DIAMETER	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz
6.0	1500	110	28	0.018	1750	130	33	0.019
8.0	1200	130	32	0.028	1450	170	36	0.029
10.0	1000	170	32	0.041	1150	200	36	0.045
12.0	850	190	32	0.055	950	245	36	0.064
14.0	700	190	32	0.065	850	245	36	0.074
16.0	600	190	32	0.075	700	245	36	0.085
18.0	550	190	32	0.082	650	245	36	0.093
20.0	500	190	32	0.092	600	245	36	0.107



RPM = rev./min.
FEED = mm/min.
Vc = m/min.
fz = mm/tooth



Being the best through innovation

CARBIDE




X-POWER END MILLS

- Medium Steels to High Hardened Steels up to HRc70



Global Cutting Tool Leader **YG-1**



SELECTION GUIDE

SOLID CARBIDE X-POWER END MILLS

◎ : Excellent ○ : Good

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	

INCH

EM154		CARBIDE, 2 FLUTE REGULAR LENGTH	◆	D1/16	D1	856
EM206		CARBIDE, 2 FLUTE LONG LENGTH	◆	D1/8	D1	856
EM959		CARBIDE, 2 FLUTE MINIATURE	◆	D.016	D.062	857
EM153		CARBIDE, 4 FLUTE REGULAR LENGTH	◆	D1/16	D1	858
EM207		CARBIDE, 4 FLUTE LONG LENGTH	◆	D1/8	D1	858
EM636		CARBIDE, 2 FLUTE STUB LENGTH CORNER RADIUS	◆	D1/16	D1/2	859
EM639		CARBIDE, 4 FLUTE STUB LENGTH CORNER RADIUS	◆	D1/16	D1/2	859
EM637		CARBIDE, 2 FLUTE REGULAR LENGTH CORNER RADIUS	◆	D1/16	D1/2	860
EM649		CARBIDE, 4 FLUTE REGULAR LENGTH CORNER RADIUS	◆	D1/16	D1/2	860
EM211		CARBIDE, 2 FLUTE LONG LENGTH CORNER RADIUS	◆	D1/4	D1/2	861
EM212		CARBIDE, 4 FLUTE LONG LENGTH CORNER RADIUS	◆	D1/4	D1/2	861
EM102		CARBIDE, 4 FLUTE 45° HELIX LONG LENGTH	◆	D3/8	D7/8	862
EM103		CARBIDE, 4 FLUTE 45° HELIX LONG REACH CORNER RADIUS	◆	D3/8	D7/8	863
EM965		CARBIDE, 4 FLUTE 55° HELIX STUB LENGTH CORNER RADIUS	◆	D1/4	D1/2	864
EM208		CARBIDE, 6&8 FLUTE 45° HELIX LONG LENGTH	◆	D1/4	D1	865
EM218		CARBIDE, 6&8 FLUTE 45° HELIX EXTRA LONG LENGTH	◆	D1/4	D1	865
EM668		CARBIDE, 6&8 FLUTE 45° HELIX LONG LENGTH CORNER RADIUS	◆	D1/4	D3/4	866

◆ U.S.A Stock

















P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									

○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○			○							
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○			○							
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○			○							
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○			○							
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○			○							
○	◎	◎	◎	○		○	○							
○	◎	◎	◎	○			○							
○	◎	◎	◎	○		○	○							

SELECTION GUIDE

SOLID CARBIDE X-POWER END MILLS

◎ : Excellent ○ : Good

ITEM	MODEL	DESCRIPTION	◆	SIZE		PAGE
				MIN	MAX	
INCH						
EM209		CARBIDE, 2 FLUTE LONG LENGTH BALL NOSE	◆	R1/64	R1/2	867
EM210		CARBIDE, 4 FLUTE LONG LENGTH BALL NOSE	◆	R1/16	R1/2	867
EM961		CARBIDE, 2 FLUTE MEDIUM LENGTH BALL NOSE	◆	R1/16	R1/2	868
EM962		CARBIDE, 2 FLUTE LONG REACH BALL NOSE	◆	R3/64	R3/8	869
EM960		CARBIDE, 2 FLUTE MINIATURE BALL NOSE	◆	R.012	R.031	870
EM109		CARBIDE, 2 FLUTE 15° HELIX STUB CUT LENGTH BALL NOSE for OVER HRc55	◆	R1/64	R1/4	871
EM963		CARBIDE, 2 FLUTE BALL NOSE with TAPER NECK	◆	R1/32	R1/4	872
EM979		CARBIDE, 2 FLUTE BALL NOSE with PENCIL NECK	◆	R3/32	R1/4	873
EM084		CARBIDE, 2 FLUTE LONG LENGTH BALL NOSE (MMC-ECONOMY TYPE)	◆	R1/16	R5/16	875
EM093		CARBIDE, 4 FLUTE LONG LENGTH BALL NOSE (MMC-ECONOMY TYPE)	◆	R1/16	R5/16	876
EM096		CARBIDE, 2 FLUTE LONG LENGTH BALL NOSE (MMC-SPHERE TYPE)	◆	R1/16	R5/16	877
EM097		CARBIDE, 4 FLUTE LONG LENGTH BALL NOSE (MMC-SPHERE TYPE)	◆	R1/16	R5/16	878
EM666		CARBIDE, MULTI FLUTE 20° HELIX STUB LENGTH FINE PITCH ROUGHING	◆	D1/4	D1	879
EM156		CARBIDE, MULTI FLUTE 20° HELIX LONG LENGTH FINE PITCH ROUGHING	◆	D1/4	D1	879
EM662		CARBIDE, MULTI FLUTE 20° HELIX LONG LENGTH FINE PITCH ROUGHING BALL NOSE	◆	R1/8	R1/2	880
EM966		CARBIDE, 2 FLUTE for RIB PROCESSING	◆	D1/32	D1/8	881
EM967		CARBIDE, 2 FLUTE BALL NOSE for RIB PROCESSING	◆	R1/64	R1/16	882
















◆ U.S.A Stock

P					H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○	○		○							
			○	◎	◎									
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○	○		○							

SELECTION GUIDE

SOLID CARBIDE X-POWER END MILLS

◎ : Excellent ○ : Good

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
METRIC					
EM899		CARBIDE, 2 FLUTE MEDIUM LENGTH BALL NOSE	◇	R1.5 R12.5	897
EM838		CARBIDE, 2 FLUTE LONG REACH BALL NOSE	◇	R1.0 R10.0	898
EM865		CARBIDE, 2 FLUTE MINIATURE BALL NOSE	◇	R0.3 R0.75	899
EM868		CARBIDE, 2 FLUTE 15° HELIX STUB CUT LENGTH BALL NOSE for OVER HRc55	◇	R0.5 R12.5	900
EM902		CARBIDE, 2 FLUTE BALL NOSE with TAPER NECK	◇	R0.5 R6.0	901
EM669		CARBIDE, 2 FLUTE LONG LENGTH BALL NOSE (MMC-ECONOMY TYPE)	◇	R1.5 R8.0	902
EM673		CARBIDE, 4 FLUTE LONG LENGTH BALL NOSE (MMC-ECONOMY TYPE)	◇	R2.5 R8.0	903
EM863		CARBIDE, 2 FLUTE LONG LENGTH BALL NOSE (MMC- SPHERE TYPE)	◇	R1.5 R8.0	904
EM864		CARBIDE, 4 FLUTE LONG LENGTH BALL NOSE (MMC- SPHERE TYPE)	◇	R2.5 R8.0	905
EM832		CARBIDE, MULTI FLUTE 20° HELIX SHORT LENGTH FINE PITCH ROUGHING	◇	D6.0 D25.0	906
EM814		CARBIDE, MULTI FLUTE 20° HELIX LONG LENGTH FINE PITCH ROUGHING	◇	D6.0 D25.0	907
EM833		CARBIDE, 3&4 FLUTE 20° HELIX LONG LENGTH FINE PITCH ROUGHING BALL NOSE	◇	R3.0 R10.0	908
EM837		CARBIDE, 2 FLUTE TAPER	◇	D2.0 D8.0	909
EM883		CARBIDE, 2 FLUTE for RIB PROCESSING	◇	D0.8 D3.0	910
EM886		CARBIDE, 2 FLUTE BALL NOSE for RIB PROCESSING	◇	R0.3 R2.0	911
RECOMMENDED CUTTING CONDITIONS					912

◇ Call for Availability

Carbon Steels	Alloy Steels	P			H High Hardened Steels HRc55~70	M Stainless Steels	K Cast Iron	N				S		
		Prehardened Steels	Hardened Steels	HRc40~45				HRc45~55	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○			○							
			○	◎	◎									
○	○	◎	◎	○										
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○	○		○							
○	◎	◎	◎	○			○							
○	◎	◎	◎	○			○							
○	◎	◎	◎	○			○							
○	◎	◎	◎	○			○							
○	◎	◎	◎	○			○							



EM154 SERIES PLAIN SHANK
EM206 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE REGULAR & LONG LENGTH

- ▶ Designed to machine tool steel, alloy steel, mold steel and other high hardened materials.
- ▶ Superior workpiece finishes.
- ▶ Increased feed rate.



MG 2 30° PLAIN P.912 ◆ U.S.A Stock

EM154 Series ■ REGULAR LENGTH Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
93074	1/16	1/8	3/16	1-1/2
93075	1/8	1/8	1/2	1-1/2
93076	3/16	3/16	5/8	2
93077	1/4	1/4	3/4	2-1/2
93078	5/16	5/16	13/16	2-1/2
93079	3/8	3/8	1	2-1/2
93080	1/2	1/2	1	3
93081	5/8	5/8	1-1/4	3-1/2
93082	3/4	3/4	1-1/2	4
93083	1	1	1-1/2	4

EM206 Series ■ LONG LENGTH Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
93084	1/8	1/8	3/4	2-1/4
93085	3/16	3/16	3/4	2-1/2
93086	1/4	1/4	1-1/8	3
93087	5/16	5/16	1-1/8	3
93088	3/8	3/8	1-1/8	3
93089	1/2	1/2	2	4
93090	5/8	5/8	2-1/4	5
93091	3/4	3/4	2-1/4	5
93092	1	1	2-1/4	5

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.0012	0~-0.0003

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○		○	○							



EM959 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE MINIATURE

- ▶ High precision milling in medical, optical, electronics and aero space industries.
- ▶ Excellent performance on high hardened steel(HRc70).



MG 2 30° PLAIN P.914 ◆ U.S.A Stock

Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
93495	.016	1/8	.031	1-1/2
93496	.020	1/8	.040	1-1/2
93497	.024	1/8	.047	1-1/2
93498	.028	1/8	.055	1-1/2
93499	.031	1/8	.063	1-1/2
93500	.035	1/8	.080	1-1/2
93501	.040	1/8	.100	1-1/2
93502	.043	1/8	.100	1-1/2
93503	.047	1/8	.157	1-1/2
93504	.052	1/8	.157	1-1/2
93505	.055	1/8	.157	1-1/2
93506	.062	1/8	.157	1-1/2

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
±.0005	0~-0.0003

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○							



EM153 SERIES PLAIN SHANK
EM207 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE REGULAR & LONG LENGTH

- ▶ Designed to machine tool steel, alloy steel, mold steel and other high hardened materials.
- ▶ 4 flute allows for better workpiece finishes.
- ▶ Increased production.



◆ U.S.A Stock

EM153 Series ■ REGULAR LENGTH Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
93093	1/16	1/8	3/16	1-1/2
93094	1/8	1/8	1/2	1-1/2
93095	3/16	3/16	5/8	2
93096	1/4	1/4	3/4	2-1/2
93097	5/16	5/16	13/16	2-1/2
93098	3/8	3/8	1	2-1/2
93594	7/16	7/16	1	2-3/4
93099	1/2	1/2	1	3
93100	5/8	5/8	1-1/4	3-1/2
93101	3/4	3/4	1-1/2	4
93102	1	1	1-1/2	4

EM207 Series ■ LONG LENGTH Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
93103	1/8	1/8	3/4	2-1/4
93104	3/16	3/16	3/4	2-1/2
93105	1/4	1/4	1-1/8	3
93106	5/16	5/16	1-1/8	3
93107	3/8	3/8	1-1/8	3
93108	1/2	1/2	2	4
93109	5/8	5/8	2-1/4	5
93110	3/4	3/4	2-1/4	5
93111	1	1	2-1/4	5

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.012	0~-0.003

◎ : Excellent ○ : Good


Series	P					H	M	K	N					S	
	Carbon Steels ~HRc20	Alloy Steels HRc20~30	Prehardened Steels HRc30~40	Hardened Steels HRc40~45 HRc45~55	High Hardened Steels HRc55~70	High Hardened Steels HRc55~70	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
EM153	○	◎	◎	◎	○		○	○							
EM207	○	◎	◎	◎	○		○	○							



EM636 SERIES PLAIN SHANK
EM639 SERIES PLAIN SHANK

CARBIDE, 2&4 FLUTE STUB LENGTH CORNER RADIUS

- ▶ Designed to machine tool steel, alloy steel, mold steel and other high hardened materials.
- ▶ Superior workpiece finishes.
- ▶ Increased feed rate.



◆ U.S.A Stock

EM636(2 FLUTE), EM639(4 FLUTE) Series Unit : Inch

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
2 FLUTE	4 FLUTE	R (±.001)				
93172	93216	R.008	1/16	1/4	1/8	2-1/4
93173	93217	R.010	1/8	1/4	1/4	2-1/4
93174	93218	R.020	1/8	1/4	1/4	2-1/4
93175	-	R.030	1/8	1/4	1/4	2-1/4
93176	93220	R.010	3/16	1/4	3/8	2-1/2
93177	93221	R.020	3/16	1/4	3/8	2-1/2
93178	93222	R.030	3/16	1/4	3/8	2-1/2
93179	93223	R.010	1/4	1/4	1/2	3
93180	93224	R.020	1/4	1/4	1/2	3
93181	93225	R.030	1/4	1/4	1/2	3
93182	93226	R.020	5/16	5/16	1/2	3
93183	93227	R.030	5/16	5/16	1/2	3
93184	93228	R.060	5/16	5/16	1/2	3
93185	93229	R.090	5/16	5/16	1/2	3
93186	93230	R.020	3/8	3/8	5/8	3
93187	93231	R.030	3/8	3/8	5/8	3
93188	93232	R.060	3/8	3/8	5/8	3
93189	93233	R.090	3/8	3/8	5/8	3
93190	93234	R.020	1/2	1/2	5/8	4
93191	93235	R.030	1/2	1/2	5/8	4
93192	93236	R.060	1/2	1/2	5/8	4
93193	93237	R.090	1/2	1/2	5/8	4

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.012	0~-0.003

◎ : Excellent ○ : Good

Series	P					H	M	K	N					S	
	Carbon Steels ~HRc20	Alloy Steels HRc20~30	Prehardened Steels HRc30~40	Hardened Steels HRc40~45 HRc45~55	High Hardened Steels HRc55~70	High Hardened Steels HRc55~70	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
EM636	○	◎	◎	◎	○										
EM639	○	◎	◎	◎	○		○	○							



EM637 SERIES PLAIN SHANK
EM649 SERIES PLAIN SHANK

CARBIDE, 2&4 FLUTE REGULAR LENGTH CORNER RADIUS

- ▶ Designed to machine tool steel, alloy steel, mold steel and other high hardened materials.
- ▶ Superior workpiece finishes.
- ▶ Increased feed rate.



MG 2&4 30° ±.001 PLAIN P.914, 915

◆ U.S.A Stock

EM637 (2 FLUTE), EM649 (4 FLUTE) Series Unit : Inch

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
2 FLUTE	4 FLUTE	R (±.001)				
93194	93238	R.008	1/16	1/4	3/16	2-1/4
93195	93239	R.010	1/8	1/4	1/2	2-1/4
93196	93240	R.020	1/8	1/4	1/2	2-1/4
93197	-	R.030	1/8	1/4	1/2	2-1/4
93198	93242	R.010	3/16	1/4	5/8	2-1/2
93199	93243	R.020	3/16	1/4	5/8	2-1/2
93200	93244	R.030	3/16	1/4	5/8	2-1/2
93201	93245	R.010	1/4	1/4	3/4	3
93202	93246	R.020	1/4	1/4	3/4	3
93203	93247	R.030	1/4	1/4	3/4	3
93204	93248	R.020	5/16	5/16	13/16	3
93205	93249	R.030	5/16	5/16	13/16	3
93206	93250	R.060	5/16	5/16	13/16	3
93207	93251	R.090	5/16	5/16	13/16	3
93208	93252	R.020	3/8	3/8	1	3
93209	93253	R.030	3/8	3/8	1	3
93210	93254	R.060	3/8	3/8	1	3
93211	93255	R.090	3/8	3/8	1	3
93600	93595	R.020	7/16	7/16	1	4
93601	93597	R.030	7/16	7/16	1	4
93602	93598	R.060	7/16	7/16	1	4
93603	93599	R.090	7/16	7/16	1	4
93212	93256	R.020	1/2	1/2	1	4
93213	93257	R.030	1/2	1/2	1	4
93214	93258	R.060	1/2	1/2	1	4
93215	93259	R.090	1/2	1/2	1	4

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~- .0012	0~- .0003

◎ : Excellent ○ : Good

Series	P					H	M	K	N					S	
	Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
	~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
EM637	○	◎	◎	◎	○										
EM649	○	◎	◎	◎	○		○	○							



EM211 SERIES PLAIN SHANK
EM212 SERIES PLAIN SHANK

CARBIDE, 2&4 FLUTE LONG LENGTH CORNER RADIUS

- ▶ Designed to machine tool steel, alloy steel, mold steel and other high hardened materials.
- ▶ Superior workpiece finishes.
- ▶ Increased feed rate.



MG 2&4 30° ±.001 PLAIN P.914, 915

◆ U.S.A Stock

EM211 (2 FLUTE), EM212 (4 FLUTE) Series Unit : Inch

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
2 FLUTE	4 FLUTE	R (±.001)				
93143	93157	R.020	1/4	1/4	1-1/8	3
93144	93158	R.030	1/4	1/4	1-1/8	3
93145	93159	R.020	5/16	5/16	1-1/8	3
93146	93160	R.030	5/16	5/16	1-1/8	3
93147	93161	R.060	5/16	5/16	1-1/8	3
93148	93162	R.090	5/16	5/16	1-1/8	3
93149	93163	R.020	3/8	3/8	1-1/8	3
93150	93164	R.030	3/8	3/8	1-1/8	3
93151	93165	R.060	3/8	3/8	1-1/8	3
93152	93166	R.090	3/8	3/8	1-1/8	3
93153	93167	R.020	1/2	1/2	2	4
93154	93168	R.030	1/2	1/2	2	4
93155	93169	R.060	1/2	1/2	2	4
93156	93170	R.090	1/2	1/2	2	4

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~- .0012	0~- .0003

◎ : Excellent ○ : Good


Series	P					H	M	K	N					S	
	Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
	~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
EM211	○	◎	◎	◎	○										
EM212	○	◎	◎	◎	○		○	○							



EM102 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE 45° HELIX LONG LENGTH

- ▶ Designed to machine tool steel, alloy steel, mold steel and other high hardened materials.
- ▶ 4 flute allows for better workpiece finishes.
- ▶ Increased production.




◆ U.S.A Stock

Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
93395	3/8	5/16	5/8	5
93396	1/2	3/8	3/4	6
93397	5/8	1/2	7/8	6-1/2
93398	3/4	5/8	1	7
93399	7/8	3/4	1-1/4	8

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.0012	0~-0.0003



Enforced cutting edge

◎ : Excellent ○ : Good


P					H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○		○	○							



EM103 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE 45° HELIX LONG REACH CORNER RADIUS

- ▶ Designed to machine tool steel, alloy steel, mold steel and other high hardened materials.
- ▶ Superior workpiece finishes.
- ▶ Increased feed rate.



◆ U.S.A Stock

Unit : Inch

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R (±.001)	D1	D2	L1	L3	L2	D3
93400	R.020	3/8	5/16	5/8	.750	5	.293
93405	R.040	3/8	5/16	5/8	.750	5	.293
93401	R.020	1/2	3/8	3/4	.875	6	.355
93406	R.040	1/2	3/8	3/4	.875	6	.355
93402	R.020	5/8	1/2	7/8	1.000	6-1/2	.480
93407	R.040	5/8	1/2	7/8	1.000	6-1/2	.480
93403	R.020	3/4	5/8	1	1.125	7	.605
93408	R.040	3/4	5/8	1	1.125	7	.605
93404	R.020	7/8	3/4	1-1/4	1.375	8	.730
93409	R.040	7/8	3/4	1-1/4	1.375	8	.730

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.0012	0~-0.0003

◎ : Excellent ○ : Good

P					H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○		○	○							



EM965 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE 55° HELIX STUB LENGTH CORNER RADIUS

- ▶ Designed to machine tool steel, alloy steel, mold steel and other high hardened materials.
- ▶ Corner radius and corner protection against chipping.




◆ U.S.A Stock

Unit : Inch

EDP No.	Corner Radius R (±.001)	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
93544	R.063	1/4	1/4	5/16	7/8	2-1/4	.230
93545	R.078	5/16	5/16	3/8	1	2-1/2	.289
93546	R.094	3/8	3/8	7/16	1-1/4	3	.344
93596	R.109	7/16	7/16	1/2	1-1/2	3-1/4	.395
93547	R.125	1/2	1/2	1/2	1-1/2	3-1/4	.461

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.0012	0~-0.0003



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○		○	○							



EM208 SERIES PLAIN SHANK
EM218 SERIES PLAIN SHANK

CARBIDE, 6&8 FLUTE 45° HELIX LONG & EXTRA LONG LENGTH

- ▶ Designed to machine high hardened materials.
- ▶ High speed cutting and finish milling with high feed rate.
- ▶ Superior workpiece finishes.
- ▶ Superior wear resistant.
- ▶ Suitable for dry milling.
- ▶ Corner Protection against chipping.



◆ U.S.A Stock

Unit : Inch

EM208 Series ■ LONG LENGTH


EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
93119	1/4	1/4	1/2	2-1/4	6
93120	5/16	5/16	3/4	2-1/2	6
93121	3/8	3/8	7/8	2-7/8	6
93122	1/2	1/2	1	3-1/4	6
93123	5/8	5/8	1-1/4	3-5/8	6
93124	3/4	3/4	1-1/2	4-1/8	8
93171	1	1	1-3/4	4-1/4	8

Unit : Inch

EM218 Series ■ EXTRALONG LENGTH

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
99666	1/4	1/4	1	2-3/4	6
99667	5/16	5/16	1-1/2	3-5/8	6
99668	3/8	3/8	1-3/4	4	6
99669	1/2	1/2	2-3/16	4-3/8	6
99670	5/8	5/8	2-5/8	5-1/8	6
99588	3/4	3/4	2-1/4	5	8
99589	3/4	3/4	3-1/4	6	8
99590	3/4	3/4	4-1/8	7	8
99591	1	1	4-1/8	7	8

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.0012	0~-0.0003



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○							



EM668 SERIES PLAIN SHANK

CARBIDE, 6&8 FLUTE 45° HELIX LONG LENGTH CORNER RADIUS

- ▶ Designed to machine high hardened materials.
- ▶ High speed cutting and finish milling with high feed rates.
- ▶ Superior workpiece finishes.
- ▶ Superior wear resistant.
- ▶ Suitable for dry milling.



◆ U.S.A Stock

Unit : Inch

EDP No.	Corner Radius R	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
93277	R.020	1/4	1/4	1/2	2-1/4	6
93278	R.020	5/16	5/16	3/4	2-1/2	6
93279	R.020	3/8	3/8	7/8	2-7/8	6
93280	R.030	3/8	3/8	7/8	2-7/8	6
93281	R.020	1/2	1/2	1	3-1/4	6
93282	R.030	1/2	1/2	1	3-1/4	6
93283	R.030	5/8	5/8	1-1/4	3-5/8	6
93284	R.060	5/8	5/8	1-1/4	3-5/8	6
93285	R.030	3/4	3/4	1-1/2	4-1/8	8
93286	R.060	3/4	3/4	1-1/2	4-1/8	8
93287	R.090	3/4	3/4	1-1/2	4-1/8	8

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.012	0~-0.003

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



EM209 SERIES PLAIN SHANK
EM210 SERIES PLAIN SHANK

CARBIDE, 2&4 FLUTE LONG LENGTH BALL NOSE

- ▶ Designed to machine tool steel, alloy steel, mold steel and other high hardened materials.
- ▶ For copy-milling machines.



◆ U.S.A Stock

EM209(2 FLUTE), EM210(4 FLUTE) Series Unit : Inch

EDP No.		Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
2 FLUTE	4 FLUTE	R (±.001)				
93260	-	R 1/64	1/32	1/4	1/32	2-1/2
93261	-	R 1/32	1/16	1/4	1/16	2-1/2
93262	-	R 3/64	3/32	1/4	3/32	2-1/2
93125	93134	R 1/16	1/8	1/8	5/16	2-3/8
93126	93135	R 3/32	3/16	3/16	3/8	3-1/8
93127	93136	R 1/8	1/4	1/4	1/2	3-1/2
93128	93137	R 5/32	5/16	5/16	9/16	4
93129	93138	R 3/16	3/8	3/8	3/4	4
93130	93139	R 1/4	1/2	1/2	7/8	4-1/4
93131	93140	R 5/16	5/8	5/8	1-1/4	5-1/2
93132	93141	R 3/8	3/4	3/4	1-1/2	6-1/4
93133	93142	R 1/2	1	1	2	7-1/8

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.012	0~-0.003

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



EM961 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE MEDIUM LENGTH BALL NOSE

- ▶ Deep slotting milling is possible by reduced neck.
- ▶ High efficiency milling is possible in deep slotting with projection of the end mill being long.



◆ U.S.A Stock

Unit : Inch

EDP No.	Radius of Ball Nose R (±.001)	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
93517	R1/16	1/8	1/4	5/16	-	2-3/4	-
93518	R3/32	3/16	1/4	1/2	-	3-1/8	-
93519	R1/8	1/4	1/4	1/2	7/8	3-1/8	.242
93520	R5/32	5/16	5/16	9/16	1-1/16	3-1/2	.305
93521	R3/16	3/8	3/8	3/4	1-1/4	4	.367
93522	R1/4	1/2	1/2	7/8	1-3/8	4-1/4	.492
93523	R5/16	5/8	5/8	1-1/4	2	5-1/2	.617
93524	R3/8	3/4	3/4	1-1/2	2-1/4	6-1/4	.742
93525	R1/2	1	1	2-1/8	3	7	.992

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.012	0~-0.003

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○	○		○							



EM962 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG REACH BALL NOSE

- ▶ Longer overall length than EM209, EM210, type and suitable for machining deeply located area.



◆ U.S.A Stock

Unit : Inch

EDP No.	Radius of Ball Nose R (±.001)	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Overall Length L2
93578	R3/64	3/32	1/8	1/4	3-1/8
93579	R1/16	1/8	1/8	5/16	4
93580	R3/32	3/16	3/16	3/8	4-3/4
93581	R1/8	1/4	1/4	3/8	4-3/4
93582	R5/32	5/16	5/16	9/16	5-1/2
93583	R3/16	3/8	3/8	3/4	7
93584	R1/4	1/2	1/2	7/8	8
93585	R5/16	5/8	5/8	1-1/4	10
93586	R3/8	3/4	3/4	1-1/2	10

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.012	0~-0.003

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○							



EM960 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE MINIATURE BALL NOSE

- ▶ High precision milling in medical, optical, electronics and aerospace industrials.
- ▶ Excellent performance at dry cutting conditon.
- ▶ Excellent performance on high hardened steel up to HRc70.



◆ U.S.A Stock

Unit : Inch

EDP No.	Radius of Ball Nose R (±.0005)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
93507	R.012	.024	1/8	.043	1-1/2
93508	R.014	.028	1/8	.060	1-1/2
93509	R.0155	.031	1/8	.080	1-1/2
93510	R.0175	.035	1/8	.087	1-1/2
93511	R.020	.040	1/8	.100	1-1/2
93512	R.0215	.043	1/8	.118	1-1/2
93513	R.0235	.047	1/8	.118	1-1/2
93514	R.026	.052	1/8	.138	1-1/2
93515	R.0275	.055	1/8	.138	1-1/2
93516	R.031	.062	1/8	.157	1-1/2

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.0010	0~-0.0003

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○							



EM109 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE 15° HELIX STUB CUT LENGTH BALL NOSE for OVER HRc55

- ▶ Suitable for HRc55~HRc70 high hardened materials.
- ▶ Strong cutting edges and higher tool rigidity.



HRc55 ~ HRc70
◆ U.S.A Stock

Unit : Inch

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R (±.0005)	D1	D2	L1	L3	L2	D3
93485	R1/64	1/32	1/4	1/32	1/16	2	.029
93486	R1/32	1/16	1/4	1/16	1/8	2	.059
93487	R3/64	3/32	1/4	3/32	3/16	2	.090
93488	R1/16	1/8	1/4	1/8	1/4	2-1/2	.121
93489	R3/32	3/16	1/4	3/16	3/8	3	.184
93490	R1/8	1/4	1/4	1/4	1/2	3-1/2	.246
93491	R5/32	5/16	5/16	5/16	5/8	4	.309
93492	R3/16	3/8	3/8	3/8	3/4	4	.371
93493	R1/4	1/2	1/2	1/2	1	4-1/2	.496

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.0012	0~-0.0003

◎ : Excellent ○ : Good



P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
			○	◎	◎									



EM963 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE with TAPER NECK

► High efficiency milling is possible in deep slotting with projection of the end mill being long.



U.S.A Stock

Unit : Inch

EDP No.	Radius of Ball Nose R (±.0005)	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Under Neck Parallel Length L4	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Neck Taper Angle θ
93526	R1/32	1/16	1/4	5/32	15/64	7/8	2-3/8	.096	1° 30'
93527	R1/32	1/16	1/4	5/32	15/64	1-5/8	3-1/8	.208	3°
93528	R1/16	1/8	1/4	1/4	21/64	2-1/16	3-5/8	.216	1° 30'
93529	R3/32	3/16	3/8	3/8	29/64	2-3/8	4-3/8	.288	1° 30'
93530	R1/8	1/4	3/8	1/2	5/8	2-1/16	4-3/8	.325	1° 30'
93531	R5/32	5/16	1/2	9/16	11/16	2-1/16	4-3/4	.385	1° 30'
93532	R3/16	3/8	1/2	11/16	13/16	2-3/8	5-1/16	.458	1° 30'
93533	R1/4	1/2	3/4	7/8	1	3-1/4	6-3/8	.618	1° 30'

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.0012	0~-0.0003

◎ : Excellent ○ : Good



P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○	○		○							



EM979 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE with PENCIL NECK

► High efficiency milling is possible in deep slotting with projection of the end mill being long.




U.S.A Stock

Unit : Inch

EDP No.	Radius of Ball Nose R (±.0005)	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Under Neck Parallel Length L4	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Neck Taper Angle θ
93534	R3/32	3/16	3/8	9/16	.659	3-11/32	7-3/4		2°
93535	R3/32	3/16	3/8	9/16	.666	2-13/16	6		2° 30'
93536	R1/8	1/4	1/2	3/4	.859	4-7/16	7-3/4		2°
93537	R1/8	1/4	1/2	3/4	.856	3-23/32	6		2° 30'
93538	R5/32	5/16	1/2	3/4	.868	4-29/32	7-3/4		1° 20'
93539	R5/32	5/16	1/2	3/4	.870	3-15/16	6		1° 45'
93540	R3/16	3/8	5/8	1-3/16	1.326	4-29/32	7-3/4		2°
93541	R3/16	3/8	5/8	1-3/16	1.325	4-3/16	6		2° 30'
93542	R1/4	1/2	5/8	1-3/16	1.309	4	7-3/4		1° 20'
93543	R1/4	1/2	5/8	1-3/16	1.329	3-3/8	6		1° 45'

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.0012	0~-0.0003



MILLING ON TAPERED WALL

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○	○		○							



X-POWER BALL NOSE END MILLS - MMC


Useful Field Area

- Die & Mold making, Turbine manufacturing and Aircraft Industry, etc.
- Difficult 3-D Forms.
- Profiling of up to HRc 65 high hardened steels and Alloy steels, Nickelbase alloys, Titanium alloys.

Characteristics

- Ultra micro grain carbide which increase both toughness and hardness.
- YG-1's unique X-POWER coating suitable for dry cutting and high speed cutting.
- Outstanding tool geometry and sphere shape ball enables more increased tool life and higher speed and feed operation.

Surpassing Milling Operation




Favorable Back Milling

Unfavorable Drilling

Operating angle 14° ~ 16°, higher speed and feed are possible by decreased cutting resistance at the cutting edges contacting the workpiece.

Excellent surface finish and faster milling process.

Enable to milling with higher speed and feed when Back Milling.



Unfavorable Profiling

Favorable Profiling

Inclination (ap=0.5D)

When 15° inclination milling operation, more productivity and higher speed and feed are possible.

Decreased cutting force.


Excellent surface roughness and brightness.



EM084 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG LENGTH BALL NOSE (MMC-ECONOMY TYPE)

- ▶ Designed for copy milling.
- ▶ Increased feed rates.
- ▶ 15° inclination.
- ▶ Easy to regrind.



◆ U.S.A Stock

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Unit : Inch Lz
	R (±.0005)	D1	D2	L1	L3	L2	D3	
93288	R1/16	1/8	1/4	5/32	1-1/4	3-1/4	.100	.060
93289	R3/32	3/16	1/4	7/32	1-1/4	3-1/4	.150	.080
93290	R1/8	1/4	1/4	9/32	1-1/4	4	.200	.080
93291	R5/32	5/16	5/16	3/8	1-1/2	4	.250	.120
93292	R3/16	3/8	3/8	13/32	1-3/4	4	.300	.120
93293	R1/4	1/2	1/2	17/32	2-1/4	4-1/4	.400	.120
93294	R5/16	5/8	5/8	5/8	2-3/4	6-1/4	.500	.120

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~.0010	0~.0003

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



◎ : Excellent ○ : Good



EM093 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG LENGTH BALL NOSE (MMC-ECONOMY TYPE)

- ▶ Designed for copy milling.
- ▶ Increased feed rates.
- ▶ 15° inclination.
- ▶ Easy to regrind.



◆ U.S.A Stock

Unit : Inch

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Lz
	R (±.0005)	D1	D2	L1	L3	L2	D3	
93295	R1/16	1/8	1/4	5/32	1-1/4	3-1/4	.100	.060
93296	R3/32	3/16	1/4	7/32	1-1/4	3-1/4	.150	.080
93297	R1/8	1/4	1/4	9/32	1-1/4	4	.200	.080
93298	R5/32	5/16	5/16	3/8	1-1/2	4	.250	.120
93299	R3/16	3/8	3/8	13/32	1-3/4	4	.300	.120
93300	R1/4	1/2	1/2	17/32	2-1/4	4-1/4	.400	.120
93301	R5/16	5/8	5/8	5/8	2-3/4	6-1/4	.500	.120

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~- .0010	0~- .0003

◎ : Excellent ○ : Good



P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○	○		○							



EM096 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG LENGTH BALL NOSE (MMC-SPHERE TYPE)

- ▶ Designed for copy milling.
- ▶ Increased feed rates.
- ▶ 15° inclination.
- ▶ Sphere Angle : 250°



◆ U.S.A Stock

Unit : Inch

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R (±.0005)	D1	D2	L1	L3	L2	D3
93410	R1/16	1/8	1/4	.100	1-1/4	3-1/4	.100
93411	R3/32	3/16	1/4	.150	1-1/4	3-1/4	.150
93412	R1/8	1/4	1/4	.200	1-1/8	4	.200
93413	R5/32	5/16	5/16	.250	1-3/8	4	.250
93414	R3/16	3/8	3/8	.300	1-5/8	4	.300
93415	R1/4	1/2	1/2	.400	2-3/16	4-1/4	.400
93416	R5/16	5/8	5/8	.500	2-3/4	6-1/4	.500

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~- .0010	0~- .0003

◎ : Excellent ○ : Good



P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○	○		○							



EM097 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG LENGTH BALL NOSE (MMC-SPHERE TYPE)

- ▶ Designed for copy milling.
- ▶ Increased feed rates.
- ▶ 15° inclination.
- ▶ Sphere Angle : 250°



◆ U.S.A Stock

Unit : Inch

EDP No.	Radius of Ball Nose R (±.0005)	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
93417	R1/16	1/8	1/4	.100	1-1/4	3-1/4	.100
93418	R3/32	3/16	1/4	.150	1-1/4	3-1/4	.150
93419	R1/8	1/4	1/4	.200	1-1/8	4	.200
93420	R5/32	5/16	5/16	.250	1-3/8	4	.250
93421	R3/16	3/8	3/8	.300	1-5/8	4	.300
93422	R1/4	1/2	1/2	.400	2-3/16	4-1/4	.400
93423	R5/16	5/8	5/8	.500	2-3/4	6-1/4	.500

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~- .0010	0~- .0003

◎ : Excellent ○ : Good


P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



EM666 SERIES PLAIN SHANK
EM156 SERIES PLAIN SHANK

CARBIDE, MULTI FLUTE 20° HELIX STUB & LONG LENGTH FINE PITCH ROUGHING

- ▶ Designed to machine tool steel, alloy steel, mold steel and other high hardened materials.
- ▶ High velocity milling of hardened steels.
- ▶ For dry and wet milling.
- ▶ Fast chip ejection.



◆ U.S.A Stock

Unit : Inch


EM666 Series ■ STUB LENGTH

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
93270	1/4	1/4	5/16	2-1/8	3
93271	5/16	5/16	3/8	2-1/4	3
93272	3/8	3/8	9/16	2-1/2	3
93273	1/2	1/2	5/8	3	4
93274	5/8	5/8	7/8	3-1/4	4
93275	3/4	3/4	1	3-3/4	4
93276	1	1	1	4	5

EM156 Series ■ LONG LENGTH

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
93112	1/4	1/4	3/4	2-1/2	3
93113	5/16	5/16	3/4	2-1/2	3
93114	3/8	3/8	7/8	2-1/2	3
93115	1/2	1/2	1	3	4
93116	5/8	5/8	1-1/4	3-1/2	4
93117	3/4	3/4	1-5/8	4	4
93118	1	1	1-3/4	4	5

Mill Dia. (inch)	Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
1/4~3/8	0 ~ -.0022	0 ~ -.0003
1/2~5/8	0 ~ -.0027	
3/4~1	0 ~ -.0033	



Enforced Cutting Edge

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○	○						



EM662 SERIES PLAIN SHANK

CARBIDE, MULTI FLUTE 20° HELIX LONG LENGTH FINE PITCH ROUGHING BALL NOSE

- ▶ Designed to machine tool steel, alloy steel, mold steel and other high hardened materials.
- ▶ High velocity milling of hardened steels.
- ▶ For dry and wet milling.
- ▶ Fast chip ejection.



◆ U.S.A Stock

Unit : Inch

EDP No.	Radius of Ball Nose R (±.001)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
93263	R1/8	1/4	1/4	3/4	2-1/2	3
93264	R5/32	5/16	5/16	3/4	2-1/2	3
93265	R3/16	3/8	3/8	7/8	2-1/2	3
93266	R1/4	1/2	1/2	1	3	4
93267	R5/16	5/8	5/8	1-1/4	3-1/2	4
93268	R3/8	3/4	3/4	1-5/8	4	4
93269	R1/2	1	1	1-3/4	4	5

Mill Dia. (inch)	Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
1/4~3/8	0 ~ -.0022	0 ~ -.0003
1/2~5/8	0 ~ -.0027	
3/4~1	0 ~ -.0033	

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○							



EM966 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE for RIB PROCESSING

- ▶ For deep slotting & pocketing.
- ▶ For depths of 6 to 10X cutting diameter.
- ▶ Machine carbon steel, alloy steel, tool steel, die and mold steels.
- ▶ Suitable for high speed cutting and high precision machining.
- ▶ Designed with reinforced shank for higher stability and rigidity.
- ▶ Long neck design for deep machining near walls.



◆ U.S.A Stock

Unit : Inch

EDP No.	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
93548	1/32	1/8	3/64	7/32	2	.029
93549	1/32	1/8	3/64	5/16	2	.029
93550	3/64	1/8	1/16	7/32	2	.045
93551	3/64	1/8	1/16	9/32	2	.045
93552	3/64	1/8	1/16	1/2	2	.045
93553	1/16	1/8	3/32	5/16	2	.060
93554	1/16	1/8	3/32	3/8	2	.060
93555	1/16	1/8	3/32	1/2	2	.060
93556	1/16	1/8	3/32	5/8	2	.060
93557	5/64	1/8	1/8	1/2	2	.076
93558	5/64	1/8	1/8	5/8	2	.076
93559	3/32	1/8	9/64	1/2	2	.090
93560	3/32	1/8	9/64	5/8	2	.090
93561	1/8	1/4	3/16	9/16	2-1/4	.120
93562	1/8	1/4	3/16	3/4	2-1/4	.120

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0 ~ -.0006	0 ~ -.0003

◎ : Excellent ○ : Good




P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○							



EM967 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE for RIB PROCESSING

- ▶ For 3-D milling, deep slotting and pocketing.
- ▶ For depths of 6 to 10X cutting diameter.
- ▶ Machine carbon steel, alloy steel, tool steel, die and mold steels.
- ▶ Suitable for high speed cutting and high precision machining.
- ▶ Designed with reinforced shank for higher stability and rigidity.
- ▶ Long neck design for deep machining near walls.



◆ U.S.A Stock

Unit : Inch

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R (±.0005)	D1	D2	L1	L3	L2	D3
93563	R1/64	1/32	1/8	3/64	7/32	2	.029
93564	R1/64	1/32	1/8	3/64	5/16	2	.029
93565	R.0234	3/64	1/8	1/16	7/32	2	.045
93566	R.0234	3/64	1/8	1/16	9/32	2	.045
93567	R.0234	3/64	1/8	1/16	1/2	2	.045
93568	R1/32	1/16	1/8	3/32	5/16	2	.060
93569	R1/32	1/16	1/8	3/32	1/2	2	.060
93570	R1/32	1/16	1/8	3/32	5/8	2	.060
93571	R.0391	5/64	1/8	1/8	5/16	2	.076
93572	R.0391	5/64	1/8	1/8	5/8	2	.076
93573	R.0391	5/64	1/8	1/8	3/4	2	.076
93574	R3/64	3/32	1/8	9/64	5/8	2	.090
93575	R3/64	3/32	1/8	9/64	3/4	2	.090
93576	R1/16	1/8	1/4	3/16	5/8	2-1/4	.120
93577	R1/16	1/8	1/4	3/16	3/4	2-1/4	.120

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-.0006	0~-.0003

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○							



EM810 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE SHORT LENGTH

- ▶ Designed to machine tool steels, alloy steels, mold steels and other hardened materials.
- ▶ Superior workpiece finishes.
- ▶ Increased feed rates.



P.912, 914

Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
	Metric	Inch			
EM810901	1.0	.0394	6	2.5	40
EM810902	1.5	.0591	6	4	40
EM810020	2.0	.0787	4	6	40
EM810903	2.0	.0787	6	6	40
EM810025	2.5	.0984	4	8	40
EM810904	2.5	.0984	6	8	40
EM810030	3.0	.1181	6	8	45
EM810035	3.5	.1378	6	10	45
EM810040	4.0	.1575	6	11	45
EM810045	4.5	.1772	6	11	45
EM810050	5.0	.1969	6	13	50
EM810055	5.5	.2165	6	13	50
EM810060	6.0	.2362	6	13	50
EM810065	6.5	.2559	8	16	60
EM810070	7.0	.2756	8	16	60
EM810075	7.5	.2953	8	16	60
EM810080	8.0	.3150	8	19	60
EM810085	8.5	.3346	10	19	70
EM810090	9.0	.3543	10	19	70
EM810095	9.5	.3740	10	19	70
EM810100	10.0	.3937	10	22	70
EM810105	10.5	.4134	12	22	75
EM810110	11.0	.4330	12	22	75
EM810115	11.5	.4527	12	22	75
EM810120	12.0	.4724	12	26	75
EM810906	13.0	.5118	12	26	85
EM810140	14.0	.5512	14	26	85
EM810905	14.0	.5512	16	26	85
EM810908	15.0	.5905	16	26	90

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○	○						



EM810 SERIES PLAIN SHANK
EM816 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE SHORT& LONG LENGTH

- ▶ Designed to machine tool steels, alloy steels, mold steels and other hardened materials.
- ▶ Superior workpiece finishes.
- ▶ Increased feed rates.



◇ Call for Availability

EM810 Series ■ SHORT LENGTH Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
	Metric	Inch			
EM810160	16.0	.6299	16	32	100
EM810909	17.0	.6692	16	32	100
EM810180	18.0	.7087	18	32	100
EM810911	19.0	.7480	20	32	100
EM810200	20.0	.7874	20	38	105
EM810220	22.0	.8661	20	38	105
EM810240	24.0	.9449	25	45	120
EM810250	25.0	.9843	25	45	120

EM816 Series ■ LONG LENGTH Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
	Metric	Inch			
EM816020	2.0	.0787	4	8	40
EM816030	3.0	.1181	6	12	50
EM816040	4.0	.1575	6	15	50
EM816050	5.0	.1969	6	20	60
EM816060	6.0	.2362	6	20	60
EM816080	8.0	.3150	8	25	70
EM816100	10.0	.3937	10	30	90
EM816120	12.0	.4724	12	30	90
EM816140	14.0	.5512	16	40	110
EM816160	16.0	.6299	16	50	110
EM816180	18.0	.7087	20	50	110
EM816200	20.0	.7874	20	55	110
EM816250	25.0	.9843	25	75	140

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○		○	○							



EM811 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE SHORT LENGTH

- ▶ Designed to machine tool steels, alloy steels, mold steels and other hardened materials.
- ▶ 4 flute allows for better workpiece finishes.
- ▶ Increased production.



◇ Call for Availability

EM811 Series ■ SHORT LENGTH Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
	Metric	Inch			
EM811020	2.0	.0787	4	6	40
EM811901	2.0	.0787	6	6	40
EM811025	2.5	.0984	4	8	40
EM811902	2.5	.0984	6	8	40
EM811030	3.0	.1181	6	8	45
EM811035	3.5	.1378	6	10	45
EM811040	4.0	.1575	6	11	45
EM811045	4.5	.1772	6	11	45
EM811050	5.0	.1969	6	13	50
EM811055	5.5	.2165	6	13	50
EM811060	6.0	.2362	6	13	50
EM811065	6.5	.2559	8	16	60
EM811070	7.0	.2756	8	16	60
EM811075	7.5	.2953	8	16	60
EM811080	8.0	.3150	8	19	60
EM811085	8.5	.3346	10	19	70
EM811090	9.0	.3543	10	19	70
EM811095	9.5	.3740	10	19	70
EM811100	10.0	.3937	10	22	70
EM811105	10.5	.4134	12	22	75
EM811110	11.0	.4330	12	22	75
EM811115	11.5	.4527	12	22	75
EM811120	12.0	.4724	12	26	75
EM811904	13.0	.5118	12	26	85
EM811140	14.0	.5512	14	26	85
EM811905	14.0	.5512	12	26	85
EM811903	14.0	.5512	16	26	85
EM811906	15.0	.5905	16	26	90
EM811160	16.0	.6299	16	32	100

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○		○	○							



EM811 SERIES PLAIN SHANK
EM817 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE SHORT& LONG LENGTH

- ▶ Designed to machine tool steels, alloy steels, mold steels and other hardened materials.
- ▶ 4 flute allows for better workpiece finishes.
- ▶ Increased production.



◇ Call for Availability

EM811 Series ■ SHORT LENGTH Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
	Metric	Inch			
EM811907	17.0	.6692	16	32	100
EM811180	18.0	.7087	18	32	100
EM811908	18.0	.7087	16	32	100
EM811909	19.0	.7480	20	32	100
EM811200	20.0	.7874	20	38	105
EM811220	22.0	.8661	20	38	105
EM811240	24.0	.9449	25	45	120
EM811250	25.0	.9843	25	45	120

EM817 Series ■ LONG LENGTH Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
	Metric	Inch			
EM817020	2.0	.0787	4	8	40
EM817030	3.0	.1181	6	12	50
EM817040	4.0	.1575	6	15	50
EM817050	5.0	.1969	6	20	60
EM817060	6.0	.2362	6	20	60
EM817080	8.0	.3150	8	25	70
EM817100	10.0	.3937	10	30	90
EM817120	12.0	.4724	12	30	90
EM817140	14.0	.5512	16	40	110
EM817160	16.0	.6299	16	50	110
EM817180	18.0	.7087	20	50	110
EM817200	20.0	.7874	20	55	110
EM817250	25.0	.9843	25	75	140

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good

Series	P					H	M	K	N					S
	Carbon Steels ~HRc20	Alloy Steels HRc20~30	Prehardened Steels HRc30~40	Hardened Steels HRc40~45 HRc45~55		High Hardened Steels HRc55~70	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium
EM811	○	◎	◎	◎	○		○	○						
EM817	○	◎	◎	◎	○			○						



EM895 SERIES PLAIN SHANK

CARBIDE, 3 FLUTE 38° HELIX SHORT LENGTH

- ▶ Designed to machine tool steels, alloy steels, mold steels and other hardened materials.
- ▶ Possesses the advantage of 2 flute and 4 flute end mill.
- ▶ Superior workpiece finishes.



◇ Call for Availability

EM895 Series ■ SHORT LENGTH Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
	Metric	Inch			
EM895010	1.0	.0394	3	2.5	38
EM895015	1.5	.0591	4	5	50
EM895025	2.5	.0984	3	7	38
EM895030	3.0	.1181	3	10	38
EM895901	3.0	.1181	6	10	50
EM895035	3.5	.1378	4	12	50
EM895902	3.5	.1378	6	12	50
EM895040	4.0	.1575	4	12	50
EM895903	4.0	.1575	6	12	50
EM895045	4.5	.1772	6	14	57
EM895050	5.0	.1969	5	14	50
EM895904	5.0	.1969	6	14	57
EM895060	6.0	.2362	6	16	57
EM895080	8.0	.3150	8	20	63
EM895100	10.0	.3937	10	22	72
EM895120	12.0	.4724	12	25	73
EM895140	14.0	.5512	14	25	75
EM895160	16.0	.6299	16	32	82
EM895180	18.0	.7087	18	32	92
EM895200	20.0	.7874	20	38	92

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good

Series	P					H	M	K	N					S
	Carbon Steels ~HRc20	Alloy Steels HRc20~30	Prehardened Steels HRc30~40	Hardened Steels HRc40~45 HRc45~55		High Hardened Steels HRc55~70	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium
EM895	○	◎	◎	◎	○		○	○						



EM810 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE MINIATURE

- ▶ High precision milling in medical, optical, electronics and aero space industries.
- ▶ Excellent performance on hardened steel



◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
	Metric	Inch			
EM810004	0.4	.0157	3	0.8	40
EM810005	0.5	.0197	3	1	40
EM810006	0.6	.0236	3	1.2	40
EM810007	0.7	.0276	3	1.4	40
EM810008	0.8	.0315	3	1.6	40
EM810009	0.9	.0354	3	2	40
EM810010	1.0	.0394	4	2.5	40
EM810011	1.1	.0433	4	2.5	40
EM810012	1.2	.0472	4	4	40
EM810013	1.3	.0512	4	4	40
EM810014	1.4	.0551	4	4	40
EM810015	1.5	.0591	4	4	40

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○							



EM818 SERIES PLAIN SHANK
EM819 SERIES PLAIN SHANK

CARBIDE, 2&4 FLUTE LONG LENGTH CORNER RADIUS

- ▶ Designed to machine tool steels, alloy steels, mold steels and other hardened materials.
- ▶ Superior workpiece finishes.
- ▶ Increased feed rates.



◇ Call for Availability

Unit : mm

EDP No.		Corner Radius	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
2 FLUTE	4 FLUTE		Metric	Inch			
EM818030	EM819030	RO.3	3.0	.1181	6	12	50
EM818040	EM819040	RO.3	4.0	.1575	6	15	50
EM818911	EM819911	RO.5	4.0	.1575	6	15	50
EM818050	EM819050	RO.3	5.0	.1969	6	20	60
EM818912	EM819912	RO.5	5.0	.1969	6	20	60
EM818913	EM819913	RO.3	6.0	.2362	6	20	60
EM818060	EM819060	RO.5	6.0	.2362	6	20	60
EM818901	EM819901	R1.0	6.0	.2362	6	20	60
EM818914	EM819914	RO.3	8.0	.3150	8	25	70
EM818080	EM819080	RO.5	8.0	.3150	8	25	70
EM818902	EM819902	R1.0	8.0	.3150	8	25	70
EM818903	EM819903	R1.5	8.0	.3150	8	25	70
EM818904	EM819904	R2.0	8.0	.3150	8	25	70
EM818915	EM819915	RO.3	10.0	.3937	10	30	90
EM818100	EM819100	RO.5	10.0	.3937	10	30	90
EM818905	EM819905	R1.0	10.0	.3937	10	30	90
EM818906	EM819906	R1.5	10.0	.3937	10	30	90
EM818907	EM819907	R2.0	10.0	.3937	10	30	90
EM818120	EM819120	RO.5	12.0	.4724	12	30	90
EM818908	EM819908	R1.0	12.0	.4724	12	30	90
EM818909	EM819909	R1.5	12.0	.4724	12	30	90
EM818910	EM819910	R2.0	12.0	.4724	12	30	90
EM818160	EM819160	RO.5	16.0	.6299	16	50	110
EM818916	EM819916	R1.0	16.0	.6299	16	50	110
EM818917	EM819917	R1.5	16.0	.6299	16	50	110
EM818918	EM819918	R2.0	16.0	.6299	16	50	110
EM818200	EM819200	RO.5	20.0	.7874	20	55	110
EM818919	EM819919	R1.0	20.0	.7874	20	55	110
EM818920	EM819920	R1.5	20.0	.7874	20	55	110
EM818921	EM819921	R2.0	20.0	.7874	20	55	110

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good


Series	P					H	M	K	N					S
	Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium
	~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70								
EM811	○	◎	◎	◎	○									
EM817	○	◎	◎	◎	○		○	○						



EM905 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE 45° HELIX SHORT LENGTH CORNER RADIUS

- ▶ No line is marked on the boundary section during step milling because this tool has radius on the end faces of the shank
- ▶ High speed cutting in wide deep wall with step milling
- ▶ Suitable for deep side milling, Helical Milling, Contour Milling



◇ Call for Availability

Unit : mm

EDP No.	Corner Radius R	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
EM905100	R0.5	10.0	.3937	8	15	19.2	130	7.5
EM905901	R1.0	10.0	.3937	8	15	19.2	130	7.5
EM905120	R0.5	12.0	.4724	10	18	22.2	150	9.5
EM905902	R1.0	12.0	.4724	10	18	22.2	150	9.5
EM905140	R0.5	14.0	.5512	12	21	25.2	160	11.5
EM905903	R1.0	14.0	.5512	12	21	25.2	160	11.5
EM905180	R0.5	18.0	.7087	16	27	31.2	180	15.5
EM905904	R1.0	18.0	.7087	16	27	31.2	180	15.5
EM905220	R0.5	22.0	.8661	20	33	37.2	200	19.5
EM905905	R1.0	22.0	.8661	20	33	37.2	200	19.5

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○	○	○	○							



EM839 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE STUB LENGTH CORNER RADIUS

- ▶ Designed to machine tool steels, alloy steels, mold steels and other hardened materials.
- ▶ Superior workpiece finishes.
- ▶ Increased feed rates.



◇ Call for Availability

Unit : mm

EDP No.	Corner Radius R	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
EM839020	R0.2	2.0	.0787	6	2.5	5	50	1.9
EM839025	R0.25	2.5	.0984	6	3	6	50	2.4
EM839030	R0.3	3.0	.1181	6	4	7	50	2.8
EM839035	R0.35	3.5	.1378	6	4.5	8	50	3.2
EM839040	R0.4	4.0	.1575	6	5	9	50	3.7
EM839050	R0.5	5.0	.1969	6	6	12	50	4.6
EM839060	R0.6	6.0	.2362	6	7	14	55	5.6
EM839080	R0.8	8.0	.3150	8	10	18	60	7.4
EM839100	R1.0	10.0	.3937	10	12	25	70	9.4
EM839120	R1.2	12.0	.4724	12	15	30	80	11.4
EM839160	R1.6	16.0	.6299	16	18	35	90	15.4

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○	○	○	○							



EM812 SERIES PLAIN SHANK
EM834 SERIES PLAIN SHANK

CARBIDE, 6&8 FLUTE 45° HELIX LONG & EXTRA LONG LENGTH

- ▶ Designed to machine hardened materials.
- ▶ High speed cutting and finish milling with high feed rates.
- ▶ Superior workpiece finishes.
- ▶ Superior wear resistant.
- ▶ Suitable for dry milling.



◇ Call for Availability


EM812 Series ■ LONG LENGTH Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length	No. of Flute
	Metric	Inch				
EM812060	6.0	.2362	6	13	57	6
EM812070	7.0	.2756	8	16	63	6
EM812080	8.0	.3150	8	19	63	6
EM812090	9.0	.3543	10	19	72	6
EM812100	10.0	.3937	10	22	72	6
EM812120	12.0	.4724	12	26	83	6
EM812140	14.0	.5512	14	26	83	6
EM812901	14.0	.5512	16	26	83	6
EM812160	16.0	.6299	16	32	92	6
EM812180	18.0	.7087	18	32	92	8
EM812200	20.0	.7874	20	38	104	8
EM812250	25.0	.9843	25	44	104	8

EM834 Series ■ EXTRA LONG LENGTH Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length	No. of Flute
	Metric	Inch				
EM834060	6.0	.2362	6	26	70	6
EM834080	8.0	.3150	8	36	90	6
EM834100	10.0	.3937	10	46	100	6
EM834120	12.0	.4724	12	56	110	6
EM834160	16.0	.6299	16	66	130	6
EM834200	20.0	.7874	20	76	140	6
EM834250	25.0	.9843	25	92	180	6

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○							



EM835 SERIES PLAIN SHANK

CARBIDE, 6 FLUTE 45° HELIX LONG LENGTH CORNER RADIUS

- ▶ Designed to machine hardened materials.
- ▶ High speed cutting and finish milling with high feed rates.
- ▶ Superior workpiece finishes.
- ▶ Superior wear resistant.
- ▶ Suitable for dry milling.



◇ Call for Availability

EM835 Series ■ LONG LENGTH CORNER RADIUS Unit : mm

EDP No.	Corner Radius R	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
		Metric	Inch			
EM835060	R0.5	6.0	.2362	6	13	70
EM835080	R0.5	8.0	.3150	8	19	90
EM835100	R0.5	10.0	.3937	10	22	100
EM835901	R1.0	10.0	.3937	10	22	100
EM835120	R0.5	12.0	.4724	12	26	110
EM835902	R1.0	12.0	.4724	12	26	110
EM835160	R1.0	16.0	.6299	16	32	130
EM835903	R1.5	16.0	.6299	16	32	130
EM835200	R1.0	20.0	.7874	20	38	140
EM835904	R1.5	20.0	.7874	20	38	140
EM835905	R2.0	20.0	.7874	20	38	140

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○							



EM897 SERIES PLAIN SHANK

CARBIDE, 6 FLUTE 45° HELIX STUB LENGTH CORNER RADIUS

- ▶ High speed cutting
- ▶ Excellent performance in dry cutting
- ▶ Cutting up to three times length of the cutting diameter due to reduced neck.



◇ Call for Availability

Unit : mm

EDP No.	Corner Radius R	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
EM897060	R0.5	6.0	.2362	6	6	14	50	5.7
EM897080	R0.5	8.0	.3150	8	8	24	60	7.65
EM897100	R1.0	10.0	.3937	10	10	30	70	9.65
EM897120	R1.0	12.0	.4724	12	12	30	75	11.6

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good

P					H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○							



EM876 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE SHORT LENGTH BALL NOSE

- ▶ Economic type with short overall length.
- ▶ Radius tolerance ±0.02mm & short length of cut.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.02)	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
		Metric	Inch			
EM876010	R0.5	1.0	.0394	3	3	38
EM876012	R0.6	1.2	.0472	3	3	38
EM876015	R0.75	1.5	.0591	3	3	38
EM876020	R1.0	2.0	.0787	6	3	50
EM876030	R1.5	3.0	.1181	6	4	50
EM876040	R2.0	4.0	.1575	6	5	54
EM876050	R2.5	5.0	.1969	6	6	54
EM876060	R3.0	6.0	.2362	6	7	54
EM876070	R3.5	7.0	.2756	8	8	58
EM876080	R4.0	8.0	.3150	8	9	58
EM876090	R4.5	9.0	.3543	10	10	66
EM876100	R5.0	10.0	.3937	10	11	66
EM876120	R6.0	12.0	.4724	12	12	73
EM876140	R7.0	14.0	.5512	14	14	75
EM876160	R8.0	16.0	.6299	16	16	82
EM876180	R9.0	18.0	.7087	18	18	84
EM876200	R10.0	20.0	.7874	20	20	92
EM876250	R12.5	25.0	.9843	25	25	104

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good


P					H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○	○		○							



EM813 / EM815 SERIES PLAIN SHANK
EM823 / EM825 SERIES FLAT SHANK

CARBIDE, 2&4 FLUTE LONG LENGTH BALL NOSE

- ▶ Designed to machine tool steel, alloy steel, mold steel and other high hardened materials.
- ▶ For copy - milling machines.



◇ Call for Availability

EM813, EM823(2 FLUTE), EM815, EM825(4 FLUTE) Series

Unit : mm

EDP No.				Radius of Ball Nose R (±0.02)	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
2 FLUTE		4 FLUTE			Metric	Inch			
PLAIN	FLAT	PLAIN	FLAT						
93302	—	93335	—	R0.5	1.0	.0394	4	2.5	50
93303	—	—	—	R0.6	1.2	.0472	4	3	50
93304	—	93336	—	R0.75	1.5	.0591	4	4	50
93305	93320	93337	93352	R1.0	2.0	.0787	6	5	50
93306	93321	93338	93353	R1.5	3.0	.1181	6	8	60
93307	93322	93339	93354	R2.0	4.0	.1575	6	8	70
93308	93323	93340	93355	R2.5	5.0	.1969	6	10	80
93309	93324	93341	93356	R3.0	6.0	.2362	6	12	90
93310	93325	93342	93357	R3.5	7.0	.2756	8	14	90
93311	93326	93343	93358	R4.0	8.0	.3150	8	14	100
93312	93327	93344	93359	R4.5	9.0	.3543	10	18	100
93313	93328	93345	93360	R5.0	10.0	.3937	10	18	100
93314	93329	93346	93361	R6.0	12.0	.4724	12	22	110
93315	93330	93347	93362	R7.0	14.0	.5512	14	26	110
93316	93331	93348	93363	R8.0	16.0	.6299	16	30	140
93317	93332	93349	93364	R9.0	18.0	.7087	18	34	140
93318	93333	93350	93365	R10.0	20.0	.7874	20	38	160
93319	93334	93351	93366	R12.5	25.0	.9843	25	50	180

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good



P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



EM899 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE MEDIUM LENGTH BALL NOSE

- ▶ Deep slotting milling is possible by reduced neck.
- ▶ High efficiency milling is possible in deep slotting with projection of the end mill being long.



◇ Call for Availability

EM899 Series

Unit : mm

EDP No.	Radius of Ball Nose R (±0.01)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric	Inch					
		D1						
EM899030	R1.5	3.0	.1181	6	8	—	70	—
EM899040	R2.0	4.0	.1575	6	8	—	70	—
EM899050	R2.5	5.0	.1969	6	12	—	80	—
EM899060	R3.0	6.0	.2362	6	12	22	80	5.8
EM899070	R3.5	7.0	.2756	8	14	—	90	—
EM899080	R4.0	8.0	.3150	8	14	27	90	7.8
EM899100	R5.0	10.0	.3937	10	18	31	100	9.8
EM899120	R6.0	12.0	.4724	12	22	35	110	11.8
EM899140	R7.0	14.0	.5512	12	26	—	120	—
EM899160	R8.0	16.0	.6299	16	30	50	140	15.8
EM899180	R9.0	18.0	.7087	16	34	—	140	—
EM899200	R10.0	20.0	.7874	20	38	58	160	19.8
EM899250	R12.5	25.0	.9843	25	55	75	180	24.8

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



EM838 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG REACH BALL NOSE

► Longer overall length than EM813 types and suitable for machining deeply located area.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.02)	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
		Metric	Inch			
EM838020	R1.0	2.0	.0787	3	6	80
EM838030	R1.5	3.0	.1181	3	8	100
EM838040	R2.0	4.0	.1575	4	8	100
EM838050	R2.5	5.0	.1969	6	10	120
EM838060	R3.0	6.0	.2362	6	10	120
EM838080	R4.0	8.0	.3150	8	14	140
EM838100	R5.0	10.0	.3937	10	18	180
EM838120	R6.0	12.0	.4724	12	22	200
EM838160	R8.0	16.0	.6299	16	30	250
EM838200	R10.0	20.0	.7874	20	38	250

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



EM865 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE MINIATURE BALL NOSE

► High precision milling in medical, optical, electronics and aerospace industrials.
 ► Excellent performance at dry cutting conditon.
 ► Excellent performance on hardened steel.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.01)	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
		Metric	Inch			
93424	RO.30	0.6	.0236	3	1.1	40
93425	RO.35	0.7	.0276	3	1.5	40
93426	RO.40	0.8	.0315	3	2.0	40
93427	RO.45	0.9	.0354	3	2.2	40
93428	RO.50	1.0	.0394	3	2.5	40
93429	RO.55	1.1	.0433	3	3.0	40
93430	RO.60	1.2	.0472	3	3.0	40
93431	RO.65	1.3	.0512	3	3.5	40
93432	RO.70	1.4	.0551	3	3.5	40
93433	RO.75	1.5	.0591	3	4.0	40

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							




EM868 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE 15° HELIX STUB CUT LENGTH BALL NOSE for OVER HRc55

HRc55 ~ HRc70

- Suitable for HRc55~HRc70 high hardened materials.
- Strong cutting edges and higher tool rigidity.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.01)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
EM868010	R0.5	1.0	.0394	4	1	2.2	50	0.95
EM868901	R0.5	1.0	.0394	6	1	2.2	50	0.95
EM868012	R0.6	1.2	.0472	4	1.2	2.6	50	1.1
EM868015	R0.75	1.5	.0591	4	1.5	3	50	1.4
EM868020	R1.0	2.0	.0787	6	2	4	50	1.9
EM868030	R1.5	3.0	.1181	6	3	6	60	2.9
EM868040	R2.0	4.0	.1575	6	4	8	70	3.9
EM868050	R2.5	5.0	.1969	6	5	10	80	4.9
EM868060	R3.0	6.0	.2362	6	6	12	90	5.9
EM868070	R3.5	7.0	.2756	8	7	14	90	6.9
EM868080	R4.0	8.0	.3150	8	8	16	100	7.9
EM868090	R4.5	9.0	.3543	10	9	18	100	8.9
EM868100	R5.0	10.0	.3937	10	10	20	100	9.9
EM868120	R6.0	12.0	.4724	12	12	24	110	11.9
EM868140	R7.0	14.0	.5512	14	14	28	110	13.8
EM868160	R8.0	16.0	.6299	16	16	32	140	15.8
EM868180	R9.0	18.0	.7087	18	18	36	140	17.8
EM868200	R10.0	20.0	.7874	20	20	40	160	19.8
EM868250	R12.5	25.0	.9843	25	25	50	180	24.8

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
			○	◎	◎									



EM902 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE with TAPER NECK

- High efficiency milling is possible in deep slotting with projection of the end mill being long.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.01)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Under Neck Parallel Length L4	Length Below Shank L3	Overall Length L2	Neck Diameter D3	Neck Taper Angle θ
		Metric D1	Inch							
EM902010	R0.5	1.0	.0394	6	2	4	23	60	2.0	1° 30'
EM902901	R0.5	1.0	.0394	6	2	4	23	60	4.3	5°
EM902902	R0.5	1.0	.0394	6	2	4	42	80	5.0	3°
EM902020	R1.0	2.0	.0787	6	4	6	23	60	2.9	1° 30'
EM902903	R1.0	2.0	.0787	6	4	6	23	60	5.0	5°
EM902904	R1.0	2.0	.0787	6	4	6	41	80	5.7	3°
EM902030	R1.5	3.0	.1181	6	6	8	32	70	5.6	3°
EM902905	R1.5	3.0	.1181	6	6	8	52	90	5.3	1° 30'
EM902040	R2.0	4.0	.1575	6	8	10	28	70	6.0	3°
EM902906	R2.0	4.0	.1575	6	8	10	49	90	6.0	1° 30'
EM902050	R2.5	5.0	.1969	8	10	12	41	90	8.0	3°
EM902907	R2.5	5.0	.1969	8	10	12	61	110	7.6	1° 30'
EM902060	R3.0	6.0	.2362	8	12	15	34	90	8.0	3°
EM902908	R3.0	6.0	.2362	8	12	15	53	110	8.0	1° 30'
EM902080	R4.0	8.0	.3150	10	14	17	36	100	10.0	3°
EM902909	R4.0	8.0	.3150	10	14	17	55	120	10.0	1° 30'
EM902100	R5.0	10.0	.3937	12	18	21	40	110	12.0	3°
EM902910	R5.0	10.0	.3937	12	18	21	59	130	12.0	1° 30'
EM902120	R6.0	12.0	.4724	16	22	25	63	140	16.0	3°
EM902911	R6.0	12.0	.4724	16	22	25	83	160	15.0	1° 30'

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○										



EM669 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG LENGTH BALL NOSE (MMC-ECONOMY TYPE)

- ▶ Designed for copy milling.
- ▶ Increased feed rates.
- ▶ 15° inclination.
- ▶ Easy to regrind.



◇ Call for Availability

EDP No.	Radius of Ball Nose R (±0.01)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	lz
		Metric	Inch						
		D1							
EM669030	R1.5	3.0	.1181	6	4	30	80	2.5	1.5
EM669040	R2.0	4.0	.1575	6	5	30	80	3.3	1.5
EM669050	R2.5	5.0	.1969	6	6	43	80	4.1	2.0
EM669060	R3.0	6.0	.2362	6	7	30	100	4.7	2.0
EM669080	R4.0	8.0	.3150	8	9	36	100	6.5	3.0
EM669100	R5.0	10.0	.3937	10	11	43	100	8.2	3.0
EM669120	R6.0	12.0	.4724	12	13	52	100	9.8	3.0
EM669160	R8.0	16.0	.6299	16	15	61	150	13.4	3.0

※ ECONOMIC TYPE HAS MORE ADVANTAGE IN RESHARPENING THAN SPHERE TYPE.

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



EM673 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG LENGTH BALL NOSE (MMC-ECONOMY TYPE)

- ▶ Designed for copy milling.
- ▶ Increased feed rates.
- ▶ 15° inclination.
- ▶ Easy to regrind.



◇ Call for Availability

EDP No.	Radius of Ball Nose R (±0.01)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	lz
		Metric	Inch						
		D1							
EM673050	R2.5	5.0	.1969	6	6	43	80	4.1	2.0
EM673060	R3.0	6.0	.2362	6	7	30	100	4.7	2.0
EM673080	R4.0	8.0	.3150	8	9	36	100	6.5	3.0
EM673100	R5.0	10.0	.3937	10	11	43	100	8.2	3.0
EM673120	R6.0	12.0	.4724	12	13	52	100	9.8	3.0
EM673160	R8.0	16.0	.6299	16	15	61	150	13.4	3.0

※ ECONOMIC TYPE HAS MORE ADVANTAGE IN RESHARPENING THAN SPHERE TYPE.

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



EM863 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG LENGTH BALL NOSE (MMC-SPHERE TYPE)

- ▶ Designed for copy milling.
- ▶ Increased feed rates.
- ▶ 15° inclination.
- ▶ Sphere Angle : 250°



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.01)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
EM863030	R1.5	3.0	.1181	6	2.3	30	80	2.5
EM863040	R2.0	4.0	.1575	6	3.1	30	80	3.3
EM863050	R2.5	5.0	.1969	6	3.9	38	80	4.1
EM863060	R3.0	6.0	.2362	6	4.9	28	100	4.7
EM863080	R4.0	8.0	.3150	8	6.3	33	100	6.5
EM863100	R5.0	10.0	.3937	10	7.9	40	100	8.2
EM863120	R6.0	12.0	.4724	12	9.5	49	100	9.8
EM863160	R8.0	16.0	.6299	16	12.4	59	150	13.4

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○	○		○							



EM864 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG LENGTH BALL NOSE (MMC-SPHERE TYPE)

- ▶ Designed for copy milling.
- ▶ Increased feed rates.
- ▶ 15° inclination.
- ▶ Sphere Angle : 250°



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (0.01)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
EM864050	R2.5	5.0	.1969	6	3.9	38	80	4.1
EM864060	R3.0	6.0	.2362	6	4.9	28	100	4.7
EM864080	R4.0	8.0	.3150	8	6.3	33	100	6.5
EM864100	R5.0	10.0	.3937	10	7.9	40	100	8.2
EM864120	R6.0	12.0	.4724	12	9.5	49	100	9.8
EM864160	R8.0	16.0	.6299	16	12.4	59	150	13.4

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○	○		○							



EM832 SERIES PLAIN SHANK

CARBIDE, MULTI FLUTE 20° HELIX SHORT LENGTH FINE PITCH ROUGHING

- Designed to machine tool steel, alloy steel, mold steel and other high hardened materials.
- High velocity milling of hardened steels.
- For dry and wet milling.
- Fast chip ejection.




◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length	No. of Flute
	Metric	Inch				
EM832060	6.0	.2362	6	7	54	3
EM832070	7.0	.2756	8	8	58	3
EM832080	8.0	.3150	8	9	58	3
EM832090	9.0	.3543	10	13	66	4
EM832100	10.0	.3937	10	14	66	4
EM832120	12.0	.4724	12	16	73	4
EM832140	14.0	.5512	14	18	75	4
EM832160	16.0	.6299	16	22	82	4
EM832180	18.0	.7087	18	24	84	4
EM832200	20.0	.7874	20	26	92	4
EM832250	25.0	.9843	25	25	110	5

Tolerances according to DIN 7160 & 7161

Tolerance range in μm					
Nominal-Diameter in mm					
	from 1 to 3	over 3 to 6	over 6 to 10	over 10 to 18	over 18 to 30
h10	0 - 40	0 - 48	0 - 58	0 - 70	0 - 84
h6	0 - 6	0 - 8	0 - 9	0 - 11	0 - 13



◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○		○	○							



EM814 SERIES PLAIN SHANK

CARBIDE, MULTI FLUTE 20° HELIX LONG LENGTH FINE PITCH ROUGHING

- Designed to machine tool steel, alloy steel, mold steel and other high hardened materials.
- High velocity milling of hardened steels.
- For dry and wet milling.
- Fast chip ejection.




◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length	No. of Flute
	Metric	Inch				
EM814060	6.0	.2362	6	16	57	3
EM814070	7.0	.2756	8	16	63	3
EM814080	8.0	.3150	8	16	63	3
EM814090	9.0	.3543	10	19	72	4
EM814100	10.0	.3937	10	22	72	4
EM814120	12.0	.4724	12	26	83	4
EM814140	14.0	.5512	14	26	83	4
EM814901	14.0	.5512	16	26	83	4
EM814160	16.0	.6299	16	32	92	4
EM814180	18.0	.7087	18	32	92	4
EM814200	20.0	.7874	20	38	104	4
EM814250	25.0	.9843	25	45	121	5

Tolerances according to DIN 7160 & 7161

Tolerance range in μm					
Nominal-Diameter in mm					
	from 1 to 3	over 3 to 6	over 6 to 10	over 10 to 18	over 18 to 30
h10	0 - 40	0 - 48	0 - 58	0 - 70	0 - 84
h6	0 - 6	0 - 8	0 - 9	0 - 11	0 - 13



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○		○	○							



EM833 SERIES PLAIN SHANK

CARBIDE, 3&4 FLUTE 20° HELIX LONG LENGTH FINE PITCH ROUGHING BALL NOSE

- ▶ Designed to machine tool steel, alloy steel, mold steel and other high hardened materials.
- ▶ High velocity milling of hardened steels.
- ▶ For dry and wet milling.
- ▶ Fast chip ejection.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.02)	Mill Diameter		Shank Diameter h6	Length of Cut	Overall Length	No. of Flute
		Metric h10	Inch				
EM833060	R3.0	6.0	.2362	6	16	57	3
EM833080	R4.0	8.0	.3150	8	16	63	3
EM833100	R5.0	10.0	.3937	10	22	72	4
EM833120	R6.0	12.0	.4724	12	26	83	4
EM833140	R7.0	14.0	.5512	14	26	83	4
EM833160	R8.0	16.0	.6299	16	32	92	4
EM833180	R9.0	18.0	.7087	18	32	92	4
EM833200	R10.0	20.0	.7874	20	38	104	4

Tolerances according to DIN 7160 & 7161

Tolerance range in µm					
Nominal-Diameter in mm					
	from 1 to 3	over 3 to 6	over 6 to 10	over 10 to 18	over 18 to 30
h10	0 - 40	0 - 48	0 - 58	0 - 70	0 - 84
h6	0 - 6	0 - 8	0 - 9	0 - 11	0 - 13

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○	○	○							



EM837 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE TAPER

- ▶ Designed for milling die cavity.
- ▶ Suitable for machining tool steels, alloy steels, mold steels and other hardened materials.



◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length	Taper Angle
	Metric	Inch				
EM837913	2.0	.0787	4	6	45	30°
EM837020	2.0	.0787	4	6	45	1°
EM837901	2.0	.0787	4	6	45	2°
EM837902	2.0	.0787	4	6	45	3°
EM837914	3.0	.1181	6	10	55	30°
EM837030	3.0	.1181	6	10	55	1°
EM837903	3.0	.1181	6	10	55	2°
EM837904	3.0	.1181	6	10	55	3°
EM837915	4.0	.1575	6	15	55	30°
EM837040	4.0	.1575	6	15	55	1°
EM837905	4.0	.1575	6	15	55	2°
EM837906	4.0	.1575	6	15	55	3°
EM837916	5.0	.1969	6	15	60	30°
EM837050	5.0	.1969	6	15	60	1°
EM837907	5.0	.1969	6	15	60	2°
EM837908	5.0	.1969	6	15	60	3°
EM837917	6.0	.2362	6	20	60	30°
EM837060	6.0	.2362	6	20	60	1°
EM837909	6.0	.2362	6	20	60	2°
EM837910	6.0	.2362	8	20	65	3°
EM837918	8.0	.3150	8	25	70	30°
EM837080	8.0	.3150	8	25	70	1°
EM837911	8.0	.3150	8	25	70	2°
EM837912	8.0	.3150	10	25	75	3°

▶ We can supply various sizes and taper angles.

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance	Taper Angle Tolerance
0~-0.03	h6	±5'

◎ : Excellent ○ : Good



P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	◎	◎	◎	○		○							



EM883 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE for RIB PROCESSING

- ▶ For deep slotting & pocketing.
- ▶ For depths of 6 to 10X cutting diameter.
- ▶ Machine carbon steel, alloy steel, tool steel, die and mold steels.
- ▶ Suitable for high speed cutting and high precision machining.
- ▶ Designed with reinforced shank for higher stability and rigidity.
- ▶ Long neck design for deep machining near walls.



◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
	Metric D1	Inch					
EM883908	0.8	.0315	4	1.2	6	45	0.75
EM883909	0.8	.0315	4	1.2	8	45	0.75
EM883010	1.0	.0394	4	1.5	6	45	0.97
EM883912	1.0	.0394	4	1.5	8	45	0.95
EM883914	1.0	.0394	4	1.5	12	45	0.93
EM883915	1.2	.0472	4	1.8	8	45	1.15
EM883917	1.2	.0472	4	1.8	12	45	1.13
EM883920	1.4	.0551	4	2.1	12	45	1.33
EM883923	1.5	.0591	4	2.3	8	45	1.45
EM883924	1.5	.0591	4	2.3	10	45	1.45
EM883925	1.5	.0591	4	2.3	12	45	1.43
EM883927	1.5	.0591	4	2.3	16	50	1.41
EM883932	1.6	.0630	4	2.4	12	45	1.53
EM883946	1.8	.0709	4	2.7	12	45	1.73
EM883960	2.0	.0787	4	3.0	12	45	1.93
EM883962	2.0	.0787	4	3.0	16	50	1.91
EM883968	2.5	.0984	4	3.7	12	45	2.40
EM883970	2.5	.0984	4	3.7	16	55	2.40
EM883977	3.0	.1181	6	4.5	14	50	2.85
EM883979	3.0	.1181	6	4.5	18	55	2.85

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.015	h6

◎ : Excellent ○ : Good



P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○							



EM886 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE BALL NOSE for RIB PROCESSING

- ▶ For 3-D milling, deep slotting and pocketing.
- ▶ For depths of 6 to 10X cutting diameter.
- ▶ Machine carbon steel, alloy steel, tool steel, die and mold steels.
- ▶ Suitable for high speed cutting and high precision machining.
- ▶ Designed with reinforced shank for higher stability and rigidity.
- ▶ Long neck design for deep machining near walls.



◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.01)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
EM886006	R0.3	0.6	.0236	3	0.9	6	35	0.55
EM886008	R0.4	0.8	.0315	4	1.2	6	45	0.75
EM886901	R0.4	0.8	.0315	4	1.2	8	45	0.75
EM886010	R0.5	1.0	.0394	4	1.5	6	45	0.97
EM886902	R0.5	1.0	.0394	4	1.5	8	45	0.95
EM886904	R0.5	1.0	.0394	4	1.5	12	45	0.93
EM886012	R0.6	1.2	.0472	4	1.8	8	45	1.15
EM886905	R0.6	1.2	.0472	4	1.8	12	45	1.13
EM886014	R0.7	1.4	.0551	4	2.1	12	45	1.33
EM886015	R0.75	1.5	.0591	4	2.3	8	45	1.45
EM886906	R0.75	1.5	.0591	4	2.3	12	45	1.43
EM886907	R0.75	1.5	.0591	4	2.3	16	50	1.41
EM886016	R0.8	1.6	.0630	4	2.4	16	50	1.51
EM886018	R0.9	1.8	.0709	4	2.7	16	50	1.71
EM886020	R1.0	2.0	.0787	4	3.0	8	45	1.95
EM886909	R1.0	2.0	.0787	4	3.0	16	50	1.91
EM886910	R1.0	2.0	.0787	4	3.0	20	55	1.89
EM886030	R1.5	3.0	.1181	6	4.5	16	55	2.85
EM886911	R1.5	3.0	.1181	6	4.5	20	60	2.85
EM886040	R2.0	4.0	.1575	6	6.0	16	60	3.85
EM886912	R2.0	4.0	.1575	6	6.0	20	65	3.85

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.02	h6

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	◎	○			○							




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE FINISH - SLOTTING

EM154, EM810 SERIES

MATERIAL	P								M	
	CARBON STEELS ALLOY STEELS CAST IRON		ALLOY STEELS TOOL STEELS		HARDENED STEELS		HARDENED STEELS		STAINLESS STEELS	
HARDNESS	~ HRC30		HRc30 ~ HRc45		HRc45 ~ HRc55		HRc55 ~ HRc65			
STRENGTH	~ 1000N/mm ²		1000 ~ 1500N/mm ²		1500 ~ 2000N/mm ²		2000N/mm ² ~			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/16	11560	7.5	7560	4.7	5040	1.4			6300	3.6
1/8	8920	8.3	5560	5.5	3360	1.6	1900	1.6	4620	4.7
3/16	6300	12.6	3780	7.5	2320	2.0	1260	1.6	3160	6.3
1/4	5560	13.8	3360	8.7	2000	2.2	1100	1.6	2840	7.1
5/16	4200	15.0	2520	7.9	1680	3.0	840	1.6	2100	7.1
3/8	3260	13.0	2000	6.3	1360	2.4	680	1.4	1680	6.3
1/2	2740	11.0	1680	5.1	1160	2.2	560	1.4	1360	5.1
5/8	2200	8.7	1360	4.3	900	1.6	440	0.8	1060	4.3
3/4	1680	6.7	1060	3.2	680	1.2	320	0.8	840	3.2
1	1360	5.1	840	2.8	540	0.8	260	0.6	680	2.4




RPM = rev./min.
FEED = inch/min.

CARBIDE, 2 FLUTE LONG LENGTH FINISH - SLOTTING

EM206, EM816 SERIES

Material	P					
	CARBON STEELS ALLOY STEELS CAST IRON		ALLOY STEELS TOOL STEELS		HARDENED STEELS	
HARDNESS	~ HRC30		HRc30 ~ HRc45		HRc45 ~ HRc55	
STRENGTH	~ 1000N/mm ²		1000 ~ 1500N/mm ²		1500 ~ 2000N/mm	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
1/8	4410	2.8	3570	2.4	2200	1.2
3/16	3050	4.1	2420	3.3	1580	1.6
1/4	2630	4.9	2100	4.1	1370	2.0
5/16	2000	5.3	1580	4.1	1050	2.0
3/8	1680	5.3	1370	4.1	840	2.0
1/2	1370	4.1	1160	3.7	700	1.6
5/8	1160	3.7	890	3.0	560	1.4
3/4	840	2.8	680	2.0	420	1.0
1	610	2.0	540	1.6	330	0.7



RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE FINISH - SIDE CUTTING

EM153, EM811 SERIES

MATERIAL	P								M	
	CARBON STEELS ALLOY STEELS CAST IRON		ALLOY STEELS TOOL STEELS		HARDENED STEELS		HARDENED STEELS		STAINLESS STEELS	
HARDNESS	~ HRC30		HRc30 ~ HRc45		HRc45 ~ HRc55		HRc55 ~ HRc65			
STRENGTH	~ 1000N/mm ²		1000 ~ 1500N/mm ²		1500 ~ 2000N/mm ²		2000N/mm ² ~			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/16	11560	11.0	7560	6.7	5040	2.0			6300	5.5
1/8	8920	12.6	5560	7.9	3360	2.4	1900	2.4	4620	6.7
3/16	6300	23.6	3780	14.2	2320	2.8	1260	2.4	3160	11.8
1/4	5560	26.0	3360	16.2	2000	3.2	1100	2.4	2840	13.0
5/16	4200	28.0	2520	15.0	1680	4.3	840	2.4	2100	13.8
3/8	3260	24.0	2000	11.8	1360	3.6	680	2.0	1680	11.8
1/2	2740	20.5	1680	9.9	1160	3.2	560	2.0	1360	9.5
5/8	2200	16.2	1360	7.9	900	2.4	440	1.2	1060	7.9
3/4	1680	12.6	1060	6.3	680	1.6	320	1.2	840	5.9
1	1360	9.9	840	5.1	540	1.2	260	0.8	680	4.7




RPM = rev./min.
FEED = inch/min.

CARBIDE, 4 FLUTE LONG LENGTH FINISH - SIDE CUTTING

EM207, EM817 SERIES

MATERIAL	P							
	CARBON STEELS ALLOY STEELS CAST IRON		ALLOY STEELS TOOL STEELS		HARDENED STEELS		HARDENED STEELS	
HARDNESS	~ HRC30		HRc30 ~ HRc45		HRc45 ~ HRc55		HRc55 ~ HRc65	
STRENGTH	~ 1000N/mm ²		1000 ~ 1500N/mm ²		1500 ~ 2000N/mm ²		2000N/mm ² ~	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8	4410	4.5	3570	3.9	2200	2.2	1890	1.2
3/16	3050	7.1	2420	5.5	1580	2.8	1260	1.6
1/4	2630	8.5	2100	7.1	1370	3.5	1160	2.0
5/16	2000	9.1	1580	7.1	1050	3.5	840	2.0
3/8	1680	9.1	1370	7.1	840	3.5	670	2.0
1/2	1370	7.1	1160	6.3	700	2.8	560	1.6
5/8	1160	6.3	890	4.9	560	2.4	440	1.4
3/4	840	4.5	680	3.5	420	1.8	340	1.0
1	670	4.5	540	3.5	340	1.8	270	1.0



RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE MINIATURE - SLOTTING


EM959, EM810 SERIES

MATERIAL	P			
	ALLOY STEELS TOOL STEELS		HARDENED STEELS	
HARDNESS	HRC30 ~ HRC45		HRC45 ~ HRC55	
STRENGTH	1000 ~ 1500N/mm ²		1500 ~ 2000N/mm ²	
DIAMETER	RPM	FEED	RPM	FEED
.016	30000	7.1	23000	3.9
.031	24000	11.8	18000	5.1
.040	20000	12.6	15000	5.9
.047	16000	12.6	12000	5.9
.062	12000	11.8	9000	5.5

D < .040
Depth=0.15xD
D ≥ .040
Depth=0.25xD



D < .040
Depth=0.02xD
D ≥ .040
Depth=0.05xD





RPM = rev./min.
FEED = inch/min.

CARBIDE, 2 FLUTE CORNER RADIUS - SLOTTING

EM636, EM637, EM211 SERIES

MATERIAL	P							
	CARBON STEELS ALLOY STEELS CAST IRON		ALLOY STEELS TOOL STEELS		HARDENED STEELS		HARDENED STEELS	
HARDNESS	~ HRC30		HRC30 ~ HRC50		HRC50 ~ HRC55		HRC55 ~ HRC65	
STRENGTH	~ 1000N/mm ²		1000 ~ 1750N/mm ²		1750 ~ 2000N/mm ²		2000N/mm ² ~	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	2630	4.9	2100	4.2	1370	2.0	1160	1.4
5/16	2000	5.3	1580	4.2	1050	2.0	840	1.4
3/8	1680	5.3	1370	4.2	840	2.0	670	1.4
1/2	1370	4.2	1160	3.8	700	1.5	550	1.0



RPM = rev./min.
FEED = inch/min.






RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE CORNER RADIUS - SIDE CUTTING

EM639, EM649, EM212 SERIES

MATERIAL	P							
	CARBON STEELS ALLOY STEELS CAST IRON		ALLOY STEELS TOOL STEELS		HARDENED STEELS		HARDENED STEELS	
HARDNESS	~ HRC30		HRC30 ~ HRC50		HRC50 ~ HRC55		HRC55 ~ HRC65	
STRENGTH	~ 1000N/mm ²		1000 ~ 1750N/mm ²		1750 ~ 2000N/mm ²		2000N/mm ² ~	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	2630	8.5	2100	7.1	1370	3.3	1160	2.0
5/16	2000	9.0	1580	7.1	1050	3.3	840	2.0
3/8	1680	9.0	1370	7.1	840	3.3	670	2.0
1/2	1370	7.1	1160	6.3	700	2.8	550	1.5







RPM = rev./min.
FEED = inch/min.

CARBIDE, 4 FLUTE 45° HELIX - SIDE CUTTING

EM102 SERIES

MATERIAL	P								M	
	CARBON STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS		STAINLESS STEELS	
HARDNESS	~ HRC30		HRC30 ~ HRC45		HRC45 ~ HRC55		HRC55 ~ HRC60			
STRENGTH	~ 1000N/mm ²		1000 ~ 1500N/mm ²		1500 ~ 2000N/mm ²		2000N/mm ² ~			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/8	3010	31.5	2610	14.3	1400	5.3	1000	2.6	1600	7.7
1/2	2260	27.0	1950	12.3	1050	4.6	750	2.0	1200	6.3
5/8	1800	22.6	1560	10.1	840	4.1	600	1.7	960	5.1
3/4	1500	19.0	1300	8.5	700	3.9	500	1.6	800	4.5
7/8	1290	16.1	1120	7.6	600	3.9	430	1.6	690	4.5



RPM = rev./min.
FEED = inch/min.





RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE 45° HELIX CORNER RADIUS - SIDE CUTTING

EM103, EM905 SERIES

MATERIAL	P								M	
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS		STAINLESS STEELS	
HARDNESS	~ HRc30		HRc30 ~ HRc45		HRc45 ~ HRc55		HRc55 ~ HRc65			
STRENGTH	~ 1000N/mm ²		1000 ~ 1500N/mm ²		1500 ~ 2000N/mm ²		2000N/mm ² ~			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/8	7690	79.0	7690	48.0	5680	29.0	3840	19.0	5680	36.0
1/2	5760	79.0	5760	48.0	4260	29.0	2880	19.0	4260	36.0
5/8	4600	71.0	4600	48.0	3410	29.0	2300	19.0	3410	36.0
3/4	3850	60.0	3850	48.0	2840	29.0	1920	19.0	2840	36.0
7/8	3300	51.0	3300	48.0	2430	29.0	1650	19.0	2430	36.0







RPM = rev./min.
FEED = inch/min.

CARBIDE, 4 FLUTE 45° HELIX CORNER RADIUS - CONTOURING

EM103, EM905 SERIES

MATERIAL	P								M	
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS		STAINLESS STEELS	
HARDNESS	~ HRc30		HRc30 ~ HRc45		HRc45 ~ HRc55		HRc55 ~ HRc65			
STRENGTH	~ 1000N/mm ²		1000 ~ 1500N/mm ²		1500 ~ 2000N/mm ²		2000N/mm ² ~			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/8	7690	45.0	5680	36.0	5680	18.0	3840	11.0	5680	31.0
1/2	5760	45.0	4260	36.0	4260	18.0	2880	11.0	4260	31.0
5/8	4600	45.0	3410	36.0	3410	18.0	2300	11.0	3410	31.0
3/4	4850	45.0	2840	36.0	2840	18.0	1920	11.0	2840	31.0
7/8	3300	45.0	2430	36.0	2430	18.0	1650	11.0	2430	31.0



RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE 55° HELIX CORNER RADIUS - SIDE CUTTING

EM965 SERIES

MATERIAL	P						M	
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS		STAINLESS STEELS	
HARDNESS	HRc30 ~ HRc40		HRc40 ~ HRc50		HRc50 ~ HRc65			
STRENGTH	1000 ~ 1250N/mm ²		1250 ~ 1700N/mm ²		1500N/mm ² ~			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8	21000	32.0	13000	9.5	7300	9.5	13000	21.0
3/16	18000	56.0	11000	9.5	4800	9.5	11000	33.0
1/4	13000	66.0	7500	13.0	4200	9.5	7500	40.0
5/16	9500	61.0	6500	17.0	3200	9.5	6500	39.0
3/8	7700	48.0	5700	22.0	3850	12.0	5700	39.0
1/2	5800	48.0	4260	25.0	2900	15.0	4260	39.0
5/8	4200	48.0	3100	29.0	2100	19.0	3100	39.0







RPM = rev./min.
FEED = inch/min.

CARBIDE, 4 FLUTE 55° HELIX CORNER RADIUS - CONTOURING

EM965 SERIES

MATERIAL	P						M	
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS		STAINLESS STEELS	
HARDNESS	HRc30 ~ HRc40		HRc40 ~ HRc50		HRc50 ~ HRc65			
STRENGTH	1000 ~ 1250N/mm ²		1250 ~ 1700N/mm ²		1500N/mm ² ~			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8	21000	24	13000	6	7300	5.5	13000	18
3/16	18000	42	11000	6	4800	5.5	11000	29
1/4	13000	50	7500	8	4200	5.5	7500	35
5/16	9500	46	6500	10	3200	5.5	6500	34
3/8	7700	36	5700	12	3850	7.5	5700	34
1/2	5800	36	4260	15	2900	9.5	4260	34
5/8	4200	36	3100	18	2100	11.5	3100	34



RPM = rev./min.
FEED = inch/min.







RECOMMENDED CUTTING CONDITIONS

CARBIDE, 6&8 FLUTE 45° HELIX LONG LENGTH - SIDE CUTTING

EM208, EM812 SERIES

■ NORMAL SPEED




MATERIAL	P							
	CARBON STEELS ALLOY STEELS CAST IRON		ALLOY STEELS TOOL STEELS		HARDENED STEELS		HARDENED STEELS	
	~HRc30		HRc30 ~ HRc50		HRc50 ~ HRc55		HRc60 ~ HRc65	
STRENGTH	~1000N/mm ²		1000 ~ 1750N/mm ²		1750 ~ 2080N/mm ²		2080N/mm ² ~	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	5560	79.0	3880	54.0	1580	8.3	1100	5.1
5/16	4200	79.0	2940	54.0	1160	8.3	840	5.1
3/8	3360	79.0	2320	54.0	1000	8.3	680	5.1
1/2	2840	66.0	2000	46.0	840	7.1	560	4.4
5/8	2100	50.0	1480	35.0	640	5.1	420	2.8
3/4	1680	40.0	1160	27.0	500	4.4	320	2.4
1	1260	25.0	870	17.5	375	3.0	240	1.5



RPM = rev./min.
FEED = inch/min.

■ HIGH SPEED

MATERIAL	P					
	CARBON STEELS TOOL STEELS		HARDENED STEELS		HARDENED STEELS	
	~HRc50		HRc50 ~ HRc60		HRc60 ~	
STRENGTH	~1750N/mm ²		1750N/mm ²		1750N/mm ² ~	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
1/4	16800	240.0	8400	120.0	4200	58.0
5/16	12600	240.0	6300	120.0	3160	58.0
3/8	9980	235.0	5040	120.0	2520	58.0
1/2	8400	199.0	4200	100.0	2100	50.0
5/8	6300	149.0	3160	75.0	1580	37.0
3/4	5040	120.0	2520	58.0	1260	30.0
1	3790	75.0	1890	38.0	950	19.0



RPM = rev./min.
FEED = inch/min.






RECOMMENDED CUTTING CONDITIONS

CARBIDE, 6&8 FLUTE 45° HELIX CORNER RADIUS - SIDE CUTTING

EM668, EM835 SERIES

■ HIGH SPEED

MATERIAL	P					
	CARBON STEELS ALLOY STEELS CAST IRON		ALLOY STEELS TOOL STEELS		HARDENED STEELS	
	~HRc50		HRc50 ~ HRc60		HRc60 ~ HRc65	
STRENGTH	~1750N/mm ²		1750 ~ 2080N/mm ²		2080N/mm ² ~	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
1/4	16800	240.0	8400	120.0	4200	58.0
5/16	12600	240.0	6300	120.0	3200	58.0
3/8	10000	235.0	5000	120.0	2500	58.0
1/2	8400	200.0	4200	100.0	2100	50.0
5/8	6300	150.0	3150	75.0	1600	37.0
3/4	5000	120.0	2500	58.0	1260	30.0





RPM = rev./min.
FEED = inch/min.

CARBIDE, 6&8 FLUTE 45° HELIX EXTRA LONG LENGTH - SIDE CUTTING

EM218, EM812, EM834 SERIES

MATERIAL	P							
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS	
	~HRc40		HRc40 ~ HRc50		HRc50 ~ HRc60		HRc60 ~ HRc65	
STRENGTH	~1250N/mm ²		1250 ~ 1750N/mm ²		1750 ~ 2080N/mm ²		2080N/mm ² ~	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	2230	19.0	1670	14.0	1390	10.0	1110	8.0
5/16	1670	18.0	1250	13.0	1050	9.5	840	7.0
3/8	1330	17.0	1000	12.0	840	9.0	680	6.3
1/2	1110	16.0	840	11.0	690	8.5	560	6.0
5/8	840	13.0	630	9.0	530	6.5	420	5.0
3/4	670	11.0	500	8.0	420	6.0	320	4.7
1	540	9.5	400	6.5	340	5.0	270	3.7



RPM = rev./min.
FEED = inch/min.



RECOMMENDED CUTTING CONDITIONS


CARBIDE, 2 FLUTE BALL NOSE

EM209, EM876, EM813, EM823 SERIES

■ NORMAL SPEED

MATERIAL	P					
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS	
	~ HRC30 ~ 1000N/mm ²		HRC30 ~ HRC40 1000 ~ 1250N/mm ²		HRC45 ~ HRC65 1500N/mm ² ~	
HARDNESS STRENGTH DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
R1/64 × 1/32	15760	9.8	12720	7.8	5800	3.5
R1/32 × 1/16	15760	13.8	12140	10.6	5320	4.7
R3/64 × 3/32	14400	29.5	10700	19.3	4680	5.9
R1/16 × 1/8	13100	26.7	10000	18.1	4520	5.9
R3/32 × 3/16	9140	32.3	7300	22.8	3680	7.1
R1/8 × 1/4	7780	33.0	6300	24.8	3160	7.5
R5/32 × 5/16	5260	37.5	4420	26.0	2100	7.5
R3/16 × 3/8	4620	40.1	3780	28.0	1780	7.5
R1/4 × 1/2	3780	35.4	2940	26.0	1360	7.5
R5/16 × 5/8	2740	36.2	2320	26.0	1160	7.5
R3/8 × 3/4	2100	33.0	1900	25.0	840	7.5

ap: D1/32~D1/4 =.008"
D5/16~D3/4=.012"
ae: 0.2×D




ap: D1/32~D1/4 =.008"
D5/16~D3/4 =.012"
ae: 0.1×D

RPM = rev./min.
FEED = inch/min.

■ HIGH SPEED

MATERIAL	P			
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		HARDENED STEELS	
	~ HRC45 ~ 1500N/mm ²		HRC45 ~ HRC65 1500N/mm ² ~	
HARDNESS STRENGTH DIAMETER	RPM	FEED	RPM	FEED
R1/64 × 1/32	25000	25.6	25000	15.7
R1/32 × 1/16	23000	27.5	23000	16.9
R3/64 × 3/32	21000	34.6	19000	19.3
R1/16 × 1/8	21000	39.4	17000	20.5
R3/32 × 3/16	21000	70.9	12000	23.6
R1/8 × 1/4	21000	90.9	10500	24.8
R5/32 × 5/16	15760	111.8	7880	29.1
R3/16 × 3/8	13660	120.0	6300	33.0
R1/4 × 1/2	10500	103.5	5260	33.0
R5/16 × 5/8	8200	103.5	3780	28.0
R3/8 × 3/4	6300	99.0	2940	20.8

ap: D1/32~D1/4 =.008"
D5/16~D3/4=.012"
ae: 0.05×D



RPM = rev./min.
FEED = inch/min.



RECOMMENDED CUTTING CONDITIONS


CARBIDE, 4 FLUTE BALL NOSE

EM210, EM815, EM825 SERIES

■ NORMAL SPEED

MATERIAL	P					
	CARBON STEELS ALLOY STEELS CAST IRON		ALLOY STEELS TOOL STEELS		HARDENED STEELS	
	~ HRC30 ~ 1000N/mm ²		HRC30 ~ HRC40 1000 ~ 1250N/mm ²		HRC45 ~ HRC65 1500N/mm ² ~	
HARDNESS STRENGTH DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
R1/16 × 1/8	13100	40.1	10000	27.0	4520	8.9
R3/32 × 3/16	9140	48.5	7300	34.0	3680	10.5
R1/8 × 1/4	7780	49.5	6300	37.0	3160	11.3
R5/32 × 5/16	5260	56.0	4420	39.0	2100	11.3
R3/16 × 3/8	4620	60.0	3780	42.0	1780	11.3
R1/4 × 1/2	3780	53.0	2940	39.0	1360	11.3
R5/16 × 5/8	2740	54.5	2320	38.5	1160	11.3

ap: D1/8~D1/4 =.008"
D5/16~D5/8=.012"
ae: 0.2×D




ap: D1/8~D1/4 =.008"
D5/16~D5/8 =.012"
ae: 0.1×D

RPM = rev./min.
FEED = inch/min.

■ HIGH SPEED

MATERIAL	P			
	CARBON STEELS ALLOY STEELS CAST IRON		ALLOY STEELS TOOL STEELS	
	~ HRC45 ~ 1500N/mm ²		HRC45 ~ HRC65 1500N/mm ² ~	
HARDNESS STRENGTH DIAMETER	RPM	FEED	RPM	FEED
R1/16 × 1/8	21000	59.0	17000	30.5
R3/32 × 3/16	21000	106.3	12000	35.5
R1/8 × 1/4	21000	136.5	10500	37.0
R5/32 × 5/16	15760	167.5	7880	43.5
R3/16 × 3/8	13660	180.0	6300	49.5
R1/4 × 1/2	10500	155.5	5260	49.5
R5/16 × 5/8	8200	155.5	3780	42.0

ap: D1/8~D1/4 =.008"
D5/16~D5/8=.012"
ae: 0.05×D



RPM = rev./min.
FEED = inch/min.



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE MEDIUM LENGTH BALL NOSE


EM961, EM899 SERIES

■ NORMAL SPEED

MATERIAL	P					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS	
	HRC30 ~ HRC40		HRC45 ~ HRC50		HRC50 ~ HRC55	
HARDNESS	1000 ~ 1250N/mm ²		1500 ~ 1750N/mm ²		1750 ~ 2000N/mm ²	
STRENGTH						
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
R1/16 × 1/8	10000	18.1	12700	43.3	12300	41.3
R3/32 × 3/16	7300	22.8	9400	43.3	9050	41.3
R1/8 × 1/4	6300	24.8	8600	45.3	8250	43.3
R5/32 × 5/16	4420	26.0	7000	41.3	6700	39.4
R3/16 × 3/8	3780	28.0	6050	39.4	5800	37.8
R1/4 × 1/2	2940	26.0	5450	39.4	5200	37.8
R5/16 × 5/8	2320	26.0	4350	34.3	4150	32.7
R3/8 × 3/4	1900	25.0	3500	27.2	3300	25.6
R1/2 × 1	1520	25.0	2800	27.2	2650	25.6

ap: D1/8~D1/4 = .008"
D5/16~D1 = .012"
ae: 0.2xD

ap: D1/8 = .006"
D3/16~D5/16 = .010"
D3/8~D1 = .012"
ae: 0.1xD




RPM = rev./min.
FEED = inch/min.

■ HIGH SPEED

MATERIAL	P					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS	
	~ HRC45		HRC45 ~ HRC50		HRC50 ~ HRC55	
HARDNESS	1000 ~ 1250N/mm ²		1500 ~ 1750N/mm ²		1750 ~ 2000N/mm ²	
STRENGTH						
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
R1/16 × 1/8	21000	39.4	12700	68.9	12300	65.7
R3/32 × 3/16	21000	70.9	9400	65.0	9050	61.8
R1/8 × 1/4	21000	90.9	8600	69.0	8250	65.7
R5/32 × 5/16	15760	111.8	7000	61.0	6700	57.5
R3/16 × 3/8	13660	120.1	6050	57.1	5800	53.5
R1/4 × 1/2	10500	103.5	5450	55.9	5200	52.4
R5/16 × 5/8	8200	103.5	4350	48.4	4150	44.5
R3/8 × 3/4	6300	99.2	3500	39.4	3300	35.4
R1/2 × 1	5040	99.2	2800	39.4	2650	35.4

ap: D1/8~D1/4 = .008
D5/16~D1 = .012
ae: 0.05xD

ap: D1/8 = .006"
D3/16~D5/16 = .010"
D3/8~D1 = .012"
ae: 0.05xD



RPM = rev./min.
FEED = inch/min.



RECOMMENDED CUTTING CONDITIONS


CARBIDE, 2 FLUTE LONG REACH BALL NOSE

EM962, EM838 SERIES

■ NORMAL SPEED

MATERIAL	P					
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS	
	~ HRC30		HRC30 ~ HRC40		HRC45 ~ HRC65	
HARDNESS	~ 1000N/mm ²		1000 ~ 1250N/mm ²		1500N/mm ² ~	
STRENGTH						
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
R3/64 × 3/32	12600	16.5	9250	10.2	3870	3.5
R1/16 × 1/8	10500	21.3	8000	14.6	3620	4.7
R3/32 × 3/16	7310	26.0	5840	18.1	2940	5.5
R1/8 × 1/4	6220	26.4	5040	19.7	2530	5.9
R5/32 × 5/16	4210	29.9	3540	20.7	1680	5.9
R3/16 × 3/8	3700	32.3	3020	22.4	1420	5.9
R1/4 × 1/2	3020	28.3	2350	20.9	1090	5.9
R5/16 × 5/8	2190	29.1	1860	20.5	930	5.9
R3/8 × 3/4	1680	26.4	1520	19.7	670	5.9

ap: D3/32~D1/4 = .008"
D5/16~D3/4 = .012"
ae: 0.2xD




ap: D3/32~D1/4 = .008"
D5/16~D3/4 = .012"
ae: 0.1xD

RPM = rev./min.
FEED = inch/min.

■ HIGH SPEED

MATERIAL	P			
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		HARDENED STEELS	
	~ HRC45		HRC45 ~ HRC65	
HARDNESS	~ 1500N/mm ²		1500N/mm ² ~	
STRENGTH				
DIAMETER	RPM	FEED	RPM	FEED
R3/64 × 3/32	16800	23.2	16800	15.0
R1/16 × 1/8	16800	31.5	13600	16.5
R3/32 × 3/16	16800	56.7	9600	18.9
R1/8 × 1/4	16800	72.8	8400	19.7
R5/32 × 5/16	12610	89.4	6300	23.2
R3/16 × 3/8	10930	96.1	5040	26.4
R1/4 × 1/2	8400	82.7	4210	26.4
R5/16 × 5/8	6560	82.7	3020	22.4
R3/8 × 3/4	5040	79.5	2350	16.5

ap: D3/32~D1/4 = .008"
D5/16~D3/4 = .012"
ae: 0.05xD



RPM = rev./min.
FEED = inch/min.



RECOMMENDED CUTTING CONDITIONS


CARBIDE, 2 FLUTE BALL NOSE for OVER HRC55

EM109, EM868 SERIES

■ NORMAL SPEED

MATERIAL	P							
	HARDENED STEELS		HARDENED STEELS		HARDENED STEELS		HARDENED STEELS	
	HRC45 ~ HRC50		HRC50 ~ HRC55		HRC55 ~ HRC60		HRC60 ~ HRC70	
HARDNESS	1500 ~ 1750N/mm ²		1750 ~ 2000N/mm ²		2000 ~ 2080N/mm ²		2080N/mm ² ~	
STRENGTH								
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
R1/16 × 1/8	12700	43.3	12300	41.3	11800	39.4	8400	26.0
R3/32 × 3/16	9400	43.3	9050	41.3	8600	37.4	5600	26.8
R1/8 × 1/4	8600	45.3	8250	43.3	7850	37.4	4850	27.6
R5/32 × 5/16	7000	41.3	6700	39.4	6350	37.4	3800	25.6
R3/16 × 3/8	6050	39.4	5800	37.8	5450	35.4	3200	24.4
R1/4 × 1/2	5450	39.4	5200	37.8	4900	35.4	2750	24.0
R5/16 × 5/8	4350	34.3	4150	32.7	3900	32.3	2150	10.4
R3/8 × 3/4	3500	27.2	3300	25.6	3150	24.8	1700	8.7
R1/2 × 1	2800	27.2	2650	25.6	2520	24.8	1360	8.7

ap: D1/8 = .006"
D3/16 ~ D5/16 = .010"
D3/8 ~ D1 = .012"
ae: 0.1xD




RPM = rev./min.
FEED = inch/min.

■ HIGH SPEED

MATERIAL	P					
	HARDENED STEELS		HARDENED STEELS		HARDENED STEELS	
	HRC45 ~ HRC50		HRC50 ~ HRC55		HRC55 ~ HRC70	
HARDNESS	1500 ~ 1750N/mm ²		1750 ~ 2000N/mm ²		2000 ~ 2080N/mm ²	
STRENGTH						
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
R1/16 × 1/8	12700	68.9	12300	65.7	11800	33.9
R3/32 × 3/16	9400	65.0	9050	61.8	8600	29.5
R1/8 × 1/4	8600	68.9	8250	65.7	7850	27.6
R5/32 × 5/16	7000	61.0	6700	57.5	6350	25.6
R3/16 × 3/8	6050	57.1	5800	53.5	5450	24.4
R1/4 × 1/2	5450	55.9	5200	52.4	4900	24.0
R5/16 × 5/8	4350	48.4	4150	44.5	3900	10.4
R3/8 × 3/4	3500	39.4	3300	35.4	3150	8.7
R1/2 × 1	2800	39.4	2640	35.4	2520	8.7

ap: D1/8 = .006"
D3/16~D5/16 = .010"
D3/8~D1 = .012"
ae: 0.05xD



RPM = rev./min.
FEED = inch/min.



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE BALL NOSE with TAPER NECK


EM963, EM902 SERIES

■ NORMAL SPEED

MATERIAL	P					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS	
	HRC30 ~ HRC40		HRC45 ~ HRC50		HRC50 ~ HRC55	
HARDNESS	1000 ~ 1250N/mm ²		1250 ~ 1750N/mm ²		1750 ~ 2000N/mm ²	
STRENGTH						
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
R1/32 × 1/16	9700	8.3	13800	19.9	13600	17.9
R1/16 × 1/8	8000	14.6	10200	34.6	9800	33.5
R3/32 × 3/16	5840	18.1	7500	34.6	7200	33.5
R1/8 × 1/4	5040	19.7	6900	36.2	6500	34.6
R5/32 × 5/16	3540	20.9	5600	33.1	5300	31.5
R3/16 × 3/8	3020	22.4	4850	31.5	4650	30.3
R1/4 × 1/2	2350	20.9	4350	31.5	4150	30.3

ap: D1/16~D1/4 = .008"
D5/16~D1/2 = .012"
ae: 0.2xD

ap: D1/16~D1/8 = 0.05xD
D3/16~D5/16 = .010"
D3/8~D1/2 = .012"
ae: 0.1xD




RPM = rev./min.
FEED = inch/min.

■ HIGH SPEED

MATERIAL	P					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS	
	~ HRC45		HRC45 ~ HRC50		HRC50 ~ HRC55	
HARDNESS	1500N/mm ²		1250 ~ 1750N/mm ²		1750 ~ 2000N/mm ²	
STRENGTH						
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
R1/32 × 1/16	18400	21.9	13800	28.9	13600	30.1
R1/16 × 1/8	16800	31.5	10200	55.1	9800	51.2
R3/32 × 3/16	16800	56.7	7500	52.0	7200	49.2
R1/8 × 1/4	16800	72.8	6900	55.1	6500	53.1
R5/32 × 5/16	12600	89.4	5600	49.2	5300	45.3
R3/16 × 3/8	10930	96.1	4850	45.3	4650	43.3
R1/4 × 1/2	8400	82.7	4350	44.5	4150	41.3

ap: D1/16~D1/4 = .008"
D5/16~D1/2 = .012"
ae: 0.05xD

ap: D1/16~D1/8 = 0.05xD
D3/16~D5/16 = .010"
D3/8~D1/2 = .012"
ae: 0.05xD



RPM = rev./min.
FEED = inch/min.



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE BALL NOSE with PENCIL NECK


EM979 SERIES

■ NORMAL SPEED

MATERIAL	P					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS	
	HRC30 ~ HRC40		HRC45 ~ HRC50		HRC50 ~ HRC55	
HARDNESS	1000 ~ 1250N/mm ²		1250 ~ 1750N/mm ²		1750 ~ 2000N/mm ²	
STRENGTH						
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
R3/32 × 3/16	4670	14.5	6000	27.7	5760	26.8
R1/8 × 1/4	4030	15.8	5520	29.0	5200	27.7
R5/32 × 5/16	2830	16.7	4480	26.5	4240	25.2
R3/16 × 3/8	2420	17.9	3880	25.2	3720	24.2
R1/4 × 1/2	1880	16.7	3480	25.2	3320	24.2

ap: D3/16~D1/4 = .008"
D5/16~D1/2 = .012"
ae: 0.2xD

ap: D3/16~D5/16 = .010"
D3/8~D1/2 = .012"
ae: 0.1xD




RPM = rev./min.
FEED = inch/min.

■ HIGH SPEED

MATERIAL	P					
	ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS	
	~ HRC45		HRC45 ~ HRC50		HRC50 ~ HRC55	
HARDNESS	1500N/mm ²		1250 ~ 1750N/mm ²		1750 ~ 2000N/mm ²	
STRENGTH						
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
R3/32 × 3/16	13440	45.4	6000	41.6	5760	39.4
R1/8 × 1/4	13440	58.2	5520	44.1	5200	42.5
R5/32 × 5/16	10080	71.5	4480	39.4	4240	36.2
R3/16 × 3/8	8740	76.9	3880	36.3	3720	34.6
R1/4 × 1/2	6720	66.2	3480	35.6	3320	33.0

ap: D3/16~D1/4 = .008"
D5/16~D1/2 = .012"
ae: 0.05xD

ap: D3/16~D5/16 = .010"
D3/8~D1/2 = .012"
ae: 0.05xD




RPM = rev./min.
FEED = inch/min.



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE BALL NOSE - MMC



RECOMMENDED CUTTING CONDITIONS

▶ ap=0.02xD1
▶ ae=0.05xD1

EM084, EM096, EM669, EM863 SERIES

■ NORMAL SPEED

MATERIAL	P					
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOYED STEELS HEAT RESISTANT STEELS		HARDENED STEELS	
	~HRC30		HRC30 ~ HRC40		HRC45 ~ HRC65	
HARDNESS	~1000N/mm ²		1000 ~ 1250N/mm ²		1500N/mm ²	
STRENGTH						
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
R1/16 × 1/8	35000	110.2	33000	102.4	12000	35.4
R5/64 × 5/32	26000	90.6	25000	86.6	9000	31.5
R3/32 × 3/16	21000	82.7	20000	78.7	7000	27.6
R1/8 × 1/4	17000	74.8	16000	70.9	6000	25.6
R5/32 × 5/16	13000	66.9	12000	63.0	4500	21.7
R3/16 × 3/8	10500	57.1	10000	55.1	3500	19.7
R1/4 × 1/2	9000	55.1	8000	51.2	3000	17.7
R5/16 × 5/8	6000	47.2	5500	43.3	2000	15.8

RPM = rev./min.
FEED = inch/min.

■ HIGH SPEED


MATERIAL	P					
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOYED STEELS HEAT RESISTANT STEELS		HARDENED STEELS	
	~HRC30		HRC30 ~ HRC40		HRC45 ~ HRC65	
HARDNESS	~1000N/mm ²		1000 ~ 1250N/mm ²		1500N/mm ²	
STRENGTH						
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
R1/16 × 1/8	47000	145.7	44000	137.8	17000	55.1
R5/64 × 5/32	35000	126.0	33000	118.1	13000	47.2
R3/32 × 3/16	28000	110.2	27000	102.4	10000	43.3
R1/8 × 1/4	23000	102.4	22000	94.5	8000	37.4
R5/32 × 5/16	18000	90.6	17000	82.7	6000	33.5
R3/16 × 3/8	14000	78.7	13000	74.8	5000	29.5
R1/4 × 1/2	12000	70.9	11000	70.9	4000	27.6
R5/16 × 5/8	9000	63.0	8000	59.1	3300	23.6

RPM = rev./min.
FEED = inch/min.



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE BALL NOSE - MMC



RECOMMENDED CUTTING CONDITIONS

▶ $ap=0.02 \times D1$
▶ $ae=0.05 \times D1$

EM093, EM097, EM673, EM864 SERIES

■ NORMAL SPEED

MATERIAL	P					
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOYED STEELS HEAT RESISTANT STEELS		HARDENED STEELS	
	~HRc30		HRc30 ~ HRc40		HRc45 ~ HRc65	
STRENGTH	~1000N/mm ²		1000 ~ 1250N/mm ²		1500N/mm ²	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
R3/32 × 3/16	21000	157.5	20000	157.5	7000	55.1
R1/8 × 1/4	17000	157.5	16000	137.8	6000	51.2
R5/32 × 5/16	13000	137.8	12000	118.1	4500	43.3
R3/16 × 3/8	10500	118.1	10000	98.4	3500	39.4
R1/4 × 1/2	9000	110.2	8000	98.4	3000	37.4
R5/16 × 5/8	6000	110.2	5500	86.6	2000	31.5

RPM = rev./min.
FEED = inch/min.

■ HIGH SPEED

MATERIAL	P					
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOYED STEELS HEAT RESISTANT STEELS		HARDENED STEELS	
	~HRc30		HRc30 ~ HRc40		HRc45 ~ HRc65	
STRENGTH	~1000N/mm ²		1000 ~ 1250N/mm ²		1500N/mm ²	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
R3/32 × 3/16	28000	220.5	27000	208.7	11000	82.7
R1/8 × 1/4	23000	200.1	22000	192.9	9000	74.8
R5/32 × 5/16	18000	181.1	17000	169.3	7000	66.9
R3/16 × 3/8	14000	153.5	13000	145.7	5000	55.1
R1/4 × 1/2	12000	145.7	11000	137.8	4500	51.2
R5/16 × 5/8	9000	122.0	8000	118.1	3300	43.3

RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE MINIATURE BALL NOSE

EM960, EM865 SERIES

MATERIAL	P			
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		HARDENED STEELS	
	HRc30 ~ HRc45		HRc45 ~ HRc55	
STRENGTH	1000 ~ 1500N/mm ²		1500 ~ 2000N/mm ²	
DIAMETER	RPM	FEED	RPM	FEED
R.012 × .024	30000	23.6	30000	11.8
R.0155 × .031	27000	25.6	27000	15.0
R.020 × .040	25000	25.6	25000	15.7
R.0235 × .047	24000	26.4	24000	16.5
R.031 × .062	23000	27.6	23000	16.9





RPM = rev./min.
FEED = inch/min.

CARBIDE, MULTI FLUTE ROUGHING - SIDE CUTTING

EM666, EM156, EM832, EM814 SERIES

MATERIAL	P									
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS	
	~HRc30		HRc30 ~ HRc38		HRc38 ~ HRc45		HRc45 ~ HRc55		HRc55 ~ HRc65	
STRENGTH	~1000N/mm ²		1000 ~ 1200N/mm ²		1200 ~ 1400N/mm ²		1400 ~ 2000N/mm ²		2000N/mm ² ~	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	15600	91.4	12400	33.1	8400	22.5	3400	10.3	2400	7.5
5/16	11600	91.4	9200	33.1	6300	22.5	2400	9.5	1800	7.1
3/8	9200	91.4	7600	33.1	5100	22.5	2000	11.4	1300	7.5
1/2	8000	94.5	6000	31.5	4200	22.5	1680	10.3	1200	7.5
5/8	6000	94.5	4800	29.9	3300	20.1	1200	6.3	800	4.4
3/4	5200	91.4	4400	28.4	2700	16.6	1100	5.9	700	4.0
1	4800	85.1	3600	22.1	2400	14.2	1000	5.9	660	4.0



RPM = rev./min.
FEED = inch/min.





RECOMMENDED CUTTING CONDITIONS

CARBIDE, MULTI FLUTE ROUGHING BALL NOSE - SIDE CUTTING

EM662, EM833 SERIES

MATERIAL	P									
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS	
HARDNESS	~ HRC30		HRC30 ~ HRC38		HRC38 ~ HRC45		HRC45 ~ HRC55		HRC55 ~ HRC65	
STRENGTH	~ 1000N/mm ²		1000 ~ 1200N/mm ²		1200 ~ 1400N/mm ²		1400 ~ 2000N/mm ²		2000N/mm ² ~	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
R1/8 × 1/4	15600	91.3	12400	33.0	8400	22.4	3400	10.2	2400	7.5
R5/32 × 5/16	11600	91.3	9200	33.0	6300	22.4	2400	9.4	1800	7.1
R3/16 × 3/8	9200	91.3	7600	33.0	5100	22.4	2000	11.4	1300	7.5
R1/4 × 1/2	8000	94.5	6000	31.5	4200	22.4	1680	10.2	1200	7.5
R5/16 × 5/8	6000	94.5	4800	29.9	3300	20.1	1200	6.3	800	4.3
R3/8 × 3/4	4800	85.0	3600	22.0	2400	14.1	1000	5.9	660	3.9




RPM = rev./min.
FEED = inch/min.

CARBIDE, 2 FLUTE FINISH for RIB PROCESSING

EM966, EM883 SERIES

MATERIAL	P								
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON			ALLOY STEELS HEAT RESISTANT STEELS			HARDENED STEELS		
HARDNESS	~ HRC30			HRC30 ~ HRC45			HRC45 ~ HRC55		
STRENGTH	~ 1000N/mm ²			1000 ~ 1500N/mm ²			1500 ~ 2000N/mm ²		
DIAMETER	RPM	FEED	ap	RPM	FEED	ap	RPM	FEED	ap
1/32	27000~35000	7.5~16.5	.0006~.0014	19500~24500	2.4~9.5	.0006~.0014	12500~14800	1.4~3.7	.0003~.0006
3/64	18500~23500	7.5~23.6	.0022~.0039	13000~16500	3.7~11.8	.0022~.0039	8300~10500	2.0~3.9	.0004~.0009
1/16	14000~18000	7.5~23.6	.0030~.0057	10200~12800	3.7~11.8	.0030~.0057	6400~8000	2.0~3.9	.0006~.0012
5/64	12000~14500	7.5~23.6	.0035~.0071	8300~10500	3.7~11.8	.0035~.0071	5300~6600	2.0~3.9	.0007~.0014
3/32	9500~12000	7.5~23.6	.0044~.0093	6700~8500	3.7~11.8	.0044~.0093	4300~5300	2.0~3.9	.0009~.0018
1/8	8000~10000	7.5~23.6	.0053~.0106	5500~7000	3.7~11.8	.0053~.0106	3500~4400	2.0~3.9	.0011~.0022

(Depth of Cut per one pass)



RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE BALL NOSE for RIB PROCESSING

EM967, EM886 SERIES

MATERIAL	P								
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON			ALLOY STEELS HEAT RESISTANT STEELS			HARDENED STEELS		
HARDNESS	~ HRC30			HRC30 ~ HRC45			HRC45 ~ HRC55		
STRENGTH	~ 1000N/mm ²			1000 ~ 1500N/mm ²			1500 ~ 2000N/mm ²		
DIAMETER	RPM	FEED	ap	RPM	FEED	ap	RPM	FEED	ap
R1/64 × 1/32	27000~35000	7.5~16.5	.0006~.0014	19500~24500	2.4~9.5	.0006~.0014	12500~14800	1.4~3.7	.0003~.0006
R.0234 × 3/64	18500~23500	7.5~23.6	.0022~.0039	13000~16500	3.7~11.8	.0022~.0039	8300~10500	2.0~3.9	.0004~.0009
R1/32 × 1/16	14000~18000	7.5~23.6	.0030~.0057	10200~12800	3.7~11.8	.0030~.0057	6400~8000	2.0~3.9	.0006~.0012
R.0391 × 5/64	12000~14500	7.5~23.6	.0035~.0071	8300~10500	3.7~11.8	.0035~.0071	5300~6600	2.0~3.9	.0007~.0014
R3/64 × 3/32	9500~12000	7.5~23.6	.0044~.0093	6700~8500	3.7~11.8	.0044~.0093	4300~5300	2.0~3.9	.0009~.0018
R1/16 × 1/8	8000~10000	7.5~23.6	.0053~.0106	5500~7000	3.7~11.8	.0053~.0106	3500~4400	2.0~3.9	.0011~.0022

(Depth of Cut per one pass)




RPM = rev./min.
FEED = inch/min.

CARBIDE, 2 FLUTE TAPER - SIDE CUTTING

EM837 SERIES

MATERIAL	P			
	NON-ALLOYED STEELS ALLOY STEELS		ALLOY STEELS HEAT RESISTANT STEELS	
HARDNESS	~ HRC30		HRC30 ~ HRC45	
STRENGTH	~ 1000N/mm ²		1000 ~ 1500N/mm ²	
DIAMETER	RPM	FEED	RPM	FEED
2.0	8400	6.7	6300	4.9
3.0	4410	4.7	3570	3.9
4.0	3570	5.5	2840	4.5
5.0	3050	7.1	2410	5.7
6.0	2630	8.3	2100	6.7
8.0	2000	9.8	1580	7.1



RPM = rev./min.
FEED = inch/min.






RECOMMENDED CUTTING CONDITIONS

CARBIDE, 3 FLUTE - SLOTTING

EM895 SERIES

MATERIAL	P								M	
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS		STAINLESS STEELS	
HARDNESS	~ HRC30		HRC30 ~ HRC45		HRC45 ~ HRC55		HRC55 ~ HRC65			
STRENGTH	~ 1000N/mm ²		1000 ~ 1500N/mm ²		1500 ~ 2000N/mm ²		2000N/mm ² ~			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
2.0	11560	6.7	7560	4.3	5040	1.2			6300	3.2
3.0	8920	7.5	5560	5.1	3360	1.4	1900	1.6	4620	4.3
4.0	7560	10.6	4620	6.3	2940	1.4	1480	1.4	3880	5.1
5.0	6300	11.0	3780	6.7	2320	1.8	1260	1.4	3160	5.5
6.0	5560	12.2	3360	7.9	2000	2.0	1100	1.4	2840	6.3
8.0	4200	13.4	2520	7.1	1680	2.6	840	1.4	2100	6.3
10.0	3260	11.8	2000	5.5	1360	2.2	680	1.2	1680	5.7
12.0	2740	9.8	1680	4.7	1160	2.0	560	1.2	1360	4.7
16.0	2200	7.9	1360	3.9	900	1.4	440	0.8	1060	3.9
18.0	1940	6.9	1210	3.4	790	1.2	380	0.8	950	3.4
20.0	1680	5.9	1060	2.8	680	1.0	320	0.8	840	2.8




RPM = rev./min. FEED = inch/min.

CARBIDE, 3 FLUTE - SIDE CUTTING

EM895 SERIES

MATERIAL	P								M	
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS		STAINLESS STEELS	
HARDNESS	~ HRC30		HRC30 ~ HRC45		HRC45 ~ HRC55		HRC55 ~ HRC65			
STRENGTH	~ 1000N/mm ²		1000 ~ 1500N/mm ²		1500 ~ 2000N/mm ²		2000N/mm ² ~			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
2.0	11560	8.3	7560	5.5	5040	1.2			6300	4.5
3.0	8920	9.5	5560	5.9	3360	1.6	1900	1.8	4620	4.9
4.0	7560	16.9	4620	10.2	2940	1.8	1480	1.8	3880	8.3
5.0	6300	17.7	3780	10.6	2320	2.2	1260	1.8	3160	9.1
6.0	5560	19.7	3360	12.2	2000	2.4	1100	1.8	2840	9.8
8.0	4200	20.9	2520	11.4	1680	3.2	840	1.8	2100	10.4
10.0	3260	18.1	2000	9.1	1360	2.8	680	1.4	1680	9.1
12.0	2740	15.4	1680	7.5	1160	2.4	560	1.4	1360	7.1
16.0	2200	12.2	1360	5.9	900	1.8	440	0.8	1060	5.9
18.0	1940	11.0	1210	5.3	790	1.4	380	0.8	950	5.1
20.0	1680	9.5	1060	4.7	680	1.2	320	0.8	840	4.5



RPM = rev./min. FEED = inch/min.





RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE LONG CORNER RADIUS - SLOTTING

EM818 SERIES

MATERIAL	P							
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS	
HARDNESS	~ HRC30		HRC30 ~ HRC45		HRC45 ~ HRC55		HRC55 ~ HRC65	
STRENGTH	~ 1000N/mm ²		1000 ~ 1500N/mm ²		1500 ~ 2000N/mm ²		2000N/mm ² ~	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3.0	6620	5.5	4280	2.8	2640	1.4	1870	0.7
4.0	5360	6.7	3410	3.4	2150	1.6	1470	0.8
5.0	4580	8.3	2900	3.9	1900	2.0	1260	1.0
6.0	3950	9.8	2520	4.9	1640	2.4	1160	1.4
8.0	3000	10.6	1900	4.9	1260	2.4	840	1.4
10.0	2520	10.6	1640	4.9	1010	2.4	670	1.4
12.0	2060	8.3	1390	4.5	840	2.0	550	1.0
16.0	1740	7.5	1070	3.5	670	1.6	440	0.8
20.0	1260	5.5	820	2.4	500	1.2	340	0.6






RPM = rev./min.
FEED = inch/min.

CARBIDE, 4 FLUTE LONG CORNER RADIUS - SIDE CUTTING

EM819 SERIES

MATERIAL	P							
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS	
HARDNESS	~ HRC30		HRC30 ~ HRC45		HRC45 ~ HRC55		HRC55 ~ HRC65	
STRENGTH	~ 1000N/mm ²		1000 ~ 1500N/mm ²		1500 ~ 2000N/mm ²		2000N/mm ² ~	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3.0	6620	6.7	4280	5.1	2640	2.6	1870	1.2
4.0	5360	8.3	3410	5.9	2150	2.8	1470	1.4
5.0	4580	8.5	2900	7.1	1900	3.4	1260	1.6
6.0	3950	8.5	2520	7.1	1640	3.4	1160	2.0
8.0	3000	9.1	1900	7.1	1260	3.4	840	2.0
10.0	2520	9.1	1640	7.1	1010	3.4	670	2.0
12.0	2060	7.1	1390	6.3	840	2.8	550	1.6
16.0	1740	6.3	1070	4.9	670	2.4	440	1.4
20.0	1260	4.5	820	3.5	500	1.8	340	1.0



RPM = rev./min.
FEED = inch/min.

CARBIDE

HSS

CBN
END MILLS

i-Xmill
END MILLS

i-SMART
MODULAR
TYPE END MILLS

X5070
END MILLS

4G MILL
END MILLS

X-POWER
END MILLS

JET-POWER
END MILLS

TitaNox
-POWER
END MILLS

V7 PLUS A
END MILLS

V7 MILL INOX
END MILLS

ALU-POWER
HPC
END MILLS

ALU-POWER
END MILLS

D-POWER
GRAPHITE
END MILLS

D-POWER
CFRP
END MILLS

ROUTERS
CFRP

STANDARD
CARBIDE
END MILLS

ONLY ONE
COATED PM60
END MILLS

SINE -POWER
END MILLS

TANK-POWER
END MILLS

STANDARD
COBALT & HSS
END MILLS

TECHNICAL
DATA




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE STUB CORNER RADIUS - SIDE CUTTING

EM839 SERIES

MATERIAL	P							
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS	
HARDNESS	~ HRC30		HRc30 ~ HRc45		HRc45 ~ HRc55		HRc55 ~ HRc65	
STRENGTH	~ 1000N/mm ²		1000 ~ 1500N/mm ²		1500 ~ 2000N/mm ²		2000N/mm ² ~	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
2.0	13870	13.4	9070	8.1	6050	2.4		
2.5	12290	14.2	7870	8.7	5040	2.6		
3.0	10700	15.2	6670	9.5	4030	2.8	2280	2.8
3.5	9890	21.1	6100	13.0	3780	2.8	2030	2.8
4.0	9070	27.0	5540	16.5	3530	2.8	1780	2.8
5.0	7560	28.4	4540	16.9	2780	3.4	1510	2.8
6.0	6670	31.1	4030	19.3	2400	3.7	1320	2.8
8.0	5040	33.5	3020	17.9	2020	5.1	1010	2.8
10.0	3910	28.7	2400	14.2	1630	4.3	820	2.4
12.0	3290	24.6	2020	11.8	1390	3.7	670	2.4
16.0	2640	19.3	1630	9.5	1080	2.8	530	1.4




RPM = rev./min.
FEED = inch/min.

CARBIDE, 6 FLUTE STUB CORNER RADIUS - SIDE CUTTING

EM897 SERIES

MATERIAL	P							
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALLOY STEELS HEAT RESISTANT STEELS		HARDENED STEELS		HARDENED STEELS	
HARDNESS	~ HRC30		HRc30 ~ HRc45		HRc45 ~ HRc55		HRc55 ~ HRc65	
STRENGTH	~ 1000N/mm ²		1000 ~ 1500N/mm ²		1500 ~ 2000N/mm ²		2000N/mm ² ~	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
6.0	6670	31.1	4030	19.3	2400	3.7	1320	2.8
8.0	5040	33.5	3020	17.9	2020	5.1	1010	2.8
10.0	3910	28.7	2400	14.2	1630	4.3	820	2.4
12.0	3290	24.6	2020	11.8	1390	3.7	670	2.4



RPM = rev./min.
FEED = inch/min.

CARBIDE & HSS



Being the best through innovation



JET-POWER END MILLS

- Exotic materials like Stainless Steels, Nickel alloys and Titanium

SELECTION GUIDE

SOLID CARBIDE & HSS JET-POWER END MILLS

◎ : Excellent ○ : Good








ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	

INCH

EH108		CARBIDE, 3&4 FLUTE 50° HELIX REGULAR LENGTH	◆	D1/8	D1	938
EE882		YPM, 6 FLUTE 35° HELIX REGULAR LENGTH	◆	D3/4	D1-1/2	939
E5075 E5105		CARBIDE, 3 FLUTE 35° HELIX STUB LENGTH CORNER RADIUS - "HOSS"	◆	D1/8	D1	940
E5074 E5104		CARBIDE, 3 FLUTE 35° HELIX REGULAR LENGTH CORNER RADIUS - "HOSS"	◆	D1/8	D1	941
EH094		CARBIDE, MULTI FLUTE STUB LENGTH FINE PITCH ROUGHING	◆	D1/4	D1	942
EH095		CARBIDE, MULTI FLUTE LONG LENGTH FINE PITCH ROUGHING	◆	D1/4	D1	943
EH969		CARBIDE, MULTI FLUTE 45° HELIX LONG LENGTH FINE PITCH ROUGHING	◆	D3/16	D1	944
EH970		CARBIDE, MULTI FLUTE 45° HELIX LONG REACH FINE PITCH ROUGHING	◆	D1/4	D3/4	945

◆ U.S.A Stock

METRIC

EH830		CARBIDE, 3&4 FLUTE 50° HELIX LONG LENGTH	◇	D6.0	D25.0	946
EE515		PREMIUM HSS-PM, 4&6 FLUTE SHORT LENGTH	◇	D3.0	D25.0	947
EH852		CARBIDE, MULTI FLUTE SHORT FINE PITCH ROUGHING	◇	D6.0	D25.0	948
EH831		CARBIDE, MULTI FLUTE LONG LENGTH FINE PITCH ROUGHING	◇	D6.0	D25.0	949
EH917		CARBIDE, MULTI FLUTE 45° HELIX SHORT LENGTH FINE PITCH ROUGHING	◇	D6.0	D20.0	950
EH919		CARBIDE, MULTI FLUTE 45° HELIX LONG LENGTH FINE PITCH ROUGHING	◇	D4.0	D25.0	951
EH921		CARBIDE, MULTI FLUTE 45° HELIX LONG REACH FINE PITCH ROUGHING	◇	D6.0	D20.0	952

RECOMMENDED CUTTING CONDITIONS

953

◇ Call for Availability

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									

○	◎	◎	○			◎	○						○	○
○	◎	◎	○			◎							◎	○
○	◎	○				◎	○							
○	◎	○				◎	○							
○	◎	◎	○			◎							◎	○
○	◎	◎	○			◎							◎	○
○	◎	◎	○			◎							◎	○
○	◎	◎	○			◎							◎	○


○	◎	◎	○			◎							◎	○
○	◎	◎	○			◎							◎	○
○	◎	◎	○			◎							◎	○
○	◎	◎	○			◎							◎	○
○	◎	◎	○			◎							◎	○
○	◎	◎	○			◎							◎	○
○	◎	◎	○			◎							◎	○



EH108 SERIES PLAIN SHANK FLAT SHANK

CARBIDE, 3&4 FLUTE 50° HELIX REGULAR LENGTH

- ▶ Suitable for low hardness materials (under HRc 45), alloy steels, tool steels, carbon steels, prehardened steels, stainless steels, inconel, nimonic, etc.
- ▶ Corner Protection against chipping.




◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
PLAIN	FLAT					
95063	—	1/8	1/8	1/2	1-1/2	3
95064	—	3/16	3/16	5/8	2	3
95065	—	1/4	1/4	3/4	2-1/2	3
95066	—	5/16	5/16	13/16	2-1/2	3
—	95067	3/8	3/8	1	2-1/2	3
95115	—	7/16	7/16	1	2-3/4	3
—	95068	1/2	1/2	1	3	3
—	95069	5/8	5/8	1-1/4	3-1/2	3
—	95070	3/4	3/4	1-1/2	4	4
—	95071	1	1	1-1/2	4	4

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~- .0012	0~- .0003



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	○			◎	○						○	○



EE882 SERIES FLAT SHANK

YPM, 6 FLUTE 35° HELIX REGULAR LENGTH

- ▶ Designed to machine low hardness materials (under HRc45), alloy steels, tool steels, carbon steels, prehardened steels, stainless steel, inconel, nimonic, etc.
- ▶ High velocity milling operation and good surface finishes.



◆ U.S.A Stock

Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
95094	3/4	3/4	1-5/8	3-7/8
95095	7/8	7/8	1-7/8	4-1/8
95096	1	1	2	4-1/2
95097	1-1/4	1-1/4	2	4-1/2
95098	1-1/2	1-1/4	2	4-1/2

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~+.0010	0~- .0003

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	○			◎							◎	○



E5075 SERIES PLAIN SHANK Ø1/8-Ø5/16
E5105 SERIES FLAT SHANK Ø11/32-Ø1

CARBIDE, 3 FLUTE 35° HELIX STUB LENGTH CORNER RADIUS - "HOSS"

- ▶ #1 Choice for slotting, ramping & pocket work on stainless, monel & other alloys up to HRc35.
- ▶ Dry milling is recommended on steel alloys to reduce thermal shock and increase the life (YG:TYLON F or E COATING).



◆ U.S.A Stock

Ø1/8-Ø5/16 Ø11/32-Ø1

Unit : Inch

EDP No.					Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E	R				
57558	57558TN	57558TC	57558TF	57558TE	.008~.010	1/8	1/8	1/4	1-1/2
57561	57561TN	57561TC	57561TF	57561TE	.008~.010	5/32	3/16	5/16	2
57565	57565TN	57565TC	57565TF	57565TE	.008~.010	3/16	3/16	5/16	2
57570	57570TN	57570TC	57570TF	57570TE	.015~.020	7/32	1/4	3/8	2
57573	57573TN	57573TC	57573TF	57573TE	.015~.020	1/4	1/4	3/8	2
57576	57576TN	57576TC	57576TF	57576TE	.015~.020	9/32	5/16	7/16	2
57579	57579TN	57579TC	57579TF	57579TE	.015~.020	5/16	5/16	7/16	2
57582	57582TN	57582TC	57582TF	57582TE	.015~.020	11/32	3/8	1/2	2
57584	57584TN	57584TC	57584TF	57584TE	.015~.020	3/8	3/8	1/2	2
57588	57588TN	57588TC	57588TF	57588TE	.015~.020	7/16	7/16	9/16	2-1/2
57593	57593TN	57593TC	57593TF	57593TE	.030~.035	1/2	1/2	5/8	2-1/2
57595	57595TN	57595TC	57595TF	57595TE	.030~.035	5/8	5/8	3/4	3
57598	57598TN	57598TC	57598TF	57598TE	.030~.035	3/4	3/4	1	3
57600	57600TN	57600TC	57600TF	57600TE	.030~.035	1	1	1-1/4	3


Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~.0012	0~.0003

RECOMMENDED CUTTING CONDITIONS

- ▶ Use stub length whenever possible
- ▶ Hardslick coating is recommended on soft gummy material Especially on tools 3/16 and under

CUTTING TOOL DIAMETER

1/8	.0003~.0015	3/8	.0015~.0035	3/4	.003~.006
3/16	.0004~.002	7/16	.002~.004	1	.003~.007
1/4	.001~.0025	1/2	.0025~.0045		
5/16	.0015~.003	5/8	.0025~.005		



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	○				◎	○							



E5074 SERIES PLAIN SHANK Ø1/8-Ø5/16
E5104 SERIES FLAT SHANK Ø11/32-Ø1

CARBIDE, 3 FLUTE 35° HELIX REGULAR LENGTH CORNER RADIUS - "HOSS"

- ▶ #1 Choice for slotting, ramping & pocket work on stainless, monel & other alloys up to HRc35.
- ▶ Dry milling is recommended on steel alloys to reduce thermal shock and increase the life (YG:TYLON F or E COATING).



P.940

◆ U.S.A Stock

Ø1/8-Ø5/16 Ø11/32-Ø1

Unit : Inch

EDP No.					Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E	R				
56558	56558TN	56558TC	56558TF	56558TE	.008~.010	1/8	1/8	1/2	1-1/2
56561	56561TN	56561TC	56561TF	56561TE	.008~.010	5/32	3/16	9/16	2
56565	56565TN	56565TC	56565TF	56565TE	.008~.010	3/16	3/16	9/16	2
56570	56570TN	56570TC	56570TF	56570TE	.015~.020	7/32	1/4	3/4	2-1/2
56573	56573TN	56573TC	56573TF	56573TE	.015~.020	1/4	1/4	3/4	2-1/2
56576	56576TN	56576TC	56576TF	56576TE	.015~.020	9/32	5/16	13/16	2-1/2
56579	56579TN	56579TC	56579TF	56579TE	.015~.020	5/16	5/16	13/16	2-1/2
56582	56582TN	56582TC	56582TF	56582TE	.015~.020	11/32	3/8	1	2-1/2
56584	56584TN	56584TC	56584TF	56584TE	.015~.020	3/8	3/8	1	2-1/2
56588	56588TN	56588TC	56588TF	56588TE	.015~.020	7/16	7/16	1	2-3/4
56593	56593TN	56593TC	56593TF	56593TE	.030~.035	1/2	1/2	1-1/4	3
56595	56595TN	56595TC	56595TF	56595TE	.030~.035	5/8	5/8	1-5/8	3-1/2
56598	56598TN	56598TC	56598TF	56598TE	.030~.035	3/4	3/4	1-5/8	4
56600	56600TN	56600TC	56600TF	56600TE	.030~.035	1	1	2	4

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~.0012	0~.0003

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	○				◎	○							



EH094 SERIES PLAIN SHANK

CARBIDE, MULTI FLUTE STUB LENGTH FINE PITCH ROUGHING

- ▶ Designed to machine low hardness materials (under HRc45), alloy steels, tool steels, carbon steels, prehardened steels, stainless steel, inconel, nimonic, etc.
- ▶ High velocity milling operation.
- ▶ Fast chip ejection.




◆ U.S.A Stock

Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
95072	1/4	1/4	5/16	2-1/8	3
95073	5/16	5/16	3/8	2-1/4	3
95074	3/8	3/8	9/16	2-1/2	3
95075	1/2	1/2	5/8	3	4
95076	5/8	5/8	7/8	3-1/4	4
95077	3/4	3/4	1	3-3/4	4
95078	1	1	1	4	5

Mill Dia. (inch)	Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
1/4~3/8	0 ~ -.0022	0 ~ -.0003
1/2~5/8	0 ~ -.0027	
3/4~1	0 ~ -.0033	



◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	○			◎							◎	○



EH095 SERIES PLAIN SHANK

CARBIDE, MULTI FLUTE LONG LENGTH FINE PITCH ROUGHING

- ▶ Suitable for low hardness materials (under HRc45), alloy steels, tool steels, carbon steels, prehardened steels, stainless steel, inconel, nimonic, etc.
- ▶ High velocity milling operation.
- ▶ Fast chip ejection.




◆ U.S.A Stock

Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
95079	1/4	1/4	3/4	2-1/2	3
95080	5/16	5/16	3/4	2-1/2	3
95081	3/8	3/8	7/8	2-1/2	3
95082	1/2	1/2	1	3	4
95083	5/8	5/8	1-1/4	3-1/2	4
95084	3/4	3/4	1-5/8	4	4
95085	1	1	1-3/4	4	5

Mill Dia. (inch)	Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
1/4~3/8	0 ~ -.0022	0 ~ -.0003
1/2~5/8	0 ~ -.0027	
3/4~1	0 ~ -.0033	



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	○			◎							◎	○

CBN END MILLS
i-Xmill END MILLS
i-SMART MODULAR TYPE END MILLS
X5070 END MILLS
4G MILL END MILLS
X-POWER END MILLS
JET-POWER END MILLS
TitaNox -POWER END MILLS
V7 PLUS A END MILLS
V7 MILL INOX END MILLS
ALU-POWER HPC END MILLS
ALU-POWER END MILLS
D-POWER GRAPHITE END MILLS
D-POWER CFRP END MILLS
ROUTERS CFRP
STANDARD CARBIDE END MILLS
ONLY ONE COATED PM60 END MILLS
SINE -POWER END MILLS
TANK-POWER END MILLS
STANDARD COBALT & HSS END MILLS
TECHNICAL DATA



CBN END MILLS
i-Xmill END MILLS
i-SMART MODULAR TYPE END MILLS
X5070 END MILLS
4G MILL END MILLS
X-POWER END MILLS
JET-POWER END MILLS
TitaNox -POWER END MILLS
V7 PLUS A END MILLS
V7 MILL INOX END MILLS
ALU-POWER HPC END MILLS
ALU-POWER END MILLS
D-POWER GRAPHITE END MILLS
D-POWER CFRP END MILLS
ROUTERS CFRP
STANDARD CARBIDE END MILLS
ONLY ONE COATED PM60 END MILLS
SINE -POWER END MILLS
TANK-POWER END MILLS
STANDARD COBALT & HSS END MILLS
TECHNICAL DATA



EH969 SERIES PLAIN SHANK

CARBIDE, MULTI FLUTE 45° HELIX LONG LENGTH FINE PITCH ROUGHING

- Suitable for low hardness materials (under HRc45), alloy steels, tool steels, carbon steels, prehardened steels, stainless steel, titanium, inconel, nimonic, etc.
- High chip removed and minimizing breakages of cutting edges.
- Corner Protection against chipping.




◆ U.S.A Stock

Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
95107	3/16	1/4	1/2	2-1/4	3
95108	1/4	1/4	3/4	2-1/2	4
95109	5/16	5/16	3/4	2-1/2	4
95110	3/8	3/8	7/8	2-1/2	4
95111	1/2	1/2	1	3	4
95112	5/8	5/8	1-1/4	3-1/2	5
95113	3/4	3/4	1-5/8	4	6
95114	1	1	1-3/4	4	6

Mill Dia. (inch)	Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
3/16	0 ~ -.0019	0 ~ -.0003
1/4~3/8	0 ~ -.0022	
1/2~5/8	0 ~ -.0027	
3/4~1	0 ~ -.0033	



◎ : Excellent ○ : Good



P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	○			◎							◎	○



EH970 SERIES PLAIN SHANK

CARBIDE, MULTI FLUTE 45° HELIX LONG REACH FINE PITCH ROUGHING

- Suitable for low hardness materials (under HRc45), alloy steels, tool steels, carbon steels, prehardened steels, stainless steel, titanium, inconel, nimonic, etc.
- High chip removed and minimizing breakages of cutting edges.
- Corner Protection against chipping.




◆ U.S.A Stock

Unit : Inch

EDP No.	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	No. of Flute
95101	1/4	1/4	3/4	7/8	2-1/2	.230	4
95102	5/16	5/16	3/4	1	2-1/2	.292	4
95103	3/8	3/8	7/8	1-1/4	2-1/2	.355	4
95104	1/2	1/2	1	1-1/2	3	.480	4
95105	5/8	5/8	1-1/4	2	4	.605	5
95106	3/4	3/4	1-5/8	2-3/8	4-3/8	.719	6

Mill Dia. (inch)	Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
1/4~3/8	0 ~ -.0022	0 ~ -.0003
1/2~5/8	0 ~ -.0027	
3/4~1	0 ~ -.0033	




◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	○			◎							◎	○

CARBIDE, 3&4 FLUTE 50° HELIX LONG LENGTH

- ▶ Reduces chipping of corner edges
- ▶ Suitable for low hardness materials (under HRc45), alloy steels, tool steels, carbon steels, prehardened steels, stainless steels, Inconel, nimonic, etc




◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length	No. of Flute
	Metric	Inch				
EH830060	6.0	.2362	6	13	50	3
EH830901	6.0	.2362	6	13	50	4
EH830080	8.0	.3150	8	19	60	3
EH830100	10.0	.3937	10	22	70	3
EH830120	12.0	.4724	12	25	75	3
EH830160	16.0	.6299	16	32	90	3
EH830180	18.0	.7087	18	32	90	3
EH830200	20.0	.7874	20	38	100	4
EH830250	25.0	.9843	25	45	120	4

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	○			◎							◎	○

PREMIUM HSS-PM, 4&6 FLUTE SHORT LENGTH

- ▶ Designed to machine low hardness materials (under HRc45), alloy steels, tool steels, carbon steels, prehardened steels, stainless steel, inconel, nimonic, etc.
- ▶ High velocity milling operation and good surface finishes.



◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length	No. of Flute
	Metric	Inch				
EE515030	3.0	.1181	6	8	52	4
EE515040	4.0	.1575	6	11	55	4
EE515050	5.0	.1969	6	13	57	4
EE515060	6.0	.2362	6	13	57	4
EE515080	8.0	.3150	10	19	69	4
EE515100	10.0	.3937	10	22	72	4
EE515120	12.0	.4724	12	26	83	4
EE515140	14.0	.5512	12	26	83	4
EE515160	16.0	.6299	16	32	92	6
EE515180	18.0	.7087	16	32	92	6
EE515200	20.0	.7874	20	38	104	6
EE515250	25.0	.9843	25	45	121	6

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~+0.03	h6

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	○			◎							◎	○



EH852 SERIES PLAIN SHANK

CARBIDE, MULTI FLUTE SHORT LENGTH FINE PITCH ROUGHING

- Designed to machine low hardness materials (under HRc45), alloy steels, tool steels, carbon steels, prehardened steels, stainless steel, inconel, nimonic.
- High velocity milling operation.
- Fast chip ejection.




◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length	No. of Flute
	Metric	Inch				
EH852060	6.0	.2362	6	7	54	3
EH852070	7.0	.2756	8	8	58	3
EH852080	8.0	.3150	8	9	58	3
EH852090	9.0	.3543	10	13	66	4
EH852100	10.0	.3937	10	14	66	4
EH852120	12.0	.4724	12	16	73	4
EH852140	14.0	.5512	14	18	75	4
EH852160	16.0	.6299	16	22	82	4
EH852180	18.0	.7087	18	24	84	4
EH852200	20.0	.7874	20	26	92	4
EH852250	25.0	.9843	25	25	110	5

Tolerances according to DIN 7160 & 7161

Tolerance range in μm					
Nominal-Diameter in mm					
	from 1 to 3	over 3 to 6	over 6 to 10	over 10 to 18	over 18 to 30
h10	0 - 40	0 - 48	0 - 58	0 - 70	0 - 84
h6	0 - 6	0 - 8	0 - 9	0 - 11	0 - 13



Enforced cutting edge

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	○			◎							◎	○



EH831 SERIES PLAIN SHANK

CARBIDE, MULTI FLUTE LONG LENGTH FINE PITCH ROUGHING

- Designed to machine low hardness materials (under HRc45), alloy steels, tool steels, carbon steels, prehardened steels, stainless steel, inconel, nimonic.
- High velocity milling operation.
- Fast chip ejection.




◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length	No. of Flute
	Metric	Inch				
EH831060	6.0	.2362	6	16	57	3
EH831070	7.0	.2756	8	16	63	3
EH831080	8.0	.3150	8	16	63	3
EH831090	9.0	.3543	10	19	72	4
EH831100	10.0	.3937	10	22	72	4
EH831120	12.0	.4724	12	26	83	4
EH831140	14.0	.5512	14	26	83	4
EH831160	16.0	.6299	16	32	92	4
EH831180	18.0	.7087	18	32	92	4
EH831200	20.0	.7874	20	38	104	4
EH831250	25.0	.9843	25	45	121	5

Tolerances according to DIN 7160 & 7161

Tolerance range in μm					
Nominal-Diameter in mm					
	from 1 to 3	over 3 to 6	over 6 to 10	over 10 to 18	over 18 to 30
h10	0 - 40	0 - 48	0 - 58	0 - 70	0 - 84
h6	0 - 6	0 - 8	0 - 9	0 - 11	0 - 13



Enforced cutting edge

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	○			◎							◎	○



EH917 SERIES PLAIN SHANK

CARBIDE, MULTI FLUTE 45° HELIX SHORT LENGTH FINE PITCH ROUGHING

- ▶ High chip removal and minimizing breakages of cutting edges.
- ▶ Suitable for low hardness materials(under HRc45), alloy steels, tool steels, carbon steels, prehardened steels, stainless steels, Inconel, nimonic, etc




◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length	No. of Flute
	Metric	Inch				
EH917060	6.0	.2362	6	7	54	4
EH917080	8.0	.3150	8	9	58	4
EH917100	10.0	.3937	10	14	66	4
EH917120	12.0	.4724	12	16	73	4
EH917160	16.0	.6299	16	22	82	5
EH917200	20.0	.7874	20	26	92	6

Tolerances according to DIN 7160 & 7161

Tolerance range in μm					
Nominal-Diameter in mm					
	from 1 to 3	over 3 to 6	over 6 to 10	over 10 to 18	over 18 to 30
h10	0 - 40	0 - 48	0 - 58	0 - 70	0 - 84
h6	0 6	0 8	0 9	0 11	0 13



◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	○			◎							◎	○



EH919 SERIES PLAIN SHANK

CARBIDE, MULTI FLUTE 45° HELIX LONG LENGTH FINE PITCH ROUGHING

- ▶ High chip removal and minimizing breakages of cutting edges.
- ▶ Suitable for low hardness materials(under HRc45), alloy steels, tool steels, carbon steels, prehardened steels, stainless steels, Inconel, nimonic, etc




◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length	No. of Flute
	Metric	Inch				
EH919040	4.0	.1575	6	11	57	3
EH919050	5.0	.1969	6	13	57	4
EH919060	6.0	.2362	6	16	57	4
EH919070	7.0	.2756	8	16	63	4
EH919080	8.0	.3150	8	16	63	4
EH919090	9.0	.3543	10	19	72	4
EH919100	10.0	.3937	10	22	72	4
EH919120	12.0	.4724	12	26	83	4
EH919140	14.0	.5512	14	26	83	5
EH919160	16.0	.6299	16	32	92	5
EH919200	20.0	.7874	20	38	104	6
EH919250	25.0	.9843	25	45	121	6

Tolerances according to DIN 7160 & 7161

Tolerance range in μm					
Nominal-Diameter in mm					
	from 1 to 3	over 3 to 6	over 6 to 10	over 10 to 18	over 18 to 30
h10	0 - 40	0 - 48	0 - 58	0 - 70	0 - 84
h6	0 - 6	0 - 8	0 - 9	0 - 11	0 - 13



◎ : Excellent ○ : Good



P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	○			◎							◎	○



EH921 SERIES PLAIN SHANK

CARBIDE, MULTI FLUTE 45° HELIX LONG REACH FINE PITCH ROUGHING

- Suitable for low hardness materials (under HRc45), alloy steels, tool steels, carbon steels, prehardened steels, stainless steel, titanium, inconel, nimonic, etc.
- High chip removed and minimizing breakages of cutting edges.
- Corner Protection against chipping.




◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3	No. of Flute
	Metric D1	Inch						
EH921060	6.0	.2362	6	16	20	57	5.5	4
EH921080	8.0	.3150	8	16	26	63	7.5	4
EH921100	10.0	.3937	10	22	31	72	9.5	4
EH921120	12.0	.4724	12	26	37	83	11.5	4
EH921160	16.0	.6299	16	32	51	100	15.5	5
EH921200	20.0	.7874	20	38	59	110	19.2	6

Tolerances according to DIN 7160 & 7161

	Tolerance range in μm				
	Nominal-Diameter in mm				
	from 1 to 3	over 3 to 6	over 6 to 10	over 10 to 18	over 18 to 30
h10	0 - 40	0 - 48	0 - 58	0 - 70	0 - 84
h6	0 - 6	0 - 8	0 - 9	0 - 11	0 - 13



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	◎	◎	○			◎							◎	○





RECOMMENDED CUTTING CONDITIONS

CARBIDE, 3&4 FLUTE FINISH - SLOTTING

EH108, EH830 SERIES

MATERIAL	P		M		S		S		S	
	CARBON STEELS ALLOY STEELS TOOL STEELS	CARBON STEELS ALLOY STEELS TOOL STEELS	STAINLESS STEELS	TITANIUM ALLOY	HIGH TEMPERATURE ALLOY		S		S	
HARDNESS	~HRc30		HRc30 ~ HRc45							
STRENGTH	~1000N/mm ²		1000 ~ 1500N/mm ²							
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	5560	12.2	3360	7.9	2840	6.3	1500	2.2	1160	1.6
5/16	4200	13.4	2520	7.1	2100	6.3	1090	2.2	840	1.6
3/8	3260	11.8	2000	5.5	1680	5.5	870	2.2	670	1.6
1/2	2740	9.8	1680	4.7	1370	4.7	730	1.8	560	1.2
5/8	2200	7.9	1360	3.9	1050	4.0	550	1.4	420	1.0
3/4	1750	6.9	1100	3.4	880	3.4	480	1.2	350	1.2
1	1360	4.5	840	2.4	670	2.4	350	0.8	270	0.6





※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

CARBIDE, 3&4 FLUTE FINISH - SIDE CUTTING

EH108, EH830 SERIES

MATERIAL	P		M		S		S		S	
	CARBON STEELS ALLOY STEELS TOOL STEELS	CARBON STEELS ALLOY STEELS TOOL STEELS	STAINLESS STEELS	TITANIUM ALLOY	HIGH TEMPERATURE ALLOY		S		S	
HARDNESS	~HRc30		HRc30 ~ HRc45							
STRENGTH	~1000N/mm ²		1000 ~ 1500N/mm ²							
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	5560	15.8	3360	9.9	2840	8.3	1360	3.0	1050	2.2
5/16	4200	16.5	2520	9.1	2100	8.7	1090	2.8	840	2.0
3/8	3260	14.6	2000	7.1	1680	8.7	880	2.8	680	2.0
1/2	2740	12.2	1680	5.9	1370	7.1	730	2.6	560	1.8
5/8	2200	9.9	1360	4.7	1050	5.3	550	2.0	420	1.4
3/4	1750	8.7	1100	4.4	880	5.4	480	1.6	350	1.2
1	1360	5.9	840	3.0	670	4.5	350	1.4	270	1.0





※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

YPM, 6 FLUTE - SIDE CUTTING

EE882 SERIES

MATERIAL	P				M		S			
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		STAINLESS STEELS		TITANIUM ALLOY		HIGH TEMPERATURE ALLOY	
HARDNESS	~HRc30		HRc30 ~ HRc45							
STRENGTH	~1000N/mm ²		1000 ~ 1500N/mm ²							
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/4	960	8.0	215	0.8	480	4.8	220	1.4	170	1.0
7/8	730	7.3	180	0.7	365	4.4	190	1.1	145	0.8
1	640	6.6	165	0.6	320	4.0	170	1.0	130	0.7
1-1/4	520	5.3	130	0.5	260	3.2	140	0.8	105	0.6
1-1/2	430	4.4	105	0.4	215	2.6	110	0.6	85	0.5





※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

PREMIUM HSS-PM, 4&6 FLUTE SHORT- SIDE CUTTING

EE515 SERIES

MATERIAL	P				M		S	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		STAINLESS STEELS TITANIUM ALLOY		HIGH TEMPERATURE ALLOY	
HARDNESS	~ HRc30		HRc30 ~ HRc45					
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3.0	4400	7.3	1100	0.9	2200	4.3	880	1.1
4.0	3600	8.3	900	1.2	1800	4.9	720	1.5
5.0	3000	8.9	750	1.2	1500	5.3	600	1.4
6.0	2600	9.3	600	1.1	1300	5.5	480	1.4
8.0	2000	9.8	500	1.1	1000	5.9	400	1.3
10.0	1600	11.2	410	1.2	800	6.7	330	1.4
12.0	1320	9.8	340	1.1	660	5.9	270	1.4
14.0	1160	9.3	290	1.1	580	5.5	230	1.3
16.0	1000	8.9	250	1.0	500	5.3	200	1.2
18.0	900	8.3	225	0.9	450	4.9	180	1.1
20.0	800	7.9	200	0.7	400	4.7	160	0.8
25.0	640	6.5	165	0.6	320	3.9	130	0.7






RPM = rev./min.
FEED = inch/min.

CARBIDE, MULTI FLUTE ROUGHING - SLOTTING

EH094, EH095, EH969, EH970, EH852, EH831, EH917, EH919, EH921 SERIES

MATERIAL	P				M		S			
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		STAINLESS STEELS		TITANIUM ALLOY		HIGH TEMPERATURE ALLOY	
HARDNESS	~HRc30		HRc30 ~ HRc45							
STRENGTH	~1000N/mm ²		1000 ~ 1500N/mm ²							
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	15600	91.4	12400	33.1	8400	22.5	3150	10.6	2400	7.5
5/16	11600	91.4	9200	33.1	6300	22.5	2350	9.8	1800	7.1
3/8	9200	91.4	7600	33.1	5100	22.5	1700	10.2	1300	7.5
1/2	8000	94.5	6000	31.5	4200	22.5	1560	10.2	1200	7.5
5/8	6000	94.5	4800	29.9	3300	20.1	1040	5.8	800	4.3
3/4	5200	91.4	4400	28.4	2500	16.6	910	5.5	675	4.0
1	4300	84.7	3200	24.4	2160	16.2	780	5.1	600	4.3



A: D1/4-D3/8:0.25xD
D1/2-D5/8:0.15xD
D3/4-D1:0.10xD




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

CARBIDE, MULTI FLUTE ROUGHING - SIDE CUTTING

EH094, EH095, EH969, EH970, EH852, EH831, EH917, EH919, EH921 SERIES

MATERIAL	P				M		S			
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		STAINLESS STEELS		TITANIUM ALLOY		HIGH TEMPERATURE ALLOY	
HARDNESS	~HRc30		HRc30 ~ HRc45							
STRENGTH	~1000N/mm ²		1000 ~ 1500N/mm ²							
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	15600	91.4	12400	33.1	8400	22.5	3150	10.6	2400	7.5
5/16	11600	91.4	9200	33.1	6300	22.5	2350	9.8	1800	7.1
3/8	9200	91.4	7600	33.1	5100	22.5	1700	10.2	1300	7.5
1/2	8000	94.5	6000	31.5	4200	22.5	1560	10.2	1200	7.5
5/8	6000	94.5	4800	29.9	3300	22.1	1040	5.9	800	4.3
3/4	5200	91.4	4400	28.4	2700	16.6	910	5.5	700	4.0
1	4300	84.7	3200	24.4	2160	16.2	780	5.1	600	4.3



A: D1/4-D3/8:0.15xD
D1/2-D5/8:0.10xD
D3/4-D1:0.05xD

※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.



Being the best through innovation

CARBIDE




TitaNox-POWER END MILLS

- High Speed Machining for Exotic Materials:
Titanium, Stainless Steels and Alloy Steels



Global Cutting Tool Leader **YG-1**










SELECTION GUIDE




SOLID CARBIDE TitaNox-POWER END MILLS

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	

INCH

UGMG42		CARBIDE, 4 FLUTE CORNER RADIUS DOUBLE CORE STANDARD LENGTH	D1/4	D1	960
UGMG43		CARBIDE, 4 FLUTE CORNER RADIUS DOUBLE CORE STANDARD LENGTH	D3/8	D1	962
UGMH12		CARBIDE, 5 FLUTE STANDARD LENGTH	D1/8	D1-1/4	963
UGMG32		CARBIDE, 5 FLUTE STANDARD LENGTH	D1/8	D1	963
UGMG34		CARBIDE, 5 FLUTE CORNER RADIUS STANDARD LENGTH	D1/8	D1-1/4	963
UGMH06		CARBIDE, 5 FLUTE EXTENDED LENGTH	D1/8	D1	966
UGMH07		CARBIDE, 5 FLUTE CORNER RADIUS EXTENDED LENGTH	D1/8	D1	966

METRIC


GMG40		CARBIDE, 4 FLUTE CORNER RADIUS DOUBLE CORE EXTENDED LENGTH	D6.0	D25.0	968
GMG24 GMG26		CARBIDE, 5 FLUTE STANDARD LENGTH	D6.0	D25.0	969
GMG28 GMG30		CARBIDE, 5 FLUTE CORNER RADIUS STANDARD LENGTH	D6.0	D25.0	970
RECOMMENDED CUTTING CONDITIONS					971

⊙ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~352	HRc30~40	HRc40~45	HRc45~55	HRc55~70									

○	○	○				⊙	○						⊙	○
○	○	○				⊙	○						⊙	○
○	○	○				⊙	○						⊙	○
○	○	○				⊙	○						⊙	○
○	○	○				⊙	○						⊙	○
○	○	○				⊙	○						⊙	○
○	○	○				⊙	○						⊙	○

○	○	○				⊙	○						⊙	○
○	○	○				⊙	○						⊙	○
○	○	○				⊙	○						⊙	○




▲ The illustration above detailed along the X-X' axis shows how the 4-flute design starts the cut with aggressive chip evacuation. The Y-Y' axis shows how the double core comes into play, providing perfect slotting operations through its extra-rigid double-core design.

TitaNox-POWER END MILLS

UGMG42 SERIES CORNER RADIUS

CARBIDE, 4 FLUTE CORNER RADIUS DOUBLE CORE STANDARD LENGTH

- ▶ Double Core E/M has a Unique Flute Design for excellent chip evacuation and higher rigidity
- ▶ The double core adds stability and aids chip flow, reducing tool deflection, improving dimensional stability and workpiece accuracy



MG HM 4 43°/45° PLAIN P.971~972

Unit : Inch

OD	SD	LOC	OAL	Corner Radius							
				.010	.015	.030	.060	.090	.125	.190	.250
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
1/4	1/4	9/16	2-1/2	UGMG42802	UGMG42016	UGMG42901	UGMG42902	-	-	-	-
		3/4	2-1/2	-	-	UGMG42924	UGMG42925	-	-	-	-
		1	3	-	-	UGMG42S926*	UGMG42S927*	-	-	-	-
3/8	3/8	1/2	2-1/2	-	-	UGMG42K998	UGMG42K999	UGMG42K801	-	-	-
		7/8	2-1/2	-	-	UGMG42928	UGMG42929	UGMG42930	-	-	-
		13/16	2-1/2	UGMG42931	-	UGMG42905	UGMG42906	UGMG42907	-	-	-
1/2	1/2	1	3	UGMG42932	UGMG42803	UGMG42933	UGMG42934	UGMG42935	-	-	-
		1-1/4	3	UGMG42S936*	UGMG42S804*	UGMG42S937*	UGMG42S938*	UGMG42S939*	-	-	-
		1	3	UGMG42940	-	UGMG42908	UGMG42909	UGMG42910	UGMG42911	-	-
5/8	5/8	1-1/4	3-1/2	-	UGMG42805	UGMG42912	UGMG42941	UGMG42942	UGMG42943	-	-
		1-5/8	4	-	-	UGMG42S944*	UGMG42S945*	UGMG42S946*	UGMG42S947*	-	-
		2	4	-	-	UGMG42S806*	UGMG42S807*	UGMG42S808*	UGMG42S809*	-	-
1	1	1-1/4	3-1/2	-	-	UGMG42040	UGMG42913	UGMG42914	UGMG42915	-	-
		1-5/8	4	-	-	UGMG42948	UGMG42949	UGMG42950	UGMG42951	-	-
		2	4	-	-	UGMG42S952*	UGMG42S953*	UGMG42S954*	UGMG42S955*	-	-
1 1/2	1 1/2	3-1/4	6	-	-	UGMG42S956*	UGMG42S957*	UGMG42S958*	UGMG42S959*	-	-

*Length of cut in excess of 3xD on 45° single-helix requires feed reduction of approximately 50%

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	○	○			◎	○						◎	○

TitaNox-POWER END MILLS

UGMG42 SERIES CORNER RADIUS

CARBIDE, 4 FLUTE CORNER RADIUS DOUBLE CORE STANDARD LENGTH

- ▶ Double Core E/M has a Unique Flute Design for excellent chip evacuation and higher rigidity
- ▶ The double core adds stability and aids chip flow, reducing tool deflection, improving dimensional stability and workpiece accuracy



MG HM 4 43°/45° PLAIN P.971~972

Unit : Inch

OD	SD	LOC	OAL	Corner Radius							
				.010	.015	.030	.060	.090	.125	.190	.250
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
3/4	3/4	1-1/2	4	-	-	UGMG42048	UGMG42916	UGMG42917	UGMG42918	UGMG42919	UGMG42960
		1-7/8	4	-	-	UGMG42961	UGMG42962	UGMG42963	UGMG42964	UGMG42965	UGMG42966
		2-1/4	5	-	-	UGMG42967	UGMG42968	UGMG42969	UGMG42970	UGMG42971	UGMG42972
		3-1/4	6	-	-	UGMG42S973*	UGMG42S974*	UGMG42S975*	UGMG42S976*	UGMG42S977*	UGMG42S978*
1	1	2	5	-	-	UGMG42064	UGMG42920	UGMG42921	UGMG42922	UGMG42923	UGMG42979
		2-5/8	5	-	-	UGMG42980	UGMG42981	UGMG42982	UGMG42983	UGMG42984	UGMG42985
		3	6	-	-	UGMG42986	UGMG42987	UGMG42988	UGMG42989	UGMG42990	UGMG42991
		4-1/4	7	-	-	UGMG42S992*	UGMG42S993*	UGMG42S994*	UGMG42S995*	UGMG42S996*	UGMG42S997*

*Length of cut in excess of 3xD on 45° single-helix requires feed reduction of approximately 50%

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.012	h6

◎ : Excellent ○ : Good


P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	○	○			◎	○						◎	○



UGMG43 SERIES CORNER RADIUS

CARBIDE, 4 FLUTE CORNER RADIUS DOUBLE CORE STANDARD LENGTH

- ▶ Double Core E/M has a Unique Flute Design for excellent chip evacuation and higher rigidity
- ▶ The double core adds stability and aids chip flow, reducing tool deflection, improving dimensional stability and workpiece accuracy



Unit : Inch

OD	SD	LOC	OAL	Corner Radius					
				.020	.030	.060	.090	.125	.190
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
3/8	3/8	13/16	2-1/2	UGMG43024	UGMG43905	UGMG43906	UGMG43907	-	-
		1	3	UGMG43032	UGMG43908	UGMG43909	UGMG43910	UGMG43911	-
1/2	1/2	1-1/4	3-1/2	-	UGMG43912	UGMG43924	-	-	-
		1-1/4	3-1/2	-	UGMG43040	UGMG43913	UGMG43914	UGMG43915	-
5/8	5/8	1-1/4	3-1/2	-	UGMG43048	UGMG43916	UGMG43917	UGMG43818	UGMG43919
3/4	3/4	1-1/2	4	-	UGMG43064	UGMG43920	UGMG43921	UGMG43922	UGMG43923

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.012	h6

◎ : Excellent ○ : Good


P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	○	○			◎	○						◎	○



UGMH12 SERIES SQUARE
UGMG32 SERIES CHAMFER
UGMG34 SERIES CORNER RADIUS

CARBIDE, 5 FLUTE STANDARD LENGTH

- ▶ Excellent performance results and long tool life when machining Titanium and other tough materials
- ▶ This tool has high rigidity of flute so that is possible to use for heavy profile and high speed milling
- ▶ For protecting Corner chipping of end teeth, Corner Radius & Chamfer are adopted



Unit : Inch

OD	SD	LOC	OAL	Square End	Chamfer	Corner Radius						
						.015	.030	.060	.090	.125	.190	.250
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
1/8	1/8	1/4	1-1/2	UGMH12008	UGMG32008	UGMG34008	UGMG34950	-	-	-	-	-
		3/8	1-1/2	UGMH12901	UGMG32901	UGMG34901	UGMG34951	-	-	-	-	
		1/2	2-1/2	UGMH12S902*	-	UGMG34S952*	UGMG34S953*	-	-	-	-	
3/16	3/16	3/4	2-1/2	UGMH12S903*	-	UGMG34S954*	UGMG34S955*	-	-	-	-	
		5/16	2	UGMH12012	UGMG32012	UGMG34012	UGMG34956	-	-	-		
		9/16	2	UGMH12904	UGMG32902	UGMG34902	UGMG34957	-	-	-		
1/4	1/4	3/4	2-1/2	UGMH12S905*	-	UGMG34S958*	UGMG34S959*	-	-	-	-	
		1	3	UGMH12016	UGMG32016	UGMG34960	UGMG34016	UGMG34961	-	-		
		1-1/4	3	UGMH12906	-	UGMG34962	UGMG34963	UGMG34964	-	-		
		1-1/4	3	UGMH12907	UGMG32903	UGMG34903	UGMG34904	UGMG34905	-	-		
		1-1/4	3	UGMH12S908*	-	UGMG34S965*	UGMG34S966*	UGMG34S967*	-	-		
5/16	5/16	1-1/4	3	UGMH12S909*	-	UGMG34S968*	UGMG34S969*	UGMG34S970*	-	-		
		7/16	2"	UGMH12020	UGMG32020	UGMG34971	UGMG34020	UGMG34972	-	-		
		13/16	2-1/2	UGMH12910	UGMG32904	UGMG34906	UGMG34907	UGMG34908	-	-		
3/8	3/8	1	3	UGMH12S911*	-	UGMG34S973*	UGMG34S974*	UGMG34S975*	-	-		
		1/2	2-1/2	UGMH12024	UGMG32024	UGMG34976	UGMG34024	UGMG34909	UGMG34977	-		
		1	3	UGMH12912	UGMG32905	UGMG34910	UGMG34911	UGMG34912	UGMG34978	-		
		1-1/4	3	UGMH12S913*	-	UGMG34S979*	UGMG34S980*	UGMG34S981*	UGMG34S982*	-		
		1-1/2	4	UGMH12S914*	-	UGMG34S983*	UGMG34S984*	UGMG34S985*	UGMG34S986*	-		
1/2	1/2	1-1/4	3-1/2	UGMH12032	UGMG32032	UGMG34032	UGMG34913	UGMG34914	UGMG34987	UGMG34988	-	
		1	3	UGMH12915	UGMG32906	UGMG34915	UGMG34916	UGMG34917	UGMG34918	UGMG34919	-	
		1-1/4	3-1/2	UGMH12916	UGMG32907	UGMG34920	UGMG34921	UGMG34922	UGMG34923	UGMG34924	-	
		1-5/8	4	UGMH12S917*	-	UGMG34S989*	UGMG34S990*	UGMG34S991*	UGMG34S992*	UGMG34S993*	-	
		2	4	UGMH12S918*	-	UGMG34S994*	UGMG34S995*	UGMG34S996*	UGMG34S997*	UGMG34S998*	-	

*Length of cut in excess of 3xD on 45° single-helix requires feed reduction of approximately 50%

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	○	○			◎	○						◎	○

CARBIDE

HSS

CBN END MILLS

i-Xmill END MILLS

i-SMART MODULAR TYPE END MILLS

X5070 END MILLS

4G MILL END MILLS

X-POWER END MILLS

JET-POWER END MILLS

TitaNox-POWER END MILLS

V7 PLUS A END MILLS

V7 MILL INOX END MILLS

ALU-POWER HPC END MILLS

ALU-POWER END MILLS

D-POWER GRAPHITE END MILLS

D-POWER CFRP END MILLS

ROUTERS CFRP

STANDARD CARBIDE END MILLS

ONLY ONE COATED PM60 END MILLS

SINE-POWER END MILLS

TANK-POWER END MILLS

STANDARD COBALT & HSS END MILLS


TECHNICAL DATA

TitaNox-POWER END MILLS

- UGMH12 SERIES SQUARE
- UGMG32 SERIES CHAMFER
- UGMG34 SERIES CORNER RADIUS

CARBIDE, 5 FLUTE STANDARD LENGTH

- ▶ Excellent performance results and long tool life when machining Titanium and other tough materials
- ▶ This tool has high rigidity of flute so that is possible to use for heavy profile and high speed milling
- ▶ For protecting Corner chipping of end teeth, Corner Radius & Chamfer are adopted



MG HM 5 43°/44°/45° PLAIN C x 45° P.973

Unit : Inch

OD	SD	LOC	OAL	Square End	Chamfer	Corner Radius						
						.015	.030	.060	.090	.125	.190	.250
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
5/8	5/8	3/4	3	UGMH12040	UGMG32040	-	UGMG34040	UGMG34925	UGMG34999	UGMG34801	-	-
		1-1/4	3-1/2	UGMH12919	UGMG32908	UGMG34926	UGMG34927	UGMG34928	UGMG34929	UGMG34930	-	-
		1-5/8	4	UGMH12920	-	-	UGMG34802	UGMG34803	UGMG34804	UGMG34805	-	-
		2-1/8	4-1/2	UGMH12S921*	-	-	UGMG34S806*	UGMG34S807*	UGMG34S808*	UGMG34S809*	-	-
		2-1/2	5	UGMH12S922*	-	-	UGMG34S810*	UGMG34S811*	UGMG34S812*	UGMG34S813*	-	-
3/4	3/4	1	3-1/2	UGMH12048	UGMG32048	-	UGMG34048	UGMG34931	UGMG34932	UGMG34814	UGMG34815	UGMG34816
		1-1/2	4	UGMH12923	UGMG32909	UGMG34933	UGMG34934	UGMG34935	UGMG34936	UGMG34937	UGMG34938	UGMG34817
		1-7/8	5	UGMH12924	-	-	UGMG34818	UGMG34819	UGMG34820	UGMG34821	UGMG34822	UGMG34823
		2-1/4	5	UGMH12925	-	-	UGMG34824	UGMG34825	UGMG34826	UGMG34827	UGMG34828	UGMG34829
		2-3/4	5	UGMH12S926*	-	-	UGMG34S830*	UGMG34S831*	UGMG34S832*	UGMG34S833*	UGMG34S834*	UGMG34S835*
		3-1/4	6	UGMH12S927*	-	-	UGMG34S836*	UGMG34S837*	UGMG34S838*	UGMG34S839*	UGMG34S840*	UGMG34S841*
1	1	1-1/8	4	UGMH12064	UGMG32064	-	UGMG34064	UGMG34939	UGMG34940	UGMG34842	UGMG34843	UGMG34844
		1-1/2	4	UGMH12928	UGMG32910	UGMG34941	UGMG34942	UGMG34943	UGMG34944	UGMG34945	UGMG34946	UGMG34845
		2	5	UGMH12929	UGMG32911	-	UGMG34947	UGMG34948	UGMG34949	UGMG34846	UGMG34847	UGMG34848
		2-5/8	5	UGMH12930	-	-	UGMG34849	UGMG34850	UGMG34851	UGMG34852	UGMG34853	UGMG34854
		3-1/4	6	UGMH12S931*	-	-	UGMG34S855*	UGMG34S856*	UGMG34S857*	UGMG34S858*	UGMG34S859*	UGMG34S860*
4-1/4	7	UGMH12S932*	-	-	UGMG34S861*	UGMG34S862*	UGMG34S863*	UGMG34S864*	UGMG34S865*	UGMG34S866*		

*Length of cut in excess of 3xD on 45° single-helix requires feed reduction of approximately 50% ▶ NEXT PAGE

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	○	○				◎	○						◎	○

CARBIDE

HSS

CBN END MILLS

i-Xmill END MILLS

i-SMART MODULAR TYPE END MILLS

X5070 END MILLS

4G MILL END MILLS

X-POWER END MILLS

JET-POWER END MILLS

TitaNox-POWER END MILLS

V7 PLUS A END MILLS

V7 MILL INOX END MILLS

ALU-POWER HPC END MILLS

ALU-POWER END MILLS

D-POWER GRAPHITE END MILLS

D-POWER CFRP END MILLS

ROUTERS CFRP

STANDARD CARBIDE END MILLS

ONLY ONE COATED PM60 END MILLS

SINE-POWER END MILLS

TANK-POWER END MILLS

STANDARD COBALT & HSS END MILLS


TECHNICAL DATA

TitaNox-POWER END MILLS

- UGMH12 SERIES SQUARE
- UGMG32 SERIES CHAMFER
- UGMG34 SERIES CORNER RADIUS

CARBIDE, 5 FLUTE STANDARD LENGTH

- ▶ Excellent performance results and long tool life when machining Titanium and other tough materials
- ▶ This tool has high rigidity of flute so that is possible to use for heavy profile and high speed milling
- ▶ For protecting Corner chipping of end teeth, Corner Radius & Chamfer are adopted



MG HM 5 43°/44°/45° PLAIN C x 45° P.973

Unit : Inch

OD	SD	LOC	OAL	Square End	Chamfer	Corner Radius						
						.015	.030	.060	.090	.125	.190	.250
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
1-1/4	1-1/4	1-1/2	4-1/2	UGMH12116	-	-	-	UGMG34116	UGMG34867	UGMG34868	UGMG34869	UGMG34870
		2	4-1/2	UGMH12933	-	-	-	UGMG34871	UGMG34872	UGMG34873	UGMG34874	UGMG34875
		2-5/8	5-1/2	UGMH12934	-	-	-	UGMG34876	UGMG34877	UGMG34878	UGMG34879	UGMG34880
		3-1/4	6	UGMH12935	-	-	-	UGMG34881	UGMG34882	UGMG34883	UGMG34884	UGMG34885
		4-1/2	7	UGMH12S936*	-	-	-	UGMG34S886*	UGMG34S887*	UGMG34S888*	UGMG34S889*	UGMG34S890*

CHAMFER KEY UGMG32

Mill Diameter (in.)	Chamfer Size
1/8	.004
3/16	.006
1/4	.007
5/16	.007
3/8	.011
1/2	.013
5/8	.015
3/4	.019
1	.019

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	h6

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	○	○				◎	○						◎	○



UGMH06 SERIES SQUARE
UGMH07 SERIES CORNER RADIUS

CARBIDE, 5 FLUTE EXTENDED LENGTH

- ▶ Excellent performance results and long tool life when machining Titanium and other tough materials.
- ▶ This tool has high rigidity of flute so that is possible to use for heavy profile and high speed milling.
- ▶ For protecting Corner chipping of end teeth, Corner Radius & Chamfer are adopted.



Unit : Inch

OD	SD	LOC	LBS	OAL	Square End	Corner Radius					
						.030	.060	.090	.125	.190	.250
D1	D2	L1	L3	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
1/8	1/8	5/32	3/8	3	UGMH06008	UGMH07008	-	-	-	-	-
		5/32	1/2	3	UGMH06901	UGMH07901	-	-	-	-	-
		5/32	5/8	3	UGMH06902	UGMH07902	-	-	-	-	-
3/16	3/16	7/32	1/2	3	UGMH06012	UGMH07012	-	-	-	-	-
		7/32	3/4	3	UGMH06903	UGMH07903	-	-	-	-	-
		7/32	1	3	UGMH06904	UGMH07904	-	-	-	-	-
1/4	1/4	3/8	3/4	4	UGMH06016	UGMH07016	UGMH07905	-	-	-	-
		3/8	1-1/8	4	UGMH06905	UGMH07906	UGMH07907	-	-	-	-
		3/8	2-1/8	4	UGMH06906	UGMH07908	UGMH07909	-	-	-	-
3/8	3/8	1/2	1-1/8	4	UGMH06024	UGMH07024	UGMH07910	UGMH07911	-	-	-
		1/2	2-1/8	4	UGMH06907	UGMH07912	UGMH07913	UGMH07914	-	-	-
		1/2	3-1/8	5	UGMH06923	UGMH07804	UGMH07805	UGMH07806	-	-	-
		1/2	3-1/8	6	UGMH06908	UGMH07915	UGMH07916	UGMH07917	-	-	-
		1/2	4-1/8	6	UGMH06909	UGMH07918	UGMH07919	UGMH07920	-	-	-
1/2	1/2	5/8	1-1/2	4	UGMH06032	UGMH07032	UGMH07921	UGMH07922	UGMH07923	-	-
		5/8	2-1/4	4	UGMH06910	UGMH07924	UGMH07925	UGMH07926	UGMH07927	-	-
		5/8	3-3/8	5	UGMH06924	UGMH07807	UGMH07808	UGMH07809	UGMH07810	-	-
		5/8	3-3/8	6	UGMH06911	UGMH07928	UGMH07929	UGMH07930	UGMH07931	-	-
		5/8	4-1/8	6	UGMH06912	UGMH07932	UGMH07933	UGMH07934	UGMH07935	-	-
5/8	5/8	3/4	1-5/8	4	UGMH06040	UGMH07040	UGMH07936	UGMH07937	UGMH07938	-	-
		3/4	2-3/8	6	UGMH06913	UGMH07939	UGMH07940	UGMH07941	UGMH07942	-	-
		3/4	3-3/8	6	UGMH06914	UGMH07943	UGMH07944	UGMH07945	UGMH07946	-	-
		3/4	4-1/8	6	UGMH06915	UGMH07947	UGMH07948	UGMH07949	UGMH07950	-	-

*Length of cut in excess of 3xD on 45° single-helix requires feed reduction of approximately 50% ▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	○	○			◎	○						◎	○



UGMH06 SERIES SQUARE
UGMH07 SERIES CORNER RADIUS

CARBIDE, 5 FLUTE EXTENDED LENGTH


- ▶ Excellent performance results and long tool life when machining Titanium and other tough materials.
- ▶ This tool has high rigidity of flute so that is possible to use for heavy profile and high speed milling.
- ▶ For protecting Corner chipping of end teeth, Corner Radius & Chamfer are adopted.



Unit : Inch

OD	SD	LOC	LBS	OAL	Square End	Corner Radius					
						.030	.060	.090	.125	.190	.250
D1	D2	L1	L3	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
3/4	3/4	1-1/8	2	4	UGMH06048	UGMH07048	UGMH07951	UGMH07952	UGMH07953	UGMH07954	UGMH07955
		1-1/8	2-5/8	5	UGMH06916	UGMH07956	UGMH07957	UGMH07958	UGMH07959	UGMH07960	UGMH07961
		1-1/8	3-1/4	6	UGMH06917	UGMH07962	UGMH07963	UGMH07964	UGMH07965	UGMH07966	UGMH07967
		1-1/8	4-1/4	7	UGMH06918	UGMH07968	UGMH07969	UGMH07970	UGMH07971	UGMH07972	UGMH07973
1	1	1-1/4	2-1/4	4	UGMH06064	UGMH07064	UGMH07974	UGMH07975	UGMH07976	UGMH07977	UGMH07978
		1-1/4	2-5/8	5	UGMH06919	UGMH07979	UGMH07980	UGMH07981	UGMH07982	UGMH07983	UGMH07984
		1-1/4	3-1/4	6	UGMH06920	UGMH07985	UGMH07986	UGMH07987	UGMH07988	UGMH07989	UGMH07990
		1-1/4	4-1/4	7	UGMH06921	UGMH07991	UGMH07992	UGMH07993	UGMH07994	UGMH07995	UGMH07996
		1-1/4	5-1/4	8	UGMH06922	UGMH07997	UGMH07998	UGMH07999	UGMH07801	UGMH07802	UGMH07803

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.012	h6



◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
○	○	○			◎	○						◎	○

TitaNox-POWER END MILLS

GMG40 SERIES CORNER RADIUS

CARBIDE, 4 FLUTE CORNER RADIUS DOUBLE CORE EXTENDED LENGTH

- ▶ Double Core E/M has a Unique Flute Design for excellent chip evacuation and higher rigidity
- ▶ The double core adds stability and aids chip flow, reducing tool deflection, improving dimensional stability and workpiece accuracy



MG HM 4 43°/45° PLAIN P.974~975

Unit : mm

OD		SD	LOC	LBS	OAL	Corner Radius					
Metric	Inch					0.50	1.00	1.50	2.00	3.00	3.50
D1		D2	L1	L3	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
6.0	.2362	6	13	20	57	GMG40060	GMG40901	-	-	-	-
8.0	.315	8	19	25	63	GMG40080	GMG40902	GMG40903	GMG40904	-	-
10.0	.3937	10	22	30	72	GMG40100	GMG40905	GMG40906	GMG40907	-	-
12.0	.4724	12	26	35	83	GMG40120	GMG40908	GMG40909	GMG40910	GMG4091	-
14.0	.5512	14	26	35	83	-	GMG40140	-	GMG40912	-	-
16.0	.6299	16	35	43	92	-	GMG40160	GMG40913	GMG40914	GMG40915	GMG40916
20.0	.7874	20	44	56	110	-	GMG40200	GMG40917	GMG40918	GMG40919	GMG40920
25.0	.9843	25	55	70	130	-	GMG40250	GMG40922	GMG40923	GMG40924	GMG40925

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	h6


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	○	○				◎	○						◎	○

TitaNox-POWER END MILLS

GMG24 SERIES CHAMFER
GMG26 SERIES CHAMFER

CARBIDE, 5 FLUTE STANDARD LENGTH

- ▶ Excellent performance results and long tool life when machining Titanium and other tough materials
- ▶ This tool has high rigidity of flute so that is possible to use for heavy profile and high speed milling
- ▶ For protecting Corner chipping of end teeth, Corner Radius & Chamfer are adopted



MG HM 5 43°/44°/45° PLAIN C x 45° P.976


Unit : mm

OD		SD	LOC	OAL	Chamfer
Metric	Inch				EDP No.
D1		D2	L1	L2	EDP No.
6.0	.2362	6	10	54	GMG24060
		6	13	57	GMG26060
8.0	.315	8	12	58	GMG24080
		8	19	63	GMG26080
10.0	.3937	10	14	66	GMG24100
		10	22	72	GMG26100
12.0	.4724	12	16	73	GMG24120
		12	26	83	GMG26120
16.0	.6299	16	22	82	GMG24160
		16	36	92	GMG26160
20.0	.7874	20	26	92	GMG24200
		20	44	104	GMG26200
25.0	.9843	25	29	100	GMG24250
		25	54	121	GMG26250

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	h6

CHAMFER KEY

Mill Diameter		Chamfer Size (mm)
Metric	Inch	
6.0	.2362	0.20
8.0	.315	0.20
10.0	.3937	0.30
12.0	.4724	0.35
16.0	.6299	0.40
20.0	.7874	0.50
25.0	.9843	0.50



P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○	○	○				◎	○						◎	○


TitaNox-POWER END MILLS

GMG28 SERIES CORNER RADIUS

GMG30 SERIES CORNER RADIUS

CARBIDE, 5 FLUTE CORNER RADIUS STANDARD LENGTH

- ▶ Excellent performance results and long tool life when machining Titanium and other tough materials
- ▶ This tool has high rigidity of flute so that is possible to use for heavy profile and high speed milling
- ▶ For protecting Corner chipping of end teeth, Corner Radius & Chamfer are adopted



Metric	Inch	D1	SD	LOC	OAL	Corner Radius								
						0.30	0.50	1.00	1.50	2.00	2.50	3.00	4.00	5.00
			D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	
6.0	.2362	6	6	10	54	-	GMG28060	-	-	-	-	-	-	
		6	6	13	57	GMG30060	GMG30901	GMG30902	-	-	-	-	-	
8.0	.315	8	8	12	58	-	GMG28080	-	-	-	-	-	-	
		8	8	19	63	-	GMG30080	GMG30903	GMG30904	GMG30905	-	-	-	
10.0	.3937	10	10	14	66	-	GMG28100	-	-	-	-	-	-	
		10	10	22	72	-	GMG30100	GMG30906	GMG30907	GMG30908	-	-	-	
12.0	.4724	12	12	16	73	-	GMG28120	-	-	-	-	-	-	
		12	12	26	83	-	GMG30120	GMG30909	GMG30910	GMG30911	GMG30912	GMG30913	-	
16.0	.6299	16	16	22	82	-	-	GMG28160	-	-	-	-	-	
		16	16	36	92	-	-	GMG30160	GMG30914	GMG30915	GMG30916	GMG30917	GMG30918	
20.0	.7874	20	20	26	92	-	-	GMG28200	-	-	-	-	-	
		20	20	44	104	-	-	GMG30200	GMG30919	GMG30920	GMG30921	GMG30922	GMG30923	GMG30924
25.0	.9843	25	25	29	100	-	-	GMG28250	-	-	-	-	-	
		25	25	54	121	-	-	GMG30250	GMG30925	GMG30926	GMG30927	GMG30928	GMG30929	GMG30930

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~.0012	h6

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRC20	HRC20~30	HRC30~40	HR c40~45 HRc45~55	HRc55~70									
○	○	○			◎	○						◎	○

TitaNox-POWER END MILLS



RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE DOUBLE CORE - INCH

UGMG42, UGMG43 SERIES

ISO Hardness (Brinell)	Work Materials	Type of Cut	Speed and Feed Recommendations				Diameter (in.)						
			Ap x D1	Ae x D1	Vc (SFM)	Parameters	1/4	5/16	3/8	1/2	5/8	3/4	1
P <300	CARBON STEELS 10**, 11**, 12**, 12L**, 15**	Side Cutting	1 *(0.7)	0.4	525 (420-630)	RPM	8021	6417	5347	4010	3208	2674	2005
						Fz	.0011	.0014	.0017	.0021	.0025	.0030	.0033
		Slotting	1 *(0.7)	1	410 (328-492)	RPM	6266	5013	4178	3133	2507	2089	1567
						Fz	.0010	.0013	.0017	.0019	.0025	.0028	.0033
P <300 P <380	ALLOY STEELS 41**, 43**, 51**, 86**	Side Cutting	1 *(0.7)	0.4	492 (394-591)	RPM	7520	6016	5013	3760	3008	2507	1880
						Fz	.0010	.0014	.0017	.0019	.0025	.0028	.0033
		Slotting	1 *(0.7)	1	394 (315-472)	RPM	6016	4813	4010	3008	2406	2005	1504
						Fz	.0010	.0013	.0017	.0019	.0025	.0028	.0030
P <380	TOOL STEELS A2, D2, H13, P20, T15	Side Cutting	1 *(0.7)	0.4	492 (394-591)	RPM	7520	6016	5013	3760	3008	2507	1880
						Fz	.0011	.0014	.0018	.0021	.0026	.0030	.0033
		Slotting	1 *(0.7)	1	394 (315-472)	RPM	6016	4813	4010	3008	2406	2005	1504
						Fz	.0011	.0014	.0017	.0021	.0025	.0030	.0033
K <260	CAST IRON Gray, Malleable, Ductile	Side Cutting	1 *(0.7)	0.4	574 (459-689)	RPM	8773	7018	5849	4386	3509	2924	2193
						Fz	.0008	.0011	.0014	.0017	.0021	.0024	.0028
		Slotting	1 *(0.7)	1	459 (367-551)	RPM	7018	5615	4679	3509	2807	2339	1755
						Fz	.0008	.0011	.0014	.0017	.0021	.0024	.0026

RPM = rev./min. Feed = in./min. SFM = ft./min. Fz = in./tooth



- NOTES:**
- ▶ Maximum recommended depth shown
 - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
 - ▶ Feed to be reduced by approximately 50% if L.O.C.(length of cut) is over 3xD
 - ▶ Reduce speed and feed recommendations for materials harder than listed
 - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions









*(0.7D): UGMG42K998, UGMG42K999, UGMGK801
0.7D cutting depth for slotting and side cutting applications due to short double-core length

TitaNox-POWER END MILLS


RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE DOUBLE CORE - INCH


UGMG42, UGMG43 SERIES

ISO Hardness (Brinell)	Work Materials	Type of Cut	Speed and Feed Recommendations				Diameter (in.)						
			Ap x D1	Ae x D1	Vc (SFM)	Parameters	1/4	5/16	3/8	1/2	5/8	3/4	1
M	STAINLESS STEELS 300 304, 316, 304L, 316L, SUS316	Side Cutting 	1 *(0.7)	0.4	344 (276-413)	RPM	5264	4211	3509	2632	2106	1755	1316
						Fz	.0010	.0013	.0016	.0019	.0024	.0028	.0032
						Feed (IPM)	20.47	22.68	23.10	19.69	20.47	19.69	16.73
		Slotting 	1 *(0.7)	1	279 (223-335)	RPM	4261	3409	2841	2131	1704	1420	1065
						Fz	.0010	.0013	.0016	.0019	.0024	.0028	.0032
						Feed (IPM)	16.57	18.36	18.70	15.94	16.57	15.94	13.55
M	STAINLESS STEELS 400 416, 420F, 430F, 440F	Side Cutting 	1 *(0.7)	0.4	509 (407-610)	RPM	7770	6216	5180	3885	3108	2590	1943
						Fz	.0013	.0018	.0022	.0026	.0034	.0037	.0045
						Feed (IPM)	41.85	44.64	46.50	40.69	41.85	38.75	34.87
		Slotting 	1 *(0.7)	1	410 (328-492)	RPM	6266	5013	4178	3133	2507	2089	1567
						Fz	.0013	.0018	.0022	.0026	.0032	.0037	.0041
						Feed (IPM)	33.75	36.00	37.50	32.81	31.87	31.25	25.78
M	STAINLESS STEELS (PH) 17-4PH, 15-5PH, 13-8PH	Side Cutting 	0.6	0.4	144 (115-173)	RPM	2206	1765	1471	1103	882	735	551
						Fz	.0006	.0008	.0010	.0013	.0016	.0018	.0021
						Feed (IPM)	5.61	5.81	6.16	5.61	5.54	5.28	4.54
		Slotting 	0.5	1	118 (94-142)	RPM	1805	1444	1203	902	722	602	451
						Fz	.0006	.0008	.0010	.0013	.0016	.0018	.0021
						Feed (IPM)	4.59	4.75	5.04	4.59	4.54	4.32	3.71
S	TITANIUM Ti6Al4V Ti5Al5V5Mo Ti7Al4Mo	Side Cutting 	1 *(0.7)	0.4	230 (184-276)	RPM	3509	2807	2339	1755	1404	1170	877
						Fz	.0013	.0019	.0022	.0026	.0034	.0037	.0045
						Feed (IPM)	18.90	21.00	21.00	18.37	18.90	17.50	15.75
		Slotting 	1 *(0.7)	1	180 (144-217)	RPM	2757	2206	1838	1379	1103	919	689
						Fz	.0013	.0018	.0022	.0026	.0034	.0037	.0041
						Feed (IPM)	14.85	15.84	16.50	14.44	14.85	13.75	11.34

RPM = rev./min. Feed = in./min.
SFM = ft./min. Fz = in./tooth



Axial cutting depth



- NOTES:**
- ▶ Maximum recommended depth shown
 - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
 - ▶ Feed to be reduced by approximately 50% if L.O.C.(length of cut) is over 3xD
 - ▶ Reduce speed and feed recommendations for materials harder than listed
 - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions









*(0.7D): UGMG42K998, UGMG42K999, UGMGK801
0.7D cutting depth for slotting and side cutting applications due to short double-core length

TitaNox-POWER END MILLS


RECOMMENDED CUTTING CONDITIONS

CARBIDE, 5 FLUTE - INCH

UGMH12, UGMG32, UGMG34, UGMH06, UGMH07 SERIES

ISO Hardness (Brinell)	Work Materials	Type of Cut	Speed and Feed Recommendations				Diameter (in.)												
			Ap x D1	Ae x D1	Vc (SFM)	Parameters	1/8	3/16	1/4	5/16	3/8	1/2	9/16	5/8	11/16	3/4	1	1-1/4	
P <300	CARBON STEELS 10**, 11**, 12**, 12L**, 15**	Side Cutting 	1.5	0.3	472 (378-567)	RPM	14438	9625	7219	5775	4813	3609	3208	2888	2625	2406	1805	1444	
						Fz	.0004	.0007	.0013	.0015	.0020	.0027	.0030	.0033	.0035	.0040	.0046		
						Feed (IPM)	28.88	33.69	48.32	43.20	47.37	44.76	43.58	43.20	42.89	42.16	35.88	33.21	
P <300 P <380	ALLOY STEELS 41**, 43**, 51**, 86**	Side Cutting 	1.5	0.3	331 (265-398)	RPM	10127	6751	5063	4051	3376	2532	2250	2025	1841	1688	1266	1013	
						Fz	.0004	.0007	.0013	.0015	.0020	.0027	.0030	.0033	.0035	.0040	.0046		
						Feed (IPM)	20.25	23.63	33.89	30.30	33.22	31.40	30.57	30.30	30.08	29.57	25.17	23.29	
P <380	TOOL STEELS A2, D2, H13, P20, T15	Side Cutting 	1.5	0.3	197 (157-236)	RPM	6016	4010	3008	2406	2005	1504	1337	1203	1094	1003	752	602	
						Fz	.0003	.0005	.0009	.0011	.0014	.0017	.0019	.0021	.0023	.0024	.0028	.0033	
						Feed (IPM)	9.02	10.03	14.21	12.79	13.82	13.03	12.89	12.79	12.49	12.24	10.51	9.93	
K <260	CAST IRON Gray, Malleable, Ductile	Side Cutting 	1.5	0.3	348 (278-417)	RPM	10628	7085	5314	4251	3543	2657	2362	2126	1932	1771	1328	1063	
						Fz	.0006	.0008	.0017	.0019	.0025	.0031	.0034	.0038	.0041	.0044	.0050	.0057	
						Feed (IPM)	31.88	28.34	44.98	40.17	43.93	41.32	40.45	40.17	39.18	38.70	32.95	30.29	
M	STAINLESS STEELS 300 304, 316, 304L, 316L, SUS316	Side Cutting 	1.5	0.3	269 (215-323)	RPM	8222	5481	4111	3289	2741	2055	1827	1644	1495	1370	1028	822	
						Fz	.0004	.0005	.0012	.0013	.0015	.0025	.0026	.0027	.0028	.0030	.0035	.0041	
						Feed (IPM)	16.44	13.70	24.28	20.72	20.50	23.38	22.33	20.60	20.50	17.80	16.85		
M	STAINLESS STEELS 400 416, 420F, 430F, 440F	Side Cutting 	1.5	0.3	384 (307-461)	RPM	11731	7820	5865	4692	3910	2933	2607	2346	2133	1955	1466	1173	
						Fz	.0003	.0004	.0009	.0010	.0012	.0018	.0020	.0021	.0022	.0024	.0028	.0033	
						Feed (IPM)	17.60	15.64	27.71	23.09	23.09	26.56	26.17	24.94	23.93	23.48	20.49	19.36	
M	STAINLESS STEELS (PH) 17-4PH, 15-5PH, 13-8PH	Side Cutting 	1.5	0.3	194 (155-232)	RPM	5915	3944	2958	2366	1972	1479	1315	1183	1076	986	739	592	
						Fz	.0004	.0005	.0012	.0013	.0015	.0025	.0026	.0027	.0028	.0030	.0035	.0041	
						Feed (IPM)	11.83	9.86	17.47	14.91	14.75	18.34	16.82	16.07	14.82	14.75	12.81	12.13	
S	TITANIUM Ti6Al4V Ti5Al5V5Mo Ti7Al4Mo	Side Cutting 	1.5	0.2	226 (181-272)	RPM	6918	4612	3459	2767	2306	1730	1537	1384	1258	1153	865	692	
						Fz	.0004	.0004	.0011	.0011	.0013	.0022	.0023	.0024	.0025	.0027	.0031	.0036	
						Feed (IPM)	13.84	9.22	18.38	15.80	15.43	19.41	17.86	16.89	15.60	15.66	13.45	12.45	

RPM = rev./min. Feed = in./min.
SFM = ft./min. Fz = in./tooth



- NOTES:**
- ▶ Maximum recommended depth shown
 - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
 - ▶ Feed to be reduced by approximately 50% if L.O.C.(length of cut) is over 3xD
 - ▶ Reduce speed and feed recommendations for materials harder than listed
 - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions



RECOMMENDED CUTTING CONDITIONS


CARBIDE, 4 FLUTE DOUBLE CORE - METRIC

GMG40 SERIES

ISO Hardness (Brinell)	Work Materials	Speed and Feed Recommendations				Diameter (mm)								
		Type of Cut	Ap x D1	Ae x D1	Vc (SFM)	Parameters	6	8	10	12	14	16	20	25
P <300	CARBON STEELS 10**, 11**, 12**, 12L**, 15**	Side Cutting	1	0.4	525 (420-630)	RPM	8488	6366	5093	4244	3638	3183	2546	2037
						Fz	.0011	.0014	.0017	.0021	.0023	.0025	.0030	.0033
						Feed (IPM)	36.09	35.09	33.69	35.42	33.23	31.58	30.88	26.95
		Slotting	1	1	410 (328-492)	RPM	6631	4974	3979	3316	2842	2487	1989	1592
						Fz	.0010	.0013	.0017	.0019	.0022	.0025	.0028	.0033
						Feed (IPM)	26.11	26.63	26.32	25.59	25.06	24.67	21.93	21.05
P <300 P <380	ALLOY STEELS 41**, 43**, 51**, 86**	Side Cutting	1	0.4	492 (394-591)	RPM	7958	5968	4775	3979	3410	2984	2387	1910
						Fz	.0010	.0014	.0017	.0019	.0022	.0025	.0028	.0033
						Feed (IPM)	31.33	32.90	31.58	30.70	30.08	29.61	26.32	25.26
		Slotting	1	1	394 (315-472)	RPM	6366	4775	3820	3183	2728	2387	1910	1528
						Fz	.0010	.0013	.0017	.0019	.0022	.0025	.0028	.0030
						Feed (IPM)	25.06	25.57	25.26	24.56	24.06	23.69	21.05	18.53
P <380	TOOL STEELS A2, D2, H13, P20, T15	Side Cutting	1	0.4	492 (394-591)	RPM	7958	5968	4775	3979	3410	2984	2387	1910
						Fz	.0011	.0014	.0018	.0021	.0024	.0026	.0030	.0033
						Feed (IPM)	33.84	32.90	34.59	33.21	32.22	31.49	28.95	25.26
		Slotting	1	1	394 (315-472)	RPM	6366	4775	3820	3183	2728	2387	1910	1528
						Fz	.0011	.0014	.0017	.0021	.0023	.0025	.0030	.0033
						Feed (IPM)	27.07	26.32	25.26	26.57	24.92	23.69	23.16	20.21
K <260	CAST IRON Gray, Malleable, Ductile	Side Cutting	1	0.4	574 (459-689)	RPM	9284	6963	5570	4642	3979	3482	2785	2228
						Fz	.0008	.0011	.0014	.0017	.0019	.0021	.0024	.0028
						Feed (IPM)	30.70	30.70	30.70	30.70	30.08	29.06	26.32	24.56
		Slotting	1	1	459 (367-551)	RPM	7427	5570	4456	3714	3183	2785	2228	1783
						Fz	.0008	.0011	.0014	.0017	.0019	.0021	.0024	.0026
						Feed (IPM)	24.56	24.56	24.56	24.56	24.06	23.25	21.05	18.81
M	STAINLESS STEELS 300 304, 316, 304L, 316L, SUS316	Side Cutting	1	0.4	344 (276-413)	RPM	5570	4178	3342	2785	2387	2089	1671	1337
						Fz	.0010	.0013	.0016	.0019	.0022	.0024	.0028	.0032
						Feed (IPM)	21.67	22.50	22.00	20.83	20.68	20.31	18.75	17.00
		Slotting	1	1	279 (223-335)	RPM	4509	3382	2706	2255	1933	1691	1353	1082
						Fz	.0010	.0013	.0016	.0019	.0022	.0024	.0028	.0032
						Feed (IPM)	17.54	18.22	17.81	16.87	16.74	16.44	15.18	13.76

RPM = rev./min. Feed = in./min.
SFM = ft./min. Fz = in./tooth

- NOTES:**
- ▶ Maximum recommended depth shown
 - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
 - ▶ Reduce speed and feed recommendations for materials harder than listed
 - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions



▶ NEXT PAGE




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE DOUBLE CORE - METRIC

GMG40 SERIES

ISO Hardness (Brinell)	Work Materials	Speed and Feed Recommendations				Diameter (mm)								
		Type of Cut	Ap x D1	Ae x D1	Vc (SFM)	Parameters	6	8	10	12	14	16	20	25
M	STAINLESS STEELS 400 416, 420F, 430F, 440F	Side Cutting	1	0.4	509 (407-610)	RPM	8223	6167	4934	4112	3524	3084	2467	1974
						Fz	.0013	.0018	.0022	.0026	.0030	.0034	.0037	.0045
						Feed (IPM)	44.29	44.29	44.29	43.06	42.18	41.52	36.91	35.43
		Slotting	1	1	410 (328-492)	RPM	6631	4974	3979	3316	2842	2487	1989	1592
						Fz	.0013	.0018	.0022	.0026	.0029	.0032	.0037	.0041
						Feed (IPM)	35.72	35.72	35.72	34.72	33.12	31.62	29.76	26.19
M	STAINLESS STEELS (PH) 17-4PH, 15-5PH, 13-8PH	Side Cutting	0.6	0.4	144 (115-173)	RPM	2334	1751	1401	1167	1000	875	700	560
						Fz	.0006	.0008	.0010	.0013	.0014	.0016	.0018	.0021
						Feed (IPM)	5.94	5.76	5.87	5.94	5.67	5.50	5.03	4.61
		Slotting	0.5	1	118 (94-142)	RPM	1910	1432	1146	955	819	716	573	458
						Fz	.0006	.0008	.0010	.0013	.0014	.0016	.0018	.0021
						Feed (IPM)	4.86	4.71	4.80	4.86	4.64	4.50	4.11	3.77
S	TITANIUM Ti6Al4V, Ti5Al5V5Mo, Ti7Al4Mo	Side Cutting	1	0.4	230 (184-276)	RPM	3714	2785	2228	1857	1592	1393	1114	891
						Fz	.0013	.0019	.0022	.0026	.0030	.0034	.0037	.0045
						Feed (IPM)	20.00	20.83	20.00	19.45	19.05	18.75	16.67	16.00
		Slotting	1	1	180 (144-217)	RPM	2918	2188	1751	1459	1251	1094	875	700
						Fz	.0013	.0018	.0022	.0026	.0030	.0034	.0037	.0041
						Feed (IPM)	15.71	15.71	15.71	15.28	14.97	14.73	13.10	11.52

RPM = rev./min. Feed = in./min.
SFM = ft./min. Fz = in./tooth



- NOTES:**
- ▶ Maximum recommended depth shown
 - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
 - ▶ Reduce speed and feed recommendations for materials harder than listed
 - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

CARBIDE

HSS

CBN
END MILLS

i-Xmill
END MILLS

i-SMART
MODULAR
TYPE END MILLS

X5070
END MILLS

4G MILL
END MILLS

X-POWER
END MILLS

JET-POWER
END MILLS

TitaNox
-POWER
END MILLS

V7 PLUS A
END MILLS

V7 MILL INOX
END MILLS

ALU-POWER
HPC
END MILLS

ALU-POWER
END MILLS

D-POWER
GRAPHITE
END MILLS

D-POWER
CFRP
END MILLS

ROUTERS
CFRP

STANDARD
CARBIDE
END MILLS

ONLY ONE
COATED PM60
END MILLS

SINE-POWER
END MILLS

TANK-POWER
END MILLS

STANDARD
COBALT & HSS
END MILLS









TECHNICAL
DATA

TitaNox-POWER END MILLS

RECOMMENDED CUTTING CONDITIONS


CARBIDE, 5 FLUTE - METRIC

GMG24, GMG26, GMG28, GMG30 SERIES

ISO Hardness (Brinell)	Work Materials	Type of Cut	Speed and Feed Recommendations				Diameter (in.)								
			Ap x D1	Ae x D1	Vc (SFM)	Parameters	6	8	10	12	14	16	18	20	25
P <300	CARBON STEELS 10**, 11**, 12**, 12L**, 15**	Side Cutting 	1.5	0.3	472 (378-567)	RPM	7639	5730	4584	3820	3274	2865	2546	2292	1833
						Fz	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040
						Feed (IPM)	51.13	42.86	45.11	47.37	44.47	42.86	41.61	40.15	36.45
P <300 P <380	ALLOY STEELS 41**, 43**, 51**, 86**	Side Cutting 	1.5	0.3	331 (265-398)	RPM	5358	4019	3215	2679	2296	2009	1786	1607	1286
						Fz	.0013	.0015	.0020	.0025	.0027	.0030	.0033	.0035	.0040
						Feed (IPM)	35.86	30.06	31.64	33.23	31.19	30.06	29.18	28.16	25.57
P <380	TOOL STEELS A2, D2, H13, P20, T15	Side Cutting 	1.5	0.3	197 (157-236)	RPM	3183	2387	1910	1592	1364	1194	1061	955	764
						Fz	.0009	.0011	.0014	.0017	.0019	.0021	.0023	.0024	.0028
						Feed (IPM)	15.04	12.69	13.16	13.79	13.16	12.69	12.11	11.65	10.68
K <260	CAST IRON Gray, Malleable, Ductile	Side Cutting 	1.5	0.3	348 (278-417)	RPM	5623	4218	3374	2812	2410	2109	1874	1687	1350
						Fz	.0017	.0019	.0025	.0031	.0034	.0038	.0041	.0044	.0050
						Feed (IPM)	47.60	39.85	41.84	43.73	41.27	39.85	38.01	36.86	33.48
M	STAINLESS STEELS 300 304, 316, 304L, 316L, SUS316	Side Cutting 	1.5	0.3	269 (215-323)	RPM	4350	3263	2610	2175	1864	1631	1450	1305	1044
						Fz	.0012	.0013	.0015	.0025	.0026	.0027	.0028	.0030	.0035
						Feed (IPM)	25.69	20.55	19.52	26.97	23.86	22.16	19.98	19.52	18.09
M	STAINLESS STEELS 400 416, 420F, 430F, 440F	Side Cutting 	1.5	0.3	384 (307-461)	RPM	6207	4655	3724	3104	2660	2328	2069	1862	1490
						Fz	.0009	.0010	.0012	.0018	.0020	.0021	.0022	.0024	.0028
						Feed (IPM)	29.32	22.91	21.99	28.10	26.71	24.74	23.22	22.36	20.82
M	STAINLESS STEELS (PH) 17-4PH, 15-5PH, 13-8PH	Side Cutting 	1.5	0.3	194 (155-232)	RPM	3130	2348	1878	1565	1341	1174	1043	939	751
						Fz	.0012	.0013	.0015	.0025	.0026	.0027	.0028	.0030	.0035
						Feed (IPM)	18.48	14.79	14.05	19.41	17.16	15.94	14.38	14.05	13.01
S	TITANIUM Ti6Al4V Ti5Al5V5Mo Ti7Al4Mo	Side Cutting 	1.5	0.3	226 (181-272)	RPM	3661	2745	2196	1830	1569	1373	1220	1098	879
						Fz	.0011	.0011	.0013	.0022	.0023	.0024	.0025	.0027	.0031
						Feed (IPM)	19.46	15.67	14.70	20.54	18.22	16.75	15.13	14.92	13.66

RPM = rev./min. Feed = in./min.
SFM = ft./min. Fz = in./tooth

Side Cutting



- NOTES:**
- ▶ Maximum recommended depth shown
 - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D1 or less
 - ▶ Reduce speed and feed recommendations for materials harder than listed
 - ▶ Recommendations above are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions

CARBIDE



Being the best through innovation



V7 PLUS A END MILLS

- Silent Cutting of Steels up to HRc40
Designed as Unequal Leads.



SQUARE



CHAMFER




CORNER RADIUS



BALL NOSE

CARBIDE, 4 FLUTE STANDARD LENGTH

- ▶ Special flute geometry and multiple helix eliminate vibrations
- ▶ Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRc40
- ▶ Advanced coating for superior performance and tool life



MG HM 4 35°/37° PLAIN ±.0008 C x 45° P.1006~1010

Unit : Inch

OD	SD	LOC	OAL	Square End	Chamfer	Corner Radius								Ball Nose
						.010	.015	.030	.060	.090	.125	.190	.250	
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
1/8	1/8	1/8	1/2	UGMF68008	-	UGMF70008	-	UGMF70955	-	-	-	-	-	UGMG53901
		3/8	1/2	UGMF68901	-	UGMF70901	-	UGMF70902	-	-	-	-	-	UGMG53008
		1/2	2/1	UGMF68915	-	UGMF70956	-	UGMF70957	-	-	-	-	-	UGMG53902
5/32	3/16	3/16	2	UGMF68010	-	UGMF70010	-	-	-	-	-	-	-	UGMG53903
		7/16	2	UGMF68902	-	UGMF70958	-	-	-	-	-	-	-	UGMG53010
		3/16	2	UGMF68012	-	UGMF70012	-	-	-	-	-	-	-	UGMG53904
3/16	3/16	5/16	2	UGMF68916	-	UGMF70959	-	UGMF70960	-	-	-	-	-	UGMG53905
		7/16	2	UGMF68903	-	UGMF70903	-	UGMF70904	-	-	-	-	-	UGMG53012
		5/8	2/1	UGMF68917	-	UGMF70961	-	UGMF70962	-	-	-	-	-	UGMG53906
7/32	1/4	1/4	2	UGMF68014	-	UGMF70014	-	-	-	-	-	-	-	UGMG53907
		7/16	2/1	UGMF68904	-	UGMF70963	-	-	-	-	-	-	-	UGMG53014
		3/8	2	UGMF68016	UGMF76016	UGMF70016	-	UGMF70905	UGMF70906	-	-	-	-	UGMG53908
1/4	1/4	1/2	2/1	UGMF68918	-	-	UGMF70964	UGMF70965	UGMF70966	-	-	-	-	UGMG53016
		3/4	2/1	UGMF68905	UGMF76902	UGMF70907	UGMF70908	UGMF70909	UGMF70967	-	-	-	-	UGMG53909
		1	3	UGMF68919	-	-	UGMF70968	UGMF70969	UGMF70970	-	-	-	-	UGMG53910
9/32	5/16	5/8	2/1	UGMF68018	-	-	UGMF70018	UGMF70971	UGMF70972	-	-	-	-	UGMG53018
		1	3	UGMF68920	-	-	UGMF70973	UGMF70974	-	-	-	-	-	UGMG53911
		7/16	2	UGMF68020	-	-	-	UGMF70020	-	-	-	-	-	UGMG53912
5/16	5/16	13/16	2/1	UGMF68906	UGMF76020	UGMF70910	-	UGMF70911	UGMF70912	-	-	-	-	UGMG53020
		1-1/4	3	UGMF68921	-	-	UGMF70975	UGMF70976	UGMF70977	-	-	-	-	UGMG53913
		1/2	2/1	UGMF68022	-	-	-	UGMF70022	-	-	-	-	-	UGMG53914
11/32	3/8	13/16	2/1	UGMF68922	-	-	-	UGMF70978	-	-	-	-	-	UGMG53022
		1/2	2/1	UGMF68024	UGMF76903	UGMF70024	-	UGMF70913	UGMF70914	UGMF70979	-	-	-	UGMG53915
		7/8	2/1	UGMF68907	UGMF76024	UGMF70915	-	UGMF70916	UGMF70917	UGMF70980	-	-	-	UGMG53024
3/8	3/8	1	3	UGMF68923	-	UGMF70981	-	UGMF70982	UGMF70983	UGMF70984	-	-	-	UGMG53916
		1-1/4	3	UGMF68924	-	UGMF70985	-	UGMF70986	UGMF70987	UGMF70988	-	-	-	UGMG53917

NOTE: * Length of cut in excess of 3xD on 37° single-helix requires feed reduction of approximately 50% ▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	○



SQUARE



CHAMFER




CORNER RADIUS



BALL NOSE

CARBIDE, 4 FLUTE STANDARD LENGTH

- ▶ Special flute geometry and multiple helix eliminate vibrations
- ▶ Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRc40
- ▶ Advanced coating for superior performance and tool life



MG HM 4 35°/37° PLAIN ±.0008 C x 45° P.1006~1010

Unit : Inch

OD	SD	LOC	OAL	Square End	Chamfer	Corner Radius								Ball Nose	
						.010	.015	.030	.060	.090	.125	.190	.250		
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	
13/32	7/16	1/2	2/3	UGMF68026	-	-	-	UGMF70026	-	-	-	-	-	UGMG53026	
		15/16	2/3	UGMF68925	-	-	-	UGMF70989	-	-	-	-	-	UGMG53918	
7/16	7/16	5/8	2-1/2	UGMF68028	-	-	UGMF70028	UGMF70918	UGMF70990	UGMF70991	-	-	-	UGMG53919	
		7/8	2-3/4	UGMF68926	UGMF76028	-	UGMF70992	UGMF70993	UGMF70994	UGMF70995	-	-	-	UGMG53920	
		1	2-3/4	UGMF68908	-	UGMF70919	-	UGMF70920	UGMF70921	-	-	-	-	UGMG53028	
15/32	1/2	5/8	2-1/2	UGMF68030	-	-	-	UGMF70030	-	-	-	-	-	UGMG53030	
		1	3	UGMF68927	-	-	-	UGMF70996	-	-	-	-	-	UGMG53921	
		1-1/4	3-1/2	UGMF68928	-	-	-	UGMF70997	-	-	-	-	-	UGMG53922	
1/2	1/2	5/8	2-1/2	UGMF68032	UGMF76032	UGMF70032	UGMF70922	UGMF70923	UGMF70924	UGMF70998	UGMF70999	-	-	UGMG53923	
		1	3	UGMF68909	UGMF76904	UGMF70925	UGMF70801	UGMF70926	UGMF70927	UGMF70802	UGMF70928	-	-	UGMG53032	
		1-1/4	3-1/2	UGMF68910	UGMF76901	UGMF70929	UGMF70930	UGMF70931	UGMF70932	UGMF70803	UGMF70933	-	-	UGMG53924	
		1-5/8	4	UGMF68929	UGMF76905	-	UGMF70934	UGMF70935	UGMF70936	UGMF70804	UGMF70937	UGMF70805	UGMF70938	-	UGMG53925
		2	4	UGMF68939	-	-	UGMF70939	UGMF70940	UGMF70941	UGMF70942	UGMF70806	UGMF70943	UGMF70807	UGMF70944	UGMG53939
		2-1/2	4-1/2	UGMF68940	UGMF76906	-	UGMF70945	UGMF70946	UGMF70947	UGMF70948	UGMF70808	UGMF70949	UGMF70809	UGMF70950	UGMG53940
5/8	5/8	3/4	3	UGMF68040	-	UGMF70040	UGMF70809	UGMF70934	UGMF70935	UGMF70810	UGMF70811	-	-	UGMG53926	
		1-1/4	3-1/2	UGMF68911	UGMF76040	UGMF70936	UGMF70937	UGMF70938	UGMF70939	UGMF70812	UGMF70940	-	-	UGMG53040	
		1-5/8	4	UGMF68930	UGMF76907	-	UGMF70813	UGMF70814	UGMF70815	UGMF70816	UGMF70817	-	-	UGMG53927	
		2	4	UGMF68931	-	-	UGMF70818	UGMF70819	UGMF70820	UGMF70821	UGMF70822	-	-	UGMG53928	
3/4	3/4	3-1/4	6	UGMF68932	-	-	UGMF70823	UGMF70824	UGMF70825	UGMF70826	UGMF70827	-	-	UGMG53929	
		3/4	3	UGMF68048	UGMF76908	-	UGMF70828	UGMF70048	UGMF70941	UGMF70829	UGMF70830	UGMF70831	UGMF70832	UGMG53930	
		1-1/2	4	UGMF68912	UGMF76048	-	UGMF70942	UGMF70943	UGMF70944	UGMF70833	UGMF70945	UGMF70834	UGMF70835	UGMG53048	
		1-7/8	4	UGMF68933	-	-	UGMF70836	UGMF70837	UGMF70838	UGMF70839	UGMF70840	UGMF70841	UGMF70842	UGMG53931	
3/8	3/8	2-1/4	5	UGMF68934	UGMF76909	-	UGMF70843	UGMF70844	UGMF70845	UGMF70846	UGMF70847	UGMF70848	UGMF70849	UGMG53932	
		3-1/4	6	UGMF68935	-	-	UGMF70850	UGMF70851	UGMF70852	UGMF70853	UGMF70854	UGMF70855	UGMF70856	UGMG53933	

NOTE: * Length of cut in excess of 3xD on 37° single-helix requires feed reduction of approximately 50% ▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	



CARBIDE, 4 FLUTE STANDARD LENGTH

- ▶ Special flute geometry and multiple helix eliminate vibrations
- ▶ Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRC40
- ▶ Advanced coating for superior performance and tool life




Unit : Inch

OD	SD	LOC	OAL	Square End	Chamfer	Corner Radius						Ball Nose		
						.010	.015	.030	.060	.090	.125		.190	.250
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	
1	1	1	4	UGMF68064	UGMF76910	-	UGMF70064	UGMF70946	UGMF70947	UGMF70857	UGMF70858	UGMF70859	UGMF70860	UGMG53934
		1-1/2	4	UGMF68913	UGMF76064	-	UGMF70948	UGMF70949	UGMF70950	UGMF70861	UGMF70951	UGMF70862	UGMF70863	UGMG53064
		2	5	UGMF68914	UGMF76911	-	UGMF70952	UGMF70953	UGMF70954	UGMF70864	UGMF70865	UGMF70866	UGMF70867	UGMG53935
		2-5/8	5	UGMF68936	UGMF76912	-	UGMF70868	UGMF70869	UGMF70870	UGMF70871	UGMF70872	UGMF70873	UGMF70874	UGMG53936
		3	6	UGMF68937	-	-	UGMF70875	UGMF70876	UGMF70877	UGMF70878	UGMF70879	UGMF70880	UGMF70881	UGMG53937
		4-1/4	7	UGMF68938	-	-	UGMF70882	UGMF70883	UGMF70884	UGMF70885	UGMF70886	UGMF70887	UGMF70888	UGMG53938
		4-1/4	7	UGMF68938	-	-	UGMF70882	UGMF70883	UGMF70884	UGMF70885	UGMF70886	UGMF70887	UGMF70888	UGMG53938

CHAMFER KEY		BALL NOSE KEY	
Mill Diameter	Chamfer Size	Mill Diameter	Radius of Ball
1/4	.007	1/8	1/16
5/16	.007	5/32	5/64
3/8	.011	3/16	3/32
7/16	.013	7/32	7/64
1/2	.013	1/4	1/8
5/8	.015	9/32	9/64
3/4	.019	5/16	5/32
1	.019	11/32	11/64
		3/8	3/16
		7/16	7/32
		1/2	1/4
		5/8	5/16
		3/4	3/8
		1	1/2

NOTE: * Length of cut in excess of 3xD on 37° single-helix requires feed reduction of approximately 50%



Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~.0012	h6



© : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	○



CARBIDE, 4 FLUTE STANDARD LENGTH

- ▶ Special flute geometry and multiple helix eliminate vibrations
- ▶ Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRC40
- ▶ Advanced coating for superior performance and tool life



Unit : Inch

OD	SD	LOC	OAL	Square End	Chamfer	Corner Radius						Ball Nose
						.010	.015	.030	.060	.090	.125	
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
11/32	3/8	1/2	2-1/2	UGMF69022	-	-	-	-	-	-	-	-
		13/16	2-1/2	-	-	-	-	-	-	-	-	UGMG54022
3/8	3/8	1/2	2-1/2	UGMF69024	UGMF77902	UGMF71024	-	UGMF71913	UGMF71914	-	-	-
		7/8	2-1/2	UGMF69907	UGMF77024	UGMF71915	-	UGMF71916	UGMF71917	-	-	UGMG54024
7/16	7/16	5/8	2-1/2	UGMF69028	-	-	UGMF71028	UGMF71918	-	-	-	-
		1	2-3/4	UGMF69908	-	UGMF71919	-	UGMF71920	UGMF71921	-	-	UGMG54028
1/2	1/2	5/8	2-1/2	UGMF69032	UGMF77032	UGMF71032	UGMF71922	UGMF71923	UGMF71924	-	-	-
		1	3	UGMF69909	UGMF77903	UGMF71925	-	UGMF71926	UGMF70927	-	UGMF71928	UGMG54032
		1-1/4	3-1/2	UGMF69910	UGMF77901	UGMF71929	UGMF71930	UGMF71931	UGMF71932	-	UGMF71933	-
		2	4	UGMF69915	-	-	UGMF71935	UGMF71936	UGMF71937	UGMF71938	UGMF71939	UGMG54901
5/8	5/8	2-1/2	4-1/2	UGMF69916	-	-	UGMF71940	UGMF71941	UGMF71942	UGMF71943	UGMF71944	UGMG54902
		3/4	3	UGMF69040	UGMF77904	UGMF71040	-	UGMF71934	UGMF71935	-	-	-
3/4	3/4	1-1/4	3-1/2	UGMF69911	UGMF77040	UGMF71936	UGMF71937	UGMF71938	UGMF71939	-	UGMF71940	UGMG54040
		3/4	3	UGMF69048	UGMF77905	-	-	UGMF71048	UGMF71941	-	-	-
3/4	3/4	1-1/2	4	UGMF69912	UGMF77048	-	UGMF71942	UGMF71943	UGMF71944	-	UGMF71945	UGMG54048

NOTE: * Length of cut in excess of 3xD on 37° single-helix requires feed reduction of approximately 50%

▶ NEXT PAGE

© : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	○



UGMF69 SQUARE


UGMF77 CHAMFER

UGMF71 CORNER RADIUS

UGMG54 BALL NOSE

CARBIDE, 4 FLUTE STANDARD LENGTH

- ▶ Special flute geometry and multiple helix eliminate vibrations
- ▶ Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRc40
- ▶ Advanced coating for superior performance and tool life



MG HM 4 35°/37° FLAT ±.0008 C x 45° P.1006~1010

Unit : Inch

OD	SD	LOC	OAL	Square End	Chamfer	Corner Radius						Ball Nose
						.010	.015	.030	.060	.090	.125	
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
1	1	1	4	UGMF69064	UGMF77906	-	UGMF71064	UGMF71946	UGMF71947	-	-	-
		1-1/2	4	UGMF69913	UGMF77064	-	UGMF71948	UGMF71949	UGMF71950	-	UGMF71951	UGMG54064
		2	5	UGMF69914	UGMF77907	-	UGMF71952	UGMF71953	UGMF71954	-	-	-


CHAMFER KEY

Mill Diameter	Chamfer Size
1/4	.007
5/16	.007
3/8	.011
7/16	.013
1/2	.013
5/8	.015
3/4	.019
1	.019

BALL NOSE KEY

Mill Diameter	Radius of Ball
1/8	1/16
5/32	5/64
3/16	3/32
7/32	7/64
1/4	1/8
9/32	9/64
5/16	5/32
11/32	11/64
3/8	3/16
7/16	7/32
1/2	1/4
5/8	5/16
3/4	3/8
1	1/2

NOTE: * Length of cut in excess of 3xD on 37° single-helix requires feed reduction of approximately 50%



◎ : Excellent ○ : Good


P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	○



UGMF72 SERIES SQUARE
UGMF74 SERIES CORNER RADIUS
UGMH10 SERIES BALL NOSE

CARBIDE, 4 FLUTE EXTENDED LENGTH

- ▶ Special flute geometry and multiple helix eliminate vibrations
- ▶ Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRc40
- ▶ Advanced coating for superior performance and tool life



MG HM 4 35°/37° PLAIN ±.0008 P.1006~1010

Unit : Inch

OD	SD	LOC	LBS	OAL	Square End	Corner Radius								Ball Nose
						.010	.015	.030	.060	.090	.125	.190	.250	
D1	D2	L1	L3	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	
1/8	1/8	5/32	3/8	3	UGMF72008	UGMF74008	-	UGMF74913	-	-	-	-	-	UGMH10008
		5/32	1/2	3	UGMF72913	UGMF74914	-	UGMF74915	-	-	-	-	-	UGMH10901
		5/32	5/8	3	UGMF72914	UGMF74916	-	UGMF74917	-	-	-	-	-	UGMH10902
3/16	3/16	7/32	1/2	3	UGMF72012	UGMF74012	-	UGMF74918	-	-	-	-	-	UGMH10012
		7/32	3/4	3	UGMF72915	UGMF74919	-	UGMF74920	-	-	-	-	-	UGMH10903
1/4	1/4	7/32	1	3	UGMF72916	UGMF74921	-	UGMF74922	-	-	-	-	-	UGMH10904
		3/8	3/4	4	UGMF72016	-	UGMF74016	UGMF74923	UGMF74924	-	-	-	-	UGMH10016
		3/8	1-1/8	4	UGMF72901	-	UGMF74901	UGMF74925	UGMF74926	-	-	-	-	UGMH10905
3/8	3/8	3/8	2-1/8	4	UGMF72902	-	UGMF74902	UGMF74927	UGMF74928	-	-	-	-	UGMH10906
		1/2	1-1/8	4	UGMF72024	-	UGMF74929	UGMF74024	UGMF74930	UGMF74931	-	-	-	UGMH10024
		1/2	2-1/8	4	UGMF72903	-	UGMF74932	UGMF74903	UGMF74933	UGMF74934	-	-	-	UGMH10907
3/8	3/8	1/2	3-1/8	5	UGMF72922	-	UGMF74815	UGMF74816	UGMF74817	UGMF74818	-	-	-	UGMH10922
		1/2	3-1/8	6	UGMF72904	-	UGMF74935	UGMF74904	UGMF74936	UGMF74937	-	-	-	UGMH10908
		1/2	4-1/8	6	UGMF72917	-	UGMF74938	UGMF74939	UGMF74940	UGMF74941	-	-	-	UGMH10909

▶ NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	○

CARBIDE

HSS

CBN END MILLS

i-Xmill END MILLS

i-SMART MODULAR TYPE END MILLS

X5070 END MILLS

4G MILL END MILLS

X-POWER END MILLS

JET-POWER END MILLS

TitaNox -POWER END MILLS

V7 PLUS A END MILLS

V7 MILL INOX END MILLS

ALU-POWER HPC END MILLS

ALU-POWER END MILLS

D-POWER GRAPHITE END MILLS

D-POWER CFRP END MILLS

ROUTERS CFRP

STANDARD CARBIDE END MILLS

ONLY ONE COATED PM60 END MILLS

SINE -POWER END MILLS

TANK-POWER END MILLS

STANDARD COBALT & HSS END MILLS


TECHNICAL DATA



UGMF72 SERIES SQUARE
UGMF74 SERIES CORNER RADIUS
UGMH10 SERIES BALL NOSE

CARBIDE, 4 FLUTE EXTENDED LENGTH

- Special flute geometry and multiple helix eliminate vibrations
Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRc40
Advanced coating for superior performance and tool life



MG HM 4 35°/37° PLAIN ±.0008 P.1006~1010

Table with columns: OD, SD, LOC, LBS, OAL, Square End, Corner Radius (.010 to .250), Ball Nose. Rows include various mill sizes like 1/2, 5/8, 3/4.

▶ NEXT PAGE

◎ : Excellent ○ : Good

Material compatibility table with columns P, H, M, K, N, S and rows for Carbon Steels, Alloy Steels, Prehardened Steels, Hardened Steels, High Hardened Steels, Stainless Steels, Cast Iron, Copper, Graphite, Aluminum, Acrylic, CFRP, Titanium, High Temperature Alloy.

CARBIDE

HSS

CBN END MILLS

i-Xmill END MILLS

i-SMART MODULAR TYPE END MILLS

X5070 END MILLS

4G MILL END MILLS

X-POWER END MILLS

JET-POWER END MILLS

TitaNox -POWER END MILLS

V7 PLUS A END MILLS

V7 MILL INOX END MILLS

ALU-POWER HPC END MILLS

ALU-POWER END MILLS

D-POWER GRAPHITE END MILLS

D-POWER CFRP END MILLS

ROUTERS CFRP

STANDARD CARBIDE END MILLS

ONLY ONE COATED PM60 END MILLS

SINE -POWER END MILLS

TANK-POWER END MILLS

STANDARD COBALT & HSS END MILLS


TECHNICAL DATA



UGMF72 SERIES SQUARE
UGMF74 SERIES CORNER RADIUS
UGMH10 SERIES BALL NOSE

CARBIDE, 4 FLUTE EXTENDED LENGTH

- Special flute geometry and multiple helix eliminate vibrations
Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRc40
Advanced coating for superior performance and tool life




MG HM 4 35°/37° PLAIN ±.0008 P.1006~1010

Table with columns: OD, SD, LOC, LBS, OAL, Square End, Corner Radius (.010 to .250), Ball Nose. Rows include various mill sizes like 1, 1/2, 5/8.

BALL NOSE KEY table with columns: Mill Diameter, Radius of Ball. Rows include sizes like 1/8, 5/32, 3/16, 7/32, 1/4, 9/32, 5/16, 11/32, 3/8, 7/16, 1/2, 5/8, 3/4, 1.

Table with columns: Mill Dia. Tolerance (inch), Shank Dia. Tolerance. Values: 0~-.0012, h6.



◎ : Excellent ○ : Good


Material compatibility table with columns P, H, M, K, N, S and rows for Carbon Steels, Alloy Steels, Prehardened Steels, Hardened Steels, High Hardened Steels, Stainless Steels, Cast Iron, Copper, Graphite, Aluminum, Acrylic, CFRP, Titanium, High Temperature Alloy.

YG V7 PLUS A END MILLS

UGMF73 SERIES SQUARE
UGMF75 SERIES CORNER RADIUS

CARBIDE, 4 FLUTE EXTENDED LENGTH

- ▶ Special flute geometry and multiple helix eliminate vibrations
- ▶ Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRc40
- ▶ Advanced coating for superior performance and tool life




MG HM 4 35°/37° FLAT P.1006~1009

Unit : mm

OD	SD	LOC	LBS	OAL	Square End	Corner Radius	
						.030	
D1	D2	L1	L3	L2	EDP No.	EDP No.	
3/8	3/8	1/2	1-1/8	4	UGMF73024	UGMF75024	
		1/2	2-1/8	4	UGMF73903	UGMF75903	
		1/2	3-1/8	5	UGMF73913	UGMF75913	
		1/2	3-1/8	6	UGMF73904	UGMF75904	
1/2	1/2	5/8	1-1/2	4	UGMF73032	UGMF75032	
		5/8	2-1/4	4	UGMF73905	UGMF75905	
		5/8	3-3/8	5	UGMF73914	UGMF75914	
		5/8	3-3/8	6	UGMF73906	UGMF75906	
5/8	5/8	3/4	1-5/8	4	UGMF73040	UGMF75040	
		3/4	2-3/8	5	UGMF73915	UGMF75915	
		3/4	3-3/8	5	UGMF73916	UGMF75916	
		3/4	2-3/8	6	UGMF73907	UGMF75907	
3/4	3/4	3/4	3-3/8	6	UGMF73908	UGMF75908	
		1	2	4	UGMF73048	UGMF75048	
		1	3	5	UGMF73917	UGMF75917	
		1	3	6	UGMF73909	UGMF75909	
1	1	1	4	6	UGMF73910	UGMF75910	
		1-1/8	2	4	UGMF73064	UGMF75064	
		1-1/8	2-5/8	5	UGMF73918	UGMF75918	
		1-1/8	3	5	UGMF73919	UGMF75919	
1	1	1-1/8	3	6	UGMF73911	UGMF75911	
		1-1/8	3	6	UGMF73911	UGMF75911	
		1-1/8	4	6	UGMF73912	UGMF75912	

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	h6

REINFORCED CUTTING EDGE



SQUARE END

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	○

YG V7 PLUS A END MILLS

UGMG20 SERIES SQUARE
UGMG22 SERIES CORNER RADIUS

CARBIDE, 6 FLUTE STANDARD LENGTH

- ▶ The unique geometry of the variable pitch reduces chatter for high-speed and trochoidal milling
- ▶ Excellent performance for stainless steels, mild steels, cast iron and low/medium hardness materials up to HRc40
- ▶ Advanced coating for superior performance and tool life



MG HM 6 45° PLAIN P.1011

Unit : Inch

OD	SD	LOC	LBS	Square End	Corner Radius							
					.015	.030	.060	.090	.120	.125	.190	.250
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
1/4	1/4	1/2	2-1/2	UGMG20914	UGMG22956	UGMG22957	UGMG22958	-	-	-	-	-
		3/4	2-1/2	UGMG20016	UGMG22016	UGMG22959	UGMG22960	-	-	-	-	-
		1-1/8	3	UGMG20901	UGMG22901	UGMG22902	UGMG22961	-	-	-	-	-
		1-1/2	4	UGMG20902	UGMG22903	UGMG22904	UGMG22962	-	-	-	-	-
5/16	5/16	3/4	2-1/2	UGMG20020	UGMG22020	-	-	-	-	-	-	-
		1-1/4	3	UGMG20903	UGMG22905	UGMG22906	-	-	-	-	-	
		1-5/8	4	UGMG20904	UGMG22907	UGMG22908	-	-	-	-	-	
3/8	3/8	5/8	2-1/2	UGMG20915	UGMG22963	UGMG22964	UGMG22965	UGMG22966	-	-	-	-
		1	3	UGMG20024	UGMG22024	UGMG22909	UGMG22910	UGMG22967	-	-	-	
		1-1/2	4	UGMG20905	UGMG22911	UGMG22912	UGMG22913	UGMG22968	-	-	-	
		2	4	UGMG20906	UGMG22914	UGMG22915	UGMG22916	UGMG22969	-	-	-	
1/2	1/2	5/8	3	UGMG20916	UGMG22970	UGMG22971	UGMG22972	UGMG22973	-	UGMG22974	-	-
		1	3	UGMG20917	UGMG22032	UGMG22917	UGMG22918	UGMG22975	-	UGMG22976	-	-
		1	3-1/4	UGMG20032	-	-	-	-	-	-	-	-
		1-1/4	3-1/2	UGMG20907	UGMG22977	UGMG22919	UGMG22920	UGMG22921	UGMG22922	UGMG22978	-	-
1/2	1/2	1-5/8	4	UGMG20918	UGMG22979	UGMG22980	UGMG22981	UGMG22982	-	UGMG22983	-	-
		2	4	UGMG20908	UGMG22984	UGMG22923	UGMG22924	UGMG22925	UGMG22926	UGMG22985	-	-
		2-5/8	5	UGMG20919	UGMG22986	UGMG22987	UGMG22988	UGMG22989	-	UGMG22990	-	-
1/2	1/2	3	5	UGMG20909	UGMG22991	UGMG22927	UGMG22928	UGMG22929	UGMG22930	UGMG22992	-	-

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	○



UGMG20 SERIES SQUARE
UGMG22 SERIES CORNER RADIUS

CARBIDE, 6 FLUTE STANDARD LENGTH


- ▶ The unique geometry of the variable pitch reduces chatter for high-speed and trochoidal milling
- ▶ Excellent performance for stainless steels, mild steels, cast iron and low/medium hardness materials up to HRc40
- ▶ Advanced coating for superior performance and tool life



Unit : Inch

OD	SD	LOC	LBS	Square End	Corner Radius							
					.015	.030	.060	.090	.120	.125	.190	.250
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
5/8	5/8	3/4	3	UGMG20920	UGMG22993	UGMG22994	UGMG22995	UGMG22996	-	UGMG22997	-	-
		1-1/4	3-1/2	UGMG20040	UGMG22998	UGMG22040	UGMG22931	UGMG22932	UGMG22933	UGMG22999	-	-
		1-7/8	4	UGMG20921	UGMG22801	UGMG22802	UGMG22803	UGMG22804	-	UGMG22805	-	-
		2	4	UGMG20910	UGMG22806	UGMG22934	UGMG22935	UGMG22936	UGMG22937	UGMG22807	-	-
		2-5/8	5	UGMG20922	UGMG22808	UGMG22809	UGMG22810	UGMG22811	-	UGMG22812	-	-
3/4	3/4	1	3-1/2	UGMG20923	UGMG22815	UGMG22816	UGMG22817	UGMG22818	-	UGMG22819	UGMG22820	UGMG22821
		1-1/2	4	UGMG20048	UGMG22822	UGMG22048	UGMG22942	UGMG22943	UGMG22944	UGMG22823	UGMG22824	UGMG22825
		1-7/8	5	UGMG20924	UGMG22826	UGMG22827	UGMG22828	UGMG22829	-	UGMG22830	UGMG22831	UGMG22832
		2-1/4	5	UGMG20925	UGMG22833	UGMG22834	UGMG22835	UGMG22836	-	UGMG22837	UGMG22838	UGMG22839
		2-3/4	5	UGMG20926	UGMG22840	UGMG22841	UGMG22842	UGMG22843	-	UGMG22844	UGMG22845	UGMG22846
1	1	1-1/2	4	UGMG20064	UGMG22851	UGMG22064	UGMG22949	UGMG22950	UGMG22951	UGMG22852	UGMG22853	UGMG22854
		2	5	UGMG20927	UGMG22855	UGMG22856	UGMG22857	UGMG22858	-	UGMG22859	UGMG22860	UGMG22861
		2-5/8	5	UGMG20928	UGMG22862	UGMG22863	UGMG22864	UGMG22865	-	UGMG22866	UGMG22867	UGMG22868
		3-1/4	6	UGMG20929	UGMG22869	UGMG22870	UGMG22871	UGMG22872	-	UGMG22873	UGMG22874	UGMG22875
		4	7	UGMG20913	UGMG22876	UGMG22952	UGMG22953	UGMG22954	UGMG22955	UGMG22877	UGMG22878	UGMG22879

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	h6



◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	○



UGMG21 SERIES SQUARE
UGMG23 SERIES CORNER RADIUS

CARBIDE, 6 FLUTE STANDARD LENGTH


- ▶ The unique geometry of the variable pitch reduces chatter for high-speed and trochoidal milling
- ▶ Excellent performance for stainless steels, mild steels, cast iron and low/medium hardness materials up to HRc40
- ▶ Advanced coating for superior performance and tool life



Unit : Inch

OD	SD	LOC	LBS	Square End	Corner Radius				
					.015	.030	.060	.090	.120
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	
3/8	3/8	1	3	UGMG21024	UGMG23024	UGMG23909	UGMG23910	-	-
		1-1/2	4	UGMG21905	UGMG23911	UGMG23912	UGMG23913	-	-
		2	4	UGMG21906	UGMG23914	UGMG23915	UGMG23916	-	-
1/2	1/2	1	3	UGMG21914	UGMG23032	UGMG23917	UGMG23918	-	-
		1	3-1/4	UGMG21032	-	-	-	-	-
		1-1/4	3-1/2	UGMG21907	-	UGMG23919	UGMG23920	UGMG23921	UGMG23922
5/8	5/8	2	4	UGMG21908	-	UGMG23923	UGMG23924	UGMG23925	UGMG23926
		3	5	UGMG21909	-	UGMG23927	UGMG23928	UGMG23929	UGMG23930
		1-1/4	3-1/2	UGMG21040	-	UGMG23040	UGMG23931	UGMG23932	UGMG23933
3/4	3/4	2	4	UGMG21910	-	UGMG23934	UGMG23935	UGMG23936	UGMG23937
		3	5	UGMG21911	-	UGMG23938	UGMG23939	UGMG23940	UGMG23941
		1-1/2	4	UGMG21048	-	UGMG23048	UGMG23942	UGMG23943	UGMG23944
1	1	3	5-1/2	UGMG21912	-	UGMG23945	UGMG23946	UGMG23947	UGMG23948
		1-1/2	4	UGMG21064	-	UGMG23064	UGMG23949	UGMG23950	UGMG23951
		4	7	UGMG21913	-	UGMG23952	UGMG23953	UGMG23954	UGMG23955

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	h6




◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	○



CARBIDE, 6 FLUTE EXTENDED LENGTH

- ▶ The unique geometry of the variable pitch reduces chatter for high-speed and trochoidal milling
- ▶ Excellent performance for stainless steels, mild steels, cast iron and low/medium hardness materials up to HRC40
- ▶ Advanced coating for superior performance and tool life



Unit : Inch

OD	SD	LOC	LBS	OAL	Square End	Corner Radius					
						.030	.060	.090	.125	.190	.250
D1	D2	L1	L3	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
1/4	1/4	3/8	3/4	4	UGMH08016	UGMH09016	UGMH09901	-	-	-	-
		3/8	1-1/8	4	UGMH08901	UGMH09902	UGMH09903	-	-	-	-
		3/8	2-1/8	4	UGMH08902	UGMH09904	UGMH09905	-	-	-	-
3/8	3/8	1/2	1-1/8	4	UGMH08024	UGMH09024	UGMH09906	UGMH09907	-	-	-
		1/2	2-1/8	4	UGMH08903	UGMH09908	UGMH09909	UGMH09910	-	-	-
		1/2	3-1/8	5	UGMH08919	UGMH09999	UGMH09801	UGMH09802	-	-	-
		1/2	3-1/8	6	UGMH08904	UGMH09911	UGMH09912	UGMH09913	-	-	-
		1/2	4-1/8	6	UGMH08905	UGMH09914	UGMH09915	UGMH09916	-	-	-
		1/2	4-1/8	6	UGMH08032	UGMH09032	UGMH09917	UGMH09918	UGMH09919	-	-
1/2	1/2	5/8	2-1/4	4	UGMH08906	UGMH09920	UGMH09921	UGMH09922	UGMH09923	-	-
		5/8	3-3/8	5	UGMH08920	UGMH09803	UGMH09804	UGMH09805	UGMH09806	-	-
		5/8	3-3/8	6	UGMH08907	UGMH09924	UGMH09925	UGMH09926	UGMH09927	-	-
		5/8	4-1/8	6	UGMH08908	UGMH09928	UGMH09929	UGMH09930	UGMH09931	-	-
		5/8	4-1/8	6	UGMH08040	UGMH09040	UGMH09932	UGMH09933	UGMH09934	-	-
5/8	5/8	3/4	1-5/8	4	UGMH08040	UGMH09040	UGMH09932	UGMH09933	UGMH09934	-	-
		3/4	2-3/8	5	UGMH08921	UGMH09807	UGMH09808	UGMH09809	UGMH09810	-	-
		3/4	3-3/8	5	UGMH08922	UGMH09811	UGMH09812	UGMH09813	UGMH09814	-	-
		3/4	2-3/8	6	UGMH08909	UGMH09935	UGMH09936	UGMH09937	UGMH09938	-	-
		3/4	3-3/8	6	UGMH08910	UGMH09939	UGMH09940	UGMH09941	UGMH09942	-	-
3/4	3/4	3/4	4-1/8	6	UGMH08911	UGMH09943	UGMH09944	UGMH09945	UGMH09946	-	-
		1-1/8	2	4	UGMH08048	UGMH09048	UGMH09947	UGMH09948	UGMH09949	UGMH09950	UGMH09951
		1-1/8	2-5/8	5	UGMH08912	UGMH09952	UGMH09953	UGMH09954	UGMH09955	UGMH09956	UGMH09957
		1-1/8	3-1/4	6	UGMH08913	UGMH09958	UGMH09959	UGMH09960	UGMH09961	UGMH09962	UGMH09963
		1-1/8	4-1/4	7	UGMH08914	UGMH09964	UGMH09965	UGMH09966	UGMH09967	UGMH09968	UGMH09969

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	○



CARBIDE, 6 FLUTE EXTENDED LENGTH


- ▶ The unique geometry of the variable pitch reduces chatter for high-speed and trochoidal milling
- ▶ Excellent performance for stainless steels, mild steels, cast iron and low/medium hardness materials up to HRC40
- ▶ Advanced coating for superior performance and tool life



Unit : Inch

OD	SD	LOC	LBS	OAL	Square End	Corner Radius					
						.030	.060	.090	.125	.190	.250
D1	D2	L1	L3	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
1	1	1-1/4	2-1/4	4	UGMH08064	UGMH09064	UGMH09970	UGMH09971	UGMH09972	UGMH09973	UGMH09974
		1-1/4	2-5/8	5	UGMH08915	UGMH09975	UGMH09976	UGMH09977	UGMH09978	UGMH09979	UGMH09980
		1-1/4	3-1/4	6	UGMH08916	UGMH09981	UGMH09982	UGMH09983	UGMH09984	UGMH09985	UGMH09986
		1-1/4	4-1/4	7	UGMH08917	UGMH09987	UGMH09988	UGMH09989	UGMH09990	UGMH09991	UGMH09992
		1-1/4	5-1/4	8	UGMH08918	UGMH09993	UGMH09994	UGMH09995	UGMH09996	UGMH09997	UGMH09998

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	h6




P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	○



GMF52 / GMF56 SERIES CHAMFER
GMF54 / GMF58 SERIES CORNER RADIUS
GMG55 SERIES BALL NOSE

CARBIDE, 4 FLUTE STANDARD LENGTH

- ▶ Special flute geometry and multiple helix eliminate vibrations
- ▶ Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRc40
- ▶ Advanced coating for superior performance and tool life



Unit : mm

OD D1	SD	LOC	OAL	Chamfer	Corner Radius					Ball Nose	
					0.30	0.50	1.00	2.00	3.00		
Metric	Inch	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	
3.0	.1181	6	7	54	GMF52030	GMF54030	GMF54901	-	-	-	-
		6	8	57	GMF56030	GMF58030	GMF58901	-	-	-	GMG55030
4.0	.1575	6	8	54	GMF52040	GMF54040	GMF54902	-	-	-	-
		6	11	57	GMF56040	GMF58040	GMF58902	-	-	-	GMG55040
5.0	.1969	6	10	54	GMF52050	GMF54050	GMF54903	-	-	-	-
		6	13	57	GMF56050	GMF58050	GMF58903	-	-	-	GMG55050
6.0	.2362	6	10	54	GMF52060	GMF54060	GMF54904	GMF54905	-	-	-
		6	13	57	GMF56060	GMF58060	GMF58904	GMF58905	-	-	GMG55060
8.0	.3150	8	12	58	GMF52080	-	GMF54080	GMF54906	-	-	-
		8	19	63	GMF56080	-	GMF58080	GMF58906	-	-	GMG55080
10.0	.3937	10	14	66	GMF52100	-	GMF54100	GMF54907	-	-	-
		10	22	72	GMF56100	-	GMF58100	GMF58907	-	-	GMG55100
12.0	.4724	12	16	73	GMF52120	-	GMF54120	GMF54908	GMF54909	-	-
		12	26	83	GMF56120	-	GMF58120	GMF58908	GMF58909	-	GMG55120
14.0	.5512	14	18	75	GMF52140	-	GMF54140	-	-	-	-
		14	26	83	GMF56140	-	GMF58140	-	-	-	-
16.0	.6299	16	22	82	GMF52160	-	-	GMF54160	GMF54912	GMF54913	-
		16	32	92	GMF56160	-	-	GMF58160	GMF58912	GMF58913	GMG55160

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	○



GMF52 / GMF56 SERIES CHAMFER
GMF54 / GMF58 SERIES CORNER RADIUS
GMG55 SERIES BALL NOSE

CARBIDE, 4 FLUTE STANDARD LENGTH

- ▶ Special flute geometry and multiple helix eliminate vibrations
- ▶ Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRc40
- ▶ Advanced coating for superior performance and tool life




Unit : mm

OD D1	SD	LOC	OAL	Chamfer	Corner Radius					Ball Nose	
					0.30	0.50	1.00	2.00	3.00		
Metric	Inch	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	
18.0	.7087	18	24	84	GMF52180	-	-	GMF54180	-	-	-
		18	32	92	GMF56180	-	-	GMF58180	-	-	-
20.0	.7874	20	26	92	GMF52200	-	-	GMF54200	GMF54916	GMF54917	-
		20	38	104	GMF56200	-	-	GMF58200	GMF58916	GMF58917	GMG55200
25.0	.9843	25	38	104	GMF56250	-	-	GMF58250	-	-	GMG55250

CHAMFER KEY		
Mill Diameter	Chamfer Size (mm)	
Metric	Inch	
3.0	.1181	0.10
4.0	.1575	0.15
5.0	.1969	0.15
6.0	.2362	0.20
8.0	.3150	0.20
10.0	.3937	0.30
12.0	.4724	0.35
14.0	.5512	0.40
16.0	.6299	0.40
18.0	.7087	0.50
20.0	.7874	0.50
25.0	.9843	0.50

BALL NOSE KEY		
Mill Diameter	Radius of Ball	
Metric	Inch	
3.0	.1181	1.5
4.0	.1575	2.0
5.0	.1969	2.5
6.0	.2362	3.0
8.0	.3150	4.0
10.0	.3937	5.0
12.0	.4724	6.0
14.0	.5512	8.0
16.0	.6299	10.0
18.0	.7087	10.0
20.0	.7874	10.0
25.0	.9843	12.5

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	h6



◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	○



GMF53 / GMF57 SERIES CHAMFER
GMF55 / GMF59 SERIES CORNER RADIUS
GMG56 SERIES BALL NOSE

CARBIDE, 4 FLUTE STANDARD LENGTH

- ▶ Special flute geometry and multiple helix eliminate vibrations
- ▶ Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRc40
- ▶ Advanced coating for superior performance and tool life



MG HM 4 35°/37° FLAT C x 45° ±0.02mm P.1012~1014

Unit : mm

Metric	Inch	D2	L1	L2	Chamfer EDP No.	Corner Radius					Ball Nose EDP No.
						0.30 EDP No.	0.50 EDP No.	1.00 EDP No.	2.00 EDP No.	3.00 EDP No.	
3.0	.1181	6	7	54	GMF53030	GMF55030	GMF55901	-	-	-	-
		6	8	57	GMF57030	GMF59030	GMF59901	-	-	-	GMG56030
4.0	.1575	6	8	54	GMF53040	GMF55040	GMF55902	-	-	-	-
		6	11	57	GMF57040	GMF59040	GMF59902	-	-	-	GMG56040
5.0	.1969	6	10	54	GMF53050	GMF55050	GMF55903	-	-	-	-
		6	13	57	GMF57050	GMF59050	GMF59903	-	-	-	GMG56050
6.0	.2362	6	10	54	GMF53060	GMF55060	GMF55904	GMF55905	-	-	-
		6	13	57	GMF57060	GMF59060	GMF59904	GMF59905	-	-	GMG56060
8.0	.3150	8	12	58	GMF53080	-	GMF55080	GMF55906	-	-	-
		8	19	63	GMF57080	-	GMF59080	GMF59906	-	-	GMG56080
10.0	.3937	10	14	66	GMF53100	-	GMF55100	GMF55907	-	-	-
		10	22	72	GMF57100	-	GMF59100	GMF59907	-	-	GMG56100
12.0	.4724	12	16	73	GMF53120	-	GMF55120	GMF55908	GMF55909	-	-
		12	26	83	GMF57120	-	GMF59120	GMF59908	GMF59909	-	GMG56120
14.0	.5512	14	18	75	GMF53140	-	GMF55140	-	-	-	-
		14	26	83	GMF57140	-	GMF59140	-	-	-	-
16.0	.6299	16	22	82	GMF53160	-	-	GMF55160	GMF55912	GMF55913	-
		16	32	92	GMF57160	-	-	GMF59160	GMF59912	GMF59913	GMG56160

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	◎	◎						○	○



GMF53 / GMF57 SERIES CHAMFER
GMF55 / GMF59 SERIES CORNER RADIUS
GMG56 SERIES BALL NOSE

CARBIDE, 4 FLUTE STANDARD LENGTH

- ▶ Special flute geometry and multiple helix eliminate vibrations
- ▶ Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRc40
- ▶ Advanced coating for superior performance and tool life




MG HM 4 35°/37° FLAT C x 45° ±0.02mm P.1012~1014

Unit : mm

Metric	Inch	D2	L1	L2	Chamfer EDP No.	Corner Radius					Ball Nose EDP No.
						0.30 EDP No.	0.50 EDP No.	1.00 EDP No.	2.00 EDP No.	3.00 EDP No.	
18.0	.7087	18	24	84	GMF53180	-	-	GMF55180	-	-	-
		18	32	92	GMF57180	-	-	GMF59180	-	-	-
20.0	.7874	20	26	92	GMF53200	-	-	GMF55200	GMF55916	GMF55917	-
		20	38	104	GMF57200	-	-	GMF59200	GMF59916	GMF59917	GMG56200
25.0	.9843	25	38	104	GMF57250	-	-	GMF59250	-	-	GMG56250

CHAMFER KEY			BALL NOSE KEY		
Mill Diameter		Chamfer Size (mm)	Mill Diameter		Radius of Ball
Metric	Inch		Metric	Inch	
3.0	.1181	0.10	3.0	.1181	1.5
4.0	.1575	0.15	4.0	.1575	2.0
5.0	.1969	0.15	5.0	.1969	2.5
6.0	.2362	0.20	6.0	.2362	3.0
8.0	.3150	0.20	8.0	.3150	4.0
10.0	.3937	0.30	10.0	.3937	5.0
12.0	.4724	0.35	12.0	.4724	6.0
14.0	.5512	0.40	16.0	.6299	8.0
16.0	.6299	0.40	20.0	.7874	10.0
18.0	.7087	0.50	25.0	.9843	12.5
20.0	.7874	0.50			
25.0	.9843	0.50			

Mill Dia. Tolerance (rd)	Shank Dia. Tolerance
0~.0012	h6




◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	◎	◎						○	○



CARBIDE, 4 FLUTE EXTENDED LENGTH

- ▶ Special flute geometry and multiple helix eliminate vibrations
- ▶ Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRc40
- ▶ Advanced coating for superior performance and tool life




Unit : mm

Metric	Inch	D2	L1	L3	L2	Chamfer EDP No.	Corner Radius				
							0.30 EDP No.	0.50 EDP No.	1.00 EDP No.	2.00 EDP No.	3.00 EDP No.
3.0	.1181	6	7	12	54	GMF60030	GMF62030	GMF62901	-	-	-
		6	7	17	57	GMF60901	GMF62902	GMF62903	-	-	-
		6	8	14	57	GMF60902	-	-	-	-	-
4.0	.1575	6	8	15	57	GMF60040	GMF62040	GMF62904	-	-	-
		6	8	22	63	GMF60903	GMF62905	GMF62906	-	-	-
		6	11	16	57	GMF60904	-	-	-	-	-
5.0	.1969	6	10	17	57	GMF60050	GMF62050	GMF62907	-	-	-
		6	10	27	67	GMF60905	GMF62908	GMF62909	-	-	-
		6	13	18	57	GMF60906	-	-	-	-	-
6.0	.2362	6	10	15	57	GMF60060	GMF62060	GMF62910	GMF62911	-	-
		6	10	20	62	GMF60907	GMF62912	GMF62913	GMF62914	-	-
		6	10	32	74	GMF60908	GMF62915	GMF62916	GMF62917	-	-
8.0	.3150	6	13	21	57	GMF60909	-	-	-	-	-
		8	12	20	63	GMF60080	-	GMF62080	GMF62918	-	-
		8	12	30	73	GMF60910	-	GMF62919	GMF62920	-	-
10.0	.3937	8	12	46	90	GMF60911	-	GMF62921	GMF62922	-	-
		8	19	27	63	GMF60912	-	-	-	-	-
		10	14	25	72	GMF60100	-	GMF62100	GMF62923	-	-
12.0	.4724	10	14	35	82	GMF60913	-	GMF62924	GMF62925	-	-
		10	14	55	102	GMF60914	-	GMF62926	GMF62927	-	-
		10	22	32	72	GMF60915	-	-	-	-	-
12.0	.4724	12	16	30	83	GMF60120	-	GMF62120	GMF62928	GMF62929	-
		12	16	40	93	GMF60916	-	GMF62930	GMF62931	GMF62932	-
		12	16	64	117	GMF60917	-	GMF62933	GMF62934	GMF62935	-
12	26	38	83	GMF60918	-	-	-	-	-	-	

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	◎	◎						○	○



CARBIDE, 4 FLUTE EXTENDED LENGTH

- ▶ Special flute geometry and multiple helix eliminate vibrations
- ▶ Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRc40
- ▶ Advanced coating for superior performance and tool life




Unit : mm

Metric	Inch	D2	L1	L3	L2	Chamfer EDP No.	Corner Radius				
							0.30 EDP No.	0.50 EDP No.	1.00 EDP No.	2.00 EDP No.	3.00 EDP No.
16.0	.6299	16	22	38	92	-	-	-	GMF62160	GMF62936	GMF62937
		16	22	55	109	-	-	-	GMF62938	GMF62939	GMF62940
		16	22	87	141	-	-	-	GMF62941	GMF62942	GMF62943
		16	32	44	92	-	-	-	-	-	-
20.0	.7874	20	26	50	104	-	-	-	GMF62200	GMF62944	GMF62945
		20	26	70	124	-	-	-	GMF62946	GMF62947	GMF62948
		20	26	110	164	-	-	-	GMF62949	GMF62950	GMF62951
		20	38	54	104	-	-	-	-	-	-

CHAMFER KEY		
Mill Diameter		Chamfer Size (mm)
Metric	Inch	
3.0	.1181	0.10
4.0	.1575	0.15
5.0	.1969	0.15
6.0	.2362	0.20
8.0	.3150	0.20
10.0	.3937	0.30
12.0	.4724	0.35
16.0	.6299	0.40
20.0	.7874	0.50

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~.0012	h6

REINFORCED CUTTING EDGE



CHAMFER


◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	◎	◎						○	○



CARBIDE, 4 FLUTE EXTENDED LENGTH

- ▶ Special flute geometry and multiple helix eliminate vibrations
- ▶ Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRc40
- ▶ Advanced coating for superior performance and tool life



Unit : mm

Metric	Inch	D1	SD	LOC	LBS	OAL	Chamfer		Corner Radius					
							0.10	0.30	0.50	1.00	2.00	3.00		
			D2	L1	L3	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.		
3.0	.1181		6	7	12	54	GMF61030	GMF63030	GMF63901	-	-	-		
			6	7	17	57	GMF61901	GMF63902	GMF63903	-	-	-		
			6	8	14	57	GMF61902	-	-	-	-	-		
4.0	.1575		6	8	15	57	GMF61040	GMF63040	GMF63904	-	-	-		
			6	8	22	63	GMF61903	GMF63905	GMF63906	-	-	-		
			6	11	16	57	GMF61904	-	-	-	-	-		
5.0	.1969		6	10	17	57	GMF61050	GMF63050	GMF63907	-	-	-		
			6	10	27	67	GMF61905	GMF63908	GMF63909	-	-	-		
			6	13	18	57	GMF61906	-	-	-	-	-		
6.0	.2362		6	10	15	57	GMF61060	GMF63060	GMF63910	GMF63911	-	-		
			6	10	20	62	GMF61907	GMF63912	GMF63913	GMF63914	-	-		
			6	10	32	74	GMF61908	GMF63915	GMF63916	GMF63917	-	-		
8.0	.3150		6	13	21	57	GMF61909	-	-	-	-	-		
			8	12	20	63	GMF61080	-	GMF63080	GMF63918	-	-		
			8	12	30	73	GMF61910	-	GMF63919	GMF63920	-	-		
10.0	.3937		8	12	46	90	GMF61911	-	GMF63921	GMF63922	-	-		
			8	19	27	63	GMF61912	-	-	-	-	-		
			10	14	25	72	GMF61100	-	GMF63100	GMF63923	-	-		
12.0	.4724		10	14	35	82	GMF61913	-	GMF63924	GMF63925	-	-		
			10	14	55	102	GMF61914	-	GMF63926	GMF63927	-	-		
			10	22	32	72	GMF61915	-	-	-	-	-		
12.0	.4724		12	16	30	83	GMF61120	-	GMF63120	GMF63928	GMF63929	-		
			12	16	40	93	GMF61916	-	GMF63930	GMF63931	GMF63932	-		
			12	16	64	117	GMF61917	-	GMF63933	GMF63934	GMF63935	-		
12	26	38	83	GMF61918	-	-	-	-	-	-				

▶ NEXT PAGE


◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	○



CARBIDE, 4 FLUTE EXTENDED LENGTH

- ▶ Special flute geometry and multiple helix eliminate vibrations
- ▶ Excellent performance for stainless steels, mild steels, cast iron, low/medium hardness materials and all exotic materials up to HRc40
- ▶ Advanced coating for superior performance and tool life




Unit : mm

Metric	Inch	D1	SD	LOC	LBS	OAL	Chamfer		Corner Radius					
							0.10	0.30	0.50	1.00	2.00	3.00		
			D2	L1	L3	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.		
16.0	.6299		16	22	38	92	GMF61160	-	-	GMF63160	GMF63936	GMF63937		
			16	22	55	109	GMF61919	-	-	GMF63938	GMF63939	GMF63940		
			16	22	87	141	GMF61920	-	-	GMF63941	GMF63942	GMF63943		
			16	32	44	92	GMF61921	-	-	-	-	-		
20.0	.7874		20	26	50	104	GMF61200	-	-	GMF63200	GMF63944	GMF63945		
			20	26	70	124	GMF61922	-	-	GMF63946	GMF63947	GMF63948		
			20	26	110	164	GMF61923	-	-	GMF63949	GMF63950	GMF63951		
			20	38	54	104	GMF61924	-	-	-	-	-		

CHAMFER KEY		
Mill Diameter		Chamfer Size (mm)
Metric	Inch	
3.0	.1181	0.10
4.0	.1575	0.15
5.0	.1969	0.15
6.0	.2362	0.20
8.0	.3150	0.20
10.0	.3937	0.30
12.0	.4724	0.35
16.0	.6299	0.40
20.0	.7874	0.50

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~.0012	h6



◎ : Excellent ○ : Good


P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎	◎						○	○

V7 PLUS A END MILLS

GMG12 / GMG14 SERIES SQUARE
GMG16 / GMG18 SERIES CORNER RADIUS

CARBIDE, 6 FLUTE STANDARD LENGTH

- ▶ The unique geometry of the variable pitch reduces chatter for high-speed and trochoidal milling
- ▶ Excellent performance for stainless steels, mild steels, cast iron and low/medium hardness materials up to HRc40
- ▶ Advanced coating for superior performance and tool life




MG HM 6 45° PLAIN P.1015

Unit : mm

Metric	Inch	D2	L1	L2	Square End EDP No.	Corner Radius						
						0.50 EDP No.	1.00 EDP No.	1.50 EDP No.	2.00 EDP No.	3.00 EDP No.	4.00 EDP No.	5.00 EDP No.
6.0	.2362	6	13	57	GMG12060	GMG16060	GMG16901	-	-	-	-	-
		6	24	75	GMG14060	GMG18060	GMG18901	-	-	-	-	-
8.0	.3150	8	19	63	GMG12080	GMG16080	GMG16902	-	-	-	-	-
		8	32	75	GMG14080	GMG18080	GMG18902	-	GMG18903	-	-	-
10.0	.3937	10	22	72	GMG12100	GMG16100	GMG16903	GMG16904	GMG16905	-	-	-
		10	40	100	GMG14100	GMG18100	GMG18904	GMG18905	GMG18906	-	-	-
12.0	.4724	12	26	83	GMG12120	GMG16120	GMG16906	GMG16907	GMG16908	GMG16909	-	-
		12	48	120	GMG14120	GMG18120	GMG18907	GMG18908	GMG18909	GMG18910	-	-
16.0	.6299	16	32	92	GMG12160	-	GMG16160	GMG16910	GMG16911	GMG16912	-	-
		16	64	140	GMG14160	-	GMG18160	GMG18911	GMG18912	GMG18913	-	-
20.0	.7874	20	38	104	GMG12200	-	GMG16200	GMG16913	GMG16914	GMG16915	-	-
		20	80	150	GMG14200	-	GMG18200	GMG18914	GMG18915	GMG18916	GMG18917	GMG18918
25.0	.9843	25	44	104	GMG12250	-	GMG16250	GMG16916	GMG16917	GMG16918	-	-
		25	100	170	GMG14250	-	GMG18250	GMG18919	GMG18920	GMG18921	GMG18922	GMG18923

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	h6



◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	◎	◎						○	○

V7 PLUS A END MILLS

GMG13 / GMG15 SERIES SQUARE
GMG17 / GMG19 SERIES CORNER RADIUS

CARBIDE, 6 FLUTE STANDARD LENGTH

- ▶ The unique geometry of the variable pitch reduces chatter for high-speed and trochoidal milling
- ▶ Excellent performance for stainless steels, mild steels, cast iron and low/medium hardness materials up to HRc40
- ▶ Advanced coating for superior performance and tool life




MG HM 6 45° FLAT P.1015

Unit : mm

Metric	Inch	D2	L1	L2	Square End EDP No.	Corner Radius						
						0.50 EDP No.	1.00 EDP No.	1.50 EDP No.	2.00 EDP No.	3.00 EDP No.	4.00 EDP No.	5.00 EDP No.
6.0	.2362	6	13	57	GMG13060	GMG17060	GMG17901	-	-	-	-	-
		6	24	75	GMG15060	GMG19060	GMG19901	-	-	-	-	-
8.0	.3150	8	19	63	GMG13080	GMG17080	GMG17902	-	-	-	-	-
		8	32	75	GMG15080	GMG19080	GMG19902	-	GMG19903	-	-	-
10.0	.3937	10	22	72	GMG13100	GMG17100	GMG17903	GMG17904	GMG17905	-	-	-
		10	40	100	GMG15100	GMG19100	GMG19904	GMG19905	GMG19906	-	-	-
12.0	.4724	12	26	83	GMG13120	GMG17120	GMG17906	GMG17907	GMG17908	GMG17909	-	-
		12	48	120	GMG15120	GMG19120	GMG19907	GMG19908	GMG19909	GMG19910	-	-
16.0	.6299	16	32	92	GMG13160	-	GMG17160	GMG17910	GMG17911	GMG17912	-	-
		16	64	140	GMG15160	-	GMG19160	GMG19911	GMG19912	GMG19913	-	-
20.0	.7874	20	38	104	GMG13200	-	GMG17200	GMG17913	GMG17914	GMG17915	-	-
		20	80	150	GMG15200	-	GMG19200	GMG19914	GMG19915	GMG19916	GMG19917	GMG19918
25.0	.9843	25	44	104	GMG13250	-	GMG17250	GMG17916	GMG17917	GMG17918	-	-
		25	100	170	GMG15250	-	GMG19250	GMG19919	GMG19920	GMG19921	GMG19922	GMG19923

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	h6



◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HB225	HB225~325	HRc30~40	HRc40~45 HRc45~55	HRc55~70	◎	◎						○	○


CARBIDE, 4 FLUTE - INCH

UGMF68, UGMF69, UGMF70, UGMF71, UGMF72, UGMF73, UGMF74, UGMF75, UGMF76, UGMF77 SERIES

ISO Hardness (BHN)	Work Materials	Speed and Feed Recommendations				Diameter (in.)			
		Type of Cut	Ap x D1	Ae x D1	Parameters	1/8	5/32	3/16	7/32
P <300	CARBON STEEL 10**, 11**, 12**, 12L**, 15**	Side Cutting	1.5 (1.2)	0.5	SFM (VC)	499 (400-599)			
					RPM	15249	12200	10166	8714
					FZ	.0002	.0003	.0004	.0005
		Slotting	1 (0.8)	1	SFM (VC)	499 (400-599)			
					RPM	15249	12200	10166	8714
					FZ	.0002	.0003	.0004	.0005
P >300 P <380	ALLOY STEEL 41**, 43**, 51**, 86**	Side Cutting	1.5 (1.2)	0.5	SFM (VC)	351 (281-422)			
					RPM	10727	8581	7151	6129
					FZ	.0002	.0003	.0004	.0005
		Slotting	1 (0.8)	1	SFM (VC)	351 (281-422)			
					RPM	10727	8581	7151	6129
					FZ	.0002	.0003	.0004	.0005
P <380	TOOL STEEL A2, D2, H13, P20, T15	Side Cutting	1.5 (1.2)	0.5	SFM (VC)	210 (168-252)			
					RPM	6418	5134	4278	3667
					FZ	.0001	.0002	.0003	.0004
		Slotting	1 (0.8)	1	SFM (VC)	210 (168-252)			
					RPM	6418	5134	4278	3667
					FZ	.0001	.0002	.0003	.0004
K <260	CAST IRON GRAY, MALLEABLE, DUCTILE	Side Cutting	1.5 (1.2)	0.5	SFM (VC)	367 (294-440)			
					RPM	11216	8972	7477	6409
					FZ	.0002	.0004	.0006	.0007
		Slotting	1 (0.8)	1	SFM (VC)	367 (294-440)			
					RPM	11216	8972	7477	6409
					FZ	.0002	.0004	.0006	.0007

RPM = rev./min. FEED = in./min.
SFM = ft./min. FZ = in./tooth

- NOTES:**
- ▶ Feed to be reduced by approximately 50% if L.O.C. (Length Of Cut) is over 3xD
 - ▶ The above recommendations are based on ideal conditions; for smaller taper machining centers or less rigid conditions please adjust parameters accordingly on diameters greater than 1/2"
 - ▶ In profile operations, engaging more than 2xD, reduce the radial depth of cut by 50%-60%
 - ▶ Finish cuts typically require reduced cutting feeds and speeds; also, it is recommended the radial width of cut (AE) should not exceed 2% x D1



CARBIDE, 4 FLUTE - INCH

UGMF68, UGMF69, UGMF70, UGMF71, UGMF72, UGMF73, UGMF74, UGMF75, UGMF76, UGMF77 SERIES

Diameter (in.)									
1/4	9/32	5/16	11/32	3/8	7/16	1/2	5/8	3/4	1
499 (400-599)	499 (400-598)	499 (400-599)	525 (420-630)	551 (441-662)	551 (441-661)	551 (441-662)			
7625	6778	6100	5834	5613	4811	4210	3368	2806	2105
.0006	.0008	.0011	.0013	.0015	.0017	.0019	.0021	.0026	.0025
19.21	22.95	25.94	29.86	33.59	32.20	31.16	28.11	28.73	21.21
499 (400-599)	499 (400-598)	499 (400-599)	525 (420-630)	551 (441-662)	551 (441-661)	551 (441-662)			
7625	6778	6100	5834	5613	4811	4210	3368	2806	2105
.0006	.0008	.0011	.0013	.0015	.0017	.0019	.0021	.0026	.0025
19.21	22.95	25.94	29.86	33.59	32.20	31.16	28.11	28.73	21.21
351 (281-422)	351 (281-421)	351 (281-422)	368 (295-441)	384 (308-461)	384 (308-460)	384 (308-461)			
5363	4767	4291	4089	3912	3353	2934	2347	1956	1467
.0006	.0008	.0011	.0013	.0015	.0017	.0019	.0021	.0026	.0025
13.51	16.14	18.24	20.93	23.41	22.44	21.71	19.59	20.02	14.78
351 (281-422)	351 (281-421)	351 (281-422)	368 (295-441)	384 (308-461)	384 (308-460)	384 (308-461)			
5363	4767	4291	4089	3912	3353	2934	2347	1956	1467
.0006	.0008	.0011	.0013	.0015	.0017	.0019	.0021	.0023	.0025
13.51	16.14	18.24	20.93	23.41	22.44	21.71	19.59	18.17	14.78
210 (168-252)			220 (176-264)		230 (184-276)				
3209	2852	2567	2445	2343	2008	1757	1406	1171	879
.0004	.0006	.0007	.0009	.0011	.0012	.0013	.0015	.0018	.0018
5.56	6.74	7.68	8.86	9.96	9.33	8.86	8.19	8.30	6.23
210 (168-252)			220 (176-264)		230 (184-276)				
3209	2852	2567	2445	2343	2008	1757	1406	1171	879
.0004	.0006	.0007	.0009	.0011	.0012	.0013	.0015	.0018	.0018
5.56	6.74	7.68	8.86	9.96	9.33	8.86	8.19	8.30	6.23
367 (294-440)			386 (309-463)		404 (324-484)				
5608	4985	4486	4290	4115	3527	3087	2469	2058	1543
.0008	.0011	.0013	.0016	.0019	.0021	.0023	.0026	.0032	.0031
17.66	21.19	24.02	27.70	31.11	29.44	28.19	25.28	26.25	19.20
367 (294-440)			386 (309-463)		404 (324-484)				
5608	4985	4486	4290	4115	3527	3087	2469	2058	1543
.0008	.0011	.0013	.0016	.0019	.0021	.0023	.0026	.0032	.0031
17.66	21.19	24.02	27.70	31.11	29.44	28.19	25.28	26.25	19.20

RPM = rev./min. FEED = in./min.
SFM = ft./min. FZ = in./tooth

NEXT PAGE ▶

Axial cutting depth	D(0.8D)		0.5D	
Length of Cut	<1.5XD	0.8XD	1.2XD	1.5XD
	≥1.5XD	1XD		


CARBIDE, 4 FLUTE - INCH

UGMF68, UGMF69, UGMF70, UGMF71, UGMF72, UGMF73, UGMF74, UGMF75, UGMF76, UGMF77 SERIES

ISO Hardness (BHN)	Work Materials	Speed And Feed Recommendations			Diameter (in.)				
		Type Of Cut	Ap x D1	Ae x D1	Parameters	1/8	5/32	3/16	7/32
M	STAINLESS STEELS 300 304, 316, 304L, 316LSUS316	Side Cutting	1.5 (1.2)	0.5	SFM (VC)	348 (279-417)			
					RPM	10635	8508	7090	6077
					FZ	.0002	.0003	.0005	.0006
		Slotting	1 (0.8)	1	SFM (VC)	348 (279-417)			
					RPM	10635	8508	7090	6077
					FZ	.0002	.0003	.0005	.0006
M	STAINLESS STEELS 400 416, 420F, 430F, 440F	Side Cutting	1.5 (1.2)	0.5	SFM (VC)	486 (389-583)			
					RPM	14852	11882	9901	8487
					FZ	.0002	.0002	.0004	.0004
		Slotting	1 (0.8)	1	SFM (VC)	486 (389-583)			
					RPM	14852	11882	9901	8487
					FZ	.0002	.0002	.0004	.0004
M	STAINLESS STEELS (PH) 17-4PH, 15-5PH, 13-8PH	Side Cutting	1.5 (1.2)	0.5	SFM (VC)	312 (250-374)			
					RPM	9535	7628	6356	5448
					FZ	.0002	.0003	.0005	.0006
		Slotting	1 (0.8)	1	SFM (VC)	312 (250-374)			
					RPM	9535	7628	6356	5448
					FZ	.0002	.0003	.0005	.0006
S	TITANIUM Ti6AL4V, Ti5AL5V5MO, Ti7AL4MO	Side Cutting	1	0.35	SFM (VC)	190 (152-228)			
					RPM	5806	4645	3871	3318
					FZ	.0002	.0003	.0004	.0005
		Slotting	0.5	1	SFM (VC)	190 (152-228)			
					RPM	5806	4645	3871	3318
					FZ	.0002	.0003	.0004	.0005
S	HIGH-TEMPERATURE ALLOY INCONEL, HASTALLOY, RENE	Side Cutting	1	0.25	SFM (VC)	85 (68-102)			
					RPM	2598	2078	1732	1484
					FZ	.0002	.0003	.0003	.0004
		Slotting	0.5	1	SFM (VC)	85 (68-102)			
					RPM	2598	2078	1732	1484
					FZ	.0002	.0003	.0003	.0004

RPM = rev./min. FEED = in./min.
SFM = ft./min. FZ = in./tooth

- NOTES:**
- ▶ Feed to be reduced by approximately 50% if L.O.C. (Length Of Cut) is over 3xD
 - ▶ The above recommendations are based on ideal conditions; for smaller taper machining centers or less rigid conditions please adjust parameters accordingly on diameters greater than 1/2"
 - ▶ In profile operations, engaging more than 2xD, reduce the radial depth of cut by 50%-60%
 - ▶ Finish cuts typically require reduced cutting feeds and speeds; also, it is recommended the radial width of cut (AE) should not exceed 2% x D1




CARBIDE, 4 FLUTE - INCH

UGMF68, UGMF69, UGMF70, UGMF71, UGMF72, UGMF73, UGMF74, UGMF75, UGMF76, UGMF77 SERIES

Diameter (in.)									
1/4	9/32	5/16	11/32	3/8	7/16	1/2	5/8	3/4	1
348 (279-417)									
5317	4727	4254	3867	3545	3039	2659	2127	1772	1329
.0007	.0009	.0011	.0015	.0019	.0020	.0022	.0024	.0030	.0030
15.07	17.12	18.76	23.14	26.80	24.64	23.03	20.77	21.49	16.12
348 (279-417)									
5317	4727	4254	3867	3545	3039	2659	2127	1772	1329
.0007	.0009	.0011	.0015	.0019	.0020	.0022	.0024	.0030	.0030
15.07	17.12	18.76	23.14	26.80	24.64	23.03	20.77	21.49	16.12
486 (389-583)									
7426	6601	5941	5401	4951	4243	3713	2970	2475	1857
.0005	.0007	.0009	.0011	.0013	.0014	.0015	.0018	.0022	.0022
15.20	18.48	20.58	23.81	26.51	24.39	22.80	21.05	21.44	16.08
486 (389-583)									
7426	6601	5941	5401	4951	4243	3713	2970	2475	1857
.0005	.0007	.0009	.0011	.0013	.0014	.0015	.0018	.0022	.0022
15.20	18.19	20.58	23.81	26.51	24.39	22.80	21.05	21.44	16.08
312 (250-374)									
4767	4238	3814	3467	3178	2724	2384	1907	1589	1192
.0007	.0009	.0011	.0015	.0019	.0020	.0022	.0024	.0030	.0030
13.51	15.35	16.82	20.75	24.02	22.09	20.65	18.62	19.02	14.26
312 (250-374)									
4767	4238	3814	3467	3178	2724	2384	1907	1589	1192
.0007	.0009	.0011	.0015	.0019	.0020	.0022	.0024	.0030	.0030
13.51	15.35	16.82	20.75	24.02	22.09	20.65	18.62	19.02	14.26
190 (152-228)									
2903	2581	2323	2111	1935	1659	1452	1161	968	726
.0006	.0008	.0010	.0013	.0017	.0018	.0020	.0022	.0027	.0027
7.32	8.33	9.14	11.14	12.80	12.02	11.43	10.06	10.36	7.89
190 (152-228)									
2903	2581	2323	2111	1935	1659	1452	1161	968	726
.0006	.0008	.0010	.0013	.0017	.0018	.0020	.0022	.0027	.0027
7.32	8.33	9.14	11.14	12.80	12.02	11.43	10.06	10.36	7.89
85 (68-102)									
1299	1154	1039	945	866	742	649	520	433	325
.0005	.0006	.0007	.0010	.0013	.0014	.0015	.0017	.0021	.0020
2.45	2.82	3.11	3.87	4.50	4.15	3.89	3.52	3.68	2.66
85 (68-102)									
1299	1154	1039	945	866	742	649	520	433	325
.0005	.0006	.0007	.0010	.0013	.0014	.0015	.0017	.0021	.0020
2.45	2.82	3.11	3.87	4.50	4.15	3.89	3.52	3.68	2.66

RPM = rev./min. FEED = in./min.
SFM = ft./min. FZ = in./tooth






RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE - INCH

UGMG53, UGMG54, UGMH10 SERIES

ISO Hardness (BHN)	Work Materials	Type of Cut	Speed and Feed Recommendations			Diameter (in.)										
			Ap x D1	Ae x D1	Parameters	1/8	3/16	1/4	5/16	3/8	1/2	5/8	11/16	3/4	1	
P <300	CARBON STEEL 10**, 11**, 12**, 12L**, 15**		1	0.5	SFM (VC)	531 (425-637)										
					RPM	16227	10818	9986	8114	6491	5409	4057	3245	2950	2705	2028
					Fz	.0010	.0011	.0012	.0016	.0024	.0026	.0028	.0030	.0031	.0035	.0039
					FEED	63.89	46.00	47.18	51.11	61.33	55.37	44.72	38.33	37.17	38.33	31.62
P >300 P <380	ALLOY STEEL 41**, 43**, 51**, 86**		1	0.5	SFM (VC)	371 (297-445)										
					RPM	11338	7559	6977	5669	4535	3779	2834	2268	2061	1890	1417
					Fz	.0010	.0011	.0012	.0016	.0024	.0026	.0028	.0029	.0031	.0035	.0039
					FEED	44.64	32.14	32.96	35.71	42.85	38.69	31.25	26.43	25.65	26.78	22.10
P <380	TOOL STEEL A2, D2, H13, P20, T15		1	0.5	SFM (VC)	223 (178-268)										
					RPM	6815	4543	4194	3407	2726	2272	1704	1363	1239	1136	852
					Fz	.0007	.0007	.0008	.0011	.0017	.0018	.0019	.0020	.0022	.0025	.0028
					FEED	18.24	13.59	13.87	15.02	18.03	16.10	13.15	11.16	10.93	11.27	9.39
K <260	CAST IRON GRAY, MALLEABLE, DUCTILE		1	0.5	SFM (VC)	390 (312-468)										
					RPM	11918	7946	7334	5959	4767	3973	2980	2384	2167	1986	1490
					Fz	.0012	.0013	.0015	.0020	.0029	.0032	.0034	.0037	.0039	.0044	.0049
					FEED	58.18	41.29	42.74	46.92	55.56	50.68	40.82	34.91	33.78	35.04	29.09
M	STAINLESS STEELS 300 304, 316, 304L, 316LSUS316		1	0.5	SFM (VC)	279 (223-335)										
					RPM	8526	5684	5247	4263	3410	2842	2132	1705	1550	1421	1066
					Fz	.0008	.0008	.0010	.0016	.0018	.0020	.0022	.0024	.0025	.0026	.0027
					FEED	26.85	17.90	20.66	27.53	24.17	22.38	18.46	16.11	15.62	14.55	11.41
M	STAINLESS STEELS 400 416, 420F, 430F, 440F		1	0.5	SFM (VC)	253 (202-304)										
					RPM	7732	5154	4758	3866	3093	2577	1933	1546	1406	1289	966
					Fz	.0006	.0006	.0010	.0012	.0016	.0018	.0020	.0021	.0023	.0023	.0023
					FEED	18.26	12.18	18.73	18.26	19.48	18.26	15.22	13.15	13.06	11.77	8.98
M	STAINLESS STEELS (PH) 17-4PH, 15-5PH, 13-8PH		1	0.5	SFM (VC)	253 (202-304)										
					RPM	7732	5154	4758	3866	3093	2577	1933	1546	1406	1289	966
					Fz	.0008	.0008	.0010	.0016	.0018	.0020	.0022	.0024	.0025	.0026	.0027
					FEED	24.35	16.23	18.73	24.96	21.92	20.29	16.74	14.61	14.17	13.19	10.35
S	TITANIUM Ti6AL4V, Ti5AL5V5MO, Ti7AL4MO		0.3	0.5	SFM (VC)	154 (123-185)										
					RPM	4706	3137	2896	2353	1882	1569	1177	941	856	784	588
					Fz	.0007	.0007	.0009	.0015	.0016	.0018	.0019	.0021	.0023	.0023	.0024
					FEED	13.34	8.89	10.03	13.71	11.86	11.12	9.08	8.00	7.82	7.16	5.65
S	HIGH-TEMPERATURE ALLOY INCONEL, HASTALLOY, RENE		0.3	0.2	SFM (VC)	69 (55-83)										
					RPM	2109	1406	1298	1054	843	703	527	422	383	351	264
					Fz	.0006	.0006	.0007	.0011	.0012	.0014	.0015	.0017	.0018	.0018	.0019
					FEED	4.65	3.10	3.47	4.65	4.12	3.87	3.15	2.79	2.72	2.49	1.99

RPM = rev./min. FEED = in./min.
SFM = ft./min. FZ = in./tooth



SEE NOTES ON NEXT PAGE




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 6 FLUTE - INCH

UGMG20, UGMG21, UGMG22, UGMG23, UGMH08, UGMH09 SERIES

ISO Hardness (BHN)	Work Materials	Type of Cut	Speed and Feed Recommendations			Diameter (in.)						
			Ap x D1	Ae x D1	Parameters	1/4	5/16	3/8	1/2	5/8	3/4	1
P <300	CARBON STEEL 10**, 11**, 12**, 12L**, 15**		2 (*)	0.05	SFM (VC)	984 (787-1181)						
					RPM	15036	12028	10024	7518	6014	5012	3759
					Fz	.0027	.0046	.0057	.0068	.0080	.0089	.0091
					FEED	241.52	329.60	340.96	307.22	286.98	266.38	206.00
P >300 P <380	ALLOY STEEL 41**, 43**, 51**, 86**		2 (*)	0.05	SFM (VC)	666 (533-799)						
					RPM	10176	8141	6784	5088	4071	3392	2544
					Fz	.0020	.0033	.0042	.0050	.0059	.0066	.0069
					FEED	120.19	163.46	169.88	153.85	143.27	133.82	104.57
P <380	TOOL STEEL A2, D2, H13, P20, T15		2 (*)	0.05	SFM (VC)	328 (262-394)						
					RPM	5012	4009	3341	2506	2005	1671	1253
					Fz	.0016	.0028	.0035	.0041	.0048	.0054	.0057
					FEED	48.54	67.25	69.46	62.15	58.25	54.06	42.62
M	STAINLESS STEELS 300 304, 316, 304L, 316LSUS316		2 (*)	0.05	SFM (VC)	482 (386-578)						
					RPM	7365	5892	4910	3682	2946	2455	1841
					Fz	.0016	.0028	.0035	.0041	.0048	.0054	.0056
					FEED	71.33	98.82	102.07	91.34	85.60	79.45	62.20
M	STAINLESS STEELS 400 416, 420F, 430F, 440F		2 (*)	0.05	SFM (VC)	699 (559-839)						
					RPM	10681	8545	7120	5340	4272	3560	2670
					Fz	.0019	.0033	.0041	.0049	.0057	.0064	.0066
					FEED	123.63	169.55	174.93	157.69	147.34	136.24	105.97
M	STAINLESS STEELS (PH) 17-4PH, 15-5PH, 13-8PH		2 (*)	0.05	SFM (VC)	440 (352-528)						
					RPM	6723	5379	4482	3362	2689	2241	1681
					Fz	.0016	.0028	.0035	.0041	.0048	.0054	.0056
					FEED	65.11	90.21	93.17	83.38	78.14	72.53	56.38
S	TITANIUM Ti6AL4V, Ti5AL5V5MO, Ti7AL4MO		2 (*)	0.05	SFM (VC)	381 (305-457)						
					RPM	5822	4657	3881	2911	2329	1941	1455
					Fz	.0013	.0022	.0028	.0033	.0038	.0044	.0046
					FEED	45.38	60.51	64.18	57.07	53.36	51.80	40.22
S	HIGH-TEMPERATURE ALLOY INCONEL, HASTALLOY, RENE		2 (*)	0.05	SFM (VC)	108 (86-130)						
					RPM	1650	1320	1100	825	660	550	413
					Fz	.0013	.0022	.0028	.0032	.0038	.0044	.0045
					FEED	12.86	17.15	18.19	15.98	15.13	14.55	11.21



RPM = rev./min. FEED = in./min.
SFM = ft./min. FZ = in./tooth

NOTES: * The above recommendations are based on ideal conditions; for smaller taper machining centers or less rigid conditions please adjust parameters accordingly on diameters greater than 1/2"
* Finish cuts typically require reduced cutting feeds and speeds; also, it is recommended the radial width of cut (AE) should not exceed 2% x D1
* If product's length of cut (L.O.C.) is below 2D, it must be applied L.O.C. x 90%

YG V7 PLUS A END MILLS

RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE - METRIC

GMF52, GMF53, GMF54, GMF55, GMF56, GMF57, GMF58, GMF59, GMF60, GMF61, GMF62, GMF63 SERIES

ISO Hardness (BHN)	Work Materials	Speed and Feed Recommendations				Diameter (mm)											
		Type of Cut	Ap x D1	Ae x D1	Parameters	3	4	5	6	8	10	12	14	16	18	20	25
P < 300	CARBON STEEL 1.1191 (C45) 1.0726 (35 S 20) 1.0715 (9 SMN 28) 1.0718 (9 SMNPB 28)	Side Cutting	1.5 (1.2)	0.5	SFM (VC)	499 (399-598)					551 (441-661)						
					RPM	16128	12096	9677	8064	6048	5348	4456	3820	3342	2971	2674	2139
					Fz	.0002	.0003	.0004	.0006	.0011	.0015	.0019	.0019	.0021	.0023	.0026	.0025
		Slotting	1 (0.8)	1	SFM (VC)	499 (399-598)					551 (441-661)						
					RPM	16128	12096	9677	8064	6048	5348	4456	3820	3342	2971	2674	2139
					Fz	.0002	.0003	.0004	.0006	.0011	.0015	.0019	.0019	.0021	.0023	.0026	.0025
P > 300 P < 380	ALLOY STEEL 1.2330 (35 CRMO 4) 1.6565 (40NICRMO6) 1.7033 (34CR4) 1.6523 (21 NICRMO2)	Side Cutting	1.5 (1.2)	0.5	SFM (VC)	351 (281-421)					384 (307-461)						
					RPM	11353	8515	6812	5677	4257	3724	3104	2660	2328	2069	1862	1490
					Fz	.0002	.0003	.0004	.0006	.0011	.0015	.0019	.0019	.0021	.0023	.0026	.0025
		Slotting	1 (0.8)	1	SFM (VC)	351 (281-421)					384 (307-461)						
					RPM	11353	8515	6812	5677	4257	3724	3104	2660	2328	2069	1862	1490
					Fz	.0002	.0003	.0004	.0006	.0011	.0015	.0019	.0019	.0021	.0023	.0026	.0025
P < 380	TOOL STEEL 1.2363 (X100 CRMOV 5 1) 1.2379 (X155 CRVMO 12 1) 1.2344 (X40 CRMOV 5 1) 1.3243 (S 6-5-2-5)	Side Cutting	1.5 (1.2)	0.5	SFM (VC)	210 (168-252)					230 (184-276)						
					RPM	6791	5093	4074	3395	2546	2228	1857	1592	1393	1238	1114	891
					Fz	.0001	.0002	.0003	.0004	.0007	.0011	.0013	.0013	.0015	.0016	.0018	.0018
		Slotting	1 (0.8)	1	SFM (VC)	210 (168-252)					230 (184-276)						
					RPM	6791	5093	4074	3395	2546	2228	1857	1592	1393	1238	1114	891
					Fz	.0001	.0002	.0003	.0004	.0007	.0011	.0013	.0013	.0015	.0016	.0018	.0018
K < 260	CAST IRON 0.6020 (GG20) 0.8145 (GTS-45-06) 0.7060 (GGG-60)	Side Cutting	1.5 (1.2)	0.5	SFM (VC)	367 (294-441)					404 (323-484)						
					RPM	11884	8913	7130	5942	4456	3915	3263	2797	2447	2175	1958	1566
					Fz	.0002	.0004	.0006	.0008	.0013	.0019	.0023	.0024	.0026	.0029	.0032	.0031
		Slotting	1 (0.8)	1	SFM (VC)	367 (294-441)					404 (323-484)						
					RPM	11884	8913	7130	5942	4456	3915	3263	2797	2447	2175	1958	1566
					Fz	.0002	.0004	.0006	.0008	.0013	.0019	.0023	.0024	.0026	.0029	.0032	.0031
M	STAINLESS STEELS 300 1.4301 (X5 CRNI 18 10) 1.4436 (X3 CRNIMO 17 13 3) 1.4306 (X2 CRNI 19 11) 1.4435 (X2 CRNIMO 18 14 3)	Side Cutting	1.5 (1.2)	0.5	SFM (VC)	348 (278-417)					348 (278-417)						
					RPM	11247	8435	6748	5623	4218	3374	2812	2410	2109	1874	1687	1350
					Fz	.0002	.0003	.0005	.0007	.0011	.0019	.0022	.0023	.0024	.0028	.0030	.0030
		Slotting	1 (0.8)	1	SFM (VC)	348 (278-417)					348 (278-417)						
					RPM	11247	8435	6748	5623	4218	3374	2812	2410	2109	1874	1687	1350
					Fz	.0002	.0003	.0005	.0007	.0011	.0019	.0022	.0023	.0024	.0028	.0030	.0030

RPM = rev./min. FEED = in./min.
SFM = ft./min. FZ = in./tooth




CHART CONTINUES ON NEXT PAGE

YG V7 PLUS A END MILLS


RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE - METRIC

GMF52, GMF53, GMF54, GMF55, GMF56, GMF57, GMF58, GMF59, GMF60, GMF61, GMF62, GMF63 SERIES

ISO Hardness (BHN)	Work Materials	Speed and Feed Recommendations				Diameter (mm)											
		Type of Cut	Ap x D1	Ae x D1	Parameters	3	4	5	6	8	10	12	14	16	18	20	25
M	STAINLESS STEELS 400 1.4005 (X12 CRS 13) 1.4104 (X12 CRMOS 17)	Side Cutting	1.5 (1.2)	0.5	SFM (VC)	486 (388-583)					486 (388-583)						
					RPM	15703	11777	9422	7852	5889	4711	3926	3365	2944	2617	2355	1884
					Fz	.0002	.0002	.0004	.0005	.0009	.0013	.0015	.0017	.0018	.0020	.0022	.0022
		Slotting	1 (0.8)	1	SFM (VC)	486 (388-583)					486 (388-583)						
					RPM	15703	11777	9422	7852	5889	4711	3926	3365	2944	2617	2355	1884
					Fz	.0002	.0002	.0004	.0005	.0009	.0013	.0015	.0017	.0018	.0020	.0022	.0022
M	STAINLESS STEELS (PH) 1.4594 (Z7 CNU 15.05)	Side Cutting	1.5 (1.2)	0.5	SFM (VC)	312 (249-374)					312 (249-374)						
					RPM	10080	7560	6048	5040	3780	3024	2520	2160	1890	1680	1512	1210
					Fz	.0002	.0003	.0005	.0007	.0011	.0019	.0022	.0023	.0024	.0027	.0030	.0030
		Slotting	1 (0.8)	1	SFM (VC)	312 (249-374)					312 (249-374)						
					RPM	10080	7560	6048	5040	3780	3024	2520	2160	1890	1680	1512	1210
					Fz	.0002	.0003	.0005	.0007	.0011	.0019	.0022	.0023	.0024	.0027	.0030	.0030
S	TITANIUM Ti6AL4V Ti5AL5V5MO Ti7AL4MO	Side Cutting	1	0.35	SFM (VC)	190 (152-228)					190 (152-228)						
					RPM	6154	4615	3692	3077	2308	1846	1538	1319	1154	1026	923	738
					Fz	.0002	.0003	.0004	.0006	.0010	.0017	.0020	.0021	.0022	.0024	.0027	.0027
		Slotting	0.5	1	SFM (VC)	190 (152-228)					190 (152-228)						
					RPM	6154	4615	3692	3077	2308	1846	1538	1319	1154	1026	923	738
					Fz	.0002	.0003	.0004	.0006	.0010	.0017	.0020	.0021	.0022	.0024	.0027	.0027
S	HIGH-TEMPERATURE ALLOY INCONEL HASTALLOY RENE	Side Cutting	1	0.25	SFM (VC)	85 (68-102)					85 (68-102)						
					RPM	2759	2069	1655	1379	1035	828	690	591	517	460	414	331
					Fz	.0002	.0003	.0003	.0005	.0007	.0013	.0015	.0016	.0017	.0019	.0021	.0020
		Slotting	0.5	1	SFM (VC)	85 (68-102)					85 (68-102)						
					RPM	2759	2069	1655	1379	1035	828	690	591	517	460	414	331
					Fz	.0002	.0003	.0003	.0005	.0007	.0013	.0015	.0016	.0017	.0019	.0021	.0020

RPM = rev./min. FEED = in./min.
SFM = ft./min. FZ = in./tooth



NOTES:

- * Feed to be reduced by approximately 50% if L.O.C. (Length Of Cut) is over 3xD
- * The above recommendations are based on ideal conditions; for smaller taper machining centers or less rigid conditions please adjust parameters accordingly on diameters greater than 1/2"
- * In profile operations, engaging more than 2xD, reduce the radial depth of cut by 50%-60%
- * Finish cuts typically require reduced cutting feeds and speeds; also, it is recommended the radial width of cut (AE) should not exceed 2% x D1


YG V7 PLUS A END MILLS

RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE - METRIC

UGMG55, UGMG56 SERIES

ISO Hardness (BHN)	Work Materials	Type of Cut	Ap x D1	Ae x D1	Parameters	Diameter (mm)										
						3	4	5	6	8	10	12	16	18	20	25
P < 300	CARBON STEEL 10**, 11**, 12**, 12L**, 15**		1	0.5	SFM (VC)	531 (425-638)										
					RPM	17189	12892	10313	8594	6446	5157	4297	3223	2865	2578	2063
					Fz	.0010	.0011	.0012	.0016	.0024	.0026	.0028	.0030	.0031	.0035	.0039
					FEED	67.67	54.81	48.72	54.14	60.90	52.78	47.37	38.07	36.09	36.54	32.16
P > 300 P < 380	ALLOY STEEL 41**, 43**, 51**, 86**		1	0.5	SFM (VC)	371 (297-445)										
					RPM	11990	8992	7194	5995	4496	3597	2997	2248	1998	1798	1439
					FZ	.0010	.0011	.0012	.0016	.0024	.0026	.0028	.0029	.0031	.0035	.0039
					FEED	47.20	38.23	33.99	37.76	42.48	36.82	33.04	26.20	24.86	25.49	22.43
P < 380	TOOL STEEL A2, D2, H13, P20, T15		1	0.5	SFM (VC)	223 (178-268)										
					RPM	7215	5411	4329	3608	2706	2165	1804	1353	1203	1082	866
					FZ	.0007	.0007	.0008	.0011	.0017	.0018	.0019	.0020	.0022	.0025	.0028
					FEED	19.32	16.19	14.32	15.91	17.90	15.34	13.92	11.08	10.60	10.74	9.54
K < 260	CAST IRON GRAY, MALLEABLE, DUCTILE		1	0.5	SFM (VC)	390 (312-469)										
					RPM	12626	9470	7576	6313	4735	3788	3157	2367	2104	1894	1515
					FZ	.0012	.0013	.0015	.0020	.0029	.0032	.0034	.0037	.0039	.0044	.0049
					FEED	61.64	49.21	44.14	49.71	55.18	48.32	43.25	34.67	32.81	33.40	29.59
M	STAINLESS STEELS 300 304, 316, 304L, 316LSUS316		1	0.5	SFM (VC)	279 (223-335)										
					RPM	9019	6764	5411	4509	3382	2706	2255	1691	1503	1353	1082
					FZ	.0008	.0008	.0010	.0016	.0018	.0020	.0022	.0024	.0025	.0026	.0027
					FEED	28.41	21.30	21.30	29.12	23.97	21.30	19.53	15.98	15.15	13.85	11.59
M	STAINLESS STEELS 400 416, 420F, 430F, 440F		1	0.5	SFM (VC)	253 (202-303)										
					RPM	8170	6127	4902	4085	3064	2451	2042	1532	1362	1225	980
					FZ	.0006	.0006	.0010	.0012	.0016	.0018	.0020	.0021	.0023	.0023	.0023
					FEED	19.30	14.47	19.30	19.30	19.30	17.37	16.08	13.03	12.65	11.19	9.11
M	STAINLESS STEELS (PH) 17-4PH, 15-5PH, 13-8PH		1	0.5	SFM (VC)	253 (202-303)										
					RPM	8170	6127	4902	4085	3064	2451	2042	1532	1362	1225	980
					FZ	.0008	.0008	.0010	.0016	.0018	.0020	.0022	.0024	.0025	.0026	.0027
					FEED	25.73	19.30	19.30	26.38	21.71	19.30	17.69	14.47	13.72	12.54	10.50
S	TITANIUM Ti6AL4V, Ti5AL5V5MO, Ti7AL4MO		0.3	0.5	SFM (VC)	154 (123-185)										
					RPM	4987	3740	2992	2493	1870	1496	1247	935	831	748	598
					FZ	.0007	.0007	.0009	.0015	.0016	.0018	.0019	.0021	.0023	.0023	.0024
					FEED	14.14	10.60	10.37	14.53	11.78	10.60	9.62	7.95	7.59	6.83	5.75
S	HIGH-TEMPERATURE ALLOY INCONEL, HASTALLOY, RENE		0.3	0.2	SFM (VC)	69 (55-83)										
					RPM	2228	1671	1337	1114	836	668	557	418	371	334	267
					FZ	.0006	.0006	.0007	.0011	.0012	.0014	.0015	.0017	.0018	.0018	.0019
					FEED	4.91	3.68	3.58	4.91	4.08	3.68	3.33	2.76	2.63	2.37	2.02



RPM = rev./min. FEED = in./min.
SFM = ft./min. FZ = in./tooth

See notes on next page

YG V7 PLUS A END MILLS

RECOMMENDED CUTTING CONDITIONS

CARBIDE, 6 FLUTE - METRIC

GMG12, GMG13, GMG14, GMG15, GMG16, GMG17, GMG18, GMG19 SERIES

ISO Hardness (BHN)	Work Materials	Type of Cut	Ap x D1	Ae x D1	Parameters	Diameter (mm)						
						6	8	10	12	16	20	25
P < 300	CARBON STEEL 10**, 11**, 12**, 12L**, 15**	Side Cutting 	2 (*)	0.05	SFM (VC)	984 (787-1181)						
					RPM	15915	11937	9549	7958	5968	4775	3820
					Fz	.0027	.0046	.0057	.0068	.0080	.0089	.0091
					FEED	255.65	327.08	324.83	325.20	284.79	253.77	209.33
P > 300 P < 380	ALLOY STEEL 41**, 43**, 51**, 86**	Side Cutting 	2 (*)	0.05	SFM (VC)	666 (533-799)						
					RPM	10769	8077	6462	5385	4039	3231	2585
					FZ	.0020	.0033	.0042	.0050	.0059	.0066	.0069
					FEED	127.20	162.18	161.80	162.81	142.14	127.45	106.24
P < 380	TOOL STEEL A2, D2, H13, P20, T15	Side Cutting 	2 (*)	0.05	SFM (VC)	328 (262-394)						
					RPM	5305	3979	3183	2653	1989	1592	1273
					FZ	.0016	.0028	.0035	.0041	.0048	.0054	.0057
					FEED	51.38	66.73	66.17	65.79	57.80	51.51	43.31
M	STAINLESS STEELS 300 304, 316, 304L, 316LSUS316	Side Cutting 	2 (*)	0.05	SFM (VC)	482 (386-579)						
					RPM	7799	5849	4679	3899	2924	2340	1872
					FZ	.0016	.0028	.0035	.0041	.0048	.0054	.0056
					FEED	75.53	98.10	97.27	96.71	84.97	75.71	63.22
M	STAINLESS STEELS 400 416, 420F, 430F, 440F	Side Cutting 	2 (*)	0.05	SFM (VC)	699 (559-839)						
					RPM	11300	8475	6780	5650	4238	3390	2712
					FZ	.0019	.0033	.0041	.0049	.0057	.0064	.0066
					FEED	130.80	168.17	166.56	166.83	146.14	129.73	107.63
M	STAINLESS STEELS (PH) 17-4PH, 15-5PH, 13-8PH	Side Cutting 	2 (*)	0.05	SFM (VC)	440 (352-528)						
					RPM	7109	5332	4265	3554	2666	2133	1706
					FZ	.0016	.0028	.0035	.0041	.0048	.0054	.0056
					FEED	68.85	89.42	88.67	88.16	77.46	69.02	57.23
S	TITANIUM Ti6AL4V, Ti5AL5V5MO, Ti7AL4MO	Side Cutting 	2 (*)	0.05	SFM (VC)	381 (304-457)						
					RPM	6154	4615	3692	3077	2308	1846	1477
					FZ	.0013	.0022	.0028	.0033	.0038	.0044	.0046
					FEED	47.97	59.97	61.06	60.33	52.88	49.28	40.82
S	HIGH-TEMPERATURE ALLOY INCONEL, HASTALLOY, RENE	Side Cutting 	2 (*)	0.05	SFM (VC)	108 (87-130)						
					RPM	1751	1313	1050	875	657	525	420
					FZ	.0013	.0022	.0028	.0032	.0038	.0044	.0045
					FEED	13.65	17.06	17.37	16.96	15.04	13.90	11.41

RPM = rev./min. FEED = in./min.
SFM = ft./min. FZ = in./tooth

- NOTES:**
- * The above recommendations are based on ideal conditions; for smaller taper machining centers or less rigid conditions please adjust parameters accordingly on diameters greater than 12mm
 - * Finish cuts typically require reduced cutting feeds and speeds; also, it is recommended the radial width of cut (AE) should not exceed 2% x D1
 - * If product's length of cut (L.O.C.) is below 2D, it must be applied L.O.C. x 90%



Being the best through innovation

CARBIDE




V7 MILL INOX END MILLS

- Silent Cutting of Stainless Steels up to HRc40.
Designed as Variable Leads, YG-1's Patent.



Global Cutting Tool Leader **YG-1**





EMC75 SERIES PLAIN SHANK
EMD60 SERIES FLAT SHANK

CARBIDE, 4 FLUTE STUB LENGTH

- ▶ Special flute geometry eliminates vibrations
- ▶ Designed for mild steels, stainless steel, cast iron, tool steels, titanium alloys, prehardened steels and low hardness material
- ▶ Excellent work piece finishes
- ▶ Higher speeds, deeper cuts and metal removal rates




◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT				
EMC75008	-	1/8	1/8	1/8	1-1/2
EMC75010	-	5/32	3/16	3/16	2
EMC75012	-	3/16	3/16	3/16	2
EMC75014	-	7/32	1/4	1/4	2
EMC75016	-	1/4	1/4	1/4	2
EMC75020	-	5/16	5/16	5/16	2
-	EMD60024	3/8	3/8	3/8	2
-	EMD60028	7/16	7/16	7/16	2-1/2
-	EMD60032	1/2	1/2	1/2	2-1/2
-	EMD60040	5/8	5/8	5/8	3
-	EMD60048	3/4	3/4	3/4	3
-	EMD60064	1	1	1	4

▶ Shanks 3/8" and over come standard with Flats.

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.0012	h6



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	○	○				◎							◎	○



EMC76 SERIES PLAIN SHANK
EMD61 SERIES FLAT SHANK

CARBIDE, 4 FLUTE STUB LENGTH CORNER RADIUS

- ▶ Special flute geometry eliminates vibrations
- ▶ Designed for mild steels, stainless steel, cast iron, tool steels, titanium alloys, prehardened steels and low hardness material
- ▶ Excellent work piece finishes
- ▶ Higher speeds, deeper cuts and metal removal rates



◆ U.S.A Stock

Unit : Inch

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT	R				
EMC76008	-	R.015	1/8	1/8	1/8	1-1/2
EMC76010	-	R.015	5/32	3/16	3/16	2
EMC76012	-	R.015	3/16	3/16	3/16	2
EMC76014	-	R.020	7/32	1/4	1/4	2
EMC76016	-	R.020	1/4	1/4	1/4	2
EMC76020	-	R.020	5/16	5/16	5/16	2
-	EMD61024	R.020	3/8	3/8	3/8	2
-	EMD61028	R.020	7/16	7/16	7/16	2-1/2
-	EMD61032	R.030	1/2	1/2	1/2	2-1/2
-	EMD61040	R.040	5/8	5/8	5/8	3
-	EMD61048	R.040	3/4	3/4	3/4	3
-	EMD61064	R.040	1	1	1	4

▶ Shanks 3/8" and over come standard with Flats.

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.0012	h6

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	○	○				◎							◎	○



EMB12 SERIES PLAIN SHANK
EMB37 SERIES FLAT SHANK

CARBIDE, 4 FLUTE REGULAR LENGTH

- Special flute geometry eliminates vibrations
- Designed for mild steels, stainless steel, cast iron, tool steels, titanium alloys, prehardened steels and low hardness material
- Excellent work piece finishes
- Higher speeds, deeper cuts and metal removal rates



MG 4 PLAIN FLAT P.1033


◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT				
EMB12008	-	1/8	1/8	3/8	1-1/2
EMB12010	-	5/32	3/16	7/16	2
EMB12012	-	3/16	3/16	7/16	2
EMB12014	-	7/32	1/4	7/16	2-1/2
EMB12016	-	1/4	1/4	1/2	2-1/2
EMB12018	-	9/32	5/16	5/8	2-1/2
EMB12020	-	5/16	5/16	13/16	2-1/2
EMB12022	-	11/32	3/8	13/16	2-1/2
-	EMB37024	3/8	3/8	7/8	2-1/2
-	EMB37026	13/32	7/16	15/16	2-3/4
-	EMB37028	7/16	7/16	1	2-3/4
-	EMB37030	15/32	1/2	1	3
-	EMB37032	1/2	1/2	1	3
-	EMB37036	9/16	9/16	1-1/8	3-1/2
-	EMB37040	5/8	5/8	1-1/4	3-1/2
-	EMB37048	3/4	3/4	1-1/2	4
-	EMB37064	1	1	1-1/2	4

► Shanks 3/8" and over come standard with Flats.

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	h6



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	○	○				◎							◎	○



EMB13 SERIES PLAIN SHANK
EMB38 SERIES FLAT SHANK

CARBIDE, 4 FLUTE REGULAR LENGTH CORNER RADIUS

- Special flute geometry eliminates vibrations
- Designed for mild steels, stainless steel, cast iron, tool steels, titanium alloys, prehardened steels and low hardness material
- Excellent work piece finishes
- Higher speeds, deeper cuts and metal removal rates



MG 4 PLAIN FLAT P.1033

◆ U.S.A Stock

Unit : Inch

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT	R				
EMB13008	-	R.015	1/8	1/8	3/8	1-1/2
EMB13012	-	R.015	3/16	3/16	7/16	2
EMB13016	-	R.020	1/4	1/4	1/2	2-1/2
EMB13020	-	R.020	5/16	5/16	13/16	2-1/2
-	EMB38024	R.020	3/8	3/8	7/8	2-1/2
-	EMB38028	R.020	7/16	7/16	1	2-3/4
-	EMB38032	R.030	1/2	1/2	1	3
-	EMB38036	R.030	9/16	9/16	1-1/8	3-1/2
-	EMB38040	R.040	5/8	5/8	1-1/4	3-1/2
-	EMB38048	R.040	3/4	3/4	1-1/2	4
-	EMB38064	R.040	1	1	1-1/2	4

► Shanks 3/8" and over come standard with Flats.

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	h6

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	○	○				◎							◎	○



EMB20 SERIES PLAIN SHANK
FLAT SHANK

CARBIDE, 4 FLUTE EXTENDED LENGTH, LONG REACH

- ▶ Higher speeds, deeper cuts and metal removal rates.
- ▶ Improved surface finishes
- ▶ New "NANO" AlTiN coating



MG 4 PLAIN FLAT P.1033

◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Reach Length	Overall Length
PLAIN	FLAT					
EMB20160	-	1/4	1/4	3/8	1-1/4	4
-	EMB20240	3/8	3/8	1/2	1-7/8	4
-	EMB20320	1/2	1/2	5/8	2-1/4	4
-	EMB20400	5/8	5/8	3/4	2-1/4	4-1/8
-	EMB20401	5/8	5/8	3/4	3-1/4	5
-	EMB20480	3/4	3/4	1	2-1/4	4-1/4
-	EMB20481	3/4	3/4	1	3-1/4	5-1/2
-	EMB20640	1	1	1-1/8	2-1/4	4-1/2
-	EMB20641	1	1	1-1/8	3-1/4	5-1/2
-	EMB20642	1	1	1-1/8	4-1/4	6-1/2

▶ Shanks 3/8" and over come standard with Flats.

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	h6

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	○	○				◎							◎	○



EMB78 SERIES PLAIN SHANK
EMB79 SERIES FLAT SHANK

CARBIDE, 4 FLUTE REGULAR LENGTH BALL NOSE

- ▶ Special flute geometry eliminates vibrations
- ▶ Designed for mild steels, stainless steel, cast iron, tool steels, titanium alloys, prehardened steels and low hardness material
- ▶ Excellent work piece finishes
- ▶ Higher speeds, deeper cuts and metal removal rates



MG 4 R ±.0004" PLAIN FLAT P.1034

◆ U.S.A Stock

Unit : Inch

EDP No.		Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT	R (±.0004)				
EMB78008	-	R1/16	1/8	1/8	3/8	1-1/2
EMB78010	-	R5/64	5/32	3/16	7/16	2
EMB78012	-	R3/32	3/16	3/16	7/16	2
EMB78016	-	R1/8	1/4	1/4	1/2	2-1/2
EMB78020	-	R5/32	5/16	5/16	13/16	2-1/2
-	EMB79024	R3/16	3/8	3/8	7/8	2-1/2
-	EMB79032	R1/4	1/2	1/2	1	3
-	EMB79040	R5/16	5/8	5/8	1-1/4	3-1/2
-	EMB79048	R3/8	3/4	3/4	1-1/2	4
-	EMB79064	R1/2	1	1	1-1/2	4

▶ Shanks 3/8" and over come standard with Flats.

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	h6

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	○	○				◎							◎	○



EMB76 SERIES PLAIN SHANK
EMB77 SERIES FLAT SHANK

CARBIDE, 5 FLUTE REGULAR LENGTH

- ▶ Special flute geometry eliminates vibrations
- ▶ Designed for mild steels, stainless steel, cast iron, tool steels, titanium alloys, prehardened steels and low hardness material
- ▶ Excellent work piece finishes
- ▶ Higher speeds, deeper cuts and metal removal rates




◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT				
EMB76016	-	1/4	1/4	1/2	2-1/2
EMB76020	-	5/16	5/16	13/16	2-1/2
EMB76024	EMB77024	3/8	3/8	7/8	2-1/2
-	EMB77032	1/2	1/2	1	3
-	EMB77036	9/16	9/16	1-1/8	3-1/2
-	EMB77040	5/8	5/8	1-1/4	3-1/2
-	EMB77048	3/4	3/4	1-1/2	4
-	EMB77064	1	1	1-1/2	4

▶ Shanks 3/8" and over come standard with Flats.

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.012	h6



Enforced cutting edge

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	○	○				◎							◎	○



EMB41 SERIES PLAIN SHANK
EMB42 SERIES FLAT SHANK

CARBIDE, 4 FLUTE SHORT LENGTH

- ▶ Special flute geometry eliminates vibrations
- ▶ Designed for mild steels, stainless steel, cast iron, tool steels, titanium alloys, prehardened steels and low hardness material
- ▶ Excellent work piece finishes
- ▶ Higher speeds, deeper cuts and metal removal rates




◇ Call for Availability

Unit : mm

EDP No.		Mill Diameter		Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT	Metric	Inch			
EMB41030	EMB42030	3.0	.1181	6	7	54
EMB41040	EMB42040	4.0	.1575	6	8	54
EMB41050	EMB42050	5.0	.1969	6	10	54
EMB41060	EMB42060	6.0	.2362	6	10	54
EMB41080	EMB42080	8.0	.3150	8	12	58
EMB41100	EMB42100	10.0	.3937	10	14	66
EMB41120	EMB42120	12.0	.4724	12	16	73
EMB41140	EMB42140	14.0	.5512	14	18	75
EMB41160	EMB42160	16.0	.6299	16	22	82
EMB41180	EMB42180	18.0	.7087	18	24	84
EMB41200	EMB42200	20.0	.7874	20	26	92

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0~-0.03	h6



Enforced cutting edge

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	○	○				◎							◎	○



EMB43 SERIES PLAIN SHANK
EMB44 SERIES FLAT SHANK

CARBIDE, 4 FLUTE SHORT LENGTH CORNER RADIUS

- ▶ Special flute geometry eliminates vibrations
- ▶ Designed for mild steels, stainless steel, cast iron, tool steels, titanium alloys, prehardened steels and low hardness material
- ▶ Excellent work piece finishes
- ▶ Higher speeds, deeper cuts and metal removal rates



◇ Call for Availability

Unit : mm

EDP No.		Corner Radius	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT		Metric	Inch			
EMB43030	EMB44030	RO.3	3.0	.1181	6	7	54
EMB43040	EMB44040	RO.3	4.0	.1575	6	8	54
EMB43050	EMB44050	RO.3	5.0	.1969	6	10	54
EMB43060	EMB44060	RO.5	6.0	.2362	6	10	54
EMB43080	EMB44080	RO.5	8.0	.3150	8	12	58
EMB43100	EMB44100	RO.5	10.0	.3937	10	14	66
EMB43120	EMB44120	RO.7	12.0	.4724	12	16	73
EMB43140	EMB44140	RO.7	14.0	.5512	14	18	75
EMB43160	EMB44160	R1.0	16.0	.6299	16	22	82
EMB43180	EMB44180	R1.0	18.0	.7087	18	24	84
EMB43200	EMB44200	R1.0	20.0	.7874	20	26	92

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	○	○			◎							◎	○



EMB14 SERIES PLAIN SHANK
EMB39 SERIES FLAT SHANK

CARBIDE, 4 FLUTE REGULAR LENGTH

- ▶ Special flute geometry eliminates vibrations
- ▶ Designed for mild steels, stainless steel, cast iron, tool steels, titanium alloys, prehardened steels and low hardness material
- ▶ Excellent work piece finishes
- ▶ Higher speeds, deeper cuts and metal removal rates




◇ Call for Availability

Unit : mm

EDP No.		Mill Diameter		Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT	Metric	Inch			
EMB14030	-	3.0	.1181	6	8	57
EMB14040	-	4.0	.1575	6	11	57
EMB14050	-	5.0	.1969	6	13	57
EMB14060	-	6.0	.2362	6	13	57
EMB14080	-	8.0	.3150	8	19	63
EMB14100	-	10.0	.3937	10	22	72
-	EMB39120	12.0	.4724	12	26	83
-	EMB39140	14.0	.5512	14	26	83
-	EMB39160	16.0	.6299	16	32	92
-	EMB39180	18.0	.7087	18	32	92
-	EMB39200	20.0	.7874	20	38	104
-	EMB39250	25.0	.9800	25	38	104

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0~-0.03	h6



◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	○	○			◎							◎	○



EMB15 SERIES PLAIN SHANK
EMB40 SERIES FLAT SHANK

CARBIDE, 4 FLUTE REGULAR LENGTH CORNER RADIUS

- ▶ Special flute geometry eliminates vibrations
- ▶ Designed for mild steels, stainless steel, cast iron, tool steels, titanium alloys, prehardened steels and low hardness material
- ▶ Excellent work piece finishes
- ▶ Higher speeds, deeper cuts and metal removal rates



◇ Call for Availability

Unit : mm

EDP No.		Corner Radius	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT		Metric	Inch			
EMB15030	-	RO.3	3.0	.1181	6	8	57
EMB15040	-	RO.3	4.0	.1575	6	11	57
EMB15050	-	RO.3	5.0	.1969	6	13	57
EMB15060	-	RO.5	6.0	.2362	6	13	57
EMB15080	-	RO.5	8.0	.3150	8	19	63
EMB15100	-	RO.5	10.0	.3937	10	22	72
-	EMB40120	RO.7	12.0	.4724	12	26	83
-	EMB40140	RO.7	14.0	.5512	14	26	83
-	EMB40160	R1.0	16.0	.6299	16	32	92
-	EMB40180	R1.0	18.0	.7087	18	32	92
-	EMB40200	R1.0	20.0	.7874	20	38	104
-	EMB40250	R1.0	25.0	.9800	25	38	104

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	○	○			◎							◎	○



EMB74 SERIES PLAIN SHANK
EMB75 SERIES FLAT SHANK

CARBIDE, 4 FLUTE REGULAR LENGTH BALL NOSE

- ▶ Special flute geometry eliminates vibrations
- ▶ Designed for mild steels, stainless steel, cast iron, tool steels, titanium alloys, prehardened steels and low hardness material
- ▶ Excellent work piece finishes
- ▶ Higher speeds, deeper cuts and metal removal rates



◇ Call for Availability

Unit : mm

EDP No.		Radius of Ball Nose	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT		Metric	Inch			
EMB74030	EMB75030	R1.5	3.0	.1181	6	8	57
EMB74040	EMB75040	R2.0	4.0	.1575	6	11	57
EMB74050	EMB75050	R2.5	5.0	.1969	6	13	57
EMB74060	EMB75060	R3.0	6.0	.2362	6	13	57
EMB74080	EMB75080	R4.0	8.0	.3150	8	19	63
EMB74100	EMB75100	R5.0	10.0	.3937	10	22	72
EMB74120	EMB75120	R6.0	12.0	.4724	12	26	83
EMB74160	EMB75160	R8.0	16.0	.6299	16	32	92
EMB74200	EMB75200	R10.0	20.0	.7874	20	38	104
EMB74250	EMB75250	R12.5	25.0	.9800	25	38	104

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	○	○			◎							◎	○



EMB72 SERIES PLAIN SHANK
EMB73 SERIES FLAT SHANK

CARBIDE, 5 FLUTE REGULAR LENGTH

- ▶ Special flute geometry eliminates vibrations
- ▶ Designed for mild steels, stainless steel, cast iron, tool steels, titanium alloys, prehardened steels and low hardness material
- ▶ Excellent work piece finishes
- ▶ Higher speeds, deeper cuts and metal removal rates




◇ Call for Availability

Unit : mm

EDP No.		Mill Diameter		Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT	Metric	Inch			
EMB72060	EMB73060	6.0	.2362	6	13	57
EMB72080	EMB73080	8.0	.3150	8	19	63
EMB72100	EMB73100	10.0	.3937	10	22	72
EMB72120	EMB73120	12.0	.4724	12	26	83
EMB72140	EMB73140	14.0	.5512	14	26	83
EMB72160	EMB73160	16.0	.6299	16	32	92
EMB72180	EMB73180	18.0	.7087	18	32	92
EMB72200	EMB73200	20.0	.7874	20	38	104
EMB72250	EMB73250	25.0	.9800	25	38	104

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0~-0.03	h6



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	○	○				◎							◎	○




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE

EMC75, EMD60, EMC76, EMD61, EMB12, EMB37, EMB13, EMB38, EMB20
EMB41, EMB42, EMB43, EMB44, EMB14, EMB39, EMB15, EMB40 SERIES

MATERIAL	P		M				S			
	ALLOY STEELS CAST IRON		STAINLESS STEELS 300SERIES		STAINLESS STEELS 400SERIES		TITANIUM		HIGH TEMPERATURE ALLOY	
HARDNESS	~HRc 20									
STRENGTH	~1000N/mm ²									
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8	12735	10.2	9625	7.3	13475	7.6	8320	7.6	2565	2.1
3/16	8490	10.9	6385	8.3	12000	8.4	5550	8.4	1685	1.8
1/4	6370	11.5	4810	9.6	6815	9.6	4160	9.6	1285	2.5
5/16	5100	13.0	3850	10.7	5390	10.7	3330	10.7	1025	2.8
3/8	4245	18.4	3210	15.4	4490	15.4	2770	15.4	855	4.1
7/16	4010	24.5	2750	20.9	3850	20.9	2380	20.7	735	5.5
1/2	3500	25.9	2400	21.0	3370	21.0	2080	21.0	640	5.6
9/16	3110	26.0	2140	21.2	2990	21.2	1850	21.2	570	5.7
5/8	2800	26.1	1925	21.2	2700	21.2	1660	21.2	510	5.6
3/4	2340	24.0	1600	19.4	2250	19.4	1390	19.4	425	5.2
1	1755	17.4	1200	14.7	1685	15.1	1040	15.1	315	4.3



*1.2 x D Axial cutting depth should be applied for Short length series DIA over 5/16mm
*0.6 x D Axial cutting depth should be applied for Stub length series.

CARBIDE

HSS

CBN
END MILLS

i-Xmill
END MILLS

i-SMART
MODULAR
TYPE END MILLS

X5070
END MILLS

4G MILL
END MILLS

X-POWER
END MILLS

JET-POWER
END MILLS

TitaNox
-POWER
END MILLS

V7 PLUS A
END MILLS

V7 MILL INOX
END MILLS

ALU-POWER
HPC
END MILLS

ALU-POWER
END MILLS

D-POWER
GRAPHITE
END MILLS

D-POWER
CFRP
END MILLS

ROUTERS
CFRP

STANDARD
CARBIDE
END MILLS

ONLY ONE
COATED PM60
END MILLS

SINE -POWER
END MILLS

TANK-POWER
END MILLS

STANDARD
COBALT & HSS
END MILLS

TECHNICAL
DATA



**V7 MILL INOX
END MILLS**

RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE BALL NOSE

EMB78, EMB79, EMB74, EMB75 SERIES

MATERIAL	P		M				S			
	ALLOY STEELS CAST IRON		STAINLESS STEELS 300SERIES		STAINLESS STEELS 400SERIES		TITANIUM		HIGH TEMPERATURE ALLOY	
HARDNESS	~HRc20									
STRENGTH	~1000N/mm ²									
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8	13530	53.2	7770	24.2	7020	16.4	5510	10.4	3010	5.2
3/16	9020	42.6	5180	20.3	4680	18.2	3680	8.7	2010	3.3
1/4	6770	40.7	3880	24.9	3510	16.4	2760	8.6	1500	3.7
5/16	5410	50.8	3110	21.9	2810	17.5	2210	10.4	1200	4.8
3/8	4510	42.6	2590	20.3	2340	16.6	1840	8.7	1000	4.2
7/16	3870	39.5	2220	18.3	2010	15.0	1580	8.6	860	4.4
1/2	3380	37.2	1940	16.8	1750	13.8	1380	8.6	750	4.5
9/16	3010	34.2	1730	15.6	1560	12.8	1230	8.0	670	4.5
5/8	2710	31.8	1550	14.7	1400	11.9	1100	7.6	600	4.4
3/4	2260	32.0	1290	13.3	1170	10.8	920	8.7	500	4.2
1	1690	26.5	970	10.7	880	8.2	690	7.4	380	3.1





RPM = rev./min.
FEED = inch/min.

CARBIDE, 5 FLUTE

EMB76, EMB77, EMB72, EMB73 SERIES

MATERIAL	P		M				S			
	ALLOY STEELS CAST IRON		STAINLESS STEELS 300SERIES		STAINLESS STEELS 400SERIES		TITANIUM		HIGH TEMPERATURE ALLOY	
HARDNESS	~HRc20									
STRENGTH	~1000N/mm ²									
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	6870	46.1	5710	34.2	5310	31.8	4200	24.9	1350	4.4
5/16	5490	41.3	4570	28.6	4250	26.5	3360	20.6	1080	4.3
3/8	4580	45.5	3810	28.5	3540	26.3	2800	20.7	900	4.5
7/16	3920	44.0	3270	32.6	3040	23.9	2400	20.8	770	4.7
1/2	3430	42.8	2860	35.7	2660	22.1	2100	20.8	680	4.8
9/16	3050	41.7	2540	32.7	2360	29.6	1860	20.9	600	5.4
5/8	2750	41.4	2290	30.9	2130	28.4	1680	20.7	540	5.1
3/4	2290	39.6	1900	28.6	1770	26.4	1400	20.7	450	5.4
1	1720	34.2	1430	24.8	1330	23.2	1050	18.3	340	5.1



RPM = rev./min.
FEED = inch/min.

1034 • phone:+1-800-765-8665, Technical Support : 888-868-5988, www.yg1usa.com



Being the best through innovation

CARBIDE



**ALU-POWER HPC
END MILLS**


- High Performance with High Feed, RPM and Chip Removal(Heavy Cutting)
- For Aluminum, Non-Ferrous and Non-Metallic Materials



JAG95 SERIES SQUARE
JAG97 SERIES CORNER RADIUS

CARBIDE, 3 FLUTE STANDARD LENGTH - DLC COATED

- ▶ Longer tool life
- ▶ Balanced cutting with less vibration
- ▶ Ability to run at higher speeds with less heat in aluminum
- ▶ More efficient chip evacuation
- ▶ Ability to counteract extreme radial forces



Unit : Inch

OD	SD	LOC	OAL	Square End	Corner Radius						
					.010	.030	.060	.090	.120	.190	.250
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
1/8	1/8	1/4	1-1/2	JAG95008	JAG97008	JAG97901	-	-	-	-	-
		3/8	1-1/2	JAG95901	JAG97902	JAG97903	-	-	-	-	-
3/16	3/16	5/16	2	JAG95012	JAG97012	JAG97904	-	-	-	-	-
		9/16	2	JAG95902	JAG97905	JAG97906	-	-	-	-	-
1/4	1/4	3/8	2	JAG95016	JAG97016	JAG97907	JAG97908	-	-	-	-
		5/8	2-1/2	JAG95903	JAG97909	JAG97910	JAG97911	-	-	-	-
5/16	5/16	1-1/4	3-1/4	JAG95904	JAG97912	JAG97913	JAG97914	-	-	-	-
		7/16	2	JAG95020	JAG97020	JAG97915	JAG97916	JAG97917	-	-	-
3/8	3/8	5/8	2-1/2	JAG95905	JAG97918	JAG97919	JAG97920	JAG97921	-	-	-
		1-1/4	3-1/2	JAG95906	JAG97922	JAG97923	JAG97924	JAG97925	-	-	-
7/16	7/16	1/2	2	JAG95024	JAG97024	JAG97926	JAG97927	JAG97928	JAG97929	-	-
		1	2-1/2	JAG95907	JAG97930	JAG97931	JAG97932	JAG97933	JAG97934	-	-
1/2	1/2	1-1/2	3-1/2	JAG95908	JAG97935	JAG97936	JAG97937	JAG97938	JAG97939	-	-
		2	4	JAG95909	JAG97940	JAG97941	JAG97942	JAG97943	JAG97944	-	-
3/4	3/4	9/16	2-1/2	JAG95028	JAG97028	JAG97945	JAG97946	JAG97947	JAG97948	-	-
		1-1/4	2-3/4	JAG95910	JAG97949	JAG97950	JAG97951	JAG97952	JAG97953	-	-
1	1	2	4	JAG95911	JAG97954	JAG97955	JAG97956	JAG97957	JAG97958	-	-
		5/8	2-1/2	JAG95032	JAG97032	JAG97959	JAG97960	JAG97961	JAG97962	JAG97963	-
1 1/8	1 1/8	1	3	JAG95927	JAG97879	JAG97880	JAG97881	JAG97882	JAG97883	JAG97884	-
		1-1/4	3	JAG95912	JAG97964	JAG97965	JAG97966	JAG97967	JAG97968	JAG97969	-
1 1/4	1 1/4	1-5/8	4	JAG95913	JAG97970	JAG97971	JAG97972	JAG97973	JAG97974	JAG97975	-
		2	4	JAG95914	JAG97976	JAG97977	JAG97978	JAG97979	JAG97980	JAG97981	-
1 1/2	1 1/2	2-1/2	5	JAG95915	JAG97982	JAG97983	JAG97984	JAG97985	JAG97986	JAG97987	-
		3	5	JAG95916	JAG97988	JAG97989	JAG97990	JAG97991	JAG97992	JAG97993	-

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70								◎	



JAG95 SERIES SQUARE
JAG97 SERIES CORNER RADIUS

CARBIDE, 3 FLUTE STANDARD LENGTH - DLC COATED

- ▶ Longer tool life
- ▶ Balanced cutting with less vibration
- ▶ Ability to run at higher speeds with less heat in aluminum
- ▶ More efficient chip evacuation
- ▶ Ability to counteract extreme radial forces



Unit : Inch

OD	SD	LOC	OAL	Square End	Corner Radius						
					.010	.030	.060	.090	.120	.190	.250
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
5/8	5/8	3/4	3	JAG95040	JAG97040	JAG97994	JAG97995	JAG97996	JAG97997	JAG97998	-
		1-5/8	3-1/2	JAG95917	JAG97999	JAG97801	JAG97802	JAG97803	JAG97804	JAG97805	-
		2-1/2	5	JAG95918	JAG97806	JAG97807	JAG97808	JAG97809	JAG97810	JAG97811	-
3/4	3/4	3	5-1/4	JAG95919	JAG97812	JAG97813	JAG97814	JAG97815	JAG97816	JAG97817	-
		1	3	JAG95048	JAG97048	JAG97818	JAG97819	JAG97820	JAG97821	JAG97822	JAG97823
3/4	3/4	1-5/8	4	JAG95920	JAG97824	JAG97825	JAG97826	JAG97827	JAG97828	JAG97829	JAG97830
		2-1/4	5	JAG95921	JAG97831	JAG97832	JAG97833	JAG97834	JAG97835	JAG97836	JAG97837
1	1	3-1/4	6	JAG95922	JAG97838	JAG97839	JAG97840	JAG97841	JAG97842	JAG97843	JAG97844
		4	6-1/4	JAG95923	JAG97845	JAG97846	JAG97847	JAG97848	JAG97849	JAG97850	JAG97851
1	1	1-1/4	3	JAG95064	JAG97064	JAG97852	JAG97853	JAG97854	JAG97855	JAG97856	JAG97857
		1-1/4	4	JAG95928	JAG97885	JAG97886	JAG97887	JAG97888	JAG97889	JAG97890	JAG97891
1	1	2	5	JAG95924	JAG97858	JAG97859	JAG97860	JAG97861	JAG97862	JAG97863	JAG97864
		3-1/4	6	JAG95925	JAG97865	JAG97866	JAG97867	JAG97868	JAG97869	JAG97870	JAG97871
1	1	4	7	JAG95926	JAG97872	JAG97873	JAG97874	JAG97875	JAG97876	JAG97877	JAG97878

Outside Diameter Tolerances (inch)		Shank Diameter Tolerance
Diameter	Tolerance	
1/8 - 3/16	+0/-0.00032	h6
1/4 - 3/8	+0/-0.00035	
1/2 - 5/8	+0/-0.00043	
3/4 - 1	+0/-0.00051	

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70								◎	



E5G95 SERIES SQUARE
E5G97 SERIES CORNER RADIUS

CARBIDE, 3 FLUTE STANDARD LENGTH

- ▶ Longer tool life
- ▶ Balanced cutting with less vibration
- ▶ Ability to run at higher speeds with less heat in aluminum
- ▶ More efficient chip evacuation
- ▶ Ability to counteract extreme radial forces



Unit : Inch

OD	SD	LOC	OAL	Square End	Corner Radius							
					.010	.030	.060	.090	.120	.190	.250	
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	
1/8	1/8	1/4	1-1/2	E5G95008	E5G97008	E5G97901	-	-	-	-	-	
		3/8	1-1/2	E5G95901	E5G97902	E5G97903	-	-	-	-	-	
3/16	3/16	5/16	2	E5G95012	E5G97012	E5G97904	-	-	-	-	-	
		9/16	2	E5G95902	E5G97905	E5G97906	-	-	-	-	-	
1/4	1/4	3/8	2	E5G95016	E5G97016	E5G97907	E5G97908	-	-	-	-	
		5/8	2-1/2	E5G95903	E5G97909	E5G97910	E5G97911	-	-	-	-	
5/16	5/16	1-1/4	3-1/4	E5G95904	E5G97912	E5G97913	E5G97914	-	-	-	-	
		7/16	2	E5G95020	E5G97020	E5G97915	E5G97916	E5G97917	-	-	-	
3/8	3/8	5/8	2-1/2	E5G95905	E5G97918	E5G97919	E5G97920	E5G97921	-	-	-	
		1-1/4	3-1/2	E5G95906	E5G97922	E5G97923	E5G97924	E5G97925	-	-	-	
7/16	7/16	1/2	2	E5G95024	E5G97024	E5G97926	E5G97927	E5G97928	E5G97929	-	-	
		1	2-1/2	E5G95907	E5G97930	E5G97931	E5G97932	E5G97933	E5G97934	-	-	
1/2	1/2	1-1/2	3-1/2	E5G95908	E5G97935	E5G97936	E5G97937	E5G97938	E5G97939	-	-	
		2	4	E5G95909	E5G97940	E5G97941	E5G97942	E5G97943	E5G97944	-	-	
1	1	9/16	2-1/2	E5G95028	E5G97028	E5G97945	E5G97946	E5G97947	E5G97948	-	-	
		1-1/4	2-3/4	E5G95910	E5G97949	E5G97950	E5G97951	E5G97952	E5G97953	-	-	
1	1	2	4	E5G95911	E5G97954	E5G97955	E5G97956	E5G97957	E5G97958	-	-	
		5/8	2-1/2	E5G95032	E5G97032	E5G97959	E5G97960	E5G97961	E5G97962	E5G97963	-	-
1	1	1	3	E5G95927	E5G97879	E5G97880	E5G97881	E5G97882	E5G97883	E5G97884	-	-
		1-1/4	3	E5G95912	E5G97964	E5G97965	E5G97966	E5G97967	E5G97968	E5G97969	-	-
1	1	1-5/8	4	E5G95913	E5G97970	E5G97971	E5G97972	E5G97973	E5G97974	E5G97975	-	-
		2	4	E5G95914	E5G97976	E5G97977	E5G97978	E5G97979	E5G97980	E5G97981	-	-
1	1	2-1/2	5	E5G95915	E5G97982	E5G97983	E5G97984	E5G97985	E5G97986	E5G97987	-	-
		3	5	E5G95916	E5G97988	E5G97989	E5G97990	E5G97991	E5G97992	E5G97993	-	-

▶ NEXT PAGE

◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
												◎	



E5G95 SERIES SQUARE
E5G97 SERIES CORNER RADIUS

CARBIDE, 3 FLUTE STANDARD LENGTH

- ▶ Longer tool life
- ▶ Balanced cutting with less vibration
- ▶ Ability to run at higher speeds with less heat in aluminum
- ▶ More efficient chip evacuation
- ▶ Ability to counteract extreme radial forces



Unit : Inch

OD	SD	LOC	OAL	Square End	Corner Radius						
					.010	.030	.060	.090	.120	.190	.250
D1	D2	L1	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
5/8	5/8	3/4	3	E5G95040	E5G97040	E5G97994	E5G97995	E5G97996	E5G97997	E5G97998	-
		1-5/8	3-1/2	E5G95917	E5G97999	E5G97801	E5G97802	E5G97803	E5G97804	E5G97805	-
		2-1/2	5	E5G95918	E5G97806	E5G97807	E5G97808	E5G97809	E5G97810	E5G97811	-
3/4	3/4	3	5-1/4	E5G95919	E5G97812	E5G97813	E5G97814	E5G97815	E5G97816	E5G97817	-
		1	3	E5G95048	E5G97048	E5G97818	E5G97819	E5G97820	E5G97821	E5G97822	E5G97823
3/4	3/4	1-5/8	4	E5G95920	E5G97824	E5G97825	E5G97826	E5G97827	E5G97828	E5G97829	E5G97830
		2-1/4	5	E5G95921	E5G97831	E5G97832	E5G97833	E5G97834	E5G97835	E5G97836	E5G97837
1	1	3-1/4	6	E5G95922	E5G97838	E5G97839	E5G97840	E5G97841	E5G97842	E5G97843	E5G97844
		4	6-1/4	E5G95923	E5G97845	E5G97846	E5G97847	E5G97848	E5G97849	E5G97850	E5G97851
1	1	1-1/4	3	E5G95064	E5G97064	E5G97852	E5G97853	E5G97854	E5G97855	E5G97856	E5G97857
		1-1/4	4	E5G95928	E5G97885	E5G97886	E5G97887	E5G97888	E5G97889	E5G97890	E5G97891
1	1	2	5	E5G95924	E5G97858	E5G97859	E5G97860	E5G97861	E5G97862	E5G97863	E5G97864
		3-1/4	6	E5G95925	E5G97865	E5G97866	E5G97867	E5G97868	E5G97869	E5G97870	E5G97871
1	1	4	7	E5G95926	E5G97872	E5G97873	E5G97874	E5G97875	E5G97876	E5G97877	E5G97878

Outside Diameter Tolerances (inch)		Shank Diameter Tolerance
Diameter	Tolerance	
1/8 - 3/16	+0/-0.0032	h6
1/4 - 3/8	+0/-0.0035	
1/2 - 5/8	+0/-0.0043	
3/4 - 1	+0/-0.0051	

◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
												◎	

YG ALU-POWER HPC END MILLS

JAG96 SERIES SQUARE
JAG98 SERIES CORNER RADIUS

CARBIDE, 3 FLUTE EXTENDED LENGTH - DLC COATED

- ▶ Longer tool life
- ▶ Balanced cutting with less vibration
- ▶ Ability to run at higher speeds with less heat in aluminum
- ▶ More efficient chip evacuation
- ▶ Ability to counteract extreme radial forces



Unit : Inch

OD	SD	LOC	LBS	Neck Dia.	OAL	Square End	Corner Radius						
							.010	.030	.060	.090	.120	.190	.250
D1	D2	L1	L3	D3	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
1/4	14	3/8	3/4	.220	2-1/2	JAG96016	JAG98016	JAG98901	JAG98902	-	-	-	-
		3/8	1-1/8	.220	3	JAG96901	JAG98903	JAG98904	JAG98905	-	-	-	-
3/8	3/8	1/2	1-1/8	.345	3	JAG96024	JAG98024	JAG98906	JAG98907	JAG98908	JAG98909	-	-
		1/2	2-1/8	.345	4	JAG96902	JAG98910	JAG98911	JAG98912	JAG98913	JAG98914	-	-
1/2	1/2	5/8	1-3/8	.470	3	JAG96032	JAG98032	JAG98915	JAG98916	JAG98917	JAG98918	JAG98919	-
		5/8	2-1/4	.470	4	JAG96903	JAG98920	JAG98921	JAG98922	JAG98923	JAG98924	JAG98925	-
		5/8	3-3/8	.470	5	JAG96904	JAG98926	JAG98927	JAG98928	JAG98929	JAG98930	JAG98931	-
		5/8	4-1/4	.470	6	JAG96905	JAG98932	JAG98933	JAG98934	JAG98935	JAG98936	JAG98937	-
5/8	5/8	3/4	1-5/8	.585	4	JAG96040	JAG98040	JAG98938	JAG98939	JAG98940	JAG98941	JAG98942	-
		3/4	3-3/8	.585	6	JAG96906	JAG98943	JAG98944	JAG98945	JAG98946	JAG98947	JAG98948	-
3/4	3/4	1	2	.710	4	JAG96048	JAG98048	JAG98949	JAG98950	JAG98951	JAG98952	JAG98953	JAG98954
		1	3-3/8	.710	6	JAG96907	JAG98955	JAG98956	JAG98957	JAG98958	JAG98959	JAG98960	JAG98961
1	1	1-1/4	2-5/8	.960	5	JAG96064	JAG98064	JAG98969	JAG98970	JAG98971	JAG98972	JAG98973	JAG98974
		1-1/4	3-3/8	.960	6	JAG96909	JAG98975	JAG98976	JAG98977	JAG98978	JAG98979	JAG98980	JAG98981
1	1	1-1/4	4-3/8	.960	7	JAG96910	JAG98982	JAG98983	JAG98984	JAG98985	JAG98986	JAG98987	JAG98988
		1-1/4	6	.960	9	JAG96911	JAG98989	JAG98990	JAG98991	JAG98992	JAG98993	JAG98994	JAG98995

Outside Diameter Tolerances (inch)		Shank Diameter Tolerance
Diameter	Tolerance	h6
1/8 - 3/16	+0/-0.00032	
1/4 - 3/8	+0/-0.00035	
1/2 - 5/8	+0/-0.00043	
3/4 - 1	+0/-0.00051	

◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
												◎	

YG ALU-POWER HPC END MILLS

E5G96 SERIES SQUARE
E5G98 SERIES CORNER RADIUS

CARBIDE, 3 FLUTE EXTENDED LENGTH

- ▶ Longer tool life
- ▶ Balanced cutting with less vibration
- ▶ Ability to run at higher speeds with less heat in aluminum
- ▶ More efficient chip evacuation
- ▶ Ability to counteract extreme radial forces



Unit : Inch

OD	SD	LOC	LBS	Neck Dia.	OAL	Square End	Corner Radius						
							.010	.030	.060	.090	.120	.190	.250
D1	D2	L1	L3	D3	L2	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.	EDP No.
1/4	14	3/8	3/4	.220	2-1/2	E5G96016	E5G98016	E5G98901	E5G98902	-	-	-	-
		3/8	1-1/8	.220	3	E5G96901	E5G98903	E5G98904	E5G98905	-	-	-	-
3/8	3/8	1/2	1-1/8	.345	3	E5G96024	E5G98024	E5G98906	E5G98907	E5G98908	E5G98909	-	-
		1/2	2-1/8	.345	4	E5G96902	E5G98910	E5G98911	E5G98912	E5G98913	E5G98914	-	-
1/2	1/2	5/8	1-3/8	.470	3	E5G96032	E5G98032	E5G98915	E5G98916	E5G98917	E5G98918	E5G98919	-
		5/8	2-1/4	.470	4	E5G96903	E5G98920	E5G98921	E5G98922	E5G98923	E5G98924	E5G98925	-
		5/8	3-3/8	.470	5	E5G96904	E5G98926	E5G98927	E5G98928	E5G98929	E5G98930	E5G98931	-
		5/8	4-1/4	.470	6	E5G96905	E5G98932	E5G98933	E5G98934	E5G98935	E5G98936	E5G98937	-
5/8	5/8	3/4	1-5/8	.585	4	E5G96040	E5G98040	E5G98938	E5G98939	E5G98940	E5G98941	E5G98942	-
		3/4	3-3/8	.585	6	E5G96906	E5G98943	E5G98944	E5G98945	E5G98946	E5G98947	E5G98948	-
3/4	3/4	1	2	.710	4	E5G96048	E5G98048	E5G98949	E5G98950	E5G98951	E5G98952	E5G98953	E5G98954
		1	3-3/8	.710	6	E5G96907	E5G98955	E5G98956	E5G98957	E5G98958	E5G98959	E5G98960	E5G98961
1	1	1-1/4	2-5/8	.960	5	E5G96064	E5G98064	E5G98969	E5G98970	E5G98971	E5G98972	E5G98973	E5G98974
		1-1/4	3-3/8	.960	6	E5G96909	E5G98975	E5G98976	E5G98977	E5G98978	E5G98979	E5G98980	E5G98981
1	1	1-1/4	4-3/8	.960	7	E5G96910	E5G98982	E5G98983	E5G98984	E5G98985	E5G98986	E5G98987	E5G98988
		1-1/4	6	.960	9	E5G96911	E5G98989	E5G98990	E5G98991	E5G98992	E5G98993	E5G98994	E5G98995

Outside Diameter Tolerances (inch)		Shank Diameter Tolerance
Diameter	Tolerance	h6
1/8 - 3/16	+0/-0.00032	
1/4 - 3/8	+0/-0.00035	
1/2 - 5/8	+0/-0.00043	
3/4 - 1	+0/-0.00051	

◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
												◎	

CARBIDE, 3 FLUTE STANDARD LENGTH – INCH


JAG95, JAG96, JAG97, JAG98, E5G95, E5G96, E5G97, E5G98 SERIES

Speed and Feed Recommendations							Diameter (D)							
ISO Hardness (BHN)	Coolant	Cutting Method	Ap x D	Ae x D	Vc (SFM)	Parameters	1/8	1/4	3/8	1/2	5/8	3/4	1	
N < 16% Silicon Aluminum Alloys: 2024, 5052, 5086, 6061,6063,7075	Emulsion	Slotting 	1	1	2000	RPM	61100	30500	20400	15300	12200	10200	7600	
					1300~10000	Fz	.0010	.0030	.0045	.0060	.0066	.0075	.0100	
						Feed (IPM)	183	275	275	275	242	230	228	
		Profiling 	1.5	0.5	3000	RPM	91700	45800	30600	23000	18300	15300	11500	
					1600~10000	Fz	.0010	.0030	.0045	.0060	.0066	.0075	.0100	
						Feed (IPM)	275	412	413	414	362	344	345	
		HSM 	2	0.05	8000	RPM	244500	122200	81500	61100	48900	40700	30600	
					1600~10000	Fz	.0021	.0055	.0105	.0140	.0150	.0165	.0195	
						Feed (IPM)	1540	2016	2567	2566	2201	2015	1790	
N > 16% Silicon Aluminum Die Cast Alloys: A-390, A392, B-390 [YG-1 recommends the use of coated tools only]	Emulsion	Slotting 	1	1	600	RPM	18336	9168	6112	4584	3667	3056	2292	
					(480-720)	Fz	.0010	.0030	.0045	.0060	.0066	.0075	.0100	
						Feed (IPM)	55	83	83	83	73	69	69	
		Profiling 	1.5	0.5	800	RPM	24448	12224	8149	6112	4890	4075	3056	
					(640-960)	Fz	.0010	.0030	.0045	.0060	.0066	.0075	.0100	
						Feed (IPM)	73	110	110	110	97	92	92	
		HSM 	2	0.05	1200	RPM	36672	18336	12224	9168	7334	6112	4584	
					(960-1440)	Fz	.0021	.0055	.0105	.0140	.0150	.0165	.0195	
						Feed (IPM)	231	303	385	385	330	303	268	
N Non-Ferrous Alloys: Copper Alloys, Aluminum Bronze, Brass, Naval Brass, Red Brass	Emulsion	Slotting 	1	1	880	RPM	26893	13446	8964	6723	5379	4482	3362	
					(704-1056)	Fz	.0008	.0020	.0040	.0050	.0055	.0060	.0070	
						Feed (IPM)	65	81	108	101	89	81	71	
		Profiling 	1.5	0.5	1150	RPM	35144	17572	11715	8786	7029	5857	4393	
					(920-1380)	Fz	.0008	.0020	.0040	.0050	.0055	.0060	.0070	
						Feed (IPM)	84	105	141	132	116	105	92	
		HSM 	2	0.05	1850	RPM	56536	28268	18845	14134	11307	9423	7067	
					(1480-2220)	Fz	.0017	.0045	.0085	.0115	.0130	.0140	.0160	
						Feed (IPM)	288	382	481	488	441	396	339	

Profiling/HSM









Slotting




- NOTES:**
- ▶ All cutting data are target values
 - ▶ Maximum recommended depth shown
 - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D or less
 - ▶ Reduce speed and feed recommendations for materials harder than listed
 - ▶ Reduce cut depth and feed by 50% for long-flute or long-reach tools
 - ▶ Above recommendations are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions
 - ▶ HSM = high-speed machining

CARBIDE, 3 FLUTE STANDARD LENGTH – INCH


JAG95, JAG96, JAG97, JAG98, E5G95, E5G96, E5G97, E5G98 SERIES

Speed and Feed Recommendations							Diameter (D)							
ISO Hardness (BHN)	Coolant	Cutting Method	Ap x D	Ae x D	Vc (SFM)	Parameters	1/8	1/4	3/8	1/2	5/8	3/4	1	
N Non-Ferrous Alloys: Copper Alloys, Beryllium Copper, C110, Manganese Bronze, Tin Bronze	Emulsion	Slotting 	1	1	300	RPM	9168	4584	3056	2292	1834	1528	1146	
					(240-360)	Fz	.0008	.0020	.0040	.0050	.0055	.0060	.0070	
						Feed (IPM)	22	28	37	34	30	28	24	
		Profiling 	1.5	0.5	450	RPM	13752	6876	4584	3438	2750	2292	1719	
					(360-540)	Fz	.0008	.0020	.0040	.0050	.0055	.0060	.0070	
						Feed (IPM)	33	41	55	52	45	41	36	
		HSM 	2	0.05	750	RPM	22920	11460	7640	5730	4584	3820	2865	
					(600-900)	Fz	.0017	.0045	.0085	.0115	.0130	.0140	.0160	
						Feed (IPM)	117	155	195	198	179	160	138	
Plastics: ABS, Polycarbonate, PVC, Polycarbonate	Air	Slotting 	1	1	1670	RPM	51035	25518	17012	12759	10207	8506	6379	
					(1336-2004)	Fz	.0015	.0040	.0075	.0100	.0110	.0120	.0140	
						Feed (IPM)	230	306	383	383	337	306	268	
		Profiling 	1.5	0.5	2070	RPM	63259	31630	21086	15815	12652	10543	7907	
					(1656-2484)	Fz	.0015	.0040	.0075	.0100	.0110	.0120	.0140	
						Feed (IPM)	285	380	474	474	418	380	332	
		HSM 	2	0.05	3350	RPM	102376	51188	34125	25594	20475	17063	12797	
					(2680-4020)	Fz	.0034	.0090	.0170	.0230	.0250	.0275	.0320	
						Feed (IPM)	1044	1382	1740	1766	1536	1408	1229	

Profiling/HSM



Slotting



- NOTES:**
- ▶ All cutting data are target values
 - ▶ Maximum recommended depth shown
 - ▶ Finish cuts typically require reduced feed rates and/or higher spindle speed, with radial width of 2% x D or less
 - ▶ Reduce speed and feed recommendations for materials harder than listed
 - ▶ Reduce cut depth and feed by 50% for long-flute or long-reach tools
 - ▶ Above recommendations are based on ideal conditions. Adjust parameters accordingly for smaller taper machining centers or less rigid conditions
 - ▶ HSM = high-speed machining



Being the best through innovation

CARBIDE & HSS




ALU-POWER END MILLS

- Silent Cutting of Aluminium Alloys, Mirror Surface



Global Cutting Tool Leader **YG-1**








SELECTION GUIDE

SOLID CARBIDE & HSS ALU-POWER END MILLS

◎ : Excellent ○ : Good

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	

METRIC - CARBIDE



E5522 EG522		CARBIDE, 2 FLUTE 45° HELIX LONG LENGTH TiCN COATED	◇	D3.0	D20.0	1066
EG930		CARBIDE, 2 FLUTE 25° HELIX STUB CUT LENGTH CORNER RADIUS TiCN COATED	◇	D2.0	D20.0	1067
EG909		CARBIDE, 2 FLUTE STUB CUT LENGTH CORNER RADIUS with NECK TiCN COATED	◇	D4.0	D20.0	1068
EG910		CARBIDE 2 FLUTE 50° HELIX STUB CUT LENGTH BALL NOSE with NECK TiCN COATED	◇	R3.0	R10.0	1069
EG908		CARBIDE, 3 FLUTE 40° HELIX LONG LENGTH BALL NOSE with NECK TiCN COATED	◇	R1.0	R8.0	1070

◇ Call for Availability

INCH / SPEED FREEK - HSS POWDERED METAL

EK191		T15, 3 FLUTE 42° HELIX REGULAR LENGTH ROUGHING for ALUMINUM	◆	D1/2	D2	1071
EK191		T15, 3 FLUTE 42° HELIX REGULAR LENGTH ROUGHING with CORNER RADIUS for ALUMINUM	◆	D3/4	D1-1/4	1071
EK226		T15, 3 FLUTE 42° HELIX MEDIUM LENGTH ROUGHING for ALUMINUM	◆	D3/4	D2	1072
EK226		T15, 3 FLUTE 42° HELIX MEDIUM LENGTH ROUGHING with CORNER RADIUS for ALUMINUM	◆	D3/4	D1-1/4	1072
EK192		T15, 3 FLUTE 42° HELIX LONG LENGTH ROUGHING for ALUMINUM	◆	D1/2	D2	1073
EK192		T15, 3 FLUTE 42° HELIX LONG LENGTH ROUGHING with CORNER RADIUS for ALUMINUM	◆	D3/4	D1-1/4	1074
EK196		3 FLUTE BALL NOSE 42° HELIX ROUGHING BALL NOSE REGULAR LENGTH for ALUMINUM	◆	R1/4	R5/8	1075
EK193 EK132		3 FLUTE FINISHING with & without CORNER RADIUS REGULAR & MEDIUM & LONG LENGTH	◆	D1/2	D1-1/2	1076

◆ U.S.A Stock

EP922		PREMIUM HSS-PM, 3 FLUTE, 42° HELIX SHORT LENGTH ROUGHING for ALUMINUM	◇	D12.0	D32.0	1078
EP924		PREMIUM HSS-PM, 3 FLUTE 42° HELIX LONG LENGTH ROUGHING for ALUMINUM	◇	D12.0	D32.0	1079
		RECOMMENDED CUTTING CONDITIONS				1080

◇ Call for Availability

P					H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									

													◎				
													◎				
													◎				
													◎				
													◎				

													◎				
													◎				
													◎				
													◎				
													◎				
													◎				
													◎				

													◎				
													◎				



E5253 SERIES FLAT SHANK

CARBIDE, 2 FLUTE 42° HELIX REGULAR LENGTH - "BANSHEE"

- ▶ High velocity milling of aluminum & other non ferrous materials.
- ▶ Excellent plunging capabilities.
- ▶ Improved surface roughness-cylindrical margin which is controlled tightly.
- ▶ Maximum-metal removal rate.
- ▶ Superior chip evacuation.
- ▶ Mirror face-excellent surface finish.



◆ U.S.A Stock


Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E				
17574	17574TN	17574TC	17574TF	17574TE	1/4	3/8	3/4	2-1/2
17580	17580TN	17580TC	17580TF	17580TE	5/16	3/8	13/16	2-1/2
17584	17584TN	17584TC	17584TF	17584TE	3/8	3/8	1	2-1/2
17593	17593TN	17593TC	17593TF	17593TE	1/2	1/2	1	3
18593	18593TN	18593TC	18593TF	18593TE	1/2	1/2	2	4
17901	17901TN	17901TC	17901TF	17901TE	1/2	1/2	1-1/4	3-1/4
17595	17595TN	17595TC	17595TF	17595TE	5/8	5/8	1-1/4	3-1/2
17598	17598TN	17598TC	17598TF	17598TE	3/4	3/4	1-1/2	4
18598	18598TN	18598TC	18598TF	18598TE	3/4	3/4	3	5-1/2
17600	17600TN	17600TC	17600TF	17600TE	1	1	1-1/2	4
18600	18600TN	18600TC	18600TF	18600TE	1	1	3	5-1/2

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.012	0~-0.003



- High performance in machining aluminum and non-ferrous materials
- Special designed geometry with high rigidity cutting edge
- Improved surface roughness - cylindrical margin which is controlled tightly.
- Excellent chip removal - higher rake angle, higher helix angle(42°), bigger chip pocket.



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
													◎	



E5254 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE 42° HELIX REGULAR LENGTH - "BANSHEE"

- ▶ High velocity milling of aluminum & other non ferrous materials.
- ▶ Excellent plunging capabilities.
- ▶ Improved surface roughness-cylindrical margin which is controlled tightly.
- ▶ Maximum-metal removal rate.
- ▶ Superior chip evacuation.
- ▶ Mirror face-excellent surface finish.



◆ U.S.A Stock


Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E				
21554	21554TN	21554TC	21554TF	21554TE	1/16	1/8	1/8	1-1/2
21556	21556TN	21556TC	21556TF	21556TE	3/32	1/8	1/4	1-1/2
21601	21601TN	21601TC	21601TF	21601TE	1/8	1/4	5/16	1-3/4
21566	21566TN	21566TC	21566TF	21566TE	3/16	1/4	7/16	2
21574	21574TN	21574TC	21574TF	21574TE	1/4	3/8	3/4	2-1/2
21580	21580TN	21580TC	21580TF	21580TE	5/16	3/8	13/16	2-1/2
21584	21584TN	21584TC	21584TF	21584TE	3/8	3/8	1	2-1/2
21588	21588TN	21588TC	21588TF	21588TE	7/16	7/16	1	2-3/4
21593	21593TN	21593TC	21593TF	21593TE	1/2	1/2	1	3
21904	21904TN	21904TC	21904TF	21904TE	1/2	1/2	1-1/4	3
21901	21901TN	21901TC	21901TF	21901TE	1/2	1/2	2	4
21595	21595TN	21595TC	21595TF	21595TE	5/8	5/8	1-1/4	3-1/2
21598	21598TN	21598TC	21598TF	21598TE	3/4	3/4	1-1/2	4
21902	21902TN	21902TC	21902TF	21902TE	3/4	3/4	3	5-1/2
21600	21600TN	21600TC	21600TF	21600TE	1	1	1-1/2	4
21903	21903TN	21903TC	21903TF	21903TE	1	1	3	5-1/2

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.012	0~-0.003



- High performance in machining aluminum and non-ferrous materials
- Special designed geometry with high rigidity cutting edge
- Improved surface roughness - cylindrical margin which is controlled tightly.
- Excellent chip removal - higher rake angle, higher helix angle(42°), bigger chip pocket.



◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
													◎	



E5976 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE 37° HELIX with EXTENDED NECK

- ▶ High velocity milling of aluminum & other non-ferrous materials.
- ▶ Excellent plunging capabilities.
- ▶ Improved surface roughness-cylindrical margin which is controlled tightly.
- ▶ Maximum-metal removal rate.
- ▶ Superior chip evacuation.
- ▶ Mirror face-excellent surface finish.




◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
UNCOATED	TiCN COATED	D1	D2	L1	L3	L2	D3
39573	39573TC	1/4	1/4	3/8	2-1/4	4	.220
39584	39584TC	3/8	3/8	1/2	2-1/4	4	.345
39593	39593TC	1/2	1/2	5/8	2-1/4	5	.470
39908	39908TC	1/2	1/2	5/8	3-1/4	6	.470
39901	39901TC	1/2	1/2	5/8	4	6	.470
39595	39595TC	5/8	5/8	3/4	2-1/4	5	.585
39902	39902TC	5/8	5/8	3/4	3-1/4	6	.585
39903	39903TC	5/8	5/8	3/4	4-1/4	7	.585
39598	39598TC	3/4	3/4	1	2-1/4	5	.710
39904	39904TC	3/4	3/4	1	3-1/4	6	.710
39905	39905TC	3/4	3/4	1	4-1/4	7	.710
39600	39600TC	1	1	1-1/8	2-1/4	5	.960
39906	39906TC	1	1	1-1/8	3-1/4	6	.960
39907	39907TC	1	1	1-1/8	4-1/4	7	.960

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0005	0~-.0003



◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
													◎	



E5980 SERIES PLAIN SHANK

CARBIDE, 3 FLUTE 45° HELIX STUB LENGTH

- ▶ Designed to machine aluminium at high speed condition.
- ▶ Improved surface roughness-cylindrical margin which is controlled tightly.
- ▶ Mirror face-excellent surface finish.



◆ U.S.A Stock


Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TiCN COATED				
25558	25558TC	1/8	1/8	1/4	1-1/2
25565	25565TC	3/16	3/16	5/16	2
25573	25573TC	1/4	1/4	3/8	2
25579	25579TC	5/16	5/16	7/16	2
25584	25584TC	3/8	3/8	1/2	2
25588	25588TC	7/16	7/16	9/16	2-1/2
25593	25593TC	1/2	1/2	5/8	2-1/2
25595	25595TC	5/8	5/8	3/4	3
25598	25598TC	3/4	3/4	1	3
25600	25600TC	1	1	1-1/4	3

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0005	0~-.0003



- High performance in machining aluminum and non-ferrous materials
- Special designed geometry with high rigidity cutting edge
- Improved surface roughness - cylindrical margin which is controlled tightly.
- Excellent chip removal - higher rake angle, higher helix angle(45°), bigger chip pocket.



◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
													◎	



E5981 SERIES PLAIN SHANK
E5983 SERIES PLAIN SHANK

CARBIDE, 3 FLUTE 45° HELIX REGULAR LENGTH & CORNER RADIUS

- ▶ High velocity milling of aluminum & other non-ferrous materials.
- ▶ 3flute and 45° helix allow harmonic balance at high speed condition and smooth cutting.
- ▶ Improved surface roughness-cylindrical margin which is controlled tightly
- ▶ Maximum-metal removal rate.
- ▶ Superior chip evacuation.
- ▶ Mirror face-excellent surface finish.



◆ U.S.A Stock

■ SQUARE Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TiCN COATED				
28558	28558TC	1/8	1/8	3/8	1-1/2
28565	28565TC	3/16	3/16	9/16	2
28573	28573TC	1/4	1/4	5/8	2-1/2
28579	28579TC	5/16	5/16	5/8	2-1/2
28584	28584TC	3/8	3/8	1	2-1/2
28588	28588TC	7/16	7/16	1-1/4	2-3/4
28593	28593TC	1/2	1/2	1-1/4	3
28595	28595TC	5/8	5/8	1-5/8	3-1/2
28598	28598TC	3/4	3/4	1-5/8	4
28600	28600TC	1	1	2	5

■ CORNER RADIUS Unit : Inch

EDP No.		Corner Radius R	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TiCN COATED					
EA50321	EA50321C	R.060	1/2	1/2	1-1/4	3
EA50401	EA50401C	R.060	5/8	5/8	1-5/8	3-1/2
EA50481	EA50481C	R.060	3/4	3/4	1-5/8	4
EA50641	EA50641C	R.065	1	1	2	5
EA20321	EA20321C	R.120	1/2	1/2	1-1/4	3
EA20401	EA20401C	R.120	5/8	5/8	1-5/8	3-1/2
EA20481	EA20481C	R.120	3/4	3/4	1-5/8	4
EA20641	EA20641C	R.120	1	1	2	5

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.005	0~-0.003

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
													◎	



E5982 SERIES PLAIN SHANK
E5984 SERIES PLAIN SHANK

CARBIDE, 3 FLUTE 45° HELIX LONG LENGTH & CORNER RADIUS

- ▶ High velocity milling of aluminum & other non-ferrous materials.
- ▶ 3flute and 45° helix allow harmonic balance at high speed condition and smooth cutting.
- ▶ Improved surface roughness-cylindrical margin which is controlled tightly
- ▶ Maximum-metal removal rate.
- ▶ Superior chip evacuation.
- ▶ Mirror face-excellent surface finish.



◆ U.S.A Stock

■ SQUARE Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TiCN COATED				
36573	36573TC	1/4	1/4	1-1/4	3-1/4
36579	36579TC	5/16	5/16	1-1/4	3-1/2
36584	36584TC	3/8	3/8	1-1/2	3-1/2
36588	36588TC	7/16	7/16	2	4
36593	36593TC	1/2	1/2	2	4
36595	36595TC	5/8	5/8	2-1/2	5
36598	36598TC	3/4	3/4	3-1/4	6
36600	36600TC	1	1	3-1/4	6

■ CORNER RADIUS Unit : Inch

EDP No.		Corner Radius R	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TiCN COATED					
EA60321	EA60321C	R.060	1/2	1/2	2	4
EA60401	EA60401C	R.060	5/8	5/8	2-1/2	5
EA60481	EA60481C	R.060	3/4	3/4	3-1/4	6
EA60641	EA60641C	R.060	1	1	3-1/4	6
EA30321	EA30321C	R.120	1/2	1/2	2	4
EA30401	EA30401C	R.120	5/8	5/8	2-1/2	5
EA30481	EA30481C	R.120	3/4	3/4	3-1/4	6
EA30641	EA30641C	R.120	1	1	3-1/4	6

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.005	0~-0.003

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
													◎	



E5E44 SERIES PLAIN SHANK
E5E98 SERIES PLAIN SHANK

CARBIDE, 3 FLUTE ROUGHING / ROUGHING with NECK

- ▶ Excellent cutting qualities on aluminum, copper
- ▶ Increased tool life and superior chip evacuation
- ▶ Reduces chipping of corner edges



* WITH NECK



◆ U.S.A Stock

ROUGHING

Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
44016	1/4	1/4	3/4	2-1/2
44024	3/8	3/8	7/8	2-1/2
44032	1/2	1/2	1	3
44040	5/8	5/8	1-1/4	3-1/2
44048	3/4	3/4	1-5/8	4
44064	1	1	1-3/4	4

ROUGHING WITH NECK

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
98016	1/4	1/4	3/4	1	2-1/2	.210
98024	3/8	3/8	7/8	1-1/4	3	.335
98032	1/2	1/2	1	1-3/8	3-1/4	.440
98040	5/8	5/8	1-1/4	1-3/4	3-3/4	.565
98048	3/4	3/4	1-5/8	2-1/4	4-1/2	.690
98064	1	1	1-3/4	2-1/2	5	.940

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0005	0~-.0003

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
													◎	



E5E45 SERIES PLAIN SHANK

CARBIDE, 3 FLUTE ROUGHING BALL NOSE

- ▶ Excellent cutting qualities on aluminum, copper
- ▶ Increased tool life and superior chip evacuation
- ▶ Reduces chipping of corner edges



◆ U.S.A Stock

ROUGHING

Unit : Inch

SAB CODE	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of FLUTE
45016	1/4	1/4	3/4	2-1/2	3
45024	3/8	3/8	7/8	2-1/2	3
45032	1/2	1/2	1	3	3
45040	5/8	5/8	1-1/4	3-1/2	3
45048	3/4	3/4	1-5/8	4	3
45064	1	1	1-3/4	4	3

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0005	0~-.0003

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
													◎	



E5977 SERIES PLAIN SHANK

CARBIDE, 3 FLUTE 37° HELIX with EXTENDED NECK

- ▶ High velocity milling of aluminum & other non-ferrous materials.
- ▶ 3flute and 37° helix allow harmonic balance at high speed condition and smooth cutting.
- ▶ Improved surface roughness-cylindrical margin which is controlled tightly.
- ▶ Maximum-metal removal rate.
- ▶ Superior chip evacuation.
- ▶ Mirror face-excellent surface finish.




◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
UNCOATED	TiCN COATED	D1	D2	L1	L3	L2	D3
40573	40573TC	1/4	1/4	3/8	2-1/4	4	.220
40584	40584TC	3/8	3/8	1/2	2-1/4	4	.345
40593	40593TC	1/2	1/2	5/8	2-1/4	5	.470
40901	40901TC	1/2	1/2	5/8	3-1/4	6	.470
40902	40902TC	1/2	1/2	5/8	4	6	.470
40595	40595TC	5/8	5/8	3/4	2-1/4	5	.585
40903	40903TC	5/8	5/8	3/4	3-1/4	6	.585
40904	40904TC	5/8	5/8	3/4	4-1/4	7	.585
40598	40598TC	3/4	3/4	1	2-1/4	5	.710
40905	40905TC	3/4	3/4	1	3-1/4	6	.710
40906	40906TC	3/4	3/4	1	4-1/4	7	.710
40600	40600TC	1	1	1-1/8	2-1/4	5	.960
40907	40907TC	1	1	1-1/8	3-1/4	6	.960
40908	40908TC	1	1	1-1/8	4-1/4	7	.960

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0005	0~-.0003



STEP MILLING

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70								◎	



E5985 SERIES PLAIN SHANK

CARBIDE, 3 FLUTE 37° HELIX with EXTENDED NECK CORNER RADIUS

- ▶ High velocity milling of aluminum & other non-ferrous materials.
- ▶ 3flute and 37° helix allow harmonic balance at high speed condition and smooth cutting.
- ▶ Improved surface roughness-cylindrical margin which is controlled tightly.
- ▶ Maximum-metal removal rate.
- ▶ Superior chip evacuation.
- ▶ Mirror face-excellent surface finish.




◆ U.S.A Stock

Unit : Inch

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
UNCOATED	TiCN COATED	R	D1	D2	L1	L3	L2	D3
EA40321	EA40321C	R.060	1/2	1/2	5/8	3-1/4	6	.470
EA40322	EA40322C	R.060	1/2	1/2	5/8	4	6	.470
EA40401	EA40401C	R.060	5/8	5/8	3/4	2-1/4	5	.585
EA40402	EA40402C	R.060	5/8	5/8	3/4	3-1/4	6	.585
EA40403	EA40403C	R.060	5/8	5/8	3/4	4-1/4	7	.585
EA40481	EA40481C	R.060	3/4	3/4	1	2-1/4	5	.710
EA40482	EA40482C	R.060	3/4	3/4	1	3-1/4	6	.710
EA40483	EA40483C	R.060	3/4	3/4	1	4-1/4	7	.710
EA40641	EA40641C	R.060	1	1	1-1/8	2-1/4	5	.960
EA40642	EA40642C	R.060	1	1	1-1/8	3-1/4	6	.960
EA40643	EA40643C	R.060	1	1	1-1/8	4-1/4	7	.960
EA10321	EA10321C	R.120	1/2	1/2	5/8	3-1/4	6	.470
EA10322	EA10322C	R.120	1/2	1/2	5/8	4	6	.470
EA10401	EA10401C	R.120	5/8	5/8	3/4	2-1/4	5	.585
EA10402	EA10402C	R.120	5/8	5/8	3/4	3-1/4	6	.585
EA10403	EA10403C	R.120	5/8	5/8	3/4	4-1/4	7	.585
EA10481	EA10481C	R.120	3/4	3/4	1	2-1/4	5	.710
EA10482	EA10482C	R.120	3/4	3/4	1	3-1/4	6	.710
EA10483	EA10483C	R.120	3/4	3/4	1	4-1/4	7	.710
EA10641	EA10641C	R.120	1	1	1-1/8	2-1/4	5	.960
EA10642	EA10642C	R.120	1	1	1-1/8	3-1/4	6	.960
EA10643	EA10643C	R.120	1	1	1-1/8	4-1/4	7	.960

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0005	0~-.0003





STEP MILLING

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70								◎	

CARBIDE, 2 FLUTE CORNER RADIUS with NECK

- ▶ Excellent cutting qualities on stainless steel, aluminum, copper.
- ▶ Increased tool life and higher cutting accuracy.
- ▶ Mirror face-excellent surface finish.




◆ U.S.A Stock

Unit : Inch

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
UNCOATED	TICN COATED	R	D1	D2	L1	L3	L2	D3
24562	24562TC	R.012	5/32	1/4	3/16	3/8	2	.140
24573	24573TC	R.020	1/4	1/4	5/16	3/4	2-3/8	.226
24579	24579TC	R.024	5/16	5/16	3/8	1-1/8	2-3/4	.282
24584	24584TC	R.031	3/8	3/8	1/2	1-1/2	3-1/8	.336
24593	24593TC	R.040	1/2	1/2	9/16	1-1/2	3-1/2	.460
24595	24595TC	R.051	5/8	5/8	3/4	1-3/4	4	.566
24598	24598TC	R.063	3/4	3/4	1	1-3/4	4	.670

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	0~-.0003





STEP MILLING

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
												◎	

CARBIDE, 2 FLUTE 50° HELIX STUB CUT LENGTH BALL NOSE with NECK

- ▶ Excellent cutting qualities on stainless steel, aluminum, copper.
- ▶ Increased tool life and higher cutting accuracy.
- ▶ Mirror face-excellent surface finish.




◆ U.S.A Stock

Unit : Inch

EDP No.		Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
UNCOATED	TICN COATED	R (±.0005)	D1	D2	L1	L3	L2	D3
37573	37573TC	R 1/8	1/4	1/4	7/32	1	2-1/4	.226
37579	37579TC	R 5/32	5/16	5/16	9/32	1-1/8	2-1/2	.280
37584	37584TC	R 3/16	3/8	3/8	11/32	1-3/8	3	.335
37593	37593TC	R 1/4	1/2	1/2	13/32	1-1/2	3	.460
37595	37595TC	R 5/16	5/8	5/8	9/16	2	3-1/2	.566
37598	37598TC	R 3/8	3/4	3/4	11/16	2	4	.671

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0010	0~-.0003



◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
												◎	

YG ALU-POWER END MILLS

E5978 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE 37° HELIX LONG REACH BALL NOSE

- ▶ High velocity milling of aluminum & other non-ferrous materials.
- ▶ Extended neck design which is suitable for step milling.
- ▶ Improved surface roughness-cylindrical margin which is controlled tightly
- ▶ Maximum-metal removal rate.
- ▶ Superior chip evacuation.
- ▶ Mirror face-excellent surface finish.




MG 2 37° ±.001 PLAIN P.1084

◆ U.S.A Stock

Unit : Inch

EDP No.		Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
UNCOATED	TICN COATED	R (±.001)	D1	D2	L1	L3	L2	D3
89573	89573TC	R 1/8	1/4	1/4	3/8	2-1/4	4	.220
89584	89584TC	R 3/16	3/8	3/8	1/2	2-1/4	4	.345
89593	89593TC	R 1/4	1/2	1/2	5/8	2-1/4	5	.470
89901	89901TC	R 1/4	1/2	1/2	5/8	3-1/4	6	.470
89902	89902TC	R 1/4	1/2	1/2	5/8	4	6	.470
89595	89595TC	R 5/16	5/8	5/8	3/4	2-1/4	5	.585
89903	89903TC	R 5/16	5/8	5/8	3/4	3-1/4	6	.585
89904	89904TC	R 5/16	5/8	5/8	3/4	4-1/4	7	.585
89598	89598TC	R 3/8	3/4	3/4	1	2-1/4	5	.710
89905	89905TC	R 3/8	3/4	3/4	1	3-1/4	6	.710
89906	89906TC	R 3/8	3/4	3/4	1	4-1/4	7	.710
89600	89600TC	R1/2	1	1	1-1/8	2-1/4	5	.960
89907	89907TC	R1/2	1	1	1-1/8	3-1/4	6	.960
89908	89908TC	R1/2	1	1	1-1/8	4-1/4	7	.960

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	0~-.0003



◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
												◎	

YG ALU-POWER END MILLS

E5975 SERIES PLAIN SHANK

CARBIDE, 3 FLUTE 40° HELIX LONG LENGTH BALL NOSE with NECK

- ▶ Excellent cutting qualities on stainless steel, aluminum, copper.
- ▶ Increased tool life and higher cutting accuracy.
- ▶ Mirror face-excellent surface finish.




MG 3 40° ±.0005 PLAIN P.1085

◆ U.S.A Stock

Unit : Inch

EDP No.		Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
UNCOATED	TICN COATED	R (±.0005)	D1	D2	L1	L3	L2	D3
38602	38602TC	R 3/64	3/32	1/4	1/8	3/16	2-3/8	.090
38601	38601TC	R 1/16	1/8	1/4	3/16	1/4	2-3/8	.117
38566	38566TC	R 3/32	3/16	1/4	1/4	3/8	2-1/2	.172
38573	38573TC	R 1/8	1/4	1/4	3/8	1/2	3	.235
38579	38579TC	R 5/32	5/16	5/16	1/2	1	3	.289
38584	38584TC	R 3/16	3/8	3/8	5/8	1-1/4	3-1/8	.351
38593	38593TC	R 1/4	1/2	1/2	3/4	1-3/8	3-1/2	.476
38595	38595TC	R 5/16	5/8	5/8	1	1-1/2	4	.601

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	0~-.0003



◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
												◎	



E5522 SERIES PLAIN SHANK
EG522 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE 45° HELIX LONG LENGTH - TiCN COATED

- Suitable for high speed machining in aluminum and other non-ferrous materials, excellent surface finishes, superior chip removal.
- Mirror face-excellent surface finish.




◇ Call for Availability


Unit : mm

EDP No.		Mill Diameter		Shank Diameter	Length of Cut	Overall Length
UNCOATED	TiCN COATED	Metric	Inch			
E5522030	EG522030	3.0	.1181	6	8	57
E5522040	EG522040	4.0	.1575	6	11	57
E5522050	EG522050	5.0	.1969	6	13	57
E5522060	EG522060	6.0	.2362	6	13	57
E5522080	EG522080	8.0	.3150	8	19	63
E5522100	EG522100	10.0	.3937	10	22	72
E5522120	EG522120	12.0	.4724	12	26	83
E5522140	EG522140	14.0	.5512	14	26	83
E5522160	EG522160	16.0	.6299	16	32	92
E5522180	EG522180	18.0	.7087	18	32	92
E5522200	EG522200	20.0	.7874	20	38	104

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6



- High performance in machining aluminum and non-ferrous materials
- Special designed geometry with high rigidity cutting edge
- Improved surface roughness - cylindrical margin which is controlled tightly.
- Excellent chip removal - higher rake angle, higher helix angle(45°), bigger chip pocket.



◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70								◎	



EG930 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE 25° HELIX STUB CUT LENGTH CORNER RADIUS TiCN COATED

- Designed for the machining aluminum and its alloys, non-ferrous materials.
- Increased tool life and higher cutting accuracy.
- Maximum-stock removal, chip ejection, stability.
- Corner Radius for avoiding the chipping.
- Mirror face-excellent surface finish.




◇ Call for Availability

Unit : mm

EDP No.	Corner Radius R (±0.025)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
EG930020	RO.2	2.0	.0787	3	3	6	40	1.9
EG930030	RO.2	3.0	.1181	3	4	8	40	2.9
EG930040	RO.2	4.0	.1575	4	5	12	50	3.8
EG930050	RO.2	5.0	.1969	5	8	14	50	4.8
EG930060	RO.2	6.0	.2362	6	8	18	65	5.7
EG930080	RO.2	8.0	.3150	8	10	22	70	7.7
EG930100	RO.2	10.0	.3937	10	14	28	80	9.7
EG930120	RO.2	12.0	.4724	12	16	35	90	11.5
EG930160	RO.2	16.0	.6299	16	20	40	90	15.5
EG930200	RO.2	20.0	.7874	20	25	50	100	19.5

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6



STEP MILLING

◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70								◎	



EG909 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE STUB CUT LENGTH CORNER RADIUS with NECK TiCN COATED

- ▶ Excellent cutting qualities on stainless steel, Aluminum, copper.
- ▶ Increased tool life and higher cutting accuracy.
- ▶ Mirror face-excellent surface finish.




MG 2 30° ±0.025 PLAIN P.1087

◇ Call for Availability

Unit : mm

EDP No.	Corner Radius R (±0.025)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
EG909040	RO.3	4.0	.1575	6	5	10	50	3.6
EG909060	RO.5	6.0	.2362	6	8	20	60	5.4
EG909080	RO.6	8.0	.3150	8	10	30	70	7.2
EG909100	RO.8	10.0	.3937	10	12	36	80	9.0
EG909120	R1.0	12.0	.4724	12	14	40	90	11.0
EG909160	R1.3	16.0	.6299	16	18	45	100	14.5
EG909200	R1.6	20.0	.7874	20	24	45	100	18.0

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6



STEP MILLING

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70								◎	



EG910 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE 50° HELIX STUB CUT LENGTH BALL NOSE with NECK TiCN COATED

- ▶ Excellent cutting qualities on stainless steel, Aluminum, copper.
- ▶ Increased tool life and higher cutting accuracy.
- ▶ Mirror face-excellent surface finish.




MG 2 50° ±0.01 PLAIN P.1087

◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.01)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
EG910060	R 3.0	6.0	.2362	6	5.5	25	55	5.4
EG910080	R 4.0	8.0	.3150	8	7	30	65	7.2
EG910100	R 5.0	10.0	.3937	10	8.5	35	75	9.0
EG910120	R 6.0	12.0	.4724	12	10.5	40	75	11.0
EG910160	R 8.0	16.0	.6299	16	14	50	90	14.5
EG910200	R 10.0	20.0	.7874	20	17	50	100	18.0

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
± 0.02	h6



STEP MILLING

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70								◎	

YG ALU-POWER END MILLS

EG908 SERIES PLAIN SHANK

CARBIDE, 3 FLUTE 40° HELIX LONG LENGTH BALL NOSE with NECK TiCN COATED

- ▶ Excellent cutting performance on stainless steels, Aluminum & copper.
- ▶ Increased tool life and higher cutting accuracy.
- ▶ Mirror face-excellent surface finish.




MG 3 40° ±0.01 PLAIN P.1088

◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.01)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
EG908020	R1.0	2.0	.0787	6	3	2.5	60	1.9
EG908025	R1.25	2.5	.0984	6	4	6	60	2.4
EG908030	R1.5	3.0	.1181	6	4.5	6.5	60	2.8
EG908035	R1.75	3.5	.1378	6	5	7	65	3.2
EG908040	R2.0	4.0	.1575	6	6	8	65	3.7
EG908050	R2.5	5.0	.1969	6	7.5	10	65	4.6
EG908060	R3.0	6.0	.2362	6	9	12	75	5.6
EG908080	R4.0	8.0	.3150	8	12	25	75	7.4
EG908100	R5.0	10.0	.3937	10	15	30	80	9.4
EG908120	R6.0	12.0	.4724	12	18	36	90	11.4
EG908160	R8.0	16.0	.6299	16	24	40	100	15.4

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
													◎	

YG ALU-POWER END MILLS

EK191 SERIES FLAT SHANK

T15, 3 FLUTE 42° HELIX REGULAR LENGTH ROUGHING for ALUMINUM

- ▶ High performance metal removal in aluminum alloys.
- ▶ Corner radius against chipping



T15 ALU 3 42° FLAT P.1090

◆ U.S.A Stock

■ SQUARE Unit : Inch

EDP No.	UNCOATED	TiCN COATED	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
66519	66519 PC	5/8	5/8	1-5/8	3-3/4	
66524	66524 PC	3/4	3/4	1-5/8	3-7/8	
66540	66540 PC	1	1	2	4-1/2	
66541	66541 PC	1-1/4	1-1/4	2	4-1/2	
66542	66542 PC	1-1/2	1-1/4	2	4-1/2	
*66543	*66543 PC	2	2	2	5-3/4	

* Combination Shank

T15 ALU 3 42° ±.001 FLAT P.1090

◆ U.S.A Stock

■ with CORNER RADIUS Unit : Inch

EDP No.	UNCOATED	TiCN COATED	Corner Radius R	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
66904	66904 PC	R .090	3/4	3/4	1-5/8	3-7/8	
66905	66905 PC	R .120	3/4	3/4	1-5/8	3-7/8	
66906	66906 PC	R .060	1	1	2	4-1/2	
66907	66907 PC	R .090	1	1	2	4-1/2	
66908	66908 PC	R .120	1	1	2	4-1/2	
66909	66909 PC	R .060	1-1/4	1-1/4	2	4-1/2	
66910	66910 PC	R .090	1-1/4	1-1/4	2	4-1/2	
66911	66911 PC	R .120	1-1/4	1-1/4	2	4-1/2	

■ The TiN coated, or TiAlN coated is available on your request.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
													◎	



EK226 SERIES FLAT SHANK

T15, 3 FLUTE 42° HELIX & MEDIUM LENGTH ROUGHING for ALUMINUM

- ▶ High performance metal removal in aluminum alloys.
- ▶ Corner radius against chipping



◆ U.S.A Stock

■ SQUARE Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TiCN COATED				
80524	80524 PC	3/4	3/4	2-1/4	4-5/8
80540	80540 PC	1	1	3	5-1/2
80541	80541 PC	1-1/4	1-1/4	3	5-1/2
80542	80542 PC	1-1/2	1-1/4	3	5-1/2
*80543	*80543 PC	2	2	3	6-3/4

*Combination Shank



◆ U.S.A Stock

■ with CORNER RADIUS Unit : Inch

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TiCN COATED	R				
80901	80901 PC	R .060	3/4	3/4	2-1/4	4-5/8
80902	80902 PC	R .090	3/4	3/4	2-1/4	4-5/8
80903	80903 PC	R .120	3/4	3/4	2-1/4	4-5/8
80904	80904 PC	R .060	1	1	3	5-1/2
80905	80905 PC	R .090	1	1	3	5-1/2
80906	80906 PC	R .120	1	1	3	5-1/2
80907	80907 PC	R .060	1-1/4	1-1/4	3	5-1/2
80908	80908 PC	R .090	1-1/4	1-1/4	3	5-1/2
80909	80909 PC	R .120	1-1/4	1-1/4	3	5-1/2

■ The TiN coated, or TiAlN coated is available on your request.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70								◎	



EK192 SERIES FLAT SHANK

T15, 3 FLUTE 42° HELIX LONG LENGTH ROUGHING for ALUMINUM

- ▶ High performance metal removal in aluminum alloys.



◆ U.S.A Stock

■ SQUARE Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TiCN COATED				
67515	67515 PC	1/2	1/2	2	4
67519	67519 PC	5/8	5/8	2-1/2	4-5/8
67524	67524 PC	3/4	3/4	3	5-1/4
67540	67540 PC	1	1	4	6-1/2
67541	67541 PC	1-1/4	1-1/4	4	6-1/2
67542	67542 PC	1-1/2	1-1/4	4	6-1/2
*67543	*67543 PC	2	2	4	7-3/4
67544	67544 PC	1-1/4	1-1/4	6	8-1/2
67545	67545 PC	1-1/2	1-1/4	6	8-1/2
*67546	*67546 PC	2	2	6	9-3/4

*Combination Shank

■ with NECK

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
UNCOATED	TiCN COATED						
EK10482	EK10482C	3/4	3/4	1-1/2	3	5-1/4	.705
EK10483	EK10483C	3/4	3/4	1-1/2	4	6-1/4	.705
EK10642	EK10642C	1	1	1-1/2	3	5-1/2	.950
EK10643	EK10643C	1	1	2	4	6-1/2	.950
EK10644	EK10644C	1	1	2	6	8-1/2	.950
EK11601	EK11601C	1-1/4	1-1/4	2	4	6-1/2	1.200
EK11602	EK11602C	1-1/4	1-1/4	2	6	8-1/2	1.200

■ The TiN coated, or TiAlN coated is available on your request.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70								◎	



EK192 SERIES FLAT SHANK

T15, 3 FLUTE 42° HELIX LONG LENGTH ROUGHING with CORNER RADIUS for ALUMINUM

- ▶ High performance metal in aluminum alloys.
- ▶ Corner radius against chipping



◆ U.S.A Stock

Unit : Inch

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TICN COATED	R				
67904	67904 PC	R .060	3/4	3/4	3	5-1/4
67905	67905 PC	R .090	3/4	3/4	3	5-1/4
67906	67906 PC	R .120	3/4	3/4	3	5-1/4
67907	67907 PC	R .060	1	1	4	6-1/2
67908	67908 PC	R .090	1	1	4	6-1/2
67909	67909 PC	R .120	1	1	4	6-1/2
67910	67910 PC	R .060	1-1/4	1-1/4	4	6-1/2
67911	67911 PC	R .090	1-1/4	1-1/4	4	6-1/2
67912	67912 PC	R .120	1-1/4	1-1/4	4	6-1/2
67913	67913 PC	R .060	1-1/4	1-1/4	6	8-1/2
67914	67914 PC	R .090	1-1/4	1-1/4	6	8-1/2
67915	67915 PC	R .120	1-1/4	1-1/4	6	8-1/2

■ The TiN coated, or TiAlN coated is available on your request.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70								◎	



EK196 SERIES FLAT SHANK

T15, 3 FLUTE 42° HELIX ROUGHING BALL NOSE REGULAR LENGTH for ALUMINUM

- ▶ High performance metal removal in aluminum alloys.



◆ U.S.A Stock

Unit : Inch

EDP No.		Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TICN COATED	R (±.001)				
EP12032	EP12032C	R1/4	1/2	1/2	1-1/4	3-1/4
EP12040	EP12040C	R5/16	5/8	5/8	1-5/8	3-3/4
EP12048	EP12048C	R3/8	3/4	3/4	1-5/8	3-7/8
EP12064	EP12064C	R1/2	1	1	2	4-1/2
EP12110	EP12110C	R5/8	1-1/4	1-1/4	2	4-1/2

■ The TiN coated, or TiAlN coated is available on your request.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70								◎	



EK193 SERIES FLAT SHANK
EK132 SERIES FLAT SHANK

**T15, 3 FLUTE FINISHING
REGULAR LENGTH & MEDIUM LENGTH & LONG LENGTH**

► High performance metal removal in aluminum alloys.



◆ U.S.A Stock

■ SQUARE Unit: Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TICN COATED				
EP10323	EP10323C	1/2	1/2	1-1/4	3-1/4
EP10324	EP10324C	1/2	1/2	2	4
EP10403	EP10403C	5/8	5/8	1-5/8	3-3/4
EP10404	EP10404C	5/8	5/8	2-1/2	4-5/8
EP10484	EP10484C	3/4	3/4	1-5/8	3-7/8
EP10485	EP10485C	3/4	3/4	2-1/4	4-5/8
EP10486	EP10486C	3/4	3/4	3	5-1/4
EP10644	EP10644C	1	1	2	4-1/2
EP10645	EP10645C	1	1	3	5-1/2
EP10646	EP10646C	1	1	4	6-1/2
EP11165	EP11165C	1-1/4	1-1/4	2	4-1/2
EP11166	EP11166C	1-1/4	1-1/4	3	5-1/2
EP11167	EP11167C	1-1/4	1-1/4	4	6-1/2
EP11324	EP11324C	1-1/2	1-1/4	2	4-1/2
EP11325	EP11325C	1-1/2	1-1/4	3	5-1/2
EP11326	EP11326C	1-1/2	1-1/4	4	6-1/2

■ SQUARE with NECK

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
UNCOATED	TICN COATED						
EK13210	EK13210C	3/4	3/4	1-1/2	3	5-1/4	.705
EK13211	EK13211C	3/4	3/4	1-1/2	4	6-1/4	.705
EK13212	EK13212C	1	1	1-1/2	3	5-1/2	.950
EK13213	EK13213C	1	1	2	4	6-1/2	.950
EK13214	EK13214C	1	1	2	6	8-1/2	.950
EK13215	EK13215C	1-1/4	1-1/4	2	4	6-1/2	1.200
EK13216	EK13216C	1-1/4	1-1/4	2	6	8-1/2	1.200

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

■ The TiN coated, or TiAlN coated is available on your request.

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70								◎	



EK193 SERIES FLAT SHANK

**T15, 3 FLUTE FINISHING CORNER RADIUS
REGULAR LENGTH & MEDIUM LENGTH & LONG LENGTH**

► High performance metal removal in aluminum alloys.
► Corner radius against chipping



◆ U.S.A Stock

■ SQUARE Unit: Inch

EDP No.		Corner Radius R	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TICN COATED					
EP10321	EP10321C	R.120	1/2	1/2	1-1/4	3-1/4
EP10322	EP10322C	R.120	1/2	1/2	2	4
EP10401	EP10401C	R.120	5/8	5/8	1-5/8	3-3/4
EP10402	EP10402C	R.120	5/8	5/8	2-1/2	4-5/8
EP10481	EP10481C	R.120	3/4	3/4	1-5/8	3-7/8
EP10482	EP10482C	R.120	3/4	3/4	2-1/4	4-5/8
EP10483	EP10483C	R.120	3/4	3/4	3	5-1/4
EP10641	EP10641C	R.120	1	1	2	4-1/2
EP10642	EP10642C	R.120	1	1	3	5-1/2
EP10643	EP10643C	R.120	1	1	4	6-1/2
EP11162	EP11162C	R.120	1-1/4	1-1/4	2	4-1/2
EP11163	EP11163C	R.120	1-1/4	1-1/4	3	5-1/2
EP11164	EP11164C	R.120	1-1/4	1-1/4	4	6-1/2
EP11321	EP11321C	R.120	1-1/2	1-1/4	2	4-1/2
EP11322	EP11322C	R.120	1-1/2	1-1/4	3	5-1/2
EP11323	EP11323C	R.120	1-1/2	1-1/4	4	6-1/2

■ The TiN coated, or TiAlN coated is available on your request.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70								◎	



EP922 SERIES PLAIN SHANK

PREMIUM HSS-PM, 3 FLUTE 42° HELIX SHORT LENGTH ROUGHING for ALUMINUM

- ▶ Maximum stock removal rates at High Speed Condition.
- ▶ Reduces vibrations and improves surface roughness.



◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
	Metric	Inch			
	js12		h6		
EP922120	12.0	.4724	12	26	83
EP922140	14.0	.5512	12	26	83
EP922160	16.0	.6299	16	32	92
EP922180	18.0	.7087	16	32	92
EP922200	20.0	.7874	20	38	104
EP922220	22.0	.8661	20	38	104
EP922250	25.0	.9843	25	45	121
EP922280	28.0	1.1024	25	45	121
EP922320	32.0	1.2598	32	53	133

Tolerances according to DIN 7160 & 7161

Tolerance range in μm						
Nominal-Diameter in mm						
	from 1 to 3	over 3 to 6	over 6 to 10	over 10 to 18	over 18 to 30	over 30 to 50
js12	± 50	± 60	± 75	± 90	± 105	± 125
h6	⁰ / ₋₆	⁰ / ₋₈	⁰ / ₋₉	⁰ / ₋₁₁	⁰ / ₋₁₃	⁰ / ₋₁₆

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
													◎	



EP924 SERIES PLAIN SHANK

PREMIUM HSS-PM, 3 FLUTE 42° HELIX LONG LENGTH ROUGHING for ALUMINUM

- ▶ Maximum stock removal rates at High Speed Condition.
- ▶ Reduces vibrations and improves surface roughness.



◇ Call for Availability

Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
	Metric	Inch			
	js12		h6		
EP924120	12.0	.4724	12	53	110
EP924140	14.0	.5512	12	53	110
EP924160	16.0	.6299	16	63	123
EP924180	18.0	.7087	16	63	123
EP924200	20.0	.7874	20	75	141
EP924220	22.0	.8661	20	75	141
EP924250	25.0	.9843	25	90	166
EP924280	28.0	1.1024	25	90	166
EP924320	32.0	1.2598	32	106	186

Tolerances according to DIN 7160 & 7161

Tolerance range in μm						
Nominal-Diameter in mm						
	from 1 to 3	over 3 to 6	over 6 to 10	over 10 to 18	over 18 to 30	over 30 to 50
js12	± 50	± 60	± 75	± 90	± 105	± 125
h6	⁰ / ₋₆	⁰ / ₋₈	⁰ / ₋₉	⁰ / ₋₁₁	⁰ / ₋₁₃	⁰ / ₋₁₆

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
													◎	





RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE 42° HELIX - "BANSHEE"

E5253, E5254 SERIES

MATERIAL	N			
	ALUMINUM NON FERROUS METALS		ALUMINUM NON FERROUS METALS	
DIAMETER	RPM	FEED	RPM	FEED
1/8	10000	27.6	10000	35.4
5/32	10000	35.4	10000	43.3
3/16	10000	39.4	10000	51.2
1/4	10000	47.2	10000	59.1
5/16	8000	55.1	8000	70.9
3/8	8000	66.9	8000	82.7
1/2	8000	82.7	8000	102.4
9/16	6000	70.9	6000	86.6
5/8	6000	74.8	6000	94.5
11/16	4000	55.1	4000	70.9
13/16	4000	63.0	4000	74.8





* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

CARBIDE, 2 FLUTE 42° HELIX TiCN COATED - "BANSHEE"

EG253, EG254 SERIES

MATERIAL	N			
	ALUMINUM NON FERROUS METALS		ALUMINUM NON FERROUS METALS	
DIAMETER	RPM	FEED	RPM	FEED
1/8	15600	42.5	12000	56.7
5/32	15600	56.7	12000	66.1
3/16	15600	61.4	12000	80.3
1/4	15600	70.9	12000	94.5
5/16	12000	85.1	9600	108.7
3/8	12000	103.9	9600	127.6
1/2	12000	127.6	9600	160.6
9/16	9600	108.7	7200	132.2
5/8	9600	118.1	7200	146.5
11/16	6000	85.0	4800	108.7
13/16	6000	94.5	4800	118.1



* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.





RECOMMENDED CUTTING CONDITIONS

CARBIDE, 3 FLUTE 45° HELIX FINISH

E5980, E5981, E5982, E5983, E5984 SERIES

MATERIAL	N			
	ALUMINUM NON FERROUS METALS		ALUMINUM NON FERROUS METALS	
DIAMETER	RPM	FEED	RPM	FEED
1/8	10000	33.1	10000	42.5
5/32	10000	42.5	10000	52.0
3/16	10000	47.3	10000	61.4
1/4	10000	56.7	10000	70.9
5/16	8000	66.2	8000	85.1
3/8	8000	80.3	8000	99.2
1/2	8000	99.2	8000	122.9
9/16	6000	85.1	6000	104.0
5/8	6000	89.8	6000	113.4
11/16	4000	66.2	4000	85.1
13/16	4000	75.6	4000	89.8





* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

CARBIDE, 3 FLUTE 45° HELIX FINISH TiCN COATED

EG980, EG981, EG982, EG983, EG984 SERIES

MATERIAL	N			
	ALUMINUM NON FERROUS METALS		ALUMINUM NON FERROUS METALS	
DIAMETER	RPM	FEED	RPM	FEED
1/8	15600	43.0	12000	55.3
5/32	15600	55.3	12000	67.6
3/16	15600	61.4	12000	79.8
1/4	15600	73.7	12000	92.2
5/16	12000	86.0	9600	110.6
3/8	12000	104.4	9600	129.0
1/2	12000	128.9	9600	159.8
9/16	9600	110.6	7200	135.2
5/8	9600	116.7	7200	147.4
11/16	6000	86.0	4800	110.6
13/16	6000	98.3	4800	116.7



* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.





RECOMMENDED CUTTING CONDITIONS

CARBIDE, 3 FLUTE 37° HELIX with EXTENDED NECK

E5977, E5985 SERIES

MATERIAL	N			
	ALUMINUM NON FERROUS METALS		ALUMINUM NON FERROUS METALS	
DIAMETER	RPM	FEED	RPM	FEED
1/4	8000	45.4	8000	56.7
3/8	6400	64.3	6400	79.4
1/2	6400	79.4	6400	98.3
5/8	4800	71.8	4800	90.7
3/4	3200	70.9	3200	87.4
1	2600	63.8	2600	78.7





※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

CARBIDE, 3 FLUTE 37° HELIX with EXTENDED NECK TiCN COATED

EG977, EG985 SERIES

MATERIAL	N			
	ALUMINUM NON FERROUS METALS		ALUMINUM NON FERROUS METALS	
DIAMETER	RPM	FEED	RPM	FEED
1/4	10500	59.0	10500	73.7
3/8	8300	83.5	8300	103.2
1/2	8300	103.2	8300	127.7
5/8	6200	93.4	6200	117.9
3/4	4200	92.1	4200	113.6
1	3400	83.0	3400	102.0



※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.







RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE CORNER RADIUS with NECK

E5973 SERIES

MATERIAL	N							
	ALUMINUM NON FERROUS METALS				COPPER ALLOYS			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
R.012 × 5/32	10000	36.4	10000	42.4	3000	9.1	3000	10.6
R.020 × 1/4	10000	45.4	10000	60.6	3000	11.5	3000	15.2
R.024 × 5/16	8000	54.5	8000	69.6	2300	13.6	2300	17.6
R.031 × 3/8	8000	66.6	8000	81.8	2300	16.7	2300	20.6
R.040 × 1/2	8000	81.8	8000	103.0	2300	20.6	2300	25.8
R.051 × 5/8	6000	75.7	6000	93.9	1800	19.1	1800	23.6
R.063 × 3/4	4000	60.6	4000	75.7	1150	15.2	1150	19.1





※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

CARBIDE, 2 FLUTE 37° HELIX with EXTENDED NECK

E5976 SERIES

MATERIAL	N			
	ALUMINUM NON FERROUS METALS		ALUMINUM NON FERROUS METALS	
DIAMETER	RPM	FEED	RPM	FEED
1/4	8000	37.8	8000	47.3
3/8	6400	53.6	6400	66.2
1/2	6400	66.2	6400	81.9
5/8	4800	59.9	4800	75.6
3/4	3200	59.1	3200	72.9
1	2600	53.2	2600	65.6



※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE 37° HELIX LONG REACH BALL NOSE

E5978 SERIES

MATERIAL	N		
	ALUMINUM NON FERROUS METALS		
DIAMETER	RPM	FEED	
R1/8 × 1/4	11200	55.1	
R5/32 × 5/16	8600	63.0	
R3/16 × 3/8	8600	74.0	
R1/4 × 1/2	8600	94.5	
R5/16 × 5/8	6800	85.0	
R3/8 × 3/4	4300	69.3	




* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

CARBIDE, 2 FLUTE 37° HELIX LONG REACH BALL NOSE TiCN COATED

EG978 SERIES

MATERIAL	N		
	ALUMINUM NON FERROUS METALS		
DIAMETER	RPM	FEED	
R1/8 1/4	14500	71.7	
R5/32 5/16	11200	81.9	
R3/16 3/8	11200	96.2	
R1/4 1/2	11200	122.9	
R5/16 5/8	8800	110.5	
R3/8 3/4	5600	104.0	



* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE 50° HELIX BALL NOSE with NECK

E5974 SERIES

MATERIAL	N			
	ALUMINUM ALUMINUM ALLOYS		COPPER ALLOYS	
DIAMETER	RPM	FEED	RPM	FEED
R1/8 × 1/4	14000	53.0	4200	13.3
R5/32 × 5/16	10800	60.5	3200	15.1
R3/16 × 3/8	10800	71.2	3200	17.5
R1/4 × 1/2	10800	90.8	3200	22.7
R5/16 × 5/8	8500	81.8	2500	20.3
R3/8 × 3/4	5400	66.6	1600	16.7




* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

CARBIDE, 3 FLUTE 40° HELIX BALL NOSE with NECK

E5975 SERIES

MATERIAL	N			
	ALUMINUM ALUMINUM ALLOYS		COPPER ALLOYS	
DIAMETER	RPM	FEED	RPM	FEED
R3/64 × 3/32	20700	28.8	6200	7.3
R1/16 × 1/8	13800	28.8	4200	7.3
R3/32 × 3/16	13800	40.9	4200	10.3
R1/8 × 1/4	13800	53.0	4200	13.3
R5/32 × 5/16	10800	60.6	3200	15.2
R3/16 × 3/8	10800	71.2	3200	17.6
R1/4 × 1/2	10800	90.9	3200	22.7
R5/16 × 5/8	8500	81.8	2500	20.3



* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.



- CBN END MILLS
- i-Xmill END MILLS
- i-SMART MODULAR TYPE END MILLS
- X5070 END MILLS
- 4G MILL END MILLS
- X-POWER END MILLS
- JET-POWER END MILLS
- TitaNox -POWER END MILLS
- V7 PLUS A END MILLS
- V7 MILL INOX END MILLS
- ALU-POWER HPC END MILLS
- ALU-POWER END MILLS
- D-POWER GRAPHITE END MILLS
- D-POWER CFRP END MILLS
- ROUTERS CFRP
- STANDARD CARBIDE END MILLS
- ONLY ONE COATED PM60 END MILLS
- SINE -POWER END MILLS
- TANK-POWER END MILLS
- STANDARD COBALT & HSS END MILLS
- TECHNICAL DATA

- CBN END MILLS
- i-Xmill END MILLS
- i-SMART MODULAR TYPE END MILLS
- X5070 END MILLS
- 4G MILL END MILLS
- X-POWER END MILLS
- JET-POWER END MILLS
- TitaNox -POWER END MILLS
- V7 PLUS A END MILLS
- V7 MILL INOX END MILLS
- ALU-POWER HPC END MILLS
- ALU-POWER END MILLS
- D-POWER GRAPHITE END MILLS
- D-POWER CFRP END MILLS
- ROUTERS CFRP
- STANDARD CARBIDE END MILLS
- ONLY ONE COATED PM60 END MILLS
- SINE -POWER END MILLS
- TANK-POWER END MILLS
- STANDARD COBALT & HSS END MILLS
- TECHNICAL DATA

CARBIDE, 2 FLUTE

E5522 SERIES

MATERIAL	N			
	ALUMINUM LOW SILICON ALUMINUM			
DIAMETER	RPM	FEED	RPM	FEED
3.0	10000	27.6	10000	35.4
4.0	10000	35.4	10000	43.3
5.0	10000	39.4	10000	51.2
6.0	10000	47.2	10000	59.1
8.0	8000	55.1	8000	70.9
10.0	8000	66.9	8000	82.7
12.0	8000	82.7	8000	102.4
14.0	6000	70.9	6000	86.6
16.0	6000	74.8	6000	94.5
18.0	4000	55.1	4000	70.9
20.0	4000	63.0	4000	74.8





A: $\varnothing 3 \sim \varnothing 10 = 0.25 \times D$
 $\varnothing 12 \sim \varnothing 20 = 0.5 \times D$

RPM = rev./min.
 FEED = inch/min.

CARBIDE, 2 FLUTE TiCN COATED

EG522, EG930 SERIES

MATERIAL	N			
	ALUMINUM LOW SILICON ALUMINUM			
DIAMETER	RPM	FEED	RPM	FEED
3.0	13000	35.4	13000	47.2
4.0	13000	47.2	13000	55.1
5.0	13000	51.2	13000	66.9
6.0	13000	59.1	13000	78.7
8.0	10000	70.9	10000	90.6
10.0	10000	86.6	10000	106.3
12.0	10000	106.3	10000	133.9
14.0	8000	90.6	8000	110.2
16.0	8000	98.4	8000	122.1
18.0	5000	70.9	5000	90.6
20.0	5000	78.7	5000	98.4





A: $\varnothing 3 \sim \varnothing 10 = 0.25 \times D$
 $\varnothing 12 \sim \varnothing 20 = 0.5 \times D$

RPM = rev./min.
 FEED = inch/min.



CARBIDE, 2 FLUTE CORNER RADIUS TiCN COATED

EG909 SERIES

MATERIAL	N							
	ALUMINUM ALUMINUM ALLOYS				COPPER ALLOYS			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
4.0	13000	47.2	13000	55.1	3900	11.8	3900	13.8
6.0	13000	59.1	13000	78.7	3900	15.0	3900	19.7
8.0	10000	70.9	10000	90.6	3000	17.7	3000	22.8
10.0	10000	86.6	10000	106.3	3000	21.7	3000	26.8
12.0	10000	106.3	10000	133.9	3000	26.8	3000	33.5
16.0	8000	98.4	8000	122.1	2400	24.8	2400	30.7
20.0	5000	78.7	5000	98.4	1500	19.7	1500	24.8



A: $\sim \varnothing 10 = 0.25D$
 $\varnothing 12 \sim \varnothing 20 = 0.5D$




A: $\sim \varnothing 10 = 0.25D$
 $\varnothing 12 \sim \varnothing 20 = 0.5D$

RPM = rev./min.
 FEED = inch/min.

CARBIDE, 2 FLUTE 50° HELIX BALL NOSE TiCN COATED

EG910 SERIES

MATERIAL	N			
	ALUMINUM ALUMINUM ALLOYS		COPPER ALLOYS	
DIAMETER	RPM	FEED	RPM	FEED
R3.0 × 6.0	18000	68.9	5500	17.3
R4.0 × 8.0	14000	78.7	4200	19.7
R5.0 × 10.0	14000	92.5	4200	22.8
R6.0 × 12.0	14000	118.1	4200	29.5
R8.0 × 16.0	11000	106.3	3300	26.4
R10.0 × 20.0	7000	86.6	2100	21.7



$ap = 0.2 \times D$
 $ae = 0.5 \times D$

RPM = rev./min.
 FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 3 FLUTE 40° HELIX BALL NOSE TiCN COATED

EG908 SERIES

MATERIAL	N			
	ALUMINUM LOW SILICON ALUMINUM		COPPER ALLOYS	
DIAMETER	RPM	FEED	RPM	FEED
R1.0 × 2.0	27000	37.4	8000	9.5
R1.25 × 2.5	22000	37.4	6500	9.5
R1.5 × 3.0	18000	37.4	5500	9.5
R2.0 × 4.0	18000	49.2	5500	12.2
R2.5 × 5.0	18000	53.2	5500	13.4
R3.0 × 6.0	18000	68.9	5500	17.3
R4.0 × 8.0	14000	78.7	4200	19.7
R5.0 × 10.0	14000	92.5	4200	22.8
R6.0 × 12.0	14000	118.1	4200	29.5
R8.0 × 16.0	11000	106.3	3300	26.4






RPM = rev./min.
FEED = inch/min.

CARBIDE, 3 FLUTE ROUGHING

E5E44, E5E98, E5E45 SERIES

MATERIAL	N					
	ALUMINUM ALUMINUM ALLOYS					
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
1/4	7000	20.7	10000	29.5	10000	29.5
3/8	4700	16.1	6700	22.8	6700	22.8
1/2	3600	16.3	5100	23.0	5100	23.0
5/8	2800	16.9	4000	24.0	4000	24.0
3/4	2300	18.5	3300	26.4	3300	26.4
1	1800	17.3	2500	24.4	2500	24.4



RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

T15, 3 FLUTE 42° HELIX SPEED-FREAK BALL NOSE

EK196 SERIES

MATERIAL	N	
	ALUMINUM ALUMINUM ALLOYS	
DIAMETER	RPM	FEED
1/4	4500	7.9
5/16	3100	9.1
3/8	2500	13.8
1/2	2000	15.8
5/8	1600	17.7





* The FEED, in long & long reach types, should be reduced by around 50%

RPM = rev./min.
FEED = inch/min.

T15, 3 FLUTE, 42° HELIX FINISHING with CORNER RADIUS

EK193 SERIES

MATERIAL	N			
	ALUMINUM ALUMINUM ALLOYS			
DIAMETER	RPM	FEED	RPM	FEED
1/2	4500	38	4095	38
5/8	3500	26	3185	39
3/4	2300	27	2093	41
1	2000	27	1820	40
1-1/4	1600	26	1456	38
1-1/2	1350	25	1229	38



* The FEED, in long & long reach types, should be reduced by around 50%

RPM = rev./min.
FEED = inch/min.

CARBIDE

HSS



YG ALU-POWER END MILLS

RECOMMENDED CUTTING CONDITIONS

PREMIUM HSS-PM, 3 FLUTE 42° HELIX ROUGHING TiAIN COATED

EP922, EP924 SERIES

MATERIAL	N			
	ALUMINUM ALUMINUM ALLOYS			
DIAMETER	RPM	FEED	RPM	FEED
12.0	2800	16.1	2800	21.7
16.0	2200	18.3	2200	24.6
20.0	1700	20.7	1700	27.6
25.0	1400	18.3	1400	24.6
32.0	1100	20.7	1100	27.6



* The FEED, in long & long reach types, should be reduced by around 50%

RPM = rev./min.
FEED = inch/min.

SPEED FREEK

YG T-15 3 FLUTE ALUMINUM ROUGHER

MATERIAL	UNCOATED	TiCN	CHIP LOAD PER TOOTH & CUTTING DIAMETER				
	SFM	SFM	1/2	3/4	1.00	1.25	2.00
ALUMINUM [SOFT]	250-500	400-2,500	.005	.007	.010	.012	.015
AIRCRAFT ALUMINUM [UNDER 10% SILICON]	250-750	500-3,250	.005	.007	.010	.012	.015

3/4 DIA. / TiCN COATED / 10,186 RPM [2,000 SFM] @ 213 IPM

SFM	$0.262 \times \text{CUTTER DIA} \times \text{RPM}$	FPT	$\frac{\text{IPM}}{\text{N} \times \text{RPM}}$	SFM = SURFACE FEET PER MINUTE RPM = REVOLUTIONS PER MINUTE N = NUMBER OF TEETH IPR = INCHES PER REVOLUTION IPM = INCHES PER MINUTE FPT = FEED PER TOOTH
RPM	$3.82 \times \frac{\text{SFM}}{\text{CUTTER DIA}}$	IPR	$\frac{\text{IPM}}{\text{RPM}}$	
IPM	$\text{FPT} \times \text{N} \times \text{RPM}$	CUTTING TIME	$\frac{\text{LENGTH OF CUT}}{\text{IPM}}$	



Being the best through innovation

CARBIDE



D-POWER GRAPHITE END MILLS

- Diamond Coated Carbide End Mills for Graphite

SELECTION GUIDE

SOLID CARBIDE D-POWER GRAPHITE END MILLS

◎ : Excellent ○ : Good





ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	

INCH

EI107		CARBIDE, 4(2) FLUTE REGULAR LENGTH	◆	D1/64	D1/2	1094
EI099		CARBIDE, 2 FLUTE REGULAR LENGTH BALL NOSE	◆	R.0391	R1/4	1095
EI106		CARBIDE, 4 FLUTE REGULAR LENGTH BALL NOSE	◆	R.0391	R1/4	1095
EI971		CARBIDE, 2 FLUTE LONG LENGTH BALL NOSE	◆	R.0391	R1/4	1096
EI972		CARBIDE, 2 FLUTE LONG REACH BALL NOSE	◆	R.0391	R5/32	1097
EIB07		CARBIDE, 4 FLUTE REGULAR LENGTH BALL NOSE with NECK	◆	R.0156	R.0625	1098
EIB05		CARBIDE, 4 FLUTE REGULAR LENGTH CORNER RADIUS	◆	D1/16	D1/2	1099
EIB06		CARBIDE, 4 FLUTE REGULAR LENGTH CORNER RADIUS with NECK	◆	D1/32	D3/8	1100

◆ U.S.A Stock

METRIC

EI880		CARBIDE, 2 FLUTE SHORT LENGTH BALL NOSE	◇	R1.0	R6.0	1101
EI881		CARBIDE, 3 FLUTE SHORT LENGTH BALL NOSE	◇	R1.0	R6.0	1101
EI451		CARBIDE, 2 FLUTE LONG LENGTH BALL NOSE	◇	R1.0	R6.0	1102
EI450		CARBIDE, 2 FLUTE LONG REACH BALL NOSE	◇	R1.0	R4.0	1103
RECOMMENDED CUTTING CONDITIONS						1104

◇ Call for Availability

P					H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									

									◎	○				
									◎	○				
									◎	○				
									◎	○				
									◎	○				
									◎	○				
									◎	○				
									◎	○				
									◎	○				

									◎	○				
									◎	○				
									◎	○				
									◎	○				

YG D-POWER GRAPHITE END MILLS

EI107 SERIES PLAIN SHANK

CARBIDE, 4(2) FLUTE REGULAR LENGTH

- ▶ Higher hardness of film and excellent wear-resistance increase the tool life dramatically.
- ▶ Ultra fine film of YG-1's diamond coated carbide end mills ensure the smooth and excellent surface on work materials.
- ▶ High performance on graphite, wrought aluminum, bakelite, plastics, wood, brass, etc.
- ▶ YG-1's diamond coated carbide end mills may have good result for the machining of non-ferrous metals and non-metallic materials.



MG 4 30° PLAIN P.1105

for GRAPHITE
◆ U.S.A Stock

Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
★ 99686	1/64	1/8	3/65	1-1/2
99629	1/8	1/8	1/2	1-1/2
99630	3/16	3/16	5/8	2
99631	1/4	1/4	3/4	2-1/2
99632	5/16	5/16	13/16	2-1/2
99633	3/8	3/8	7/8	2-1/2
99635	1/2	1/2	1	3

- ★ 2Flute
- ▶ Recommended Cutting Condition
 - ▶ Cutting speed : 500~1200 SFPM
 - ▶ Feed : .002~.006 inch/tooth

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-.0012	0~-.0003

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
									◎	○				

YG D-POWER GRAPHITE END MILLS

EI099 SERIES PLAIN SHANK
EI106 SERIES PLAIN SHANK

CARBIDE, 2&4 FLUTE REGULAR LENGTH BALL NOSE

- ▶ Higher hardness of film and excellent wear-resistance increase the tool life dramatically.
- ▶ Ultra fine film of YG-1's diamond coated carbide ball end mills ensure the smooth and excellent surface on work materials.
- ▶ High performance on graphite, wrought aluminum, bakelite, plastics, wood, brass, etc.
- ▶ YG-1's diamond coated carbide ball end mills may have good result for the machining of non-ferrous metals and non-metallic materials.



MG 2 30° ±.0008 PLAIN P.1104

for GRAPHITE
◆ U.S.A Stock

Unit : Inch

EI099(2 FLUTE), EI106(4 FLUTE) Series

EDP No.		Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
2 FLUTE	4 FLUTE	R (±.0008)				
99572	99621	R .0391	5/64	1/8	1/4	1-1/2
99573	99622	R 3/64	3/32	1/8	3/8	1-1/2
99574	99623	R 1/16	1/8	1/8	1/2	1-1/2
99575	99624	R 3/32	3/16	3/16	5/8	2
99576	99625	R 1/8	1/4	1/4	3/4	2-1/2
99577	99626	R 5/32	5/16	5/16	13/16	2-1/2
99578	99627	R 3/16	3/8	3/8	7/8	2-1/2
99583	99628	R 1/4	1/2	1/2	1	3

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-.0012	0~-.0003

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
									◎	○				

YG D-POWER GRAPHITE END MILLS

EI971 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG LENGTH BALL NOSE

- ▶ Higher hardness of film and excellent wear-resistance increase the tool life dramatically.
- ▶ Ultra fine film of YG-1's diamond coated carbide ball end mills ensure the smooth and excellent surface on work materials.
- ▶ High performance on graphite, wrought aluminum, bakelite, plastics, wood, brass, etc.
- ▶ YG-1's diamond coated carbide ball end mills may have good result for the machining of non-ferrous metals and non-metallic materials.




MG 2 30° ±.0008 PLAIN P.1104

for GRAPHITE
◆ U.S.A Stock

Unit : Inch

EDP No.	Radius of Ball Nose R (±.0008)	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
99671	R.0391	5/64	1/8	3/8	3/4	3-1/4	.076
99672	R 1/16	1/8	1/8	5/8	1	3-1/4	.120
99973	R 3/32	3/16	3/16	1-1/8	2	4	.182
99673	R 3/32	3/16	1/4	1-1/8	2	4	.185
99674	R 1/8	1/4	1/4	1-1/8	2	4	.230
99675	R 5/32	5/16	5/16	1-1/2	2-3/8	4-1/2	.293
99676	R 3/16	3/8	3/8	2	2-3/4	4-3/4	.355
99677	R1/4	1/2	1/2	2-1/8	3	5-1/8	.480

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~.0012	0~.0003



◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
									◎	○				

YG D-POWER GRAPHITE END MILLS

EI972 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG REACH BALL NOSE

- ▶ Higher hardness of film and excellent wear-resistance increase the tool life dramatically.
- ▶ Ultra fine film of YG-1's diamond coated carbide ball end mills ensure the smooth and excellent surface on work materials.
- ▶ High performance on graphite, wrought aluminum, bakelite, plastics, wood, brass, etc.
- ▶ YG-1's diamond coated carbide ball end mills may have good result for the machining of non-ferrous metals and non-metallic materials.




MG 2 30° ±.0008 PLAIN P.1104

for GRAPHITE
◆ U.S.A Stock

Unit : Inch

EDP No.	Radius of Ball Nose R (±.0008)	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
99678	R.0391	5/64	1/8	3/8	3/4	4	.076
99679	R1/16	1/8	1/8	5/8	1	4	.120
99980	R3/32	3/16	3/16	1-1/8	2	4-3/4	.182
99680	R3/32	3/16	1/4	1-1/8	2	4-3/4	.186
99681	R1/8	1/4	1/4	1-1/8	2	6	.230
99682	R5/32	5/16	5/16	1-1/2	2-3/8	6	.293

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~.0012	0~.0003



◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
									◎	○				

YG D-POWER GRAPHITE END MILLS

EIB07 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE REGULAR LENGTH BALL NOSE with NECK

- ▶ Higher hardness of film and excellent wear-resistance increase the tool life dramatically.
- ▶ Ultra fine film of YG-1's diamond coated carbide ball end mills ensure the smooth and excellent surface on work materials.
- ▶ High performance on graphite, wrought aluminum, bakelite, plastics, wood, brass, etc.
- ▶ YG-1's diamond coated carbide ball end mills may have good result for the machining of non-ferrous metals and non-metallic materials.



MG 4 30° ±.0008 PLAIN P.1104

for GRAPHITE
◆ U.S.A Stock

Unit : Inch

EDP No.	Radius of Ball Nose R (±.0008)	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
EIB07002	R.0156	1/32	1/8	3/32	3/8	3	.028
EIB07901	R.0156	1/32	1/8	3/32	1/2	3	.028
EIB07003	R.0234	3/64	1/8	9/64	9/16	3	.043
EIB07902	R.0234	3/64	1/8	9/64	3/4	3	.043
EIB07004	R.0312	1/16	1/8	3/16	3/4	3	.057
EIB07903	R.0312	1/16	1/8	3/16	1	3	.057
EIB07006	R.0469	3/32	1/8	9/32	1	3	.086
EIB07904	R.0469	3/32	1/8	9/32	1-1/2	3	.086
EIB07008	R.0625	1/8	1/8	3/8	1-1/2	3	.115
EIB07905	R.0625	1/8	1/8	3/8	2	3	.115

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.012	0~-0.003

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
									◎	○				

YG D-POWER GRAPHITE END MILLS

EIB05 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE REGULAR LENGTH CORNER RADIUS

- ▶ Higher hardness of film and excellent wear-resistance increase the tool life dramatically.
- ▶ Ultra fine film of YG-1's diamond coated carbide ball end mills ensure the smooth and excellent surface on work materials.
- ▶ High performance on graphite, wrought aluminum, bakelite, plastics, wood, brass, etc.
- ▶ YG-1's diamond coated carbide ball end mills may have good result for the machining of non-ferrous metals and non-metallic materials.



MG 4 30° ±.001 PLAIN P.1104

for GRAPHITE
◆ U.S.A Stock

Unit : Inch

EDP No.	Corner Radius R (±.001)	Mill Diameter D1	Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
EIB05004	R.010	1/16	1/8	3/16	-	1-1/2	-
EIB05901	R.015	1/16	1/8	3/16	-	1-1/2	-
EIB05006	R.010	3/32	1/8	3/8	-	1-1/2	-
EIB05008	R.015	1/8	1/8	1/2	-	1-1/2	-
EIB05902	R.020	1/8	1/8	1/2	-	1-1/2	-
EIB05012	R.020	3/16	3/16	5/8	-	2	-
EIB05911	R.020	3/16	3/16	3/16	1-1/2	4	.169
EIB05903	R.030	3/16	3/16	5/8	-	2	-
EIB05016	R.020	1/4	1/4	3/4	-	2-1/2	-
EIB05913	R.020	1/4	1/4	1/4	2	4	.230
EIB05912	R.020	1/4	1/4	1/4	2	6	.230
EIB05904	R.030	1/4	1/4	3/4	-	2-1/2	-
EIB05024	R.020	3/8	3/8	7/8	-	2-1/2	-
EIB05908	R.020	3/8	3/8	3/8	2	4	.355
EIB05907	R.020	3/8	3/8	3/8	-	4	-
EIB05905	R.030	3/8	3/8	7/8	-	2-1/2	-
EIB05032	R.030	1/2	1/2	1	-	3	-
EIB05906	R.060	1/2	1/2	1	-	3	-
EIB05909	R.030	1/2	1/2	1-1/2	-	4	-
EIB05910	R.030	1/2	1/2	3	-	6	-

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.012	0~-0.003

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
									◎	○				

YG D-POWER GRAPHITE END MILLS

EIB06 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE REGULAR LENGTH CORNER RADIUS with NECK

- ▶ Higher hardness of film and excellent wear-resistance increase the tool life dramatically.
- ▶ Ultra fine film of YG-1's diamond coated carbide ball end mills ensure the smooth and excellent surface on work materials.
- ▶ High performance on graphite, wrought aluminum, bakelite, plastics, wood, brass, etc.
- ▶ YG-1's diamond coated carbide ball end mills may have good result for the machining of non-ferrous metals and non-metallic materials.



MG 4 30° ±.001 PLAIN P.1105

for GRAPHITE
◆ U.S.A Stock

Unit : Inch

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
	R (±.001)	D1	D2	L1	L3	L2	D3
EIB06002	R.005	1/32	1/8	3/32	3/8	3	.028
EIB06901	R.005	1/32	1/8	3/32	1/2	3	.028
EIB06003	R.010	3/64	1/8	9/64	9/16	3	.043
EIB06902	R.010	3/64	1/8	9/64	3/4	3	.043
EIB06004	R.010	1/16	1/8	3/16	3/4	3	.057
EIB06903	R.010	1/16	1/8	3/16	1	3	.057
EIB06006	R.010	3/32	1/8	9/32	1	3	.086
EIB06904	R.010	3/32	1/8	9/32	1-1/2	3	.086
EIB06008	R.010	1/8	1/8	3/8	1-1/2	3	.115
EIB06905	R.010	1/8	1/8	3/8	2	3	.115
EIB06906	R.015	1/8	1/8	3/16	.800	2-1/2	.115
EIB06907	R.020	3/8	3/8	3/8	3	6	.355

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-0.012	0~-0.003

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
									◎	○				

YG D-POWER GRAPHITE END MILLS

EI880 SERIES PLAIN SHANK
EI881 SERIES PLAIN SHANK

CARBIDE, 2&3 FLUTE SHORT LENGTH BALL NOSE

- ▶ Higher hardness of film and excellent wear-resistance increase the tool life dramatically.
- ▶ Ultra fine film of YG-1's diamond coated carbide ball end mills ensure the smooth and excellent surface on work materials.
- ▶ High performance on graphite, wrought aluminum, bakelite, plastics, wood, brass, etc.
- ▶ YG-1's diamond coated carbide ball end mills may have good result for the machining of non-ferrous metals and non-metallic materials.



MG 2&3 30° ±0.01 PLAIN P.1105

for GRAPHITE
◇ Call for Availability

Unit : mm

EDP No.		Radius of Ball Nose R (±0.01)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
2 FLUTE	3 FLUTE		Metric	Inch					
EI880020	EI881020	R1.0	2.0	.0787	6	3	5	60	1.9
EI880025	EI881025	R1.25	2.5	.0984	6	4	6	60	2.4
EI880030	EI881030	R1.5	3.0	.1181	6	4.5	6.5	60	2.8
EI880035	EI881035	R1.75	3.5	.1378	6	5	7	65	3.2
EI880040	EI881040	R2.0	4.0	.1575	6	6	8	65	3.7
EI880050	EI881050	R2.5	5.0	.1969	6	7.5	10	65	4.6
EI880060	EI881060	R3.0	6.0	.2362	6	9	12	75	5.6
EI880080	EI881080	R4.0	8.0	.3150	8	12	25	75	7.4
EI880100	EI881100	R5.0	10.0	.3937	10	15	30	80	9.4
EI880120	EI881120	R6.0	12.0	.4724	12	18	36	90	11.4

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
									◎	○				

YG D-POWER GRAPHITE END MILLS

EI451 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG LENGTH BALL NOSE

- ▶ Higher hardness of film and excellent wear-resistance increase the tool life dramatically.
- ▶ Ultra fine film of YG-1's diamond coated carbide ball end mills ensure the smooth and excellent surface on work materials.
- ▶ High performance on graphite, wrought aluminum, bakelite, plastics, wood, brass, etc.
- ▶ YG-1's diamond coated carbide ball end mills may have good result for the machining of non-ferrous metals and non-metallic materials.




MG 2 30° ±0.01 PLAIN P.1105

for GRAPHITE
◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.01)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
99558	R1.0	2.0	.0787	4	10	20	80	1.95
99559	R1.5	3.0	.1181	4	15	25	80	2.9
99560	R2.0	4.0	.1575	4	20	30	80	3.9
99561	R2.5	5.0	.1969	6	30	50	100	4.9
99562	R3.0	6.0	.2362	6	30	50	100	5.5
99563	R4.0	8.0	.3150	8	40	60	110	7.5
99564	R5.0	10.0	.3937	10	50	70	120	9.5
99565	R6.0	12.0	.4724	12	55	75	130	11.5

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6



◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
								◎	○				

YG D-POWER GRAPHITE END MILLS

EI450 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG REACH BALL NOSE

- ▶ Higher hardness of film and excellent wear-resistance increase the tool life dramatically.
- ▶ Ultra fine film of YG-1's diamond coated carbide ball end mills ensure the smooth and excellent surface on work materials.
- ▶ High performance on graphite, wrought aluminum, bakelite, plastics, wood, brass, etc.
- ▶ YG-1's diamond coated carbide ball end mills may have good result for the machining of non-ferrous metals and non-metallic materials.




MG 2 30° ±0.01 PLAIN P.1105

for GRAPHITE
◇ Call for Availability

Unit : mm

EDP No.	Radius of Ball Nose R (±0.01)	Mill Diameter		Shank Diameter D2	Length of Cut L1	Length Below Shank L3	Overall Length L2	Neck Diameter D3
		Metric D1	Inch					
99566	R1.0	2.0	.0787	4	10	20	100	1.95
99567	R1.5	3.0	.1181	4	15	25	100	2.9
99568	R2.0	4.0	.1575	4	20	30	100	3.9
99569	R2.5	5.0	.1969	6	30	50	120	4.9
99570	R3.0	6.0	.2362	6	30	50	150	5.5
99571	R4.0	8.0	.3150	8	40	60	150	7.5

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6



◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
								◎	○				

YG D-POWER GRAPHITE END MILLS


RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE BALL NOSE

EI106 SERIES

MATERIAL	N	
	GRAPHITE	
DIAMETER	RPM	FEED
5/64	16000	63.0
3/32	16000	88.2
1/8	16000	114.2
9/64	16000	137.8
5/32	16000	165.4
3/16	15500	200.8
1/4	15000	232.3
5/16	13000	236.2
3/8	11500	324.2
1/2	10500	248.0

RPM = rev./min.
FEED = inch/min.




RPM = rev./min.
FEED = inch/min.

CARBIDE, 4 FLUTE BALL NOSE with NECK

EIB07 SERIES

MATERIAL	N	
	GRAPHITE	
DIAMETER	RPM	FEED
1/32	20000	37.9
3/64	20000	42.5
1/16	20000	51.7
5/64	16000	56.7
3/32	16000	79.4
1/8	16000	101.8
9/64	16000	124.7
5/32	16000	147.4
3/16	15500	182.0
1/4	15000	210.5
5/16	13000	211.5
3/8	11500	216.8
1/2	10500	224.7



RPM = rev./min.
FEED = inch/min.


YG D-POWER GRAPHITE END MILLS

RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE CORNER RADIUS with NECK

EIB06 SERIES

MATERIAL	N	
	GRAPHITE	
DIAMETER	RPM	FEED
1/32	40000	44.1
3/64	40000	66.1
1/16	40000	88.2
5/64	40000	110.2
1/8	40000	154.3
5/32	40000	220.5
3/16	40000	264.6
1/4	40000	308.7
5/16	32000	308.7
3/8	26000	316.1
1/2	21000	301.4




RPM = rev./min.
FEED = inch/min.

CARBIDE, 3 FLUTE BALL NOSE

EI881 SERIES

MATERIAL	N	
	GRAPHITE	
DIAMETER	RPM	FEED
2.0	16000	47.2
2.5	16000	66.9
3.0	16000	84.7
3.5	16000	104.3
4.0	16000	122.1
5.0	15500	149.6
6.0	15000	175.2
8.0	13000	177.2
10.0	11500	181.1
12.0	10500	187.0




RPM = rev./min.
FEED = inch/min.

CARBIDE, 2 FLUTE BALL NOSE

EI880, EI451, EI450 SERIES

MATERIAL	N	
	GRAPHITE	
DIAMETER	RPM	FEED
2.0	16000	31.5
2.5	16000	44.1
3.0	16000	57.1
3.5	16000	68.9
4.0	16000	82.7
5.0	15500	100.4
6.0	15000	116.1
8.0	13000	118.1
10.0	11500	120.1
12.0	10500	124.0




RPM = rev./min.
FEED = inch/min.

CARBIDE, 4 FLUTE

EI107 SERIES

MATERIAL	N	
	GRAPHITE	
DIAMETER	RPM	FEED
1/64	40000	31.5
1/8	40000	63.0
3/16	40000	126.0
1/4	40000	189.0
5/16	32000	196.9
3/8	26000	204.7
1/2	20000	189.0



RPM = rev./min.
FEED = inch/min.



Being the best through innovation

CARBIDE




D-POWER CFRP END MILLS



- For composite materials including CFRP, GFRP



Global Cutting Tool Leader **YG-1**



SELECTION GUIDE

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
GUG82		CARBIDE, MULTI FLUTE DUAL HELIX	D1/4	D1/2	1110
GUG83		CARBIDE, 4 FLUTE	D1/4	D1/2	1111
RECOMMENDED CUTTING CONDITIONS					1112

SOLID CARBIDE D-POWER CFRP END MILLS

◎ : Excellent ○ : Good


P					H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
									○			◎		
									○			◎		



GUG82 SERIES PLAIN SHANK

CARBIDE, MULTI FLUTE DUAL HELIX

- ▶ For composite materials - CFRP, GFRP.
- ▶ Reduce delamination and burrs.
- ▶ Diamond coating with excellent abrasion resistance



MG 4-8 20°/20° PLAIN P.1112 for CFRP

Unit : Inch

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
	R	D1	D2	L1(l)	L2	
GUG82016	R.020	1/4	1/4	1/2(1/8)	2-1/2	4
GUG82024	R.020	3/8	3/8	3/4(3/16)	3	6
GUG82032	R.020	1/2	1/2	1(1/4)	3-1/2	8

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-.0012	h6

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
												◎		



GUG83 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE

- ▶ For composite materials - CFRP, GFRP.
- ▶ Reduce delamination and burrs.
- ▶ Diamond coating with excellent abrasion resistance



MG 4 15° PLAIN P.1112 for CFRP

Unit : Inch

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
	R	D1	D2	L1(l)	L2	
GUG83016	R.010	1/4	1/4	3/4	2-1/2	4
GUG83024	R.015	3/8	3/8	1-1/4	3-1/4	4
GUG83032	R.015	1/2	1/2	1-1/2	4	4

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0~-.0012	h6

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
												◎		

CARBIDE

HSS

CBN
END MILLS

i-Xmill
END MILLS

i-SMART
MODULAR
TYPE END MILLS

X5070
END MILLS

4G MILL
END MILLS

X-POWER
END MILLS

JET-POWER
END MILLS

TitaNox
-POWER
END MILLS

V7 PLUS A
END MILLS

V7 MILL INOX
END MILLS

ALU-POWER
HPC
END MILLS

ALU-POWER
END MILLS

D-POWER
GRAPHITE
END MILLS

D-POWER
CFRP
END MILLS

ROUTERS
CFRP

STANDARD
CARBIDE
END MILLS

ONLY ONE
COATED PM60
END MILLS

SINE -POWER
END MILLS

TANK-POWER
END MILLS

STANDARD
COBALT & HSS
END MILLS

TECHNICAL
DATA



YG D-POWER CFRP END MILLS

RECOMMENDED CUTTING CONDITIONS

CARBIDE, MULTI FLUTE DUAL HELIX

GUG82 SERIES

MATERIAL	N							
	CFRP		GFRP		CFRP		GFRP	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	7520	41.45	4010	15.79	10026	74.21	5013	27.63
3/8	5013	65.13	2674	23.37	6684	121.58	3342	35.53
1/2	3760	76.97	2005	27.16	5013	145.26	2507	39.47





RPM = rev./min.
FEED = inch/min.

CARBIDE, 4 FLUTE

GUG83 SERIES

MATERIAL	N							
	CFRP		GFRP		CFRP		GFRP	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	10026	55.26	5013	19.74	10026	44.21	5013	19.74
3/8	6684	57.89	3342	19.47	6684	46.32	3342	16.84
1/2	5013	51.32	2507	16.97	5013	41.05	2507	13.82



RPM = rev./min.
FEED = inch/min.



Being the best through innovation

CARBIDE

ROUTERS CFRP


- For composite materials including CFRP, GFRP



SELECTION GUIDE

SOLID CARBIDE ROUTERS CFRP

◎ : Excellent ○ : Good

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
RT1105		CARBIDE, ROUTER END MILL TYPE	D1/4	D1/2	1116
		RECOMMENDED CUTTING CONDITIONS			


P					H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
												◎		



RTI105 SERIES PLAIN SHANK

CARBIDE, ROUTER END MILL TYPE


- ▶ For composite materials - CFRP, GFRP.
- ▶ Reduce delamination and burrs.
- ▶ Diamond coating with excellent abrasion resistance



Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
	D1	D2	L1	L2
RTI105016	1/4	1/4	3/4	2-1/4
RTI105024	3/8	3/8	1-1/4	3-1/2
RTI105032	1/2	1/2	1-1/2	4

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
-.0008~-.003	h6




RECOMMENDED CUTTING CONDITIONS

CARBIDE, ROUTER END MILL TYPE

RTI105 SERIES

MATERIAL	N					
	CFRP			GFRP		
DIAMETER	RPM	FEED	SFM	RPM	FEED	SFM
1/4	10030	82.78	656	5010	41.34	328
3/8	6680	126.20	656	3340	63.10	328
1/2	5010	126.24	656	2510	63.12	329



RPM = rev./min.
FEED = inch/min.
SFM = ft/min.



Being the best through innovation

CARBIDE




**STANDARD CARBIDE
END MILLS**

- General Purpose



Global Cutting Tool Leader **YG-1**





UGMF90 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE REGULAR LENGTH

- ▶ These are designed for slotting, drilling, pocketing and general operation.
- ▶ Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
Y-COATED				
UGMF90008	1/8	1/8	1/2	1-1/2
UGMF90012	3/16	3/16	5/8	2
UGMF90016	1/4	1/4	3/4	2-1/2
UGMF90024	3/8	3/8	1	2-1/2
UGMF90032	1/2	1/2	1	3
UGMF90040	5/8	5/8	1-1/4	3-1/2
UGMF90048	3/4	3/4	1-1/2	4
UGMF90064	1	1	1-1/2	4

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.012	0~-0.005

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○				○	○						○	



E5020 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE REGULAR LENGTH

- ▶ These are designed for slotting, drilling, pocketing and general operation.
- ▶ Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E				
01552	01552TN	01552TC	01552TF	01552TE	1/32	1/8	5/64	1-1/2
01553	01553TN	01553TC	01553TF	01553TE	3/64	1/8	7/64	1-1/2
01554	01554TN	01554TC	01554TF	01554TE	1/16	1/8	3/16	1-1/2
01555	01555TN	01555TC	01555TF	01555TE	5/64	1/8	3/16	1-1/2
01556	01556TN	01556TC	01556TF	01556TE	3/32	1/8	3/8	1-1/2
01557	01557TN	01557TC	01557TF	01557TE	7/64	1/8	3/8	1-1/2
01558	01558TN	01558TC	01558TF	01558TE	1/8	1/8	1/2	1-1/2
01560	01560TN	01560TC	01560TF	01560TE	9/64	3/16	1/2	2
01562	01562TN	01562TC	01562TF	01562TE	5/32	3/16	9/16	2
01564	01564TN	01564TC	01564TF	01564TE	11/64	3/16	5/8	2
01565	01565TN	01565TC	01565TF	01565TE	3/16	3/16	5/8	2
01569	01569TN	01569TC	01569TF	01569TE	13/64	1/4	5/8	2-1/2
01570	01570TN	01570TC	01570TF	01570TE	7/32	1/4	5/8	2-1/2
01572	01572TN	01572TC	01572TF	01572TE	15/64	1/4	3/4	2-1/2
01573	01573TN	01573TC	01573TF	01573TE	1/4	1/4	3/4	2-1/2
01579	01579TN	01579TC	01579TF	01579TE	5/16	5/16	13/16	2-1/2
01584	01584TN	01584TC	01584TF	01584TE	3/8	3/8	1	2-1/2
01588	01588TN	01588TC	01588TF	01588TE	7/16	7/16	1	2-3/4
01593	01593TN	01593TC	01593TF	01593TE	1/2	1/2	1	3
01595	01595TN	01595TC	01595TF	01595TE	5/8	5/8	1-1/4	3-1/2
01598	01598TN	01598TC	01598TF	01598TE	3/4	3/4	1-1/2	4
01600	01600TN	01600TC	01600TF	01600TE	1	1	1-1/2	4

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.012	0~-0.005

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎				○	○	○					○	



UGMF89 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE REGULAR LENGTH

- ▶ These are designed for slotting, drilling, pocketing and general operation.
- ▶ Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
Y-COATED				
UGMF89004	1/16	1/8	3/16	1-1/2
UGMF89005	5/64	1/8	3/16	1-1/2
UGMF89006	3/32	1/8	3/8	1-1/2
UGMF89007	7/64	1/8	3/8	1-1/2
UGMF89008	1/8	1/8	1/2	1-1/2
UGMF89009	9/64	3/16	1/2	2
UGMF89010	5/32	3/16	9/16	2
UGMF89011	11/64	3/16	5/8	2
UGMF89012	3/16	3/16	5/8	2
UGMF89013	13/64	1/4	5/8	2-1/2
UGMF89014	7/32	1/4	5/8	2-1/2
UGMF89015	15/64	1/4	3/4	2-1/2
UGMF89016	1/4	1/4	3/4	2-1/2
UGMF89018	9/32	5/16	3/4	2-1/2
UGMF89020	5/16	5/16	13/16	2-1/2
UGMF89024	3/8	3/8	1	2-1/2
UGMF89028	7/16	7/16	1	2-3/4
UGMF89032	1/2	1/2	1	3
UGMF89036	9/16	9/16	1-1/4	3-1/2
UGMF89040	5/8	5/8	1-1/4	3-1/2
UGMF89048	3/4	3/4	1-1/2	4
UGMF89056	7/8	7/8	1-1/2	4
UGMF89064	1	1	1-1/2	4

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.0012	0~-0.0005

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○			○	○						○	



E5021 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE REGULAR LENGTH

- ▶ Possible for high-speed cutting, suitable for high efficiency machining for hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E				
07554	07554TN	07554TC	07554TF	07554TE	1/16	1/8	3/16	1-1/2
07555	07555TN	07555TC	07555TF	07555TE	5/64	1/8	3/16	1-1/2
07556	07556TN	07556TC	07556TF	07556TE	3/32	1/8	3/8	1-1/2
07557	07557TN	07557TC	07557TF	07557TE	7/64	1/8	3/8	1-1/2
07558	07558TN	07558TC	07558TF	07558TE	1/8	1/8	1/2	1-1/2
07560	07560TN	07560TC	07560TF	07560TE	9/64	3/16	1/2	2
07561	07561TN	07561TC	07561TF	07561TE	5/32	3/16	9/16	2
07564	07564TN	07564TC	07564TF	07564TE	11/64	3/16	5/8	2
07565	07565TN	07565TC	07565TF	07565TE	3/16	3/16	5/8	2
07569	07569TN	07569TC	07569TF	07569TE	13/64	1/4	5/8	2-1/2
07570	07570TN	07570TC	07570TF	07570TE	7/32	1/4	5/8	2-1/2
07572	07572TN	07572TC	07572TF	07572TE	15/64	1/4	3/4	2-1/2
07573	07573TN	07573TC	07573TF	07573TE	1/4	1/4	3/4	2-1/2
07576	07576TN	07576TC	07576TF	07576TE	9/32	5/16	3/4	2-1/2
07579	07579TN	07579TC	07579TF	07579TE	5/16	5/16	13/16	2-1/2
07584	07584TN	07584TC	07584TF	07584TE	3/8	3/8	1	2-1/2
07588	07588TN	07588TC	07588TF	07588TE	7/16	7/16	1	2-3/4
07593	07593TN	07593TC	07593TF	07593TE	1/2	1/2	1	3
07595	07595TN	07595TC	07595TF	07595TE	5/8	5/8	1-1/4	3-1/2
07598	07598TN	07598TC	07598TF	07598TE	3/4	3/4	1-1/2	4
07600	07600TN	07600TC	07600TF	07600TE	1	1	1-1/2	4

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.0012	0~-0.0005

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎			○	○	○	○	○			○	



E5244 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE STUB LENGTH

► Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E				
30554	30554TN	30554TC	30554TF	30554TE	1/16	1/8	1/8	1-1/2
30556	30556TN	30556TC	30556TF	30556TE	3/32	1/8	3/16	1-1/2
30558	30558TN	30558TC	30558TF	30558TE	1/8	1/8	1/4	1-1/2
30561	30561TN	30561TC	30561TF	30561TE	5/32	3/16	5/16	2
30565	30565TN	30565TC	30565TF	30565TE	3/16	3/16	3/8	2
30570	30570TN	30570TC	30570TF	30570TE	7/32	1/4	7/16	2
30573	30573TN	30573TC	30573TF	30573TE	1/4	1/4	1/2	2
30579	30579TN	30579TC	30579TF	30579TE	5/16	5/16	1/2	2
30584	30584TN	30584TC	30584TF	30584TE	3/8	3/8	5/8	2
30588	30588TN	30588TC	30588TF	30588TE	7/16	7/16	5/8	2-1/2
30593	30593TN	30593TC	30593TF	30593TE	1/2	1/2	5/8	2-1/2
30595	30595TN	30595TC	30595TF	30595TE	5/8	5/8	3/4	3
30598	30598TN	30598TC	30598TF	30598TE	3/4	3/4	1	3

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	0~-.0005

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎				○	○	○		○				



UGMGF57 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE STUB LENGTH

► Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
Y-COATED				
UGMGF57004	1/16	1/8	1/8	1-1/2
UGMGF57006	3/32	1/8	3/16	1-1/2
UGMGF57008	1/8	1/8	1/4	1-1/2
UGMGF57010	5/32	3/16	5/16	2
UGMGF57012	3/16	3/16	3/8	2
UGMGF57014	7/32	1/4	7/16	2
UGMGF57016	1/4	1/4	1/2	2
UGMGF57020	5/16	5/16	1/2	2
UGMGF57024	3/8	3/8	5/8	2
UGMGF57028	7/16	7/16	5/8	2-1/2
UGMGF57032	1/2	1/2	5/8	2-1/2
UGMGF57040	5/8	5/8	3/4	3
UGMGF57048	3/4	3/4	1	3

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	0~-.0005

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎				○	○	○		○				



E5245 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE STUB LENGTH

► Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E				
31554	31554TN	31554TC	31554TF	31554TE	1/16	1/8	1/8	1-1/2
31556	31556TN	31556TC	31556TF	31556TE	3/32	1/8	3/16	1-1/2
31558	31558TN	31558TC	31558TF	31558TE	1/8	1/8	1/4	1-1/2
31561	31561TN	31561TC	31561TF	31561TE	5/32	3/16	5/16	2
31565	31565TN	31565TC	31565TF	31565TE	3/16	3/16	3/8	2
31570	31570TN	31570TC	31570TF	31570TE	7/32	1/4	7/16	2
31573	31573TN	31573TC	31573TF	31573TE	1/4	1/4	1/2	2
31579	31579TN	31579TC	31579TF	31579TE	5/16	5/16	1/2	2
31584	31584TN	31584TC	31584TF	31584TE	3/8	3/8	5/8	2
31588	31588TN	31588TC	31588TF	31588TE	7/16	7/16	5/8	2-1/2
31593	31593TN	31593TC	31593TF	31593TE	1/2	1/2	5/8	2-1/2
31595	31595TN	31595TC	31595TF	31595TE	5/8	5/8	3/4	3
31598	31598TN	31598TC	31598TF	31598TE	3/4	3/4	1	3

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	0~-.0005

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎				○	○	○					○	



E5011 SERIES PLAIN SHANK
E5012 SERIES PLAIN SHANK

CARBIDE, 2&4 FLUTE LONG LENGTH

► Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

E5011(2 FLUTE) Series

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E				
02558	02558TN	02558TC	02558TF	02558TE	1/8	1/8	3/4	2-1/4
02565	02565TN	02565TC	02565TF	02565TE	3/16	3/16	3/4	2-1/2
02573	02573TN	02573TC	02573TF	02573TE	1/4	1/4	1-1/8	3
02579	02579TN	02579TC	02579TF	02579TE	5/16	5/16	1-1/8	3
02584	02584TN	02584TC	02584TF	02584TE	3/8	3/8	1-1/8	3
02588	02588TN	02588TC	02588TF	02588TE	7/16	7/16	2	4
02593	02593TN	02593TC	02593TF	02593TE	1/2	1/2	2	4
02595	02595TN	02595TC	02595TF	02595TE	5/8	5/8	2-1/4	5
02598	02598TN	02598TC	02598TF	02598TE	3/4	3/4	2-1/4	5
02600	02600TN	02600TC	02600TF	02600TE	1	1	2-1/4	5

Unit : Inch

E5012(4 FLUTE) Series

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E				
08558	08558TN	08558TC	08558TF	08558TE	1/8	1/8	3/4	2-1/4
08565	08565TN	08565TC	08565TF	08565TE	3/16	3/16	3/4	2-1/2
08573	08573TN	08573TC	08573TF	08573TE	1/4	1/4	1-1/8	3
08579	08579TN	08579TC	08579TF	08579TE	5/16	5/16	1-1/8	3
08584	08584TN	08584TC	08584TF	08584TE	3/8	3/8	1-1/8	3
08588	08588TN	08588TC	08588TF	08588TE	7/16	7/16	2	4
08593	08593TN	08593TC	08593TF	08593TE	1/2	1/2	2	4
08595	08595TN	08595TC	08595TF	08595TE	5/8	5/8	2-1/4	5
08598	08598TN	08598TC	08598TF	08598TE	3/4	3/4	2-1/4	5
08600	08600TN	08600TC	08600TF	08600TE	1	1	2-1/4	5

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	0~-.0005

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎				○	○	○					○	



UGMGF58 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG LENGTH

► Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
Y-COATED				
UGMGF58008	1/8	1/8	3/4	2-1/4
UGMGF58012	3/16	3/16	3/4	2-1/2
UGMGF58016	1/4	1/4	1-1/8	3
UGMGF58020	5/16	5/16	1-1/8	3
UGMGF58024	3/8	3/8	1-1/8	3
UGMGF58028	7/16	7/16	2	4
UGMGF58032	1/2	1/2	2	4
UGMGF58040	5/8	5/8	2-1/4	5
UGMGF58048	3/4	3/4	2-1/4	5
UGMGF58064	1	1	2-1/4	5

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	0~-.0005

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎			○	○	○		○				



E5026 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE EXTRA LONG LENGTH

► Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E				
54558	54558TN	54558TC	54558TF	54558TE	1/8	1/8	1	3
54565	54565TN	54565TC	54565TF	54565TE	3/16	3/16	1-1/8	3
54904	54904TN	54904TC	54904TF	54904TE	3/16	3/16	1	4
54573	54573TN	54573TC	54573TF	54573TE	1/4	1/4	1-1/2	4
54901	54901TN	54901TC	54901TF	54901TE	1/4	1/4	1-1/2	6
54579	54579TN	54579TC	54579TF	54579TE	5/16	5/16	1-5/8	4
54584	54584TN	54584TC	54584TF	54584TE	3/8	3/8	1-3/4	4
54902	54902TN	54902TC	54902TF	54902TE	3/8	3/8	1-1/2	6
54588	54588TN	54588TC	54588TF	54588TE	7/16	7/16	3	6
54903	54903TN	54903TC	54903TF	54903TE	1/2	1/2	1-1/2	6
54593	54593TN	54593TC	54593TF	54593TE	1/2	1/2	3	6
54595	54595TN	54595TC	54595TF	54595TE	5/8	5/8	3	6
54598	54598TN	54598TC	54598TF	54598TE	3/4	3/4	3	6
54600	54600TN	54600TC	54600TF	54600TE	1	1	3	6

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	0~-.0005

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎			○	○	○		○				



UGMGF59 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE EXTRA LONG LENGTH

► Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
Y-COATED				
UGMGF59008	1/8	1/8	1	3
UGMGF59012	3/16	3/16	1-1/8	3
UGMGF59016	1/4	1/4	1-1/2	4
UGMGF59020	5/16	5/16	1-5/8	4
UGMGF59024	3/8	3/8	1-3/4	4
UGMGF59028	7/16	7/16	3	6
UGMGF59032	1/2	1/2	3	6
UGMGF59040	5/8	5/8	3	6
UGMGF59048	3/4	3/4	3	6
UGMGF59064	1	1	3	6
UGMGF59901	1/4	1/4	1-1/2	6
UGMGF59902	3/8	3/8	1-1/2	6
UGMGF59903	1/2	1/2	1-1/2	6
UGMGF59904	3/16	3/16	1	4

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.012	0~-0.005

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎				○	○	○		○				



E5065 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE EXTRA LONG LENGTH

► Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E				
55558	55558TN	55558TC	55558TF	55558TE	1/8	1/8	1	3
55565	55565TN	55565TC	55565TF	55565TE	3/16	3/16	1-1/8	3
55904	55904TN	55904TC	55904TF	55904TE	3/16	3/16	1	4
55573	55573TN	55573TC	55573TF	55573TE	1/4	1/4	1-1/2	4
55901	55901TN	55901TC	55901TF	55901TE	1/4	1/4	1-1/2	6
55579	55579TN	55579TC	55579TF	55579TE	5/16	5/16	1-5/8	4
55584	55584TN	55584TC	55584TF	55584TE	3/8	3/8	1-3/4	4
55902	55902TN	55902TC	55902TF	55902TE	3/8	3/8	1-1/2	6
55588	55588TN	55588TC	55588TF	55588TE	7/16	7/16	3	6
55903	55903TN	55903TC	55903TF	55903TE	1/2	1/2	1-1/2	6
55593	55593TN	55593TC	55593TF	55593TE	1/2	1/2	3	6
55595	55595TN	55595TC	55595TF	55595TE	5/8	5/8	3	6
55598	55598TN	55598TC	55598TF	55598TE	3/4	3/4	3	6
55600	55600TN	55600TC	55600TF	55600TE	1	1	3	6

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.012	0~-0.005

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎				○	○	○		○				



E5022 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE STUB LENGTH DOUBLE

- ▶ Same construction features as 2&4 flute single end mill in a more economical version.
- ▶ Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E				
32552	32552TN	32552TC	32552TF	32552TE	1/32	1/8	1/16	1-1/2
32553	32553TN	32553TC	32553TF	32553TE	3/64	1/8	3/32	1-1/2
32554	32554TN	32554TC	32554TF	32554TE	1/16	1/8	1/8	1-1/2
32555	32555TN	32555TC	32555TF	32555TE	5/64	1/8	1/8	1-1/2
32556	32556TN	32556TC	32556TF	32556TE	3/32	1/8	3/16	1-1/2
32557	32557TN	32557TC	32557TF	32557TE	7/64	1/8	3/16	1-1/2
32558	32558TN	32558TC	32558TF	32558TE	1/8	1/8	1/4	1-1/2
32560	32560TN	32560TC	32560TF	32560TE	9/64	3/16	5/16	2
32562	32562TN	32562TC	32562TF	32562TE	5/32	3/16	5/16	2
32564	32564TN	32564TC	32564TF	32564TE	11/64	3/16	5/16	2
32565	32565TN	32565TC	32565TF	32565TE	3/16	3/16	3/8	2
32569	32569TN	32569TC	32569TF	32569TE	13/64	1/4	1/2	2-1/2
32570	32570TN	32570TC	32570TF	32570TE	7/32	1/4	1/2	2-1/2
32572	32572TN	32572TC	32572TF	32572TE	15/64	1/4	1/2	2-1/2
32573	32573TN	32573TC	32573TF	32573TE	1/4	1/4	1/2	2-1/2
32579	32579TN	32579TC	32579TF	32579TE	5/16	5/16	1/2	2-1/2
32584	32584TN	32584TC	32584TF	32584TE	3/8	3/8	9/16	2-1/2
32588	32588TN	32588TC	32588TF	32588TE	7/16	7/16	9/16	2-3/4
32593	32593TN	32593TC	32593TF	32593TE	1/2	1/2	5/8	3

Mill Dia. Tolerance (inch)	
0~-.0012	** 0~-.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎			○	○	○		○				



E5023 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE STUB LENGTH DOUBLE

- ▶ Same construction features as 2&4 flute single end mill in a more economical version.
- ▶ Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E				
33554	33554TN	33554TC	33554TF	33554TE	1/16	1/8	1/8	1-1/2
33555	33555TN	33555TC	33555TF	33555TE	5/64	1/8	1/8	1-1/2
33556	33556TN	33556TC	33556TF	33556TE	3/32	1/8	3/16	1-1/2
33557	33557TN	33557TC	33557TF	33557TE	7/64	1/8	3/16	1-1/2
33558	33558TN	33558TC	33558TF	33558TE	1/8	1/8	1/4	1-1/2
33560	33560TN	33560TC	33560TF	33560TE	9/64	3/16	5/16	2
33561	33561TN	33561TC	33561TF	33561TE	5/32	3/16	5/16	2
33564	33564TN	33564TC	33564TF	33564TE	11/64	3/16	5/16	2
33565	33565TN	33565TC	33565TF	33565TE	3/16	3/16	3/8	2
33569	33569TN	33569TC	33569TF	33569TE	13/64	1/4	1/2	2-1/2
33570	33570TN	33570TC	33570TF	33570TE	7/32	1/4	1/2	2-1/2
33572	33572TN	33572TC	33572TF	33572TE	15/64	1/4	1/2	2-1/2
33573	33573TN	33573TC	33573TF	33573TE	1/4	1/4	1/2	2-1/2
33579	33579TN	33579TC	33579TF	33579TE	5/16	5/16	1/2	2-1/2
33584	33584TN	33584TC	33584TF	33584TE	3/8	3/8	9/16	2-1/2
33588	33588TN	33588TC	33588TF	33588TE	7/16	7/16	9/16	2-3/4
33593	33593TN	33593TC	33593TF	33593TE	1/2	1/2	5/8	3

Mill Dia. Tolerance (inch)	
0~-.0012	** 0~-.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎			○	○	○		○				



E5025 SERIES FLAT SHANK

E5024 SERIES FLAT SHANK

CARBIDE, 2&4 FLUTE REGULAR LENGTH DOUBLE

- ▶ Same construction features as single end mill in a more economical version.
- ▶ Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



E5025(2 FLUTE) Series

Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E				
11559	11559TN	11559TC	11559TF	11559TE	1/8	3/8	3/8	3-1/16
11563	11563TN	11563TC	11563TF	11563TE	5/32	3/8	7/16	3-1/8
11567	11567TN	11567TC	11567TF	11567TE	3/16	3/8	1/2	3-1/4
11571	11571TN	11571TC	11571TF	11571TE	7/32	3/8	9/16	3-3/8
11574	11574TN	11574TC	11574TF	11574TE	1/4	3/8	5/8	3-3/8
11577	11577TN	11577TC	11577TF	11577TE	9/32	3/8	11/16	3-3/8
11580	11580TN	11580TC	11580TF	11580TE	5/16	3/8	3/4	3-1/2
11582	11582TN	11582TC	11582TF	11582TE	11/32	3/8	3/4	3-1/2
11584	11584TN	11584TC	11584TF	11584TE	3/8	3/8	3/4	3-1/2
11589	11589TN	11589TC	11589TF	11589TE	7/16	1/2	7/8	4
11593	11593TN	11593TC	11593TF	11593TE	1/2	1/2	1	4

E5024(4 FLUTE) Series

Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E				
13559	13559TN	13559TC	13559TF	13559TE	1/8	3/8	3/8	3-1/16
13563	13563TN	13563TC	13563TF	13563TE	5/32	3/8	7/16	3-1/8
13567	13567TN	13567TC	13567TF	13567TE	3/16	3/8	1/2	3-1/4
13571	13571TN	13571TC	13571TF	13571TE	7/32	3/8	9/16	3-3/8
13574	13574TN	13574TC	13574TF	13574TE	1/4	3/8	5/8	3-3/8
13577	13577TN	13577TC	13577TF	13577TE	9/32	3/8	11/16	3-3/8
13580	13580TN	13580TC	13580TF	13580TE	5/16	3/8	3/4	3-1/2
13582	13582TN	13582TC	13582TF	13582TE	11/32	3/8	3/4	3-1/2
13584	13584TN	13584TC	13584TF	13584TE	3/8	3/8	3/4	3-1/2
13589	13589TN	13589TC	13589TF	13589TE	7/16	1/2	7/8	4
13593	13593TN	13593TC	13593TF	13593TE	1/2	1/2	1	4

Mill Dia. Tolerance (inch)	
0~- .0012	** 0~- .0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎			○	○	○		○				



E5249 SERIES PLAIN SHANK

E5250 SERIES PLAIN SHANK

CARBIDE, 2&4 FLUTE REGULAR LENGTH BALL NOSE

- ▶ Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



E5249(2 FLUTE) Series

Unit : Inch

EDP No.					Radius of Ball Nose R (±.0008)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E					
41558	41558TN	41558TC	41558TF	41558TE	R1/16	1/8	1/8	1/2	1-1/2
41561	41561TN	41561TC	41561TF	41561TE	R5/64	5/32	3/16	9/16	2
41565	41565TN	41565TC	41565TF	41565TE	R3/32	3/16	3/16	5/8	2
41570	41570TN	41570TC	41570TF	41570TE	R7/64	7/32	1/4	5/8	2-1/2
41573	41573TN	41573TC	41573TF	41573TE	R1/8	1/4	1/4	3/4	2-1/2
41579	41579TN	41579TC	41579TF	41579TE	R5/32	5/16	5/16	13/16	2-1/2
41584	41584TN	41584TC	41584TF	41584TE	R3/16	3/8	3/8	1	2-1/2
41588	41588TN	41588TC	41588TF	41588TE	R7/32	7/16	7/16	1	2-3/4
41593	41593TN	41593TC	41593TF	41593TE	R1/4	1/2	1/2	1	3
41595	41595TN	41595TC	41595TF	41595TE	R5/16	5/8	5/8	1-1/4	3-1/2
41598	41598TN	41598TC	41598TF	41598TE	R3/8	3/4	3/4	1-1/2	4
41600	41600TN	41600TC	41600TF	41600TE	R1/2	1	1	1-1/2	4

E5250(4 FLUTE) Series

Unit : Inch

EDP No.					Radius of Ball Nose R (±.0008)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E					
43558	43558TN	43558TC	43558TF	43558TE	R1/16	1/8	1/8	1/2	1-1/2
43561	43561TN	43561TC	43561TF	43561TE	R5/64	5/32	3/16	9/16	2
43565	43565TN	43565TC	43565TF	43565TE	R3/32	3/16	3/16	5/8	2
43570	43570TN	43570TC	43570TF	43570TE	R7/64	7/32	1/4	5/8	2-1/2
43573	43573TN	43573TC	43573TF	43573TE	R1/8	1/4	1/4	3/4	2-1/2
43579	43579TN	43579TC	43579TF	43579TE	R5/32	5/16	5/16	13/16	2-1/2
43584	43584TN	43584TC	43584TF	43584TE	R3/16	3/8	3/8	1	2-1/2
43588	43588TN	43588TC	43588TF	43588TE	R7/32	7/16	7/16	1	2-3/4
43593	43593TN	43593TC	43593TF	43593TE	R1/4	1/2	1/2	1	3
43595	43595TN	43595TC	43595TF	43595TE	R5/16	5/8	5/8	1-1/4	3-1/2
43598	43598TN	43598TC	43598TF	43598TE	R3/8	3/4	3/4	1-1/2	4
43600	43600TN	43600TC	43600TF	43600TE	R1/2	1	1	1-1/2	4

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~- .0012	0~- .0005

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○				○	○		○			



UGMF91 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE REGULAR LENGTH

- ▶ These are designed for slotting, drilling, pocketing and general operation.
- ▶ Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

EDP No.	Radius of BallNose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
Y-COATED					
UGMF91008	1/16	1/8	1/8	1/2	1-1/2
UGMF91010	5/64	5/32	3/16	9/16	2
UGMF91012	3/32	3/16	3/16	5/8	2
UGMF91016	1/8	1/4	1/4	3/4	2-1/2
UGMF91020	5/32	5/16	5/16	13/16	2-1/2
UGMF91024	3/16	3/8	3/8	1	2-1/2
UGMF91028	7/32	7/16	7/16	1	2-3/4
UGMF91032	1/4	1/2	1/2	1	3
UGMF91040	5/16	5/8	5/8	1-1/4	3-1/2
UGMF91048	3/8	3/4	3/4	1-1/2	4
UGMF91064	1/2	1	1	1-1/2	4

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	0~-.0005

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○			○	○						○	



E5014 SERIES PLAIN SHANK
E5060 SERIES PLAIN SHANK

CARBIDE, 2&4 FLUTE LONG LENGTH BALL NOSE

- ▶ Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

E5014(2 FLUTE) Series

EDP No.					Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E	R (±.0008)				
50558	50558TN	50558TC	50558TF	50558TE	R1/16	1/8	1/8	3/4	2-1/4
50565	50565TN	50565TC	50565TF	50565TE	R3/32	3/16	3/16	3/4	2-1/2
50573	50573TN	50573TC	50573TF	50573TE	R1/8	1/4	1/4	1-1/8	3
50579	50579TN	50579TC	50579TF	50579TE	R5/32	5/16	5/16	1-1/8	3
50584	50584TN	50584TC	50584TF	50584TE	R3/16	3/8	3/8	1-1/8	3
50588	50588TN	50588TC	50588TF	50588TE	R7/32	7/16	7/16	2	4
50593	50593TN	50593TC	50593TF	50593TE	R1/4	1/2	1/2	2	4
50595	50595TN	50595TC	50595TF	50595TE	R5/16	5/8	5/8	2-1/4	5
50598	50598TN	50598TC	50598TF	50598TE	R3/8	3/4	3/4	2-1/4	5
50600	50600TN	50600TC	50600TF	50600TE	R1/2	1	1	2-1/4	5

E5060(4 FLUTE) Series

EDP No.					Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E	R (±.0008)				
51558	51558TN	51558TC	51558TF	51558TE	R1/16	1/8	1/8	3/4	2-1/4
51565	51565TN	51565TC	51565TF	51565TE	R3/32	3/16	3/16	3/4	2-1/2
51573	51573TN	51573TC	51573TF	51573TE	R1/8	1/4	1/4	1-1/8	3
51579	51579TN	51579TC	51579TF	51579TE	R5/32	5/16	5/16	1-1/8	3
51584	51584TN	51584TC	51584TF	51584TE	R3/16	3/8	3/8	1-1/8	3
51588	51588TN	51588TC	51588TF	51588TE	R7/32	7/16	7/16	2	4
51593	51593TN	51593TC	51593TF	51593TE	R1/4	1/2	1/2	2	4
51595	51595TN	51595TC	51595TF	51595TE	R5/16	5/8	5/8	2-1/4	5
51598	51598TN	51598TC	51598TF	51598TE	R3/8	3/4	3/4	2-1/4	5
51600	51600TN	51600TC	51600TF	51600TE	R1/2	1	1	2-1/4	5

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	0~-.0005

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○				○	○				○	



E5018 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE EXTRA LONG LENGTH BALL NOSE

► Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



MG 2 30° ±.0008 PLAIN P.1167

Unit : Inch

EDP No.					Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E	R (±.0008)				
52558	52558TN	52558TC	52558TF	52558TE	R1/16	1/8	1/8	1	3
52565	52565TN	52565TC	52565TF	52565TE	R3/32	3/16	3/16	1-1/8	3
52904	52904TN	52904TC	52904TF	52904TE	R3/32	3/16	3/16	1	4
52573	52573TN	52573TC	52573TF	52573TE	R1/8	1/4	1/4	1-1/2	4
52901	52901TN	52901TC	52901TF	52901TE	R1/8	1/4	1/4	1-1/2	6
52579	52579TN	52579TC	52579TF	52579TE	R5/32	5/16	5/16	1-5/8	4
52584	52584TN	52584TC	52584TF	52584TE	R3/16	3/8	3/8	1-3/4	4
52902	52902TN	52902TC	52902TF	52902TE	R3/16	3/8	3/8	1-1/2	6
52588	52588TN	52588TC	52588TF	52588TE	R7/32	7/16	7/16	3	6
52903	52903TN	52903TC	52903TF	52903TE	R1/4	1/2	1/2	1-1/2	6
52593	52593TN	52593TC	52593TF	52593TE	R1/4	1/2	1/2	3	6
52595	52595TN	52595TC	52595TF	52595TE	R5/16	5/8	5/8	3	6
52598	52598TN	52598TC	52598TF	52598TE	R3/8	3/4	3/4	3	6
52600	52600TN	52600TC	52600TF	52600TE	R1/2	1	1	3	6

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.012	0~-0.005

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○				○	○		○				



E5062 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE EXTRA LONG LENGTH BALL NOSE

► Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



MG 4 30° ±.0008 PLAIN P.1168

Unit : Inch

EDP No.					Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E	R (±.0008)				
53558	53558TN	53558TC	53558TF	53558TE	R1/16	1/8	1/8	1	3
53565	53565TN	53565TC	53565TF	53565TE	R3/32	3/16	3/16	1-1/8	3
53573	53573TN	53573TC	53573TF	53573TE	R1/8	1/4	1/4	1-1/2	4
53901	53901TN	53901TC	53901TF	53901TE	R1/8	1/4	1/4	1-1/2	6
53579	53579TN	53579TC	53579TF	53579TE	R5/32	5/16	5/16	1-5/8	4
53584	53584TN	53584TC	53584TF	53584TE	R3/16	3/8	3/8	1-3/4	4
53902	53902TN	53902TC	53902TF	53902TE	R3/16	3/8	3/8	1-1/2	6
53588	53588TN	53588TC	53588TF	53588TE	R7/32	7/16	7/16	3	6
53903	53903TN	53903TC	53903TF	53903TE	R1/4	1/2	1/2	1-1/2	6
53593	53593TN	53593TC	53593TF	53593TE	R1/4	1/2	1/2	3	6
53595	53595TN	53595TC	53595TF	53595TE	R5/16	5/8	5/8	3	6
53904	53904TN	53904TC	53904TF	53904TE	R5/16	5/8	5/8	1-1/2	6
53598	53598TN	53598TC	53598TF	53598TE	R3/8	3/4	3/4	3	6
53905	53905TN	53905TC	53905TF	53905TE	R3/8	3/4	3/4	1-1/2	6
53600	53600TN	53600TC	53600TF	53600TE	R1/2	1	1	3	6
53906	53906TN	53906TC	53906TF	53906TE	R1/2	1	1	1-1/2	6

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.012	0~-0.005

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○				○	○		○				



E5251 SERIES PLAIN SHANK
E5252 SERIES PLAIN SHANK

CARBIDE, 2&4 FLUTE STUB LENGTH DOUBLE BALL NOSE

- ▶ Same construction features as single end mill in a more economical version.
- ▶ Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



MG 2&4 30° ±.0008 PLAIN P.1167, 1168

E5251 Series ■ 2 FLUTE Unit : Inch

EDP No.					Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E	R (±.0008)				
47570	47570TN	47570TC	47570TF	47570TE	R7/64	7/32	1/4	1/2	2-1/2
47573	47573TN	47573TC	47573TF	47573TE	R1/8	1/4	1/4	1/2	2-1/2
47579	47579TN	47579TC	47579TF	47579TE	R5/32	5/16	5/16	1/2	2-1/2
47584	47584TN	47584TC	47584TF	47584TE	R3/16	3/8	3/8	9/16	2-1/2
47588	47588TN	47588TC	47588TF	47588TE	R7/32	7/16	7/16	9/16	2-3/4
47593	47593TN	47593TC	47593TF	47593TE	R1/4	1/2	1/2	5/8	3

E5252 Series ■ 4 FLUTE Unit : Inch

EDP No.					Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E	R (±.0008)				
48570	48570TN	48570TC	48570TF	48570TE	R7/64	7/32	1/4	1/2	2-1/2
48573	48573TN	48573TC	48573TF	48573TE	R1/8	1/4	1/4	1/2	2-1/2
48579	48579TN	48579TC	48579TF	48579TE	R5/32	5/16	5/16	1/2	2-1/2
48584	48584TN	48584TC	48584TF	48584TE	R3/16	3/8	3/8	9/16	2-1/2
48588	48588TN	48588TC	48588TF	48588TE	R7/32	7/16	7/16	9/16	2-3/4
48593	48593TN	48593TC	48593TF	48593TE	R1/4	1/2	1/2	5/8	3

Mill Dia. Tolerance (inch)	
0~-.0012	* * 0~-.0020

* * The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○				○	○		○				



E5216 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE REGULAR LENGTH CORNER RADIUS

- ▶ Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



MG 4 30° ±.001 PLAIN P.1166

Unit : Inch

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	YG:TYLON F	R				
07558-015R	07558TF-015R	R.015	1/8	1/8	1/2	1-1/2
07558-030R	07558TF-030R	R.030	1/8	1/8	1/2	1-1/2
07565-015R	07565TF-015R	R.015	3/16	3/16	5/8	2
07565-030R	07565TF-030R	R.030	3/16	3/16	5/8	2
07573-015R	07573TF-015R	R.015	1/4	1/4	3/4	2-1/2
07573-030R	07573TF-030R	R.030	1/4	1/4	3/4	2-1/2
07573-045R	07573TF-045R	R.045	1/4	1/4	3/4	2-1/2
07579-015R	07579TF-015R	R.015	5/16	5/16	13/16	2-1/2
07579-030R	07579TF-030R	R.030	5/16	5/16	13/16	2-1/2
07579-045R	07579TF-045R	R.045	5/16	5/16	13/16	2-1/2
07584-015R	07584TF-015R	R.015	3/8	3/8	1	2-1/2
07584-030R	07584TF-030R	R.030	3/8	3/8	1	2-1/2
07584-045R	07584TF-045R	R.045	3/8	3/8	1	2-1/2
07584-060R	07584TF-060R	R.060	3/8	3/8	1	2-1/2
07588-015R	07588TF-015R	R.015	7/16	7/16	1	2-3/4
07588-030R	07588TF-030R	R.030	7/16	7/16	1	2-3/4
07588-045R	07588TF-045R	R.045	7/16	7/16	1	2-3/4
07588-060R	07588TF-060R	R.060	7/16	7/16	1	2-3/4
07588-090R	07588TF-090R	R.090	7/16	7/16	1	2-3/4
07593-015R	07593TF-015R	R.015	1/2	1/2	1	3
07593-030R	07593TF-030R	R.030	1/2	1/2	1	3
07593-045R	07593TF-045R	R.045	1/2	1/2	1	3
07593-060R	07593TF-060R	R.060	1/2	1/2	1	3
07593-090R	07593TF-090R	R.090	1/2	1/2	1	3
07593-125R	07593TF-125R	R.125	1/2	1/2	1	3
07595-015R	07595TF-015R	R.015	5/8	5/8	1-1/4	3-1/2
07595-030R	07595TF-030R	R.030	5/8	5/8	1-1/4	3-1/2
07595-045R	07595TF-045R	R.045	5/8	5/8	1-1/4	3-1/2

▶ NEXT PAGE

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○				○	○	○			○		



E5216 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE REGULAR LENGTH CORNER RADIUS

► Suitable for cutting hardened & high alloy steels, steel casting, chill casting, malleable cast iron, CrNi-steels, brass, copper, aluminum with a high percentage of silicon and abrasive plastics.



Unit : Inch

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	YG:TYLON F	R				
07595-060R	07595TF-060R	R.060	5/8	5/8	1-1/4	3-1/2
07595-090R	07595TF-090R	R.090	5/8	5/8	1-1/4	3-1/2
07595-125R	07595TF-125R	R.125	5/8	5/8	1-1/4	3-1/2
07598-015R	07598TF-015R	R.015	3/4	3/4	1-1/2	4
07598-030R	07598TF-030R	R.030	3/4	3/4	1-1/2	4
07598-045R	07598TF-045R	R.045	3/4	3/4	1-1/2	4
07598-060R	07598TF-060R	R.060	3/4	3/4	1-1/2	4
07598-090R	07598TF-090R	R.090	3/4	3/4	1-1/2	4
07598-125R	07598TF-125R	R.125	3/4	3/4	1-1/2	4
07600-015R	07600TF-015R	R.015	1	1	1-1/2	4
07600-030R	07600TF-030R	R.030	1	1	1-1/2	4
07600-045R	07600TF-045R	R.045	1	1	1-1/2	4
07600-060R	07600TF-060R	R.060	1	1	1-1/2	4
07600-090R	07600TF-090R	R.090	1	1	1-1/2	4
07600-125R	07600TF-125R	R.125	1	1	1-1/2	4

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	0~-.0005

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○			○	○	○		○				



E5069 SERIES PLAIN SHANK

CARBIDE, 5 FLUTE 45° HELIX REGULAR LENGTH CORNER RADIUS

Designed to machine stainless steels, Inconols and other alloys. 5 Flute and 45° medium helix allow harmonic balance and smooth cutting.



Unit : Inch

EDP No.	Corner Radius R	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
86573TF-030R	R.030	1/4	1/4	3/4	2-1/2
86584TF-030R	R.030	3/8	3/8	1	2-1/2
86584TF-060R	R.060	3/8	3/8	1	2-1/2
86593TF-030R	R.030	1/2	1/2	1-1/4	3
86593TF-060R	R.060	1/2	1/2	1-1/4	3
86593TF-090R	R.090	1/2	1/2	1-1/4	3
86595TF-030R	R.030	5/8	5/8	1-5/8	3-1/2
86595TF-060R	R.060	5/8	5/8	1-5/8	3-1/2
86595TF-090R	R.090	5/8	5/8	1-5/8	3-1/2
86595TF-125R	R.125	5/8	5/8	1-5/8	3-1/2
86598TF-030R	R.030	3/4	3/4	1-5/8	4
86598TF-060R	R.060	3/4	3/4	1-5/8	4
86598TF-090R	R.090	3/4	3/4	1-5/8	4
86598TF-125R	R.125	3/4	3/4	1-5/8	4
86598TF-156R	R.156	3/4	3/4	1-5/8	4
86598TF-187R	R.187	3/4	3/4	1-5/8	4
86600TF-030R	R.030	1	1	2	4
86600TF-060R	R.060	1	1	2	4
86600TF-090R	R.090	1	1	2	4
86600TF-125R	R.125	1	1	2	4
86600TF-156R	R.156	1	1	2	4
86600TF-187R	R.187	1	1	2	4

Any non stocked radius available in 1 week for uncoated tools

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-.0012	0~-.0005

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○			◎	○	○					○	○



E5243 SERIES PLAIN SHANK FLAT SHANK

CARBIDE, 3 FLUTE 45° HELIX REGULAR LENGTH

- ▶ Designed to machine stainless steel, inconel, titanium and other hard to machine materials.
- ▶ It's 3 flute design gives high stability and allows good chip removal in plunging & slotting operations.
- ▶ The normal rake angle and 45° medium helix allows an extremely wide range of application.
- ▶ YG:TYLON super TiAlN coating are recommended for maximum performance.



Ø1/8~Ø5/16 Ø3/8~Ø1

Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E				
34558	34558TN	34558TC	34558TF	34558TE	1/8	1/8	3/8	1-1/2
34565	34565TN	34565TC	34565TF	34565TE	3/16	3/16	9/16	2
34573	34573TN	34573TC	34573TF	34573TE	1/4	1/4	3/4	2-1/2
34579	34579TN	34579TC	34579TF	34579TE	5/16	5/16	13/16	2-1/2
34584	34584TN	34584TC	34584TF	34584TE	3/8	3/8	7/8	2-1/2
34593	34593TN	34593TC	34593TF	34593TE	1/2	1/2	1	3
34594	34594TN	34594TC	34594TF	34594TE	9/16	9/16	1-1/4	3-1/2
34595	34595TN	34595TC	34595TF	34595TE	5/8	5/8	1-1/4	3-1/2
34598	34598TN	34598TC	34598TF	34598TE	3/4	3/4	1-1/2	4
34600	34600TN	34600TC	34600TF	34600TE	1	1	1-1/2	4

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.0012	0~-0.0005

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○			◎	○	○					○	○



E5059 SERIES PLAIN SHANK

CARBIDE, 3 FLUTE 50° HELIX STUB & REGULAR & LONG LENGTH

- ▶ Designed to machine stainless steel, inconel, titanium and other hard to machine materials.
- ▶ It's 3 flute design gives high stability and allows good chip removal in plunging & slotting operations.
- ▶ The high rake angle and 50° helix allows an extremely wide range of application.
- ▶ YG:TYLON super TiAlN coating are recommended for maximum performance.




P.1162

Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E				
83573	83573TN	83573TC	83573TF	83573TE	1/4	1/4	1/2	2
83901	83901TN	83901TC	83901TF	83901TE	1/4	1/4	3/4	2-1/2
83902	83902TN	83902TC	83902TF	83902TE	1/4	1/4	1-1/4	3
83584	83584TN	83584TC	83584TF	83584TE	3/8	3/8	1/2	2
83903	83903TN	83903TC	83903TF	83903TE	3/8	3/8	1	2-1/2
83904	83904TN	83904TC	83904TF	83904TE	3/8	3/8	1-1/2	3-1/2
83593	83593TN	83593TC	83593TF	83593TE	1/2	1/2	5/8	2-1/2
83905	83905TN	83905TC	83905TF	83905TE	1/2	1/2	1	3
83906	83906TN	83906TC	83906TF	83906TE	1/2	1/2	2	4
83595	83595TN	83595TC	83595TF	83595TE	5/8	5/8	7/8	3
83907	83907TN	83907TC	83907TF	83907TE	5/8	5/8	2-1/2	6
83598	83598TN	83598TC	83598TF	83598TE	3/4	3/4	1	3-1/2
83908	83908TN	83908TC	83908TF	83908TE	3/4	3/4	3	6

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.0012	0~-0.0005



Enforced cutting edge

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○			◎	○	○					○	○



E5246 SERIES PLAIN SHANK FLAT SHANK

CARBIDE, 3 FLUTE 60° HELIX REGULAR LENGTH

- ▶ Excellent shearing and chip ejection due to 60° Helix.
- ▶ 20% ~ 30% increase in chip load recommended over 30° helix tools.




Ø1/8-Ø5/16 Ø3/8-Ø1

Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E				
20558	20558TN	20558TC	20558TF	20558TE	1/8	1/8	3/8	1-1/2
20565	20565TN	20565TC	20565TF	20565TE	3/16	3/16	9/16	2
20573	20573TN	20573TC	20573TF	20573TE	1/4	1/4	3/4	2-1/2
20579	20579TN	20579TC	20579TF	20579TE	5/16	5/16	13/16	2-1/2
20584	20584TN	20584TC	20584TF	20584TE	3/8	3/8	7/8	2-1/2
20593	20593TN	20593TC	20593TF	20593TE	1/2	1/2	1	3
20594	20594TN	20594TC	20594TF	20594TE	9/16	9/16	1-1/4	3-1/2
20595	20595TN	20595TC	20595TF	20595TE	5/8	5/8	1-1/4	3-1/2
20598	20598TN	20598TC	20598TF	20598TE	3/4	3/4	1-1/2	4
20600	20600TN	20600TC	20600TF	20600TE	1	1	1-1/2	4

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.0012	0~-0.0005



Enforced cutting edge

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○			◎	○	○					○	○




E5066 SERIES PLAIN SHANK

CARBIDE, 5 FLUTE 45° HELIX STUB LENGTH

- ▶ Designed to machine stainless steels, inconels and other alloys.
- ▶ The new design of stub length allows cutting at maximum speeds and feeds with minimum deflection
- ▶ 5 Flute and 45° medium helix allow harmonic balance and smooth cutting.



up to Ø3/16 over Ø3/16



P.1162

Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E				
85558	85558TN	85558TC	85558TF	85558TE	1/8	1/8	1/4	1-1/2
85561	85561TN	85561TC	85561TF	85561TE	5/32	3/16	5/16	2
85565	85565TN	85565TC	85565TF	85565TE	3/16	3/16	5/16	2
85570	85570TN	85570TC	85570TF	85570TE	7/32	1/4	3/8	2
85573	85573TN	85573TC	85573TF	85573TE	1/4	1/4	3/8	2
85579	85579TN	85579TC	85579TF	85579TE	5/16	5/16	7/16	2
85584	85584TN	85584TC	85584TF	85584TE	3/8	3/8	1/2	2
85588	85588TN	85588TC	85588TF	85588TE	7/16	7/16	9/16	2-1/2
85593	85593TN	85593TC	85593TF	85593TE	1/2	1/2	5/8	2-1/2
85595	85595TN	85595TC	85595TF	85595TE	5/8	5/8	3/4	3
85598	85598TN	85598TC	85598TF	85598TE	3/4	3/4	1	3
85600	85600TN	85600TC	85600TF	85600TE	1	1	1-1/4	3

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.0012	0~-0.0003

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○			◎	○	○					○	○



E5067 SERIES PLAIN SHANK

CARBIDE, 5 FLUTE 45° HELIX REGULAR LENGTH

- ▶ Designed to machine stainless steels, inconels and other alloys.
- ▶ The new design of stub length allows cutting at maximum speeds and feeds with minimum deflection
- ▶ 5 Flute and 45° medium helix allow harmonic balance and smooth cutting.



Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E				
86558	86558TN	86558TC	86558TF	86558TE	1/8	1/8	1/2	1-1/2
86561	86561TN	86561TC	86561TF	86561TE	5/32	3/16	9/16	2
86565	86565TN	86565TC	86565TF	86565TE	3/16	3/16	9/16	2
86570	86570TN	86570TC	86570TF	86570TE	7/32	1/4	3/4	2-1/2
86573	86573TN	86573TC	86573TF	86573TE	1/4	1/4	3/4	2-1/2
86579	86579TN	86579TC	86579TF	86579TE	5/16	5/16	13/16	2-1/2
86584	86584TN	86584TC	86584TF	86584TE	3/8	3/8	1	2-1/2
86588	86588TN	86588TC	86588TF	86588TE	7/16	7/16	1	2-3/4
86593	86593TN	86593TC	86593TF	86593TE	1/2	1/2	1-1/4	3
86595	86595TN	86595TC	86595TF	86595TE	5/8	5/8	1-5/8	3-1/2
86598	86598TN	86598TC	86598TF	86598TE	3/4	3/4	1-5/8	4
86599	86599TN	86599TC	86599TF	86599TE	7/8	7/8	2	4
86600	86600TN	86600TC	86600TF	86600TE	1	1	2	4

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~.0012	0~.0003

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○			◎	○	○					○	○



E5068 SERIES PLAIN SHANK

CARBIDE, 5 FLUTE 45° HELIX MEDIUM & LONG LENGTH

- ▶ Designed to machine stainless steel, inconels and other alloys.
- ▶ The new design of stub length allows cutting at maximum speeds and feeds with minimum deflection
- ▶ 5 Flute and 45° medium helix allow harmonic balance and smooth cutting.



Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E				
58573	58573TN	58573TC	58573TF	58573TE	1/4	1/4	1-1/4	4
58579	58579TN	58579TC	58579TF	58579TE	5/16	5/16	1-1/4	4
58584	58584TN	58584TC	58584TF	58584TE	3/8	3/8	1-1/2	4
58588	58588TN	58588TC	58588TF	58588TE	7/16	7/16	2	4
58593	58593TN	58593TC	58593TF	58593TE	1/2	1/2	2	4
58595	58595TN	58595TC	58595TF	58595TE	5/8	5/8	2-1/2	5
58598	58598TN	58598TC	58598TF	58598TE	3/4	3/4	3-1/4	6
58901	58901TN	58901TC	58901TF	58901TE	3/4	3/4	2-1/4	5
58600	58600TN	58600TC	58600TF	58600TE	1	1	3-1/4	6
58902	58902TN	58902TC	58902TF	58902TE	1	1	2-5/8	6

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~.0012	0~.0003

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○			◎	○	○					○	○



E5073 SERIES PLAIN SHANK

CARBIDE, 5 FLUTE 45° HELIX EXTRA LONG LENGTH

- ▶ Designed to machine stainless steel, inconels and other alloys.
- ▶ The new design of stub length allows cutting at maximum speeds and feeds with minimum deflection
- ▶ 5 Flute and 45° medium helix allow harmonic balance and smooth cutting.



Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E				
59579	59579TN	59579TC	59579TF	59579TE	5/16	5/16	2-1/8	4
59584	59584TN	59584TC	59584TF	59584TE	3/8	3/8	2-1/2	6
59593	59593TN	59593TC	59593TF	59593TE	1/2	1/2	3-1/8	6
59595	59595TN	59595TC	59595TF	59595TE	5/8	5/8	4	6
59598	59598TN	59598TC	59598TF	59598TE	3/4	3/4	4	6
59600	59600TN	59600TC	59600TF	59600TE	1	1	4-1/8	7

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.012	0~-0.003

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○			◎	○	○					○	○



E5058 SERIES PLAIN SHANK

CARBIDE, 6 FLUTE 40° HELIX REGULAR LENGTH

- ▶ For finishing in most materials.
- ▶ 20 ~ 40% increase in inches per minute over 4 flute tools.
- ▶ YG:TYLON SUPER TiAlN coating recommended for maximum performance.



Unit : Inch

EDP No.					Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E				
84565	84565TN	84565TC	84565TF	84565TE	3/16	3/16	5/8	2
84573	84573TN	84573TC	84573TF	84573TE	1/4	1/4	3/4	2-1/2
84579	84579TN	84579TC	84579TF	84579TE	5/16	5/16	7/8	2-1/2
84584	84584TN	84584TC	84584TF	84584TE	3/8	3/8	7/8	2-1/2
84588	84588TN	84588TC	84588TF	84588TE	7/16	7/16	1	2-1/2
84593	84593TN	84593TC	84593TF	84593TE	1/2	1/2	1	3
84595	84595TN	84595TC	84595TF	84595TE	5/8	5/8	1-1/4	3-1/2
84598	84598TN	84598TC	84598TF	84598TE	3/4	3/4	1-1/2	4

MATERIAL HARDNESS		
Recommended Coating	Under 45 Rc F	Over 45 Rc E

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~-0.012	0~-0.005

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○			◎	○	○					○	○



E5056 SERIES FLAT SHANK
E5057 SERIES FLAT SHANK

CARBIDE, 5 FLUTE 45° HELIX STUB & REGULAR LENGTH FINE PITCH ROUGHING CORNER RADIUS

- ▶ 5 flute design gives minimum harmonic vibration.
- ▶ Stub tools for minimum deflection and maximum rigidity.
- ▶ Ideal for profile milling.
- ▶ Not recommended for slotting.



E5056 Series ■ STUB LENGTH Unit : Inch

EDP No.					Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E	R				
81584	81584TN	81584TC	81584TF	81584TE	.040	3/8	3/8	1/2	2
81593	81593TN	81593TC	81593TF	81593TE	.040	1/2	1/2	5/8	2-1/2
81595	81595TN	81595TC	81595TF	81595TE	.060	5/8	5/8	3/4	3
81598	81598TN	81598TC	81598TF	81598TE	.060	3/4	3/4	1	3
81600	81600TN	81600TC	81600TF	81600TE	.060	1	1	1-1/4	3

E5057 Series ■ REGULAR LENGTH Unit : Inch

EDP No.					Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E	R				
82584	82584TN	82584TC	82584TF	82584TE	.040	3/8	3/8	1	2-1/2
82593	82593TN	82593TC	82593TF	82593TE	.040	1/2	1/2	1-1/4	3
82595	82595TN	82595TC	82595TF	82595TE	.060	5/8	5/8	1-5/8	3-1/2
82598	82598TN	82598TC	82598TF	82598TE	.060	3/4	3/4	1-5/8	4
82600	82600TN	82600TC	82600TF	82600TE	.060	1	1	2	4

Mill Dia. Tolerance (inch)	Shank Dia. Tolerance
0~.003	0~.0005

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		◎							○	



E5077 SERIES PLAIN SHANK

CARBIDE, 3 FLUTE TAPER

- ▶ Designed for milling die cavity.
- ▶ Many different center line angles are available on your job requirement.



E5077 Series ■ TAPER LENGTH Unit : Inch

EDP No.					Cutting Small Diameter	Shank Diameter	Length of Cut	Overall Length	Center Ling Angle
UNCOATED	TIN COATED	TiCN COATED	YG:TYLON F	YG:TYLON E					
87552	87552TN	87552TC	87552TF	87552TE	1/8	1/4	1-1/2	3	1°
87553	87553TN	87553TC	87553TF	87553TE	1/8	1/4	1-1/2	3	1.5°
87554	87554TN	87554TC	87554TF	87554TE	1/8	1/4	1-1/4	3	2°
87556	87556TN	87556TC	87556TF	87556TE	1/8	1/4	1	3	3°
87560	87560TN	87560TC	87560TF	87560TE	1/8	1/4	3/4	3	5°
87564	87564TN	87564TC	87564TF	87564TE	1/8	1/4	1/2	3	7°
87570	87570TN	87570TC	87570TF	87570TE	3/32	1/4	1/2	3	10°
87572	87572TN	87572TC	87572TF	87572TE	3/16	3/8	1-3/4	3-1/2	1°
87573	87573TN	87573TC	87573TF	87573TE	3/16	3/8	1-3/4	3-1/2	1.5°
87574	87574TN	87574TC	87574TF	87574TE	3/16	3/8	1-3/4	3-1/2	2°
87576	87576TN	87576TC	87576TF	87576TE	5/32	3/8	1-3/4	3-1/2	3°
87580	87580TN	87580TC	87580TF	87580TE	1/8	3/8	1-1/2	3-1/2	5°
87584	87584TN	87584TC	87584TF	87584TE	1/8	3/8	1	3-1/2	7°
87590	87590TN	87590TC	87590TF	87590TE	1/8	3/8	3/4	3-1/2	10°
87592	87592TN	87592TC	87592TF	87592TE	1/4	1/2	2	4	1°
87594	87594TN	87594TC	87594TF	87594TE	1/4	1/2	2	4	2°
87596	87596TN	87596TC	87596TF	87596TE	1/4	1/2	2	4	3°
87600	87600TN	87600TC	87600TF	87600TE	1/4	1/2	1-1/4	4	5°
87902	87902TN	87902TC	87902TF	87902TE	3/16	1/2	1-1/4	4	7°
87903	87903TN	87903TC	87903TF	87903TE	1/8	1/2	1	4	10°

Cutting Small Dia. Tolerance(mm)		Shank Dia. Tolerance	Center Line Angle Tolerance
Ø1/16 ~ Ø1/4	0~.0020	0~.0005	±5'
Ø17/64 ~ Ø1	0~.0030		

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		○	○	○	○	○				



E5078 SERIES PLAIN SHANK

CARBIDE, 3 FLUTE TAPER BALL NOSE

- Designed for milling die cavity.
- Many different center line angles are available on your job requirement.



Unit : Inch

EDP No.					TIP Radius	Cutting Small Diameter	Shank Diameter	Length of Cut	Overall Length	Center Ling Angle
UNCOATED	TIN COATED	TICN COATED	YG:TYLON F	YG:TYLON E	R (±.0008)					
88552	88552TN	88552TC	88552TF	88552TE	.062	1/8	1/4	1-1/2	3	1°
88553	88553TN	88553TC	88553TF	88553TE	.062	1/8	1/4	1-1/2	3	1.5°
88554	88554TN	88554TC	88554TF	88554TE	.062	1/8	1/4	1-1/4	3	2°
88556	88556TN	88556TC	88556TF	88556TE	.062	1/8	1/4	1	3	3°
88560	88560TN	88560TC	88560TF	88560TE	.062	1/8	1/4	3/4	3	5°
88564	88564TN	88564TC	88564TF	88564TE	.062	1/8	1/4	1/2	3	7°
88570	88570TN	88570TC	88570TF	88570TE	.047	3/32	1/4	1/2	3	10°
88572	88572TN	88572TC	88572TF	88572TE	.093	3/16	3/8	1-3/4	3-1/2	1°
88573	88573TN	88573TC	88573TF	88573TE	.093	3/16	3/8	1-3/4	3-1/2	1.5°
88574	88574TN	88574TC	88574TF	88574TE	.093	3/16	3/8	1-3/4	3-1/2	2°
88576	88576TN	88576TC	88576TF	88576TE	.078	5/32	3/8	1-3/4	3-1/2	3°
88580	88580TN	88580TC	88580TF	88580TE	.062	1/8	3/8	1-1/2	3-1/2	5°
88584	88584TN	88584TC	88584TF	88584TE	.062	1/8	3/8	1	3-1/2	7°
88590	88590TN	88590TC	88590TF	88590TE	.062	1/8	3/8	3/4	3-1/2	10°
88592	88592TN	88592TC	88592TF	88592TE	.125	1/4	1/2	2	4	1°
88594	88594TN	88594TC	88594TF	88594TE	.125	1/4	1/2	2	4	2°
88596	88596TN	88596TC	88596TF	88596TE	.125	1/4	1/2	2	4	3°
88600	88600TN	88600TC	88600TF	88600TE	.125	1/4	1/2	1-1/4	4	5°
88902	88902TN	88902TC	88902TF	88902TE	.093	3/16	1/2	1-1/4	4	7°
88903	88903TN	88903TC	88903TF	88903TE	.062	1/8	1/2	1	4	10°

Cutting Small Dia. Tolerance(mm)	Shank Dia. Tolerance	Center Line Angle Tolerance
Ø1/16 ~ Ø1/4 0~~.0020	0~~.0005	±5'
Ø17/64 ~ Ø1 0~~.0030		

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○			○	○	○		○				



EH527 SERIES PLAIN SHANK

CARBIDE, 2 FLUTE LONG LENGTH - TiAlN 'F' Coated



Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
	Metric	Inch			
	h10		h6		
EH527035	3.5	.1378	3.5	7	50
EH527040	4.0	.1575	4	8	50
EH527045	4.5	.1772	4.5	8	50
EH527050	5.0	.1969	5	10	50
EH527055	5.5	.2165	5.5	10	57
EH527060	6.0	.2362	6	10	57
EH527065	6.5	.2559	6.5	13	60
EH527070	7.0	.2756	7	13	60
EH527075	7.5	.2953	7.5	16	63
EH527080	8.0	.3150	8	16	63
EH527085	8.5	.3346	8.5	16	67
EH527090	9.0	.3543	9	16	67
EH527095	9.5	.3740	9.5	19	72
EH527100	10.0	.3937	10	19	72
EH527110	11.0	.4330	11	22	83
EH527120	12.0	.4724	12	22	83
EH527130	13.0	.5118	13	22	83
EH527140	14.0	.5512	14	22	83
EH527150	15.0	.5905	15	26	92
EH527160	16.0	.6299	16	26	92
EH527180	18.0	.7087	18	26	92
EH527200	20.0	.7874	20	32	104

Tolerances according to DIN 7160 & 7161

	Tolerance range in µm				
	Nominal-Diameter in mm				
	from 1 to 3	over 3 to 6	over 6 to 10	over 10 to 18	over 18 to 30
h10	- 40	- 48	- 58	- 70	- 84
h6	- 6	- 8	- 9	- 11	- 13


◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎	○			○	○	○		○				



EH540 SERIES PLAIN SHANK

CARBIDE, 4 FLUTE LONG LENGTH - TiAlN 'F' Coated



Unit : mm

EDP No.	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
	Metric	Inch			
EH540035	3.5	.1378	3.5	10	50
EH540040	4.0	.1575	4	11	50
EH540045	4.5	.1772	4.5	11	50
EH540050	5.0	.1969	5	13	50
EH540055	5.5	.2165	5.5	13	57
EH540060	6.0	.2362	6	13	57
EH540065	6.5	.2559	6.5	16	60
EH540070	7.0	.2756	7	16	60
EH540075	7.5	.2953	7.5	19	63
EH540080	8.0	.3150	8	19	63
EH540085	8.5	.3346	8.5	19	67
EH540090	9.0	.3543	9	19	67
EH540095	9.5	.3740	9.5	22	72
EH540100	10.0	.3937	10	22	72
EH540110	11.0	.4330	11	26	83
EH540120	12.0	.4724	12	26	83
EH540130	13.0	.5118	13	26	83
EH540140	14.0	.5512	14	26	83
EH540150	15.0	.5905	15	32	92
EH540160	16.0	.6299	16	32	92
EH540180	18.0	.7087	18	32	92
EH540200	20.0	.7874	20	38	104

Tolerances according to DIN 7160 & 7161

Tolerance range in μm					
Nominal-Diameter in mm					
	from 1 to 3	over 3 to 6	over 6 to 10	over 10 to 18	over 18 to 30
h10	0 - 40	0 - 48	0 - 58	0 - 70	0 - 84
h6	0 - 6	0 - 8	0 - 9	0 - 11	0 - 13

◎ : Excellent ○ : Good

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○		○	○	○		○				



EH882 SERIES PLAIN SHANK

CARBIDE, 3 FLUTE 35° HELIX CORNER RADIUS - TiAlN 'F' Coated



Unit : mm

EDP No.	Corner Radius R	Mill Diameter		Shank Diameter	Length of Cut	Overall Length
		Metric	Inch			
EH882030	0.20~0.25	3.0	.1181	3	4	38
EH882040	0.20~0.25	4.0	.1575	6	5	54
EH882050	0.20~0.25	5.0	.1969	6	6	54
EH882060	0.40~0.50	6.0	.2362	6	7	54
EH882080	0.40~0.50	8.0	.3150	8	9	58
EH882100	0.40~0.50	10.0	.3937	10	11	66
EH882120	0.75~0.85	12.0	.4724	12	12	73
EH882160	0.75~0.85	16.0	.6299	16	16	82
EH882200	0.75~0.85	20.0	.7874	20	20	92

TiN & TiCN-COATING are available on your request.

Tolerances according to DIN 7160 & 7161

Tolerance range in μm					
Nominal-Diameter in mm					
	from 1 to 3	over 3 to 6	over 6 to 10	over 10 to 18	over 18 to 30
h10	0 - 40	0 - 48	0 - 58	0 - 70	0 - 84
h6	0 - 6	0 - 8	0 - 9	0 - 11	0 - 13

TiAlN FEED CHART

Unit : inch

Mill Diameter	Feed / Tooth	Mill Diameter	Feed / Tooth
3	.0035 ~ .0070	10	.0018 ~ .0040
5	.0050 ~ .0025	12	.0025 ~ .0050
6	.0012 ~ .0030	16	.0030 ~ .0060
8	.0018 ~ .0035	20	.0035 ~ .0070

P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎	○			○	◎		◎				




RECOMMENDED CUTTING CONDITIONS

SPEED & FEED RECOMMENDATIONS

Material	Speed	Chip Load per Tooth by End Mill Diameter			Recommended Coating
		Up to 1/4"	Up to 1/2"	Up to 1"	
Carbon + Alloy Steel <45Rc	100-700	.0002-.002	.001-.003	.003-.007	TF
Carbon + Alloy Steel >45Rc	50-400	.0002-.001	.0005-.0015	.001-.003	TE
Stainless Steels Non-Hardenable 200-300 Series	150-500	.0002-.001	.001-.002	.002-.006	TF
Stainless Steels Hardenable 400 Series Martensitic and PH Series	100-450	.0002-.0005	.0005-.001	.001-.005	TF
Cast+Ductile Iron	100-800	.0002-.0015	.002-.003	.003-.008	TF or TE
Nickel+Cobalt Based Alloys	20-200	.0003-.0008	.0008-.001	.001-.002	TE
Titanium	30-200	.0002-.0008	.0008-.002	.002-.004	TE
Aluminum	600-2000	.0002-.002	.002-.004	.004-.008	TiCN
Copper	300-1000	.0005-.002	.002-.003	.003-.006	CrN
Brass+ Bronze Alloys	600-1000	.0005-.002	.002-.003	.003-.006	TiCN
Graphite	600-1000	.0005-.005	.001-.008	.002-.010	D
Plastic	600-1200	.0006-.003	.003-.006	.006-.012	TF

TF = YG:TYLON F
 TE = YG:TYLON E
 D = DIAMOND
 CrN = CROME NITRIDE



SPEED & FEED DETERMINANTS

1. MATERIAL HARDNESS
2. MACHINE RIGIDITY
3. TYPE OF COATING
4. TOOL GEOMETRY
5. FINISH REQUIREMENTS
6. DEPTH & WIDTH OF CUT




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE - SIDE CUTTING

UGMF89, UGMGF57, UGMGF58, UGMGF59 SERIES

WORK MATERIAL	P												M			
	CARBON STEELS ALLOY STEELS TOOL STEELS ~ HRC 20				CARBON STEELS ALLOY STEELS TOOL STEELS HRC 20 ~ HRC 30				CARBON STEELS ALLOY STEELS TOOL STEELS HRC 30 ~ HRC 40				STAINLESS STEELS TITANIUM ALLOYS			
HARDNESS	500 ~ 800N/mm ²				800N/mm ² ~ 1000N/mm ²				1000/mm ² ~ 1300N/mm ²							
STRENGTH																
DIAMETER	RPM	FEED	SFM	Fz	RPM	FEED	SFM	Fz	RPM	FEED	SFM	Fz	RPM	FEED	SFM	Fz
1/16	11200	15.38	183	.0003	9640	13.40	158	.0003	8090	10.42	132	.0003	15560	12.90	255	.0002
5/64	10080	15.38	206	.0004	8680	13.40	178	.0004	7280	10.42	149	.0004	14000	12.90	287	.0002
3/32	9070	15.38	223	.0004	7810	13.40	192	.0004	6550	10.42	161	.0004	12600	12.90	309	.0003
7/64	7560	16.37	217	.0005	6550	14.39	188	.0005	5420	10.91	155	.0005	10650	12.90	305	.0003
1/8	6050	17.37	198	.0007	5290	15.37	173	.0007	4280	11.41	140	.0007	8690	12.90	285	.0004
9/64	5320	17.37	196	.0008	4600	15.37	169	.0008	3780	11.41	139	.0008	7620	12.90	281	.0004
5/32	4590	17.37	188	.0009	3910	15.37	160	.0010	3280	11.41	134	.0009	6550	12.90	268	.0005
11/64	4100	17.37	185	.0011	3530	15.37	159	.0011	2900	11.41	131	.0010	5920	12.90	267	.0005
3/16	3600	17.37	177	.0012	3150	15.37	155	.0012	2520	11.41	124	.0011	5290	12.90	260	.0006
13/64	3460	17.37	184	.0013	2990	15.37	159	.0013	2430	11.41	129	.0012	5040	12.90	268	.0006
7/32	3310	17.37	190	.0013	2840	15.37	162	.0014	2330	11.41	134	.0012	4790	12.90	275	.0007
15/64	3170	17.37	195	.0014	2680	15.37	164	.0014	2240	11.41	138	.0013	4540	12.90	279	.0007
1/4	3020	17.37	198	.0014	2520	15.37	165	.0015	2140	11.41	140	.0013	4280	12.90	280	.0008
9/32	2650	17.37	195	.0016	2210	15.37	162	.0017	1890	11.41	139	.0015	3780	12.90	279	.0009
5/16	2270	17.37	186	.0019	1890	15.37	155	.0020	1640	11.41	134	.0017	3280	12.90	269	.0010
3/8	1760	17.37	173	.0025	1510	15.37	149	.0025	1260	11.41	124	.0023	2520	12.90	248	.0013
7/16	1640	17.37	188	.0026	1390	15.37	159	.0028	1170	11.41	134	.0024	2330	12.90	267	.0014
1/2	1510	17.37	198	.0029	1260	15.37	165	.0031	1080	11.41	141	.0026	2140	12.90	280	.0015
9/16	1260	17.37	186	.0034	1130	15.37	167	.0034	930	11.41	137	.0031	1760	12.90	259	.0018
5/8	1130	19.34	185	.0043	1010	16.87	165	.0042	820	14.39	134	.0044	1640	14.39	269	.0022
3/4	980	19.34	193	.0049	830	16.87	164	.0051	690	14.39	136	.0052	1350	15.37	265	.0028
7/8	830	17.41	190	.0052	700	16.87	160	.0054	590	12.95	135	.0055	1130	13.83	259	.0031
1	750	15.67	197	.0052	630	16.87	165	.0054	530	11.65	139	.0055	1020	12.45	267	.0031

WORK MATERIAL	K				N							
	CAST IRON				ALUMINIUM ALLOYS				COPPER, BRASS NON-FERROUS METALS			
HARDNESS												
STRENGTH												
DIAMETER	RPM	FEED	SFM	Fz	RPM	FEED	SFM	Fz	RPM	FEED	SFM	Fz
1/16	13220	28.77	216	.0005	31110	59.52	509	.0005	23330	46.63	382	.0005
5/64	11900	28.77	244	.0006	28000	59.52	573	.0005	21000	46.63	430	.0006
3/32	10710	28.77	263	.0007	25200	59.52	619	.0006	18900	46.63	464	.0006
7/64	8820	28.77	253	.0008	21420	59.52	614	.0007	15750	46.63	451	.0007
1/8	6930	28.77	227	.0010	17640	59.52	578	.0008	12600	46.63	413	.0009
9/64	6110	28.77	225	.0012	15120	59.52	557	.0010	11340	46.63	418	.0010
5/32	5290	28.77	217	.0014	12600	59.52	516	.0012	10080	46.63	413	.0012
11/64	4730	28.77	213	.0015	11530	59.52	519	.0013	8950	46.63	403	.0013
3/16	4160	28.77	204	.0017	10460	59.52	514	.0014	7810	46.63	384	.0015
13/64	3970	30.26	211	.0019	10020	60.77	533	.0015	7500	47.37	399	.0016
7/32	3780	31.75	217	.0021	9580	62.01	549	.0016	7180	48.12	412	.0017
15/64	3590	33.24	220	.0023	9140	63.25	561	.0017	6870	48.86	422	.0018
1/4	3400	34.72	223	.0026	8690	64.49	569	.0019	6550	49.60	429	.0019
9/32	2960	35.72	218	.0030	7620	64.49	561	.0021	5800	49.60	427	.0021
5/16	2520	36.71	206	.0036	6550	64.49	536	.0025	5040	49.60	413	.0025
3/8	2140	38.69	210	.0045	5290	64.49	520	.0030	3910	49.60	384	.0032
7/16	1890	39.68	217	.0052	4790	64.49	549	.0034	3590	49.60	412	.0035
1/2	1640	40.68	215	.0062	4280	64.49	561	.0038	3280	49.60	430	.0038
9/16	1510	42.66	223	.0071	3780	64.49	557	.0043	2770	49.60	408	.0045
5/8	1260	43.66	206	.0087	3280	64.49	537	.0049	2520	49.60	413	.0049
3/4	1100	38.69	216	.0088	2710	64.49	533	.0059	2100	49.60	413	.0059
7/8	950	34.82	218	.0092	2270	58.04	520	.0064	1770	44.64	406	.0063
1	850	31.34	223	.0092	2040	52.24	534	.0064	1590	40.18	417	.0063



RPM = rev./min.
 Feed = inch/min.
 SFM = ft/min
 Fz = inch/tooth



RECOMMENDED CUTTING CONDITIONS


CARBIDE, 2 FLUTE - SLOTTING

UGMF90 SERIES

WORK MATERIAL	P												M			
	CARBON STEELS ALLOY STEELS TOOL STEELS				CARBON STEELS ALLOY STEELS TOOL STEELS				CARBON STEELS ALLOY STEELS TOOL STEELS				STAINLESS STEELS TITANIUM ALLOYS			
HARDNESS	~ HRc 20				HRc 20 ~ HRc 30				HRc 30 ~ HRc 40							
STRENGTH	500 ~ 800N/mm ²				800N/mm ² ~ 1000N/mm ²				1000/mm ² ~ 1300N/mm ²							
DIAMETER	RPM	FEED	SFM	Fz	RPM	FEED	SFM	Fz	RPM	FEED	SFM	Fz	RPM	FEED	SFM	Fz
1/8	6050	5.94	198	.0005	5290	5.21	173	.0005	4280	3.97	140	.0005	8690	4.22	285	.0002
3/16	3600	5.94	177	.0008	3150	5.21	155	.0008	2520	3.97	124	.0008	5290	4.22	260	.0004
1/4	3020	5.94	198	.0010	2520	5.21	165	.0010	2140	3.97	140	.0009	4280	4.22	280	.0005
3/8	1760	5.94	173	.0017	1510	5.21	148	.0017	1260	3.97	124	.0016	2520	4.22	248	.0008
1/2	1510	5.94	198	.0020	1260	5.21	165	.0021	1080	3.97	141	.0018	2140	4.22	280	.0010
5/8	1130	6.45	185	.0029	1010	5.46	165	.0027	820	4.97	134	.0030	1640	4.97	269	.0015
3/4	980	6.45	193	.0033	830	5.46	163	.0033	690	4.97	136	.0036	1350	4.97	265	.0018
1	750	5.22	197	.0035	630	4.42	165	.0035	530	4.02	139	.0038	1020	4.02	267	.0020

WORK MATERIAL	K				N											
	CAST IRON				ALUMINIUM ALLOYS				COPPER, BRASS NON-FERROUS METALS							
HARDNESS																
STRENGTH																
DIAMETER	RPM	FEED	SFM	Fz	RPM	FEED	SFM	Fz	RPM	FEED	SFM	Fz	RPM	FEED	SFM	Fz
1/8	6930	9.91	227	.0007	17640	20.84	578	.0006	12600	15.37	413	.0006				
3/16	4160	9.91	204	.0012	10460	20.84	514	.0010	7810	15.37	384	.0010				
1/4	3400	11.41	223	.0017	8690	21.82	569	.0013	6550	16.87	429	.0013				
3/8	2140	12.90	210	.0030	5290	21.82	520	.0021	3910	16.87	384	.0022				
1/2	1640	13.40	215	.0041	4280	21.82	561	.0025	3280	16.87	430	.0026				
5/8	1260	14.39	206	.0057	3280	21.82	537	.0033	2520	16.87	413	.0033				
3/4	1100	15.37	216	.0070	2710	21.82	533	.0040	2100	16.87	413	.0040				
1	850	12.45	223	.0073	2040	17.67	534	.0043	1590	13.67	417	.0043				


RPM = rev./min.
Feed = inch/min.
SFM = ft/min
Fz = inch/tooth



CARBIDE, 4 FLUTE BALL NOSE

UGMF91 SERIES

WORK MATERIAL	P								K				N			
	CARBON STEELS ALLOY STEELS TOOL STEELS				CARBON STEELS ALLOY STEELS TOOL STEELS				CAST IRON				ALUMINIUM ALLOYS			
HARDNESS	~ HRc 30				HRc 30 ~ HRc 40											
STRENGTH	~ 1000N/mm ²				1000N/mm ² ~ 1300N/mm ²											
DIAMETER	RPM	FEED	SFM	Fz	RPM	FEED	SFM	Fz	RPM	FEED	SFM	Fz	RPM	FEED	SFM	Fz
1/8	5670	9.91	186	.0004	4790	4.46	157	.0002	8060	15.37	264	.0005	23440	27.28	768	.0003
3/16	3400	10.42	167	.0008	2770	4.46	136	.0004	4790	22.32	235	.0012	13860	32.25	681	.0006
1/4	2770	9.91	181	.0009	2380	4.46	156	.0005	3910	24.31	256	.0016	11840	32.25	776	.0007
3/8	1640	8.94	161	.0014	1390	4.46	137	.0008	2380	30.77	234	.0032	7060	36.71	694	.0013
1/2	1390	8.43	182	.0015	1200	4.46	157	.0009	2020	30.77	265	.0038	5920	42.65	776	.0018
5/8	1070	8.43	175	.0020	880	4.46	144	.0013	1510	31.74	247	.0052	4410	36.71	722	.0021
3/4	980	8.43	193	.0022	800	4.46	157	.0014	1320	31.74	259	.0060	4030	36.71	792	.0023
1	770	6.83	202	.0022	630	3.61	165	.0014	1020	25.71	267	.0063	3160	29.73	828	.0024



RPM = rev./min.
Feed = inch/min.
SFM = ft/min
Fz = inch/tooth




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE - SLOTTING

E5020, E5244, E5011, E5026, E5022, E5025 SERIES

MATERIAL	P						M		K		N			
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		STAINLESS STEELS TITANIUM ALLOYS		CAST IRON		ALUMINIUM ALLOYS		COPPER, BRASS NON-FERROUS METALS	
HARDNESS	~ HRc 20		HRc 20 ~ HRc 30		HRc 30 ~ HRc 40									
STRENGTH	500 ~ 800N/mm ²		800 ~ 1000N/mm ²		1000 ~ 1300N/mm ²									
DIAMETER	RPM	FEED	RPM	FEED	FEED	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/32	5500	3.2	4800	2.8	4000	2.2	8000	2.6	6500	5.9	16000	12.6	12000	9.5
1/8	3700	3.5	3200	3.2	2600	2.4	5300	2.6	4200	5.9	11000	12.6	8000	9.5
5/32	2800	3.5	2400	3.2	2000	2.4	4000	2.6	3200	5.9	8000	12.6	6000	9.5
3/16	2200	3.5	1900	3.2	1600	2.4	3200	2.6	2500	5.9	6400	12.6	4800	9.5
1/4	1800	3.5	1600	3.2	1300	2.4	2600	2.6	2100	7.1	5300	13.4	4000	10.2
5/16	1400	3.5	1200	3.2	1000	2.4	2000	2.6	1600	7.5	4000	13.4	3000	10.2
3/8	1100	3.5	950	3.2	800	2.4	1600	2.6	1300	7.9	3200	13.4	2400	10.2
1/2	900	3.5	800	3.2	660	2.4	1300	2.6	1000	8.3	2600	13.4	2000	10.2
9/16	800	3.5	700	3.2	570	2.4	1100	2.6	900	8.7	2300	13.4	1700	10.2
5/8	700	3.9	600	3.4	500	3.0	1000	3.0	800	8.9	2000	13.4	1500	10.2
13/16	550	3.9	480	3.4	400	3.0	800	3.2	640	9.5	1600	13.4	1200	10.2




* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min. FEED = inch/min.

CARBIDE, 2 FLUTE TiAlN "F" COATED - SLOTTING

EH020, EH244, EH011, EH026, EH022, EH025 SERIES

MATERIAL	P						M		K		N			
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		STAINLESS STEELS TITANIUM ALLOYS		CAST IRON		ALUMINIUM ALLOYS		COPPER, BRASS NON-FERROUS METALS	
HARDNESS	~ HRc 20		HRc 20 ~ HRc 30		HRc 30 ~ HRc 40									
STRENGTH	500 ~ 800N/mm ²		800 ~ 1000N/mm ²		1000 ~ 1300N/mm ²									
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/32	8640	4.7	7440	4.3	6240	3.3	12000	4.0	10200	9.4	24000	19.9	18000	14.6
1/8	5760	5.7	5040	5.0	4080	3.8	8280	4.0	6600	9.4	16800	19.9	12000	14.6
5/32	4370	5.7	3720	5.0	3120	3.8	6240	4.0	5040	9.4	12000	19.9	9600	14.6
3/16	3430	5.7	3000	5.0	2400	3.8	5040	4.0	3960	9.4	9960	19.9	7440	14.6
1/4	2880	5.7	2400	5.0	2040	3.8	4080	4.0	3240	10.9	8280	20.8	6240	16.1
5/16	2160	5.7	1800	5.0	1560	3.8	3120	4.0	2400	11.8	6240	20.8	4800	16.1
3/8	1680	5.7	1440	5.0	1200	3.8	2400	4.0	2040	12.3	5040	20.8	3720	16.1
1/2	1440	5.7	1200	5.0	1030	3.8	2040	4.0	1560	12.8	4080	20.8	3120	16.1
9/16	1200	5.7	1080	5.0	890	3.8	1680	4.0	1440	13.2	3600	20.8	2640	16.1
5/8	1080	6.1	960	5.2	780	4.7	1560	4.8	1200	13.7	3120	20.8	2400	16.1
13/16	880	6.1	740	5.2	620	4.7	1200	4.8	1000	14.6	2400	20.8	1870	16.1



* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min. FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE - SIDE CUTTING

E5021, E5245, E5012, E5065, E5023, E5024, E5216 SERIES

MATERIAL	P						M		K		N			
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		STAINLESS STEELS TITANIUM ALLOYS		CAST IRON		ALUMINUM ALLOYS		COPPER. BRASS NON-FERROUS METALS	
HARDNESS	~ HRC 20		HRc 20 ~ HRc 30		HRc 30 ~ HRc 40									
STRENGTH	500 ~ 800N/mm ²		800 ~ 1000N/mm ²		1000 ~ 1300N/mm ²									
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/32	5500	9.5	4800	8.3	4000	6.3	8000	7.9	6500	17.7	16000	37.8	12000	25.4
1/8	3700	10.6	3200	9.5	2600	7.1	5300	7.9	4200	17.7	11000	37.8	8000	25.4
5/32	2800	10.6	2400	9.5	2000	7.1	4000	7.9	3200	17.7	8000	37.8	6000	25.4
3/16	2200	10.6	1900	9.5	1600	7.1	3200	7.9	2500	17.7	6400	37.8	4800	25.4
1/4	1800	10.6	1600	9.5	1300	7.1	2600	7.9	2100	21.3	5300	40.2	4000	30.7
5/16	1400	10.6	1200	9.5	1000	7.1	2000	7.9	1600	22.4	4000	40.2	3000	30.7
3/8	1100	10.6	950	9.5	800	7.1	1600	7.9	1300	23.6	3200	40.2	2400	30.7
1/2	900	10.6	800	9.5	660	7.1	1300	7.9	1000	24.8	2600	40.2	2000	30.7
9/16	800	10.6	700	9.5	570	7.1	1100	7.9	900	26.0	2300	40.2	1700	30.7
5/8	700	11.8	600	10.2	500	8.7	1000	8.9	800	26.8	2000	40.2	1500	30.7
13/16	550	11.8	480	10.2	400	8.7	800	9.5	640	28.4	1600	40.2	1200	30.7




* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min. FEED = inch/min.

CARBIDE, 4 FLUTE TiAIN "F" COATED - SIDE CUTTING

EH021, EH245, EH012, EH065, EH023, EH024, EH216 SERIES

MATERIAL	P						M		K		N			
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		STAINLESS STEELS TITANIUM ALLOYS		CAST IRON		ALUMINUM ALLOYS		COPPER. BRASS NON-FERROUS METALS	
HARDNESS	~ HRC 20		HRc 20 ~ HRc 30		HRc 30 ~ HRc 40									
STRENGTH	500 ~ 800N/mm ²		800 ~ 1000N/mm ²		1000 ~ 1300N/mm ²									
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/32	8640	14.7	7440	12.8	6240	9.9	12000	12.3	10200	27.4	24000	56.7	18000	44.4
1/8	5760	16.5	5040	14.6	4080	10.9	8280	12.3	6600	27.4	16800	56.7	12000	44.4
5/32	4370	16.5	3720	14.6	3120	10.9	6240	12.3	5040	27.4	12000	56.7	9600	44.4
3/16	3430	16.5	3000	14.6	2400	10.9	5040	12.3	3960	27.4	9960	56.7	7440	44.4
1/4	2880	16.5	2400	14.6	2040	10.9	4080	12.3	3240	33.1	8280	61.4	6240	47.2
5/16	2160	16.5	1800	14.6	1560	10.9	3120	12.3	2400	35.0	6240	61.4	4800	47.2
3/8	1680	16.5	1440	14.6	1200	10.9	2400	12.3	2040	36.9	5040	61.4	3720	47.2
1/2	1440	16.5	1200	14.6	1030	10.9	2040	12.3	1560	38.8	4080	61.4	3120	47.2
9/16	1200	16.5	1080	14.6	890	10.9	1680	12.3	1440	40.6	3600	61.4	2640	47.2
5/8	1080	18.4	960	16.1	780	13.7	1560	13.7	1200	41.6	3120	61.4	2400	47.2
13/16	880	18.4	740	16.1	620	13.7	1200	14.6	1000	36.9	2400	61.4	1870	47.2



* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min. FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE BALL NOSE

E5249, E5014, E5018, E5251 SERIES

MATERIAL	P				K		N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CAST IRON		ALUMINUM ALLOYS	
HARDNESS	~ HRC30		HRc30 ~ HRc 40					
STRENGTH	~ 1000N/mm ²		1000 ~ 1300N/mm ²					
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/32	5200	3.5	4400	1.8	7300	5.9	21500	11.0
1/8	3500	3.9	2900	1.8	4900	6.3	14300	11.0
5/32	2600	3.9	2100	1.8	3600	7.9	10900	11.0
3/16	2100	4.1	1700	1.8	2900	9.1	8800	13.0
1/4	1700	3.9	1430	1.8	2400	9.9	7260	13.0
5/16	1270	3.7	1100	1.8	1800	12.6	5500	15.0
3/8	1000	3.7	870	1.8	1430	12.6	4300	15.0
1/2	870	3.4	730	1.8	1200	12.6	3600	17.3
9/16	750	3.4	620	1.8	1000	12.8	3000	17.3
5/8	650	3.4	540	1.8	920	12.8	2700	15.0
11/16	580	3.4	480	1.8	810	12.8	2400	15.0
13/16	500	3.4	430	1.8	730	11.4	2100	15.0



* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min. FEED = inch/min.

CARBIDE, 2 FLUTE BALL NOSE TiAIN "F" COATED

EH249, EH014, EF018, EF251 SERIES

MATERIAL	P				K		N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CAST IRON		ALUMINUM ALLOYS	
HARDNESS	~ HRC30		HRc30 ~ HRc40					
STRENGTH	~ 1000N/mm ²		1000 ~ 1300N/mm ²					
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/32	8110	5.7	6840	2.8	11400	9.4	33600	17.0
1/8	5400	6.1	4560	2.8	7680	9.9	22320	17.0
5/32	4080	6.1	3240	2.8	5640	12.3	16800	17.0
3/16	3240	6.4	2640	2.8	4560	14.2	13200	20.3
1/4	2640	6.1	2270	2.8	3720	15.6	11280	20.3
5/16	1920	5.7	1680	2.8	2760	19.9	8640	23.2
3/8	1560	5.7	1320	2.8	1680	19.9	6720	23.2
1/2	1320	5.2	1140	2.8	1920	19.9	5640	26.9
9/16	1180	5.2	960	2.8	1560	19.9	4680	26.9
5/8	1020	5.2	840	2.8	1440	19.9	4200	23.2
11/16	900	5.2	740	2.8	1200	19.9	3720	23.2
13/16	780	5.2	670	2.8	1140	18.0	3240	23.2



* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min. FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 4 FLUTE BALL NOSE

E5250, E5060, E5062, E5252 SERIES

MATERIAL	P				K		N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CAST IRON		IRON RPM FEED ALUMINUM ALLOYS	
HARDNESS	~ HRC30		HRC30 ~ HRC40					
STRENGTH	~ 1000N/mm ²		1000 ~ 1300N/mm ²					
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/32	5200	5.5	4400	2.8	7300	9.1	21500	16.5
1/8	3500	5.9	2900	2.8	4900	9.5	14300	16.5
5/32	2600	5.9	2100	2.8	3600	11.8	10900	16.5
3/16	2100	6.3	1700	2.8	2900	13.8	8800	19.7
1/4	1700	5.9	1430	2.8	2400	15.0	7260	19.7
5/16	1270	5.5	1100	2.8	1800	18.9	5500	22.4
3/8	1000	5.5	870	2.8	1430	18.9	4300	22.4
1/2	870	5.1	730	2.8	1200	18.9	3600	26.0
9/16	750	5.1	620	2.8	1000	19.3	3000	26.0
5/8	650	5.1	540	2.8	920	19.3	2700	22.4
11/16	580	5.1	480	2.8	810	19.3	2400	22.4
13/16	500	5.1	430	2.8	730	17.3	2100	22.4




* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min. FEED = inch/min.

CARBIDE, 4 FLUTE BALL NOSE TiAIN "F" COATED

EH250, EH060, EH062, EH252 SERIES

MATERIAL	P				K		N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CAST IRON		ALUMINUM ALLOYS	
HARDNESS	~ HRC30		HRC30 ~ HRC40					
STRENGTH	~ 1000N/mm ²		1000 ~ 1300N/mm ²					
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/32	8110	8.5	6840	4.3	11400	14.2	33600	26.0
1/8	5400	9.4	4560	4.3	7680	14.6	22320	26.0
5/32	4080	9.4	3240	4.3	5640	18.4	16800	26.0
3/16	3240	9.9	2640	4.3	4560	21.3	13200	30.7
1/4	2640	9.4	2270	4.3	3720	23.2	11280	30.7
5/16	1920	8.5	1680	4.3	2760	29.3	8640	35.0
3/8	1560	8.5	1320	4.3	2270	29.3	6720	35.0
1/2	1320	8.0	1140	4.3	1920	29.3	5640	40.6
9/16	1180	8.0	960	4.3	1560	30.2	4680	40.6
5/8	1020	8.0	840	4.3	1440	30.2	4200	35.0
11/16	900	8.0	740	4.3	1200	30.2	3720	35.0
13/16	780	8.0	670	4.3	1140	26.9	3240	35.0



* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min. FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

CARBIDE, 2 FLUTE TiAIN-COATED - SLOTTING

EH527 SERIES

MATERIAL	P						M		K		N			
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		STAINLESS STEELS TITANIUM ALLOYS		CAST IRON		ALUMINUM ALLOYS		COPPER. BRASS NON-FERROUS METALS	
HARDNESS	~ HRC 20		HRC 20 ~ HRC 30		HRC 30 ~ HRC 40									
STRENGTH	500 ~ 800N/mm ²		800 ~ 1000N/mm ²		1000 ~ 1300N/mm ²									
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
2.0	7700	4.3	6720	3.9	5600	3.0	11200	3.5	9100	8.3	22400	17.7	16800	13.2
3.0	5180	4.9	4480	4.3	3640	3.4	7420	3.5	5880	8.3	15400	17.7	11200	13.2
4.0	3920	4.9	3360	4.3	2800	3.4	5600	3.5	4480	8.3	11200	17.7	8400	13.2
5.0	3080	4.9	2660	4.3	2240	3.4	4480	3.5	3500	8.3	8960	17.7	6720	13.2
6.0	2520	4.9	2240	4.3	1820	3.4	3640	3.5	2940	9.8	7420	18.7	5600	14.4
8.0	1960	4.9	1680	4.3	1400	3.4	2800	3.5	2240	10.4	5600	18.7	4200	14.4
10.0	1540	4.9	1330	4.3	1120	3.4	2240	3.5	1820	11.0	4480	18.7	3360	14.4
12.0	1260	4.9	1120	4.3	924	3.4	1820	3.5	1400	11.6	3640	18.7	2800	14.4
14.0	1120	4.9	980	4.3	798	3.4	1540	3.5	1260	12.2	3220	18.7	2380	14.4
16.0	980	5.5	840	4.7	700	4.1	1400	4.1	1120	12.4	2800	18.7	2100	14.4
20.0	770	5.5	672	4.7	560	4.1	1120	4.3	900	13.2	2240	18.7	1680	14.4




* The FEED, in long & extra long types, should be reduced by around 50%

RPM = rev./min. FEED = inch/min.

CARBIDE, 4 FLUTE TiAIN-COATED - SIDE CUTTING

EH540 SERIES

MATERIAL	P						M		K		N			
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		STAINLESS STEELS TITANIUM ALLOYS		CAST IRON		ALUMINUM ALLOYS		COPPER. BRASS NON-FERROUS METALS	
HARDNESS	~ HRC 20		HRC 20 ~ HRC 30		HRC 30 ~ HRC 40									
STRENGTH	500 ~ 800N/mm ²		800 ~ 1000N/mm ²		1000 ~ 1300N/mm ²									
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
2.0	7700	13.2	6720	11.6	5600	8.9	11200	11.0	9100	24.8	22400	53.0	16800	39.8
3.0	5180	15.0	4480	13.2	3640	9.8	7420	11.0	5880	24.8	15400	53.0	11200	39.8
4.0	3920	15.0	3360	13.2	2800	9.8	5600	11.0	4480	24.8	11200	53.0	8400	39.8
5.0	3080	15.0	2660	13.2	2240	9.8	4480	11.0	3500	24.8	8960	53.0	6720	39.8
6.0	2520	15.0	2240	13.2	1820	9.8	3640	11.0	2940	29.7	7420	56.3	5600	42.9
8.0	1960	15.0	1680	13.2	1400	9.8	2800	11.0	2240	31.5	5600	56.3	4200	42.9
10.0	1540	15.0	1330	13.2	1120	9.8	2240	11.0	1820	33.1	4480	56.3	3360	42.9
12.0	1260	15.0	1120	13.2	920	9.8	1820	11.0	1400	34.7	3640	56.3	2800	42.9
14.0	1120	15.0	980	13.2	800	9.8	1540	11.0	1260	36.4	3220	56.3	2380	42.9
16.0	980	16.5	840	14.4	700	12.2	1400	12.4	1120	37.4	2800	56.3	2100	42.9
20.0	770	16.5	670	14.4	560	12.2	1120	13.2	900	39.8	2240	56.3	1680	42.9



* The FEED, in long & extra long types, should be reduced by around 50%

RPM = rev./min. FEED = inch/min.

CARBIDE

HSS

CBN
END MILLS

i-Xmill
END MILLS

i-SMART
MODULAR
TYPE END MILLS

X5070
END MILLS

4G MILL
END MILLS

X-POWER
END MILLS

JET-POWER
END MILLS

TitaNox
-POWER
END MILLS

V7 PLUS A
END MILLS

V7 MILL INOX
END MILLS

ALU-POWER
HPC
END MILLS

ALU-POWER
END MILLS

D-POWER
GRAPHITE
END MILLS

D-POWER
CFRP
END MILLS

ROUTERS
CFRP

STANDARD
CARBIDE
END MILLS

ONLY ONE
COATED PM60
END MILLS

SINE -POWER
END MILLS

TANK-POWER
END MILLS

STANDARD
COBALT & HSS
END MILLS

TECHNICAL
DATA



RECOMMENDED CUTTING CONDITIONS

PROPERTIES AND APPLICATIONS OF COATINGS

	Titanium Nitride	Titanium Carbonitride	Super TiAlN "F" Coatings	Super TiAlN "E" Coatings
Hardness	82 Rc	92 Rc	92 Rc	95 Rc
Coefficient of Friction Against Dry Steel (.8)	.4	.4	.4	.4
Coating Thickness 3 Microns = .0001	1- 4	1- 4	1- 5	1- 3
Maximum Working Temperature	1100 F	750 F	1470 F	1470 F
Coating Color	Gold	Blue - Gray	Violet - Gray	Violet - Gray
Key Characteristics	Good General Purpose	Good Wear Resistance Good Toughness Moderate Heat Resistance	Enhanced Toughness High Heat Resistance	High Hardness Enhanced Toughness High Heat Resistance
Primary Applications	Machining of Iron Based Materials	General Machining of Various Materials	Steel, Cast Iron, Stainless, Nickel Based Alloys, High Temp and Titanium Alloys, High Speed Machining Wet, Dry, or Semi Dry Condition	Hardened Workpieces, Steel, Cast Iron, Stainless, Nickel Based Alloys, High Temp and Titanium Alloys, Machining Wet, Dry, or Semi Dry Condition
YG:TYLON SUPER TiAlN COATED TOOLS CAN BE RUN 20% - 50% FASTER THAN TiN or TiCN ON MOST MATERIALS				










Being the best through innovation

HSS



ONLY ONE COATED PM60 END MILLS

- Perfect solution to protect carbide chipping problems under vibrations

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
GYG64		PM60, 2 FLUTE (Center Cut)	D1/8	D1	1174
GYG67		PM60, 4 FLUTE BALL NOSE	R1/16	R1/2	1175
GYG65		PM60, 4 FLUTE (Center Cut)	D1/8	D1	1176
GYG66		PM60, 4 FLUTE MULTIPLE HELIX (Center Cut)	D1/8	D1	1177
GYG69		PM60, MULTI FLUTE MULTIPLE HELIX CORNER RADIUS ROUGHING - FINE (Center Cut)	D1/4	D1	1178
GYG68		PM60, MULTI FLUTE ROUGHING- FINE (Center Cut)	D1/4	D1-1/4	1179
GYG70		PM60, MULTI FLUTE ROUGHING - COARSE (Center Cut)	D1/4	D1-1/4	1180
RECOMMENDED CUTTING CONDITIONS					1181


◎ : Excellent ○ : Good

Carbon Steels	Alloy Steels	P			High Hardened Steels	M	K	N					S		
		Prehardened Steels	Hardened Steels					Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70										
◎	◎	○	○			◎	◎	○							
◎	◎	○	○			◎	◎	○							
◎	◎	○	○			◎	◎	○							
◎	◎	○	○			◎	◎	○							
◎	◎	○	○			◎	◎	○							
◎	◎	○	○			◎	◎	○							

YG ONLY ONE END MILLS

GYG64 SERIES FLAT SHANK

PM60, 2 FLUTE (Center Cut)



PM 60 2 30° FLAT P. 1181

Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
Y-COATED	D1	D2	L1	L2
GYG64008	1/8	3/8	3/8	2-5/16
GYG64012	3/16	3/8	7/16	2-5/16
GYG64016	1/4	3/8	1/2	2-5/16
GYG64020	5/16	3/8	9/16	2-5/16
GYG64024	3/8	3/8	9/16	2-5/16
GYG64032	1/2	1/2	1	3
GYG64040	5/8	5/8	1-5/16	3-7/16
GYG64048	3/4	3/4	1-5/16	3-7/16
GYG64064	1	1	1-5/8	4-1/8

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0 ~ -.0012	h6


◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○	○			◎	◎	○						

YG ONLY ONE END MILLS

GYG67 SERIES FLAT SHANK

PM60, 4 FLUTE BALL NOSE



PM 60 4 30° R ±.001 FLAT P.1182

Unit : Inch

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
Y-COATED	R	D1	D2	L1	L2
GYG67008	R1/16	1/8	3/8	3/8	2-5/16
GYG67012	R3/32	3/16	3/8	1/2	2-3/8
GYG67016	R1/8	1/4	3/8	5/8	2-7/16
GYG67020	R5/32	5/16	3/8	3/4	2-1/2
GYG67024	R3/16	3/8	3/8	3/4	2-1/2
GYG67032	R1/4	1/2	1/2	1-1/4	3-1/4
GYG67040	R5/16	5/8	5/8	1-5/8	3-3/4
GYG67048	R3/8	3/4	3/4	1-5/8	3-7/8
GYG67064	R1/2	1	1	2	4-1/2

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0 ~ -.0012	h6


◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○	○			◎	◎	○						



GYG65 SERIES FLAT SHANK

PM60, 4 FLUTE (Center Cut)



Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
Y-COATED	D1	D2	L1	L2
GYG65008	1/8	3/8	3/8	2-5/16
GYG65012	3/16	3/8	1/2	2-3/8
GYG65016	1/4	3/8	5/8	2-7/16
GYG65020	5/16	3/8	3/4	2-1/2
GYG65024	3/8	3/8	3/4	2-1/2
GYG65032	1/2	1/2	1-1/4	3-1/4
GYG65040	5/8	5/8	1-5/8	3-3/4
GYG65048	3/4	3/4	1-5/8	3-7/8
GYG65056	7/8	7/8	1-7/8	4-1/8
GYG65064	1	1	2	4-1/2

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0 ~ -.0012	h6


◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○	○			◎	◎	○						



GYG66 SERIES FLAT SHANK

PM60, 4 FLUTE MULTIPLE HELIX (Center Cut)



Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
Y-COATED	D1	D2	L1	L2
GYG66008	1/8	3/8	3/8	2-5/16
GYG66012	3/16	3/8	1/2	2-3/8
GYG66016	1/4	3/8	5/8	2-7/16
GYG66020	5/16	3/8	3/4	2-1/2
GYG66024	3/8	3/8	3/4	2-1/2
GYG66032	1/2	1/2	1-1/4	3-1/4
GYG66040	5/8	5/8	1-5/8	3-3/4
GYG66048	3/4	3/4	1-5/8	3-7/8
GYG66064	1	1	2	4-1/2

Mill Dia. Tolerance(inch)	Shank Dia. Tolerance
0 ~ -.0012	h6


◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○	○			◎	◎	○						



GYG69 SERIES FLAT SHANK

PM60, MULTI FLUTE MULTIPLE HELIX CORNER RADIUS ROUGHING - FINE (Center Cut)



5 Flute, 44°/45°/45° Unit : Inch

EDP No.	Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
Y-COATED	R	D1	D2	L1	L2	
GYG69016	R.020	1/4	3/8	5/8	2-7/16	4
GYG69020	R.020	5/16	3/8	3/4	2-1/2	4
GYG69024	R.020	3/8	3/8	3/4	2-1/2	4
GYG69032	R.020	1/2	1/2	1-1/4	3-1/4	4
GYG69040	R.040	5/8	5/8	1-1/4	3-3/8	5
GYG69048	R.040	3/4	3/4	1-5/8	3-7/8	5
GYG69064	R.040	1	1	2	4-1/2	5

Mill Dia. Tolerance(inch)
0 ~ +.0030


© : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○	○		◎	◎	○						



GYG68 SERIES FLAT SHANK

PM60, MULTI FLUTE ROUGHING- FINE (Center Cut)



Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
Y-COATED	D1	D2	L1	L2	
GYG68016	1/4	3/8	5/8	2-7/16	3
GYG68020	5/16	3/8	3/4	2-1/2	3
GYG68901	5/16	3/8	1-3/8	3-3/16	3
GYG68024	3/8	3/8	3/4	2-1/2	4
GYG68902	3/8	3/8	1-1/2	3-1/4	4
GYG68032	1/2	1/2	1-1/4	3-1/4	4
GYG68903	1/2	1/2	2	4	4
GYG68040	5/8	5/8	1-5/8	3-3/4	4
GYG68904	5/8	5/8	2-1/2	4-5/8	4
GYG68048	3/4	3/4	1-5/8	3-7/8	4
GYG68905	3/4	3/4	2-1/2	4-3/4	4
GYG68906	3/4	3/4	3	5-1/4	4
GYG68064	1	1	2	4-1/2	5
GYG68907	1	1	4	6-1/2	5
GYG68116	1-1/4	1-1/4	2	4-1/2	6

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060


© : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○	○		◎	◎	○						



GYG70 SERIES FLAT SHANK

PM60, MULTI FLUTE ROUGHING- COARSE (Center Cut)



EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
Y-COATED	D1	D2	L1	L2	
GYG70016	1/4	3/8	5/8	2-7/16	3
GYG70020	5/16	3/8	3/4	2-1/2	3
GYG70024	3/8	3/8	3/4	2-1/2	4
GYG70032	1/2	1/2	1-1/4	3-1/4	4
GYG70040	5/8	5/8	1-5/8	3-3/4	4
GYG70048	3/4	3/4	1-5/8	3-7/8	4
GYG70064	1	1	2	4-1/2	5
GYG70116	1-1/4	1-1/4	2	4-1/2	6

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060

© : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○	○		◎	◎	○						




RECOMMENDED CUTTING CONDITIONS

PM60, 2 FLUTE (Center Cut)

GYG64 SERIES

MATERIAL	P												M	
	STRUCTURAL STEELS CARBON STEELS		STRUCTURAL STEELS CARBON STEELS CAST IRONS		CARBON STEELS ALLOY STEELS TOOL STEELS		PREHARDENED STEELS ALLOY STEELS TOOL STEELS		ALLOY STEELS TOOL STEELS		ALLOY STEELS TOOL STEELS		STAINLESS STEELS	
HARDNESS			~ HRc20		HRc20 ~ HRc30		HRc30 ~ HRc35		HRc35 ~ HRc40		HRc40 ~ HRc45			
STRENGTH	~ 500N/mm ²		500 ~ 800N/mm ²		800 ~ 1000N/mm ²		1000 ~ 1100N/mm ²		1100 ~ 1300N/mm ²		1300 ~ 1400N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8	5710	7.20	4610	5.81	3810	5.10	2610	3.49	2010	2.68	1400	1.99	2210	3.13
3/16	4950	12.85	4080	9.95	3280	9.03	2140	4.88	1670	3.68	1200	2.75	1870	4.13
1/4	3960	11.85	3310	9.38	2610	8.62	1650	4.82	1300	3.69	900	2.56	1450	4.12
5/16	3130	13.05	2650	11.46	2170	9.55	1400	5.64	1080	4.01	760	2.82	1200	4.45
3/8	2640	14.76	2270	13.24	1840	11.43	1140	6.17	870	4.86	630	3.60	970	5.42
1/2	2030	12.15	1650	10.81	1300	9.34	850	5.30	650	3.64	450	2.52	730	4.06
5/8	1620	12.66	1380	9.26	1080	8.53	680	4.83	540	3.84	380	2.64	580	4.17
3/4	1200	10.99	990	8.23	890	7.46	550	4.52	450	3.52	320	2.50	500	3.99
1	890	7.22	750	6.63	580	5.40	430	3.52	300	2.37	200	1.50	330	2.51



RPM = rev./min.
FEED = inch/min.






RECOMMENDED CUTTING CONDITIONS

PM60, 4 FLUTE BALL NOSE

GYG67 SERIES

MATERIAL	P										M	
	STRUCTURAL STEELS CARBON STEELS		STRUCTURAL STEELS CARBON STEELS CAST IRONS		CARBON STEELS ALLOY STEELS TOOL STEELS		PREHARDENED STEELS ALLOY STEELS TOOL STEELS		ALLOY STEELS TOOL STEELS		STAINLESS STEELS	
HARDNESS	~ 500N/mm ²		~ HRC20		HRC20 ~ HRC30		HRC30 ~ HRC40		HRC40 ~ HRC45			
STRENGTH	~ 500N/mm ²		500 ~ 800N/mm ²		800 ~ 1000N/mm ²		1000 ~ 1300N/mm ²		1300 ~ 1400N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8	8320	23.59	6620	15.63	4410	8.34	2310	3.63	1600	2.53	2510	3.95
3/16	6270	29.13	4950	19.65	3260	10.71	1690	4.99	1190	3.51	1880	5.97
1/4	5010	32.37	3960	21.83	2610	11.91	1350	5.54	950	3.90	1500	6.63
5/16	4050	37.64	3130	24.63	2170	14.32	1080	5.97	760	4.20	1200	7.01
3/8	3480	44.88	2640	29.52	1770	17.29	870	7.53	600	5.40	940	7.96
1/2	2610	35.72	2030	23.34	1350	13.43	650	5.54	450	3.84	730	6.52
5/8	2070	34.48	1560	22.91	1080	12.96	540	5.80	380	4.08	600	6.63
3/4	1700	31.41	1250	20.72	870	11.22	450	5.40	320	3.75	500	6.00
1	1130	21.67	880	14.51	550	8.16	300	3.55	200	2.24	330	3.90



RPM = rev./min.
FEED = inch/min.






RECOMMENDED CUTTING CONDITIONS

PM60, 4 FLUTE (Center Cut)

GYG65 SERIES

MATERIAL	P										M			
	STRUCTURAL STEELS CARBON STEELS		STRUCTURAL STEELS CARBON STEELS CAST IRONS		CARBON STEELS ALLOY STEELS TOOL STEELS		PREHARDENED STEELS ALLOY STEELS TOOL STEELS		ALLOY STEELS TOOL STEELS		ALLOY STEELS TOOL STEELS		STAINLESS STEELS	
HARDNESS	~ 500N/mm ²		~ HRC20		HRC20 ~ HRC30		HRC30 ~ HRC35		HRC35 ~ HRC40		HRC40 ~ HRC45			
STRENGTH	~ 500N/mm ²		500 ~ 800N/mm ²		800 ~ 1000N/mm ²		1000 ~ 1100N/mm ²		1100 ~ 1300N/mm ²		1300 ~ 1400N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8	7520	17.76	6820	16.11	5010	11.05	3110	8.32	2710	5.54	1900	3.90	3010	6.16
3/16	5550	25.34	5010	20.53	3680	16.21	2540	11.20	2140	7.75	1470	5.56	2340	8.47
1/4	4410	24.32	4060	19.82	2960	14.91	2060	10.36	1650	8.08	1150	5.63	1800	8.81
5/16	3730	27.02	3130	22.66	2410	17.43	1680	11.41	1400	8.84	960	6.06	1520	9.36
3/8	2910	31.14	2640	26.19	2010	18.63	1270	13.40	1140	10.02	800	7.20	1240	10.91
1/2	2260	25.22	2030	21.42	1580	16.41	1000	10.74	800	8.08	580	5.90	900	8.95
5/8	1950	24.20	1680	20.43	1200	16.11	820	10.49	660	7.92	460	5.52	740	8.76
3/4	1570	21.77	1320	18.29	990	13.66	670	8.63	550	6.95	380	4.90	600	7.58
7/8	1250	19.04	1130	14.97	820	11.96	560	7.48	470	6.03	330	4.20	530	6.68
1	1180	17.25	990	14.03	750	10.66	490	6.93	430	5.84	300	4.17	460	6.43



RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

PM60, 4 FLUTE MULTIPLE HELIX (Center Cut)

GYG66 SERIES

MATERIAL	P								M	
	STRUCTURAL STEELS CARBON STEELS CAST IRONS		CARBON STEELS ALLOY STEELS TOOL STEELS		PREHARDENED STEELS ALLOY STEELS TOOL STEELS		ALLOY STEELS TOOL STEELS		STAINLESS STEELS	
HARDNESS	~ HRC20		HRC20 ~ HRC30		HRC30 ~ HRC35		HRC35 ~ HRC45			
STRENGTH	~ 800N/mm ²		800 ~ 1000N/mm ²		1000 ~ 1300N/mm ²		1100 ~ 1400N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8	7020	5.53	6420	5.05	4410	3.47	2710	1.71	4810	3.79
3/16	4680	8.84	4210	7.29	2940	5.09	1800	2.84	3210	6.57
1/4	3510	8.84	3210	8.08	2210	5.56	1350	2.98	2410	6.82
5/16	2810	12.38	2570	11.32	1760	7.78	1080	4.09	1930	8.79
3/8	2570	15.81	2340	14.37	1640	9.80	1000	5.05	1600	12.13
1/2	1930	14.29	1750	12.99	1230	9.09	730	4.58	1200	10.61
5/8	1540	12.89	1400	11.72	980	8.05	600	4.17	960	9.55
3/4	1290	13.17	1170	11.97	820	8.51	500	4.42	800	9.73
1	970	9.57	880	8.70	610	6.29	360	3.09	600	7.39



RPM = rev./min.
FEED = inch/min.




RECOMMENDED CUTTING CONDITIONS

PM60, MULTI FLUTE MULTIPLE HELIX
CORNER RADIUS ROUGHING - FINE (Center Cut)

GYG69 SERIES

MATERIAL	P								M			
	STRUCTURAL STEELS CARBON STEELS		STRUCTURAL STEELS CARBON STEELS CAST IRONS		CARBON STEELS ALLOY STEELS TOOL STEELS		PREHARDENED STEELS ALLOY STEELS TOOL STEELS		ALLOY STEELS TOOL STEELS		STAINLESS STEELS	
HARDNESS	~ HRC20		HRC20 ~ HRC30		HRC30 ~ HRC40		HRC40 ~ HRC45					
STRENGTH	~ 500N/mm ²		500 ~ 800N/mm ²		800 ~ 1000N/mm ²		1000 ~ 1300N/mm ²		1300 ~ 1400N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	3810	12.00	3010	9.95	2160	6.11	1750	5.53	1250	3.95	1960	5.85
5/16	3490	16.48	2770	13.07	2050	9.02	1520	7.20	1080	4.95	1720	8.15
3/8	2870	24.89	2270	18.97	1570	11.38	1340	9.47	940	6.48	1440	10.18
1/2	2180	22.32	1630	17.70	1230	12.19	1000	9.63	700	6.63	1080	10.86
5/8	1740	23.70	1380	18.79	960	13.07	800	10.42	560	7.18	860	11.71
3/4	1450	25.18	1140	19.46	800	13.58	670	10.66	470	7.37	740	12.16
1	1130	23.31	850	17.78	590	12.41	510	10.12	350	6.91	550	11.29



RPM = rev./min.
FEED = inch/min.

CARBIDE

HSS



YG ONLY ONE END MILLS

RECOMMENDED CUTTING CONDITIONS

PM60, MULTI FLUTE ROUGHING (Center Cut)

GYG68, GYG70 SERIES

MATERIAL	P										M	
	STRUCTURAL STEELS CARBON STEELS		STRUCTURAL STEELS CARBON STEELS CAST IRONS		CARBON STEELS ALLOY STEELS TOOL STEELS		PREHARDENED STEELS ALLOY STEELS TOOL STEELS		ALLOY STEELS TOOL STEELS		STAINLESS STEELS	
HARDNESS			~ HRC20		HRC20 ~ HRC30		HRC30 ~ HRC40		HRC40 ~ HRC45			
STRENGTH	~ 500N/mm ²		500 ~ 800N/mm ²		800 ~ 1000N/mm ²		1000 ~ 1300N/mm ²		1300 ~ 1400N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	3160	10.07	2510	7.99	1800	5.12	1450	4.64	1050	3.48	1650	4.88
5/16	2890	13.98	2290	10.80	1680	7.56	1280	6.06	880	4.17	1440	6.65
3/8	2410	20.84	1900	15.90	1340	9.89	1140	7.87	800	5.68	1200	8.53
1/2	1800	18.47	1350	14.71	1030	10.36	850	8.05	580	5.45	900	9.09
5/8	1440	19.78	1140	15.66	800	10.99	660	8.44	460	5.96	720	9.66
3/4	1200	21.03	950	16.35	670	11.26	550	8.77	380	6.11	600	10.04
1	940	19.43	710	14.91	490	10.20	430	8.39	300	5.92	460	9.31
1 1/4	670	17.77	500	13.38	350	9.45	300	7.67	210	5.32	330	8.52



RPM = rev./min.
FEED = inch/min.



Being the best through innovation

HSS



SINE-POWER END MILLS

- High Performane HSS Rongher for Titanium and Titanium Alloys

CBN END MILLS

i-Xmill END MILLS

i-SMART MODULAR TYPE END MILLS

X5070 END MILLS

4G MILL END MILLS

X-POWER END MILLS

JET-POWER END MILLS

TitaNox -POWER END MILLS

V7 PLUS A END MILLS

V7 MILL INOX END MILLS

ALU-POWER HPC END MILLS

ALU-POWER END MILLS

D-POWER GRAPHITE END MILLS

D-POWER CFRP END MILLS

ROUTERS CFRP

STANDARD CARBIDE END MILLS


ONLY ONE COATED PM60 END MILLS

SINE -POWER END MILLS

TANK-POWER END MILLS

STANDARD COBALT & HSS END MILLS

TECHNICAL DATA

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
E2F64		HSS Co8, 4&6 FLUTE	D3/4	D2	1190
		RECOMMENDED CUTTING CONDITIONS			1191


◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
													◎	



E2F64 SERIES FLAT SHANK

HSSCo8, 4&6 FLUTE



Unit : Inch

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	Chamfer	No. of Flute
	D1	D2	L1	L2		
E2F64048	3/4	3/4	1 5/8	3 7/8	.030	4
E2F64901	3/4	3/4	2 1/4	4 1/2	.030	4
E2F64902	3/4	3/4	3	5 1/4	.030	4
E2F64064	1	1	2	4 1/2	.030	4
E2F64903	1	1	2	4 1/2	.030	6
E2F64904	1	1	3	5 1/2	.030	4
E2F64905	1	1	3	5 1/2	.030	6
E2F64906	1	1	4	6 1/2	.030	4
E2F64907	1	1	4	6 1/2	.030	6
E2F64116	1 1/4	1 1/4	2	4 1/2	.040	4
E2F64908	1 1/4	1 1/4	2	4 1/2	.040	6
E2F64909	1 1/4	1 1/4	3	5 1/2	.040	4
E2F64910	1 1/4	1 1/4	3	5 1/2	.040	6
E2F64911	1 1/4	1 1/4	4	6 1/2	.040	4
E2F64912	1 1/4	1 1/4	4	6 1/2	.040	6
E2F64132	1 1/2	1 1/4	2	4 1/2	.040	6
E2F64913	1 1/2	1 1/4	3	5 1/2	.040	6
E2F64914	1 1/2	1 1/4	4	6 1/2	.040	6
E2F64915	1 1/2	1 1/4	6	8 1/2	.040	6
E2F64200	2	2	2	5 3/4	.040	6
E2F64916	2	2	3	6 3/4	.040	6
E2F64917	2	2	4	7 3/4	.040	6
E2F64918	2	2	6	9 3/4	.040	6
E2F64919	2	2	8	11 3/4	.040	6

Cutting Dia. Tolerance(inch)	Shank Dia. Tolerance(inch)
0~ + .0030	- .0001~ - .0005

※ Radius, coatings and HSS-PM available on request

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70								◎	




RECOMMENDED CUTTING CONDITIONS

HSSCo8, 4&6 FLUTE

E2F64 SERIES

SIDE CUTTING


MATERIAL	S			
	TITANIUM ALLOYS		TITANIUM ALLOYS - DIFFICULT	
DIAMETER	RPM	Feed	RPM	Feed
3/4	382	4	306	3
1	287	4	229	3
1-1/4	229	4	183	3
1-1/2	191	4	153	3
2	143	4	115	3



RPM = rev./min.
FEED = inch/min.

SLOTING

MATERIAL	S			
	TITANIUM ALLOYS		TITANIUM ALLOYS - DIFFICULT	
DIAMETER	RPM	Feed	RPM	Feed
3/4	331	3	204	2
1	248	4	153	2
1-1/4	199	4	122	2
1-1/2	166	4	102	2
2	124	4	76	3



RPM = rev./min.
FEED = inch/min.




Being the best through innovation

HSS



Global Cutting Tool Leader **YG-1**














TANK-POWER END MILLS

- Next Generation of Powdered Metal End Mills
Higher Edge Strength & Feed Rates

SELECTION GUIDE



HSS TANK-POWER END MILLS

◎ : Excellent ○ : Good

ITEM	MODEL	DESCRIPTION	SIZE		PAGE	
			MIN	MAX		
INCH						
E9983		PREMIUM HSS-PM, 2 FLUTE REGULAR LENGTH	◆	D1/8	D1	1196
E9984		PREMIUM HSS-PM, 2 FLUTE REGULAR LENGTH DOUBLE	◆	D1/8	D1	1197
E9985		PREMIUM HSS-PM, 4 FLUTE REGULAR LENGTH	◆	D1/8	D1	1198
E9986		PREMIUM HSS-PM, 4 FLUTE REGULAR LENGTH DOUBLE	◆	D1/8	D1	1199
E9988		PREMIUM HSS-PM, 3&4 FLUTE 60° HELIX REGULAR LENGTH	◆	D1/4	D1	1200
E9992		PREMIUM HSS-PM, 2 FLUTE REGULAR LENGTH BALL NOSE	◆	R1/16	R1/2	1201
E9990		PREMIUM HSS-PM, MULTI FLUTE REGULAR LENGTH FINE PITCH ROUGHING	◆	D1/4	D1-1/4	1202
E9991		PREMIUM HSS-PM, MULTI FLUTE REGULAR LENGTH COARSE PITCH ROUGHING	◆	D1/4	D1-1/4	1203
E9A86		PREMIUM HSS-PM, MULTI FLUTE LONG LENGTH FINE PITCH ROUGHING	◆	D5/16	D1-1/4	1204
E9A87		PREMIUM HSS-PM, MULTI FLUTE LONG LENGTH COARSE PITCH ROUGHING	◆	D5/16	D1-1/4	1205
E9921		PREMIUM HSS-PM, MULTI FLUTE FINE PITCH ROUGHING EXTENDED NECK CENTER CUTTING	◆	D1/2	D1-1/4	1206
RECOMMENDED CUTTING CONDITIONS						1207

◆ U.S.A Stock

Carbon Steels	Alloy Steels	P			High Hardened Steels	M	K	N				S						
		Prehardened Steels	Hardened Steels	HRc40~45				HRc45~55	HRc55~70	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70													
◎	◎	◎				◎	◎	○										
◎	◎	◎				◎	◎	○										
◎	◎	◎				◎	◎	○										
◎	◎	◎				◎	◎	○										
◎	◎	◎				◎	◎	○										
◎	◎	◎				◎	◎	○										
◎	◎	◎				◎	◎	○										
◎	◎	◎				◎	◎	○										






E9983 SERIES FLAT SHANK

PREMIUM HSS-PM, 2 FLUTE REGULAR LENGTH

► Faster feed & speed than normal HSS can be applied to hardened steels up to Rc 45. Accordingly, YPM made by powder metallurgy makes much higher productivity possible.



◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TANK-POWER COATED				
E9983008	E9983008TF	1/8	3/8	3/8	2-5/16
E9983012	E9983012TF	3/16	3/8	7/16	2-5/16
E9983016	E9983016TF	1/4	3/8	1/2	2-5/16
E9983020	E9983020TF	5/16	3/8	9/16	2-5/16
E9983024	E9983024TF	3/8	3/8	9/16	2-5/16
E9983032	E9983032TF	1/2	1/2	1	3
E9983040	E9983040TF	5/8	5/8	1-5/16	3-7/16
E9983048	E9983048TF	3/4	3/4	1-5/16	3-7/16
E9983056	E9983056TF	7/8	7/8	1-1/2	3-3/4
E9983064	E9983064TF	1	1	1-5/8	4-1/8

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎				◎	◎	○						



E9984 SERIES FLAT SHANK

PREMIUM HSS-PM, 2 FLUTE REGULAR LENGTH DOUBLE

► Series E9984, E9984 two flute, end mills are the double end version of E9983, E9983 single-end tools. Faster feed & speed than normal HSS can be applied to hardened steels up to Rc 45. Accordingly, YPM made by powder metallurgy makes much higher productivity possible.



◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TANK-POWER COATED				
E9984008	E9984008TF	1/8	3/8	3/8	3-1/16
E9984012	E9984012TF	3/16	3/8	7/16	3-1/8
E9984016	E9984016TF	1/4	3/8	1/2	3-1/8
E9984020	E9984020TF	5/16	3/8	9/16	3-1/8
E9984024	E9984024TF	3/8	3/8	9/16	3-1/8
E9984032	E9984032TF	1/2	1/2	13/16	3-3/4
E9984040	E9984040TF	5/8	5/8	1-1/8	4-1/2
E9984048	E9984048TF	3/4	3/4	1-5/16	5
E9984056	E9984056TF	7/8	7/8	1-9/16	5-1/2
E9984064	E9984064TF	1	1	1-5/8	5-7/8

Mill Dia. Tolerance (inch)	
0~-0.0010	** 0~-0.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎				◎	◎	○						



E9985 SERIES FLAT SHANK

PREMIUM HSS-PM, 4 FLUTE REGULAR LENGTH

► Faster feed & speed than normal HSS can be applied to hardened steels up to Rc 45. Accordingly, YPM made by powder metallurgy makes much higher productivity possible.



◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TANK-POWER COATED				
E9985008	E9985008TF	1/8	3/8	3/8	2-5/16
E9985012	E9985012TF	3/16	3/8	1/2	2-3/8
E9985016	E9985016TF	1/4	3/8	5/8	2-7/16
E9985020	E9985020TF	5/16	3/8	3/4	2-1/2
E9985024	E9985024TF	3/8	3/8	3/4	2-1/2
E9985032	E9985032TF	1/2	1/2	1-1/4	3-1/4
E9985040	E9985040TF	5/8	5/8	1-5/8	3-3/4
E9985048	E9985048TF	3/4	3/4	1-5/8	3-7/8
E9985056	E9985056TF	7/8	7/8	1-7/8	4-1/8
E9985064	E9985064TF	1	1	2	4-1/2

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎				◎	◎	○						



E9986 SERIES FLAT SHANK

PREMIUM HSS-PM, 4 FLUTE REGULAR LENGTH DOUBLE

► Series E9986,EP986 four flute end mills are the double end version of E9985,EP985 single-end tools. Faster feed & speed than normal HSS can be applied to hardened steels up to Rc 45. Accordingly, YPM made by powder metallurgy makes much higher productivity possible.



◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TANK-POWER COATED				
E9986008	E9986008TF	1/8	3/8	3/8	3-1/16
E9986012	E9986012TF	3/16	3/8	1/2	3-1/4
E9986016	E9986016TF	1/4	3/8	5/8	3-3/8
E9986020	E9986020TF	5/16	3/8	3/4	3-1/2
E9986024	E9986024TF	3/8	3/8	3/4	3-1/2
E9986032	E9986032TF	1/2	1/2	1	4-1/8
E9986040	E9986040TF	5/8	5/8	1-3/8	5
E9986048	E9986048TF	3/4	3/4	1-5/8	5-5/8
E9986056	E9986056TF	7/8	7/8	1-7/8	6-1/8
E9986064	E9986064TF	1	1	1-7/8	6-3/8

Mill Dia. Tolerance (inch)	
0~-0.0010	** 0~-0.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎				◎	◎	○						



E9988 SERIES FLAT SHANK

PREMIUM HSS-PM, 3&4 FLUTE 60° HELIX REGULAR LENGTH

► Faster feed & speed than normal HSS can be applied to hardened steels up to Rc 45. Accordingly, YPM made by powder metallurgy makes much higher productivity possible.




◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
UNCOATED	TANK-POWER COATED					
E9988016	E9988016TF	1/4	3/8	5/8	2-7/16	3
E9988020	E9988020TF	5/16	3/8	3/4	2-1/2	3
E9988024	E9988024TF	3/8	3/8	3/4	2-1/2	3
E9988028	E9988028TF	7/16	3/8	1	2-11/16	3
E9988032	E9988032TF	1/2	1/2	1-1/4	3-1/4	3
E9988040	E9988040TF	5/8	5/8	1-5/8	3-3/4	3
E9988048	E9988048TF	3/4	3/4	1-5/8	3-7/8	3
E9988901	E9988901TF	7/8	3/4	1-7/8	4-1/8	4
E9988056	E9988056TF	7/8	7/8	1-7/8	4-1/8	4
E9988064	E9988064TF	1	1	2	4-1/2	4

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.



◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎				◎	◎	○						



E9992 SERIES FLAT SHANK

PREMIUM HSS-PM, 2 FLUTE REGULAR LENGTH BALL NOSE

► The two flute ball end mills are designed for milling of radius bottom slots, fillets and special contours. The end teeth are cut to center allowing these end mills to drill into material at the beginning of a slotting cut. The two flute design provides good chip removal ability in slotting.



◆ U.S.A Stock

Unit : Inch

EDP No.		Radius of Ball Nose R (±.001)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
UNCOATED	TANK-POWER COATED					
E9992008	E9992008TF	R1/16	1/8	3/8	3/8	2-5/16
E9992012	E9992012TF	R3/32	3/16	3/8	1/2	2-3/8
E9992016	E9992016TF	R1/8	1/4	3/8	5/8	2-7/16
E9992020	E9992020TF	R5/32	5/16	3/8	3/4	2-1/2
E9992024	E9992024TF	R3/16	3/8	3/8	3/4	2-1/2
E9992032	E9992032TF	R1/4	1/2	1/2	1	3
E9992040	E9992040TF	R5/16	5/8	5/8	1-3/8	3-1/2
E9992048	E9992048TF	R3/8	3/4	3/4	1-5/8	3-7/8
E9992056	E9992056TF	R7/16	7/8	7/8	2	4-1/4
E9992064	E9992064TF	R1/2	1	1	2-1/4	4-3/4

Mill Dia. Tolerance (inch)
0~- .0015

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎				◎	◎	○						



E9990 SERIES FLAT SHANK

PREMIUM HSS-PM, MULTI FLUTE REGULAR LENGTH FINE PITCH ROUGHING

► This TANK-POWER rougher is designed for high production metal removal in a wide range of work piece material. It is suitable for a very broad spectrum of materials having up to high tensile strengths. In many cases, the milled surfaces are of acceptable quality.



◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
UNCOATED	TANK-POWER COATED					
E9990016	E9990016TF	1/4	3/8	5/8	2-7/16	3
E9990907	E9990907TF	1/4	3/8	1-1/8	2-15/16	3
E9990020	E9990020TF	5/16	3/8	3/4	2-1/2	3
E9990024	E9990024TF	3/8	3/8	3/4	2-1/2	4
E9990028	E9990028TF	7/16	3/8	1	2-11/16	4
E9990032	E9990032TF	1/2	1/2	1-1/4	3-1/4	4
E9990908	E9990908TF	1/2	1/2	1-5/8	3-5/8	4
E9990036	E9990036TF	9/16	1/2	1-3/8	3-3/8	4
E9990040	E9990040TF	5/8	5/8	1-5/8	3-3/4	4
E9990048	E9990048TF	3/4	3/4	1-5/8	3-7/8	4
E9990948	E9990948TF	3/4	5/8	1-5/8	3-7/8	4
E9990909	E9990909TF	3/4	3/4	2-1/2	4-3/4	4
E9990056	E9990056TF	7/8	7/8	1-7/8	4-1/8	5
E9990901	E9990901TF	7/8	3/4	1-7/8	4-1/8	5
E9990064	E9990064TF	1	1	2	4-1/2	5
E9990905	E9990905TF	1	1	3	5-1/2	5
E9990108	E9990108TF	1-1/8	1	2	4-1/2	6
E9990116	E9990116TF	1-1/4	1-1/4	2	4-1/2	6
E9990906	E9990906TF	1-1/4	1-1/4	3	5-1/2	6

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060

◎ : Excellent ○ : Good


P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎			◎	◎	○						



E9991 SERIES FLAT SHANK

PREMIUM HSS-PM, MULTI FLUTE REGULAR LENGTH COARSE PITCH ROUGHING

► This TANK-POWER rougher is designed for high production metal removal in a wide range of work piece material. It is suitable for a very broad spectrum of materials having up to high tensile strengths.




◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
UNCOATED	TANK-POWER COATED					
E9991016	E9991016TF	1/4	3/8	5/8	2-7/16	3
E9991902	E9991902TF	1/4	3/8	1-1/8	2-15/16	3
E9991020	E9991020TF	5/16	3/8	3/4	2-1/2	3
E9991024	E9991024TF	3/8	3/8	3/4	2-1/2	4
E9991028	E9991028TF	7/16	3/8	1	2-11/16	4
E9991032	E9991032TF	1/2	1/2	1-1/4	3-1/4	4
E9991903	E9991903TF	1/2	1/2	1-5/8	3-5/8	4
E9991036	E9991036TF	9/16	1/2	1-3/8	3-3/8	4
E9991040	E9991040TF	5/8	5/8	1-5/8	3-3/4	4
E9991048	E9991048TF	3/4	3/4	1-5/8	3-7/8	4
E9991948	E9991948TF	3/4	5/8	1-5/8	3-7/8	4
E9991904	E9991904TF	3/4	3/4	2-1/2	4-3/4	4
E9991056	E9991056TF	7/8	7/8	1-7/8	4-1/8	5
E9991901	E9991901TF	7/8	3/4	1-7/8	4-1/8	5
E9991064	E9991064TF	1	1	2	4-1/2	5
E9991905	E9991905TF	1	1	3	5-1/2	5
E9991108	E9991108TF	1-1/8	1	2	4-1/2	6
E9991116	E9991116TF	1-1/4	1-1/4	2	4-1/2	6
E9991906	E9991906TF	1-1/4	1-1/4	3	5-1/2	6

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060



◎ : Excellent ○ : Good


P				H	M	K	N						S
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎			◎	◎	○						



E9A86 SERIES FLAT SHANK

PREMIUM HSS-PM, MULTI FLUTE LONG LENGTH FINE PITCH ROUGHING

► This TANK-POWER rougher is designed for high production metal removal in a wide range of work piece material. It is suitable for a very broad spectrum of materials having up to high tensile strengths.




◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
UNCOATED	TANK-POWER COATED					
E9A86020	E9A86020TF	5/16	3/8	1-3/8	3-3/16	3
E9A86024	E9A86024TF	3/8	3/8	1-1/2	3-1/4	4
E9A86924	E9A86924TF	3/8	3/8	1-1/2	4	4
E9A86032	E9A86032TF	1/2	1/2	2	4	4
E9A86040	E9A86040TF	5/8	5/8	2-1/2	4-5/8	4
E9A86048	E9A86048TF	3/4	5/8	3	5-1/8	4
E9990902	E9990902TF	3/4	3/4	3	5-1/4	4
E9A86056	E9A86056TF	7/8	3/4	3-1/2	5-3/4	5
E9A86956	E9A86956TF	7/8	7/8	3-1/2	5-3/4	5
E9990903	E9990903TF	1	1	4	6-1/2	5
E9A86116	E9A86116TF	1-1/4	3/4	4	6-1/4	6
E9990904	E9990904TF	1-1/4	1-1/4	4	6-1/2	6

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060



◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎			◎	◎	○						



E9A87 SERIES FLAT SHANK

PREMIUM HSS-PM, MULTI FLUTE LONG LENGTH COARSE PITCH ROUGHING

► This TANK-POWER rougher is designed for high production metal removal in a wide range of work piece material. It is suitable for a very broad spectrum of materials having up to high tensile strengths.




◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
UNCOATED	TANK-POWER COATED					
E9A87020	E9A87020TF	5/16	3/8	1-3/8	3-3/16	3
E9A87024	E9A87024TF	3/8	3/8	1-1/2	3-1/4	4
E9A87924	E9A87924TF	3/8	3/8	1-1/2	4	4
E9A87032	E9A87032TF	1/2	1/2	2	4	4
E9A87040	E9A87040TF	5/8	5/8	2-1/2	4-5/8	4
E9A87048	E9A87048TF	3/4	5/8	3	5-1/8	4
E9A87948	E9A87948TF	3/4	3/4	3	5-1/4	4
E9A87056	E9A87056TF	7/8	3/4	3-1/2	5-3/4	5
E9A87956	E9A87956TF	7/8	7/8	3-1/2	5-3/4	5
E9A87064	E9A87064TF	1	1	4	6-1/2	5
E9A87116	E9A87116TF	1-1/4	3/4	4	6-1/4	6
E9A87917	E9A87917TF	1-1/4	1-1/4	4	6-1/2	6

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060



◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	◎			◎	◎	○						



E9921 SERIES FLAT SHANK

**PREMIUM HSS-PM, MULTI FLUTE FINE PITCH ROUGHING
EXTENDED NECK CENTER CUTTING**

► This TANK-POWER rougher is designed for high production metal removal in a wide range of work piece material. It is suitable for a very broad spectrum of materials having up to high tensile strengths.




◆ U.S.A Stock

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Reach Extended Neck	Overall Length	No. of Flute
UNCOATED	TiN COATED						
EP20322	EP20322F	1/2	1/2	1-1/4	3	5	5
EP20402	EP20402F	5/8	5/8	1-5/8	4	6-1/8	5
EP20482	EP20482F	3/4	3/4	1-5/8	4	6-1/4	5
EP20484	EP20484F	3/4	3/4	1-5/8	6	8-1/4	5
EP20642	EP20642F	1	1	2	4	6-1/2	6
EP20643	EP20643F	1	1	2	6	8-1/2	6
EP21161	EP21161F	1-1/4	1 1/4	2	4	6-1/2	6
EP21162	EP21162F	1-1/4	1 1/4	2	6	8-1/2	6

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060



◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎				◎	◎	○						




RECOMMENDED CUTTING CONDITIONS

PREMIUM HSS-PM, 2 FLUTE FINISH - SLOTTING

E9983, E9984 SERIES

MATERIAL	P									
	STRUCTURAL STEELS CARBON STEELS		STRUCTURAL STEELS CARBON STEELS CAST IRONS		CARBON STEELS ALLOY STEELS TOOL STEELS		PREHARDENED STEELS ALLOY STEELS TOOL STEELS		ALLOY STEELS TOOL STEELS AUSTENITIC STAINLESS STEELS	
HARDNESS	~ 500N/mm ²		~HRc20		HRc20~HRc30		HRc30~HRc35		HRc35~HRc40	
STRENGTH	~ 500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1100N/mm ²		1100~1300N/mm ²	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
	1/8	4600	5.9	3800	5.0	3150	4.2	2150	2.8	1650
3/16	3800	8.5	3150	6.7	2600	6.1	1650	3.5	1350	2.6
1/4	3150	9.1	2650	7.5	2100	6.6	1350	3.8	1050	3.0
5/16	2500	9.4	2100	8.2	1700	6.9	1100	3.9	855	3.0
3/8	2100	10.1	1800	8.9	1450	7.6	910	4.2	715	3.4
1/2	1650	9.3	1350	8.1	1050	7.0	665	3.9	525	2.9
5/8	1300	9.1	1100	7.3	855	6.1	535	3.6	425	2.8
3/4	995	7.9	820	6.2	710	5.3	450	3.2	360	2.5
7/8	795	6.2	675	5.1	560	4.3	375	2.7	300	2.0
1	710	5.2	590	4.7	465	3.9	335	2.5	235	1.7




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min. FEED = inch/min.

PREMIUM HSS-PM, 4 FLUTE FINISH - SIDE CUTTING

E9985, E9986 SERIES

MATERIAL	P									
	STRUCTURAL STEELS CARBON STEELS		STRUCTURAL STEELS CARBON STEELS CAST IRONS		CARBON STEELS ALLOY STEELS TOOL STEELS		PREHARDENED STEELS ALLOY STEELS TOOL STEELS		ALLOY STEELS TOOL STEELS AUSTENITIC STAINLESS STEELS	
HARDNESS	~ 500N/mm ²		~HRc20		HRc20~HRc30		HRc30~HRc35		HRc35~HRc40	
STRENGTH	~ 500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1100N/mm ²		1100~1300N/mm ²	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
	1/8	6300	17.7	6000	14.4	4250	10.4	2700	7.2	2320
3/16	4600	19.7	4100	16.1	3040	12.6	2070	8.5	1780	6.2
1/4	3800	22.1	3300	18.1	2500	13.0	1700	9.7	1400	7.1
5/16	3100	22.4	2600	18.9	2000	14.2	1400	9.4	1150	7.2
3/8	2500	24.8	2200	20.5	1680	15.0	1180	10.2	960	7.7
1/2	1900	22.1	1720	18.5	1270	14.4	860	9.3	690	2.7
5/8	1600	20.1	1410	16.9	1000	13.3	690	8.9	620	6.7
3/4	1400	17.7	1150	15.2	830	11.5	580	7.3	470	5.7
7/8	1030	15.8	930	12.4	675	9.8	470	6.3	390	5.1
1	1000	14.6	830	11.8	620	8.8	420	5.6	360	4.9




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min. FEED = inch/min.

PREMIUM HSS-PM, 3&4 FLUTE 60° HELIX - SIDE CUTTING

E9988 SERIES

MATERIAL	P					
	STRUCTURAL STEELS CARBON STEELS CAST IRONS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALLOY STEELS, TOOL STEELS AUSTENITIC STAINLESS STEELS	
HARDNESS	~HRc20		HRc20 ~ HRc30		HRc30 ~ HRc40	
STRENGTH	500 ~ 800N/mm ²		800 ~ 1000N/mm ²		1000 ~ 1300N/mm ²	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED
1/4	3850	7.9	2500	5.3	1900	3.5
5/16	3050	7.9	2100	6.3	1700	3.5
3/8	2700	8.5	1700	6.3	1450	3.8
1/2	1850	9.7	1200	6.3	960	4.1
5/8	1300	11.0	845	8.5	690	5.4
3/4	895	14.6	580	11.9	475	7.9
7/8	720	16.6	475	14.0	380	8.8
1	630	19.0	415	16.0	335	10.0




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

PREMIUM HSS-PM, MULTI FLUTE ROUGHING - SIDE CUTTING

E9990, E9991, E9A86, E9A87, E9921 SERIES

MATERIAL	P								M	
	STRUCTURAL STEELS CARBON STEELS		STRUCTURAL STEELS CARBON STEELS CAST IRONS		CARBON STEELS ALLOY STEELS TOOL STEELS		PREHARDENED STEELS ALLOY STEELS TOOL STEELS		STAINLESS STEELS	
HARDNESS	~HRc20		HRc20 ~ HRc30		HRc30 ~ HRc35		HRc35 ~ HRc40			
STRENGTH	~800N/mm ²		800 ~ 1000N/mm ²		1000 ~ 1100N/mm ²		1100 ~ 1300N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	2650	7.8	2050	6.3	1450	4.4	1200	3.4	1900	5.6
3/8	1900	13.1	1500	10.1	1050	6.4	885	5.2	1270	8.6
1/2	1450	14.2	1100	11.4	805	7.9	665	6.1	950	9.3
5/8	1150	14.2	905	11.4	630	7.9	525	6.1	760	9.7
3/4	960	14.4	780	11.4	540	7.9	445	6.1	630	9.5
7/8	845	14.5	615	11.4	445	7.8	375	6.1	540	9.3
1	740	14.0	560	10.6	395	7.4	315	6.0	470	9.0




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

PREMIUM HSS-PM, 2 FLUTE BALL NOSE - PROFILING

E9992 SERIES

MATERIAL	P							
	STRUCTURAL STEELS CARBON STEELS		STRUCTURAL STEELS CARBON STEELS CAST IRONS		CARBON STEELS ALLOY STEELS TOOL STEELS		PREHARDENED STEELS ALLOY STEELS TOOL STEELS	
HARDNESS	~HRc20		HRc20 ~ HRc30		HRc20 ~ HRc30		HRc30 ~ HRc40	
STRENGTH	~500N/mm ²		500 ~ 800N/mm ²		800 ~ 1000N/mm ²		1000 ~ 1300N/mm ²	
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8	6800	12.3	5300	8.2	3550	4.5	1850	2.1
3/16	5100	15.3	4000	10.3	2650	5.7	1350	2.7
1/4	4050	16.8	3150	11.2	2100	6.2	1100	3.0
5/16	3250	18.1	2550	12.2	1700	6.9	860	3.0
3/8	2750	19.9	2100	13.4	1450	7.6	700	3.4
1/2	2100	17.8	1600	12.0	1100	6.8	530	2.9
5/8	1600	16.6	1250	11.1	860	6.1	425	2.8
3/4	1350	14.7	1050	9.8	700	5.4	360	2.5
7/8	1100	12.6	865	8.4	560	4.6	300	2.1
1	890	10.5	690	7.0	445	3.9	235	1.7



※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.




Being the best through innovation

HSS



Global Cutting Tool Leader **YG-1**
























COBALT & HSS END MILLS

- General Purpose, Non-coated, Many Coatings Available

SELECTION GUIDE

STANDARD COBALT & HSS END MILLS

◎ : Excellent ○ : Good

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
E2039 E2042		HSSCo8, MULTI FLUTE MEDIUM LENGTH CENTER CUTTING	D1	D2	1242
E2040 E1040		HSSCo8 & HSS, 4 FLUTE LONG LENGTH CENTER CUTTING	D1/4	D1-1/2	1243
E2162 E1162		HSSCo8 & HSS, 6 FLUTE LONG LENGTH CENTER CUTTING	D1/2	D2	1243
E2041 E1041		HSSCo8 & HSS, 4 FLUTE EXTRA LONG LENGTH CENTER CUTTING	D1/4	D1-1/4	1244
E2175 E1175		HSSCo8 & HSS, 6 FLUTE EXTRA LONG LENGTH CENTER CUTTING	D1/2	D2	1244
E2053 E1053		HSSCo8 & HSS, 4 FLUTE REGULAR LENGTH DOUBLE CENTER CUTTING	D1/8	D1	1245
E2100 E1100		HSSCo8 & HSS, 6 FLUTE REGULAR with COMBINATION 2" SHANK CENTER CUTTING	D2	D2	1247
E2001 E1001		HSSCo8 & HSS, 2 FLUTE MINIATURE STUB LENGTH DOUBLE	D1/32	D3/16	1248
E2003 E1003		HSSCo8 & HSS, 2 FLUTE MINIATURE REGULAR LENGTH DOUBLE	D1/32	D3/16	1249
E2005 E1005		HSSCo8 & HSS, 2 FLUTE MINIATURE LONG LENGTH DOUBLE	D1/16	D3/16	1250
E2002 E1002		HSSCo8 & HSS, 4 FLUTE MINIATURE STUB LENGTH DOUBLE	D1/16	D3/16	1251
E2004 E1004		HSSCo8 & HSS, 4 FLUTE MINIATURE REGULAR LENGTH DOUBLE	D1/16	D3/16	1252
E2006 E1006		HSSCo8 & HSS, 4 FLUTE MINIATURE LONG LENGTH DOUBLE	D1/16	D3/16	1253
E2008 E1008		HSSCo8 & HSS, 2 FLUTE MINIATURE STUB LENGTH BALL NOSE DOUBLE	R1/32	R3/32	1254
E2013 E1013		HSSCo8 & HSS, 2 FLUTE MINIATURE REGULAR LENGTH BALL NOSE DOUBLE	R1/64	R3/32	1255
E2015 E1015		HSSCo8 & HSS, 2 FLUTE MINIATURE LONG LENGTH BALL NOSE DOUBLE	R1/32	R3/32	1256
E1070		HSS, 2 FLUTE 42° HELIX REGULAR & MEDIUM LENGTH for ALUMINUM	D1/4	D2	1257
E1071		HSS, 2 FLUTE 42° HELIX LONG LENGTH for ALUMINUM	D1/4	D2	1258
E1072		HSS, 2 FLUTE 42° HELIX EXTRA LONG LENGTH for ALUMINUM	D1/4	D1-1/2	1258
E2086		HSSCo8, MULTI FLUTE STUB LENGTH FINE PITCH ROUGHING CENTER CUTTING	D1/4	D1	1259
E2085		HSSCo8, MULTI FLUTE REGULAR LENGTH FINE PITCH ROUGHING CENTER CUTTING	D1/4	D1	1260

P					H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎	○						○						
◎	◎	○						○		○				
◎	◎													

SELECTION GUIDE

STANDARD COBALT & HSS END MILLS

◎ : Excellent ○ : Good

ITEM	MODEL	DESCRIPTION	SIZE		PAGE
			MIN	MAX	
INCH					
E2079		HSSCo8, MULTI FLUTE REGULAR LENGTH FINE PITCH ROUGHING	D1/4	D2	1261
E2077		HSSCo8, MULTI FLUTE LONG LENGTH FINE PITCH ROUGHING	D1/2	D2	1262
E2086		HSSCo8, 3 FLUTE STUB LENGTH FINE PITCH ROUGHING CENTER CUTTING	D1/4	D1	1263
E2170		HSSCo8, MULTI FLUTE REGULAR LENGTH COARSE PITCH ROUGHING	D1/4	D2	1264
E2171		HSSCo8, MULTI FLUTE MEDIUM LENGTH COARSE PITCH ROUGHING	D1	D2	1265
E2172		HSSCo8, MULTI FLUTE LONG LENGTH COARSE PITCH ROUGHING	D1/2	D2	1266
E2241		HSSCo8, 3 FLUTE STUB LENGTH COARSE PITCH ROUGHING CENTER CUTTING	D1/4	D1	1267
E2195		HSSCo8, MULTI FLUTE REGULAR LENGTH COARSE PITCH ROUGHING CENTER CUTTING	D1/2	D1-1/2	1268
E2197		HSSCo8, MULTI FLUTE LONG LENGTH COARSE PITCH ROUGHING CENTER CUTTING	D1/2	D1-1/2	1268
E2193 E2125		HSSCo8, MULTI FLUTE REGULAR & LONG LENGTH COARSE PITCH ROUGHING BALL NOSE	R1/8	R3/4	1269
E2248		HSSCo8, MULTI FLUTE REGULAR LENGTH ROUGHING & FINISHING	D1/4	D2	1270
E2191		HSSCo8, 3 FLUTE 37° HELIX REGULAR LENGTH ROUGHING for ALUMINUM	D1/4	D1-1/2	1271
E2226 E2192		HSSCo8, 3 FLUTE 37° HELIX MEDIUM & LONG LENGTH ROUGHING for ALUMINUM	D1/2	D1-1/2	1272
E2163 E1163		HSSCo8 & HSS, 2 FLUTE 15° HELIX for KEYWAY CUTTING	D1/8	D1	1273
E2120 E2121		HSSCo8, 3&4 FLUTE 60° HELIX REGULAR LENGTH	D1/4	D3/4	1274
E2160		HSSCo8, 3 FLUTE SHORT LENGTH THROW AWAY	D7/8 D1/16	D2 D1/4	1275
E2161		HSSCo8, 3 FLUTE LONG LENGTH THROW AWAY	D1/16	D1/4	1275
E2237 E1237		HSSCo8 & HSS, 4 FLUTE CORNER ROUNDING	D1/4	D5/8	1276
METRIC					
E2482 E1482		HSSCo8 & HSS, 2 FLUTE REGULAR LENGTH - METRIC	D2.0 (.0787)	D45.0 (1.772)	1277
E2483 E1483		HSSCo8 & HSS, 4 FLUTE REGULAR LENGTH - METRIC	D2.0 (.0787)	D45.0 (1.772)	1278
END MILL SET SERIES / RECOMMENDED CUTTING CONDITIONS					1281

Carbon Steels ~HRc20	Alloy Steels HRc20~30	Prehardened Steels HRc30~40	Hardened Steels		High Hardened Steels HRc55~70	Stainless Steels	Cast Iron	N				S		
			HRc40~45	HRc45~55				Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		◎				
◎	◎	○						○		◎				
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				
◎	◎	○						○		○				

SUPER CUTTING END MILLS

DESCRIPTION				YG-1	**ANSI	REMARK
TYPE	NO. OF FLUTE	LENGTH OF CUT	TYPE OF END			
SINGLE END	2	REGULAR LONG EX. LONG	ALL	+ .0010 .0000 * (+ .0015) .0000	+ .0030 .0000	
	MULTIPLE	ALL	ALL	+ .0010 .0000 * (+ .0015) .0000	+ .0030 .0000	
KEY WAY	2	ALL	CENTER CUTTING	+ .0000 - .0015	+ .0000 - .0015	
DOUBLE END	2	REGULAR	ALL	.0000 - .0010 * (.0000) - .0020	.0000 - .0015	
	4	ALL	CENTER CUTTING	.0000 - .0010 * (.0000) - .0020	.0000 - .0015	
	4	ALL	NON CENTER CUTTING	+ .0010 .0000 * (.0000) - .0020	+ .0030 .0000 * (.0000) - .0025	
3/16 SHANK DOUBLE END	2	STUB REGULAR	ALL	.0000 - .0010 * (.0000) - .0020	.0000 - .0015	
		LONG	ALL	+ .0010 .0000 * (.0000) - .0020	+ .0030 .0000 * (.0000) - .0025	
	4	ALL	ALL	+ .0010 .0000 * (.0000) - .0020	+ .0030 .0000 * (.0000) - .0025	
ROUGHING	MULTIPLE	ALL	ALL	+ .0060 .0000	+ .025 - .005	
ROUGHING & FINISHING	MULTIPLE	REGULAR	ALL	+ .0025 + .0005		
HELICAL 60°	3.4	REGULAR	CENTER CUTTING	+ .0010 .0000 * (+ .0015) .0000		
THROW AWAY 1/4 SHANK	3	ALL	CENTER CUTTING	- .0005 - .0013		

* The shank of End Mills is the same diameter as the cutting portion.

** ANSI B94-19-1977 published by the American Society of Mechanical Engineers.

HSSCo8 & HSS, 2 FLUTE REGULAR LENGTH

► These end mills are furnished as regular with right-hand cutting and right-hand helical flutes. All shanks are flatted for holder set screw. These are designed for slotting, drilling, pocketing and general-purpose operation.



P.1281, 1287, 1291

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
01289	01039	1/8	3/8	3/8	2-5/16
01291	01041	5/32	3/8	7/16	2-5/16
01293	01043	3/16	3/8	7/16	2-5/16
01295	01045	7/32	3/8	1/2	2-5/16
01297	01047	1/4	3/8	1/2	2-5/16
01299	01049	9/32	3/8	9/16	2-5/16
01301	01051	5/16	3/8	9/16	2-5/16
01303	01053	11/32	3/8	9/16	2-5/16
01305	01055	3/8	3/8	9/16	2-5/16
01308	01058	13/32	3/8	13/16	2-1/2
01312	01062	7/16	3/8	13/16	2-1/2
01316	01066	15/32	3/8	13/16	2-1/2
01320	01070	1/2	3/8	13/16	2-1/2
01321	01071	1/2	1/2	1	3
01328	01078	9/16	1/2	1-1/8	3-1/8
01336	01086	5/8	1/2	1-1/8	3-1/8
01337	01087	5/8	5/8	1-5/16	3-7/16
01348	01098	11/16	5/8	1-5/16	3-7/16
01357	01107	3/4	1/2	1-5/16	3-5/16
01358	01108	3/4	5/8	1-5/16	3-7/16
01359	01109	3/4	3/4	1-5/16	3-7/16
01373	01123	13/16	5/8	1-1/2	3-5/8
01391	01141	7/8	3/4	1-1/2	3-3/4
01394	01144	7/8	7/8	1-1/2	3-3/4
01409	01159	15/16	7/8	1-1/2	3-3/4
01420	01170	1	5/8	1-1/2	3-5/8

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

► NEXT PAGE

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2030 SERIES 8% COBALT (M42) FLAT SHANK
E1030 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 2 FLUTE REGULAR LENGTH

► These end mills are furnished as regular with right-hand cutting and right-hand helical flutes. All shanks are flatted for holder set screw. These are designed for slotting, drilling, pocketing and general-purpose operation.



HSS Co8 HSS 2 30° FLAT P.1281, 1287, 1291

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
01422	01172	1	3/4	1-1/2	3-3/4
01426	01176	1	1	1-5/8	4-1/8
01435	01185	1-1/8	1	1-5/8	4-1/8
01445	01195	1-1/4	1-1/4	1-5/8	4-1/8
01451	01201	1-3/8	1	1-5/8	4-1/8
01453	01203	1-3/8	1-1/4	1-5/8	4-1/8
01459	01209	1-1/2	1	1-5/8	4-1/8
01461	01211	1-1/2	1-1/4	1-5/8	4-1/8
01469	01219	1-3/4	1-1/4	1-5/8	4-1/8
01477	01227	2	1-1/4	1-5/8	4-1/8
* 01480	* 01230	2	2	2	5-3/4

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
 - Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
 - Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
 - Coated Price Shown in Price List. Call for Availability.
- * Combination Shank

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○						○		○				



E2080 SERIES 8% COBALT (M42) FLAT SHANK
E1080 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 2 FLUTE LONG LENGTH

► Longer flute length than E2030 type and allows deeper cutting.



HSS Co8 HSS 2 30° FLAT P.1281, 1287, 1291

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
02297	02047	1/4	3/8	1-1/4	3-1/8
02301	02051	5/16	3/8	1-3/8	3-1/8
02305	02055	3/8	3/8	1-1/2	3-1/4
02321	02071	1/2	1/2	2	4
02337	02087	5/8	5/8	2	4-1/8
02359	02109	3/4	3/4	2-1/4	4-1/2
02394	02144	7/8	7/8	2-1/2	4-3/4
02426	02176	1	1	3	5-1/2
02435	02185	1-1/8	1	3	5-1/2
02443	02193	1-1/4	1	3	5-1/2
02445	02195	1-1/4	1-1/4	3	5-1/2
02461	02211	1-1/2	1-1/4	3	5-1/2
02469	02219	1-3/4	1-1/4	3	5-1/2
02477	02227	2	1-1/4	3	5-1/2
* 02482	* 02232	2	2	3	6-3/4

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
 - Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
 - Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
 - Coated Price Shown in Price List. Call for Availability.
- * Combination Shank

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○						○		○				



E2033 SERIES 8% COBALT (M42) FLAT SHANK
E1033 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 2 FLUTE EXTENDED LENGTH

► Provided with the longest flute length and suitable for high accuracy machining of deep step.



HSS Co8 HSS 2 30° FLAT P.1281, 1287, 1291

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length
8% COBALT (M42)	HSS (M2)					
03289	03039	1/8	3/8	3/8	-	2-3/8
03293	03043	3/16	3/8	1/2	1-1/8	2-11/16
03297	03047	1/4	3/8	5/8	1-1/2	3-1/16
03301	03051	5/16	3/8	3/4	1-3/4	3-5/16
03305	03055	3/8	3/8	3/4	1-3/4	3-5/16
03321	03071	1/2	1/2	1	2-7/32	4
03337	03087	5/8	5/8	1-3/8	2-23/32	4-5/8
03359	03109	3/4	3/4	1-5/8	3-11/32	5-3/8
03394	03144	7/8	7/8	2	4	6
03426	03176	1	1	2-1/2	4-31/32	7-1/4
03445	03195	1-1/4	1-1/4	3	4-31/32	7-1/4

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○						○		○				



E2050 SERIES 8% COBALT (M42) FLAT SHANK
E1050 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 2 FLUTE REGULAR LENGTH DOUBLE

► Series E2050 two flute end mills are the double-end version of E2030 single-end tools. Same excellent tool geometry for slotting, keying and general purpose milling, plus the added economy offered by the double-end design.



HSS Co8 HSS 2 30° FLAT P.1281, 1287, 1291

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
11289	11039	1/8	3/8	3/8	3-1/16
11290	11040	9/64	3/8	7/16	3-1/8
11291	11041	5/32	3/8	7/16	3-1/8
11292	11042	11/64	3/8	7/16	3-1/8
11293	11043	3/16	3/8	7/16	3-1/8
11294	11044	13/64	3/8	1/2	3-1/8
11295	11045	7/32	3/8	1/2	3-1/8
11296	11046	15/64	3/8	1/2	3-1/8
11297	11047	1/4	3/8	1/2	3-1/8
11298	11048	17/64	3/8	9/16	3-1/8
11299	11049	9/32	3/8	9/16	3-1/8
11300	11050	19/64	3/8	9/16	3-1/8
11301	11051	5/16	3/8	9/16	3-1/8
11302	11052	21/64	3/8	9/16	3-1/8
11303	11053	11/32	3/8	9/16	3-1/8
11304	11054	23/64	3/8	9/16	3-1/8
11305	11055	3/8	3/8	9/16	3-1/8
11307	11057	25/64	1/2	13/16	3-3/4
11309	11059	13/32	1/2	13/16	3-3/4
11311	11061	27/64	1/2	13/16	3-3/4
11313	11063	7/16	1/2	13/16	3-3/4
11315	11065	29/64	1/2	13/16	3-3/4
11317	11067	15/32	1/2	13/16	3-3/4
11319	11069	31/64	1/2	13/16	3-3/4
11321	11071	1/2	1/2	13/16	3-3/4
11326	11076	17/32	5/8	1-1/8	4-1/2

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

► NEXT PAGE

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○						○		○				



E2050 SERIES 8% COBALT (M42) FLAT SHANK
E1050 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 2 FLUTE REGULAR LENGTH DOUBLE

► Series E2050 two flute end mills are the double-end version of E2030 single-end tools. Same excellent tool geometry for slotting, keying and general purpose milling, plus the added economy offered by the double-end design.



HSS Co8 HSS 2 30° FLAT P.1281, 1287, 1291

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
11330	11080	9/16	5/8	1-1/8	4-1/2
11334	11084	19/32	5/8	1-1/8	4-1/2
11337	11087	5/8	5/8	1-1/8	4-1/2
11344	11094	21/32	3/4	1-5/16	5
11350	11100	11/16	3/4	1-5/16	5
11354	11104	23/32	3/4	1-5/16	5
11359	11109	3/4	3/4	1-5/16	5
11368	11118	25/32	7/8	1-9/16	5-1/2
11377	11127	13/16	7/8	1-9/16	5-1/2
11384	11134	27/32	7/8	1-9/16	5-1/2
11394	11144	7/8	7/8	1-9/16	5-1/2
11402	11152	29/32	1	1-5/8	5-7/8
11410	11160	15/16	1	1-5/8	5-7/8
11417	11167	31/32	1	1-5/8	5-7/8
11426	11176	1	1	1-5/8	5-7/8

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~-.0010	** 0~-.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2110 SERIES 8% COBALT (M42) FLAT SHANK
E1110 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 2 FLUTE REGULAR LENGTH BALL NOSE

► The two flute ball end mills are designed for milling of radius bottom slots, fillets and special contours. The end teeth are cut to center allowing these end mills to drill into material at the beginning of a slotting cut. The two flute design provides good chip removal ability in slotting.



HSS Co8 HSS 2 30° FLAT P.1284, 1289, 1293

Unit : Inch

EDP No.		Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)					
41289	41039	R1/16	1/8	3/8	3/8	2-5/16
41293	41043	R3/32	3/16	3/8	1/2	2-3/8
41297	41047	R1/8	1/4	3/8	5/8	2-7/16
41301	41051	R5/32	5/16	3/8	3/4	2-1/2
41305	41055	R3/16	3/8	3/8	3/4	2-1/2
41313	41063	R7/32	7/16	1/2	1	3
41321	41071	R1/4	1/2	1/2	1	3
41328	41078	R9/32	9/16	1/2	1-1/8	3-1/8
41336	41086	R5/16	5/8	1/2	1-1/8	3-1/8
41337	41087	R5/16	5/8	5/8	1-3/8	3-1/2
41357	41107	R3/8	3/4	1/2	1-5/16	3-5/16
41359	41109	R3/8	3/4	3/4	1-5/8	3-7/8
41391	41141	R7/16	7/8	3/4	2	4-1/4
41394	41144	R7/16	7/8	7/8	2	4-1/4
41422	41172	R1/2	1	3/4	2-1/4	4-1/2
41426	41176	R1/2	1	1	2-1/4	4-3/4
41431	41181	R9/16	1-1/8	3/4	1-5/8	3-7/8
41435	41185	R9/16	1-1/8	1	2-1/4	4-3/4
41439	41189	R5/8	1-1/4	3/4	1-5/8	3-7/8
41445	41195	R5/8	1-1/4	1-1/4	2-1/2	5
41449	41199	R11/16	1-3/8	3/4	1-5/8	4-1/8
41453	41203	R11/16	1-3/8	1-1/4	2-1/2	5
41457	41207	R3/4	1-1/2	3/4	1-5/8	4-1/8
41461	41211	R3/4	1-1/2	1-1/4	2-1/2	5
41478	41227	R1	2	1-1/4	2-1/2	5

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2111 SERIES 8% COBALT (M42) FLAT SHANK
E1111 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 2 FLUTE EXTENDED LENGTH BALL NOSE

► Longer flute length than E2110 type and suitable for high efficient copying process and deep cutting of die mold corner radius.



HSS Co8 HSS 2 30° FLAT P.1284, 1289, 1293

Unit : Inch

EDP No.		Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length
8% COBALT (M42)	HSS (M2)	R					
42289	42039	R1/16	1/8	3/8	3/8	-	2-3/8
42293	42043	R3/32	3/16	3/8	1/2	1-1/8	2-11/16
42297	42047	R1/8	1/4	3/8	5/8	1-1/2	3-1/16
42301	42051	R5/32	5/16	3/8	3/4	1-3/4	3-5/16
42305	42055	R3/16	3/8	3/8	3/4	1-3/4	3-5/16
42313	42063	R7/32	7/16	1/2	1	1-7/8	3-11/16
42321	42071	R1/4	1/2	1/2	1	2-1/4	4
42337	42087	R5/16	5/8	5/8	1-3/8	2-3/4	4-5/8
42359	42109	R3/8	3/4	3/4	1-5/8	3-3/8	5-3/8
42426	42176	R1/2	1	1	2-1/2	5	7-1/4

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2112 SERIES 8% COBALT (M42) FLAT SHANK
E1112 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 2 FLUTE REGULAR LENGTH BALL NOSE DOUBLE

► Same construction features as E2110 end mill in a more economical version. Removes more material per grind. Machine ground notch assures positive anchorage in tool holder.



HSS Co8 HSS 2 30° FLAT P.1284, 1289, 1293

Unit : Inch

EDP No.		Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)	R				
45289	45039	R1/16	1/8	3/8	3/8	3-1/16
45293	45043	R3/32	3/16	3/8	7/16	3-1/8
45297	45047	R1/8	1/4	3/8	1/2	3-1/8
45301	45051	R5/32	5/16	3/8	9/16	3-1/8
45305	45055	R3/16	3/8	3/8	9/16	3-1/8
45313	45063	R7/32	7/16	1/2	13/16	3-3/4
45321	45071	R1/4	1/2	1/2	13/16	3-3/4
45337	45087	R5/16	5/8	5/8	1-1/8	4-1/2
45359	45109	R3/8	3/4	3/4	1-5/8	5
45426	45176	R1/2	1	1	1-5/8	5-7/8

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~-.0010	** 0~-.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2031 SERIES 8% COBALT (M42) FLAT SHANK
E1031 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 4 FLUTE REGULAR LENGTH

► Possible for high-speed cutting, suitable for high efficiency machining. Easy to regrind.



HSS Co8 HSS 4 30° FLAT P.1283, 1288, 1292

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
04289	04039	1/8	3/8	3/8	2-5/16
04290	04040	9/64	3/8	7/16	2-3/8
04291	04041	5/32	3/8	7/16	2-3/8
04292	04042	11/64	3/8	1/2	2-3/8
04293	04043	3/16	3/8	1/2	2-3/8
04294	04044	13/64	3/8	9/16	2-7/16
04295	04045	7/32	3/8	9/16	2-7/16
04296	04046	15/64	3/8	5/8	2-7/16
04297	04047	1/4	3/8	5/8	2-7/16
04298	04048	17/64	3/8	11/16	2-1/2
04299	04049	9/32	3/8	11/16	2-1/2
04300	04050	19/64	3/8	3/4	2-1/2
04301	04051	5/16	3/8	3/4	2-1/2
04302	04052	21/64	3/8	3/4	2-1/2
04303	04053	11/32	3/8	3/4	2-1/2
04304	04054	23/64	3/8	3/4	2-1/2
04305	04055	3/8	3/8	3/4	2-1/2
04306	04056	25/64	3/8	1	2-11/16
04308	04058	13/32	3/8	1	2-11/16
04310	04060	27/64	3/8	1	2-11/16
04312	04062	7/16	3/8	1	2-11/16
04315	04065	29/64	1/2	1-1/4	3-1/4
04317	04067	15/32	1/2	1-1/4	3-1/4
04319	04069	31/64	1/2	1-1/4	3-1/4
04320	04070	1/2	3/8	1	2-11/16
04321	04071	1/2	1/2	1-1/4	3-1/4
04324	04074	17/32	1/2	1-3/8	3-3/8

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

► NEXT PAGE

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○						○		○				



E2031 SERIES 8% COBALT (M42) FLAT SHANK
E1031 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 4 FLUTE REGULAR LENGTH

► Possible for high-speed cutting, suitable for high efficiency machining. Easy to regrind.



HSS Co8 HSS 4 30° FLAT P.1283, 1288, 1292

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
04328	04078	9/16	1/2	1-3/8	3-3/8
04332	04082	19/32	1/2	1-3/8	3-3/8
04336	04086	5/8	1/2	1-3/8	3-3/8
04337	04087	5/8	5/8	1-5/8	3-3/4
04340	04090	21/32	1/2	1-5/8	3-5/8
04348	04098	11/16	5/8	1-5/8	3-3/4
04352	04102	23/32	1/2	1-5/8	3-5/8
04357	04107	3/4	1/2	1-5/8	3-5/8
04358	04108	3/4	5/8	1-5/8	3-3/4
04359	04109	3/4	3/4	1-5/8	3-7/8
04364	04114	25/32	5/8	1-7/8	4
04375	04125	13/16	3/4	1-7/8	4-1/8
04380	04130	27/32	5/8	1-7/8	4
04391	04141	7/8	3/4	1-7/8	4-1/8
04394	04144	7/8	7/8	1-7/8	4-1/8
04399	04149	29/32	3/4	1-7/8	4-1/8
04407	04157	15/16	3/4	1-7/8	4-1/8
04414	04164	31/32	3/4	1-7/8	4-1/8
04420	04170	1	5/8	1-7/8	4
04422	04172	1	3/4	1-7/8	4-1/8
04426	04176	1	1	2	4-1/2

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○						○		○				



E2032 SERIES 8% COBALT (M42) FLAT SHANK
E1032 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 6 FLUTE REGULAR LENGTH

► Possible for high-speed cutting, suitable for high efficiency machining. Easy to regrind.



HSS Co8 HSS 6 30° FLAT P.1283, 1288, 1292

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
04338	04088	5/8	5/8	1-5/8	3-3/4
04360	04110	3/4	3/4	1-5/8	3-7/8
04376	04126	13/16	3/4	1-7/8	4-1/8
04390	04140	7/8	5/8	1-7/8	4
04395	04145	7/8	7/8	1-7/8	4-1/8
04405	04155	15/16	5/8	1-7/8	4
04421	04171	1	5/8	1-7/8	4
04427	04177	1	1	2	4-1/2
04432	04182	1-1/8	3/4	2	4-1/4
04436	04186	1-1/8	1	2	4-1/2
04440	04190	1-1/4	3/4	2	4-1/4
04444	04194	1-1/4	1	2	4-1/2
04446	04196	1-1/4	1-1/4	2	4-1/2
04452	04202	1-3/8	1	2	4-1/2
04460	04210	1-1/2	1	2	4-1/2
04462	04212	1-1/2	1-1/4	2	4-1/2
04470	04220	1-3/4	1-1/4	2	4-1/2
04478	04228	2	1-1/4	2	4-1/2
04481	04231	2	2	2	5-3/4

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○						



E2034 / E2035 SERIES 8% COBALT (M42) FLAT SHANK
E1034 / E1035 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 4&6 FLUTE LONG LENGTH

► Longer flute length than E2031 type and allows deeper cutting. Easy to regrind.



HSS Co8 HSS 4&6 30° FLAT P.1283, 1288, 1292

Unit : Inch

E2034(8% COBALT) , E1034(HSS) Series ■ 4 FLUTE

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
05297	05047	1/4	3/8	1-1/4	3-1/16
05301	05051	5/16	3/8	1-3/8	3-1/8
05305	05055	3/8	3/8	1-1/2	3-1/4
05313	05063	7/16	1/2	1-3/4	3-3/4
05321	05071	1/2	1/2	2	4
05337	05087	5/8	5/8	2-1/2	4-5/8
05359	05109	3/4	3/4	3	5-1/4
05394	05144	7/8	7/8	3-1/2	5-3/4
05426	05176	1	1	4	6-1/2

E2035(8% COBALT) , E1035(HSS) Series ■ 6 FLUTE

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
05436	05186	1-1/8	1	4	6-1/2
05444	05194	1-1/4	1	4	6-1/2
05446	05196	1-1/4	1-1/4	4	6-1/2
05460	05210	1-1/2	1	4	6-1/2
05462	05212	1-1/2	1-1/4	4	6-1/2
05470	05220	1-3/4	1-1/4	4	6-1/2
05478	05228	2	1-1/4	4	6-1/2
* 05485	* 05235	2	2	4	7-3/4

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

* Combination Shank

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

Series	P				H	M	K	N				S		
	Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
	~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
E1034	◎	◎	○					○		○				
E2034	◎	◎	○					○						
E1035	◎	◎	○					○						
E2035	◎	◎	○					○						



E2036 / E2037 SERIES 8% COBALT (M42) FLAT SHANK
E1036 / E1037 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 4&6 FLUTE EXTRA LONG LENGTH

► Provided with the longest flute length and suitable for high accuracy machining of deep step. Easy to regrind.



E2036(8% COBALT) , E1036(HSS) Series ■ 4 FLUTE Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
06297	06047	1/4	3/8	1-3/4	3-9/16
06301	06051	5/16	3/8	2	3-3/4
06305	06055	3/8	3/8	2-1/2	4-1/4
06321	06071	1/2	1/2	3	5
06337	06087	5/8	5/8	4	6-1/8
06359	06109	3/4	3/4	4	6-1/4
06394	06144	7/8	7/8	5	7-1/4
06426	06176	1	1	6	8-1/2

E2037(8% COBALT) , E1037(HSS) Series ■ 6 FLUTE Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
06446	06196	1-1/4	1-1/4	6	8-1/2
06462	06212	1-1/2	1-1/4	8	10-1/2
* 06491	* 06241	2	2	8	11-3/4

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
 - Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
 - Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
 - Coated Price Shown in Price List. Call for Availability.
- * Combination Shank

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

Series	P				H	M	K	N				S		
	Carbon Steels ~HRc20	Alloy Steels HRc20~30	Prehardened Steels HRc30~40	Hardened Steels HRc40~45 HRc45~55	High Hardened Steels HRc55~70	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
E1036	◎	◎	○					○					○	
E2036	◎	◎	○					○					○	
E1037	◎	◎	○					○					○	
E2037	◎	◎	○					○					○	



E2051 SERIES 8% COBALT (M42) FLAT SHANK
E1051 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 4 FLUTE REGULAR LENGTH DOUBLE

► Series E2051 four flute end mills are the double-end version of E2031 four flute tools and are used for the same type of finishing operation. Two tools on one shank saves on sharpening set-up as well as on initial tool costs. Easy to regrind.



E2051(8% COBALT) , E1051(HSS) Series ■ 4 FLUTE Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
12289	12039	1/8	3/8	3/8	3-1/16
12290	12040	9/64	3/8	7/16	3-1/8
12291	12041	5/32	3/8	7/16	3-1/8
12292	12042	11/64	3/8	1/2	3-1/4
12293	12043	3/16	3/8	1/2	3-1/4
12294	12044	13/64	3/8	9/16	3-1/4
12295	12045	7/32	3/8	9/16	3-1/4
12296	12046	15/64	3/8	5/8	3-3/8
12297	12047	1/4	3/8	5/8	3-3/8
12298	12048	17/64	3/8	11/16	3-3/8
12299	12049	9/32	3/8	11/16	3-3/8
12300	12050	19/64	3/8	3/4	3-1/2
12301	12051	5/16	3/8	3/4	3-1/2
12302	12052	21/64	3/8	3/4	3-1/2
12303	12053	11/32	3/8	3/4	3-1/2
12304	12054	23/64	3/8	3/4	3-1/2
12305	12055	3/8	3/8	3/4	3-1/2
12307	12057	25/64	1/2	1	4-1/8
12309	12059	13/32	1/2	1	4-1/8
12311	12061	27/64	1/2	1	4-1/8
12313	12063	7/16	1/2	1	4-1/8
12315	12065	29/64	1/2	1	4-1/8
12317	12067	15/32	1/2	1	4-1/8
12319	12069	31/64	1/2	1	4-1/8

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
 - Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
 - Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
 - Coated Price Shown in Price List. Call for Availability.
- NEXT PAGE

◎ : Excellent ○ : Good

Series	P				H	M	K	N				S		
	Carbon Steels ~HRc20	Alloy Steels HRc20~30	Prehardened Steels HRc30~40	Hardened Steels HRc40~45 HRc45~55	High Hardened Steels HRc55~70	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
E1051	◎	◎	○					○					○	
E2051	◎	◎	○					○					○	



E2051 SERIES 8% COBALT (M42) FLAT SHANK
E1051 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 4 FLUTE REGULAR LENGTH DOUBLE

► Series E2051 four flute end mills are the double-end version of E2031 four flute tools and are used for the same type of finishing operation. Two tools on one shank saves on sharpening set-up as well as on initial tool costs. Easy to regrind.



HSS Co8 HSS 4 30° FLAT P.1283, 1288, 1292

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
12321	12071	1/2	1/2	1	4-1/8
12330	12080	9/16	5/8	1-3/8	5
12337	12087	5/8	5/8	1-3/8	5
12350	12100	11/16	3/4	1-5/8	5-5/8
12359	12109	3/4	3/4	1-5/8	5-5/8
12377	12127	13/16	7/8	1-7/8	6-1/8
12394	12144	7/8	7/8	1-7/8	6-1/8
12410	12160	15/16	1	1-7/8	6-3/8
12426	12176	1	1	1-7/8	6-3/8

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~-.0010	** 0~-.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

Series	P				H	M	K	N				S		
	Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
E1031	◎	◎	○					○		○				
E2031	◎	◎	○					○		○				



E2031 / E2032 SERIES 8% COBALT (M42) FLAT SHANK
E1031 / E1032 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 4, 6&8 FLUTE REGULAR LENGTH 3/4" SHANK

► E2031(3/4" shank, multi flute, general purpose end mills) are recommended for finishing operations for Bridgeport machines and other similar operations. Easy to regrind.



HSS Co8 HSS 4-8 30° FLAT P.1283, 1288, 1292

Unit : Inch

E2031(8% COBALT) , E1031(HSS) Series ■ 4 FLUTE

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
04359	04109	3/4	3/4	1-5/8	3-7/8
04375	04125	13/16	3/4	1-7/8	4-1/8
04391	04141	7/8	3/4	1-7/8	4-1/8
04407	04157	15/16	3/4	1-7/8	4-1/8
04422	04172	1	3/4	1-7/8	4-1/8

Unit : Inch

E2032(8% COBALT) , E1032(HSS) Series ■ 6&8 FLUTE

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No.of Flute
8% COBALT (M42)	HSS (M2)					
04432	04182	1-1/8	3/4	2	4-1/4	6
04440	04190	1-1/4	3/4	2	4-1/4	6
04458	04208	1-1/2	3/4	2	4-1/4	6
04468	04218	1-3/4	3/4	2	4-1/2	6
04476	04226	2	3/4	2	4-1/2	8

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

Series	P				H	M	K	N				S		
	Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
	~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70								
E1031	◎	◎	○					○		○				
E2031	◎	◎	○					○		○				



E2020 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, 4 FLUTE REGULAR LENGTH BALL NOSE

► The four flute ball end mills are designed for milling of radius bottom slots fillets and special contours. The end teeth are cut to center allowing these end mills to drill into material at the beginning of a slotting cut.



HSS Co8 4 30° FLAT P.1284, 1289, 1293

Unit : Inch

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)					
43289	R1/16	1/8	3/8	3/8	2-5/16
43293	R3/32	3/16	3/8	1/2	2-3/8
43297	R1/8	1/4	3/8	5/8	2-7/16
43301	R5/32	5/16	3/8	3/4	2-1/2
43305	R3/16	3/8	3/8	3/4	2-1/2
43312	R7/32	7/16	3/8	1	2-11/16
43321	R1/4	1/2	1/2	1-1/4	3-1/4
43337	R5/16	5/8	5/8	1-5/8	3-3/4
43350	R11/32	11/16	5/8	1-5/8	3-3/4
43359	R3/8	3/4	3/4	1-5/8	3-7/8
43394	R7/16	7/8	7/8	1-7/8	4-1/8
43426	R1/2	1	1	2	4-1/2
43435	R9/16	1-1/8	1	2	4-1/2
43445	R5/8	1-1/4	1-1/4	2	4-1/2
43461	R3/4	1-1/2	1-1/4	2	4-1/2
43477	R1	2	1-1/4	2	4-1/2

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○						○		○				



E2021 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, 4 FLUTE LONG LENGTH BALL NOSE

► Longer flute length than E2020 type and suitable for high efficient copying process and deep cutting of die mold corner radius.



HSS Co8 4 30° FLAT P.1284, 1289, 1293

Unit : Inch

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)					
44297	R1/8	1/4	3/8	1-1/4	3-1/16
44301	R5/32	5/16	3/8	1-3/8	3-1/8
44305	R3/16	3/8	3/8	1-1/2	3-1/4
44321	R1/4	1/2	1/2	2	4
44337	R5/16	5/8	5/8	2-1/2	4-5/8
44359	R3/8	3/4	3/4	3	5-1/4
44394	R7/16	7/8	7/8	3-1/2	5-3/4
44426	R1/2	1	1	4	6-1/2

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○						○		○				



E2069 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, 4 FLUTE REGULAR LENGTH BALL NOSE DOUBLE

► Same construction features as E2020 end mill in a more economical version. Removes more material per grind. Machine ground notch assures positive anchorage in tool holder.



HSS Co8 4 30° FLAT P.1284, 1289, 1293

Unit : Inch

EDP No.	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	R				
46289	R1/16	1/8	3/8	3/8	3-1/16
46293	R3/32	3/16	3/8	1/2	3-1/4
46297	R1/8	1/4	3/8	5/8	3-3/8
46301	R5/32	5/16	3/8	3/4	3-1/2
46305	R3/16	3/8	3/8	3/4	3-1/2
46313	R7/32	7/16	1/2	1	4-1/8
46321	R1/4	1/2	1/2	1	4-1/8
46337	R5/16	5/8	5/8	1-3/8	5
46359	R3/8	3/4	3/4	1-5/8	5-5/8
46426	R1/2	1	1	1-7/8	6-3/8

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~-.0010	** 0~-.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○					○	



E2039 SERIES 8% COBALT (M42) FLAT SHANK
E1039 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 4 FLUTE REGULAR LENGTH CENTER CUTTING

► Center cutting allows these end mills to drill into the part for the beginning of a slot. These center cutting end mills are recommended for pocketing, tracer milling, cam milling, die sinking and slotting.



HSS Co8 HSS 4 30° FLAT P.1283, 1288, 1292

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
07289	07039	1/8	3/8	3/8	2-5/16
07291	07041	5/32	3/8	7/16	2-3/8
07293	07043	3/16	3/8	1/2	2-3/8
07295	07045	7/32	3/8	9/16	2-7/16
07297	07047	1/4	3/8	5/8	2-7/16
07299	07049	9/32	3/8	11/16	2-1/2
07301	07051	5/16	3/8	3/4	2-1/2
07303	07053	11/32	3/8	3/4	2-1/2
07305	07055	3/8	3/8	3/4	2-1/2
07308	07058	13/32	3/8	1	2-11/16
07312	07062	7/16	3/8	1	2-11/16
07316	07066	15/32	3/8	1	2-11/16
07320	07070	1/2	3/8	1	2-11/16
07321	07071	1/2	1/2	1-1/4	3-1/4

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

► NEXT PAGE

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○					○	



E2039 SERIES 8% COBALT (M42) FLAT SHANK
E1039 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 4 FLUTE REGULAR LENGTH CENTER CUTTING

► Center cutting allows these end mills to drill into the part for the beginning of a slot. These center cutting end mills are recommended for pocketing, tracer milling, cam milling, die sinking and slotting.



HSS Co8 HSS 4 30° FLAT P.1283, 1288, 1292

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
07336	07086	5/8	1/2	1-3/8	3-3/8
07337	07087	5/8	5/8	1-5/8	3-3/4
07348	07098	11/16	5/8	1-5/8	3-3/4
07357	07107	3/4	1/2	1-5/8	3-5/8
07358	07108	3/4	5/8	1-5/8	3-3/4
07359	07109	3/4	3/4	1-5/8	3-7/8
07391	07141	7/8	3/4	1-7/8	4-1/8
07394	07144	7/8	7/8	1-7/8	4-1/8
07420	07170	1	5/8	1-7/8	4
07422	07172	1	3/4	1-7/8	4-1/8
07426	07176	1	1	2	4-1/2
07435	07185	1-1/8	1	2	4-1/2
07445	07195	1-1/4	1-1/4	2	4-1/2
07461	07211	1-1/2	1-1/4	2	4-1/2

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2042 SERIES 8% COBALT (M42) FLAT SHANK
E1042 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 6 FLUTE REGULAR LENGTH CENTER CUTTING

► Center cutting allows these end mills to drill into the part for the beginning of a slot. These center cutting end mills are recommended for pocketing, tracer milling, cam milling, die sinking and slotting.



HSS Co8 HSS 6 30° FLAT P.1283, 1288, 1292

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
07322	07072	1/2	1/2	1-1/4	3-1/4
07338	07088	5/8	5/8	1-5/8	3-3/4
07349	07099	11/16	5/8	1-5/8	3-3/4
07360	07110	3/4	3/4	1-5/8	3-7/8
07395	07145	7/8	7/8	1-7/8	4-1/8
07427	07177	1	1	2	4-1/2
07436	07186	1-1/8	1	2	4-1/2
07446	07196	1-1/4	1-1/4	2	4-1/2
07448		1-5/16	3/4	2	4-1/4
07462	07212	1-1/2	1-1/4	2	4-1/2
07478	07228	2	1-1/4	2	4-1/2
* 07481	* 07231	2	2	2	5-3/4

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

* Combination Shank

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○						



E2039 SERIES 8% COBALT (M42) FLAT SHANK

E2042 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, MULTI FLUTE MEDIUM LENGTH CENTER CUTTING

► Center cutting allows these end mills to drill into the part for the beginning of a slot. These center cutting end mills are recommended for pocketing, tracer milling, cam milling, die sinking and slotting.



E2039(4 FLUTE), E2042(6&8 FLUTE) Series Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
07901	1	1	3	5-1/2	4
07902	1-1/4	1-1/4	3	5-1/2	4
07903	1-1/2	1-1/4	3	5-1/2	4
07094	1	1	3	5-1/2	6
07095	1-1/4	1-1/4	3	5-1/2	6
07096	1-1/2	1-1/4	3	5-1/2	6
07097	1-3/4	1-1/4	3	5-1/2	6
99098	2	1-1/4	3	5-1/2	8

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

© : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRC20	HRC20~30	HRC30~40	HRC40~45	HRC45~55	HRC55~70									
◎	◎	○						○		○				



E2040 / E2162 SERIES 8% COBALT (M42) FLAT SHANK

E1040 / E1162 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 4&6 FLUTE LONG LENGTH CENTER CUTTING

► Longer flute length than E2039 type, E2042 and allows deeper cutting.



E2040(8% COBALT) , E1040(HSS) Series ■ 4 FLUTE Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
08297	08047	1/4	3/8	1-1/4	3-1/16
08301	08051	5/16	3/8	1-3/8	3-1/8
08305	08055	3/8	3/8	1-1/2	3-1/4
08321	08071	1/2	1/2	2	4
08337	08087	5/8	5/8	2-1/2	4-5/8
08359	08109	3/4	3/4	3	5-1/4
08394	08144	7/8	7/8	3-1/2	5-3/4
08426	08176	1	1	4	6-1/2
08445	08195	1-1/4	1-1/4	4	6-1/2
08461	08211	1-1/2	1-1/4	4	6-1/2

E2162(8% COBALT) , E1162(HSS) Series ■ 6 FLUTE Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
08322	08072	1/2	1/2	2	4
08338	08088	5/8	5/8	2-1/2	4-5/8
08360	08110	3/4	3/4	3	5-1/4
08395	08145	7/8	7/8	3-1/2	5-3/4
08427	08177	1	1	4	6-1/2
08446	08196	1-1/4	1-1/4	4	6-1/2
08462	08212	1-1/2	1-1/4	4	6-1/2
08478	08228	2	1-1/4	4	6-1/2
* 08485	* 08235	2	2	4	7-3/4
* 08489	* 08239	2	2	6	9-3/4

* Combination Shank

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.



E2041 / E2175 SERIES 8% COBALT (M42) FLAT SHANK
E1041 / E1175 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 4&6 FLUTE EXTRA LONG LENGTH CENTER CUTTING

► Provided with longest flute length and suitable for high accuracy machining of deep step.



E2041(8% COBALT) , E1041(HSS) Series ■ 4 FLUTE Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
09297	09047	1/4	3/8	1-3/4	3-9/16
09301	09051	5/16	3/8	2	3-3/4
09305	09055	3/8	3/8	2-1/2	4-1/4
09321	09071	1/2	1/2	3	5
09337	09087	5/8	5/8	4	6-1/8
09359	09109	3/4	3/4	4	6-1/4
09394	09144	7/8	7/8	5	7-1/4
09426	09176	1	1	6	8-1/2
09445	09195	1-1/4	1-1/4	6	8-1/2

E2175(8% COBALT) , E1175(HSS) Series ■ 6 FLUTE Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
09322	09072	1/2	1/2	3	5
09338	09088	5/8	5/8	4	6-1/8
09360	09110	3/4	3/4	4	6-1/4
09395	09145	7/8	7/8	5	7-1/4
09427	09177	1	1	6	8-1/2
09446	09196	1-1/4	1-1/4	6	8-1/2
09462	09212	1-1/2	1-1/4	8	10-1/2
* 09491	* 09241	2	2	8	11-3/4

- The TiN coated, TiCN coated or TiAlN coated is available on your request. * Combination Shank
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)
0~+.0010
**0~+.0015

** The shank of end mills is the same diameter as the cutting portion. ◎ : Excellent ○ : Good

Series	P				H	M	K	N				S		
	Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
E1041 E2041	◎	◎	○					○		○				
E1175 E2175	◎	◎	○					○						



E2053 SERIES 8% COBALT (M42) FLAT SHANK
E1053 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 4 FLUTE REGULAR LENGTH DOUBLE CENTER CUTTING

► Series E2053 end mills are the double-end version of E2039 center cutting single-end tools. They are used for slotting, shallow pocketing, tracer milling or die sinking and similar operation.



E2053(8% COBALT) , E1053(HSS) Series ■ 4 FLUTE Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
13289	13039	1/8	3/8	3/8	3-1/16
13290	13040	9/64	3/8	7/16	3-1/8
13291	13041	5/32	3/8	7/16	3-1/8
13292	13042	11/64	3/8	1/2	3-1/4
13293	13043	3/16	3/8	1/2	3-1/4
13294	13044	13/64	3/8	9/16	3-1/4
13295	13045	7/32	3/8	9/16	3-1/4
13296	13046	15/64	3/8	5/8	3-3/8
13297	13047	1/4	3/8	5/8	3-3/8
13298	13048	17/64	3/8	11/16	3-3/8
13299	13049	9/32	3/8	11/16	3-3/8
13300	13050	19/64	3/8	3/4	3-1/2
13301	13051	5/16	3/8	3/4	3-1/2
13302	13052	21/64	3/8	3/4	3-1/2
13303	13053	11/32	3/8	3/4	3-1/2
13304	13054	23/64	3/8	3/4	3-1/2
13305	13055	3/8	3/8	3/4	3-1/2
13307	13057	25/64	1/2	1	4-1/8
13309	13059	13/32	1/2	1	4-1/8
13311	13061	27/64	1/2	1	4-1/8
13313	13063	7/16	1/2	1	4-1/8
13315	13065	29/64	1/2	1	4-1/8
13317	13067	15/32	1/2	1	4-1/8

- The TiN coated, TiCN coated or TiAlN coated is available on your request. ► NEXT PAGE
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Series	P				H	M	K	N				S		
	Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
E2053 E1053	◎	◎	○					○		○				



E2053 SERIES 8% COBALT (M42) FLAT SHANK
E1053 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 4 FLUTE REGULAR LENGTH DOUBLE CENTER CUTTING

► Series E2053 end mills are the double-end version of E2039 center cutting single-end tools. They are used for slotting, shallow pocketing, tracer milling or die sinking and similar operation.



HSS Co8 HSS 4 30° FLAT P.1283, 1288, 1292

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
13319	13069	31/64	1/2	1	4-1/8
13321	13071	1/2	1/2	1	4-1/8
13330	13080	9/16	5/8	1-3/8	5
13337	13087	5/8	5/8	1-3/8	5
13350	13100	11/16	3/4	1-5/8	5-5/8
13359	13109	3/4	3/4	1-5/8	5-5/8
13377	13127	13/16	7/8	1-7/8	6-1/8
13394	13144	7/8	7/8	1-7/8	6-1/8
13426	13176	1	1	1-7/8	6-3/8

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~-.0010	** 0~-.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2100 SERIES 8% COBALT (M42) FLAT SHANK
E1100 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 6 FLUTE REGULAR with COMBINATION 2" SHANK CENTER CUTTING

► These are to be used for heavy hogging cuts in die-sinking, tape & tracer controlled milling and similar work. The Heavy-Duty end mills are made with toughened Combination shank, heavy web construction, accurate machine-ground end-teeth notching and a special surface treatment to reduce cutting-edge wear.



HSS Co8 HSS 6 30° FLAT P.1283, 1288, 1292

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
10481	10231	2	2	2	5-3/4
10485	10235	2	2	4	7-3/4
10487	10237	2	2	5	8-3/4
10489	10239	2	2	6	9-3/4
10491	10241	2	2	8	11-3/4

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)
0~+.0030

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○						



E2001 SERIES 8% COBALT (M42) PLAIN SHANK
E1001 SERIES HSS (M2) PLAIN SHANK

HSSCo8 & HSS, 2 FLUTE MINIATURE STUB LENGTH DOUBLE

► Tools under Miniature end mills have 3/16" shank diameter without flats. They are designed with positive rake angle geometry and a high helix angle to insure free cutting action. The flute design provides good strength behind the cutting edge. Suitable for finishing of precision components such as watch, camera, electronic apparatus molds, etc.



HSS Co8 HSS 2 39° 30° PLAIN P.1286
 ~Ø3/32 Ø7/64~

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
49252	49002	1/32	3/16	3/64	2
49254	49004	3/64	3/16	1/16	2
49256	49006	1/16	3/16	3/32	2
49258	49008	5/64	3/16	1/8	2
49260	49010	3/32	3/16	9/64	2
49262	49012	7/64	3/16	5/32	2
49264	49014	1/8	3/16	3/16	2
49266	49016	9/64	3/16	7/32	2
49268	49018	5/32	3/16	15/64	2
49270	49020	11/64	3/16	1/4	2
49272	49022	3/16	3/16	9/32	2

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~.0010	** 0~.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2003 SERIES 8% COBALT (M42) PLAIN SHANK
E1003 SERIES HSS (M2) PLAIN SHANK

HSSCo8 & HSS, 2 FLUTE MINIATURE REGULAR LENGTH DOUBLE

► Suitable for finishing of precision components such as watch, camera electronic apparatus molds, etc.



HSS Co8 HSS 2 39° 30° PLAIN P.1286
 ~Ø3/32 Ø7/64~

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
50252	50002	1/32	3/16	3/32	2-1/4
50254	50004	3/64	3/16	9/64	2-1/4
50256	50006	1/16	3/16	3/16	2-1/4
50258	50008	5/64	3/16	15/64	2-1/4
50260	50010	3/32	3/16	9/32	2-1/4
50262	50012	7/64	3/16	21/64	2-1/4
50264	50014	1/8	3/16	3/8	2-1/4
50266	50016	9/64	3/16	13/32	2-1/4
50268	50018	5/32	3/16	7/16	2-1/4
50270	50020	11/64	3/16	1/2	2-1/4
50272	50022	3/16	3/16	1/2	2-1/4

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~.0010	** 0~.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2005 SERIES 8% COBALT (M42) PLAIN SHANK
E1005 SERIES HSS (M2) PLAIN SHANK

HSSCo8 & HSS, 2 FLUTE MINIATURE LONG LENGTH DOUBLE

► Suitable for finishing of precision components such as watch, camera electronic apparatus molds, etc.



HSS Co8 HSS 2 39° 30° PLAIN P.1286
 ~Ø3/32 Ø7/64~

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
51256	51006	1/16	3/16	7/32	2-1/2
51258	51008	5/64	3/16	1/4	2-1/2
51260	51010	3/32	3/16	9/32	2-5/8
51262	51012	7/64	3/16	9/32	2-5/8
51264	51014	1/8	3/16	3/4	3-1/8
51266	51016	9/64	3/16	3/4	3-1/8
51268	51018	5/32	3/16	7/8	3-1/4
51270	51020	11/64	3/16	7/8	3-1/4
51272	51022	3/16	3/16	1	3-3/8

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~-.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2002 SERIES 8% COBALT (M42) PLAIN SHANK
E1002 SERIES HSS (M2) PLAIN SHANK

HSSCo8 & HSS, 4FLUTE MINIATURE STUB LENGTH DOUBLE

► Suitable for finishing of precision components such as watch, camera electronic apparatus molds, etc.



HSS Co8 HSS 4 39° 30° PLAIN P.1286
 ~Ø3/32 Ø7/64~

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
52256	52006	1/16	3/16	3/32	2
52258	52008	5/64	3/16	1/8	2
52260	52010	3/32	3/16	9/64	2
52262	52012	7/64	3/16	5/32	2
52264	52014	1/8	3/16	3/16	2
52266	52016	9/64	3/16	7/32	2
52268	52018	5/32	3/16	15/64	2
52270	52020	11/64	3/16	1/4	2
52272	52022	3/16	3/16	9/32	2

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~-.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2004 SERIES 8% COBALT (M42) PLAIN SHANK
E1004 SERIES HSS (M2) PLAIN SHANK

HSSCo8 & HSS, 4FLUTE MINIATURE REGULAR LENGTH DOUBLE

► Suitable for finishing of precision components such as watch, camera electronic apparatus molds, etc.



HSS Co8 HSS 4 39° 30° PLAIN P.1286
 ~Ø3/32 Ø7/64~

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
53256	53006	1/16	3/16	3/16	2-1/4
53258	53008	5/64	3/16	15/64	2-1/4
53260	53010	3/32	3/16	9/32	2-1/4
53262	53012	7/64	3/16	21/64	2-1/4
53264	53014	1/8	3/16	3/8	2-1/4
53266	53016	9/64	3/16	13/32	2-1/4
53268	53018	5/32	3/16	7/16	2-1/4
53270	53020	11/64	3/16	1/2	2-1/4
53272	53022	3/16	3/16	1/2	2-1/4

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~-.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2006 SERIES 8% COBALT (M42) PLAIN SHANK
E1006 SERIES HSS (M2) PLAIN SHANK

HSSCo8 & HSS, 4FLUTE MINIATURE LONG LENGTH DOUBLE

► Suitable for finishing of precision components such as watch, camera electronic apparatus molds, etc.



HSS Co8 HSS 4 39° 30° PLAIN P.1286
 ~Ø3/32 Ø7/64~

Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
54256	54006	1/16	3/16	7/32	2-1/2
54258	54008	5/64	3/16	1/4	2-1/2
54260	54010	3/32	3/16	9/32	2-5/8
54262	54012	7/64	3/16	9/32	2-5/8
54264	54014	1/8	3/16	3/4	3-1/8
54266	54016	9/64	3/16	3/4	3-1/8
54268	54018	5/32	3/16	7/8	3-1/4
54270	54020	11/64	3/16	7/8	3-1/4
54272	54022	3/16	3/16	1	3-3/8

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~-.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2008 SERIES 8% COBALT (M42) PLAIN SHANK
E1008 SERIES HSS (M2) PLAIN SHANK

HSSCo8 & HSS, 2 FLUTE MINIATURE STUB LENGTH BALL NOSE DOUBLE

► Helical flute in the nose radius.
 Suitable for high efficient copying process and cutting of die mold corner radius.



~03/32 07/64~

Unit : Inch

EDP No.		Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)	R				
55256	55006	R1/32	1/16	3/16	3/32	2
55260	55010	R3/64	3/32	3/16	9/64	2
55264	55014	R1/16	1/8	3/16	3/16	2
55268	55018	R5/64	5/32	3/16	15/64	2
55272	55022	R3/32	3/16	3/16	9/32	2

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
 Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
 Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~.0010	** 0~.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2013 SERIES 8% COBALT (M42) PLAIN SHANK
E1013 SERIES HSS (M2) PLAIN SHANK

HSSCo8 & HSS, 2 FLUTE MINIATURE REGULAR LENGTH BALL NOSE DOUBLE

► Helical flute in the nose radius.
 Suitable for high efficient copying process and cutting of die mold corner radius.



~03/32 07/64~

Unit : Inch

EDP No.		Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)	R				
56252	56002	R1/64	1/32	3/16	3/32	2-1/4
56254	56004	R3/128	3/64	3/16	9/64	2-1/4
56256	56006	R1/64	1/16	3/16	3/16	2-1/4
56258	56008	R5/128	5/64	3/16	15/64	2-1/4
56260	56010	R3/64	3/32	3/16	9/32	2-1/4
56262	56012	R7/128	7/64	3/16	21/64	2-1/4
56264	56014	R1/16	1/8	3/16	3/8	2-1/4
56266	56016	R9/128	9/64	3/16	13/32	2-1/4
56268	56018	R5/64	5/32	3/16	7/16	2-1/4
56270	56020	R11/128	11/64	3/16	1/2	2-1/4
56272	56022	R3/32	3/16	3/16	1/2	2-1/4

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
 Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
 Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~.0010	** 0~.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2015 SERIES 8% COBALT (M42) PLAIN SHANK
E1015 SERIES HSS (M2) PLAIN SHANK

HSSCo8 & HSS, 2 FLUTE MINIATURE LONG LENGTH BALL NOSE DOUBLE

► Helical flute in the nose radius.
 Suitable for high efficient copying process and cutting of die mold corner radius.



HSS Co8
HSS
2
39°
30°
PLAIN
P.1286

~03/32 07/64~

Unit : Inch

EDP No.		Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)	R				
57256	57006	R1/32	1/16	3/16	7/32	2-1/2
57260	57010	R3/64	3/32	3/16	9/32	2-5/8
57264	57014	R1/16	1/8	3/16	3/4	3-1/8
57268	57018	R5/64	5/32	3/16	7/8	3-1/4
57272	57022	R3/32	3/16	3/16	1	3-3/8

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
 Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
 Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~-.0020

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○						○		○				



E1070 SERIES HSS (M2) FLAT SHANK

HSS, 2 FLUTE 42° HELIX REGULAR & MEDIUM LENGTH for ALUMINUM

► The two flute end mills for aluminum have High Helix flute design making them well suited for milling aluminum and other non-ferrous materials. Special rake angles and low micro inch finishes on the primary clearance angles and flute faces insure free cutting action, fine finishes and longer tool life for both non-ferrous materials as well as harder alloys. These tools are made from regular HSS(M2), which is good for aluminum cutting.



HSS
2
42°
FLAT
P.1281

Unit : Inch

■ REGULAR LENGTH

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
HSS (M2)				
17047	1/4	3/8	5/8	2-7/16
17051	5/16	3/8	3/4	2-1/2
17055	3/8	3/8	3/4	2-1/2
17062	7/16	3/8	1	2-11/16
17071	1/2	1/2	1-1/4	3-1/4
17087	5/8	5/8	1-5/8	3-3/4
17109	3/4	3/4	1-5/8	3-7/8
17141	7/8	3/4	1-7/8	4-1/8
17144	7/8	7/8	1-7/8	4-1/8
17172	1	3/4	1-7/8	4-1/8
17176	1	1	2	4-1/2
17195	1-1/4	1-1/4	2	4-1/2
17211	1-1/2	1-1/4	2	4-1/2
17219	1-3/4	1-1/4	2	4-1/2
17227	2	1-1/4	2	4-1/2

Unit : Inch

■ MEDIUM LENGTH

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
HSS (M2)				
99089	1	1	3	5-1/2
99090	1-1/4	1-1/4	3	5-1/2
99091	1-1/2	1-1/4	3	5-1/2
99092	1-3/4	1-1/4	3	5-1/2
99093	2	1-1/4	3	5-1/2

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for HSS
 Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

◎ : Excellent ○ : Good

** The shank of end mills is the same diameter as the cutting portion.


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
○													◎	



E1071 SERIES HSS (M2) FLAT SHANK
E1072 SERIES HSS (M2) FLAT SHANK

HSS, 2 FLUTE 42° HELIX LONG & EXTRA LONG LENGTH for ALUMINUM

► Sharp cutting most suitable flute shape for cutting aluminum alloy, etc.
 These tools are made from regular HSS(M2), which is good for aluminum cutting.



LONG LENGTH

Unit : Inch

EDP No. HSS (M2)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
18047	1/4	3/8	1-1/4	3-1/16
18051	5/16	3/8	1-3/8	3-1/8
18055	3/8	3/8	1-1/2	3-1/4
18063	7/16	1/2	1-3/4	3-3/4
18071	1/2	1/2	2	4
18087	5/8	5/8	2-1/2	4-5/8
18109	3/4	3/4	3	5-1/4
18176	1	1	4	6-1/2
18195	1-1/4	1-1/4	4	6-1/2
18211	1-1/2	1-1/4	4	6-1/2
18227	2	1-1/4	4	6-1/2

EXTRA LONG LENGTH

Unit : Inch

EDP No. HSS (M2)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
19047	1/4	3/8	1-3/4	3-9/16
19051	5/16	3/8	2	3-3/4
19055	3/8	3/8	2-1/2	4-1/4
19071	1/2	1/2	3	5
19087	5/8	5/8	4	6-1/8
19109	3/4	3/4	4	6-1/4
19176	1	1	6	8-1/2
19195	1-1/4	1-1/4	6	8-1/2
19211	1-1/2	1-1/4	8	10-1/2

■ The TiN coated, TiCN coated or TiAlN coated is available on your request.
 ■ Coating Codes for HSS
 Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
 ► Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70								◎	



E2086 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, MULTI FLUTE STUB LENGTH FINE PITCH ROUGHING CENTER CUTTING

► This general purpose rougher is designed for high production metal removal in a wide range of work piece material. It is suitable for a very broad spectrum of materials having up to high tensile strengths. In many cases, the milled surfaces are of acceptable quality.




LONG LENGTH

Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
75297	1/4	3/8	1/4	2-1/16	4
75305	3/8	3/8	3/8	2-5/32	4
75313	7/16	1/2	1/2	2-1/2	4
75321	1/2	1/2	1/2	2-1/2	4
75337	5/8	5/8	5/8	2-3/4	4
75359	3/4	3/4	3/4	2-7/8	4
75391	7/8	3/4	7/8	3-1/8	5
75426	1	1	1	3-1/2	5

■ The TiN coated, TiCN coated or TiAlN coated is available on your request.
 ■ Coating Codes for Cobalt
 Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
 ► Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060



Enforced Cutting Edge


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70								○	○



E2085 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, MULTI FLUTE REGULAR LENGTH FINE PITCH ROUGHING CENTER CUTTING

► This general purpose rougher is designed for high production metal removal in a wide range of work piece material. It is suitable for a very broad spectrum of materials having up to high tensile strengths. In many cases, the milled surfaces are of acceptable quality.




Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
76297	1/4	3/8	5/8	2-7/16	3
76301	5/16	3/8	3/4	2-1/2	3
76305	3/8	3/8	3/4	2-1/2	4
76312	7/16	3/8	1	2-11/16	4
76321	1/2	1/2	1-1/4	3-1/4	4
76328	9/16	1/2	1-3/8	3-3/8	4
76337	5/8	5/8	1-5/8	3-3/4	4
76359	3/4	3/4	1-5/8	3-7/8	4
76391	7/8	3/4	1-7/8	4-1/8	5
76394	7/8	7/8	1-7/8	4-1/8	5
76422	1	3/4	2	4-1/4	5
76426	1	1	2	4-1/2	5

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060



◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2079 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, MULTI FLUTE REGULAR LENGTH FINE PITCH ROUGHING

► This general purpose rougher is designed for high production metal removal in a wide range of work piece material. It is suitable for a very broad spectrum of materials having up to high tensile strengths. In many cases, the milled surfaces are of acceptable quality.




Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
70297	1/4	3/8	5/8	2-7/16	3
70301	5/16	3/8	3/4	2-1/2	3
70305	3/8	3/8	3/4	2-1/2	4
70312	7/16	3/8	1	2-11/16	4
70321	1/2	1/2	1-1/4	3-1/4	4
70328	9/16	1/2	1-3/8	3-3/8	4
70337	5/8	5/8	1-5/8	3-3/4	4
70358	3/4	5/8	1-5/8	3-3/4	4
70359	3/4	3/4	1-5/8	3-7/8	4
70391	7/8	3/4	1-7/8	4-1/8	5
70394	7/8	7/8	1-7/8	4-1/8	5
70422	1	3/4	2	4-1/4	5
70426	1	1	2	4-1/2	5
70431	1-1/8	3/4	2	4-1/4	6
70435	1-1/8	1	2	4-1/2	6
70439	1-1/4	3/4	2	4-1/4	6
70445	1-1/4	1-1/4	2	4-1/2	6
70449	1-3/8	3/4	2	4-1/4	6
70457	1-1/2	3/4	2	4-1/4	6
70461	1-1/2	1-1/4	2	4-1/2	6
70469	1-3/4	1-1/4	2	4-1/2	6
70475	2	3/4	2	4-1/4	6
70477	2	1-1/4	2	4-1/2	6

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060



◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2077 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, MULTI FLUTE LONG LENGTH FINE PITCH ROUGHING

► This general purpose rougher is designed for high production metal removal in a wide range of work piece material. It is suitable for a very broad spectrum of materials having up to high tensile strengths. In many cases, the milled surfaces are of acceptable quality.




HSS Co8
FINE
4-6
30°
FLAT
P.1285, 1290, 1294

Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
71321	1/2	1/2	2	4	4
71337	5/8	5/8	2-1/2	4-5/8	4
71358	3/4	5/8	3	5-1/4	4
71359	3/4	3/4	3	5-1/4	4
71394	7/8	7/8	3-1/2	5-3/4	5
71426	1	1	4	6-1/2	5
71445	1-1/4	1-1/4	4	6-1/2	6
71457	1-1/2	3/4	4	6-1/4	6
71461	1-1/2	1-1/4	4	6-1/2	6
71469	1-3/4	1-1/4	4	6-1/2	6
71477	2	1-1/4	4	6-1/2	6

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardstick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060



Enforced Cutting Edge

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○						○		○				



E2086 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, 3 FLUTE STUB LENGTH FINE PITCH ROUGHING CENTER CUTTING

► This general purpose rougher is designed for high production metal removal in a wide range of work piece material. It is suitable for a very broad spectrum of materials having up to high tensile strengths. In many cases, the milled surfaces are of acceptable quality.




HSS Co8
FINE
3
30°
FLAT
P.1285, 1290, 1294

Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
72297	1/4	3/8	1/4	2-1/16
72305	3/8	3/8	3/8	2-5/32
72321	1/2	1/2	1/2	2-1/2
72337	5/8	5/8	5/8	2-3/4
72359	3/4	3/4	3/4	2-7/8
72391	7/8	3/4	7/8	3-1/8
72422	1	3/4	1	3-1/4
72426	1	1	1	3-1/2

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardstick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060



Enforced cutting edge

◎ : Excellent ○ : Good


P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○						○		○				

YG COBALT & HSS END MILLS

E2170 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, MULTI FLUTE REGULAR LENGTH COARSE PITCH ROUGHING

► This general purpose rougher is designed for high production metal removal in a wide range of work piece material. It is recommended for cutting steel grades and many non-ferrous materials. The end tooth of this tool has a center hole design for many accurate resharpenings between centers.




HSS Co8 COARSE 3-8 30° FLAT P.1285, 1290, 1294

Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
60297	1/4	3/8	5/8	2-7/16	3
60301	5/16	3/8	3/4	2-1/2	3
60305	3/8	3/8	3/4	2-1/2	4
60312	7/16	3/8	1	2-11/16	4
60321	1/2	1/2	1-1/4	3-1/4	4
60328	9/16	1/2	1-3/8	3-3/8	4
60337	5/8	5/8	1-5/8	3-3/4	4
60348	11/16	5/8	1-5/8	3-3/4	4
60358	3/4	5/8	1-5/8	3-3/4	4
60359	3/4	3/4	1-5/8	3-3/4	4
60375	13/16	3/4	1-7/8	4-1/8	4
60391	7/8	3/4	1-7/8	4-1/8	5
60394	7/8	7/8	1-7/8	4-1/8	5
60409	15/16	7/8	1-7/8	4-1/8	5
60422	1	3/4	2	4-1/4	5
60426	1	1	2	4-1/2	5
60431	1-1/8	3/4	2	4-1/4	6
60435	1-1/8	1	2	4-1/2	6
60439	1-1/4	3/4	2	4-1/4	6
60445	1-1/4	1-1/4	2	4-1/2	6
60449	1-3/8	3/4	2	4-1/4	6
60457	1-1/2	3/4	2	4-1/4	6
60461	1-1/2	1-1/4	2	4-1/2	6
60467	1-3/4	3/4	2	4-1/4	6
60469	1-3/4	1-1/4	2	4-1/2	6
60475	2	3/4	2	4-1/4	6
60477	2	1-1/4	2	4-1/2	6
* 60480	2	2	2	5-3/4	8
* 60482	2	2	3	6-3/4	8
* 60484	2	2	4	7-3/4	8

Mill Dia. Tolerance (inch)
up to 1 0~+.0030
over 1 0~+.0060



■ The TiN coated, TiCN coated or TiAlN coated is available on your request.
 ■ Coating Codes for Cobalt
 Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
 ► Coated Price Shown in Price List. Call for Availability.

* Combination Shank

◎ : Excellent ○ : Good

P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				

YG COBALT & HSS END MILLS

E2171 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, MULTI FLUTE MEDIUM LENGTH COARSE PITCH ROUGHING

► This general purpose rougher is designed for high production metal removal in a wide range of work piece material. It is recommended for cutting steel grades and many non-ferrous materials. The end tooth of this tool has a center hole design for many accurate resharpenings between centers.




HSS Co8 COARSE 5-8 30° FLAT P.1285, 1290, 1294

Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
61426	1	1	3	5-1/2	5
61445	1-1/4	1-1/4	3	5-1/2	6
61461	1-1/2	1-1/4	3	5-1/2	6
61488	2	2	6	9-3/4	8

■ The TiN coated, TiCN coated or TiAlN coated is available on your request.
 ■ Coating Codes for Cobalt
 Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
 ► Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060



Enforced cutting edge

◎ : Excellent ○ : Good


P				H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2172 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, MULTI FLUTE LONG LENGTH COARSE PITCH ROUGHING

► This general purpose rougher is designed for high production metal removal in a wide range of work piece material. It is recommended for cutting steel grades and many non-ferrous materials. The end tooth of this tool has a center hole design for many accurate resharpenings between centers.



HSS Co8 COARSE 4-8 30° FLAT P.1285, 1290, 1294


Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
62321	1/2	1/2	2	4	4
62337	5/8	5/8	2-1/2	4-5/8	4
62358	3/4	5/8	3	5-1/8	4
62359	3/4	3/4	3	5-1/4	4
62391	7/8	3/4	3-1/2	5-3/4	5
62422	1	3/4	4	6-1/4	5
62426	1	1	4	6-1/2	5
62439	1-1/4	3/4	4	6-1/4	6
62445	1-1/4	1-1/4	4	6-1/2	6
62457	1-1/2	3/4	4	6-1/4	6
62461	1-1/2	1-1/4	4	6-1/2	6
62469	1-3/4	1-1/4	4	6-1/2	6
62477	2	1-1/4	4	6-1/2	6
* 62490	2	2	8	11-3/4	8

* Combination Shank

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060



Enforced cutting edge

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2241 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, 3FLUTE STUB LENGTH COARSE PITCH ROUGHING CENTER CUTTING

► This general purpose rougher is designed for high production metal removal in a wide range of work piece material. It is recommended for cutting steel grades and many non-ferrous materials. The end tooth of this tool has a center hole design for many accurate resharpenings between centers.




HSS Co8 COARSE 3 30° FLAT P.1285, 1290, 1294

Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
63297	1/4	3/8	1/4	2-1/16
63305	3/8	3/8	3/8	2-5/32
63321	1/2	1/2	1/2	2-1/2
63337	5/8	5/8	5/8	2-3/4
63359	3/4	3/4	3/4	2-7/8
63426	1	1	1	3-1/2

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060



Enforced cutting edge


◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



HSSCo8, MULTI FLUTE REGULAR & LONG LENGTH COARSE PITCH ROUGHING CENTER CUTTING

► This general purpose rougher is designed for high production metal removal in a wide range of work piece material. It is recommended for cutting steel grades and many non-ferrous materials.



E2195 Series ■ REGULAR LENGTH Unit : Inch


EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No.of Flute
64321	1/2	1/2	1-1/4	3-1/4	4
64337	5/8	5/8	1-5/8	3-3/4	4
64359	3/4	3/4	1-5/8	3-7/8	4
64426	1	1	2	4-1/2	5
64445	1-1/4	1-1/4	2	4-1/2	6
64461	1-1/2	1-1/4	2	4-1/2	6

E2197 Series ■ LONG LENGTH Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No.of Flute
65321	1/2	1/2	2	4	4
65337	5/8	5/8	2-1/2	4-5/8	4
65359	3/4	3/4	3	5-1/4	4
65426	1	1	4	6-1/2	5
65445	1-1/4	1-1/4	4	6-1/2	6
65461	1-1/2	1-1/4	4	6-1/2	6

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060



◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○					○	



HSSCo8, MULTI FLUTE REGULAR & LONG LENGTH COARSE PITCH ROUGHING BALL NOSE

► This general purpose rougher is designed for high production metal removal in a wide range of work piece material. It is recommended for cutting steel grades and many non-ferrous materials.



E2193 Series ■ REGULAR LENGTH Unit : Inch

EDP No. 8% COBALT (M42)	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No.of Flute
68297	R1/8	1/4	3/8	5/8	2-7/16	3
68301	R5/32	5/16	3/8	3/4	2-1/2	3
68305	R3/16	3/8	3/8	3/4	2-1/2	4
68321	R1/4	1/2	1/2	1-1/4	3-1/4	4
68337	R5/16	5/8	5/8	1-5/8	3-3/4	4
68359	R3/8	3/4	3/4	1-3/4	4	4
68422	R1/2	1	3/4	2	4-1/2	5
68426	R1/2	1	1	2	4-1/2	5
68439	R5/8	1-1/4	3/4	2	4-1/2	6
68445	R5/8	1-1/4	1-1/4	2	4-1/2	6
68457	R3/4	1-1/2	3/4	2	4-1/2	6
68461	R3/4	1-1/2	1-1/4	2	4-1/2	6

E2125 Series ■ LONG LENGTH Unit : Inch

EDP No. 8% COBALT (M42)	Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No.of Flute
69321	R1/4	1/2	1/2	2-1/2	4-1/2	4
69337	R5/16	5/8	5/8	2-1/2	4-5/8	4
69359	R3/8	3/4	3/4	3	5-1/4	4
69426	R1/2	1	1	4	6-1/2	5
69445	R5/8	1-1/4	1-1/4	4	6-1/2	6
69461	R3/4	1-1/2	1-1/4	4	6-1/2	6

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060

◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○							○			○	

YG COBALT & HSS END MILLS

E2248 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, MULTI FLUTE REGULAR LENGTH ROUGHING & FINISHING

► This general purpose rougher is designed for high production metal removal in a wide range of work piece material. It is suitable for a very broad spectrum of materials having up to high tensile strengths. In many cases, the milled surfaces are of acceptable quality.



HSS Co8 NF 4-8 30° FLAT P.1285, 1290, 1294

Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
73297	1/4	3/8	5/8	2-7/16	4
73301	5/16	3/8	3/4	2-1/2	4
73305	3/8	3/8	3/4	2-1/2	4
73312	7/16	3/8	1	2-11/16	4
73321	1/2	1/2	1-1/4	3-1/4	4
73328	9/16	1/2	1-3/8	3-3/8	4
73337	5/8	5/8	1-5/8	3-3/4	4
73348	11/16	5/8	1-5/8	3-3/4	4
73358	3/4	5/8	1-5/8	3-3/4	4
73359	3/4	3/4	1-5/8	3-3/4	4
73391	7/8	3/4	1-7/8	4-1/8	5
73394	7/8	7/8	1-7/8	4-1/8	5
73422	1	3/4	2	4-1/4	5
73426	1	1	2	4-1/2	5
73431	1-1/8	3/4	2	4-1/4	6
73435	1-1/8	1	2	4-1/2	6
73439	1-1/4	3/4	2	4-1/4	6
73445	1-1/4	1-1/4	2	4-1/2	6
73457	1-1/2	3/4	2	4-1/4	6
73461	1-1/2	1-1/4	2	4-1/2	6
73467	1-3/4	3/4	2	4-1/4	6
73469	1-3/4	1-1/4	2	4-1/2	6
73475	2	3/4	2	4-1/4	6
73477	2	1-1/4	2	4-1/2	6
* 73480	2	2	2	5-3/4	8
* 73482	2	2	3	6-3/4	8
* 73484	2	2	4	7-3/4	8

* Combination Shank

Mill Dia. Tolerance (inch)
+ .0025
+ .0005

Enforced cutting edge

■ The TiN coated, TiCN coated or TiAlN coated is available on your request.
 ■ Coating Codes for Cobalt
 Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
 ► Coated Price Shown in Price List. Call for Availability.

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				

YG COBALT & HSS END MILLS

E2191 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, 3 FLUTE 37° HELIX REGULAR LENGTH ROUGHING for ALUMINUM

► This general purpose rougher is designed for high production metal removal in a wide range of work piece material. It is suitable for a very broad spectrum of materials having up to high tensile strengths. In many cases, the milled surfaces are of acceptable quality.




HSS Co8 ALU 3 37° FLAT P.1285, 1290, 1294

Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
66297	1/4	3/8	5/8	2-7/16
66301	5/16	3/8	3/4	2-1/2
66305	3/8	3/8	3/4	2-1/2
66321	1/2	1/2	1-1/4	3-1/4
66337	5/8	5/8	1-5/8	3-3/4
66359	3/4	3/4	1-5/8	3-7/8
66391	7/8	3/4	1-7/8	4-1/8
66426	1	1	2	4-1/2
66445	1-1/4	1-1/4	2	4-1/2
66461	1-1/2	1-1/4	2	4-1/2

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
 Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
 ► Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060



P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		◎				



E2226 SERIES 8% COBALT (M42) FLAT SHANK
E2192 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, 3 FLUTE 37° HELIX MEDIUM & LONG LENGTH ROUGHING for ALUMINUM

► This general purpose rougher is designed for high production metal removal in a wide range of work piece material. It is recommended for cutting aluminum, aluminum alloy and many non-ferrous materials.



E2226 Series ■ MEDIUM LENGTH Unit : Inch


EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
66901	1	1	3	5-1/2
66902	1-1/4	1-1/4	3	5-1/2

E2192 Series ■ LONG LENGTH Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
67321	1/2	1/2	2	4
67337	5/8	5/8	2-1/2	4-5/8
67359	3/4	3/4	3	5-1/4
67426	1	1	4	6-1/2
67445	1-1/4	1-1/4	4	6-1/2
67461	1-1/2	1-1/4	4	6-1/2

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060



◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2163 SERIES 8% COBALT (M42) FLAT SHANK
E1163 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 2 FLUTE 15° HELIX for KEYWAY CUTTING

► E2163(E1163) are keyway cutting end mills that have the same design as the general purpose of two flute single end mill, but are held to a mill diameter tolerance of +.0000 -.0015. These close tolerance end mills are recommended for cutting keyway which must be held close to nominal size.



E2163 Series ■ MEDIUM LENGTH Unit : Inch

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)				
14289	14039	1/8	3/8	3/8	2-5/16
14293	14043	3/16	3/8	7/16	2-5/16
14297	14047	1/4	3/8	1/2	2-5/16
14301	14051	5/16	3/8	9/16	2-5/16
14305	14055	3/8	3/8	9/16	2-5/16
14312	14062	7/16	3/8	13/16	2-1/2
14321	14071	1/2	1/2	1	3
14337	14087	5/8	5/8	1-5/16	3-7/16
14359	14109	3/4	3/4	1-5/16	3-9/16
14394	14144	7/8	7/8	1-1/2	3-3/4
14426	14176	1	1	1-5/8	4-1/8

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)
0~-0.0015

◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2120 SERIES 8% COBALT (M42) FLAT SHANK
E2121 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, 3&4 FLUTE 60° HELIX REGULAR LENGTH

► Provided with high helix angle(60°).
 Smooth cutting and small cutting resistance.
 Suitable for machining of difficult-to-cut materials.



E2120 Series ■ 3 FLUTE

Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
20297	1/4	3/8	5/8	2-7/16
20301	5/16	3/8	3/4	2-1/2
20305	3/8	3/8	3/4	2-1/2
20312	7/16	3/8	1	2-11/16
20321	1/2	1/2	1-1/4	3-1/4
20337	5/8	5/8	1-5/8	3-3/4
20359	3/4	3/4	1-5/8	3-7/8

E2121 Series ■ 4 FLUTE


Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
20394	7/8	7/8	1-7/8	4-1/8
20426	1	1	2	4-1/2
20445	1-1/4	1-1/4	2	4-1/2
20461	1-1/2	1-1/4	2	4-1/2
20477	2	1-1/4	2	4-1/2

■ The TiN coated, TiCN coated or TiAlN coated is available on your request.
 ■ Coating Codes for Cobalt
 Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
 ► Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.



◎ : Excellent ○ : Good


P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○						



E2160 SERIES 8% COBALT (M42) FLAT SHANK
E2161 SERIES 8% COBALT (M42) FLAT SHANK

HSSCo8, 3 FLUTE SHORT & LONG LENGTH THROW AWAY

► Well balanced web design to minimize deflection & chattering. High accuracy for O.D. is guaranteed under the strict tolerance control. Much higher(50%) table speed than 2 Flute is allowed.



E2160 Series ■ SHORT LENGTH

Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
22257	1/16	1/4	3/32	31/32
22261	3/32	1/4	5/32	1-1/64
22265	1/8	1/4	3/16	1-3/32
22269	5/32	1/4	1/4	1-9/32
22273	3/16	1/4	9/32	1-11/32
22277	7/32	1/4	5/16	1-13/32
22281	1/4	1/4	3/8	1-13/32

E2161 Series ■ LONG LENGTH

Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
23257	1/16	1/4	5/32	1-3/32
23261	3/32	1/4	1/4	1-1/4
23265	1/8	1/4	5/16	1-11/32
23269	5/32	1/4	3/8	1-17/32
23273	3/16	1/4	7/16	1-21/32
23277	7/32	1/4	1/2	1-3/4
23281	1/4	1/4	5/8	1-3/4

■ The TiN coated, TiCN coated or TiAlN coated is available on your request.
 ■ Coating Codes for Cobalt
 Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
 ► Coated Price Shown in Price List. Call for Availability.

Mill Dia. Tolerance (inch)
-.0005
-.0013

◎ : Excellent ○ : Good

P				H	M	K	N				S		
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels	High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45 HRc45~55	HRc55~70									
◎	◎	○					○		○				



E2237 SERIES 8% COBALT (M42) FLAT SHANK

E1237 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 4 FLUTE CORNER ROUNDING

This general corner rounding end mills are designed for machining fillets on work piece.



Table with 7 columns: EDP No. (8% COBALT (M42), HSS (M2)), Radius, Pilot Diameter, Outside Diameter, Shank Diameter, Overall Length. Lists various end mill models and their specifications.

■ The TiN coated, TiCN coated or TiAlN coated is available on your request.
■ Coating Codes for Cobalt
■ Coating Codes for HSS
▶ Coated Price Shown in Price List. Call for Availability.

Material compatibility table with columns P, H, M, K, N, S and rows for Carbon Steels, Alloy Steels, Prehardened Steels, Hardened Steels, High Hardened Steels, Stainless Steels, Cast Iron, Copper, Graphite, Aluminum, Acrylic, CFRP, Titanium, High Temperature Alloy.



E2482 SERIES 8% COBALT (M42) FLAT SHANK

E1482 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 2 FLUTE REGULAR LENGTH

Two flute end mills with metric cutting diameter are especially recommended for slotting operation, pocketing keyway cutting and other general purpose work including plunge cutting.



Table with 6 columns: EDP No. (8% COBALT (M42), HSS (M2)), Mill Diameter (Metric, Inch), Shank Diameter, Length of Cut, Overall Length. Lists various end mill models and their specifications.

Table for Mill Dia. Tolerance (inch) showing 0~+.0010 and ** 0~+.0015.

** The shank of end mills is the same diameter as the cutting portion.

■ The TiN coated, TiCN coated or TiAlN coated is available on your request.
■ Coating Codes for Cobalt
■ Coating Codes for HSS
▶ Coated Price Shown in Price List. Call for Availability.

Material compatibility table with columns P, H, M, K, N, S and rows for Carbon Steels, Alloy Steels, Prehardened Steels, Hardened Steels, High Hardened Steels, Stainless Steels, Cast Iron, Copper, Graphite, Aluminum, Acrylic, CFRP, Titanium, High Temperature Alloy.



E2483 SERIES 8% COBALT (M42) FLAT SHANK
E1483 SERIES HSS (M2) FLAT SHANK

HSSCo8 & HSS, 4 FLUTE REGULAR LENGTH

► E2483 have an extensive range of standard regular length in metric diameter.
 End mills with center cutting are recommended for a wide range of cutting jobs, including slotting, shallow pocketing and tracer milling.



Unit : Inch

EDP No.		Mill Diameter		Shank Diameter	Length of Cut	Overall Length
8% COBALT (M42)	HSS (M2)	Metric	Inch			
16252	16002	2.0	.0787	3/8	3/8	2-5/16
16253	16003	2.5	.0984	3/8	3/8	2-5/16
16254	16004	3.0	.1181	3/8	3/8	2-5/16
16255	16005	3.5	.1378	3/8	1/2	2-3/8
16256	16006	4.0	.1575	3/8	1/2	2-3/8
16257	16007	4.5	.1772	3/8	9/16	2-1/2
16258	16008	5.0	.1969	3/8	9/16	2-1/2
16259	16009	5.5	.2165	3/8	5/8	2-1/2
16260	16010	6.0	.2362	3/8	5/8	2-1/2
16261	16011	7.0	.2756	3/8	11/16	2-1/2
16262	16012	8.0	.3150	3/8	3/4	2-1/2
16263	16013	9.0	.3543	3/8	3/4	2-1/2
16264	16014	10.0	.3937	3/8	1	2-11/16
16265	16015	11.0	.4330	3/8	1	2-11/16
16266	16016	12.0	.4724	3/8	1	2-11/16
16267	16017	12.5	.4921	1/2	1-1/4	3-1/4
16268	16018	13.0	.5118	1/2	1-1/4	3-1/4
16270	16020	14.0	.5512	1/2	1-3/8	3-3/8
16276	16026	16.0	.6299	5/8	1-5/8	3-3/4
16280	16030	18.0	.7087	5/8	1-5/8	3-3/4
16282	16032	20.0	.7874	5/8	1-7/8	4-1/8
16284	16034	22.0	.8661	3/4	1-7/8	4-1/8
16288	16038	24.0	.9449	3/4	2	4-1/2
16290	16040	25.0	.9843	1	2	4-1/2
16296	16046	32.0	1.2598	1	2	4-1/2
16298	16048	36.0	1.4173	1	2	4-1/2
16300	16050	40.0	1.5748	1-1/4	2	4-1/2
16302	16052	45.0	1.7717	1-1/4	2	4-1/2

Mill Dia. Tolerance (inch)	
0~+.0010	** 0~+.0015

** The shank of end mills is the same diameter as the cutting portion.

- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt
 Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
 Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- ▶ Coated Price Shown in Price List. Call for Availability.

◎ : Excellent ○ : Good

P					H	M	K	N					S	
Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Stainless Steels	Cast Iron	Copper	Graphite	Aluminum	Acrylic	CFRP	Titanium	High Temperature Alloy
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	○						○		○				



END MILL SET SERIES

► Various range of sizes in these end mill sets gives you plenty of opportunities to reduce manufacturing costs and improve productivity.

SET OF MINIATURE, (3/16" SHANK) DOUBLE

EDP No.	ITEM No.	EDP No.	ITEM No.	Type	Length	Mill Diameter	No.of Flute
8% COBALT (M42)		HSS (M2)					
96002	CMR211	96001	MR211	Sq. END (11PCS.)	REGULAR	1/32, 3/64, 1/16, 5/64, 3/32, 7/64, 1/8, 9/64, 5/32, 11/64, 3/16	2
96004	CMR409	96003	MR409	Sq. END (9PCS.)	REGULAR	1/16, 5/64, 3/32, 7/64, 1/8, 9/64, 5/32, 11/64, 3/16	4
96006	CMS211	96005	MS211	Sq. END (11PCS.)	STUB	1/32, 3/64, 1/16, 5/64, 3/32, 7/64, 1/8, 9/64, 5/32, 11/64, 3/16	2
96008	CMS409	96007	MS409	Sq. END (9PCS.)	STUB	1/16, 5/64, 3/32, 7/64, 1/8, 9/64, 5/32, 11/64, 3/16	4

- The TiN coated, TiCN coated or TiAlN coated is available on your request. * WITH TRANSPARENT PLASTIC CASE
- Coating Codes for Cobalt
 Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
 Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- ▶ Coated Price Shown in Price List. Call for Availability.

SET OF 3/8" SHANK, (WELDON) SINGLE

EDP No.	ITEM No.	EDP No.	ITEM No.	Type	Length	Mill Diameter	No.of Flute
8% COBALT (M42)		HSS (M2)					
96010	CWR205	96009	WR205	Sq. END (5PCS.)	REGULAR	1/8, 3/16, 1/4, 5/16, 3/8	2
96012	CWR405	96011	WR405	Sq. END (5PCS.)	REGULAR	1/8, 3/16, 1/4, 5/16, 3/8	4
96014	CWRC05	96013	WRC05	CENTER CUT (5PCS.)	REGULAR	1/8, 3/16, 1/4, 5/16, 3/8	04

- The TiN coated, TiCN coated or TiAlN coated is available on your request. * WITH TRANSPARENT PLASTIC CASE
- Coating Codes for Cobalt
 Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
 Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- ▶ Coated Price Shown in Price List. Call for Availability.



END MILL SET SERIES

► Various range of sizes in these end mill sets gives you a plenty of opportunities to reduce manufacturing costs and improve productivity.

■ SET OF 3/8" SHANK, (WELDON) DOUBLE

EDP No.	ITEM No.	EDP No.	ITEM No.	Type	Length	Mill Diameter	No. of Flute
8% COBALT (M42)		HSS (M2)					
96016	CDR209	96015	DR209	Sq. END (9PCS.)	REGULAR	1/8, 5/32, 3/16, 7/32, 1/4, 9/32, 5/16, 11/32, 3/8	2
96018	CDR409	96017	DR409	Sq. END (9PCS.)	REGULAR	1/8, 5/32, 3/16, 7/32, 1/4, 9/32, 5/16, 11/32, 3/8	4
96020	CDRC09	96019	DRC09	CENTER CUT (9PCS.)	REGULAR	1/8, 5/32, 3/16, 7/32, 1/4, 9/32, 5/16, 11/32, 3/8	4


- The TiN coated, TiCN coated or TiAlN coated is available on your request. * WITH TRANSPARENT PLASTIC CASE
- Coating Codes for Cobalt
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coating Codes for HSS
Uncoated EDP NO. + HN(TiN), HC(TiCN), HF(TiAlN F), HE(TiAlN E), HH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.



RECOMMENDED CUTTING CONDITIONS

HSSCo8 & HSS, 2 FLUTE FINISH - SLOTTING

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
HARDNESS			~HRc20		HRc20~HRc30		HRc30~HRc40			
STRENGTH	~ 500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8	3500	2.2	3200	1.8	2500	1.6	1600	0.8	11000	9.8
1/4	1800	3.5	1600	3.1	1200	2.4	800	1.6	5600	12.2
3/8	1100	4.0	900	3.5	800	3.1	450	1.8	3100	15.8
1/2	900	4.3	800	4.0	630	3.1	400	2.0	2500	15.0
5/8	700	4.3	560	3.5	450	2.8	280	1.8	2000	13.8
3/4	630	4.0	500	3.5	400	2.8	250	1.8	1800	13.8
7/8	500	4.0	450	3.5	350	2.8	220	1.8	1400	11.8
1	450	3.5	400	3.1	310	2.4	180	1.4	1200	11.0
1-1/8	400	3.1	350	2.8	280	2.2	160	1.2	1100	10.5
1-3/8	310	2.4	250	2.0	200	1.6	120	1.0	900	8.7
1-1/2	310	2.4	250	2.0	200	1.6	120	1.0	900	8.7
1-3/4	280	2.4	220	2.0	180	1.6	110	1.0	800	7.8
2	250	2.0	190	1.8	110	1.0	80	0.8	630	6.3





※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSS, 2 FLUTE, 42° HELIX FINISH for ALUMINUM


MATERIAL	K		N	
	NON-ALLOYED STEELS ALLOY STEELS CAST IRON		ALUMINUM NONFERROUS METALS	
DIAMETER	RPM	FEED	RPM	FEED
1/8	8000	29.0	8000	22.5
3/16	7400	32.5	7400	25.0
1/4	6800	37.0	6800	28.5
5/16	5200	55.0	5200	43.5
7/16	5000	47.0	5000	47.0
1/2	4500	61.0	4500	47.0
9/16	3500	63.0	3500	49.0
5/8	3500	63.0	3500	49.0
3/4	2300	67.0	2300	51.0
13/16	2000	67.0	2000	51.0



RPM = rev./min.
FEED = inch/min.

HSSCo8, 3 FLUTE FINISH - SLOTting


MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
HARDNESS	~HRC20		HRC20~HRC30		HRC30~HRC40					
STRENGTH	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/32	5600	2.4	4500	1.8	4000	1.8	2200	0.8	12000	9.4
1/8	3500	3.1	3200	2.6	2500	2.4	1600	1.2	11000	15.0
1/4	1800	5.3	1600	4.7	1200	3.5	800	2.4	5600	18.5
3/8	1100	6.0	900	5.3	800	4.7	450	2.6	3100	23.6
1/2	900	6.5	800	6.0	630	4.7	400	3.0	2500	22.4
9/16	800	6.5	700	5.3	560	4.7	350	3.0	2200	20.9
5/8	700	6.5	560	5.3	450	4.1	280	2.6	2000	20.9
7/8	500	6.0	450	5.3	350	4.1	220	2.6	1400	17.7
1	450	5.3	400	4.7	310	3.5	180	2.0	1200	16.5
1-1/8	400	4.7	350	4.1	280	3.1	160	1.8	1100	15.8



* The Feed, in long & extra long types, should be reduced by around 50%. RPM = rev./min. FEED = inch/min.

HSSCo8, 3 FLUTE FINISH - SIDE CUTTING


MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
HARDNESS	~HRC20		HRC20~HRC30		HRC30~HRC40					
STRENGTH	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/32	5600	2.4	4500	1.6	4000	1.4	2200	0.6	12000	7.1
1/8	3500	3.1	3200	2.4	2500	1.8	1600	0.8	11000	11.0
5/32	2800	4.1	2200	3.0	1800	2.0	1100	1.2	8000	13.0
3/16	2200	5.3	1800	3.7	1600	2.6	900	1.4	6300	13.8
1/4	1800	5.3	1600	4.3	1200	2.6	800	1.8	5600	13.8
5/16	1400	6.0	1100	4.7	900	3.1	560	2.0	4000	17.3
3/8	1100	6.0	900	4.7	800	3.8	450	2.0	3100	17.7
1/2	900	6.5	800	5.3	630	3.8	400	2.2	2500	16.9
9/16	800	6.5	700	4.7	560	3.8	350	2.2	2200	15.8
5/8	700	6.5	560	4.7	450	3.1	280	2.0	2000	15.8
11/16	630	6.0	500	4.7	400	3.1	250	2.0	1800	15.8
13/16	560	6.0	450	4.7	400	3.1	220	2.0	1600	14.2
7/8	500	6.0	450	4.7	350	3.1	220	2.0	1400	13.4
1	450	5.3	400	4.3	310	2.6	180	1.4	1200	12.6
1-1/8	400	4.7	350	3.7	280	2.4	160	1.2	1100	11.8
1-3/16	350	4.1	310	3.1	250	2.2	160	1.2	1100	11.8



* The Feed, in long & extra long types, should be reduced by around 50%. RPM = rev./min. FEED = inch/min.

HSSCo8 & HSS, MULTI FLUTE FINISH - SIDE CUTTING


MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
HARDNESS	~HRC20		HRC20~HRC30		HRC30~HRC40					
STRENGTH	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8	3500	4.3	3200	3.1	2500	2.4	1600	1.2	11000	15.0
1/4	1800	7.1	1600	5.7	1200	3.5	800	2.4	5600	18.5
3/8	1100	7.9	900	6.3	800	4.7	450	2.6	3100	23.6
1/2	900	8.7	800	7.1	630	4.7	400	3.0	2500	22.4
5/8	700	8.7	560	6.3	450	4.1	280	2.6	2000	20.9
3/4	630	7.9	500	6.3	400	4.1	250	2.6	1800	20.9
13/16	500	7.9	450	6.3	350	4.1	220	2.6	1400	17.7
15/16	500	7.9	450	6.3	350	4.1	220	2.6	1400	17.7
1	450	7.1	400	5.7	310	3.5	180	2.0	1200	16.5
1-1/2	310	4.7	250	3.5	200	2.4	120	1.4	900	13.0
1-3/4	280	4.7	220	3.5	150	2.4	110	1.4	800	11.8
2	280	4.7	190	3.5	110	1.8	80	1.0	630	11.8



* The Feed, in long & extra long types, should be reduced by around 50%. RPM = rev./min. FEED = inch/min.

HSSCo8, MULTI FLUTE 60° HELIX FINISH - SIDE CUTTING


MATERIAL	P				M		K		
	MILD STEELS		ALLOY STEELS		TOOL STEELS STAINLESS STEELS		CAST IRON		
	~HRC13		HRC13~HRC32		HRC25~HRC35		~HRC20		
DIAMETER	wxd	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	0.02 x 0.35	1840	3.6	1250	2.2	980	1.8	2050	4.8
1/4	0.08 x 0.35	1600	3.6	650	2.2	510	1.6	1100	4.5
5/8	0.02 x 1	750	2.9	460	2.0	390	1.4	840	4.1
5/8	0.18 x 1	650	2.9	400	2.0	340	1.4	730	4.1
3/4	0.02 x 1.2	520	2.5	370	1.8	300	1.4	630	4.1
3/4	0.26 x 1.2	450	2.5	320	1.8	260	1.4	550	4.1
1	0.02 x 1.6	460	2.9	290	1.8	240	1.4	510	4.3
1	0.30 x 1.6	400	2.9	250	1.8	210	1.4	440	4.3
1-1/2	0.02 x 1.6	280	2.5	170	1.4	150	1.3	320	3.6
1-1/2	0.80 x 1.6	240	2.5	150	1.4	130	1.3	280	3.6
2	0.02 x 2	220	2.2	140	1.3	115	1.1	260	2.9
2	1.60 x 2	190	2.2	120	1.3	100	1.1	225	2.9



* The Feed, in long & extra long types, should be reduced by around 50%. RPM = rev./min. FEED = inch/min.

HSSCo8 & HSS, 2 FLUTE BALL NOSE

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~HRC20		HRC20~HRC30		HRC30~HRC40					
HARDNESS	~ 500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
STRENGTH										
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
R1/16 x 1/8	4500	3.7	3400	2.8	2000	1.2	1400	0.8	11000	9.1
R5/64 x 5/32	3200	4.5	2400	3.1	1400	1.4	1000	1.0	8000	10.2
R1/8 x 1/4	2200	5.3	1700	3.5	1000	1.8	700	1.0	5600	11.0
R5/32 x 5/16	1600	6.3	1200	4.1	700	2.0	500	1.2	4000	13.8
R3/16 x 3/8	1300	7.1	1000	4.7	560	2.4	400	1.4	3200	14.2
R1/4 x 1/2	1000	6.7	800	4.1	450	2.2	320	1.4	2500	13.4
R5/16 x 5/8	800	6.0	600	4.0	350	2.2	250	1.4	2000	11.8
R3/32 x 3/16	600	5.5	500	3.4	300	2.0	200	1.4	1600	11.0
R1/2 x 1	500	5.1	400	2.8	220	1.6	160	1.2	1300	9.8




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8 & HSS, MULTI FLUTE BALL NOSE

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~HRC20		HRC20~HRC30		HRC30~HRC40					
HARDNESS	~ 500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
STRENGTH										
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
R1/8 x 1/4	2200	7.9	1700	5.3	1000	2.8	700	1.6	5600	16.5
R5/32 x 5/16	1600	9.4	1200	6.3	700	3.0	500	1.8	4000	20.9
R3/16 x 3/8	1300	10.6	1000	7.1	560	3.5	400	2.0	3200	21.3
R1/4 x 1/2	1000	10.2	800	6.3	450	3.1	320	2.0	2500	20.1
R5/16 x 5/8	800	9.1	600	6.0	350	3.1	250	2.0	2000	17.7
R3/32 x 3/16	600	8.3	500	5.1	300	3.0	200	2.0	1600	16.5
R1/2 x 1	500	7.9	400	4.1	220	2.4	160	1.8	1300	15.0




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8, MULTI FLUTE ROUGHING - SIDE CUTTING

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~HRC20		HRC20~HRC30		HRC30~HRC40					
HARDNESS	~ 500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
STRENGTH										
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	1800	3.1	1600	2.4	1200	2.2	800	1.2	4500	7.9
5/16	1400	4.1	1100	3.0	900	2.6	560	1.4	3100	9.1
3/8	1100	6.0	900	4.7	800	4.3	450	2.4	2500	13.8
1/2	900	7.1	800	5.5	630	4.3	400	2.8	2000	15.8
5/8	700	7.1	560	5.5	450	4.3	280	2.8	1600	17.7
11/16	630	7.1	500	5.5	400	4.3	250	2.8	1400	18.5
7/8	500	8.7	450	6.7	350	5.5	220	3.4	1100	18.5
1	450	8.7	400	6.7	310	5.5	180	3.4	1000	17.7
1-1/8	400	8.1	350	6.3	280	5.1	160	3.4	900	20.1
1-1/4	350	8.1	280	6.3	220	5.1	140	3.4	800	19.7
1-3/8	310	8.1	250	6.3	200	5.1	120	3.4	700	18.5
1-3/4	280	7.9	220	6.0	180	4.7	110	3.1	630	17.7
2	220	7.9	180	6.7	160	5.5	90	3.1	500	14.6




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8, MULTI FLUTE BALL NOSE ROUGHING - SIDE CUTTING

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~HRC20		HRC20~HRC30		HRC30~HRC40					
HARDNESS	~ 500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
STRENGTH										
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
R5/32 x 5/16	1400	4.1	1100	3.0	900	2.6	560	1.4	3100	9.1
R3/16 x 3/8	1100	6.0	900	4.7	800	4.3	450	2.4	2500	9.8
R1/4 x 1/2	900	7.1	800	5.5	630	4.3	400	2.8	2000	15.8
R5/16 x 5/8	700	7.1	560	5.5	450	4.3	280	2.8	1600	17.7
R7/16 x 7/8	560	7.1	450	5.5	400	4.3	220	2.8	1200	19.7
R1/2 x 1	450	8.7	400	6.7	310	5.5	180	3.4	1000	17.7
R5/8 x 1-1/4	350	8.1	280	6.3	220	5.1	140	3.4	800	19.7
R7/8 x 1-3/4	280	7.9	220	6.0	180	4.7	110	3.1	630	17.7




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8 & HSS, MULTI FLUTE ROUGHING & FINISHING - SIDE CUTTING

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~HRC20		HRC20~HRC30		HRC30~HRC40					
HARDNESS	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
STRENGTH										
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	1800	2.5	1300	2.0	1200	1.8	800	1.0	4500	6.3
5/16	1400	3.4	1100	2.4	900	2.2	560	1.2	3100	7.3
3/8	1100	4.7	900	3.7	800	3.5	450	2.0	2500	11.0
1/2	900	5.7	800	4.3	630	3.5	400	2.2	2000	12.6
5/8	700	5.7	560	4.3	450	3.5	280	2.2	1600	14.2
11/16	630	5.7	500	4.3	400	3.5	250	2.2	1400	15.0
7/8	500	6.9	450	5.3	350	4.3	220	2.8	1100	15.0
1	450	6.9	400	5.3	310	4.3	180	2.8	1000	14.2
1-1/4	350	6.7	280	5.1	220	4.1	140	2.8	800	15.8
1-3/8	310	6.7	250	5.1	200	4.1	120	2.8	700	15.0
2	240	5.4	190	4.0	150	3.4	110	2.6	500	11.2



※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8 & HSS, MINIATURE

MATERIAL	P								N	
	HIGH TENSILE STEELS MEDIUM STRENGTH STAINLESS STEELS MEDIUM STRENGTH TITANIUM SLOOYS		MEDIUM TENSILE STEELS UNALLOYED TITANIUM TOOL STEELS HEAT RESISTANT FERRITIC LOW ALLOYS		VILD STEEL FORGING HARD BRASS & BRONZE COPPER		ALUMINUM ALUMINUM ALLOYS PLASTIC WOODS		ALUMINUM ALUMINUM ALLOYS	
	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	6600~8800	0.3	11000 up	0.5	11000 up	0.8	11000 up	1.2	11000 up	1.5
1/32	3300~4400	0.5	5500~5600	0.6	7700~9900	1.6	11000 up	1.6	11000 up	2.5
3/64	2200~2935	0.6	3665~4400	0.6	5135~6600	2.5	7335~8800	2.0	11000 up	2.6
1/16	1650~2260	0.6	2750~3300	1.0	3350~4950	3.3	5500~6600	2.6	11000 up	4.2
5/64	1320~1760	0.6	2200~2640	1.0	3850~3960	3.3	4400~5820	2.6	8500 up	4.2
3/32	1100~1285	0.6	1835~2200	1.0	2565~3300	3.3	3665~4400	2.6	7330up	4.2
7/64	345~1255	0.6	1570~1885	1.0	2200~2830	3.3	3140~3770	2.6	5625 up	4.3
1/8	825~1100	0.6	1375~1650	1.0	1925~2475	3.3	2750~3300	2.8	5500 up	4.5
9/64	735~980	0.6	1220~1465	1.0	1710~2200	3.4	2445~3770	2.8	4890~9780	4.5
5/32	560~880	0.8	1100~1320	1.1	1540~1980	3.6	2205~2640	2.9	4400~8800	4.5
11/64	600~800	0.9	1000~1200	1.2	1400~1800	3.7	2000~2400	3.0	4000~3000	4.6
3/16	550~735	1.0	915~1100	1.4	1285~1650	3.3	1535~2200	3.3	3685~7335	4.7


NOTES :
(1) The cutting conditions in this table are given for reference, which should be varied depending on the machine, tooling, depth of cut, cutting fluid and other conditons.

(2) Use a holder of strong gripping force and machine of high stiffness

RPM = rev./min.
FEED = inch/min.

HSSCo8 & HSS, 2 FLUTE FINISH TiN-COATED - SLOTTING

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~HRC20		HRC20~HRC30		HRC30~HRC40					
HARDNESS	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
STRENGTH										
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8	4200	2.6	3840	2.2	3000	1.9	1920	1.0	13200	11.8
1/4	2160	4.2	1920	3.7	1440	2.9	960	1.9	6720	14.6
3/8	1320	4.8	1080	4.2	960	3.7	540	2.2	3720	19.0
1/2	1090	5.2	960	4.8	756	3.7	480	2.4	3000	18.0
5/8	840	5.2	672	4.2	540	3.7	336	2.2	2400	16.6
3/4	756	4.8	600	4.2	480	3.4	300	2.2	2160	16.6
7/8	600	4.8	540	4.2	420	3.4	264	2.2	1680	14.2
1	540	4.2	480	3.7	372	2.9	260	2.2	1440	13.2
1-1/8	480	3.7	420	3.4	336	2.6	432	1.7	1320	12.6
1-3/8	372	2.9	300	2.4	240	1.9	144	1.2	1080	10.4
1-1/2	372	2.9	300	2.4	240	1.9	144	1.2	1080	10.4
1-3/4	336	2.9	264	2.4	216	1.9	132	1.2	960	9.5
2	300	2.4	228	2.2	132	1.2	96	1.0	756	7.6




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8 & HSS, 3 FLUTE FINISH TiN-COATED - SLOTTING

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~HRC20		HRC20~HRC30		HRC30~HRC40					
HARDNESS	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
STRENGTH										
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/32	6720	2.8	5400	2.2	4800	2.2	2640	1.0	14400	11.3
1/5	4200	3.7	3840	3.1	3000	2.9	1920	1.4	13200	18.0
1/4	2160	6.4	1920	5.6	1440	4.2	960	2.9	6720	21.7
3/8	1320	7.2	1080	6.4	960	5.6	540	3.1	3720	28.3
1/2	1080	7.8	960	7.2	756	5.6	480	3.6	3000	26.9
5/8	840	7.8	672	6.4	540	4.9	336	3.1	2400	25.1
11/16	756	7.2	600	6.4	480	4.9	300	3.1	2160	25.1
7/8	600	7.2	540	6.4	420	4.9	264	3.1	1680	21.2
1	540	6.4	480	5.6	372	4.2	216	2.4	1440	19.8
1-1/8	430	5.6	420	4.9	336	3.7	192	2.2	1320	19.0
1-3/16	420	4.9	372	4.2	300	3.6	192	2.2	1320	19.0




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8 & HSS, 3 FLUTE FINISH TiN-COATED - SIDE CUTTING

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~HRC20		HRC20~HRC30		HRC30~HRC40					
HARDNESS	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
STRENGTH										
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/32	6720	2.9	5400	1.9	4800	1.7	2640	0.7	14400	8.5
1/8	4200	3.7	3840	2.9	3000	2.2	1920	1.0	13200	13.2
1/4	2160	6.4	1920	5.2	1440	3.1	960	2.2	6720	16.6
3/8	1320	7.2	1080	5.6	960	4.2	540	2.4	3720	21.2
1/2	1080	7.8	960	6.4	756	4.2	480	2.6	3000	20.3
9/16	960	7.8	840	5.6	672	4.2	420	2.6	2640	19.0
5/8	840	7.8	672	5.6	540	3.7	336	2.4	2400	19.0
11/16	756	7.2	600	5.6	480	3.7	300	2.4	2160	19.0
7/8	600	7.2	540	5.6	420	3.7	264	2.4	1680	16.1
1	540	6.4	480	5.2	372	3.1	216	1.7	1440	15.1
1-1/8	430	5.6	420	4.4	336	2.9	192	1.4	1320	14.2




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8 & HSS, MULTI FLUTE FINISH TiN-COATED - SIDE CUTTING

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~HRC20		HRC20~HRC30		HRC30~HRC40					
HARDNESS	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
STRENGTH										
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8	4200	5.2	3840	3.7	3000	2.9	1920	1.4	13200	18.0
1/4	2640	8.5	1920	6.8	1440	4.2	960	2.9	6720	22.2
3/8	1320	9.5	1080	7.6	960	5.6	540	3.1	3700	28.3
1/2	1080	10.4	960	8.5	756	5.6	480	3.6	3000	26.9
5/8	840	10.4	672	7.6	540	4.9	336	3.1	2400	25.1
3/4	756	9.5	600	7.6	480	4.9	300	3.1	2160	25.1
7/8	600	9.5	540	7.6	420	4.9	264	3.1	1680	21.2
15/16	600	9.5	540	7.6	420	4.9	264	3.1	1680	21.2
1	540	8.5	480	6.8	372	4.2	216	2.4	1440	19.8
1-1/2	372	5.6	300	4.2	240	2.9	144	1.7	1080	15.6
1-3/4	336	5.6	264	4.2	216	2.9	132	1.7	960	14.2
2	336	5.6	264	4.2	168	2.2	96	1.2	960	14.2




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8 & HSS, 2 FLUTE BALL NOSE TiN-COATED

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~HRC20		HRC20~HRC30		HRC30~HRC40					
HARDNESS	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
STRENGTH										
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
R1/16 × 1/8	5400	4.4	4080	3.4	2400	1.4	1680	1.0	13200	10.9
R5/64 × 5/32	3840	5.4	2880	3.7	1680	1.7	1200	1.2	9600	12.2
R1/8 × 1/4	2640	6.4	2040	4.2	1200	2.2	840	1.2	6720	13.2
R5/32 × 5/16	1920	7.6	1440	4.9	840	2.4	600	1.4	4800	16.6
R3/16 × 3/8	1560	8.5	1200	5.6	672	2.9	480	1.7	3840	17.0
R1/4 × 1/2	1200	8.0	960	4.9	540	2.6	384	1.7	3330	16.1
R5/16 × 5/8	960	7.2	720	4.8	420	2.6	300	1.7	2400	14.2
R3/32 × 3/16	720	6.6	600	4.1	360	2.4	240	1.7	1923	13.2
R1/2 × 1	600	6.1	480	3.4	264	1.9	192	1.4	1560	11.8




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8 & HSS, MULTI FLUTE BALL NOSE TiN-COATED

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~HRC20		HRC20~HRC30		HRC30~HRC40					
HARDNESS	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
STRENGTH										
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
R1/8 × 1/4	2640	9.5	2040	6.4	1200	3.4	840	1.9	6720	19.8
R5/32 × 5/16	1920	11.3	1440	7.6	840	3.6	600	2.2	4800	25.1
R3/16 × 3/8	1560	12.7	1200	8.5	672	4.2	480	2.4	3840	25.6
R1/4 × 1/2	1200	12.2	960	7.6	540	3.7	384	2.4	3000	24.1
R5/16 × 5/8	960	10.9	720	7.2	420	3.7	300	2.4	2400	21.2
R3/32 × 3/16	720	10.0	600	6.1	380	3.6	240	2.4	1920	19.8
R1/2 × 1	600	9.5	480	4.8	264	2.9	192	2.2	1560	18.0




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8, MULTI FLUTE ROUGHING TiN-COATED - SIDE CUTTING

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~HRC20		HRC20-HRC30		HRC30-HRC40					
HARDNESS	~500N/mm ²		500-800N/mm ²		800-1000N/mm ²		1000-1300N/mm ²			
STRENGTH	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
DIAMETER										
1/4	2160	3.7	1920	2.9	1440	2.6	960	1.4	5400	9.5
5/16	1680	4.9	1320	3.6	1080	3.1	672	1.7	3720	10.9
3/8	1320	7.2	1080	5.6	960	5.2	540	2.9	3000	16.6
1/2	1080	8.5	960	6.6	756	5.2	480	3.4	2400	19.0
5/8	840	8.5	672	6.6	540	5.2	336	3.4	1920	22.2
11/16	756	8.5	600	6.6	480	5.2	300	3.4	1680	22.2
7/8	600	10.4	540	8.0	420	6.6	264	4.1	1320	21.2
1	540	10.4	480	8.0	372	6.6	216	4.1	1200	21.2
1-1/8	480	9.7	420	7.6	336	6.1	192	4.1	1680	24.1
1-1/4	420	9.7	336	7.6	264	6.1	168	4.1	960	23.6
1-3/8	372	9.7	300	7.6	240	6.1	144	4.1	840	22.2
1-3/4	336	9.5	264	7.2	216	5.6	132	3.7	756	21.2
2	264	9.5	216	8.0	192	6.6	108	3.7	600	17.5




* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8, MULTI FLUTE ROUGHING & FINISHING TiN-COATED - SIDE CUTTING

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~HRC20		HRC20-HRC30		HRC30-HRC40					
HARDNESS	~500N/mm ²		500-800N/mm ²		800-1000N/mm ²		1000-1300N/mm ²			
STRENGTH	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
DIAMETER										
1/4	2160	3.0	1920	2.4	1440	2.2	960	1.2	5400	7.6
5/16	1680	4.0	1320	2.9	1080	2.4	672	1.4	3720	8.8
3/8	1320	5.6	1080	4.4	960	4.2	540	2.4	3000	13.2
1/2	1080	6.8	960	5.2	756	4.2	480	2.6	2400	15.1
5/8	840	6.8	672	5.2	540	4.2	336	2.6	1920	17.6
11/16	756	6.8	600	5.2	480	4.2	300	2.6	1680	18.0
7/8	600	8.3	540	6.4	420	5.2	264	3.4	1320	18.0
1	540	8.3	480	6.4	372	5.2	216	3.4	1200	17.6
1-1/4	420	8.0	336	6.1	264	4.9	168	3.4	960	19.0
1-3/8	372	8.0	300	6.1	240	4.9	144	3.4	840	18.0
2	288	6.4	228	4.8	192	4.1	132	3.1	600	13.4




* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8 & HSS, 2 FLUTE FINISH TiCN-COATED - SLOTting

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~HRC20		HRC20-HRC30		HRC30-HRC40					
HARDNESS	~500N/mm ²		500-800N/mm ²		800-1000N/mm ²		1000-1300N/mm ²			
STRENGTH	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
DIAMETER										
1/8	4550	2.9	3840	2.3	3250	2.1	2048	1.0	14300	12.7
1/4	2340	4.6	2080	4.0	1560	3.1	1040	3.2	7280	15.9
3/8	1430	5.2	1170	4.6	1040	4.0	585	3.2	4030	20.5
1/2	1170	5.6	1040	5.2	819	4.0	520	2.8	3250	19.5
5/8	910	5.6	728	4.6	585	3.6	364	2.3	2600	17.9
3/4	819	5.2	650	4.6	520	3.6	325	2.3	2340	17.9
7/8	650	5.2	585	4.6	455	3.6	286	2.3	1820	15.3
1	585	4.6	520	4.0	403	3.1	234	1.8	1560	14.3
1-1/8	520	4.0	455	3.6	364	2.9	208	1.6	1430	13.7
1-3/8	403	3.1	325	2.6	260	2.1	156	1.3	1170	11.3
1-1/2	403	3.1	325	2.6	260	2.1	156	1.3	1170	11.3
1-3/4	364	3.1	286	2.6	234	2.1	143	1.3	1040	10.3
2	325	2.6	228	2.3	143	1.3	104	1.0	819	8.2




* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8, 3 FLUTE FINISH TiCN-COATED - SLOTting

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~HRC20		HRC20-HRC30		HRC30-HRC40					
HARDNESS	~500N/mm ²		500-800N/mm ²		800-1000N/mm ²		1000-1300N/mm ²			
STRENGTH	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
DIAMETER										
3/32	7280	3.1	5850	2.3	5200	2.3	2860	1.0	15600	12.2
1/8	4550	4.0	2340	3.4	3250	3.1	2080	1.6	14300	19.5
1/4	2340	6.9	2080	6.1	1560	4.6	1040	3.1	7280	23.5
3/8	1430	7.8	1170	6.9	1040	6.1	585	3.4	4030	30.7
1/2	1170	8.5	1040	7.8	819	6.1	520	3.8	3250	29.1
9/16	1040	8.5	910	6.9	728	6.1	455	3.8	2860	27.2
5/8	910	8.5	728	6.9	585	5.3	364	3.4	2600	27.2
7/8	650	7.8	585	6.9	455	5.3	286	3.4	1820	23.0
1	585	6.9	520	6.1	403	4.6	234	2.6	1560	21.5
1-1/8	520	6.9	455	5.3	364	4.3	208	2.3	1430	20.5



* The Feed, in long & extra long types, should be reduced by around 50%.


RPM = rev./min.
FEED = inch/min.

CBN END MILLS
i-Xmill END MILLS
i-SMART MODULAR TYPE END MILLS
X5070 END MILLS
4G MILL END MILLS
X-POWER END MILLS
JET-POWER END MILLS
TiTaNox -POWER END MILLS
V7 PLUS A END MILLS
V7 MILL INOX END MILLS
ALU-POWER HPC END MILLS
ALU-POWER END MILLS
D-POWER GRAPHITE END MILLS
D-POWER CFRP END MILLS
ROUTERS CFRP
STANDARD CARBIDE END MILLS
ONLY ONE COATED PM60 END MILLS
SINE -POWER END MILLS
TANK-POWER END MILLS
STANDARD COBALT & HSS END MILLS
TECHNICAL DATA

CBN END MILLS
i-Xmill END MILLS
i-SMART MODULAR TYPE END MILLS
X5070 END MILLS
4G MILL END MILLS
X-POWER END MILLS
JET-POWER END MILLS
TiTaNox -POWER END MILLS
V7 PLUS A END MILLS
V7 MILL INOX END MILLS
ALU-POWER HPC END MILLS
ALU-POWER END MILLS
D-POWER GRAPHITE END MILLS
D-POWER CFRP END MILLS
ROUTERS CFRP
STANDARD CARBIDE END MILLS
ONLY ONE COATED PM60 END MILLS
SINE -POWER END MILLS
TANK-POWER END MILLS
STANDARD COBALT & HSS END MILLS
TECHNICAL DATA

HSSCo8 & HSS, 3 FLUTE FINISH TiCN-COATED - SIDE CUTTING

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
HARDNESS	~HRc20								HRc20~HRc30	
STRENGTH	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
3/32	7280	3.1	5850	2.1	5200	1.8	2860	0.8	15600	9.2
1/8	4550	4.0	4160	3.1	3250	2.3	2080	1.0	14300	14.3
1/4	2240	6.9	2080	5.6	1560	3.4	1040	2.3	7280	17.9
5/16	1820	7.8	1430	5.1	1170	4.0	728	2.6	5200	22.5
1/2	1170	8.5	1040	6.9	819	4.6	520	2.9	3250	22.0
9/16	1040	8.5	910	6.1	728	4.6	455	2.9	2860	20.5
5/8	910	8.5	728	6.1	585	4.6	364	2.6	2600	20.5
11/16	819	7.8	650	6.1	520	4.0	325	2.6	2340	20.5
7/8	650	7.8	585	6.1	455	4.0	286	2.6	1820	17.4
1	585	6.9	520	5.6	403	3.4	234	1.8	1560	16.4
1-1/8	520	6.1	455	4.8	362	3.1	208	1.6	1430	15.3




* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8 & HSS, MULTI FLUTE FINISH TiCN-COATED - SIDE CUTTING

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
HARDNESS	~HRc20								HRc20~HRc30	
STRENGTH	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/8	4550	5.6	4160	4.0	3250	3.1	22080	1.6	14300	19.5
1/4	2340	9.2	2090	8.4	1560	4.6	1040	3.1	7280	24.1
3/8	1430	10.3	1170	8.2	1040	6.1	585	3.4	4030	30.7
1/2	1170	11.3	1040	9.2	818	6.1	520	3.9	3250	29.1
5/8	910	11.3	728	8.2	585	5.3	364	3.4	2600	27.2
3/4	819	10.3	650	8.2	520	5.3	325	3.4	2340	27.2
7/8	650	10.3	585	8.2	455	5.3	286	3.4	1820	23.0
15/16	650	10.3	585	8.2	455	5.3	234	3.4	1820	23.0
1	585	9.2	520	8.4	403	4.6	208	2.6	1560	21.9
1-1/2	403	6.1	325	4.6	260	3.1	156	1.8	1170	16.9
1-3/4	364	6.1	286	4.6	234	3.1	143	1.8	1040	15.3
2	364	6.1	286	4.6	182	2.3	104	1.3	1040	15.3




* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8 & HSS, 2 FLUTE BALL NOSE TiCN-COATED

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
HARDNESS	~HRc20								HRc20~HRc30	
STRENGTH	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
R1/16 × 1/8	5850	4.8	4420	3.6	2600	1.6	1820	1.0	14300	11.8
R5/64 × 5/32	4160	5.9	3120	4.0	1820	1.8	1300	1.3	10400	13.3
R1/8 × 1/4	2860	6.9	2210	4.6	1300	2.3	910	1.3	7280	12.3
R5/32 × 5/16	2080	8.2	1560	5.3	910	2.6	650	1.6	5200	17.9
R3/16 × 3/8	1690	9.2	1300	6.1	728	3.1	520	1.8	4160	18.5
R1/4 × 1/2	1300	8.7	1040	5.3	585	2.9	416	1.8	3250	17.4
R5/16 × 5/8	1043	7.8	780	5.2	455	2.9	325	1.8	2600	15.3
R3/32 × 3/16	780	7.2	650	4.4	390	2.6	263	1.8	2080	14.8
R1/2 × 1	650	6.6	520	3.6	286	2.1	208	1.6	1690	12.7




* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8 & HSS, MULTI FLUTE BALL NOSE TiCN-COATED

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
HARDNESS	~HRc20								HRc20~HRc30	
STRENGTH	~500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
R1/8 × 1/4	2860	10.3	2210	6.9	1300	3.6	910	2.1	7280	21.5
R5/32 × 5/16	2080	12.2	1560	8.2	910	3.9	650	2.3	5200	27.2
R3/16 × 3/8	1690	13.8	1300	9.2	728	4.6	520	2.6	4160	27.7
R1/4 × 1/2	1300	13.3	1040	8.2	585	4.0	416	2.6	3250	26.1
R5/16 × 5/8	1040	11.8	780	7.8	455	4.0	325	2.6	2600	23.0
R3/32 × 3/16	780	10.8	650	6.6	390	3.9	260	2.6	2080	21.5
R1/2 × 1	650	10.3	520	5.2	286	3.1	208	2.3	1690	19.5



* The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

CARBIDE

HSS

CBN
END MILLS

i-Xmill
END MILLS

i-SMART
MODULAR
TYPE END MILLS

X5070
END MILLS

4G MILL
END MILLS

X-POWER
END MILLS

JET-POWER
END MILLS

TitaNox
-POWER
END MILLS

V7 PLUS A
END MILLS

V7 MILL INOX
END MILLS

ALU-POWER
HPC
END MILLS

ALU-POWER
END MILLS

D-POWER
GRAPHITE
END MILLS

D-POWER
CFRP
END MILLS

ROUTERS
CFRP

STANDARD
CARBIDE
END MILLS

ONLY ONE
COATED PM60
END MILLS

SINE -POWER
END MILLS

TANK-POWER
END MILLS

STANDARD
COBALT & HSS
END MILLS


TECHNICAL
DATA



RECOMMENDED CUTTING CONDITIONS

HSSCo8, MULTI FLUTE ROUGHING TiCN-COATED - SIDE CUTTING

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~ 500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
HARDNESS	~HRC20		HRC20~HRC30		HRC30~HRC40					
STRENGTH	~ 500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	2340	4.0	2080	3.1	1560	2.9	1040	1.6	5850	10.3
5/16	1820	5.3	1430	3.9	1170	3.4	728	1.8	4030	11.5
3/8	1430	7.8	1170	6.1	1040	5.6	585	3.1	3250	17.9
1/2	1170	9.2	1040	7.2	819	5.6	520	3.6	2600	20.5
5/8	910	9.2	728	7.2	585	5.6	364	3.6	2080	24.1
11/16	819	9.2	650	7.2	520	5.6	325	3.6	1820	24.1
7/8	650	11.3	585	8.7	455	7.2	286	4.4	1430	23.0
1	585	11.3	520	8.7	403	7.2	234	4.4	1300	23.0
1-1/8	520	10.5	455	8.2	364	6.6	208	4.4	1170	26.1
1-1/4	455	10.5	364	8.2	286	6.6	182	4.4	1040	25.6
1-3/8	403	10.5	325	8.2	260	6.6	156	4.4	910	24.1
1-3/4	364	10.3	286	7.8	234	6.1	143	4.0	819	23.0
2	286	10.3	234	8.7	208	7.2	117	4.0	650	19.0




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.

HSSCo8, MULTI FLUTE ROUGHING & FINISHING TiCN-COATED - SIDE CUTTING

MATERIAL	P								N	
	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~ 500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
HARDNESS	~HRC20		HRC20~HRC30		HRC30~HRC40					
STRENGTH	~ 500N/mm ²		500~800N/mm ²		800~1000N/mm ²		1000~1300N/mm ²			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	2340	3.3	2080	2.6	1560	2.3	1040	1.3	5850	8.2
5/16	1820	4.4	1430	3.1	1170	2.6	728	1.6	4030	9.5
3/8	1430	6.1	1170	4.8	1040	4.6	585	2.6	3250	14.3
1/2	1170	7.4	1040	5.6	819	4.6	520	2.9	2600	16.4
5/8	910	7.4	728	5.6	585	4.6	364	2.9	2080	18.5
11/16	819	7.4	650	5.6	520	4.6	325	2.9	1820	19.5
7/8	650	9.0	585	6.9	455	5.6	286	3.6	1430	19.5
1	585	9.0	520	6.9	403	5.6	234	3.6	1300	18.5
1-1/4	455	8.7	384	6.6	286	5.3	182	3.6	1040	20.5
1-3/4	403	8.7	325	6.6	260	5.3	156	3.6	910	19.5
2	312	7.0	247	5.2	238	4.4	143	3.9	650	14.6



※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.
FEED = inch/min.



Being the best through innovation


END MILLS




TECHNICAL DATA



Names of End Mill Parts




Type of End Mill



Speed, feed and depth of cut are the most important factors to consider for best results in milling. Improper feeds and speeds often cause low production, poor work quality and unnecessary damage to the cutter.

This section covers the basic principles of speed and feed selection for milling cutters and end mills. It will serve as a guide in setting-up new milling jobs.



Speeds

In milling, Speed is measured in peripheral feet per minute.(revolution per minute × cutter circumference in feet) This is frequently referred to as “peripheral speed” “cutting speed” or “surface speed”.

$$\text{Revolutions per Minute } N = \frac{1000V}{\pi \times D}$$

V : Cutting Speed(m/min)
 D : Diameter of Tool(mm)
 N : Revolution per minute(rev/min)
 π : 3.1416

They will have to be tempered to suit the conditons ON THE JOB. For example:

Use Lower Speed Ranges for	Use Higher Speed Ranges for
Hard materials Tough materials Abrasive materials Heavy cuts Minimum tool wear Maximum cutter life	Softer materials Better finishes Smaller diameter cutters Light cuts Frail work pieces or set-ups Hand feed operations Maximum production rates Non-metallics



Feeds

Feed is usually measured in millimeters per minute. It is the product of feed per tooth times revolution per minute times the number of teeth in the cutter. Due to variations in cutter sizes, numbers of teeth and revolutions per minute, all feed rates should be calculated from feed per tooth. Feed per tooth is the basis of all feed rates per minute, whether the cutters are large or small, fine or coarse tooth, and are run at high or low peripheral speed. Because feed per tooth affects chip thickness. It is a very important factor in cutter life.

Highest possible feed per tooth will usually give longer cutter life between grinds and greater production per grind. Excessive feeds may over load the cutter teeth and cause breakage or chipping of the cutting edges. The following factors should be kept in mind when using the recommended starting feed per tooth.

Feed in millimeters per Minute
 $F.M = F.R. \times R.P.M$

F.R. : Feed per Revolutions in millimeters
 R.P.M .: Revolutions per Minutes

The following factors should be kept in mind when using the recommended stating feed per tooth.

Use Higher Feeds For	Use Lower Feeds For
Heavy, roughing cuts Rigid set-ups Easy-to-machine work materials Rugged cutters Slab milling cuts Low tensile strength materials Coarse tooth cutters Abrasive materials	Light, and finishing cuts Frail set-ups Hard to machine work materials Frail and small cutters Deep slots High tensile strength materials Fine tooth cutters

SPEED AND FEED CALCULATIONS FOR MILLING CUTTERS AND OTHER ROTATING TOOLS

TO FIND	HAVING	FORMULA
Surface(or Periphery) Speed in meter Per Minute=S.P.M.	Diameter of Tool in millimeters =D Revolutions per Minute =R.P.M.	$V = \frac{D \times 3.1416 \times R.P.M.}{1000}$
Revolutions Per Minute=R.P.M.	Surface Speed in meter per Minute =S.P.M Diameter of Tool in millimeters =D	$R.P.M. = \frac{V \times 1000}{D \times 3.1416}$
Feed per Revolution in millimeters-F.R.	Feed in millimeters per Minute =F.M. Revolution per Minute =R.P.M.	$F.R. = \frac{F.M.}{R.P.M.}$
Feed in millimeters Per Minute-F.M.	Feed per Revolution in millimeters =F.R. Revolution per Minute =R.P.M.	$F.M. = F.R. \times R.P.M.$
Number of Cutting Teeth per Minute=T.M.	Number of Teeth in Tool =T Revolution per Minute =R.P.M.	$T.M. = T \times R.P.M.$
Feed per tooth=F.T.	Number of Teeth in Tool =T Feed per Revolution in millimeters =R.P.M.	$F.T. = \frac{F.R.}{T}$
Feed per Tooth=F.T.	Number of Teeth in Tool =T Feed in millimeters per Minute =F.M. Speed in Revolution per Minute =R.P.M.	$F.T. = \frac{F.M.}{T \times R.P.M.}$

5 Case of Resharpener

When the product finish become worse, the cutting edge must get dulled, chips become smaller and the cutting sound gets louder. In such cases, an end mill must be resharpened. The following are the damages of end mills when the resharpening is required.




Fig. 1. Damages of Cutting Edge

6 Sharpen at Predetermined Wear Land

Cutters should be sharpened as soon as the wear land(Fig. 2.) reaches a predetermined width. This width should permit sharpening without excessive loss of tool life. It may vary from a few hundredths to some tenth of a millimeter, depending on the type of cutter and the finish required on the product. This method is used on production runs where uneven amounts of stock is removed or where the material varies in machinability. It is also used on small quantity product lots.




Fig. 2. Wear Land

7 Resharpener Peripheral Cutting Edge

1 RESHARPENING PERIPHERAL CUTTING EDGE

The geometry of relief angle in an end mill consists of three methods as shown in Fig.3 concave, flat, and eccentric. Recently, most end mills have the eccentric relief(eccentric sharpening). In this method, since the relief is formed an eccentric arc surface in cylindrical grinding method, the roughness of the finished surface of the relief improves and the strength of cutting edge increase at the same time.(Fig.4) As a result, the tool life is improved.




Fig. 3. Three Types of Primary Relief




Fig. 4. Tothing of Eccentric Relief Angle

2 ANGLE OF WHEEL INCLINATION

Eccentric relief is produced with a plain wheel positioned with its axis parallel or at a slight angle with the cutter axis. The degree of relief is varied by changing the angle of wheel inclination.

Table 1. RECOMMENDED RELIEF ON END MILLS

Mill Diameter (inches)	Eccentric relief indicator drop for relief Angles shown		Checking Distance	Wheel Angles(Deg.) \ominus			Radial Relief Angles(α 1)	Clearance Angles(α 2)
	Min	Max.		15° Helix	30° Helix	60° Helix		
-			-	*Angle	*Angle	*Angle	*Angle	*Angle
1/8	.0040	.0052	.015	4°42'	10°02'	27°58'	17°03'	25°
1/4	.0035	.0050	.020	3°15'	6°59'	20°12'	12°00'	25°
1/2	.0040	.0053	.025	2°51'	6°07'	17°51'	10°32'	25°
1	.0038	.0055	1/32	2°16'	4°54'	14°27'	8°27'	25°
1-1/2	.0033	.0050	1/32	2°02'	4°22'	12°57'	7°33'	25°
2	.0033	.0050	1/32	2°02'	4°22'	12°57'	7°33'	25°

The actual at the radial relief angle is normally kept within the range shown but may be varied to suit the cutter material, the work material and the operating conditions.

* Angle is calculated from the basic mean at the radical angle.

8 Resharpener End Teeth

The three necessary operations and one option feature, along with setup suggestions are shown in Fig.5 A to D in each drawing, the shaded area indicates the surface being ground.




Fig 5. PROCEDURE FOR SHARPENING END OF 2 FLUTE SQUARE END MILLS

9 Inspection

The inspection is calculated by using the formula shown in Table1.

Procedure To Check Radial Relief Angles With Indicators.

1. Mount the cutter to rotate freely with no end movement.
2. Adjust the sharp pointed indicator to bear at the very tip of the cutting edge, pointing in a radial line, shown in Figure6
3. Roll the cutter the tabulated amount gives under "checking distance" using the second indicator as control.
4. Consult chart for amount of drop for the particular diameter and relief angle.





Fig. 6. Indicator Set-Up for Checking

10 Standard Weldon Shanks



11 Dimensions

All dimensions are given in inches.

Diameter of Shank S	Length of Shank U	V	W		X	Y
			Min.	Max.		
3/8	1-9/16	25/32	0.280	0.282	0.325	-
1/2	1-25/32	57/64	0.330	0.332	0.440	-
5/8	1-29/32	61/64	0.400	0.402	0.560	-
3/4	2-1/32	1-1/64	0.455	0.457	0.675	-
7/8	2-1/32	1-1/64	0.455	0.457	0.810	1/2
1	2-9/32	1-9/64	0.515	0.517	0.925	1/2
1-1/4	2-9/32	1-9/64	0.515	0.517	1.156	1/2
1-1/2	2-11/16	1-3/16	0.515	0.517	1.406	9/16
2	3-1/4	1-27/32	0.700	0.702	1.900	27/32
2-1/2	3-1/2	1-15/16	0.700	0.702	2.400	27/32


12 Tolerances

Element	Range	Direction	Tolerance
Diameter of Shank, S	All Sizes	minus	.0001 to .0005
Length of Shank, U	All Sizes	plus or minus	1/32
Dimension, V	All Sizes	plus or minus	1/64
Dimension, X	All Sizes	minus	1/64
Dimension, Y	7/8 to 2-1/2 inc.	plus or minus	1/32

Extracted from Milling Cutters and End Mills. MCTI 1989.

13 Combination Shanks for End Mills

Right hand End Mill shank shown. For left hand End Mills flat "F" and pin groove "K" should be located 180° from that shown, maintaining 12° relationship of flat "F" and groove "K"



14 Dimensions

All dimensions are given in inches.

Diameter of Shank A	Length of Shank L	B	C	D	E	F	G	H	J	K	M
1-1/2	2-11/16	1-3/16	0.515	1.406	1-1/2	0.515	1.371	9/16	1.302	0.377	7/16
2	3-1/4	1-23/32	0.700	1.900	1-3/4	0.700	1.809	5/8	1.772	0.440	1/2
2-1/2	3-1/2	1-15/16	0.700	2.400	2	0.700	2.312	3/4	2.245	0.503	9/16

15 Tolerances

Element	Direction	Tolerance
Diameter of Shank, A	minus	.0001 to .0005
Length of Shank, L	plus or minus	1/32
Dimension, B	plus or minus	1/64
Dimension, C	plus	.002
Dimension, D	minus	1/64
Dimension, E	plus or minus	1/64
Dimension, F	plus or minus	.005
Dimension, G	minus	1/64
Dimension, H	plus	1/64
Dimension, J	plus or minus	.002
Dimension, K	plus	.003

Extracted from Milling Cutters and End Mills. MCTI 1989.

16 Troubleshooting in Endmilling

Trouble	Occurrences of trouble	Countermeasures
Breaking of tool	<ul style="list-style-type: none"> At time of engaging with work material When ending cut 	<ol style="list-style-type: none"> Decrease feed rate. Decrease projection amount Shorten cutting edge length to required minimum limit
	<ul style="list-style-type: none"> During normal cutting 	<ol style="list-style-type: none"> Decrease feed rate Control wear → replace tool early Replace chuck or collet Decrease projection amount Carry out honing If 4 flute, reduce to 2 flute(clogging of chipping) If dry cutting change to wet cutting utilize cutting fluid. In case of wet cutting flow oil supplied from the front, change to from rear angle of side top. Use ample with rate.
	<ul style="list-style-type: none"> When changing direction of feed 	<ol style="list-style-type: none"> Utilize circular interpolation(in case of NC machine) or temporarily stop feed(Dowelling) Reduce feed rate before and after change of directions Replace chuck or collect
Fracture of cutting edge	<ul style="list-style-type: none"> Fracture of corners 	<ol style="list-style-type: none"> Carry out chamfering or nose with hand lapper. Down cut → Up cut
	<ul style="list-style-type: none"> Fracture at boundary of depth of cut 	<ol style="list-style-type: none"> Down cut → Up cut Reduce cutting speed
	<ul style="list-style-type: none"> Chipping at center part or overall 	<ol style="list-style-type: none"> Carry out honing. Or enlarge. Change number of rotation(in case machine vibrates) Increase cutting speed In ease of squeaking noise during cutting, increase feed. If dry cutting use cutting fluid or blow air. Replace chuck or collet Reduce cutting speed
Rapid tool wear	<ul style="list-style-type: none"> Large fracturing of cutting edge 	<ol style="list-style-type: none"> Decrease feed rate If 4 flute reduce to 2 flute Carry out honing. Or enlarge Replace chuck or collet Reduce cutting speed If dry cutting, change to wet cutting. In case oil supply in wet cutting is from the front, change to rear at an angle or from side top. Use ample supply.
		<ol style="list-style-type: none"> Reduce cutting speed Up cut → Down cut Increase feed Utilize wet cutting or air If reground tool, improve surface roughness of flank.



Trouble	Occurrences of trouble	Countermeasures
Inferior finished surface	• Surface is good but rough	1. Decrease feed 2. In case using 2 flute, increase to 4 flute
	• Small chip welding	1. Increase cutting speed 2. Utilize wet cutting air blow(ample supply) 3. Carry out fine honing 4. Up cut → Down cut 5. Increase feed or enlarge finish allowance
	• With transverse streaks	1. Carry out fine honing 2. Use water insoluble cutting fluid 3. Down cut → Up cut
	• Signs of excessive cutting	1. Reduce finishing depth of cut 2. Increase cutting speed 3. Reduce feed
Poor machining accuracy	• Finish dimensions are on minus side	1. Up cut → Down cut 2. Reduce finishing depth of cut 3. Replace chuck or collet 4. Reduce projection amount 5. Increase cutting speed
	• Poor perpendicularity	1. Reduce finishing depth of cut 2. Replace chuck or collet 3. Reduce projection amount 4. Increase cutting speed 5. 2Flute → 4 Flute 6. Reduce feed 7. Check wear rate → Replace tool
Chattering		1. Increase feed rate(in case over 0.05 mm/Zahn, try reducing) 2. Change cutting speed 3. Replace chuck or collet 4. Reduce projection amount 5. Use 2 flute cutter for rough cutting and 4 flute for finishing 6. Down cut → Up cut

ROTARY TOOL HOLDERS

HYDRAULIC CHUCK - CAT, BT

DUAL CONTACT HYDRAULIC CHUCK - CCT, CBT, HSK

HYDRAULIC CHUCK COLLET (REDUCTION SLEEVE)

SHRINK FIT HOLDER - CAT, BT

DUAL CONTACT SHRINK FIT HOLDER - CCT, CBT, HSK

SHRINK FIT EXTENSION - ST

END MILL HOLDER & SIDE LOCK ARBOR - CAT, BT

DUAL CONTACT SIDE LOCK ARBOR - CCT, CBT

DUAL CONTACT END MILL HOLDER - HSK

ER COLLET CHUCK - CAT, BT

DUAL CONTACT ER COLLET CHUCK - HSK

SHORT & TENSION ER COLLET CHUCK - SHORT, DUAL CONTACT NC DRILL CHUCK - HSK

TENSION (For TAPPING)

NC ER COLLET CHUCK - NC (For CNC LATHE)

ER COLLET

DUAL CONTACT SK SLIM CHUCK - CCT, CBT, HSK

STRAIGHT SK SLIM CHUCK - K

SK COLLET

TG COLLET CHUCK - CAT, BT

MILLING CHUCK - CAT, BT

DUAL CONTACT HIGH SPEED MILLING CHUCK - CCT, CBT, HSK

MILLING CHUCK COLLET

MORSE TAPER ADAPTER - CAT, BT

TAPPING CHUCK - CAT, BT

SYNCHRO TAPPING ER CHUCK - CAT

QUICK CHANGE TAP ADAPTER

SHELL MILL ARBOR - CAT, BT

DUAL CONTACT SHELL MILL ARBOR - CCT, CBT

NC DRILL CHUCK - CAT, BT

DUAL CONTACT NC DRILL CHUCK - HSK

STRAIGHT NC DRILL CHUCK - K

JACOBS TAPER ARBOR - CAT, BT

STUB ARBOR - CAT, BT

SLITTING SAW ARBOR - CAT, BT

PULL STUD

TOOL CLAMP

COOLANT TUBE

SELECTION GUIDE


MODEL	DESCRIPTION	PAGE
	HYDRAULIC CHUCK	
	• CAT	1308
	• BT	1314
	DUAL CONTACT HYDRAULIC CHUCK	
	• CCT	1320
	• CBT	1323
	• HSK	1326
	HYDRAULIC CHUCK COLLET (REDUCTION SLEEVE)	1331
	SHRINK FIT HOLDER	
	• CAT	1339
	• BT	1341
	DUAL CONTACT SHRINK FIT HOLDER	
	• CCT	1343
	• CBT	1345
	• HSK	1347
	SHRINK FIT EXTENSION	
	• ST	1349
	END MILL HOLDER	
	• CAT	1352
	• BT	1358
	DUAL CONTACT SIDE LOCK ARBOR	
	• CCT	1363
	• CBT	1364
	DUAL CONTACT END MILL HOLDER	
	• HSK (COOLANT CHANNEL TYPE)	1365
	ER COLLET CHUCK	
	• CAT	1366
	• BT	1368
	DUAL CONTACT ER COLLET CHUCK	
	• HSK	1371
	ER COLLET CHUCK	
• SHORT	1372	
	• TENSION (For TAPPING)	1372
	NC ER COLLET CHUCK	
	• NC (For CNC LATHE)	1373
	ACCESSORY & PART	1374
	DUAL CONTACT SK SLIM CHUCK	
	• CAT	1384
	• CCT	1385
	• CBT	1386
	• HSK	1387
	STRAIGHT SK SLIM CHUCK	
• STRAIGHT-K	1388	
	ACCESSORY & PART	1389
	TG COLLET CHUCK	
	• CAT	1393
	• BT	1394
	ACCESSORY & PART	1395

TG COLLET CHUCK

MODEL	DESCRIPTION	PAGE
	POWER MILLING CHUCK	
	• CAT	1396
	• BT	1396
	DUAL CONTACT HIGH SPEED POWER MILLING CHUCK	
	• CCT	1397
	• CBT	1398
	• HSK	1399
	ACCESSORY & PART	1400
MORSE TAPER ADAPTER	MORSE TAPER ADAPTER	
	• CAT	1401
	• BT	1401
	TAPPING CHUCK	
	• CAT	1402
	• BT	1403
	SYNCHRO TAPPING ER CHUCK	
	• CAT	1404
	ACCESSORY & PART	1405
	SHELL MILL ARBOR	
	• CAT	1406
	• BT	1407
	DUAL CONTACT SHELL MILL ARBOR	
	• CCT	1408
	• CBT	1409
	ACCESSORY & PART	1410
	NC DRILL CHUCK	
	• CAT	1411
	• BT	1412
	DUAL CONTACT NC DRILL CHUCK	
	• HSK	1413
	STRAIGHT NC DRILL CHUCK	
• STRAIGHT-K	1413	
JACOBS TAPER ARBOR	JACOBS TAPER ARBOR	
	• CAT	1414
	• BT	1414
STUB ARBOR	STUB ARBOR	
	• CAT	1415
	• BT	1415
SLITTING SAW ARBOR	SLITTING SAW ARBOR	
	• CAT	1417
	• BT	1417
PULL STUD & TOOL CLAMP	PULL STUD	1418
	TOOL CLAMP	1419
	COOLANT TUBE	1419
TECHNICAL INFORMATION		1420

HYDRAULIC CHUCK (SLIM)

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD/B
------------------	--------------------	-------------	------------	---------------------------	---------------------

ASME B5.50-2009-CAT


Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	D3	L	L1	L2	G	Remarks
WK020	40	CAT40 AD/B - HC 1/4 - 4.00	0.250	1.024	1.750	-	4.000	1.280	1.063	M5x0.8mm	FIG.1
WK022		CAT40 AD/B - HC 3/8 - 4.00	0.375	1.181	1.750	-	4.000	1.634	1.260	M6x1.0mm	
WK024		CAT40 AD/B - HC 1/2 - 4.00	0.500	1.260	1.750	-	4.000	1.634	1.457	M10x1.0mm	
WK026		CAT40 AD/B - HC 5/8 - 4.00	0.625	1.496	1.750	-	4.000	1.949	1.654	M10x1.0mm	
WK028		CAT40 AD/B - HC 3/4 - 4.00	0.750	1.654	1.750	-	4.000	1.949	1.654	M10x1.0mm	
WK030		CAT40 AD/B - HC 1 - 4.00	1.000	2.165	2.480	-	4.000	2.618	1.890	M16x1.0mm	
WK032		CAT40 AD/B - HC 1 1/4 - 4.00	1.250	2.480	3.150	-	4.000	1.378	2.165	M16x1.0mm	
WL020		50	CAT50 AD/B - HC 1/4 - 4.00	0.250	1.024	1.978	2.752	4.000	1.280	1.063	
WL022	CAT50 AD/B - HC 3/8 - 4.00		0.375	1.181	1.978	2.752	4.000	1.417	1.260	M6x1.0mm	
WL024	CAT50 AD/B - HC 1/2 - 4.00		0.500	1.260	1.978	2.752	4.000	1.634	1.457	M10x1.0mm	
WL026	CAT50 AD/B - HC 5/8 - 4.00		0.625	1.496	1.978	2.752	4.000	1.870	1.654	M10x1.0mm	
WL028	CAT50 AD/B - HC 3/4 - 4.00		0.750	1.654	1.978	2.752	4.000	1.949	1.654	M10x1.0mm	
WL030	CAT50 AD/B - HC 1 - 4.00		1.000	2.244	2.480	2.752	4.000	1.949	1.890	M16x1.0mm	
WL032	CAT50 AD/B - HC 1 1/4 - 4.00		1.250	2.520	-	2.752	4.000	2.559	2.165	M16x1.0mm	

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

HYDRAULIC CHUCK (SLIM)

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD/B
------------------	--------------------	-------------	------------	---------------------------	---------------------

ASME B5.50-2009-CAT


Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	G	
WK060	40	CAT40 AD/B - HC 6 - 80.5	6	26	49.5	80.5	29.5	27	M5x0.8	
WK062		CAT40 AD/B - HC 6 - 110	6	26	49.5	110	29.5	27	M5x0.8	
WK064		CAT40 AD/B - HC 8 - 80.5	8	28	49.5	80.5	30	27	M6x1.0	
WK066		CAT40 AD/B - HC 8 - 110	8	28	49.5	110	30	27	M6x1.0	
WK068		CAT40 AD/B - HC 10 - 80.5	10	30	49.5	80.5	31	32	M8x1.0	
WK070		CAT40 AD/B - HC 10 - 110	10	30	49.5	110	31	32	M8x1.0	
WK072		CAT40 AD/B - HC 12 - 80.5	12	32	49.5	80.5	31.5	37	M10x1.0	
WK074		CAT40 AD/B - HC 12 - 110	12	32	49.5	110	31.5	37	M10x1.0	
WK076		CAT40 AD/B - HC 16 - 80.5	16	38	49.5	80.5	33	42	M12x1.0	
WK078		CAT40 AD/B - HC 16 - 110	16	38	49.5	110	33	42	M12x1.0	
WK080		CAT40 AD/B - HC 20 - 80.5	20	42	49.5	80.5	34	42	M16x1.0	
WK082		CAT40 AD/B - HC 20 - 110	20	42	49.5	110	34	42	M16x1.0	
WK084		CAT40 AD/B - HC 25 - 80.5	25	55	66	80.5	22	48	M16x1.	
WK086		CAT40 AD/B - HC 32 - 80.5	32	63	80	80.5	25.5	55	M16x1.0	
WL060		50	CAT50 AD/B - HC 6 - 80.5	6	26	49.5	80.5	30	27	M5x0.8
WL062			CAT50 AD/B - HC 8 - 80.5	8	28	49.5	80.5	30	27	M6x1.0
WL064	CAT50 AD/B - HC 10 - 80.5		10	30	49.5	80.5	32	32	M8x1.0	
WL066	CAT50 AD/B - HC 12 - 80.5		12	32	49.5	80.5	35	37	M10x1.0	
WL068	CAT50 AD/B - HC 16 - 80.5		16	38	49.5	80.5	40	42	M12x1.0	
WL070	CAT50 AD/B - HC 20 - 80.5		20	42	49.5	80.5	40	42	M16x1.0	

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

HYDRAULIC CHUCK (Power E Hydro)

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD/B
------------------	------------------------------	-----------------------	----------------------	-------------------------------------	-------------------------------

ASME B5.50-2009-CAT

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G
WK022PE	40	CAT40 AD/B - HC 3/4P - 2.539	0.75	1.496	1.938	2.539	1.889	M8x1.0mm
WK023PE		CAT40 AD/B - HC 3/4P - 4.000	0.75	1.496	1.938	4.000	1.889	M8x1.0mm
WLO28PE	50	CAT50 AD/B - HC 1 1/4P - 3.188	1.25	2.303	2.834	3.188	2.244	M8x1.0mm
WLO30PE		CAT50 AD/B - HC 1 1/4P - 6.000	1.25	2.303	2.834	6.000	2.244	M8x1.0mm


Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G
WK102PE	40	CAT40 AD/B - HC 20P - 64.5	20	38	49.25	64.5	48	M8x1.0
WK103PE		CAT40 AD/B - HC 20P - 101.6	20	38	49.25	101.6	48	M8x1.0
WL104PE	50	CAT50 AD/B - HC 32P - 81	32	58.5	72	81	57	M8x1.0
WL106PE		CAT50 AD/B - HC 32P - 152.4	32	58.5	72	152.4	57	M8x1.0

- * High Clamping Torque Power version (Please refer to page 1420, Technical Information)
- * Applicable for milling(roughing and finishing)
- * Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

HYDRAULIC CHUCK (Short & Rigid)

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD/B
------------------	------------------------------	-----------------------	----------------------	-------------------------------------	-------------------------------

ASME B5.50-2009-CAT

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G
WK020SNR	40	CAT40 AD/B - HC 1/2S - 2.52	0.500	1.260	1.654	2.520	1.457	M8x1.0mm
WK021SNR		CAT40 AD/B - HC 5/8S - 2.52	0.625	1.362	1.752	2.520	1.654	M10x1.0mm
WK022SNR		CAT40 AD/B - HC 3/4S - 2.52	0.750	1.469	1.949	2.520	1.654	M10x1.0mm
WK024SNR		CAT40 AD/B - HC 1S - 3.50	1.000	2.244	2.598	3.500	1.890	M16x1.0mm
WLO20SNR	50	CAT50 AD/B - HC 1/2S - 3.19	0.500	1.879	2.752	3.189	1.457	M8x1.0mm
WLO22SNR		CAT50 AD/B - HC 5/8S - 3.19	0.625	1.819	2.752	3.189	1.654	M8x1.0mm
WLO24SNR		CAT50 AD/B - HC 3/4S - 3.19	0.75	2.185	2.752	3.189	1.654	M10x1.0mm
WLO26SNR		CAT50 AD/B - HC 1.00S - 3.19	1.000	2.185	2.752	3.189	1.890	M16x1.0mm
WLO28SNR		CAT50 AD/B - HC 1.25S - 3.19	1.250	2.185	2.752	3.189	2.165	M16x1.0mm


Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G
WK100SNR	40	CAT40 AD/B - HC 12S - 50	12	32	42	50	37	M8x1.0
WK102SNR		CAT40 AD/B - HC 20S - 64.5	20	37	49.5	64.5	42	M16x1.0
WL100SNR	50	CAT50 AD/B - HC 12S - 50	12	32	42	50	37	M8x1.0
WL102SNR		CAT50 AD/B - HC 20S - 64.5	20	37	49.5	64.5	42	M16x1.0
WL104SNR		CAT50 AD/B - HC 32S - 81	32	55	72	81	55	M16x1.0

- * Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

HYDRAULIC CHUCK (RADIAL TOOL LENGTH PRE-SETTING TYPE)

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD/B
------------------	--------------------	-------------	------------	---------------------------	---------------------

ASME B5.50-2009-CAT


Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2
WK100HCR	40	CAT40 AD/B - HCR 12 - 80.5	12	32	49.5	80.5	31.5	37
WK102HCR		CAT40 AD/B - HCR 20 - 80.5	20	42	49.5	80.5	34	42
WK104HCR		CAT40 AD/B - HCR 32 - 110	32	64	80	110	50	55
WL100HCR	50	CAT50 AD/B - HCR 12 - 80.5	12	32	49.5	80.5	31.5	37
WL102HCR		CAT50 AD/B - HCR 20 - 80.5	20	42	49.5	80.5	34	42
WL104HCR		CAT50 AD/B - HCR 32 - 100	32	60	60	100	-	55

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

HYDRAULIC CHUCK (For MOULD)

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD/B
------------------	--------------------	-------------	------------	---------------------------	---------------------

ASME B5.50-2009-CAT

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	G	
WK020HMC	40	CAT40 AD/B - HMC 1/4 - 4.72	0.250	0.787	1.949	4.724	2.756	1.063	M5x0.8mm	
WK022HMC		CAT40 AD/B - HMC 1/4 - 5.91	0.250	0.787	1.949	5.906	3.937	1.063	M5x0.8mm	
WK024HMC		CAT40 AD/B - HMC 5/16 - 4.72	0.313	0.866	1.949	4.724	2.756	1.063	M6x1.0mm	
WK026HMC		CAT40 AD/B - HMC 5/16 - 5.91	0.313	0.866	1.949	5.906	3.937	1.063	M6x1.0mm	
WK028HMC		CAT40 AD/B - HMC 3/8 - 4.72	0.375	0.945	1.949	4.724	2.756	1.260	M8x1.0mm	
WK030HMC		CAT40 AD/B - HMC 3/8 - 5.91	0.375	0.945	1.949	5.906	3.937	1.260	M8x1.0mm	
WK032HMC		CAT40 AD/B - HMC 1/2 - 4.72	0.500	1.024	1.949	4.724	2.756	1.457	M10x1.0mm	
WK034HMC		CAT40 AD/B - HMC 1/2 - 5.91	0.500	1.024	1.949	5.906	3.937	1.457	M10x1.0mm	
WK036HMC		CAT40 AD/B - HMC 5/8 - 4.72	0.625	1.260	1.949	4.724	2.756	1.654	M12x1.0mm	
WK038HMC		CAT40 AD/B - HMC 5/8 - 5.91	0.625	1.260	1.949	5.906	3.937	1.654	M12x1.0mm	
WK040HMC		CAT40 AD/B - HMC 3/4 - 4.72	0.750	1.339	1.949	4.724	2.756	1.654	M16x1.0mm	
WK042HMC		CAT40 AD/B - HMC 3/4 - 5.91	0.750	1.339	1.949	5.906	3.937	1.654	M16x1.0mm	
WLO20HMC		50	CAT50 AD/B - HMC 1/4 - 5.91	0.250	0.787	1.752	5.906	3.937	1.063	M5x0.8mm
WLO22HMC			CAT50 AD/B - HMC 5/16 - 5.91	0.313	0.866	1.752	5.906	3.937	1.063	M6x1.0mm
WLO24HMC	CAT50 AD/B - HMC 3/8 - 5.91		0.375	0.945	1.752	5.906	3.937	1.260	M8x1.0mm	
WLO26HMC	CAT50 AD/B - HMC 1/2 - 5.91		0.500	1.024	1.752	5.906	3.937	1.457	M10x1.0mm	
WLO28HMC	CAT50 AD/B - HMC 5/8 - 5.91		0.625	1.260	1.752	5.906	3.937	1.654	M12x1.0mm	
WLO30HMC	CAT50 AD/B - HMC 3/4 - 5.91		0.750	1.339	1.752	5.906	3.937	1.654	M16x1.0mm	


Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	G	
WK100HMC	40	CAT40 AD/B - HMC 6 - 120	6	20	49.5	120	70	27	M5X0.8	
WK102HMC		CAT40 AD/B - HMC 6 - 150	6	20	49.5	150	100	27	M5X0.8	
WK104HMC		CAT40 AD/B - HMC 8 - 120	8	22	49.5	120	70	27	M6X1.0	
WK106HMC		CAT40 AD/B - HMC 8 - 150	8	22	49.5	150	100	27	M6X1.0	
WK108HMC		CAT40 AD/B - HMC 10 - 120	10	24	49.5	120	70	32	M8X1.0	
WK110HMC		CAT40 AD/B - HMC 10 - 150	10	24	49.5	150	100	32	M8X1.0	
WK112HMC		CAT40 AD/B - HMC 12 - 120	12	25	49.5	120	70	37	M10X1.0	
WK114HMC		CAT40 AD/B - HMC 12 - 150	12	25	49.5	150	100	37	M10X1.0	
WK116HMC		CAT40 AD/B - HMC 16 - 120	16	32	49.5	120	70	42	M12X1.0	
WK118HMC		CAT40 AD/B - HMC 16 - 150	16	32	49.5	150	100	42	M12X1.0	
WK120HMC		CAT40 AD/B - HMC 20 - 120	20	34	49.5	120	70	42	M16X1.0	
WK122HMC		CAT40 AD/B - HMC 20 - 150	20	34	49.5	150	100	42	M16X1.0	
WL100HMC		50	CAT50 AD/B - HMC 6 - 150	6	20	44.5	150	100	27	M5X0.8
WL102HMC			CAT50 AD/B - HMC 8 - 150	8	22	44.5	150	100	27	M6X1.0
WL104HMC	CAT50 AD/B - HMC 10 - 150		10	24	44.5	150	100	32	M8X1.0	
WL106HMC	CAT50 AD/B - HMC 12 - 150		12	25	44.5	150	100	37	M10X1.0	
WL108HMC	CAT50 AD/B - HMC 16 - 150		16	32	44.5	150	100	42	M12X1.0	
WL110HMC	CAT50 AD/B - HMC 20 - 150		20	34	44.5	150	100	42	M16X1.0	

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

HYDRAULIC CHUCK (SLIM)

BT



JIS B6339 - BT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD or AD/B
----------------	------------------------------	-----------------------	----------------------	------------------------------	-------------------------------------

JIS B6339/MAS 403-BT


Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	G
WG020	30	BT30 - HC 1/4 - 2.75	0.250	1.024	1.752	2.750	1.161	1.063	M5x0.8mm
WG022		BT30 - HC 5/16 - 2.75	0.313	1.102	1.752	2.750	1.181	1.063	M6x1.0mm
WG024		BT30 - HC 3/8 - 2.95	0.375	1.181	1.752	2.953	1.220	1.260	M8x1.0mm
WG026		BT30 - HC 1/2 - 3.35	0.500	1.260	1.772	3.346	1.575	1.457	M10x1.0mm
WG028		BT30 - HC 5/8 - 3.54	0.625	1.496	1.772	3.543	1.811	1.654	M10x1.0mm
WG030		BT30 - HC 3/4 - 3.54	0.750	1.654	1.772	3.543	1.890	1.654	M6x1.0mm
WH020		40	BT40 AD/B - HC 1/4 - 3.54	0.250	1.024	1.752	3.543	1.181	1.063
WH022	BT40 AD/B - HC 5/16 - 3.54		0.313	1.102	1.752	3.543	1.280	1.063	M6x1.0mm
WH024	BT40 AD/B - HC 3/8 - 3.54		0.375	1.181	1.752	3.543	1.260	1.260	M8x1.0mm
WH026	BT40 AD/B - HC 1/2 - 3.54		0.500	1.260	1.752	3.543	1.378	1.457	M10x1.0mm
WH028	BT40 AD/B - HC 5/8 - 3.54		0.625	1.496	1.870	3.543	1.575	1.654	M12x1.0mm
WH030	BT40 AD/B - HC 3/4 - 3.54		0.750	1.654	1.870	3.543	1.575	1.654	M16x1.0mm
WH032	BT40 AD/B - HC 1" - 3.94		1.000	1.969	2.362	3.937	1.772	1.890	M16x1.0mm
WH034	BT40 AD/B - HC 1 1/4 - 4.13		1.250	2.362	-	4.134	-	2.165	M16x1.0mm

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

HYDRAULIC CHUCK (SLIM)

BT



JIS B6339 - BT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD or AD/B
----------------	------------------------------	-----------------------	----------------------	------------------------------	-------------------------------------

JIS B6339/MAS 403-BT


Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	G
WG100	30	BT30 - HC 6 - 70	6	26	44.5	70	29.5	27	M5x0.8
WG102		BT30 - HC 8 - 70	8	28	44.5	70	30	27	M6x1.0
WG104		BT30 - HC 10 - 75	10	30	44.5	75	31	32	M8x1.0
WG106		BT30 - HC 12 - 85	12	32	45	85	45	37	M10x1.0
WG108		BT30 - HC 14 - 85	14	34	45	85	45	37	M10x1.0
WG110		BT30 - HC 16 - 90	16	38	45	90	50	42	M10x1.0
WG112		BT30 - HC 18 - 90	18	40	45	90	50	42	M10x1.0
WG114	BT30 - HC 20 - 90	20	42	45	90	50	42	M6x1.0	
WH100	40	BT40 AD/B - HC 6 - 90	6	26	44.5	90	43	27	M5x0.8
WH102		BT40 AD/B - HC 8 - 90	8	28	44.5	90	44.5	27	M6x1.0
WH104		BT40 AD/B - HC 10 - 90	10	30	44.5	90	44.5	32	M8x1.0
WH106		BT40 AD/B - HC 12 - 90	12	32	44.5	90	44.5	37	M10x1.0
WH108		BT40 AD/B - HC 14 - 90	14	34	44.5	90	44.5	37	M10x1.0
WH110		BT40 AD/B - HC 16 - 90	16	38	44.5	90	47.5	42	M12x1.0
WH112		BT40 AD/B - HC 18 - 90	18	40	44.5	90	47.5	42	M12x1.0
WH114		BT40 AD/B - HC 20 - 90	20	42	44.5	90	47.5	42	M16x1.0
WH116	BT40 AD/B - HC 25 - 100	25	50	60	100	47.5	48	M16x1.0	
WH118	BT40 AD/B - HC 32 - 105	32	60	-	105	-	55	M16x1.0	

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

HYDRAULIC CHUCK (Power E Hydro)

BT



JIS B6339 - BT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD or AD/B
----------------	------------------------------	-----------------------	----------------------	-------------------------------------	-------------------------------------

JIS B6339/MAS 403-BT

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	D3	L	L2	G	FIG.
WG002PE	30	BT30 - HC 3/4P - 3.543	0.75	1.496	1.653	1.751	3.543	1.889	M8x1.0mm	1
WH002PE	40	BT40 AD/B - HC 3/4P - 2.854	0.75	1.496	1.938	-	2.854	1.889	M8x1.0mm	2
WI003PE	50	BT50 AD/B - HC 1 1/4P - 3.543	1.25	2.303	2.834	-	3.543	2.244	M8x1.0mm	2


Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	D3	L	L2	G	FIG.
WG100PE	30	BT30 - HC 12P - 69	12	32	42	44.5	69	41	M8x1.0	1
WG102PE		BT30 - HC 20P - 90	20	38	42	44.5	90	48	M8x1.0	1
WH100PE	40	BT40 AD/B - HC 12P - 58	12	32	42	-	58	41	M8x1.0	2
WH102PE		BT40 AD/B - HC 20P - 72.5	20	38	49.25	-	72.5	48	M8x1.0	2
WI100PE	50	BT50 AD/B - HC 20P - 83.5	20	38	49.25	-	83.5	48	M8x1.0	2
WI102PE		BT50 AD/B - HC 32P - 90	32	58.5	72	-	90	57	M8x1.0	2

- * High Clamping Torque Power version (Please refer to page 1420, Technical Information)
- * Applicable for milling(roughing and finishing)
- * Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

HYDRAULIC CHUCK (Short & Rigid)

BT



JIS B6339 - BT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD or AD/B
----------------	------------------------------	-----------------------	----------------------	-------------------------------------	-------------------------------------

JIS B6339/MAS 403-BT


Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G
WG100SNR	30	BT30 - HC 20S - 85	20	41	44	85	42	M6x1.0
WH100SNR	40	BT40 AD/B - HC 12S - 58	12	32	42	58	37	M8x1.0
WH102SNR		BT40 AD/B - HC 20S - 72.5	20	38	49.25	72.5	42	M8x1.0

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

HYDRAULIC CHUCK (RADIAL TOOL LENGTH PRE-SETTING TYPE)

BT



JIS B6339 - BT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD or AD/B
----------------	------------------------------	-----------------------	----------------------	-------------------------------------	-------------------------------------

JIS B6339/MAS 403-BT


Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2
WG100HCR	30	BT30 - HCR 12 - 85	12	32	44.5	85	40	37
WG102HCR		BT30 - HCR 20 - 85	20	44	-	85	-	42
WH100HCR	40	BT40 AD/B - HCR 12 - 90	12	32	44.5	90	42.5	37
WH102HCR		BT40 AD/B - HCR 20 - 90	20	42	44.5	90	47.5	42
WH104HCR		BT40 AD/B - HCR 32 - 105	32	60	-	105	-	55

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

HYDRAULIC CHUCK (For MOULD)

BT



JIS B6339 - BT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD/B
----------------	------------------------------	-----------------------	----------------------	-------------------------------------	-------------------------------


JIS B6339/MAS 403-BT

Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	G
WH100HMC	40	BT40 AD/B - HMC 6 - 120	6	20	44.5	120	70	27	M5x0.8
WH102HMC		BT40 AD/B - HMC 6 - 150	6	20	44.5	150	100	27	M5x0.8
WH104HMC		BT40 AD/B - HMC 8 - 120	8	22	44.5	120	70	27	M6x1.0
WH106HMC		BT40 AD/B - HMC 8 - 150	8	22	44.5	150	100	27	M6x1.0
WH108HMC		BT40 AD/B - HMC 10 - 120	10	24	44.5	120	70	32	M8x1.0
WH110HMC		BT40 AD/B - HMC 10 - 150	10	24	44.5	150	100	32	M8x1.0
WH112HMC		BT40 AD/B - HMC 12 - 120	12	25	44.5	120	70	37	M10x1.0
WH114HMC		BT40 AD/B - HMC 12 - 150	12	25	44.5	150	100	37	M10x1.0
WH116HMC		BT40 AD/B - HMC 16 - 120	16	32	44.5	120	70	42	M12x1.0
WH118HMC		BT40 AD/B - HMC 16 - 150	16	32	44.5	150	100	42	M12x1.0
WH120HMC		BT40 AD/B - HMC 20 - 120	20	36	43.75	120	-	42	M16x1.0
WH122HMC		BT40 AD/B - HMC 20 - 150	20	36	46.9	150	-	42	M16x1.0

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

DUAL CONTACT HYDRAULIC CHUCK (SLIM) CCT



CCT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD/B
-----	------------------------------	-----------------------	----------------------	-------------------------------------	-------------------------------


CCT (CAT DUAL CONTACT)

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	G	
WB020	40	CCT40 AD/B - HC 1/4 - 3.54	0.250	1.024	1.752	3.543	1.280	1.063	M5x0.8mm	
WB022		CCT40 AD/B - HC 5/16 - 3.54	0.313	1.102	1.752	3.543	1.280	1.063	M6x1.0mm	
WB024		CCT40 AD/B - HC 3/8 - 3.54	0.375	1.181	1.752	3.543	1.634	1.260	M8x1.0mm	
WB026		CCT40 AD/B - HC 1/2 - 3.54	0.500	1.260	1.752	3.543	1.634	1.457	M10x1.0mm	
WB028		CCT40 AD/B - HC 5/8 - 3.54	0.625	1.496	1.752	3.543	1.949	1.654	M10x1.0mm	
WB030		CCT40 AD/B - HC 3/4 - 3.54	0.750	1.654	1.752	3.543	1.949	1.654	M10x1.0mm	
WB032		CCT40 AD/B - HC 1" - 3.94	1.000	2.165	2.480	3.937	2.559	1.890	M16x1.0mm	
WB034		CCT40 AD/B - HC 1 1/4 - 4.13	1.250	2.480	3.150	4.134	1.378	2.165	M16x1.0mm	
WC020		50	CCT50 AD/B - HC 1/4 - 3.54	0.250	1.024	1.969	3.543	1.181	1.063	M5x0.8mm
WC022			CCT50 AD/B - HC 5/16 - 3.54	0.313	1.102	1.969	3.543	1.181	1.063	M6x1.0mm
WC024	CCT50 AD/B - HC 3/8 - 3.54		0.375	1.181	1.969	3.543	1.260	1.260	M8x1.0mm	
WC026	CCT50 AD/B - HC 1/2 - 3.54		0.500	1.260	1.969	3.543	1.378	1.457	M10x1.0mm	
WC028	CCT50 AD/B - HC 5/8 - 3.54		0.625	1.496	1.969	3.543	1.575	1.654	M10x1.0mm	
WC030	CCT50 AD/B - HC 3/4 - 3.54		0.750	1.654	1.969	3.543	1.575	1.654	M10x1.0mm	
WC032	CCT50 AD/B - HC 1" - 4.13		1.000	2.244	2.480	4.134	2.047	1.890	M16x1.0mm	
WC034	CCT50 AD/B - HC 1 1/4 - 4.53		1.250	2.480	2.953	4.528	2.441	2.165	M16x1.0mm	

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

HYDRAULIC CHUCK (Power E Hydro) CCT



CCT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD/B
-----	------------------------------	-----------------------	----------------------	-------------------------------------	-------------------------------

CCT (CAT DUAL CONTACT)

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G
WB030PE	40	CCT40 AD/B - HC 3/4P - 2.539	0.75	1.496	49.25	2.539	1.889	M8x1.0mm
WB031PE		CCT40 AD/B - HC 3/4P - 4.000	0.75	1.496	49.25	4.000	1.889	M8x1.0mm


Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G
WB130PE	40	CCT40 AD/B - HC 20P - 64.5	20	38	49.25	64.5	48	M8x1.0
WB131PE		CCT40 AD/B - HC 20P - 101.6	20	38	49.25	101.6	48	M8x1.0

* High Clamping Torque Power version
 (Please refer to page 1420, Technical Information)
 * Applicable for milling(roughing and finishing)
 * Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

DUAL CONTACT HYDRAULIC CHUCK (For MOULD)

CCT



CCT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD/B
-----	------------------------------	-----------------------	----------------------	-------------------------------------	-------------------------------

CCT (CAT DUAL CONTACT)

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	G
WB020HMC	40	CCT40 AD/B - HMC 1/4 - 4.72	0.250	0.787	1.949	4.724	2.756	1.063	M5x0.8mm
WB022HMC		CCT40 AD/B - HMC 1/4 - 5.91	0.250	0.787	1.949	5.906	3.937	1.063	M5x0.8mm
WB024HMC		CCT40 AD/B - HMC 5/16 - 4.72	0.313	0.866	1.949	4.724	2.756	1.063	M6x1.0mm
WB026HMC		CCT40 AD/B - HMC 5/16 - 5.91	0.313	0.866	1.949	5.906	3.937	1.063	M6x1.0mm
WB028HMC		CCT40 AD/B - HMC 3/8 - 4.72	0.375	0.945	1.949	4.724	2.756	1.260	M8x1.0mm
WB030HMC		CCT40 AD/B - HMC 3/8 - 5.91	0.375	0.945	1.949	5.906	3.937	1.260	M8x1.0mm
WB032HMC		CCT40 AD/B - HMC 1/2 - 4.72	0.500	1.024	1.949	4.724	2.756	1.457	M10x1.0mm
WB034HMC		CCT40 AD/B - HMC 1/2 - 5.91	0.500	1.024	1.949	5.906	3.937	1.457	M10x1.0mm
WB036HMC		CCT40 AD/B - HMC 5/8 - 4.72	0.625	1.260	1.949	4.724	2.756	1.654	M12x1.0mm
WB038HMC		CCT40 AD/B - HMC 5/8 - 5.91	0.625	1.260	1.949	5.906	3.937	1.654	M12x1.0mm
WB040HMC		CCT40 AD/B - HMC 3/4 - 4.72	0.750	1.339	1.949	4.724	2.756	1.654	M16x1.0mm
WB042HMC		CCT40 AD/B - HMC 3/4 - 5.91	0.750	1.339	1.949	5.906	3.937	1.654	M16x1.0mm
WC020HMC	50	CCT50 AD/B - HMC 1/4 - 5.91	0.250	0.787	1.752	5.906	3.937	1.063	M5x0.8mm
WC022HMC		CCT50 AD/B - HMC 5/16 - 5.91	0.313	0.866	1.752	5.906	3.937	1.063	M6x1.0mm
WC024HMC		CCT50 AD/B - HMC 3/8 - 5.91	0.375	0.945	1.752	5.906	3.937	1.260	M8x1.0mm
WC026HMC		CCT50 AD/B - HMC 1/2 - 5.91	0.500	1.024	1.752	5.906	3.937	1.457	M10x1.0mm
WC028HMC		CCT50 AD/B - HMC 5/8 - 5.91	0.625	1.260	1.752	5.906	3.937	1.654	M12x1.0mm
WC030HMC		CCT50 AD/B - HMC 3/4 - 5.91	0.750	1.339	1.752	5.906	3.937	1.654	M16x1.0mm


Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	G
WB100HMC	40	CCT40 AD/B - HMC 6 - 120	6	20	49.5	120	70	27	M5X0.8
WB102HMC		CCT40 AD/B - HMC 6 - 150	6	20	49.5	150	100	27	M5X0.8
WB104HMC		CCT40 AD/B - HMC 8 - 120	8	22	49.5	120	70	27	M6X1.0
WB106HMC		CCT40 AD/B - HMC 8 - 150	8	22	49.5	150	100	27	M6X1.0
WB108HMC		CCT40 AD/B - HMC 10 - 120	10	24	49.5	120	70	32	M8X1.0
WB110HMC		CCT40 AD/B - HMC 10 - 150	10	24	49.5	150	100	32	M8X1.0
WB112HMC		CCT40 AD/B - HMC 12 - 120	12	25	49.5	120	70	37	M10X1.0
WB114HMC		CCT40 AD/B - HMC 12 - 150	12	25	49.5	150	100	37	M10X1.0
WB116HMC		CCT40 AD/B - HMC 16 - 120	16	32	49.5	120	70	42	M12X1.0
WB118HMC		CCT40 AD/B - HMC 16 - 150	16	32	49.5	150	100	42	M12X1.0
WB120HMC		CCT40 AD/B - HMC 20 - 120	20	34	49.5	120	70	42	M16X1.0
WB122HMC		CCT40 AD/B - HMC 20 - 150	20	34	49.5	150	100	42	M16X1.0
WC100HMC	50	CCT50 AD/B - HMC 6 - 150	6	20	44.5	150	100	27	M5X0.8
WC102HMC		CCT50 AD/B - HMC 8 - 150	8	22	44.5	150	100	27	M6X1.0
WC104HMC		CCT50 AD/B - HMC 10 - 150	10	24	44.5	150	100	32	M8X1.0
WC106HMC		CCT50 AD/B - HMC 12 - 150	12	25	44.5	150	100	37	M10X1.0
WC108HMC		CCT50 AD/B - HMC 16 - 150	16	32	44.5	150	100	42	M12X1.0
WC110HMC		CCT50 AD/B - HMC 20 - 150	20	34	44.5	150	100	42	M16X1.0

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

DUAL CONTACT HYDRAULIC CHUCK (SLIM)

CBT



CBT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD
-----	------------------------------	-----------------------	----------------------	-------------------------------------	-----------------------------

CBT (BT DUAL CONTACT)

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	G
WD020	30	CBT 30 - HC 1/4 - 2.76	0.250	1.024	1.752	2.756	1.161	1.063	M5x0.8mm
WD022		CBT 30 - HC 5/16 - 2.76	0.313	1.102	1.752	2.756	1.181	1.063	M6x1.0mm
WD024		CBT 30 - HC 3/8 - 2.95	0.375	1.181	1.752	2.953	1.220	1.260	M8x1.0mm
WD026		CBT 30 - HC 1/2 - 3.35	0.500	1.260	1.772	3.346	1.575	1.457	M10x1.0mm
WD028		CBT 30 - HC 5/8 - 3.54	0.625	1.496	1.772	3.543	1.811	1.654	M10x1.0mm
WD030		CBT 30 - HC 3/4 - 3.54	0.750	1.654	1.772	3.543	1.890	1.654	M16x1.0mm
WE020	40	CBT 40 - HC 1/4 - 3.54	0.250	1.024	1.752	3.543	1.181	1.063	M5x0.8mm
WE022		CBT 40 - HC 5/16 - 3.54	0.313	1.102	1.752	3.543	1.280	1.063	M6x1.0mm
WE024		CBT 40 - HC 3/8 - 3.54	0.375	1.181	1.752	3.543	1.260	1.260	M8x1.0mm
WE026		CBT 40 - HC 1/2 - 3.54	0.500	1.260	1.752	3.543	1.378	1.457	M10x1.0mm
WE028		CBT 40 - HC 5/8 - 3.54	0.625	1.496	1.870	3.543	1.575	1.654	M12x1.0mm
WE030		CBT 40 - HC 3/4 - 3.54	0.750	1.654	1.870	3.543	1.575	1.654	M16x1.0mm
WE032		CBT 40 - HC 1 - 3.94	1.000	1.969	2.362	3.937	1.772	1.890	M16x1.0mm
WE034		CBT 40 - HC 1 1/4 - 4.13	1.250	2.362	-	4.134	-	2.165	M16x1.0mm


Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	G
WD100	30	CBT 30 - HC 6 - 70	6	26	44.5	70	29.5	27	M5x0.8
WD102		CBT 30 - HC 8 - 70	8	28	44.5	70	30	27	M6x1.0
WD104		CBT 30 - HC 10 - 75	10	30	44.5	75	31	32	M8x1.0
WD106		CBT 30 - HC 12 - 85	12	32	45	85	45	37	M10x1.0
WD108		CBT 30 - HC 14 - 85	14	34	45	85	45	37	M10x1.0
WD110		CBT 30 - HC 16 - 90	16	38	45	90	50	42	M10x1.0
WD112	CBT 30 - HC 18 - 90	18	40	45	90	50	42	M10x1.0	
WD114	CBT 30 - HC 20 - 90	20	42	45	90	50	42	M6x1.0	
WE100	40	CBT 40 - HC 6 - 90	6	26	44.5	90	43	27	M5x0.8
WE102		CBT 40 - HC 8 - 90	8	28	44.5	90	44.5	27	M6x1.0
WE104		CBT 40 - HC 10 - 90	10	30	44.5	90	44.5	32	M8x1.0
WE106		CBT 40 - HC 12 - 90	12	32	44.5	90	44.5	37	M10x1.0
WE108		CBT 40 - HC 14 - 90	14	34	44.5	90	44.5	37	M10x1.0
WE110		CBT 40 - HC 16 - 90	16	38	44.5	90	47.5	42	M12x1.0
WE112		CBT 40 - HC 18 - 90	18	40	44.5	90	47.5	42	M12x1.0
WE114		CBT 40 - HC 20 - 90	20	42	44.5	90	47.5	42	M16x1.0
WE116		CBT 40 - HC 25 - 100	25	50	60	100	47.5	48	M16x1.0
WE118		CBT 40 - HC 32 - 105	32	60	-	105	-	55	M16x1.0

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

DUAL CONTACT HYDRAULIC CHUCK (Power E Hydro)

CBT



CBT	Taper Accuracy	G Value	RPM	Run-Out (at 3D)	Coolant System
	AT3	2.5	25,000	≤0.00012"	AD

CBT (BT DUAL CONTACT)

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	D3	L	L2	G	FIG.
WDO30PE	30	CBT 30 - HC 3/4P - 3.543	0.75	1.496	1.653	1.751	3.543	1.889	M8x1.0mm	1
WEO30PE	40	CBT 40 - HC 3/4P - 2.854	0.75	1.496	1.938	-	2.854	1.889	M8x1.0mm	2


Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	D3	L	L2	G	FIG.
WD112PE	30	CBT 30 - HC 12P - 69	12	32	42	44.5	69	41	M8x1.0	1
WD120PE		CBT 30 - HC 20P - 90	20	38	42	44.5	90	48	M8x1.0	1
WE112PE	40	CBT 40 - HC 12P - 58	12	32	42	-	58	41	M8x1.0	2
WE120PE		CBT 40 - HC 20P - 72.5	20	38	49.25	-	72.5	48	M8x1.0	2

- * High Clamping Torque Power version (Please refer to page 1420, Technical Information)
- * Applicable for milling(roughing and finishing)
- * Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

DUAL CONTACT HYDRAULIC CHUCK (For MOULD)

CBT



CBT	Taper Accuracy	G Value	RPM	Run-Out (at 3D)	Coolant System
	AT3	2.5	25,000	≤0.00012"	AD

Unit : inch


CBT (BT DUAL CONTACT)

Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	G
WE100HMC	40	CBT 40 - HMC 6 - 120	6	20	44.5	120	70	27	M5x0.8
WE102HMC		CBT 40 - HMC 6 - 150	6	20	44.5	150	100	27	M5x0.8
WE104HMC		CBT 40 - HMC 8 - 120	8	22	44.5	120	70	27	M6x1.0
WE106HMC		CBT 40 - HMC 8 - 150	8	22	44.5	150	100	27	M6x1.0
WE108HMC		CBT 40 - HMC 10 - 120	10	24	44.5	120	70	32	M8x1.0
WE110HMC		CBT 40 - HMC 10 - 150	10	24	44.5	150	100	32	M8x1.0
WE112HMC		CBT 40 - HMC 12 - 120	12	25	44.5	120	70	37	M10x1.0
WE114HMC		CBT 40 - HMC 12 - 150	12	25	44.5	150	100	37	M10x1.0
WE116HMC		CBT 40 - HMC 16 - 120	16	32	44.5	120	70	42	M12x1.0
WE118HMC		CBT 40 - HMC 16 - 150	16	32	44.5	150	100	42	M12x1.0
WE120HMC		CBT 40 - HMC 20 - 120	20	34	43.8	120	-	42	M16x1.0
WE122HMC		CBT 40 - HMC 20 - 150	20	34	46.9	150	-	42	M16x1.0

- * Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

DUAL CONTACT HYDRAULIC CHUCK (SLIM) HSK



DIN 69893 - HSK	Taper Accuracy	G Value	RPM	Run-Out (at 3D)	Coolant System
-	-	2.5	25,000	≤0.00012"	AD




DIN 69893/ISO 12164-1 HSK FROM A

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	G
WQ020	63A	HSK 63A - HC 1/4 - 2.76	0.250	1.024	1.969	2.756	0.945	1.063	M5x0.8mm
WQ022		HSK 63A - HC 3/8 - 3.15	0.375	1.181	1.969	3.150	1.378	1.260	M8x1.0mm
WQ024		HSK 63A - HC 1/2 - 3.35	0.500	1.260	1.969	3.346	1.575	1.457	M10x1.0mm
WQ026		HSK 63A - HC 3/4 - 3.54	0.750	1.654	1.969	3.543	1.890	1.654	M16x1.0mm
WQ028		HSK 63A - HC 1" - 4.72	1.000	2.244	2.480	4.724	2.323	1.890	M16x1.0mm
WQ030		HSK 63A - HC 1 1/4 - 4.92	1.250	2.520	2.953	4.921	2.480	2.165	M16x1.0mm
WR020	100A	HSK 100A - HC 1/4 - 2.95	0.250	1.024	1.969	2.953	1.024	1.063	M5x0.8mm
WR022		HSK 100A - HC 3/8 - 2.95	0.375	1.181	1.969	3.543	1.654	1.260	M8x1.0mm
WR024		HSK 100A - HC 1/2 - 3.74	0.500	1.260	1.969	3.740	1.850	1.457	M10x1.0mm
WR026		HSK 100A - HC 3/4 - 4.13	0.750	1.654	1.969	4.134	2.323	1.654	M16x1.0mm
WR028		HSK 100A - HC 1" - 4.33	1.000	2.244	2.480	4.331	2.441	1.890	M16x1.0mm
WR032		HSK 100A - HC 1 1/4 - 4.33	1.250	2.520	2.953	4.331	2.441	2.165	M16x1.0mm

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

HYDRAULIC CHUCK (Power E Hydro) HSK



DIN 69893 - HSK	Taper Accuracy	G Value	RPM	Run-Out (at 3D)	Coolant System
-	-	2.5	25,000	≤0.00012"	AD

DIN 69893/ISO 12164-1-HSK FORM A

Unit : inch


EDP No.	TAPER No.	MODEL No.	d1	D1	D2	D3	L	L2	G	FIG.
WQ002PE	63A	HSK 63A - HC 3/4P - 3.149	0.75	1.496	2.066	-	3.149	1.889	M8x1.0mm	1
WQ003PE		HSK 63A - HC 3/4P - 5.118	0.75	1.496	2.066	-	5.118	1.889	M8x1.0mm	1
WR002PE	100A	HSK 100A - HC 1 1/4P - 3.937	1.25	2.303	2.834	-	3.937	2.244	M8x1.0mm	1

Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	D3	L	L2	G	FIG.
WQ100PE	63A	HSK 63A - HC 12P - 80	12	32	42	52.5	80	41	M8x1.0	2
WQ102PE		HSK 63A - HC 20P - 80	20	38	52.5	-	80	48	M8x1.0	1
WR100PE	100A	HSK 100A - HC 20P - 90	20	38	52.5	-	90	48	M8x1.0	1
WR102PE		HSK 100A - HC 32P - 100	32	58.5	72	-	100	57	M8x1.0	1

- * High Clamping Torque Power version (Please refer to page 1420, Technical Information)
- * Applicable for milling(roughing and finishing)
- * Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

DUAL CONTACT HYDRAULIC CHUCK (SHORT & RIGID) HSK



DIN 69893 - HSK	Taper Accuracy	G Value	RPM	Run-Out (at 3D)	Coolant System
-	-	2.5	25,000	≤0.00012"	AD


DIN 69893/ISO 12164-1-HSK FORM A

Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G
WQ100SNR	63A	HSK 63A - HC 12S - 80	12	32	42	80	37	M8x1.0
WQ102SNR		HSK 63A - HC 20S - 80	20	38	52.5	80	42	M8x1.0
WR100SNR	100A	HSK 100A - HC 12S - 85	12	32	42	85	35	M8x1.0
WR102SNR		HSK 100A - HC 20S - 90	20	38	52.5	90	42	M8x1.0

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

DUAL CONTACT HYDRAULIC CHUCK (RADIAL TOOL LENGTH PRE-SETTING TYPE) HSK



DIN 69893 - HSK	Taper Accuracy	G Value	RPM	Run-Out (at 3D)	Coolant System
-	-	2.5	25,000	≤0.00012"	AD

DIN 69893/ISO 12164-1-HSK FORM A


Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	
WQ100HCR	63A	HSK 63A - HCR 6 - 85	6	26	50	85	33	27	
WQ102HCR		HSK 63A - HCR 8 - 85	8	28	50	85	33	27	
WQ104HCR		HSK 63A - HCR 10 - 85	10	30	50	85	38	32	
WQ106HCR		HSK 63A - HCR 12 - 95	12	32	50	95	40	37	
WQ108HCR		HSK 63A - HCR 14 - 95	14	34	50	95	46	37	
WQ110HCR		HSK 63A - HCR 16 - 95	16	38	50	95	51	42	
WQ112HCR		HSK 63A - HCR 18 - 95	18	40	50	95	52	42	
WQ114HCR		HSK 63A - HCR 20 - 100	20	42	50	100	51	42	
WQ116HCR		HSK 63A - HCR 25 - 120	25	57	63	120	54.5	48	
WQ118HCR		HSK 63A - HCR 32 - 125	32	64	75	125	57.5	55	
WR100HCR		100A	HSK 100A - HCR 6 - 90	6	26	63	90	33	27
WR102HCR			HSK 100A - HCR 8 - 90	8	28	63	90	33	27
WR104HCR			HSK 100A - HCR 10 - 95	10	30	63	95	36	32
WR106HCR			HSK 100A - HCR 12 - 100	12	32	63	100	40	37
WR108HCR	HSK 100A - HCR 14 - 100		14	34	63	100	41	37	
WR110HCR	HSK 100A - HCR 16 - 105		16	38	63	105	46	42	
WR112HCR	HSK 100A - HCR 18 - 105		18	40	63	105	46	42	
WR114HCR	HSK 100A - HCR 20 - 105		20	42	75	105	51	42	
WR116HCR	HSK 100A - HCR 25 - 115	25	57	75	115	55.5	48		
WR118HCR	HSK 100A - HCR 32 - 120	32	64	75	120	63.5	55		

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

DUAL CONTACT HYDRAULIC CHUCK (For MOULD)

HSK



DIN 69893 -HSK	Taper Accuracy	G Value	RPM	Run-Out (at 3D)	Coolant System
-	-	2.5	25,000	≤0.00012"	AD

DIN 69893/ISO 12164-1-HSK FORM A

Unit : inch


EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	G
WQ020HMC	63A	HSK 63A - HMC 1/4 - 5.71	0.250	0.787	1.969	5.709	3.543	1.063	M5x0.8mm
WQ022HMC		HSK 63A - HMC 5/16 - 5.71	0.313	0.866	1.969	5.709	3.543	1.063	M6x1.0mm
WQ024HMC		HSK 63A - HMC 3/8 - 5.71	0.375	0.945	1.969	5.709	3.543	1.260	M8x1.0mm
WQ026HMC		HSK 63A - HMC 1/2 - 5.71	0.500	1.024	1.969	5.709	3.543	1.457	M10x1.0mm
WQ028HMC		HSK 63A - HMC 5/8 - 5.71	0.625	1.260	1.969	5.709	3.543	1.654	M12x1.0mm
WQ030HMC		HSK 63A - HMC 3/4 - 5.71	0.750	1.339	1.969	5.709	3.543	1.654	M16x1.0mm
WR100HMC	100A	HSK 100A - HMC 1/4 - 5.71	0.250	0.787	1.969	5.709	3.543	1.063	M5x0.8mm
WR102HMC		HSK 100A - HMC 5/16 - 5.71	0.313	0.866	1.969	5.709	3.543	1.063	M6x1.0mm
WR104HMC		HSK 100A - HMC 3/8 - 5.71	0.375	0.945	1.969	5.709	3.543	1.260	M8x1.0mm
WR106HMC		HSK 100A - HMC 1/2 - 5.71	0.500	1.024	1.969	5.709	3.543	1.457	M10x1.0mm
WR108HMC		HSK 100A - HMC 5/8 - 5.71	0.625	1.260	1.969	5.709	3.543	1.654	M12x1.0mm
WR110HMC		HSK 100A - HMC 3/4 - 5.71	0.750	1.339	1.969	5.709	3.543	1.654	M16x1.0mm

Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	L2	G
WQ100HMC	63A	HSK 63A - HMC 6 - 145	6	20	50	145	90	27	M5x0.8
WQ102HMC		HSK 63A - HMC 8 - 145	8	22	50	145	90	27	M6x1.0
WQ104HMC		HSK 63A - HMC 10 - 145	10	24	50	145	90	32	M8x1.0
WQ106HMC		HSK 63A - HMC 12 - 145	12	25	50	145	90	37	M10x1.0
WQ108HMC		HSK 63A - HMC 16 - 145	16	32	50	145	90	42	M12x1.0
WQ110HMC		HSK 63A - HMC 20 - 145	20	34	50	145	90	42	M16x1.0
WR200HMC	100A	HSK 100A - HMC 6 - 150	6	20	50	150	90	27	M5x0.8
WR202HMC		HSK 100A - HMC 8 - 150	8	22	50	150	90	27	M6x1.0
WR204HMC		HSK 100A - HMC10 - 150	10	24	50	150	90	32	M8x1.0
WR206HMC		HSK 100A - HMC12 - 150	12	25	50	150	90	37	M10x1.0
WR208HMC		HSK 100A - HMC16 - 150	16	32	50	150	90	42	M12x1.0
WR210HMC		HSK 100A - HMC20 - 150	20	34	50	150	90	42	M16x1.0

* Applicable Hydraulic Chuck collets(reduction sleeves) on page 1331~1338.

HYDRAULIC CHUCK COLLET (REDUCTION SLEEVE : OPEN TYPE)



METRIC / INCH

Unit : inch

EDP No.	TYPE	d	D1	D2	L	L2
412108	HK12	1/8"	0.125	0.472	0.748	1.850
412316		3/16"	0.188	0.472	0.748	1.850
412104		1/4"	0.250	0.472	0.748	1.850
412516		5/16"	0.313	0.472	0.748	1.850
420108	HK20	1/8"	0.125	0.787	1.063	2.067
420316		3/16"	0.188	0.787	1.063	2.067
420104		1/4"	0.250	0.787	1.063	2.067
420516		5/16"	0.313	0.787	1.063	2.067
420308		3/8"	0.375	0.787	1.063	2.067
420102		1/2"	0.500	0.787	1.063	2.067
420508	5/8"	0.625	0.787	1.063	2.067	0.079
432108	HK32	1/8"	0.125	1.260	1.535	2.500
432316		3/16"	0.188	1.260	1.535	2.500
432104		1/4"	0.250	1.260	1.535	2.500
432516		5/16"	0.313	1.260	1.535	2.500
432308		3/8"	0.375	1.260	1.535	2.500
432102		1/2"	0.500	1.260	1.535	2.500
432508		5/8"	0.625	1.260	1.535	2.500
432304		3/4"	0.750	1.260	1.535	2.500
432100		1	1.000	1.260	1.535	2.500

* Other special sizes of Hydraulic Chuck collets can be supplied on request.


Feature

Hydraulic Chuck collet(reduction sleeve) is cut into trisection by high precision cutting to guarantee precise I.D and strong clamping power.

Chucking Method

Please assemble cutting tool with collet first, and then insert collet into Hydraulic Chuck.

HYDRAULIC CHUCK COLLET (REDUCTION SLEEVE : CLOSED TYPE)



METRIC / INCH

Unit : inch

EDP No.	TYPE	d	D1	D2	L	L2	
512108	HS12	1/8"	0.125	0.472	0.748	1.850	0.079
512316		3/16"	0.188	0.472	0.748	1.850	0.079
512104		1/4"	0.250	0.472	0.748	1.850	0.079
512516		5/16"	0.313	0.472	0.748	1.850	0.079
520108		1/8"	0.125	0.787	1.063	2.067	0.079
520316	HS20	3/16"	0.188	0.787	1.063	2.067	0.079
520104		1/4"	0.250	0.787	1.063	2.067	0.079
520516		5/16"	0.313	0.787	1.063	2.067	0.079
520308		3/8"	0.375	0.787	1.063	2.067	0.079
520102		1/2"	0.500	0.787	1.063	2.067	0.079
520508	HS32	5/8"	0.625	0.787	1.063	2.067	0.079
532108		1/8"	0.125	1.260	1.535	2.500	0.118
532316		3/16"	0.188	1.260	1.535	2.500	0.118
532104		1/4"	0.250	1.260	1.535	2.500	0.118
532516		5/16"	0.313	1.260	1.535	2.500	0.118
532308		3/8"	0.375	1.260	1.535	2.500	0.118
532102		1/2"	0.500	1.260	1.535	2.500	0.118
532508		5/8"	0.625	1.260	1.535	2.500	0.118
532304		3/4"	0.750	1.260	1.535	2.500	0.118
532100		1	1.000	1.260	1.535	2.500	0.118

* Other special sizes of Hydraulic Chuck collets can be supplied on request.


Feature

The wall of Hydraulic Chuck collet(reduction sleeve) is cut by high precision wire-cutting to guarantee precise I.D and strong clamping power.

Chucking Method

Please assemble cutting tool with collet first, and then insert collet into Hydraulic Chuck.

HYDRAULIC CHUCK COLLET (REDUCTION SLEEVE : CLOSED TYPE)



INCH / INCH

Unit : inch

EDP No.	TYPE	d	D1	D2	L	L2	
612108	HK1/2"	1/8"	0.125	0.500	0.748	1.850	0.079
612316		3/16"	0.188	0.500	0.748	1.850	0.079
612104		1/4"	0.250	0.500	0.748	1.850	0.079
612516		5/16"	0.313	0.500	0.748	1.850	0.079
625108		1/8"	0.125	0.750	1.063	2.067	0.079
625316	HK3/4"	3/16"	0.188	0.750	1.063	2.067	0.079
625104		1/4"	0.250	0.750	1.063	2.067	0.079
625516		5/16"	0.313	0.750	1.063	2.067	0.079
625308		3/8"	0.375	0.750	1.063	2.067	0.079
625102		1/2"	0.500	0.750	1.063	2.067	0.079
625508	HK1 1/4"	5/8"	0.625	0.750	1.063	2.067	0.079
632108		1/8"	0.125	1.250	1.535	2.500	0.118
632316		3/16"	0.188	1.250	1.535	2.500	0.118
632104		1/4"	0.250	1.250	1.535	2.500	0.118
632516		5/16"	0.313	1.250	1.535	2.500	0.118
632308		3/8"	0.375	1.250	1.535	2.500	0.118
632102		1/2"	0.500	1.250	1.535	2.500	0.118
632508		5/8"	0.625	1.250	1.535	2.500	0.118
632304		3/4"	0.750	1.250	1.535	2.500	0.118
632100		1	1.000	1.250	1.535	2.500	0.118

* Other special sizes of Hydraulic Chuck collets can be supplied on request.


Feature

Hydraulic Chuck collet(reduction sleeve) is cut into trisection by high precision cutting to guarantee precise I.D and strong clamping power.

Chucking Method

Please assemble cutting tool with collet first, and then insert collet into Hydraulic Chuck.

HYDRAULIC CHUCK COLLET (REDUCTION SLEEVE : CLOSED TYPE)



INCH / INCH

Unit : inch


EDP No.	TYPE	d	D1	D2	L	L2	
712108	HS1/2"	1/8"	0.125	0.500	0.748	1.850	0.079
712316		3/16"	0.188	0.500	0.748	1.850	0.079
712104		1/4"	0.250	0.500	0.748	1.850	0.079
712516		5/16"	0.313	0.500	0.748	1.850	0.079
725108		1/8"	0.125	0.750	1.063	2.067	0.079
725316	HS3/4"	3/16"	0.188	0.750	1.063	2.067	0.079
725104		1/4"	0.250	0.750	1.063	2.067	0.079
725516		5/16"	0.313	0.750	1.063	2.067	0.079
725308		3/8"	0.375	0.750	1.063	2.067	0.079
725102		1/2"	0.500	0.750	1.063	2.067	0.079
725508	5/8"	0.625	0.750	1.063	2.067	0.079	
732108	HS1 1/4"	1/8"	0.125	1.250	1.535	2.500	0.118
732316		3/16"	0.188	1.250	1.535	2.500	0.118
732104		1/4"	0.250	1.250	1.535	2.500	0.118
732516		5/16"	0.313	1.250	1.535	2.500	0.118
732308		3/8"	0.375	1.250	1.535	2.500	0.118
732102		1/2"	0.500	1.250	1.535	2.500	0.118
732508		5/8"	0.625	1.250	1.535	2.500	0.118
732304		3/4"	0.750	1.250	1.535	2.500	0.118
732100		1	1.000	1.250	1.535	2.500	0.118

* Other special sizes of Hydraulic Chuck collets can be supplied on request.

Feature The wall of Hydraulic Chuck collet(reduction sleeve) is cut by high precision wire-cutting to guarantee precise I.D and strong clamping power.

Chucking Method Please assemble cutting tool with collet first, and then insert collet into Hydraulic Chuck.

HYDRAULIC CHUCK COLLET (REDUCTION SLEEVE : CLOSED TYPE)



METRIC / METRIC

Unit : mm


EDP No.	TYPE	d	D1	D2	L	L2		
812030	HK12	3	3	12	19	47	2	
812040		4	4	12	19	47	2	
812050		5	5	12	19	47	2	
812060		6	6	12	19	47	2	
812070		7	7	12	19	47	2	
812008		8	8	12	19	47	2	
820030		HK20	3	3	20	27	52.5	2
820040			4	4	20	27	52.5	2
820050	5		5	20	27	52.5	2	
820060	6		6	20	27	52.5	2	
820070	7		7	20	27	52.5	2	
820080	8		8	20	27	52.5	2	
820090	9		9	20	27	52.5	2	
820100	10		10	20	27	52.5	2	
820110	11		11	20	27	52.5	2	
820120	12		12	20	27	52.5	2	
820130	13		13	20	27	52.5	2	
820140	14		14	20	27	52.5	2	
820150	15		15	20	27	52.5	2	
820160	16		16	20	27	52.5	2	
832060	HK32		6	6	32	39	63.5	3
832080		8	8	32	39	63.5	3	
832100		10	10	32	39	63.5	3	
832120		12	12	32	39	63.5	3	
832140		14	14	32	39	63.5	3	
832160		16	16	32	39	63.5	3	
832180		18	18	32	39	63.5	3	
832200		20	20	32	39	63.5	3	
832250		25	25	32	39	63.5	3	

* Other special sizes of Hydraulic Chuck collets can be supplied on request.

Feature Hydraulic Chuck collet(reduction sleeve) is cut into trisection by high precision cutting to guarantee precise I.D and strong clamping power.

Chucking Method Please assemble cutting tool with collet first, and then insert collet into Hydraulic Chuck.

HYDRAULIC CHUCK COLLET (REDUCTION SLEEVE : CLOSED TYPE)



METRIC / METRIC

Unit : mm


EDP No.	TYPE	d	D1	D2	L	L2		
912030	HS12	3	3	12	19	47	2	
912040		4	4	12	19	47	2	
912050		5	5	12	19	47	2	
912060		6	6	12	19	47	2	
912070		7	7	12	19	47	2	
912080		8	8	12	19	47	2	
920030		HS20	3	3	20	27	52.5	2
920040			4	4	20	27	52.5	2
920050	5		5	20	27	52.5	2	
920060	6		6	20	27	52.5	2	
920070	7		7	20	27	52.5	2	
920080	8		8	20	27	52.5	2	
920090	9		9	20	27	52.5	2	
920100	10		10	20	27	52.5	2	
920110	11		11	20	27	52.5	2	
920120	12		12	20	27	52.5	2	
920130	13		13	20	27	52.5	2	
920140	14		14	20	27	52.5	2	
920150	15	15	20	27	52.5	2		
920160	16	16	20	27	52.5	2		
932060	HS32	6	6	32	39	63.5	3	
932080		8	8	32	39	63.5	3	
932100		10	10	32	39	63.5	3	
932120		12	12	32	39	63.5	3	
932140		14	14	32	39	63.5	3	
932160		16	16	32	39	63.5	3	
932180		18	18	32	39	63.5	3	
932200		20	20	32	39	63.5	3	
932250		25	25	32	39	63.5	3	

* Other special sizes of Hydraulic Chuck collets can be supplied on request.

Feature The wall of Hydraulic Chuck collet(reduction sleeve) is cut by high precision wire-cutting to guarantee precise I.D and strong clamping power.

Chucking Method Please assemble cutting tool with collet first, and then insert collet into Hydraulic Chuck.

HYDRAULIC CHUCK COLLET (REDUCTION SLEEVE : OPEN TYPE)



INCH / METRIC

Unit : inch


EDP No.	TYPE	d	D1	D2	L	L2		
101203	HK1/2"	3	3mm	0.500	0.748	1.850	0.079	
101204		4	4mm	0.500	0.748	1.850	0.079	
101205		5	5mm	0.500	0.748	1.850	0.079	
101206		6	6mm	0.500	0.748	1.850	0.079	
101208		8	8mm	0.500	0.748	1.850	0.079	
102503		HK3/4"	3	3mm	0.750	1.063	2.067	0.079
102504			4	4mm	0.750	1.063	2.067	0.079
102505			5	5mm	0.750	1.063	2.067	0.079
102506	6		6mm	0.750	1.063	2.067	0.079	
102508	8		8mm	0.750	1.063	2.067	0.079	
102510	10		10mm	0.750	1.063	2.067	0.079	
102512	12		12mm	0.750	1.063	2.067	0.079	
102514	14	14mm	0.750	1.063	2.067	0.079		
103208	HK1 1/4"	8	8mm	1.250	1.535	2.500	0.118	
103210		10	10mm	1.250	1.535	2.500	0.118	
103212		12	12mm	1.250	1.535	2.500	0.118	
103214		14	14mm	1.250	1.535	2.500	0.118	
103216		16	16mm	1.250	1.535	2.500	0.118	
103218		18	18mm	1.250	1.535	2.500	0.118	
103220		20	20mm	1.250	1.535	2.500	0.118	
103225	25	25mm	1.250	1.535	2.500	0.118		

* Other special sizes of Hydraulic Chuck collets can be supplied on request.

Feature Hydraulic Chuck collet(reduction sleeve) is cut into trisection by high precision cutting to guarantee precise I.D and strong clamping power.

Chucking Method Please assemble cutting tool with collet first, and then insert collet into Hydraulic Chuck.

HYDRAULIC CHUCK COLLET (REDUCTION SLEEVE : CLOSED TYPE)



INCH / METRIC

Unit : inch


EDP No.	TYPE	d	D1	D2	L	L2		
111203	HS1/2"	3	3mm	0.500	0.748	1.850	0.079	
111204		4	4mm	0.500	0.748	1.850	0.079	
111205		5	5mm	0.500	0.748	1.850	0.079	
111206		6	6mm	0.500	0.748	1.850	0.079	
111208		8	8mm	0.500	0.748	1.850	0.079	
112503		HS3/4"	3	3mm	0.750	1.063	2.067	0.079
112504	4		4mm	0.750	1.063	2.067	0.079	
112505	5		5mm	0.750	1.063	2.067	0.079	
112506	6		6mm	0.750	1.063	2.067	0.079	
112508	8		8mm	0.750	1.063	2.067	0.079	
112510	10		10mm	0.750	1.063	2.067	0.079	
112512	12		12mm	0.750	1.063	2.067	0.079	
112514	14		14mm	0.750	1.063	2.067	0.079	
113208	HS1 1/4"		8	8mm	1.250	1.535	2.500	0.118
113210			10	10mm	1.250	1.535	2.500	0.118
113212			12	12mm	1.250	1.535	2.500	0.118
113214			14	14mm	1.250	1.535	2.500	0.118
113216			16	16mm	1.250	1.535	2.500	0.118
113218			18	18mm	1.250	1.535	2.500	0.118
113220		20	20mm	1.250	1.535	2.500	0.118	
113225		25	25mm	1.250	1.535	2.500	0.118	

* Other special sizes of Hydraulic Chuck collets can be supplied on request.

- Feature** The wall of Hydraulic Chuck collet(reduction sleeve) is cut by high precision wire-cutting to guarantee precise I.D and strong clamping power.
- Chucking Method** Please assemble cutting tool with collet first, and then insert collet into Hydraulic Chuck.

SHRINK FIT HOLDER

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD/B
------------------	--------------------	-------------	------------	---------------------------	---------------------



ASME B5.50-2009-CAT

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G
VK020	40	CAT40 AD/B - SFH 1/8 - 3.15	0.125	0.394	0.748	3.150	0.354	-
VK022		CAT40 AD/B - SFH 3/16 - 3.15	0.188	0.394	0.748	3.150	0.472	-
VK024		CAT40 AD/B - SFH 1/4 - 3.15	0.250	0.827	1.063	3.150	1.417	M5x0.8mm
VK026		CAT40 AD/B - SFH 1/4 - 6.30	0.250	0.827	1.063	6.300	1.417	M5x0.8mm
VK028		CAT40 AD/B - SFH 3/8 - 3.15	0.375	0.945	1.260	3.150	1.654	M8x1.0mm
VK030		CAT40 AD/B - SFH 3/8 - 6.30	0.375	0.945	1.260	6.300	1.654	M8x1.0mm
VK032		CAT40 AD/B - SFH 1/2 - 3.15	0.500	0.945	1.260	3.150	1.811	M10x1.0mm
VK034		CAT40 AD/B - SFH 1/2 - 6.30	0.500	0.945	1.260	6.300	1.850	M10x1.0mm
VK036		CAT40 AD/B - SFH 5/8 - 3.15	0.625	1.063	1.339	3.150	1.969	M12x1.0mm
VK038		CAT40 AD/B - SFH 5/8 - 6.30	0.625	1.063	1.339	6.300	1.969	M12x1.0mm
VK040		CAT40 AD/B - SFH 3/4 - 3.15	0.750	1.299	1.654	3.150	2.047	M16x1.0mm
VK042		CAT40 AD/B - SFH 3/4 - 6.30	0.750	1.299	1.654	6.300	2.047	M16x1.0mm
VK044		CAT40 AD/B - SFH 1" - 3.94	1.000	1.732	2.087	3.937	2.283	M16x1.0mm
VK046		CAT40 AD/B - SFH 1" - 6.30	1.000	1.732	2.087	6.300	2.283	M16x1.0mm
VK048		CAT40 AD/B - SFH 1 1/4 - 3.94	1.250	1.732	2.087	3.937	2.283	M16x1.0mm
VK050		CAT40 AD/B - SFH 1 1/4 - 6.30	1.250	1.732	2.087	6.300	2.283	M16x1.0mm
VL020	50	CAT50 AD/B - SFH 1/8 - 3.15	0.125	0.394	0.748	3.150	0.354	-
VL022		CAT50 AD/B - SFH 3/16 - 3.15	0.188	0.394	0.748	3.150	0.472	-
VL024		CAT50 AD/B - SFH 1/4 - 3.15	0.250	0.827	1.063	3.150	1.417	M5x0.8mm
VL026		CAT50 AD/B - SFH 1/4 - 6.30	0.250	0.827	1.063	6.300	1.417	M5x0.8mm
VL028		CAT50 AD/B - SFH 3/8 - 3.15	0.375	0.945	1.260	3.150	1.575	M8x1.0mm
VL030		CAT50 AD/B - SFH 3/8 - 6.30	0.375	0.945	1.260	6.300	1.575	M8x1.0mm
VL032		CAT50 AD/B - SFH 1/2 - 3.15	0.500	0.945	1.260	3.150	1.850	M10x1.0mm
VL034		CAT50 AD/B - SFH 1/2 - 6.30	0.500	0.945	1.260	6.300	1.850	M10x1.0mm
VL036		CAT50 AD/B - SFH 5/8 - 3.15	0.625	1.063	1.339	3.150	1.969	M12x1.0mm
VL038		CAT50 AD/B - SFH 5/8 - 6.3	0.625	1.063	1.339	6.300	1.969	M12x1.0mm
VL040		CAT50 AD/B - SFH 3/4 - 3.15	0.750	1.299	1.654	3.150	2.047	M16x1.0mm
VL042		CAT50 AD/B - SFH 3/4 - 6.3	0.750	1.299	1.654	6.300	2.047	M16x1.0mm
VL044		CAT50 AD/B - SFH 1" - 3.94	1.000	1.732	2.087	3.937	2.283	M16x1.0mm
VL046		CAT50 AD/B - SFH 1" - 6.30	1.000	1.732	2.087	6.300	2.283	M16x1.0mm
VL048		CAT50 AD/B - SFH 1 1/4 - 3.94	1.250	1.732	2.087	3.937	2.283	M16x1.0mm
VL050		CAT50 AD/B - SFH 1 1/4 - 6.30	1.250	1.732	2.087	6.300	2.283	M16x1.0mm

SHRINK FIT HOLDER (Coolant Channel Type)

CAT



ASME B5.50 -CAT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD/B+C
-----------------	--------------------	-------------	------------	---------------------------	-----------------------

ASME B5.50-2009-CAT


Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G
VK028J	40	CAT40 AD/B - SFH 3/8C - 3.15	0.375	0.945	1.260	3.150	1.654	M8x1.0mm
VK030J		CAT40 AD/B - SFH 3/8C - 6.30	0.375	0.945	1.260	6.300	1.654	M8x1.0mm
VK032J		CAT40 AD/B - SFH 1/2C - 3.15	0.500	0.945	1.260	3.150	1.850	M10x1.0mm
VK034J		CAT40 AD/B - SFH 1/2C - 6.30	0.500	0.945	1.260	6.300	1.850	M10x1.0mm
VK036J		CAT40 AD/B - SFH 5/8C - 3.15	0.625	1.063	1.339	3.150	1.969	M12x1.0mm
VK038J		CAT40 AD/B - SFH 5/8C - 6.30	0.625	1.063	1.339	6.300	1.969	M12x1.0mm
VK040J		CAT40 AD/B - SFH 3/4C - 3.15	0.750	1.299	1.654	3.150	2.047	M16x1.0mm
VK042J		CAT40 AD/B - SFH 3/4C - 6.30	0.750	1.299	1.654	6.300	2.047	M16x1.0mm
VK044J		CAT40 AD/B - SFH 1C - 3.94	1.000	1.732	2.087	3.940	2.283	M16x1.0mm
VK046J		CAT40 AD/B - SFH 1C - 6.30	1.000	1.732	2.087	6.300	2.283	M16x1.0mm
VK048J		CAT40 AD/B - SFH 1 1/4C - 3.94	1.250	1.732	2.087	3.940	2.283	M16x1.0mm
VK050J		CAT40 AD/B - SFH 1 1/4C - 6.30	1.250	1.732	2.087	6.300	2.283	M16x1.0mm
VL028J	50	CAT50 AD/B - SFH 3/8C - 3.15	0.375	0.945	1.260	3.150	1.575	M8x1.0mm
VL030J		CAT50 AD/B - SFH 3/8C - 6.30	0.375	0.945	1.260	6.300	1.575	M8x1.0mm
VL032J		CAT50 AD/B - SFH 1/2C - 3.15	0.500	0.945	1.260	3.150	1.850	M10x1.0mm
VL034J		CAT50 AD/B - SFH 1/2C - 6.30	0.500	0.945	1.260	6.300	1.850	M10x1.0mm
VL036J		CAT50 AD/B - SFH 5/8C - 3.15	0.625	1.063	1.339	3.150	1.969	M12x1.0mm
VL038J		CAT50 AD/B - SFH 5/8C - 6.3	0.625	1.063	1.339	6.300	1.969	M12x1.0mm
VL040J		CAT50 AD/B - SFH 3/4C - 3.15	0.750	1.299	1.654	3.150	2.047	M16x1.0mm
VL042J		CAT50 AD/B - SFH 3/4C - 6.3	0.750	1.299	1.654	6.300	2.047	M16x1.0mm
VL044J		CAT50 AD/B - SFH 1C - 3.94	1.000	1.732	2.087	3.940	2.283	M16x1.0mm
VL046J		CAT50 AD/B - SFH 1C - 6.30	1.000	1.732	2.087	6.300	2.283	M16x1.0mm
VL048J		CAT50 AD/B - SFH 1 1/4C - 3.94	1.250	1.732	2.087	3.940	2.283	M16x1.0mm
VL050J		CAT50 AD/B - SFH 1 1/4C - 6.30	1.250	1.732	2.087	6.300	2.283	M16x1.0mm

* Effective cooling by coolant through cooling channel bores.

SHRINK FIT HOLDER

BT




JIS B6339 -BT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD or AD/B
---------------	--------------------	-------------	------------	---------------------------	---------------------------

JIS B6339/MAS 403-BT

Unit : inch

SHRINK FIT HOLDER (Coolant Channel Type)

BT



JIS B6339 - BT	Taper Accuracy	G Value	RPM	Run-Out (at 3D)	Coolant System
	AT3	2.5	25,000	≤0.00012"	AD+C or AD/B+C

JIS B6339/MAS 403-BT


Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G
VG024J	30	BT30 - SFH 1/4C - 2.36	0.250	0.827	1.063	2.360	1.417	M5x0.8mm
VG026J		BT30 - SFH 3/8C - 2.36	0.375	0.945	1.180	2.360	1.654	M8x1.0mm
VG028J		BT30 - SFH 1/2C - 3.15	0.500	0.945	1.260	3.150	1.850	M10x1.0mm
VG030J		BT30 - SFH 5/8C - 3.15	0.625	1.063	1.339	3.150	1.969	M12x1.0mm
VG032J		BT30 - SFH 3/4C - 3.54	0.750	1.299	1.654	3.540	2.008	M16x1.0mm
VH024J	40	BT40 AD/B - SFH 1/4C - 3.54	0.250	0.827	1.063	3.540	1.417	M5x0.8mm
VH026J		BT40 AD/B - SFH 1/4C - 6.30	0.250	0.827	1.063	6.300	1.417	M5x0.8mm
VH028J		BT40 AD/B - SFH 3/8C - 3.54	0.375	0.945	1.260	3.540	1.654	M8x1.0mm
VH030J		BT40 AD/B - SFH 3/8C - 6.30	0.375	0.945	1.260	6.300	1.654	M8x1.0mm
VH032J		BT40 AD/B - SFH 1/2C - 3.54	0.500	0.945	1.260	3.540	1.850	M10x1.0mm
VH034J		BT40 AD/B - SFH 1/2C - 6.30	0.500	0.945	1.260	6.300	1.850	M10x1.0mm
VH036J		BT40 AD/B - SFH 5/8C - 3.54	0.625	1.063	1.339	3.540	1.969	M12x1.0mm
VH038J		BT40 AD/B - SFH 5/8C - 6.30	0.625	1.063	1.339	6.300	1.969	M12x1.0mm
VH040J		BT40 AD/ 4C - 3.54	0.750	1.299	1.654	3.540	2.047	M16x1.0mm
VH042J		BT40 AD/B - SFH 3/4C - 6.30	0.750	1.299	1.654	6.300	2.047	M16x1.0mm
VH044J		BT40 AD/B - SFH 1C - 3.94	1.000	1.732	2.087	3.940	2.283	M16x1.0mm
VH046J	BT40 AD/B - SFH 1C - 6.30	1.000	1.732	2.087	6.300	2.283	M16x1.0mm	

* Effective cooling by coolant through cooling channel bores.

DUAL CONTACT SHRINK FIT HOLDER

CCT



CCT	Taper Accuracy	G Value	RPM	Run-Out (at 3D)	Coolant System
	AT3	2.5	25,000	≤0.00012"	AD/B


CCT (CAT DUAL CONTACT)

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G
VB020	40	CCT40 AD/B - SFH 1/8 - 3.15	0.125	0.394	0.748	3.150	0.354	-
VB022		CCT40 AD/B - SFH 3/16 - 3.15	0.188	0.394	0.748	3.150	0.472	-
VB024		CCT40 AD/B - SFH 1/4 - 3.15	0.250	0.827	1.063	3.150	1.417	M5x0.8mm
VB026		CCT40 AD/B - SFH 1/4 - 6.30	0.250	0.827	1.063	6.300	1.417	M5x0.8mm
VB028		CCT40 AD/B - SFH 3/8 - 3.15	0.375	0.945	1.260	3.150	1.654	M8x1.0mm
VB030		CCT40 AD/B - SFH 3/8 - 6.30	0.375	0.945	1.260	6.300	1.654	M8x1.0mm
VB032		CCT40 AD/B - SFH 1/2 - 3.15	0.500	0.945	1.260	3.150	1.850	M10x1.0mm
VB034		CCT40 AD/B - SFH 1/2 - 6.30	0.500	0.945	1.260	6.300	1.850	M10x1.0mm
VB036		CCT40 AD/B - SFH 5/8 - 3.15	0.625	1.063	1.339	3.150	1.969	M12x1.0mm
VB038		CCT40 AD/B - SFH 5/8 - 6.30	0.625	1.063	1.339	6.300	1.969	M12x1.0mm
VB040		CCT40 AD/B - SFH 3/4 - 3.15	0.750	1.299	1.654	3.150	2.047	M16x1.0mm
VB042		CCT40 AD/B - SFH 3/4 - 6.30	0.750	1.299	1.654	6.300	2.047	M16x1.0mm
VB044		CCT40 AD/B - SFH 1" - 3.94	1.000	1.732	2.087	3.937	2.283	M16x1.0mm
VB046		CCT40 AD/B - SFH 1" - 6.30	1.000	1.732	2.087	6.300	2.283	M16x1.0mm
VB048		CCT40 AD/B - SFH 1 1/4 - 3.94	1.250	1.732	2.087	3.937	2.283	M16x1.0mm
VB050		CCT40 AD/B - SFH 1 1/4 - 6.30	1.250	1.732	2.087	6.300	2.283	M16x1.0mm
VC020	50	CCT50 AD/B - SFH 1/8 - 3.15	0.125	0.394	0.748	3.150	0.354	-
VC022		CCT50 AD/B - SFH 3/16 - 3.15	0.188	0.394	0.748	3.150	0.472	-
VC024		CCT50 AD/B - SFH 1/4 - 3.15	0.250	0.827	1.063	3.150	1.417	M5x0.8mm
VC026		CCT50 AD/B - SFH 1/4 - 6.30	0.250	0.827	1.063	6.300	1.417	M5x0.8mm
VC028		CCT50 AD/B - SFH 3/8 - 3.15	0.375	0.945	1.260	3.150	1.575	M8x1.0mm
VC030		CCT50 AD/B - SFH 3/8 - 6.30	0.375	0.945	1.260	6.300	1.575	M8x1.0mm
VC032		CCT50 AD/B - SFH 1/2 - 3.15	0.500	0.945	1.260	3.150	1.850	M10x1.0mm
VC034		CCT50 AD/B - SFH 1/2 - 6.30	0.500	0.945	1.260	6.300	1.850	M10x1.0mm
VC036		CCT50 AD/B - SFH 5/8 - 3.15	0.625	1.063	1.339	3.150	1.969	M12x1.0mm
VC040		CCT50 AD/B - SFH 5/8 - 6.30	0.625	1.063	1.339	6.300	1.969	M12x1.0mm
VC042		CCT50 AD/B - SFH 3/4 - 3.15	0.750	1.299	1.654	3.150	2.047	M16x1.0mm
VC044		CCT50 AD/B - SFH 3/4 - 6.30	0.750	1.299	1.654	6.300	2.047	M16x1.0mm
VC046		CCT50 AD/B - SFH 1" - 3.94	1.000	1.732	2.087	3.937	2.283	M16x1.0mm
VC048		CCT50 AD/B - SFH 1" - 6.30	1.000	1.732	2.087	6.300	2.283	M16x1.0mm
VC050		CCT50 AD/B - SFH 1 1/4 - 3.94	1.250	1.732	2.087	3.937	2.283	M16x1.0mm
VC052		CCT50 AD/B - SFH 1 1/4 - 6.30	1.250	1.732	2.087	6.300	2.283	M16x1.0mm

DUAL CONTACT SHRINK FIT HOLDER (Coolant Channel Type)

CCT



CCT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD/B+C
-----	------------------------------	-----------------------	----------------------	-------------------------------------	---------------------------------

CCT (CAT DUAL CONTACT)


Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G	
VBO24J	40	CCT40 AD/B - SFH 1/4C - 3.15	0.250	0.827	1.063	3.150	1.417	M5x0.8mm	
VBO26J		CCT40 AD/B - SFH 1/4C - 6.30	0.250	0.827	1.063	6.300	1.417	M5x0.8mm	
VBO28J		CCT40 AD/B - SFH 3/8C - 3.15	0.375	0.945	1.260	3.150	1.654	M8x1.0mm	
VBO30J		CCT40 AD/B - SFH 3/8C - 6.30	0.375	0.945	1.260	6.300	1.654	M8x1.0mm	
VBO32J		CCT40 AD/B - SFH 1/2C - 3.15	0.500	0.945	1.260	3.150	1.850	M10x1.0mm	
VBO34J		CCT40 AD/B - SFH 1/2C - 6.30	0.500	0.945	1.260	6.300	1.850	M10x1.0mm	
VBO36J		CCT40 AD/B - SFH 5/8C - 3.15	0.625	1.063	1.339	3.150	1.969	M12x1.0mm	
VBO38J		CCT40 AD/B - SFH 5/8C - 6.30	0.625	1.063	1.339	6.300	1.969	M12x1.0mm	
VBO40J		CCT40 AD/B - SFH 3/4C - 3.15	0.750	1.299	1.654	3.150	2.047	M16x1.0mm	
VBO42J		CCT40 AD/B - SFH 3/4C - 6.30	0.750	1.299	1.654	6.300	2.047	M16x1.0mm	
VBO44J		CCT40 AD/B - SFH 1C - 3.94	1.000	1.732	2.087	3.940	2.283	M16x1.0mm	
VBO46J		CCT40 AD/B - SFH 1C - 6.30	1.000	1.732	2.087	6.300	2.283	M16x1.0mm	
VBO48J		CCT40 AD/B - SFH 1 1/4C - 3.94	1.250	1.732	2.087	3.940	2.283	M16x1.0mm	
VBO50J		CCT40 AD/B - SFH 1 1/4C - 6.30	1.250	1.732	2.087	6.300	2.283	M16x1.0mm	
VC024J		50	CCT50 AD/B - SFH 1/4C - 3.15	0.250	0.827	1.063	3.150	1.417	M5x0.8mm
VC026J			CCT50 AD/B - SFH 1/4C - 6.30	0.250	0.827	1.063	6.300	1.417	M5x0.8mm
VC028J	CCT50 AD/B - SFH 3/8C - 3.15		0.375	0.945	1.260	3.150	1.654	M8x1.0mm	
VC030J	CCT50 AD/B - SFH 3/8C - 6.30		0.375	0.945	1.260	6.300	1.654	M8x1.0mm	
VC032J	CCT50 AD/B - SFH 1/2C - 3.15		0.500	0.945	1.260	3.150	1.850	M10x1.0mm	
VC034J	CCT50 AD/B - SFH 1/2C - 6.30		0.500	0.945	1.260	6.300	1.850	M10x1.0mm	
VC036J	CCT50 AD/B - SFH 5/8C - 3.15		0.625	1.063	1.339	3.150	1.969	M12x1.0mm	
VC040J	CCT50 AD/B - SFH 5/8C - 6.30		0.625	1.063	1.339	6.300	1.969	M12x1.0mm	
VC042J	CCT50 AD/B - SFH 3/4C - 3.15		0.750	1.299	1.654	3.150	2.047	M16x1.0mm	
VC044J	CCT50 AD/B - SFH 3/4C - 6.30		0.750	1.299	1.654	6.300	2.047	M16x1.0mm	
VC046J	CCT50 AD/B - SFH 1C - 3.94		1.000	1.732	2.087	3.940	2.283	M16x1.0mm	
VC048J	CCT50 AD/B - SFH 1C - 6.30		1.000	1.732	2.087	6.300	2.283	M16x1.0mm	
VC050J	CCT50 AD/B - SFH 1 1/4C - 3.94		1.250	1.732	2.087	3.940	2.283	M16x1.0mm	
VC052J	CCT50 AD/B - SFH 1 1/4C - 6.30		1.250	1.732	2.087	6.300	2.283	M16x1.0mm	

* Effective cooling by coolant through cooling channel bores.

DUAL CONTACT SHRINK FIT HOLDER

CBT




CBT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD
-----	------------------------------	-----------------------	----------------------	-------------------------------------	-----------------------------

CBT (BT DUAL CONTACT)

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G
VD020	30	CBT30 - SFH 1/8 - 2.36	0.125	0.394	0.629	2.362	0.354	-
VD022		CBT30 - SFH 3/16 - 2.36	0.188	0.394	0.629	2.362	0.472	-
VD024		CBT30 - SFH 1/4 - 2.36	0.250	0.827	1.062	2.362	1.417	M5x0.8mm
VD026		CBT30 - SFH 3/8 - 2.36	0.375	0.945	1.180	2.362	1.614	M8x1.0mm
VD028		CBT30 - SFH 1/2 - 3.15	0.500	0.945	1.260	3.150	1.850	M10x1.0mm
VD030		CBT30 - SFH 5/8 - 3.15	0.625	1.063	1.339	3.150	1.969	M12x1.0mm
VD032		CBT30 - SFH 3/4 - 3.54	0.750	1.299	1.654	3.543	2.047	M16x1.0mm
VE020		40	CBT40 - SFH 1/8 - 3.54	0.125	0.394	0.748	3.543	0.354
VE022	CBT40 - SFH 3/16 - 3.54		0.188	0.394	0.748	3.543	0.472	-
VE024	CBT40 - SFH 1/4 - 3.54		0.250	0.827	1.063	3.543	1.417	M5x0.8mm
VE026	CBT40 - SFH 1/4 - 6.30		0.250	0.827	1.063	6.300	1.417	M5x0.8mm
VE028	CBT40 - SFH 3/8 - 3.54		0.375	0.945	1.260	3.543	1.654	M8x1.0mm
VE030	CBT40 - SFH 3/8 - 6.30		0.375	0.945	1.260	6.300	1.654	M8x1.0mm
VE032	CBT40 - SFH 1/2 - 3.54		0.500	0.945	1.260	3.543	1.850	M10x1.0mm
VE034	CBT40 - SFH 1/2 - 6.30		0.500	0.945	1.260	6.300	1.850	M10x1.0mm
VE036	CBT40 - SFH 5/8 - 3.54		0.625	1.063	1.339	3.543	1.969	M12x1.0mm
VE038	CBT40 - SFH 5/8 - 6.30		0.625	1.063	1.339	6.300	1.969	M12x1.0mm
VE040	CBT40 - SFH 3/4 - 3.54		0.750	1.299	1.654	3.543	2.047	M16x1.0mm
VE042	CBT40 - SFH 3/4 - 6.30		0.750	1.299	1.654	6.300	2.047	M16x1.0mm
VE044	CBT40 - SFH 1" - 3.94		1.000	1.732	2.087	3.937	2.283	M16x1.0mm
VE046	CBT40 - SFH 1" - 6.30		1.000	1.732	2.087	6.300	2.283	M16x1.0mm

DUAL CONTACT SHRINK FIT HOLDER (Coolant Channel Type) CBT



CBT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD+C
-----	------------------------------	-----------------------	----------------------	-------------------------------------	-------------------------------


CBT (BT DUAL CONTACT)

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G
VD024J	30	CBT30 - SFH 1/4C - 2.36	0.250	0.827	1.062	2.360	1.417	M5x0.8mm
VD026J		CBT30 - SFH 3/8C - 2.36	0.375	0.945	1.180	2.360	1.614	M8x1.0mm
VD028J		CBT30 - SFH 1/2C - 3.15	0.500	0.945	1.260	3.150	1.850	M10x1.0mm
VD030J		CBT30 - SFH 5/8C - 3.15	0.625	1.063	1.339	3.150	1.969	M12x1.0mm
VD032J		CBT30 - SFH 3/4C - 3.54	0.750	1.299	1.654	3.540	2.047	M16x1.0mm
VE024J	40	CBT40 - SFH 1/4C - 3.54	0.250	0.827	1.063	3.540	1.417	M5x0.8mm
VE026J		CBT40 - SFH 1/4C - 6.30	0.250	0.827	1.063	6.300	1.417	M5x0.8mm
VE028J		CBT40 - SFH 3/8C - 3.54	0.375	0.945	1.260	3.540	1.654	M8x1.0mm
VE030J		CBT40 - SFH 3/8C - 6.30	0.375	0.945	1.260	6.300	1.654	M8x1.0mm
VE032J		CBT40 - SFH 1/2C - 3.54	0.500	0.945	1.260	3.540	1.850	M10x1.0mm
VE034J		CBT40 - SFH 1/2C - 6.30	0.500	0.945	1.260	6.300	1.850	M10x1.0mm
VE036J		CBT40 - SFH 5/8C - 3.54	0.625	1.063	1.339	3.540	1.969	M12x1.0mm
VE038J		CBT40 - SFH 5/8C - 6.30	0.625	1.063	1.339	6.300	1.969	M12x1.0mm
VE040J		CBT40 - SFH 3/4C - 3.54	0.750	1.299	1.654	3.540	2.047	M16x1.0mm
VE042J		CBT40 - SFH 3/4C - 6.30	0.750	1.299	1.654	6.300	2.047	M16x1.0mm
VE044J		CBT40 - SFH 1C - 3.94	1.000	1.732	2.087	3.940	2.283	M16x1.0mm
VE046J		CBT40 - SFH 1C - 6.30	1.000	1.732	2.087	6.300	2.283	M16x1.0mm

* Effective cooling by coolant through cooling channel bores.

DUAL CONTACT SHRINK FIT HOLDER HSK



DIN 69893 - HSK	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD
-----------------	------------------------------	-----------------------	----------------------	-------------------------------------	-----------------------------


DIN 69893/ISO 12164-1-HSK FORM A

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G	
VQ020	63A	HSK 63A - SFH 1/8 - 3.15	0.125	0.394	0.728	3.150	0.354	-	
VQ022		HSK 63A - SFH 3/16 - 3.15	0.188	0.394	0.728	3.150	0.472	-	
VQ024		HSK 63A - SFH 1/4 - 3.15	0.250	0.827	1.063	3.150	1.417	M5x0.8mm	
VQ026		HSK 63A - SFH 1/4 - 6.30	0.250	0.827	1.063	6.300	1.417	M5x0.8mm	
VQ028		HSK 63A - SFH 3/8 - 3.35	0.375	0.945	1.260	3.346	1.654	M8x1.0mm	
VQ030		HSK 63A - SFH 3/8 - 6.30	0.375	0.945	1.260	6.300	1.654	M8x1.0mm	
VQ032		HSK 63A - SFH 1/2 - 3.54	0.500	0.945	1.260	3.543	1.850	M10x1.0mm	
VQ034		HSK 63A - SFH 1/2 - 6.30	0.500	0.945	1.260	6.300	1.850	M10x1.0mm	
VQ036		HSK 63A - SFH 5/8 - 3.74	0.625	1.063	1.339	3.740	1.969	M12x1.0mm	
VQ038		HSK 63A - SFH 5/8 - 6.30	0.625	1.063	1.339	6.300	1.969	M12x1.0mm	
VQ040		HSK 63A - SFH 3/4 - 3.94	0.750	1.299	1.654	3.937	2.047	M16x1.0mm	
VQ042		HSK 63A - SFH 3/4 - 6.30	0.750	1.299	1.654	6.300	2.047	M16x1.0mm	
VQ046		HSK 63A - SFH 1" - 4.53	1.000	1.732	2.087	4.528	2.283	M16x1.0mm	
VQ048		HSK 63A - SFH 1" - 6.30	1.000	1.732	2.087	6.300	2.283	M16x1.0mm	
VR020		100A	HSK 100A - SFH 1/8 - 3.15	0.125	0.394	0.648	3.150	0.354	-
VR022			HSK 100A - SFH 3/16 - 3.15	0.188	0.394	0.648	3.150	0.472	-
VR023			HSK 100A - SFH 1/4 - 3.15	0.250	0.827	1.063	3.150	1.417	M5x0.8mm
VR024			HSK 100A - SFH 3/8 - 3.54	0.375	0.945	1.260	3.543	1.654	M8x1.0mm
VR026	HSK 100A - SFH 3/8 - 6.30		0.375	0.945	1.260	6.300	1.654	M8x1.0mm	
VR028	HSK 100A - SFH 1/2 - 3.74		0.500	0.945	1.260	3.740	1.850	M10x1.0mm	
VR030	HSK 100A - SFH 1/2 - 6.30		0.500	0.945	1.260	6.300	1.850	M10x1.0mm	
VR032	HSK 100A - SFH 5/8 - 3.94		0.625	1.063	1.339	3.937	1.969	M12x1.0mm	
VR034	HSK 100A - SFH 5/8 - 6.30		0.625	1.063	1.339	6.300	1.969	M12x1.0mm	
VR036	HSK 100A - SFH 3/4 - 4.13		0.750	1.299	1.654	4.134	2.047	M16x1.0mm	
VR038	HSK 100A - SFH 3/4 - 6.30		0.750	1.299	1.654	6.300	2.047	M16x1.0mm	
VR040	HSK 100A - SFH 1" - 4.53		1.000	1.732	2.087	4.528	2.283	M16x1.0mm	
VR042	HSK 100A - SFH 1" - 6.30		1.000	1.732	2.087	6.300	2.283	M16x1.0mm	
VR044	HSK 100A - SFH 1 1/4 - 4.72		1.250	1.732	2.087	4.724	2.283	M16x1.0mm	
VR046	HSK 100A - SFH 1 1/4" - 6.30		1.250	1.732	2.087	6.300	2.283	M16x1.0mm	

DUAL CONTACT SHRINK FIT HOLDER (Coolant Channel Type)

HSK



DIN 69893 - HSK	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Run-Out (at 3D) ≤0.00012"	Coolant System AD+C
-----------------	---------------------------	--------------------	-------------------	----------------------------------	----------------------------

DIN 69893/ISO 12164-1-HSK FORM A


Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L2	G	
VG024J	63A	HSK 63A - SFH 1/4C - 3.15	0.250	0.827	1.063	3.150	1.417	M5x0.8mm	
VG026J		HSK 63A - SFH 1/4C - 6.30	0.250	0.827	1.063	6.300	1.417	M5x0.8mm	
VG028J		HSK 63A - SFH 3/8C - 3.35	0.375	0.945	1.260	3.350	1.654	M8x1.0mm	
VG030J		HSK 63A - SFH 3/8C - 6.30	0.375	0.945	1.260	6.300	1.654	M8x1.0mm	
VG032J		HSK 63A - SFH 1/2C - 3.54	0.500	0.945	1.260	3.540	1.850	M10x1.0mm	
VG034J		HSK 63A - SFH 1/2C - 6.30	0.500	0.945	1.260	6.300	1.850	M10x1.0mm	
VG036J		HSK 63A - SFH 5/8C - 3.74	0.625	1.063	1.339	3.740	1.969	M12x1.0mm	
VG038J		HSK 63A - SFH 5/8C - 6.30	0.625	1.063	1.339	6.300	1.969	M12x1.0mm	
VG040J		HSK 63A - SFH 3/4C - 3.94	0.750	1.299	1.654	3.940	2.047	M16x1.0mm	
VG042J		HSK 63A - SFH 3/4C - 6.30	0.750	1.299	1.654	6.300	2.047	M16x1.0mm	
VG046J		HSK 63A - SFH 1C - 4.53	1.000	1.732	2.087	4.530	2.283	M16x1.0mm	
VG048J		HSK 63A - SFH 1C - 6.30	1.000	1.732	2.087	6.300	2.283	M16x1.0mm	
VR023J		100A	HSK 100A - SFH 1/4C - 3.54	0.250	0.827	1.063	3.540	1.417	M5x0.8mm
VR024J			HSK 100A - SFH 3/8C - 3.54	0.375	0.945	1.260	3.540	1.654	M8x1.0mm
VR026J	HSK 100A - SFH 3/8C - 6.30		0.375	0.945	1.260	6.300	1.654	M8x1.0mm	
VR028J	HSK 100A - SFH 1/2C - 3.74		0.500	0.945	1.260	3.740	1.850	M10x1.0mm	
VR030J	HSK 100A - SFH 1/2C - 6.30		0.500	0.945	1.260	6.300	1.850	M10x1.0mm	
VR032J	HSK 100A - SFH 5/8C - 3.94		0.625	1.063	1.339	3.940	1.969	M12x1.0mm	
VR034J	HSK 100A - SFH 5/8C - 6.30		0.625	1.063	1.339	6.300	1.969	M12x1.0mm	
VR036J	HSK 100A - SFH 3/4C - 4.13		0.750	1.299	1.654	4.130	2.047	M16x1.0mm	
VR038J	HSK 100A - SFH 3/4C - 6.30		0.750	1.299	1.654	6.300	2.047	M16x1.0mm	
VR040J	HSK 100A - SFH 1C - 4.53		1.000	1.732	2.087	4.530	2.283	M16x1.0mm	
VR042J	HSK 100A - SFH 1C - 6.30		1.000	1.732	2.087	6.300	2.283	M16x1.0mm	
VR044J	HSK 100A - SFH 1 1/4C - 4.72		1.250	1.732	2.087	4.720	2.283	M16x1.0mm	
VR046J	HSK 100A - SFH 1 1/4C - 6.30		1.250	1.732	2.087	6.300	2.283	M16x1.0mm	

* Effective cooling by coolant through cooling channel bores.

SHRINK FIT EXTENSION

ST




INCH

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	G
VS010	ST1/2	ST 1/2 - SFH 1/8 - 6.30	0.125	0.394	0.500	6.300	0.354	-
VS011		ST 1/2 - SFH 3/16 - 6.30	0.188	0.394	0.500	6.300	0.472	-
VS012		ST 1/2 - SFH 1/4 - 6.30	0.250	0.394	0.500	6.300	1.417	M5x0.8mm
VS020	ST5/8	ST 5/8 - SFH 1/8 - 6.30	0.125	0.394	0.625	6.300	0.354	-
VS021		ST 5/8 - SFH 3/16 - 6.30	0.188	0.394	0.625	6.300	0.472	-
VS022		ST 5/8 - SFH 1/4 - 6.30	0.250	0.394	0.625	6.300	1.417	M5x0.8mm
VS023	ST 5/8 - SFH 5/16 - 6.30	0.313	0.472	0.625	6.300	1.535	M6x1.0mm	
VS030	ST3/4	ST 3/4 - SFH 1/8 - 6.30	0.125	0.394	0.750	6.300	0.354	-
VS031		ST 3/4 - SFH 3/16 - 6.30	0.188	0.394	0.750	6.300	0.472	-
VS032		ST 3/4 - SFH 1/4 - 6.30	0.250	0.551	0.750	6.300	1.417	M5x0.8mm
VS033		ST 3/4 - SFH 5/16 - 6.30	0.313	0.551	0.750	6.300	1.417	M6x1.0mm
VS034	ST 3/4 - SFH 3/8 - 6.30	0.375	0.551	0.750	6.300	1.654	M8x1.0mm	
VS035	ST 3/4 - SFH 1/2 - 6.30	0.500	0.630	0.750	6.300	1.850	M10x1.0mm	
VS040	ST1	ST 1 - SFH 1/8 - 6.30	0.125	0.394	1.000	6.300	0.354	-
VS041		ST 1 - SFH 3/16 - 6.30	0.188	0.394	1.000	6.300	0.472	-
VS042		ST 1 - SFH 1/4 - 6.30	0.250	0.551	1.000	6.300	1.417	M5x0.8mm
VS043		ST 1 - SFH 5/16 - 6.30	0.313	0.551	1.000	6.300	1.417	M6x1.0mm
VS044		ST 1 - SFH 3/8 - 6.30	0.375	0.787	1.000	6.300	1.654	M8x1.0mm
VS045		ST 1 - SFH 1/2 - 6.30	0.500	0.787	1.000	6.300	1.850	M10x1.0mm
VS046		ST 1 - SFH 5/8 - 6.30	0.625	0.866	1.000	6.300	1.929	M12x1.0mm
VS050	ST1-1/4	ST 1 - 1/4 - SFH 1/8 - 6.30	0.125	0.394	1.250	6.300	0.354	-
VS051		ST 1 - 1/4 - SFH 3/16 - 6.30	0.188	0.394	1.250	6.300	0.472	-
VS052		ST 1 - 1/4 - SFH 1/4 - 6.30	0.250	0.551	1.250	6.300	1.417	M5x0.8mm
VS053		ST 1 - 1/4 - SFH 5/16 - 6.30	0.313	0.551	1.250	6.300	1.417	M6x1.0mm
VS054		ST 1 - 1/4 - SFH 3/8 - 6.30	0.375	0.945	1.250	6.300	1.654	M8x1.0mm
VS055		ST 1 - 1/4 - SFH 1/2 - 6.30	0.500	0.945	1.250	6.300	1.850	M10x1.0mm
VS056		ST 1 - 1/4 - SFH 5/8 - 6.30	0.625	1.063	1.250	6.300	1.929	M12x1.0mm
VS057		ST 1 - 1/4 - SFH 3/4 - 6.30	0.750	1.063	1.250	6.300	2.008	M16x1.0mm

SHRINK FIT EXTENSION

ST




METRIC (STANDARD)

Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	G
VS010M	12	ST12 - SFH3 - 120	3	8	12	120	10	-
VS011M		ST12 - SFH4 - 120	4	8	12	120	12	-
VS012M		ST12 - SFH5 - 120	5	10	12	120	15	-
VS013M		ST12 - SFH6 - 120	6	10	12	120	36	M5x0.8
VS020M	16	ST16 - SFH3 - 120	3	10	16	120	10	-
VS021M		ST16 - SFH4 - 120	4	10	16	120	12	-
VS022M		ST16 - SFH5 - 120	5	10	16	120	15	-
VS023M		ST16 - SFH6 - 120	6	10	16	120	36	M5x0.8
VS024M	20	ST16 - SFH8 - 120	8	12	16	120	36	M6x1.0
VS030M		ST20 - SFH3 - 120	3	10	20	120	10	-
VS031M		ST20 - SFH4 - 120	4	10	20	120	12	-
VS032M		ST20 - SFH5 - 120	5	10	20	120	15	-
VS033M	20	ST20 - SFH6 - 120	6	10	20	120	36	M5x0.8
VS034M		ST20 - SFH8 - 120	8	12	20	120	36	M6x1.0
VS035M		ST20 - SFH10 - 120	10	14	20	120	41.5	M8x1.0
VS036M		ST20 - SFH12 - 120	12	16	20	120	46	M10x1.0

SHRINK FIT EXTENSION

ST




METRIC (EXTENDED)

Unit : mm

EDP No.	TAPER No.	MODEL No.	d1	D1	D2	L	L1	G
VS110M	12	ST12 - SFH 3 - 160	3	8	12	160	10	-
VS111M		ST12 - SFH 4 - 160	4	8	12	160	12	-
VS112M		ST12 - SFH 5 - 160	5	10	12	160	15	-
VS113M		ST12 - SFH 6 - 160	6	10	12	160	36	M5x0.8
VS210M	16	ST16 - SFH 3 - 160	3	10	16	160	10	-
VS211M		ST16 - SFH 4 - 160	4	10	16	160	12	-
VS212M		ST16 - SFH 5 - 160	5	10	16	160	15	-
VS213M		ST16 - SFH 6 - 160	6	10	16	160	36	M5x0.8
VS214M	20	ST16 - SFH 8 - 160	8	12	16	160	36	M6x1.0
VS310M		ST20 - SFH 3 - 160	3	10	20	160	10	-
VS311M		ST20 - SFH 4 - 160	4	10	20	160	12	-
VS312M		ST20 - SFH 5 - 160	5	10	20	160	15	-
VS313M	20	ST20 - SFH 6 - 160	6	10	20	160	36	M5x0.8
VS314M		ST20 - SFH 8 - 160	8	12	20	160	36	M6x1.0
VS315M		ST20 - SFH 10 - 160	10	14	20	160	41.5	M8x1.0
VS316M		ST20 - SFH 12 - 160	12	16	20	160	46	M10x1.0
VS410M	25	ST25 - SFH 3 - 160	3	10	25	160	10	-
VS411M		ST25 - SFH 4 - 160	4	10	25	160	12	-
VS412M		ST25 - SFH 5 - 160	5	15	25	160	15	-
VS413M		ST25 - SFH 6 - 160	6	20	25	160	36	M5x0.8
VS414M		ST25 - SFH 8 - 160	8	20	25	160	36	M6x1.0
VS415M		ST25 - SFH 10 - 160	10	20	25	160	41.5	M8x1.0
VS416M		ST25 - SFH 12 - 160	12	20	25	160	46	M10x1.0
VS417M		ST25 - SFH 14 - 160	14	20	25	160	46	M10x1.0
VS418M	32	ST25 - SFH 16 - 160	16	22	25	160	49	M12x1.0
VS510M		ST32 - SFH 6 - 160	6	20	32	160	36	M5x0.8
VS511M		ST32 - SFH 8 - 160	8	20	32	160	36	M6x1.0
VS512M		ST32 - SFH 10 - 160	10	24	32	160	41.5	M8x1.0
VS513M	32	ST32 - SFH 12 - 160	12	24	32	160	46	M10x1.0
VS514M		ST32 - SFH 14 - 160	14	27	32	160	46	M10x1.0
VS515M		ST32 - SFH 16 - 160	16	27	32	160	49	M12x1.0
VS516M		ST32 - SFH 18 - 160	18	27	32	160	49	M12x1.0
VS517M		ST32 - SFH 20 - 160	20	27	32	160	51	M16x1.0

END MILL HOLDER

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 6.3	RPM 15,000	Coolant System AD
------------------	--------------------	-------------	------------	-------------------

ASME B5.50-2009-CAT

■ **STUB**


Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L
AK206	40	CAT40 - EMH 1/2 - 1.75	0.500	1.25	1.75
AK208		CAT40 - EMH 5/8 - 1.75	0.625	1.50	1.75
AK210		CAT40 - EMH 3/4 - 1.75	0.750	1.75	1.75
AK214		CAT40 - EMH 1" - 1.75	1.000	1.75	1.75
AK217		CAT40 - EMH 1 1/4 - 2.00	1.250	2.25	2.00

* High balanced End Mill Holders on page 1356~1357.
 * Set screws for End Mill Holders on page 1365.

END MILL HOLDER

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 6.3	RPM 15,000	Coolant System AD/B
------------------	--------------------	-------------	------------	---------------------

ASME B5.50-2009-CAT

■ **STANDARD**


Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L	
AK000B	40	CAT40 AD/B - EMH 1/8 - 2.50	0.125	0.69	2.50	
AK001B		CAT40 AD/B - EMH 3/16 - 2.50	0.187	0.69	2.50	
AK002B		CAT40 AD/B - EMH 1/4 - 2.50	0.250	0.78	2.50	
AK003B		CAT40 AD/B - EMH 5/16 - 2.50	0.312	0.88	2.50	
AK004B		CAT40 AD/B - EMH 3/8 - 2.50	0.375	1.00	2.50	
AK005B		CAT40 AD/B - EMH 7/16 - 2.50	0.437	1.13	2.50	
AK006B		CAT40 AD/B - EMH 1/2 - 2.63	0.500	1.25	2.63	
AK008B		CAT40 AD/B - EMH 5/8 - 3.75	0.625	1.50	3.75	
AK010B		CAT40 AD/B - EMH 3/4 - 3.75	0.750	1.75	3.75	
AK012B		CAT40 AD/B - EMH 7/8 - 4.00	0.875	1.88	4.00	
AK014B		CAT40 AD/B - EMH 1" - 4.00	1.000	2.00	4.00	
AK017B		CAT40 AD/B - EMH 1 1/4 - 4.25	1.250	2.50	4.25	
AK021B		CAT40 AD/B - EMH 1 1/2 - 4.63	1.500	2.50	4.63	
AL002B		50	CAT50 AD/B - EMH 1/4 - 2.50	0.250	0.78	2.50
AL003B			CAT50 AD/B - EMH 5/16 - 2.50	0.312	0.88	2.50
AL004B			CAT50 AD/B - EMH 3/8 - 2.50	0.375	1.00	2.50
AL005B			CAT50 AD/B - EMH 7/16 - 2.63	0.437	1.13	2.63
AL006B	CAT50 AD/B - EMH 1/2 - 2.63		0.500	1.25	2.63	
AL008B	CAT50 AD/B - EMH 5/8 - 3.75		0.625	1.50	3.75	
AL010B	CAT50 AD/B - EMH 3/4 - 3.75		0.750	1.75	3.75	
AL012B	CAT50 AD/B - EMH 7/8 - 3.75		0.875	1.88	3.75	
AL014B	CAT50 AD/B - EMH 1" - 4.00		1.000	2.00	4.00	
AL017B	CAT50 AD/B - EMH 1 1/4 - 4.00		1.250	2.50	4.00	
AL021B	CAT50 AD/B - EMH 1 1/2 - 4.00		1.500	2.50	4.00	
AL029B	CAT50 AD/B - EMH 2" - 5.63		2.000	3.75	5.63	

* High balanced End Mill Holders are available on request.
 * Set screws for End Mill Holders on page 1365.

END MILL HOLDER

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 6.3	RPM 15,000	Coolant System AD/B
------------------	--------------------	-------------	------------	---------------------

ASME B5.50-2009-CAT

■ EXTENDED


Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L	
AK104B	40	CAT40 AD/B - EMH 3/8 - 4.50	0.375	1.00	4.50	
AK106B		CAT40 AD/B - EMH 1/2 - 4.63	0.500	1.25	4.63	
AK108B		CAT40 AD/B - EMH 5/8 - 5.75	0.625	1.50	5.75	
AK110B		CAT40 AD/B - EMH 3/4 - 5.75	0.750	1.75	5.75	
AK112B		CAT40 AD/B - EMH 7/8 - 6.00	0.875	1.88	6.00	
AK114B		CAT40 AD/B - EMH 1" - 6.00	1.000	2.00	6.00	
AK117B		CAT40 AD/B - EMH 1 1/4 - 6.25	1.250	2.50	6.25	
AK121B		CAT40 AD/B - EMH 1 1/2 - 6.63	1.500	2.50	6.63	
AL104B		50	CAT50 AD/B - EMH 3/8 - 4.50	0.375	1.00	4.50
AL106B			CAT50 AD/B - EMH 1/2 - 4.63	0.500	1.25	4.63
AL108B	CAT50 AD/B - EMH 5/8 - 5.75		0.625	1.50	5.75	
AL110B	CAT50 AD/B - EMH 3/4 - 5.75		0.750	1.75	5.75	
AL112B	CAT50 AD/B - EMH 7/8 - 5.75		0.875	1.88	5.75	
AL114B	CAT50 AD/B - EMH 1" - 6.00		1.000	2.00	6.00	
AL117B	CAT50 AD/B - EMH 1 1/4 - 6.00		1.250	2.50	6.00	
AL121B	CAT50 AD/B - EMH 1 1/2 - 6.00		1.500	2.50	6.00	
AL129B	CAT50 AD/B - EMH 2" - 7.63		2.000	3.75	7.63	

* High balanced End Mill Holders are available on request.
* Set screws for End Mill Holders on page 1365.

END MILL HOLDER (Coolant Channel Type)

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 6.3	RPM 15,000	Coolant System AD/B+C
------------------	--------------------	-------------	------------	-----------------------

ASME B5.50-2009-CAT


Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L	
AK002C	40	CAT40 AD/B - EMH 1/4C - 1.97	0.250	0.780	1.969	
AK003C		CAT40 AD/B - EMH 5/16C - 1.97	0.313	0.880	1.969	
AK004C		CAT40 AD/B - EMH 3/8C - 1.97	0.375	1.000	1.969	
AK005C		CAT40 AD/B - EMH 1/2C - 1.97	0.500	1.250	1.969	
AK008C		CAT40 AD/B - EMH 5/8C - 2.48	0.625	1.500	2.480	
AK010C		CAT40 AD/B - EMH 3/4C - 2.48	0.750	1.750	2.480	
AK012C		CAT40 AD/B - EMH 1C - 3.94	1.000	2.000	3.937	
AK017C		CAT40 AD/B - EMH 1 1/4C - 3.94	1.250	2.500	3.937	
AL002C		50	CAT50 AD/B - EMH 1/4C - 2.48	0.250	0.780	2.480
AL003C			CAT50 AD/B - EMH 5/16C - 2.48	0.313	0.880	2.480
AL004C	CAT50 AD/B - EMH 3/8C - 2.48		0.375	1.000	2.480	
AL005C	CAT50 AD/B - EMH 1/2C - 2.48		0.500	1.250	2.480	
AL008C	CAT50 AD/B - EMH 5/8C - 2.48		0.625	1.500	2.480	
AL010C	CAT50 AD/B - EMH 3/4C - 2.48		0.750	1.750	2.480	
AL012C	CAT50 AD/B - EMH 1C - 3.15		1.000	2.000	3.150	
AL017C	CAT50 AD/B - EMH 1 1/4C - 3.94		1.250	2.500	3.937	

* High balanced End Mill Holders are available on request.
* Set screws for End Mill Holders on page 1365.

HIGH BALANCED END MILL HOLDER

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Coolant System AD
------------------	-----------------------	----------------	---------------	----------------------

ASME B5.50-2009-CAT

■ **STUB**

Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L
AK206B25	40	CAT40 - EMH 1/2 - 1.75	0.500	1.25	1.75
AK208B25		CAT40 - EMH 5/8 - 1.75	0.625	1.50	1.75
AK210B25		CAT40 - EMH 3/4 - 1.75	0.750	1.75	1.75
AK214B25		CAT40 - EMH 1" - 1.75	1.000	1.75	1.75
AK217B25		CAT40 - EMH 1 1/4 - 2.00	1.250	2.25	2.00

■ **STANDARD**


Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L	
AK000B25	40	CAT40 - EMH 1/8 - 2.50	0.125	0.69	2.50	
AK001B25		CAT40 - EMH 3/16 - 2.50	0.187	0.69	2.50	
AK002B25		CAT40 - EMH 1/4 - 2.50	0.250	0.78	2.50	
AK003B25		CAT40 - EMH 5/16 - 2.50	0.312	0.88	2.50	
AK004B25		CAT40 - EMH 3/8 - 2.50	0.375	1.00	2.50	
AK005B25		CAT40 - EMH 7/16 - 2.50	0.437	1.13	2.50	
AK006B25		CAT40 - EMH 1/2 - 2.63	0.500	1.25	2.63	
AK008B25		CAT40 - EMH 5/8 - 3.75	0.625	1.50	3.75	
AK010B25		CAT40 - EMH 3/4 - 3.75	0.750	1.75	3.75	
AK012B25		CAT40 - EMH 7/8 - 4.00	0.875	1.88	4.00	
AK014B25		CAT40 - EMH 1" - 4.00	1.000	2.00	4.00	
AK017B25		CAT40 - EMH 1 1/4 - 4.25	1.250	2.50	4.25	
AK021B25		CAT40 - EMH 1 1/2 - 4.63	1.500	2.50	4.63	
AL002B25		50	CAT50 - EMH 1/4 - 2.50	0.250	0.78	2.50
AL003B25			CAT50 - EMH 5/16 - 2.50	0.312	0.88	2.50
AL004B25			CAT50 - EMH 3/8 - 2.50	0.375	1.00	2.50
AL005B25			CAT50 - EMH 7/16 - 2.63	0.437	1.13	2.63
AL006B25			CAT50 - EMH 1/2 - 2.63	0.500	1.25	2.63
AL008B25	CAT50 - EMH 5/8 - 3.75		0.625	1.50	3.75	
AL010B25	CAT50 - EMH 3/4 - 3.75		0.750	1.75	3.75	
AL012B25	CAT50 - EMH 7/8 - 3.75		0.875	1.88	3.75	
AL014B25	CAT50 - EMH 1" - 4.00		1.000	2.00	4.00	
AL017B25	CAT50 - EMH 1 1/4 - 4.00		1.250	2.50	4.00	
AL021B25	CAT50 - EMH 1 1/2 - 4.00		1.500	2.50	4.00	
AL029B25	CAT50 - EMH 2" - 5.63		2.000	3.75	5.63	

* Set screws for End Mill Holders on page 1365.

HIGH BALANCED END MILL HOLDER

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Coolant System AD
------------------	-----------------------	----------------	---------------	----------------------

ASME B5.50-2009-CAT

■ **EXTENDED**


Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L	
AK104B25	40	CAT40 - EMH 3/8 - 4.50	0.375	1.00	4.50	
AK106B25		CAT40 - EMH 1/2 - 4.63	0.500	1.25	4.63	
AK108B25		CAT40 - EMH 5/8 - 5.75	0.625	1.50	5.75	
AK110B25		CAT40 - EMH 3/4 - 5.75	0.750	1.75	5.75	
AK112B25		CAT40 - EMH 7/8 - 6.00	0.875	1.88	6.00	
AK114B25		CAT40 - EMH 1" - 6.00	1.000	2.00	6.00	
AK117B25		CAT40 - EMH 1 1/4 - 6.25	1.250	2.50	6.25	
AK121B25		CAT40 - EMH 1 1/2 - 6.63	1.500	2.50	6.63	
AL104B25		50	CAT50 - EMH 3/8 - 4.50	0.375	1.00	4.50
AL106B25			CAT50 - EMH 1/2 - 4.63	0.500	1.25	4.63
AL108B25			CAT50 - EMH 5/8 - 5.75	0.625	1.50	5.75
AL110B25			CAT50 - EMH 3/4 - 5.75	0.750	1.75	5.75
AL112B25	CAT50 - EMH 7/8 - 5.75		0.875	1.88	5.75	
AL114B25	CAT50 - EMH 1" - 6.00		1.000	2.00	6.00	
AL117B25	CAT50 - EMH 1 1/4 - 6.00		1.250	2.50	6.00	
AL121B25	CAT50 - EMH 1 1/2 - 6.00		1.500	2.50	6.00	
AL129B25	CAT50 - EMH 2" - 7.63		2.000	3.75	7.63	

* Set screws for End Mill Holders on page 1365.

END MILL HOLDER

BT



JIS B6339 -BT	Taper Accuracy AT3	G Value 6.3	RPM 15,000	Coolant System AD
---------------	--------------------	-------------	------------	-------------------

JIS B6339/MAS 403-BT

■ **STUB**

Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L
AH206	40	BT40 - EMH 1/2 - 1.25	0.500	1.25	1.25
AH208		BT40 - EMH 5/8 - 1.38	0.625	1.50	1.38
AH210		BT40 - EMH 3/4 - 1.44	0.750	1.75	1.44
AH214		BT40 - EMH 1" - 2.50	1.000	2.00	2.50
AH217		BT40 - EMH 1 1/4 - 2.50	1.250	2.50	2.50

■ **STANDARD**

Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L
AI002	50	BT50 - EMH 1/4 - 3.00	0.250	0.78	3.00
AI004		BT50 - EMH 3/8 - 3.00	0.375	1.00	3.00
AI006		BT50 - EMH 1/2 - 3.00	0.500	1.25	3.00
AI008		BT50 - EMH 5/8 - 3.00	0.625	1.50	3.00
AI010		BT50 - EMH 3/4 - 3.00	0.750	1.75	3.00
AI012		BT50 - EMH 7/8 - 4.00	0.875	1.88	4.00
AI014		BT50 - EMH 1" - 4.25	1.000	2.00	4.25
AI017		BT50 - EMH 1 1/4 - 4.25	1.250	2.50	4.25
AI021		BT50 - EMH 1 1/2 - 4.25	1.500	2.50	4.25
AI029		BT50 - EMH 2" - 5.00	2.000	3.75	5.00

■ **EXTENDED**


Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L
AI104	50	BT50 - EMH 3/8 - 6.00	0.375	1.00	6.00
AI106		BT50 - EMH 1/2 - 6.00	0.500	1.25	6.00
AI108		BT50 - EMH 5/8 - 6.00	0.625	1.50	6.00
AI110		BT50 - EMH 3/4 - 6.00	0.750	1.75	6.00
AI112		BT50 - EMH 7/8 - 6.00	0.875	1.88	6.00
AI114		BT50 - EMH 1" - 6.00	1.000	2.00	6.00
AI117		BT50 - EMH 1 1/4 - 6.00	1.250	2.50	6.00
AI121		BT50 - EMH 1 1/2 - 6.00	1.500	2.50	6.00
AI129		BT50 - EMH 2" - 6.00	2.000	3.75	6.00

* High balanced End Mill Holders on page 1356~1357.
* Set screws for End Mill Holders on page 1365.

END MILL HOLDER

BT



JIS B6339 -BT	Taper Accuracy AT3	G Value 6.3	RPM 15,000	Coolant System AD/B
---------------	--------------------	-------------	------------	---------------------

JIS B6339/MAS 403-BT

■ **STANDARD**

Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L
AH000B	40	BT40 AD/B - EMH 1/8 - 2.50	0.125	0.69	2.50
AH001B		BT40 AD/B - EMH 3/16 - 2.50	0.187	0.69	2.50
AH002B		BT40 AD/B - EMH 1/4 - 2.50	0.250	0.78	2.50
AH003B		BT40 AD/B - EMH 5/16 - 2.50	0.312	0.88	2.50
AH004B		BT40 AD/B - EMH 3/8 - 2.50	0.375	1.00	2.50
AH005B		BT40 AD/B - EMH 7/16 - 2.50	0.437	1.13	2.50
AH006B		BT40 AD/B - EMH 1/2 - 2.50	0.500	1.25	2.50
AH008B		BT40 AD/B - EMH 5/8 - 2.50	0.625	1.50	2.50
AH010B		BT40 AD/B - EMH 3/4 - 2.50	0.750	1.75	2.50
AH012B		BT40 AD/B - EMH 7/8 - 3.50	0.875	1.88	3.50
AH014B		BT40 AD/B - EMH 1" - 3.75	1.000	2.00	3.75
AH017B		BT40 AD/B - EMH 1 1/4 - 3.75	1.250	2.50	3.75
AH021B		BT40 AD/B - EMH 1 1/2 - 4.25	1.500	2.50	4.25

■ **EXTENDED**



Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L
AH104B	40	BT40 AD/B - EMH 3/8 - 4.00	0.375	1.00	4.00
AH106B		BT40 AD/B - EMH 1/2 - 4.00	0.500	1.25	4.00
AH108B		BT40 AD/B - EMH 5/8 - 4.00	0.625	1.50	4.00
AH110B		BT40 AD/B - EMH 3/4 - 4.00	0.750	1.75	4.00
AH114B		BT40 AD/B - EMH 1" - 5.00	1.000	2.00	5.00
AH117B		BT40 AD/B - EMH 1 1/4 - 5.00	1.250	2.50	5.00
AH121B		BT40 AD/B - EMH 1 1/2 - 6.00	1.500	2.50	6.00

* High balanced End Mill Holders are available on request.
* Set screws for End Mill Holders on page 1365.

END MILL HOLDER (COOLANT CHANNEL TYPE)

BT



JIS B6339 -BT	Taper Accuracy AT3	G Value 6.3	RPM 15,000	Coolant System AD/B+C
---------------	--------------------	-------------	------------	-----------------------

JIS B6339/MAS 403-BT


Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L
AH002C	40	BT40 AD/B - EMH 1/4C - 1.97	0.250	0.780	1.969
AH003C		BT40 AD/B - EMH 5/16C - 1.97	0.313	0.880	1.969
AH004C		BT40 AD/B - EMH 3/8C - 2.48	0.375	1.000	2.480
AH006C		BT40 AD/B - EMH 1/2C - 2.48	0.500	1.250	2.480
AH008C		BT40 AD/B - EMH 5/8C - 2.48	0.625	1.500	2.480
AH010C		BT40 AD/B - EMH 3/4C - 2.48	0.750	1.750	2.480
AH012C		BT40 AD/B - EMH 1C - 3.54	1.000	2.000	3.543
AH014C		BT40 AD/B - EMH 1 1/4C - 3.94	1.250	2.500	3.937

* High balanced End Mill Holders are available on request.
* Set screws for End Mill Holders on page 1365.

HIGH BALANCED END MILL HOLDER

BT



JIS B6339 -BT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Coolant System AD
---------------	--------------------	-------------	------------	-------------------

JIS B6339/MAS 403-BT

STUB

Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L
AH206B25	40	BT40 - EMH 1/2 - 1.25	0.500	1.25	1.25
AH208B25		BT40 - EMH 5/8 - 1.38	0.625	1.50	1.38
AH210B25		BT40 - EMH 3/4 - 1.44	0.750	1.75	1.44
AH214B25		BT40 - EMH 1" - 2.50	1.000	2.00	2.50
AH217B25		BT40 - EMH 1 1/4 - 2.50	1.250	2.50	2.50

STANDARD


Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L	
AH000B25	40	BT40 - EMH 1/8 - 2.50	0.125	0.69	2.50	
AH001B25		BT40 - EMH 3/16 - 2.50	0.187	0.69	2.50	
AH002B25		BT40 - EMH 1/4 - 2.50	0.250	0.78	2.50	
AH003B25		BT40 - EMH 5/16 - 2.50	0.312	0.88	2.50	
AH004B25		BT40 - EMH 3/8 - 2.50	0.375	1.00	2.50	
AH005B25		BT40 - EMH 7/16 - 2.50	0.437	1.13	2.50	
AH006B25		BT40 - EMH 1/2 - 2.50	0.500	1.25	2.50	
AH008B25		BT40 - EMH 5/8 - 2.50	0.625	1.50	2.50	
AH010B25		BT40 - EMH 3/4 - 2.50	0.750	1.75	2.50	
AH012B25		BT40 - EMH 7/8 - 3.50	0.875	1.88	3.50	
AH014B25		BT40 - EMH 1" - 3.75	1.000	2.00	3.75	
AH017B25		BT40 - EMH 1 1/4 - 3.75	1.250	2.50	3.75	
AH021B25		BT40 - EMH 1 1/2 - 4.25	1.500	2.50	4.25	
AI002B25		50	BT50 - EMH 1/4 - 3.00	0.250	0.78	3.00
AI004B25			BT50 - EMH 3/8 - 3.00	0.375	1.00	3.00
AI006B25			BT50 - EMH 1/2 - 3.00	0.500	1.25	3.00
AI008B25			BT50 - EMH 5/8 - 3.00	0.625	1.50	3.00
AI010B25			BT50 - EMH 3/4 - 3.00	0.750	1.75	3.00
AI012B25	BT50 - EMH 7/8 - 4.00		0.875	1.88	4.00	
AI014B25	BT50 - EMH 1" - 4.25		1.000	2.00	4.25	
AI017B25	BT50 - EMH 1 1/4 - 4.25		1.250	2.50	4.25	
AI021B25	BT50 - EMH 1 1/2 - 4.25		1.500	2.50	4.25	
AI029B25	BT50 - EMH 2" - 5.00		2.000	3.75	5.00	

* Set screws for End Mill Holders on page 1365.

HIGH BALANCED END MILL HOLDER

BT



JIS B6339 -BT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Coolant System AD
---------------	--------------------	-------------	------------	-------------------

JIS B6339/MAS 403 - BT

EXTENDED



Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L
AH104B25	40	BT40 - EMH 3/8 - 4.00	0.375	1.00	4.00
AH106B25		BT40 - EMH 1/2 - 4.00	0.500	1.25	4.00
AH108B25		BT40 - EMH 5/8 - 4.00	0.625	1.50	4.00
AH110B25		BT40 - EMH 3/4 - 4.00	0.750	1.75	4.00
AH114B25		BT40 - EMH 1" - 5.00	1.000	2.00	5.00
AH117B25		BT40 - EMH 1 1/4 - 5.00	1.250	2.50	5.00
AH121B25	BT40 - EMH 1 1/2 - 6.00	1.500	2.50	6.00	
AI104B25	50	BT50 - EMH 3/8 - 6.00	0.375	1.00	6.00
AI106B25		BT50 - EMH 1/2 - 6.00	0.500	1.25	6.00
AI108B25		BT50 - EMH 5/8 - 6.00	0.625	1.50	6.00
AI110B25		BT50 - EMH 3/4 - 6.00	0.750	1.75	6.00
AI112B25		BT50 - EMH 7/8 - 6.00	0.875	1.88	6.00
AI114B25		BT50 - EMH 1" - 6.00	1.000	2.00	6.00
AI117B25		BT50 - EMH 1 1/4 - 6.00	1.250	2.50	6.00
AI121B25		BT50 - EMH 1 1/2 - 6.00	1.500	2.50	6.00
AI129B25		BT50 - EMH 2" - 6.00	2.000	3.75	6.00

* Set screws for End Mill Holders on page 1365.

DUAL CONTACT SIDE LOCK ARBOR

CCT



CCT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Coolant System AD/B
-----	--------------------	-------------	------------	---------------------



CCT (CAT DUAL CONTACT)

Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L	FIG.	
AB020	40	CCT40 AD/B - SLA 1/4 - 2.36	0.250	0.780	2.362	1	
AB022		CCT40 AD/B - SLA 5/16 - 2.36	0.313	0.880	2.362	1	
AB024		CCT40 AD/B - SLA 3/8 - 2.36	0.375	1.000	2.362	1	
AB026		CCT40 AD/B - SLA 1/2 - 2.36	0.500	1.250	2.362	1	
AB028		CCT40 AD/B - SLA 5/8 - 3.54	0.625	1.500	3.543	1	
AB030		CCT40 AD/B - SLA 3/4 - 3.54	0.750	1.750	3.543	1	
AB032		CCT40 AD/B - SLA 1" - 3.54	1.000	2.000	3.543	2	
AB034		CCT40 AD/B - SLA 1 1/4 - 3.54	1.250	2.500	3.543	2	
AC020		50	CCT50 AD/B - SLA 1/4 - 3.54	0.250	0.780	3.543	1
AC022			CCT50 AD/B - SLA 5/16 - 3.54	0.313	0.880	3.543	1
AC024	CCT50 AD/B - SLA 3/8 - 3.54		0.375	1.000	3.543	1	
AC026	CCT50 AD/B - SLA 1/2 - 3.54		0.500	1.250	3.543	1	
AC028	CCT50 AD/B - SLA 5/8 - 4.13		0.625	1.500	4.134	1	
AC030	CCT50 AD/B - SLA 3/4 - 4.13		0.750	1.750	4.134	1	
AC032	CCT50 AD/B - SLA 1" - 4.13		1.000	2.000	4.134	2	
AC034	CCT50 AD/B - SLA 1 1/4 - 4.13		1.250	2.500	4.134	2	

* Set screws for End Mill Holders on page 1365.

DUAL CONTACT SIDE LOCK ARBOR CBT




CBT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Coolant System AD
-----	------------------------------	-----------------------	----------------------	-----------------------------

CBT (BT DUAL CONTACT)

EDP No.	TAPER No.	MODEL No.	d	D	L	FIG.
AD020	30	CBT30 - SLA 1/4 - 2.36	0.250	0.780	2.362	1
AD022		CBT30 - SLA 5/16 - 2.36	0.313	0.880	2.362	1
AD024		CBT30 - SLA 3/8 - 2.36	0.375	1.000	2.362	1
AD026		CBT30 - SLA 1/2 - 2.36	0.500	1.250	2.362	1
AD028		CBT30 - SLA 5/8 - 2.95	0.625	1.500	2.953	1
AD030		CBT30 - SLA 3/4 - 2.95	0.750	1.750	2.953	2
AD032	CBT30 - SLA 1" - 2.95	1.000	2.000	2.953	2	
AE020	40	CBT40 - SLA 1/4 - 2.36	0.250	0.780	2.362	1
AE022		CBT40 - SLA 5/16 - 2.36	0.313	0.880	2.362	1
AE024		CBT40 - SLA 3/8 - 2.36	0.375	1.000	2.362	1
AE026		CBT40 - SLA 1/2 - 2.36	0.500	1.250	2.362	1
AE028		CBT40 - SLA 5/8 - 3.54	0.625	1.500	3.543	1
AE030		CBT40 - SLA 3/4 - 3.54	0.750	1.750	3.543	1
AE032		CBT40 - SLA 1" - 3.54	1.000	2.000	3.543	2
AE034		CBT40 - SLA 1 1/4 - 3.54	1.250	2.500	3.543	2

* Set screws for End Mill Holders on page 1365.

DUAL CONTACT END MILL HOLDER (COOLANT CHANNEL TYPE) HSK



DIN 69893 - HSK	Taper Accuracy -	G Value 2.5	RPM 25,000	Coolant System AD+C
-----------------	----------------------------	-----------------------	----------------------	-------------------------------


DIN 69893/ISO 12164-1-HSK FORM A

EDP No.	TAPER No.	MODEL No.	d	D	L	
AQ020C	63A	HSK63A - EMH 1/4C - 2.56	0.250	0.780	2.559	
AQ022C		HSK63A - EMH 5/16C - 2.56	0.313	0.880	2.559	
AQ024C		HSK63A - EMH 3/8C - 2.56	0.375	1.000	2.559	
AQ026C		HSK63A - EMH 1/2C - 3.15	0.500	1.250	3.150	
AQ028C		HSK63A - EMH 5/8C - 3.15	0.625	1.500	3.150	
AQ030C		HSK63A - EMH 3/4C - 3.15	0.750	1.750	3.150	
AQ032C		HSK63A - EMH 1C - 4.33	1.000	2.000	4.331	
AQ034C		HSK63A - EMH 1 1/4C - 4.33	1.250	2.500	4.331	
AR020C		100A	HSK100A - EMH 1/4C - 3.15	0.250	0.780	3.150
AR022C			HSK100A - EMH 5/16C - 3.15	0.313	0.880	3.150
AR024C	HSK100A - EMH 3/8C - 3.15		0.375	1.000	3.150	
AR026C	HSK100A - EMH 1/2C - 3.15		0.500	1.250	3.150	
AR028C	HSK100A - EMH 5/8C - 3.94		0.625	1.500	3.937	
AR030C	HSK100A - EMH 3/4C - 3.94		0.750	1.750	3.937	
AR032C	HSK100A - EMH 1C - 3.94		1.000	2.000	3.937	
AR034C	HSK100A - EMH 1 1/4C - 3.94		1.250	2.500	3.937	

END MILL HOLDER SCREWS



HEXAGON SOCKET SET SCREW (FLAT TYPE)

EDP No.	SCREW	END MILL Dia.
ZZ000	UNC #8 - 32	1/8
ZZ001	UNF #10 - 32	3/16
ZZ002	UNF 1/4 - 28	1/4
ZZ003	UNF 5/16 - 24	5/16
ZZ004	UNF 3/8 - 24	3/8
ZZ005	UNF 3/8 - 24	7/16
ZZ006	UNF 7/16 - 20	1/2
ZZ007	UNF 1/2 - 20	5/8
ZZ008	UNF 5/8 - 18	3/4
ZZ009	UNF 5/8 - 18	7/8
ZZ010	UNF 3/4 - 16	1"
ZZ011	UNF 3/4 - 16	1 1/4
ZZ012	UNF 3/4 - 16	1 1/2
ZZ013	UN 1" - 14	2"



ER COLLET CHUCK

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 6.3	RPM 15,000	Coolant System AD/B
------------------	--------------------	-------------	------------	---------------------

ASME B5.50-2009-CAT

■ **STUB**

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BK232B	40	CAT40 AD/B - ER 20 - 2.55	0.039 - 0.511	1.26	2.55	ER20
BK233B		CAT40 AD/B - ER 25 - 2.50	0.039 - 0.629	1.65	2.50	ER25
BK234B		CAT40 AD/B - ER 32 - 2.70	0.078 - 0.787	1.88	2.70	ER32

■ **STANDARD**

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BK030B	40	CAT40 AD/B - ER 11 - 3.00	0.019 - 0.275	0.75	3.00	ER11
BK031B		CAT40 AD/B - ER 16 - 3.00	0.019 - 0.393	1.10	3.00	ER16
BK032B		CAT40 AD/B - ER 20 - 4.00	0.039 - 0.511	1.33	4.00	ER20
BK133B		CAT40 AD/B - ER 25 - 4.00	0.039 - 0.629	1.65	4.00	ER25
BK134B		CAT40 AD/B - ER 32 - 4.00	0.078 - 0.787	1.96	4.00	ER32
BK136B	50	CAT40 AD/B - ER 40 - 4.00	0.118 - 1.024	2.48	4.00	ER40
BL031B		CAT50 AD/B - ER 16 - 4.00	0.031 - 0.406	1.10	4.00	ER16
BL032B		CAT50 AD/B - ER 20 - 4.00	0.039 - 0.511	1.33	4.00	ER20
BL033B		CAT50 AD/B - ER 25 - 4.00	0.039 - 0.629	1.65	4.00	ER25
BL034B		CAT50 AD/B - ER 32 - 4.00	0.078 - 0.787	1.96	4.00	ER32
BL036B		CAT50 AD/B - ER 40 - 4.00	0.118 - 1.024	2.48	4.00	ER40

■ **EXTENDED**

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BK331B	40	CAT40 AD/B - ER 16 - 6.00	0.019 - 0.393	1.10	6.00	ER16
BK332B		CAT40 AD/B - ER 20 - 6.00	0.039 - 0.511	1.33	6.00	ER20
BK333B		CAT40 AD/B - ER 25 - 6.00	0.039 - 0.629	1.65	6.00	ER25
BK334B		CAT40 AD/B - ER 32 - 6.00	0.078 - 0.787	1.96	6.00	ER32
BL331B	50	CAT50 AD/B - ER 16 - 6.00	0.031 - 0.406	1.10	6.00	ER16
BL332B		CAT50 AD/B - ER 20 - 6.00	0.039 - 0.511	1.33	6.00	ER20
BL333B		CAT50 AD/B - ER 25 - 6.00	0.039 - 0.629	1.65	6.00	ER25
BL334B		CAT50 AD/B - ER 32 - 6.00	0.078 - 0.787	1.96	6.00	ER32

■ **EXTRA EXTENDED**



Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BK432B	40	CAT40 AD/B - ER 20 - 8.00	0.039 - 0.511	1.33	8.00	ER20

* High balanced ER Collet Chucks are available on request.
 * Supplied without wrench.
 * ER collets on page 1375~1383 and Nut / Wrench / Stop Screw on page 1374.

HIGH BALANCED ER COLLET CHUCK

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Coolant System AD
------------------	--------------------	-------------	------------	-------------------

ASME B5.50-2009-CAT

■ **STUB**

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BK232B25	40	CAT40 - ER 20 - 2.55	0.039 - 0.511	1.339	2.55	ER20
BK233B25		CAT40 - ER 25 - 2.50	0.039 - 0.629	1.654	2.50	ER25
BK234B25		CAT40 - ER 32 - 2.70	0.078 - 0.787	1.969	2.70	ER32

■ **STANDARD**

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BK030B25	40	CAT40 - ER 11 - 3.00	0.019 - 0.275	0.748	3.00	ER11
BK031B25		CAT40 - ER 16 - 2.88	0.019 - 0.393	1.102	2.88	ER16
BK032B25		CAT40 - ER 20 - 4.00	0.039 - 0.511	1.339	4.00	ER20
BK133B25		CAT40 - ER 25 - 4.00	0.039 - 0.629	1.654	4.00	ER25
BK134B25		CAT40 - ER 32 - 4.00	0.078 - 0.787	1.969	4.00	ER32
BL031B25	50	CAT50 - ER 16 - 4.00	1/32 - 13/32	1.102	4.88	ER16
BL032B25		CAT50 - ER 20 - 4.00	0.039 - 0.511	1.339	4.00	ER20
BL033B25		CAT50 - ER 25 - 4.00	0.039 - 0.629	1.654	4.00	ER25
BL034B25		CAT50 - ER 32 - 4.00	0.078 - 0.787	1.969	4.00	ER32

■ **EXTENDED**

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BK331B25	40	CAT40 - ER 16 - 4.88	0.019 - 0.393	1.102	4.88	ER16
BK332B25		CAT40 - ER 20 - 6.00	0.039 - 0.511	1.339	6.00	ER20
BK333B25		CAT40 - ER 25 - 6.00	0.039 - 0.629	1.654	6.00	ER25
BK334B25		CAT40 - ER 32 - 6.00	0.078 - 0.787	1.969	6.00	ER32
BL331B25	50	CAT50 - ER 16 - 6.88	1/32 - 13/32	1.102	6.88	ER16
BL332B25		CAT50 - ER 20 - 6.00	0.039 - 0.511	1.339	6.00	ER20
BL333B25		CAT50 - ER 25 - 6.00	0.039 - 0.629	1.654	6.00	ER25
BL334B25		CAT50 - ER 32 - 6.00	0.078 - 0.787	1.969	6.00	ER32

■ **EXTRA EXTENDED**



Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BK432B25	40	CAT40 - ER 20 - 8.00	0.039 - 0.511	1.339	8.00	ER20

* Supplied without wrench.
 * ER collets on page 1375~1383 and Nut / Wrench / Stop Screw on page 1374.

ER COLLET CHUCK

BT



JIS B6339 -BT	Taper Accuracy AT3	G Value 6.3	RPM 15,000	Coolant System AD/B
---------------	--------------------	-------------	------------	---------------------

JIS B6339/MAS 403-BT

■ **STUB**

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BH232B	40	BT40 AD/B - ER 20 - 2.20	0.039 - 0.511	1.33	2.20	ER20
BH233B		BT40 AD/B - ER 25 - 2.50	0.039 - 0.629	1.65	2.50	ER25
BH234B		BT40 AD/B - ER 32 - 2.40	0.078 - 0.787	1.96	2.40	ER32

■ **STANDARD**

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BH030B	40	BT40 AD/B - ER 11 - 3.00	0.019 - 0.275	0.75	3.00	ER11
BH031B		BT40 AD/B - ER 16 - 3.00	0.019 - 0.393	1.10	3.00	ER16
BH032B		BT40 AD/B - ER 20 - 4.00	0.039 - 0.511	1.33	4.00	ER20
BH133B		BT40 AD/B - ER 25 - 4.00	0.039 - 0.629	1.65	4.00	ER25
BH134B		BT40 AD/B - ER 32 - 4.00	0.078 - 0.787	1.96	4.00	ER32
BH136B		BT40 AD/B - ER 40 - 4.00	0.118 - 1.024	2.48	4.00	ER40

■ **EXTENDED**

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BH331B	40	BT40 AD/B - ER 16 - 6.00	0.019 - 0.393	1.10	6.00	ER16
BH332B		BT40 AD/B - ER 20 - 6.00	0.039 - 0.511	1.33	6.00	ER20
BH333B		BT40 AD/B - ER 25 - 6.00	0.039 - 0.629	1.65	6.00	ER25
BH334B		BT40 AD/B - ER 32 - 6.00	0.078 - 0.787	1.96	6.00	ER32

■ **EXTRA EXTENDED**



Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BH432B	40	BT40 AD/B - ER 20 - 8.00	0.039 - 0.511	1.33	8.00	ER20

* High balanced ER Collet Chucks are available on request.
 * Supplied without wrench.
 * ER collets on page 1375~1383 and Nut / Wrench / Stop Screw on page 1374.

ER COLLET CHUCK

BT



JIS B6339 -BT	Taper Accuracy AT3	G Value 6.3	RPM 15,000	Coolant System AD
---------------	--------------------	-------------	------------	-------------------

JIS B6339/MAS 403-BT

■ **STANDARD**

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BI031	50	BT50 - ER 16 - 4.88	0.019 - 0.393	1.102	4.88	ER16
BI032		BT50 - ER 20 - 2.63	0.039 - 0.511	1.339	2.63	ER20
BI033		BT50 - ER 25 - 2.63	0.039 - 0.629	1.654	2.63	ER25
BI034		BT50 - ER 32 - 4.00	0.078 - 0.787	1.969	4.00	ER32

■ **EXTENDED**


Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BI331	50	BT50 - ER 16 - 6.00	0.019 - 0.393	1.102	6.00	ER16
BI332		BT50 - ER 20 - 6.00	0.039 - 0.511	1.339	6.00	ER20
BI333		BT50 - ER 25 - 6.00	0.039 - 0.629	1.654	6.00	ER25
BI334		BT50 - ER 32 - 6.00	0.078 - 0.787	1.969	6.00	ER32

* High balanced ER Collet Chucks are on page 72.
 * Supplied without wrench.
 * ER collets on page 1375~1383 and Nut / Wrench / Stop Screw on page 1374.

HIGH BALANCED ER COLLET CHUCK

BT



JIS B6339 -BT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Coolant System AD
---------------	-----------------------	----------------	---------------	----------------------

JIS B6339/MAS 403-BT

■ **STUB**

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BH232B25	40	BT40 - ER 20 - 2.20	0.039 - 0.511	1.339	2.20	ER20
BH233B25		BT40 - ER 25 - 2.50	0.039 - 0.629	1.654	2.50	ER25
BH234B25		BT40 - ER 32 - 2.40	0.078 - 0.787	1.969	2.40	ER32

■ **STANDARD**

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BH030B25	40	BT40 - ER 11 - 3.00	0.019 - 0.275	0.748	3.00	ER11
BH031B25		BT40 - ER 16 - 2.88	0.019 - 0.393	1.102	2.88	ER16
BH032B25		BT40 - ER 20 - 4.00	0.039 - 0.511	1.339	4.00	ER20
BH133B25		BT40 - ER 25 - 4.00	0.039 - 0.629	1.654	4.00	ER25
BH134B25	50	BT40 - ER 32 - 4.00	0.078 - 0.787	1.969	4.00	ER32
BI031B25		BT50 - ER 16 - 4.88	1/32 - 13/32	1.102	4.88	ER16
BI032B25		BT50 - ER 20 - 2.63	0.039 - 0.511	1.339	2.63	ER20
BI033B25		BT50 - ER 25 - 2.63	0.039 - 0.629	1.654	2.63	ER25
BI034B25		BT50 - ER 32 - 4.00	0.078 - 0.787	1.969	4.00	ER32

■ **EXTENDED**

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BH331B25	40	BT40 - ER 16 - 4.88	0.019 - 0.393	1.102	4.88	ER16
BH332B25		BT40 - ER 20 - 6.00	0.039 - 0.511	1.339	6.00	ER20
BH333B25		BT40 - ER 25 - 6.00	0.039 - 0.629	1.654	6.00	ER25
BH334B25		BT40 - ER 32 - 6.00	0.078 - 0.787	1.969	6.00	ER32
BI331B25	50	BT50 - ER 16 - 6.00	1/32 - 13/32	1.102	6.00	ER16
BI332B25		BT50 - ER 20 - 6.00	0.039 - 0.511	1.339	6.00	ER20
BI333B25		BT50 - ER 25 - 6.00	0.039 - 0.629	1.654	6.00	ER25
BI334B25		BT50 - ER 32 - 6.00	0.078 - 0.787	1.969	6.00	ER32

■ **EXTRA EXTENDED**

Unit : inch


EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BH432B25	40	BT40 - ER 20 - 8.00	0.039 - 0.511	1.339	8.00	ER20

* Supplied without wrench.

* ER collets on page 1375~1383 and Nut / Wrench / Stop Screw on page 1374.

DUAL CONTACT ER COLLET CHUCK

HSK



DIN 69893 -HSK	Taper Accuracy -	G Value 2.5	RPM 25,000	Coolant System AD
----------------	---------------------	----------------	---------------	----------------------

DIN 69893/ISO 12164-1-HSK FORM A

Unit : inch


EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	L	COLLET SERIES
BQ010	63A	HSK63A - ER 16 - 3.94	0.019 - 0.393	1.10	3.94	ER16
BQ012		HSK63A - ER 20 - 3.94	0.039 - 0.511	1.33	3.94	ER20
BQ014		HSK63A - ER 25 - 3.94	0.039 - 0.629	1.65	3.94	ER25
BQ016		HSK63A - ER 32 - 3.94	0.078 - 0.787	1.96	3.94	ER32
BQ018	100A	HSK63A - ER 40 - 4.72	0.118 - 1.18	2.48	4.72	ER40
BR010		HSK100A - ER 16 - 3.94	0.019 - 0.393	1.10	3.94	ER16
BR012		HSK100A - ER 20 - 3.94	0.039 - 0.511	1.33	3.94	ER20
BR014		HSK100A - ER 25 - 3.94	0.039 - 0.629	1.65	3.94	ER25
BR016		HSK100A - ER 32 - 3.94	0.078 - 0.787	1.96	3.94	ER32
BR018		HSK100A - ER 40 - 4.72	0.118 - 1.18	2.48	4.72	ER40

* Supplied without wrench.

* ER collets on page 1375~1383 and Nut / Wrench / Stop Screw on page 1374.

ER COLLET CHUCK (SHORT)

CAT/BT



ASME B5.50-2009-CAT

Unit : inch

EDP No.	TAPER No.	MODEL No.	L	ER WRENCH
BK020SHT	40	CAT40 - ER32 - SHORT	1.063	32 (for Hex. Nut)
BLO20SHT	50	CAT50 - ER32 - SHORT	1.063	32 (for Hex. Nut)


JIS B6339/MAS 403-BT

Unit : inch

EDP No.	TAPER No.	MODEL No.	L	ER WRENCH
BHO20SHT	40	BT40 - ER32 - SHORT	1.378	32 (for Hex. Nut)

TENSION ER COLLET CHUCK (For TAPPING)

K



STRAIGHT-K

Unit : inch


EDP No.	TAPER No.	MODEL No.	D1	D2	L
BS110	K	K1 - ERT 16 - 2.76	1.000	1.102	2.756
BS111		K1 - ERT 20 - 3.15	1.000	1.339	3.150
BS112		K1 1/4 - ERT 16 - 2.76	1.250	1.102	2.756
BS113		K1 1/4 - ERT 20 - 3.15	1.250	1.339	3.150
BS114		K1 1/4 - ERT 25 - 3.15	1.250	1.654	3.150
BS115		K1 1/4 - ERT 32 - 3.15	1.250	1.969	3.150

* Supplied without wrench.

* ER collets on page 1375~1383 and Nut / Wrench / Stop Screw on page 1374.

NC ER COLLET CHUCK (For CNC LATHE)

NC



NC

Unit : inch

EDP No.	TAPER No.	MODEL No.	D1	D2	L1	L2
BN110	NC	NC 1 - ER11	1.000	0.748	2.559	1.260
BN111		NC 1 - ER16	1.000	1.102	2.559	1.260
BN112		NC 1 - ER20	1.000	1.339	2.559	1.260
BN113		NC 1 - ER25	1.000	1.654	2.559	1.260
BN114		NC 1 1/4 - ER20	1.250	1.339	2.756	1.260
BN115		NC 1 1/4 - ER25	1.250	1.654	2.756	1.496
BN116		NC 1 1/4 - ER32	1.250	1.969	2.756	1.496
BN117		NC 1 1/4 - ER40	1.250	2.480	2.953	1.496
BN118		NC 1 1/2 - ER25	1.500	1.654	2.953	2.087
BN119		NC 1 1/2 - ER32	1.500	1.969	2.953	2.087
BN120		NC 1 1/2 - ER40	1.500	2.480	2.953	2.087

* Supplied without wrench.

* ER collets on page 1375~1383 and Nut / Wrench / Stop Screw on page 1374.

ER NUT

FIG.1

EDP No.	SERIES	TYPE
ZZ061	ER11 - NUT	FIG.1
ZZ063	ER16 - NUT	FIG.1
ZZ066	ER20 - NUT	FIG.1


FIG.2

EDP No.	SERIES	TYPE
ZZ069	ER25 - NUT	FIG.2
ZZ072	ER32 - NUT	FIG.2
ZZ077	ER40 - NUT	FIG.2

FIG.1



FIG.2



ER WRENCH

FIG.1

EDP No.	SERIES	TYPE
ZZ062	ER11	FIG.1
ZZ064	ER16	FIG.1
ZZ067	ER20	FIG.1

EDP No.	SERIES	TYPE
ZZ070	ER25	FIG.2
ZZ073	ER32	FIG.2
ZZ076	ER40	FIG.2



FIG.1



FIG.2

* Design and shape could be changed without prior notice.

ER STOP SCREW

FIG.1




FIG.2





FIG.1

EDP No.	SERIES	L	d	D	TYPE
ZZ060	ER11	0.50	0.25	UN 5/16 - 18	FIG.1

FIG.2

EDP No.	SERIES	L	d	D	TYPE
ZZ065	ER16	0.50	0.35	UN 7/16 - 16	FIG.2
ZZ068	ER20	0.50	0.48	UN 9/16 - 16	FIG.2
ZZ071	ER25	0.50	0.60	UN 11/16 - 16	FIG.2
ZZ074	ER32	0.50	0.79	UN 7/8 - 16	FIG.2

ER COLLET (INCH TYPE)



ER 11		ER 16		ER 20		ER 25		ER 32		ER 40	
EDP No.	CLAMPING CAPACITY	EDP No.	CLAMPING RANGE	EDP No.	CLAMPING RANGE	EDP No.	CLAMPING RANGE	EDP No.	CLAMPING RANGE	EDP No.	CLAMPING RANGE
110116	1/16	160116	1/16	200116	1/16	250116	1/16	320332	3/32	400108	1/8
110332	3/32	160332	3/32	200332	3/32	250332	3/32	320108	1/8	400532	5/32
110108	1/8	160108	1/8	200108	1/8	250108	1/8	320532	5/32	400316	3/16
110532	5/32	160532	5/32	200532	5/32	250532	5/32	320316	3/16	400732	7/32
110316	3/16	160316	3/16	200316	3/16	250316	3/16	320732	7/32	400104	1/4
110732	7/32	160732	7/32	200732	7/32	250732	7/32	320104	1/4	400932	9/32
110104	1/4	160104	1/4	200104	1/4	250104	1/4	320932	9/32	400516	5/16
		160932	9/32	200932	9/32	250932	9/32	320516	5/16	401132	11/32
		160516	5/16	200516	5/16	250516	5/16	321132	11/32	400308	3/8
		161132	11/32	201132	11/32	251132	11/32	320308	3/8	401332	13/32
		160308	3/8	200308	3/8	250308	3/8	321332	13/32	400716	7/16
		161332	13/32	201332	13/32	251332	13/32	320716	7/16	401532	15/32
				200716	7/16	250716	7/16	321532	15/32	400102	1/2
				201532	15/32	251532	15/32	320102	1/2	401732	17/32
				200102	1/2	250102	1/2	321732	17/32	400916	9/16
								320916	9/16	401932	19/32
								321932	19/32	400508	5/8
								320508	5/8	402132	21/32
								322132	21/32	401116	11/16
								321116	11/16	402332	23/32
								322332	23/32	400304	3/4
								320304	3/4	402532	25/32
										401316	13/16
										402732	27/32
										400708	7/8
										402932	29/32
										401516	15/16
										403132	31/32
										401000	1
ER11S07	STANDARD SET	ER16S12	STANDARD SET	ER20S15	STANDARD SET	ER25S19	STANDARD SET	ER32S22	STANDARD SET	ER40S29	STANDARD SET
Ø1/16" to 1/4"		Ø1/16" to 13/32"		Ø1/16" to 1/2"		Ø1/16" to 5/8"		Ø3/32" to 3/4"		Ø1/8" to 1"	
7pcs		12pcs		15pcs		19pcs		22pcs		29pcs	

ER COLLET (Metric Type)



Unit : mm

ER 8		ER 11		ER 16		ER 20	
EDP No.	CLAMPING RANGE	EDP No.	CLAMPING RANGE	EDP No.	CLAMPING RANGE	EDP No.	CLAMPING RANGE
208010	1.0 - 0.5	211010	1.0 - 0.5	216010	1.0 - 0.5	220010	1.0 - 0.5
208015	1.5 - 1.0	211015	1.5 - 1.0	216015	1.5 - 1.0	220015	1.5 - 1.0
208020	2.0 - 1.5	211020	2.0 - 1.5	216020	2.0 - 1.0	220020	2.0 - 1.0
208025	2.5 - 2.0	211025	2.5 - 2.0	216025	2.5 - 2.0	220025	2.5 - 2.0
208030	3.0 - 2.5	211030	3.0 - 2.5	216030	3.0 - 2.0	220030	3.0 - 2.0
208035	3.5 - 3.0	211035	3.5 - 3.0	216040	4.0 - 3.0	220040	4.0 - 3.0
208040	4.0 - 3.5	211040	4.0 - 3.5	216050	5.0 - 4.0	220050	5.0 - 4.0
208045	4.5 - 4.0	211045	4.5 - 4.0	216060	6.0 - 5.0	220060	6.0 - 5.0
208050	5.0 - 4.5	211050	5.0 - 4.5	216070	7.0 - 6.0	220070	7.0 - 6.0
		211055	5.5 - 5.0	216080	8.0 - 7.0	220080	8.0 - 7.0
		211060	6.0 - 5.5	216090	9.0 - 8.0	220090	9.0 - 8.0
		211065	6.5 - 6.0	216100	10.0 - 9.0	220100	10.0 - 9.0
		211070	7.0 - 6.5			220110	11.0 - 10.0
						220120	12.0 - 11.0
						220130	13.0 - 12.0
208000	STANDARD SET Ø1.0 - 5.0mm 9pcs	211000	STANDARD SET Ø1.0 - 7.0mm 13pcs	216000	STANDARD SET Ø1.0 - 10.0mm 10pcs	220000	STANDARD SET Ø2.0 - 13.0mm 12pcs
108110	WOODEN TRAY ZWT 8	011110	WOODEN TRAY ZWT 11	016110	WOODEN TRAY ZWT 16	020110	WOODEN TRAY ZWT 20

ER COLLET (Metric Type)




Unit : mm

ER 25		ER 32		ER 40		ER 50	
EDP No.	CLAMPING RANGE	EDP No.	CLAMPING RANGE	EDP No.	CLAMPING RANGE	EDP No.	CLAMPING RANGE
225010	1.0 - 1.5	232020	2.0 - 1.0	240030	3.0 - 2.0	250060	6.0 - 4.0
225015	1.5 - 1.0	232025	2.5 - 2.0	240040	4.0 - 3.0	250080	8.0 - 6.0
225020	2.0 - 1.0	232030	3.0 - 2.0	240050	5.0 - 4.0	250100	10.0 - 8.0
225025	2.5 - 2.0	232040	4.0 - 3.0	240060	6.0 - 5.0	250120	12.0 - 10.0
225030	3.0 - 2.0	232050	5.0 - 4.0	240070	7.0 - 6.0	250140	14.0 - 12.0
225040	4.0 - 3.0	232060	6.0 - 5.0	240080	8.0 - 7.0	250160	16.0 - 14.0
225050	5.0 - 4.0	232070	7.0 - 6.0	240090	9.0 - 8.0	250180	18.0 - 16.0
225060	6.0 - 5.0	232080	8.0 - 7.0	240100	10.0 - 9.0	250200	20.0 - 18.0
225070	7.0 - 6.0	232090	9.0 - 8.0	240110	11.0 - 10.0	250220	22.0 - 20.0
225080	8.0 - 7.0	232100	10.0 - 9.0	240120	12.0 - 11.0	250240	24.0 - 22.0
225090	9.0 - 8.0	232110	11.0 - 10.0	240130	13.0 - 12.0	250250	25.0 - 23.0
225100	10.0 - 9.0	232120	12.0 - 11.0	240140	14.0 - 13.0	250260	26.0 - 24.0
225110	11.0 - 10.0	232130	13.0 - 12.0	240150	15.0 - 14.0	250280	28.0 - 26.0
225120	12.0 - 11.0	232140	14.0 - 13.0	240160	16.0 - 15.0	250300	30.0 - 28.0
225130	13.0 - 12.0	232150	15.0 - 14.0	240170	17.0 - 16.0	250320	32.0 - 30.0
225140	14.0 - 13.0	232160	16.0 - 15.0	240180	18.0 - 17.0	250340	34.0 - 32.0
225150	15.0 - 14.0	232170	17.0 - 16.0	240190	19.0 - 18.0		
225160	16.0 - 15.0	232180	18.0 - 17.0	240200	20.0 - 19.0		
		232190	19.0 - 18.0	240210	21.0 - 20.0		
		232200	20.0 - 19.0	240220	22.0 - 21.0		
				240230	23.0 - 22.0		
				240240	24.0 - 23.0		
				240250	25.0 - 24.0		
				240260	26.0 - 25.0		
				240270	27.0 - 26.0		
				240280	28.0 - 27.0		
				240290	29.0 - 28.0		
				240300	30.0 - 29.0		
225000	STANDARD SET Ø2.0 - 16.0mm 15pcs	232000	STANDARD SET Ø3.0 - 20.0mm 18pcs	240000	STANDARD SET Ø4.0 - 26.0mm 23pcs	250000	STANDARD SET Ø12.0 - 34.0mm 12pcs
025110	WOODEN TRAY ZWT 25	032110	WOODEN TRAY ZWT 32	040110	WOODEN TRAY ZWT 40	050110	WOODEN TRAY ZWT 50

TAP ER COLLET (Inch Type : ANSI)

CAT/BT



Below standard Tap ER Collet conforms to ANSI (For PIPE TAPS)

Unit : inch


RD 16TCP						RD 20TCP						RD 25TCP					
EDP No.	TAP		D(Φ)	W(□)	L	EDP No.	TAP		D(Φ)	W(□)	L	EDP No.	TAP		D(Φ)	W(□)	L
	Inch	Metric					Inch	Metric					Inch	Metric			
16TP3123	1/8(SS)	-	0.312	0.234	0.709	20TP3123	1/8(SS)	-	0.312	0.234	0.787	25TP3123	1/8(SS)	-	0.312	0.234	0.787
16TP4332	1/8(LS)	-	0.437	0.328	0.709	20TP4332	1/8(LS)	-	0.437	0.328	0.787	25TP4332	1/8(LS)	-	0.437	0.328	0.787
												25TP5642	1/4	-	0.562	0.420	0.787

RD 32TCP						RD 40TCP					
EDP No.	TAP		D(Φ)	W(□)	L	EDP No.	TAP		D(Φ)	W(□)	L
	Inch	Metric					Inch	Metric			
32TP3123	1/8(SS)	-	0.312	0.234	0.787	40TP3123	1/8(SS)	-	0.312	0.234	0.787
32TP4332	1/8(LS)	-	0.437	0.328	0.787	40TP4332	1/8(LS)	-	0.437	0.328	0.787
32TP5642	1/4	-	0.562	0.420	0.787	40TP5642	1/4	-	0.562	0.420	0.787
						40TP7053	3/8	-	0.700	0.530	0.866
						40TP6851	1/2	-	0.687	0.515	0.866
						40TP9067	3/4	-	0.906	0.679	0.945

* SS : Short Series / LS : Long Series

TAP ER COLLET (Metric Type : JIS)

NC




Below standard Tap ER Collet conforms to JIS

Unit : mm

RDT 16					RDT 20					RDT 25					RDT 32					RDT 40				
EDP No.	TAP	D(Φ)	W(□)	L	EDP No.	TAP	D(Φ)	W(□)	L	EDP No.	TAP	D(Φ)	W(□)	L	EDP No.	TAP	D(Φ)	W(□)	L	EDP No.	TAP	D(Φ)	W(□)	L
16T40032	M3	4.0	3.2	15	20T50040	M4	5.0	4.0	15	25T50032	M4	5.0	4.0	15	32T50045	M5	5.5	4.5	15	40T70055	M10	7.0	5.5	20
16T50040	M4	5.0	4.0	15	20T55045	M5	5.5	4.5	15	25T55045	M5	5.5	4.5	15	32T55045	M5	5.5	4.5	15	40T85065	M12	8.5	6.5	25
16T55045	M5	5.5	4.5	15	20T60045	M6	6.0	4.5	15	25T60045	M6	6.0	4.5	15	32T60045	M6	6.0	4.5	15	40T10580	M14	10.5	8.0	25
16T60045	M6	6.0	4.5	15	20T62050	M8	6.2	5.0	20	25T62050	M8	6.2	5.0	20	32T62050	M8	6.2	5.0	20	40T12510	M16	12.5	10.0	25
16T62050	M8	6.2	5.0	15	20T70055	M10	7.0	5.5	20	25T70055	M10	7.0	5.5	20	32T70055	M10	7.0	5.5	20	40T15012	M20	15.0	12.0	28
										25T85065	M12	8.5	6.5	20	32T85065	M12	8.5	6.5	20	40T17013	M22	17.0	13.0	28
										25T10580	M14	10.5	8.0	20	32T10560	M14	10.5	8.0	20	40T19015	M24	19.0	15.0	28

TAP ER COLLET (Metric Type : DIN)




Below standard Tap ER Collet conforms to DIN

Unit : mm

DIN STANDARD			RD 11TCD			RD 16TCD			RD 20TCD		
DIN 374/376	DIN 352/2181	DIN 371	EDP No.	D(∅)	W(□)	EDP No.	D(∅)	W(□)	EDP No.	D(∅)	W(□)
M5	M3	M3	11TD3527	3.5	2.7	16TD3527	3.5	2.7	20TD3527	3.5	2.7
M5.5	M3.5	M3.5	11TD4030	4.0	3.0	16TD4030	4.0	3.0	20TD4030	4.0	3.0
M6	M4	M4	11TD4534	4.5	3.4	16TD4534	4.5	3.4	20TD4534	4.5	3.4
M5	-	-	11TD5040	5.0	4.0	16TD5040	5.0	4.0	20TD5040	5.0	4.0
M7	-	-	11TD5543	5.5	4.3	16TD5543	5.5	4.3	20TD5543	5.5	4.3
M8	M4.5-M8	M4.5-M8	11TD6049	6.0	4.9	16TD6049	6.0	4.9	20TD6049	6.0	4.9
M9+M10	M9+M10	M7				16TD7055	7.0	5.5	20TD7055	7.0	5.5
M11	M11	M8							20TD8062	8.0	6.2
M12	M12	M9							20TD9070	9.0	7.0
-	-	M10							20TD10080	10.0	8.0
M13+M14	M13+M14	-									
M15-M17	M15-M17	-									
M18+M19	M18+M19	-									
M20+M21	M20+M21	-									
M22-M26	M22-M26	-									
M27+M28	M27+M28	-									
M29-M32	M29-M32	-									
M33	M33	-									
M34-M38	M34-M38	-									
M39-M42	M39-M42	-									

TAP ER COLLET (Metric Type : DIN)




Below standard Tap ER Collet conforms to DIN

Unit : mm

RD 25TCD			RD 32TCD			RD 40TCD			RD 50TCD		
EDP No.	D(∅)	W(□)	EDP No.	D(∅)	W(□)	EDP No.	D(∅)	W(□)	EDP No.	D(∅)	W(□)
25TD3527	3.5	2.7	32TD3527	3.5	2.7	40TD3527	3.5	2.7			
25TD4030	4.0	3.0	32TD4030	4.0	3.0	40TD4030	4.0	3.0			
25TD4534	4.5	3.4	32TD4534	4.5	3.4	40TD4534	4.5	3.4			
25TD5040	5.0	4.0	32TD5040	5.0	4.0	40TD5040	5.0	4.0			
25TD5543	5.5	4.3	32TD5543	5.5	4.3	40TD5543	5.5	4.3			
25TD6049	6.0	4.9	32TD6049	6.0	4.9	40TD6049	6.0	4.9			
25TD7055	7.0	5.5	32TD7055	7.0	5.5	40TD7055	7.0	5.5			
25TD8062	8.0	6.2	32TD8062	8.0	6.2	40TD8062	8.0	6.2	50TD8062	8.0	6.2
25TD9080	9.0	7.0	32TD9070	9.0	7.0	40TD9070	9.0	7.0	50TD9070	9.0	7.0
25TD10090	10.0	8.0	32TD10080	10.0	8.0	40TD10080	10.0	8.0	50TD10080	10.0	8.0
25TD11090	11.0	9.0	32TD11090	11.0	9.0	40TD11090	11.0	9.0	50TD11090	11.0	9.0
25TD12090	12.0	9.0	32TD12090	12.0	9.0	40TD12090	12.0	9.0	50TD12090	12.0	9.0
25TD140110	14.0	11.0	32TD140110	14.0	11.0	40TD140110	14.0	11.0	50TD140110	14.0	11.0
25TD160120	16.0	12.0	32TD160120	16.0	12.0	40TD160120	16.0	12.0	50TD160120	16.0	12.0
						40TD180145	18.0	14.5	50TD180145	18.0	14.5
						40TD200160	20.0	16.0	50TD200160	20.0	16.0
						40TD220180	22.0	18.0	50TD220180	22.0	18.0
									50TD250200	25.0	20.0
									50TD280220	28.0	22.0
									50TD320240	32.0	24.0

SK SLIM CHUCK

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Coolant System AD/B
------------------	---------------------------	--------------------	-------------------	----------------------------

ASME B5.50-2009- CAT


Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	L	C	C1	H		COLLET	
							Min.	Max.		
TK020	40	CAT40 AD/B - SKA 6 - 3.54	0.036 - 0.236	3.540	0.787	0.768	0.827	1.378	SKC6	
TK021		CAT40 AD/B - SKA 6 - 4.72	0.036 - 0.236	4.720	0.787	0.768	0.827	1.378	SKC6	
TK022		CAT40 AD/B - SKA 6 - 5.90	0.036 - 0.236	5.900	0.787	0.768	0.827	1.378	SKC6	
TK023		CAT40 AD/B - SKA 10 - 3.54	0.068 - 0.394	3.540	1.102	1.083	1.181	1.969	SKC10	
TK024		CAT40 AD/B - SKA 10 - 4.72	0.068 - 0.394	4.720	1.102	1.083	1.181	1.969	SKC10	
TK025		CAT40 AD/B - SKA 10 - 5.90	0.068 - 0.394	5.900	1.102	1.083	1.181	1.969	SKC10	
TK026		CAT40 AD/B - SKA 13 - 3.54	0.108 - 0.512	3.540	1.299	1.299	1.220	2.559	SKC13	
TK027		CAT40 AD/B - SKA 13 - 4.72	0.108 - 0.512	4.720	1.299	1.299	1.220	2.559	SKC13	
TK028		CAT40 AD/B - SKA 13 - 5.90	0.108 - 0.512	5.900	1.299	1.299	1.220	2.559	SKC13	
TK029		CAT40 AD/B - SKA 16 - 3.54	0.108 - 0.630	3.540	1.575	1.575	1.772	2.756	SKC16	
TK030		CAT40 AD/B - SKA 16 - 4.72	0.108 - 0.630	4.720	1.575	1.575	1.772	2.756	SKC16	
TK031		CAT40 AD/B - SKA 16 - 5.90	0.108 - 0.630	5.900	1.575	1.575	1.772	2.756	SKC16	
TK032		CAT40 AD/B - SKA 20 - 3.54	0.138 - 0.787	3.540	1.909	1.909	1.850	3.150	SKC20	
TK033		CAT40 AD/B - SKA 20 - 4.72	0.138 - 0.787	4.720	1.909	1.909	1.850	3.150	SKC20	
TK034		CAT40 AD/B - SKA 20 - 5.90	0.138 - 0.787	5.900	1.909	1.909	1.850	3.150	SKC20	
TK035		CAT40 AD/B - SKA 25 - 3.54	0.630 - 1.000	3.540	2.165	2.165	2.165	3.346	SKC25	
TK036		CAT40 AD/B - SKA 25 - 4.72	0.630 - 1.000	4.720	2.165	2.165	2.165	3.346	SKC25	
TK037		CAT40 AD/B - SKA 25 - 5.90	0.630 - 1.000	5.900	2.165	2.165	2.165	3.346	SKC25	
TL020		50	CAT50 AD/B - SKA 6 - 4.13	0.036 - 0.236	4.130	0.787	0.768	0.827	1.378	SKC6
TL021			CAT50 AD/B - SKA 6 - 5.31	0.036 - 0.236	5.310	0.787	0.768	0.827	1.378	SKC6
TL022			CAT50 AD/B - SKA 6 - 6.50	0.036 - 0.236	6.500	0.787	0.768	0.827	1.378	SKC6
TL023			CAT50 AD/B - SKA 6 - 7.68	0.036 - 0.236	7.680	0.787	0.768	0.827	1.378	SKC6
TL024			CAT50 AD/B - SKA 10 - 4.13	0.068 - 0.394	4.130	1.102	1.083	1.181	1.969	SKC10
TL025			CAT50 AD/B - SKA 10 - 5.31	0.068 - 0.394	5.310	1.102	1.083	1.181	1.969	SKC10
TL026			CAT50 AD/B - SKA 10 - 6.50	0.068 - 0.394	6.500	1.102	1.083	1.181	1.969	SKC10
TL027			CAT50 AD/B - SKA 10 - 7.68	0.068 - 0.394	7.680	1.102	1.083	1.181	1.969	SKC10
TL028			CAT50 AD/B - SKA 13 - 4.13	0.108 - 0.512	4.130	1.299	1.299	1.220	2.559	SKC13
TL029			CAT50 AD/B - SKA 13 - 5.31	0.108 - 0.512	5.310	1.299	1.299	1.220	2.559	SKC13
TL030			CAT50 AD/B - SKA 13 - 6.50	0.108 - 0.512	6.500	1.299	1.299	1.220	2.559	SKC13
TL031			CAT50 AD/B - SKA 13 - 7.68	0.108 - 0.512	7.680	1.299	1.299	1.220	2.559	SKC13
TL032			CAT50 AD/B - SKA 16 - 4.13	0.108 - 0.630	4.130	1.575	1.575	1.772	2.362	SKC16
TL033			CAT50 AD/B - SKA 16 - 5.31	0.108 - 0.630	5.310	1.575	1.575	1.772	2.756	SKC16
TL034			CAT50 AD/B - SKA 16 - 6.50	0.108 - 0.630	6.500	1.575	1.575	1.772	2.756	SKC16
TL035	CAT50 AD/B - SKA 16 - 7.68		0.108 - 0.630	7.680	1.575	1.575	1.772	2.756	SKC16	
TL036	CAT50 AD/B - SKA 20 - 4.13		0.138 - 0.787	4.130	1.909	1.909	1.850	3.150	SKC20	
TL037	CAT50 AD/B - SKA 20 - 5.31		0.138 - 0.787	5.310	1.909	1.909	1.850	3.150	SKC20	
TL038	CAT50 AD/B - SKA 20 - 6.50		0.138 - 0.787	6.500	1.909	1.909	1.850	3.150	SKC20	
TL039	CAT50 AD/B - SKA 20 - 7.68		0.138 - 0.787	7.680	1.909	1.909	1.850	3.150	SKC20	
TL040	CAT50 AD/B - SKA 25 - 4.13		0.630 - 1.000	4.130	2.165	2.165	2.165	3.346	SKC25	
TL041	CAT50 AD/B - SKA 25 - 5.31		0.630 - 1.000	5.310	2.165	2.165	2.165	3.346	SKC25	
TL042	CAT50 AD/B - SKA 25 - 6.50		0.630 - 1.000	6.500	2.165	2.165	2.165	3.346	SKC25	
TL043	CAT50 AD/B - SKA 25 - 7.68		0.630 - 1.000	7.680	2.165	2.165	2.165	3.346	SKC25	

* SK collet on page 1389~1391.

DUAL CONTACT SK SLIM CHUCK

CCT



CCT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Coolant System AD/B
-----	---------------------------	--------------------	-------------------	----------------------------

CCT (CAT DUAL CONTACT)


Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	L	C	C1	H		COLLET	
							Min.	Max.		
TB020	40	CCT40 AD/B - SKA 6 - 3.54	0.036 - 0.236	3.540	0.787	0.768	0.827	1.378	SKC6	
TB021		CCT40 AD/B - SKA 6 - 4.72	0.036 - 0.236	4.720	0.787	0.768	0.827	1.378	SKC6	
TB022		CCT40 AD/B - SKA 6 - 5.90	0.036 - 0.236	5.900	0.787	0.768	0.827	1.378	SKC6	
TB023		CCT40 AD/B - SKA 10 - 3.54	0.068 - 0.394	3.540	1.102	1.083	1.181	1.969	SKC10	
TB024		CCT40 AD/B - SKA 10 - 4.72	0.068 - 0.394	4.720	1.102	1.083	1.181	1.969	SKC10	
TB025		CCT40 AD/B - SKA 10 - 5.90	0.068 - 0.394	5.900	1.102	1.083	1.181	1.969	SKC10	
TB026		CCT40 AD/B - SKA 13 - 3.54	0.108 - 0.512	3.540	1.299	1.299	1.220	2.559	SKC13	
TB027		CCT40 AD/B - SKA 13 - 4.72	0.108 - 0.512	4.720	1.299	1.299	1.220	2.559	SKC13	
TB028		CCT40 AD/B - SKA 13 - 5.90	0.108 - 0.512	5.900	1.299	1.299	1.220	2.559	SKC13	
TB029		CCT40 AD/B - SKA 16 - 3.54	0.108 - 0.630	3.540	1.575	1.575	1.772	2.756	SKC16	
TB030		CCT40 AD/B - SKA 16 - 4.72	0.108 - 0.630	4.720	1.575	1.575	1.772	2.756	SKC16	
TB031		CCT40 AD/B - SKA 16 - 5.90	0.108 - 0.630	5.900	1.575	1.575	1.772	2.756	SKC16	
TB032		CCT40 AD/B - SKA 20 - 3.54	0.138 - 0.787	3.540	1.909	1.909	1.850	3.150	SKC20	
TB033		CCT40 AD/B - SKA 20 - 4.72	0.138 - 0.787	4.720	1.909	1.909	1.850	3.150	SKC20	
TB034		CCT40 AD/B - SKA 20 - 5.90	0.138 - 0.787	5.900	1.909	1.909	1.850	3.150	SKC20	
TB035		CCT40 AD/B - SKA 25 - 3.54	0.630 - 1.000	3.540	2.165	2.165	2.165	3.346	SKC25	
TB036		CCT40 AD/B - SKA 25 - 4.72	0.630 - 1.000	4.720	2.165	2.165	2.165	3.346	SKC25	
TB037		CCT40 AD/B - SKA 25 - 5.90	0.630 - 1.000	5.900	2.165	2.165	2.165	3.346	SKC25	
TC020		50	CCT50 AD/B - SKA 6 - 4.13	0.036 - 0.236	4.130	0.787	0.768	0.827	1.378	SKC6
TC021			CCT50 AD/B - SKA 6 - 5.31	0.036 - 0.236	5.310	0.787	0.768	0.827	1.378	SKC6
TC022			CCT50 AD/B - SKA 6 - 6.50	0.036 - 0.236	6.500	0.787	0.768	0.827	1.378	SKC6
TC023			CCT50 AD/B - SKA 6 - 7.68	0.036 - 0.236	7.680	0.787	0.768	0.827	1.378	SKC6
TC024			CCT50 AD/B - SKA 10 - 4.13	0.068 - 0.394	4.130	1.102	1.083	1.181	1.969	SKC10
TC025			CCT50 AD/B - SKA 10 - 5.31	0.068 - 0.394	5.310	1.102	1.083	1.181	1.969	SKC10
TC026			CCT50 AD/B - SKA 10 - 6.50	0.068 - 0.394	6.500	1.102	1.083	1.181	1.969	SKC10
TC027			CCT50 AD/B - SKA 10 - 7.68	0.068 - 0.394	7.680	1.102	1.083	1.181	1.969	SKC10
TC028			CCT50 AD/B - SKA 13 - 4.13	0.108 - 0.512	4.130	1.299	1.299	1.220	2.559	SKC13
TC029			CCT50 AD/B - SKA 13 - 5.31	0.108 - 0.512	5.310	1.299	1.299	1.220	2.559	SKC13
TC030			CCT50 AD/B - SKA 13 - 6.50	0.108 - 0.512	6.500	1.299	1.299	1.220	2.559	SKC13
TC031			CCT50 AD/B - SKA 13 - 7.68	0.108 - 0.512	7.680	1.299	1.299	1.220	2.559	SKC13
TC032			CCT50 AD/B - SKA 16 - 4.13	0.108 - 0.630	4.130	1.575	1.575	1.772	2.362	SKC16
TC033			CCT50 AD/B - SKA 16 - 5.31	0.108 - 0.630	5.310	1.575	1.575	1.772	2.756	SKC16
TC034			CCT50 AD/B - SKA 16 - 6.50	0.108 - 0.630	6.500	1.575	1.575	1.772	2.756	SKC16
TC035			CCT50 AD/B - SKA 16 - 7.68	0.108 - 0.630	7.680	1.575	1.575	1.772	2.756	SKC16
TC036			CCT50 AD/B - SKA 20 - 4.13	0.138 - 0.787	4.130	1.909	1.909	1.850	3.150	SKC20
TC037			CCT50 AD/B - SKA 20 - 5.31	0.138 - 0.787	5.310	1.909	1.909	1.850	3.150	SKC20
TC038			CCT50 AD/B - SKA 20 - 6.50	0.138 - 0.787	6.500	1.909	1.909	1.850	3.150	SKC20
TC039	CCT50 AD/B - SKA 20 - 7.68		0.138 - 0.787	7.680	1.909	1.909	1.850	3.150	SKC20	
TC040	CCT50 AD/B - SKA 25 - 4.13		0.630 - 1.000	4.130	2.165	2.165	2.165	3.346	SKC25	
TC041	CCT50 AD/B - SKA 25 - 5.31		0.630 - 1.000	5.310	2.165	2.165	2.165	3.346	SKC25	
TC042	CCT50 AD/B - SKA 25 - 6.50		0.630 - 1.000	6.500	2.165	2.165	2.165	3.346	SKC25	
TC043	CCT50 AD/B - SKA 25 - 7.68		0.630 - 1.000	7.680	2.165	2.165	2.165	3.346	SKC25	

* SK collet on page 1389~1391.

DUAL CONTACT SK SLIM CHUCK

CBT



CBT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Coolant System AD
-----	------------------------------	-----------------------	----------------------	-----------------------------

CBT (BT DUAL CONTACT)


Unit : mm

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	L	C	C1	H		COLLET
							Min.	Max.	
TD100	30	CBT30 - SKA 06 - 60	0.9 - 6.0	60	20	19.5	21	35	SKC6
TD102		CBT30 - SKA 06 - 90	0.9 - 6.0	90	20	19.5	21	35	SKC6
TD104		CBT30 - SKA 10 - 60	1.75 - 10.0	60	28	27.5	30	50	SKC10
TD106		CBT30 - SKA 10 - 90	1.75 - 10.0	90	28	27.5	30	50	SKC10
TD108		CBT30 - SKA 13 - 60	2.75 - 13.0	60	33	33	31	65	SKC13
TD110		CBT30 - SKA 13 - 90	2.75 - 13.0	90	33	33	31	65	SKC13
TD112		CBT30 - SKA 16 - 60	2.75 - 16.0	60	40	40	45	60	SKC16
TD114		CBT30 - SKA 16 - 90	2.75 - 16.0	90	40	40	45	60	SKC16
TD116		CBT30 - SKA 20 - 60	4.0 - 20.0	60	48.5	48.5	65	75	SKC20
TD118		CBT30 - SKA 20 - 90	4.0 - 20.0	90	48.5	48.5	65	75	SKC20
TD120		CBT30 - SKA 25 - 90	16.0 - 25.4	90	55	55	55	75	SKC25
TE100		40	CBT40 - SKA 06 - 90	0.9 - 6.0	90	20	19.5	21	35
TE102	CBT40 - SKA 06 - 120		0.9 - 6.0	120	20	19.5	21	35	SKC6
TE104	CBT40 - SKA 06 - 150		0.9 - 6.0	150	20	19.5	21	35	SKC6
TE106	CBT40 - SKA 10 - 90		1.75 - 10.0	90	28	27.5	30	50	SKC10
TE108	CBT40 - SKA 10 - 120		1.75 - 10.0	120	28	27.5	30	50	SKC10
TE110	CBT40 - SKA 10 - 150		1.75 - 10.0	150	28	27.5	30	50	SKC10
TE112	CBT40 - SKA 13 - 90		2.75 - 13.0	90	33	33	31	65	SKC13
TE114	CBT40 - SKA 13 - 120		2.75 - 13.0	120	33	33	31	65	SKC13
TE116	CBT40 - SKA 13 - 150		2.75 - 13.0	150	33	40	31	65	SKC13
TE118	CBT40 - SKA 16 - 90		2.75 - 16.0	90	40	40	45	70	SKC16
TE121	CBT40 - SKA 16 - 120		2.75 - 16.0	120	40	40	45	70	SKC16
TE122	CBT40 - SKA 16 - 150		2.75 - 16.0	150	40	40	45	70	SKC16
TE124	CBT40 - SKA 20 - 90		4.0 - 20.0	90	48.5	48.5	47	80	SKC20
TE126	CBT40 - SKA 20 - 120		4.0 - 20.0	120	48.5	48.5	47	80	SKC20
TE128	CBT40 - SKA 20 - 150		4.0 - 20.0	150	48.5	48.5	47	80	SKC20
TE130	CBT40 - SKA 25 - 90		16.0 - 25.4	90	55	55	55	85	SKC25
TE132	CBT40 - SKA 25 - 120		16.0 - 25.4	120	55	55	55	85	SKC25
TE134	CBT40 - SKA 25 - 150		16.0 - 25.4	150	55	55	55	85	SKC25

* SK collet on page 1389~1391.

DUAL CONTACT SK SLIM CHUCK

HSK



DIN 69893 - HSK	Taper Accuracy -	G Value 2.5	RPM 25,000	Coolant System AD
-----------------	----------------------------	-----------------------	----------------------	-----------------------------

DIN 69893/ISO 12164-1-HSK FORM A


Unit : mm

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	D	D1	L	H		COLLET
							Min.	Max.	
TQ100	63A	HSK63A - SKA 06 - 100	0.75 - 6.0	20	19.5	100	21	35	SKC6
TQ102		HSK63A - SKA 10 - 100	1.75 - 10.0	28	27.5	100	30	50	SKC10
TQ104		HSK63A - SKA 13 - 100	2.75 - 13.0	33	33	100	31	65	SKC13
TQ106		HSK63A - SKA 16 - 120	2.75 - 16.0	40	40	120	45	70	SKC16
TQ108		HSK63A - SKA 20 - 120	4.0 - 20.0	48.5	48.5	120	65	75	SKC20
TQ110		HSK63A - SKA 25 - 150	16.0 - 25.4	55	55	150	55	85	SKC25
TR100	100A	HSK100A - SKA 06 - 120	0.75 - 6.0	20	19.5	120	21	35	SKC6
TR102		HSK100A - SKA 10 - 150	1.75 - 10.0	28	27.5	150	30	50	SKC10
TR104		HSK100A - SKA 13 - 150	2.75 - 13.0	33	40	150	31	65	SKC13
TR106		HSK100A - SKA 16 - 150	2.75 - 16.0	40	40	150	45	70	SKC16
TR108		HSK100A - SKA 20 - 150	4.0 - 20.0	48.5	48.5	150	65	75	SKC20
TR110		HSK100A - SKA 25 - 160	16.0 - 25.4	55	55	160	55	85	SKC25

* SK collet on page 1389~1391.

STRAIGHT SK SLIM CHUCK

K




STRAIGHT-K

Unit : inch

EDP No.	TAPER No.	MODEL No.	D	C	L1	L2
TS020	K3/4	K3/4 - SKA 6 - 100	0.750	0.787	3.937	0.827 - 1.378
TS021		K3/4 - SKA 6 - 140	0.750	0.787	5.512	0.827 - 1.378
TS022		K3/4 - SKA 10 - 100	0.750	1.102	3.937	1.181 - 1.969
TS023		K3/4 - SKA 10 - 140	0.750	1.102	5.512	1.181 - 1.969
TS030	K1	K1 - SKA 6 - 100	1.000	0.787	3.937	0.827 - 1.378
TS031		K1 - SKA 6 - 140	1.000	0.787	5.512	0.827 - 1.378
TS032		K1 - SKA 10 - 100	1.000	1.102	3.937	1.181 - 1.969
TS033		K1 - SKA 10 - 150	1.000	1.102	5.906	1.181 - 1.969
TS034		K1 - SKA 13 - 100	1.000	1.299	3.937	1.220 - 2.559
TS035		K1 - SKA 13 - 150	1.000	1.299	5.906	1.220 - 2.559
TS040		K1 1/4	K1 1/4 - SKA 10 - 100	1.250	1.102	3.937
TS041	K1 1/4 - SKA 10 - 150		1.250	1.102	5.906	1.181 - 1.969
TS042	K1 1/4 - SKA 13 - 100		1.250	1.299	3.937	1.220 - 2.559
TS043	K1 1/4 - SKA 13 - 150		1.250	1.299	5.906	1.220 - 2.559
TS044	K1 1/4 - SKA 16 - 100		1.250	1.575	3.937	1.575 - 2.756
TS045	K1 1/4 - SKA 16 - 150		1.250	1.575	5.906	1.575 - 2.756
TS046	K1 1/4 - SKA 20 - 100		1.250	1.909	3.937	1.850 - 3.150
TS047	K1 1/4 - SKA 20 - 150	1.250	1.909	5.906	1.850 - 3.150	

* SK collet on page 1389~1391.

SK COLLET (Metric Type)



◇ T.I.R of standard collet is 5Um at 3D.

Unit : mm


EDP No.	TYPE	MODEL No.	CLAMPING RANGE (d)	EDP No.	TYPE	MODEL No.	CLAMPING RANGE (d)	EDP No.	TYPE	MODEL No.	CLAMPING RANGE (d)
306010	SKC6	SKC6 - 1	0.9 - 1.0	310020	SKC10	SKC10 - 2	1.75 - 2.0	313030	SKC13	SKC13 - 3	2.75 - 3.0
306015		SKC6 - 1.5	1.3 - 1.5	310025		SKC10 - 2.5	2.25 - 2.5	313035		SKC13 - 3.5	3.0 - 3.5
306020		SKC6 - 2	1.8 - 2.0	310030		SKC10 - 3	2.75 - 3.0	313040		SKC13 - 4	3.5 - 4.0
306025		SKC6 - 2.5	2.3 - 2.5	310035		SKC10 - 3.5	3.0 - 3.5	313045		SKC13 - 4.5	4.0 - 4.5
306030		SKC6 - 3	2.8 - 3.0	310040		SKC10 - 4	3.5 - 4.0	313050		SKC13 - 5	4.5 - 5.0
306035		SKC6 - 3.5	3.0 - 3.5	310045		SKC10 - 4.5	4.0 - 4.5	313055		SKC13 - 5.5	5.0 - 5.5
306040		SKC6 - 4	3.5 - 4.0	310050		SKC10 - 5	4.5 - 5.0	313060		SKC13 - 6	5.5 - 6.0
306045		SKC6 - 4.5	4.0 - 4.5	310055		SKC10 - 5.5	5.0 - 5.5	313065		SKC13 - 6.5	6.0 - 6.5
306050		SKC6 - 5	4.5 - 5.0	310060		SKC10 - 6	5.5 - 6.0	313070		SKC13 - 7	6.5 - 7.0
306055		SKC6 - 5.5	5.0 - 5.5	310065		SKC10 - 6.5	6.0 - 6.5	313075		SKC13 - 7.5	7.0 - 7.5
306060	SKC6 - 6	5.5 - 6.0	310070	SKC10 - 7	6.5 - 7.0	313080	SKC13 - 8	7.5 - 8.0			
			310075	SKC10 - 7.5	7.0 - 7.5	313085	SKC13 - 8.5	8.0 - 8.5			
			310080	SKC10 - 8	7.5 - 8.0	313090	SKC13 - 9	8.5 - 9.0			
			310085	SKC10 - 8.5	8.0 - 8.5	313095	SKC13 - 9.5	9.0 - 9.5			
			310090	SKC10 - 9	8.5 - 9.0	313100	SKC13 - 10	9.5 - 10.0			
			310095	SKC10 - 9.5	9.0 - 9.5	313105	SKC13 - 10.5	10.0 - 10.5			
			310100	SKC10 - 10	9.5 - 10.0	313110	SKC13 - 11	10.5 - 11.0			
						313115	SKC13 - 11.5	11.0 - 11.5			
						313120	SKC13 - 12	11.5 - 12.0			
						313125	SKC13 - 12.5	12.0 - 12.5			
						313130	SKC13 - 13	12.5 - 13.0			

SKC COLLET Dimension

Unit : mm

TYPE	D	L	L1	H	C
SKC6	7.5	25.7	17.6	3.8	10
SKC10	12	32	21.3	5	15
SKC13	15.4	39	28.3	5.5	20
SKC16	18.8	46	32	8	24
SKC20	22.5	54.2	41	8	29
SKC25	28.9	58.2	43	8.5	35

SK NUT



Unit : mm

EDP No.	TYPE	A	B	C	FIG.
ZS106	SKN06	20	15	M15.5 × 1.0	1
ZS110	SKN10	28	17	M21.5 × 1.0	1
ZS113	SKN13	33	21	M27 × 1.0	2
ZS116	SKN16	40	24	M32 × 1.5	2
ZS120	SKN20	48.5	24	M40 × 1.0	2
ZS125	SKN25	55	30	M42 × 1.5	2

SK WRENCH

EDP No.	TYPE	FIG.
ZS206	SK06	1
ZS210	SK10	1
ZS213	SK13	1
ZS216	SK16	2
ZS220	SK20	2
ZS225	SK25	2

FIG. 1




FIG. 2



TG COLLET CHUCK

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value -	RPM -	Coolant System AD
------------------	--------------------	-----------	-------	-------------------

ASME B5.50-2009-CAT

TG75

■ STANDARD

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	L	D	COLLET SERIES
VK012	40	CAT40 - TG75 - 2.50	0.047 - 0.750	2.50	1.81	75TG

■ EXTENDED

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	L	D	COLLET SERIES
VK312	40	CAT40 - TG75 - 3.00	0.047 - 0.750	3.00	1.81	75TG

TG100

■ STANDARD

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	L	D	COLLET SERIES
OK014	40	CAT40 - TG100 - 3.25	0.063 - 1.000	3.25	2.36	100TG
OL014	50	CAT50 - TG100 - 3.25	0.063 - 1.000	3.25	2.36	100TG

■ EXTENDED

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	L	D	COLLET SERIES
OK314	40	CAT40 - TG100 - 4.50	0.063 - 1.000	4.50	2.36	100TG
OL314	50	CAT50 - TG100 - 5.50	0.063 - 1.000	5.50	2.36	100TG

TG150

■ STANDARD

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	L	D	COLLET SERIES
UL052	50	CAT50 - TG150 - 3.50	0.500 - 1.500	3.50	3.43	150TG

■ EXTENDED

Unit : inch


EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	L	D	COLLET SERIES
UL352	50	CAT50 - TG150 - 6.00	0.500 - 1.500	6.00	3.43	150TG

* TG Nut : Swiss made precision TG Nut

* Wrenches on page 1395.

TG COLLET CHUCK

BT



JIS B6339 -BT	Taper Accuracy AT3	G Value -	RPM -	Coolant System AD
------------------	-----------------------	--------------	----------	----------------------

JIS B6339/MAS 403-BT

TG75

■ STANDARD

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	L	D	COLLET SERIES
VH012	40	BT40 - TG75 - 3.00	0.047 - 0.750	3.00	1.81	75TG

TG100

■ STANDARD

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	L	D	COLLET SERIES
OH014	40	BT40 - TG100 - 3.50	0.063 - 1.000	3.50	2.36	100TG
OI014	50	BT50 - TG100 - 3.50	0.063 - 1.000	3.50	2.36	100TG

■ EXTENDED

Unit : mm

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	L	D	COLLET SERIES
OH314	40	BT40 - TG100 - 5.50	0.063 - 1.000	5.50	2.36	100TG
OI314	50	BT50 - TG100 - 6.00	0.063 - 1.000	6.00	2.36	100TG

TG150

■ STANDARD

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	L	D	COLLET SERIES
UI052	50	BT50 - TG150 - 4.00	0.500 - 1.500	4.00	3.43	150TG

■ EXTENDED

Unit : inch

EDP No.	TAPER No.	MODEL No.	CLAMPING RANGE	L	D	COLLET SERIES
UI352	50	BT50 - TG150 - 6.00	0.500 - 1.500	6.00	3.43	150TG

* TG Nut : Swiss made precision TG Nut
* Wrenches on page 1395.

TG NUT

TG NUT

EDP No.	SERIES
ZZ084	TG75-NUT
ZZ081	TG100-NUT
ZZ087	TG150-NUT



TG WRENCH

TG WRENCH


EDP No.	SERIES
ZZ085	TG75
ZZ082	TG100
ZZ088	TG150



TG STOP SCREW



TG STOP SCREW

EDP No.	SERIES
ZZ086	TG75
ZZ083	TG100
ZZ089	TG150



POWER MILLING CHUCK

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value -	RPM -	Coolant System AD
------------------	-----------------------	--------------	----------	----------------------

ASME B5.50-2009-CAT

STANDARD



Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L
LK010	40	CAT40 - C3/4 - 4.13	0.750	2.126	4.13
LK014		CAT40 - C1" - 4.13	1.000	2.461	4.13
LK017		CAT40 - C1 1/4 - 4.13	1.250	2.835	4.13
LL010	50	CAT50 - C3/4 - 4.13	0.750	2.126	4.13
LL014		CAT50 - C1" - 4.13	1.000	2.461	4.13
LL017		CAT50 - C1 1/4 - 4.13	1.250	2.835	4.13

* Collets / Wrenches for Power Milling Chucks on page 1400.

POWER MILLING CHUCK

BT



JIS B6339 - BT	Taper Accuracy AT3	G Value -	RPM -	Coolant System AD
----------------	-----------------------	--------------	----------	----------------------

JIS B6339/MAS 403-BT

STANDARD


Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L
LH010	40	BT40 - C 3/4 - 3.56	0.750	2.126	3.56
LH014		BT40 - C1" - 4.13	1.000	2.461	4.13
LH017		BT40 - C1 1/4 - 4.13	1.250	2.835	4.13
LI010	50	BT50 - C 3/4 - 4.13	0.750	2.126	4.13
LI014		BT50 - C1" - 4.13	1.000	2.461	4.13
LI017		BT50 - C1 1/4 - 4.13	1.250	2.835	4.13

* Collets / Wrenches for Power Milling Chucks on page 1400.

DUAL CONTACT HIGH SPEED POWER MILLING CHUCK

CCT



CCT	Taper Accuracy AT3	G Value 6.3	RPM 20,000	Coolant System AD
-----	-----------------------	----------------	---------------	----------------------

CCT (CAT DUAL CONTACT)


Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L
LB020	40	CCT40 - C 3/4 - 4.13HS	0.750	2.126	4.13
LB022		CCT40 - C 1" - 4.13HS	1.000	2.461	4.13
LB024		CCT40 - C 1 1/4 - 4.13HS	1.250	2.835	4.13
LB026		CCT40 - C 1 1/4 - 5.31HS	1.250	2.835	5.31
LC020	50	CCT50 - C 3/4 - 4.13HS	0.750	2.126	4.13
LC022		CCT50 - C 1" - 4.13HS	1.000	2.461	4.13
LC024		CCT50 - C 1 1/4 - 4.13HS	1.250	2.835	4.13
LC026		CCT50 - C 1 1/4 - 5.31HS	1.250	2.835	5.31
LC028		CCT50 - C 1 1/4 - 6.5HS	1.250	2.835	6.50

* Collets / Wrenches for Power Milling Chucks on page 1400.

DUAL CONTACT HIGH SPEED POWER MILLING CHUCK

CBT



CBT	Taper Accuracy AT3	G Value 6.3	RPM 20,000	Coolant System AD
------------	------------------------------	-----------------------	----------------------	-----------------------------

CBT (BT DUAL CONTACT)


Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	L
LE020	40	CBT40 - C 3/4 - 3.15HS	0.750	2.126	3.15
LE022		CBT40 - C 3/4 - 4.13HS	0.750	2.126	4.13
LE024		CBT40 - C 1" - 4.13HS	1.000	2.461	4.13
LE026		CBT40 - C 1 1/4 - 3.54HS	1.250	2.835	3.54
LE028		CBT40 - C 1 1/4 - 4.13HS	1.250	2.835	4.13
LE030		CBT40 - C 1 1/4 - 5.31HS	1.250	2.835	5.31

* Collets / Wrenches for Power Milling Chucks on page 1400.

DUAL CONTACT HIGH SPEED POWER MILLING CHUCK

HSK



DIN 69893 - HSK	Taper Accuracy -	G Value 6.3	RPM 20,000	Coolant System AD
------------------------	----------------------------	-----------------------	----------------------	-----------------------------


DIN 69893/ISO 12164-1-HSK FORM A

Unit : inch

EDP No.	TAPER No.	MODEL No.	d1	D1	L
LQ020	63A	HSK63 A - C 3/4 - 4.13HS	0.750	2.126	4.13
LQ022		HSK63 A - C 1" - 4.72HS	1.000	2.461	4.72
LQ024		HSK63 A - C 1 1/4 - 5.31HS	1.250	2.835	5.31
LR020		100A	HSK100 A - C 3/4 - 4.33HS	0.750	2.126
LR022	HSK100 A - C 1" - 5.12HS		1.000	2.461	5.12
LR024	HSK100 A - C 1 1/4 - 5.31HS		1.250	2.835	5.31


* Collets / Wrenches for Power Milling Chucks on page 1400.

POWER MILLING CHUCK COLLET



ADJUST SCREW

Unit : inch			Unit : inch			Unit : inch		
EDP No.	TYPE	D	EDP No.	TYPE	D	EDP No.	TYPE	D
MZ002	C3/4	1/4	MZ102	C1	1/4	MZ302	C1 1/4	1/4
MZ003	C3/4	5/16	MZ103	C1	5/16	MZ303	C1 1/4	5/16
MZ004	C3/4	3/8	MZ104	C1	3/8	MZ304	C1 1/4	3/8
MZ006	C3/4	1/2	MZ106	C1	1/2	MZ306	C1 1/4	1/2
MZ008	C3/4	5/8	MZ108	C1	5/8	MZ308	C1 1/4	5/8
			MZ110	C1	3/4	MZ310	C1 1/4	3/4
						MZ312	C1 1/4	7/8
						MZ314	C1 1/4	1"



Unit : inch			Unit : inch			Unit : inch		
EDP No.	TYPE	D	EDP No.	TYPE	D	EDP No.	TYPE	D
MY002	C3/4	1/4	MY102	C1	1/4	MY302	C1 1/4	1/4
MY003	C3/4	5/16	MY103	C1	5/16	MY303	C1 1/4	5/16
MY004	C3/4	3/8	MY104	C1	3/8	MY304	C1 1/4	3/8
MY006	C3/4	1/2	MY106	C1	1/2	MY306	C1 1/4	1/2
MY008	C3/4	5/8	MY108	C1	5/8	MY308	C1 1/4	5/8
			MY110	C1	3/4	MY310	C1 1/4	3/4
						MY312	C1 1/4	7/8
						MY314	C1 1/4	1"


WRENCH

Unit : inch	
EDP No.	SERIES
ZZ056	C3/4
ZZ057	C1
ZZ058	C1 1/4



MORSE TAPER ADAPTER

CAT




ASME B5.50 -CAT	Taper Accuracy AT3	G Value 6.3	RPM 15,000	Coolant System AD
-----------------	--------------------	-------------	------------	-------------------

ASME B5.50-2009-CAT

Unit : inch					
EDP No.	TAPER No.	MODEL No.	MT No.	D	L
CK037	40	CAT40 - MTA 1 - 1.75	#1	1.00	1.75
CK038		CAT40 - MTA 2 - 2.00	#2	1.26	2.00
CK039		CAT40 - MTA 3 - 2.75	#3	1.75	2.75
CK040		CAT40 - MTA 4 - 3.63	#4	1.75	3.63
CLO38	50	CAT50 - MTA 2 - 1.38	#2	2.75	1.38
CLO39		CAT50 - MTA 3 - 1.88	#3	1.57	1.88
CLO40		CAT50 - MTA 4 - 2.75	#4	1.97	2.75
CLO41		CAT50 - MTA 5 - 4.06	#5	2.48	4.06

MORSE TAPER ADAPTER

BT




JIS B6339 -BT	Taper Accuracy AT3	G Value 6.3	RPM 15,000	Coolant System AD
---------------	--------------------	-------------	------------	-------------------

JIS B6339/MAS 403-BT

Unit : inch					
EDP No.	TAPER No.	MODEL No.	MT No.	D	L
CH037	40	BT40 - MTA 1 - 1.75	#1	1.00	1.75
CH038		BT40 - MTA 2 - 2.36	#2	1.26	2.36
CH039		BT40 - MTA 3 - 2.95	#3	1.57	2.95
CH040		BT40 - MTA 4 - 3.74	#4	1.97	3.74
CIO38	50	BT50 - MTA 2 - 2.36	#2	1.26	2.36
CIO39		BT50 - MTA 3 - 2.95	#3	1.58	2.95
CIO40		BT50 - MTA 4 - 3.74	#4	1.97	3.74
CIO41		BT50 - MTA 5 - 4.13	#5	2.55	4.13

TAPPING CHUCK

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value -	RPM -	Coolant System -
------------------	--------------------	-----------	-------	------------------

ASME B5.50-2009-CAT

■ TO USE TAP ADAPTER QCT12

Unit : inch

EDP No.	TAPER No.	MODEL No.	D	L	F1	F2
JK048	40	CAT40 - TC#1 - 4.56	1.77	4.56	0.591	0.197
JL048	50	CAT50 - TC#1 - 4.56	1.77	4.56	0.591	0.197

■ TO USE TAP ADAPTER QCT24

Unit : inch

EDP No.	TAPER No.	MODEL No.	D	L	F1	F2
JK049	40	CAT40 - TC#2 - 6.47	2.48	6.47	0.787	0.197
JL049	50	CAT50 - TC#2 - 5.82	2.48	5.82	0.787	0.197

■ TO USE TAP ADAPTER QCT32


Unit : inch

EDP No.	TAPER No.	MODEL No.	D	L	F1	F2
JL050	50	CAT50 - TC#3 - 7.75	3.86	7.75	0.984	0.394

* Tap Adapters are on page 1405.

TAPPING CHUCK

BT



JIS B6339 - BT	Taper Accuracy AT3	G Value -	RPM -	Coolant System -
----------------	--------------------	-----------	-------	------------------

JIS B6339/MAS 403-BT

■ TO USE TAP ADAPTER QCT12

Unit : inch

EDP No.	TAPER No.	MODEL No.	D	L	F1	F2
JH048	40	BT40 - TC#1 - 4.53	1.77	4.53	0.591	0.197
JI048	50	BT50 - TC#1 - 4.64	1.77	4.64	0.591	0.197

■ TO USE TAP ADAPTER QCT24

Unit : inch

EDP No.	TAPER No.	MODEL No.	D	L	F1	F2
JH049	40	BT40 - TC#2 - 6.72	2.48	6.72	0.787	0.197
JI049	50	BT50 - TC#2 - 6.72	2.48	6.72	0.787	0.197

■ TO USE TAP ADAPTER QCT38


Unit : inch

EDP No.	TAPER No.	MODEL No.	D	L	F1	F2
JI050	50	BT50 - TC#3 - 8.33	3.86	8.33	0.984	0.394

* Tap Adapters are on page 1405.

SYNCHRO TAPPING ER CHUCK

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value -	RPM -	Coolant System AD/B
------------------	--------------------	-----------	-------	---------------------

ASME B5.50-2009-CAT


Unit : mm

EDP No.	TAPER No.	MODEL No.	TAP SIZE	CLAMPING RANGE	NUT	D	L
JK060SYT	40	CAT40 AD/B - SYTER 12 - 79	M3 - M12	3.5 - 10	ER16	28	79
JK062SYT		CAT40 AD/B - SYTER 16 - 85	M3 - M16	3.5 - 10	ER20	35	85
JK064SYT		CAT40 AD/B - SYTER 20 - 90	M3 - M20	3.5 - 16	ER25	42	90
JK066SYT		CAT40 AD/B - SYTER 27 - 100	M4 - M27	3.5 - 16	ER32	50	100
JK068SYT		CAT40 AD/B - SYTER 33 - 105	M4 - M33	7 - 16	ER40	63	105
JL060SYT	50	CAT50 AD/B - SYTER 12 - 79	M3 - M12	3.5 - 10	ER16	28	79
JL062SYT		CAT50 AD/B - SYTER 16 - 85	M3 - M16	3.5 - 10	ER20	35	85
JL064SYT		CAT50 AD/B - SYTER 20 - 90	M3 - M20	3.5 - 16	ER25	42	90
JL066SYT		CAT50 AD/B - SYTER 27 - 100	M4 - M27	3.5 - 16	ER32	50	100
JL068SYT		CAT50 AD/B - SYTER 33 - 105	M4 - M33	7 - 16	ER40	63	105

* BT(JIS B6339/MAS-403), HSK(DIN 69893/ISO 12164-1) and STRAIGHT-K Taper products are available.
For details, please discuss separately.
* Applicable TAP ER collets on page 1379~1383.

- Feature**
- To compensate for synchronization errors to extend tap life and to improve thread quality
 - To compensate for pitch tolerances of taps
 - For machine with synchronized spindle

QUICK CHANGE TAP ADAPTER




POSITIVE DRIVE-SOLID TYPE

Unit : inch

EDP No.	ADAPTER SIZE	TAP SIZE RANGE	TAP SIZE	TAP Dia.	TAP SQUARE		
QCT12001	QCT 12	0 - 9/16"	# 0 - 6	0.141	0.110		
QCT12002			# 8	0.168	0.131		
QCT12003			# 10	0.194	0.152		
QCT12004			# 12	0.220	0.165		
QCT12005			1/4	0.255	0.191		
QCT12006			5/16	0.318	0.238		
QCT12007			3/8	0.381	0.286		
QCT12008			7/16	0.323	0.242		
QCT12009			1/2	0.367	0.275		
QCT12010			9/16	0.429	0.322		
QCT12011	1/8" PIPE	1/8" PIPE	1/8pss	0.3125	0.234		
QCT12012			1/8pls	0.4370	0.328		
QCT24001	QCT 24	5/16 - 7/8"	5/16	0.318	0.238		
QCT24002			3/8	0.381	0.286		
QCT24003			7/16	0.323	0.242		
QCT24004			1/2	0.367	0.275		
QCT24005			9/16	0.429	0.322		
QCT24006			5/8	0.480	0.360		
QCT24007			11/16	0.542	0.406		
QCT24008			3/4	0.590	0.421		
QCT24009			13/16	0.652	0.489		
QCT24010			7/8	0.697	0.523		
QCT24011			1/4" - 3/8" PIPE	1/4" - 3/8" PIPE	1/4p	0.5620	0.42
QCT24012					3/8p	0.7000	0.531
QCT24013					1/2p	0.6875	0.515
QCT32001	QCT 32	13/16 - 1 - 3/8"	13/16	0.652	0.489		
QCT32002			7/8	0.697	0.523		
QCT32003	D = 48mm/1.890" L = 69.5mm/2.736"	13/16 - 1 - 3/8"	15/16	0.760	0.570		
QCT32004			1	0.800	0.600		
QCT32005			1 - 1/8	0.896	0.672		
QCT32006			1 - 1/4	1.021	0.766		
QCT32007			1 - 3/8	1.108	0.831		
QCT32008			1/2/3/4 & 1" PIPE	1/2/3/4 & 1" PIPE	1/2p	0.6875	0.515
QCT32009					3/4p	0.9060	0.679
QCT32010	1p	1.1250			0.843		

SHELL MILL ARBOR

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value 6.3	RPM 15,000	Coolant System AD/B
------------------	--------------------	-------------	------------	---------------------

ASME B5.50-2009-CAT

■ STANDARD

Unit : inch

EDP No.	TAPER No.	MODEL No.	d	L	D
EK006B	40	CAT40 AD/B - SMA 1/2 - 1.50	0.500	1.50	1.44
EK010B		CAT40 AD/B - SMA 3/4 - 1.50	0.750	1.50	1.69
EK014B		CAT40 AD/B - SMA 1" - 2.00	1.000	2.00	2.19
EK017B		CAT40 AD/B - SMA 1 1/4 - 2.00	1.250	2.00	2.75
EK021B		CAT40 AD/B - SMA 1 1/2 - 3.00	1.500	3.00	3.81
EL010B	50	CAT50 AD/B - SMA 3/4 - 1.50	0.750	1.50	1.69
EL014B		CAT50 AD/B - SMA 1" - 2.00	1.000	2.00	2.19
EL017B		CAT50 AD/B - SMA 1 1/4 - 2.00	1.250	2.00	2.75
EL021B		CAT50 AD/B - SMA 1 1/2 - 2.50	1.500	2.50	3.81
EL029B		CAT50 AD/B - SMA 2" - 3.00	2.000	3.00	4.88

■ EXTENDED



Unit : inch

EDP No.	TAPER No.	MODEL No.	d	L	D
EK306B	40	CAT40 AD/B - SMA 1/2 - 3.50	0.500	3.50	1.44
EK310B		CAT40 AD/B - SMA 3/4 - 3.50	0.750	3.50	1.69
EK314B		CAT40 AD/B - SMA 1" - 4.00	1.000	4.00	2.19
EK317B		CAT40 AD/B - SMA 1 1/4 - 4.00	1.250	4.00	2.75
EK321B		CAT40 AD/B - SMA 1 1/2 - 4.00	1.500	4.00	3.81
EL310B	50	CAT50 AD/B - SMA 3/4 - 3.50	0.750	3.50	1.69
EL314B		CAT50 AD/B - SMA 1" - 4.00	1.000	4.00	2.19
EL317B		CAT50 AD/B - SMA 1 1/4 - 4.00	1.250	4.00	2.75
EL321B		CAT50 AD/B - SMA 1 1/2 - 4.00	1.500	4.00	3.81
EL329B		CAT50 AD/B - SMA 2" - 4.00	2.000	4.00	4.88

* High balanced Shell Mill Arbors are available on request.
 * Drive Key / Lock Screw for Shell Mill Arbors on page 1410.

SHELL MILL ARBOR

BT



JIS B6339 - BT	Taper Accuracy AT3	G Value 6.3	RPM 15,000	Coolant System AD/B
----------------	--------------------	-------------	------------	---------------------

JIS B6339/MAS 403-BT

■ STANDARD

Unit : inch

EDP No.	TAPER No.	MODEL No.	d	L	D
EH006B	40	BT40 AD/B - SMA 1/2 - 1.75	0.500	1.75	1.44
EH010B		BT40 AD/B - SMA 3/4 - 1.77	0.750	1.77	1.69
EH014B		BT40 AD/B - SMA 1" - 1.77	1.000	1.77	2.19
EH017B		BT40 AD/B - SMA 1 1/4 - 1.81	1.250	1.81	2.75
EH021B		BT40 AD/B - SMA 1 1/2 - 2.36	1.500	2.36	3.81
EI010	50	BT50 - SMA 3/4 - 1.75	0.750	1.75	1.69
EI014		BT50 - SMA 1" - 1.75	1.000	1.75	2.19
EI017		BT50 - SMA 1 1/4 - 1.75	1.250	1.75	2.75
EI021		BT50 - SMA 1/2 - 1.75	1.500	1.75	3.81
EI029		BT50 - SMA 2" - 3.00	2.000	3.00	4.88

■ EXTENDED


Unit : inch

EDP No.	TAPER No.	MODEL No.	d	L	D
EH306B	40	BT 40 AD/B - SMA 1/2 - 3.50	0.500	3.50	1.44
EH310B		BT 40 AD/B - SMA 3/4 - 4.13	0.750	4.13	1.69
EH314B		BT 40 AD/B - SMA 1" - 4.13	1.000	4.13	2.19
EH317B		BT 40 AD/B - SMA 1 1/4 - 4.13	1.250	4.13	2.75
EH321B		BT 40 AD/B - SMA 1 1/2 - 4.72	1.500	4.72	3.81
EI310	50	BT 50 - SMA 3/4 - 3.50	0.750	3.50	1.69
EI314		BT 50 - SMA 1" - 4.00	1.000	4.00	2.19
EI317		BT 50 - SMA 1 1/4 - 4.00	1.250	4.00	2.75
EI321		BT 50 - SMA 1 1/2 - 4.00	1.500	4.00	3.81
EI329		BT 50 - SMA 2" - 4.00	2.000	4.00	4.88

* High balanced Shell Mill Arbors are available on request.
 * Drive Key / Lock Screw for Shell Mill Arbors on page 1410.

DUAL CONTACT SHELL MILL ARBOR

CCT



CCT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Coolant System AD/B
-----	------------------------------	-----------------------	----------------------	-------------------------------

CCT (CAT DUAL CONTACT)


Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L	
EBO20	40	CCT40 AD/B - SMA 1/2 - 2.36	0.500	1.438	2.360	
EBO22		CCT40 AD/B - SMA 1/2 - 4.72	0.500	1.438	4.720	
EBO24		CCT40 AD/B - SMA 3/4 - 2.36	0.750	1.688	2.360	
EBO26		CCT40 AD/B - SMA 3/4 - 4.72	0.750	1.688	4.720	
EBO28		CCT40 AD/B - SMA 1" - 2.36	1.000	2.188	2.360	
EBO30		CCT40 AD/B - SMA 1" - 4.72	1.000	2.188	4.720	
EBO32		CCT40 AD/B - SMA 1 1/4 - 2.36	1.250	2.750	2.360	
EBO34		CCT40 AD/B - SMA 1 1/4 - 4.72	1.250	2.750	4.720	
ECO20		50	CCT50 AD/B - SMA 1/2 - 2.95	0.500	1.438	2.950
ECO22			CCT50 AD/B - SMA 1/2 - 4.72	0.500	1.438	4.720
ECO24	CCT50 AD/B - SMA 3/4 - 2.95		0.750	1.688	2.950	
ECO26	CCT50 AD/B - SMA 3/4 - 4.72		0.750	1.688	4.720	
ECO28	CCT50 AD/B - SMA 1" - 2.95		1.000	2.188	2.950	
ECO30	CCT50 AD/B - SMA 1" - 4.72		1.000	2.188	4.720	
ECO32	CCT50 AD/B - SMA 1 1/4 - 2.95		1.250	2.750	2.950	
ECO34	CCT50 AD/B - SMA 1 1/4 - 4.72		1.250	2.750	4.720	
ECO36	CCT50 AD/B - SMA 1 1/2 - 2.95		1.500	3.813	2.950	
ECO38	CCT50 AD/B - SMA 1 1/2 - 4.72		1.500	3.813	4.720	

* Drive Key / Lock Screw for Shell Mill Arbors on page 1410.

DUAL CONTACT SHELL MILL ARBOR

CBT



CBT	Taper Accuracy AT3	G Value 2.5	RPM 25,000	Coolant System AD
-----	------------------------------	-----------------------	----------------------	-----------------------------


CBT (BT DUAL CONTACT)

Unit : inch

EDP No.	TAPER No.	MODEL No.	d	D	L
ED100	30	CBT 30 - SMA 1/2 - 1.97	0.500	1.438	1.970
ED102		CBT 30 - SMA 3/4 - 1.97	0.750	1.688	1.970
ED104		CBT 30 - SMA 1" - 1.97	1.000	2.188	1.970
ED106		CBT 30 - SMA 1 1/4 - 1.97	1.250	2.750	1.970
EE100	40	CBT 40 - SMA 1/2 - 2.36	0.500	1.438	2.360
EE102		CBT 40 - SMA 3/4 - 2.36	0.750	1.688	2.360
EE104		CBT 40 - SMA 1" - 2.36	1.000	2.188	2.360
EE106		CBT 40 - SMA 1 1/4 - 2.36	1.250	2.750	2.360

* Drive Key / Lock Screw for Shell Mill Arbors on page 1410.

SHELL MILL DRIVE KEY




SHELL MILL DRIVE KEY

Unit : inch

EDP No.	SERIES	B
ZZ021	SMA 1/2 - KEY	0.25
ZZ022	SMA 3/4 - KEY	0.312
ZZ023	SMA 1" - KEY	0.375
ZZ024	SMA 1 1/4 - KEY	0.5
ZZ025	SMA 1 1/2 - KEY	0.625
ZZ026	SMA 2" - KEY	0.75

SHELL MILL LOCK SCREW




SHELL MILL LOCK SCREW

Unit : inch

EDP No.	TYPE (M)	L	D	SERIES
ZZ031	UNF 1/4 - 28	0.906	0.618	SMA 1/2 - SCREW
ZZ032	UNF 3/8 - 24	1.26	0.882	SMA 3/4 - SCREW
ZZ033	UNF 1/2 - 20	1.69	1.181	SMA 1" - SCREW
ZZ034	UNF 5/8 - 18	2.05	1.5	SMA 1 1/4 - SCREW
ZZ035	UNF 3/4 - 16	2.36	1.88	SMA 1 1/2 - SCREW
ZZ036	UN 1" - 14	2.52	2.5	SMA 2" - SCREW

NC DRILL CHUCK

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value -	RPM -	Coolant System -
------------------	--------------------	-----------	-------	------------------


ASME B5.50-2009-CAT

Unit : inch

EDP No.	TAPER No.	MODEL No.	RANGE	D	L	L1
RK020	40	CAT 40 - NPU8 - 2.95	0.012 - 0.315	1.437	2.950	3.174
RK022		CAT 40 - NPU8 - 4.33	0.012 - 0.315	1.437	4.331	4.555
RK024		CAT 40 - NPU8 - 5.91	0.012 - 0.315	1.437	5.906	6.130
RK026		CAT 40 - NPU13 - 3.54	0.039 - 0.512	1.984	3.543	3.937
RK028		CAT 40 - NPU13 - 5.12	0.039 - 0.512	1.984	5.118	5.512
RK030		CAT 40 - NPU13 - 5.91	0.039 - 0.512	1.984	5.906	6.299
RL020	50	CAT 50 - NPU8 - 3.54	0.012 - 0.315	1.437	3.543	3.768
RL022		CAT 50 - NPU8 - 4.33	0.012 - 0.315	1.437	4.331	4.555
RL024		CAT 50 - NPU8 - 6.69	0.012 - 0.315	1.437	6.693	6.917
RL026		CAT 50 - NPU13 - 3.94	0.039 - 0.512	1.984	3.937	4.331
RL028		CAT 50 - NPU13 - 5.12	0.039 - 0.512	1.984	5.118	5.512
RL030		CAT 50 - NPU13 - 5.91	0.039 - 0.512	1.984	5.906	6.299
RL032		CAT 50 - NPU13 - 6.69	0.039 - 0.512	1.984	6.693	7.087

NC DRILL CHUCK

BT



JIS B6339 -BT	Taper Accuracy AT3	G Value -	RPM -	Coolant System -
---------------	------------------------------	--------------	----------	---------------------

JIS B6339/MAS 403-BT


Unit : mm

EDP No.	TAPER No.	MODEL No.	RANGE	D	L(Min.)	L1(Max.)
RG100	30	BT30 - NPU8 - 75	0.3 - 8	36.5	75	80.7
RG102		BT30 - NPU13 - 105	1 - 13	50.4	105	115
RH100	40	BT40 - NPU8 - 80	0.3 - 8	36.5	80	85.7
RH102		BT40 - NPU8 - 110	0.3 - 8	36.5	110	115.7
RH104		BT40 - NPU8 - 150	0.3 - 8	36.5	150	155.7
RH106		BT40 - NPU13 - 95	1 - 13	50.4	95	100.7
RH108		BT40 - NPU13 - 130	1 - 13	50.4	130	140
RH110		BT40 - NPU13 - 150	1 - 13	50.4	150	160

* Chucking Length
- NPU8 : 20mm
- NPU13 : 28mm

DUAL CONTACT NC DRILL CHUCK

HSK



DIN 69893 - HSK	Taper Accuracy -	G Value -	RPM -	Coolant System -
-----------------	---------------------	--------------	----------	---------------------


DIN 69893/ISO 12164-1-HSK FORM A

Unit : mm

EDP No.	TAPER No.	MODEL No.	CAPACITY	D	L(Min.)	L1(Max.)
RQ100	63A	HSK63A - NPU8 - 125	0.3 - 8	36.5	125	130.7
RQ102		HSK63A - NPU13 - 150	1 - 13	50.4	150	160
RR100	100A	HSK100A - NPU8 - 130	0.3 - 8	36.5	130	135.7
RR102		HSK100A - NPU13 - 1510	1 - 13	50.4	150	160

STRAIGHT NC DRILL CHUCK

K





STRAIGHT-K

Unit : mm

EDP No.	TYPE	MODEL No.	RANGE	D	L(Min.)	L1(Max.)	d1
RS100	32	K32 - NPU8 - 75	0.3 - 8	36.5	75	80.7	32.0
RS102		K32 - NPU13 - 100	1 - 13	50.4	100	110	32.0
RS104	42	K42 - NPU8 - 70	0.3 - 8	36.5	70	75.7	42.0
RS106		K42 - NPU13 - 100	1 - 13	50.4	100	110	42.0

JACOBS TAPER ARBOR

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value -	RPM -	Coolant System -
------------------	------------------------------	--------------	----------	---------------------



ASME B5.50-2009-CAT

EDP No.	TAPER No.	MODEL No.	K	L
GK042	40	CAT40 - JTA 1 - 1.50	#1	1.50
GK043		CAT40 - JTA 2 - 1.50	#2	1.50
GK044		CAT40 - JTA 3 - 1.50	#3	1.50
GK045		CAT40 - JTA 4 - 1.50	#4	1.50
GK046		CAT40 - JTA 6 - 1.50	#6	1.50
GK047		CAT40 - JTA 33 - 1.50	#33	1.50
GLO42	50	CAT50 - JTA 1 - 1.50	#1	1.50
GLO43		CAT50 - JTA 2 - 1.50	#2	1.50
GLO44		CAT50 - JTA 3 - 1.50	#3	1.50
GLO45		CAT50 - JTA 4 - 1.50	#4	1.50
GLO46		CAT50 - JTA 6 - 1.50	#6	1.50
GLO47		CAT50 - JTA 33 - 1.50	#33	1.50

Unit : inch

JACOBS TAPER ARBOR

BT



JIS B6339 - BT	Taper Accuracy AT3	G Value -	RPM -	Coolant System -
----------------	------------------------------	--------------	----------	---------------------


JIS B6339/MAS 403-BT

EDP No.	TAPER No.	MODEL No.	K	L
GH042	40	BT40 - JTA 1 - 1.34	#1	1.34
GH043		BT40 - JTA 2 - 1.77	#2	1.77
GH044		BT40 - JTA 3 - 1.77	#3	1.77
GH045		BT40 - JTA 4 - 1.77	#4	1.77
GH046		BT40 - JTA 6 - 1.77	#6	1.77
GH047		BT40 - JTA 33 - 1.77	#33	1.77
GI042	50	BT50 - JTA 1 - 1.80	#1	1.80
GI043		BT50 - JTA 2 - 1.77	#2	1.77
GI044		BT50 - JTA 3 - 1.77	#3	1.77
GI045		BT50 - JTA 4 - 1.77	#4	1.77
GI046		BT50 - JTA 6 - 1.77	#6	1.77
GI047		BT50 - JTA 33 - 1.77	#33	1.77

Unit : inch

STUB ARBOR

CAT



ASME B5.50 - CAT	Taper Accuracy AT3	G Value -	RPM -	Coolant System -
------------------	------------------------------	--------------	----------	---------------------

ASME B5.50-2009-CAT


■ STANDARD

EDP No.	TAPER No.	MODEL No.	CUTTER SIZE I.D	L1	D	L2
PK014	40	CAT40 - STUB 1" - 4.00	1.000	4.00	1.56	6.25
PK017		CAT40 - STUB 1 1/4 - 4.00	1.250	4.00	1.87	6.50
PK021		CAT40 - STUB 1 1/2 - 4.00	1.500	4.00	2.12	6.75
PL014	50	CAT50 - STUB 1" - 4.00	1.000	4.00	1.56	6.25
PL017		CAT50 - STUB 1 1/4 - 4.00	1.250	4.00	1.87	6.50
PL021		CAT50 - STUB 1 1/2 - 4.00	1.500	4.00	2.12	6.75

Unit : inch

STUB ARBOR

BT



JIS B6339 - BT	Taper Accuracy AT3	G Value -	RPM -	Coolant System -
----------------	------------------------------	--------------	----------	---------------------

JIS B6339/MAS 403-BT

■ STANDARD

EDP No.	TAPER No.	MODEL No.	CUTTER SIZE I.D	L1	D	L2
PH014	40	BT40 - STUB 1" - 3.00	1.000	3.00	1.56	5.25
PH017		BT40 - STUB 1 1/4 - 3.00	1.250	3.00	1.87	5.50
PH021		BT40 - STUB 1 1/2 - 3.00	1.500	3.00	2.12	5.75
PI014	50	BT50 - STUB 1" - 4.00	1.000	4.00	1.56	6.25
PI017		BT50 - STUB 1 1/4 - 4.00	1.250	4.00	1.87	6.50
PI021		BT50 - STUB 1 1/2 - 4.00	1.500	4.00	2.12	6.75


Unit : inch

* Nuts / Key / Spacer for Stub Arbors on page 1416.

NUT

Unit : inch


EDP No.	TYPE (M)	L	D	SERIES
ZZ041	UNF 1 - 12	1.00	1.56	STUB 1"
ZZ046	UNF 1 1/4 - 12	1.25	1.87	STUB 1 1/4
ZZ052	UNF 1 1/2 - 12	1.50	2.12	STUB 1 1/2




KEY

Unit : inch

EDP No.	SERIES	B
ZZ042	STUB 1"	0.25
ZZ047	STUB 1 1/4	0.312
ZZ054	STUB 1 1/2	0.375



SPACER



Unit : inch


EDP No.	TYPE	H	D	d	SERIES
ZZ043	1/4 - SPACER	0.25	1.56	1.00	STUB 1"
ZZ044	3/8 - SPACER	0.375	1.56	1.00	STUB 1"
ZZ045	3/4 - SPACER	0.75	1.56	1.00	STUB 1"

EDP No.	TYPE	H	D	d	SERIES
ZZ048	1/4 - SPACER	0.25	1.87	1.25	STUB 1 1/4
ZZ049	3/8 - SPACER	0.375	1.87	1.25	STUB 1 1/4
ZZ050	3/4 - SPACER	0.75	1.87	1.25	STUB 1 1/4

EDP No.	TYPE	H	D	d	SERIES
ZZ037	1/4 - SPACER	0.25	2.12	1.50	STUB 1 1/2
ZZ038	3/8 - SPACER	0.375	2.12	1.50	STUB 1 1/2
ZZ039	3/4 - SPACER	0.75	2.12	1.50	STUB 1 1/2

SLITTING SAW ARBOR

CAT




■ STANDARD

Unit : inch

EDP No.	TAPER No.	MODEL No.	COLLET SERIES	L	D
QK014	40	CAT40 - SSA 1" - 4.00	1.000	4.00	1.50
QK017		CAT40 - SSA 1 1/4 - 4.00	1.250	4.00	2.00
QL014	50	CAT50 - SSA 1" - 4.00	1.000	4.00	1.50
QL017		CAT50 - SSA 1 1/4 - 4.00	1.250	4.00	2.00

SLITTING SAW ARBOR

BT



■ STANDARD


Unit : inch

EDP No.	TAPER No.	MODEL No.	COLLET SERIES	L	D
QH014	40	BT40 - SSA 1" - 4.00	1.000	4.00	1.50
QH017		BT40 - SSA 1 1/4 - 4.00	1.250	4.00	2.00


CAP

Unit : inch

EDP No.	TYPE	L	D	d
ZZ051	SSA 1"	1.02	1.50	1.00
ZZ053	SSA 1 1/4	1.30	2.00	1.25



PULL STUD



Unit : inch

EDP NO.	MODEL No.	ANGLE	S	P	D3	A	N	D	W	M
SK661	CAT - 40ANSI C	45°	0.740	0.490	0.490	1.500	0.440	0.640	0.120	5/8 - 11
SL661	CAT - 50ANSI C	45°	1.140	0.820	0.820	2.300	0.700	1.000	0.200	1 - 8
SK561	CAT - 40ANSI	45°	0.740	0.490	0.490	1.500	0.440	0.640	0.120	5/8 - 11
SL561	CAT - 50ANSI	45°	1.140	0.820	0.820	2.300	0.700	1.000	0.200	1 - 8
SK761	CAT - 40TYPE I	45°	0.590	0.394	0.512	2.250	0.990	1.266	0.120	5/8 - 11
SK762	CAT - 40TYPE II	60°	0.590	0.394	0.512	2.250	0.990	1.266	0.120	5/8 - 11
SK763	CAT - 40TYPE III	90°	0.590	0.394	0.512	2.250	0.990	1.266	0.120	5/8 - 11
SK861	CAT - 40TYPE I C	45°	0.590	0.394	0.512	2.250	0.990	1.266	0.120	5/8 - 11
SK862	CAT - 40TYPE II C	60°	0.590	0.394	0.512	2.250	0.990	1.266	0.120	5/8 - 11
SK863	CAT - 40TYPE III C	90°	0.590	0.394	0.512	2.250	0.990	1.266	0.120	5/8 - 11
SL761	CAT - 50TYPE I	45°	0.906	0.669	0.827	3.346	1.377	1.772	0.390	1 - 8
SL762	CAT - 50TYPE II	60°	0.906	0.669	0.827	3.346	1.377	1.772	0.390	1 - 8
SL763	CAT - 50TYPE III	90°	0.906	0.669	0.827	3.346	1.377	1.772	0.390	1 - 8
SL861	CAT - 50TYPE I C	45°	0.906	0.669	0.827	3.346	1.377	1.772	0.390	1 - 8
SL862	CAT - 50TYPE II C	60°	0.906	0.669	0.827	3.346	1.377	1.772	0.390	1 - 8
SL863	CAT - 50TYPE III C	90°	0.906	0.669	0.827	3.346	1.377	1.772	0.390	1 - 8
SH061	BT - 40PS 1	45°	0.590	0.394	0.669	2.360	1.102	1.378	0.230	M16
SI061	BT - 50PS 5	45°	0.905	0.669	0.984	3.346	1.377	1.772	0.390	M24
SH062	BT - 40PS 2	60°	0.590	0.394	0.669	2.360	1.102	1.378	0.230	M16
SI062	BT - 50PS 6	60°	0.905	0.669	0.984	3.346	1.377	1.772	0.390	M24
SH063	BT - 40PS 8	90°	0.590	0.394	0.669	2.360	1.102	1.378	0.230	M16
SI063	BT - 50PS 0	90°	0.905	0.669	0.984	3.346	1.377	1.772	0.390	M24
SK161	CAT - 40TYPE I	45°	0.590	0.394	0.512	2.250	0.990	1.266	0.236	5/8 - 11
SK162	CAT - 40TYPE II	60°	0.590	0.394	0.512	2.250	0.990	1.266	0.236	5/8 - 11
SK163	CAT - 40TYPE III	90°	0.590	0.394	0.512	2.250	0.990	1.266	0.236	5/8 - 11
SK261	CAT - 40TYPE I C	45°	0.590	0.394	0.512	2.250	0.990	1.266	0.236	5/8 - 11
SK262	CAT - 40TYPE II C	60°	0.590	0.394	0.512	2.250	0.990	1.266	0.236	5/8 - 11
SK263	CAT - 40TYPE III C	90°	0.590	0.394	0.512	2.250	0.990	1.266	0.236	5/8 - 11

* Suffix "C" in MODEL No. is through coolant type.
 * Improper selection of pull studs can cause serious damage and possible injury.
 Please make sure the machine accepts the pull stud you select.

TOOL CLAMP

EDP No.	MODEL No.	SHANK FLANGE TYPE
RK099	TCT - 40	CAT - 40
RH099	TBT - 40	BT - 40
RL099	TCT - 50	CAT - 50
RM099	TBT - 50	BT - 50


* Available in all tapers.

- Feature**
- Access both ends of your tool holders simultaneously
 - Minimizes tool holders handling
 - Speeds up your operations
 - Convenient



COOLANT TUBE

CT




Unit : mm

EDP Code	TAPER No.	G	L	D
CT320	32A	M10x1.0	26	6
CT400	40A	M12x1.0	29.1	8
CT500	50A	M16x1.0	32.9	10
CT630	63A	M18x1.0	36.6	12
CT100	100A	M24x1.5	43.9	16


TECHNICAL INFORMATION (HYDRAULIC CHUCK)

- High precision T.I.R : $\leq 0.00012''$ (Without Reduction Sleeve)




- Less than 0.00012" T.I.R
- ⇒ Suitable for high-speed precision machining

- Flexible use of cutting tools by using reduction sleeves




- Easy Tool Change



- Easy clamping and unclamping by use of T wrench
- ⇒ Reducing tool change time

CLAMPING SCREW



TECHNICAL INFORMATION (HYDRAULIC CHUCK)


- Strong Torque Power

Hydraulic Chuck I.D(mm)	Tool Shank O.D(mm)	Applicable RPM	Minimum Clamping Depth (mm)		Min. Torque Power (Nm)	
			Slim	Power E Hydro	Slim	Power E Hydro
6	6	40,000	27		16	
8	8	40,000	27		23	
10	10	40,000	32		45	
12	12	40,000	27	41	90	110
14	14	40,000	37		110	
16	16	40,000	42		185	
18	18	40,000	42		240	
20	20	40,000	42	48	330	520
25	25	25,000	48		400	
32	32	25,000	55	57	650	900

- Tool Holder I.D Tolerance : H6
- Operating Temperature : 20~25°C
- Maximum pressure of coolant oil : 80bar



- Test of Torque Power and Hydraulic Oil Leakage




- Test Model : BT40AD/B-HC20-90
- No oil leakage for long period ⇒ Maintaining stable torque power

TECHNICAL INFORMATION (HYDRAULIC CHUCK)

Radial Tool Length Pre-setting Type

- Easy to adjust pre-setting length of cutting tool (Saving time to pre-set cutting tool to one fifth compared with conventional Hydraulic Chuck)
- Precise adjustment of cutting tool length
- Designed to separate tool length adjustment screw from clamping screw




Adjustable range of cutting tool length : 0~0.394"

APPLICATION

Milling	High Speed Cutting	Fine Drilling
Reaming	Tapping & Thread Milling	Chamfering


TECHNICAL INFORMATION (SHRINK FIT HOLDER)

- High Precision I.D
Run-out : $\leq 0.00012''$




- Less than 0.00012" of Tool Holder accuracy at I.D

- Strong and Consistent Torque Power









- Achieving strong torque power by integration of chuck and tool

- Deep hole Machining




- Suitable for high-speed precision deep hole machining

TECHNICAL INFORMATION (SHRINK FIT HOLDER)

APPLICATION		
Rough Milling 	Finish Milling 	High Speed Cutting 
Drilling 	Reaming 	Countersinking 

Shank Type of Cutting Tool




• One Weldon flat shaft type tool is usable, but there is a possibility that the I.D of shrink fit holder may be deformed.

Material of Cutting Tool

CARBIDE TOOL	HSS TOOL
OK	NO

TECHNICAL INFORMATION (POWER MILLING CHUCK)



SPECIAL FEATURES

TOOL CLAMPING

For complete tool clamping, clamping cap should be fully turned up to the point where the bottom of clamping cap touches the flange of tool holder.


HOLDING POWER

Thicker body structure of clamping cap assures strong holding power maximum durability and smooth movement of needle bearings 300 kgf holding force.

ACCURACY

Slots on the inside of bore help prevent excessive oil and grime from building up between shank of end mill and inside of bore which increases accuracy and holding power.

STRUCTURE



DURABILITY

Special engineered steels and alloys are used in the bearing and stop seal to increase life and reduce maintenance.

TECHNICAL INFORMATION (T.I.R and TOLEARANCE)

T.I.R (Total Indicated Run-out)

HYDRAULIC CHUCK

Concentric to 0.00012" T.I.R (at 3D)

SHRINK FIT HOLDER

Concentric to 0.00012" T.I.R (at I.D)

ER COLLET CHUCK

Concentric to 0.0002" T.I.R (at I.D)

END MILL HOLDER

Concentric to 0.0002" T.I.R (at I.D)

SLITTING SAW ARBOR

Face perpendicular to taper within 0.0002" T.I.R (at I.D)

STUB ARBOR

Face perpendicular to taper within 0.0002" T.I.R (at I.D)

SHELL MILL ARBOR

Face perpendicular to taper within 0.0001" T.I.R

Out diameter to taper within 0.0002" T.I.R

MORSE & JACOBS TAPER ARBOR

Concentric to 0.0003" T.I.R

* To put tool precisely on spindle center line for getting correct T.I.R.

AT3 or better accuracy on all shank tapers

TAPER	AT3
#30	0.000078"
#40	0.00012"
#50	0.00016"

Accurate and rigid tool holder mounting to spindle

The bore diameter of all tool holders is controlled by H5 grade tolerance limit.

EDP No. INDEX

EDP No.	PAGE	EDP No.	PAGE	EDP No.	PAGE	EDP No.	PAGE
01039~01230	1219~1220	13039~13176	1245~1246	3160108A~3160508A	1391	53006~53022	1252
01289~01480	1219~1220	13289~13426	1245~1246	316030~316160	1390	532108~532100	1332
01552~01600	1125	13559~13593	1138	320108S~320304S	1378	53256~53272	1252
02047~02232	1221	14039~14176	1273	320332~320304	1375	53558~53906	1143
02297~02482	1221	14287~14426	1273	323040~323200	1390	54006~54022	1253
02558~02600	1131	15002~15052	1277	3250316A~3250304A	1391	54256~54272	1253
03039~03195	1222	15252~15302	1277	325165~325254	1390	54558~54600	1133
03289~03445	1222	16002~16052	1278	32552~32593	1136	55006~55022	1254
04039~04176	1228~1229	160108S~161332S	1378	32T50040~32T14011	1381	55256~55272	1254
04088~04231	1230	160116~161332	1375	32TC1411~32TC6548	1379	55558~55600	1135
04109~04172	1235	16252~16302	1278	32TD3527~32TD160120	1383	56002~56022	1255
04182~04226	1235	16T30025~16T62050	1381	32TP3123~32TP5642	1380	56252~56272	1255
04289~04426	1228~1229	16TC1411~16TC3224	1379	33554~33593	1137	56558~56600	941
04338~04481	1230	16TD3527~16TD7055	1382	34558~34600	1148	57006~57022	1256
04359~04422	1235	16TP3123~16TP4332	1380	36573~36600	1057	57256~57272	1256
04432~04476	1235	17047~17227	1257	37573~37598	1063	57558~57600	940
05047~05176	1231	17574~18600	1052	38602~38595	1065	58573~58902	1153
05186~05235	1231	18047~18227	1258	39573~39907	1054	59579~59600	1154
05297~05426	1231	19047~19277	1258	400108~401000	1375	60297~60484	1264
05436~05485	1231	200108S~200102S	1378	400108S~401000S	1378	612108~612516	1333
06047~06176	1232	200116~200102	1375	40573~40908	1060	61426~61488	1265
06196~06241	1232	20297~20359	1274	40T62050~40T19015	1381	62321~62490	1266
06297~06426	1232	20394~20477	1274	40TC1411~40TC8060	1379	625108~625508	1333
06446~06491	1232	20558~20600	1150	40TD3527~40TD220180	1383	632108~632100	1333
07039~07211	1239~1240	208010~208050	1376	40TP3123~40TP9067	1380	63297~63426	1267
07072~07231	1241	20T40032~20T70055	1381	41039~41227	1225	64321~64461	1268
07289~07461	1239~1240	20TC1411~20TC3828	1379	412108~412516	1331	65321~65461	1268
07322~07481	1241	20TD3527~20TD10080	1382	41289~41478	1225	66297~66461	1271
07554~07600	1127	20TP3123~20TP4332	1380	41558~41600	1139	66515~66543	1071
07558-015R-07600-125R	1145~1146	211010~211070	1376	420108~420508	1331	66901~66902	1272
07901~07097	1242	21554~21903	1053	42039~42176	1226	66903~66911	1071
08047~08211	1243	216010~216100	1376	42287~42426	1226	67321~67461	1272
08072~08239	1243	220010~220130	1376	432108~432100	1331	67515~67546	1073
08297~08461	1243	22257~22281	1275	43289~43477	1236	67904~67915	1074
08322~08489	1243	225010~225160	1377	43558~43600	1139	68297~68461	1269
08558~08600	1132	232020~232200	1377	44016~44064	1058	69321~69461	1269
09047~09195	1244	23257~23281	1275	44297~44426	1237	70297~70477	1261
09072~09241	1244	240030~240300	1377	45016~45064	1059	712108~712516	1334
09297~09445	1244	24562~24598	1062	45039~45176	1227	71321~71477	1262
09322~09491	1244	250060~250340	1377	45289~45426	1227	72297~72426	1263
101203~101208	1337	250108S~250508S	1378	46289~46426	1238	725108~725508	1334
10231~10241	1247	250116~250508	1375	47570~47593	1144	732108~732100	1334
102503~102514	1337	25558~25600	1055	48570~48593	1144	73297~73484	1270
103208~103225	1337	25T40032~25T10580	1381	49002~49022	1248	75297~75426	1259
10481~10491	1247	25TC1411~25TC5944	1379	49252~49272	1248	76297~76426	1260
110108S~110104S	1378	25TD3527~25TD160120	1383	50002~50022	1249	80524~80543	1072
110116~110104	1375	25TP3123~25TP5642	1380	50252~50272	1249	80901~80909	1072
11039~11176	1223~1224	28558~28600	1056	50558~50600	1141	812030~812008	1335
111203~111208	1338	29001~29032	1276	50TD8062~50TD320240	1383	81584~81600	1156
112503~112514	1338	29251~29282	1276	51006~51022	1250	820030~820160	1335
11289~11426	1223~1224	30554~30598	1128	512108~512516	1332	82584~82600	1156
113208~113225	1338	306010~306060	1389	51256~51272	1250	832060~832250	1335
11559~11593	1138	3060108A~3060316A	1391	51558~51600	1141	83573~83908	1149
11TC1411~11TC2519	1379	3100108A~3100308A	1391	52006~52022	1251	84565~84598	1155
11TD3527~11TD6049	1382	310020~310100	1389	520108~520508	1332	85558~85600	1151
12039~12176	1233~1234	313030~313130	1389	52256~52272	1251	86558~86600	1152
12289~12426	1233~1234	31554~31598	1130	52558~52600	1142	86573TF-030R-86600TF-187R	1147

EDP No. INDEX

EDP No.	PAGE	EDP No.	PAGE	EDP No.	PAGE	EDP No.	PAGE
87552-87903	1157	99621-99628	1095	BI331-BI334	1369	D2GP186	202
88552-88903	1158	99666-99591	865	BI331B25-BI334B25	1370	D2GP187	203
89573-89908	1064	99671-99677	1096	BK	395	D2N90	262
912030-912080	1336	99678-99682	1097	BK020SHT	1372	D3	409-411
920030-920160	1336	99686-99635	1094	BK030B-BK136B	1366	D4107	229-231
93074-93083	856	AB020-AB034	1363	BK030B25-BK134B25	1367	D4146	221
93084-93092	856	AC020-AC034	1363	BK232B-BK234B	1366	D4147	222
93093-93102	858	AD020-AD032	1364	BK232B25-BK234B25	1367	D4148	223-224
93103-93111	858	AE020-AE034	1364	BK331B-BK334B	1366	D5412	172
93112-93118	879	AH000B-AH021B	1359	BK331B25-BK334B25	1367	D5413	173
93119-93171	865	AH000B25-AH021B25	1361	BK432B25	1367	D5417	174
93134-93142	867	AH002C-AH014C	1360	BL020SHT	1372	D6	399-400
93143-93156	861	AH104B-AH121B	1359	BL031B-BL036B	1366	D8	415
93157-93170	861	AH104B25-AH121B25	1362	BL031B25-BL034B25	1367	D8182	198
93172-93193	859	AH206-AH217	1358	BL331B-BL334B	1366	D9	417
93194-93215	860	AH206B25-AH217B25	1361	BL331B25-BL334B25	1367	DGE433	137-140
932060-932250	1336	AI002-AI029	1358	BM	394	DGE466	136
93216-93237	859	AI002B25-AI029B25	1361	BN110-BN120	1373	DGE718	136
93238-93259	860	AI104-AI129	1358	BO	396	DGR493	94-97
93260-93133	867	AI104B25-AI129B25	1362	BQ010-BQ018	1371	DGR495	98-101
93263-93269	880	AK000B-AK021B	1353	BR010-BR018	1371	DGR496	94-97
93270-93276	879	AK000B25-AK021B25	1356	BS	407	DGR497	98-101
93277-93287	866	AK002C-AK017C	1355	BS110-BS115	1372	DH404	76-77
93288-93294	875	AK104B-AK121B	1354	BT	407	DH406	63-66
93295-93301	876	AK104B25-AK121B25	1357	BU	412-413	DH408	67-71
93302-93319	896	AK206-AK217	1352	BV	412-413	DH412	172
93320-93334	896	AK206B25-AK217B25	1356	BW	416	DH413	173
93335-93351	896	AL002B-AL029B	1353	BX	416	DH414	61
93352-93366	896	AL002B25-AL029B25	1356	C0	415	DH416	58-59
93395-93399	862	AL002C-AL017C	1355	C2	417	DH417	174
93400-93409	863	AL104B-AL129B	1354	C3	417	DH418	60
93410-93416	877	AL104B25-AL129B25	1357	C4	417	DH421	72-75
93417-93423	878	AQ020C-AQ034C	1365	CH037-CH040	1401	DH423	78-82
93424-93433	899	AR020C-AR034C	1365	CI038-CI041	1401	DH424	83-87
93485-93493	871	B0	404-406	CK037-CK040	1401	DH451	117-121
93495-93506	857	B1	404-406	CL038-CL041	1401	DH452	122-126
93507-93516	870	B2	404-406	CT320-CT100	1419	DH453	127-130
93517-93525	868	B3	399-400	D1115	219	DH463	114-115
93526-93533	872	B5	399-400	D1118	218	DH464	116
93534-93543	873	BB	392-393	D1119	220	DH500	166
93544-93547	864	BD	396	D1191	250	DH501	164-165
93548-93562	881	BF	395	D1211	256-257	DH510	146-148
93563-93577	882	BG	403	D1631	243	DH515	149-151
93578-93586	869	BG-GB	403	D1632	244	DH520	152-154
95063-95115	938	BH	394	D1633	245	DH711	58-59
95067-95071	938	BH020SHT	1372	D1634	243	DH712	60
95072-95078	942	BH030B-BH136B	1368	D1635	244	DH714	114-115
95079-95085	943	BH030B25-BH134B25	1370	D1636	245	DH714	116
95094-95098	939	BH232B-BH234B	1368	D1C90	268	DH722	62
95101-95106	945	BH232B25-BH234B25	1370	D1GP138	200	DHM10	155
95107-95114	944	BH331B-BH334B	1368	D1GP139	199	DHM15	155
98016-98064	1058	BH331B25-BH334B25	1370	D1GP182	198	DHM20	155
99089-99093	1257	BH432B	1368	D2	404-406	DHM25	145-157
99098	1242	BH432B25	1370	D2146	221	DHM30	158-159
99558-99565	1102	BI	392-393	D2147	222	DL517	228
99566-99571	1103	BI031-BI034	1369	D2148	223-224	DL601	240
99572-99583	1095	BI031B25-BI034B25	1370	D2GP185	201	DL602	241

EDP No. INDEX

EDP No.	PAGE	EDP No.	PAGE	EDP No.	PAGE	EDP No.	PAGE
DL603	242	EH882	1161	EMB44	1028	G9D68	792
DL604	240	EH917	950	EMB72	1032	G9D69	793
DL605	241	EH919	951	EMB73	1032	G9D75	791
DL606	242	EH921	952	EMB74	1031	G9D76	792
DLGP195	207~208	EI010~EI029	1407	EMB75	1031	G9D77	793
DLGP511	204	EI310~EI329	1407	EMB76	1026	GAE53	794
DLGP512	206	EI880	1101	EMB77	1026	GH042~GH047	1414
DLGP513	205	EI881	1101	EMB78	1025	GI042~GI047	1414
DN514	225	EIB05	1099	EMB79	1025	GK042~GK047	1414
DN515	227	EIB06	1100	EMC75	1020	GL042~GL047	1414
DN516	226	EIB07	1098	EMC76	1021	GMF15	666~667
DPGP506	209~210	EK006B~EK021B	1406	EMD60	1020	GMF16	668~670
DPP447	106~109	EK10482~EK11602	1073	EMD61	1021	GMF17	671
DX517	228	EK132	1076	EP10321~EP11323	1077	GMF18	672~674
E0	409~411	EK306B~EK321B	1406	EP10323~EP11326	1076	GMF19	675~680
E2	414	EL010B~EL029B	1406	EP12032~EP12110	1075	GMF20	681~682
E2F64	1190	EL310B~EL329B	1406	EP20322~EP21162	1206	GMF21	683~687
E4	414	EM669	902	EP922	1078	GMF22	688~690
E5	414	EM673	903	EP924	1079	GMF23	691~693
E5522	1066	EM810	883, 884, 888	ESB94	592	GMF24	694~695
E5G95	1040~1041	EM811	885~886	ESD02	593	GMF25	696
E5G96	1043	EM812	892	F4	418~419	GMF26	697
E5G97	1040~1041	EM814	907	F6	418~419	GMF27	698~699
E5G98	1043	EM816	884	F8	418~419	GMF28	700
E6	408	EM817	886	G0	421~422	GMF29	701
E8	408	EM818	889	G1	421~422	GMF52	996~997
E9	408	EM819	889	G2	421~422	GMF53	998~999
E9983	1196	EM832	906	G4	420	GMF54	996~997
E9984	1197	EM833	908	G5	420	GMF55	998~999
E9985	1198	EM834	892	G6	420	GMF56	996~997
E9986	1199	EM835	893	G7	401	GMF57	998~999
E9988	1200	EM837	909	G8	401	GMF58	996~997
E9990	1202	EM838	898	G826	630	GMF59	998~999
E9991	1203	EM839	891	G850	632	GMF60	1000~1001
E9992	1201	EM863	904	G851	633	GMF61	1002~1003
E9A86	1204	EM864	905	G854	635	GMF62	1000~1001
E9A87	1205	EM868	900	G859	634	GMF63	1002~1003
EA40321~EA10643	1061	EM876	895	G8A28	641	GMG12	1004
EA50321~EA20641	1056	EM883	910	G8A36	645~646	GMG13	1005
EA60321~EA30641	1057	EM886	911	G8A37	649	GMG14	1004
EB020~EB034	1408	EM895	887	G8A38	642	GMG15	1005
EC020~EC038	1408	EM897	894	G8A39	650	GMG16	1004
ED100~ED106	1409	EM899	897	G8A43	631	GMG17	1005
EE100~EE106	1409	EM902	901	G8A46	636~639	GMG18	1004
EE515	947	EM905	890	G8A47	648	GMG19	1005
EG522	1066	EMB12	1022	G8A50	647	GMG24	969
EG908	1070	EMB13	1023	G8A53	643	GMG26	969
EG909	1068	EMB14	1029	G8A54	640	GMG28	970
EG910	1069	EMB15	1030	G8A59	644	GMG30	970
EG930	1067	EMB20	1024	G9	401	GMG40	968
EH006B~EH021B	1407	EMB37	1022	G907	702	GMG55	996~997
EH306B~EH321B	1407	EMB38	1023	G908	703	GMG56	998~999
EH527	1159	EMB39	1029	G909	704	GUG82	1110
EH540	1160	EMB40	1030	G928	702	GUG83	1111
EH830	946	EMB41	1027	G929	703	GYG64	1174
EH831	949	EMB42	1027	G930	704	GYG65	1176
EH852	948	EMB43	1028	G9D67	791	GYG66	1177

EDP No. INDEX

EDP No.	PAGE	EDP No.	PAGE	EDP No.	PAGE	EDP No.	PAGE
GYG67	1175	LB020~LB026	1397	RK020~RK030	1411	S09Z01~S09Z08	276
GYG68	1179	LC020~LC028	1397	RK099	1419	S1	514
GYG69	1178	LE020~LE030	1398	RL020~RL032	1411	S10402~S01440	274~275
GYG70	1180	LH010~LH017	1396	RL099	1419	S11001~S11018	283~284
H0	401	LI010~LI017	1396	RM099	1419	S11101~S11122	284
H2	402	LK010~LK017	1396	RQ100~RQ102	1413	S11201~S11226	285
H4	402	LL010~LL017	1396	RR100~RR102	1413	S11Y01~S11Y11	283
H6	397	LQ020~LQ024	1399	RS100~RS106	1413	S11Z01~S11Z08	283
H7	397	LR020~LR024	1399	RTI105	1116	S13001~S13018	283~284
H8	397	M0	439	S0	513	S13101~S13122	284
I0	440~442	M1	439	S01101~S01122	272	S13201~S13226	285
I2	440~442	M2	439	S01201~S01226	272~273	S13Y01~S13Y11	283
I3	437~438	M3	439	S01301~S01328	273~274	S13Z01~S13Z08	283
I5	437~438	M4	435	S01501~S01524	275	S14001~S14018	283~284
I9	454	M5	435	S01602~S01622	275	S14101~S14122	284
IA	443	M6	435	S01804~S01815	275	S14201~S14226	285
IB	449~450	M7	435	S03101~S03122	272	S14Y01~S14Y11	283
IC	449~450	M8	437~438	S03201~S03226	272~273	S14Z01~S14Z08	283
J0	454	M9	430~431	S03301~S03328	273~274	S16001~S16018	287
J1	454	MY002~MY314	1400	S03402~S03440	274~275	S16101~S16122	288
J2	440~442	MZ002~MZ314	1400	S03501~S03524	275	S16201~S16226	289
J3	445~448	N3	434	S03601~S06328	278~279	S16Y01~S16Y11	286
J4	445~448	N4	433	S03602~S03622	275	S16Z01~S16Z08	286
J6	437~438	N7	432	S03703~S03722	275	S18001~S18018	287
J7	454	N8	432	S03804~S03815	275	S18101~S18122	288
J8	445~448	O1	430~431	S04101~S04122	272	S18201~S18226	289
J9	451	O3	434	S04201~S04226	272~273	S18Y01~S18Y11	286
JAG95	1038~1039	O5	433	S04301~S04328	273~274	S18Z01~S18Z08	286
JAG96	1042	O9	443	S04402~S04440	274~275	S2	514
JAG97	1038~1039	OH014	1394	S04501~S04524	275	S21001~S21018	287
JAG98	1042	OH314	1394	S04602~S04622	275	S21101~S21122	288
JH048	1403	OI014	1394	S04703~S04722	275	S21201~S1226	289
JH049	1403	OI314	1394	S04804~S04815	275	S21301~S21328	290
JI048	1403	OK014	1393	S06001~S06018	276~277	S21Y01~S21Y11	286
JI049	1403	OK314	1393	S06101~S06122	277	S21Z01~S21Z08	286
JI050	1403	OL014	1393	S06201~S06226	277~278	S23001~S23018	287
JK048	1402	OL314	1393	S06402~S06440	279~280	S23101~S23122	287
JK049	1402	PH014~PH021	1415	S06Y01~S06Y11	276	S23201~S23226	288
JK060SYT~JK068SYT	1404	PI014~PI021	1415	S06Z01~S06Z08	276	S23301~S23328	290
JL048	1402	PK014~PK021	1415	S07103~S01722	275	S23Y01~S23Y11	286
JL049	1402	PL014~PL021	1415	S08001~S08018	276~277	S23Z01~S23Y11	286
JL050	1402	Q0	511	S08101~S08122	277	S23Z01~S23Z08	286
JL060SYT~JL068SYT	1404	Q1	511	S08201~S08226	277~278	S26001~S26018	287
K2	451	Q6	511	S08301~S08328	278~279	S26101~S26122	288
K3	444	Q9	512	S08402~S08440	279~280	S26201~S26226	289
K5	444	QCT12001~QCT32010	1405	S08Y01~S08Y11	276	S26301~S26328	290
K6	444	QH014~QH017	1417	S08Z01~Z08Z08	276	S26Y01~S26Y11	286
K7	451	QK014~QK017	1417	S09001~S09018	276~277	S26Z01~S26Z08	286
K9	455	QL014~QL017	1417	S09101~S09122	277	S28001~S28018	287
L0	455	R0	512	S09201~S09226	277~278	S28101~S28122	288
L1	455	R1	512	S09301~S09328	278~279	S28201~S28226	289
L3	457	R7	513	S09402~S09440	279~280	S28307~S28328	290
L4	457	R8	513	S09501~S09524	280~281	S28Y01~S28Y11	286
L5	457	R9	513	S09601~S09622	281	S28Z01~S28Z08	286
L7	456	RG100~RG102	1412	S09701~S09722	282~282	SEM845	769~775
L8	456	RH099	1419	S09801~S09815	282	SEM846	710~717
L9	456	RH100~RH110	1412	S09Y01~S09Y11	276	SEM846	718~720

EDP No. INDEX

EDP No.	PAGE	EDP No.	PAGE	EDP No.	PAGE	EDP No.	PAGE
SEMD98	705~709	T6226	465	T8226	465	TK858	398
SEMD99	721~726	T6236	467	T8236	467	TK-C	384
SEME01	742~746	T6256	462~463	T8295	423	TKR03	491
SEME35	759~763	T6295	423	T8315	482	TK-S	384
SEME36	776~777	T6315	482	T8316	476~481	TL020~TL043	1384
SEME61	727~741	T6316	476~481	T8546	517	TQ100~TQ110	1387
SEME64	747~758	T6505	516	T8616	487	TQ808	436
SEME70	764~768	T6536	515	T8A85	424	TQ858	398
SEME71	778~780	T6616	487	T8A86	424	TR	472~473
SEME72	781~785	T6A85	424	T8A96	423	TR100~TR110	1387
SEME73	786~789	T6A86	424	T8B17	466	TR808	436
SEME75	790	T6A96	423	T8C16	458~461	TR858	398
SF05024~SF05124	298	T6B17	466	T8D01	425	TR-A	474~475
SF15024~SF15124	298	T6C16	458~461	T8D02	425	TR-R	474~475
SI	501	T6G36	467	T8G36	467	TS020~TS047	1388
SI	504	T6L36	515	T8-N	369	UGMF68	982~984
SK661~SK263	1418	T6-N	368	T8R01	498	UGMF69	985~986
SKC6~SKC25	1389	T7	370~371	T8R02	498	UGMF70	982~984
SM08001~SM08018	292	T7216	458~461	T9	372	UGMF71	985~986
SM08101~SM08122	292	T7217	464	T9-C	372	UGMF72	987~989
SM08201~SM08266	293	T7226	465	TA-C	374	UGMF73	990
SM08301~SM08328	293	T7236	467	TA-S	374	UGMF74	987~989
SM08401~SM0840	294	T7256	462~463	TB	381	UGMF75	990
SM08501~SM08524	294	T7295	423	TB020~TB037	1385	UGMF76	982~984
SM08601~SM08621	295	T7315	482	TB-N	381	UGMF77	985~986
SM08622~SM08722	295	T7316	476~481	TC020~TC043	1385	UGMF89	1126
SM08801~SM08815	295	T7326	483	TCA-C	375~376	UGMF90	1124
SM08Y07~SM08Y11	292	T7336	485	TCA-S	375~376	UGMF91	1140
SM08Z01~SM08Z08	292	T7405	508	TCB-C	375~376	UGMG20	991~992
SM28001~SM28018	296	T7406	502	TCB-S	375~376	UGMG21	993
SM28101~SM28122	296	T7415	506	TC-C	383	UGMG22	991~992
SM28201~SM28226	297	T7425	503	TCC-C	377	UGMG23	993
SM28301~SM28328	297	T7426	507	TCC-S	377	UGMG32	963~965
SM28Y01~SM28Y11	296	T7436	505	TCD-C	377	UGMG34	963~965
SM28Z01~SM28Z08	296	T7505	516	TCD-S	377	UGMG42	960~961
ST	501	T7536	515	TCE-C	385~386	UGMG43	962
ST	504	T7546	517	TCE-S	385~386	UGMG53	982~984
T0C01	471	T7616	487	TCF-C	385~386	UGMG54	985~986
T1-C	373	T7A15	486	TCF-S	385~386	UGMGF57	1129
T1-S	373	T7A16	476~481	TCG-C	387	UGMGF58	1132
T2	365~366	T7A85	424	TCG-S	387	UGMGF59	1134
T2496	452	T7A86	424	TCH-C	387	UGMH06	966~967
T2-C	365~366	T7A96	423	TCH-S	387	UGMH07	966~967
T2K01	453	T7B15	484	TC-S	383	UGMH08	994~995
T2-S	365~366	T7B16	476~481	TD	358	UGMH09	994~995
T3	380	T7B17	466	TD100~TD120	1386	UGMH10	987~989
T3-C	380	T7-C	370~371	TE	357	UGMH12	963~965
T3-S	380	T7C16	458~461	TE100~TE134	1386	UI052	1394
T4	378~379	T7D01	425	TF	359	UI352	1394
T4-C	378~379	T7D02	425	TG	359	UL052	1393
T4-S	378~379	T7G36	467	TH	382	UL352	1393
T5	367	T7L36	515	TH505	516	VB020~VB050	1343
T5-C	367	T7R01	498	TH-N	382	VB024J~VB050J	1344
T5-S	367	T7R02	498	THR01	498	VC020~VC052	1343
T6	368	T8	369	THR02	498	VC024J~VC052J	1344
T6216	458~461	T8216	458~461	TK020~TK037	1384	VD020~VD032	1345
T6217	464	T8217	464	TK808	436	VD024J~VD032J	1346

EDP No. INDEX

EDP No.	PAGE	EDP No.	PAGE	EDP No.	PAGE	EDP No.	PAGE
VE020~VE046	1345	WG100~WG114	1315	WR100HMC~WR110HMC	1330	YI3F	47
VE024J~VE046J	1346	WG100HCR~WG102HCR	1318	WR100PE~WR102PE	1327	YI3G	48
VG020~VG032	1341	WG100PE~WG102PE	1316	WR100SNR~WR102SNR	1328	YI3H	48
VG024J~VG032J	1342	WG100SNR	1317	WR200HMC~WR210HMC	1330	YI3I	49
VH012	1394	WH002PE	1316	XB1A	598	YI3J	49
VH020~VH046	1341	WH020~WH034	1314	XB1D	598	Z0	493~494
VH024J~VH046J	1342	WH100~WH118	1315	XB1N	603	Z1	493~494
VK012	1393	WH100HCR~WH104HCR	1318	XB2C	598	Z2	493~494
VK020~VK050	1339	WH100HMC~WH122HMC	1319	XB2N	603	Z3	493~494
VK028J~VK050J	1340	WH100PE~WH102PE	1316	XBAD	603	Z4	495~496
VK312	1393	WH100SNR~WH102SNR	1317	XGMF15	616	Z5	495~496
VL020~VL050	1339	WI003PE	1316	XGMF17	617	Z6	495~496
VL028J~VL050J	1340	WI100PE~WI102PE	1316	XGMF20	618	Z7	495~496
VQ020~VQ048	1347	WK020~WK032	1308	XGMF25	619	Z8	497
VQ024J~VQ048J	1348	WK020HMC~WK042HMC	1313	XGMF29	620	Z9	497
VR020~VR046	1347	WK020SNR~WK024SNR	1311	XR1A	601	ZA	497
VR023J~VR046J	1348	WK022PE~WK023PE	1310	XR1D	601	ZB	497
VS010~VS057	1349	WK060~WK086	1309	XR2A	601	ZBC	600, 605
VS010M~VS036M	1350	WK100HCR~WK104HCR	1312	XRAA	606	ZBS	599, 604
VS110M~VS517M	1351	WK100HMC~WK122HMC	1313	XRAD	606	ZBT	599, 604
WB020~WB034	1320	WK100SNR~WK102SNR	1311	XRBA	606	ZC	497
WB020HMC~WB042HMC	1322	WK102PE~WK103PE	1310	Y03A	44	ZD	497
WB030PE~WB031PE	1321	WL020HMC~WL030HMC	1313	Y03B	44	ZF	492
WB100HMC~WB122HMC	1322	WL020SNR~WL028SNR	1311	Y03B	45	ZMC	621
WB130PE~WB131PE	1321	WL028PE~WL030PE	1310	Y03C	45	ZMS	622
WC020~WC034	1320	WL060~WL070	1309	Y03C	46	ZMT	623
WC020HMC~WC030HMC	1322	WL100HCR~WL104HCR	1312	Y03D	46	ZRS	602, 609
WC100HMC~WC110HMC	1322	WL100HMC~WL110HMC	1313	Y03E	47	ZRT	602, 609
WD020~WD030	1323	WL100SNR~WL104SNR	1311	Y03F	47	ZS106~ZS225	1392
WD030PE	1324	WL104PE~WL106PE	1310	Y03G	48	ZZ000~ZZ013	1365
WD100~WD114	1323	WQ002PE~WQ003PE	1327	Y03H	48	ZZ021~ZZ026	1410
WD112PE~WD120PE	1324	WQ020~WQ030	1326	Y03I	49	ZZ031~ZZ036	1410
WE020~WE034	1323	WQ020HMC~WQ030HMC	1330	Y03J	49	ZZ041~ZZ054	1416
WE020HMC~WE042HMC	1325	WQ100HCR~WQ118HCR	1329	YI3A	44	ZZ051~ZZ053	1417
WE030PE	1324	WQ100HMC~WQ110HMC	1330	YI3B	44	ZZ056~ZZ058	1400
WE100~WE118	1323	WQ100PE~WQ102PE	1327	YI3B	45	ZZ061~ZZ077	1374
WE100HMC~WE122HMC	1325	WQ100SNR~WQ102SNR	1328	YI3C	45	ZZ084~ZZ089	1395
WE112PE~WE120PE	1324	WR002PE	1327	YI3C	46		
WG002PE	1316	WR020~WR032	1326	YI3D	46		
WG020~WG030	1314	WR100HCR~WR118HCR	1329	YI3E	47		